

PATENT SPECIFICATION

(11)

1 585 252

1 585 252

(21) Application No. 2007/80 (22) Filed 18 May 1978
(62) Divided Out of No. 1585251
(31) Convention Application No. 812335 (32) Filed 1 Jul. 1977 in
(33) United States of America (US)
(44) Complete Specification Published 25 Feb. 1981
(51) INT. CL³ C08L 1/10 33/00 67/00
(52) Index at Acceptance
C3M 103 110 120C 145 163 168 201 XA
C3Y B180 B212 B215 B217 B230 B240
B245 F110 F530

(19)



(72) Inventor: WALTER CARL MEYER

(54) ACRYLIC LACQUER COMPOSITION

(71) We, E.I. DU PONT DE NEMOURS AND COMPANY, a Corporation organised and existing under the laws of the State of Delaware, United States of America, located at Wilmington, State of Delaware, United States of America, do hereby declare the invention for which we pray that a patent may be granted to us and the method by which it is to be performed to be particularly described in and by the following statement:

This invention relates to coating compositions and in particular to acrylic lacquer coating compositions.

To refinish or repair acrylic lacquer and acrylic enamel finishes of automobile and truck bodies, different coating compositions have been utilized for the enamel and for the lacquer finishes. Willey U.S. 3,711,433 issued January 16, 1973 illustrates a typical composition utilized to refinish or repair acrylic lacquer finishes and Walus et al., U.S. 3,488,307 issued January 6, 1970 illustrates a typical composition utilized to refinish or repair acrylic enamel finishes. These aforementioned compositions are excellent refinish compositions. However, to reduce costs and simplify inventories for both suppliers and users which typically are auto body repair shops, a single composition is desired that could be used to refinish or repair both enamel and lacquer finishes.

The novel composition of this invention can be used to refinish or repair enamel and lacquer finishes of automobile and truck bodies and has excellent adhesion to these finishes, good appearance, good durability and weatherability. The composition can also be used as an original equipment finish that is applied by a manufacturer to automobile and truck bodies.

According to this invention we provide a coating composition comprising 5-40% by weight of a film-forming binder and 95-60% by weight of a volatile organic solvent; wherein the binder consists essentially of

(a) 30-50% by weight, based on the weight of the binder, of polymethyl methacrylate having a relative viscosity of 1.17 to 1.20 measured at 25°C on a 0.5% polymer solids solution using a dichloroethylene solvent;

(b) 20-40% by weight, based on the weight of the binder, of cellulose acetate butyrate having a viscosity of 1-3 seconds and a butyryl content of 30-55% by weight;

(c) 5-15% by weight, based on the weight of the binder, of a phthalate ester plasticizer;

(d) 10-30% by weight, based on the weight of the binder, of a polyester plasticizer of a polyol and an organic dicarboxylic acid or an anhydride of a dicarboxylic acid and having an acid number of 0.1-10; and

(e) 1-10% by weight, based on the weight of the binder, of a polymer of methyl methacrylate, an alkyl acrylate having 2-12 carbon atoms in the alkyl group and an α , β -unsaturated monocarboxylic acid and in which the polymer is reacted with an alkylene imine and having a relative viscosity of 1.17 to 1.20 measured as above; wherein the total of (a), (b), (c), (d) and (e) are 100%.

The coating composition has a binder content of film-forming constituents of 5-40% by weight. The remainder of the constituents in the composition is a solvent blend for the binder. In addition, the composition optionally contains pigment in a pigment to binder ratio of 1.0/100 to 100/100.

The acrylic polymers utilized in the coating composition may be prepared by solution polymerization in which the monomers are blended with a solvent, polymerization catalyst and heated to 75-150°C for 2-6 hours to form a polymer that has a relative viscosity of

5

10

15

20

25

30

35

40

45

1.17-1.20 measured at 0.5% polymer solids at 25°C using dichloroethylene as the solvent. Typical solvents which are used to prepare the acrylic polymers are the following: toluene, ethyl acetate, acetone, ethylene monoethylether acetate, methylethyl ketone, isopropyl alcohol, and other aliphatic, cyclo-aliphatic and aromatic hydrocarbon, esters, ethers, ketones and alcohols which are conventionally used.

5 Usually, 0.1-4% by weight, based on the weight of the monomers, of the polymerization catalyst is used to prepare the acrylic polymer. Typical catalysts are: azo-bis-isobutyronitrile, azo-bis(- α -gamma dimethyl) valeronitrile, benzoyl peroxide and t-butyl pivalate.

10 A chain transfer agent can be used to control the molecular weight of the acrylic polymers. Typical chain transfer agents are 12-mercaptop ethanol, dodecyl mercaptan, benzene thioethanol, mercapto succinic acid, butyl mercaptan and mercapto propionic acid.

15 The coating composition contains 30-50% by weight, based on the weight of the binder, of polymethyl methacrylate having the aforementioned relative viscosity.

15 The coating composition contains 1-10% by weight, based on the weight of the binder, of a polymer of methyl methacrylate, an alkyl acrylate having 2-12 carbon atoms in the alkyl group and an α , β -unsaturated monocarboxylic acid in which the polymer is reacted with an alkylene imine. Any of the aforementioned alkyl acrylates can be used to prepare the polymer including nonyl acrylate, decyl acrylate and lauryl acrylate. Preferably, ethyl acrylate, butyl acrylate, butyl acrylate or 2 ethyl acrylate is used. Typically useful acids used to prepare this polymer are acrylic acid and methacrylic acid. Alkylene imines such as propylene imine or ethylene imine or hydroxy ethyl ethylene imine are reacted with the carboxyl groups of the acid of the polymer. Generally, 90-100% of the carboxyl groups are reacted with an alkylene imine. 2-5% by weight, based on the weight of the binder, of one particularly useful polymer can be used in the composition in which the polymer is of 70-90% by weight of methyl methacrylate, 9-20% by weight of ethyl acrylate and 1-10% by weight of methacrylic acid which is reacted with propylene imine.

20 20-40% by weight, based on the weight of the binder, of cellulose acetate butyrate (CAB) is used in the coating composition. The CAB has a butyryl content of 30-55% by weight and a viscosity of 1-3 seconds measured according to ASTMD 1343-56.

20 The composition contains 10-30% by weight, based on the weight of the binder, of a polyester plasticizer of a polyol and an organic dicarboxylic acid or an anhydride thereof having an acid number of 0.1-10 and, optionally, a saturated fatty oil. The polyester may be prepared by conventional polymerization techniques in which the constituents and a conventional esterification catalyst such as lead tallate, sodium naphthenate, barium oxide, barium hydroxide, and lithium hydroxide are reacted at 80-200°C for 0.5-6 hours. A typical saturated fatty oil that can be used to prepare the polyester is coconut oil. Polyesters of a polyol and an organic dicarboxylic acid or anhydride thereof without a saturated fatty oil can also be used.

25 Typical polyols that can be used to prepare the polyester are ethylene glycol, propylene glycol, dipropylene glycol, butane diol, diethylene glycol and neopentyl glycol. Other polyols that can be used are glycerol, trimethylol propane, trimethylol ethane, pentaerythritol, and dipentaery-thritol and sorbitol.

25 Typical organic dicarboxylic acids or anhydrides that can be used to prepare the polyester are adipic acid, azelaic acid, chlorendic acid, chlorendic anhydride, phthalic acid, phthalic anhydride, terephthalic acid, isophthalic acid, succinic acid, succinic anhydride trimellitic acid and trimellitic anhydride.

30 One particularly useful polyester used in the coating composition is of coconut oil, ethylene glycol and phthalic anhydride. 20-25% by weight, based on the weight of the binder, of the alkyd resin is used in the composition.

30 Preferred phthalate ester plasticizers are butyl cyclohexyl phthalate and butyl benzyl phthalate.

35 As mentioned before, the composition can contain pigments. These pigments can be introduced into the composition by first forming a mill base with any of the above polymers utilized in the coating composition or with other compatible polymers by conventional techniques, such as sand-grinding, ball milling, attritor grinding, or two roll milling to disperse the pigments. The mill base is blended with the film-forming constituents as shown in the following Examples.

40 Any of the conventional pigments used in the coating compositions can be utilized in this composition. Examples of typical pigments that can be used are as follows: metallic oxides, such as titanium dioxide, zinc oxide and iron oxide, metal hydroxides, metal flakes such as aluminum flake, sulfide, sulfates, carbonates, carbon black, silica, talc, china clay, phthalocyanine blues and greens, organo reds, organo maroons and other organic dyes.

45 The coating composition of this invention can be applied over a variety of substrates,

45 55

50 55

55 60

60 65

65 65

such as metal, primed metal, metal coated with enamels or lacquers, wood, glass and plastics, by any of the conventional application methods, such as spraying, electrostatic spraying, dipping, brushing, and flow-coating. The viscosity of the composition can be adjusted for any of these methods by adding solvents if necessary.

5 The applied coatings can be dried at ambient temperatures or baked at relatively low temperatures of 35-100°C. for 15 minutes-2 hours. The resulting finish is 0.1-5 mils thick but for most uses, a 1-3 mil thick finish is used. The resulting finish has good appearance and can be rubbed, or polished with conventional techniques to improve the smoothness or gloss or both. The finish has good adhesion to substrates of all types particularly industrial lacquers or enamel finished substrates. The finish is hard and resistant to weathering, staining, scratches and the like. These characteristics make the composition particularly useful for finishing or refinish automobile and truck bodies. The coating composition can also be used on aircraft, farm equipment such as tractors, appliances, vending machines, bridges, water tanks, gas tanks and the like.

10

15 The following Example illustrates the invention. All quantities are shown on a weight basis unless otherwise indicated.

Example

20 An iminated acrylic polymer solution is prepared by charging the following constituents into a reaction vessel equipped with a thermometer, a stirrer, a reflux condenser and a heating mantel;

		Parts by Weight	
25	<i>Portion 1</i>		25
	Toluene	54.79	
	Isopropanol	110.83	
	Ethyl Acetate	148.05	
30	Methyl methacrylate monomer	254.08	
	Ethyl acrylate monomer	45.80	30
	Methacrylic acid monomer	13.80	
	Azobisisobutyronitrile	0.73	
35	<i>Portion 2</i>		35
	Azobisisobutyronitrile	0.83	
	Ethyl acetate	6.70	
	Toluene	4.80	
40	<i>Portion 3</i>		40
	Azobisisobutyronitrile	1.26	
	Ethyl acetate	7.32	
	Toluene	13.60	
45	<i>Portion 4</i>		45
	Isopropanol	19.86	
50	Toluene	104.55	
	<i>Portion 5</i>		50
	Propylene imine	9.20	
55	Isopropanol	13.80	
	Total	810.00	55

Portion 1 is premixed and then is charged into the reaction vessel with constant mixing and heated and then the heat is turned off. The temperature of the resulting reaction mixture rises to a reflux temperature of about 82-84°C and is maintained at this temperature by slightly refluxing the mixture for about 60 minutes. Portion 2 is premixed and added to the reaction vessel and the resulting reaction mixture is held at about 81-83°C by slightly refluxing the mixture for about 90 minutes. Portion 3 is premixed and added to the reaction vessel and the resulting reaction mixture is held at about 81-83°C at a slight reflux for about 45 minutes. Portion 4 is added with mixing and then Portion 5 is premixed and added and the reaction mixture is thoroughly mixed for about 15 minutes and held at about 76-80°C for

60
65

about 2 hours or until the acid number of the reaction mixture reaches about 0.1-3.5 and then cooled to room temperature.

The resulting polymer solution has a solids content of about 39% by weight, a Gardner Holdt Viscosity measured at 25°C of about W-Y and the polymer has the following composition: methyl methacrylate/ethyl acrylate/methacrylic acid/propyleneimine in a weight ratio of 81.0/14.6/4.4/2.9 in which all of the propyleneimine has reacted with the methacrylic acid. The polymer has a relative viscosity of about 1.2 measured on a 0.5% polymer solids solution using a dichloroethylene solvent at 25°C.

A methyl methacrylate polymer solution is prepared by charging the following constituents into a reaction vessel equipped as above:

		Parts by Weight	
	<i>Portion 1</i>		
15	Methyl methacrylate monomer	322.28	15
	Acetone	112.71	
	Toluene	48.33	
	Benzoyl peroxide	2.18	
20	<i>Portion 2</i>		20
	Acetone	32.29	
	Toluene	290.29	
		808.08	

25 Portion 1 is premixed and charged into a reaction vessel and heated to about 100°C and held at this temperature for about 1-1/2 hours and then Portion 2 is added and the resulting polymer solution is cooled to room temperature.

30 The polymer solution has a polymer solids content of about 40% by weight and the polymer has a relative viscosity of about 1.19 measured as above.

A coconut oil/ethylene glycol/phthalic anhydride ester resin solution is prepared by charging the following constituents in a reaction vessel equipped as above:

		Parts by weight	
35	<i>Portion 1</i>		35
	Coconut oil	275.70	
	Ethylene glycol	185.00	
40	Dibutyltin oxide	0.26	40
	Lead tallate drier	0.23	
	<i>Portion 2</i>		
45	Phthalic Anhydride	394.70	45
	<i>Portion 3</i>		
	Toluene	63.74	
50	<i>Portion 4</i>		50
	Toluene	75.36	
	Total	994.99	

55 Portion 1 is charged into the reaction vessel and heated to 188°C and held at this temperature for about 1 hour. Portion 2 is then added and then the temperature of the resulting reaction mixture is brought to 150°C. Portion 3 is added and the reaction mixture is held at its reflux temperature of about 190°C for about 30 minutes and then the temperature of the reaction mixture is increased to about 200°C and held at this temperature for 30 minutes. The reaction mixture is heated to 232°C and held for 2 hours at this temperature and then heated to 245°C and held until the acid number of the reaction mixture is below about 10 which usually takes about 1 hour. The reaction mixture is heated to 250°C and held at this temperature for about 2 hours. During the above reaction, water is removed from the reaction mixture. Portion 4 is added and the resulting alkyd resin solution is cooled to room temperature.

60

65

The ester resin solution has a solids content of about 85% by weight and a Gardner Holdt Viscosity measured at 25°C of about Y-Z₁ and the alkyd resin has an acid number of about 7-10.

5 The following constituents are blended together to form a clear lacquer that will dry at room temperatures: 5

			Parts by Weight	
10	Isopropanol	386.0		10
	Acetone	464.0		
	Toluene	156.0		
	Xylene	276.0		
15	Cellulose Acetate Butyrate (having a butyryl content of 38% and a viscosity of 2 seconds measured according to ASTMD-1343-56 at 25°C in a solvent blend of 60 parts acetone 25 parts toluene)	220.3		15
20	Ethylene glycol monoethyl ether acetate	232.0		20
	DOBP U.V. Screening agent (4-dodecyloxy-2-hydroxy-benzophenone)	25.7		
25	Silicone solution (1% solids silicone SF69 in xylene)	7.8		25
	Butyl cyclohexyl phthalate	73.3		
30	Ester resin solution (prepared as above)	197.0		30
	Iminated Acrylic Polymer solution (prepared as above)	94.4		
	Methyl methacrylate polymer solution (prepared as above)	850.0		
35	Total	2982.5		35

40 The above lacquer is sprayed onto primed steel panels coated with an acrylic lacquer and primed steel panels coated with an acrylic enamel and in each case dried at 43°C for 24 hours. The adhesion of the lacquer on each of the substrates is checked as follows.

40 The adhesion of the topcoat to the substrate is determined on a set of these panels by scribing a rectangular grid through the topcoat to the metal with a knife and placing scotch tape over the grid and then removing the tape. A subjective rating of 10 means that none of the topcoat is removed while a rating of 0 indicates that all of the topcoat is removed. The 45 panels are tested for initial adhesion, wet adhesion after 96 hours exposure to 100% relative humidity at 38°C and recovered adhesion, i.e. the panel subjected to the wet adhesion test is allowed to dry at room temperature for 24 hours and then tested as above.

In case the lacquer has an acceptable level of adhesion to the panel, i.e. an adhesion level 7 and above when dry.

50 **WHAT WE CLAIM IS:**

50 1. A coating composition comprising 5-40% by weight of a film-forming binder and 60-95% by weight of volatile organic solvents; wherein the binder consists essentially of about

55 (a) 30%-50% by weight, based on the weight of the binder, of polymethyl methacrylate having a relative viscosity of 1.17-1.20 measured at 25°C on a 0.5% polymer solids solution using dichloroethylene solvent;

(b) 20-40% by weight, based on the weight of the binder, of cellulose acetate butyrate having a viscosity of 1-3 seconds and a butyryl content of 30-55% by weight;

(c) 5-15% by weight, based on the weight of the binder, of a phthalate ester plasticizer;

60 (d) 10-30% by weight, based on the weight of the binder, of a polyester plasticizer of a polyol and an organic carboxylic acid or an anhydride of an organic dicarboxylic acid and having an acid number of 0.1-10; and

65 (e) 1-10% by weight, based on the weight of the binder, of a polymer of methyl methacrylate, an alkyl acrylate having 2-12 carbon atoms in the alkyl group and an α, β-unsaturated mono-carboxylic acid and in which the polymer is reacted with an alkylene

imine and having a relative viscosity of 1.17 to 1.20 measured as above; wherein the total of (a), (b), (c), (d), and (e) are 100%.

2. The coating composition of Claim 1 containing pigment in a pigment to binder weight ratio of 1/100 to 100/100.

5 3. The coating composition of Claim 1 or 2 in which the phthalate plasticizer is butyl cyclohexyl phthalate or butyl benzyl phthalate. 5

4. The coating composition of Claim 1, 2 or 3 in which the polyester plasticizer contains saturated fatty oil.

10 5. The coating composition of Claim 4 in which the polyester plasticizer consists essentially of coconut oil, ethylene glycol and phthalic anhydride. 10

6. The coating composition of any one of Claims 1 to 5 in which the methyl methacrylate, alkyl acrylate, α , β -unsaturated monocarboxylic polymer reacted with an alkylene imine consists essentially of methyl methacrylate, ethyl acrylate, methacrylic acid and the alkylene imine is propylene imine.

15 7. The coating composition of Claim 6 in which the polymer consists essentially of 70-90% by weight of methyl methacrylate, 9-20% by weight of ethyl acrylate and 1-10% by weight of methacrylic acid which is reacted with propylene imine. 15

8. The coating composition of Claim 1 in which the binder consists essentially of (a) polymethyl methacrylate; 20

(b) cellulose acetate butyrate having a viscosity of 1-3 seconds and a butyryl content of 35-40% by weight; (c) a phthalate plasticizer consisting essentially of butyl cyclohexyl phthalate; (d) a polyester plasticizer consisting essentially of coconut oil, ethylene glycol and phthalic anhydride; and 25

(e) a polymer consisting essentially of 70-90% by weight methyl methacrylate, 9-20% by weight of ethyl acrylate and 1-10% by weight of methacrylic acid which is reacted with propylene imine. 25

9. A coating composition substantially as hereinbefore described in the Example.

10. An article coated with dried coating composition according to any one of Claims 1 to 9. 30 30

For the Applicants,
CARPMAELS & RANSFORD,
Chartered Patent Agents,
43 Bloomsbury Square,
London, WC1A 2RA.

35 35