



(86) **Date de dépôt PCT/PCT Filing Date:** 2012/11/14
(87) **Date publication PCT/PCT Publication Date:** 2013/05/23
(45) **Date de délivrance/Issue Date:** 2020/04/14
(85) **Entrée phase nationale/National Entry:** 2014/06/12
(86) **N° demande PCT/PCT Application No.:** JP 2012/079482
(87) **N° publication PCT/PCT Publication No.:** 2013/073561
(30) **Priorité/Priority:** 2011/11/15 (JP2011-249968)

(51) **Cl.Int./Int.Cl. H01M 4/58** (2010.01),
H01M 10/052 (2010.01), **H01M 10/0566** (2010.01),
H01M 4/136 (2010.01), **H01M 4/36** (2006.01),
C01B 25/45 (2006.01)
(72) **Inventeurs/Inventors:**
KAWASAKI, TAKASHI, JP;
YOSHINO, NOBUYUKI, JP;
MURATA, HIROSHI, JP;
SAWAI, TAKEHIKO, JP;
SAITO, SHINJI, JP;
URAO, KAZUNORI, JP
(73) **Propriétaires/Owners:**
DENKA COMPANY LIMITED, JP;

(54) **Titre : PARTICULES COMPOSITES, LEUR PROCEDE DE FABRICATION, MATIERE D'ELECTRODE POUR BATTERIE SECONDAIRE, ET BATTERIE SECONDAIRE**

(54) **Title: COMPOSITE PARTICLES, MANUFACTURING METHOD THEREOF, ELECTRODE MATERIAL FOR SECONDARY BATTERY, AND SECONDARY BATTERY**

(57) **Abrégé/Abstract:**

Provided is positive electrode material for a highly safe lithium-ion secondary battery that can charge and discharge a large current while having long service life. Disclosed are composite particles comprising: at least one carbon material selected from the group consisting of (i) fibrous carbon material, (ii) chain-like carbon material, and (iii) carbon material produced by linking together fibrous carbon material and chain-like carbon material; and lithium-containing phosphate, wherein at least one fine pore originating from the at least one carbon material opens to outside the composite particle. Preferably, the composite particles are coated with carbon. The fibrous carbon material is preferably a carbon nanotube with an average fiber size of 5 to 200 nm. The chain-like carbon material is preferably carbon black produced by linking, like a chain, primary particles with an average particle size of 10 to 100 nm.

(73) **Propriétaires(suite)/Owners(continued):**SEI CORPORATION, JP

(74) **Agent:** BERESKIN & PARR LLP/S.E.N.C.R.L.,S.R.L.

Abstract

Provided is positive electrode material for a highly safe lithium-ion secondary battery that can charge and discharge a large current while having long service life. Disclosed are composite particles comprising: at least one carbon material selected from the group consisting of (i) fibrous carbon material, (ii) chain-like carbon material, and (iii) carbon material produced by linking together fibrous carbon material and chain-like carbon material; and lithium-containing phosphate, wherein at least one fine pore originating from the at least one carbon material opens to outside the composite particle. Preferably, the composite particles are coated with carbon. The fibrous carbon material is preferably a carbon nanotube with an average fiber size of 5 to 200 nm. The chain-like carbon material is preferably carbon black produced by linking, like a chain, primary particles with an average particle size of 10 to 100 nm.

DESCRIPTION

COMPOSITE PARTICLES, MANUFACTURING METHOD THEREOF, ELECTRODE MATERIAL FOR SECONDARY BATTERY, AND SECONDARY BATTERY

Technical Field

The present invention relates to electrode materials for a lithium-ion secondary battery.

Background Art

In a lithium-ion secondary battery, a negative electrode may be formed using material capable of storing and releasing a lithium ion. The lithium-ion secondary battery may have less precipitation of dendrites than a lithium secondary battery having a negative electrode made of metal lithium. Because of this, the lithium-ion secondary battery has advantages that a high-capacity battery with an increased energy density can be provided while a short circuit in the battery is prevented to increase its safety.

Recently, a much higher capacity of this lithium-ion secondary battery has been sought. At the same time, it is required for a cell for high-power usage that cell resistance is reduced to increase performance of charging and discharging a large current. In this respect, the following considerations have been conventionally given: to increase a capacity of carbon-based negative electrode material and/or positive electrode material made of lithium metal oxide, a cell reactant; to miniaturize reactant particles; to increase an electrode surface area by increasing a specific surface area of the particles and/or by designing a cell; and to reduce liquid diffusion resistance by making a separator thinner, etc. However, in one hand, the particles are made smaller and the specific surface area is increased, which causes an increase in an amount of a binder. On the other hand, this increase is inconsistent with making the capacity higher. Further, positive and negative electrode materials are peeled and detached from a metal foil, which is a collector. This results in a short circuit inside a cell. Consequently, cell voltage is lowered and uncontrolled heating occurs, etc., so that the lithium-ion secondary battery sometimes becomes unsafe. Then, consideration has been made to modify a type of the binder so as to increase adhesion to the foil (see Patent Literature 1).

However, the modification of the type of the binder may increase the cell capacity, but insufficiently improves characteristics of charging and discharging a large current by decreasing its resistance. When the lithium-ion secondary batteries are compared with secondary batteries such as a nickel-cadmium battery and a nickel-hydrogen battery, it is difficult to develop application to an electric tool

and a hybrid car. This is because in the application, a large current should be charged and discharged, which provides a big performance barrier for the lithium-ion secondary batteries.

In view of charging and discharging a large current in the lithium-ion secondary battery, a carbon conductive material has been devised so as to decrease its electrode resistance (see Patent Literatures 2 to 4). Unfortunately, when a large current is used to repeat a cycle of charge and discharge, positive and negative electrode materials are subject to expansion and contraction, which damages a conductive path of particles between positive and negative electrodes. As a result, a large current cannot be made to flow after a short period of time.

Meanwhile, metal oxide such as LiCoO_2 , LiNiO_2 , Li_2MnO_4 , or $\text{LiCo}_x\text{Ni}_y\text{Mn}_z\text{O}_2$ ($x + y + z = 1$) has been conventionally used as a positive electrode active substance for the lithium-ion secondary battery. Recently, much attention has been paid to lithium-containing phosphate such as LiFePO_4 , LiMnPO_4 , $\text{LiMn}_x\text{Fe}_{(1-x)}\text{PO}_4$, LiCoPO_4 , or $\text{Li}_3\text{V}_2(\text{PO}_4)_3$.

The first feature of the lithium-containing phosphate is that its anion is a polyanion (a phosphate ion: PO_4^{3-}), which is more stable than an oxide ion (O^{2-}). Differing from metal oxide, the lithium-containing phosphate generates no oxygen (O_2), which is a combustion-supporting substance, after decomposition. Accordingly, use of the lithium-containing phosphate as a positive electrode active substance can increase safety of the lithium-ion secondary battery.

The second feature of the lithium-containing phosphate is that resistance of the material itself is large. Consequently, it is a big issue to make the battery highly conductive (see Patent Literatures 5 and 6). In order to provide possible solutions, various considerations have been made: to coat the surface of particles of the lithium-containing phosphate with carbon, a conductive material to prepare positive electrode material; or to make a composite of the lithium-containing phosphate and carbon, etc., (see Patent Literatures 7 to 13). These considerations have improved performance of the positive electrode material using phosphate.

Citation List

Patent Literature

- Patent Literature 1: JP05-226004A
- Patent Literature 2: JP2005-19399A
- Patent Literature 3: JP2001-126733A
- Patent Literature 4: JP2003-168429A
- Patent Literature 5: JP2000-509193A
- Patent Literature 6: JP09-134724A
- Patent Literature 7: JP2002-75364A
- Patent Literature 8: JP2002-110162A

Patent Literature 9: JP2004-63386A
Patent Literature 10: JP2005-123107A
Patent Literature 11: JP2006-302671A
Patent Literature 12: JP2007-80652A
Patent Literature 13: JP2010-108889A
Patent Literature 14: JP2009-503182A

SUMMARY OF INVENTION

Technical Problem

When a current is discharged or charged, however, a positive electrode active substance has to not only transfer electrons but also store and release a lithium ion that is a carrier for electrons and charges. Accordingly, it is necessary to not only transfer electrons but also make easier diffusion during storage and release of the lithium ion when a large current is used for charge and discharge. In a common lithium-ion secondary battery, lithium ions diffuse in an electrolytic solution to be stored and released in active substances of positive and negative electrodes. Carbon coating of the active substance of the positive electrode increases electron conductivity, but rather restricts the storage and release of the lithium ions because the carbon coating is interposed between the electrolytic solution and the active substance of the positive electrode. Consequently, although the carbon coating somewhat improves performance of the positive electrode material, the improvement can be said to be insufficient when a large current is used for charge and discharge. Meanwhile, lithium-containing phosphate and carbon are used to make a composite, which does not inhibit storage and release of lithium ions. This differs from the case of the carbon coating. However, carbon itself has no function to increase conductivity of lithium ions. Thus, formation of the composite containing lithium-containing phosphate and carbon fails to make diffusion of lithium ions essentially easier. Hence, the above does not radically resolve a decrease in performance when a large current is used for charge and discharge.

The present invention has been made so as to address the above problems of the positive electrode material for a lithium-ion secondary battery. It is an object of the present invention to provide positive electrode material for a lithium-ion secondary battery in which a large current is used for charge and discharge in a long period during service life of the battery.

Solution to Problem

Specifically, in order to solve the above problems, the present invention has the following aspect (1):

(1) Composite particles comprising: at least one carbon material selected from the group consisting of (i) fibrous carbon material, (ii) chain-like carbon material, and (iii) carbon material produced by linking together fibrous carbon material and chain-like carbon material; and lithium-containing phosphate, wherein at least one fine pore originating from the at least one carbon material opens to outside the composite particle.

In addition, the present invention preferably provides the following aspects:

(2) The composite particles according to the aspect (1), wherein the composite particles are coated with carbon;

(3) The composite particles according to the aspect (1) or (2), wherein the fibrous carbon material is a carbon nanotube with an average fiber size of 5 to 200 nm;

(4) The composite particles according to any one of the aspects (1) to (3), wherein the chain-like carbon material is carbon black produced by linking, like a chain, primary particles with an average particle size of 10 to 100 nm;

(5) The composite particles according to any one of the aspects (1) to (4), wherein the lithium-containing phosphate is LiFePO_4 , LiMnPO_4 , $\text{LiMn}_x\text{Fe}_{(1-x)}\text{PO}_4$, LiCoPO_4 , or $\text{Li}_3\text{V}_2(\text{PO}_4)_3$;

(6) The composite particles according to any one of the aspects (1) to (5), wherein primary particles have an average size of 0.02 to 20 μm ;

(7) A process for producing the composite particles according to any one of the aspects (1) to (6), the process comprising: a first step of subjecting to surface treatment at least one carbon material selected from the group consisting of (i) fibrous carbon material, (ii) chain-like carbon material, and (iii) carbon material produced by linking together fibrous carbon material and chain-like carbon material; a second step of mixing the at least one surface-treated carbon material and source material for lithium-containing phosphate; a third step of heating the mixture to form composite particles comprising: the at least one surface-treated carbon material; and a lithium-containing phosphate precursor and/or the lithium-containing phosphate; and a fourth step of heating the composite particles to create at least one fine pore opening to outside the composite particle, wherein the at least one fine pore originates from the at least one carbon material;

(8) The process for producing composite particles according to the aspect (7), further comprising the step of adding a heat-degradable carbon source compound in one or more steps from the second to fourth steps;

(9) The process for producing composite particles according to the aspect (7) or (8), wherein the third and fourth steps are continuously performed.

(10) The process for producing composite particles according to any one of the aspects (7) to (9), wherein oxidation treatment is used for the surface treatment of the at least one carbon material;

(11) The process for producing composite particles according to any one of the aspects (7) to (9), wherein a method using a surfactant is used for the surface treatment of the at least one carbon material;

(12) The process for producing composite particles according to any one of the aspects (7) to (9), wherein a method using a polymer dispersant is used for the surface treatment of the at least one carbon material selected;

(13) The process for producing composite particles according to any one of the aspects (7) to (12), wherein the method for mixing the source material for the lithium-containing phosphate and the at least one surface-treated carbon material is a method for dispersing and mixing the at least one surface-treated carbon material into a solution having dissolved into a solvent a lithium ion (Li^+), a phosphate ion (PO_4^{3-}), and a metal ion other than from lithium;

(14) The process for producing composite particles according to the aspect (13), wherein the solvent is water, alcohol, or a mixed solvent of water and alcohol;

(15) The process for producing composite particles according to the aspect (13) or (14), wherein a method using a pressured and heated solvent is used for the method comprising: dispersing the at least one surface-treated carbon material into the solution; mixing the solution; and then heating the solution to form the composite particles comprising: the at least one surface-treated carbon material; and the lithium-containing phosphate precursor and/or the lithium-containing phosphate;

(16) The process for producing composite particles according to any one of the aspects (7) or (15), wherein the method for heating the composite particles comprising the at least one carbon material and the lithium-containing phosphate to create the at least one fine pore is a method for heating the composite particles comprising the at least one surface-treated carbon material and the lithium-containing phosphate precursor and/or the lithium-containing phosphate under an inert atmosphere or reducing atmosphere *in vacuo* to volatilize an oxygen-containing functional group on a surface of the at least one surface-treated carbon material or to decompose a surfactant or a polymer dispersant on the surface;

(17) Electrode material for a lithium-ion secondary battery, comprising 60 to 95% by mass of the composite particles according to any one of the aspects (1) to (6) and the remainder consisting of a conduction aid and a binder; and

(18) A lithium-ion secondary battery comprising: a positive electrode produced using the electrode material according to the aspect (17); a negative electrode; an electrolytic solution; and a separator that electrically insulates the positive electrode from the negative electrode and helps retain the electrolytic solution.

Advantageous Effects of Invention

Composite particles according to the present invention may be used for electrode material for a lithium-ion secondary battery. The particles of a positive electrode active substance contain at least one carbon material selected from the group consisting of (i) fibrous carbon material, (ii) chain-like carbon material, and (iii) carbon material produced by linking together fibrous carbon material and chain-like carbon material. As the first effect, this carbon material can enhance an electron conduction network, so that electrons can be smoothly transferred between lithium-containing phosphate particles and a conduction aid. Further, fine pores that originate from the at least one carbon material and open to outside the composite particle are filled with an electrolytic solution when a lithium-ion secondary battery is manufactured. As the second effect, these fine pores help create a diffusion path for a lithium ion inside the particles of the active substance, so that diffusion resistance can be decreased during storage and release of the lithium ion. These two effects help decrease both ion diffusion resistance and electron conduction resistance inside a positive electrode. Accordingly, rate characteristics of the battery improve. This enables a large current to be charged and discharged in a long period during service life of the battery.

Description of Embodiments

The following details embodiments of the present invention.

In an embodiment of the present invention, carbon material is (i) fibrous carbon material, (ii) chain-like carbon material, (iii) carbon material produced by linking together fibrous carbon material and chain-like carbon material, or a mixture thereof.

Examples of the fibrous carbon material include a carbon nanotube, carbon nanofiber, vapor-grown carbon fiber, polyacrylonitrile (PAN)-based carbon fiber, and pitch-based carbon fiber. Among them, a carbon nanotube with an average fiber size of 5 to 200 nm is preferable.

Examples of the chain-like carbon material include carbon black such as acetylene black (e.g., DENKA BLACK manufactured by DENKI KAGAKU KOGYO KABUSHIKI KAISHA) or furnace black (e.g., SUPER-P manufactured by TIMCAL GRAPHITE & CARBON, Inc.; Ketjenblack manufactured by Ketjen Black International Company). Among them, carbon black whose primary particles have an average size of 10 to 100 nm is preferable. Among the carbon black, particularly preferred is acetylene black.

Examples of a method for linking fibrous carbon material and chain-like carbon material include:, but are not particularly limited to, a method for injecting fibrous carbon material during thermolysis of hydrocarbon to link the material and carbon black generated; a method for supplying and linking hydrocarbon

containing a fibrous carbon-forming catalyst during thermolysis of acetylene gas and/or while acetylene gas is subjected to thermolysis (see Patent Literature 14); a method for dispersing fibrous carbon and carbon black into a liquid carbonization source such as hydrocarbon and alcohol to carbonize the liquid carbonization source by heating, etc., while keeping it in a liquid or gas phase; a method including: mixing beforehand a fibrous carbon-forming catalyst and carbon black; causing them to contact source gas for fibrous carbon; and linking the carbon black and the fibrous carbon while generating the fibrous carbon; and a method for linking fibrous carbon and carbon black by a mechanochemical process using a solid medium. Examples of the linking using a mechanochemical process include linking using a media mixing mill such as a bead mill, a vibrating mill, or a ball mill. For example, an SEM image can be examined to calculate an average fiber size of fibrous carbon material and an average particle size of primary particles of chain-like carbon material, which sizes may be a number average fiber size and a number average particle size, respectively. The average fiber size may be, for example, 5, 10, 15, 20, 30, 50, 100, 150, or 200 nm. The size may be between any two of the above values. The average particle size of primary particles of chain-like carbon may be, for example, 10, 20, 30, 40, 50, 60, 70, 80, 90, or 100 nm. The size may be between any two of the above values.

In an embodiment of the present invention, lithium-containing phosphate may be phosphate capable of storing and releasing a lithium ion. Specific examples of the lithium-containing phosphate include LiFePO_4 , LiMnPO_4 , $\text{LiMn}_x\text{Fe}_{(1-x)}\text{PO}_4$, LiCoPO_4 , and $\text{Li}_3\text{V}_2(\text{PO}_4)_3$. Particularly preferred are LiFePO_4 and $\text{LiMn}_x\text{Fe}_{(1-x)}\text{PO}_4$.

In an embodiment of the present invention, the composite particles have an average primary particle size of preferably 0.02 to 20 μm and more preferably 0.05 to 5 μm . When the average particle size is smaller than the above, it is difficult to include carbon material, lithium-containing phosphate, and fine pores all together inside the particles because the particles are too small. When the average particle size is larger than that, it is difficult to uniformly disperse carbon material, lithium-containing phosphate, and fine pores all together inside the particles, so that their distribution is likely to be deviated. This results in a region having an elongated conductive path for electrons and lithium ions inside the particles, thereby increasing resistance. The average particle size may be, for example, 0.02, 0.05, 0.1, 0.5, 1, 2, 3, 4, 5, 10, 15, or 20 μm . The size may be between any two of the above values. This average particle size can be calculated by examining, for example, an SEM image and may be a number average particle size.

In an embodiment of the present invention, composite particles can be produced as follows: the above carbon material is subjected to surface treatment; next, source material for lithium-containing phosphate is mixed therewith; the

mixture is heated to form composite particles comprising the surface-treated carbon material and a lithium-containing phosphate precursor and/or the lithium-containing phosphate; and the composite particles are further heated to produce composite particles of interest.

As the first step, the carbon material is subjected to surface treatment. This process is, for example, oxidation treatment or treatment using a surfactant or a polymer dispersant.

In the oxidation treatment, an oxidizer is used on a surface of the above carbon material to introduce a hydroxyl group (-OH), a carbonyl group (>C=O), a carboxyl group (-COOH), or a functional group containing an ether bond or an ester bond. Specific examples of the oxidation treatment include: (i) heating the carbon material under an oxygen-containing atmosphere (gas phase oxidation); (ii) retaining the carbon material under an ozone-containing atmosphere or in an ozone-containing solution (ozone oxidation); (iii) heating the carbon material in a solution containing an oxidizing compound (e.g., sulfuric acid, nitric acid, perchloric acid, hydrogen peroxide, potassium permanganate, osmic acid); and (iv) subjecting the carbon material to treatment using a wet jet mill in water, an organic solvent containing a functional group such as a hydroxy group (-OH) or a carbonyl group (>C=O) (e.g., ethanol, isopropyl alcohol, methyl ethyl ketone, methyl isobutyl ketone), or a mixed solution thereof. For example, a Star Burst manufactured by SUGINO MACHINE LIMITED, a Nano Jet Pal manufactured by JOKOH, Inc., a Nano Maker manufactured by Advanced Nano Technology Co., Ltd., or a microfluidizer manufactured by Powrex Corp. is suitable for the wet jet mill processor.

The treatment using a surfactant refers to a method for mixing the above carbon material and a surfactant in a polar solvent such as water or alcohol. Examples of the surfactant include: anionic surfactants such as sodium dodecyl sulfate (SDS); cationic surfactants such as dodecyltrimethylammonium chloride (C₁₂TAC) or hexadecyltrimethylammonium bromide (C₁₆TAB); amphoteric surfactants such as cocamidopropyl betaine or cocamidopropyl hydroxybetaine; and nonionic surfactants such as polyvinyl alcohol or polyoxyethylene octylphenylether (product name: Triton X-100). Note that paragraphs (0015) and (0028) of Patent Literature 10 (JP2005-123107A) disclose acetone as an example of a surfactant. When acetone is used as the surfactant, however, an object of the present invention cannot be achieved. Thus, acetone is excluded from the surfactant of the present invention.

The treatment using a polymer dispersant refers to a method for mixing the above carbon material and a polymer dispersant in water or an organic solvent. Examples of the polymer dispersant include polyvinylpyrrolidone (PVP) and poly(allylamine hydrochloride) (PAH).

The second step is to mix source material for lithium-containing phosphate and carbon material that has been subjected to surface treatment by using any of the above methods. The source material for lithium-containing phosphate varies depending on types of lithium-containing phosphate produced or a production process thereof. For example, lithium iron phosphate (LiFePO_4) may be produced using a method for mixing and heating solid source material as a solid state. In this case, lithium carbonate (Li_2CO_3), ferrous oxalate dihydrate ($\text{FeC}_2\text{O}_4 \cdot 2\text{H}_2\text{O}$), and ammonium dihydrogen phosphate ($(\text{NH}_4)\text{H}_2\text{PO}_4$) or ferric phosphate dihydrate ($\text{FePO}_4 \cdot 2\text{H}_2\text{O}$) may be used. Also, lithium iron phosphate (LiFePO_4) may be produced using a method (i.e., a solution reaction) for dissolving and mixing solid or liquid source material into a solvent and for heating the mixture. In this case, it is preferable to use: lithium hydroxide monohydrate ($\text{LiOH} \cdot \text{H}_2\text{O}$), lithium sulfate monohydrate ($\text{Li}_2\text{SO}_4 \cdot \text{H}_2\text{O}$), lithium formate monohydrate ($\text{Li}(\text{HCOO}) \cdot \text{H}_2\text{O}$), and/or lithium nitrate (LiNO_3); ferrous oxalate dihydrate and/or ferric sulfate heptahydrate ($\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$) and/or ferrous chloride tetrahydrate ($\text{FeCl}_2 \cdot 4\text{H}_2\text{O}$); and phosphoric acid (H_3PO_4), ammonium dihydrogen phosphate, ammonium monohydrogen phosphate ($(\text{NH}_4)_2\text{HPO}_4$), and/or ammonium phosphate ($(\text{NH}_4)_3\text{PO}_4$).

In addition, lithium manganese phosphate (LiMnPO_4) may be produced. In this case, as source material, manganese carbonate (MnCO_3), manganese dioxide (MnO_2), manganese sulfate monohydrate ($\text{MnSO}_4 \cdot \text{H}_2\text{O}$), manganese nitrate tetrahydrate ($\text{Mn}(\text{NO}_3)_2 \cdot 4\text{H}_2\text{O}$), and/or manganese acetate tetrahydrate ($(\text{CH}_3\text{COO})_2\text{Mn} \cdot 4\text{H}_2\text{O}$), for example, may be used to substitute the iron compound such as ferrous oxalate dihydrate, ferric phosphate dihydrate, ferric sulfate heptahydrate, and/or ferrous chloride tetrahydrate in the case of the lithium iron phosphate. Further, lithium manganese iron phosphate ($\text{LiMn}_x\text{Fe}_{(1-x)}\text{PO}_4$) may be produced. In this case, source material for the lithium iron phosphate and source material for the lithium manganese phosphate may be used at the same time.

Furthermore, lithium cobalt phosphate (LiCoPO_4) may be produced. In this case, as source material, cobalt sulfate heptahydrate ($\text{CoSO}_4 \cdot 7\text{H}_2\text{O}$), for example, may be used to substitute the iron compound in the case of the lithium iron phosphate. Moreover, lithium vanadium phosphate ($\text{Li}_3\text{V}_2(\text{PO}_4)_3$) may be produced. In this case, as source material, divanadium pentoxide (V_2O_5) and/or vanadium oxide sulfate hydride ($\text{VOSO}_4 \cdot x\text{H}_2\text{O}$) ($x = 3$ to 4), for example, may be used to substitute the iron compound in the case of the lithium iron phosphate. When solid or liquid source material is dissolved in a solvent, components of the source material are present as a lithium ion (Li^+), a phosphate ion (PO_4^{3-}), and a metal ion other than from lithium. The above surface-treated carbon material is dispersed in and mixed with a solution containing the ions. Accordingly, this process should increase uniformity of the source material mixture, compared with the case

of mixing solid source material as a solid state.

In an embodiment of the present invention, composite particles may be coated with carbon so as to further increase electron conductivity. In this case, source material for carbon coating is added to the above source material. The source material for carbon coating is a heat-degradable carbon source compound. Examples include glucose ($C_6H_{12}O_6$), sucrose ($C_{12}H_{22}O_{11}$), dextrin ($(C_6H_{12}O_5)_n$), ascorbic acid ($C_6H_8O_6$), carboxymethyl cellulose, and coal pitch. The above source material can be added at the same time when the surface-treated carbon material and source material for lithium-containing phosphate are mixed. Alternatively, the above source material can be added after particles containing the surface-treated carbon material and a lithium-containing phosphate precursor and/or lithium iron phosphate are formed by heating a source material mixture containing the surface-treated carbon material and source material for lithium iron phosphate.

The surface-treated carbon material and source material may be mixed. In this process, solid source material may be mixed as a solid state. In this case, it is possible to use a ball mill, a vibrating mill, a Henschel mixer, a planetary mixer, a kneader, a ribbon blender, a V-type mixer, a W-type mixer, etc. In addition, solid or liquid source material may be dissolved in a solvent and be mixed with the surface-treated carbon material. In this case, it is possible to use a tank with a mixer, a sonicator, a homogenizer, etc. In this case, water, alcohol, or a mixed solvent of water and alcohol is suitable for the solvent. Note that when a surfactant or a polymer dispersant is used for surface treatment, pretreatment may be carried out before the source material is mixed or treatment may be carried out at the same time when the source material is mixed.

The third step is to heat a mixture containing the surface-treated carbon material and source material to form particles containing the surface-treated carbon material and a lithium-containing phosphate precursor and/or lithium-containing phosphate. When a mixture is obtained by mixing the solid source material as a solid state, the mixture is preferably heated under an inert atmosphere, reducing atmosphere, or atmosphere in which inert and reducing gases are mixed. Their atmospheric pressure is preferably an ordinary pressure or a reduced pressure. Examples of the inert gas include argon (Ar), helium (He), and nitrogen (N_2). Examples of the reducing gas include hydrogen (H_2) and ammonia (NH_3). The heating temperature is preferably from 100 to 400°C and more preferably from 200 to 400°C. This heating temperature may be, for example, 100, 150, 200, 250, 300, 350, or 400°C. The temperature may be between any two of the above values.

The surface-treated carbon material is dispersed in and mixed with a solution having dissolved in a solvent a lithium ion (Li^+), a phosphate ion (PO_4^{3-}),

and a metal ion other than from lithium to yield a mixture. This mixture is preferably heated using a tank with a mixer while stirring. The heating temperature is preferably from 60 to 100°C. In order to increase a reaction rate, however, it is preferable to use a method using a pressured and heated solvent at from 100 to 250°C (i.e., a hydrothermal synthesis method). In this case, the heating is carried out using a pressure-resistant vessel such as an autoclave. This heating temperature may be, for example, 60, 80, 100, 150, 200, or 250°C. The temperature may be between any two of the above values. In a method using a solvent, depending on the need, a pH modifier such as ammonia (NH₃), phosphoric acid (H₃PO₄), or sulfuric acid (H₂SO₄) may be added to a solution having dissolved therein a lithium ion (Li⁺), a phosphate ion (PO₄³⁻), and a metal ion other than from lithium.

The fourth step is to further heat the composite particles containing the surface-treated carbon material and a lithium-containing phosphate precursor and/or lithium-containing phosphate. Then, an oxygen-containing functional group is volatilized from a surface of the surface-treated carbon material. Alternatively, a surfactant or a polymer dispersant is decomposed. These methods help create at least one fine pore which originates from the carbon material and opens to outside the composite particle.

The mixture obtained by mixing solid source material as a solid state may be used as a starting material. In this case, the particles containing the surface-treated carbon material as obtained in the previous step and a lithium-containing phosphate precursor and/or lithium-containing phosphate are used as they are or are cracked if aggregated particles are present. After that, the particles are heated *in vacuo* under an inert atmosphere or reducing atmosphere. The starting material may be a mixture obtained by dispersing and mixing the above surface-treated carbon material in a solution having dissolved in a solvent a lithium ion (Li⁺), a phosphate ion (PO₄³⁻), and a metal ion other than from lithium. In this case, the particles containing the surface-treated carbon material as obtained in the previous step and a lithium-containing phosphate precursor and/or lithium-containing phosphate are filtered, centrifuged, and dried, etc., to separate them from the solvent. These particles are used as they are or are cracked if aggregated particles are present. After that, the particles are heated *in vacuo* under an inert atmosphere or reducing atmosphere. The heating temperature is preferably from 400 to 900°C and more preferably from 500 to 800°C. This heating temperature may be, for example, 400, 450, 500, 550, 600, 650, 700, 750, 800, 850, or 900°C. The temperature may be between any two of the above values. Note that the starting material may be a mixture obtained by mixing the solid source material as a solid state. In this case, the heating of this step may be continuously carried out after the heating of the previous step of

forming the particles containing the surface-treated carbon material and a lithium-containing phosphate precursor and/or lithium-containing phosphate.

During the fourth step, an oxygen-containing functional group is volatilized or a surfactant or a polymer dispersant is decomposed on a surface of the surface-treated (i) fibrous carbon material, (ii) chain-like carbon material, and (iii) carbon material produced by linking together fibrous carbon material and chain-like carbon material. At this time, any of volatile components derived from the oxygen-containing functional group or decomposition components derived from the surfactant or the polymer dispersant is gas. Accordingly, the volume should markedly expand compared with the original solid or liquid, which results in formation of foam. Because its pressure gradually increases, gas enclosed in foam diffuses outside composite particles where a pressure is lower. At this time, a gas diffusion path remains as a fine pore, creating fine pores that originate from the carbon material and open to outside the composite particles. Accordingly, the present inventors have discovered these new findings. The fine pores have a size of about several to 10 nm. The size of each fine pore increases as an amount of the oxygen-containing functional group, surfactant, or polymer dispersant increases or the temperature increasing rate during the heating of the fourth step increases. This fine pore size may be, for example, 0.5, 0.8, 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, or 12 nm. The size may be between any two of the above values.

Composite particles according to an embodiment of the present invention, a conduction aid, and a binder may be mixed to form an electrode material for a lithium-ion secondary battery. Examples of the conduction aid used include: carbon black such as acetylene black or furnace black, and/or a carbon nanotube or carbon nanofiber. Polyvinylidene fluoride (PVDF) may be used as the binder. With regard to a mixing ratio in an embodiment of the present invention, the composite particles have, for example, 60 to 95% by mass and the remainder consists of the conduction aid and the binder. When the composite particles contain less than 60% by mass, the lithium-ion secondary battery has a reduced charge/discharge capacity. In addition, when the composite particles contain more than 95% by mass, the amount of the conduction aid is insufficient. This increases the electric resistance of a positive electrode. In addition, the insufficient amount of the binder causes insufficient firmness of the positive electrode. Unfortunately, this results in a problem that the positive electrode material is likely to detach from a collector (mostly made of aluminum) during charge and discharge.

In an embodiment of the present invention, a positive electrode material is used for a positive electrode formed on a collector and the positive electrode may be used for a lithium-ion secondary battery. Examples of other components used for the lithium-ion secondary battery include a separator, an electrolytic solution, and

a negative electrode material. The separator electrically insulates the positive electrode from the negative electrode and helps retain the electrolytic solution. Separators made of synthetic resin such as polyethylene and polypropylene may be used. In order to increase retention of the electrolytic solution, a porous film is preferably used for the separators.

In addition, in a lithium secondary battery using a positive electrode according to an embodiment of the present invention, a lithium salt-containing nonaqueous electrolytic solution or ion conductive polymer may be preferably used as an electrolytic solution in which a group of the electrodes is soaked. Examples of a nonaqueous solvent for a nonaqueous electrolyte in the lithium salt-containing nonaqueous electrolytic solution include ethylene carbonate (EC), propylene carbonate (PC), diethyl carbonate (DEC), dimethyl carbonate (DMC), and methylethyl carbonate (MEC). In addition, examples of the lithium salt capable of being dissolved in the above nonaqueous solvent include lithium hexafluorophosphate (LiPF_6), lithium tetrafluoroborate (LiBF_4), and lithium trifluoromethanesulfonate (LiSO_3CF_3).

A preferable active substance of a negative electrode is a material that can reversibly store and release a Li ion in the same manner as in the case of the positive electrode, has poor reactivity with the electrolyte, and has a less redox potential than the positive electrode material. Examples include graphite, lithium titanate, silicon (Si), and tin (Sn). Two or more of them may be combined depending on the need. These compounds may be combined with a conduction aid and a binder in the same manner as in the case of the positive electrode, and may be practically used as a negative electrode material formed on a collector (in the case of the negative electrode, copper is mainly used).

The material members disclosed in paragraphs (0029) to (0031) are combined. Then, in order to prevent damage, deformation, and contact with an ambient air, the members are sealed in a container to form a lithium-ion secondary battery. The shape and material of the container are appropriately selected depending on its usage. For example, when charge and discharge characteristics, for example, are tested in a simple way, it is preferable to form a coin cell using a disk container made of metal such as stainless for sealing.

A high capacity and long service life may be required for industrial or consumer use. In this case, a positive electrode material, a separator, and a negative electrode material are alternately wound to form a wound cell using a metal cylinder-type or rectangular-type container for sealing. In the case of intermediate usage, a positive electrode material, a separator, and a negative electrode material are alternately stacked to form a laminated cell (aluminum pouch cell) using an aluminum-laminated package, etc., for sealing.

Examples

The following details composite particles, a process for producing the same, electrode material for a secondary battery and a secondary battery according to the present invention by referring to Examples and Comparative Examples. The present invention, however, is not limited to the following Examples without departing from the scope of the present invention.

Examples 1 to 7

(First Step: Surface Treatment of Carbon Material)

Tables 1 and 2 list carbon materials used for treatment and treatment methods. Note that organic functional groups introduced onto a surface of the carbon materials by oxidation treatment were determined by temperature-programmed desorption gas chromatography/mass spectrometry (a TDS-GC/MS method) using a temperature-programmed desorption device (Double-Shot Pyrolyzer 7683B manufactured by Agilent Technologies Inc.), gas chromatography equipment (HP6890 manufactured by Hewlett-Packard Development Company, L.P.), and a mass spectrometer (5973 manufactured by Hewlett-Packard Development Company, L.P.). Qualitative analysis was performed by examining whether or not there were mass spectral peaks of water (mass number = 18), carbon monoxide (mass number = 28), and carbon dioxide (mass number = 44). Note that a mass spectrum detected below 200°C was considered to be due to detachment of adsorbed gas. Accordingly, the mass spectrum was neglected. In addition, the same condition as of the temperature-programmed desorption device (i.e., heating *in vacuo* at a temperature increasing rate of 25°C/min from 200°C to 1000°C) was applied to heat 10 g of the carbon materials in an electric furnace and to determine a change in mass before and after the heating. The following equation was used to calculate an amount of decrease in mass and the amount was defined as a content of the organic functional groups.

$$[\text{Organic functional group content (\% by mass)}] = \{[(\text{Mass of carbon material after heating at } 200^{\circ}\text{C}) - (\text{Mass of carbon material after heating at } 1000^{\circ}\text{C})] / (\text{Mass of carbon material after heating at } 200^{\circ}\text{C})\} \times 100$$

Table 1

Example	Carbon Material	Product Name	Manufacturer	Average Fiber Size or Average Primary Particle Size	Carbon Material Linking Method	Carbon Material Linking Conditions	Surface Treatment Method	Surface Treatment Condition	Organic Functional Group Type*	Amount of Organic Functional Group
1	Carbon nanofiber	CNF-T	Mitsubishi Materials Electronic Chemicals Co., Ltd.	15nm	—	—	Oxidation treatment (Adding nitric acid while heating in sulfuric acid)	CNF-T : 500g Sulfuric acid : 5L 60% Nitric acid : 1.8L stirring	-OH >C=O -COOH	1.2% by mass
2	Acetylene black	HS-100	DENKI KAGAKU KOGYO KABUSHIKI KAISHA	60nm	—	—	Treatment with polymer dispersant polyvinylpyrrolidone (PVP)	HS-100 : 500g PVP(K-30 manufactured by NIPPON SHOKUBAI CO., LTD.) : 50g Distilled water : 10L	—	—
3	Particles produced by linking carbon nanofiber and acetylene black	CNF-T Acetylene black	Mitsubishi Materials Electronic Chemicals Co., Ltd (CNF-T) (Acetylene black : generated from C ₂ H ₂ gas)	15nm (CNF-T average fiber size) 50nm (Acetylene black average primary particle size)	Powder CNF-T was injected into AB- generating site to precipitate AB on NF-T surface	2000°C 1hr CNF-T feed rate : 500g/hr C ₂ H ₂ feed rate : 30L/min N ₂ (dilution gas) feed rate : 400L/min	Treatment with surfactant polyoxyethylene octylphenylether (TritonX-100)	Particles produced by linking CNF-T and acetylene black : 500g TritonX-100 (manufactured by Roche Applied Science) : 25mL Distilled water : 10L	—	—
4	Particles produced by linking carbon nanofiber and acetylene black	Carbon nanofiber AB	(Carbon nanofiber : generated from CO gas) DENKI KAGAKU KOGYO KABUSHIKI KAISHA(AB)	20nm (Carbon nanofiber average fiber size) 40nm (AB average primary particle size)	AB was injected into carbon nanofiber- generating site to precipitate carbon nanofiber on AB surface	600°C 3hr AB : 30g Cobalt oxide powder (Sigma-Aldrich 637025 : Particle size 50nm or less) : 1g CO feed rate : 1.6L/min H ₂ feed rate : 0.6L/min N ₂ (dilution gas) feed rate : 0.8L/min	Treatment with surfactant sodium dodecyl sulfate (SDS)	Particles produced by linking carbon nanofiber and AB : 60g SDS(Sigma-Aldrich 71717) : 5g Distilled water : 1L	—	—
5	Particles produced by linking carbon nanofiber and acetylene black	CNF-T HS-100 acetylene black	Mitsubishi Materials Electronic Chemicals Co., Ltd. DENKI KAGAKU KOGYO KABUSHIKI KAISHA	15nm (CNF-T average fiber size) 60nm (HS-100 average primary particle size)	Mixing with wet vibrating mill	Mixing period : 1hr CNF-T : 20g HS-100 : 80g Ethanol : 1L Al ₂ O ₃ ball : 1kg	Oxidation treatment (Stirring in ozone-containing water)	Particles produced by linking CNF-T/HS-100 : 100g Ozone level : 50ppm Distilled water : 2L	-OH >C=O -COOH	1.8% by mass

*Regarding types of organic functional groups: H₂O, CO, and CO₂ detected by TDS-GC/MS method were presumed to be attributed to -OH, >C=O, and -COOH groups, respectively.

Table 2

Example	Carbon Material	Product Name	Manufacturer	Average Fiber Size or Average Primary Particle Size	Carbon Material Linking Method	Carbon Material Linking Conditions	Surface Treatment Method	Surface Treatment Condition	Organic Functional Group Type*	Amount of Organic Functional Group
6	Particles produced by linking carbon nanofiber (two kinds) and acetylene black	VGCF-H	SHOWA DENKO K.K.(VGCF-H)	150nm (VGCF-H average fiber size)	Mixing with wet vibrating mill	VGCF-H : 25g CNF-T : 25g HS-100 : 50g Ethanol : 1L Al ₂ O ₃ ball : 1kg	Oxidation treatment (Treatment using wet jet mill (Star Burst manufactured by SUGINO MACHINE LIMITED))	Particles produced by linking VGCF-H/CNF-T/Acetylene black : 100g Ethanol : 1L (using post-mixing solution as it was)	-OH >C=O -COOH	1.0% by mass
		CNF-T	Mitsubishi Materials Electronic Chemicals Co., Ltd.(CNF-T)	15nm (CNF-T average fiber size)						
		HS-100	DENKI KAGAKU KOGYO KABUSHIKI KAISHA(HS-100)	60nm (HS-100 average primary particle size)						
7	Furnace black	Super-P	TIMCAL Inc.	40nm	-	-	Treatment with polymer dispersant poly(allylamine hydrochloride)(PAH)	Super-P : 300g PAH(Sigma-Aldrich 283215, average molecular weight: 15000) : 20g Distilled water : 10L	-	-

*Regarding types of organic functional groups, H₂O, CO, and CO₂ detected by TDS-GC/MS method were presumed to be attributed to -OH, >C=O, and -COOH groups, respectively.

Examples 8 to 14

(Second Step: Mixing of Surface-treated Carbon Material and Source Material for Lithium-containing Phosphate) and (Third Step: Heating of Mixture of Surface-treated Carbon Material and Source Material)

The surface-treated carbon material as produced in the first step (Examples 1 to 7) was mixed with source material under conditions designated in Tables 3 and 4. Then, the mixture was heated under conditions designated in Tables 3 and 4.

Table 3

Example	Carbon Material	Source Material for Lithium-containing Phosphate • Solvent • Carbon Source Material, etc.	Mixing Method	Mixing Conditions	Heating Method	Heating Conditions	Drying Conditions
8	Example 1 : 100g	Li_2CO_3 (Sigma-Aldrich 62472) : 370g $\text{FeC}_2\text{O}_4 \cdot 2\text{H}_2\text{O}$ (Sigma-Aldrich 44951) : 1800g $(\text{NH}_4)_2\text{HPO}_4$ (Sigma-Aldrich 215996) : 1320g	Henschel mixer	30°C 5min	Heating under inert gas atmosphere	N_2 300°C 4hr	—
9	Example 2 : 10g	$\text{LiOH} \cdot \text{H}_2\text{O}$ (Sigma-Aldrich 402974) : 126g $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$ (Sigma-Aldrich 44982) : 278g $(\text{NH}_4)_2\text{HPO}_4$ (Sigma-Aldrich 215996) : 10g H_3PO_4 (Sigma-Aldrich P5811) : 91g Distilled water : 1L	Mixing with mixer	30°C 1hr	Heating in autoclave while mixing with mixer (hydrothermal treatment)	190°C 12hr	Filtration, washing, drying in vacuo
10	Example 3 : 10g	$\text{LiOH} \cdot \text{H}_2\text{O}$ (Sigma-Aldrich 402974) : 126g $\text{MnSO}_4 \cdot \text{H}_2\text{O}$ (Sigma-Aldrich M7634) : 169g $(\text{NH}_4)_2\text{HPO}_4$ (Sigma-Aldrich 215996) : 10g H_3PO_4 (Sigma-Aldrich P5811) : 91g Distilled water : 0.7L Ethanol : 0.3L	Mixing with mixer	30°C 1hr	Heating in autoclave while mixing with mixer (hydrothermal treatment)	170°C 12hr	Filtration, washing, drying in vacuo
11	Example 4 : 10g	$\text{LiOH} \cdot \text{H}_2\text{O}$ (Sigma-Aldrich 402974) : 126g $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$ (Sigma-Aldrich 44982) : 93g $\text{MnSO}_4 \cdot \text{H}_2\text{O}$ (Sigma-Aldrich M7634) : 113g $(\text{NH}_4)_2\text{HPO}_4$ (Sigma-Aldrich 215996) : 10g H_3PO_4 (Sigma-Aldrich P5811) : 91g Distilled water : 1L	Mixing with mixer	30°C 1hr	Heating in autoclave while mixing with mixer (hydrothermal treatment)	190°C 12hr	Filtration, washing, drying in vacuo
12	Example 5 : 10g	$\text{LiOH} \cdot \text{H}_2\text{O}$ (Sigma-Aldrich 402974) : 126g $\text{CoSO}_4 \cdot 7\text{H}_2\text{O}$ (Sigma-Aldrich C6768) : 281g $(\text{NH}_4)_2\text{HPO}_4$ (Sigma-Aldrich 215996) : 10g H_3PO_4 (Sigma-Aldrich P5811) : 91g Distilled water : 1L	Mixing with mixer	30°C 1hr	Heating while mixing with mixer	90°C 24hr	Filtration, washing, drying in vacuo

Table 4

Example	Carbon Material	Source Material for Lithium-containing Phosphate·Solvent·Carbon Source Material, etc.	Mixing Method	Mixing Conditions	Heating Method	Heating Conditions	Drying Conditions
13	Example 6 : 10g	Li ₂ CO ₃ (Sigma-Aldrich 62472) : 37g V ₂ O ₅ (Sigma-Aldrich 223794) : 61g (NH ₄) ₂ HPO ₄ (Sigma-Aldrich 215996) : 132g Dextrin (Sigma-Aldrich 31410) : 30g	Wet mixing with ball mill Al ₂ O ₃ ball : 1kg Ethanol : 1L	30°C 5min Filtration and drying after mixing(85 °C, 1hr, in vacuo)	Heating under atmosphere in which inert and reducing gases were mixed	Ar : H ₂ = 9 : 1 800°C 4hr	—
14	Example 7 : 10g	LiOH·H ₂ O(Sigma-Aldrich 402974) : 126g FeSO ₄ ·7 H ₂ O(Sigma-Aldrich 44982) : 278g (NH ₄) ₂ HPO ₄ (Sigma-Aldrich 215996) : 10g H ₃ PO ₄ (Sigma-Aldrich P5811) : 91g Ascorbic acid(Sigma-Aldrich 95212) : 35g Distilled water : 1L	Mixing with mixer	30°C 1hr	Heating in autoclave while mixing with mixer (hydrothermal treatment)	190°C 12hr	Spray dry

Examples 15 to 21

(Fourth Step: Further Heating of Composite Particles Containing Surface-treated Carbon Material and Lithium-containing Phosphate Precursor and/or Lithium-containing Phosphate)

The composite particles as produced through the first to third steps (Examples 8 to 14) were further heated under conditions designated in Table 5 to prepare composite particles according to an example of the present invention. The crystal phase of the composite particles was identified by powder X - ray diffraction (using an X-ray diffractometer RU-200A manufactured by Rigaku Corporation; an X-ray source: Cu-K α ; a voltage: 40 kV; a current: 30 mA). In addition, a scanning electron microscope (a scanning electron microscope (SEM) JSM-6301F manufactured by JEOL Ltd.; an acceleration voltage: 1 kV; magnification: 10,000 to 50,000 x) was used to measure an average primary particle size of the composite particles. Further, a transmission electron microscope (a transmission electron microscope (TEM) 2000FX manufactured by JEOL Ltd.; an acceleration voltage: 200 kV; magnification: 200,000 x) was used to observe the presence or absence of a fine pore. The fine pore size was measured by a BHJ method using a fine pore distribution tester (BELSORP-miniII manufactured by BEL Japan, Inc.).

Table 5

Example	Heated Mixture	Carbon Source Material	Method for Adding Carbon Source Material	Heating Temperature · Hour	Heating Atmosphere	Crystal Phase of Product	Average Primary Particle Size	The Presence or Absence of Fine Pore · Fine Pore Size
15	Example 8 : 100g was recovered	None	—	700°C 2hr	Ar : H ₂ = 9 : 1	LiFePO ₄	2μm	Fine pore was present 5~10nm
16	Example 9 : 100g was recovered	Sucrose (Sigma-Aldrich 84097) : 20g	Solution after heating at 190°C for 12 hours was filtered, washed, and dried in vacuo to yield power, and 100 g of the powder was recovered and dispersed in 500 mL of distilled water while adding sucrose. The mixture was stirred for 30 min and then dried with spray dryer.	800°C 1hr	In vacuo	LiFePO ₄	0.1μm	Fine pore was present 1~5nm
17	Example 10 : 100g was recovered	Glucose (Sigma-Aldrich 158968) : 20g	Solution after heating at 170°C for 12 hours was filtered, washed, and dried in vacuo to yield power, and 100 g of the powder was recovered and dispersed in 500 mL of distilled water while adding glucose. The mixture was stirred for 30 min and then dried under reduced pressure while heating at 100°C.	600°C 3hr	N ₂	LiMnPO ₄	0.5μm	Fine pore was present 1~5nm
18	Example 11 : 100g was recovered	Carboxymethyl cellulose (NIPPON PAPER INDUSTRIES CO., LTD. CHEMICAL DIVISION · Grade A) : 20g	Solution after heating at 190°C for 12 hours was filtered, washed, and dried in vacuo to yield power, and 100 g of the powder was recovered and dispersed in a mixed solution of 300 mL of distilled water and 200 mL of ethanol while adding CMC. The mixture was stirred for 30 min and then dried under reduced pressure while heating at 100°C.	800°C 1hr	N ₂ : H ₂ = 7 : 3	LiMn _{0.67} Fe _{0.33} PO ₄	0.1μm	Fine pore was present 1~5nm
19	Example 12 : 100g was recovered	None	—	700°C 1hr	In vacuo	LiCoPO ₄	0.05μm	Fine pore was present 1~5nm
20	Example 13 : 100g was recovered (Heating was completed)	Third step (of heating mixture of surface-treated carbon material and source material) and fourth step (of further heating particles containing surface-treated carbon material and lithium-containing phosphate precursor and/or lithium-containing phosphate) were continuously performed.			Ar	Li ₃ V ₂ (PO ₄) ₃	10μm	Fine pore was present 5~10nm
21	Example 14 : 100g was recovered	None	(Carbon source material was already added in second step (of mixing source material)).	700°C 2hr		LiFePO ₄	0.5μm	Fine pore was present 1~5nm

Comparative Examples 1 to 21

Composite particles (Comparative Examples 15 to 21) were prepared by performing the second to fourth steps without the first step (surface treatment of carbon material). Tables 6 to 9 show these conditions and results together.

Table 6

Comparative Example	Carbon Material	Product Name	Manufacturer	Average Fiber Size or Average Primary Particle Size	Carbon Material Linking Method	Carbon Material Linking Conditions	Surface Treatment Method	Organic Functional Group Type*
1	Carbon nanofiber	CNF-T	Mitsubishi Materials Electronic Chemicals Co., Ltd.	15nm	—	—	—	—
2	Acetylene black	HS-100	DENKI KAGAKU KOGYO KABUSHIKI KAISHA	60nm	—	—	—	—
3	Particles produced by linking carbon nanofiber and acetylene black	CNF-T Acetylene black	Mitsubishi Materials Electronic Chemicals Co., Ltd. (CNF-T) (Acetylene black : generated from C ₂ H ₂ gas)	15nm (CNF-T average fiber size) 50nm (Acetylene black average primary particle size)	Powder CNF-T was injected into AB-generating site to precipitate AB on NF-T surface	CNF-T feed rate : 500g/hr C ₂ H ₂ feed rate : 30L/min N ₂ (dilution gas) feed rate : 400L/min	2000°C 1hr	—
4	Particles produced by linking carbon nanofiber and acetylene black	Carbon nanofiber AB	(Carbon nanofiber : generated from CO gas) DENKI KAGAKU KOGYO KABUSHIKI KAISHA(AB)	20nm (Carbon nanofiber average fiber size) 40nm (AB average primary particle size)	AB was injected into carbon nanofiber-generating site to precipitate carbon nanofiber on AB surface	AB : 30g Cobalt oxide powder(Sigma-Aldrich 637025 : Particle size 50nm or less) : 1g CO feed rate : 1.6L/min H ₂ feed rate : 0.6L/min N ₂ (dilution gas) feed rate : 0.8L/min	600°C 3hr	—
5	Particles produced by linking carbon nanofiber and acetylene black	CNF-T HS-100	Mitsubishi Materials Electronic Chemicals Co., Ltd. DENKI KAGAKU KOGYO KABUSHIKI KAISHA	15nm (CNF-T average fiber size) 60nm (HS-100 average primary particle size)	Mixing with wet vibrating mill	CNF-T : 20g HS-100 : 80g Ethanol : 1L Al ₂ O ₃ ball : 1kg	Mixing period : 1hr	—
6	Particles produced by linking carbon nanofiber (two kinds) and acetylene black	VGCF-H CNF-T HS-100	SHOWA DENKO K.K.(VGCF-H) Mitsubishi Materials Electronic Chemicals Co., Ltd.(CNF-T) DENKI KAGAKU KOGYO KABUSHIKI KAISHA(HS-100)	150nm (VGCF-H average fiber size) 15nm (CNF-T average fiber size) 60nm (HS-100 average primary particle size)	Mixing with wet vibrating mill	VGCF-H : 25g CNF-T : 25g HS-100 : 50g Ethanol : 1L Al ₂ O ₃ ball : 1kg	Mixing period : 1hr	—
7	Furnace black	Super-P	TIMCAL Inc.	40nm	—	—	—	—

*Regarding types of organic functional groups, H₂O, CO, and CO₂ detected by TDS-GCMS method were presumed to be attributed to -OH, >C=O, and -COOH groups, respectively.

Table 7

Comparative Example	Carbon Material	Source Material for Lithium-containing Phosphate·Solvent·Carbon Source Material, etc.	Mixing Method	Mixing Conditions	Heating Method	Heating Conditions	Drying Conditions
8	Comparative Example 1 : 100g	Li ₂ CO ₃ (Sigma-Aldrich 62472) : 370g FeC ₂ O ₄ ·2H ₂ O(Sigma-Aldrich 44951) : 1800g (NH ₄) ₂ HPO ₄ (Sigma-Aldrich 215996) : 1320g	Henschel mixer	30°C 5min	Heating under inert gas atmosphere	N ₂ 300°C 4hr	—
9	Comparative Example 2 : 10g	LiOH·H ₂ O(Sigma-Aldrich 402974) : 126g FeSO ₄ ·7H ₂ O(Sigma-Aldrich 44982) : 278g (NH ₄) ₂ HPO ₄ (Sigma-Aldrich 215996) : 10g H ₃ PO ₄ (Sigma-Aldrich P5811) : 91g Distilled water : 1L	Mixing with mixer	30°C 1hr	Heating in autoclave while mixing with mixer (hydrothermal treatment)	190°C 12hr	filtration, washing, drying in vacuo
10	Comparative Example 3 : 10g	LiOH·H ₂ O(Sigma-Aldrich 402974) : 126g MnSO ₄ ·H ₂ O(Sigma-Aldrich M7634) : 169g (NH ₄) ₂ HPO ₄ (Sigma-Aldrich 215996) : 10g H ₃ PO ₄ (Sigma-Aldrich P5811) : 91g Distilled water : 0.7L Ethanol : 0.3L	Mixing with mixer	30°C 1hr	Heating in autoclave while mixing with mixer (hydrothermal treatment)	170°C 12hr	filtration, washing, drying in vacuo
11	Comparative Example 4 : 10g	LiOH·H ₂ O(Sigma-Aldrich 402974) : 126g FeSO ₄ ·7H ₂ O(Sigma-Aldrich 44982) : 93g MnSO ₄ ·H ₂ O(Sigma-Aldrich M7634) : 113g (NH ₄) ₂ HPO ₄ (Sigma-Aldrich 215996) : 10g H ₃ PO ₄ (Sigma-Aldrich P5811) : 91g Distilled water : 1L	Mixing with mixer	30°C 1hr	Heating in autoclave while mixing with mixer (hydrothermal treatment)	190°C 12hr	filtration, washing, drying in vacuo
12	Comparative Example 5 : 10g	LiOH·H ₂ O(Sigma-Aldrich 402974) : 126g CoSO ₄ ·7H ₂ O(Sigma-Aldrich C6768) : 281g (NH ₄) ₂ HPO ₄ (Sigma-Aldrich 215996) : 10g H ₃ PO ₄ (Sigma-Aldrich P5811) : 91g Distilled water : 1L	Mixing with mixer	30°C 1hr	Heating while mixing with mixer	90°C 24hr	filtration, washing, drying in vacuo

Table 8

Comparative Example	Carbon Material	Source Material for Lithium-containing Phosphate-Solvent-Carbon Source Material, etc.	Mixing Method	Mixing Conditions	Heating Method	Heating Conditions	Drying Conditions
13	Comparative Example 6 : 10g	Li ₂ CO ₃ (Sigma-Aldrich 62472) : 37g V ₂ O ₅ (Sigma-Aldrich 223794) : 61g (NH ₄) ₂ HPO ₄ (Sigma-Aldrich 215996) : 132g Dextrin (Sigma-Aldrich 31410) : 30g	Wet mixing with ball mill Al ₂ O ₃ ball : 1kg Ethanol : 1L	30°C 5min Filtration and drying after mixing(85 °C, 1hr, in vacuo)	Heating under atmosphere in which inert and reducing gases were mixed	Ar : H ₂ = 9 : 1 800°C 4hr	—
14	Comparative Example 7 : 10g	LiOH·H ₂ O(Sigma-Aldrich 402974) : 126g FeSO ₄ ·7H ₂ O(Sigma-Aldrich 44982) : 278g (NH ₄) ₂ HPO ₄ (Sigma-Aldrich 215996) : 10g H ₃ PO ₄ (Sigma-Aldrich P5811) : 91g Ascorbic acid(Sigma-Aldrich 95212) : 35g Distilled water : 1L	Mixing with mixer	30°C 1hr	Heating in autoclave while mixing with mixer (hydrothermal treatment)	190°C 12hr	Spray dry

Table 9

Comparative Example	Heated Mixture	Carbon Source Material	Method for Adding Carbon Source Material	Heating Temperature · Hour	Heating Atmosphere	Crystal Phase of Product	Average Primary Particle Size	The Presence or Absence of Fine Pore · Fine Pore Size
15	Comparative Example 8 : 100g was recovered	None	—	700°C 2hr	Ar : H ₂ = 9 : 1	LiFePO ₄	2μm	No fine pore
16	Comparative Example 9 : 100g was recovered	Sucrose (Sigma-Aldrich 84097) : 20g	Solution after heating at 190°C for 12 hours was filtered, washed, and dried in vacuo to yield power, and 100 g of the powder was recovered and dispersed in 500 mL of distilled water while adding sucrose. The mixture was stirred for 30 min and then dried with spray dryer.	800°C 1hr	In vacuo	LiFePO ₄	0.1μm	No fine pore
17	Comparative Example 10 : 100g was recovered	Glucose (Sigma-Aldrich 158968) : 20g	Solution after heating at 170°C for 12 hours was filtered, washed, and dried in vacuo to yield power, and 100 g of the powder was recovered and dispersed in 500 mL of distilled water while adding glucose. The mixture was stirred for 30 min and then dried under reduced pressure while heating at 100°C.	600°C 3hr	N ₂	LiMnPO ₄	0.5μm	No fine pore
18	Comparative Example 11 : 100g was recovered	Carboxymethyl cellulose (NIPPON PAPER INDUSTRIES CO., LTD. CHEMICAL DIVISION · Grade A) : 20g	Solution after heating at 190°C for 12 hours was filtered, washed, and dried in vacuo to yield power, and 100 g of the powder was recovered and dispersed in a mixed solution of 300 mL of distilled water and 200 mL of ethanol while adding CMC. The mixture was stirred for 30 min and then dried under reduced pressure while heating at 100°C.	800°C 1hr	N ₂ : H ₂ = 7 : 3	LiMn _{0.65} Fe _{0.35} PO ₄	0.1μm	No fine pore
19	Comparative Example 12 : 100g was recovered	None	—	700°C 1hr	In vacuo	LiCoPO ₄	0.05μm	No fine pore
20	Comparative Example 13 : 100g was recovered (Heating was completed)	Third step (of heating mixture of surface-treated carbon material and source material) and fourth step (of further heating particles containing surface-treated carbon material and lithium-containing phosphate precursor and/or lithium-containing phosphate) were continuously performed.			Ar	Li _{1.5} V ₂ (PO ₄) ₃	10μm	No fine pore
21	Comparative Example 14 : 100g was recovered	None	Carbon source material was already added in second step (of mixing source material).	700°C 2hr		LiFePO ₄	0.5μm	No fine pore

Examples 22 to 28

The composite particles of Examples 15 to 21, carbon as a conduction aid, and polyvinylidene fluoride (a KF polymer solution manufactured by KUREHA CORPORATION) as a binder were combined at predetermined ratios designated in Table 10. N-methylpyrrolidone (catalog No. 328634 manufactured by Sigma-Aldrich Co. LLC.) was added thereto as a dispersion solvent. Then, the mixture was kneaded to prepare a positive electrode combination (slurry). This combination was used as positive electrode material to manufacture a laminated

cell. After that, its charge and discharge characteristics were evaluated. The following shows an example of a method for manufacturing a positive electrode and a laminated cell. First, the composite particles of Examples 15 to 21 were used as a positive electrode combination slurry. Next, an aluminum foil with a thickness of 20 μm was coated with this slurry and dried. Then, the foil was cut at 40 mm x 40 mm to prepare a positive electrode for a lithium secondary battery. Graphite (synthetic graphite MCMB6-28 manufactured by OSAKA GAS CO., Ltd.) was used for a negative electrode. Polyvinylidene fluoride as a binder was mixed at a predetermined ratio. Then, a slurry was prepared in the same manner as in the case of the positive electrode. Subsequently, a copper foil with a thickness of 10 μm was coated with this slurry and dried. After that, the foil was pressed and cut at 45 mm x 45 mm to manufacture a negative electrode for a lithium secondary battery. An olefin fiber nonwoven fabric with a size of 50 mm x 50 mm was used as a separator that electrically separate the positive electrode from the negative electrode. An electrolytic solution was a solution prepared by mixing EC (ethylene carbonate manufactured by Aldrich Inc.) and MEC (methylethyl carbonate manufactured by Aldrich Inc.) at a volume ratio of 30:70 and by dissolving lithium hexafluorophosphate (LiPF_6 manufactured by Stella Chemifa Corporation) at 1 mol/L in the solution. After terminals were connected to the positive and negative electrodes, the whole body was enclosed in an aluminum-laminated package to form a laminated cell with a size of 60 mm x 60 mm.

Discharge performance of the cell was tested as follows. First, a cell was initially charged. Next, its charge/discharge efficiency was verified to be at or near 100%. Then, a constant current was discharged at a current density of 0.7 mA/cm^2 until the voltage reached 2.1 V. At that time, the discharge capacity was measured. After that, the discharge capacity was divided by an amount of positive electrode active substance to calculate a capacity density (mAh/g). A current level that can charge and discharge this capacity (mAh) in 1 hour was defined as "1C".

After the initial charge and discharge, its charge was conducted at 4.2 V (4.8 V was used for Examples 26 and 27 and Comparative Examples 26 and 27)(at a constant current of 0.2C; terminated when a current was 0.05C). With regard to the discharge, a current level in each cycle was gradually increased from 0.2C, 0.33C, 0.5C, 1C, 5C to 10C (at a constant current; terminated when the voltage was 2.1 V). Then, a 10-min interval was placed between the cycles, and the charge and discharge were performed therebetween. Rate characteristics were defined as a ratio (%) of a charge/discharge capacity at 10C to a charge/discharge capacity at 0.2C. Further, I-V characteristics at a SOC (charge depth) of 50% were used to calculate direct current resistance (DCR) of the cell. The direct current resistance during charge is defined as "charge DCR" and the direct current resistance during discharge is defined as "discharge DCR". Table 10 lists these

results.

Comparative Examples 22 to 28

Except using the composite particles of Comparative Examples 15 to 21 as alternatives for those of Examples 22 to 28, the same procedure as in Examples 22 to 28 was applied to form a laminated cell. Then, the discharge performance of the cell was tested. Table 10 shows the results.

Table 10

	Composite Particles Used	Positive Electrode Combination	Negative Electrode Combination	Capacity Density (mAh/g)	10C/0.2C Rate Characteristics (%)	Charge DCR (mΩ)	Discharge DCR (mΩ)
Example 22	Example 15	Composite particles : 85% by mass Conduction aid*1 : 9% by mass Binder*2 : 6% by mass	Graphite : 94% by mass Conduction aid*3 : 1% by mass Binder*4 : 5% by mass	160	59	1107	1247
Example 23	Example 16			155	63	1071	1190
Example 24	Example 17			80	53	2221	2272
Example 25	Example 18			125	56	1631	1651
Example 26	Example 19			135	60	1089	1367
Example 27	Example 20			130	51	1519	1610
Example 28	Example 21			150	54	1181	1300
Comparative Example 22	Comparative Example 15			155	42	1520	1715
Comparative Example 23	Comparative Example 16			150	43	1468	1634
Comparative Example 24	Comparative Example 17			70	37	3067	3135
Comparative Example 25	Comparative Example 18			120	40	2285	2314
Comparative Example 26	Comparative Example 19			130	41	1554	1758
Comparative Example 27	Comparative Example 20			125	32	2326	2466
Comparative Example 28	Comparative Example 21			145	39	1634	1799

*1. Powder obtained by mixing CNF-T (Mitsubishi Materials Corporation) and HS-100 (DENKI KAGAKU KOGYO KABUSHIKI KAISHA) at a mass ratio of 1:4 was used as the conduction aid for a positive electrode.

*2. The binder for a positive electrode was polyvinylidene fluoride (PVDF) L#7208 manufactured by KUREHA CORPORATION (% by mass was a value converted to a solid content).

*3. The conduction aid for a negative electrode was VGCF-H (SHOWA DENKO K.K.).

*4. The binder for a negative electrode was PVDF L#9130 manufactured by KUREHA CORPORATION (% by mass was a value converted to a solid content).

It has been found from Examples and Comparative Examples that cells using composite particles according to the present invention have remarkable improvements in rate characteristics of the cells.

Industrial Applicability

Positive electrode material for a lithium-ion secondary battery according to the present invention has excellent electron conductivity and ion conductivity while using lithium-containing phosphate as a positive electrode active substance and overcoming its drawback. The lithium-containing phosphate should be heat-stable and highly safe, but has the drawback that its resistance is high. The positive electrode material of the present invention has resolved the drawback of the lithium-containing phosphate. As a result, it is possible to manufacture a

highly safe lithium-ion secondary battery capable of repeating charge and discharge using a large current. A lithium-ion secondary battery using positive electrode material of the present invention can be suitably used for application such as an electric tool and a hybrid car, which require charge and discharge using a large current.

Claims

1. Composite particles comprising:

at least one carbon material selected from the group consisting of (i) fibrous carbon material, (ii) chain-shaped carbon material, and (iii) carbon material produced by linking together fibrous carbon material and chain-shaped carbon material; and

lithium-containing phosphate,

wherein the composite particles comprise at least one fine pore originating from the at least one carbon material and opening to outside the composite particle, thus connecting the inside of the composite particles with the outside of the composite particles, and

the size of the at least one fine pore is from 0.5 nm to 12 nm.

2. The composite particles according to Claim 1, wherein the fibrous carbon material is a carbon nanotube with an average fiber size of 5 to 200 nm.

3. The composite particles according to Claim 1 or Claim 2, wherein the chain-shaped carbon material is carbon black produced by linking, in a chain shape, primary particles with an average particle size of 10 to 100 nm.

4. The composite particles according to any one of Claims 1 to 3, wherein the lithium-containing phosphate is LiFePO_4 , LiMnPO_4 , $\text{LiMn}_x\text{Fe}_{(1-x)}\text{PO}_4$, LiCoPO_4 , or $\text{Li}_3\text{V}_2(\text{PO}_4)_3$.

5. The composite particles according to any one of Claims 1 to 4, wherein the composite particles have an average primary particle size of 0.02 to 20 μm .

6. A process for producing the composite particles according to any one of Claims 1 to 5, the process comprising:

a first step of subjecting to surface treatment at least one carbon material selected from the group consisting of (i) fibrous carbon material, (ii) chain-shaped carbon material, and (iii) carbon material produced by linking together fibrous carbon material and chain-shaped carbon material;

a second step of mixing the at least one surface-treated carbon material and source material for lithium-containing phosphate;

a third step of heating the mixture to form composite particles

comprising: the at least one surface-treated carbon material; and a lithium-containing phosphate precursor and/or the lithium-containing phosphate; and

a fourth step of heating the composite particles to create at least one fine pore opening to outside the composite particle, wherein the at least one fine pore originates from the at least one carbon material.

7. The process for producing composite particles according to Claim 6, further comprising the step of adding a heat-degradable carbon source compound in one or more steps from the second to fourth steps.

8. The process for producing composite particles according to Claim 6 or 7, wherein the third and fourth steps are continuously performed.

9. The process for producing composite particles according to any one of Claims 6 to 8, wherein oxidation treatment is used for the surface treatment of the at least one carbon material.

10. The process for producing composite particles according to any one of Claims 6 to 8, wherein a method using a surfactant is used for the surface treatment of the at least one carbon material.

11. The process for producing composite particles according to any one of Claims 6 to 8, wherein a method using a polymer dispersant is used for the surface treatment of the at least one carbon material.

12. The process for producing composite particles according to any one of Claims 6 to 11, wherein the method for mixing the source material for the lithium-containing phosphate and the at least one surface-treated carbon material is a method for dispersing and mixing the at least one surface-treated carbon material into a solution having dissolved into a solvent a lithium ion (Li^+), a phosphate ion (PO_4^{3-}), and a metal ion other than from lithium.

13. The process for producing composite particles according to Claim 12, wherein the solvent is water, alcohol, or a mixed solvent of water and alcohol.

14. The process for producing composite particles according to Claim 12 or 13, wherein a method using a pressured and heated solvent is used for the method comprising: dispersing the at least one surface-treated carbon material into the solution; mixing the solution; and then heating the solution to form the composite particles comprising: the at least one surface-treated carbon material; and the lithium-containing phosphate precursor and/or the lithium-containing phosphate.

15. The process for producing composite particles according to any one of Claims 6 to 14, wherein the fourth heating step comprises heating the composite particles of the third step under an inert atmosphere or reducing atmosphere *in vacuo* to volatilize an oxygen-containing functional group on a surface of the at least one surface-treated carbon material or to decompose a surfactant or a polymer dispersant on the surface.

16. Electrode material for a lithium-ion secondary battery, comprising 60 to 95% by mass of the composite particles according to any one of Claims 1 to 5 and the remainder consisting of a conduction aid and a binder.

17. A lithium-ion secondary battery comprising:

- a positive electrode produced using the electrode material according to Claim 16;

- a negative electrode;

- an electrolytic solution; and

- a separator that electrically insulates the positive electrode from the negative electrode and retains the electrolytic solution.