

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
23 December 2010 (23.12.2010)

PCT

(10) International Publication Number  
**WO 2010/148081 A2**

(51) International Patent Classification:  
C07D 307/89 (2006.01)

(21) International Application Number:  
PCT/US2010/038813

(22) International Filing Date:  
16 June 2010 (16.06.2010)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
61/187,444 16 June 2009 (16.06.2009) US

(71) Applicant (for all designated States except US):  
**DRATHS CORPORATION** [US/US]; 2367 Science  
Parkway, Suite 2, Okemos, MI 48864-1667 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **FROST, John, W.**  
[US/US]; 1621 Dobie Circle, Okemos, MI 48864 (US).  
**MIERMONT, Adeline** [FR/US]; 9 Meadow Lane Drive,  
Delta, OH 43515 (US). **SCHWEITZER, Dirk** [DE/US];  
4221 Southport Circle, Apt. 3C, Okemos, MI 48864 (US).  
**BUI, Vu** [US/US]; 5404 Okemos Rd., East Lansing, MI  
48823 (US).

(74) Agents: **SIMS, Norman, L.** et al.; Dobrusin & Thennisch  
PC, 29 W. Lawrence Street, Suite 210, Pontiac, MI 48342  
(US).

(81) Designated States (unless otherwise indicated, for every  
kind of national protection available): AE, AG, AL, AM,  
AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ,  
CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO,  
DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT,  
HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP,  
KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD,  
ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI,  
NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD,  
SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR,  
TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every  
kind of regional protection available): ARIPO (BW, GH,  
GM, KE, LR, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG,  
ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ,  
TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK,  
EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU,  
LV, MC, MK, MT, NL, NO, PL, PT, RO, SE, SI, SK,  
SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,  
GW, ML, MR, NE, SN, TD, TG).

Published:

— without international search report and to be republished  
upon receipt of that report (Rule 48.2(g))



WO 2010/148081 A2

(54) Title: NOVEL TEREPHTHALIC AND TRIMELLITIC BASED ACIDS AND CARBOXYLATE DERIVATIVES THERE-  
OF

(57) Abstract: The present invention relates to novel substituted and unsubstituted terephthalic acid and carboxylate derivatives and products prepared therefrom having a significant renewable content. The invention also relates to processes for preparing substituted and unsubstituted terephthalic and carboxylate derivatives thereof wherein a portion of the starting materials utilized is derived from renewable resources. The invention also relates to novel cyclohexene based intermediates prepared in these processes and to conversion of these intermediates to substituted and unsubstituted cyclohexane-1,4-dicarboxylates and carboxylate derivatives thereof and novel forms of the resulting products having renewable content. The invention also relates to products prepared from substituted and unsubstituted terephthalic acid and carboxylate derivatives thereof derived from starting materials derived from renewable resources.

**NOVEL TEREPHTHALIC AND TRIMELLITIC BASED ACIDS AND  
CARBOXYLATE DERIVATIVES THEREOF**

**CROSS-REFERENCE TO RELATED APPLICATIONS**

**[0001]** This application claims priority from United States Provisional Application Serial Number 61/187,444 filed June 16, 2009 titled "NOVEL TEREPHTHALIC AND TRIMELLITIC BASED ACIDS AND CARBOXYLATE DERIVATIVES THEREOF" incorporated herein by reference.

**FIELD OF INVENTION**

**[0002]** The present invention relates to novel benzene 1,4-dicarboxylate compounds (terephthalic acid and carboxylate derivatives thereof) and products prepared therefrom having a significant renewable content. The invention also relates to processes for preparing benzene 1,4-dicarboxylate compounds (terephthalic and carboxylate derivatives thereof) wherein a portion of the starting materials utilized is derived from renewable resources. The invention also relates to novel cyclohexene 1,4-dicarboxylate based intermediates prepared in these processes and to conversion of these intermediates to substituted and unsubstituted cyclohexane 1,4-dicarboxylates and derivatives thereof. The invention also relates to products prepared from such compounds derived from starting materials themselves derived from renewable resources.

**BACKGROUND OF THE INVENTION**

**[0003]** Terephthalic acid and trimellitic acids comprise a benzene ring with carboxylate groups at the 1,4 and the 1,2,4 positions respectively. These acids and their carboxylate derivatives are useful in a variety of commercial products such as polyesters and plasticizers. At the present time these acids and their carboxylate derivatives are synthesized commercially from petroleum based starting materials, such as *p*-xylene. Due to volatility in hydrocarbon markets and the limited amount of hydrocarbons available for future use it is desirable that methods of preparing such important compounds from renewable resources be developed.

**[0004]** Some large agricultural crops such as corn and sugar cane and the by-products associated with their harvesting and processing which cannot be used as a food source contain starch or cellulosic materials which can be broken down to simple sugars

which can then be converted to useful products. See, for instance, Frost et. al. US 5,629,181; Frost US 5,168,056; Frost et. al. US 5,272,073; Frost US Patent publication 2007/0178571, and Frost et. al. US 5,616,496, incorporated herein by reference.

**[0005]** There is a need for substituted and unsubstituted benzene 1,4-dicarboxylate compounds (terephthalic acid and carboxylate derivatives thereof) and processes for preparing such compounds from starting materials that can be made or derived from renewable resources, such as, for example, biomass or simple sugars which can then be derived from biomass.

## SUMMARY OF THE INVENTION

**[0006]** The present invention provides a method for preparing compounds containing at least one benzene ring and carboxylate derivatives at the 1 and 4 positions of the benzene ring, and optionally at the 2 position of the benzene ring. Such compounds include substituted and unsubstituted terephthalic acid and carboxylate derivatives thereof. Substituted terephthalates include compounds having a benzene ring with carboxylic acid groups or carboxylate derivatives thereof at the 1 and 4 position wherein the benzene ring may be substituted on other carbons. In one preferred embodiment, the benzene ring is substituted at the 2 position. One preferred substituent at the 2 position is a carboxylic acid or carboxylate derivative thereof. Another preferred group of substituents comprise a phenyl, an alkyl or a halogen group. Included in more preferred substituted terephthalates are trimellitic acid and phenylterephthalic acid. As used herein, the term carboxylate refers to any group which contains a carbonyl group (C=O) wherein the carbonyl group is bonded to an anion so as to form a salt, to a heteroatom, such as oxygen, nitrogen, sulfur or one or more halogens. The heteroatom may be further bonded by a covalent bond to one or more other groups, such as hydrogen or hydrocarbyl groups which may optionally contain one or more heteroatoms, or may be electronically bonded to a cation to form a salt. Alternatively, the carboxylate derivative can be a nitrile. Preferably, the carboxylate is an acyl halide, carboxylic acid, amide, ester, thiol ester, mercaptocarbonyl, anhydride, nitrile, salt with an anion or salt with a cation. Preferred cations include alkali metals and unsubstituted and hydrocarbyl substituted ammonium ions. The term carboxylate as used herein includes the carboxylic acid form of carboxylate derivatives. The term carboxylic acid or acid is used herein in contexts wherein the acid form is distinguished from other carboxylate forms. The particular use hereinafter is clear from the context. The method comprises: contacting one or more muconic acid dienes or carboxylate derivatives thereof with one or more dienophiles under conditions such that the one or more muconic acids or carboxylate derivatives thereof and one or more dienophiles form one or more cyclohexene ring containing compounds; and contacting the cyclohexene ring containing compounds with one or more dehydrogenation catalysts, optionally in the presence of one or more oxidants, under conditions such that compounds containing an aromatic ring with carboxylate derivatives at the 1 and 4 position, and optionally the 2 position, are prepared. Where there are carboxylate derivatives at the 1 and 4 position, the compounds are referred to herein as terephthalic acid or carboxylate derivatives thereof. Where the final compounds additionally contain a carboxylate at the 2 position of the aromatic ring in addition to the carboxylate derivatives at the 1 and 4 positions, the compounds are referred to herein as a trimellitic acids or carboxylate derivatives thereof. In a

preferred embodiment, the carboxylate derivatives are esters of the carboxylic acids, preferably hydrocarbyl carboxylates. The one or more muconic acids, or carboxylate derivatives thereof, and the one or more dienophiles may be contacted neat or in the presence of a solvent. In another preferred embodiment, the one or more muconic acids or carboxylate derivatives thereof are contacted with one or more dienophiles at a temperature of about 130 °C to about 170 °C. In yet another embodiment, the one or more muconic acids or carboxylate derivatives thereof and the one or more dienophiles are contacted in the presence of one or more compounds which inhibit the polymerization of compounds containing unsaturated groups. In yet another embodiment, the one or more muconic acids or carboxylate derivatives thereof and the one or more dienophiles are contacted in the presence of a Diels-Alder cycloaddition catalyst (Lewis acid). In yet another embodiment, the one or more muconic acids or carboxylate derivatives thereof and the one or more dienophiles are contacted in the presence of an isomerization catalyst, which interconverts the different muconic acids or carboxylate derivatives thereof to the *trans,trans* isomer.

**[0007]** Preferably, the one or more muconic acids, or carboxylate derivatives thereof, reacted with the dienophile are in the *trans,trans* isomeric arrangement. In a preferred embodiment, the starting muconic acid is *cis,cis* muconic acid prepared by microbial synthesis. The product of known microbial synthesis is the *cis,cis* muconic acid isomer. Preferably, the muconic acid or the carboxylate derivatives used in the process of reacting one or more muconic acids or carboxylate esters thereof with one or more dienophiles are prepared by isomerization of *cis,cis* muconic acid or *cis,trans* muconic acid. In a preferred embodiment, the one or more muconic acids or carboxylate derivatives thereof are prepared from one or more of *cis,trans* and *cis,cis* muconic acid or carboxylate derivatives thereof by contacting one or more of *cis,cis* and *cis,trans* muconic acid or carboxylate derivatives thereof with one or more isomerization catalysts, ultraviolet radiation sources or both, in a solvent under conditions such that the *cis,cis* and/or *cis,trans* muconic acid or carboxylate derivatives thereof isomerize to the *trans,trans* muconic acid or carboxylate derivatives thereof. In another preferred embodiment, the *cis,cis* muconic acid is converted to *trans,trans* muconic acid by the process comprising: a) exposing *cis,cis* muconic acid in water to elevated temperatures, above room temperature (about 23°C) to form *cis,trans* muconic acid; b) cooling the muconic acid in water to a temperature at which the *cis,trans* isomer precipitates from water; c) recovering the *cis,trans* muconic acid; and d) contacting the *cis,trans* muconic acid and one or more isomerization catalysts, ultraviolet radiation sources or both, under conditions such that the *cis,trans* muconic acid isomerizes to *trans,trans* muconic acid.

**[0008]** In one preferred embodiment, an ester form of muconic acid is reacted with one or more dienophiles. Preferably, the ester is in the *trans,trans* isomeric form. The

sequence of isomerization and esterification of muconic acid is not critical. Thus, the esterified form of muconic acid may be subjected to isomerization after esterification. Preferably, muconic acid is isomerized to the *trans,trans* isomer before being esterified. The esterification step can be performed by contacting one or more muconic acids with one or more esterifying agents under conditions that one or more dihydrocarbyl muconates are formed. The one or more esterifying agents can be any compounds which are capable, under reasonable reaction conditions, of replacing the hydrogens on the carboxylic acids located on the one or more muconic acids with hydrocarbyl groups wherein the resulting esters are capable of reacting with the dienophiles as described hereinbefore. Preferred esterification agents are hydrocarbon based compounds containing hydroxyl groups. More preferred esterifying agents include alkanols, benzyl alcohol or phenol. In one preferred embodiment, the *trans,trans* esters of muconic acid are prepared by a) contacting *cis,cis* muconic acid and one or more isomerization catalysts, ultraviolet radiation sources, or both, in a solvent under conditions such that the *cis,cis* muconic acid isomerizes to the *trans,trans* muconic acid; b) recovering the *trans,trans* muconic acid; and c) contacting the *trans,trans* muconic acid with an esterifying agent under conditions that *trans,trans* dihydrocarbyl muconate is formed. In another embodiment, the one or more esters of muconic acid contacted with the dienophile are prepared by: a) exposing *cis,cis* muconic acid to elevated temperatures in water; b) cooling the muconic acid in water to a temperature at which the *cis,trans* isomer precipitates from water; c) recovering the *cis,trans* muconic acid; and d) contacting the *cis,trans* muconic acid and one or more isomerization catalysts, ultraviolet radiation sources or both, in a solvent under conditions such that the *cis,trans* muconic acid isomerizes to the *trans,trans* muconic acid; e) recovering the *trans,trans* muconic acid; and f) contacting the *trans,trans* muconic acid with an esterifying agent in the presence of one or more acids under conditions that *trans,trans* dihydrocarbyl muconate is formed. In another embodiment, the invention is a method for preparing *trans,trans* dihydrocarbyl muconate comprising: a) contacting *cis,cis* muconic acid with an esterifying agent in the presence of an acid under conditions that one or more of *cis,cis* and *cis,trans* dihydrocarbyl muconate is formed; b) recovering the one or more of *cis,cis* and *cis,trans* dihydrocarbyl muconate; and c) contacting the one or more of *cis,cis* and *cis,trans* dihydrocarbyl muconate and one or more isomerization catalysts, ultraviolet radiation sources or both, in a solvent for a period of time such that the *cis,cis* and *cis,trans* dihydrocarbyl muconate isomerize to the *trans,trans* dihydrocarbyl muconate.

**[0009]** In one preferred embodiment, the invention is a method for preparing a substituted or unsubstituted benzene 1,4 dicarboxylate (terephthalic acid or terephthalate carboxylate ester based compound) comprising a) contacting *cis,cis* muconic acid and iodine in the presence of ultraviolet light in a protic or aprotic solvent at a temperature for a period

of time such that the *cis,cis* muconic acid isomerizes to the *trans,trans* muconic acid; b) recovering the *trans,trans* muconic acid; and c) contacting the *trans,trans* muconic acid with one or more alkanols in the presence of one or more strong acids under conditions that one or more *trans,trans* dialkyl muconates are formed; d) contacting the one or more dialkyl muconates with one or more dienophiles at a temperature of about 130 °C to about 170 °C under conditions such that the dialkyl muconates and dienophiles form one or more cyclohexene ring containing compounds; and contacting the one or more cyclohexene ring containing compounds with one or more dehydrogenation catalysts, optionally in the presence of one or more oxidants, under conditions such that one or more compounds containing a benzene ring with hydrocarbyl carboxylate esters or carboxylic acid groups at the 1 and 4 position are prepared.

**[0010]** In one embodiment, the isomerization of the one or more dihydrocarbyl esters of muconic acid to the *trans,trans* isomer can be performed in situ in the same reaction mixture as the reaction of the esters with the dienophiles. In this embodiment, one or more compounds containing a benzene ring with hydrocarbyl carboxylates esters at the 1 and 4 position (one or more terephthalate ester based compounds) are prepared by the process comprising contacting one or more of *cis,cis* or *cis,trans* muconic acid esters with one or more dienophiles at elevated temperatures under conditions such that the one or more muconic acid esters and the one or more dienophiles form one or more compounds with a cyclohexene ring having carboxylate ester groups at the 1 and 4 position; and contacting the one or more cyclohexene ring containing compounds with one or more dehydrogenation catalysts, optionally in the presence of one or more oxidants, under conditions such that one or more compounds containing a benzene ring with hydrocarbyl carboxylate esters at the 1 and 4 position are prepared. This process is preferably conducted in a solvent, preferably a nonpolar aprotic solvent. Preferably this reaction is carried out at a temperature of about 130°C to about 170 °C. In one embodiment, the isomerization of the one or more isomers of muconic acid to the *trans,trans* isomer can be performed in situ in the same reaction mixture as the reaction of the muconic acids with the dienophiles. In this embodiment, one or more compounds containing a benzene ring with hydrocarbyl carboxylates esters at the 1 and 4 position (one or more terephthalate ester based compounds) are prepared by the process comprising contacting one or more of *cis,cis* or *cis,trans* muconic acid with one or more dienophiles at elevated temperatures under conditions such that the one or more muconic acid isomers and the one or more dienophiles form one or more compounds with a cyclohexene ring having carboxylic acid groups at the 1 and 4 position; and contacting the one or more cyclohexene ring containing compounds with one or more dehydrogenation catalysts, optionally in the presence of one or more oxidants, under conditions such that one or more

compounds containing a benzene ring with carboxylic acid groups at the 1 and 4 position are prepared and/or reacted with an esterifying agent under conditions such that carboxylic acid groups are converted to hydrocarbyl carboxylate groups. The hydrogenation and esterification steps may be performed in either sequence.

**[0011]** In one embodiment, the one or more starting dienophiles is one or more alkene based compounds. In this embodiment, the reaction of the one or more muconic acids, or carboxylate derivatives thereof, with the one or more alkene based compounds comprises contacting one or more muconic acids or carboxylate derivatives thereof with one or more alkene based compounds under conditions such that the one or more muconic acids, or carboxylate derivatives thereof, and the one or more alkene compounds form one or more compounds containing a cyclohexene ring having carboxylate groups at the 1 and 4 position.

**[0012]** In another embodiment, the invention is a method for preparing one or more trimellitate based compounds comprising contacting one or more muconic acids, or carboxylate derivatives thereof, with one or more alkynes, having a carboxylate ester bound to one carbon of the triple bond, under conditions such that the one or more muconic acids, or carboxylate derivatives thereof, and one or more alkynes form one or more trimellitate based acids, or carboxylate derivatives thereof. In this embodiment, an oxidant, such as oxygen, present in the reaction mixture affects oxidation to the aromatic compound, so no separate dehydrogenation step is required.

**[0013]** In another embodiment the invention relates to the products prepared by the processes described herein. In those embodiments wherein the starting muconic acid is prepared from biomass, the resulting products of the process contain a significant percentage of carbon derived from renewable resources. Such products are unique because the products contain a detectable trace or amount of carbon 14, and preferably up to about 1 part per trillion, as determined according to ASTM D6866-08. The resulting products preferably contain 6 or greater carbons, more preferably 8 or greater carbons, derived from renewable resources, such as biomass, preferably by microbial synthesis. The resulting products are prepared from renewable resources prepared by microbial synthesis. In embodiments wherein the products are utilized to prepare polymers, the monomer units preferably contain 6 or greater carbons, and more preferably 8 or greater carbons, derived from renewable resources, such as biomass.

## DESCRIPTION OF THE PREFERRED EMBODIMENT

**[0014]** The following discussion applies to the teachings as a whole. Unless otherwise stated, all ranges include both endpoints and all numbers between the endpoints. The use of “about” or “approximately” in connection with a range applies to both ends of the range. Thus, “about 20 to 30” is intended to cover “about 20 to about 30”, inclusive of at least the specified endpoints.

**[0015]** The disclosures of all articles and references, including patent applications and publications, are incorporated by reference for all purposes. References to the term “consisting essentially of” to describe a combination shall include the elements, ingredients, components or steps identified, and such other elements ingredients, components or steps that do not materially affect the basic and novel characteristics of the combination. The use of the terms “comprising” or “including” to describe combinations of elements, ingredients, components or steps herein also contemplates embodiments that consist essentially of the elements, ingredients, components or steps.

**[0016]** Plural elements, ingredients, components or steps can be provided by a single integrated element, ingredient, component or step. Alternatively, a single integrated element, ingredient, component or step might be divided into separate plural elements, ingredients, components or steps. The disclosure of “a” or “one” to describe an element, ingredient, component or step is not intended to foreclose additional elements, ingredients, components or steps. Likewise, any reference to “first” or “second” items is not intended to foreclose additional items (e.g., third, fourth, or more items); such additional items are also contemplated, unless otherwise stated. All references herein to elements or metals belonging to a certain Group refer to the Periodic Table of the Elements published and copyrighted by CRC Press, Inc., 1989. Any reference to the Group or Groups shall be to the Group or Groups as reflected in this Periodic Table of the Elements using the IUPAC system for numbering groups. Monomer units as used herein refer to the repeating unit of a polymeric structure. Derived from means prepared from or prepared using. Hydrocarbyl as used herein refers to a group containing one or more carbon atom backbones and hydrogen atoms, which may optionally contain one or more heteroatoms. Where the hydrocarbyl group contains heteroatoms, the heteroatoms may form one or more functional groups well known to one skilled in the art. Hydrocarbyl groups may contain cycloaliphatic, aliphatic, aromatic or any combination of such segments. The aliphatic segments can be straight or branched. The aliphatic and cycloaliphatic segments may include one or more double and/or triple bonds. Included in hydrocarbyl groups are alkyl, alkenyl, alkynyl, aryl, cycloalkyl, cycloalkenyl, alkaryl and aralkyl groups. Cycloaliphatic groups may contain both cyclic portions and noncyclic portions.

**[0017]** The present invention pertains generally to the synthesis of monomeric materials, polymeric materials or both. In one aspect, the invention is directed at synthesis that uses as a source of at least one starting material a biomass-derived product. For example, one preferred approach that is addressed herein pertains to the use of at least one dicarboxylic acid (e.g., muconic acid) or carboxylate derivative thereof derived from microbial synthesis. Examples of microbial synthesis processes taught in the art include, without limitation, Frost et. al. U.S. Patent No. 5,616,496, incorporated herein by reference.

**[0018]** Another aspect of the invention pertains to the isomerization of at least one dicarboxylic acid (e.g., muconic acid) or carboxylate derivative thereof. More specifically, according to this aspect, *cis,cis* muconic acid or an ester thereof, is isomerized to a *trans,trans* configuration. The isomerization may be pursued under an approach that includes one or more of a step of esterifying *cis,cis* muconic acid and then isomerizing the resulting ester, a step of isomerizing *cis,cis* muconic acid and then esterifying the resulting isomer, or a step of in situ isomerization (pursuant to which *trans,trans* muconic acid is reacted in the presence of one or more dieneophiles).

**[0019]** Another aspect of the invention relates to the formation of one or more cyclohexenes from one or more muconic acids or carboxylate derivatives thereof. For example, pursuant to this aspect a *trans,trans* muconic acid or a carboxylate derivative thereof (e.g., the *trans,trans* muconic acid or a carboxylate derivative thereof described above, optionally derived from biomass) may be reacted to form a cyclohexene having a carboxylate derivatives located in at least two positions, such as the 1 and 4 positions, of the cyclohexene rings.

**[0020]** Yet another aspect of the invention relates to the formation of one or more carboxylate derivatives of the above described one or more cyclohexene ring containing compounds. In particular, the teachings herein describe reactions for hydrogenating or dehydrogenating one or more cyclohexene containing compounds (e.g., derived from one or more muconic acids or carboxylate derivatives thereof) to form cyclohexene hydrogenation products (e.g. substituted cyclohexane products) or cyclohexene dehydrogenation products thereof (e.g. substituted benzene products). The dehydrogenation products are one or more products selected from substituted or unsubstituted terephthalic acid or carboxylate derivatives thereof.

**[0021]** Yet another aspect of the invention herein pertains to unique products that have the characteristics realized from the reactions described, and use of these products in subsequent applications.

**[0022]** The processes of the invention include the preparation of compounds having at least one benzene ring and carboxylates at the 1 and 4 position of the benzene ring and

optionally at the 2 position of the benzene ring. In preferred embodiments these products can be referred to as substituted or unsubstituted terephthalic acid or carboxylate derivatives thereof. The process of the invention requires reaction of one or more muconic acids or carboxylate derivatives thereof with one or more dienophiles. Several other process steps may be included with this step. The following steps may be included in the preparation of the desired products: conversion of sugars, carbohydrates or cellulosic matter contained in biomass to muconic acid, typically the *cis,cis* isomer of muconic acid; isomerization of *cis,cis* and/or *cis,trans* muconic acid, or an ester thereof, to the *trans,trans* isomer; esterification of the one or more muconic acids to form one or more dihydrocarbyl esters of muconic acid; conversion of the one or more carboxylic acids or carboxylate esters thereof to another carboxylate derivative form; formation of one or more cyclohexene or benzene ring containing compounds having carboxylates at the 1 and 4, and optionally the 2 position, of the rings; dehydrogenation of the one or more cyclohexene compounds to form benzene ring containing compounds or hydrogenation of the one or more cyclohexene compounds to form cyclohexane ring containing compounds; and esterification of one or more benzene, cyclohexene, cyclohexane having carboxylate groups at the 1,4 and optionally 2, positions.

**[0023]** Muconic acid can be prepared from biomass by any means known in the art, including the process described in Frost et. al US Patent 5,616,496, incorporated herein by reference. The resulting product is typically recovered by filtration techniques in the form of the *cis,cis* isomer of muconic acid. The *cis,cis* and *cis,trans* isomers of muconic acid do not react with dienophiles and therefore need to be isomerized for use in the reaction with dienophiles as described herein. Other methods of preparing muconic acid are known and muconic acid prepared by these processes can be used as the starting material in the processes of this invention. Preferably, the muconic acid used in the process steps described herein is prepared from biomass and more preferably by a microbial synthesis itself utilizing biomass or compounds derived from biomass such as, for example carbohydrates.

**[0024]** In the embodiment where *cis,cis* and/or *cis,trans* muconic acids are used as the starting materials, they may be used in crude form or in purified form. When used in crude form it is preferred to remove microorganisms used as host cells in the preparation of muconic acid from sugars, starches, cellulosic materials and the like. The microorganisms are removed to prevent their interference with the various synthetic steps performed in the process. The microorganisms may be removed by means well known in the art, such as by filtration. The crude muconic acids may contain proteins, inorganic salts and the like. In certain processing sequences, as described hereinafter, it is preferable to purify the muconic acids. Preferably, purified *cis,cis* and/or *cis,trans* muconic acid are used for these processes: for the in situ isomerization of muconic acid and subsequent reaction with a dienophile in the

same reaction vessel and where the *cis,cis* or *cis,trans* are esterified before isomerization to the *trans,trans* isomeric form.

**[0025]** Crude *cis,cis* and/or *cis,trans* muconic acid can be purified by dissolution in water or organic solvents and subsequent recrystallization from solution. Generally, the crude muconic acid and water or organic solvents need to be heated to dissolve the muconic acid. Cooling to ambient temperature, about 23°C, typically results in precipitation of purified muconic acid. Cooling to less than ambient, down to about 0°C facilitates higher recovery or yields of purified muconic acids. The mixture of crude muconic acid and water or organic solvent is preferably heated to about 50°C or greater to dissolve the muconic acid. The upper limit on heating of the mixture is limited by decomposition of the muconic acid and practicality. Preferred organic solvents for this process step are polar aprotic solvents, with alkanols being more preferred. Alkanols useful as solvents comprise straight and branched hydrocarbon chain further containing compounds further one or more, preferably one, hydroxyl groups. Preferred alkanols are C<sub>1-6</sub> straight and branched chain alkanols, with methanol, ethanol, and isopropanol most preferred. After precipitation of the purified muconic acid, the solvent is decanted off and the solid muconic acid is further dried, that is the residual solvent is removed by evaporation under reduced pressure. Preferably, the feedstock for this process is crude *cis,cis* muconic acid.

**[0026]** *Cis,cis* muconic acid can be isomerized directly to *trans,trans* muconic acid or isomerized to *cis,trans* muconic acid and then the *cis,trans* muconic acid can be isomerized to *trans,trans* muconic acid. Mixtures of *cis,cis* and *cis,trans* muconic acid can be isomerized to *trans,trans* muconic acid. Either muconic acid, or a carboxylate ester thereof, may be reacted with dienophiles to prepare the desired compounds. When an ester is used, the muconic acid can be isomerized or esterified first and then the other process step performed. Thus, in the isomerization step or steps performed to transform *cis,cis* muconate to the *trans,trans* muconate, the starting material can be in the acid or the carboxylate ester form.

**[0027]** In one embodiment, the *cis,cis* muconic acid, or ester thereof, may be converted to the *cis,trans* isomer in a discrete step. In such discrete step, the *cis,cis* muconic acid or ester thereof is dissolved or dispersed in water and exposed to elevated temperatures to convert the *cis,cis* muconic acid, or ester thereof, to the *cis,trans* isomer. Preferably, a sufficient amount of base is added such that the pH of the reaction mixture is about 4 or greater and more preferably about 4.5 or greater. Preferably, a sufficient amount of base is added such that the pH of the reaction mixture is about 6 or less and more preferably about 5.5 or less. Temperatures which may be used for this process steps include any temperature at which the isomerization proceeds. In one embodiment, the process is performed under reflux conditions. This process step is performed as long as required to convert the desired amount

of *cis,cis* muconic acid or ester thereof to the *cis,trans* isomer. Preferably, this process step is performed for about 10 minutes or greater. Preferably, this process step is performed for about 60 minutes or less and more preferably about 30 minutes or less. The pH of the reaction mixture, the reaction temperature and the reaction time are interdependent. Within the preferred ranges recited, as the pH and temperature are increased the required reaction times are decreased. Preferably, the temperature, pH and reaction time are chosen to minimize the time required to perform the isomerization, while avoiding unwanted reactions or impractical operations.


**[0028]** In one embodiment, the starting muconic acid or carboxylate derivative thereof, are contacted with one or more isomerization catalysts, a source of ultraviolet radiation or both, in solvent to form the *trans,trans* muconic acid. The starting muconic acid or carboxylate derivative thereof can be in the *cis,cis*, *cis,trans* or any combination of both isomeric forms. Any source of ultraviolet radiation which generates a radical under the conditions of the process may be used. Among preferred sources of ultraviolet radiation are light bulbs, xenon lamps, medium pressure mercury lamps or electrodeless lamps, natural light and the like. To enhance radical formation, where the radical former is ultraviolet radiation, a photoinitiator may be used in combination with the ultraviolet radiation source. Any commonly known photoinitiator useful with olefinically unsaturated compounds may be used in the processes described herein. Included in photoinitiators useful in this process are those disclosed in Baikerikar et. al. US Patent Publication 2007/0151178 paragraphs 0029, 0030 and 0032 incorporated herein by reference. Among preferred photoinitiators are alpha aminoketones, alpha hydroxyketone, phosphine oxides, phenylglyoxalates, thioanthonnes, benzophenones, benzoin ethers, oxime esters, amine synergists, maleimides, mixtures thereof and the like. Isomerization catalysts include any compounds which form radicals in unsaturated compounds when exposed to the reaction conditions, preferably under thermal conditions. Any isomerization catalyst with a suitable half life at the reaction temperatures of this process step can be used. Among preferred isomerization catalysts are compounds contained in the following classes: elemental halogens; dialkyl peroxides, such as di-tertiary-butyl peroxide, 2,5-dimethyl-2,5-di-tertiary-butyl-peroxyhexane, di-cumyl peroxide; alkyl peroxides, such as, tertiary-butyl hydroperoxide, tertiary-octyl hydroperoxide, cumene hydroperoxide; aroyl peroxides, such as benzoyl peroxide; peroxy esters, such as tertiary-butyl peroxy pivalate, tertiary-butyl perbenzoate; and azo compounds, such as azo-bis-isobutyronitrile, and the like. More preferred compounds useful as isomerization catalysts are elemental halogens; with bromine, chlorine and iodine even more preferred; and iodine most preferred. Alternatively, the isomerization catalyst can be a hydrogenation catalyst as described hereinafter. Among preferred hydrogenation catalysts useful as an isomerization

catalyst are nickel, platinum and palladium in homogeneous and heterogeneous forms. More preferred are heterogeneous catalysts, with carbon as the most preferred support. A most preferred catalyst for this purpose is palladium on carbon. The amount of isomerization catalyst used is that amount which catalyzes the isomerization of the muconic acid or a carboxylate derivative thereof. If too little is used the reaction does not proceed at a practical rate. If too much is used the isomerization catalyst may add to one of the double bonds of the muconic acid or carboxylate derivative thereof. The isomerization catalysts are preferably present in the reaction mixture in an amount of about 0.0001 equivalents or greater based on the equivalents of muconic acid or carboxylate derivatives thereof, more preferably about 0.001 equivalents or greater and most preferably about 0.005 equivalents or greater. The isomerization catalysts are preferably present in the reaction mixture in an amount of about 1.0 equivalent or less based on the equivalents of the muconic acid or carboxylate esters thereof, more preferably about 0.1 equivalents or less and about 0.01 equivalents or less. Any temperature at which isomerization of the muconic acid or ester thereof to the *trans,trans* isomeric form occurs may be used. Preferably, the temperature is about 23 °C or greater and most preferably about 60 °C or greater. Preferably, the temperature is about 150 °C or less, more preferably about 120 °C or less and most preferably about 100 °C or less. This process step is preferably performed at ambient temperatures or elevated temperatures. The limiting factor is solubility of the starting muconic acid or carboxylate esters in the solvents. Preferably, the solvent is saturated with muconic acid or one or more carboxylate derivatives thereof. The use of elevated temperatures renders the process more efficient by allowing a greater amount of starting muconic acid or carboxylate esters thereof to contact the isomerization catalyst. Preferably this process step is performed in a solvent. Any solvent which dissolves or disperses the reactants and which does not interfere in the desired reaction may be used for this step. Preferably, the solvent is polar and may be protic or aprotic. Protic in regard to a solvent means the solvent has a proton which freely dissociates, such as an active hydrogen. Aprotic in regard to a solvent means the solvent does not have a proton which freely dissociates. Among preferred solvents are cyclic ethers, acyclic ethers, acetonitrile, dimethyl sulphoxide, *N*-methylpyrrolidone, ketones, alkyl acetates, alkanols or dimethylformamide and the like. More preferred solvents include C<sub>1-4</sub> alkanols, cyclic ethers, acyclic ethers, ethyl acetate, acetone and acetonitrile. This process step is performed as long as required to convert the desired amount of *cis,cis* and/or *cis,trans* muconic acid or ester thereof to the *trans,trans* isomer. In one preferred embodiment wherein *cis,trans* muconic acid is the starting material, the solvent used is aprotic and is more preferably an aprotic solvent from which *trans,trans* muconic acid precipitates at ambient temperatures. In this embodiment, the preferred solvents are cyclic ethers, alkyl acetates, and nitriles; with

tetrahydrofuran, alkyl substituted tetrahydrofuran, dioxane, and acetonitrile more preferred; and tetrahydrofuran and methyl tetrahydrofuran most preferred. In a preferred embodiment, the starting muconic acid or carboxylate derivatives thereof are contacted with an isomerization catalyst and a source of ultraviolet radiation at elevated temperatures. The *trans,trans* muconic acid or carboxylate derivatives thereof are insoluble in the preferred solvents and precipitate from the reaction mixture. It can be recovered by simple removal, for instance by decantation, of the solvent from the reaction mixture. Preferably, the yield of *trans,trans* muconic acid or ester thereof is about 80 percent by weight or greater based on the weight of the starting muconic acid or ester thereof, more preferably about 90 percent by weight or greater and most preferably about 99 percent by weight or greater. Preferably, the *trans,trans* muconic acid recovered exhibits a purity of about 99 percent by weight or greater. Preferably the *trans,trans* muconic acid exhibits a detectable trace of carbon 14 number and more preferably up to about 1 part per trillion of carbon 14. In a preferred embodiment, the recovered *trans,trans* muconic acid or ester thereof has about 6 carbon atoms or greater derived from renewable resources such as biomass.

**[0029]** In the embodiment wherein muconic acid, or an ester thereof, is in the *cis,trans* isomeric arrangement, a preferred means of converting the *cis,trans* muconic acid, or ester thereof, to the *trans,trans* muconic acid or an ester thereof comprises contacting the *cis,trans* muconic acid, or an ester thereof, with an isomerization catalyst in an organic solvent. This is because *cis,trans* muconic acid or an ester thereof exhibit a higher solubility in organic solvents than the *cis,cis* and *trans,trans* isomers *cis,cis*.

**[0030]** Muconic acid and the esters of muconic acid can be represented by the following formulas



wherein R<sup>1</sup> is independently in each occurrence hydrogen, a hydrocarbyl group optionally containing a heteroatom containing functional group wherein the hydrocarbyl group does not interfere in the formation of a cyclohexene compound.

**[0031]** Muconic acid is esterified by contact with an esterifying agent under conditions that a hydrocarbyl group replaces the hydrogen on the oxygen of the carboxylic acid. The esterifying agent can be any compound which under the reaction conditions forms

an ester on the carboxyxy groups (C(O)<sub>2</sub>) of the muconic acid. The esterification agent can be any hydroxyl containing compound which reacts to form an ester under reaction conditions. Preferred esterification agents include hydrocarbon compounds having hydroxyl groups bonded thereto. More preferred esterifying agents include compounds corresponding to the formula R<sup>1</sup>OH wherein R<sup>1</sup> is a hydrocarbyl group, optionally containing a heteroatom containing functional group, wherein the hydrocarbyl group does not interfere in the formation of the cyclohexene compound. Preferred classes of esterifying agents include alkanols, aryl alcohols and aryl substituted alkanols. Preferred esterifying agents include alkanols, with C<sub>1-10</sub> alkanols being more preferred and methanol being most preferred. Among preferred aryl substituted alkanols is benzyl alcohol. Among preferred aryl alcohols are phenol and the various isomers of dihydroxy benzene. In another embodiment, the esterifying agent can be a polyglycol having one or more hydroxyl groups and one or more ether groups.


**[0032]** Muconic acid in one or more of its isomeric forms is contacted with one or more esterifying agents in the presence of one or more acids. The acids utilized can be any acids which facilitate the replacement of the hydroxyl group on the carboxylic acids with hydrocarbyloxy groups. Preferred acids are Bronsted acids. Bronsted acids are acids containing a protonic hydrogen that disassociates in solution. The acids are preferably strong acids. Strong acids as used herein mean acids with a pKa of lower than about 0. In a more preferred embodiment, the acids are strong mineral acids. Preferred strong mineral acids include sulfuric acid, nitric acid, phosphoric acid and hydrochloric acid, with sulfuric acid being most preferred. The acids are present in a sufficient amount to facilitate the esterification reaction. Where the esterification agent is in the liquid state no solvent is required. If the esterification agent is a solid or cannot function as a solvent, a solvent may be utilized. Preferred solvents are polar aprotic solvents as described hereinbefore which solubilize the muconic acid. More preferred solvents are cyclic and acyclic ethers, with cyclic ethers, such as tetrahydrofuran, more preferred. The esterification agent is preferably present in a sufficient amount to convert substantially all of the muconic acid to the carboxylate ester form. In a more preferred embodiment, the esterification agent is present in greater than an equivalent ratio based on the equivalents of muconic acid. Preferably, the esterification agent is present in a two to one molar ratio or greater as compared to the muconic acid. Where the esterification agent is also the solvent, the equivalent and molar ratios are much greater. The reaction can take place at any temperature wherein the esterification reaction proceeds at a reasonable rate. Preferably, the temperature is elevated. Elevated temperatures increase the amount of muconic acid which can be dissolved and contacted with the esterification agent. Preferably the temperature of the reaction is about 23 °C or greater, more preferably about 50 °C or greater and most preferably about 120 °C or greater. Preferably the temperature of the

reaction is about 200 °C or less and most preferably about 150 °C or less. The reaction time utilized is chosen to give the desired yield of product. The product recovered may be a monohydrocarbyl muconate, a dihydrocarbyl muconate or a mixture thereof, in a more preferred embodiment the product is substantially dihydrocarbyl muconate. More preferred dihydrocarbyl muconates include dialkyl muconates, more preferably a C<sub>1-10</sub> dialkyl muconates and most preferably dimethyl muconate. The hydrocarbyl groups can be substituted with substituents which do not interfere with the reaction of the dihydrocarbyl muconate with one or more dienophiles. The *trans,trans* muconate esters precipitate from the solution upon cooling. Preferably the reaction mixture is cooled to less than about 40 °C to facilitate precipitation, and preferably to ambient (23 °C) or less. The dihydrocarbyl muconate may be recovered by simple removal of the solvent or excess esterification agent, such as by decantation. Preferably, the yield of dihydrocarbyl muconate is about 70 percent by weight or greater based on the weight of the starting muconic acid. Preferably, dihydrocarbyl muconate recovered exhibits a purity of about 99 percent by weight or greater and most preferably about 99.5 percent by weight or greater. Preferably, the dihydrocarbyl muconate exhibits a detectable amount of carbon 14 number and preferably of up to about one part per trillion. In a preferred embodiment, the recovered dihydrocarbyl muconate has about 6 carbon atoms or greater derived from renewable resources, such as biomass.

**[0033]** In another embodiment, muconic acid may be contacted with an esterifying agent in an aqueous base solution to form a dihydrocarbyl muconate. Preferably this reaction is performed at a temperature of from ambient to (about 23 °C) to about 40 °C. The base can be any base which binds the protons of the carboxyl groups of muconic acid. Preferably, the esterifying agents are present in an equivalent ratio of about 2:1 or greater. The upper limit on the equivalents is practicality. The dihydrocarbyl muconate is recovered by extraction into organic solvent and subsequent evaporation of the extracting organic solvent.

**[0034]** The one or more muconic acids can be converted to other forms of carboxylate derivative groups using reaction sequences known to those skilled in the art. As used herein the term carboxylate derivative refers to any group which contains a carbonyl group (C=O) or a nitrile group ( $\text{---C}\equiv\text{N}$ ), wherein the carbonyl group is bonded to an anion so as to form a salt or to a heteroatom, such as oxygen, nitrogen, sulfur or one or more halogens. The heteroatom may be further bonded by a covalent bond to one or more other groups, such as hydrocarbyl groups which may optionally contain one or more heteroatoms, or may be electronically (electrostatically) bonded to a cation to form a salt. Preferably, the carboxylate derivative is an acyl halide, carboxylic acid, amide, ester, thiol ester, mercaptocarbonyl, an anhydride, a nitrile, a salt with an anion or a salt with a cation. Preferred cations include alkali metal ions and unsubstituted and hydrocarbyl substituted ammonium ions. Preferred

carboxylate derivatives comprise carboxylic acids, acyl halides, amides, anhydrides and esters. More preferred carboxylate derivatives include carboxylic acids and esters, with esters most preferred. Preferred carboxylate derivative groups correspond to the formula



wherein R<sup>1</sup> is independently in each occurrence hydrogen, a hydrocarbyl group optionally containing one or more heteroatoms or a cation;

Z is independently in each occurrence an anion, oxygen, nitrogen, sulfur, a nitrile, or a halogen; and,

b is independently in each occurrence 0, 1 or 2 with the proviso that b is 0 when Z is an anion, halogen or nitrile; 1 when Z is oxygen or sulfur and 2 when Z is nitrogen. R<sup>1</sup> is preferably hydrogen or a C<sub>1-12</sub> hydrocarbyl group which may contain one or more heteroatoms, more preferably hydrogen or a C<sub>1-10</sub> alkyl group which may contain one or more heteroatoms, more preferably hydrogen or a C<sub>1-3</sub> alkyl group and most preferably hydrogen or methyl.

Acyl halides preferably correspond to the formula  $\begin{array}{c} \text{O} \\ || \\ \text{---C---} \\ \text{X} \end{array}$  wherein X is a halogen. X is preferably chlorine or bromine, with chlorine most preferred.

Amides preferably correspond to the formula  $\begin{array}{c} \text{O} \\ || \\ \text{---C---} \\ \text{NH}_{2-c}(\text{R}^1)_c \end{array}$

wherein c is separately in each occurrence 0, 1 or 2, with 0 or 1 being preferred.

Esters preferably correspond to the formula  $\begin{array}{c} \text{O} \\ || \\ \text{---C---} \\ \text{OR}^1 \end{array}$ .


Mercaptocarbonyls preferably correspond to the formula  $\begin{array}{c} \text{O} \\ || \\ \text{---C---} \\ \text{SH} \end{array}$ .

Thiol esters preferably correspond to the formula  $\begin{array}{c} \text{O} \\ || \\ \text{---C---} \\ \text{SR}^1 \end{array}$ .

Anhydrides preferably correspond to the formula  $\begin{array}{c} \text{O} \quad \text{O} \\ || \quad || \\ \text{---C---O---C---} \\ \quad \quad \text{R}^1 \end{array}$ .


Nitriles preferably correspond to the formula:  $\text{---C}\equiv\text{N}$ .

**[0035]** Carboxylate derivatives of muconic acid can be represented by the following formulas




wherein  $R^1$  is as defined hereinbefore. In alternative embodiments, the dihydrocarbyl muconates, especially the *trans,trans* isomeric versions, can be prepared from muconic acid by any known synthetic sequence. For example the dihydrocarbyl muconates may be prepared by the processes disclosed in the following sections of Jerry March, Advanced Organic Chemistry, 2<sup>nd</sup> Edition, Wiley, 1977, at pages 361-367, incorporated herein by reference: section 0-22 alcoholysis of acyl halides, section 0-23 alcoholysis of anhydrides, and section 0-24 esterification of acids. Amide based carboxylate derivatives may be prepared by processes known to those skilled in the art including those disclosed in March, *ibid*, in sections 0-52 amination of alkanes, 0-53 formation of nitriles, 0-54 acylation of amines by acyl halides, and 0-55 acylation of amines by anhydrides at pages 381 to 384, incorporated herein by reference. Acyl halides may be prepared by processes known to those skilled in the art including those disclosed in March, *ibid*, section 0-75 formation of acyl halides from acids at page 398 incorporated herein by reference. Thioesters of muconic acid may be prepared by processes known to those skilled in the art, including those disclosed in March, *ibid*, wherein muconic acid is converted to acyl halides as described above and then converted to a thiol or a thiol ester by the process disclosed in section 0-40 on pages 375 and 376, incorporated herein by reference. Muconic acids may be converted to dianhydride analogs by processes known to those skilled in the art such as disclosed in March, *ibid*, section 0-29 acylation of acids with acyl halides and section 0-30 acylation of acids with acids, at pages 369 and 370 incorporated herein by reference. Muconic acids may be converted to nitriles by processes known to those skilled in the art such as disclosed in March, second edition, section 6-63 at pages 883 and 884 conversion of acid salts to nitriles.

**[0036]** One or more muconic acid or carboxylate derivatives thereof are reacted with one or more dienophiles to prepare a cyclohexene compound having carboxylate groups



in the 1 and 4 positions, and optionally in the 2 position. One or more muconic acids means that a mixture of isomers may be used. In one preferred embodiment the starting muconic acid or carboxylate thereof is in the *trans-trans* isomeric form. Preferably such


carboxylates are in the *trans,trans* isomeric arrangement. In one embodiment, the *cis,cis* and/or *cis,trans* isomers of muconic acid or carboxylate derivatives thereof may be utilized as starting materials. In this embodiment, it is believed that the muconic acid or carboxylate derivatives thereof isomerize in situ before reacting with the dienophile. Carboxylate esters are preferred as starting materials in this reaction. The dienophile can be any compound having unsaturation which reacts with muconic acid or a carboxylate derivative thereof to form a cyclohexene compound. Preferred dienophiles correspond to the following formula



wherein


R<sup>2</sup> is independently in each occurrence hydrogen, halogen, a hydrocarbyl group optionally containing one or more heteroatoms or heteroatom containing functional groups wherein the hydrocarbyl group does not interfere in the formation of the cyclohexene compound; and R<sup>3</sup> is independently in each occurrence hydrogen, halogen or a hydrocarbyl group optionally containing one or more heteroatoms or heteroatom containing functional groups wherein the hydrocarbyl group does not interfere in the formation of the cyclohexene compound; with the proviso that R<sup>2</sup> and R<sup>3</sup> may be combined to form a cyclic ring which may contain heteroatoms. Preferred classes of dienophiles include alkenes, unsaturated cyclic compounds, alkynes, aromatic compounds having unsaturated substituents, and the like. Preferred alkenes useful as dienophiles include any straight or branched aliphatic compound containing at least one double bond wherein such compounds may contain heteroatoms or heteroatom containing functional groups which do not interfere in the formation of the compounds having 6 membered cyclic rings. Such heteroatoms include oxygen, nitrogen, phosphorous, sulfur and halogens. Preferred halogens include chlorine and bromine, with chlorine preferred. Preferred alkenes include unsaturated acids, carbonates containing unsaturation, unsaturated esters, unsaturated nitriles, vinyl chloride, vinyl acetate, unsaturated aliphatic hydrocarbons having one or more double bonds (including ethylene, propylene, all isomers of butene, pentene, hexane, heptene, octene), and the like. Alkenes useful herein can have unsaturation at any point of the carbon chain. Preferred alkenes are those having unsaturation at the terminal end of a chain, which is between the 1 and 2 carbon atoms. Among preferred unsaturated carbonates is vinylidene carbonate. Among unsaturated acids are any carboxylic acids having unsaturation in the backbone of the carbon chain including methacrylic and acrylic acids. Ethylene and propylene are more preferred unsaturated aliphatic hydrocarbons, and ethylene is most preferred. Preferred unsaturated cyclic compounds include cyclopropene, cyclobutene, cyclopentene, cyclohexene which may optionally contain a heteroatom or be substituted with

a heteroatom containing substituent as described hereinbefore. Any unsaturated ester which reacts with muconic acid, or a carboxylate derivative thereof, may be used as a dienophile in this process. Preferred unsaturated acids or esters correspond to the formula



wherein  $R^3$  is as described hereinbefore, and

$R^4$  is independently in each occurrence hydrogen, a hydrocarbyl group optionally containing a heteroatom containing functional group. Preferred unsaturated esters include hydrocarbyl acrylates, hydrocarbyl alkylacrylates and the like. Preferably, the double bond is located on a terminal carbon. More preferred unsaturated esters include hydrocarbyl acrylates and hydrocarbyl alkylacrylates, such as methyl methacrylate, with the hydrocarbyl acrylates being more preferred. The unsaturated esters may contain heteroatoms or heteroatom containing functional groups which do not interfere in the formation of the compounds having 6 membered cyclic rings as described hereinbefore. Preferred hydrocarbyl acrylates include  $C_{1-10}$  alkyl acrylates with methyl acrylate, butyl acrylate and 2-ethylhexyl acrylate being more preferred. The aromatic compounds having unsaturated substituents useful as dienophiles include any aromatic compound having an unsaturated substituent which reacts with muconic acid or a carboxylate derivative thereof under the reaction conditions defined herein. Among preferred aromatic compounds containing unsaturated substituents are styrene, *alpha*-methylstyrene, *o*-methylstyrene, *m*-methylstyrene, *p*-methylstyrene, *ar*-ethylstyrene, *ar*-vinylstyrene, *ar*-chlorostyrene or *ar*-bromostyrene, and the like. Preferably, the unsaturated aromatic compound corresponds to the formula



wherein

$R^5$  is independently in each occurrence a hydrocarbyl group optionally containing a heteroatom containing functional group or a halogen; and

$R^6$  is an alkenyl group optionally containing a heteroatom containing functional group.


Another preferred class of cyclic unsaturated compounds is cyclic unsaturated anhydrides.


Among preferred cyclic anhydrides is maleic anhydride, and the like, with maleic anhydride preferred. The alkyne containing compounds useful as dienophiles include any compound


containing a triple bond ( $\text{---C}\equiv\text{C---}$ ) which reacts with muconic acid or a

carboxylate derivative thereof under the reaction conditions. The triple bond can be located at

any position in the carbon chain of the alkyne, and is preferably between two terminal carbon atoms. Preferably alkyne containing compounds include all isomers of  $C_{2-n}$  alkynes, acetylenecarboxylic acid and carboxylate derivatives thereof and acetylene dicarboxylic acid and carboxylate derivatives thereof. More preferable alkynes include acetylene, acetylenic esters, propyne, butyne and the like, with acetylenic esters being most preferred. Preferred

alkynes correspond to the formula  wherein  $R^2$  and  $R^3$  are as described herein before.

Preferred acetylenic esters correspond to one of the formulas  and more

preferably  wherein  $R^1$ ,  $R^2$ ,  $R^3$ ,  $Z$  and  $b$  are as described hereinbefore. Preferred acetylenic esters comprise one or more carboxylate esters bonded directly to carbons of the triple bond.

**[0037]** Preferably the reactants are contacted at a temperature at which they are in liquid form so as to mix intimately or are in a solvent which dissolves the starting materials. Preferably, the reaction is performed neat, that is, in the absence of solvent. The one or more muconic acids, or carboxylate derivatives thereof, and one or more dienophiles are contacted at elevated temperatures. Any temperature at which the one or more muconic acids, or carboxylate derivatives thereof, and dienophiles are in the same phase and react at a reasonable rate may be used. Preferably, the temperature is about 100 °C or greater, more preferably about 130 °C or greater and more preferably about 140 °C or greater. Preferably, the temperature is about 180 °C or less, more preferably about 170 °C or less, even more preferably about 160 °C or less and most preferably about 150 °C or less. The reaction can take place neat, that is, in the absence of a solvent, or in the presence of a solvent. In those embodiments wherein a solvent is used, any solvent which facilitates the reaction and which does not interfere in the reaction may be used. Preferred solvents are aprotic solvents. Preferred solvents are nonpolar. More preferred solvents are hydrocarbons, acyclic ethers, alkyl polyethers, and cyclic ethers which can be used at the temperatures of the reaction, that

are liquid at the reaction temperatures, that is, have a boiling point above the reaction temperature. Among preferred solvents are xylene, decaline, toluene, cyclic ethers, glycol ethers and polyglycol ethers and the like. In the embodiment where *trans,trans* muconic acid is used as a starting material it is preferable to perform the reaction in water or in a solvent which does not transesterify the acid groups of the muconic acid to avoid side reactions and in which the muconic acid is soluble. The reaction is allowed to proceed until the desired yield of product is obtained. Preferably, the reaction time is about 24 hours or greater. Preferably, the reaction time is about 48 hours or less. Optionally, the reactants are reacted in the presence of a Lewis acid. The Lewis acid may be present in a catalytic amount, preferably about 0.01 percent by weight or greater of the reaction mixture and more preferably about 0.1 percent by weight or greater of the reaction mixture; and preferably about 10.0 percent by weight or less of the reaction mixture and more preferably about 1.0 percent by weight or less of the reaction mixture. The Lewis acid may be homogeneous or heterogeneous and is preferably heterogeneous. In a preferred embodiment, the reaction is carried out in the presence of the one or more compounds which inhibit the polymerization of unsaturated compounds. Any compound which prevents the polymerization of unsaturated compounds may be used in the reaction. Among preferred classes of compounds which prevent the polymerization of unsaturated compounds are hydroquinones, benzoquinones, phenothiazines and anisoles, mixtures thereof and the like. Among preferred compounds which prevent the polymerization of unsaturated compounds are benzoquinone, hydroquinone, *t*-butyl benzoquinone, methyl ether of hydroquinone, catechol, alkylated catechols, butylated hydroxyanisoles and the like, with hydroquinone being more preferred. The compounds which inhibit the polymerization of unsaturated compounds are present in the reaction mixture in a sufficient amount to prevent polymerization. Preferably, compounds which inhibit the polymerization of unsaturated compounds are present in an amount of about 0.05 percent by weight or greater based on the weight of the muconic acid, or carboxylate derivative thereof, most preferably about 0.01 percent by weight or greater. Preferably, compounds which inhibit the polymerization of unsaturated compounds are present in an amount of about 10.0 percent by weight or less based on the weight of the one or more muconic acids or carboxylate derivative thereof, more preferably about 2.0 percent by weight or less and most preferably about 1.0 percent by weight or less. The ratio of the one or more muconic acids or carboxylate derivatives thereof to one or more dienophiles is selected to maximize the yield of the desired products. Preferably, the mole ratio of dienophiles to muconic acid and carboxylate derivatives thereof is about 1.7:1.0 or greater, more preferably about 2.0:1.0 or greater and most preferably about 3.0:1.0 or greater. The upper limit of the mole ratio of dienophiles to muconic acid and carboxylate derivatives thereof is based on

practicality and is preferably about 10.0:1.0 or less. In those embodiments wherein a solvent is utilized, the concentration of the one or more muconic acids, or carboxylate derivatives thereof, in the solvent is preferably about 0.2 Molar (M) or greater, and most preferably about 0.5 M or greater. In those embodiments wherein a solvent is utilized, the concentration of one or more muconic acids or carboxylate derivatives thereof in the solvent is dictated by solubility of the muconic acid in the solvent and is preferably about 4.0 Molar (M) or less and most preferably about 3.0 M or less. The concentration of dienophile in the solvent is chosen in accordance with the concentration of the one or more muconic acids or carboxylate derivatives thereof in the solvent and the desired mole ratios of dienophiles to muconic acids or carboxylate derivatives thereof as described hereinbefore. The concentration of dienophile in the solvent is preferably about 0.5 M or greater and most preferably about 1.0 M or greater. The upper limit of the concentration of dienophile in the solvent is practicality. Preferably the dienophile is also used as the solvent. Where the dienophile is not the solvent a practical upper limit is about 2.4 M or less.

**[0038]** The cyclohexene compound may be recovered by any means which allows isolation of the cyclohexene compound in a manner wherein the cyclohexene compound is recovered in the desired purity and yields. where the reaction is performed neat, the cyclohexene compound may be recovered by distillation or contacting the mixture with a low polar solvent, such as an ether, in a manner such that the cyclohexene compound dissolves, filtering off the unreacted materials which do not dissolve and concentrating the solvent by evaporation to give relatively pure cyclohexene compound. Where a solvent is used, recovery is performed by distillation of the reaction mixture or by chromatographic separation. Preferably, the yield of cyclohexene compound is about 70 percent by weight or greater based on the weight of the starting muconic acid. Preferably, cyclohexene compound recovered exhibits a purity of about 90 percent by weight or greater and most preferably about 99 percent by weight or greater. Preferably the cyclohexene compound exhibits a detectable amount of carbon 14 and preferably up to about 1 part per trillion. In a preferred embodiment the recovered cyclohexene compound has about six or greater, preferably about eight or greater, of its carbon atoms derived from renewable resources such as biomass.

**[0039]** In the embodiment wherein the muconic acid or carboxylate derivatives thereof are in the *cis,cis* or *cis,trans* isomeric form, the reaction with dienophiles is preferably performed in solvent. Preferably, in this embodiment carboxylate esters of muconic acid are reacted with the dienophiles. In this embodiment the process can be performed in the presence of an isomerization catalyst and/or the presence of Lewis acid catalyst as described herein.

**[0040]** In the embodiment wherein the starting dienophile is an alkene which is in the gaseous form at ambient pressure and temperature, the one or more muconic acids or carboxylate derivatives thereof are preferably dissolved in a solvent, as described hereinbefore, and the solution is contacted with the alkene gas. Where the alkenes are liquid, the one or more muconic acids or carboxylates thereof are preferably dissolved in a solvent or alkene in as high a concentration as possible, the concentration is limited by the solubility of the one or more muconic acids or carboxylate derivatives thereof. Preferably, the one or more muconic acids or carboxylate derivatives thereof are dissolved in the solvent or alkene at a molarity of about 0.01 M or greater and more preferably about 0.12 M or greater. Preferably, the one or more muconic acids or carboxylate derivatives thereof are dissolved in the solvent or alkene at a molarity of about 4.0 M or less and more preferably about 3.0 M or less. The process is performed at ambient or elevated pressures. Elevated pressures are preferred as this allows the use of a significant excess of alkene. When elevated pressures are utilized, it is preferred to utilize a closed system and elevate the pressure by adding the alkene up to the chosen reaction pressure. Preferably, after the reaction system, containing one or more muconic acids and/or carboxylate derivatives thereof in the solvent of choice, optionally in the presence of a catalyst, is closed, it is evacuated at normal pressure to remove air and refilled with the gaseous alkene. This evacuation/refilling cycle is preferably repeated several times. The reaction system is then filled up to the chosen gaseous alkene pressure and stirred for up to 30 minutes so as to saturate the solvent with the gaseous alkene. Then is the reaction system closed and heated to the desired reaction temperature. Air or an inert gas may also be present in the system but this is not desirable because this lowers the reaction rate. The pressure chosen is limited by the equipment used in the reaction and the equipment used to deliver the alkene and any other gas present. Preferably, the pressure is about 14.7 psi (0.101 MPa) or greater, more preferably 100 psi (0.689 MPa) or greater and most preferably about 250 psi (1.72 MPa) or greater. Preferably, the pressure is about 50,000 psi (345 MPa) or less, more preferably 15,000 psi (103 MPa) or less, even more preferably about 10,000 psi (68.9 MPa) and most preferably about 270 psi (1.86 MPa) or less. Where the alkene is a gas, the alkene is preferably introduced in a significant excess and the desired pressure to be used dictates the amount of the excess utilized. If the alkene is liquid it is preferred to use the alkene as the solvent provided the muconic acid or carboxylate derivatives thereof are soluble in the alkene at reaction temperatures. Preferably the resulting product is soluble in the liquid alkene where used as the solvent. The reaction rate is significantly impacted by the reaction temperature and the pressure of the alkene present where it is a gas. Thus the reaction temperature is chosen such that the reaction rate is reasonable. Preferably, the reaction temperature is about 100 °C or greater, more preferably about 120 °C or greater and most


preferably about 150 °C or greater. Preferably, the reaction temperature is less than about 170 °C as the products decompose near this temperature and more preferably the temperature is about 160 °C or less. The reaction time is selected to allow preparation of the cyclohexene compounds in the desired yield. Preferably, the reaction time is about 1 hour or greater and most preferably about 6 hours or greater. Preferably, the reaction time is about 24 hours or less, more preferably about 12 hours or less and most preferably about 9 hours or less. The cyclohexene compound may be recovered by removing the solvent by evaporation. Where the reaction is performed neat the resulting product is recovered by distillation. Preferably, the yield of cyclohexene compound is about 90 percent by weight or greater based on the weight of the starting muconic acid or carboxylate derivatives thereof and more preferably about 95 percent by weight or greater. Preferably, cyclohexene compound recovered exhibits a purity of about 95 percent by weight or greater and most preferably about 99 percent by weight or greater. Preferably, the cyclohexene compound exhibits a detectable amount of carbon 14 number and preferably up to about one part per trillion. In a preferred embodiment, the recovered cyclohexene compound has about six or greater, preferably about eight or greater, of its carbon atoms derived from renewable resources such as biomass. In one preferred embodiment, the alkene is derived from renewable resources, such as ethylene derived from ethanol. Processes for the preparation of alkenes from renewable resources are well known in the art. In such embodiments, the number of renewable carbon atoms in the final product is about 8 or greater.

**[0041]** In the embodiment wherein the alkene dienophiles are reacted with muconic acid in water as a solvent, the product undergoes partial tautomerization. The resulting product mix includes products with the double bond between the 1 and 2 carbons of the cyclohexene ring and products with a double bond between the 2 and 3 carbons of the cyclohexene ring. In the embodiment wherein muconic acid is the starting material and the solvent is an esterifying agent, such as an alkanol, the resulting cyclohexene product undergoes esterification.

**[0042]** In the embodiment wherein the one or more dienophiles includes one or more alkynes which are in the gaseous form, such as acetylene, the one or more dienophiles are dispersed or dissolved in one or more solvents, such as those used for the reaction of dienophiles with alkenes. The reaction can be performed at atmospheric pressure or at elevated pressures by providing the alkyne in sufficient amount to pressurize the reaction mixture. Alternatively the alkyne can be introduced in admixture with an inert gas. Any gas which is inert and which can carry the dienophiles can be used. Among preferred gases are air, nitrogen, argon, and the like. Where the alkyne is liquid, the alkyne may be used as the solvent or the one or more alkynes and dienophiles may be contacted in one or more solvents.


Preferred solvents are non polar solvents which are liquid under reaction conditions. Preferred solvents are cyclic and acyclic ethers and hydrocarbon solvents, such as xylene or decalin. Preferably, the reaction is performed with an excess of the alkyne as the reaction medium. Preferably, the reaction is performed in a closed reactor under pressure. The pressure is chosen to provide an excess of the alkyne and to keep liquid alkynes in the liquid state under the reaction conditions, such as at elevated temperatures. Preferably, the alkyne is present in a molar excess. More preferably, the alkyne is present in a molar excess or about 3.0:1.0 or greater and more preferably about 5.0:1.0 or greater. The upper limit on the excess of the alkyne is practicality and the ratio is preferably about 6.0:1.0 or less. The temperature of the reaction is chosen such that the reaction rate is reasonable and to be below the decomposition temperature of the reactants and the products. Preferably, the temperature is about 130 °C or greater, more preferably about 140 °C or greater and most preferably about 150 °C or greater. Preferably the temperature is about 160 °C or less. The reaction time is preferably about one hour or greater, more preferably about 2 hours or greater and most preferably about 4 hours or greater. The reaction time is preferably about 24 hours or less and most preferably about 16 hours or less. The resulting product has a six membered aromatic ring in the desired products. Aromatic compounds with five membered rings are also prepared as by-products. The products are separated by column chromatography. Preferably, the yield of desired products is about 80 percent by weight or greater based on the weight of the starting muconic acid or carboxylate derivatives thereof and more preferably about 90 percent by weight or greater. Preferably, desired compounds recovered exhibit purity of about 90 percent by weight or greater and most preferably 99 percent by weight or greater. Preferably the desired product exhibits a detectable amount of carbon 14 and preferably up to about one part per trillion. In a preferred embodiment, the recovered compound has about six or greater, preferably about 8 or greater, of its carbon atoms derived from renewable resources such as biomass.

**[0043]** In a preferred embodiment, the cyclohexene compounds prepared correspond to one of the formulas




wherein R<sup>1</sup>, R<sup>2</sup>, R<sup>3</sup>, Z and b are as described herein before.


**[0044]** In a more preferred embodiment, the cyclohexene compounds prepared correspond to one of the formula




wherein  $R^1$ ,  $R^2$  and  $R^3$  are as described herein before. In the embodiment wherein the dienophile is an unsaturated ester the cyclohexene compound preferably corresponds to one of the formulas



wherein  $R^1$ ,  $R^3$  and  $R^4$  are as described hereinbefore. In the embodiment, the wherein the starting dienophiles comprise maleic anhydride or an analog thereof the cyclohexene formed preferably corresponds to one of the formulas




wherein  $R^1$  is as described hereinbefore. In the embodiment, wherein the starting dienophile is an aromatic compound having an unsaturated substituent the cyclohexene formed preferably corresponds to one of the formulas



wherein  $R^1$ ,  $R^3$  and  $R^5$  are as described hereinbefore. In the embodiment where the starting dienophile is an acetylenic ester the product is a trimellitate or a derivative thereof which

corresponds to the formula



wherein  $R^1$ ,  $R^2$ ,  $R^3$ ,  $Z$  and  $b$  are as described hereinbefore.

**[0045]** Preferably  $R^1$  is independently in each occurrence hydrogen, or an alkyl, haloalkyl, aryl, haloaryl, alkylaryl, alkyloxy, or carboxyl group containing not more than 10 carbon atoms. Even more preferably,  $R^1$  is independently in each occurrence a  $C_{1-10}$  alkyl group; and most preferably  $R^1$  is methyl. Preferably,  $R^2$  and  $R^3$  are independently in each occurrence hydrogen, halogen, alkyl, alkaryl, aryl, carboxyalkyl or may be combined to form a cyclic ring which may contain one or more hetero atoms. More preferably,  $R^2$  and/or  $R^3$  are independently in each occurrence hydrogen, halogen, or an alkyl, haloalkyl, aryl, haloaryl, alkylaryl, alkyloxy, or carboxyl group containing not more than 10 carbon atoms. Even more preferably,  $R^2$  and  $R^3$  are independently in each occurrence hydrogen, chloro, bromo,  $C_{1-8}$  alkyl, phenyl, or carboxyalkyl  $C_{1-8}$  alkyl or may be combined to form a cyclic anhydride.  $R^2$  is even more preferably hydrogen, chloro, methyl, ethyl or phenyl. Preferably,  $R^4$  is independently in each occurrence a  $C_{1-10}$  alkyl group. More preferably,  $R^4$  is independently in each occurrence a  $C_{1-8}$  alkyl group. Most preferably,  $R^4$  is independently in each occurrence methyl, butyl or ethylhexyl. Preferably,  $R^5$  is independently in each occurrence a hydrocarbyl group optionally containing a heteroatom containing functional group. More preferably,  $R^5$  is independently in each occurrence a  $C_{1-10}$  alkyl group. Preferably,  $a$  is independently in each occurrence 0 or 1, and most preferably  $a$  is 0. In one embodiment,  $R^2$  is independently in each occurrence halogen, an alkyl, haloalkyl, aryl, haloaryl, alkylaryl, alkyloxy, or carboxyl group containing not more than 10 carbon atoms and  $R^3$  is hydrogen; even more preferably,  $R^2$  is independently in each occurrence hydrogen, chloro, bromo,  $C_{1-8}$  alkyl, phenyl, or carboxyalkyl  $C_{1-8}$  alkyl and  $R^3$  is hydrogen; and  $R^2$  is even more preferably hydrogen, chloro, methyl, ethyl or phenyl while  $R^3$  is hydrogen.

**[0046]** To prepare compounds having at least one benzene ring having carboxylate groups at the 1 and 4, and optionally at the 2 position, such as substituted or unsubstituted terephthalic acid or carboxylate derivatives thereof (including trimellitic acid or carboxylate derivatives thereof), from the cyclohexene compounds prepared by the reaction of muconic acid and/or carboxylate derivatives thereof with dienophiles as described herein, the cyclohexene compounds are subjected to dehydrogenation, which can also be called oxidation or aromatization. In the dehydrogenation step, the cyclohexene compounds are contacted with


one or more dehydrogenation catalysts. In one embodiment, the cyclohexene compound is contacted with an oxidant and one or more dehydrogenation catalysts, at elevated temperatures. In one preferred embodiment the cyclohexene compound is contacted with the dehydrogenation catalyst in the absence of an oxidant. Preferably, an inert gas is passed through the reactor to carry away hydrogen gas generated in the dehydrogenation process. Oxidants as used herein refer to any element of compound which facilitates the oxidation of a cyclic ring to remove hydrogen atoms and to form unsaturated bond in a ring. Preferably the oxidation of the cyclic ring results in the formation of an aromatic ring. Among preferred oxidation agents are oxygen, monoclinic sulfur, nitric acid, peroxides, hydrochlorites and persulfates, chloranil and dicyanodichlorobenzoquinone. Oxygen in the form of air is a preferred oxidant. The oxidation agent is present in stoichiometric or greater amounts, preferably greater than stoichiometric amounts. The excess is chosen so as to drive the rate of the reaction. In one preferred embodiment the reaction is performed in the presence of an oxidant that reacts with the hydrogen generated in the process. Oxidants that react with hydrogen include oxygen. The reactants can be contacted neat or in a solvent. Preferable solvents are aprotic solvents with hydrocarbons, ethers (such as tetrahydrofuran) and pyrrolidones (such as *N*-methylpyrrolidone). Preferably, the solvents are liquid under reaction conditions. The cyclohexene ring containing compound concentration in solvent is at a concentration below the concentration at which disproportionation occurs. Preferably, the cyclohexene ring containing compound concentration in solvent is about 3.0 M or less and most preferably about 2.0 M or less. Preferably, the cyclohexene ring containing compound concentration in solvent is about 0.05 M or greater and most preferably about 0.10 M or greater. In one embodiment the reaction is performed at atmospheric pressure (14.7 psi, 0.101 MPa). At atmospheric pressure, the reaction can be performed at reflux of the solvent, provided the solvent boils at acceptable temperatures. Alternatively, the reaction can be performed at elevated pressures. Preferably, the oxidation agents are present in a molar excess of greater than about 2.0:1.0. Preferably, the oxidation agents are present in a molar excess of about 8.0:1.0 or less. Suitable temperatures are those at which hydrogen is abstracted from the cyclohexene compound to form double bonds in the ring of the cyclohexene containing compound. Preferably, the temperature is about 120 °C or greater and more preferably about 130 °C or greater. Preferably, the temperature is about 400 °C or less, more preferably about 350 °C or less and most preferably about 325 °C or less. If the reaction is performed at elevated pressures, the pressure is preferably about 14.7 psi (0.101 MPa) or greater and more preferably about 100 psi (.689 MPa) or greater. If the reaction is performed at elevated pressures, the pressure is preferably about 1,000 psi (6.89 MPa) or less, more preferably about 600 psi (4.14 MPa) or less and most preferably about 500 psi (3.45 MPa) or less. The reaction

time is chosen to facilitate preparing the desired compounds in the desired yield. Preferably, the reaction time is about 12 hours or greater, even more preferably about 18 hours or greater and most preferably about 24 hours or greater. Preferably the reaction time is about 48 hours or less, even more preferably about 36 hours or less and most preferably about 24 hours or less. The catalyst can be any dehydrogenation catalyst which under the reaction conditions abstracts hydrogen from the cyclohexene ring to form an aromatic ring. Preferred dehydrogenation catalysts are based on metals, more preferably Group VIII metals. The metals can be present in pure form, as alloys, in the form of metal oxides or mixtures thereof. The catalysts can also contain modifiers to impact or enhance the catalytic effect or selectivity of the catalyst. Such modifiers are well known in the art. Preferred reaction modifiers are transition metals and compounds containing transition metals. Preferred metals upon which the catalysts are based are platinum, palladium and nickel, with palladium most preferred. The catalyst can be used in a homogeneous manner but is preferably a heterogeneous catalyst on a support. The catalysts can also be in the form of sponge metals which are known to those of skill in the art. The support can be any support useful for heterogeneous catalysts. Among preferred supports are aluminum oxides, spinels, zeolites and carbon. The most preferred supports are carbon supports. The dehydrogenation reaction can be performed in a solvent. Preferably, the reaction is performed at reflux in a solvent. Preferably the solvent has a boiling point at the temperatures of reaction described earlier. Where the reaction is performed in a solvent at reflux, oxygen, preferably in the form of air, may be bubbled through the refluxing solvent. The catalyst is present in a sufficient amount such that the reaction proceeds in a reasonably efficient manner to give the desired product in the desired yield. The catalyst is preferably present in an amount of about 0.01 mole percent or greater based on the amount of the cyclohexene containing compound, more preferably about 0.03 mole percent or greater and most preferably about 1 mole percent or greater. The catalyst is preferably present in an amount of about 10 mole percent or less based on cyclohexene ring containing compound, more preferably about 5 mole percent or less and most preferably about 3 mole percent or less. The product is recovered by any means known in the art which allows isolation of the desired product at the desired yields and purity. Preferred means of recovering the desired products include filtering the reaction medium to remove the catalyst, concentrating the product by evaporation and separating the products recovered by chromatographic separation, distillation, and/or recrystallization from a suitable solvent. Preferably, the yield of products is about 60 percent by weight or greater based on the weight of the starting cyclohexene compound and more preferably about 65 percent by weight or greater. Preferably, the products recovered exhibit a purity of about 90 percent by weight or greater and most preferably about 99 percent by weight or greater. Preferably, the products

exhibit a detectable amount of carbon 14, preferably up to about one part per trillion. In a preferred embodiment, the recovered products have greater than about 6 carbon atoms derived from renewable resources such as biomass and more preferably greater than about 8 carbon atoms derived from renewable resources such as biomass.


**[0047]** The reaction of one or more of muconic acid and carboxylate derivatives thereof with one or more dienophiles and the dehydrogenation reaction step may be performed without recovery of the cyclohexene from the solvent after the first reaction step. Both reactions can be performed as described hereinbefore. In the embodiment wherein the reaction of one or more of muconic acid and carboxylate derivatives thereof with one or more dienophiles is performed in the presence of a Lewis Acid, preferably the Lewis Acid is removed prior to dehydrogenation. The dehydrogenation catalyst is added to the reaction mixture containing the cyclohexene compound before the dehydrogenation step is initiated. In this embodiment the solvent is a glycol ether, polyglycol ether, aromatic hydrocarbon, such as xylene, and the like. More preferred solvents are dimethyl glycol ether and xylene. The dehydrogenation catalyst may be added to the reaction at any temperature up to the desired reaction temperature.

**[0048]** In a preferred embodiment the product recovered corresponds to the formula




wherein  $R^1$ ,  $R^2$ ,  $Z$  and  $b$  are as described hereinbefore.


**[0049]** In a more preferred embodiment the product recovered corresponds to the formula




wherein  $R^1$  and  $R^2$  are as described hereinbefore. In the embodiment wherein the starting dienophile is an unsaturated ester the product is a trimellitate preferably corresponding to the formula



wherein  $R^1$ ,  $R^3$  and  $R^4$  are as described hereinbefore. In the embodiment wherein the starting dienophile is maleic anhydride the resulting product preferably corresponds to the formula



wherein  $R^1$ ,  $R^3$  and  $R^4$  are as described hereinbefore. Wherein the starting dienophile used to make the cyclohexene was an aromatic compound with an unsaturated substituent the product preferably corresponds to the formula




wherein  $R^1$ ,  $R^3$  and  $R^5$  are as described hereinbefore.

**[0050]** To prepare cyclohexane based compounds from the cyclohexene compounds prepared by the reaction of muconic acid and/or carboxylate derivatives thereof with dienophiles as described herein the cyclohexene compounds are subjected to hydrogenation. In the hydrogenation step, the cyclohexene compounds are contacted with hydrogen in the presence of one or more hydrogenation catalysts. Suitable temperatures are those at which hydrogen is inserted to the cyclohexene compound to remove double bonds in the ring at a reasonable rate. Preferably, the cyclohexene compound is contacted with hydrogen and one or more hydrogenation catalysts at ambient temperature. The reaction can be performed at atmospheric and elevated pressures. The upper limit on elevated pressures is the capability of the reaction equipment to handle the pressures. Preferably the pressure is less than about 200 psi (1.38 MPa). Preferably, pressure is applied by adding hydrogen gas to achieve the desired pressures. At atmospheric pressure hydrogen is bubbled through the reaction medium and/or the reaction mixture is stirred under atmospheric pressure. The reaction time is chosen to facilitate preparing the desired compounds in the desired yield. Preferably the reaction time is about 0.5 hours or greater, more preferably about 1.0 hour or greater and most preferably about 2.0 hours or greater. Preferably the reaction time is about 24 hours or less, more preferably about 16 hours or less, most preferably about 8 hours or less, and most preferably

about 3 hours or less. The catalyst can be any hydrogenation catalyst which under the reaction conditions inserts hydrogen to the cyclohexene ring to form a cyclohexane ring. Preferred hydrogenation catalysts are based on metals, preferably Group VIII metals. The metals can be present in pure form, as alloys, in the form of metal oxides or mixtures thereof. The catalysts can also contain modifiers to impact or enhance the catalytic effect or selectivity of the catalyst. Such modifications are well known in the art. Preferred metals upon which the catalysts are based are platinum, palladium and nickel, with palladium most preferred. The catalyst can be used in a homogeneous manner but is preferably a heterogeneous catalyst on a support. The catalysts may also be sponge metal catalysts known to those skilled in the art. The support can be any support useful for heterogeneous catalysts. Among preferred supports are aluminum oxides, spinels, zeolites and carbon. The most preferred support is carbon. The hydrogenation reaction can be performed in a solvent. Among preferred solvents are chlorinated hydrocarbons, acyclic ethers, cyclic ethers and alcohols (such as alkanols and acetyl alcohol), and the like. Preferably, cyclohexene compounds are present in an amount of about 5 percent by weight or greater based on the solvent and most preferably about 8 percent by weight or greater. Preferably, the cyclohexene compounds are present in an amount of about 15 percent by weight or less based on the solvent and most preferably about 12 percent by weight or less. The catalyst is present in a sufficient amount such that the reaction proceeds in a reasonably efficient manner to give the desired product in the desired yield. The catalyst is preferably present in an amount of about 0.01 mole percent or greater based on the amount of the cyclohexene containing compound, more preferably about 0.03 mole percent or greater and most preferably about 1.0 mole percent or greater. The catalyst is preferably present in an amount of about 10.0 mole percent or less based on cyclohexene ring containing compound, more preferably about 5.0 mole percent or less and most preferably about 3.0 mole percent or less. The product is recovered by any means known in the art which allows isolation of the desired product at the desired yields and purity. Preferred means of recovering the desired product (here cyclohexane ring containing compounds) in the desired yield include filtering the reaction medium to remove the catalyst, concentrating the product by evaporation and separating the products recovered by chromatographic separation, distillation, and/or recrystallization from a suitable solvent. Preferably, the yield of cyclohexane ring containing compounds is about 90 percent by weight or greater based on the weight of the starting cyclohexene compound and more preferably about 99 percent by weight or greater. Preferably, cyclohexane ring containing compounds recovered exhibit a purity of about 90 percent by weight or greater and most preferably about 99 percent by weight or greater. Preferably, the cyclohexane ring containing compounds exhibit a detectable amount of carbon 14, preferably up to about one part per trillion. In a preferred embodiment, the


recovered cyclohexane ring containing compounds have about 6 or greater carbon atoms derived from renewable resources such as biomass and more preferably about 8 greater carbon atoms derived from renewable resources such as biomass.

**[0051]** In a preferred embodiment the hydrogenated product recovered corresponds to the formula




wherein  $R^1$ ,  $R^2$ ,  $Z$  and  $b$  are as described hereinbefore.


**[0052]** In a more preferred embodiment the hydrogenated product recovered corresponds to the formula




wherein  $R^1$  and  $R^2$  are as described hereinbefore. In the embodiment wherein the starting dienophile is an unsaturated ester the product is a cyclohexane preferably corresponding to the formula



wherein  $R^1$ ,  $R^3$  and  $R^4$  are as described hereinbefore. In the embodiment wherein the starting dienophile is maleic anhydride, the resulting product preferably corresponds to the formula




wherein  $R^1$ ,  $R^3$  and  $R^4$  are as described hereinbefore. Wherein the starting dienophile used to make the cyclohexene was an aromatic compound with an unsaturated substituent, the product preferably corresponds to the formula



wherein  $R^1$ ,  $R^3$  and  $R^5$  are as described hereinbefore.

**[0053]** The cyclohexane compounds having carboxylate groups at the 1 and 4, and optionally the 2, positions may be subjected to conditions to convert the carboxylate groups to methylol groups. Such conditions are well known in the art. In one embodiment the cyclohexane compounds having carboxylate groups at the 1 and 4, and optionally the 2, positions may be subjected to catalytic hydrogenation under conditions such that the carboxylate groups are converted to methylol groups, as disclosed in section 20.22 of *Organic Chemistry*, 4<sup>th</sup> ed. Morrison and Boyd, Allyn and Bacon, New York, 1983, incorporated herein by reference. Generally, higher pressures and temperatures are utilized for hydrogenation of carboxylate groups. Alternatively, the carboxylate groups may be converted to methylol groups by chemical reduction as disclosed in Morrison and Boyd, supra. Generally, the cyclohexane compounds having carboxylate groups at the 1 and 4, and optionally the 2, positions are contacted with sodium metal and alcohol or with lithium aluminum hydride. In yet another embodiment, the conversion is achieved by contacting the cyclohexane compounds having carboxylate groups at the 1 and 4, and optionally the 2, positions with acid at elevated temperatures according to Advance Organic Chemistry, 2d, Edition March, McGraw Hill, New York 1977. In another embodiment the process of US Patent 4,302,595, incorporated herein by reference, may be utilized. The cyclohexane compounds having carboxylate groups at the 1 and 4, and optionally the 2, positions, preferably correspond to the formula;



wherein  $R^2$  may comprise a methylol group where the starting compound had carboxylate at the 2 position.

**[0054]** The benzene, cyclohexene and cyclohexane compounds having carboxylic acid groups at the 1 and 4, and optionally the 2, positions; can be esterified to add hydrocarbyl groups at the 1 and 4, and optionally the 2, positions to form carboxylate groups at these positions. The esterification reaction can be performed by any esterification process known to those skilled in the art including the processes disclosed at March, *ibid*, pages 363 to

365 and the processes disclosed hereinbefore. In one embodiment an esterifying agent, an alcohol as described hereinbefore, is contacted with the benzene, cyclohexene and cyclohexane compounds having carboxylic acid groups at the 1 and 4, and optionally the 2, positions in the presence of a strong acid with removal of the water and ester formed or a significant excess alcohol. The acidic catalysts are described hereinbefore.

**[0055]** The compounds prepared in this invention can be used as monomers to prepare a variety of known polymers. Some of the compounds can be used as plasticizers for various polymeric systems. The phenyl substituted terephthalates may be used to prepare liquid crystal polymers as described in US Patent 4,391,966, relevant disclosure incorporated herein be reference. The benzene, cyclohexene and cyclohexane compounds having carboxylic acid groups at the 1 and 4, and optionally the 2, positions, preferably terephthalic acid or dimethyl terephthalates, can be reacted with alkylene glycols, such ethylene glycol or 1,4-butane diol, to prepare polyesters. Processes for preparing such polyesters are well known in the art. For instance, terephthalic acid can be reacted with ethylene glycol to prepare polyethylene terephthalate as described in "Contemporary Polymer Chemistry" Second Edition, Harry R. Alcock, Frederick W. Lampe, 1990, Prentice-Hall at pages 27 and 28, incorporated herein by reference. In one embodiment the invention relates to methods for preparing polyalkylene polyester comprising a) contacting *cis-cis* muconic acid and one or more isomerization catalysts, sources of ultraviolet radiation, or both in a solvent at elevated temperatures for a period of time such that the *cis-cis* muconic acid isomerizes to *trans-trans* muconic acid; b) recovering the *trans-trans* muconic acid; c) optionally, contacting the *trans-trans* muconic acid with one or more esterifying agents in the presence of one or more strong acids under conditions such that one or more *trans-trans* dihydrocarbyl muconates are formed; d) contacting one or more *trans-trans* muconic acid or dihydrocarbyl muconates with one or more dienophiles at elevated temperatures under conditions such that the one or more muconic acid dihydrocarbyl muconates and dienophiles form one or more cyclohexene ring containing compounds; and e) contacting the cyclohexene ring containing compounds with one or more alkylene glycols under conditions such that one or more polyalkylene polyesters are prepared. In another embodiment the invention relates to methods for preparing polyalkylene polyesters comprising a) contacting *cis-cis* muconic acid and one or more isomerization catalysts, sources of ultraviolet radiation, or both in a solvent at elevated temperatures for a period of time such that the *cis-cis* muconic acid isomerizes to *trans-trans* muconic acid; b) recovering the *trans-trans* muconic acid; c) optionally, contacting the *trans-trans* muconic acid with one or more esterifying agents in the presence of one or more strong acids under conditions such that one or more *trans-trans* dihydrocarbyl muconates are formed; d) contacting one or more *trans-trans* muconic acids or dihydrocarbyl muconates

with one or more dienophiles at elevated temperatures under conditions such that the one or more muconic acids or dihydrocarbyl muconates and dienophiles form one or more cyclohexene ring containing compounds; and e) contacting the cyclohexene ring containing compounds with a hydrogenation catalyst under conditions such that one or more cyclohexane compounds having carboxylic acid groups at the 1 and 4, and optionally the 2, positions are prepared; f) contacting one or more cyclohexane compounds having carboxylic acid groups at the 1 and 4, and optionally the 2, positions with one or more alkylene glycols under conditions such that one or more polyalkylene polyesters are prepared. In one embodiment the invention relates to methods for preparing polyalkylene terephthalate comprising a) contacting *cis-cis* muconic acid and one or more isomerization catalysts, sources of ultraviolet radiation, or both in a solvent at elevated temperatures for a period of time such that the *cis-cis* muconic acid isomerizes to *trans-trans* muconic acid; b) recovering the *trans-trans* muconic acid; c) optionally, contacting the *trans-trans* muconic acid with one or more esterifying agents in the presence of one or more strong acids under conditions such that one or more *trans-trans* dihydrocarbyl muconates are formed; d) contacting one or more *trans-trans* muconic acids or dihydrocarbyl muconates with one or more dienophiles at elevated temperatures under conditions such that the one or more muconic acids or dihydrocarbyl muconates and dienophiles form one or more cyclohexene ring containing compounds; and e) contacting the cyclohexene ring containing compounds with a dehydrogenation catalyst, optionally in the presence of an oxidant, under conditions such that one or more of terephthalic acid or dihydrocarbyl terephthalates are prepared; f) contacting one or more of terephthalic acid or dihydrocarbyl terephthalates with one or more alkylene glycols under conditions such that one or more polyalkylene terephthalates are prepared. In another embodiment the invention is a method for preparing polyethylene terephthalate comprising a) contacting *cis-cis* muconic acid and iodine, a source of ultraviolet radiation or both in a solvent at elevated temperatures for a period of time such that the *cis-cis* muconic acid isomerizes to *trans-trans* muconic acid; b) recovering the *trans-trans* muconic acid; c) contacting the *trans-trans* muconic acid with methanol in the presence of one or more strong acids under conditions such that *trans,trans* dimethyl muconate is formed; d) contacting *trans-trans* dimethyl muconate with ethylene at elevated temperatures under conditions such that dimethyl cyclohex-2-ene-1,4-dicarboxylate, and/or its 1-ene-tautomer, is prepared; e) contacting the dimethyl cyclohex-2-ene-1,4-dicarboxylate with a dehydrogenation catalyst, optionally in the presence of an oxidant under conditions such that dimethyl terephthalate is prepared; f) hydrolyzing dimethyl terephthalate to form terephthalic acid; and g) contacting terephthalic acid with ethylene glycol under conditions such that polyethylene terephthalate is prepared. In yet another embodiment the invention is a method for preparing polyethylene

terephthalate comprising a) contacting *cis-cis* muconic acid and iodine, a source of ultraviolet radiation or both in a solvent at elevated temperatures for a period of time such that the *cis-cis* muconic acid isomerizes to *trans-trans* muconic acid; b) recovering the *trans-trans* muconic acid; c) contacting *trans-trans* muconic acid with ethylene at elevated temperatures under conditions such that cyclohex-2-ene-1,4-dicarboxylic acid, and/or its 1-ene tautomer, is prepared; d) contacting the cyclohex-2-ene-1,4-dicarboxylic acid with a dehydrogenation catalyst, optionally in the presence of an oxidant, under conditions such that terephthalic acid is prepared; and e) contacting terephthalic acid with ethylene glycol under conditions such that polyethylene terephthalate is prepared. The invention also includes a method for preparing polybutylene terephthalate comprising a) contacting *cis-cis* muconic acid and iodine, a source of ultraviolet radiation or both in a solvent at elevated temperatures for a period of time such that the *cis-cis* muconic acid isomerizes to *trans-trans* muconic acid; b) recovering the *trans-trans* muconic acid; c) contacting the *trans-trans* muconic acid with methanol in the presence of one or more strong acids under conditions such that *trans,trans* dimethyl muconate is formed; d) contacting *trans-trans* dimethyl muconate with ethylene at elevated temperatures under conditions such that dimethyl cyclohex-2-ene-1,4-dicarboxylate, and/or its 1-ene tautomer, is prepared; e) contacting the dimethyl cyclohex-2-ene-1,4-dicarboxylate with a dehydrogenation catalyst, optionally in the presence of an oxidant, under conditions such that dimethyl terephthalate is prepared; f) contacting dimethyl terephthalate with 1,4-butanediol under conditions such that polybutylene terephthalate is prepared. The resulting polyesters contain at least about 6 carbons per monomer unit, and preferably at least about 8 carbon atoms, derived from renewable resources, that are from muconic acid or muconic acid and ethylene precursors. In a preferred embodiment the resulting polyesters contain a detectable amount of carbon 14 and preferably up to about 1 part per trillion. This invention relates to polyesters wherein a portion, up to and including all, of the benzene, cyclohexene and cyclohexane compounds having carboxylic acid groups at the 1 and 4, and optionally the 2, positions used to prepare the polyesters are synthesized from one or more of muconic acid or carboxylate derivatives thereof derived from biomass. The muconic acid or carboxylate derivatives thereof may be derived from biomass by microbial synthesis. The benzene, cyclohexene and cyclohexane compounds having carboxylic acid groups at the 1 and 4, and optionally the 2, positions used to prepare the polyesters may be synthesized from ethylene derived from a renewable resource. The benzene, cyclohexene and cyclohexane compounds having carboxylic acid groups at the 1 and 4, and optionally the 2, positions used to prepare the polyesters may be synthesized from one or more of muconic acid or carboxylate derivatives thereof derived from biomass and from ethylene derived from a renewable resource. In another embodiment, the diol, such as ethylene glycol and butanediol,

reacted with the benzene, cyclohexene and cyclohexane compounds having carboxylic acid groups at the 1 and 4, and optionally the 2, positions may be derived from renewable resources, such as biomass or derivatives thereof, as is known in the art. In this embodiment, the number of carbon atoms in each monomer unit derived from renewable resources may be about 10 or greater or about 12 or greater.

**[0056]** The novel compounds of the invention and those prepared by the novel processes of the invention are preferably derived from renewable resources. Compounds prepared from renewable resources exhibit a characteristic  $^{13}\text{C}/^{12}\text{C}$  ratio as described in US 7,531,593 Column 6 line 60 to column 8 line 42, incorporated herein by reference.

**[0057]** It is understood that the above description is intended to be illustrative and not restrictive. Many embodiments as well as many applications besides the examples provided will be apparent to those of skill in the art upon reading the above description. It is further intended that any combination of the features of different aspects or embodiments of the invention may be combined. The explanations and illustrations presented herein are intended to acquaint others skilled in the art with the invention, its principles, and its practical application. Those skilled in the art may adapt and apply the invention in its numerous forms, as may be best suited to the requirements of a particular use. Accordingly, the specific embodiments of the present invention as set forth are not intended as being exhaustive or limiting of the invention. The scope of the invention should, therefore, be determined not with reference to the above description, but should instead be determined with reference to the appended claims, along with the full scope of equivalents to which such claims are entitled. Other combinations are also possible as will be gleaned from the following claims, which are also hereby incorporated by reference into this written description. The omission in the following claims of any aspect of subject matter that is disclosed herein is not a disclaimer of such subject matter, nor should it be regarded that the inventors did not consider such subject matter to be part of the disclosed inventive subject matter.

#### **SPECIFIC EMBODIMENTS**

**[0058]** Unless otherwise stated, all parts and percentages are by weight.

**[0059]** Purification of *cis,cis* Muconic Acid

**[0060]** Example 1 - Purification of crude *cis,cis* Muconic Acid



In two separate 125 ml Erlenmeyer flask, a suspension in each of crude *cis,cis* muconic acid (10.0 g each for a total of 20.0 g) in methanol (50 ml) is heated to reflux with a heat-gun. The


hot suspension is filtered. Additional methanol (30 ml) is added to the residue. It is heated again to reflux and filtered through the same filter paper into the same round-bottom flask. All solid present on the filter paper is now moved back into the Erlenmeyer flask, additional methanol (30 ml) is added and the heating to reflux followed by filtering sequence is repeated. The combined methanol solution (110 ml) is allowed to cool to room temperature, then placed into an ice bath. After warming to room temperature overnight, the mother liquid is decanted to reveal a microcrystalline beige solid, which after drying under high vacuum weighs 4.84 g. This exact sequence is now repeated with the second 10 g batch of *cis,cis*-muconic acid to obtain 4.23 g. The mother liquids from both recrystallizations are then combined and evaporated to dryness. A single recrystallization of the remaining residue from methanol (75 ml) yields an additional 2.82 g. In total, 11.89 g (59 percent mass recovery) of pure *cis,cis* muconic acid.

**[0061]** Example 2 - Purification of crude Muconic Acid

**[0062]** A stirred suspension of dried (less than 5 weight percent of water), crude *cis,cis* or *cis,trans* muconic acid (200 g) in tetrahydrofuran (THF) (1.8 liter (l)) is heated to 50 °C. Within 45 minutes at 50 °C most of the solid dissolves. Activated charcoal (35 g) is added. After 1 hour, the hot suspension is clarified by filtration through a bed of Celite™ diatomaceous earth. The filtrate is evaporated to dryness and the residue is dried under high vacuum to yield pure *cis,cis* or *cis,trans* muconic acid (166 g, 83 percent mass recovery). In the case of *cis,cis* muconic acid, any traces of *cis,trans* muconic acid can be removed by resuspending the solid twice in refluxing ethyl acetate, which is removed each time by decantation from the cooled solution. The approximate solubilities at room temperature in ethyl acetate are 1 mg/ml for *cis,cis* muconic acid, 5 mg/ml for *cis,trans* muconic acid, and 0.1 mg/ml for *trans,trans* muconic acid.

**[0063]** Isomerization to *cis,trans* and *trans,trans* Muconic Acid

**[0064]** Example 3 - Synthesis of *cis,trans* Muconic Acid from Crude *cis,cis* Muconic Acid



Crude *cis,cis* muconic acid (15.0 g) suspended in water (250 ml) is heated to reflux for 10 minutes using a heat gun. At reflux, everything is in solution. The hot solution is allowed to cool to room temperature, and then placed into an ice bath. After warming to room temperature overnight, the mother liquid is decanted to reveal pure *cis,trans* muconic acid as a microcrystalline beige solid, which after drying under high-vacuum weighs 9.0 g, giving a 60 percent mass recovery.

**[0065]** Example 4 - Synthesis of *cis,trans* Muconic Acid from pure *cis,cis* Muconic Acid

**[0066]** An aqueous (150 ml) suspension of purified *cis,cis* muconic acid (15.0 g) is heated to reflux for 15 minutes using a heat gun. After cooling to room temperature overnight, the precipitated solid, pure *cis,trans* muconic acid, is collected by filtration, washed with a small amount of water, and dried under high vacuum (10.4 g, 69 percent). A sample of the mother liquid is concentrated, and the entire remaining residue is dissolved in DMSO-d<sub>6</sub> for <sup>1</sup>H NMR analysis. The bulk of the mother liquid is evaporated to dryness (4.2 g). Based on integration of the <sup>1</sup>H NMR spectrum of the evaporation residue of the mother liquid sample, 3 percent of the total muconic acid remained in solution as the *cis,trans* isomer, 25 percent is converted to its internal lactone, and the remaining 3 percent undergoes lactone-hydrolysis followed by decarboxylation to form laevulinic acid.

**[0067]** Example 5 - Synthesis of *trans,trans* Muconic Acid from pure *cis,cis* or *cis,trans* Muconic Acid

**[0068]** A mixture consisting of purified *cis,cis* or *cis,trans* muconic acid (12.5 g, 88 mmol), I<sub>2</sub> (110 mg, 0.5 mol percent), and THF (110 ml, 0.8 M) is refluxed for 4 hours. After cooling to room temperature, the precipitated solid, pure *trans,trans* muconic acid, is collected by filtration. To remove all traces of I<sub>2</sub>, the solid is resuspended on the frit in room temperature THF, which is again removed via aspirator vacuum filtration. The material is dried under high vacuum (11.3 g, 90 percent).

**[0069]** Examples 6 to 13 - Synthesis of *trans,trans* Muconic Acid from crude *cis,cis* or *cis,trans* Muconic Acid

**[0070]** Dried, purified *cis,cis* muconic acid (5.0 g, 35.2 mmol) is suspended in THF (44 ml, 0.8 M). Either pure water (1, 5, 10, or 20 weight percent) or (NH<sub>4</sub>)<sub>2</sub>SO<sub>4</sub> (1, 5, 10, or 20 weight percent) is added. I<sub>2</sub> (45 mg, 0.5 mol percent) is added and the mixture is heated to reflux for 4 hour. After cooling to room temperature, the precipitated *trans,trans* muconic acid is collected by filtration and dried. In the case of the (NH<sub>4</sub>)<sub>2</sub>SO<sub>4</sub> experiments, the mass of collected *trans,trans* muconic acid is corrected for the presence of (NH<sub>4</sub>)<sub>2</sub>SO<sub>4</sub>. A sample of the mother liquid is concentrated and all of the residue is dissolved in DMSO-d<sub>6</sub> for <sup>1</sup>H NMR analysis. Integration allowed an estimation of the composition of the mother liquid. The results are compiled in Tables 1 and 2

[0071] Tables 1 and 2:


Ex	added H <sub>2</sub> O (weight %)	<i>tt</i> -MA isolated (g)	<i>tt</i> -MA isolated (% yield)	composition of the mother liquid		
				% <i>tt</i> -MA	% <i>ct</i> -MA	% lactone
6	1	4.1	82	94	4	2
7	5	4.5	90	95	3	2
8	10	4.2	84	93	6	2
9	20	4.2	84	82	13	5

*tt*-MA = *trans-trans* muconic acid, *ct*-MA = *cis-trans* muconic acid.

Ex	added H <sub>2</sub> O (weight %)	<i>tt</i> -MA isolated (g)	<i>tt</i> -MA isolated (% yield)	composition of the mother liquid			
				% <i>tt</i> -MA	% <i>ct</i> -MA	% <i>cc</i> -MA	% lactone
10	1	3.9	78	30	45	25	traces
11	5	3.1	62	24	65	11	1
12	10	3.0	60	21	73	5	1
13	20	2.5	50	15	79	4	2


*tt*-MA = *trans-trans* muconic acid, *ct*-MA = *cis-trans* muconic acid, *cc*-MA = *cis-cis* muconic acid.

[0072] Example 14 - Synthesis of *cis,trans*-Muconic Acid from crude *cis,cis*-Muconic Acid



*Cis,cis*-Muconic acid (100 g) is dissolved in water (1 L, then adjusted to pH 6 by adding base, sodium hydroxide) and the mixture is heated at 90°C for 3.5 hours. Samples are taken every 30 minutes and analyzed by HPLC. HPLC analyses of these samples show that the isomerization process is almost complete after 1 hour of heating at 90°C. After 3.5 hours of heating at 90°C, the mixture is treated with charcoal (10 g) for 30 minutes and filtered through a Whatman filter paper (# 2). The pH of the solution is adjusted to 3.5 by adding base, sodium hydroxide. The precipitate is obtained by filtration, washed with ice-cold water (200 mL), and dried under reduced pressure to yield 64.5 g (65 percent yield) of light yellow *cis,trans*-muconic acid.


[0073] Example 15 - Synthesis of *trans,trans* Muconic Acid from *cis,cis* Muconic Acid



A mixture containing purified *cis,cis* muconic acid (0.50 g), a catalytic amount of iodine (25


mg), and acetonitrile (35 ml) is heated to reflux for 36 hours. The reaction is performed in the presence of ambient light in the laboratory. The precipitated solid is filtered off from the still hot solution and washed with cold acetonitrile. After drying under high vacuum, 0.40 g (80 percent yield) of pure *trans,trans* muconic acid are present as a tan-colored powder.

**[0074]** Example 16 - Synthesis of *trans,trans* Muconic Acid from *cis,trans* Muconic Acid




A mixture containing *cis,trans* muconic acid (1.00 g), a catalytic amount of iodine (53 mg, 3.0 mole percent), and acetonitrile (35 ml) is heated to reflux for 11 hours. The reaction is performed in the presence of ambient light in the laboratory. After cooling to room temperature, the precipitated solid is filtered off and washed with acetonitrile. After drying under high vacuum, 0.80 g (80 percent yield) of pure *trans,trans* muconic acid are present as a tan-colored powder. The material obtained by this procedure from *cis,trans* muconic acid is identical to the material obtained from *cis,cis* muconic acid by the previous procedure.

**[0075]** Example 17 - Synthesis of *trans,trans*-Muconic Acid from *cis,trans*-Muconic Acid



*Cis,trans* muconic acid (10 g, 70.4 mmol) is dissolved in THF (200 mL) along with 200 mg of iodine (1.1 mole percent). The reaction is performed in the presence of ambient light in the laboratory. The mixture is then brought to reflux and samples are taken every 30 minutes to be analyzed by HPLC. After 2 hours of reflux, the precipitate is filtered, washed with excess THF, and dried to yield 6.2 g of light yellow solid. HPLC analysis of the isolated solid indicated that it is pure *trans,trans*-muconic acid and that the isomerization is completed after 1 hour of reflux.

**[0076]** Example 18 - Synthesis of *trans,trans*-Muconic Acid from *cis,trans*-Muconic Acid




*Cis,trans*-muconic acid (19 g, 133.8 mmol) is dissolved in THF (250 mL) at room temperature and a crystal of iodine (160 mg, 0.63 mmol, 0.5 mole percent) is added. The reaction is performed in the presence of ambient light in the laboratory. The reaction mixture is allowed to stir at room temperature for 5 hours and the precipitant is filtered, washed with

acetonitrile and dried under reduced pressure to yield 16 g of *trans,trans*-muconic acid, an 84 percent yield.


**[0077]** Esterification of Muconic Acid

**[0078]** Example 19 - Synthesis of *cis,cis* Dimethyl Muconate from *cis,cis* Muconic Acid




Purified *cis,cis* muconic acid (10.0 g, 70.4 mmol) is suspended in aqueous sodium hydroxide (NaOH, 42.2 ml, 5.0 M, 211 mmol, 3.0 equivalents). At room temperature, dimethyl sulfate (18.4 ml, 194 mmol, 2.75 equivalents) is added after 15 min and the mixture is rapidly stirred for 6 hours. The mixture is taken up in ethyl acetate and shaken until all solid is dissolved. The organic phase is reextracted 3 times with 1 M (molar) aqueous NaOH and once with saturated aqueous sodium chloride (NaCl). Drying with magnesium sulfate (MgSO<sub>4</sub>), filtering, and evaporation of all solvent yields an off-white crystalline solid (6.2 g, 36.4 mmol, 52 percent yield) which is identified as pure *cis,cis* dimethyl muconate, free of any dimethyl sulfate.

**[0079]** Example 20 - Synthesis of *cis,trans* Dimethyl Muconate from *cis,trans* Muconic Acid



Purified *cis,trans* muconic acid (10.0 g, 70.4 mmol) is suspended in aqueous NaOH (42.2 ml, 5.0 M, 211 mmol, 3.0 equivalents). At room temperature, dimethyl sulfate (18.4 ml, 194 mmol, 2.75 equivalents) is added after 15 minutes and the mixture is rapidly stirred for 5 hours. The mixture is taken up in ethyl acetate and shaken until all solid is dissolved. The organic phase is reextracted 3 times with 1 M aqueous NaOH and once with saturated aqueous NaCl. Drying with magnesium sulfate (MgSO<sub>4</sub>), filtering, and evaporation of all solvent yields an off-white crystalline solid (6.0 g, 35.3 mmol, 50 percent yield) which is identified as pure *cis,trans* dimethyl muconate, free of any dimethyl sulfate.


**[0080]** Example 21 - Synthesis of Isomeric Dimethyl Muconates from *cis,cis* Muconic Acid



*Cis,cis* muconic acid (10.0 g, 70.4 mmol) is suspended in methanol (250 ml). A catalytic amount of H<sub>2</sub>SO<sub>4</sub> (0.6 ml) is added and the reaction mixture is refluxed for 18 hours. After concentration, the remaining brown residue is taken up in ethyl acetate and extracted 3 times

with saturated aqueous  $K_2CO_3$ . Drying ( $Na_2SO_4$ ), filtering, and evaporation of all solvent results in a light brown solid (10.8 g, 63.5 mmol, 90 percent yield), consisting mainly of *cis,cis* and *cis,trans* dimethyl muconate, which is used as described hereinafter without further purification.

**[0081]** Example 22 - Synthesis of *trans,trans* Dimethyl Muconate from *trans,trans* Muconic Acid




*Trans,trans* muconic acid (4.6 g, 32.4 mmol) is suspended in methanol (125 ml). A catalytic amount of sulfuric acid,  $H_2SO_4$  (0.3 ml) is added and the reaction mixture is refluxed for 18 hours. After concentration, the remaining brown residue is taken up in ethyl acetate and extracted 3 times with saturated aqueous potassium carbonate, aq.  $K_2CO_3$ . Drying over sodium sulfate ( $Na_2SO_4$ ), filtering, and evaporation of all solvent yields an off-white solid (5.2 g, 30.6 mmol, 94 percent yield), which is identified as pure *trans,trans* dimethyl muconate.

**[0082]** Example 23 - Synthesis of *trans,trans* Dimethyl Muconate from *trans,trans* Muconic Acid

**[0083]** Concentrated  $H_2SO_4$  (0.52 ml, 0.1 volume percent) is added to a stirred suspension of *trans,trans* muconic acid (60 g, 0.42 mol) in methanol (0.52 l, 0.8 M). The reaction mixture is stirred at reflux for 16 hours. This reaction transforms a low solubility solid into another low solubility solid. The density of crystalline *trans,trans* dimethyl muconate is higher than that of crystalline *trans,trans* muconic acid: *trans,trans* muconic acid is suspended throughout the stirring methanol reaction mixture whereas *trans,trans* dimethyl muconate remains accumulated on the bottom of the flask at all investigated stirring rates. After cooling to room temperature, the mother liquid is decanted and the precipitate is washed with methanol. To remove all traces of  $H_2SO_4$ , fresh methanol (200 ml) is introduced and the mixture is heated to reflux for 10 minutes. After cooling to room temperature, the mother liquid is again decanted and the precipitate is washed with methanol. Drying under high vacuum provides clean *trans,trans* dimethyl muconate (68 g, 0.40 mol, 95 percent).


**[0084]** Example 24 - Synthesis of *trans,trans* Di-*n*-butyl Muconate from *trans,trans* Muconic Acid



*Trans,trans* muconic acid (5.0 g, 35.2 mmol) is suspended in normal butanol (40 ml). A

catalytic amount of  $\text{H}_2\text{SO}_4$  (0.45 ml) is added and the reaction mixture is refluxed for 16 hours. The reaction mixture is diluted with ethyl acetate and extracted 3 times with saturated aqueous  $\text{K}_2\text{CO}_3$ . Drying ( $\text{Na}_2\text{SO}_4$ ), filtering, and evaporation of all solvent yields a light yellow gel (8.3 g, 32.7 mmol, 93 percent yield), which is identified as pure *trans,trans* di-*n*-butyl muconate.


**[0085]** Example 25 - Synthesis of *trans,trans* Di-(2-ethyl-hexyl) Muconate from *trans,trans* Muconic Acid



*Trans,trans* muconic acid (5.0 g, 35.2 mmol) is suspended in 2-ethyl-hexanol (50 ml). A catalytic amount of  $\text{H}_2\text{SO}_4$  (0.45 ml) is added and the reaction mixture is refluxed for 18 hours. Most of the solvent is evaporated and via a short chromatographic separation ( $\text{SiO}_2$ , hexanes as the eluent) a light yellow oil (11.2 g, 30.6 mmol, 87 percent yield) is obtained, which is identified as pure *trans,trans* di-(2-ethyl-hexyl) muconate.


**[0086]** Isomerization of *cis,cis* and *cis,trans* Dimethyl Muconate to *trans,trans* Dimethyl Muconate

**[0087]** Example 26 - Synthesis of *trans,trans* Dimethyl Muconate from *cis,cis* Dimethyl Muconate



A solution of *cis,cis* dimethyl muconate (0.60 g, 3.43 mmol) and a catalytic amount of iodine (30 mg, 3.3 mole percent) in acetonitrile (10 ml) is heated to reflux for 15 hours. The reaction is performed in the presence of ambient light in the laboratory. Removal of all solvent on a rotary evaporator followed by high vacuum, washing with 15 ml diethyl ether and hexane in a 3/2 volumetric ratio to remove all of the iodine, and drying under high vacuum yields an off-white crystalline solid (0.58 g, 3.41 mmol, 97 percent yield), which is identified as pure *trans,trans* dimethyl muconate.


**[0088]** Example 27 - Synthesis of *trans,trans* Dimethyl Muconate from *cis,trans* Dimethyl Muconate



A solution of *cis,trans* dimethyl muconate (0.60 g, 3.53 mmol) and a catalytic amount of

iodine (43 mg, 4.8 mole percent) in acetonitrile (10 ml) is heated to reflux for 25 hours. The reaction is performed in the presence of ambient light in the laboratory. Removal of all solvent on a rotary evaporator is followed by applying a high vacuum, washing with 15 ml diethyl ether and hexane in a 3/2 volumetric ratio to remove all iodine, and drying under high vacuum yields an off-white crystalline solid (0.60 g, 3.53 mmol, 100 percent yield) which is identified as pure *trans,trans* dimethyl muconate.


**[0089]** Example 28 - Synthesis of *trans,trans* Dimethyl Muconate from the isomeric Dimethyl Muconates



A solution of the mixture of *cis,cis* and *cis,trans* dimethyl muconate (10.8 g, 63.5 mmol) obtained in Example 21 and a catalytic amount of I<sub>2</sub> (300 mg, 1.9 mol percent) in methanol (250 ml) is heated to reflux for 60 hours, at which time TLC and GC-MS confirms complete conversion. Upon cooling to 0 °C, *trans,trans* dimethyl muconate precipitates. It is collected by filtration, washed with ice-cold methanol, and dried under high vacuum (8.2 g, 48.2 mmol, 76 percent yield). The material obtained by this procedure is identical to the material obtained by the previous two procedures.


**[0090]** Reactions of *trans,trans* Muconic Acid and *trans,trans* Dimethyl Muconate

**[0091]** Example 29 - Reaction of *trans,trans* Dimethyl Muconate and Maleic Anhydride




In a 5 ml pressure tube, *trans,trans* dimethyl muconate (1.0 g, 5.9 mmol) and maleic anhydride (1.7 g, 17.6 mmol, 3 eq.) are heated to 150 °C for 1 hour. <sup>1</sup>H NMR analysis of the cooled reaction mixture reveals the presence of about 79 percent desired addition product.

**[0092]** Example 30 - Reaction between *cis,cis* Dimethyl Muconate and Maleic Anhydride




A solution of *cis,cis* dimethyl muconate (0.1 g, 0.6 mmol) and maleic anhydride (173 mg, 1.8 mmol, 3 eq.) in decahydronaphthalene (2 ml) is heated to 150 °C for 24 hours. All of the cooled reaction mixture is dissolved in DMSO- $d_6$  for  $^1\text{H}$  NMR analysis, showing the presence of about 60 percent unreacted *cis,cis* dimethyl muconate, 20 percent isomerized *trans,trans* dimethyl muconate, and 20 percent of the Diels-Alder addition product between *trans,trans* dimethyl muconate and maleic anhydride.

**[0093]** Example 31 - Reaction between *cis,trans* Dimethyl Muconate and Maleic Anhydride



A solution of *cis,trans* dimethyl muconate (0.1 g, 0.6 mmol) and maleic anhydride (173 mg, 1.8 mmol, 3 eq.) in decahydronaphthalene (2 ml) is heated to 150 °C for 24 hours. All of the cooled reaction mixture is dissolved in DMSO- $d_6$  for  $^1\text{H}$  NMR analysis, showing the presence of about 69 percent unreacted *cis,trans* dimethyl muconate, 9 percent isomerized *trans,trans* dimethyl muconate, and 22 percent of the addition product between *trans,trans* dimethyl muconate and maleic anhydride.


**[0094]** Example 32 - Preparation of Trimethyl Trimellitate via Reaction between *trans,trans* Dimethyl Muconate and Methyl Propiolate



In a 5 ml pressure tube, a solution of *trans,trans* dimethyl muconate (1.0 g, 5.9 mmol) in methyl propiolate (2.5 ml, 29.4 mmol, 5 eq.) is heated to 160 °C for 19 hours.  $^1\text{H}$  NMR analysis of the cooled reaction solution reveals that no unreacted *trans,trans* dimethyl muconate remains. Three substances are found to be present in near equal quantities. Repeated column chromatography (Si35, SF25-40g, AnaLogix column with 13 percent ethyl acetate/hexane isocratic eluent) of the crude reaction mixture, and analysis of single fractions, allows the identification of the three distinct reaction products: trimethyl trimellitate (23 percent), arising by an oxidation of the initially formed diene product, dimethyl 2-(2-methoxy-2-oxoethylidene)cyclopenta-3,5-diene-1,3-dicarboxylate (29 percent), arising from a


cheletropic addition (end-on) of the alkyne to the diene followed by oxidation, and an *E/Z* mixture of methyl 3-(2-methoxy-2-oxoethylidene)cyclopenta-1,4-dienecarboxylate (27 percent), arising from an attack of the alkyne onto the  $\beta$ -carbon of the ene, followed by methanol elimination to form a cumulene which undergoes rearrangement under expulsion of CO. Similar experiments with *cis,cis* and *cis,trans* dimethyl muconate only produce the products derived from *trans,trans* dimethyl muconate due to initial isomerization to *trans,trans* dimethyl muconate followed by addition.

**[0095]** Example 33 - Diels-Alder Reaction between *trans,trans* Muconic Acid and Acrylic Acid




A stirred mixture of *trans,trans* muconic acid (1.0 g, 7.0 mmol) and acrylic acid (0.96 ml, 14.0 mmol, 2.0 eq.) in a 5 ml round-bottom flask equipped with a reflux condenser is heated to 140 °C for 3 hours. To achieve a larger amount of conversion, more acrylic acid is added over the course of the reaction (1.0 eq. at 2 hours). In order to facilitate the characterization of the product, the reaction mixture is esterified in methanol overnight. GC-MS analysis of the crude esterified product shows the presence of trimethyl cyclohex-5-ene-1,2,4-tricarboxylate, thus confirming the formation of cyclohex-5-ene-1,2,4-tricarboxylic acid via reaction between *trans,trans* muconic acid and acrylic acid.

**[0096]** Example 34 - Preparation of Trimethyl Cyclo-5-ene-1,2,4-tricarboxylate




*Trans,trans* dimethyl muconate (1 g, 5.9 mmol), methyl acrylate (1.6 ml, 17.6 mmol, 3 eq) and hydroquinone (65 mg, 0.59 mmol, 0.1 eq) are mixed in *m*-xylene (30 ml). The reaction mixture is refluxed under nitrogen for 72 hours. The reaction mixture is then concentrated down to a clear colorless gel, which is purified by column chromatography using the Analogix BSR SimpliFlash system (Hexanes/Ethyl acetate, 8:2). A mixture of the two diastereomers of the desired product is isolated as a clear colorless and colorless oil with a 61 percent yield, 0.9g, 3.6 mmol.

**[0097]** Example 35 - Preparation of 2-butyl-1,4-dimethyl Cyclo-5-ene-1,2,4-tricarboxylate




*Trans,trans* dimethyl muconate (1g, 5.9 mmol) is mixed with butyl acrylate (0.85 ml, 5.9 mmol, 1.0 eq) and hydroquinone (65 mg, 0.59 mmol, 0.1 eq). The reaction mixture is heated to 140°C for 1 hour. After one hour, 0.5 equivalents of butyl acrylate (0.42 ml, 2.9 mmol) are added to the mixture and it is heated for an additional hour. Then, 0.2 equivalents of butyl acrylate (0.17 ml, 1.2 mmol) are added to the reaction mixture, which is heated for one more hour. After a total of 3 hours, the reaction mixture is allowed to cool down to room temperature. The excess butyl acrylate is evaporated and the resulting residue is purified by column chromatography using an Analogix BSR SimpliFlash system (Hexanes/Ethyl acetate, 8:2). The desired product is obtained as a mixture of two diastereomers of the expected Diels-Alder addition product with an 81 percent yield (1.4 g, 4.8 mmol, clear gel).

**[0098]** Example 36 - Preparation of Tributyl Cyclo-5-ene-1,2,4-tricarboxylate



A stirred mixture of *trans,trans* di-*n*-butyl muconate (1.0 g, 3.9 mmol) and *n*-butyl acrylate (0.85 ml, 5.9 mmol, 1.5 eq.) with hydroquinone (0.1 eq) in a 5 ml round-bottom flask equipped with a reflux condenser is heated to 140 °C for 4 hours. To achieve a larger amount of conversion, more *n*-butyl acrylate is added over the course of the reaction (1.0 eq. at 3 hours). The cooled reaction mixture is purified by column chromatography (Si35, SF25-40g, AnaLogix column with 10 percent ethyl acetate/hexane isocratic eluent) to provide two diastereomers of the expected addition product (1.1 g, 3.0 mmol, 78 percent yield) as a clear light-yellow oil.


**[0099]** Example 37 - Preparation of Tri-(2-ethyl-hexyl) Cyclohex-5-ene-1,2,4-tricarboxylate



A stirred mixture of *trans,trans* di-(2-ethyl-hexyl) muconate (1.0 g, 2.7 mmol), 2-ethyl-hexyl acrylate (1.1 ml, 5.4 mmol, 2.0 eq.), and hydroquinone (30 mg, 0.27 mmol, 0.1 eq.) in a 5 ml round-bottom flask equipped with a reflux condenser is heated to 140 °C for 4 hours. To


achieve a larger amount of conversion, more 2-ethyl-hexyl acrylate is added over the course of the reaction (2.0 eq. at 1 h, 1.0 eq. at 3 hours). The cooled reaction mixture is purified by column chromatography (Si35, SF25-40g, AnaLogix column, gradient: 100 percent hexanes to 20 percent ethyl acetate/hexanes) to provide two diastereomers of the addition product (0.72 g, 1.3 mmol, 49 percent yield) in the form of a clear light-yellow oil. When this reaction is run in the absence of hydroquinone, the same two diastereomers of the addition product are formed.

**[00100]** Example 38 to 40 - Preparation of dimethyl cyclohex-2-ene-1,4-dicarboxylate



In a Parr pressure reactor, a rapidly stirred solution of *trans,trans* dimethyl muconate (2.58 g, 15.2 mmol) in *m*-xylene (120 ml) is heated under an ethylene atmosphere (260 psi at 23 °C after the solution is saturated with ethylene) at a 150 °C set-point temperature (151 - 168 °C observed) for 24 hours. <sup>1</sup>H NMR analysis of the near-colorless cooled reaction solution revealed about 96 percent conversion to dimethyl cyclohex-2-ene-1,4-dicarboxylate. Removal of the solvent provided a white-cloudy oil. The precipitated traces of *trans,trans* dimethyl muconate are separated by taking up the oil in *tert*-butyl-methyl-ether and filtering it to provide, after removal of the solvent, an over 98 percent pure product (near-colorless oil). Another batch is purified by column chromatography (Si35, SF25-40g, AnaLogix column with 13 percent ethyl acetate/hexane isocratic eluent) to obtain an analytical sample. Diastereomers of dimethyl cyclohex-2-ene-1,4-dicarboxylate are detected by GC. As shown in the following table, the reaction can also be conducted successfully on a larger scale and also with free *trans,trans* muconic acid (Examples 41 - 42). Table 3 shows the amount of dimethyl muconate, pressure (psi), c(M), solvent, set and reaction temperatures, reaction time in hours and the result of the reaction. In Examples 41 and 42 the *trans,trans* muconic acid is the starting material instead of *trans,trans* dimethyl muconate.

**[00101]** Examples 41 and 42 - Reaction Between Free *Trans,trans* Muconic Acid and Ethylene



In a Parr pressure reactor, a rapidly stirred (155 rpm) mixture of *trans,trans* muconic acid (2.10 g, 14.7 mmol) and water (120 ml) is heated under an ethylene atmosphere (270 psi at 23 °C after the solution was saturated with ethylene) at a 150 °C set-point temperature for 3 days. After opening the cooled Parr reactor, an orange solid is present on the ground of a yellow solution. The yellow solution is decanted and the orange solid is dried (paper towel) to provide 0.85 g (5.0 mmol, 34 percent yield). <sup>1</sup>H NMR analysis identifies it to be the tautomerized ethylene-Diels-Alder addition product. An additional quantity of the tautomerized product was present in the yellow solution. In addition, the yellow solution also contained a small quantity of the untautomerized initial Diels-Alder addition product and decomposed material. A subsequent reaction (Example 42) at 125 °C for 1 day shows that at such lower temperature more (44 percent) untautomerized initial Diels-Alder addition product is present at the time the reaction is worked-up; in addition, 13 percent tautomerized product is present, 41 percent unreacted starting material was recovered, and only 2 percent decomposed material is present. The results of Examples 38 to 42 are shown in Table 3.

Table 3

Ex	M g	P psi	Solvent	c (M)	T °C	t d	y perce nt	Remarks
38	2.6	270	<i>m</i> -xylene	0.12	150	1	96	
39	7.6	260	<i>m</i> -xylene	0.36	150	2	98	
40	2.1	250	<i>n</i> -butanol	0.12	150	3	74	<i>n</i> -butyl carboxylate product, and 26 percent di <i>n</i> -butyl muconate
41	2.1	270	water	0.12	150	3	>34	> 0.85 g (> 34 percent) of tautomerized DAp
42	2.1	270	water	0.12	125	1	44	13 percent of tautomerized DAp

M muconate amount in grams

c(M) means molar concentration of muconate in solvent.

T is temperature in degrees centigrade.

t is reaction time in days.


y is yield in weight percent.

DAp is Diels Alder product.

**[00102]**

Examples 43 to 47 - One-Pot Isomerization and Diels-Alder followed

by Esterification



**[00103]** In a Parr pressure reactor, a stirred suspension of *cis,cis* muconic acid (8.6 g, 60.6 mmol) and I<sub>2</sub> (114 mg, 0.7 mol percent) in diglyme (diglycol methyl ether, 120 ml, 0.5 M) is heated under ethylene pressure (270 psi (1.86 MPa) at 23 °C) to 200 °C for 48 hours. All solvent is removed, and methanol (200 ml) and a catalytic amount of concentrated H<sub>2</sub>SO<sub>4</sub> (0.2 ml) are added. After reflux for 14 hours, the solution is analyzed by GC to quantify the amounts of dimethyl cyclohex-2-ene-1,4-dicarboxylate (13 - 19 percent) and dimethyl cyclohex-1-ene-1,4-dicarboxylate (74 - 76 percent) present. Removal of the solvent and distillation provides clean product. The results are shown in Table 4.


Table 4

Ex	solvent	catalyst / mol %	T (°C)	% yield		
				<i>eq-ax</i> Me <sub>2</sub> -Δ <sup>2</sup>	<i>bis-eq</i> Me <sub>2</sub> -Δ <sup>2</sup>	Me <sub>2</sub> -Δ <sup>1</sup>
43	diglyme	I <sub>2</sub> , 0.6	165	60		9
44	diglyme	I <sub>2</sub> , 0.7	200	8	11	76
45	diglyme	none	200	3	4	4
46	MeOH	I <sub>2</sub> , 0.7	200	9	7	5
47	diglyme	I <sub>2</sub> , 0.7	200	13		74

**[00104]** Example 48 - Synthesis of Dimethyl Cyclohex-2-ene-1,4-dicarboxylate from *trans,trans* Dimethyl Muconate - Larger Scale


**[00105]** In a Parr pressure reactor, a stirred suspension of *trans,trans* dimethyl muconate (40.8 g, 240 mmol) in diglyme (120 ml, 2.0 M) is heated under ethylene pressure (270 psi (1.86 MPa) at 23 °C) to 165 °C for 24 hours. Analysis of the reaction mixture by GC allows quantification of the products; dimethyl cyclohex-2-ene-1,4-dicarboxylate (75 percent) and dimethyl cyclohex-1-ene-1,4-dicarboxylate (1 percent) are present. Removal of the solvent and distillation provides clean product.

**[00106]** Example 49 - One step *cis,trans* dimethyl muconate isomerization to *trans,trans* dimethyl muconate and reaction with ethylene



**[00107]** In a Parr reactor, a mixture of *cis,trans* dimethyl muconate (9.80 g, 57.6 mmol), iodine (73 mg, 0.29 mmol, 0.5 mol percent), and dioxane (120 ml, 0.48 M) is heated to 160 °C for 24 hours under ethylene pressure ( $p_{RT} = 270$  psi (1.86 MPa)). After cooling to room temperature, a weakly yellow, cloudy suspension is present. All solvent is evaporated on a rotary evaporator from a sample of this suspension to reveal a colorless oil with a yellow solid suspended in it. All of this material is dissolved in dimethylsulfoxide (DMSO- $D_6$ ) and analyzed by  $^1H$  NMR spectroscopy: 86 percent of dimethyl cyclohex-2-ene-1,4-dicarboxylate is found to be present.

**[00108]** Example 50 - One step *cis,trans* muconic acid isomerization to *trans,trans* muconic acid and reaction with ethylene




**[00109]**

**[00110]** In a Parr reactor, a mixture of *cis,trans* muconic acid (8.18 g, 57.6 mmol),  $I_2$  (293 mg, 1.15 mmol, 2.0 mole percent), and THF (120 ml, 0.48 M) is heated to 160 °C for 25 hours under ethylene pressure ( $p_{RT} = 252$  psi (1.74 MPa)). After cooling to room temperature, a white solid is found to be suspended in a weakly yellow solution. The solution is filtered to remove the precipitated *trans,trans* muconic acid and all solvent is evaporated on a rotary evaporator. The residue is suspended in hot ethyl acetate/dioxane; after cooling to room temperature, the precipitated solid is removed by filtration and the filtrate is evaporated to dryness to yield cyclohex-2-ene-1,4-dicarboxylic acid (7.22 g, 42.4 mmol, 75 percent).

**[00111]** Oxidation to Terephthalic Acid and its Esters

**[00112]** Example 51 - Preparation of Terephthalic Acid by Oxidation of the Reaction Products between *trans,trans* Muconic Acid and Ethylene




In a Parr pressure reactor, the product of example 50 (0.85 g, 5.0 mmol) is suspended in  $H_2O$  (120 ml, 0.04 M) and Pt/C (390 mg, 5 percent Pt/C, 2 mole percent Pt) powder is added. The reactor is pressurized with air (240 psi at 23 °C after saturation of the liquid phase) and its

contents heated to 150 °C set-point temperature for 3 days under rapid stirring (155 rpm). After opening the cooled Parr reactor, a white solid, partly submerged under the aqueous Pt/C suspension, is present on the surface of the glass reaction vessel. The combined material is filtered and repeatedly washed using copious quantities of hot methanol to provide, after concentration to dryness, a near white solid (0.43 g). <sup>1</sup>H NMR analysis shows the presence of 55 percent terephthalic acid, 40 percent *trans*-, and 5 percent *cis*-cyclohexane-1,4-dicarboxylic acid.

**[00113]** Example 52 - Preparation of Dimethyl Terephthalate - Oxidation


with Air at normal Pressure



Air is bubbled through a refluxing solution of dimethyl cyclohex-2-ene-1,4-dicarboxylate (0.25 g, 1.26 mmol) in acetic acid (20 ml) containing a catalytic amount of platinum on carbon powder (200 mg, 5 percent Pt/C, 10 mg Pt, 4 mole percent) for a period of 87 hours. <sup>1</sup>H NMR analysis of the cooled reaction suspension reveals about 69 percent conversion to the desired oxidation product. Filtration and removal of the solvent provides a near-white solid (0.24 g). Purification by column chromatography (Si35, SF40-80g, AnaLogix column with 13 percent ethyl acetate /hexane isocratic eluent) provides an analytical sample of dimethyl terephthalate.

**[00114]** Example 53 - Preparation of Dimethyl Terephthalate - Oxidation


with Air in a Parr Reactor




In a Parr pressure reactor, dimethyl cyclohex-2-ene-1,4-dicarboxylate (2.42 g, 12.2 mmol) is dissolved in cyclohexane (120 ml, 0.10 M) and a catalytic amount of platinum on carbon (476 mg, 5 percent Pt/C, 1 mole percent platinum) powder is added. The reactor is pressurized with air (240 psi (1.65 MPa) at 23 °C after saturation of the solution) and its contents are heated at a 150 °C set-point temperature for 3 days under rapid stirring (160 rpm). After opening the cooled Parr reactor, a suspension of black platinum on carbon (Pt/C) in a near colorless solution is present. All solvent is removed from a sample of the suspension, and the entire residue is dissolved in CDCl<sub>3</sub> for <sup>1</sup>H NMR analysis. Integration of the respective

resonances shows the presence of about 23 percent unreacted dimethyl cyclohex-2-ene-1,4-dicarboxylate starting material, of about 59 percent dimethyl terephthalate oxidation product, and of about 18 percent dimethyl cyclohexane-1,4-dicarboxylate disproportionation by-product. Column chromatography (Si35, SF40-150g, AnaLogix column with 10 percent ethyl acetate/hexane isocratic eluent) provides pure dimethyl terephthalate.

**[0090]** Example 54 - Reaction of *trans,trans* dimethyl muconate with ethylene and dehydrogenation in the same solvent




**[0091]** In a Parr reactor, a mixture of *trans,trans* dimethyl muconate (6.13 g, 36.0 mmol) and diglyme (120 ml, 0.30 M) is heated to 165 °C for 24 hours under ethylene pressure ( $p_{RT} = 259$  psi (1.79 MPa)). After cooling to room temperature, the weakly yellow, clear solution is diluted using diglyme to 200 ml in a volumetric flask, transferred into a round-bottom flask equipped with a magnetic stirring bar, and catalytic palladium on carbon (Pd/C) is added (356 mg of Johnson-Matthey 5 percent Pd/C # 6, 0.2 mole percent) at room temperature. The flask is equipped with a reflux condenser, fritted gas dispersion tube, and internal Temperature probe. Under  $N_2$  flow (190 ml/min) and stirring (190 rpm) the mixture is heated to reflux ( $T_{max, observed} = 169$  °C) while samples were taken at appropriate intervals ( $t = 0.0, 0.25, 0.5, 1.0, 2.0, 4.0, 8.0$  h) to monitor the progress of the reactions occurring. Rapid ( $t \leq 1$  h) disappearance of the dimethyl cyclohex-2-ene-1,4-dicarboxylate,  $\Delta^2/2$ -ene is observed concurrent with some material undergoing tautomerization to its thermodynamically more stable isomer (dimethyl cyclohex-1-ene-1,4-dicarboxylate,  $\Delta^1/1$ -ene), while also the desired oxidation/dehydrogenation/aromatization product dimethyl terephthalate (DMT) and some reduced material (dimethyl cyclohexane-1,4-dicarboxylate CHa) are formed. After 8 hours reaction time, 77 percent DMT, 17 percent cyclohexane, and 5 percent tautomer are present. The following graph shows the concentration of materials at various time intervals.



[0092] Examples 55 - 63

[0093] Synthesis of Dimethyl Terephthalate (DMT) - Batch Reaction



[0094] In a flask equipped with a reflux condenser, fritted gas dispersion tube, and internal T probe, a solution of dimethyl cyclohexene-1,4-carboxylate, both the 2-ene and 1-ene tautomer are starting materials, containing heterogeneous catalyst, palladium on a support, is heated to reflux under N<sub>2</sub> flow (190 ml/min) and stirring (190 rpm). Samples are taken at appropriate intervals ( $t = 0.0, 0.25, 0.5, 1.0, 2.0, 4.0, 8.0$  hours) to monitor the progress of the reactions occurring. Filtration to remove the catalyst, followed by solvent evaporation, and recrystallization of the remaining residue from methanol provides clean dimethyl terephthalate. The results are shown in Table 5.

[0095] Table 5

Ex	catalyst	equiv. T <sub>added</sub>	solvent c <sub>substrate</sub> (M)	% yield after 8 h reflux				c <sub>DMT</sub> /c <sub>CHa</sub> at 8 h
				Me <sub>2</sub> -Δ <sup>2</sup>	DMT	Me <sub>2</sub> - Δ <sup>1</sup>	Me <sub>2</sub> - CHa	
55	5 % Pd/C, 35 micron, JM # 6	0.2 mol % RT	<i>m</i> -xylene 0.18	3	42	46	9	4.5/1
56	5 % Pd/C, 35 micron, JM # 6	0.1 mol % RT	diglyme 0.18	3	39	49	9	4.3/1
54	5 % Pd/C, 35 micron, JM # 6	0.2 mol % RT	diglyme 0.18	0	77	5	17	4.6/1
57	5 % Pd/C, 35 micron, JM # 6	0.4 mol % RT	diglyme 0.18	0	76	0	21	3.7/1
58	5 % Pd/C, 35 micron, JM # 6	0.2 mol % RT	Et <sub>2</sub> diglyme 0.18	3	24	66	7	3.3/1
59	8.6 % Pd/Davisil 635, 60-100 mesh	0.3 mol % RT	diglyme 0.22	3	27	58	13	2.1/1
60	5 % Pd/Al <sub>2</sub> O <sub>3</sub> , 50 micron, JM # 12	0.3 mol % RT	diglyme 0.22	0	68	0	30	2.3/1
61	5 % Pd/Al <sub>2</sub> O <sub>3</sub> , 50 micron, JM # 12	0.3 mol % reflux	triglyme 0.22	0	75	0	23	3.3/1
62	5 % Pd(S)/C, 25 micron, JM # 11	0.3 mol % RT	diglyme 0.22	0	73	0	25	2.9/1
63	5 % Pt/C, 30 micron, JM # 23	0.3 mol % RT	diglyme 0.22	16	13	65	6	2.2/1


JM = Johnson-Matthey commercial catalyst screening kit. T<sub>final reflux</sub> = 145 °C (*m*-xylene), 162 °C (diglyme), 190 °C (Et<sub>2</sub>diglyme), and 225 °C (triglyme).

[0096] Davisil is a magnesium silica gel. Et<sub>2</sub>diglyme is diethyl diglycol ether.

Microns refer to the mean particle size.

[0097] Example 64 - Hydrolysis of Dimethyl Terephthalate to Terephthalic Acid Following, US-4,302,595, incorporated herein by reference, a suspension of dimethyl terephthalate in H<sub>2</sub>O is heated to 250 °C for 4 hour in a Parr pressure reactor resulting in hydrolysis to terephthalic acid.


[0098] Examples 66 and 67 - High Yield Synthesis of Dimethyl Cyclohexane-1,4-dicarboxylate



**[0099]** A solution of dimethyl cyclohex-2-ene-1,4-dicarboxylate and dimethyl cyclohex-1-ene-1,4-dicarboxylate is hydrogenated under balloon pressure at room temperature over Pd/C catalyst. If methylene chloride is used as the solvent, primarily the 2-ene tautomer is reduced, whereas most of the 1-ene tautomer remains unreacted. If ethanol is used as the solvent both tautomers are reduced.


**[00100]** Substituted Diels-Alder Products and Terephthalates

**[00101]** Example 68 - Dimethyl 2-Chloro-cyclohexene-1,4-dicarboxylate, Dimethyl Chloro-terephthalate, and Dimethyl 2-Chloro-cyclohexane-1,4-dicarboxylate




**[00102]** In a Parr pressure reactor, a stirred suspension of *trans,trans* dimethyl muconate (6.1 g, 36 mmol) in dimethyldipropyleneglycol (120 ml, 0.3 M) is heated under vinyl chloride pressure (18 psi (0.124 MPa) at 23 °C) to 165 °C for 48 hours. After cooling to room temperature, the reaction mixture is diluted using the same solvent to 200 ml in a volumetric flask, transferred into a round-bottom flask equipped with a magnetic stirring bar, and Pd/C catalyst is added (360 mg of Johnson-Matthey 5 percent Pd/C # 6, 0.2 mol percent) at room temperature. The flask is equipped with a reflux condenser, fritted gas dispersion tube, and internal T probe. Under N<sub>2</sub> flow (190 ml/min) and stirring (190 rpm) the mixture is heated to reflux while samples are taken at appropriate intervals ( $t = 0.0, 0.25, 0.5, 1.0, 2.0, 4.0, 8.0$  h) to monitor the progress of the reactions occurring. After 8 hour reaction time, dimethyl chloro-terephthalate is present. Some material also undergoes C-Cl bond cleavage and dimethyl 2-chloro-cyclohexane-1,4-dicarboxylate is also formed.

**[00103]** Example 69 - Dimethyl 2-Methyl-cyclohexene-1,4-dicarboxylate, Dimethyl Methyl-terephthalate, and Dimethyl 2-Methyl-cyclohexane-1,4-dicarboxylate




In a Parr pressure reactor, a stirred suspension of *trans,trans* dimethyl muconate (6.1 g, 36 mmol) in diglyme (120 ml, 0.3 M) is heated under propylene pressure (119 psi (.0820 MPa) at 23 °C) to 165 °C for 48 hours. After cooling to room temperature, the reaction mixture is transferred to a flask and concentrated (0.5 M). Pd/C catalyst is added (0.3 mol percent of Johnson-Matthey 5 percent Pd/C # 6) at room temperature. The flask is equipped with a reflux condenser, fritted gas dispersion tube, and internal Temperature probe. Under N<sub>2</sub> flow (190 ml/min) and stirring (190 rpm) the mixture is heated to reflux for 27 hours whereby dimethyl methyl-terephthalate is formed. Some dimethyl 2-methyl-cyclohexane-1,4-dicarboxylate is also produced.

**[00106]** Example 70 - Trimethyl Cyclohexene-1,2,4-tricarboxylate, Trimethyl Trimellitate, and Trimethyl Cyclohexane-1,2,4-tricarboxylate




**[00107]** In a 75 ml sealed tube, a stirred suspension of *trans,trans* dimethyl muconate (10.0 g, 58.8 mmol), two equivalents of methyl acrylate (10.6 ml, 117.6 mmol), neutral Al<sub>2</sub>O<sub>3</sub> (300 mg of Aldrich 199974, 3 mass percent), and *tert*-butyl catechol (25 mg, 0.2 mol percent) in diglyme (20 ml, 2.9 M) is heated to 150 °C for 24 hours. After cooling to room temperature, the reaction mixture is filtered, transferred to a flask, and concentrated (0.5 M). Pd/C catalyst is added (856 mg (0.3 mol percent) of Johnson-Matthey 5 percent Pd/C # 6) at room temperature. The flask is equipped with a reflux condenser, fritted gas dispersion tube, and internal T probe. Under N<sub>2</sub> flow (190 ml/min) and stirring (190 rpm) the mixture is heated to reflux for 27 hours whereby trimethyl trimellitate (46 percent over 2 steps) is formed. Some trimethyl cyclohexane-1,2,4-tricarboxylate is also produced.

**[00108]** Example 71 - Dimethyl 2-Phenyl-cyclohexene-1,4-dicarboxylate, Dimethyl Phenyl-terephthalate, and Dimethyl 2-Phenyl-cyclohexane-1,4-dicarboxylate




**[00109]** In a 75 ml sealed tube, a stirred suspension of *trans,trans* dimethyl muconate (10.0 g, 58.8 mmol), two equivalents of styrene (13.5 ml, 117.6 mmol), neutral  $\text{Al}_2\text{O}_3$  (300 mg of Aldrich 199974, 3 mass percent), and *tert*-butyl catechol (25 mg, 0.2 mol percent) in diglyme (20 ml, 2.9 M) is heated to 150 °C for 24 hours. After cooling to room temperature, the reaction mixture is filtered, transferred to a flask, and concentrated. The residue is redissolved in triglyme (0.5 M). Pd/ $\text{Al}_2\text{O}_3$  catalyst is added (636 mg (0.5 mol percent) of Johnson-Matthey 5 percent Pd/ $\text{Al}_2\text{O}_3$  # 12) at room temperature. The flask is equipped with a reflux condenser, fritted gas dispersion tube, and internal Temperature probe. Under  $\text{N}_2$  flow (190 ml/min) and stirring (190 rpm) the mixture is heated to reflux for 63 hours whereby dimethyl phenyl-terephthalate is formed. Some dimethyl 2-phenyl-cyclohexane-1,4-dicarboxylate is also produced.

**[00110]** Example 72 - Thermal isomerization of *cis,trans* muconic acid to *trans,trans* muconic acid



**[00112]** A mixture of *cis,trans* muconic acid (5.11 g, 36.0 mmol) and Methanol (200 ml, 0.18 M) is heated to reflux. At appropriate intervals ( $t = 0, 2, 4, 24, 48, 72, 96, 168$  hours) samples are analyzed by HPLC to determine the amounts of *cis,trans* muconic acid and *trans,trans* muconic acid being present. After 168 hours reaction time, 5.1 percent of *trans,trans* muconic acid are found to be present with the remaining material being unreacted *cis,trans* muconic acid.


**[00113]** Example 73 - Pd/C-catalyzed isomerization of *cis,trans* muconic acid to *trans,trans* muconic acid



**[00115]** A mixture of *cis,trans* muconic acid (5.11 g, 36.0 mmol), Pd/C (511 mg of 5 percent Pd/C, 10 mass percent), and methanol (200 ml, 0.18 M) is heated to reflux. At appropriate intervals ( $t = 0, 2, 4, 24, 48, 72, 96, 168$  hours) samples are analyzed by HPLC to determine the amounts of *cis,trans* muconic acid and *trans,trans* muconic acid being present. After 168 hour reaction time, 22.7 percent of *trans,trans* muconic acid are found to be present with the remaining material being unreacted *cis,trans* muconic acid.

**[00116]** Oxidation to Esters of Trimellitic Acid

**[00117]** Example 74 - Preparation of Trimethyl Trimellitate




Trimethyl cyclohex-5-ene-1,2,4-tricarboxylate (200 mg, 0.78 mmol) is mixed with 305 mg of 5 percent by weight platinum on a carbon support in *m*-xylene (30 ml). The reaction mixture is refluxed with the reflux apparatus being open to air for 4 days. The residual platinum on carbon is then filtered off and the filtrate is concentrated down to a clear colorless gel. The desired product is obtained with a 65 percent yield. The yield is determined by GC/MS using a dodecane as an internal standard.

**[00118]** Example 75 - Preparation of 2-butyl-1,4-dimethyl benzene-1,2,4-tricarboxylate

Tri-*n*-butyl cyclohex-5-ene-1,2,4-tricarboxylate (500 mg, 1.7 mmol) is mixed with 5 percent by weight platinum on a carbon support (663 mg) in *m*-xylene (30 ml). The reaction mixture is refluxed with the reflux apparatus being open to air for 4 days. The residual platinum on a carbon support is then filtered off and the filtrate is concentrated down to a clear colorless gel. The resulting residue purified by column chromatography using an Analogix BSR SimpliFlash system (Hexanes/Ethyl acetate, 9:1). Due to very similar polarities between the starting material and the desired product, they cannot be completely separated. In order to determine a yield, the 2-butyl-1,4-dimethylbenzene-1,2,4-tricarboxylate undergoes a transesterification to form the trimethyl trimellitate. The transesterification does not go to completion and the yield determined by GC is 48 percent.


**[00119]** Reduction to Esters of Cyclohexane-1,2,4-tricarboxylic Acid

**[00120]** Example 76 - Preparation of Trimethyl Cyclohexane-1,2,4-tricarboxylate



A solution of trimethyl cyclohex-5-ene-1,2,4-tricarboxylate (0.50 g, 1.9 mmol) in methylene chloride (15 ml) containing a catalytic amount of palladium on carbon (150 mg, 5 percent Pd/C, 7.5 mg Pd, 4 mole percent) is stirred at room temperature under balloon pressure of hydrogen gas for 2 hours, at which point GC-MS analysis shows complete conversion. Filtration and removal of the solvent provides trimethyl cyclohexane-1,2,4-tricarboxylate as a clear, colorless gel (0.42 g, 1.6 mmol, 85 percent yield).

**[00121]** Example 77 - Isomerization of *cis,cis*-muconic acid to *cis,trans*-muconic acid in water



*cis,cis*-Muconic acid (265 g) is suspended in water (2 L) and the pH of the solution is adjusted to 5.1 with 10 M NaOH (250 mL). The mixture is heated at 90°C for 2 hours. The progress of the isomerization is monitored by HPLC. After 2 hours of heating at 90°C, the mixture is treated with charcoal (20 g) for 30 minutes and the hot solution is filtered through a thin bed of Celite. The solution is adjusted to a pH of 2 with concentrated sulfuric acid (50 mL) and allowed to cool to 0°C in an ice-bath. The precipitate is recovered by filtration and dried under reduced pressure overnight to yield 71 g *cis,trans*-muconic acid as light yellow solid. The filtrate is concentrated to 600 mL and allowed to incubate at 0°C overnight. More precipitate is observed and is filtered and dried to yield an additional 152 g of *cis,trans*-muconic acid, an overall yield of 84 percent is achieved.

**[00122]** Example 78 - Isomerization of *cis,trans*-muconic acid to *trans,trans*-muconic acid in Methanol



*cis,trans*-Muconic acid (105 mg, 0.739 mmol) is dissolved in methanol (10 mL) at room temperature and a crystal of iodine (26 mg, 0.102 mmol) is added. The reaction mixture is allowed to stir at room temperature for 24 hours. The precipitate is filtered, washed with ice-cold acetonitrile and dried under reduced pressure to yield 65 mg of *trans,trans*-muconic acid, a 62 percent yield.

**[00123]** Example 79 - Isomerization of *cis,trans*-Muconic acid to *trans,trans*-Muconic acid in Ethanol



*cis,trans*-Muconic acid (105 mg, 0.739 mmol) is dissolved in ethanol (10 mL) at room temperature and a crystal of iodine (13 mg, 0.05 mmol) is added. The reaction mixture is allowed to stir at room temperature for 24 hour. The precipitate is filtered, washed with acetonitrile and dried under reduced pressure to yield 70 mg of *trans,trans*-muconic acid, a 67 percent yield.

**[00124]** Example 80 - Isomerization of *cis,trans*-Muconic acid to *trans,trans*-Muconic acid in *n*-Propanol

*cis,trans*-Muconic acid (103 mg, 0.725 mmol) is dissolved in *n*-propanol (10 mL) at room temperature and a crystal of iodine (10 mg, 0.04 mmol) is added. The reaction mixture is allowed to stir at room temperature for 24 hours. The precipitate is filtered, washed with acetonitrile and dried under reduced pressure to yield 75 mg of *trans,trans*-muconic acid, a 73 percent yield.

**[00125]** Example 81 - Isomerization of *cis,trans*-Muconic acid to *trans,trans*-Muconic acid in *n*-Butanol

*cis,trans*-Muconic acid (105 mg, 0.739 mmol) is dissolved in *n*-butanol (10 mL) at room temperature and a crystal of iodine (17 mg, 0.067 mmol) is added. The reaction mixture is allowed to stir at room temperature for 24 hours. The precipitate is filtered, washed with ice-cold acetonitrile and dried under reduced pressure to yield 80 mg of *trans,trans*-muconic acid, a 76 percent yield.


**[00126]** Example 82 - Isomerization of *cis,trans*-Muconic acid to *trans,trans*-Muconic acid in Acetone

*cis,trans*-Muconic acid (109 mg, 0.767 mmol) is dissolved in acetone (10 mL) at room temperature and a crystal of iodine (13 mg, 0.05 mmol) was added. The reaction mixture is allowed to stir at room temperature for 24 hour. The precipitate is filtered, washed with ice-cold acetonitrile and dried under reduced pressure to yield 15 mg of *trans,trans*-muconic acid, a 13 percent yield.

**[00127]** Example 83 - Isomerization of *cis,trans*-Muconic acid to *trans,trans*-Muconic acid in Ethyl acetate


*cis,trans*-muconic acid (103 mg, 0.767 mmol) is dissolved in ethyl acetate (10 mL) at room temperature and a crystal of iodine (27 mg, 0.106 mmol) is added. The reaction mixture is allowed to stir at room temperature for 24 hours. The precipitate is filtered, washed with ice-cold acetonitrile and dried under reduced pressure to yield 60 mg of *trans,trans*-muconic acid, a 58 percent yield.

**[00128]** Example 84 - Isomerization of *cis,trans*-Muconic acid to *trans,trans*-muconic acid in ethyl ether




*cis,trans*-Muconic acid (119 mg, 0.838 mmol) is dissolved in ethyl ether (10 mL) at room temperature and a crystal of iodine (7.2 mg, 0.028 mmol) is added. The reaction mixture is allowed to stir at room temperature for 24 hour. The precipitate is filtered, washed with ice-cold acetonitrile and dried under reduced pressure to yield 100 mg of *trans,trans*-muconic acid, a 84 percent yield.

**[00129]** Example 85 - Isomerization of *cis,trans*-muconic acid to *trans,trans*-muconic acid in tetrahydrofuran



*cis,trans*-Muconic acid (38.3 g, 269.7 mmol) is dissolved in THF (400 mL) at room temperature and a crystal of iodine (247 mg, 0.972 mmol) is added. The reaction mixture is allowed to stir at room temperature for 24 hours. The precipitate is obtained by filtration, washed with ice-cold tetrahydrofuran (2X) and dried under reduced pressure to yield 33.2 g (a 86percent yield) of *trans,trans*-muconic acid.

**[00130]** Examples 86 to 90 - Isomerization of *cis,trans*-dimethyl muconate to *trans,trans*-dimethyl muconate




Several experiments for the isomerization of *cis,trans*-dimethyl muconate to *trans,trans*-dimethyl muconate are performed according to the following procedure. *Cis,trans*-dimethyl muconate is dissolved in tetrahydrofuran (50 mL) and stirred. Iodine is then added and the progress of the isomerization is monitored by HPLC. The precipitate, *trans,trans*-dimethyl muconate, is obtained by filtration and washed with ice-cold

tetrahydrofuran. The filtrate is analyzed by HPLC to determine the total yield of the conversion. Table 6 summarizes the results obtained for this reaction.

Table 6

Example	Amount Muconate g	Amount Iodine mg	Time hours	Yield percent Isolated	Yield percent Total
86	10	74.7	3	88	97
87	10	75.3	5	54	75
88	10	79.3	24	91	100
89	10	78.6	6	90	94
90	10	80.0	6	91	97


[00131]

Example 91 - Synthesis of *cis,trans*-dimethyl muconate

*cis,trans*-muconic acid (42.6 g, 0.30 mol) is dissolved in methanol (1500 mL) to which is added concentrated sulfuric acid (2 mL, 0.037 mol). The resulting solution is refluxed for 24 hours and the progress of the reaction is monitored by HPLC. Once the conversion of *cis,trans*-dimethyl muconate is completed as detected by HPLC, the reaction is cooled to room temperature and concentrated until white solid began crashing out and the reaction mixture is then cooled to 0°C overnight. The *cis,trans*-dimethyl muconate is obtained by filtration, washed with cold tetrahydrofuran and dried under reduced pressure to provide a total yield of 95 percent.

What is claimed is:

1. A composition comprising a compound corresponding to the formula



wherein:

R<sup>1</sup> is independently in each occurrence hydrogen or a hydrocarbyl group optionally containing a heteroatom containing functional group wherein the hydrocarbyl group does not interfere in the formation of the cyclohexene compound;

R<sup>2</sup> is independently in each occurrence hydrogen or a hydrocarbyl group optionally containing a heteroatom containing functional group wherein the hydrocarbyl group does not interfere in the formation of the cyclohexene compound; and


R<sup>3</sup> is independently in each occurrence hydrogen or a hydrocarbyl group optionally containing a heteroatom containing functional group wherein the hydrocarbyl group does not interfere in the formation of the cyclohexene compound;

with the proviso that R<sup>2</sup> and R<sup>3</sup> may be combined to form a cyclic ring which may contain heteroatoms;

Z is independently in each occurrence an anion, oxygen, nitrogen, sulfur halogen or nitrile; and,

b is independently in each occurrence 0, 1 or 2 with the proviso that b is 0 when Z is an anion, nitrile or halogen; 1 when Z is oxygen or sulfur and 2 when Z is nitrogen; wherein the compounds contain detectable traces of Carbon 14 and 6 or more of the carbon atoms are derived from renewable resources.

2. A composition according to Claim 1 wherein the composition comprises Carbon 14 in an amount of up to about 1 part per trillion.
3. A composition according to Claim 1 comprising compounds corresponding to the formula



wherein:

$R^1$  is independently in each occurrence hydrogen or a hydrocarbyl group optionally containing a heteroatom containing functional group wherein the hydrocarbyl group does not interfere in the formation of the cyclohexene compound;


$R^2$  is independently in each occurrence hydrogen or a hydrocarbyl group optionally containing a heteroatom containing functional group wherein the hydrocarbyl group does not interfere in the formation of the cyclohexene compound; and

$R^3$  is independently in each occurrence hydrogen or a hydrocarbyl group optionally containing a heteroatom containing functional group wherein the hydrocarbyl group does not interfere in the formation of the cyclohexene compound; with the proviso that  $R^2$  and  $R^3$  may be combined to form a cyclic ring which may contain heteroatoms.

4. A composition according to Claim 3 wherein:

$R^1$  is independently in each occurrence a  $C_{1-10}$  alkyl group; and  $R^2$  and  $R^3$  are independently in each occurrence hydrogen, alkyl, alkaryl, aryl, carboxyoxy alkyl or may be combined to form a cyclic ring which may contain one or more hetero atoms.

5. A composition according to Claim 1 comprising compounds corresponding to the formula



wherein

$R^1$  is independently in each occurrence hydrogen, a hydrocarbyl group optionally containing a heteroatom containing functional group;

$R^3$  is independently in each occurrence hydrogen, alkyl, alkaryl, aryl, carboxyoxy alkyl which

may contain one or more hetero atoms;

R<sup>4</sup> is independently in each occurrence hydrogen, a hydrocarbyl group optionally containing a heteroatom containing functional group;

R<sup>5</sup> is independently in each occurrence a hydrocarbyl group optionally containing a heteroatom containing functional group; and

a is independently in each occurrence an integer of from 0 to 5.

6. A method for preparing a compound according to any one of Claims 1 to 5 comprising contacting one or more muconic acid dienes or carboxylate derivatives thereof with one or more dienophiles under conditions such that the one or more muconic acid dienes or carboxylate derivatives thereof and one or more dienophiles form one or more cyclohexene ring containing compounds; and contacting the cyclohexene ring containing compounds with a dehydrogenation catalyst under conditions such that one or more compounds containing a benzene ring with carboxylate derivatives at the 1 and 4 position are formed.

7. A method according to Claim 6 wherein the cyclohexene ring containing compounds are contacted with a dehydrogenation catalyst in the presence of an oxidant.

8. A method according to Claim 6 or 7 wherein the temperature of contacting the one or more muconic acids or carboxylate derivatives with one or more dienophiles is about 130 °C to about 170 °C.

9. A method according to any one of Claims 6 to 8 wherein the one or more muconic acids or carboxylate derivatives thereof are in the *trans, trans* isomeric arrangement.

10. A method according to any one of Claims 6 to 9 wherein one or more carboxylate esters of muconic acid are contacted with the one or more dienophiles.

11. A method according to any one of Claims 6 to 10 wherein the one or more dienophiles comprise one or more unsaturated cyclic compounds, one or more unsaturated esters or aromatic compounds having at least one unsaturated substituent.

12. A method according to any one of Claims 6 to 11 wherein the one or more dienophiles are reacted with one or more *trans, trans* muconic acids or carboxylate derivatives thereof, wherein the one or more of muconic acid or carboxylate derivatives thereof are prepared by a process including the step of isomerization of one or more of *cis, cis* muconic


acid or carboxylate derivatives thereof and *cis, trans* muconic acid and carboxylate derivatives thereof to *trans,trans* muconic acid and carboxylate derivatives thereof.

13. A method according to any one of Claims 6 to 12 wherein the one or more of muconic acid, or carboxylate esters thereof, are prepared from one or more of *cis, trans* and *cis, cis* muconic acid which process comprises contacting one or more of *cis, cis* and *cis,trans* muconic acids or carboxylate esters thereof, with one or more isomerization catalysts, a source of ultraviolet radiation or both in a solvent for a period of time such that the *cis, cis* and/or *cis,trans* muconic acid, or carboxylate esters thereof, isomerize to *trans,trans* muconic acid or carboxylate esters thereof.


14. A method according to any one of Claims 6 to 13 wherein one or more *trans,trans* carboxylate esters of muconic acid are reacted with the one or more dienophiles wherein the *trans, trans* esters of muconic acid are prepared by

- a) contacting *cis, cis* muconic acid and one or more isomerization catalysts, a source of ultraviolet radiation or both in a solvent for a period of time such that the *cis, cis* muconic acid isomerizes to *trans, trans* muconic acid;
- b) recovering the *trans, trans* muconic acid; and
- c) contacting the *trans, trans* muconic acid with one or more esterifying agents in the presence of one or more strong acids under conditions that one or more *trans, trans* dialkyl muconates are formed.


15. A method according to any one of Claims 6 to 14 wherein the muconic acids or carboxylate derivatives thereof correspond to one of the formulas;




the dienophile corresponds to the formula;



the cyclohexene compound corresponds to one of the formulas



and the compounds prepared correspond to the formula



wherein

the dienophile contains one or more double or triple bonds;

$R^1$  is independently in each occurrence hydrogen or a hydrocarbyl group optionally containing a heteroatom containing functional group wherein the hydrocarbyl group does not interfere in the formation of the cyclohexene compound;

$R^2$  is independently in each occurrence hydrogen or a hydrocarbyl group optionally containing a heteroatom containing functional group wherein the hydrocarbyl group does not interfere in the formation of the cyclohexene compound; and

$R^3$  is independently in each occurrence hydrogen or a hydrocarbyl group optionally containing a heteroatom containing functional group wherein the hydrocarbyl group does not interfere in the formation of the cyclohexene compound;

with the proviso that  $R^2$  and  $R^3$  may be combined to form a cyclic ring which may contain heteroatoms;

$Z$  is independently in each occurrence an anion, oxygen, nitrogen, sulfur halogen or nitrile; and,

$b$  is independently in each occurrence 0, 1 or 2 with the proviso that  $b$  is 0 when  $Z$  is an anion, nitrile or halogen; 1 when  $Z$  is oxygen or sulfur and 2 when  $Z$  is nitrogen.

16. A method for preparing one or more terephthalate ester based compounds according to Claim 6 comprising

a) contacting *cis, cis* muconic acid and iodine, exposing the *cis, cis* muconic acid to

ultraviolet light, or both in a protic or aprotic solvent for a period of time such that the *cis,cis* muconic acid isomerizes to the *trans,trans* muconic acid;

- b) recovering the *trans,trans* muconic acid; and
- c) contacting the *trans,trans* muconic acid with an alkanol in the presence of a strong acid under conditions that *trans,trans* dialkyl muconate is formed:
- d) contacting the dialkyl muconate with one or more dienophiles at a temperature of about 130 °C to about 170 °C under conditions such that the dialkyl muconate and one or more dienophiles form one or more cyclohexene ring containing compounds; and
- e) contacting the cyclohexene ring containing compounds with an oxidant in the presence of one or more dehydrogenation catalysts under conditions such that one or more compounds containing a benzene ring with alkyl carboxylate or carboxylic acid groups at the 1 and 4 position are prepared.

17. A method according to Claim 16 wherein the *cis,cis* muconic acid is prepared by microbial synthesis under fermentor controlled conditions.

18. A method according to Claim 6 comprising contacting one or more of *cis,cis* and *cis,trans* muconic acids or carboxylate esters thereof, with one or more isomerization catalysts, a source of ultraviolet radiation or both and one or more dienophiles in a solvent under conditions such that the one or more muconic acid dienes or carboxylate derivatives thereof and one or more dienophiles form one or more cyclohexene ring containing compounds; and

contacting the cyclohexene ring containing compounds with a dehydrogenation catalyst under conditions such that one or more compounds containing a benzene ring with carboxylate derivatives at the 1 and 4 position are formed.

19. A method according to Claim 18 comprising contacting one or more muconic acid dienes or carboxylate derivatives thereof with one or more dienophiles in a solvent under conditions such that the one or more muconic acid dienes or carboxylate derivatives thereof and one or more dienophiles form one or more cyclohexene ring containing compounds; and contacting the cyclohexene ring containing compounds in the solvent of the first step with a dehydrogenation catalyst under conditions such that one or more compounds containing a benzene ring with carboxylate derivatives at the 1 and 4 position are formed.

20. A method according to Claim 19 wherein the solvent is a glycol ether or polyglycol ether.

21. A method according to Claim 6 comprising contacting one or more muconic acids or carboxylates thereof with one or more 1,2-acetylenic acids or esters thereof in air or an inert gas at elevated temperature and elevated pressure under conditions such that the one or more muconic acids or carboxylate derivatives thereof and one or more 1,2-acetylenic acids or esters thereof form one or more trimellitates.

22. A method according to any one of Claims 6 to 21 wherein the cyclohexene compounds are derived from muconic acid prepared from renewable resources.

23. A method according to Claim 6 comprising contacting one or more muconic acids or carboxylate derivatives thereof with one or more dienophiles comprising one or more acrylic acids or esters thereof at elevated temperatures under conditions such that the one or more muconic acids or carboxylate derivatives thereof and acrylic acids or esters thereof form one or more cyclohexene ring containing compounds wherein a carboxylate is substituted on the cyclohexane ring at the 1, 2 and 4 positions; and contacting the cyclohexene ring containing compound with an oxidant under conditions such that one or more trimellitic acid or carboxylates thereof are prepared.