P/00/008
Section 29(1)
Regulation 3.1(2)

AUSTRALIA
Patents Act 1990

NOTICE OF ENTITLEMENT

I/We BASF LACKE + FARBEN AKTIENGESELLSCHAFT

of GLASURITSTRASSE 1
D-48165 MUNSTER
GERMANY

being the applicant(s) and nominated person(s) in respect of an application for a patent for an invention entitled PROCESS FOR THE PRODUCTION OF A TWO-COAT FINISH, AND POWDER COATINGS SUITABLE FOR THIS PROCESS (Application No. 45001/93), state the following:

1. The nominated person(s) has/have, for the following reasons, gained entitlement from the actual inventor(s):

   THE NOMINATED PERSON WOULD BE ENTITLED TO HAVE ASSIGNED TO IT A PATENT GRANTED TO ANY OF THE INVENTORS IN RESPECT OF THE SAID INVENTION.

2. The nominated person(s) has/have, for the following reasons, gained entitlement from the applicant(s) listed in the declaration under Article 8 of the PCT:

   THE APPLICANT AND NOMINATED PERSON IS THE BASIC APPLICANT.

3. The basic application(s) listed in the declaration under Article 8 of the PCT is/are the first application(s) made in a Convention country in respect of the invention.

DATED: 7 December 1994

BASF LACKE + FARBEN AKTIENGESELLSCHAFT

GRIFFITH HACK & CO.

Patent Attorney for and
on behalf of the applicant

AU9345001

(12) PATENT ABRIDGMENT (11) Document No. AU-B-45001/93
(19) AUSTRALIAN PATENT OFFICE (10) Acceptance No. 668578

(54) Title
PROCESS FOR OBTAINING A DOUBLE-LAYER COATING AND POWDER LACQUER FOR IMPLEMENTING THIS PROCESS

International Patent Classification(s)
(51)[5] C09D 133/14 B05D 007/16 C08G 059/32 C09D 167/02
(51)[6] C09D 005/03 C09D 133/08 C09D 133/12

(21) Application No. : 45001/93 (22) Application Date : 23.06.93

(87) PCT Publication Number : WO94/01504

(30) Priority Data

(31) Number	(32) Date	(33) Country
4222194	07.07.92	DE GERMANY

(43) Publication Date : 31.01.94

(44) Publication Date of Accepted Application : 09.05.96

(71) Applicant(s)
BASF LACKE + FARBEN AKTIENGESELLSCHAFT

(72) Inventor(s)
WOLFGANG KRANIG; KLAUS CIBURA; JOACHIM WOLTERING; CHRISTOPHER HILGER; JOSEF RADEMACHER

(74) Attorney or Agent
GRIFFITH HACK & CO , GPO Box 1285K, MELBOURNE VIC 3001

(56) Prior Art Documents
AU 632617 62220/90 C09D 133/08
AU 616059 43152/89 C09D 133/08
DE 4032391

(57) Claim

1. Process for the production of two-coat finishes on a substrate surface, in which

(1) a pigmented basecoat is applied to the substrate surface,

(2) a polymer film is formed from the coat applied in step (1),

(3) a, powder clearcoat which contains an epoxide group-containing polyacrylate resin as binder is applied to the resulting basecoat film, and subsequently

(4) the basecoat is baked together with the powder clearcoat,q

characterized in that the powder clearcoat employed in step (3) as crosslinking agent contains a mixture of

.../2

(A) 5 to 95 percent by weight of a compound which contains on statistical average at least two carboxyl groups and at least one acid anhydride group per molecule, or a mixture of such compounds, and

(B) 95 to 5 percent by weight of a carboxyl group-containing polyester resin obtainable by reacting

(b1) a diol or a mixture of diols,

(b2) a compound which contains per molecule at least three functional groups selected from hydroxyl, primary amino, secondary amino, carboxyl and acid anhydride groups, one acid anhydride group being regarded as equivalent to two carboxyl groups, or a mixture of such compounds and

(b3) a dicarboxylic acid, a dicarboxylic acid anhydride or a mixture of dicarboxylic acids and/or dicarboxylic acid anhydrides

in a molar ratio of (b1) : (b2) : (b3) = 0.0 to 3.0 : 1.0 : 1.5 to 9.0 to give a polyester resin having an acid value of 40 to 300,

the percentages by weight relating to (A) + (B) = 100 percent by weight.

2. Powder coatings which contain an epoxide group containing polyacrylate resin as binder, characterized in that they contain as crosslinking agent a mixture of

(A) 5 to 95 percent by weight of a compound which contains on statistical average at least two carboxyl groups and at least one acid anhydride group

per molecule, or a mixture of such compounds, and

(B) 95 to 5 percent by weight of a carboxyl group-containing polyester resin obtainable by reacting

(b1) a diol or a mixture of diols,

(b2) a compound which contains per molecule at least three functional groups selected from hydroxyl, primary amino, secondary amino, carboxyl and acid anhydride groups, one acid anhydride group being regarded as equivalent to two carboxyl groups, or a mixture of such compounds and

(b3) a dicarboxylic acid, a dicarboxylic acid anhydride or a mixture of dicarboxylic acids and/or dicarboxylic acid anhydrides

in a molar ratio of (b1) : (b2) : (b3) = 0.0 to 3.0 : 1.0 : 1.5 to 9.0 to give a polyester resin having an acid value of 40 to 300,

the percentages by weight relating to (A) + (B) = 100 percent by weight.

OPI DATE 31/01/94 APPLN. ID 45001/93
AOJP DATE 28/04/94 PCT NUMBER PCT/EP93/01601

AU9345001

INTERNATIONALE ANMELDUNG VERÖFFENTLICHT NACH DEM VERTRAG ÜBER DIE INTERNATIONALE ZUSAMMENARBEIT AUF DEM GEBIET DES PATENTWESENS (PCT)

(51) Internationale Patentklassifikation 5 :
C09D 133/14, 167/02
B05D 7/16, C08G 59/32

A1

(11) Internationale Veröffentlichungsnummer: WO 94/01504

(43) Internationales Veröffentlichungsdatum: 20. Januar 1994 (20.01.94)

(21) Internationales Aktenzeichen: PCT/EP93/01601

(22) Internationales Anmeldedatum: 23. Juni 1993 (23.06.93)

(30) Prioritätsdaten:
P 42 22 194.3 7. Juli 1992 (07.07.92) DE

(71) Anmelder *(für alle Bestimmungsstaaten ausser US)*: BASF LACKE + FARBEN AKTIENGESELLSCHAFT [DE/DE]; Glasuritstraße 1, D-48165 Münster (DE).

(72) Erfinder; und
(75) Erfinder/Anmelder *(nur für US)* : KRANIG, Wolfgang [DE/DE]; Erlengrund 42, D-4403 Senden (DE). CIBURA, Klaus [DE/DE]; Am Schütthook 159, D-4400 Münster (DE). WOLTERING, Joachim [DE/DE]; Rudolphstraße 24, D-4400 Münster (DE). HILGER, Christopher [DE/DE]; Goebenstraße 33, D-4400 Münster (DE). RADEMACHER, Josef [DE/DE]; Linckensstraße 33, D-4400 Münster (DE).

(81) Bestimmungsstaaten: AU, BR, CA, JP, US, europäisches Patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).

Veröffentlicht
Mit internationalem Recherchenbericht.

668578

(54) Title: PROCESS FOR OBTAINING A DOUBLE-LAYER COATING AND POWDER LACQUER FOR IMPLEMENTING THIS PROCESS

(54) Bezeichnung: VERFAHREN ZUR HERSTELLUNG EINER ZWEISCHICHTIGEN LACKIERUNG UND FÜR DIESES VERFAHREN GEEIGNETE PULVERLACKE

(57) Abstract

A process is disclosed for obtaining a double-layer coating. A pigmented base paint is first applied, the thus obtained base paint layer is covered with a translucent powder lacquer and finally the base paint layer and the translucent lacquer layer are baked together. As translucent powder lacquer is used a powder lacquer which contains an epoxide group-containing polyacrylate resin as binder and a mixture of (A) a polyanhydride and (B) a carboxyl group-containing polyester resin as cross-linking agent. The polyester resin is produced by reacting a diol (b1), a compound (b2) that contains per molecule at least three functional groups selected among hydroxyl, primary amino, secondary amino, carboxyl and acid anhydride groups and (b3) a dicarboxylic acid, in a molar ratio between (b1) : (b2) : (b3) equal to 0.0-3.0:1.0:1.5-9.0, until a polyester resin having an acid number from 40 to 300 is obtained.

(57) Zusammenfassung

Die Erfindung betrifft ein Verfahren zur Herstellung von Zweischichtlackierungen, bei dem ein pigmentierter Basislack vorlackiert wird, die so erhaltene Basislackschicht mit einem Pulverklarlack überlackiert wird und anschließend Basislakschicht und Klarlackschicht zusammen eingebrannt werden. Als Pulverklarlack wird erfindungsgemäß ein Pulverlack eingesetzt, der ein epoxidgruppenhaltiges Polyacrylatharz als Bindemittel und eine Mischung aus (A) einem Polyanhydrid und (B) einem carboxylgruppenhaltigen Polyesterharz als Vernetzungsmittel enthält. Das Polyesterharz ist herstellbar, indem ein Diol (b1), eine Verbindung (b2), die pro Molekül mindestens drei funktionelle Gruppen ausgewählt aus Hydroxyl-, primären Amino-, sekundären Amino-, Carboxyl- und Säureanhydridgruppen enthält und (b3) eine Dicarbonsäure in einem Molverhältnis von (b1):(b2):(b3) = 0,0 bis 3,0:1,0:1,5 bis 9,0 zu einem Polyesterharz mit einer Säurezahl von 40 bis 300 umgesetzt werden.

RB

PAT 92 345

20.05.1992

WOL 1199

BASF Lacke + Farben AG, Münster

Process for the production of a two-coat finish, and powder coatings suitable for this process

The invention relates to a process for the production of two-coat finishes on a substrate surface, in which

(1) a pigmented basecoat is applied to the substrate surface,

(2) a polymer film is formed from the coat applied in step (1),

(3) a powder clearcoat which contains an epoxide group-containing polyacrylate resin as binder is applied to the resulting basecoat film, and subsequently

(4) the basecoat is baked together with the powder clearcoat.

The invention also relates to powder coatings which contain an epoxide group-containing polyacrylate resin as binder.

The process described above for the production of two-coat finishes is known. Using this process, finishes (for cars in particular) can be produced which, particularly with regard to gloss, hiding ability, decorative effect, weathering

AUSTRALIAN PATENT OFFICE RB

resistance and refinishability, have distinct advantages over one-coat finishes. To achieve these advantages, however, the coatings employed must have quite specific properties tailored to the coating process described above.

The basecoat applied in step (1) provides color, hiding ability and effect (especially when using metallic pigments for a metallic effect).

The pigmented basecoat film obtained after applying the basecoat is preferably coated in the unbaked state with a clearcoat. Basecoat and clearcoat are then baked together. It is of decisive importance here that the spatial distribution and/or the spatial orientation of the pigments contained in the basecoat should be disturbed neither during the coating with a clearcoat nor during the combined baking. A disturbance of this nature leads to impairment of the visual appearance of the coating. The clearcoat applied to the basecoat is intended to provide the two-coat finish in particular with gloss, body, topcoat appearance and resistance to weathering, chemicals, water and physical stresses. The clearcoat is not permitted to disturb the basecoat either during the overcoating of the basecoat or during the baking operation, but must provide clearcoat films which, after baking, adhere well to the basecoat and exhibit the stated properties.

For economic and ecological reasons it is desirable for the clearcoats employed in the process under discussion for the production of two-coat finishes to be powder clearcoats. Attempts have

PATENT 12B

therefore been made to use powder clearcoats which contain an epoxide group-containing polyacrylate resin as binder to produce two-coat finishes of the type described above (cf. EP-A-299,420). However, it was found that the resulting two-coat finishes are in need of improvement.

The object on which the present invention is based consists in the provision of a process for the production of two-coat finishes of the type described above, in which a powder clearcoat is employed in step (3) which contains an epoxide group-containing polyacrylate resin as binder and with which two-coat finishes can be produced which in comparison to two-coat finishes of the prior art have improved properties.

This object is surprisingly achieved by a process of the type described above in which a powder clearcoat is employed in step (3) which contains as crosslinking agent a mixture of

(A) 5 to 95, preferably 5 to 80, particularly preferably 10 to 50 percent by weight of a compound which contains on statistical average at least two carboxyl groups and at least one, preferably at least two acid anhydride groups per molecule, or a mixture of such compounds, and

(B) 95 to 5, preferably 95 to 20, particularly preferably 90 to 50 percent by weight of a carboxyl group-containing polyester resin which is obtainable by reacting

(b1) a diol or a mixture of diols,

(b2) a compound which contains per molecule at least three functional groups selected from hydroxyl, primary amino, secondary amino, carboxyl and acid anhydride groups, one acid anhydride group being regarded as equivalent to two carboxyl groups, or a mixture of such compounds, and

(b3) a dicarboxylic acid, a dicarboxylic acid anhydride or a mixture of dicarboxylic acids and/or dicarboxylic acid anhydrides

in a molar ratio of (b1) : (b2) : (b3) = 0.0 to 3.0 : 1.0 : 1.5 to 9.0, preferably 0.0 to 2.0 : 1.0 : 2.0 to 8.0, particularly preferably 0.5 to 2.0 : 1.0 : 2.0 to 6.0 to give a polyester resin having an acid value of 40 to 300, preferably 80 to 250,

the percentages by weight relating to (A) + (B) = 100 percent by weight.

Two-coat finishes obtained using the process according to the invention in relation to two-coat finishes of the prior art have improved resistance to alkalis, wood resin, pancreatin, premium-grade petrol and methyl ethyl ketone, better scratch resistances and better metallic effects, and are harder than two-coat finishes of the prior art.

In step (1) of the process according to the invention any pigmented basecoats suitable for producing two-coat finishes can be employed. Such basecoats are familiar to those skilled in the art. Both water-thinnable basecoats and basecoats based on

organic solvents can be employed. Suitable basecoats are described in, for example, US-A-3,639,147, DE-A-3,333 072, DE-A-38 14 853, GB-A-2 012 191, US-A-3,953,644, EP-A-260 447, DE-A-39 03 804, EP-A-320 552, DE-A-36 28 124, US-A-4,719,132, EP-A-297 576, EP-A-69 936, EP-A-89 497, EP-A-195 931, EP-A-228 003, EP-A-38 127 and DE-A-28 18 100.

It is preferred in step (1) to employ a basecoat which contains a metallic pigment, preferably an aluminum flake pigment.

In step (2) of the process according to the invention, the organic solvents or the water are/is removed in a flash-off phase from the basecoat applied in step (1). It is preferred in step (2) for the basecoat not to be baked. It is of course also possible in step (2) to bake the basecoat at least partially. However, this is disadvantageous on economic grounds since two baking operations instead of one are then required to produce the two-coat finish.

It is essential to the invention that in step (3) of the process according to the invention a powder clearcoat is applied which contains an epoxide group-containing polyacrylate resin as binder and as crosslinking agent a mixture of

(A) 5 to 95, preferably 5 to 80, particularly preferably 10 to 50 percent by weight of a compound which contains on statistical average at least two carboxyl groups and at least one, preferably at least two acid anhydride groups per molecule, or a mixture of such compounds, and

AUSTRALIAN PATENT OFFICE RB

(B) 95 to 5, preferably 95 to 20, particularly preferably 90 to 50 percent by weight of a carboxyl group-containing polyester resin which is obtainable by reacting

(b1) a diol or a mixture of diols,

(b2) a compound which contains per molecule at least three functional groups selected from hydroxyl, primary amino, secondary amino, carboxyl and acid anhydride groups, one acid anhydride group being regarded as equivalent to two carboxyl groups, or a mixture of such compounds, and

(b3) a dicarboxylic acid, a dicarboxylic acid anhydride or a mixture of dicarboxylic acids and/or dicarboxylic acid anhydrides

in a molar ratio of (b1) : (b2) : (b3) = 0.0 to 3.0 : 1.0 : 1.5 to 9.0, preferably 0.0 to 2.0 : 1.0 : 2.0 to 8.0, particularly preferably 0.5 to 2.0 : 1.0 : 2.0 to 6.0 to give a polyester resin having an acid value of 40 to 300 preferably 80 to 250,

the percentages by weight being related in that (A) + (B) = 100 percent by weight.

Powder clearcoats are understood to be powder coatings which are transparent, i.e. they either contain no pigments or are pigmented such that they are still transparent.

An epoxide group-containing polyacrylate resin is understood to be a polymer which can be prepared by copolymerization of at least one ethylenically unsaturated monomer which contains at

RB

least one epoxide group in the molecule with at least one further ethylenically unsaturated monomer which contains no epoxide group in the molecule, at least one of the monomers being an ester of acrylic acid or methacrylic acid.

Epoxide group-containing polyacrylate resins are known (cf. e.g. EP-A-299,420, DE-B-2,214,650, US-A-4,091,048 and US-A-3,781,379).

Examples of ethylenically unsaturated monomers which contain at least one epoxide group in the molecule are glycidyl acrylate, glycidyl methacrylate and allyl glycidyl ether.

Examples of ethylenically unsaturated monomers which contain no epoxide group in the molecule are alkyl esters of acrylic and methacrylic acid which contain 1 to 20 carbon atoms in the alkyl radical, in particular methyl acrylate, methyl methacrylate, ethyl acrylate, ethyl methacrylate, butyl acrylate, butyl methacrylate, 2-ethylhexyl acrylate and 2-ethylhexyl methacrylate. Further examples of ethylenically unsaturated monomers which contain no epoxide groups in the molecule are acids such as acrylic acid and methacrylic acid, acid amides such as acrylamide and methacrylamide, aromatic vinyl compounds such as styrene, methylstyrene and vinyltoluene, nitriles such as acrylonitrile and methacrylonitrile, vinyl and vinylidene halides such as vinyl chloride and vinylidene fluoride, vinyl esters such as vinyl acetate and hydroxyl group-containing monomers such as hydroxyethyl acrylate and hydroxyethyl methacrylate.

RB

The epoxide group-containing polyacrylate resin conventionally has an epoxide equivalent weight of 400 to 2500, preferably 500 to 1500, particularly preferably 600 to 1200, a number-average molecular weight (determined by gel permeation chromatics [sic] using a polystyrene standard) from 1000 to 15,000, preferably from 1200 to 7000, particularly preferably from 1500 to 5000 and a glass transition temperature (T_G) from 30 to 80°C, preferably from 40 to 70°C, particulaly preferably from 40 to 60°C (measured with the aid of differential scanning calorimetry (DSC)).

The epoxide group-containing polyacrylate resin can be prepared according to generally well-known methods by free-radical polymerization.

The powder clearcoats employed in accordance with the invention contain as crosslinking agent a mixture of

(A) 5 to 95, preferably 5 to 80, particularly preferably 10 to 50 percent by weight of a compound which contains on statistical average at least two carboxyl groups and at least one, preferably at least two acid anhydride groups per molecule, or a mixture of such compounds, and

(B) 95 to 5, preferably 95 to 20, particularly preferably 90 to 50 percent by weight of a carboxyl group-containing polyester resin which is obtainable by reacting

(b1) a diol or a mixture of diols,

(b2) a compound which contains per molecule at least three functional groups selected from

AUSTRALIAN PATENT OFFICE RB

hydroxyl, primary amino, secondary amino, carboxyl and acid anhydride groups, one acid anhydride group being regarded as equivalent to two carboxyl groups, or a mixture of such compounds, and

(b3) a dicarboxylic acid, a dicarboxylic acid anhydride or a mixture of dicarboxylic acids and/or dicarboxylic acid anhydrides

in a molar ratio of (b1) : (b2) : (b3) = 0.0 to 3.0 : 1.0 : 1.5 to 9.0, preferably 0.0 to 2.0 : 1.0 : 2.0 to 8.0, particularly preferably 0.5 to 2.0 : 1.0 : 2.0 to 6.0 to give a polyester resin having an acid value of 40 to 300, preferably 80 to 250,

the percentages by weight relating to (A) + (B) = 100 percent by weight.

As component (A) it is possible to employ polyanhydrides of polycarboxylic acids or mixtures of polycarboxylic acids, in particular polyanhydrides of dicarboxylic acids or mixtures of dicarboxylic acids. Such polyanhydrides can be prepared by removing water from the polycarboxylic acid or the mixture of polycarboxylic acids, in each case two carboxyl groups being converted to one anhydride group. Such preparation processes are well known and therefore require no further discussion.

As component (A) it is also possible to employ polyanhydrides modified with a polyol, as are described in EP-A-299,420.

RB

As component (A) it is preferred to employ linear polyanhydrides of aliphatic or cycloaliphatic dicarboxylic acids having 3 to 20, preferably 6 to 12 carbon atoms in the molecule or linear polyanhydrides of mixtures of such dicarboxylic acids. Specific examples of polyanhydrides which are preferably employed are poly(adipic anhydride), poly-(azelaic anhydride), poly(sebacic anhydride), poly-(dodecanedioic anhydride) and poly(cyclohexane-dicarboxylic anhydride).

The carboxyl group-containing polyester resin employed as component (B) can be obtained by reacting

(b1) a diol or a mixture of diols,

(b2) a compound which contains per molecule at least three functional groups selected from hydroxyl, primary amino, secondary amino, carboxyl and acid anhydride groups, one acid anhydride group being regarded as equivalent to two carboxyl groups, or a mixture of such compounds, and

(b3) a dicarboxylic acid, a dicarboxylic acid anhydride or a mixture of dicarboxylic acids and/or dicarboxylic acid anhydrides

in a molar ratio of (b1) : (b2) : (b3) = 0.0 to 3.0 : 1.0 : 1.5 to 9.0, preferably 0.0 to 2.0 : 1.0 : 2.0 to 8.0, particularly preferably 0.5 to 2.0 : 1.0 : 2.0 to 6.0 to give a polyester resin having an acid value of 40 to 300, preferably 80 to 250.

The reaction of (b1), (b2) and (b3) is carried out in accordance with the well-known methods

RB

of polyester resin preparation. The reaction temperatures are conventionally from 140 to 240°C, preferably 160 to 200°C.

As component (b1) a diol or a mixture of diols is employed. A diol is understood to be an organic compound which contains two hydroxyl groups per molecule. Examples of diols which can be employed are ethylene glycol, propylene glycol, neopentyl glycol, 1,6-hexanediol, cyclohexanediol, cyclohexanedimethanol, hydrogenated bisphenol A, adducts of ethylene oxide or propylene oxide with bisphenol A, hydrogenated bisphenol A and diethylene glycol. As component (b1) it is preferred to employ aliphatic or cycloaliphatic diols having 2 to 16, preferably 2 to 12 carbon atoms in the molecule, or mixtures of such diols.

As component (b2) a compound is employed which contains per molecule at least three functional groups selected from hydroxyl, primary amino, secondary amino, carboxyl and acid anhydride groups, one acid anhydride group being regarded as equivalent to two carboxyl groups, or a mixture of such compounds.

As component (b2) it is possible to employ compounds which contain per molecule at least three hydroxyl groups. Examples of such compounds are trimethylolpropane, pentaerythritol, trimethylolethane and glycerol.

As component (b2) it is also possible to employ compounds which contain per molecule two hydroxyl and one carboxyl group. An example of such a compound is dimethylolpropionic acid.

AUSTRALIAN PATENT OFFICE RB

As component (b2) it is also possible to employ compounds which contain per molecule two primary amino and one hydroxyl group. An example of such a compound is diaminopropanol.

As component (b2) it is also possible to employ compounds which contain per molecule at least three carboxyl or at least one acid anhydride and one carboxyl group. Examples of such compounds are trimellitic acid, trimellitic anhydride, pyromellitic acid and pyromellitic anhydride.

As component (b3) a dicarboxylic acid, a dicarboxylic acid anhydride or a mixture of dicarboxylic acids and/or dicarboxylic acid anhydrides is employed. Examples of dicarboxylic acids which can be employed are saturated and unsaturated aliphatic or cycloaliphatic dicarboxylic acids such as adipic acid, sebacic acid, azelaic acid, dodecanedioic acid, maleic acid, fumaric acid, succinic acid, hexahydrophthalic acid and tetrahydrophthalic acid. Examples of dicarboxylic acid anhydrides which can be employed are the anhydrides of the stated acids.

As component (b3) it is also possible to employ aromatic dicarboxylic acids and their anhydrides, for example phthalic acid, isophthalic acid and terephthalic acid. The use of aromatic dicarboxylic acids and their anhydrides is less preferred.

The mixture of (A) and (B) is usually employed in an amount such that 0.5 to 1.5, preferably 0.75 to 1.25 equivalents of carboxyl groups are present per equivalent of epoxide groups of the epoxide group-

RB

containing polyacrylate resin, each anhydride group being regarded as equivalent to one carboxyl group. The amount of carboxyl groups present can be determined by titration with an alcoholic KOH solution. In this titration, one monofunctional carboxyl group is found for each anhydride group.

The powder clearcoats employed in accordance with the invention can also contain, in addition to the epoxide group-containing polyacrylate resin and the mixture of (A) and (B), one or more crosslinking catalysts, transparent pigments and further additives conventional for powder clearcoats, for example UV stabilizers and leveling assistants.

The powder clearcoats employed in accordance with the invention can be prepared by mixing the epoxide group-containing polyacrylate resin, the mixture of (A) and (B) and any further conventional additives, extruding the mixture and milling the resulting extrudate.

The two-coat finishes produced according to the process of the present invention can be applied to any desired substrates, for example metal, wood, glass or plastic. It is preferred to use the process according to the invention for the production of two-coat finishes for car bodies.

By admixing white or colored pigments, colored powder coatings can also be produced from the powder clearcoats employed in accordance with the invention. These powder coatings can also be employed

AUSTRALIAN PATENT OFFICE RB

for coating any desired substrates, for example metal, wood, glass or plastic, with a single coat.

The powder coatings employed in accordance with the invention can be employed using all application techniques conventional for powder coatings. The powder coatings are preferably applied electrostatically.

The invention is illustrated in more detail in the following examples. All parts and percentages are by weight, unless expressly stated otherwise.

1. Preparation of an epoxide group-containing polyacrylate resin

A mixture of 37.06 parts by weight of methyl methacrylate, 14.40 parts by weight of glycidyl methacrylate, 9.00 parts by weight of n-butyl acrylate and 6.54 parts by weight of styrene is added over 4 hours at 120°C to 30.0 parts by weight of xylene. Commencing with the addition of the monomer mixture, 3.0 parts of tert-butyl per-2-ethylhexanoate (TBPEH; manufacturer: Peroxid Chemie) are added over 4.5 hours. During the addition of the monomer mixture and the peroxide, the reaction temperature is 140°C. When the addition of the peroxide is complete this temperature is maintained for a further hour. The xylene is then removed under reduced pressure, and the synthetic resin is heated to 180°C and drained off from the reaction vessel. The resulting polyacrylate resin has an epoxide equivalent weight of 686 g/mol.

2. **Preparation of component (A)**

67.2 parts by weight of dodecanedioic acid together with 29.8 parts by weight of acetic anhydride are weighed out and charged to a reaction vessel with reflux sensor [sic]. The mixture is heated slowly until reflux commences and left under reflux for 3 hours. The acetic acid which is formed is then distilled off. 3.00 parts by weight of acetic anhydride again are then added to the reaction product, and the mixture is heated for one hour at reflux temperature. Finally, the acetic acid which has formed is distilled off and the reaction product is drained off from the reaction vessel at 90°C.

3. **Preparation of Component (B)**

3.1. 153.3 g of hexane-1,6-diol, 370.6 g of trimethylolpropane, 119.9 g of diethylene glycol and 1419.3 g of hexahydrophthalic anhydride are weighed out and charged to a reaction vessel.

The mixure is heated slowly and the water which forms is removed from the reaction mixture using a water separator. As soon as the reaction product has reached an acid value of 160, the mixture is cooled and drained off from the reaction vessel at 100°C. The resulting carboxylic group-containing polyester resin has a glass transition temperature ($_{TG}$) of 26°C.

3.2. 612.9 g of cyclohexane-1,4-dimethanol, 513.9 g of succinic anhydride, 792.4 g of hexahydrophthalic anhydride and 328.8 g of trimethylolpropane are

RB

weighed out and charged to a reaction vessel. The mixure is heated slowly and the water which forms is removed from the reaction mixture using a water separator. As soon as the reaction product has reached an acid value of 135, the mixture is cooled and drained off from the reaction vessel at 100°C. The resulting carboxylic group-containing polyester resin has a glass transition temperature (T_G) of 25°C.

4. Preparation of powder clearcoats according to the invention

4.1. 1372 g of the epoxide group-containing polyacrylate resin prepared as in Section 1, together with 124 g of component (A) prepared as in Section 2, 438 g of component (B) prepared as in Section 3.1, 48.8 g of a first light stabilizer (Tinuvin® 900, manufacturer: Ciba Geigy AG), 32.5 g of a second light stabilizer (Tinuvin® 144, manufacturer: Ciba Geigy AG), 813 [sic] g of benzoin and 8.13 g of a polyacrylate resin-based leveling agent (Perenol® F40, manufacturer: Henkel KGaA), are comminuted and premixed in a precutting mill. The mixture thus obtained is then extruded in a co-kneader from Buss (type PLK 46), the temperature in the center of the extrusion space being 90 - 110°C. The extrudate is cooled rapidly to room temperature, milled in an impact mill (ACM 2 L from Hosokawa MikroPul) to a powder with an average particle diameter of 30 - 40 µm,

RB

and screened through a sieve with a pore size of 125 µm.

4.2. 1372 g of the epoxide group-containing polyacrylate resin prepared as in Section 1, together with 126.7 g of component (A) prepared as in Section 2, 553.3 g of component (B) prepared as in Section 3.1, 53.9 g of a first light stabilizer (Tinuvin® 900, manufacturer: Ciba Geigy AG), 36.0 g of a second light stabilizer (Tinuvin® 144, manufacturer: Ciba Geigy AG), 9.0 g of benzoin and 9.0 g of a polyacrylate resin-based leveling agent (Perenol® F40, manufacturer: Henkel KGaA), are comminuted and premixed in a precutting mill. The mixture thus obtained is then extruded in a co-kneader from Buss (type PLK 46), the temperature in the center of the extrusion space being 90 - 110°C. The extrudate is cooled rapidly to room temperature, milled in an impact mill (ACM 2 L from Hosokawa MikroPul) to a powder with an average particle diameter of 30 - 40 µm, and screened through a sieve with a pore size of 125 µm.

5. Preparation of powder clearcoats of the prior art

5.1. Preparation of a polymeric anhydride modified according to the teaching of EP-A-299,420

97.8 parts by weight of trimethylolpropane are added to 874 parts by weight of component (A) prepared as in Section 2 and the reaction mixture is held for 1.5 hours at 130°C. The reaction



product is then drained off from the reaction vessel at 90°C.

5.2. Preparation of a powder clearcoat according to the teaching of EP-A-299,420

1372 g of the epoxide group-containing polyacrylate resin prepared as in Section 1, together with 380 g of the polymeric anhydride modified as in Section 5.1, 44.2 g of a first light stabilizer (Tinuvin® 900, manufacturer: Ciba Geigy AG), 29.5 g of a second light stabilizer (Tinuvin® 144, manufacturer: Ciba Geigy AG), 7.4 g of benzoin and 7.4 g of a polyacrylate-based leveling agent (Perenol® F40, manufacturer: Henkel), are comminuted and premixed in a precutting mill. The mixture thus obtained is then extruded in a co-kneader from Buss (type PLK 46), the temperature in the center of the extrusion space being 90 - 110°C. The extrudate is cooled rapidly to room temperature, milled in an impact mill (ACM 2 L from Hosokawa MikroPul) to a powder with an average particle diameter of 30 - 40 µm, and screened through a sieve with a pore size of 125 µm. This powder coating contains a quantity of the polymeric anhydride modified as in Section 5.1 such that - as in the powder coatings according to the invention prepared as in Sections 4.1. and 4.2. - one free carboxyl group or one anhydride group of the crosslinking agent is present per epoxide group of the polyacrylate resin. The remaining components were each employed

in quantities such that the percentage proportions - based on the content of binder plus crosslinking agent equal to 100 % by weight - correspond to those in the powder clearcoats according to the invention prepared as in Sections 4.1. and 4.2.

5.3. Preparation of a powder clearcoat containing only component (A) as crosslinking agent

1372 g of the epoxide group-containing polyacrylate resin prepared as in Section 1, together with 380 g of component (A) prepared as in Section 2, 44.2 g of a first light stabilizer (Tinuvin® 900, manufacturer: Ciba Geigy AG), 29.5 g of a second light stabilizer (Tinuvin® 144, manufacturer: Ciba Geigy AG), 7.4 g of benzoin and 7.4 g of a polyacrylate resin-based leveling agent (Perenol® F40, manufacturer: Henkel KGaA), are comminuted and premixed in a precutting mill. The mixture thus obtained is then extruded in a co-kneader from Buss (type PLK 46), the temperature in the center of the extrusion space being 90 - 110°C. The extrudate is cooled rapidly to room temperature, milled in an impact mill (ACM 2 L from Hosokawa MikroPul) to a powder with an average particle diameter of 30 - 40 µm, and screened through a sieve with a pore size of 125 µm. This powder coating contains a quantity of the polymeric anhydride modified as in Section 5.1 such that - as in the powder clearcoats according to the invention prepared as in Sections 4.1. and 4.2. - one free carboxyl group or one anhydride

group of the crosslinking agent is present per epoxide group of the polyacrylate resin. The remaining components were each used in a quantity such that the percentage proportions - based on the content of the binder plus crosslinking agent equal to 100 % by weight - correspond to those in the powder coatings according to the invention prepared as in Sections 4.1. and 4.2.

6. Production of two-coat finishes

A commercially available, water-thinnable basecoat containing polyurethane, polyester and melamine resin and pigmented with aluminum flakes is applied to phosphatized steel panels coated with a commercially available electrodeposition coating and a commercially available filler so that a dry film thickness of 12 to 15 µm is obtained. The basecoat applied is dried for 10 minutes at room temperature and 10 minutes at 80°C. The steel panels coated in this way are then coated electrostatically with the powder clearcoats prepared as in Sections 4.1., 4.2., 5.2, and 5.3 so that a film thickness of the clearcoat of 50 to 60 µm is obtained. Finally, basecoat and powder clearcoat are baked for 20 minutes at 160°C (panel temperature).

The two-coat finishes prepared using the powder clearcoats according to the invention prepared as in Sections 4.1. and 4.2. exhibit better resistance to alkalis, tree resin, pancreatin, premium-grade petrol and methyl ethyl ketone,

AUSTRALIAN PATENT OFFICE RB

better scratch resistances and better metallic effects and are harder than the two-coat finishes prepared using the powder clearcoats of the prior art prepared as in Sections 5.2. and 5.3.

RCB

Patent claims

1. Process for the production of two-coat finishes on a substrate surface, in which

(1) a pigmented basecoat is applied to the substrate surface,

(2) a polymer film is formed from the coat applied in step (1),

(3) a powder clearcoat which contains an epoxide group-containing polyacrylate resin as binder is applied to the resulting basecoat film, and subsequently

(4) the basecoat is baked together with the powder clearcoat,q

characterized in that the powder clearcoat employed in step (3) as crosslinking agent contains a mixture of

(A) 5 to 95 percent by weight of a compound which contains on statistical average at least two carboxyl groups and at least one acid anhydride group per molecule, or a mixture of such compounds, and

(B) 95 to 5 percent by weight of a carboxyl group-containing polyester resin obtainable by reacting

(b1) a diol or a mixture of diols,

(b2) a compound which contains per molecule at least three functional groups selected from hydroxyl, primary amino, secondary amino, carboxyl and acid anhydride groups, one acid anhydride group being regarded as equivalent to two carboxyl groups, or a mixture of such compounds and

RB

(b3) a dicarboxylic acid, a dicarboxylic acid anhydride or a mixture of dicarboxylic acids and/or dicarboxylic acid anhydrides

in a molar ratio of (b1) : (b2) : (b3) = 0.0 to 3.0 : 1.0 : 1.5 to 9.0 to give a polyester resin having an acid value of 40 to 300,

the percentages by weight relating to (A) + (B) = 100 percent by weight.

2. Powder coatings which contain an epoxide group containing polyacrylate resin as binder, characterized in that they contain as crosslinking agent a mixture of

(A) 5 to 95 percent by weight of a compound which contains on statistical average at least two carboxyl groups and at least one acid anhydride group per molecule, or a mixture of such compounds, and

(B) 95 to 5 percent by weight of a carboxyl group-containing polyester resin obtainable by reacting

(b1) a diol or a mixture of diols,

(b2) a compound which contains per molecule at least three functional groups selected from hydroxyl, primary amino, secondary amino, carboxyl and acid anhydride groups, one acid anhydride group being regarded as equivalent to two carboxyl groups, or a mixture of such compounds and

(b3) a dicarboxylic acid, a dicarboxylic acid anhydride or a mixture of dicarboxylic acids and/or dicarboxylic acid anhydrides

RB

in a molar ratio of (b1) : (b2) : (b3) = 0.0 to 3.0 : 1.0 : 1.5 to 9.0 to give a polyester resin having an acid value of 40 to 300,

the percentages by weight relating to (A) + (B) = 100 percent by weight.

3. Process according to claim 1, characterized in that the basecoat applied in step (1) contains a metallic pigment, preferably an aluminum flake pigment.

4. Process or powder coatings according to claim 1 or 2, characterized in that component (A) is a polyanhydride of an aliphatic or cycloaliphatic polycarboxylic acid, preferably of an aliphatic or cycloaliphatic dicarboxylic acid.

5. Use of the powder coatings according to claim 2 or 4 as powder clearcoats for the production of two-coat finishes, the two-coat finishes being able to be produced by

(1) applying a pigmented basecoat to the substrate surface,

(2) forming a polymer film from the coat applied in step (1),

(3) applying a powder clearcoat according to claim 2 or 4 to the resulting basecoat film, and subsequently

(4) baking the basecoat together with the powder clearcoat.

AUSTRALIAN PATENT OFFICE RB

Abstract

The invention relates to a process for the production of two-coat finishes, in which a pigmented basecoat is first applied, the resulting basecoat film is coated with a powder clearcoat, and basecoat and clearcoat are subsequently baked together. In accordance with the invention, the powder clearcoat employed is a powder coating which contains an epoxide group-containing polyacrylate resin as binder and a mixture of (A) a polyanhydride and (B) a carboxyl group-containing polyester resin as crosslinking agent. The polyester resin can be prepared by reacting a diol (b1), a compound (b2) which contains per molecule at least three functional groups selected from hydroxyl, primary amino, secondary amino, carboxyl and acid anhydride groups, and (b3) a dicarboxylic acid in a molar ratio of (b1) : (b2) : (b3) = 0.0 to 3.0 : 1.0 : 1.5 to 9.0 to give a polyester resin having an acid value of 40 to 300.

RB

INTERNATIONAL SEARCH REPORT

International application No.
PCT/EP 93/01601

A. CLASSIFICATION OF SUBJECT MATTER

Int.Cl.[5]: C 09 D 133/14; C 09 D 167/02; B 05 D 7/16; C 08 G 59/32

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

Int.Cl.[5]: C 09 D; C 08 G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DE, A, 4 032 391 (HOECHST AG) 16 April 1992 see page 2, line 23 - line 57; claims 1,5,6; examples 1,2,5 -.-	1-5
A	EP, A, 0 212 457 (PPG INDUSTRIES) 4 March 1987 see page 6, line 17 - line 19 see page 7, line 6 - line 9 see page 9, line 9 - line 14 see page 26, line 8 - line 20 see claims 1-11 -.-	1-5
A	EP, A, 0 038 635 (DAINIPPON) 28 October 1981 see page 2, line 7 - line 18 see page 3, line 3 - line 10 see examples 1,7 see claims 1,2,9	1,2

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search	Date of mailing of the international search report
12 October 1993 (12.10.93)	26 October 1993 (26.10.93)
Name and mailing address of the ISA/ European Patent Office Facsimile No.	Authorized officer Telephone No.

Form PCT/ISA/210 (second sheet) (July 1992)

ANNEX TO THE INTERNATIONAL SEARCH REPORT ON INTERNATIONAL PATENT APPLICATION NO.

EP 9301601
SA 75762

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information. 12/10/93

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
DE-A-4032391	16-04-92	None		
EP-A-0212457	04-03-87	US-A-	4703101	27-10-87
		US-A-	4650718	17-03-87
		US-A-	4681811	21-07-87
		AU-B-	574579	07-07-88
		AU-A-	6091086	02-04-87
		CA-A-	1251298	14-03-89
		DE-A-	3682847	23-01-92
		JP-A-	62087288	21-04-87
		US-A-	4764430	16-08-88
EP-A-0038635	28-10-81	JP-C-	1649850	30-03-92
		JP-B-	3002915	17-01-91
		JP-A-	56136856	26-10-81
		US-A-	4499239	12-02-85

INTERNATIONALER RECHERCHENBERICHT

Internationales Aktenzeichen PCT/EP 93/01601

I. KLASSIFIKATION DES ANMELDUNGSGEGENSTANDS (bei mehreren Klassifikationssymbolen sind alle anzugeben)[6]

Nach der Internationalen Patentklassifikation (IPC) oder nach der nationalen Klassifikation und der IPC

Int.Kl. 5 C09D133/14; C09D167/02; B05D7/16; C08G59/32

II. RECHERCHIERTE SACHGEBIETE

Recherchierter Mindestprüfstoff [7]

Klassifikationssytem	Klassifikationssymbole
Int.Kl. 5	C09D ; C08G

Recherchierte nicht zum Mindestprüfstoff gehörende Veröffentlichungen, soweit diese unter die recherchierten Sachgebiete fallen [8]

III. EINSCHLAGIGE VEROFFENTLICHUNGEN [9]

Art.°	Kennzeichnung der Veröffentlichung[11], soweit erforderlich unter Angabe der maßgeblichen Teile[12]	Betr. Anspruch Nr.[13]
A	DE,A,4 032 391 (HOECHST AG) 16. April 1992 siehe Seite 2, Zeile 23 - Zeile 57; Ansprüche 1,5,6; Beispiele 1,2,5 ---	1-5
A	EP,A,0 212 457 (PPG INDUSTRIES) 4. März 1987 siehe Seite 6, Zeile 17 - Zeile 19 siehe Seite 7, Zeile 6 - Zeile 9 siehe Seite 9, Zeile 9 - Zeile 14 siehe Seite 26, Zeile 8 - Zeile 20 siehe Ansprüche 1-11 --- -/--	1-5

° Besondere Kategorien von angegebenen Veröffentlichungen [10] :

"A" Veröffentlichung, die den allgemeinen Stand der Technik definiert, aber nicht als besonders bedeutsam anzusehen ist

"E" älteres Dokument, das jedoch erst am oder nach dem internationalen Anmeldedatum veröffentlicht worden ist

"L" Veröffentlichung, die geeignet ist, einen Prioritätsanspruch zweifelhaft erscheinen zu lassen, oder durch die das Veröffentlichungsdatum einer anderen im Recherchenbericht genannten Veröffentlichung belegt werden soll oder die aus einem anderen besonderen Grund angegeben ist (wie ausgeführt)

"O" Veröffentlichung, die sich auf eine mündliche Offenbarung, eine Benutzung, eine Ausstellung oder andere Maßnahmen bezieht

"P" Veröffentlichung, die vor dem internationalen Anmeldedatum, aber nach dem beanspruchten Prioritätsdatum veröffentlicht worden ist

"T" Spätere Veröffentlichung, die nach dem internationalen Anmeldedatum oder dem Prioritätsdatum veröffentlicht worden ist und mit der Anmeldung nicht kollidiert, sondern nur zum Verständnis des der Erfindung zugrundeliegenden Prinzips oder der ihr zugrundeliegenden Theorie angegeben ist

"X" Veröffentlichung von besonderer Bedeutung; die beanspruchte Erfindung kann nicht als neu oder auf erfinderischer Tätigkeit beruhend betrachtet werden

"Y" Veröffentlichung von besonderer Bedeutung; die beanspruchte Erfindung kann nicht als auf erfinderischer Tätigkeit beruhend betrachtet werden, wenn die Veröffentlichung mit einer oder mehreren anderen Veröffentlichungen dieser Kategorie in Verbindung gebracht wird und diese Verbindung für einen Fachmann naheliegend ist

"&" Veröffentlichung, die Mitglied derselben Patentfamilie ist

IV. BESCHEINIGUNG

Datum des Abschlusses der internationalen Recherche	Absendedatum des internationalen Recherchenberichts
12.OKTOBER 1993	26. 10. 93
Internationale Recherchenbehörde	**Unterschrift des bevollmächtigten Bediensteten**
EUROPAISCHES PATENTAMT	ENGEL S.L.

III. EINSCHLAGIGE VEROFFENTLICHUNGEN (Fortsetzung von Blatt 2)

Art °	Kennzeichnung der Veröffentlichung, soweit erforderlich unter Angabe der maßgeblichen Teile	Betr. Anspruch Nr.
A	EP,A,0 038 635 (DAINIPPON) 28. Oktober 1981 siehe Seite 2, Zeile 7 - Zeile 18 siehe Seite 3, Zeile 3 - Zeile 10 siehe Beispiele 1,7 siehe Ansprüche 1,2,9	1,2

ANHANG ZUM INTERNATIONALEN RECHERCHENBERICHT ÜBER DIE INTERNATIONALE PATENTANMELDUNG NR.

EP 9301601
SA 75762

In diesem Anhang sind die Mitglieder der Patentfamilien der im obengenannten internationalen Recherchenbericht angeführten Patentdokumente angegeben.
Die Angaben über die Familienmitglieder entsprechen dem Stand der Datei des Europäischen Patentamts am 12/10/93
Diese Angaben dienen nur zur Unterrichtung und erfolgen ohne Gewähr.

Im Recherchenbericht angeführtes Patentdokument	Datum der Veröffentlichung	Mitglied(er) der Patentfamilie	Datum der Veröffentlichung
DE-A-4032391	16-04-92	Keine	
EP-A-0212457	04-03-87	US-A- 4703101	27-10-87
		US-A- 4650718	17-03-87
		US-A- 4681811	21-07-87
		AU-B- 574579	07-07-88
		AU-A- 6091086	02-04-87
		CA-A- 1251298	14-03-89
		DE-A- 3682847	23-01-92
		JP-A- 62087288	21-04-87
		US-A- 4764430	16-08-88
EP-A-0038635	28-10-81	JP-C- 1649850	30-03-92
		JP-B- 3002915	17-01-91
		JP-A- 56136856	26-10-81
		US-A- 4499239	12-02-85

EPO FORM P0473