



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : H01B 3/46	A1	(11) International Publication Number: WO 94/27298 (43) International Publication Date: 24 November 1994 (24.11.94)
(21) International Application Number: PCT/GB94/01042 (22) International Filing Date: 16 May 1994 (16.05.94) (30) Priority Data: 9310146.7 17 May 1993 (17.05.93) GB (71) Applicant (for all designated States except US): RAYCHEM LIMITED [GB/GB]; Faraday Road, Dorcan, Swindon, Wiltshire SN3 5HH (GB). (72) Inventor; and (75) Inventor/Applicant (for US only): DURSTON, David, John [GB/GB]; 3 Rectory Wood, Aldbourne, Marlborough, Wiltshire SN8 2SJ (GB). (74) Agents: JAY, Anthony, William et al.; Raychem Limited, Intellectual Property Law Dept., Faraday Road, Dorcan, Swindon, Wiltshire SN3 5HH (GB).		(81) Designated States: AU, BG, BR, BY, CA, CN, CZ, FI, HU, JP, KR, KZ, NO, NZ, PL, RO, RU, SK, UA, US, UZ, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: POLYMER COMPOSITION AND ELECTRICAL WIRE INSULATION (57) Abstract Polymer blend for insulating electrical wires comprises a first polymer (polyester) having an inherent L.O.I. not higher than 21 % and up to 40 % by weight of a polyimide-siloxane (PIS) copolymer. Preferred polyesters are polybutylene terephthalate or polyester-ester block copolymers. Preferred wire constructions have core insulation layer of polyethylene or polyester overlaid with jacket of the polyester/PIS copolymer blend.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

POLYMER COMPOSITION AND ELECTRICAL WIRE INSULATION

This invention relates to insulating polymeric compositions comprising polyimide siloxanes, especially polyetherimide siloxanes, and to electrical wire or cable provided with a layer of insulating or jacketing material formed from said compositions.

Polymeric compositions comprising polyetherimide siloxanes are known for a number of applications. EP-A-0407061, for example, describes a wire having an inner coating of a halogen free plastics material and a halogen free, hard flexible outer coating of a copolymer of, or a mixture of, a siloxane and a polyetherimide. The outer coating advantageously has the low flammability known to be associated with polyetherimides, although it is preferred to add a further outer layer of poly-ether-etherketone to reduce still further the flammability and also to improve cut through and abrasion resistance and resistance to attack by fluids or gaseous chemicals. EP-A-0407061 also discloses blending unspecified amounts of polyphenylene ether or nylon with the polyetherimide-siloxane.

In another reference, EP-0307670, improved flammability is achieved by blending flame resistant polyetherimide siloxane polyetherimide copolymer blends with fluorocarbon polymers. The compositions described are particularly useful for aircraft panels and interiors. Although the materials have particularly good flame retardancy properties they do have the disadvantage of incorporating halogens, which are not desired, and indeed are often barred by legislation, for certain applications, because of the toxic nature of halogens if escaping during a fire.

EP-A-0323142 describes a ternary polymeric blend for use as wire insulation comprising a blend of polyarylene ether ketone with polyetherimide and silicone polyimide copolymer. Each of these polymeric components has excellent flame retardancy properties and the triblend

similarly has excellent flame retardancy. However disadvantageously all the components are expensive and the triblend similarly expensive.

Flame retardancy of polymeric compositions can conveniently be assessed by analysing the L.O.I. (Limiting Oxygen Index) of the polymers. This test is specified in ASTM D2863- 1987. It determines the lowest percentage of oxygen needed to support burning of the polymer under test. A higher value of L.O.I. therefore indicates a material with higher flame retardancy. Specifically polymer compositions with a L.O.I. of at least 21% will not burn in air, and are preferred for certain applications. Where L.O.I.'s are referred to in the present invention, they are determined according to ASTM D2863- 1987.

We have discovered that the flame retardancy properties of a polymer composition or blend of polymer compositions that used alone would exhibit an L.O.I less than 21% can be significantly enhanced by blending or mixing the said polymer composition or blend with a minor proportion (at most 40 weight %) of a polyimide-siloxane copolymer, preferably a polyetherimide-siloxane copolymer.

Accordingly a first aspect of the present invention provides a polymer composition having a L.O.I. of at least 27%, preferably at least 28%, more preferably at least 29% comprising a blend of

- (a) a first component which is a polymer or a polymer blend which polymer or blend
 - (i) in the absence of any other component, would exhibit a L.O.I. of at most 21%, and
 - (ii) is substantially halogen free; and
- (b) at most 40% by weight (based on the overall weight of the composition) of a second component which is a polyimide-siloxane polymer, preferably a polyetherimide-siloxane polymer.

Components of the composition are quantified as percentages by weight, based on the overall weight of the composition. Preferably, the composition comprises at most 35%, more preferably at most 30%, of the said second component, and may comprise at most 25 or 20% thereof.

When we say that a polymer or blend is substantially halogen free, we mean that the weight percentage of halogen in that polymer or blend is less than 0.1 %, preferably less than 0.01%, especially preferably less than 0.001%.

Preferably the first component is also phosphorous-free, and/or preferably also sulphur-free. This is particularly advantageous for wire and cable insulation properties. A particularly preferred material for the first component is a polyester or a blend of polyesters. As examples there may be mentioned polyetheresters (e.g. Hytrel - 5556 available from Du Pont), polyesteresters (e.g. Elastotec E-7011 available from Elastogran), polybutyleneterephthalate (e.g. Valox-325 available from General Electric) and blends of polybutyleneterephthalate and polyesteresters.

The use of polyesters as the first component is particularly preferred since inter alia the polyesters advantageously provide significantly enhanced fluid resistance, for example to hydrocarbon fluids, especially chlorinated hydrocarbon fluids, compared to the use of polyimide siloxanes (e.g. polyetherimide-siloxanes) alone, and are also significantly cheaper than polyimide siloxanes (e.g. polyetherimide-siloxanes). Polyesters, in the absence of other components typically exhibit a L.O.I of about 20%, and it is surprising that the enhanced chemical resistance can be obtained in blends where the polyester is the major component, while still achieving high flame retardancy.

As an example the use of a polyester as the major component of the composition according to the invention imparts good fluid resistance to chlorinated hydrocarbon fluids , e.g. 1,1,1, trichloroethane.

To the man skilled in the art it would not be obvious that the low flammability first component of the composition would blend effectively with the polyimide siloxane component, nor that the addition of at most 40% of the polyimide siloxane would increase the L.O.I of the overall composition to at least 27, 28 or 29%. For example, the polymer components used may not be compatible with each other, and there is no indication to the skilled man that, for example, a polyester would blend with a polyimide siloxane at the concentrations of polyimide siloxane required to give the desired flame retardancy in the overall composition. The blending achieved is particularly surprising in view of the different processing temperatures of substantially pure polyimide siloxanes (e.g. polyetherimide siloxanes typically processed at about 300°C) and polyesters (typically processed at about 250°C).

We have also surprisingly found that the L.O.I of a blended composition of a polyetherimide siloxane and a polyester increases substantially uniformly as the concentration of polyetherimide siloxane blended with polyester increases from 0% to 100% polyetherimide siloxane (especially in the 0-40% range), i.e. a graph of L.O.I vs. concentration of polyetherimide is a substantially straight line rising from approximately 20% (for 100% polyester/0% polyetherimide-siloxane) to 46 % (for 100 % polyetherimide-siloxane/0% polyester). It is surprising that such a high increase in the L.O.I. of the polyester occurs as the polyetherimide siloxane is added, since this is not usually the case for blends of polymers with initially different L.O.I. values in which the lower-L.O.I. material is the major component.

In addition to flame retardancy, it is often desirable for polymeric compositions to exhibit good (i.e. low) smoke-release characteristics. It is known that magnesium hydroxide can act as a smoke suppressant when included in polymer compositions. However, magnesium hydroxide can not easily be included in unblended polyimide siloxanes (especially in unblended polyetherimide-siloxanes) or blends in which polyimide siloxane (especially polyetherimide-siloxane) is the significant component, since the processing temperature of polyimide siloxanes is generally too high. For example the processing temperature of polyetherimide-siloxane is about 300°C, at which

temperature magnesium hydroxide is not stable. According to the present invention the first component preferably has a processing temperature of at most 270°C, more preferably at most 260°C, especially at most 250°C, and the composition preferably includes magnesium hydroxide. Preferably the percentage by weight (based on the overall weight of the composition) of magnesium hydroxide is in the range 10 to 50%, more preferably 15-40 %, especially 20 to 30% or about 20 %. Similarly, according to the invention, the processing temperature of the overall composition is preferably at most 270°C, preferably at most 260°C, especially at most 250°C. Even though a polyimide siloxane is one of the components of the composition and if used alone would need to be processed at higher temperatures (e.g. 300°C for polyetherimide siloxane), the fact that it is only used as a minor component (less than 40 wt % of the overall composition) means that the overall composition can be processed at lower temperatures. By the addition of magnesium hydroxide a composition with good flame retardancy and good smoke-release characteristics is achieved.

A particularly preferred polyimide siloxane copolymer used according to the present invention is a polyetherimide siloxane, Siltem 1500 (as supplied by General Electric Plastics).

The polymer composition according to the invention is preferably electrically insulating.

The composition of the invention is particularly useful as an insulating layer on an electrical wire or cable, and a second aspect of the invention provides an electric wire or cable provided with an insulating layer of a polymer composition according to the first aspect of the invention. The layer of polymer composition may be provided as a single layer primary insulation, as the inner or outer layer of a dual wall wire construction, or as any layer in a multi wall construction. The insulating layer may also or instead provide an insulating cable jacket to single or bundles of wires. As an example, the insulating composition may be provided on the wire by extrusion.

The invention also provides self supporting articles e.g. hollow articles such as tubular or branched moulded parts made from a composition according to the first aspect of the present invention.

The composition according to the invention is preferably cross-linkable, and may be cross-linked. Cross-linking may be achieved in a known manner using a beam of high energy electrons, or by peroxide curing. Where the composition is provided on a wire or cable, cross-linking is preferably carried out after application of the composition onto the wire or cable.

The preferred compositions wherein the first component is a polyester or blend of polyesters, especially those which are or include polyester/esters, have been found especially well suited to the many technical requirements of wire coatings and are unexpectedly convenient and economical to process.

Example 1

A copper conductor coated with a polymer composition according to the present invention was made from the following components:

<u>component</u>	<u>wt %</u>
VALOX 325 pellet form	46
SILTEM 1500 pellet form	30
Magnesium Hydroxide	20
STABOXOL P	2
Titanium dioxide	2

VALOX 325 is a polybutylene terephthalate available from General Electric

SILTEM 1500 is a polyetherimide siloxane available from General Electric
Plastics

STABOXOL P is a polycarbodiimide added as a hydrolysis stabiliser, and
titanium dioxide is added as a pigment

The above components were dried for at least 4 hours at 120°C, and then the pellets of VALOX and SILTEM mixed together and the powdered magnesium hydroxide, STABOXOL-P and titanium dioxide similarly mixed together. The two dry mixes were then fed separately into the initial feed zone of a twin screw extruder with a maximum temperature set to 250°C. The materials were fully mixed in the extruder and the homogeneous extrudate cooled and pelletised for further processing.

The pellets obtained from the above process were dried at 120°C for 4 hours, and introduced into a single screw extruder with a maximum set temperature of 250°C. The extrudate was drawn down onto an 18 AWG tin coated copper conductor to form an insulated wire with a thickness of insulation equal to 0.25mm (0.01inches) at a line speed of 20 metres per minute.

Example 2

A polymer composition was made in a manner similar to that described in Example 1, using the following components:

<u>component</u>	<u>wt %</u>
Elastotec E5511	36.63
Siltem 1300	29.70
Magnesium Hydroxide	29.70
Irganox 1010 (antioxidant)	0.99
Staboxol P	1.98
Titanium Dioxide (optional)	1.00

The Elastotec material is a polyester block copolymer having polybutylene terephthalate hard blocks and polycaprolactone soft blocks, available from Elastogran GmbH, a subsidiary of BASF.

Example 3 Dual-wall wire coatings.

A. The compositions of Examples 1 and 2 respectively were extruded and drawn in a manner known per se onto a wire already carrying a 0.15 mm thick coating of high density polyethylene having the usual amounts of the usual wire coating additives such as antioxidant, metal deactivator, pigment, etc. This resulted in a wire having a primary core insulation of the HDPE and a primary jacket layer, also 0.15 mm thick, of the respective compositions of Examples 1 and 2. Such wires are very suitable for uses which do not require the jacket to be bonded to the core.

B. Part A was repeated with the HDPE core coating replaced with a similar coating based on polybutylene terephthalate. This produced wires with the jacket bonded to the core.

Example 4

A polymer composition according to the invention was made in a manner similar to that described in Example 1, using "Armitel" (Trade Mark) UM550, a thermoplastic polyester-ester-urethane available from Akzo Plastics. The blend containing 33 parts of the Armitel UM550, 20 parts of Siltem 1300, 45 parts of magnesium hydroxide, and 2 parts of Staboxol-P, produced an L.O.I. of 31 % and retained an elongation of 63% after ageing at 150°C for 0.605 Megaseconds (168 hours = 1 week) in the form of a single coating of 0.23 mm (0.009 inches) thickness on a 16 AWG wire.

The PBT/polycaprolactone polyesterester material of Example 2 is preferred since it has been found to tolerate higher loadings (e.g. above 30 wt. %) of the flame-retardant magnesium hydroxide and to resist embrittlement on ageing for 0.1908 Megaseconds (53 hours) in an oven at 180°C. This was surprising, since blends of polycaprolactone with PBT did not show such resistance to embrittlement. Polyetherester block copolymers such as "Hytrel" (Trade Mark) have also been found subject to embrittlement, and are preferably excluded from the term polyester as used herein. Preferably, the polymer composition will retain elongation in excess of 100% after ageing.

It has unexpectedly been found that co-extrusion of the core and jacket layers (instead of sequential extrusion) onto the wire improves the cut-through resistance of the insulation even when tested by the demanding "thumb-nail test". This is especially so for the preferred HDPE core layer with Example 2 jacket.

The blends of the present invention appear to produce a synergistic improvement in properties, as demonstrated, for example, by the fact that a blend of 54% PBT and 36% "Siltem" with 10% of a stabiliser masterbatch (20% "Staboxol" in "Hytrel" polymer) retains elongation of 104% after ageing at 150°C for 0.605 Megaseconds (168 hours = 1 week), whereas PBT or Siltem alone (with the same stabiliser content) each retain less than 50% elongation after similar ageing. The aforementioned "Elastotec" E5511 of Example 2 also suffers severe loss of elongation on ageing when the "Siltem" is omitted.

CLAIMS

1. A polymer composition having a L.O.I. of at least 27%, preferably at least 28%, more preferably at least 29%, comprising a blend of
 - (a) a first component which is a polymer or a polymer blend which polymer or blend
 - (i) in the absence of any other component, would exhibit a L.O.I. of at most 21%, and
 - (ii) is substantially halogen free; and
 - (b) at most 40% by weight (based on the overall weight of the composition) of a second component which is a polyimide-siloxane polymer, preferably a polyetherimide-siloxane polymer.
2. A composition according to claim 1 comprising at most 35% by weight, preferably at most 25% by weight of the second component.
3. A composition according to claim 1 or 2, wherein the first component is a polyester or a blend of polyesters, preferably being or including a polyester/ester block copolymer.
4. A composition according to claim 1, 2 or 3 comprising magnesium hydroxide, preferably in a weight percent range of 10 to 50 wt %.
5. A composition according to claim 4 which has been processed at a temperature less than 270°C, preferably less than 250 °C.
6. A cross-linkable composition according to any of claims 1-5.
7. A cross-linked composition according to any of claims 1-5.

8. An electrical wire or cable provided with an insulating layer of a polymer composition according to any of claims 1-7.
9. An electrical wire or cable having a primary core insulation layer of a first polymer composition overlaid with a jacket layer of a composition according to any of claims 1 to 7.
10. An insulated wire or cable according to claim 9, wherein the core layer comprises polyolefin, preferably high-density polyethylene.
11. An insulated wire or cable according to claim 9, wherein the core layer comprises a polyester, preferably polybutylene terephthalate.
12. A wire or cable according to any of claims 9 to 11, onto which the core layer and the jacket layer have been co-extruded.
13. An insulated wire or cable according to any of claims 8 to 12, wherein the or each polymer composition has been cross-linked after application of the composition onto the wire or cable.

* * * * *

INTERNATIONAL SEARCH REPORT

International application No.

PCT/GB 94/01042

A. CLASSIFICATION OF SUBJECT MATTER
IPC 5 H01B3/46

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 5 H01B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP,A,0 380 244 (AMERICAN TELEPHONE AND TELEGRAPH COMPANY) 1 August 1990 see page 4, line 52 - page 5, line 34 see page 7; example 4 -----	1,2,4, 8-10,12, 13



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

9 August 1994

Date of mailing of the international search report

30. 08. 94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Stienon, P

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/GB 94/01042

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0380244	01-08-90	US-A- 4941729	17-07-90
		CA-A- 2007835	27-07-90
		CN-B- 1022358	06-10-93
		JP-A- 2239514	21-09-90
