



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 657 377 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
17.05.2006 Bulletin 2006/20

(51) Int Cl.:
E04D 5/10 (2006.01) E04D 5/12 (2006.01)

(21) Application number: **04078109.8**

(22) Date of filing: **11.11.2004**

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IS IT LI LU MC NL PL PT RO SE SI SK TR**
Designated Extension States:
AL HR LT LV MK YU

(71) Applicant: **ICOPAL A/S**
2770 Kastrup (DK)

(72) Inventor: **Damgaard, Jan**
2730 Herlev (DK)

(74) Representative: **Kjerrumgaard, Bent et al**
Budde, Schou & Ostenfeld A/S,
Vester Soegade 10
1601 Copenhagen V (DK)

Remarks:
Amended claims in accordance with Rule 86 (2) EPC.

(54) **Roofing membrane comprising microspheres**

(57) A foam suitable for use in roofing systems is provided. Roofing membranes comprising the foam have superior flowing properties at high temperatures without sacrificing low temperature performance. A particular useful roofing membrane comprises an upper surface layer, a reinforcement layer, and optionally a lower self-

adhesive layer, wherein expanded microspheres are provided in one or more of said layers in an amount of between 0.01 and 10% based on the total weight of the roofing membrane. Moreover a method of making roofing membranes is provided.

EP 1 657 377 A1

Description

[0001] The present invention relates to a foam in roofing systems for achieving superior flowing properties at high temperatures without sacrificing low temperature performance. More particularly, the present invention is in the field of roofing membranes and shingles, having a modified bituminous compound on the top surface, wherein microspheres are employed in the bituminous compound in order to achieve superior flowing properties.

Roofing membranes

[0002] Of the two general types of bituminous sheet materials used for roofing applications, i.e., bitumen-SBS and bitumen-APP materials, the bitumen-SBS products are more elastic, with greater flexibility at low temperatures.

[0003] The waterproofing properties of a bituminous membrane depend upon the existence of continuous films of bitumen. To prevent rupture or flow of the bitumen a sheet material (felt) is normally incorporated. Felts add strength and spanning ability to the membrane but may, in turn, be responsible for membrane failures. A bituminous membrane acts as a single composite structure, but its behaviour is influenced by the properties of the materials from which it is made, the surface to which it adheres, and the environment in which it must serve.

[0004] Bitumen, a material that behaves as a viscous fluid at some temperatures and as an elastic solid at lower ones, has been employed for centuries in construction because of its waterproofing and adhesive properties. Through long experience many of its limitations have been recognized, but improved understanding of the factors affecting its performance has been gained through scientific research.

[0005] The waterproofing capability of bitumen is primarily a result of its nonporous characteristic. Although absorption of water by bitumens does occur, it is generally very limited and of little significance. For bitumen to perform as a water barrier there must be a continuous film free of any voids, pin holes or cracks. Provided this continuity is achieved the film can be as little as 0.005 inch thick, but deterioration of bitumen and other practical considerations usually dictate the use of a much thicker film.

[0006] The cohesion, or internal strength, and the flow properties of bitumens vary considerably with temperature and stress conditions. Bitumen behaves in a viscoelastic manner, and under the influence of an applied strain its deformation will depend upon the rate of strain and the temperature at which it occurs. At a warm temperature bitumen behaves as a liquid; at lower temperatures it behaves as an elastic solid. As the behaviour of both solid and liquid materials is involved, any mechanical properties such as load-strain must be related to the rate of deformation and temperature.

[0007] Deterioration, or loss of the desirable properties of bitumen, normally takes the form of hardening. The net result is a decrease in adhesive and flow properties and an increase in the softening point temperature and coefficient of thermal expansion. Hardening of a bitumen results in a reduction in its ability to accommodate deformations without splitting. The actual mechanisms of deterioration are not fully understood, but it is known that photo-oxidation is a major factor and that it is most active at high temperatures under solar radiation. Water, dissolved compounds from atmospheric pollution, attack by microbiological organisms, and changes in its internal structure are other factors contributing to hardening of bitumens.

[0008] Reinforcement is employed in a bituminous membrane to stabilize the bitumen film, to provide the strength required to span irregularities in its supporting surface, and to distribute local strains over a greater dimension. Adhesion between the bitumen films and reinforcement is essential, and it is normal to factory prime these materials by saturating them with hot bitumen. Bitumen saturation also minimizes the water absorption of felts, but since saturation is not complete they do absorb moisture and are not vapor impermeable. Bitumen coating of saturated felts further reduces the vapor permeance and increases the resistance to moisture penetration.

[0009] The manufacture of bituminous roofing material with multiple layers is well-known. For example, U.S. Pat. Nos. 2,893,889; 4,755,409; 4,871,605; and EP Patent No. 903435 disclose membranes comprised of a core and a plurality of different layers of waterproofing material. The '409 patent also discloses a release sheet applied to the one side of the membrane for purposes of protection. Products are in the market, which combine the more flexible and elastic bitumen-SBS upper layer with a self-adhesive lower surface.

[0010] Bituminous roofing materials are used in e.g. steep slope roofing applications and, therefore, must provide good traction for the safety of the roofer installing the material. A typical installation involves mechanically fastening the material to a substrate. Alternatively torching may be applied to the roofing material. Less commonly the roofing material is adhered to the substrate using an adhesive compound.

[0011] It is essential to note that in hot areas the material must withstand high temperature without being deformed. This sometimes poses severe problems with roofing products that are modified with a styrene-butadiene-styrene (SBS) compound, which softens and flows at temperatures above 110 degrees Celsius. Hence it is necessary to develop a product that has high heat resistance with minimal impact on the flexibility of the cold material.

[0012] Roofing membranes typically comprise multiple layers of various materials configured to protect and optionally to insulate a roof deck or upper surface of a structure or building. The roofing system protects the deck and the interior

of the structure from the weather, including wind, rain, and other precipitation.

[0013] The roofing membrane is a sheet or mat of a solid, elastomeric substance, which protects the deck from the aforementioned weather elements. Conventional membranes include those of EPDM (ethylene-propylenediene elastomer), modified bitumen, and plasticized polyvinylchloride.

[0014] Optionally, a paving layer may be placed or laid on top of the membrane. The paving layer typically comprises materials such as gravel or stone ballast, shingles, brick, or concrete. The paving layer functions to physically protect the membrane from foot traffic and direct exposure to sunlight and the weather.

[0015] A problem commonly encountered with roofing systems is rupture of the membrane due to distortion or deterioration of the protective layer underneath the membrane. The distortion and deterioration problems arise from the exposure of the protective layer to extreme heat from direct sunlight or moisture buildup due to weather exposure. The membrane, which is typically dark and elastomeric, absorbs significant heat from the sunlight, and further does not allow for timely escape of moisture trapped underneath it. When the insulating and/or protective layer becomes distorted or deteriorated, the membrane and the protective layer may separate to form void pockets, which leave the membrane with diminished mechanical support on its undersurface. The diminished support renders the membrane more subject to rupture.

[0016] The source of distortion and deterioration problems of the material in the protective layer varies according to the nature of the material. Some materials are susceptible to heat, some are susceptible to moisture, and some have inherently low mechanical strength.

Microspheres and foams

[0017] Extruded, closed-cell polystyrene foams offer excellent mechanical strength and water resistance, but can become distorted at high service temperatures due to their relatively low heat distortion temperature. Such high service temperatures are typically encountered under a dark membrane in direct sunlight.

[0018] Expanded polystyrene bead foams typically better maintain their shape in a high temperature environment than extruded, closed-cell polystyrene foams because they typically have better bowing characteristics. Their bowing characteristics are better because the coalesced expanded bead structure allows for greater mechanical relaxation compared to the solid, cellular form of extruded, closed-cell foams. However, the coalesced expanded bead structure also results in lower mechanical strength and lower resistance to water transmission.

[0019] Closed-cell polyisocyanate foams have high heat distortion temperatures but have poor moisture resistance. Moisture weakens the cellular structure of such foams, and renders them subject to physical deterioration over time. Moisture also diminishes the insulation value of the foam. They are also relatively friable, which affects their handling characteristics. Closed-cell polyurethane foams, like closed-cell polyisocyanate foams, have high heat distortion temperatures and poor moisture resistance. They are also relatively friable, which affects their handling characteristics.

[0020] Expandable thermoplastic polymer beads are microspheres each comprising a thermoplastic polymer shell and a blowing agent as entrapped therein. When such expandable beads are heated at a temperature high enough to induce a sufficient degree of expansion for a certain length of time, expanded thermoplastic polymer beads are obtained. For example, when expandable micro sphere beads measuring about 15 μm in diameter and having a true specific weight of about 1.3 Kg/l are expanded by heating, expanded micro spheres measuring about 60 μm and having a true specific weight of about 0.03 kg/l may be obtained.

The expanded micro sphere can be obtained by heating the expandable micro sphere at a predetermined temperature. The expanded micro sphere is a balloon-like artefact which can be imaged as a small rubber ball. The expandable micro sphere is a thermally expandable micro sphere comprising a thermoplastic polymer shell and a blowing agent as entrapped therein.

[0021] The thermoplastic polymer which can be used in the present invention includes polymers obtainable by polymerizing various monomers such as (meth)acrylonitrile, (meth)acrylates, styrenic monomers, vinyl halides, vinylidene halides, vinyl acetate, butadiene, vinylpyridine, chloroprene, etc; all of which may contain other comonomeric substances and crosslinking agents, such as divinylbenzene, ethylene glycol di(meth)acrylate, triethylene glycol di(meth)acrylate, trimethylolpropane tri(meth)acrylate, 1,3-butylene glycol di(meth)acrylate, allyl (meth)acrylate, triacrylfomal, triallyl isocyanurate, etc. Among them, the homopolymers, copolymers or terpolymer of at least one monomer selected from among methyl methacrylate, acrylonitrile and vinylidene chloride are especially useful.

[0022] The blowing agent (foaming agent) for causing thermal expansion of the micro spheres have a boiling point not higher than the softening temperature of the thermoplastic polymer shell and includes n-pentane, isopentane, neopentane, butane, isobutane, hexane, isohexane, neohexane, heptane, isoheptane, octane and isooctane, or mixtures thereof, to mention just a few preferred examples. Aside from them, hydrocarbons such as petroleum ether, etc. and chlorinated hydrocarbons such as methyl chloride, methylene chloride, dichloroethane, dichloroethylene, trichloroethane, trichloroethylene, etc. can also be used.

[0023] The weight average particle diameter of expandable micro spheres is preferably about 1-100 μm . The true

specific weight of the expandable micro spheres is preferably about 1.1-1.5 kg/l. Heating the expandable micro sphere at a predetermined temperature gives the expanded micro sphere. The heating can be effected by various methods such as air heating, steam heating, microwave heating, infrared or far-infrared heating, etc.

[0024] The expandable micro spheres mentioned above are commercially available and any of such commercial products can be utilized.

[0025] The art of making cellular thermoplastic products is very well developed. It has long been known, for example in extrusion and molding processes, to form expanded thermoplastic products having a cellular structure by the injection of a gas under pressure into molten thermoplastic materials. Of the more recent patent literature, U.S. Pat. Nos. 2,98,130; 3,268,636; 3,436,446 and 3,975,473 are examples of such processes. These patents, however, are merely illustrative and it is not intended to suggest that they are the only or most pertinent background patents. Such patents disclose the widely used technique of injecting gas under high pressures into an extruder or barrel for solubilization in a thermoplastic melt, followed by discharge of the melt under reduced pressure thereby resulting in the production of foam.

[0026] Techniques are disclosed for making hot melt thermoplastic adhesive foams in U.S. application Ser. No. 710,377, filed Aug. 2, 1976 entitled "Hot Melt Thermoplastic Adhesive Foam System" now U.S. Pat. No. 4,059,714 and U.S. application Ser. No. 710,378, filed Aug. 2, 1976 for "Hot Melt Thermoplastic Adhesive Foam System" now U.S. Pat. No. 4,059,466. These applications are directed to methods of making and using hot melt foamed adhesives which offer significant improvements over conventional non-foamed adhesives. According to the techniques described in these applications, the gas is intimately mixed with a thermoplastic adhesive while the adhesive is in a molten state and then the mixture is pressurized to form a solution which, upon dispensing at a lower pressure, releases the gas and foamed adhesive results. The techniques described in these applications result in very useful foamed adhesives and bonding techniques. However, such techniques are not entirely satisfactory in producing hot melt thermoplastic adhesives on a continuous, uniform quality basis. Such techniques have also been found to be limited in their applicability to hot melt thermoplastic materials and further improvements are needed.

Objects of the invention

[0027] Many of the undesirable characteristics of bitumens can be modified by the addition of specially formulated compounds. There are a number of additives that improve adhesion properties, making it possible for bitumens to adhere to a wet surface and even retain their bond when later wetting of the bitumen-solid interface occurs. Anti-oxidants retard the rate of hardening from chemical and internal structure changes resulting from oxidation. However the problems with flowing bituminous roofing materials at higher temperatures still remains to be solved.

[0028] The common art roofing membranes function within a temperature range; if it is exceeded the product will melt and flow or freeze and become brittle. It is well known in the art to shift the interval to lower temperatures or to higher. But it has shown to be very difficult to change the width of this interval.

[0029] Hence it would be desirable to provide bituminous roofing materials which resist softening and flow at high temperatures, while maintaining plasticity at low temperatures. Thereby it would be possible to use the roofing material on sloped or even vertical substrates under hot climate conditions without sacrificing the cold properties.

[0030] The major object of the present invention is to provide a high temperature resistant roofing membrane without sacrificing the low temperature performance of the membrane.

Surprisingly by foaming the roofing membrane with microspheres it is possible to improve the flow resistance at high temperatures with minimal effect on the flow resistance at low temperatures. The density of the microsphere foamed membranes of the present invention is approx. 25% lower than membranes not employing a foam.

[0031] The present invention involves roof coverings in the form of roofing membranes and shingles having an upper layer of a modified bituminous compound, whose composition utilizes bitumen, plastomeric modifiers and fillers, a reinforcement layer, and optionally a lower layer of a self-adhesive compound, whose composition utilizes bitumen (asphalt), elastomeric modifiers, tackifying resins, and fillers. The expanded microspheres may be distributed across the entire membrane, but is preferably only used in the top layer.

[0032] According to the present invention there is provided a roofing membrane comprising:

- an upper surface layer,
- a reinforcement layer, and
- optionally a lower self-adhesive layer,

wherein expanded microspheres are provided in one or more of said layers in an amount of between 0.01 and 10% based on the total weight of the roofing membrane.

EP 1 657 377 A1

Example

[0033] The top-layers of membranes having no microspheres and membranes including commercially available expanded microspheres (Expancel 095) were made using the following blends:

	1	2
Nynäs B250	61.6	61.0
Kraton 1184	8.4	8.3
Nordkalk kö100	30	29.7
Expancel 095		1.0
TOTAL	100	100

[0034] The blends are made on the diaf mixer at a mixing temperature of 180 °C, according to normal procedure.

[0035] Expancel is added after the filler. The addition is timed in such a way that the Expancel is mixed for 15 minutes after the addition.

[0036] The following table summarises the results:

	1	2
Melting point R&B (°C)	126.4	133.2
Cold bend pass (°C)	-24	-20
Density (kg/l)	1.34	1.07
Viscosity Brookfield (mPas)		
160°C	11094	36583
180°C	4317	13000
200°C	2100	3583
Flow, time to flow > 50mm, at 280 °C	48h	>>2 weeks
Resistance to footprints (Deformation: load: 2499 g/cm ² ; time: 1 min; temperature: 60 °C)		
Reduction of thickness:		
When load is removed:	84%	82%
After 15 min at 60 °C	0%	*
After 2 hours at 60 °C	0%	*
After 3 hours at 60 °C	0%	0%

[0037] The cold bend temperature of the foamed blend is 4 °C higher than for the non-foamed blend, while the melting point R&B of the foamed blend is 6.8 °C higher. The flow resistance is measured using only the weight of the membrane itself. The time to 50mm flow is 48 hours for the non-foamed blend, while it is well in excess of two weeks for the foamed blend.

[0038] From the above it is seen that by foaming it is possible to improve the flow resistance of a blend with only a minimal impact on the cold bend.

[0039] The density of the non-foamed blend is approx. 25% higher than for the foamed blend.

[0040] The handling of foamed and non-foamed membranes was compared using the 0.4m times 1.0m test specimens. With these specimens we do not find any difference in the stiffness/flexibility of the membranes. A manual test of the adhesion of the slate does not suggest any difference in adhesion of slates on foamed and non-foamed bitumen.

[0041] The resistance against footprints is at the same level for the foamed and the non-foamed product.

[0042] The size distribution of the air bubbles was found by taking microscope pictures and then counting the bubbles and measuring their sizes. Expancel has provided a size distribution curve for Expancel 095D120 expanded in air for comparison.

[0043] It is seen that the size distribution of an unaged foamed sample is in the same interval as the curve given by Expancel. However the size distribution of the unaged foamed sample is much wider than the curve from Expancel. This indicates that there is still a possibility to improve the yield of the Expancel in bitumen.

[0044] The size distribution for a foamed sample that was kept at 180 °C for 24 hours is very close to the curve for the unaged sample; this indicates that the blend can be kept at elevated temperatures for some time without losing the

bubbles. A second foamed sample was kept at 190 °C for one hour; it can be seen that the size distribution moves towards higher sizes. So it would seem that there is an upper limit for the temperature the blends can be kept at for a longer period, without changing the characteristics.

5

Claims

1. a roofing membrane comprising:

10

- an upper surface layer
- a reinforcement layer, and
- optionally a lower self-adhesive layer,

15

wherein expanded microspheres are provided in one or more of said layers in an amount of between 0.01 and 10% based on the total weight of the roofing membrane.

2. The membrane of claim 1, wherein the lower self-adhesive layer is discretely distributed, preferably in form of stripes or patches, over the reinforcement layer.

20

3. The membrane of claims 1 or 2 further, wherein at least the upper surface layer comprises modified bitumen.

25

4. The membrane of any one of claims 1 to 3, wherein the expanded microspheres are based on polymers obtainable by polymerizing monomers selected from the group consisting of (meth)acrylonitrile, (meth)acrylates, styrenic monomers, vinyl halides, vinylidene halides, vinyl acetate, butadiene, vinylpyridine, and chloroprene.

30

5. The membrane of claim 4, wherein further comonomeric substances and crosslinking agents are selected from the group consisting of divinylbenzene, ethylene glycol di(meth)acrylate, triethylene glycol di(meth)acrylate, trimethylolpropane tri(meth)acrylate, 1,3-butylene glycol di(meth)acrylate, allyl (meth)acrylate, triacrylformal, and triallyl isocyanurate.

6. A method of making the roof membrane of claim 1 comprising:

35

- providing a reinforcement layer having top and bottom surfaces,
- coating a microsphere-containing modified bitumen in a molten state on the top surface of said reinforcement layer,
- coating an adhesive layer on the lower surface of said reinforcement layer, and
- solidifying the molten embossed layers by cooling the membrane to room temperature.

40

8. Microsphere-containing bitumen for use in manufacturing a roofing membrane according to any one of claims 1 to 5.

9. Use of microspheres in the preparation of bitumen for extending the temperature interval in which the bitumen remains flow resistant.

45

10. Method for preparing a microsphere-containing bitumen comprising the steps of heating and melting a bitumen product, adding expanded microspheres and cooling the bitumen so as to obtain a foamed bitumen product.

50

11. Method for preparing a microsphere-containing bitumen comprising the steps of adding expandable microspheres to a bitumen product, heating until at least a part of the expandable microspheres expand, and cooling the bitumen so as to obtain a foamed bitumen product.

Amended claims in accordance with Rule 86(2) EPC.

1. a roofing membrane comprising:

55

- an upper surface layer
- a reinforcement layer, and
- optionally a lower self-adhesive layer,

wherein pre-expanded microspheres are provided in one or more of said layers in an amount of between 0.01 and 10% based on the total weight of the roofing membrane, said microspheres having been expanded before being added to the roofing membrane.

2. The membrane of claim 1, wherein the lower self-adhesive layer is discretely distributed, preferably in form of stripes or patches, over the reinforcement layer.

3. The membrane of claims 1 or 2 further, wherein at least the upper surface layer comprises modified bitumen.

4. The membrane of any one of claims 1 to 3, wherein the expanded microspheres are based on polymers obtainable by polymerizing monomers selected from the group consisting of (meth)acrylonitrile, (meth)acrylates, styrenic monomers, vinyl halides, vinylidene halides, vinyl acetate, butadiene, vinylpyridine, and chloroprene.

5. The membrane of claim 4, wherein further comonomeric substances and crosslinking agents are selected from the group consisting of divinylbenzene, ethylene glycol di(meth)acrylate, triethylene glycol di(meth)acrylate, trimethylolpropane tri(meth)acrylate, 1,3-butylene glycol di(meth)acrylate, allyl (meth)acrylate, triacrylformal, and triallyl isocyanurate.

6. A method of making the roof membrane of claim 1 comprising:

- providing a reinforcement layer having top and bottom surfaces,
- coating a microsphere-containing modified bitumen in a molten state on the top surface of said reinforcement layer,
- coating an adhesive layer on the lower surface of said reinforcement layer, and
- solidifying the molten embossed layers by cooling the membrane to room temperature.

7. Microsphere-containing bitumen for use in manufacturing a roofing membrane according to any one of claims 1 to 5.

8. Use of microspheres in the preparation of bitumen for extending the temperature interval in which the bitumen remains flow resistant.

9. Method for preparing a microsphere-containing bitumen comprising the steps of heating and melting a bitumen product, adding expanded microspheres and cooling the bitumen so as to obtain a foamed bitumen product.

10. Method for preparing a microsphere-containing bitumen comprising the steps of adding expandable microspheres to a bitumen product, heating until at least a part of the expandable microspheres expand, and cooling the bitumen so as to obtain a foamed bitumen



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 04 07 8109

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	US 4 879 163 A (WOICESHYN ET AL) 7 November 1989 (1989-11-07)	1,3-5,8	E04D5/10 E04D5/12
Y	* the whole document *	2	
A	-----	6,9-11	
Y	US 2003/101671 A1 (GRAAE NIELS ET AL) 5 June 2003 (2003-06-05) * paragraph [0030]; claim 1; figure 2 *	2,6	

X	US 4 512 806 A (GRAHAM ET AL) 23 April 1985 (1985-04-23)	9-11	
Y	* the whole document *	6	
A	-----	1,8	
A	US 4 195 461 A (THIIS-EVENSEN, EYVIND M) 1 April 1980 (1980-04-01) * abstract; figure 3 *	1,6,8-11	

A	PATENT ABSTRACTS OF JAPAN vol. 1999, no. 11, 30 September 1999 (1999-09-30) & JP 11 166300 A (SHOWA KOGYO KK), 22 June 1999 (1999-06-22) * abstract *	1,6,8-11	TECHNICAL FIELDS SEARCHED (Int.Cl.7) E04D D06N

A	US 5 593 766 A (WOICESHYN ET AL) 14 January 1997 (1997-01-14) * abstract; figure 5 *	1,6	

A	US 2003/032356 A1 (KIIK MATTI ET AL) 13 February 2003 (2003-02-13) * paragraphs [0009] - [0014] *	1,6,8-11	

A	US 2003/091812 A1 (ZUBRY BORIS) 15 May 2003 (2003-05-15) * paragraph [0009] *	8-11	

The present search report has been drawn up for all claims			
Place of search Munich		Date of completion of the search 8 September 2005	Examiner Vratsanou, V
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

1
EPO FORM 1503 03.82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 04 07 8109

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

08-09-2005

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4879163	A	07-11-1989	NONE
US 2003101671	A1	05-06-2003	DE 20009382 U1 31-08-2000 AU 7395301 A 03-12-2001 WO 0190506 A1 29-11-2001 EP 1283929 A1 19-02-2003 NO 20025606 A 10-01-2003
US 4512806	A	23-04-1985	US 4234639 A 18-11-1980 AU 528687 B2 12-05-1983 AU 6067380 A 29-01-1981 CA 1140700 A1 01-02-1983 DE 3069497 D1 29-11-1984 EP 0023764 A2 11-02-1981 JP 56018630 A 21-02-1981
US 4195461	A	01-04-1980	NO 781918 A 04-12-1979 DE 2964199 D1 13-01-1983 DK 230279 A 02-12-1979 EP 0006081 A1 12-12-1979 FR 2427442 A1 28-12-1979
JP 11166300	A	22-06-1999	NONE
US 5593766	A	14-01-1997	US 5439726 A 08-08-1995 US 5314556 A 24-05-1994 CA 2041784 A1 09-11-1991
US 2003032356	A1	13-02-2003	US 6586353 B1 01-07-2003 US 2002160210 A1 31-10-2002 US 2003040241 A1 27-02-2003 US 2004055240 A1 25-03-2004 AT 297483 T 15-06-2005 AU 770979 B2 11-03-2004 AU 1799101 A 12-06-2001 CA 2392394 A1 07-06-2001 DE 60020743 D1 14-07-2005 EP 1266067 A2 18-12-2002 MX PA02005182 A 25-09-2003 WO 0140568 A2 07-06-2001 US 2003224679 A1 04-12-2003 US 2003176125 A1 18-09-2003 US 2003228460 A1 11-12-2003 US 6500560 B1 31-12-2002 US 6872440 B1 29-03-2005 CA 2450559 A1 16-01-2003

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 04 07 8109

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

08-09-2005

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2003032356 A1		EP 1404518 A1	07-04-2004
		WO 03004264 A1	16-01-2003
		AT 287013 T	15-01-2005
		CA 2455026 A1	20-02-2003
		CA 2457378 A1	20-02-2003
		DE 60202612 D1	17-02-2005
		EP 1412591 A1	28-04-2004
		EP 1412592 A1	28-04-2004
		MX PA04000897 A	05-04-2004
		MX PA04000898 A	05-04-2004
		WO 03014491 A1	20-02-2003
		WO 03014492 A1	20-02-2003

US 2003091812 A1	15-05-2003	NONE	
