



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : C08L 23/08, 27/18, 27/12 // (C08L 23/08, 27:12, 53:00) (C08L 27/18, 27:12, 53:00) (C08L 27/12, 27:12, 53:00)</p>	A1	<p>(11) International Publication Number: WO 97/47683</p> <p>(43) International Publication Date: 18 December 1997 (18.12.97)</p>
<p>(21) International Application Number: PCT/US97/09469</p> <p>(22) International Filing Date: 4 June 1997 (04.06.97)</p> <p>(30) Priority Data: 08/660,998 10 June 1996 (10.06.96) US</p> <p>(71) Applicant: RAYCHEM CORPORATION [US/US]; 300 Constitution Drive, Mail Stop 120/6600, Menlo Park, CA 94025 (US).</p> <p>(72) Inventors: KADUK, Brian; 900 High School Way #2127, Mountain View, CA 94041 (US). DAWES, Keith; 520 Warren Road, San Mateo, CA 94402 (US). SINGH, Awtar; 113 North Gadsden Drive, Milpitas, CA 95035 (US). TIAN, Jing; 316 North El Camino Real #120, San Mateo, CA 94401 (US).</p> <p>(74) Agents: CHAO, Yuan et al.; Raychem Corporation, Intellectual Property Law Dept., 300 Constitution Drive, Mail Stop 120/6600, Menlo Park, CA 94025 (US).</p>	<p>(81) Designated States: AU, CA, CN, JP, KR, MX, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>	
<p>(54) Title: COMPATIBILIZED FLUOROPLASTIC BLENDS</p>		
<p>(57) Abstract</p> <p>A composition comprises a blend of (a) a first crystalline fluoroplastic which is an ethylene-tetrafluoroethylene copolymer, in an amount 20 and 70 weight %; (b) a second crystalline fluoroelastic which is a terpolymer of tetrafluoroethylene, hexafluoropropylene, and vinylidene fluoride, in an amount between 25 and 70 weight %; and (c) a fluorinated thermoplastic elastomer which is a block copolymer having at least one elastomeric segment comprising tetrafluoroethylene, vinylidene fluoride, and hexafluoropropylene repeat units in a mole ratio 45-90:5-50:0-35 and at least one nonelastomeric segment comprising tetrafluoroethylene and ethylene repeat units, in an amount between 5 and 25 weight %. The fluorinated thermoplastic elastomer acts as a compatibilizer for the two fluoroplastics. The composition exhibits improved flexibility, tensile strength, and/or elongation.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LJ	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

COMPATIBILIZED FLUOROPLASTIC BLENDS

Technical Field of the Invention

This invention relates to a compatibilized blend of fluoroplastics.

Background of the Invention

5 Blending of two or more polymers is a common practice, the objective being to produce a composition having improved mechanical, rheological, and/or degradative properties compared to the individual polymers. It can be an effective way to customize a composition, providing properties which may not be available in a single known polymer or which would require the time-consuming and expensive development of a new polymer.

10 A virtually infinite number of polymer blends is theoretically possible, but not all polymer blends result in compositions with desirable properties. If the component polymers are incompatible, the resulting blend often has inferior properties. This is especially the case for blends involving fluoropolymers. Normally, incompatibility is the rule, and compatibility is the exception. A rigorous and technically precise definition of a compatible
15 blend is a blend in which the constituents are capable of forming a single phase mixture, at least in the amorphous phase, if not the crystalline phase as well. However, at a practical level a compatible blend is often defined as one which displays useful properties. In this application, this latter definition of compatibility will be used.

Miscibility (compatibility) in blends of two different polymers is generally limited
20 to instances involving amorphous polymers and even such instances are rare. Where blends of two different semicrystalline polymers are involved, instances of miscibility are even rarer. Compatibilizers, which are usually block or graft copolymers having segments in common with the main polymer components of the two polymers being blended, can be used to improve the chances of obtaining a compatible blend. But even the use of a
25 compatibilizer does not assure success and most examples of successful use of compatibilizers involve polyolefin blends. We are not aware of any compatibilized blends involving two fluoroplastics.

Fluoroplastics are unique among polymers, offering performance characteristics unobtainable with most other polymers. Commercially available fluoropolymers include polytetrafluoroethylene (PTFE), fluorinated ethylene-propylene copolymer (FEP), perfluoroalkoxy resin (PFA), polychlorotrifluoroethylene (PCTFE), ethylene-chlorotrifluoroethylene copolymer (ECTFE), ethylene-tetrafluoroethylene copolymer (ETFE), polyvinylidene fluoride (PVDF), and polyvinyl fluoride (PVF). Some fluoroplastics such as PTFE are completely fluorinated, while others such as ETFE or PVDF are only partially fluorinated. Typically, fluoroplastics are characterized by high melting points and low glass transition temperatures, enabling them to be advantageously used over a wide temperature range, such as from well below 0 °C to +260 °C. Other desirable properties of fluoroplastics include their excellent solvent resistance, electrical insulative properties, low coefficient of friction, low flammability, low gas permeability, and high inertness and stability. The selection of commercially available fluoroplastics is much more limited than for non-fluorinated polymers, because options regarding both the choice of fluorinated monomer and type of polymerization chemistry are much more limited. Thus, it is desirable to develop novel blends of fluoroplastics having improved properties.

Summary of the Invention

We disclose here our discovery of a blend of two fluoroplastics and a thermoplastic fluoroelastomer as compatibilizer, which blend unexpectedly has improved flexibility, tensile strength, and/or elongation compared to corresponding blend without the compatibilizer. Accordingly, this invention provides a composition comprising:

- (a) a first crystalline fluoroplastic which is an ethylene-tetrafluoroethylene copolymer, in an amount between 20 and 70 weight %;
- (b) a second crystalline fluoroplastic which is a terpolymer of tetrafluoroethylene, hexafluoropropylene, and vinylidene fluoride, in an amount between 25 and 70 weight %; and
- (c) a thermoplastic fluoroelastomer which is a block copolymer comprising at least one elastomeric segment comprising tetrafluoroethylene, vinylidene fluoride, and hexafluoropropylene repeat units in a mole ratio 45-90:5-50:0-

35 and at least one nonelastomeric segment comprising tetrafluoroethylene and ethylene repeat units, in an amount between 5 and 25 weight %; the weight %'s being based on the combined weights of the first and second crystalline fluoroplastics and the thermoplastic fluoroelastomer.

5

Description of the Preferred Embodiments

The first crystalline fluoroplastic is an ethylene-tetrafluoroethylene copolymer, in an amount of between 20 and 70, preferably between 30 and 70, weight %. As used herein, "ethylene-tetrafluoroethylene copolymer" means a crystalline thermoplastic polymer (i.e., a fluoroplastic) which is a copolymer of ethylene, tetrafluoroethylene and optionally a third
10 monomer. Ethylene-tetrafluoroethylene copolymer is also known in the art as ETFE or poly(ethylene-tetrafluoroethylene), and herein the acronym ETFE may be used synonymously for convenience. The mole ratio of ethylene to tetrafluoroethylene can be about 35-60:65-40. A third monomer can be present in an amount such that the mole ratio of ethylene to tetrafluoroethylene to third monomer is about 40-60:15-50:0-35. Preferably
15 the third monomer, if present, is so in an amount of about 5 to about 30 mole %. The third monomer can be, for example hexafluoropropylene; 3,3,3-trifluoropropylene-1; 2-trifluoromethyl-3,3,3-trifluoropropylene-1; or perfluoro(alkyl vinyl ether). The melting point of ETFE varies depending on the mole ratio of ethylene and tetrafluoroethylene and the presence or not of a third monomer. Commercially available ETFE's have melting
20 points between 220 and 270 °C. Preferably, ETFE used in the invention has a crystallinity on the order of 50%.

ETFE suitable for use in this invention is available from a number of suppliers, including from Du Pont under the tradename Tefzel (e.g., grades 200, 280, 2055, 2127, 2181 and 2129) and from Daikin Industries under the tradename Neoflon (e.g., grades 541,
25 610 and 620).

The second crystalline fluoroplastic is a terpolymer of tetrafluoroethylene, hexafluoropropylene, and vinylidene fluoride and is used in an amount of between 25 and 70, preferably 35 and 65, weight %. It has substantial crystallinity associated with the tetrafluoroethylene repeat units.

A suitable second crystalline fluoroplastic is available commercially under the tradename THV (for example grades THV 200, THV 400, and THV 500, especially the first one) from Minnesota Mining and Mfg. The monomer ratio affects mechanical properties and the melting temperature. THV 200 terpolymer has a peak melting temperature (T_m) of 119 °C, a crystallinity level of about 26 %, and a glass transition temperature (T_g) of 5 °C. THV 500 terpolymer has a T_m of 165 °C, a crystallinity level of about 29 %, and a T_g of 26 °C. Generally, an increase in the tetrafluoroethylene in the monomer mix leads to an increase in T_m and T_g .

The thermoplastic fluoroelastomer, which acts as a compatibilizer between the first and second crystalline fluoroplastics, has elastomeric (soft) and non-elastomeric (hard) segments (or blocks). The elastomeric segment comprises tetrafluoroethylene, vinylidene fluoride, and hexafluoropropylene repeat units with preferred relative weight ratios of about 20-40:40-60:10-30, respectively. The nonelastomeric segment comprises substantially alternating tetrafluoroethylene and ethylene repeat units. A preferred weight ratio of elastomeric to nonelastomeric segments of between about 70-95:30-5. The elastomeric segment preferably has a molecular weight of from about 10,000 to about 10,000,000. The nonelastomeric segment preferably has a molecular weight of from about 1,000 to about 1,000,000, more preferably from about 5,000 to about 500,000. The thermoplastic fluoroelastomer is present in an amount between 5 and 25, preferably between 5 and 12, weight %.

A preferred thermoplastic fluoroelastomer is available under the tradename Daiei T-530 from Daikin (Japan).

Compatibilized blends of this invention exhibit unexpectedly improved properties in the form of increased flexibility (as measured by secant modulus (2 %)), tensile strength, and/or elongation. Improvements are especially noticeable in the flexibility. The blends of this invention may be crosslinked, for example with electron beam or gamma radiation.

Without being bound by theory, we believe that the fluoroelastomer is effective as a compatibilizer because its ethylene-tetrafluoroethylene hard block is compatible with the first crystalline fluoroplastic (an ethylene-tetrafluoroethylene copolymer) while its tetrafluoroethylene-hexafluoropropylene-vinylidene fluoride soft block is compatible with

the second crystalline fluoroplastic (tetrafluoroethylene-hexafluoropropylene-vinylidene fluoride terpolymer). Thus, it is likely the fluoroelastomer lowers the interfacial tension between the phases of the first and second crystalline fluoroplastic, thereby promoting interfacial adhesion and a higher level of dispersion during mixing.

5 Blends of this invention may contain additives commonly used in polymer formulations, such as radiation crosslinking promoters (or prorad), antioxidants, UV stabilizers, and pigments, in typical amounts.

The efficiency of radiation crosslinking may be increased by adding an effective amount of a prorad in intimate mixture with the polymeric components. Generally, a prorad
10 is a compound having at least two ethylenic double bonds, present as allyl, methallyl, propargyl, acrylyl, or vinyl groups. Examples of suitable prorads include triallyl cyanurate (TAC), triallyl isocyanurate (TAIC), triallyl trimellitate, triallyl trimesate, tetraallyl pyromellitate, the diallyl ester of 1,1,3-trimethyl-5-carboxy-3-(p-carboxyphenyl)indane, diallyl adipate, diallyl phthalate (DAP), diallyl isophthalate, diallyl terephthalate, 1,4-butylene
15 glycol dimethacrylate, trimethylolpropane trimethacrylate (TMPTM), pentaerythritol trimethacrylate, glycerol propoxy trimethacrylate, liquid poly(1,2-butadiene), tri-(2-acryloxyethyl)isocyanurate, and tri-(2-methacryloxyethyl)isocyanurate, and the like, and combinations thereof. Preferred crosslinking agents are TAIC, TAC, and TMPTM. Other crosslinking agents which can be used are disclosed in US Pat. 3,763,222; 3,840,619; 3,894,118;
20 3,911,192; 3,970,770; 3,985,716; 3,995,091; 4,031,167; 4,155,823; and 4,353,961, the disclosures of which are incorporated herein by reference. Mixtures of crosslinking promoters can be used. Preferably, the radiation crosslinking promoter is used in an amount of between 0.1 % and 10 %, more preferably between 1 % and 5 %, per cent by weight based on the weight of the composition.

25 An effective amount of an antioxidant (which can be a single compound or a combination of two or more compounds) may be added to increase thermal stability, forming an intimate mixture or blend with the polymers. Suitable antioxidants include alkylated phenols, e.g. those commercially available as Goodrite 3125™, Irganox B225™, Irganox 1010™ (pentaerythrityl tetrakis-3-(3,5-di-*tert*-butyl-4-hydroxyphenyl)propionate,
30 Irganox 1035™, Irganox 1076™ (octadecyl 3-(3,5-di-*tert*-butyl-4-hydroxyphenyl)propio-

nate), Irganox 3114TM (1,3,5-tris-(3,5-di-*tert*-butyl-4-hydroxybenzyl)isocyanurate), Topanol CATM (1,1,3-tris-(5-*tert*-butyl-4-hydroxy-2-methylphenyl)butane), Irganox 1093TM, and Vulkanox BKFTM; organic phosphite or phosphates, e.g. dilauryl phosphite and Mark 1178TM; alkylidene polyphenols, e.g. Ethanox 330TM (1,3,5-tris-(3,5-di-*tert*-butyl-4-hydroxybenzyl)mesitylene); thio-bis-alkylated phenols, e.g. Santonox RTM (4,4'-thiobis-(3-methyl-6-*tert*-butylphenol) and polymerized derivatives thereof; dilauryl thio-dipropionate, e.g. Carstab DLTDTM; dimyristyl thiodipropionate, e.g. Carstab DMTDP; distearyl thiodipropionate (DSTDTM), e.g. Cyanox STDP; amines, e.g. Wingstay 29, and the like. Combinations of antioxidants can be used. Preferably, the antioxidant is used in an amount of between 0.1 % and 5 %, more preferably between 0.2 % and 2 %, per cent by weight based on the weight of the composition.

Other additives which can be added include: UV stabilizers such as [2,2'-thio-bis(4-*t*-octylphenolato)] *n*-butylamine nickel, Cyasorb UV 1084, 3,5-di-*t*-butyl-*p*-hydroxybenzoic acid, UV Chek AM-240; conductive fillers such as carbon black for imparting electrical conductivity; zinc oxide as an acid acceptor or scavenger; and pigments such as titanium dioxide and carbon black.

To measure tensile strength and elongation, the procedure of ASTM D638-94b was generally followed and is summarized as follows: an Instron Model 5567 tensile tester driven by Merlin/Series IX software was set up with a 225 lb Tension Load Cell. The jaw separation was 50.8 mm (2 in). The crosshead speed was 2.0 in/min. These adjustments were made using Windows-based Merlin Series IX software. The extension return limit was set at 763 mm. Test specimens were cut from slabs 0.020 to 0.030 inch thick with a dumbbell-shaped D-die per ASTM specifications with a reduced section dimension of 0.125 inch. The Instron tester was calibrated using the built-in calibration capability. Measurements were done at ambient (room) temperature (20-25 °C). Each test specimen was measured for width and thickness before analysis, using a micrometer. Two bench marks were marked on each specimen with a 1.0 inch (25.4 mm) separation, centered on the reduced section, in order to measure elongation. The specimens were stretched until break at a crosshead speed of 2 in/min. The elongation between the benchmarks was measured with a video extensometer. The tensile strength, elongation and secant modulus were all

recorded automatically using the Merlin software. "Elongation" means the elongation at break, also referred to as the ultimate elongation. Similarly, "tensile strength" means the tensile strength at break, also referred to as the ultimate tensile strength, and is calculated by dividing the tension at break by the initial cross-sectional area. Secant modulus (2 %) was calculated as follows: the load at 2 % strain was determined. This load was divided by the original cross-sectional area to obtain the tensile stress, in pounds/square inch (psi). The tensile stress was then divided by 0.02 inch/inch to derive the secant modulus (2 %).

The compatibilized blends of this invention may be used in products in which fluoroplastics normally are used, and are especially suitable for wire and cable insulation, heat-recoverable articles, and other applications where fluoropolymers having superior flexibility, elongation, and tensile strength are desirable.

The practice of our invention may be understood by reference to the following examples, which are provided by means of illustration and not limitation.

Example 1

In this example, the first fluoroplastic was Tefzel 2129 ETFE from Du Pont (T_m 230 °C), the second fluoroplastic was THV 200 from 3M, and the fluoroelastomer compatibilizer was Daiel T-530 from Daikin. Various amounts of the fluoroelastomer compatibilizer and various ratios of the first and second fluoroplastic were used.

Blends were prepared according to the following procedure: the component polymers along with the additive package described following were mixed in a Brabender mixer for 9-11 min at 30 rpm at 275 °C. Each sample composition was molded into 25 mil thick slabs. Crosslinked samples were irradiated with electron beam radiation at a total dosage of 15 MR and annealed at 150 °C for 1 hr. For each blend, a control was prepared in which the ratio of the first and second fluoroplastics was kept substantially the same as in the test sample but with the compatibilizer omitted. Each blend contained about 4.35 parts by weight (ppw) (per 95 parts by weight of blend) of an additive package consisting of 0.10 ppw DSTDP antioxidant, 0.25 ppw Irganox 1010 antioxidant, 0.5 ppw Kadox 15 zinc oxide, and 3.50 ppw TAIC prorad.

Tables IA and IB give formulation and mechanical properties (uncrosslinked and crosslinked), respectively, of compositions where the amount of compatibilizer was kept at about 5% while the ratio of the first and second fluoroplastics was varied. Table IB also includes, for reference purposes, the mechanical properties of the first and second fluoroplastics alone. Each set of data is paired with a corresponding control in which the compatibilizer is omitted while the ratio of first and second fluoroplastics is kept constant.

Experiment No.	Tefzel 2129 (wt. %) ^a	THV 200 (wt %) ^a	Daiel T-530 (wt %) ^a	Ratio 1st/2nd Fluoroplastic
1 (control)	79.09	20.91	—	3.78
1	74.96	19.81	5.23	3.78
2 (control)	58.18	41.82	—	1.39
2	55.14	39.63	5.23	1.39
3 (control)	20.91	79.09	—	0.26
3	19.81	74.96	5.23	0.26
4 (control)	50.01	49.99	—	1.00
4	50.86	43.91	5.23	1.15

^a Weight %'s based on combined weights of 1st and 2nd fluoroplastic and compatibilizer

TABLE I-B — MECHANICAL PROPERTIES OF COMPATIBILIZED BLENDS: TEFZEL 2129/THV 200/DAIEL T-530 APPROXIMATELY 5 WT% COMPATIBILIZER						
Experiment No.	Unbeamed (Uncrosslinked)			Beamed (Crosslinked) ^a		
	Secant Modulus, 2% (psi) ^b	Tensile Strength (psi) ^b	Elonga- tion (%) ^b	Secant Modulus, 2% (psi) ^b	Tensile Strength (psi) ^b	Elonga- tion (%) ^b
Tefzel 2129 ^c	66,160	5,360	400	77,990	5,160	160
THV 200 ^c	9,200	3,380	690	30,300	3,780	220
1 (Control)	51,080	4,890	410	68,990	5,120	210
1	43,570	4,940	420	62,320	4,710	190
2 (control)	35,970	2,330	310	52,690	4,260	220
2	26,490	3,850	440	39,200	3,700	200
3 (control)	10,350	1,460	470	24,140	2,950	210
3	9,270	2,620	480	26,090	3,160	190
4 (control)	27,900	1,600	220	45,960	4,050	210
4	31,360	4,160	440	40,720	4,120	200

^a Beamed with 15 Mrad electron beam radiation and then annealed at 150°C for 1 hr.

^b Reported values are averages of 5 measurements, unless noted otherwise

^c Average of 2 sets of 5 measurements

- 5 The data for compositions in which the amount of compatibilizer was kept at about 10 wt% while the ratio of first and second crystalline fluoroplastics was varied are presented in Tables II-A and II-B, which are organized in the same manner as the preceding Tables I-A and I-B.

TABLE II-A — COMPOSITION OF COMPATIBILIZED BLENDS: TEFZEL 2129/THV 200/DAIEL T-530 APPROXIMATELY 10 WT% COMPATIBILIZER				
Experiment No.	Tefzel 2129 (wt. %) ^a	THV 200 (wt %) ^a	Daiel T-530 (wt %) ^a	Ratio 1st/2nd Fluoroplastic
1 (control)	79.09	20.91	—	3.78
1	70.82	18.72	10.45	3.78
2 (control)	58.18	41.82	—	1.39
2	52.10	37.45	10.45	1.39
3 (control)	20.91	79.09	—	0.26
3	18.73	70.81	10.45	0.26
4 (control)	50.01	49.99	—	1.00
4	45.64	43.91	10.45	1.03

^a Weight %'s based on combined weights of 1st and 2nd fluoroplastic and compatibilizer

TABLE II-B — MECHANICAL PROPERTIES OF
 COMPATIBILIZED BLENDS: TEFZEL 2129/THV 200/DAIEL T-530
 APPROXIMATELY 10 WT% COMPATIBILIZER

Experiment No.	Unbeamed (Uncrosslinked)			Beamed (Crosslinked) ^a		
	Secant Modulus, 2% (psi) ^b	Tensile Strength (psi) ^b	Elongation (%) ^b	Secant Modulus, 2% (psi) ^b	Tensile Strength (psi) ^b	Elongation (%) ^b
Tefzel 2129 ^c	66,160	5,360	400	77,990	5,160	160
THV 200 ^c	9,200	3,380	690	30,300	3,780	220
1 (Control)	43,670	4,060	390	66,920	4,580	190
1	43,850	5,000	440	51,710	4,380	200
2 (control)	31,710	1,420	110	56,060	3,930	190
2	21,580	3,260	440	35,640	3,450	180
3 (control)	12,360	1,590	510	27,670	2,940	190
3	8,370	2,850	540	19,980	3,400	220
4 (control)	27,900	1,600	220	45,960	4,050	210
4	24,620	3,920	430	35,650	3,570	190

^a Beamed with 15 Mrad electron beam radiation and then annealed at 150°C for 1 hr.

^b Reported values are averages of 5 measurements, unless noted otherwise

^c Average of 2 sets of 5 measurements

- 5 The data for compositions in which the amount of compatibilizer was kept at about 20 wt% while the ratio of first and second crystalline fluoroplastics was varied are presented in Tables III-A and III-B, which are organized in the same manner as the preceding tables.

**TABLE III-A — COMPOSITION OF
COMPATIBILIZED BLENDS: TEFZEL 2129/THV 200/DAIEL T-530
APPROXIMATELY 20 WT% COMPATIBILIZER**

Experiment No.	Tefzel 2129 (wt. %) ^a	THV 200 (wt %) ^a	Daiel T-530 (wt %) ^a	Ratio 1st/2nd Fluoroplastic
1 (control)	79.09	20.91	—	3.78
1	62.55	16.53	20.91	3.78
2 (control)	58.18	41.82	—	1.39
2	46.02	33.06	20.91	1.39
3 (control)	20.91	79.09	—	0.26
3	16.51	62.57	20.91	0.26

^a Weight %'s based on combined weights of 1st and 2nd fluoroplastic and compatibilizer

**TABLE III-B — MECHANICAL PROPERTIES OF
COMPATIBILIZED BLENDS: TEFZEL 2129/THV 200/DAIEL T-530
APPROXIMATELY 20 WT% COMPATIBILIZER**

Experiment No.	Unbeamed (Uncrosslinked)			Beamed (Crosslinked) ^a		
	Secant Modulus, 2% (psi) ^b	Tensile Strength (psi) ^b	Elongation (%) ^b	Secant Modulus, 2% (psi) ^b	Tensile Strength (psi) ^b	Elongation (%) ^b
Tefzel 2129 ^c	66,160	5,360	400	77,990	5,160	160
THV 200 ^c	9,200	3,380	690	30,300	3,780	220
1 (Control)	50,130	4,120	430	73,120	4,860	190
1	24,870	3,940	480	44,380	3,840	190
2 (control)	31,830	2,530	350	44,680	3,610	190
2	16,630	3,440	480	27,600	3,600	200
3 (control)	15,660	2,120	540	24,800	3,130	200
3	5,350	2,870	560	17,860	3,110	210

^a Beamed with 15 Mrad electron beam radiation and then annealed at 150°C for 1 hr.

^b Reported values are averages of 5 measurements, unless noted otherwise

^c Average of 2 sets of 5 measurements

5

Example 2

In this example, the first fluoroplastic was Neoflon EP620 ETFE from Daikin (T_m 225 °C), the second fluoroplastic was THV 200, and the fluoroelastomer compatibilizer was Daiel T-530. The blends were prepared as in Example 1. The data for the instance in which the amount of compatibilizer was about 5 wt % is presented in Tables IV-A/IV-B, arranged in the same manner as in the preceding tables.

TABLE IV-A — COMPOSITION OF COMPATIBILIZED BLENDS: NEOFロン EP620/THV 200/DAIEL T-530 APPROXIMATELY 5 WT% COMPATIBILIZER				
Experiment No.	Neoflon EP620 (wt. %) ^a	THV 200 (wt %) ^a	Daiel T-530 (wt %) ^a	Ratio 1st/2nd Fluoroplastic
1 (control)	79.09	20.91	—	3.78
1	74.96	19.81	5.23	3.78
2 (control)	58.18	41.82	—	1.39
2	55.14	39.63	5.23	1.39
3 (control)	20.91	79.09	—	0.26
3	19.81	74.96	5.23	0.26
4 (control)	50.01	49.99	—	1.00
4	50.86	43.91	5.23	1.15

^a Weight %'s based on combined weights of 1st and 2nd fluoroplastic and compatibilizer

TABLE IV-B — MECHANICAL PROPERTIES OF COMPATIBILIZED BLENDS: NEOFロン EP620/THV 200/DAIEL T-530 APPROXIMATELY 5 WT% COMPATIBILIZER						
Experiment No.	Unbeamed (Uncrosslinked)			Beamed (Crosslinked) ^a		
	Secant Modulus, 2% (psi) ^b	Tensile Strength (psi) ^b	Elonga- tion (%) ^b	Secant Modulus, 2% (psi) ^b	Tensile Strength (psi) ^b	Elonga- tion (%) ^b
Neoflon 620 ^c	48,310	4,440	380	88,150	4,420	130
THV 200 ^c	9,200	3,280	690	30,300	3,780	220
1 (Control)	43,000	4,780	440	56,800	4,150	190
1	33,800	4,660	440	54,890	3,860	180
2 (control)	28,700	2,910	410	48,210	3,810	210
2	30,130	4,020	450	48,830	3,850	200
3 (control)	12,760	1,770	520	29,770	2,740	190
3	8,570	2,830	520	21,680	3,320	230
4 (control)	25,100	2,280	400	45,800	4,030	200
4	23,320	3,770	470	42,460	3,770	190

^a Beamed with 15 Mrad electron beam radiation and then annealed at 150°C for 1 hr.

^b Reported values are averages of 5 measurements, unless noted otherwise

^c Average of 2 sets of 5 measurements

- 5 Data for the instance in which the amount of compatibilizer was about 10 wt % is presented in Tables V-A and V-B.

TABLE V-A — COMPOSITION OF COMPATIBILIZED BLENDS: NEOFロン EP620/THV 200/DAIEL T-530 APPROXIMATELY 10 WT% COMPATIBILIZER				
Experiment No.	Neoflon EP620 (wt. %) ^a	THV 200 (wt %) ^a	Daiel T-530 (wt %) ^a	Ratio 1st/2nd Fluoroplastic
1 (control)	50.01	49.99	—	1.00
1	45.64	43.91	10.45	1.03

^a Weight %'s based on combined weights of 1st and 2nd fluoroplastic and compatibilizer

TABLE V-B — MECHANICAL PROPERTIES OF COMPATIBILIZED BLENDS: NEOFロン EP620/THV 200/DAIEL T-530 APPROXIMATELY 10 WT% COMPATIBILIZER						
Experiment No.	Unbeamed (Uncrosslinked)			Beamed (Crosslinked) ^a		
	Secant Modulus, 2% (psi) ^b	Tensile Strength (psi) ^b	Elonga- tion (%) ^b	Secant Modulus, 2% (psi) ^b	Tensile Strength (psi) ^b	Elonga- tion (%) ^b
Neoflon 620 ^c	48,310	4,440	380	88,150	4,420	130
THV 200 ^c	9,200	3,280	690	30,300	3,780	220
1 (control)	25,100	2,280	400	45,800	4,030	200
1	17,550	4,000	540	33,240	3,960	210

^a Beamed with 15 Mrad electron beam radiation and then annealed at 150°C for 1 hr.

^b Reported values are averages of 5 measurements, unless noted otherwise

^c Average of 2 sets of 5 measurements

5

Example 3

In this example, the first fluoroplastic was Tefzel 2181 ETFE from Du Pont (T_m 265 °C), the second fluoroplastic was THV 200, and the compatibilizer was Daiel T-530. The blends were prepared as in Example 1, except that the Brabender mixing was done at 300 °C. The data is provided in Tables VI-A and VI-B, arranged as before.

10

Experiment No.	TEFZEL 2181 (wt. %) ^a	THV 200 (wt %) ^a	Daiel T-530 (wt %) ^a	Ratio 1st/2nd Fluoroplastic
1 (control)	79.09	20.91	—	3.78
1	74.96	19.81	5.23	3.78
2 (control)	58.18	41.82	—	1.39
2	55.14	39.63	5.23	1.39
3 (control)	20.91	79.09	—	0.26
3	19.81	74.96	5.23	0.26

^a Weight %'s based on combined weights of 1st and 2nd fluoroplastic and compatibilizer

Experiment No.	Unbeamed (Uncrosslinked)			Beamed (Crosslinked) ^a		
	Secant Modulus, 2% (psi) ^b	Tensile Strength (psi) ^b	Elongation (%) ^b	Secant Modulus, 2% (psi) ^b	Tensile Strength (psi) ^b	Elongation (%) ^b
Tefzel 2181 ^c	97,060	6,550	350	118,250	6,970	140
THV 200 ^c	9,380	3,470	670	33,370	3,780	220
1 (Control)	78,250	4,880	330	87,930	6,200	190
1	67,450	5,210	360	85,570	5,480	190
2 (control) ^d	45,100	1,630	50	59,620	4,040	160
2	36,760	3,260	330	58,600	4,690	200
3 (control)	19,230	1,730	480	40,680	3,270	180
3	13,980	2,920	450	29,390	3,490	200

^a Beamed with 15 Mrad electron beam radiation and then annealed at 150°C for 1 hr.

^b Reported values are averages of 5 measurements, unless noted otherwise

^c Average of 2 sets of 5 measurements

^d Average of 2 sets of 5 measurements

5

The above results show that the compatibilized blends of this invention (whether crosslinked or not) generally exhibit an increase in at least one of flexibility (i.e., decreased secant modulus (2 %)), tensile strength, and/or elongation, without any offsetting decrement in the other mechanical properties. Improvement is especially marked in the flexibility. In some instances, improvements in two or even all three properties are observed.

The foregoing detailed description of the invention includes passages which are chiefly or exclusively concerned with particular parts or aspects of the invention. It is to be understood that this is for clarity and convenience, that a particular feature may be relevant in more than just the passage in which it is disclosed, and that the disclosure herein includes all the appropriate combinations of information found in the different passages. Similarly, although the various passages may relate to specific embodiments of the invention, it is to be understood that where a specific feature is disclosed in the context of a particular embodiment, such feature can also be used, to the extent appropriate, in the context of another embodiment, in combination with another feature, or in the invention in general.

Claims

What is claimed is:

1. A composition comprising a blend of:
 - 5 (a) a first crystalline fluoroplastic which is an ethylene-tetrafluoroethylene copolymer, in an amount between 20 and 70 weight %;
 - (b) a second crystalline fluoroplastic which is a terpolymer of tetrafluoroethylene, hexafluoropropylene, and vinylidene fluoride, in an amount between 25 and 70 weight %; and
 - 10 (c) a thermoplastic fluoroelastomer which is a block copolymer comprising at least one elastomeric segment comprising tetrafluoroethylene, vinylidene fluoride, and hexafluoropropylene repeat units in a mole ratio 45-90:5-50:0-35 and at least one nonelastomeric segment comprising tetrafluoroethylene and ethylene repeat units, in an amount between 5 and 25 weight %;
- 15 the weight %'s being based on the combined weights of the first and second crystalline fluoroplastics and the thermoplastic fluoroelastomer.
2. A composition according to claim 1, wherein the first crystalline fluoroplastic is present in an amount between 30 and 70 weight %.
- 20 3. A composition according to claim 1, wherein the second crystalline fluoroplastic is present in an amount between 35 and 65 weight %.
4. A composition according to claim 1, wherein the thermoplastic fluoroelastomer is present in an amount of between 5 and 12 weight %.
- 25 5. A composition according to any of claims 1 to 4, which has been crosslinked by electron beam radiation.

6. A composition according to any of claims 1 to 4, which has been crosslinked by gamma radiation.

* * * * *

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 97/09469

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 6 C08L23/08 C08L27/18 C08L27/12 //(C08L23/08,27:12,53:00),
 (C08L27/18,27:12,53:00),(C08L27/12,27:12,53:00)

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	JP 06 025 500 A (DAIKIN IND LTD) 1 February 1994 & CHEMICAL ABSTRACTS, vol. 120, no. 26, 27 June 1994 Columbus, Ohio, US; abstract no. 325555, see abstract	1
A	---	
A	EP 0 524 700 A (RAYCHEM CORP) 27 January 1993 see claims	1
A	---	
A	EP 0 458 195 A (DAIKIN IND LTD) 27 November 1991 see claims	1

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

20 October 1997

Date of mailing of the international search report

10. 11. 97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

DE LOS ARCOS, E

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 97/09469

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 06025500 A	01-02-94	NONE	
EP 0524700 A	27-01-93	CA 1335738 A	30-05-95
		AU 608320 B	28-03-91
		AU 1574088 A	10-10-88
		DE 3881125 A	24-06-93
		EP 0304487 A	01-03-89
		JP 1502676 T	14-09-89
		WO 8807063 A	22-09-88
		US 4935467 A	19-06-90
EP 0458195 A	27-11-91	JP 4023855 A	28-01-92
		US 5214097 A	25-05-93