

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

**(19) World Intellectual Property Organization
International Bureau**



**(43) International Publication Date
13 November 2003 (13.11.2003)**

PCT

(10) International Publication Number
WO 03/093333 A1

(51) International Patent Classification⁷: C08F 214/26

(81) Designated States (national): CN, JP.

(21) International Application Number: PCT/US03/13210

(84) Designated States (regional): European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR).

(25) Filing Language: English

Declarations under Rule 4.17:

(26) Publication Language: English
(30) Priority Data: 60/376,645, 30 April 2002 (30.04.2002), US

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations CN, JP, European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR)
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations

(71) **Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 [US]**

B. L. K. B.

Published: *with illustrations by a much younger*

(72) **Inventors:** **ATEN, Ralph, M.**; 28 Lynnwood Drive, Vienna, WV 26105 (US). **LIBERT, Sharon, Ann**; 605 Oriole Place, Hockessin, DE 19707 (US).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(74) Agent: HENDRICKSON, John, S.; E.I. DuPont De Nemours And Company, Legal Patent Records Center, 4417 Lancaster Pike, Wilmington, DE 19805 (US).

A standard 1D barcode is positioned vertically on the right side of the page, consisting of a series of vertical black bars of varying widths.

WO 03/093333 A1

(54) Title: HIGH VINYL ETHER MODIFIED SINTERABLE POLYTETRAFLUOROETHYLENE

(57) Abstract: Modified polytetrafluoroethylene powder of a sinterable copolymer of tetrafluoroethylene containing about 0.5 to about 10 weight % of fluorinated vinyl ether, the copolymer having a melt creep viscosity of greater than about 1×10^6 PaS. In preferred embodiments, the sinterable copolymer has a melt creep viscosity of greater than about 1×10^7 PaS and fluorinated vinyl ether content of from about 1 to about 7 weight %. The polymer has a combination of a high level of fluorinated vinyl ether and a melt creep viscosity which is high enough to enable the fabrication of articles by sintering.

TITLE OF INVENTION**HIGH VINYL ETHER MODIFIED SINTERABLE
POLYTETRAFLUOROETHYLENE****FIELD OF THE INVENTION**

This invention relates to improved polytetrafluoroethylene granular powders.

BACKGROUND OF THE INVENTION

Two general processes for polymerizing tetrafluoroethylene (TFE) to make non-melt processible polytetrafluoroethylene (PTFE) are known – (1) dispersion polymerization and (2) suspension polymerization. Each process produces polymer with distinctly different properties.

Polymer particles isolated from dispersion polymerization are commonly referred to as fine powder and have the characteristic property of fibrillating under shear stress. The powders can be fabricated into articles by a lubricated extrusion process known as paste extrusion with subsequent removal of the lubricant. The extrudate typically is processed further by heating the extrudate above the melting point of the polytetrafluoroethylene to sinter the extrudate into a tough, coherent article. Fine powder is not fabricable into articles by the common techniques described below used to process suspension polymerized PTFE.

Polymer particles isolated from suspension polymerization are commonly referred to as granular and are non-fibrillating and cannot be paste extruded. The isolated particles are typically irregular, fibrous and coarse and commonly subjected to various finishing operations such as cutting, or cutting and pelletizing, to obtain resin with better processing characteristics. Articles are commonly fabricated from granular powders by a preform/sintering technique adapted from powder metallurgy. The technique involves creating a preform and compacting at room temperature and then sintering the preform, optionally followed by machining. The sintering stage reduces and/or eliminates the void space by coalescence of the molten PTFE particles. These steps are quite time consuming.

Another important granular processing technique is called ram extrusion, which is a continuous powder sintering extrusion process for the production of continuous tubes and rods. In this process, a

polytetrafluoroethylene powder is introduced, by means of an automatic metering device, in repetitive cycles into a tube which has been heated to sintering temperature, is compressed by means of a ram and is moved forward a corresponding distance within the sintering tube each time. Under these conditions, the powder sinters together to form a uniformly extruded shaped article.

Fine powder differs distinctly from granular powder in that it is not ram extrudable and is not fabricable into articles of any significant mass or thickness by the preform/sinter technique.

Efforts have been made to modify suspension polymerized polytetrafluoroethylene to make smaller, rounder raw polymer particles suitable for use in ram extrusion without the necessity of further pretreatment, such as cutting and pelletization. Such modification includes the addition of low levels of a comonomer of perfluoro(alkyl vinyl ether) (PAVE), where the perfluoro(alkyl) group is 1 to 3 carbon atoms as provided, for example, in British Patent Specification 1,116,210 issued May 24, 1967. Although levels of up to 1.5 mol % (4.3 wt %) of perfluoro(propyl vinyl ether) (PPVE) are postulated, the highest level of PPVE exemplified is 0.28 weight percent.

Heretofore, it has been believed by those skilled in the art that obtaining high molecular weight PTFE of a sinterable magnitude requires limiting comonomer incorporation. It has been previously demonstrated that copolymerization of TFE with high levels of fluorinated vinyl ether, even in the absence of chain transfer agent, results in a low molecular weight, melt processible polymer. Use of chain transfer agent in melt processible TFE/PAVE copolymerization imparts desirable secondary attributes, namely decreased unstable end groups and narrowed molecular weight distribution. As exemplified in Example 1 of U.S. Patent 3,635,926 to Gresham et al., even when initiator is reduced to the level where chain transfer agent is required to lower molecular weight (thus enabling the acquisition of the desired secondary benefits of chain transfer agent), the polymer produced by copolymerization in dispersion aqueous polymerization is still melt processible and not sufficiently high in molecular weight to be sinterable.

What is desired is an improved granular resin that can be more easily processed and produce sintered articles with equal or improved mechanical properties.

BRIEF SUMMARY OF THE INVENTION

The invention provides a modified polytetrafluoroethylene powder of a sinterable copolymer of tetrafluoroethylene with from about 0.5 to about 10 weight % of fluorinated vinyl ether, said copolymer having a melt creep viscosity of greater than about 1×10^6 Pa·S. In preferred embodiments, the sinterable copolymer has a melt creep viscosity of greater than about 1×10^7 Pa·S and fluorinated vinyl ether content of from about 1 to about 7 weight %.

The invention further provides for a process for polymerizing tetrafluoroethylene and fluorinated vinyl ether in a suspension polymerization process by feeding pressurized tetrafluoroethylene into a polymerization vessel containing an agitated liquid medium, preferably water, with a dissolved free radical initiator and an initial amount of fluorinated vinyl ether. The polymerization is conducted in the absence of any significant amount of telogenic agent. After the initiation of the polymerization, fluorinated vinyl ether is continuously added in an amount sufficient to produce a sinterable copolymer of tetrafluoroethylene having from about 0.5 to about 10 weight % and a melt creep viscosity of greater than about 1×10^6 Pa·S.

The polymer of this invention is characterized by having surprisingly a combination of a high level of fluorinated vinyl ether and a melt creep viscosity which is high enough to enable fabrication of articles by sintering. The resulting new polymer composition combines the advantages of ultrahigh molecular weight perfluoropolymer in chemical resistance with the ease of processibility and superior physical properties of perfluorinated copolymer.

DETAILED DESCRIPTION OF THE INVENTION

The invention relates to highly modified sinterable polytetrafluoroethylene (PTFE). Modified PTFE refers to copolymers of TFE with small concentrations of a comonomer so that the melting point of the resultant polymer is not substantially reduced below that of PTFE homopolymer. Whereas it has been previously thought that the concentration of such comonomer should be preferably less than 0.5 weight % to preserve the desired characteristics of ultrahigh molecular weight perfluoropolymer, the modified sinterable PTFE of this invention comprises a copolymer of tetrafluoroethylene containing about 0.5 to about 10 weight % of fluorinated vinyl ether, preferably about 1 to about 7

weight % of the fluorinated vinyl ether, and most preferably about 1.5 to about 7 weight % of the fluorinated vinyl ether. The modified copolymer has a melt creep viscosity of greater than about 1×10^6 Pa·S and preferably greater than about 1×10^7 Pa·S. The fluorinated vinyl ether is preferably perfluoro(alkyl vinyl ether) (PAVE) and the alkyl group contains 1 to 5 carbon atoms. The PAVE can be, for example, perfluoro(methyl vinyl ether) (PMVE), perfluoro(ethyl vinyl ether) (PEVE) or perfluoro(propyl vinyl ether) (PPVE). Mixtures of fluorinated vinyl ethers can be used if desired.

The modified PTFE of this invention has the general non-fibrillatable character of PTFE made by previously known suspension polymerization processes. Because of its extremely high molecular weight, the resin is sinterable. By sinterable resin it is meant that the resin is non-melt processible and has a measurable melt creep viscosity as determined by the method described in U. S. Patent 3,819,594. Such molecular weight ordinarily corresponds to standard specific gravity (SSG) of less than 2.25, and more commonly to SSG of less than 2.20, SSG being a parameter that decreases with increasing molecular weight. The general relationship between SSG and number average molecular weight is well known. See, for example, Sperati & Starkweather, *Fortschr. Hochpolym.-Forsch.* 2, 465 (1961).

The highly modified product of this invention, after appropriate finishing operations such as cutting, or cutting and pelletizing, is useful as granular resin, also known as molding resin. Because of the lower melting point of the highly modified resin of this invention, articles can be sintered at lower temperatures with shorter sintering cycles. The lower melting point provides a resin that can be processed by ram extrusion enabling manufacturing processes that are faster, conducted at lower temperatures and that produce articles with thinner walls.

As will be shown by example, polymer of this invention subjected to ram extrusion and sintering produces tube shaped products such as pipe liners and hoses that are at least 3X smoother than commercially available sintered PTFE and at least 1.5X smoother than commercially available sintered modified PTFE. Because the resin can be processed with fewer voids and smoother surfaces, such products have excellent electrical properties. Such resins also have value in semiconductor manufacturing areas where there is a stringent need for reducing contaminants. The present invention satisfies the need for a

molded article having the heat and chemical resistance properties of PTFE and in addition having a smoother surface that resists adhesion of contaminants to the surface. The surface smoothness of the article substantially suppresses contamination in fluid handling equipment and therefore may be adapted to a broad range of applications in the area of the precision materials industry.

As will also be shown by example, the highly modified PTFE polymer of this invention exhibits better stress cracking resistance than commercially available PFA copolymer. A preferred highly modified PTFE of this invention has a stress crack resistance as measured by MIT flex life of greater than 50,000 cycles. The resin also has excellent optical properties with extremely low haze. Further, extruded products made from the resin of this invention exhibit superior mechanical properties such as better tensile strength and higher elongation than products made from commercially available PTFE, modified PTFE, and standard PFA copolymer resin.

The process of this invention is similar to TFE suspension polymerizations known in the art, involving the steps of precharging a liquid medium to a stirred autoclave, deoxygenating, pressuring with TFE to a predetermined level, adding comonomer and optional surfactant(s), and adding initiator at sufficient level to start and to maintain the polymerization reaction. Additional TFE and vinyl ether comonomer is added on a predetermined basis, for example to maintain a specified pressure or at a specified feed rate. Any workable pressure can be used in the process of this invention. High pressure offers an advantage over low pressure in increased reaction rate. Low pressure offers an advantage over higher pressure in increased comonomer incorporation. Generally, pressures in the range of about 0.3 to 7 MPa are used, and pressures in the range of 0.7 to 3.5 MPa are preferred. Pressures in the range of 0.7 to 2.5 MPa are more preferred, and pressures in the range of 0.7 to 1.9 MPa are especially preferred.

The vinyl ether comonomer is precharged and continuously added in an amount sufficient to produce a sinterable copolymer of tetrafluoroethylene with from about 0.5 to about 10 weight %, preferably from about 1 to about 7 weight %, and most preferably about 1.5 to about 7 weight % of the fluorinated vinyl ether, the copolymer having a melt creep viscosity of greater than about 1×10^6 Pa·S, preferably greater than about 1×10^7 Pa·S.

Polymerization temperatures known for use in the suspension polymerization of TFE may also be used for the practice of the present invention. Choice of temperature is generally determined by temperature dependence of initiator. Generally, the co-polymerization in accordance with the invention is carried out at a temperature of about 0°C to about 100°C, more preferably about 10°C to about 90°C, most preferably about 15°C to about 75°C.

As in the suspension polymerization of unmodified high molecular weight PTFE and high molecular weight PTFE with low levels of comonomer, the reaction vessel in this polymerization process is agitated sufficiently to coagulate the polymer. In a preferred embodiment, the agitator is operated in a range of about 300 to about 800 rpm such as described in U.S. Patent 5,405,923 to Aten. Because the polymer coagulates during polymerization, isolation can be performed directly from aqueous medium such as by draining the aqueous medium from the resulting polymer and drying. Washing and/or cutting the polymer can also be done if desired.

The suspension polymerization process is conducted in the absence of any significant amount of telogenic agent. For the purposes of this patent application, the term telogenic agent broadly refers to any agent that will prematurely stop chain growth and includes what is commonly known as chain transfer agents. The term chain transfer implies the stopping of growth of one polymer chain and the initiation of growth of another in that the number of growing polymer radicals remains the same and the polymerization proceeds at the same rate without the introduction of more initiator. A telogenic agent produces lower molecular weight polymer in its presence than in its absence and the number of polymer chain radicals growing either remains the same or decreases. In practice most agents, if present in sufficient quantities, tend to decrease the number of radicals and ultimately the polymerization rate.

The suspension polymerization process of this invention is preferably conducted in aqueous medium. Water is convenient, liquid over a broad temperature range, essentially non-telogenic when impurities are reduced to a low level, inexpensive and safe. Preferably, the aqueous medium is essentially free of fluorine-containing organic solvent.

Initiator levels can be high relative to the amounts typically used for known modified PTFE polymerization. This achieves a surprisingly high space-time yield without the decrease in molecular

weight expected in the presence of high levels of initiator. Initiators that can be used in the practice of this invention include any free radical initiator for TFE polymerization that is effective over the temperature range to be employed. Initiators commonly employed in aqueous polymerization are thermally activated water-soluble free radical initiators such as ammonium persulfate (APS), potassium persulfate (KPS), or combinations thereof, or chemically activated redox systems such as potassium permanganate/oxalic acid/potassium bisulfite, potassium persulfate/potassium bisulfite/iron sulfate, or potassium bromate/potassium bisulfite/oxalic acid and the like.

Small amounts of non-telogenic fluorinated surfactant can be used in the process of this invention as polymerization aids. Amounts of such non-telogenic fluorinated surfactant are preferably less than 1000 ppm, more preferably less than 500 ppm and most preferably less than 100 ppm, by weight based on the amount of liquid medium employed in the polymerization. Such surfactants can include, for example, ammonium perfluorooctanoate, ammonium omega-hydroperfluorononanoate, and the perfluoroalkyl ethane sulfonic acids and salts thereof disclosed in U.S. Patent 4,380,618. Of particular utility in the production of the resin of this invention are relatively small amounts of perfluoro(polyether) carboxylic acids or dicarboxylic acids, or perfluoro(polyether) sulfonic acids or disulfonic acids, or the salts thereof. Use of such surfactants tends to enhance incorporation of vinyl ether comonomer and overall polymerization rate.

TEST METHODS

Fluoropolymer composition is determined by using Fourier transform infrared (FTIR) spectroscopy on 0.095-0.105 mm thick films pressed at 380°C. The FTIR absorption band to 4.25 μm is used as an internal thickness standard. PPVE content is determined from the FTIR band at 10.1 μm and is calculated in wt % as 0.97x the ratio of the 10.1 μm absorbance to the 4.25 μm absorbance. PEVE content is determined from the FTIR band at 9.18 μm and is calculated in weight % as 1.3x the ratio of the 9.18 μm absorbance to the 4.25 μm absorbance.

Melt viscosity measured by extrusion through a capillary orifice (capillary or extrusion viscosity) is determined at 372°C by ASTM method D1238-52T modified as described in U.S. Pat. No. 4,380,618. This capillary

viscosity is that which is normally employed for melt processible resins. A sinterable, non-melt processible resin in this test does not extrude through the capillary orifice.

Melt creep viscosity measured by the rate of elongation of a strip of resin under tensile stress (elongational viscosity) is determined at 380°C as described in U.S. Pat. No. 3,819,594 unless otherwise specified. This elongational viscosity is that which is normally employed for sinterable, non-melt processible resins. A strip of melt processible resin, defined as a resin with an observable extrusion through the above described capillary test, in the elongational test drips and breaks before rate of elongation can be measured under load.

Standard Specific Gravity (SSG) of finished resin is characterized according to ASTM Specification D-4894 which describes procedures for molding, sintering, determination of SSG unless otherwise specified.

MIT Flex Life is a modification of ASTM D-2176, the standard test method for folding endurance of paper by the MIT tester. The test is adapted to determine the flex life of films of polymer resin. The test shows the ability of a film to withstand repeated bending, folding and creasing.

Measurements are made on skived films having a rectangular shape 0.5 inches wide by 5 inches long and 0.050 inch thick (1.27 mm) unless otherwise noted. Skived film is prepared according to the method described in ASTM D4894.

The standard MIT Flex Tester, folding endurance test apparatus is available from Tinius Olsen, Testing Machine Co. of Willow Grove Pa. The test apparatus is provided with a No. 8 spring and a 1.0 kg load. Tests are conducted in two directions (machine and transverse) of the film sample. The results of five tests are averaged. The test results indicate the number of double folds required to break a sample.

Tensile strength and **elongation** of extruded tubing are measured per ASTM D-638 with a special test specimen shape. The test specimens are strips cut with a utility knife from the extruded tube in the axial direction (long dimension). Each specimen dimension is 7.62 cm (3 inches) long by 1.0 cm (0.4 inches) wide. The thickness is determined by the wall thickness of the tube 3.30 mm (0.130 inches) unless otherwise noted. The

initial jaw separation is be 22.2 ± 0.13 mm (0.875 ± 0.005 inches) and the speed of testing is 50 mm (2.0 inch) / min.

Surface smoothness is measured on a sample of tubing 10 cm long using a profilometer (Mitutoyo Surftest Model SJ-301) with a diamond stylus. The stylus is calibrated to a reference surface and then set on the outside surface of the tube, with the long dimension of the stylus centered over the tube and parallel to the long dimension of the tube. The stylus is translated along the tube surface in the axial direction (long dimension) for a distance of 0.03 inches (0.762 mm) and the Rq (root mean square) is recorded. This measurement is made at five evenly spaced places along the length of the tube. Reported values are the average of the five measurements taken. Smaller values of Rq indicate a smoother surface.

EXAMPLES

The polymerizations described in the comparative examples and examples below are all conducted in a 37.9-liter stainless steel autoclave encased in a jacket through which heat transfer fluid is circulated for heating or cooling purposes. This autoclave is equipped with a two-bladed, 45-degree angled, flat downdraft agitator mounted on a vertical shaft. Pressures reported in the following are on an absolute basis. Wet product of polymerization, unless otherwise noted, is finished by cutting at about 3-7°C in a high speed comminuting machine (Model VFSTS-06-SSB, Taylor, Stiles & Co.) and then drying in a circulating air oven for 24-48 hr at about 150°C.

COMPARATIVE EXAMPLES A – D

Comparative Examples A through D produce sinterable, vinyl ether modified granular PTFE similar to that taught by the prior art of granular PTFE polymerization.

Comparative Example A

The autoclave is charged with 21.3 L of demineralized water, 1 g of citric acid, 1 g of oxalic acid and 0.1 g of potassium meta-bisulfite. After oxygen removal, 15 g of perfluoro(propyl vinyl ether), PPVE, is introduced through the stopcock. The autoclave is pressured to 1.83 MPa at 15°C and agitated at 700 rpm. An initiator solution of 0.12 mg/L of KMnO₄ is injected at 5 ml/minute, for an injection rate of 0.6 mg KMnO₄ per minute,

continuously through the remainder of the batch. After 10 minutes of KMnO₄ initiator solution injection, a slight drop in pressure indicated onset of polymerization. At this point TFE is fed continuously into the autoclave to maintain a pressure of 1.83 MPa. After 141 minutes, 7258 g of TFE has been converted into polymer. At this point the TFE feed valve is closed and the autoclave is reacted down from 1.83 MPa to 0.7 MPa. The raw polymer, before cutting, has a finely shredded fibrous appearance typical of PTFE granular. The polymer has a comonomer content of 0.08 weight percent PPVE, an SSG of 2.159 and a melt creep viscosity of 1.4x10⁹ Pa·S. The second melting point of this resin as measured by DSC is 323.22°C, which is typical of modified PTFE.

Comparative Example B

A batch is run in a manner similar to Comparative Example A, except that 48 g of perfluoro(ethyl vinyl ether), PEVE, is charged to the autoclave with the injection pump after oxygen removal, and KMnO₄ initiator solution is injected at a rate of 0.25 mg KMnO₄ per minute. After 180 minutes 1497 g of TFE has been converted into polymer. At this point the TFE feed valve is closed and the excess monomer is vented from the autoclave. The resulting polymer has a comonomer content of 0.10 weight percent PEVE, an SSG of 2.145 and a melt creep viscosity of 1.5x10⁹ Pa·S as measured by elongational deformation.

Comparative Example C

The autoclave is charged with 21.3 L of demineralized water and 1 g of citric acid. Oxygen is then removed from the autoclave by alternately pressuring with 1540 g of TFE and evacuating. Using a high-pressure pump (microfeeder), 23 g of perfluoro(propyl vinyl ether), PPVE, is charged. The autoclave is pressured with TFE to 1.83 MPa at 65°C and agitated at 700 rpm. A solution of ammonium persulfate, APS, with a concentration of 5 g/L is injected at 50 ml/min into the autoclave for 6 minutes, for a total of 1.5 g APS injected. At the end of the APS injection, a slight pressure drop is observed indicating start of polymerization (kickoff). The TFE feed valve is opened, and additional TFE monomer is continuously fed into the autoclave to maintain the pressure at 1.83 MPa during the subsequent course of the reaction. During the course of the reaction, the temperature is maintained at 65°C. After 85 min of reaction measured from kickoff, 5443 g of TFE has been converted into polymer.

At this point the TFE feed valve is closed and the autoclave is reacted down from 1.83 MPa to 0.2 MPa. The resulting polymer has a comonomer content of 0.10 weight percent PPVE, an SSG of 2.170 and a melt creep viscosity of 1.1×10^9 Pa·S.

Comparative Example D

A batch is run in a manner similar to Comparative Example C, except that the polymerization temperature is 71°C, after oxygen removal 15 grams of PPVE is introduced through a stopcock funnel, and a total of 2.3 g of APS is used as the initiator. After 55 min of reaction measured from kickoff, 7258 g of TFE has been converted into polymer. At this point the TFE feed valve is closed and excess monomer is vented from the autoclave. The resulting polymer has a comonomer content of 0.08 weight percent PPVE, an SSG of 2.194 and an melt creep viscosity of 8×10^8 Pa·S.

Example 1

This example illustrates the suspension polymerization of highly modified sinterable PTFE at elevated temperature similar to the preparation exemplified in Brubaker U.S. Patent 2,393,967. The autoclave is charged with 21.3 L of demineralized water and 1 g of citric acid. After oxygen removal, 25 g of perfluoro(propyl vinyl ether), PPVE, is charged through the stopcock. The autoclave is pressured to 1.83 MPa with TFE at 65°C. A total of 3 g of APS is injected as initiator. After kickoff, the TFE feed valve is opened, and additional TFE monomer is continuously fed into the autoclave to maintain the pressure at 1.83 MPa during the subsequent course of the reaction. At the same time, additional PPVE is injected into the autoclave at a rate of 4.5 g/min for 60 minutes, for a total of 180 g of PPVE added after kickoff. During the course of the reaction, the temperature is maintained at 65°C. After 100 min of reaction measured from kickoff, 5443 g of TFE has been converted into polymer. At this point the TFE feed valve is closed and the excess monomer is vented from the autoclave. The resulting polymer has a comonomer content of 1.40 weight percent PPVE, an SSG of 2.178 and a melt creep viscosity of 1.2×10^9 Pa·S. The second melting point of this resin as measured by DSC is 322.36°C, very similar to the lightly modified resin of Comparative Example A, even though the vinyl ether content is higher by over an order of magnitude.

Example 2

This example illustrates the suspension polymerization of highly modified sinterable PTFE using low initiation temperature as taught by Aten in U.S. Patent 5,405,923. The autoclave is charged with 21.3 L of demineralized water, 1 g of citric acid, 1 g of oxalic acid and 0.1 g of potassium *meta*-bisulfite. After oxygen removal, 9 g of PPVE is introduced through the stopcock. The autoclave is pressured to 1.83 MPa at 15°C and agitated at 700 rpm. An initiator solution of 1 g/L of KMnO₄ is injected at 10 ml/minute, for an injection rate of 10 mg KMnO₄ per minute, continuously through the remainder of the batch. After kickoff, TFE is fed continuously into the autoclave to maintain a pressure of 1.83 MPa. At the same time, additional PPVE is injected into the autoclave at a rate of 1.5 g/min for 60 minutes, for a total of 90 g of PPVE added after kickoff. After 100 min of reaction measured from kickoff, 1678 g of TFE has been converted into polymer. At this point the TFE feed valve is closed and the autoclave is vented. The resulting polymer has a comonomer content of 1.42 weight percent PPVE, an SSG of 2.147 and a melt creep viscosity of 1.3x10⁹ Pa·S.

Example 3

This example illustrates use of non-telogenic surfactant as a polymerization aid in the suspension polymerization of highly modified sinterable PTFE. A batch is run in a manner similar to Example 1, except that 1 gram of KRYTOX® 157FSL, a poly(hexafluoropropylene oxide) carboxylic acid (commercially available from the DuPont Company), is precharged, 300 g of PPVE is precharged, 16.2 g of APS is used as the initiator, and an additional PPVE is injected into the autoclave at a rate of 7.5 g/min for 40 minutes, for a total of 3000 g of PPVE added after kickoff. After 83 min of reaction measured from kickoff, 5443 g of TFE has been converted into polymer. At this point the TFE feed valve is closed and the excess monomer is vented from the autoclave. The resulting polymer has a comonomer content of 1.64 weight percent PPVE, an SSG of 2.189 and a melt creep viscosity of 4x10⁸ Pa·S.

Example 4

This example further illustrates use of non-telogenic surfactant as a polymerization aid in the suspension polymerization of highly modified

sinterable PTFE. A batch is run in a manner similar to Example 1, except that 1 gram of FLUOROLINK® C, a perfluoropolyether dicarboxylic acid (commercially available from Ausimont), is precharged, 300 g of PPVE is precharged, 16.2 g of APS is used as the initiator, and an additional PPVE is injected into the autoclave at a rate of 7.5 g/min for 40 minutes, for a total of 3000 g of PPVE added after kickoff. After 86 min of reaction measured from kickoff, 5443 g of TFE has been converted into polymer. At this point the TFE feed valve is closed and the excess monomer is vented from the autoclave. The resulting polymer has a comonomer content of 2.53 weight percent PPVE, an SSG of 2.178 and a melt creep viscosity of 8×10^8 Pa·S.

Examples 5-24

Examples employing PPVE comonomer are run in a manner similar to Example 1 to further demonstrate and exemplify the invention. Variations of the recipe of Example 1 and the results of the polymerizations thereof are shown in Table 1.

TABLE 1

Example	g APS prech.	g PPVE prech.	g/min PPVE injected	PPVE Injection time, min	g PPVE injected	Batch time, min	g TFE Consumed	wt% PPVE	SSG	Melt creep Viscosity Pa·s
5	6.9	150	1.5	83	125	83	5443	0.83	2.178	1.7×10^9
6	6	75	3	45	135	78	5443	0.77	2.179	1.4×10^9
7	6	38	4.5	60	270	89	5443	0.98	2.178	1.3×10^9
8	6	75	3	75	225	100	5534	0.96	2.172	2.3×10^9
9	10.4	38	4.5	60	270	65	3901	1.22	2.203	2×10^8
10	6	38	4.5	60	270	74	4627	1.24	2.209	1×10^8
11	3	38	4.5	60	270	92	4944	1.27	2.195	3×10^8
12	6	38	6	45	270	81	4763	1.27	2.200	1×10^8
13	6	18	7.5	40	300	50	1769	0.94	2.192	6×10^7
14	6	18	7.5	40	300	69	4808	1.39	2.200	2×10^8
15	6	38	7.5	40	300	67	3175	1.60	2.203	1×10^8
16	12	75	7.5	40	300	77	5443	1.42	2.205	2×10^8
17	12	75	7.5	40	300	72	5851	1.52	2.212	2×10^8
18	12	75	7.5	40	300	83	6895	1.51	2.205	2×10^8
19	12	37	7.5	40	300	83	5443	1.12	2.175	1.1×10^8
20 ^a	6	37	7.5	40	300	85	5443	1.13	2.191	2×10^8
21 ^a	6	37	7.5	40	300	86	5443	1.28	2.187	4×10^8
22 ^b	3	37	7.5	40	300	83	5443	1.35	2.197	1.4×10^8
23	27	300	4.5	80	360	79	5443	1.74	2.188	5×10^7
24	27	600	7.5	45	338	75	5443	2.30	2.200	7×10^7

a – Polymerized at 70°C.

b – Polymerized at 75°C.

Example 25

A batch is run in a manner similar to Example 1, except that 300 g of perfluoro(ethyl vinyl ether), PEVE is precharged, 27 g of APS is used as the initiator, and additional PEVE is injected into the autoclave at a rate of 4.5 g/min for 80 minutes, for a total of 360 g of PEVE added after kickoff. After 100 min of reaction measured from kickoff, 4536 g of TFE has been converted into polymer. At this point the TFE feed valve is closed and the excess monomer is vented from the autoclave. The resulting polymer has a comonomer content of 5.10 weight percent PEVE. The second melting

point of this resin as measured by DSC is 315.4°C, significantly lower than the ca. 323°C observed of PTFE modified with PPVE. PEVE, being a more reactive comonomer, gave higher level of incorporation which disrupted the crystallinity sufficiently to lower the melting point.

Consequently, the melt creep viscosity of this resin is measured at 372°C. The melt creep viscosity is 3×10^6 Pa·S. Taking advantage of the lowered melting point in a similar manner, the SSG chip is sintered by directly inserting into a preheated oven at 335°C for 20 minutes followed by removal to cool on the laboratory bench top. The SSG chip upon exit of the oven is completely transparent, with none of the haze normally observed in a partially sintered homopolymer or modified PTFE billet. The specific gravity measured on the sintered chip is 2.153.

Examples 26- 30

Examples employing PEVE comonomer are run in a manner similar to Example 25 to further demonstrate and exemplify the invention. Variations of the recipe of Example 1 and the results of the polymerizations thereof are shown in Table 2.

TABLE 2

Example	g APS pre.	g PEVE pre.	g/min PEVE Injected	PEVE Injection Time, min	G PEVE Injected	Batch time, min	g TFE Consumed	wt% PEVE	SG ^c	Melt creep creep viscosity ^d Pa·S
26	12	37	7.5	40	300	83	5443	2.91	2.183	4×10^6
27 ^a	8	37	7.5	40	300	93	5443	3.28	2.174	4×10^6
28 ^b	3	37	7.5	40	300	80	907	3.00	2.139	9×10^6
29 ^b	3	37	7.5	40	300	100	4536	3.57	2.180	1.0×10^7
30	27	1800	15	80	800	100	1588	5.31	2.155	5×10^6

a – Polymerized at 70°C.

b – Polymerized at 75°C.

c – Measured on SSG chip after sintering 20 minutes in a preheated 325°C oven.

d – Measured at 372°C.

Examples 31-34

Batches are run in a manner similar to Example 1, except that 300 g of perfluoro(methyl vinyl ether), PMVE, is precharged, 27 g of APS is used as the initiator, and additional PMVE is injected into the autoclave at a rate of 4.5 g/min for 40 minutes, for a total of 180 g of PMVE added after kickoff. Results of the polymerizations are shown in Table 3.

TABLE 3

Example	Batch time minutes	g TFE Consumed	wt% PMVE	SG ^a	Melt creep Viscosity Pa·S
31	100	1179	1.08	2.130	3.03×10^7
32	51	1814	2.73	2.135	1.82×10^6
33	100	3175	4.00	2.103	2.66×10^6
34	35	907	4.12	2.121	6.12×10^6

a - Measured on SSG chip after sintering 20 minutes in a preheated 335°C oven.

Example 35 – MIT FLEX LIFE

The standard MIT folding endurance tester as modified in the description above is used to determine the flex life of polymers of this invention in comparison to commercially available polymer compositions.

Measurements are made on skived films of polymers prepared in Examples 1, 5-8. The film samples have a rectangular shape of 0.5 inch (1.27 cm) wide by 5 inches (12.7 cm) long and 0.050 inch thick (01.27 mm).

Measurements are made on Comparative Film E which is commercially available DuPont PFA 6000 film, a melt processible copolymer of TFE and PPVE with PPVE content of 4 weight percent and melt viscosity, as measured by the capillary technique in a melt indexer, of 3×10^4 Pa·S. The film sample has a rectangular shape 0.5 inch (1.27 cm) wide by 5 inches (12.7 cm) long and 0.060 inch thick (01.52 mm).

MIT Flex Life results are reported in Table 4.

TABLE 4

<u>Polymer</u>	<u>MIT Flex Life (cycles)</u>
Example 1	67,953
Example 5	82,875
Example 6	76,117
Example 7	70,788
Example 8	132,618
Comparative E	417

High MIT flex life of greater than 50,000 cycles for film of highly modified granular resin indicates much better stress cracking resistance than film made from commercial copolymer (Comparative Film E).

Example 36 – RAM EXTRUSION

The physical properties of ram extruded polymer of this invention are compared to commercially available polymer.

Polymers used for this example are:

Example 26

Comparative Polymer F Commercially available NXT 75 (available from DuPont Fluoroproducts, Wilmington DE), a PPVE modified sinterable granular with PTFE content of 0.1 weight percent and melt creep viscosity of 1×10^9 Pa·S.

Comparative Polymer G Commercially available 9B (available DuPont Fluoroproducts, Wilmington DE), an unmodified homopolymer granular with melt creep viscosity of 5×10^{10} Pa·S.

Comparative Polymer H Commercially available PFA 350 (available from DuPont Fluoroproducts, Wilmington, DE), a melt processible copolymer of TFE and PPVE with PPVE content of 4 weight percent and melt viscosity, as measured by the capillary technique in a melt indexer, of 3×10^4 Pa·S.

Samples of tubing material for the polymers of this example, except Comparative Polymer H, are obtained by the process of ram extruding in a

commercial machine model number DU.VRE.10J available from Phillips Scientific Company located in Rock Hill, SC.

The ram extrusion run conditions that are used to produce the tubing shaped material are listed in Table 5.

In this process a metered charge of resin is fed to the cold end of an extruder die that is heated over most of its length. A ram of cylindrical shape fitted with a mandrel through the center is driven down with hydraulic pressure at a controlled rate of speed and compresses the resin in the feed throat of the extruder into a charge. The hydraulic pressure driving the ram overcomes the backpressure generated by friction at the extruder walls and the brake force and moves the compressed resin charge into the barrel of the ram extruder. The ram retracts to allow the next charge to be fed. Each subsequent compressed resin charge advances the material step by step into the six heated zones of the extruder where the material is sintered at temperatures ranging from the melting point of the highly modified material up to the standard sintering temperatures for PTFE as detailed in Table 5. The individual resin charges are welded together during the sintering phase of the ram extrusion process. A continuous length of sintered extrudate emerges from the end of the ram die.

TABLE 5
Ram Extrusion Run Conditions

Polymer	Comp. F,G	Example 26
Barrel Temps, °F		
Zone 1	680	660
Zone 2	720	680
Zone 3	720	690
Zone 4	720	660
Zone 5	720	660
Zone 6	680	660
Barrel Pressure, psi	577	532
Extrusion rate, ft/hr	11	11

Melt extruded tubing of Comparative Polymer H is produced on a 1½ inch Davis Standard extruder (commercially available from Davis-Standard Corporation located in Pawcatuck, CT). The extruder setup includes a ¾ in. OD/0.060 in. wall tubing die, a vacuum box leveling die, the tube take-up system and automatic cutter.

The extruder and die temperature profiles are recorded in Table 6. The polymer melt temperatures average 640°F (338°C) and all grades achieved stable melt cones that averaged 1¼ inch (3.175 cm) in length. The temperature profiles are maintained as follows. The wall thickness of the extruded tube is 0.060 inches (1.52 mm).

TABLE 6
Melt Extruder Conditions

Extruder zone Temp, °F	1	2	3	4
	625	650	665	665
Die zone Temp, °F	1	2	3	4
	665	665	675	680
				5
				690

As described under Test Methods, test specimens for all polymers are cut according to the dimensions specified for Tensile Strength and

Elongation measurement except that the film sample from Comparative Polymer H has a thickness dimension of 0.060 inch (1.52 mm), in accordance with the extruded tubing wall thickness. In addition, surface smoothness is determined according to the method described above. Tensile strength, elongation and smoothness for all specimens are recorded in Table 7 below.

The highly modified vinyl ether resins processed in the ram extrusion process produces tubing with superior properties when compared to standard PTFE, standard modified PTFE and PFA.

The highly modified vinyl ether resin produces tube shaped products that are at least 3X smoother than commercially available sintered PTFE and at least 1.5X smoother than commercially available sintered modified PTFE.

Further, the resin exhibits superior mechanical properties such as better tensile strength and higher elongation than commercially available PTFE, modified PTFE, and standard PFA copolymer resin.

TABLE 7
Physical Properties of Highly Modified PTFE versus
Commercially Available Polymer

Resin	Comparative G 9B	Comparative F NXT	Comparative H PFA	Example 26
Physical Property				
Tensile Strength, psi	2500	1870	2360	2825
Elongation, %	390	280	260	700
Surface smoothness, Rq	14.9	6.9	4.2	4.4

What is claimed is:

1. Modified polytetrafluoroethylene powder comprising a sinterable copolymer of tetrafluoroethylene containing about 0.5 to about 10 weight % of fluorinated vinyl ether, said copolymer having a melt creep viscosity of greater than about 1×10^6 Pa·S.
2. The modified polytetrafluoroethylene powder of claim 1 wherein said sinterable copolymer contains from about 1 to about 7 weight % of said fluorinated vinyl ether.
3. The modified polytetrafluoroethylene powder of claim 1 wherein said sinterable copolymer has a melt creep viscosity of greater than about 1×10^7 Pa·S.
4. The modified polytetrafluoroethylene powder of claim 1 wherein said fluorinated vinyl ether is perfluoro(alkyl vinyl ether) and the alkyl group contains 1 to 5 carbon atoms.
5. The modified polytetrafluoroethylene powder of claim 4 wherein said perfluoro(alkyl vinyl ether) is perfluoro(propyl vinyl ether).
6. The modified polytetrafluoroethylene powder of claim 4 wherein said perfluoro(alkyl vinyl ether) is perfluoro(ethyl vinyl ether).
7. The modified polytetrafluoroethylene powder of claim 4 wherein said perfluoro(alkyl vinyl ether) is perfluoro(methyl vinyl ether).
8. The modified polytetrafluoroethylene powder of claim 1 having a stress crack resistance as measured by MIT flex life of greater than 50,000 cycles.
9. A process for polymerizing tetrafluoroethylene and fluorinated vinyl ether in a suspension polymerization process by feeding pressurized tetrafluoroethylene into a polymerization vessel containing an agitated liquid medium containing a dissolved free radical initiator, said polymerization vessel containing an initial amount of fluorinated vinyl ether, conducting the polymerization in the absence of any significant amount of telogenic agent, and after the initiation of the polymerization, continuously adding fluorinated vinyl ether in an amount sufficient to produce a sinterable copolymer of tetrafluoroethylene with from about 0.5 to about 10 weight % of said fluorinated vinyl ether, said copolymer having a melt creep viscosity of greater than about 1×10^6 Pa·S.
10. The process of claim 9 wherein said liquid medium is water.

11. The process of claim 9 wherein a sufficient amount of fluorinated vinyl ether is added to produce sinterable copolymer containing from about 1 to about 7 weight % of said fluorinated vinyl ether.

12. The process of claim 9 wherein said sinterable copolymer has a melt creep viscosity of greater than about 1×10^7 Pa·S.

13. The process of claim 9 wherein said fluorinated vinyl ether is perfluoro(alkyl vinyl ether) and the alkyl group contains 1 to 5 carbon atoms.

14. The process of claim 13 wherein said perfluoro(alkyl vinyl ether) is perfluoro(propyl vinyl ether).

15. The process of claim 13 wherein said perfluoro(alkyl vinyl ether) is perfluoro(ethyl vinyl ether).

16. The process of claim 13 wherein said perfluoro(alkyl vinyl ether) is perfluoro(methyl vinyl ether).

17. The process of claim 9 wherein said sinterable copolymer has a stress crack resistance as measured by MIT flex life of greater than 50,000 cycles.

18. The process of claim 9 wherein the polymerization is conducted in the presence of non-telogenic fluorinated surfactant.

19. The process of claim 18 wherein the fluorinated surfactant is perfluoro(polyether) carboxylic acid or perfluoro(polyether) dicarboxylic acid.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 03/13210A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C08F214/26

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 583 481 A (DAIKIN IND LTD) 23 February 1994 (1994-02-23) claims 1,3,11 example 4 page 7, line 35-49 page 8, line 12-15 example 1	1-8
A	---	9-19
X	US 5 709 944 A (NAKAMURA YUKINARU ET AL) 20 January 1998 (1998-01-20) claims example 4 example 1	1-8
A	---	9-19
	-/-	

 Further documents are listed in the continuation of box C. Patent family members are listed in annex.

° Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

4 August 2003

Date of mailing of the international search report

11/08/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Baekelmans, D

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 03/13210

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 3 819 594 A (FASIG E ET AL) 25 June 1974 (1974-06-25) cited in the application claims 1,2,5,6 column 3, line 70-75 column 6, line 29 -column 7, line 30 example 1 ---	1-8
X	US 3 635 926 A (GRESHAM WILLIAM FRANKLIN ET AL) 18 January 1972 (1972-01-18) cited in the application example 1 column 5, line 1-14 ---	1-8
A	US 4 380 618 A (KHAN AUSAT A ET AL) 19 April 1983 (1983-04-19) example 2 claims -----	9-19

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 03/13210

Patent document cited in search report	Publication date		Patent family member(s)	Publication date
EP 0583481	A 23-02-1994	DE	69326979 D1	16-12-1999
		DE	69326979 T2	20-04-2000
		EP	0583481 A1	23-02-1994
		JP	3177983 B2	18-06-2001
		US	5763082 A	09-06-1998
		WO	9316126 A1	19-08-1993
		US	5709944 A	20-01-1998
US 5709944	A 20-01-1998	DE	69326979 D1	16-12-1999
		DE	69326979 T2	20-04-2000
		EP	0583481 A1	23-02-1994
		WO	9316126 A1	19-08-1993
		JP	3177983 B2	18-06-2001
		US	5763082 A	09-06-1998
US 3819594	A 25-06-1974	CA	1024700 A1	17-01-1978
		DE	2325042 A1	24-01-1974
		FR	2190845 A1	01-02-1974
		GB	1423707 A	04-02-1976
		IT	987654 B	20-03-1975
		JP	49027588 A	12-03-1974
		JP	50038159 B	08-12-1975
		NL	7306916 A	20-11-1973
US 3635926	A 18-01-1972	CA	927049 A1	22-05-1973
		DE	2052495 A1	06-05-1971
		FR	2066540 A5	06-08-1971
		GB	1311370 A	28-03-1973
		JP	48020788 B	23-06-1973
		NL	7015740 A , B ,	29-04-1971
US 4380618	A 19-04-1983	BR	8204789 A	02-08-1983
		CA	1224900 A1	28-07-1987
		DE	3267591 D1	02-01-1986
		EP	0073121 A1	02-03-1983
		JP	1376335 C	22-04-1987
		JP	58038706 A	07-03-1983
		JP	61043364 B	27-09-1986