



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : B41M 5/00, 7/00, C08J 7/04, C09D 171/02, 133/14</p>	<p>A1</p>	<p>(11) International Publication Number: WO 99/21724</p> <p>(43) International Publication Date: 6 May 1999 (06.05.99)</p>
<p>(21) International Application Number: PCT/US98/22209</p> <p>(22) International Filing Date: 22 October 1998 (22.10.98)</p> <p>(30) Priority Data: 08/958,907 28 October 1997 (28.10.97) US</p> <p>(71) Applicant: PPG INDUSTRIES OHIO, INC. [US/US]; 3800 West 143rd Street, Cleveland, OH 44111 (US).</p> <p>(72) Inventors: LI, Huawen; 213 Rose Court North, Delmont, PA 15626 (US). WANG, Alan, E.; 3870 Anjou Lane, Hoffman Estates, IL 60195 (US). HILL, Charles, T.; 211 Lynn Drive, New Brighton, PA 15066 (US). SWISHER, Robert; 204 Sunridge Road, Pittsburgh, PA 15238 (US). DIEHL, David, A.; 310 Nichols Road, Pittsburgh, PA 15237 (US).</p> <p>(74) Agents: MORRIS, George, D.; PPG Industries, Inc., One PPG Place, Pittsburgh, PA 15272 (US) et al.</p>		<p>(81) Designated States: CA, JP, MX, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>With international search report.</i></p>
<p>(54) Title: INKJET PRINTING MEDIUM COMPRISING CROSSLINKED PRINTING SURFACE</p>		
<p>(57) Abstract</p> <p>An article comprises: (a) a substrate having at least one surface; (b) an interior water-absorptive coating on the surface wherein the interior water-absorptive coating comprises hydrophilic organic polymer which is substantially free from crosslinks derived from ethylenic unsaturation or which contains few crosslinks derived from ethylenic unsaturation; and (c) an exterior water-absorptive coating on the interior water-absorptive coating wherein the exterior water-absorptive coating comprises hydrophilic organic polymer which contains numerous crosslinks derived from ethylenic unsaturation; wherein: (d) the interior coating, the exterior coating, or each of the interior coating and the exterior coating further comprises discrete particles having a number average particle size in the range of from 1 to 500 nanometers.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

- 1 -

INKJET PRINTING MEDIUM COMPRISING CROSSLINKED PRINTING SURFACE

Low wet smear resistance is a considerable problem that has arisen in inkjet printing. "Wet smear resistance" is the ability of inkjet printing to resist smearing when the inkjet printed and dried substrate is rubbed in the presence of water.

Printing media which may be inkjet printed to provide images of improved wet smear resistance when used with wide variety of inkjet printing inks, printed media which provides images of improved wet smear resistance, and a method for producing such products have now been found.

Accordingly one embodiment of the invention is a process comprising: (a) providing a substrate having at least one surface; (b) forming an interior coating on the surface by applying to the surface an interior coating composition comprising: (1) first volatile aqueous liquid; and (2) water-solubilized or water-dispersed film-forming hydrophilic organic polymer which is substantially free from ethylenically unsaturated groups or which contains only few ethylenically unsaturated groups; (c) forming an exterior coating on the interior coating by applying to the interior coating an exterior coating composition comprising: (1) second volatile aqueous liquid; and (2) a film-forming member selected from the group consisting of: (A) water-solubilized film-forming hydrophilic organic polymer which contains numerous ethylenically unsaturated groups, (B) water-dispersed film-forming hydrophilic organic polymer which contains numerous ethylenically unsaturated groups, (C) water-solubilized film-forming hydrophilic organic oligomer which contains numerous ethylenically unsaturated groups, (D) water-dispersed film-forming hydrophilic organic oligomer which contains numerous

- 2 -

ethylenically unsaturated groups, (E) water-solubilized film-forming hydrophilic organic monomer which contains numerous ethylenically unsaturated groups, (F) water-dispersed film-forming hydrophilic organic monomer which contains numerous ethylenically unsaturated groups, and (G) a mixture of two or more thereof; and (d) exposing the substrate, the interior coating, and the exterior coating to actinic light, ionizing radiation, or heat to provide the exterior coating with numerous crosslinks derived from ethylenically unsaturated groups present in the applied exterior coating composition; wherein: (e) the interior coating composition, the exterior coating composition, or each of the interior coating composition and the exterior coating composition further comprises discrete particles which are not film-forming and which have a number average particle size in the range of from 1 to 500 nanometers; (f) first volatile aqueous liquid is removed from the interior coating to produce an interior water-absorptive coating on the surface of the substrate; and (g) second volatile aqueous liquid is removed from the exterior coating to produce an exterior water-absorptive coating on the surface of the interior water-absorptive coating.

Another embodiment of the invention is the product produced by the above process.

Yet another embodiment of the invention is an article comprising: (a) a substrate having at least one surface; (b) an interior water-absorptive coating on the surface wherein the interior water-absorptive coating comprises hydrophilic organic polymer which is substantially free from crosslinks derived from ethylenic unsaturation or which contains few crosslinks derived from ethylenic unsaturation; and (c) an exterior water-absorptive coating on

- 3 -

the interior water-absorptive coating wherein the exterior water-absorptive coating comprises hydrophilic organic polymer which contains numerous crosslinks derived from ethylenic unsaturation; wherein: (d) the interior coating, the exterior coating, or each of the interior coating and the exterior coating further comprises discrete particles having a number average particle size in the range of from 1 to 500 nanometers.

The interior water-absorptive coating and the exterior water-absorptive coating both comprise hydrophilic organic polymer. The difference is that the hydrophilic organic polymer of the interior water-absorptive coating contains few, if any at all, crosslinks derived from ethylenic unsaturation, whereas the hydrophilic organic polymer of the second binder contains numerous crosslinks derived from ethylenic unsaturation. The crosslinks derived from ethylenic unsaturation may be provided by reacting linear polymer containing a plurality of ethylenically unsaturated groups along the polymer backbone, with monomer containing at least one ethylenically unsaturated group. Preferably, however, the crosslinks derived from ethylenic unsaturation are provided from polymer, oligomer, and/or monomer containing at least two ethylenically unsaturated groups.

The water absorbency of the interior water-absorptive coating is greater than that of the exterior water-absorptive coating. Crosslinks in water-absorptive coatings serve to reduce the water solubility of the organic polymer, but they also tend to reduce the water-absorbency of the coating. The crosslinks present in the exterior water-absorptive coating improve the wet smear resistance of the printing medium, but they are not so numerous as will seriously preclude absorption of water from applied inkjet

- 4 -

printing ink or transfer of such water to the interior water-absorptive coating. The crosslinks in the exterior water-absorptive coating should also not be so numerous that the time required for drying ink at the surface of the coating is unduly extended. Crosslinks in the interior water-absorptive coating, if present at all, should not be so numerous as would unduly reduce the rate of transfer of water from the exterior water-absorptive coating to the interior water-absorptive coating.

10 Organic polymer which contains crosslinks may be a single polymer, but it is more often a mixture of two or more polymers, at least one of which contains crosslinks. It is permissible but not necessary that all polymers in a mixture of polymers contain crosslinks.

15 The number of crosslinks derived from ethylenic unsaturation is principally determined by the number of ethylenically unsaturated groups present in the organic polymer, organic oligomer, and/or organic monomer present in the coating composition which is applied to form the coating.

20 In the interests of brevity, the coating composition used to form the interior water-absorptive coating will be referred to as the "interior coating composition" and the coating composition used to form the exterior water-absorptive coating will be referred to as the "exterior coating composition".

25 Because crosslinking changes the structure of monomers, oligomers, and polymers, the hydrophilic organic polymer present in the interior water-absorptive coating and the hydrophilic organic polymer present in the exterior water-absorptive coating are best described in connection with the hydrophilic polymers, oligomers, and/or monomers present in the coating compositions used to form these coatings.

30

- 5 -

The number average particle size of the discrete particles is in the range of from 1 to 500 nanometers. Often the number average particle size is in the range of from 1 to 100 nanometers. Frequently the number average particle size is in the range of from 1 to 50 nanometers. Preferably the number average particle size is in the range of from 1 to 20 nanometers.

As used herein and in the claims number average particle size is determined by transmission electron microscopy.

The discrete particles may be inorganic filler particles, thermoset organic particles, or substantially nonfilm-forming thermoplastic organic polymer particles.

The discrete inorganic filler particles which may be present are often discrete particles of metal oxide. The metal oxide constituting the particles may be a simple metal oxide (i.e., the oxide of a single metal) or it may be a complex metal oxide (i.e., the oxide of two or more metals). The particles of metal oxide may be particles of a single metal oxide or they may be a mixture of different particles of different metal oxides.

Examples of suitable metal oxides include alumina, silica, and titania. Further examples of suitable metal oxides include cerium oxide, tin oxide, and zinc oxide. Other oxides may optionally be present in minor amount. Examples of such optional oxides include, but are not limited to, zirconia, hafnia, and yttria. Yet other metal oxides that may optionally be present are those which are ordinarily present as impurities such as for example, iron oxide. For purposes of the present specification and claims, silicon is considered to be a metal.

- 6 -

When the discrete particles are particles of alumina, most often the alumina is alumina monohydroxide. Particles of alumina monohydroxide, $AlO(OH)$, and their preparation are known. The preparation and properties of alumina monohydroxide are described by B. E. Yoldas in The American Ceramic Society Bulletin, Vol. 54, No. 3, (March 1975), pages 289-290, in Journal of Applied Chemical Biotechnology, Vol. 23 (1973), pages 803-809, and in Journal of Materials Science, Vol. 10 (1975), pages 1856-1860.

10 Briefly, aluminum isopropoxide or aluminum secondary-butoxide are hydrolyzed in an excess of water with vigorous agitation at from 75 C to 80°C to form a slurry of aluminum monohydroxide. The aluminum monohydroxide is then peptized at temperatures of at least 80°C with an acid to form a clear

15 alumina monohydroxide sol which exhibits the Tyndall effect when illuminated with a narrow beam of light. Since the alumina monohydroxide of the sol is neither white nor colored, it is not a pigment and does not function as a pigment in the present invention. The acid employed is noncomplexing with

20 aluminum, and it has sufficient strength to produce the required charge effect at low concentration. Nitric acid, hydrochloric acid, perchloric acid, acetic acid, chloroacetic acid, formic acid and methacrylic acid meet these requirements. The acid concentration is usually in the range

25 of from 0.03 to 0.1 mole of acid per mole of aluminum alkoxide. Although it is desired not to be bound by any theory, it is believed that the alumina monohydroxide produced in this manner is pseudoboehmite. Pseudoboehmite is indeed the preferred alumina monohydroxide for use in the present

30 invention. The alumina monohydroxide is not a pigment and does not function as a pigment in the present invention. In

- 7 -

most instances the alumina monohydroxide is transparent and colorless.

Colloidal silica is also known. Its preparation and properties are described by R. K. Iler in The Chemistry of Silica, John Wiley & Sons, Inc., New York (1979) ISBN 0-471-02404-X, pages 312-337, and in United States Patents No. 2,601,235; 2,614,993; 2,614,994; 2,617,995; 2,631,134; 2,885,366; and 2,951,044, the disclosures of which are, in their entireties, incorporated herein by reference.

Examples of commercially available colloidal silica include Ludox® HS, LS, SM, TM and CL-X colloidal silica (E. I. du Pont de Nemours & Company, Inc.) in which the counter ion is the sodium ion, and Ludox® AS colloidal silica (E. I. du Pont de Nemours & Company, Inc.) in which the counter ion is the ammonium ion. Another example is Ludox® AM colloidal silica (E. I. du Pont de Nemours & Company, Inc.) in which some of the silicon atoms have been replaced by aluminum atoms and the counter ion is the sodium ion.

Colloidal titania is also known. Its preparation and properties are described in United States Patent No. 4,275,118. Colloidal titania may also be prepared by reacting titanium isopropoxide [CAS 546-68-9] with water and tetramethyl ammonium hydroxide.

Discrete thermoset organic filler particles which may be present are particles of organic polymer crosslinked at least to the extent that they cannot be significantly softened or remelted by heat. The thermoset organic filler particles are not film-forming. Examples of such thermoset organic polymer particles include particles of thermoset melamine-aldehyde polymer, thermoset resorcinol-aldehyde polymer, thermoset phenol-resorcinol-aldehyde polymer, thermoset

- 8 -

(meth)acrylate polymer, or thermoset styrene-divinylbenzene polymer.

The discrete thermoplastic organic filler particles which may be present are thermoplastic in that they may be
5 softened and/or melted at elevated temperatures. Nevertheless they are not film-forming when used in accordance with this invention. Examples of suitable discrete thermoplastic organic polymer particles include polyethylene particles such as those contained in Poly Emulsion 316N30 sol (ChemCor Inc.,
10 Chester, NY), maleated polypropylene particles such as those contained in Poly Emulsion 43C30 sol (ChemCor Inc., Chester, NY), and polyacrylate, polymethacrylate, polystyrene, and/or fluoropolymer particles made by microemulsion processes.

15 When discrete particles which are not film-forming and which have a number average particle size in the range of from 1 to 500 nanometers are present in both the interior coating composition and the exterior coating composition, they may be the same or different. Similarly, the number average
20 particle size of the discrete nonfilm-forming particles present in the interior coating composition may be the same or different from the number average particle size of the discrete nonfilm-forming particles present in the exterior coating composition.

25 The amount of the discrete nonfilm-forming particles in the interior water-absorptive coating, or in the exterior water-absorptive coating, as the case may be, may vary widely. Usually the discrete nonfilm-forming particles constitute from 1 to 80 percent by weight of the coating. In
30 many cases the discrete nonfilm-forming particles constitute from 5 to 75 percent by weight of the coating. From 15 to 65 percent by weight is preferred.

- 9 -

Each of the coating compositions used to produce the printing media of the invention can independently be in the form of an aqueous solution in which case the volatile aqueous liquid is a volatile aqueous solvent for the film-forming organic polymer of the coating composition, or the coating
5 composition can be in the form of an aqueous dispersion in which instance the volatile aqueous liquid is a volatile aqueous dispersion liquid for at least some of the film-forming organic polymer of the coating composition.

10 The volatile aqueous liquid is predominately water. Small amounts of low boiling volatile water-miscible organic liquids may be intentionally added for particular purposes. Examples of such low boiling volatile water-miscible organic liquids solvents include methanol
15 [CAS 67-56-1], ethanol [CAS 64-17-5], 1-propanol, [CAS 71-23-8], 2-propanol [CAS 67-63-0], 2-butanol [CAS 78-92-2], 2-methyl-2-propanol [CAS 75-65-0], 2-propanone [CAS 67-64-1], and 2-butanone [CAS 78-93-3]. The listing of such liquids is by no means exhaustive.

20 Similarly, water-miscible organic liquids which themselves are of low, moderate, or even negligible volatility may be intentionally added for particular purposes, such as for example, retardation of evaporation. Examples of such organic liquids include 2-methyl-1-propanol [CAS 78-83-1],
25 1-butanol [CAS 71-36-3], 1,2-ethanediol [CAS 107-21-1], and 1,2,3-propanetriol [CAS 56-81-5]. The listing of such liquids is by no means exhaustive.

Those materials which, although not intentionally added for any particular purpose, are normally present as
30 impurities in one or more of the components of the coating compositions of the invention and which become components of

- 10 -

the volatile aqueous liquid, may be present at low concentrations.

In most instances water constitutes at least 60 percent by weight of the volatile aqueous liquid. Often
5 water constitutes at least 80 percent by weight of the volatile aqueous liquid. Preferably water constitutes substantially all of the volatile aqueous liquid.

The amount of volatile aqueous liquid present in the coating composition may vary widely. The minimum amount is
10 that which will produce a coating composition having a viscosity low enough to apply as a coating. The maximum amount is not governed by any theory, but by practical considerations such as the cost of the volatile aqueous liquid, the minimum desired thickness of the coating to be
15 deposited, and the cost and time required to remove volatile aqueous liquid from the applied wet coating. Usually, however, the volatile aqueous liquid constitutes from 30 to 98 percent by weight of the coating composition. In many cases the volatile aqueous liquid constitutes from 50 to 96 percent
20 by weight of the coating composition. Often the volatile aqueous liquid constitutes from 60 to 95 percent by weight of the coating composition. Preferably the volatile aqueous liquid constitutes from 80 to 95 percent by weight of the composition.

25 In general, the film-forming hydrophilic organic polymers, film-forming hydrophilic organic oligomers, and/or film-forming hydrophilic organic monomers present in the coating compositions as film-forming members are water-soluble or water-dispersible.

30 The water-soluble film-forming hydrophilic organic polymers which may be used in the present invention are numerous and widely varied. Examples include poly(ethylene

- 11 -

oxide), poly(vinyl alcohol), poly(vinyl pyrrolidone), water-soluble cellulosic organic polymer, or a mixture of two or more thereof.

Water-soluble poly(ethylene oxide) is known. Such materials are ordinarily formed by polymerizing ethylene oxide [CAS 75-21-8], usually in the presence of a small amount of an initiator such as low molecular weight glycol or triol. Examples of such initiators include ethylene glycol [CAS 107-21-1], diethylene glycol [CAS 111-46-6], triethylene glycol [CAS 112-27-6], tetraethylene glycol [CAS 112-60-7], propylene glycol [CAS 57-55-6], trimethylene glycol [CAS 504-63-2], dipropylene glycol [CAS 110-98-5], glycerol [CAS 56-81-5], trimethylolpropane [CAS 77-99-6], and α,ω -diaminopoly(propylene glycol) [CAS 9046-10-0]. One or more other lower alkylene oxides such as propylene oxide [CAS 75-56-9] and trimethylene oxide [CAS 503-30-0] may also be employed as comonomer with the ethylene oxide, whether to form random polymers or block polymers, but they should be used only in those small amounts as will not render the resulting polymer both water-insoluble and nondispersible in water. As used herein and in the claims, the term "poly(ethylene oxide)" is intended to include the foregoing copolymers of ethylene oxide with small amounts of lower alkylene oxide, as well as homopolymers of ethylene oxide. The configuration of the poly(ethylene oxide) can be linear, branched, comb, or star-shaped. The preferred terminal groups of the poly(ethylene oxide) are hydroxyl groups, but terminal lower alkoxy groups such as methoxy groups may be present provided their types and numbers do not render the poly(ethylene oxide) polymer unsuitable for its purpose. In most cases the poly(ethylene oxide) is water-soluble. The preferred poly(ethylene oxide) is a water-soluble homopolymer

- 12 -

of ethylene oxide produced using a small amount of ethylene glycol as an initiator.

The weight average molecular weight of the water-soluble poly(ethylene oxide) may vary widely. Usually
5 it is in the range of from 100,000 to 3,000,000 although a weight average molecular weights somewhat below 100,000 or somewhat above 3,000,000 may be used. Often the weight average molecular weight of the water-soluble poly(ethylene oxide) is in the range of from 150,000 to 1,000,000.
10 Frequently the weight average molecular weight of the water-soluble poly(ethylene oxide) is in the range of from 200,000 to 1,000,000. From 300,000 to 700,000 is preferred.

Water-soluble poly(vinyl alcohol) may be broadly classified as one of two types. The first type is fully
15 hydrolyzed water-soluble poly(vinyl alcohol) in which less than 1.5 mole percent acetate groups are left on the molecule. The second type is partially hydrolyzed water-soluble poly(vinyl alcohol) in which from 1.5 to as much as 20 mole percent acetate groups are left on the molecule.
20 The water-soluble organic polymer may comprise either type or a mixture of both. The weight average molecular weight of the water-soluble poly(vinyl alcohol) may vary considerably, but often it is in the range of from 10,000 to 800,000. In many cases the weight average molecular weight is in the range of
25 from 50,000 to 700,000. From 100,000 to 500,000 is preferred.

Water-soluble poly(vinylpyrrolidone) is a known material and may be used. Usually, but not necessarily, the weight average molecular weight of the poly(vinylpyrrolidone) is in the range of from 1,000 to 3,000,000. Often the weight
30 average molecular weight is in the range of from 5,000 to 1,000,000. From 5,000 to 500,000 is preferred.

- 13 -

There are many widely varying types of water-soluble cellulosic organic polymers which may be employed in the present invention. Of these, the water-soluble cellulose ethers are preferred water-soluble cellulosic organic polymers. Many of the water-soluble cellulose ethers are also excellent water retention agents. Examples of the water-soluble cellulose ethers include water-soluble methylcellulose [CAS 9004-67-5], water-soluble carboxymethylcellulose, water-soluble sodium carboxymethylcellulose [CAS 9004-32-4], water-soluble ethylmethylcellulose, water-soluble hydroxyethylmethylcellulose [CAS 9032-42-2], water-soluble hydroxypropylmethylcellulose [CAS 9004-65-3], water-soluble hydroxyethylcellulose [CAS 9004-62-0], water-soluble ethylhydroxyethylcellulose, water-soluble sodium carboxymethylhydroxyethylcellulose, water-soluble hydroxypropylcellulose [CAS 9004-64-2], water-soluble hydroxybutylcellulose [CAS 37208-08-5], water-soluble hydroxybutylmethylcellulose [CAS 9041-56-9] and water-soluble cellulose sulfate sodium salt [CAS 9005-22-5]. Water-soluble hydroxypropylcellulose is preferred.

Water-soluble hydroxypropylcellulose is a known material and is available commercially in several different weight average molecular weights. The weight average molecular weight of the water-soluble hydroxypropylcellulose used in the present invention can vary widely, but usually it is in the range of from 100,000 to 1,000,000. Often the weight average molecular weight is in the range of from 100,000 to 500,000. From 200,000 to 400,000 is preferred. Two or more water-soluble hydroxypropylcelluloses having different weight average molecular weights may be admixed to

- 14 -

obtain a water-soluble hydroxypropyl cellulose having a differing weight average molecular weight.

Similarly, there are many widely varying kinds of other water-soluble polymers which may be employed in the present invention. Examples include water-soluble poly(vinylpyridine), water-soluble poly(ethylenimine), water-soluble ethoxylated poly(ethylenimine), water-soluble poly(ethylenimine)-epichlorohydrin, water-soluble polyacrylate, water-soluble sodium polyacrylate, water-soluble poly(acrylamide), water-soluble carboxy modified poly(vinyl alcohol), water-soluble poly(2-acrylamido-2-methylpropane sulfonic acid), water-soluble poly(styrene sulfonate), water-soluble vinyl methyl ether/maleic acid copolymer, water-soluble styrene-maleic anhydride copolymer, water-soluble ethylene-maleic anhydride copolymer, water-soluble acrylamide/acrylic acid copolymer, water-soluble poly(diethylene triamine-co-adipic acid), water-soluble poly[(dimethylamino)ethyl methacrylate hydrochloride], water-soluble quaternized poly(imidazoline), water-soluble poly(N,N-dimethyl-3,5-dimethylene piperidinium chloride), water-soluble poly(vinylpyridinium halide), water-soluble starch, water-soluble oxidized starch, water-soluble casein, water-soluble gelatin, water-soluble sodium alginate, water-soluble carrageenan, water-soluble dextran, water-soluble gum arabic, water-soluble pectin, water-soluble albumin, and water-soluble agar-agar.

Still other kinds of other water-soluble polymers which may be employed in the present invention include the water-soluble anionic polyacrylates and the water-soluble cationic polyacrylates. Water-soluble anionic polyacrylates are themselves well known. Usually, but not necessarily, they are copolymers of one or more (meth)acrylic esters and enough

- 15 -

(meth)acrylic acid and/or (meth)acrylic acid salt to provide sufficient carboxylate anions to render the polymer water-soluble. Similarly, water-soluble cationic polyacrylates are themselves well known. Usually, but not necessarily, they are copolymers of one or more (meth)acrylic esters and enough amino-functional ester of (meth)acrylic acid to provide sufficient onium cations to render the acrylic polymer water-soluble. The onium may be primary ammonium, secondary ammonium, tertiary ammonium, quaternary ammonium, phosphonium, or sulfonium. Secondary ammonium, tertiary ammonium, or quaternary ammonium is preferred. Quaternary ammonium is especially preferred. Usually the water-soluble cationic polyacrylate is a primary, secondary, tertiary, or quaternary ammonium salt, or it is a quaternary ammonium hydroxide.

Water-dispersible film-forming polymers such as water-dispersible poly(ethylene-co-acrylic acid) or water-dispersible cationic acrylic polymer may be used.

The water-soluble or water-dispersible film-forming hydrophilic organic polymers, oligomers, and monomers which contain numerous ethylenically unsaturated groups may be widely varied. In view of the enormous variations in structure, there are no sharp boundaries or distinctions between polymers, oligomers, and monomers. Often the classification depends upon what is viewed as a repeating unit, viz., a mer unit. For example trimethylolpropane, chain extended with oxy-1,2-ethanediyl groups and terminated with acryloyl groups can be viewed as a monomer if the trimethylolpropane moiety is viewed as the central portion of a mer unit, or it can be viewed as a polymer or oligomer, as the case may be, if oxy-1,2-ethanediyl is regarded as a mer unit.

- 16 -

The number of ethylenically unsaturated groups provided by each molecule may be zero, small, or large, but collectively the molecules contain numerous ethylenically unsaturated groups. In order for crosslinked polymer to form,
5 at least a portion of the polymer, oligomer, or monomer should contain at least two ethylenically unsaturated groups per molecule.

In most instances the ethylenic unsaturation is provided by acryloyl groups, methacryloyl groups, allyl
10 groups, vinyl groups, fumaroyl groups, and maleoyl groups. Examples of such polymers, monomers, and oligomers which may be used include the water-soluble polyacrylates, polymethacrylates, polyfumarates, and polymaleates of low, medium, or high molecular weight water-soluble poly(ethylene
15 oxides). Of particular importance are water-soluble poly(ethylene oxide) diacrylate [CAS 26570-48-9], water-soluble poly(ethylene oxide) dimethacrylate [CAS 25852-47-5], and water-soluble poly(ethylene oxide) dimaleate [CAS 36247-43-5]. Other examples are the
20 water-soluble poly(vinyl alcohols) in which the hydrogens of some of the hydroxyl groups have been replaced with acryloyl or methacryloyl groups. Yet other examples include water-soluble or water-dispersible materials formed by chain extending a central unit with oxy-1,2-ethanediyl groups and
25 terminating with acryloyl or methacryloyl groups. Examples of central groups which may be used include the oxy-1,2-ethanediyl extended aliphatic or aromatic diols, triols, and tetrols, such as for example, trimethylolpropane, glycerine, bisphenol A, propylene glycol, and pentaerythritol.

30 Water-soluble or water-dispersible organic polymers, oligomers, and monomers, which contain one ethylenically unsaturated group per molecule may also be present. In most

- 17 -

instances the ethylenic unsaturation is provided by acryloyl groups, methacryloyl groups, allyl groups, vinyl groups, fumaroyl groups, and maleoyl groups. Examples of such polymers, oligomers, and monomers include the water-soluble
5 monoacrylates, monomethacrylates, monofumarates, and monomaleates of the water-soluble poly(ethylene oxides) and the oxy-1,2-ethanediyl extended aliphatic or aromatic diols, triols, and tetrols described above. Of particular importance are water-soluble poly(ethylene oxide) monoacrylate
10 [CAS 26403-58-7], water-soluble poly(ethylene oxide) monomethacrylate [CAS 25736-86-1], and water-soluble poly(ethylene oxide) monomaleate [CAS 37916-19-1].

Usually the ratio of the number of ethylenically unsaturated groups per gram of the film-forming organic
15 polymer present in the interior coating composition to the number of ethylenically unsaturated groups per gram of the film-forming member present in the exterior coating composition is less than 0.9:1. Often the ratio is less than 0.1:1. Frequently the ratio is less than 0.01:1. In many
20 instances the ratio is substantially zero.

Usually the film-forming organic polymer of the interior coating composition constitutes at least 1 percent by weight of the of the interior coating composition. Generally the film-forming organic polymer constitutes at least 3
25 percent by weight of the interior coating composition. In many instances the film-forming organic polymer constitutes at least 5 percent by weight of the interior coating composition. Often the film-forming organic polymer constitutes from 1 to 40 percent by weight of the interior
30 coating composition. Frequently the film-forming organic polymer constitutes from 2 to 30 percent by weight of the interior coating composition. In many cases the film-forming

- 18 -

organic polymer constitutes from 3 to 20 percent by weight of the interior coating composition.

Similarly the film-forming member of the exterior coating composition constitutes at least 1 percent by weight of the of the exterior coating composition. Generally the film-forming organic member constitutes at least 3 percent by weight of the exterior coating composition. In many instances the film-forming organic member constitutes at least 5 percent by weight of the exterior coating composition. Often the film-forming organic member constitutes from 1 to 40 percent by weight of the exterior coating composition. Frequently the film-forming organic member constitutes from 2 to 30 percent by weight of the exterior coating composition. In many cases the film-forming organic constitutes from 3 to 20 percent by weight of the exterior coating composition.

When the discrete nonfilm-forming particles having a number average particle size of from 1 to 500 nanometers are present in the a coating composition, they usually constitute at least 0.1 percent by weight of the of the coating composition. Generally the discrete nonfilm-forming particles having a number average particle size of from 1 to 500 nanometers constitute at least 1 percent by weight of the coating composition. In many instances the discrete nonfilm-forming particles having a number average particle size of from 1 to 500 nanometers constitute at least 2 percent by weight of the coating composition. Often the discrete nonfilm-forming particles having a number average particle size of from 1 to 500 nanometers constitute from 0.1 to 30 percent by weight of the coating composition. Frequently the discrete nonfilm-forming particles having a number average particle size of from 1 to 500 nanometers constitute from 1 to 25 percent by weight of the coating composition. In many

- 19 -

cases the discrete nonfilm-forming particles having a number average particle size of from 1 to 500 nanometers constitute from 2 to 20 percent by weight of the coating composition.

A material which may optionally be present in the coating composition is mordant. For purposes of the present specification and claims mordant is considered not to be a part of the film-forming organic polymer. Mordants, also known as ink-fixing agents, are materials which interact, usually by reaction or absorption, with binder, dye, and/or pigment of the ink applied to the coated substrate. There are many available mordants which may be used. Suitable mordants include, but are not limited to, the poly(ethylenimines), the ethoxylated poly(ethylenimines), and other derivatives of poly(ethylenimine). Examples include Lupasol™ SC-61B ink-fixing agent (BASF Aktiengesellschaft), Lupasol™ SC-62J mordant (BASF Aktiengesellschaft), and Lupasol™ SC-86X mordant (BASF Aktiengesellschaft), Lupasol™ PS mordant (BASF Aktiengesellschaft), Lupasol™ G-35 mordant (BASF Aktiengesellschaft), and Lupasol™ FG mordant (BASF Aktiengesellschaft).

When used, the amount of mordant present in the coating composition may vary considerably. In such instances the weight ratio of the mordant to the film-forming organic polymer is usually in the range of from 0.5:100 to 30:100. Frequently the weight ratio is in the range of from 0.5:100 to 20:100. Often the weight ratio is in the range of from 1:100 to 10:100. From 2:100 to 5:100 is preferred. These ratios are on the basis of mordant dry solids and film-forming organic polymer dry solids.

Another material which may optionally be present in the coating composition is surfactant. For purposes of the present specification and claims surfactant is considered not

- 20 -

to be a part of the film-forming organic polymer. There are many available surfactants and combinations of surfactants which may be used. Examples of suitable surfactants include, but are not limited to, Fluorad[®] FC-170-C surfactant (3M
5 Company), and Triton[®] X-405 surfactant (Union Carbide Corporation).

When used, the amount of surfactant present in the coating composition may vary considerably. In such instances the weight ratio of the surfactant to the film-forming
10 hydrophilic organic polymer is usually in the range of from 0.01:100 to 10:100. In many instances the weight ratio is in the range of from 0.1:100 to 10:100. Often the weight ratio is in the range of from 0.2:100 to 5:100. From 0.5:100 to 2:100 is preferred. These ratios are on the basis of
15 surfactant dry solids and film-forming hydrophilic organic polymer dry solids.

There are many other conventional adjuvant materials which may optionally be present in the coating composition. These include such materials as lubricants, waxes,
20 plasticizers, antioxidants, organic solvents, lakes, and pigments. The listing of such materials is by no means exhaustive. These and other ingredients may be employed in their customary amounts for their customary purposes so long as they do not seriously interfere with good coating
25 composition formulating practice.

The coating compositions are usually prepared by simply admixing the various ingredients. The ingredients may be mixed in any order. Although the mixing of liquid and solids is usually accomplished at room temperature, elevated
30 temperatures are sometimes used. The maximum temperature which is usable depends upon the heat stability of the ingredients.

- 21 -

The coatings are formed by applying coating compositions using any conventional technique known to the art. These include spraying, spinning, curtain coating, dipping, rod coating, blade coating, roller application, size
5 press, printing, brushing, drawing, slot-die coating, and extrusion.

Exterior coating composition may be applied to the interior coating with or without significant removal of first volatile aqueous liquid from the interior coating prior to the
10 application.

The same coating composition may be applied once or a multiplicity of times. When the same coating composition is applied a multiplicity of times, the applied coating composition may be applied with or without significant prior
15 removal of volatile aqueous liquid from the previous coating or coatings.

Following application of a coating composition, volatile aqueous liquid may be partially or totally removed from one or more of the coatings. Following final application
20 of the final coating composition, volatile aqueous liquid is partially or totally removed from one or more of the coatings. This may be accomplished by any conventional drying technique.

The thickness of the interior coating may vary
25 widely, but in most instances the thickness of the interior coating is in the range of from 1 to 30 μm . In many cases the thickness of the interior coating is in the range of from 5 to 20 μm . From 8 to 18 μm is preferred.

Similarly, the thickness of the exterior coating may
30 vary widely, but usually the thickness of the exterior coating is in the range of from 0.1 to 10 μm . Frequently the

- 22 -

thickness of the exterior coating is in the range of from 0.5 to 5 μm . From 0.7 to 3 μm is preferred.

The substrate may be any substrate at least one surface of which is capable of bearing the coating discussed above. In most instances the substrate is in the form of an individual sheet or in the form of a roll, web, strip, film, or foil of material capable of being cut into sheets. It may be an uncoated material or it may be the exposed coating of a material which has been previously coated with one or more coatings.

The substrate may be porous throughout, it may be nonporous throughout, or it may comprise both porous regions and nonporous regions.

Examples of porous substrates include paper, paperboard, wood, cloth, nonwoven fabric, felt, unglazed ceramic material, polymer membranes, porous foam, and microporous foam.

Examples of substrates which are substantially nonporous throughout include sheets or films of organic polymer such as poly(ethylene terephthalate), polyethylene, polypropylene, cellulose acetate, poly(vinyl chloride), and copolymers such as saran. The sheets or films may be metallized or unmetallized as desired. Additional examples include metal substrates including but not limited to metal foils such as aluminum foil and copper foil. Yet another example is a porous or microporous foam comprising thermoplastic organic polymer which foam has been compressed to such an extent that the resulting deformed material is substantially nonporous. Still another example is glass.

Base stocks which are normally porous such as for example paper, paperboard, wood, cloth, nonwoven fabric, felt, unglazed ceramic material, polymer membranes, porous foam, or

- 23 -

microporous foam may be coated or laminated to render one or more surfaces substantially nonporous and thereby provide substrates having at least one substantially nonporous surface.

5 The substrate may be substantially transparent, it may be substantially opaque, or it may be of intermediate transparency. For some applications such as ink jet printed overhead slides, the substrate must be sufficiently transparent to be useful for that application. For other
10 applications such as ink jet printed paper, transparency of the substrate is not so important.

 After the interior water-absorptive coating and the exterior intermediate coating have been formed on the surface of the substrate, they are exposed to actinic light, ionizing
15 radiation, or heat to provide the exterior coating with numerous crosslinks derived from ethylenically unsaturated groups present in the hydrophilic organic polymer of the applied exterior coating composition. This process is known as "curing". Some or substantially all of the ethylenically
20 unsaturated groups may be converted to crosslinks, as desired. The numbers of crosslinks present in the exterior coating should in any event be sufficient to increase the wet smear resistance of the inkjet printed printing medium as compared with the same exterior coating which has not been
25 exposed to actinic light, ionizing radiation, or heat in accordance with this invention.

 When the exterior intermediate coating is to be exposed to actinic light, photoinitiator, photosensitizer, or a mixture of photoinitiator and photosensitizer is usually
30 present. Usually the actinic light is ultraviolet light having a wavelength in the range of from about 185 to about 400 nanometers.

- 24 -

Photoinitiators are compounds which absorb photons and thereby obtain energy to form radical pairs, at least one of which is available to initiate addition polymerization of ethylenically unsaturated groups in the well-known manner.

5 Photosensitizers are compounds which are good absorbers of photons, but which are themselves poor photoinitiators. They absorb photons to produce excited molecules which then interact with a second compound to produce free radicals suitable for initiation of addition polymerization. The
10 second compound may be a monomer, a polymer or an added initiator. Examples of photoinitiators are benzoin, methyl benzoin ether, butyl benzoin ether, isobutyl benzoin ether, α,α -diethoxyacetophenone and α -chloroacetophenone. Examples of photosensitizers are benzil, 1-naphthaldehyde,
15 anthraquinone, benzophenone, 3-methoxybenzophenone, benzaldehyde, and anthrone.

The amount of photoinitiator, photosensitizer or mixture of photoinitiator and photosensitizer present in the exterior coating composition and the exterior intermediate
20 coating can vary widely. When any of these materials is present, the amount is usually in the range of from 0.001 to 10 percent by weight of the binder of the coating composition and the exterior intermediate coating. Most often, the amount is in the range of from 0.002 to 8 percent by weight of the
25 binder. An amount in the range of from 0.005 to 5 percent by weight of the binder is preferred. When the exterior intermediate coating is to be exposed to ionizing radiation, these materials are usually omitted from the exterior coating composition and hence from the exterior intermediate coating,
30 although their presence is permissible.

Any-suitable source which emits ultraviolet light, viz., electromagnetic radiation having a wavelength in the

- 25 -

range of from about 180 to about 400 nanometers, may be used in the practice-of this invention. Because such ultraviolet light possesses insufficient energy to produce ions in a medium composed of common elements such as air or water, it is considered to be nonionizing radiation. Suitable sources of ultraviolet light are mercury arcs, carbon arcs, low pressure mercury lamps, medium pressure mercury lamps, high pressure mercury lamps, swirlflow plasma arc, and ultraviolet light emitting diodes. Particularly preferred are ultraviolet light emitting lamps of the medium or high pressure mercury vapor type. Such lamps usually have fused quartz envelopes to withstand the heat and to transmit the ultraviolet radiation and are ordinarily in the form of long tubes having an electrode at both ends.

The times of exposure to actinic light and the intensity of the actinic light to which the polymerizable composition is exposed may vary greatly. Usually the exposure to actinic light is continued at least until many, and in some cases, most, of the photoinitiator and/or photosensitizer molecules have been activated.

The ionizing radiation employed in the invention is radiation possessing an energy at least sufficient to produce ions either directly or indirectly in a medium composed of common elements such as air or water, and includes ionizing particle radiation and ionizing electromagnetic radiation. Ionizing particle radiation designates the emission of electrons or accelerated nuclear particles such as protons, alpha particles, deuterons, beta particles, neutrons or their analogs. Charged particles can be accelerated using such devices as resonance chamber accelerators, DC potential gradient accelerators, betatrons, synchrotrons, cyclotrons, etc. Neutron radiation can be produced by bombarding a

- 26 -

selected light metal such as beryllium with positively charged particles of high energy. Ionizing particle radiation can also be obtained by the use of an atomic pile, radioactive isotopes, or other natural or synthetic radioactive materials. Ionizing electromagnetic radiation comprises high energy photons. Examples are X-rays, bremsstrahlung, and gamma rays.

X-rays may be produced when a metallic target such as tungsten, copper, or molybdenum is bombarded with electrons of suitable energy. This energy is conferred to the electrons by accelerators, usually, but not necessarily, of the linear type. Traveling wave linear accelerators, standing wave linear accelerators and DC potential gradient linear accelerators are ordinarily employed for this purpose.

Bremsstrahlung, also known as continuous X-rays, is produced by the deceleration of electrons. The continuum extends from a short-wave limit dependent upon the maximum energy of the electrons indefinitely toward the long wavelength end of the spectrum.

Gamma rays may be obtained by means of a nuclear reactor, such as a pile, by the use of natural or synthetic radioactive materials such as cobalt 60 or radium which emit gamma rays, or by absorption of a neutron in the (n,γ) reaction.

The ionizing radiation, whether particle radiation or electromagnetic radiation, ordinarily has an energy of at least about 10 electron volts. While there is no upper limit to the energy of ionizing radiation which can be used advantageously, the effects desired in the practice of this invention can be accomplished without resorting to the use of ionizing radiation having energies above about 20,000,000 electron volts.

- 27 -

Accelerated electrons is the preferred ionizing radiation for crosslinking coatings of the radiation curable coating composition. Bremsstrahlung generated by the deceleration) of the electrons is also present and probably contributes to crosslinking. Various types of linear electron accelerators are known, for example, the ARCO type traveling wave accelerator, model Mark I, operating at 3 to 10 million electron volts supplied by High Voltage Engineering Corporation, Burlington, Massachusetts., or other types of accelerators such as are described in U.S. Patent No. 2,763,609 and British Patent Specification No. 762,953 are satisfactory for the practice of this invention. Usually the electrons are accelerated to energies in the range of from about 10,000 electron volts to about 1,000,000 electron volts. Typically, the energy is in the range of from about 20,000 electron volts to about 500,000 electron volts. Preferably, the energy is in the range of from about 25,000 electron volts to about 200,000 electron volts.

The unit of dose of ionizing radiation is the "rad" which is equal to 100 ergs of energy absorbed from ionizing radiation per gram of material being irradiated. Dose is initially determined using an absolute method such as calorimetry or ionization dosimetry. These absolute methods are quite sophisticated and hence are not generally practical for routine determinations. Once a radiation field has been explored by an absolute method of dosimetry, it is possible to calibrate secondary radiation indicators in that field using relative dosimetry techniques. One simple method of relative dosimetry is based upon the bleaching of blue cellophane by ionizing radiation. The blue cellophane is exposed to a standard source for a known time and the transmittance of light having a wavelength of 655 nanometers is measured with a

- 28 -

spectrophotometer. The transmittance of unexposed cellophane is also measured and the percent change in transmittance due to exposure to ionizing radiation is calculated. From several such readings and calculations, a graph may be constructed
5 relating change in transmittance with dose. A blue cellophane manufactured by the E. I. du Pont de Nemours & Company has been used for this purpose. The calibrated blue cellophane may then be used to calibrate other sources of the same kind of radiation and other kinds of blue cellophane which may be
10 used in routine work. Avisco cellophane 195 CMS light blue manufactured by the American Viscose Division of FMC Corporation has been calibrated and used for routine dose determinations. In practice, the calibrated blue cellophane is exposed to the ionizing radiation before, after or
15 simultaneously with the coated substrate being irradiated. The dose received by the coating is considered to be the same as that received by the blue cellophane. This presumes that the absorption of energy by the coating is the same as that of the blue cellophane. Except for materials containing rather
20 large proportions of atoms of very high atomic weight, the absorption of ionizing radiation is nearly independent of the identity of the material. The presumption is therefore valid for the ordinary work of coatings manufacturing where very high degrees of accuracy of dose measurement are not needed.
25 As used throughout the specification and claims, dose is referenced to the bleaching of calibrated blue cellophane film irrespective of the identity of the coating composition being irradiated.

Coatings of the radiation curable coating
30 composition ordinarily receive a dose of ionizing radiation in the range of from about 0.01 megarad to about 20 megarads, although doses greater than 20 megarads may be used

- 29 -

satisfactorily. The dose, however, should not be so great that the chemical or physical properties of the coating are seriously impaired. Typically, the dose is in the range of from about 0.1 megarad to about 20 megarads. The preferred
5 dose is in the range of from about 1 megarad to about 10 megarads.

The free radical curing of ethylenically unsaturated groups of many, but not all, coatings containing such groups is significantly inhibited by oxygen when the coatings are
10 exposed to actinic light or ionizing radiation. In such instances the surface of the coating remains undercured. Often the oxygen inhibition is so severe that even massive exposures to very large amounts of actinic light or ionizing radiation will not cure the surface to the desired degree.
15 When the coating has sufficient thickness and when the coating is exposed to actinic light or ionizing radiation, oxygen inhibition can result in a surface layer of the coating having a significantly lesser degree of cure than the interior of the coating.

20 When oxygen inhibition does occur the effect can sometimes be reduced by the inclusion of materials which inhibit oxygen inhibition. Oxygen inhibition can always be reduced by sufficiently lowering the molecular oxygen concentration of the atmosphere in contact with the coating
25 during exposure.

Controlling oxygen inhibition can in some instances be used to vary the degree of curing in a manner that enhances wet smear resistance of the printing medium. Parameters which affect oxygen inhibition can often be used to vary wet smear
30 resistance. Included among these are the identities of the polymers, oligomers, and monomers of the coating composition, the concentration of molecular oxygen in the atmosphere in

- 30 -

which exposure to radiation takes place, and the intensity of the actinic light or ionizing radiation. In the case of actinic light, the identities and amounts of actinic light absorbers can sometimes be used. See United States Patent No. 5 4,170,663, the entire disclosure of which is incorporated herein by reference, for a discussion of general principles.

When the ethylenically unsaturated groups of the exterior intermediate coating are to be polymerized by heating the exterior intermediate coating to elevated temperatures, 10 thermal initiator is usually present.

The thermal initiators which may be used in the present invention may be widely varied, but in general they are thermally decomposable to produce radical pairs. One or both members of the radical pair are available to initiate 15 addition polymerization of ethylenically unsaturated groups in the well-known manner.

The preferred thermal initiators are peroxy initiators. Examples of suitable peroxy initiators include peroxydicarbonate esters such as di-n-propyl 20 peroxydicarbonate, diisopropyl peroxydicarbonate, di-n-butyl peroxydicarbonate, di-sec-butyl peroxydicarbonate, diisobutyl peroxydicarbonate, di(2-ethylhexyl) peroxydicarbonate, diacetyl peroxy dicarbonate, dicyclohexyl peroxydicarbonate, di(4-tert-butylcyclohexyl) peroxy dicarbonate, and isopropyl 25 sec-butyl peroxydicarbonate; diacetyl peroxides such as diacetyl peroxide, dibenzoyl peroxide, dilauroyl peroxide, and diisobutyryl peroxide; and peroxy esters such as tertiary-butyl perpivalate, tertiary-butyl peroctoate, and tertiary-butyl perneodecanoate.

30 Other examples of suitable peroxy initiators include monoperoxycarbonates such as tertiary-butylperoxy isopropyl carbonate and tertiary-amyl peroxyisopropyl carbonate.

- 31 -

Only one initiator or a plurality of thermal initiators may be used as desired.

The amount of thermal initiator present in the exterior coating composition and the exterior intermediate coating can vary widely. When thermal initiator is present, the amount is usually in the range of from 0.001 to 10 percent by weight of the binder of the coating composition and the exterior intermediate coating. Most often, the amount is in the range of from 0.01 to 8 percent by weight of the binder. An amount in the range of from 0.1 to 5 percent by weight of the binder is preferred.

Usually thermal polymerization is conducted at temperatures in the range of from 28°C to 150°C. Often the temperature is in the range of from 35°C to 140°C. In many instances the temperature is in the range of from 50°C to 130°C.

The times of exposure to elevated temperatures may vary greatly. Generally, heating is continued until most of the ethylenically unsaturated groups are polymerized.

The coatings may collectively be substantially transparent, substantially opaque, or of intermediate transparency. They may be substantially colorless, they may be highly colored, or they may be of an intermediate degree of color. Preferably the coatings are substantially transparent and substantially colorless. As used herein and in the claims, the coatings are collectively transparent if their luminous transmission in the visible region is at least 80 percent of the incident light. Often the luminous transmission of the coating is at least 85 percent of the incident light. Preferably the collective luminous transmission of the coatings is at least 90 percent. Also as used herein and in the claims, the coatings are collectively

- 32 -

colorless if the luminous transmission is substantially the same for all wavelengths in the visible region, viz., 400 to 800 nanometers.

The gloss of the exterior water-absorptive coating
5 of the printing medium may vary widely. Although lower glosses are acceptable for many purposes, it is preferred that the gloss be at least 20. As used herein gloss is determined according to TAPPI Standard T653 pm-90.

The exterior coating may optionally be printed upon
10 by applying liquid ink droplets to the exterior coating. This is most often accomplished by inkjet printing.

The liquid ink droplets may be applied to the exterior coating before second volatile aqueous liquid is removed from the exterior coating or after second volatile
15 aqueous liquid has been removed from the exterior coating.

The liquid ink droplets may be applied to the exterior coating before the substrate, the interior coating, and the exterior coating are exposed to actinic light, ionizing radiation, or heat to provide the exterior coating
20 with numerous crosslinks derived from ethylenically unsaturated groups present in the applied exterior coating composition. Alternatively the liquid ink droplets may be applied to the exterior coating after the substrate, the interior coating, and the exterior coating have been exposed
25 to actinic light, ionizing radiation, or heat to provide the exterior coating with numerous crosslinks derived from ethylenically unsaturated groups present in the applied exterior coating composition.

The invention is further described in conjunction
30 with the following examples which are to be considered illustrative rather than limiting, and in which all parts are

- 33 -

parts by weight and all percentages are percentages by weight unless otherwise specified.

EXAMPLE 1

5 The charges shown in Table 1 were used in the preparation of a cationic acrylic polymer aqueous dispersion.

TABLE 1

<u>Ingredients</u>	<u>Weight, kilograms</u>
	<u>Charge 1</u>
Methyl ethyl ketone	55.93
	<u>Charge 2</u>
Methyl ethyl ketone	28.67
Initiator ¹	10.16
	<u>Charge 3</u>
n-Butyl acrylate	30.44
Methyl methacrylate	87.32
2-(tert-Butylamino)ethyl methacrylate [CAS 3775-90-4]	40.64
Styrene	44.68
	<u>Charge 4</u>
Methyl ethyl ketone	2.27
	<u>Charge 5</u>
Methyl ethyl ketone	2.27
	<u>Charge 6</u>
Glacial acetic acid	9.89
Methyl ethyl ketone	2.27
	<u>Charge 7</u>
Deionized water	579.1
	<u>Charge 8</u>
Deionized water	11.1

¹ VAZO[®] 67 2,2'-Azobis(2-methylbutanenitrile) initiator,
E. I. du Pont de Nemours and Company, Wilmington, Delaware.

- 34 -

Charge 1 was heated in a reactor with agitation to reflux temperature (80°C). The addition of Charge 2 from a catalyst tank to the reactor was then begun. The addition of Charge 2 was made over a period of 305 minutes. Five minutes after beginning the addition of Charge 2, the addition of Charge 3 from a monomer tank was begun. The addition of Charge 3 was made over a period of 240 minutes. When the addition of Charge 3 was completed, Charge 4 was added to the monomer tank as a rinse and then the rinse liquid was added from the monomer tank to the reactor over a period of 10 minutes. Upon completion of the addition of Charge 2, Charge 5 was added to the catalyst tank as a rinse and then the rinse liquid was added from the catalyst tank to the reactor over a period of 10 minutes. The reaction mixture was then agitated at reflux for three hours while the temperature of the reaction mixture was in the range of from 83°C to 86°C. At the end of the three hour period, the reaction mixture was cooled to temperatures in the range of from 48°C to 52°C. Charge 6 was added over a period of 10 minutes and the reaction mixture was thereafter agitated for 15 minutes. Charge 7 was added to a thinning tank equipped for distillation and heated to temperatures in the range of from 48°C to 52°C. The reaction mixture was dropped from the reactor to the thinning tank as quickly as possible. Charge 8 was added to the reactor as a rinse and then the rinse liquid was also dropped to the thinning tank. The contents of the thinning tank were agitated for 30 minutes at temperatures in the range of from 48°C to 52°C. Over a thirty minute period the pressure was reduced to 71.3 kilopascals, absolute. The temperature was then increased and liquid was stripped off under vacuum until the solids content of the batch was about 30 percent by weight. The resulting product which was a

- 35 -

cationic acrylic polymer aqueous dispersion, was cooled to about 48°C, filtered, and then discharged into drums.

The charges shown in Table 2 were used in the preparation of a first quaternary cationic polymer aqueous composition.

TABLE 1

<u>Ingredients</u>	<u>Weight, kilograms</u>
<u>Charge 1</u>	
Deionized water	100.0
Aqueous isopropanol ¹	200.0
Initiator ²	5.0
<u>Charge 2</u>	
Methyl methacrylate	20.0
Styrene	20.0
n-Butyl acrylate	15.0
Aqueous quaternary monomer ³	56.3

¹ 70% isopropanol, 30% water, by weight.

² VAZO[®] 67 2,2'-Azobis(2-methylbutanenitrile) initiator, E. I. du Pont de Nemours and Company, Wilmington, Delaware.

³ 80% [2-(methacryloyloxy)ethyl]trimethyl ammonium methylsulfate, 20% water, by weight.

Charge 1 was heated to 75°C. Charge 2 was introduced to Charge 1 at 75°C over a period of 3 hours. The reaction mixture was then stirred for 5 hours at 80°C. The isopropanol was removed by stripping on a Rotovap at 60°C. Water was added to provide a first quaternary cationic polymer aqueous composition having a solids content of 25.5% by weight.

Disperal P2 pseudoboehmite powder (Condea, Germany) (140 grams) was gradually added to dilute nitric acid aqueous solution (860 grams, 0.25%) under stirring. The

- 36 -

mixture was stirred until a translucent pseudoboehmite dispersion was obtained.

To a plastic container, an aqueous solution of polyethylene oxide having a weight average molecular weight in the range of from 300,000 to 450, 000 (200 grams, 6%) was
5 added. While the solution was under stirring, a portion of the above cationic acrylic polymer aqueous dispersion (24.0 grams, 29.4%), a portion of the above quaternary cationic polymer aqueous composition (40.0 grams, 25.5%), a portion of
10 the above pseudoboehmite dispersion (60.0 grams, 14%) and Cymel 1172 urea/glyoxal adduct (Cytec Industries Inc., West Patterson, New Jersey) (3.3 grams, 50%) were added. After each addition the mixture was stirred until a homogeneous aqueous dispersion was obtained. The product was an interior
15 coating composition.

To another plastic container, an aqueous solution of polyethylene oxide having a weight average molecular weight in the range of from 300,000 to 450, 000 (280 grams, 6%) was added. While the solution was under stirring, a portion of
20 the above pseudoboehmite dispersion (72.0 grams, 14%), ChemCor 540C cationic polyethylene polyemulsion (ChemCor Inc., Chester, New York) (11.7 grams, 25%), Sartomer SR415 triacrylate-terminated ethoxylated trimethylolpropane (12.0 grams, 100%), and Cymel 1172 urea/glyoxal adduct
25 (3.3 grams, 50%) were added. After each addition the mixture was stirred until a homogeneous aqueous dispersion was obtained. At the end, Darocure 1173 hydroxymethylphenylpropanone photoinitiator (Ciba-Geigy Corp., Tarrytown, New York) (0.4 grams) was added, and the aqueous
30 dispersion was stirred for 10 minutes to produce an exterior coating composition.

- 37 -

A portion of the interior coating composition was drawn down on Glory Base photograde basestock paper (Felix Schoeller, Germany) using Meyer Rod #160. The wet coating was dried in an oven at 105°C for 3.5 minutes to form an interior
5 coating on the substrate. The thickness of the interior coating was about 15 μm . A portion of the exterior coating composition was coated on the interior coating by rod coating using as Meyer Rod #14. The wet coating was dried in the oven at 105°C for 3.5 minutes to produce an exterior coating. The
10 thickness of the exterior coating was in the range of from 1 to 2 μm .

The coated substrate was passed once, at a speed of 21.3 meters/min, in an air atmosphere, under two mercury vapor arc lamps which were emitting ultraviolet light. The lamps
15 were positioned 6 inches above the surface of the coated substrate as it passed under the lamps. The dose was 500 mJ/cm^2 . The product was a printing medium.

EXAMPLE 2

20 A printing medium was prepared as described in Example 1 except that exposure to ultraviolet light was conducted in a nitrogen atmosphere in which the oxygen content was maintained below 100 ppm.

EXAMPLE 3

25 The charges shown in Table 3 were used in the preparation of a second quaternary cationic polymer aqueous composition.

- 38 -

TABLE 3

	<u>Ingredients</u>	<u>Weight, kilograms</u>
5	<u>Charge 1</u>	
	Isopropanol	100.0
	<u>Charge 2</u>	
	Isopropanol	106.5
10	Initiator ¹	18.2
	<u>Charge 3</u>	
	Isopropanol	205.7
	Styrene	182.5
15	Aqueous quaternary monomer ²	243.3
	<u>Charge 4</u>	
	Deionized Water	790
20		
	¹ VAZO [®] 67 2,2'-Azobis(2-methylbutanenitrile) initiator, E. I. du Pont de Nemours and Company, Wilmington, Delaware.	
25	² 75% [2-(methacryloyloxy)ethyl]trimethyl ammonium chloride, 20% water, by weight.	

Charge 1 was heated in a reactor with agitation to reflux (77 C - 80°C). At a reflux, Charge 2 was added over a period of 3 hours. After Charge 2 had been added, the addition of Charge 3 was begun. Charge 3 was added over a period of 3 hours. Charge 4 was added to the catalyst tank and the monomer tank as a rinse and used for further additions of deionized water. Upon completion of the additions of Charge 2 and Charge 3, the reaction mixture was agitated at reflux for 4 hours. The reactor was then set for total distillation. About 300 grams of deionized water was added to the reactor, the jacket temperature was reduced, and vacuum was applied slowly. Vacuum distillation was begun. After collecting 491 grams of distillates, and additional 490 grams of deionized water was added and vacuum distillation was

- 39 -

continued. After most of the isopropanol had been removed, the percent solids was determined and the product was adjusted to 29.5 percent solids (as determined by weight difference of a sample before and after heating at 110°C for one hour. The product which was a second quaternary cationic polymer aqueous composition, was filtered through a 5 micrometer glass fiber filter.

To a plastic container, an aqueous solution of polyethylene oxide having a weight average molecular weight in the range of from 300,000 to 450, 000 (200 grams, 6%) was added. While the solution was under stirring, a portion of the above cationic acrylic polymer aqueous dispersion (48.5 grams, 29.4%), a portion of the second quaternary cationic polymer aqueous composition (7.6 grams, 29.5%), a portion of the above pseudoboehmite dispersion (50 grams, 14%) and Cymel 1172 urea/glyoxal adduct (5.3 grams, 50%) were added. After each addition the mixture was stirred until a homogeneous aqueous dispersion was obtained. The product was an interior coating composition.

To another plastic container, an aqueous solution of polyethylene oxide having a weight average molecular weight in the range of from 300,000 to 450, 000 (200 grams, 6%) was added. While the solution was under stirring, a portion of the above alumina dispersion (71.5 grams, 14%), a portion of the above cationic acrylic polymer aqueous dispersion (48.5 grams, 29.4%), ChemCor 540C cationic polyethylene polyemulsion (16.0 grams, 25%), Sartomer SR415 triacrylate-terminated ethoxylated trimethylolpropane (12.0 grams, 100%), Cymel 1172 urea/glyoxal adduct (3.3 grams, 50%) were added. After each addition, the mixture was stirred until a homogeneous aqueous dispersion was obtained. At the end, Darocure 1173 hydroxymethylphenylpropanone photoinitiator (0.4 grams) was

- 40 -

added, and the solution was stirred for 10 minutes to produce an exterior coating composition.

A portion of the interior coating composition was drawn down on Glory Base paper using a Meyer Rod #160. The wet coating was dried in an oven at 105°C for 3.5 minutes to form an interior coating on the substrate. The thickness of the interior coating was about 15 μm . A portion of the exterior coating composition was drawn down on the interior coating using a Meyer Rod #14. The wet coating was dried in the oven at 105°C for 3.5 minutes to produce an exterior coating. The thickness of the exterior coating was in the range of from 1 to 2 μm .

The coated substrate was passed once, at a speed of 21.3 meters/min, in an air atmosphere, under two mercury vapor arc lamps which were emitting ultraviolet light. The lamps were positioned 6 inches above the surface of the coated substrate as it passed under the lamps. The dose was 500 mJ/cm^2 . The product was a printing medium.

20

EXAMPLE 4

To a plastic container, an aqueous solution of polyethylene oxide having a weight average molecular weight in the range of from 300,000 to 450,000 (280 grams, 6%) was added. While the solution was under stirring, a portion of the above alumina dispersion (72.0 grams, 14%), ChemCor 540C cationic polyethylene polyemulsion (11.7 grams, 25%), Sartomer SR415 triacrylate-terminated ethoxylated trimethylolpropane (12.0 grams, 100%), and Cymel 1172 urea/glyoxal adduct (3.3 grams, 50%) were added. After each addition the mixture was stirred until a homogeneous aqueous dispersion was obtained. The resulting product was an exterior coating composition.

30

- 41 -

A portion of the interior coating composition of Example 1 was drawn down on Glory Base paper using a Meyer Rod #160. The wet coating was dried in an oven at 105°C for 3.5 minutes to form an interior coating on the substrate. The thickness of the interior coating was about 15 μm . A portion of the exterior coating composition of this Example 4 was drawn down on the interior coating using a Meyer Rod #14. The wet coating was dried in the oven at 105°C for 3.5 minutes to produce an exterior coating. The thickness of the exterior coating was in the range of from 1 to 2 μm .

The coated substrate was passed once, at a speed of 4.18 meters/min, in an air atmosphere, through an electron beam processing system, 300 KeV-15mA, self shielded unit, manufactured by High Voltage Engineering, Inc. The operating conditions were 210 KeV and 5 mA. A dosimeter was used to measure the exposure to radiation. The dose received by the coated substrate was 5 Megarads. The resulting product was a printing medium.

20 Example 5

To a plastic container, an aqueous solution of polyethylene oxide having a weight average molecular weight in the range of from 300,000 to 450,000 (200 grams, 6%) was added. While the solution was under stirring, a portion of the above alumina dispersion (60 grams, 14%), a portion of the above cationic acrylic polymer aqueous dispersion (28.0 grams, 29.4%), a portion of the first quaternary cationic polymer aqueous composition (25.4 grams, 25.5%), ChemCor 540C cationic polyethylene polyemulsion (16.0 grams, 25%), Sartomer SR415 triacrylate-terminated ethoxylated trimethylolpropane (10.0 grams, 100%), Cymel172 durea/glyoxal adduct (3.6 grams, 50%) were added. After each addition, the mixture was stirred

- 42 -

until a homogeneous aqueous dispersion was obtained. The resulting product was an exterior coating composition.

A portion of the interior coating composition of Example 3 was drawn down on Glory Base paper using a Meyer Rod #160. The wet coating was dried in an oven at 105°C for 3.5 minutes to form an interior coating on the substrate. The thickness of the interior coating was about 15 μm . A portion of the exterior coating composition of this Example 5 was drawn down on the interior coating by rod coating using a Meyer Rod #14. The wet coating was dried in the oven at 105°C for 3.5 minutes to produce an exterior coating. The thickness of the exterior coating was in the range of from 1 to 2 μm .

The coated substrate was passed once, at a speed of 4.18 meters/min, in an air atmosphere, through the electron beam processing system described in Example 4. The operating conditions were 210 KeV and 5 mA. A dosimeter was used to measure the exposure to radiation. The dose received by the coated substrate was 5 Megarads. The resulting product was a printing medium.

Although the present invention has been described with reference to specific details of certain embodiments thereof, it is not intended that such details should be regarded as limitations upon the scope of the invention except insofar as they are included in the accompanying claims.

CLAIMS:

1. A process comprising:
 - (a) providing a substrate having at least one surface;
 - 5 (b) forming an interior coating on the surface by applying to the surface an interior coating composition comprising:
 - (1) first volatile aqueous liquid; and
 - (2) water-solubilized or water-dispersed film-
10 forming hydrophilic organic polymer which is substantially free from ethylenically unsaturated groups or which contains only few ethylenically unsaturated groups;
 - (c) forming an exterior coating on the interior
15 coating by applying to the interior coating an exterior coating composition comprising:
 - (1) second volatile aqueous liquid; and
 - (2) a film-forming member selected from the group consisting of:
20 (A) water-solubilized film-forming hydrophilic organic polymer which contains numerous ethylenically unsaturated groups,
(B) water-dispersed film-forming
25 hydrophilic organic polymer which contains numerous ethylenically unsaturated groups,
(C) water-solubilized film-forming
30 hydrophilic organic oligomer which contains numerous ethylenically unsaturated groups,

- 44 -

- (D) water-dispersed film-forming hydrophilic organic oligomer which contains numerous ethylenically unsaturated groups,
- 5 (E) water-solubilized film-forming hydrophilic organic monomer which contains numerous ethylenically unsaturated groups,
- (F) water-dispersed film-forming hydrophilic organic monomer which contains numerous ethylenically unsaturated groups, and
- 10 (G) a mixture of two or more thereof; and

- 15 (d) exposing the substrate, the interior coating, and the exterior coating to actinic light, ionizing radiation, or heat to provide the exterior coating with numerous crosslinks derived from ethylenically unsaturated groups present in the applied exterior coating composition;
- 20

wherein:

- (e) the interior coating composition, the exterior coating composition, or each of the interior coating composition and the exterior coating composition further comprises discrete particles which are not film-forming and which have a number average particle size in the range of from 1 to 500 nanometers;
- 25
- (f) first volatile aqueous liquid is removed from the interior coating to produce an interior
- 30

- 45 -

water-absorptive coating on the surface of the substrate; and

(g) second volatile aqueous liquid is removed from the exterior coating to produce an exterior water-absorptive coating on the surface of the interior water-absorptive coating.

5
10
2. The process of claim 1 wherein the interior coating composition comprises discrete particles which are not film-forming and which have a number average particle size in the range of from 1 to 500 nanometers.

15
3. The process of claim 1 wherein the exterior coating composition comprises discrete particles which are not film-forming and which have a number average particle size in the range of from 1 to 500 nanometers.

20
4. The process of claim 1 wherein each of the interior coating composition and the exterior coating composition comprises discrete particles which are not film-forming and which have a number average particle size in the range of from 1 to 500 nanometers.

25
5. The process of claim 1 wherein first volatile aqueous liquid is removed from the interior coating before application of the exterior coating composition to the interior coating.

- 46 -

6. The process of claim 1 wherein first volatile aqueous liquid is removed from the interior coating after application of the exterior coating composition to the interior coating.

5

7. The process of claim 1 wherein second volatile aqueous liquid is removed from the exterior coating before exposing the substrate, the interior coating, and the exterior coating to actinic light, ionizing radiation, or heat to provide the exterior coating with numerous crosslinks derived from ethylenically unsaturated groups present in the film-forming member of the applied exterior coating composition.

8. The process of claim 1 wherein first volatile aqueous liquid is removed from the interior coating and second volatile aqueous liquid is removed from the exterior coating before exposing the substrate, the interior coating, and the exterior coating to actinic light, ionizing radiation, or heat to provide the exterior coating with numerous crosslinks derived from ethylenically unsaturated groups present in the film-forming member of the applied exterior coating composition.

9. The process of claim 1 wherein second volatile aqueous liquid is removed from the exterior coating after exposing the substrate, the interior coating, and the exterior coating to actinic light, ionizing radiation, or heat to provide the exterior coating with numerous crosslinks derived from ethylenically unsaturated groups present in the film-forming member of the applied exterior coating composition.

30

- 47 -

10 10. The process of claim 1 wherein first volatile aqueous liquid is removed from the interior coating and second volatile aqueous liquid is removed from the exterior coating after exposing the substrate, the interior coating, and the exterior coating to actinic light, ionizing radiation, or heat to provide the exterior coating with numerous crosslinks derived from ethylenically unsaturated groups present in the film-forming member of the applied exterior coating composition.

10

 11. The process of claim 1 which further comprises printing on the exterior coating by applying liquid ink droplets to the exterior coating.

15

 12. The process of claim 11 wherein the liquid ink droplets are applied to the exterior coating before second volatile aqueous liquid is removed from the exterior coating.

 13. The process of claim 11 wherein the liquid ink droplets are applied to the exterior coating after second volatile aqueous liquid has been removed from the exterior coating.

 14. The process of claim 11 wherein the liquid ink droplets are applied to the exterior coating before the substrate, the interior coating, and the exterior coating are exposed to actinic light, ionizing radiation, or heat to provide the exterior coating with numerous crosslinks derived from ethylenically unsaturated groups present in the applied exterior coating composition.

30

- 48 -

15 15. The process of claim 11 wherein the liquid ink droplets are applied to the exterior coating after the substrate, the interior coating, and the exterior coating have been exposed to actinic light, ionizing radiation, or heat to provide the exterior coating with numerous crosslinks derived from ethylenically unsaturated groups present in the applied exterior coating composition.

10 16. The process of claim 1 wherein the discrete particles are discrete particles of alumina, silica, or titania.

15 17. The process of claim 1 wherein the discrete particles are discrete particles of alumina monohydroxide.

 18. The process of claim 1 wherein the discrete particles are discrete particles of pseudoboehmite.

20 19. The process of claim 1 wherein discrete nonfilm-forming particles constitute from 1 to 80 percent by weight of the interior coating composition, the exterior coating composition, or each of the interior coating composition and the exterior coating composition.

25 20. The process of claim 1 wherein the water-solublized or water-dispersed film-forming hydrophilic organic polymer of the interior coating composition comprises poly(ethylene oxide), poly(vinyl alcohol), poly(vinyl pyrrolidone), water-soluble cellulosic organic polymer, or a
30 mixture of two or more thereof.

- 49 -

21. The process of claim 20 wherein the film-forming hydrophilic organic polymer of the interior coating composition comprises water-soluble poly(ethylene oxide) having a weight average molecular weight in the range of from
5 100,000 to 3,000,000.

22. The process of claim 1 wherein the water-solublized or water-dispersed film-forming hydrophilic organic polymer of the exterior coating composition comprises
10 poly(ethylene oxide), poly(vinyl alcohol), poly(vinyl pyrrolidone), water-soluble cellulosic organic polymer, or a mixture of two or more thereof.

23. The process of claim 22 wherein the film-forming hydrophilic organic polymer of the exterior coating composition comprises water-soluble poly(ethylene oxide) having a weight average molecular weight in the range of from
15 100,000 to 3,000,000.

24. The process of claim 1 wherein the ratio of the number of ethylenically unsaturated groups per gram of the film-forming organic polymer present in the interior coating composition to the number of ethylenically unsaturated groups per gram of the film-forming member present in the exterior
20 coating composition is less than 0.9:1.
25

- 50 -

25. The process of claim 1 wherein the film-forming organic polymer of the interior coating composition independently constitutes at least 1 percent by weight of the of the interior coating composition and the film-forming
5 member of the exterior coating composition constitutes at least 1 percent by weight of the of the exterior coating composition.

26. The process of claim 1 wherein the discrete
10 nonfilm-forming particles having a number average particle size of from 1 to 500 nanometers constitute at least 0.1 percent by weight of the of the interior coating composition, the exterior coating composition, or each of the interior coating composition and the exterior coating
15 composition.

27. The process of claim 1 wherein the substrate, the interior coating, and the exterior coating are exposed to ultraviolet light to provide the exterior coating with
20 numerous crosslinks derived from ethylenically unsaturated groups present in the applied exterior coating composition.

28. The product produced by the process of claim 1.

25

29. The product produced by the process of claim 2.

30. The product produced by the process of claim 3.

30

- 51 -

31. The product produced by the process of
claim 4.
- 5 32. The product produced by the process of
claim 11.
33. The product produced by the process of
claim 16.
- 10 34. The product produced by the process of
claim 17.
35. The product produced by the process of
claim 18.
- 15 36. The product produced by the process of
claim 19.
37. The product produced by the process of
20 claim 20.
38. The product produced by the process of
claim 21.
- 25 39. The product produced by the process of
claim 22.
40. The product produced by the process of
claim 23.
- 30 41. The product produced by the process of
claim 24.

42. An article comprising:

- (a) a substrate having at least one surface;
- (b) an interior water-absorptive coating on the
5 surface wherein the interior water-absorptive
coating comprises hydrophilic organic polymer
which is substantially free from crosslinks
derived from ethylenic unsaturation or which
contains few crosslinks derived from ethylenic
10 unsaturation; and
- (c) an exterior water-absorptive coating on the
interior water-absorptive coating wherein the
exterior water-absorptive coating comprises
hydrophilic organic polymer which contains
15 numerous crosslinks derived from ethylenic
unsaturation;

wherein:

- (d) the interior coating, the exterior coating ,
or each of the interior coating and the
20 exterior coating further comprises discrete
particles having a number average particle
size in the range of from 1 to 500 nanometers.

43 The article of claim 42 wherein the thickness
25 of the interior coating is in the range of from 1 to 30 μm and
the thickness of the exterior coating is in the range of from
0.1 to 10 μm .

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/22209

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B41M5/00 B41M7/00 C08J7/04 C09D171/02 C09D133/14

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B41M C08J C09D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	GB 2 151 945 A (MITSUBISHI YUKA FINE CHEM;SANYO KOKUSAKU PULP CO) 31 July 1985 see claims 1,13 ---	1,28,42
A	WO 97 22476 A (PPG INDUSTRIES INC) 26 June 1997 see claims 1,29 ---	1,28,42
A	PATENT ABSTRACTS OF JAPAN vol. 097, no. 011, 28 November 1997 & JP 09 174998 A (OJI PAPER CO LTD), 8 July 1997 see abstract --- -/--	1,28,42

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

° Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

11 January 1999

Date of mailing of the international search report

19/01/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Markham, R

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/22209

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	PATENT ABSTRACTS OF JAPAN vol. 096, no. 012, 26 December 1996 & JP 08 207423 A (NEW OJI PAPER CO LTD), 13 August 1996 see abstract <p style="text-align: center;">-----</p>	1, 28, 42

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/22209

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB 2151945 A	31-07-1985	JP 1913875 C	23-03-1995
		JP 6030950 B	27-04-1994
		JP 60143991 A	30-07-1985
		DE 3443565 A	11-07-1985
		US 4564560 A	14-01-1986

WO 9722476 A	26-06-1997	AU 1409397 A	14-07-1997
		EP 0866749 A	30-09-1998
