

(12) STANDARD PATENT
(19) AUSTRALIAN PATENT OFFICE

(11) Application No. **AU 2006229894 B2**

- (54) Title
Modification of copper/iron selectivity in oxime-based copper solvent extraction systems
- (51) International Patent Classification(s)
C22B 15/00 (2006.01) **C22B 3/30** (2006.01)
- (21) Application No: **2006229894** (22) Date of Filing: **2006.03.23**
- (87) WIPO No: **WO06/104816**
- (30) Priority Data
- (31) Number (32) Date (33) Country
60/666,030 **2005.03.29** **US**
- (43) Publication Date: **2006.10.05**
(44) Accepted Journal Date: **2010.08.19**
- (71) Applicant(s)
Cytec Technology Corp.
- (72) Inventor(s)
Maes, Charles J.;Tetlow, Peter Eric;Tinkler, Owen Stewart;Cramer, Keith Alan;Campbell, John
- (74) Agent / Attorney
Spruson & Ferguson, Level 35 St Martins Tower 31 Market Street, Sydney, NSW, 2000
- (56) Related Art
US 5470552 A
JP 2004-307983 A
JP 08-092665 A
WO 2004/028964 A
US 4507268 A
JP 06-264156 A

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
5 October 2006 (05.10.2006)

PCT

(10) International Publication Number
WO 2006/104816 A1

- (51) International Patent Classification:
C22B 15/00 (2006.01) *C22B 3/30* (2006.01)
- (21) International Application Number:
PCT/US2006/010502
- (22) International Filing Date: 23 March 2006 (23.03.2006)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/666,030 29 March 2005 (29.03.2005) US
- (71) Applicant (for all designated States except US): **CYTEC TECHNOLOGY CORP.** [US/US]; 300 Delaware Avenue, Wilmington, Delaware 19801 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **TINKLER, Owen, Stewart** [GB/US]; 2103 E. Sesame Street, Tempe, Arizona 85283 (US). **CRAMER, Keith, Alan** [US/US]; 41 Fieldstone Drive, Whippany, New Jersey 07981 (US). **TETLOW, Peter, Eric** [GB/US]; 1118 W. Monte Cristo Avenue, Phoenix, Arizona 85023 (US). **CAMPBELL, John** [GB/GB]; 13 Midge Hall Drive, Rochdale OL114AX (GB). **MAES, Charles, J.** [US/US]; 2034 E. Cathedral Rock Drive, Phoenix, Arizona 85048 (US).
- (74) Agents: **WASSERMAN, Fran, S.** et al.; CYTEC INDUSTRIES INC., 1937 West Main Street, P.O. Box 60, Stamford, Connecticut 06904-0060 (US).

- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 2006/104816 A1

(54) Title: MODIFICATION OF COPPER/IRON SELECTIVITY IN OXIME-BASED COPPER SOLVENT EXTRACTION SYSTEMS

(57) Abstract: A solvent extraction composition for the recovery of metals, particularly copper and iron, from leach solutions, comprises one or more orthohydroxyaryllaldoximes and/or one or more orthohydroxyarylketoimes, and one or more selectivity modifiers consisting of phosphinic and/or phosphonic acids, and salts and esters thereof and optionally one or more equilibrium modifiers is provided. The solvent extractant formulation enables to achieve controlled respectively desired metal transfer ratios.

MODIFICATION OF COPPER/IRON SELECTIVITY IN OXIME-BASED COPPER SOLVENT EXTRACTION SYSTEMS

Description

The present invention concerns a solvent extraction composition, a solvent
5 extraction process and especially a process for the extraction of metals, particularly
copper and iron, from aqueous solutions, especially solutions obtained by leaching ores.

It is known to extract metals, especially copper and to a much lesser degree iron,
from aqueous solutions containing the metals in the form of, for example, salts, by
contacting the aqueous solution with a solution of a solvent extractant in a water
10 immiscible organic solvent and then separating the solvent phase loaded with the metals,
i.e. containing at least a part of the metals in the form of a complex. The metals can then
be recovered by stripping with a solution of lower pH (the electrolyte) followed for
example, by electrowinning. Most commonly, the aqueous metal-containing solutions for
extraction are the result of the acid leaching of ores.

15 References in this technical field included JP-A-06 264 156; JP-A-08 092665; JP-
A-2004 307983; WO-A-2004/028964; WO-A-2004/094676; US-A-5 470 552; and WO-
A-2006/032097.

Solvent extractants which have found favour in recent years particularly for the
recovery of copper from aqueous solutions include oxime reagents, especially o-
20 hydroxyaryldoximes and o-hydroxyarylketoimes. The oxime reagents exhibit a high
degree of selectivity of copper over iron which is commonly expressed as the transfer
ratio. The transfer ratio is the ratio of the loaded organic copper concentration minus the
stripped organic copper concentration divided by the loaded organic iron concentration
minus the stripped organic iron concentration. Although a high transfer ratio is usually
25 desired, the presence of some iron in the electrolyte can also have benefits as described in
for example US patent application 2005/0023151. In some cases iron is desired as a
counter ion to maintain a certain EMF value in the electrolyte. The selectivity of copper
over iron is a function of the metal extractant, the metal and acid concentrations in the
leach solution and electrolyte, and the operating conditions in the solvent extraction plant.
30 In many instances using the present copper solvent extractant the selectivity of copper
over iron is such that insufficient iron is transferred to the electrolyte via the organic
phase to maintain the concentration range required. In such cases iron sulphate is added to
the electrolyte to achieve the desired concentration.

Using the solvent extraction process it is common for other impurities to be transferred to the electrolyte by a physical means. Impurities transferred to the strip solution will eventually build up in the circuit and have a negative impact on the electrowinning step. For that reason, operations often bleed a portion of the electrolyte to control the build up of impurities. In those cases, the electrolyte must be replaced with fresh water, acid, and iron (usually as ferrous sulphate). In some cases the amount of iron which must be added to make up for that which is lost in the bleed can be excessive. The addition of iron can negatively effect the economics of an operation. For these reasons it would be highly desirable to have a solvent extractant formulation which would allow an operation to achieve a desired transfer ratio - without losing the well know benefits of the hydroxyl oxime formulations commonly used today.

Although there are many chelating reagents which have a higher affinity for iron than the hydroxy oximes, it has surprisingly been found that the addition of small quantities of a select few iron chelating reagents (hereafter referred to as selectivity modifiers) to oxime reagents has a profound effect on the copper over iron selectivity characteristics of the resulting extractant composition. This effect on the resulting copper iron transfer ration is significantly greater than the effect of the sum of the two products when used independently.


According to a first aspect of the present invention, there is provided a solvent extraction composition comprising one or more orthohydroxyaryldoximes and/or one or more orthohydroxyarylketoimes, and one or more selectivity modifiers consisting of phosphinic and/or phosphonic acids, and salts and esters thereof, and one or more equilibrium modifiers selected from alkylphenols, alcohols, esters, ethers and polyethers, carbonates, ketones, nitriles, amides, carbamates, sulphoxides, or salts of amines and quaternary ammonium compounds, wherein the selectivity modifier is present in a molar ratio of the o-hydroxy oxime from 0.001 to 0.05.

According to a second aspect of the present invention, there is provided a process for the extraction of a metal from solution in which an acidic solution containing a dissolved metal is contacted with a solvent extraction composition, whereby at least a fraction of the metal is extracted into the organic solution, characterised in that the solvent extraction composition comprises a water immiscible organic solvent, one or more orthohydroxyaryldoximes and/or one or more orthohydroxyarylketoimes, and one or more selectivity modifiers selected from phosphinic and/or phosphonic acids, and salts and esters thereof and one or more equilibrium modifiers selected from alkylphenols, alcohols, esters, ethers and polyethers, carbonates, ketones, nitriles, amides, carbamates,

sulphoxides, or salts or amines and quaternary ammonium compounds, wherein the selectivity modifier is present in a molar ratio of the o-hydroxyoxime from 0.001 to 0.05.

Compositions according to the present invention may facilitate Increased iron transfer in solvent extraction circuits. Higher iron transfer can be translated into a decrease in the use of iron sulphate addition to the electrolyte to maintain a target electrolyte iron concentration. Composition according to the present invention may find particular use with processes which require electrolyte iron concentrations significantly above the conventional range.

The orthohydroxyarylketoimine compounds employed in the present invention are substantially water insoluble and preferably have the formula:




Formula (1)

wherein

R¹ is an optionally substituted hydrocarbyl group

R² is an optionally substituted ortho-hydroxyaryl group,
and salts thereof.

The orthohydroxyarylaldoxime compounds employed in the present invention are substantially water insoluble and preferably have the formula:



Formula (2)

wherein

R³ is an optionally substituted ortho-hydroxyaryl group,
and salts thereof.

Whilst the invention is described herein with reference to compounds of Formula (1) and (2), it is understood that it relates to said compound in any possible tautomeric forms, and also the complexes formed between orthohydroxyarylaldoximes or orthohydroxyarylketoimines and metals, particularly copper.

Optionally substituted hydrocarbyl groups which may be represented by R¹ preferably comprise optionally substituted alkyl and aryl groups including combinations of these, such as optionally substituted aralkyl and alkaryl groups.

Examples of optionally substituted alkyl groups which may be represented by R¹ include groups in which the alkyl moieties can contain from 1 to 20, especially from 1 to 4, carbon atoms. A preferred orthohydroxyarylketoimine is one in which R¹ is alkyl,

preferably containing up to 20, and especially up to 10, and more preferably up to 3 saturated aliphatic carbon atoms, and most preferably R^1 is a methyl group.

Examples of optionally substituted aryl groups which may be represented by R^1 include optionally substituted phenyl groups. When R^1 is an aryl group, it is preferably an unsubstituted phenyl group.

The orthohydroxyarylaloximes and orthohydroxyarylketoimes are often present in a total amount of up to 70% by weight of the composition, commonly no more than 60%, and usually no more than 50 % w/w. Often, the total amount of orthohydroxyarylaloxime and orthohydroxyarylketoime in use comprises at least 1% by weight, commonly at least 2.5% by weight and usually at least 5% by weight of composition, and preferably comprises from 7.5 to 20%, such as about 10%, by weight of the composition.

The criteria for selectivity modifier selection is stringent as the chemistry used must have no detrimental effect on the copper solvent extraction process. More specifically, the selectivity modifier must not interfere with copper transfer; it must be selective over other metals likely to be present in significant concentration in the leach solution; it must not have a detrimental affect on kinetic performance; it must not have a detrimental affect on stability of the extractant, and it must not be detrimental to the physical performance of the organic phase. The selectivity modifiers employed in the present invention are substantially water insoluble phosphinic and phosphonic acids, or salts or esters therefore. Preferred selectivity modifiers are selected from the group of phosphinic acids, or salts or esters thereof of the formula $R_4R_5P(O)OR_6$ where R_4 is H, C1 - C20 alkyl, aryl or arylalkyl group R_5 is H, C1 - C20 alkyl, aryl or arylalkyl group, and R_6 is H, a metal cation or NR_7 where R_7 is H, a C1 - C20 alkyl, aryl or arylalkyl group, or phosphonic acids or salts or esters thereof of the formula $R_8R_9OP(O)OR_{10}$ where R_8 is H, C1 - C20 alkyl, aryl or arylalkyl group, R_9 is H, C1 - C20 alkyl, aryl or arylalkyl group, and R_{10} is H, a metal cation, or NR_7 where R_7 is H, C1 - C20 alkyl, aryl or arylalkyl group. Examples of suitable phosphinic acids include bis(2,4,4-trimethyl)phosphinic acid and bis(2-ethylhexyl)phosphinic acid or their salts. Examples of suitable phosphonic acids include bis(2-ethylhexyl)phosphonic acid and phenylphosphonic acid or their salts. Examples of suitable phosphonic acids esters include 2-ethylhexylphosphonic acid, mono-2-ethylhexyl ester. The selectivity modifier preferably is present in a molar ratio of the o-hydroxyoxime: selectivity modifier from about 0.001 to 0.05.

Equilibrium modifiers employed in the present invention are substantially water insoluble. Equilibrium modifiers are selected from one or more of alkylphenols, alcohols,

esters, ethers and polyethers, carbonates, ketones, nitriles, amides, carbamates, sulphoxides, and salts of amines and quaternary ammonium compounds.

Organic solvents which may be present in the composition include any mobile organic solvent, or mixture of solvents, which is immiscible with water and is inert under the extraction conditions to the other materials present. Preferably the organic solvent has a low aromatic hydrocarbon content.

Preferred organic solvents are hydrocarbon solvents which include aliphatic, alicyclic and aromatic hydrocarbons and mixtures thereof as well as chlorinated hydrocarbons such as trichloroethylene, perchloroethylene, trichloroethane and chloroform.

Highly preferred organic solvents having a low aromatics content include solvents and solvent mixtures where the amount of aromatic hydrocarbons present in the organic solvent is less than 30%, usually around 23% or less, often less than 5%, and frequently less than 1%.

Examples of suitable hydrocarbon solvents include ESCAID 110, ESCAID 115, ESCAID 120, ESCAID 200, and ESCAID 300 commercially available from Exxon (ESCAID is a trade mark), SHELLSOL D70 and D80 300 commercially available from Shell (SHELLSOL is a trade mark), and CONOCO 170 commercially available from Conoco (CONOCO is a trade mark). Suitable solvents are hydrocarbon solvents include high flash point solvents and solvents with a high aromatic content such as SOLVESSO 150 commercially available from Exxon (SOLVESSO is a trade mark).

More preferred are solvents with a low aromatic content. Certain suitable solvents with a low aromatic content, have aromatic contents of <1% w/w, for example, hydrocarbon solvents such as ESCAID 110 commercially available from Exxon (ESCAID is a trade mark), and ORFOM SX 10 and ORFOM SX11 commercially available from Phillips Petroleum (ORFOM is a trade mark). Especially preferred, however on grounds of low toxicity and wide availability, are hydrocarbon solvents of relatively low aromatic content such as kerosene, for example ESCAID 100 which is a petroleum distillate with a total aromatic content of 23% commercially available from Exxon (ESCAID is a trade mark), or ORFOM SX7, commercially available from Phillips Petroleum (ORFOM is a trade mark).

In many embodiments, the composition comprises at least 30%, often at least 45% by weight, preferably from 50 to 95% w/w of water-immiscible hydrocarbon solvent. Advantageously, it may be preferred to make and supply the composition in the form of a concentrate. The concentrate may then be diluted by the addition of organic solvents as

2006229894 21 Oct 2009

4b

described herein above to produce compositions in the ranges as described herein above. Where the concentrate contains a solvent, it is preferred that the same solvent is used to dilute the concentrate to the "in use" concentration range. In many embodiments, the

concentrate composition comprises up to 30%, often up to 20% by weight, preferably up to 10% w/w of water-immiscible hydrocarbon solvent. Often the concentrate composition comprises greater than 5% w/w of water-immiscible hydrocarbon solvent. In certain high strength concentrates it may be necessary to employ a higher than normal aromatic hydrocarbon content. In such cases where a high aromatic hydrocarbon containing solvent is used in the concentrate, solvent of very low aromatic hydrocarbon content may be used to dilute the concentrate to the "in use" concentration range.

Examples of suitable solvent extraction compositions are those which comprise one of the following:

1) Blends of 5-(C₈ to C₁₄ alkyl)-2-hydroxybenzaldoxime and 5-(C₈ to C₁₄ alkyl)-2-hydroxyacetophenone oxime in a weight ratio of from about 90:10 to about 50:50 aldoxime to ketoxime, and/or optionally one or more modifiers selected from 2,2,4-trimethyl-1,3-pentanediol mono-isobutyrate, 2,2,4-trimethyl-1,3-pentanediol mono-benzoate, 2,2,4-trimethyl-1,3-pentanediol di-isobutyrate, 2,2,4-trimethyl-1,3-pentanediol di-benzoate, butyl adipate, pentyl adipate, hexyl adipate, isobutyl heptyl ketone, nonanone, diundecyl ketone, 5,8-diethyldodecane-6,7-dione, tridecanol, tetraethyleglycol di-2-ethylhexanoate, and nonyl phenol, and a selectivity modifier selected from bis(2,4,4-trimethylpentyl)phosphinic acid or 2-ethylhexylphosphonic acid, mono-2-ethylhexyl ester, present as a molar ratio of the o-hydroxyoxime : selectivity modifier from about 0.001 to 0.05.

2) Blends of 5-(C₈ to C₁₄ alkyl)-2-hydroxybenzaldoxime or 5-(C₈ to C₁₄ alkyl)-2-hydroxyacetophenone oxime, optionally one or more modifiers selected from 2,2,4-trimethyl-1,3-pentanediol mono-isobutyrate, 2,2,4-trimethyl-1,3-pentanediol mono-benzoate, 2,2,4-trimethyl-1,3-pentanediol di-isobutyrate, 2,2,4-trimethyl-1,3-pentanediol di-benzoate, butyl adipate, pentyl adipate, hexyl adipate, isobutyl heptyl ketone, nonanone, diundecyl ketone, 5,8-diethyldodecane-6,7-dione, tridecanol, and nonyl phenol, and a selectivity modifier selected from bis(2,4,4-trimethylpentyl)phosphinic acid or 2-ethylhexylphosphonic acid, mono-2-ethylhexyl ester, present as a molar ratio of the o-hydroxyoxime : selectivity modifier from about 0.001 to 0.05.

According to a second aspect of the present invention, there is provided a process for the extraction of a metal from solution in which an acidic solution containing a dissolved metal is contacted with a solvent extraction composition, whereby at least a fraction of the metal is extracted into the organic solution, characterised in that the solvent extraction composition comprises a water immiscible organic solvent, one or more orthohydroxyarylaloximes and one or more orthohydroxyarylketoimes, and a selectivity modifier present in a molar ratio of the o-hydroxyoxime from about 0.001 to 0.05.

Metals that may be extracted in the process according to the second aspect of the present invention include copper, iron, cobalt, nickel, manganese and zinc, most preferably copper.

The orthohydroxyaryldoximes, orthohydroxyarylketoxyimes, the equilibrium modifiers, the selectivity modifiers and the water immiscible organic solvent are as herein described above.

5 The aqueous acidic solution from which metals are extracted by the process of the second aspect of the present invention often has a pH in the range of from -1 to 7, preferably from 0 to 5, and most preferably from 0.25 to 3.5. The solution can be derived from the leaching of ores or may be obtained from other sources, for example metal containing waste streams

10 The concentration of metal, particularly copper, in the aqueous acidic solution will vary widely depending for example on the source of the solution. Where the solution is derived from the leaching of ores, the metal concentration is often up to 75g/l and most often from 1 to 40g/l.

15 The process of the second aspect of the present invention can be carried out by contacting the solvent extractant composition with the aqueous acidic solution. Ambient or elevated temperatures, such as up to 75°C can be employed if desired. Often a temperature in the range of from 5 to 60°C, and preferably from 15 to 40°C, is employed. The aqueous solution and the solvent extractant are usually agitated together to maximise the interfacial areas between the two solutions. The volume ratio of solvent extractant to aqueous solution are commonly in the range of from 20:1 to 1:20, and preferably in the
20 range of from 5:1 to 1:5. In many embodiments, to reduce plant size and to maximise the use of solvent extractant, organic to aqueous volume ratios close to 1:1 are maintained by recycle of one of the streams.

After contact with the aqueous acidic solution, the metal can be recovered from the solvent extractant by contact with an aqueous acidic strip solution.

25 The aqueous strip solution employed in the process according to the second aspect of the present invention is usually acidic, commonly having a pH of 2 or less, and preferably a pH of 1 or less, for example, a pH in the range of from -1 to 0.5. The strip solution commonly comprises a mineral acid, particularly sulphuric acid, nitric acid or hydrochloric acid. In many embodiments, acid concentrations, particularly for sulphuric acid, in the range
30 of from 130 to 200g/l and preferably from 150 to 180g/l are employed. When the extracted metal is copper, preferred strip solutions comprise stripped or spent electrolyte from a copper electro-winning cell, typically comprising up to 80g/l copper, often greater than 20g/l copper and preferably from 30 to 70g/l copper, and up to 220g/l sulphuric acid, often greater than 120g/l sulphuric acid, and preferably from 150 to 180g/l sulphuric acid.

35 The volume ratio of organic solution to aqueous strip solution in the process of the second aspect of the present invention is commonly selected to be such so as to achieve transfer, per litre of strip solution, of up to 50g/l of metal, especially copper into the strip solution from the organic solution. In many industrial copper electrowinning processes transfer is often from 10g/l to 35g/l, and preferably from 15 to 20g/l of copper per litre of
40 strip solution is transferred from the organic solution. Volume ratios of organic solution to

aqueous solution of from 1:2 to 15:1 and preferably from 1:1 to 10:1, especially less than 6:1 are commonly employed.

Both the separation and stripping process can be carried out by a conventional batch extraction technique or column contactors or by a continuous mixer settler technique. The latter technique is generally preferred as it recycles the stripped organic phase in a continuous manner, thus allowing the one volume of organic reagent to be repeatedly used for metal recovery.

A preferred embodiment of the second aspect of the present invention comprises a process for the extraction of a metal from aqueous acidic solution in which:

in step 1, the solvent extraction composition comprising a water immiscible organic solvent, one or more orthohydroxyaryldoximes and/or one or more orthohydroxyarylketoimes, and one or more equilibrium modifiers and a selectivity modifier is first contacted with the aqueous acidic solution containing metal,

in step 2, separating the solvent extraction composition containing metal-solvent extractant complex from the aqueous acidic solution;

in step 3, contacting the solvent extraction composition containing metal-solvent extractant complex with an aqueous acidic strip solution to effect the stripping of the metal from the water immiscible phase;

in step 4, separating the metal-depleted solvent extraction composition from the loaded aqueous strip solution.

The invention is further illustrated, but not limited, by the following examples.

Examples

Example 1

Extractant compositions were prepared as described in the following table. 150ml of each of the extractant compositions was then stirred with 150 ml of an aqueous "extraction" solution containing 1.8 g/l Cu, 1.0 g/l Fe (of which 0.042 g/l was Fe(III)) & pH 2.1. The aqueous and organic were stirred for 3min to simulate extraction. After 3min the extractant compositions were separated, and the organic was sampled. The metal loaded extractant was then mixed with 30ml of an aqueous "strip" solution containing 35.3 g/l Cu and 179 g/l of sulphuric acid for 3 minutes. After separation the extractant compositions were sampled. The samples of the organic phase were then analysed for copper and iron content. The table below shows the results for each extractant composition in terms of Transfer ratio.

	Extractant Composition	Cycle				Cu/Fe	Cu/Fe
			Org.Cu	Org.Fe	% Cu	Transfer	
			(g/l)	(g/l)	Strip	Ratio	
A	0.179M 2-hydroxy-5-nonylsalicylaldoxime + 0.1M 2,4,4-trimethyl-1,3-pentanediol diisobutyrate In kerosene	Load	4.77	0.00063	55.14	4696	
		Strip	2.14	0.00007			
B	0.00179M Bis(2,4,4-trimethyl)phosphinic acid In kerosene	Load	0.001	0.0051	0.00	0	
		Strip	0.001	0.00116			
C	0.179M 2-hydroxy-5-nonylsalicylaldoxime + 0.1M 2,4,4-trimethyl-1,3-pentanediol diisobutyrate + 0.00179M Bis(2,4,4-trimethyl)phosphinic acid In kerosene	Load	4.71	0.069	55.84	132	
		Strip	2.08	0.049			
D	0.179M 2-hydroxy-5-nonylacetophenone oxime In kerosene	Load	4.28	0.0014	46.96	2051	
		Strip	2.27	0.00042			
E	0.179M 2-hydroxy-5-nonylacetophenone oxime + 0.00179M Bis(2,4,4-trimethyl)phosphinic acid In kerosene	Load	3.82	0.0628	66.23	173	
		Strip	1.29	0.0482			

As shown neither the modified aldoxime (A), nor the ketoxime (D) was capable of transferring significant amounts of iron in the presence of copper. The phosphinic acid (B) transferred some iron without copper, however the blend of oxime with phosphinic acid (Examples C and E) transferred significantly more iron than would be expected relative to the individual components. Transfer ratios dropped from over 2000:1 to less than 200:1 without impacting copper transfer.

The increased iron transfer and corresponding lower Cu:Fe transfer ratio was achieved without impact to the stability of the oxime, or other negative physical or metallurgical effects.

10 Example 2

8a

Extractant compositions were prepared by mixing aliquots of 2-hydroxy-5-nonylsalicylaldoxime (an aldoxime) & 2,2,4-trimethyl-1,3-pentanediol di-isobutyrate (a modifier) with varying masses of Tributyl Phosphite (TBP). In each case 11.76g (0.179M) of aldoxime, 7.23g (0.1M) of modifier and 0g (Blank); 0.118g (0.00179M) & 1.18g (0.0179M) of TBP (95% purity) was made up to 0.25 litre with Orfom SX7 (a diluent).

200ml of the extractant composition was then stirred with 200ml of an aqueous "extraction" solution containing 3.5 g/l Cu, 3.8 g/l Fe (of which 1.0 g/l was Fe(III)) & pH 2.1 for 30min to simulate extraction. After 30min the extractant composition was separated from the aqueous and sampled. The extractant formulation was then stirred for a further 30 minutes with 40ml of an aqueous "strip" solution containing 35.3 g/l Cu and 179 g/l of sulphuric acid. After separation the extractant composition was sampled. The samples of the organic phase were then analysed for copper and iron content. The table below shows the results for 100:1 and 10:1 molar ratios of aldoxime to potential selectivity modifier.

	Cycle	Org. Cu (g/l)	Org. Fe (g/l)	Transfer Ratio
0.179M 2-hydroxy-5-nonylsalicylaldoxime + 0.1M 2,2,4-trimethyl-1,3-pentanediol di-isobutyrate (BLANK)	Load	5.22	0.0022	1275
	Strip	2.44	0.00002	
+BLANK + 0.0179M TBP	Load	4.99	0.0029	961
	Strip	2.55	0.00036	
+BLANK + 0.00179M TBP	Load	5.31	0.00153	1986
	Strip	2.51	0.00012	

10

As shown TBP is surprisingly not suitable as a selectivity modifier and did not enhance iron transfer relative to the 'BLANK' extractant composition.

Example 3

15

Extractant compositions were prepared by mixing aliquots of 2-hydroxy-5-nonylsalicylaldoxime (an aldoxime) & 2,2,4-trimethyl-1,3-pentanediol di-isobutyrate (a modifier) with varying masses of Di(2-ethylhexyl) phosphoric acid (DEHPA). In each case 11.76g (0.179M) of aldoxime, 7.23g (0.1M) of modifier and 0g (Blank); 0.149g (0.00179M) & 1.49g (0.0179M) of DEHPA (97% purity) was made up to 0.25 litre with Orfom SX7 (a diluent).

20

200ml of the extractant composition was then stirred with 200ml of an aqueous "extraction" solution containing 3.5 g/l Cu, 3.8 g/l Fe (of which 1.0 g/l was Fe(III)) & pH 2.1 for 30min to simulate extraction. After 30min the extractant composition was separated and sampled. The extractant composition was then stirred for a further 30 minutes with 40ml of an aqueous "strip" solution containing 35.3 g/l Cu and 179 g/l of sulphuric acid. After separation the extractant composition was sampled. The samples of the organic phase were then analysed for copper and iron content. The table below shows the results for 100:1 and 10:1 molar ratios of aldoxime to potential selectivity modifier.

25

	Cycle 3	Org. Cu	Org. Fe	Transfer
		(g/l)	(g/l)	Ratio
0.179M 2-hydroxy-5-nonylsalicylaldoxime + 0.1M 2,2,4-trimethyl-1,3-pentanediol di-isobutyrate (BLANK)	Load	5.22	0.0022	1275
	Strip	2.44	0.00002	
+BLANK + 0.0179M DEHPA	Load	4.42	0.549	14
	Strip	2.1	0.386	
+BLANK + 0.00179M DEHPA	Load	5.22	0.075	151
	Strip	2.8	0.059	

Although the addition of DEHPA succeeded in reducing the Cu:Fe transfer ratio, the amount of iron remaining in the organic phase following the strip cycle was greater than 70%. On repetition of the experiment it was determined DEHPA loads readily but does not strip easily – using standard strength electrolyte. DEHPA is therefore effectively poisoned by iron and therefore unsuitable as a selectivity modifier.

Example 4

Extractant compositions were prepared by mixing aliquots of 2-hydroxy-5-nonylsalicylaldoxime (an aldoxime) & 2,2,4-trimethyl-1,3-pentanediol di-isobutyrate (a modifier) with varying masses of Acorga SBX-50. SBX-50 is a mixture of which is a mixture of iso-octadecyl-phosphoric and di-iso-octadecyl-phosphoric acids. In each case 11.76g (0.179M) of aldoxime, 7.23g (0.1M) of modifier and 0g (Blank); 0.199g (0.00179M) & 1.99g (0.0179M) of SBX-50 (90% purity) was made up to 0.25 litre with Orfom SX7 (a diluent). 200ml of the extractant composition was then stirred with 200ml of an aqueous "extraction" solution containing 3.5 g/l Cu, 3.8 g/l Fe (of which 1.0 g/l was Fe(III)) & pH 2.1 for 30min to simulate extraction. After 30min the extractant composition was separated and sampled. The extractant composition was then stirred for a further 30 minutes with 40ml of an aqueous "strip" solution containing 35.3 g/l Cu and 179 g/l of sulphuric acid. After separation the extractant composition was sampled. The samples of the organic phase were then analysed for copper and iron content. The table below shows the results for 100:1 and 10:1 molar ratios of aldoxime to potential selectivity modifier.

	Cycle	Org. Cu	Org. Fe	Transfer
		(g/l)	(g/l)	Ratio
0.179M 2-hydroxy-5-nonylsalicylaldoxime + 0.1M 2,2,4-trimethyl-1,3-pentanediol di-isobutyrate (BLANK)	Load	5.22	0.0022	1275
	Strip	2.44	0.00002	
+BLANK + 0.0179M SBX-50	Load	4.9	0.607	39
	Strip	2.18	0.538	
+BLANK + 0.00179M SBX-50	Load	5.21	0.076	130
	Strip	2.47	0.0549	

Again the example shows that the extractant formulations containing SBX-50 are poisoned by iron. The iron loads readily but does not strip easily. SBX-50 is therefore unsuitable as a selectivity modifier.

Example 5

Extractant compositions were prepared by mixing aliquots of 2-hydroxy-5-nonylsalicylaldoxime (an aldoxime) & 2,2,4-trimethyl-1,3-pentanediol di-isobutyrate (a modifier) with varying masses of tris (2-ethylhexyl)amine (TEHA). In each case 11.76g (0.179M) of aldoxime, 7.23g (0.1M) of modifier and 0g (Blank); 0.16g (0.00179M) of TEHA was made up to 0.25 litre with Orfom SX7 (a diluent).

200ml of the extractant composition was then stirred with 200ml of an aqueous "extraction" solution containing 3.5 g/l Cu, 3.8 g/l Fe (of which 1.0 g/l was Fe(III)) & pH 2.1 for 30 min to simulate extraction. After 30min the extractant composition was separated and sampled. The extractant composition was then stirred for a further 30 minutes with 40ml of an aqueous "strip" solution containing 35.3 g/l Cu and 179 g/l of sulphuric acid. After separation the extractant composition was sampled. The samples of the organic phase were then analysed for copper and iron content. The table below shows the results for 100:1 and 10:1 molar ratios of aldoxime to potential selectivity modifier.

		Org. Cu	Org. Fe	Transfer
	Cycle 3	(g/l)	(g/l)	Ratio
Blank	Load	5.22	0.0022	1275
+0.00179M TEHA	Load	5.12	0.00254	1073
	Strip	2.48	0.00008	

As shown TEHA (a known iron extractant) does not complex iron readily under the test conditions and is therefore unsuitable as a selectivity modifier.

Example 6

5

Extractant compositions were prepared by mixing aliquots of 2-hydroxy-5-nonylsalicylaldoxime (an aldoxime) & 2,2,4-trimethyl-1,3-pentanediol di-isobutyrate (a modifier) with varying masses of dinonylnaphthalene sulfonic acid (DNNSA) – a known iron transferring agent. In each case 11.76g (0.179M) of aldoxime, 7.23g (0.1M) of modifier and

10

0g (Blank) & 0.16g (0.00179M) of DNNSA was made up to 0.25 litre with Orfom SX7 (a diluent).

Accelerated degradation tests were carried out on the extractant compositions. 250ml of each extractant composition was mixed with an aqueous solution containing 30.0 g/l of copper and 179 g/l of sulphuric acid for 284 hours at 60 °C. samples were taken periodically and the rate constants calculated.

15

	K =(hr ⁻¹)
0.179M 2-hydroxy-5-nonylsalicylaldoxime + 0.1M 2,2,4-trimethyl-1,3-pentanediol di-isobutyrate (BLANK)	0.000651
+BLANK + 0.00179M DNNSA	0.012352

Although DNNSA is known to extract iron under the test conditions – in formulation with an oxime extractant it is not suitable as a “selectivity modifier”. The example demonstrates that the degradation rate of the extractant formulation containing DNNSA was several order of magnituded greater than the Blank. DNNSA would therefore be unsuitable as a selectivity modifier.

20

Example 7

25

Extractant compositions were prepared by mixing aliquots of 2-hydroxy-5-nonylsalicylaldoxime (an aldoxime) & 2,2,4-trimethyl-1,3-pentanediol di-isobutyrate (an equilibrium modifier) with varying masses of phosphinic and phosphonic selectivity modifiers. In each case 47.1g of aldoxime, 28.64g of modifier and 0.00179M of each potential selectivity modifier was made up to 1.0 litre with Orfom SX7 (a diluent).

30

100ml of the extractant composition was then stirred with 300ml of an aqueous "extraction" solution containing 1.43 g/l Cu, 7.91 g/l Fe & pH 2.0 for 30min to simulate extraction. After 30min the extractant composition was separated and sampled. The extractant composition was then stirred for a further 30 minutes with 20ml of an aqueous "strip" solution containing

35

35.6 g/l Cu, 3.1 g/l Fe and 179 g/l of sulphuric acid. After separation the extractant composition was sampled. The samples of the organic phase were then analysed for

copper and iron content. The table below shows the results for a 100:1 molar ratio of aldoxime to selectivity modifier.

	Cycle	Org. Cu	Org. Fe	Transfer Ratio
		(g/l)	(g/l)	
Aldoxime + Equilibrium Modifier	Load	5.19	0.0034	726
	Strip	3.23	0.0007	
+Aldoxime + Equilibrium Modifier+ Bis(2,4,4- trimethyl)phosphinic acid,	Load	5.04	0.096	43
	Strip	3.18	0.053	
Aldoxime+Equilibrium Modifier+ 2-ethylhexylphosphonic acid, mono-2-ethylhexyl ester,	Load	5.04	0.093	53
	Strip	3.18	0.058	

- 5 The example demonstrates that both Bis(2,4,4-trimethyl)phosphinic acid and 2-ethylhexylphosphonic acid, mono-2-ethylhexyl ester would be suitable selectivity modifiers.

Example 8

- 10 High ratio of 2-hydroxy-5-nonylsalicylaldoxime to Selectivity Modifier

Extractant compositions A, B & C were prepared as described in the following table. 50ml of each of the extractant compositions was stirred with 150ml of an aqueous "extraction" solution containing 5.0 g/l Cu, 0.2 g/l Fe (III), pH 1.74 for 3min to simulate extraction. After
15 extraction the extractant compositions were separated, and then mixed for a further 3 minutes with 25ml of an aqueous "strip" solution containing 32.5 g/l Cu and 176 g/l of sulfuric acid. After separation the aqueous phase was discarded and the extraction and strip procedures repeated a further two times. The ratio of extractant composition to aqueous "extraction" solution was 1:2 for the second and third contacts. The ratio of extractant
20 composition to "strip" solution was 2:1 for the second and third contacts. After the third cycle samples of the organic and aqueous phases were taken and copper and iron concentration in each measured. The table below shows the results after the third cycle.

	Extractant Composition	Cycle	Org. Cu (g/l)	Org. Fe (g/l)	Cu Strip (%)	Cu/Fe Rejection Ratio	Cu/Fe Transfer Ratio	Cu Transfer (g/l)
A	0.365M 2-hydroxy-5-nonylsalicylaldoxime +0.268M 2,2,4-trimethyl-1,3-pentanediol di-isobutyrate	Load	7.72	0.00029	55.2	26621	17040	4.3
		Strip	3.46	0.00004				
B	0.365M 2-hydroxy-5-nonylsalicylaldoxime +0.268M 2,2,4-trimethyl-1,3-pentanediol di-isobutyrate +0.000073M Bis(2,4,4-trimethylpentyl) phosphinic acid	Load	8.15	0.00074	57.1	11014	6940	4.7
		Strip	3.5	0.00007				
C	0.365M 2-hydroxy-5-nonylsalicylaldoxime +0.268M 2,2,4-trimethyl-1,3-pentanediol di-isobutyrate +0.000073M 2-ethylhexylphosphonic acid, mono-2-ethylhexyl ester	Load	8.78	0.00106	56.2	8283	5135	4.9
		Strip	3.85	0.0001				

Formulation composition A contained no selectivity modifier and under the test conditions a Cu/Fe transfer ratio of 17040 was obtained. Formulation composition B included the addition of the selectivity modifier bis(2,4,4-trimethylpentyl)phosphinic acid to achieve a molar ratio of a ratio of 2-hydroxy-5-nonylsalicylaldoxime to bis(2,4,4-trimethylpentyl)phosphinic acid of 5000:1. Under the same test conditions as for A, the Cu/Fe Transfer Ratio of B decreased to 6940 from 17040.

Formulation composition C included the addition of 2-ethylhexylphosphonic acid, mono-2-ethylhexyl ester to achieve a molar ratio of 2-hydroxy-5-nonylsalicylaldoxime to 2-ethylhexylphosphonic acid, mono-2-ethylhexyl ester of 5000:1. Under the test conditions as for A, the Cu/Fe transfer ratio of C decreased from to 5135 from 17040.

Example 9

High ratio of 2-hydroxy-5-nonylsalicylaldoxime + 2-hydroxy-5-nonylacetophenone oxime to Selectivity Modifier.

Extractant compositions A, B & C were prepared as described in the following table. 50ml of each of the extractant compositions was stirred with 150ml of an aqueous "extraction" solution containing 7.0 g/l Cu, 0.2 g/l Fe (III)), pH 1.74 for 3min to simulate extraction. After extraction the extractant compositions were separated, and then mixed for a further 3 minutes with 25ml of an aqueous "strip" solution containing 32.5 g/l Cu and 176 g/l of sulfuric acid. After separation the aqueous phase was discarded and the extraction and strip procedures repeated a further two times. The ratio of extractant composition to aqueous "extraction" solution was 1:2 for the second and third contacts. The ratio of extractant composition to "strip" solution was 2:1 for the second and third contacts. After the third cycle samples of the organic and aqueous phases were taken and copper and iron concentration in each measured. The table below shows the results after the third cycle.

Extractant Composition	Cycle	Org. Cu (g/l)	Org. Fe (g/l)	Cu Strip (%)	Cu/Fe Rejection Ratio	Cu/Fe Transfer Ratio	Cu Transfer (g/l)
A 0.18M 2-hydroxy-5-nonylsalicylaldoxime +0.17M 2-hydroxy-5-nonylacetophenone oxime	Load	8.85	0.00053	55.6	16698	22364	4.9
	Strip	3.93	0.00031				
B 0.18M 2-hydroxy-5-nonylsalicylaldoxime +0.17M 2-hydroxy-5-nonylacetophenone oxime +0.00035M Bis(2,4,4-trimethylpentyl) phosphinic acid	Load	8.92	0.0039	56.6	2287	1573	5.1
	Strip	3.87	0.00069				
C 0.18M 2-hydroxy-5-nonylsalicylaldoxime +0.17M 2-hydroxy-5-nonylacetophenone oxime +0.00035M 2-ethylhexylphosphonic acid, mono-2-ethylhexyl ester	Load	8.87	0.0044	57.3	2016	1261	5.1
	Strip	3.79	0.00037				

Formulation composition A contained no selectivity modifier and under the test conditions a Cu/Fe transfer ratio of 22364 was obtained. Formulation composition B included the addition of the selectivity modifier bis(2,4,4-trimethylpentyl)phosphinic acid to achieve a molar ratio of a ratio of 2-hydroxy-5-nonylsalicylaldoxime/2-hydroxy-5-nonylacetophenone oxime to bis(2,4,4-trimethylpentyl)phosphinic acid of 1000:1. Under the same test conditions as for A, the Cu/Fe Transfer Ratio of B decreased to 1573 from 22364.

Formulation composition C included the addition of 2-ethylhexylphosphonic acid, mono-2-ethylhexyl ester to achieve a molar ratio of 2-hydroxy-5-nonylsalicylaldoxime/2-hydroxy-5-nonylaceto-
 5 1000:1. Under the test conditions as for A, the Cu/Fe transfer ratio of C decreased to 1261 from 22364.

Example 10

Low ratio of 2-hydroxy-5-nonylsalicylaldoxime to Selectivity Modifier

10 Extractant compositions D, E, F, G & H were prepared as described in the following table. 50ml of each of the extractant compositions was stirred with 150ml of an aqueous "extraction" solution containing 4.6 g/l Cu, 0.8 g/l Fe (III), pH 2.0 for 3min to simulate extraction. After extraction the extractant compositions were separated, and then mixed for
 15 a further 3 minutes with 25ml of an aqueous "strip" solution containing 35.0 g/l Cu and 181 g/l of sulfuric acid. After separation the aqueous phase was discarded and the extraction and strip procedures repeated a further two times. The ratio of extractant composition to aqueous "extraction" solution was 1:2 for the second and third contacts. The ratio of extractant composition to "strip" solution was 2:1 for the second and third contacts. After the
 20 third cycle samples of the organic and aqueous phases were taken and copper and iron concentration in each measured. The table below shows the results after the third cycle.

	Extractant Composition	Cycle	Crg. Cu (g/l)	Org. Fe (g/l)	Cu Strip (%)	Cu/Fe Rejection Ratio	Cu/Fe Transfer Ratio	Cu Transfer (g/l)
D	0.456M 2-hydroxy-5-nonylsalicylaldoxime +0.334M 2,2,4-trimethyl-1,3-pentanediol di-isobutyrate	Load	11.05	0.0005	59.4	22100	16400	6.6
		Strip	4.49	0.0001				
E	0.456M 2-hydroxy-5-nonylsalicylaldoxime +0.334M 2,2,4-trimethyl-1,3-pentanediol di-isobutyrate +0.228M Bis(2,4,4-trimethylpentyl)phosphonic acid	Load	7.9	0.71	74.7	11	32	5.9
		Strip	2	0.52				
F	0.456M 2-hydroxy-5-nonylsalicylaldoxime +0.334M 2,2,4-trimethyl-1,3-pentanediol di-isobutyrate +0.091M Bis(2,4,4-trimethylpentyl) phosphonic acid	Load	9.3	0.37	64.7	25	34	6.0
		Strip	3.28	0.19				
G	0.456M 2-hydroxy-5-nonylsalicylaldoxime +0.334M 2,2,4-trimethyl-1,3-pentanediol di-isobutyrate +0.228M 2-ethylhexylphosphonic acid, mono-2-ethylhexyl ester	Load	8.3	2.85	71.1	3	19	5.9
		Strip	2.4	2.54				
H	0.456M 2-hydroxy-5-nonylsalicylaldoxime +0.334M 2,2,4-trimethyl-1,3-pentanediol di-isobutyrate +0.091M 2-ethylhexylphosphonic acid, mono-2-ethylhexyl ester	Load	9.88	1.37	63.7	7	20	6.3
		Strip	3.59	1.05				

25 Formulation composition D contained no selectivity modifier and under the test conditions a Cu/Fe transfer ratio of 16400 was obtained. Formulation E included the addition of the selectivity modifier bis(2,4,4-trimethylpentyl)phosphonic acid to achieve a molar ratio of 2-hydroxy-5-nonylsalicylaldoxime to bis(2,4,4-trimethylpentyl)phosphonic acid of 2:1. Under the
 30 same test conditions as for D, the Cu/Fe Transfer Ratio of E decreased to 32 from 16400.

Formulation F included the addition of the selectivity modifier bis(2,4,4-trimethylpentyl)phosphinic acid to achieve a molar ratio of 2-hydroxy-5-nonylsalicylaldoxime to bis(2,4,4-trimethylpentyl)phosphinic acid of 5:1. Under the same test conditions as for D, the Cu/Fe Transfer Ratio of F decreased to 34 from 16400.

5

Formulation G included the addition of the selectivity modifier 2-ethylhexylphosphonic acid, mono 2-ethylhexyl ester to achieve a molar ratio of 2-hydroxy-5-nonylsalicylaldoxime to 2-ethylhexylphosphonic acid, mono 2-ethylhexyl ester of 2:1. Under the same test conditions as for D, the Cu/Fe Transfer Ratio of G decreased to 19 from 16400.

10

Formulation H included the addition of the selectivity modifier 2-ethylhexylphosphonic acid, mono 2-ethylhexyl ester to achieve a molar ratio of 2-hydroxy-5-nonylsalicylaldoxime to 2-ethylhexylphosphonic acid, mono 2-ethylhexyl ester of 5:1. Under the same test conditions as for D, the Cu/Fe Transfer Ratio of H decreased to 20 from 16400.

The claims defining the invention are as follows:

1. A solvent extraction composition comprising one or more orthohydroxyaryalldoximes and/or one or more orthohydroxyarylketoximes, and one or more selectivity modifiers consisting of phosphinic and/or phosphonic acids, and salts and esters therefore and one or more equilibrium modifiers selected from alkylphenols, alcohols, esters, ethers and polyethers, carbonates, ketones, nitriles, amides, carbamates, sulphoxides, or salts of amines and quaternary ammonium compounds, wherein the selectivity modifier is present in a molar ratio of the o-hydroxyoxime from 0.001 to 0.05.
2. A solvent extraction composition according to Claim 1 wherein the selectivity modifier is selected from the group of phosphinic acids, or salts or esters thereof of the formula $R_4R_5P(O)OR_6$ where R_4 is H, C1 - C20 alkyl, aryl or arylalkyl group R_5 is H, C1 - C20 alkyl, aryl or arylalkyl group, and R_6 is H, a metal cation or NR_7 where R_7 is H, a C1 - C20 alkyl, aryl or arylalkyl group, or phosphonic acids or salts or esters thereof of the formula $R_8R_9OP(O)OR_{10}$ where R_8 is H, C1 - C20 alkyl, aryl or arylalkyl group, R_9 is H, C1 - C20 alkyl, aryl or arylalkyl group, and R_{10} is H, a metal cation, or NR_7 where R_7 is H, C1 - C20 alkyl, aryl or arylalkyl group.
3. A solvent extraction composition according to Claim 2 wherein the selectivity modifier is selected from the group bis(2,4,4-trimethyl)phosphinic acid, bis(2-ethylhexyl)phosphinic acid, bis(2-ethylhexyl)phosphonic acid, phenylphosphonic acid or their salts and 2-ethylhexylphosphonic acid, mono-2-ethylhexyl ester.
4. A solvent extraction composition according to Claim 3 wherein the selectivity modifier is bis(2,4,4-trimethylpentyl)phosphinic acid, or 2-ethylhexylphosphonic acid, mono-2-ethylhexyl ester.
5. A solvent extraction composition according to Claim 1 wherein the selectivity modifier is present in a molar ratio of the o-hydroxyoxime from 0.001 to 0.01.
6. A solvent extraction composition according to Claim 1 wherein the orthohydroxyarylketoxime is a 5-(C₈ to C₁₄ alkyl)-2-hydroxyacetophenone oxime, and the orthohydroxyaryalldoxime is a 5-(C₈ to C₁₄ alkyl)-2-hydroxybenzalldoxime.
7. A solvent extraction composition according to Claim 1 wherein one or more equilibrium modifiers is selected from the group consisting of 2,2,4-trimethyl-1,3-pentanediol mono-isobutyrate, 2,2,4-trimethyl-1,3-pentanediol mono-benzoate, 2,2,4-trimethyl-1,3-pentanediol di-isobutyrate, 2,2,4-trimethyl-1,3-pentanediol di-benzoate, di-butyl adipate, di-pentyl adipate, di-hexyl adipate, isobutyl heptyl ketone, nonanone, 2,6,8-trimethyl-4- nonanone, diundecyl ketone, 5,8-diethyldodecane-6,7-dione, tridecanol, tetraethyleneglycol di-2-ethylhexanoate and nonyl phenol.

8. A solvent extraction composition according to Claim 7 wherein the orthohydroxyarylketoimine is 2-hydroxy-5-nonylbenzophenone oxime, and the orthohydroxyarylaldoimine is 2-hydroxy-5-nonylsalicylaldoimine and equilibrium modifier is 2,2,4-trimethyl-1,3-pentanediol di-isobutyrate.

5 9. A solvent extraction composition according to Claim 1 wherein the ratio of orthohydroxyarylaldoimines and/or one or more orthohydroxyarylketoimines to equilibrium modifier is from about 5000:1 to about 2:1.

10 10. A process for the extraction of a metal from solution in which an acidic solution containing a dissolved metal is contacted with a solvent extraction composition, whereby at least a fraction of the metal is extracted into the organic solution, characterised in that the solvent extraction composition comprises a water immiscible organic solvent, one or more orthohydroxyarylaldoimines and/or one or more orthohydroxyarylketoimines, and one or more selectivity modifiers selected from phosphinic and/or phosphonic acids, and salts and esters thereof and one or more
15 equilibrium modifiers selected from alkylphenols, alcohols, esters, ethers and polyethers, carbonates, ketones, nitriles, amides, carbamates, sulphoxides, or salts or amines and quaternary ammonium compounds, wherein the selectivity modifier is present in a molar ratio of the o-hydroxyoxime from 0.001 to 0.05.

20 11. A process according to Claim 10 wherein the metal is copper, iron, cobalt, nickel, manganese or zinc.

12. A process according to claim 10 or claim 11 wherein the solvent extraction composition comprises a composition as claimed in any of claims 1 to 9.

25 13. A process according to claim 10 in which the selectivity modifier is present as a molar ratio of the o-hydroxyoxime from 0.001 to 0.01.

Dated 20 October, 2009

Cytec Technology Corp.

Patent Attorneys for the Applicant/Nominated Person

SPRUSON & FERGUSON