



(86) **Date de dépôt PCT/PCT Filing Date:** 2010/09/17  
(87) **Date publication PCT/PCT Publication Date:** 2012/03/22  
(45) **Date de délivrance/Issue Date:** 2017/08/15  
(85) **Entrée phase nationale/National Entry:** 2013/03/13  
(86) **N° demande PCT/PCT Application No.:** JP 2010/066182  
(87) **N° publication PCT/PCT Publication No.:** 2012/035650

(51) **Cl.Int./Int.Cl. C10L 5/44** (2006.01)  
(72) **Inventeurs/Inventors:**  
KIYAMA, MICHIMIRO, JP;  
YAMAMOTO, MASAYUKI, JP  
(73) **Propriétaire/Owner:**  
CREATIVE CO. LTD., JP  
(74) **Agent:** SMART & BIGGAR

(54) **Titre : CARBURANT SOLIDE**  
(54) **Title: SOLID FUEL**

(57) **Abrégé/Abstract:**

[Object] To provide a solid fuel which comprises a binder, a form retaining agent and a vegetable oil-containing substance in a balanced manner, has a stable calorific value and suppresses the production of carbon dioxide. [Solution] A solid fuel formed from a mixture of a binder, a form retaining agent and a vegetable oil-containing substance, wherein the amount of the binder is 1 to 85 parts by weight, the amount of the form retaining agent is 5 to 55 parts by weight, and the amount of the vegetable oil-containing substance is 10 to 85 parts by weight based on 100 parts by weight of the mixture, and the mixture is molded. [Selected Drawing] None



ABSTRACT

[Object] To provide a solid fuel which comprises a binder, a form retaining agent and a vegetable oil-containing substance in a balanced manner, has a stable calorific value and suppresses the production of carbon dioxide.

[Solution] A solid fuel formed from a mixture of a binder, a form retaining agent and a vegetable oil-containing substance, wherein the amount of the binder is 1 to 85 parts by weight, the amount of the form retaining agent is 1 to 55 parts by weight, and the amount of the vegetable oil-containing substance is 10 to 85 parts by weight based on 100 parts by weight of the mixture, and the mixture is molded.

[Selected Drawing] None

## SOLID FUEL

## BACKGROUND OF THE INVENTION

[Field of the Invention]

5 [0001]

The present invention relates to a solid fuel. More specifically, it relates to a solid fuel which makes effective use of a binder, a form retaining agent and a vegetable oil-containing substance. Much more specifically, it relates to a solid fuel which makes effective use of a binder and a form retaining agent derived from natural products while using a vegetable oil-containing substance, produces as small an amount as possible of a harmful gas or residue, has a large calorific value and leads to the suppression of the production of carbon dioxide, especially a solid fuel suitable for use as a fuel for power generation.

[Prior Art]

[0002]

The causes of global warming which is one of the global environmental issues include an increasing amount of carbon dioxide existent in air. Various approaches to the suppression of the production of carbon dioxide are being made on a global basis. As one of the approaches, the production of biofuels and use of them in automobiles and power boilers as alternatives to fossil fuels such as coal and gasoline are under way. However, use of foods such as corn which are used as raw materials of the biofuels is breaking down ecological balance and economical balance and therefore it cannot be said that this is the best approach. Thus, it is necessary to take the global environment into consideration while effects on clothing, food and housing whose balance is essential to human lives are minimized. Since this is a very difficult problem to be solved, various studies are under way but the problem is not solved yet. Then, a solid fuel making use of plastics is used in power boilers as an alternative to oil and coal but it cannot be said that its effect

of suppressing the production of carbon dioxide is satisfactory.

[0003]

Meanwhile, Patent Documents 1 to 3 propose the recycling  
5 of wood waste, paper waste and plastic waste into a solid fuel.

Patent Document 1 proposes a solid fuel which makes use  
of used paper and plastic waste. This solid fuel actually  
comprises 25 to 100 parts by weight of plastic waste based on  
100 parts by weight of used paper. Thus, a relatively large  
10 amount of plastic waste (20 to 50 wt% of the total) is used.  
Although this Patent Document 1 teaches that a wood-based waste  
material may be further used, the amount of the wood-based waste  
material used in Examples is no more than 10 wt% of the total.  
The above solid fuel contains plastic waste in a relatively  
15 large proportion and therefore, the step of dechlorinating the  
obtained solid fuel by heating it is required to suppress a  
trouble caused by the inclusion of polyvinyl chloride at the  
time of combustion.

[0004]

20 Patent Document 2 proposes a solid fuel obtained by  
pressure bonding together plastics, wooden powders, bark and  
used paper and molding the obtained product into a pellet.  
Although the amount of the plastics contained in the solid fuel  
is specified as 10 to 80 %, judging from Figs. 2 to 4, the amount  
25 of the plastics is estimated at 30 % or more, preferably 50 %  
or more.

[0005]

Patent Document 3 proposes a method of obtaining a fuel  
by kneading 5 to 10 parts by weight of a synthetic resin-based  
30 waste material with 100 parts by weight of a wood-based waste  
material and pelletizing the kneaded product. The pellet  
obtained by this method has a small diameter of about 6 to 12  
mm, it cannot be said that the calorific value of the pellet  
is sufficiently large, and further, its form retention  
35 stability is unsatisfactory. Therefore, the pellet is

unsuitable for use as a solid fuel for thermal power generation.  
[0006]

Meanwhile, along with the frequent occurrence of a  
wide-scale disaster which is seemed to be caused by the global  
5 warming phenomenon in recent years, each country is trying to  
suppress the production of carbon dioxide which is one of  
greenhouse effect gases but it can be said that this is still  
unsatisfactory. Then, solid fuels making use of various waste  
products are used in power boilers as alternatives to oil and  
10 coal but it can be said that their effect of suppressing the  
production of carbon dioxide is still unsatisfactory.  
[0007]

That is, since plastics are used as a binder and a fuel  
source in the solid fuels proposed by the above Patent Documents  
15 1 to 3, considering that the plastics are produced from oil,  
these solid fuels are unsatisfactory in the effect of  
suppressing the production of carbon dioxide.

[Prior Art Documents]

[Patent Documents]

20 [0008]

Patent Document 1: JP-A 7-82581

Patent Document 2: JP-A 57-57796

Patent Document 3: JP-A 62-43490

[Summary of the Invention]

25 [Problem to Be Solved by the Invention]

[0009]

Then, the inventors of the present invention conducted  
intensive studies to develop a solid fuel which can be used as  
an energy source capable of suppressing the production of carbon  
30 dioxide without using plastics derived from oil. As a result,  
they found that, when a vegetable oil-containing substance  
which is a natural resource is used in place of waste wood, used  
paper and plastics which have been used in the prior art and  
mixed with a binder and a form retaining agent derived from  
35 natural products in a certain ratio and the resulting mixture

is molded, a solid having a certain shape and a certain size can be formed, and this solid has excellent form retaining ability, has a large calorific value as a fuel, rarely produces a harmful gas or a harmful residue, greatly serves to suppress the production of carbon dioxide as all the raw materials are derived from natural plants and is useful as a solid fuel for power generation. Thus, according to the present invention, there can be provided a solid fuel which can be used for power generation as a clean energy source because all of its raw materials are derived from plants without using plastics which have been used in the prior art.

[Means for Solving the Problem]

[0010]

According to the present invention, there is provided the following solid fuel.

1. A solid fuel which is formed from a mixture of a binder (component A), a form retaining agent (component B) and a vegetable oil-containing substance (component C), wherein the amount of the component A is 1 to 85 parts by weight, the amount of the component B is 1 to 55 parts by weight, and the amount of the component C is 10 to 85 parts by weight based on 100 parts by weight of the mixture, and the mixture is compression molded.

2. The solid fuel in the above paragraph (1), wherein the total amount of the components A and B is 15 to 90 parts by weight based on 100 parts by weight of the mixture.

3. The solid fuel in the above paragraph (1), wherein the amount of the component C is 10 to 80 parts by weight based on 100 parts by weight of the mixture.

4. The solid fuel in the above paragraph (1), wherein the weight ratio of the component A to the component B is 1:25 to 85:1.

5. The solid fuel in the above paragraph (1), wherein the binder (component A) is starch derived from sea alga.

6. The solid fuel in the above paragraph (1), wherein the form retaining agent (component B) is natural rubber.

67616-293

5

7. The solid fuel in the above paragraph (1), wherein the vegetable oil-containing substance (component C) is the fruit seed of *Ricinus communis* or *Jatropha curcas*, or a pulverized product thereof.

5 8. The solid fuel in the above paragraph (1) having an average size of 10 to 100/ $\mu\text{m}$  each.

9. The solid fuel in the above paragraph (1) which is prismatic or cylindrical in shape.

10 10. The solid fuel in the above paragraph (1) having an apparent specific gravity of 0.3 to 0.6  $\text{g}/\text{cm}^3$ .

11. The solid fuel in the above paragraph (1) having a calorific value of 20 to 30 MJ/kg.

12. The solid fuel in the above paragraph (1) which is used for thermal power generation.

15 [0010a]

There is also provided a solid fuel which is formed from a mixture of a binder consisting of starch derived from sea alga (component A), a form retaining agent consisting of natural rubber (component B) and a vegetable oil-containing substance consisting of the fruit seed of  
20 *Ricinus communis* or *Jatropha curcas*, or a pulverized product thereof (component C), wherein the amount of the component B is 1 to 55 parts by weight, the amount of the component C is 10 to 85 parts by weight based on 100 parts by weight of the mixture, and the mixture is compression molded.

25 [0010b]

There is also provided use of the solid fuel according to the invention for thermal power generation.

[Effect of the Invention]

30 [0011]

The solid fuel of the present invention can be effectively used as a new energy source, especially an energy source for power generation, by using a binder, a form retaining agent and a vegetable

67616-293

5a

oil-containing substance in a balanced manner. The solid fuel of the present invention can be a new type of solid fuel which rarely produces a harmful gas or a harmful residue, has a large calorific value and leads to the suppression of the production of carbon  
5 dioxide.

The binder and the form retaining agent serve as binders and the vegetable oil-containing substance effectively serves to secure a certain amount of heat in the solid fuel of the present invention, thereby making it possible to mold a solid fuel. Since the solid  
10 fuel of the present invention comprises a binder and a form retaining agent derive from plants and a vegetable oil-containing substance without using plastics derived from oil, it has a remarkable effect of suppressing the production of carbon dioxide.

15 BEST MODE FOR CARRYING OUT THE INVENTION  
[0012]

The solid fuel of the present invention is a solid obtained by molding a mixture of a binder, a form retaining agent and a vegetable oil-containing substance. A description is subsequently given of the ratio of raw materials and a molding method.

[0013]

(a) binder

The binder is starch collected from sea alga containing alginic acid, as exemplified by agarose, carrageenan, curdlan and glucomannan. At least one dried binder out of these or a combination of a binder and a form retaining agent may be used. The binder is cut or severed to a size of 1 to 50 mm. The term "size" as used herein means the size of a binder passing through a sieve having an opening of 50 mm or less. The binder may be powdery.

[0014]

(b) form retaining agent

Natural rubber or a natural rubber-containing product is used as the form retaining agent. Examples thereof include guar gum, tara gum, locust bean gum, tamarind seed gum, psyllium seed gum, gum arabic, gellan gum, curdlan, pectin, cellulose, chitin, chitosan, xanthan gum, karaya gum, arabinogalactan, ghatti gum, tragacanth gum, furcellan, pullulan, aeromonas gum, agrobacterium succinoglycan, azotobacter vinelandii gum, linseed gum, almond gum, welan gum, erwinia mitsuensis gum, gum elemi, enterobacter gum, enterobacter simanus gum, oligoglucosamine, cassia gum, carob bean gum, glucosamine, artemisia sphaerocephala seed gum, sclero gum, sesbania gum, dextran, triacanthos gum, abelmoschus manihot, macrophomopsis gum, rhamsan gum, levan, daruman resin, peach gum and tamarind. At least one dried form retaining agent out of these or a combination of a form retaining agent and a binder may be used.

Out of these, guar gum, tara gum, locust bean gum, tamarind seed gum, psyllium seed gum, gellan gum, curdlan, xanthan gum, gum arabic, pectin, cellulose, chitin, chitosan, xanthan gum,

karaya gum and carob bean gum are preferred, and guar gum, tara gum, locust bean gum, tamarind seed gum, psyllium seed gum, gellan gum, curdlan and xanthan gum are most preferred.

The form retaining agent is cut or severed to a size of 1 to 50 mm. The term "size" as used herein means the size of a form retaining agent passing through a sieve having an opening of 50 mm or less. The form retaining agent may be powdery. [0015]

(c) vegetable oil-containing substance

*Sapium sebiferum*, *Quercus suber*, millet, rice, food carbide, flax, jute, ramie, kenaf, *Abutilon avicennae*, roselle, Musa basjoo, *Juncus effuses L. var. decipens Buchen.*, *Cyperus monophyllus Vahl*, okra, *Morus bombycis*, banana, pineapple, *Agave Tequilana*, sarago, wisteria, linden, bamboo, reed, esparto, sabai grass, *Alpinia zerumbet*, *Hermerocallis aurantiaca*, raran grass, morochi grass, papyrus, ryusu grass, *Pueraria lobata*, *Edgeworthia chrysantha*, aotan, cashew nut, oat, lupine, calendula, coffee, hazelnut, spurge, pumpkin, coriander, mustard seed, *Carthamus tinctorius*, cacao, *Tenderstem broccoli*, *Brassica campestris*, macadamia nut, nuts, *Ricinus communis*, *Jatropha curcas*, palm, sugarcane, *Sorghum bicolor*, potato, wheat, *Oryza sativa*, olive, sunflower, soybean, safflower, peanut, willow, poplar, switchgrass, elephant grass, *Evodiopanax innovans*, cactus, lumber, sugar beet, *Pistacia chinesis Bunge*, cotton, copaiba, *Pongamia pinnata*, jojoba, *Euphorbia tirucalli*, *Zea mays*, sweet potato, *Sargassum fulvellum*, sesame, cardoon, avocado, kusabinoki, quinoa, *Guizotia abyssinica*, hemp and paulownia are used as the vegetable oil-containing substance. *Sapium sebiferum*, *Ricinus communis*, *Jatropha curcas*, palm, sugarcane, *Zea mays* and processed residues thereof are preferred and used as heat sources for burning the solid fuel as a fuel at a power generation facility. The term "processed residues" means press cakes obtained after oil is squeezed out of the fruits and seeds of *Sapium sebiferum*, *Quercus suber*, millet, rice, food carbide,

flax, jute, ramie, kenaf, *Abutilon avicennae*, roselle, *Musa*  
*basjoo*, *Juncus effuses* L. var. *decipens* Buchen., *Cyperus*  
*monophyllus* Vahl, okra, *Morus bombycis*, banana, pineapple,  
*Agave Tequilana*, sarago, wisteria, linden, bamboo, reed,  
5 *esparto*, sabai grass, *Alpinia zerumbet*, *Hermerocallis*  
*aurantiaca*, raran grass, morochi grass, papyrus, ryusu grass,  
*Pueraria lobata*, *Edgeworthia chrysantha*, aotan, cashew nut, oat,  
lupine, calendula, coffee, hazelnut, spurge, pumpkin,  
coriander, mustard seed, *Carthamus tinctorius*, cacao,  
10 *Tenderstem broccoli*, *Brassica campestris*, macadamia nut, nuts,  
*Ricinus communis*, *Jatropha curcas*, palm, sugarcane, *Sorghum*  
*bicolor*, potato, wheat, *Oryza sativa*, olive, sunflower, soybean,  
safflower, peanut, willow, poplar, switchgrass, elephant grass,  
*Evodiopanax innovans*, cactus, lumber, sugar beet, *Pistacia*  
15 *chinesis* Bunge, cotton, copaiba, *Pongamia pinnata*, jojoba,  
*Euphorbia tirucalli*, *Zea mays*, sweet potato, *Sargassum*  
*fulvellum*, sesame, cardoon, avocado, kusabinoki, quinoa,  
*Guizotia abyssinica*, hemp and paulownia. The fruit seeds of  
*Sapium sebiferum*, *Ricinus communis*, *Jatropha curcas*, palm,  
20 sugarcane and *Zea mays* or pulverized products thereof are  
preferred. Out of these, the fruit seeds of *Sapium sebiferum*,  
*Ricinus communis* and *Jatropha curcas* or pulverized products  
thereof are particularly preferred. These vegetable  
oil-containing substances are cut or severed to a size of 1 to  
25 50 mm. The term "size" as used herein means the size of a  
vegetable oil-containing substance passing through a sieve  
having an opening of 50 mm or less. Although seeds are mainly  
used, branches or trunks may be partially mixed.

[0016]

30 (d) composition

The amount of the component A is 1 to 85 parts by weight,  
the amount of the component B is 1 to 55 parts by weight, and  
the amount of the component C is 10 to 85 parts by weight based  
on 100 parts by weight of the mixture of all the components.  
35 The total amount of the components A and B is 15 to 90 parts

by weight, preferably 20 to 85 parts by weight, and the amount of the component C is preferably 15 to 80 parts by weight.

Further, the weight ratio of the component A to the component B is 1:25 to 85:1, preferably 1:29 to 80:1.

5 [0017]

Within the above ranges, the solid fuel of the present invention can be solidified by using relatively small amounts of a binder, a form retaining agent and a vegetable oil-containing substance, whereby the calorific value becomes  
10 stable. When the total amount of the binder and the form retaining agent is 15 to 90 parts by weight, the amount of the vegetable oil-containing substance is desirably 10 to 85 parts by weight. This ratio is changed by the desired calorific value of the solid fuel.

15 [0018]

(e) molding method

A mixture of the above binder, form retaining agent and vegetable oil-containing substance in the above ratio is preferably pressurized and compressed such that they are  
20 closely dispersed.

A method in which the binder and the vegetable oil-containing substance are pre-mixed together and the form retaining agent is mixed with the resulting mixture is particularly preferred, and a single-screw or double-screw  
25 extruder may be used as a mixing machine. The use of a double-screw extruder is particularly desirable. A composition which has been compressed and extruded by the extruder is ejected from a prismatic or circular nozzle and cut to a suitable length to obtain a prismatic or cylindrical molded  
30 product.

A solid fuel having a desired size can be obtained by setting the diameter of the cylindrical nozzle to 5 to 50 mm and the cut length to 10 to 100 mm.

[0019]

35 (f) characteristic properties of solid fuel

Since the solid fuel of the present invention is preferably manufactured by the above molding method industrially, the shape thereof is desirably cylindrical or prismatic and particularly advantageously cylindrical. The size of the solid fuel is each desirably 10 to 100 cm<sup>3</sup> on average in terms of volume. The apparent specific gravity of the solid fuel is desirably in the range of 0.3 to 0.6 g/cm<sup>3</sup>.

The calorific value of the solid fuel is stable at 20 to 30 MJ/kg. Therefore, the solid fuel of the present invention comprises the binder, the form retaining agent and the vegetable oil-containing substance in a balanced manner, has a highly stable calorific value and a great effect of suppressing the production of carbon dioxide and therefore is advantageously used as a fuel for thermal power generation.

## 15 EXAMPLES

### [0020]

The following examples are provided to further illustrate the present invention.

The following binder, form retaining agent and caloric augmentation agent were used in the following examples.

#### (a) Binder

The binder was obtained by crushing dried carrageenan (size of 25 mm or less).

#### (b) Form retaining agent

25 Guar gum powders were used as the form retaining agent.

#### (c) vegetable oil-containing substance

A seed collected from the cultivated *Ricinus communis* and a residue thereof.

### [0021]

#### 30 Example 1

10 parts by weight of the component B was mixed with a mixture of 48 parts by weight of the component A and 42 parts by weight of the component C, and the resulting mixture was extruded by a double-screw extruder to obtain a cylindrical solid fuel having a diameter of about 35 mm (length of 50 mm).

The apparent specific gravity (bulk specific gravity), calorific value, chlorine content and form retention stability test result of this solid fuel are shown in Table 1.

[0022]

5 Example 2

5 parts by weight of the component B was mixed with a mixture of 15 parts by weight of the component A and 80 parts by weight of the component C, and the resulting mixture was extruded by a double-screw extruder to obtain a cylindrical  
10 solid fuel having a diameter of about 35 mm (length of 50 mm). The apparent specific gravity (bulk specific gravity), calorific value, chlorine content and form retention stability test result of this solid fuel are shown in Table 1.

[0023]

15 Example 3

50 parts by weight of the component B was mixed with a mixture of 1 parts by weight of the component A and 49 parts by weight of the component C, and the resulting mixture was extruded by a double-screw extruder to obtain a cylindrical  
20 solid fuel having a diameter of about 35 mm (length of 50 mm). The apparent specific gravity (bulk specific gravity), calorific value, chlorine content and form retention stability test result of this solid fuel are shown in Table 1.

[0024]

25 Example 4

5 parts by weight of the component B was mixed with a mixture of 80 parts by weight of the component A and 15 parts by weight of the component C, and the resulting mixture was extruded by a double-screw extruder to obtain a cylindrical  
30 solid fuel having a diameter of about 35 mm (length of 50 mm). The apparent specific gravity (bulk specific gravity), calorific value, chlorine content and form retention stability test result of this solid fuel are shown in Table 1.

[0025]

Table 1

Product: solid fuel						
Size (length) mm	bulk specific gravity g/cm <sup>2</sup>	Calorific value		Chlorine content %	Form retention stability	
		Joule (MJ/Kg)	Calorie (cal/g)			
Ex. 1	50	0.44	24.03	5739.16	0.042	satisfactory
Ex. 2	50	0.58	29.67	7086.20	0.049	satisfactory
Ex. 3	50	0.41	24.72	5903.82	0.075	satisfactory
Ex. 4	50	0.34	20.09	4799.50	0.068	satisfactory

[0026]

<form retention stability test on solid fuel>

The form retention stability of each of the solid fuels obtained in the above Examples 1 to 4 was checked. The  
5 expression "weight ratio of pieces" means the ratio of the total weight of pieces having a size of about 10 cm<sup>3</sup> or less obtained by sieving the solid fuel to the weight of the solid fuel before sieving.

The form retention stability was checked by loading 500  
10 kg of the solid fuel after molding into a transport vehicle from a storage installation twice by using a reach loader. The evaluation results are as follows.

Example 1: The solid fuel has a good molded state and retains a certain shape and a certain size even at the time of delivery  
15 to a storage installation (weight ratio of pieces: 3 %)

Example 2: The solid fuel has a good molded state and retains a certain shape and a certain size even at the time of delivery to a storage installation (weight ratio of pieces: 5 %)

Example 3: The solid fuel has a good molded state and retains  
20 a certain shape and a certain size even at the time of delivery to a storage installation (weight ratio of pieces: 3 %)

Example 4: The solid fuel has a good molded state and retains a certain shape and a certain size even at the time of delivery to a storage installation (weight ratio of pieces: 2 %)

25 (evaluation: weight ratio % of pieces)

0 to 5 %: good

6 to 10 %: moderate

11 to 15 %: bad

67616-293

14

CLAIMS:

1. A solid fuel which is formed from a mixture of a binder consisting of starch derived from sea alga (component A), a form retaining agent consisting of natural rubber (component B) and a vegetable oil-containing substance consisting of the fruit seed of *Ricinus communis* or *Jatropha curcas*, or a pulverized product thereof (component C), wherein the amount of the component B is 1 to 55 parts by weight, the amount of the component C is 10 to 85 parts by weight based on 100 parts by weight of the mixture, and the mixture is compression molded.
2. The solid fuel according to claim 1, wherein the total amount of the components A and B is 15 to 90 parts by weight based on 100 parts by weight of mixture.
3. The solid fuel according to claim 1, wherein the amount of the component C is 10 to 80 parts by weight of the mixture.
4. The solid fuel according to claim 1, wherein the weight of ratio of the component A to the component B is 1:25 to 85:1.
5. The solid fuel according to claim 1 having an average size of 10 to 100 cm<sup>3</sup> each.
6. The solid fuel according to claim 1 which is prismatic or cylindrical in shape.
7. The solid fuel according to claim 1 having an apparent specific gravity of 0.3 to 0.6 g/cm<sup>3</sup>.
8. The solid fuel according to claim 1 having a calorific value of 20 to 30 MJ/kg.
9. Use of the solid fuel according to any one of claims 1 to 8 for thermal power generation.