



AU9461089

(12) PATENT ABRIDGMENT (11) Document No. AU-B-61089/94
(19) AUSTRALIAN PATENT OFFICE (10) Acceptance No. 688755

- (54) Title
UNLEADED TRANSPARENT VITREOUS GLASS COMPOSITION AND ARTICLES
- International Patent Classification(s)
(51)^s **C03C 003/091**
- (21) Application No. : **61089/94** (22) Application Date : **11.02.94**
- (87) PCT Publication Number : **WO94/18134**
- (30) Priority Data
- (31) Number (32) Date (33) Country
9302927 13.02.93 GB UNITED KINGDOM
- (43) Publication Date : **29.08.94**
- (44) Publication Date of Accepted Application : **19.03.98**
- (71) Applicant(s)
PROCERAM
- (72) Inventor(s)
PHILIP ANTHONY EVANS; PAUL HARRISON; ROLF ALFRED WIRTZ
- (74) Attorney or Agent
SPRUSON & FERGUSON, GPO Box 3898, SYDNEY NSW 2001
- (56) Prior Art Documents
EP 0444821
US 3801356
GB 812576
- (57) Claim

1. An unleaded durable transparent vitreous glass composition consisting of a combination of

- (a) a low alumina alkali borosilicate consisting of:
40 to 69 wt% silica (SiO_2),
10 to 30 wt% boric oxide (B_2O_3),
0.5 to 6.0 wt% aluminium oxide (Al_2O_3),
0.5 to 6.0 wt% calcium oxide (CaO),
10 to 30 wt% sodium oxide (Na_2O) and/or potassium oxide (K_2O),
0.1 to 2.0 wt% lithium oxide (Li_2O),
based on the total amount of the low alumina alkali borosilicate,
- (b) 2-20 wt% of a major addition of one element selected from the group of zirconium, tin and titanium, and
- (c) less than 10 wt% of at least one element selected from bismuth, barium, strontium, zinc, lanthanum, molybdenum and cerium wherein the amounts of (a), (b) and (c) are calculated on the basis of the total amount of the oxide forms of (a), (b) and (c).



INT

(51) International Patent Classification ⁵ : C03C 3/091		A1	(11) International Publication Number: WO 94/18134 (43) International Publication Date: 18 August 1994 (18.08.94)
(21) International Application Number: PCT/EP94/00403 (22) International Filing Date: 11 February 1994 (11.02.94) (30) Priority Data: 9302927 13 February 1993 (13.02.93) GB (71)(72) Applicants and Inventors: EVANS, Philip, Anthony [GB/GB]; 12 Methley Drive, Chapel Allerton, Leeds LS7 3NE (GB). HARRISON, Paul [GB/GB]; 11 Rochester Terrace, Headingley, Leeds, West Yorkshire LS6 3DF (GB). (72) Inventor; and (75) Inventor/Applicant (for US only): WIRTZ, Rolf, Alfred [DE/GB]; Crossford House, Bulstrode Way, Gerrards Cross SL9 7QU (GB). (74) Agent: WEBER, Thomas; Bahnhofsvorplatz 1, D-50667 Köln (DE).			(81) Designated States: AU, BR, CA, CN, CZ, FI, HU, JP, KR, NO, PL, RU, SK, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: UNLEADED TRANSPARENT VITREOUS GLASS COMPOSITION AND ARTICLES			
(57) Abstract The present invention relates to an unleaded durable transparent vitreous glass composition comprising a combination of (a) up to 98 wt. % of a low alumina alkali borosilicate, (b) 2-20 wt. % of a major addition of one element selected from the group of zirconium, tin and titanium, and (c) less than 10 wt. % of at least one element selected from bismuth, barium, strontium, zinc, lanthanum, molybdenum, cerium and/or a fluoride containing inorganic compound wherein the amounts of (a), (b) and (c) are calculated on the basis of the total amount of the oxide forms of (a), (b) and (c), a process for its production and the use of said composition.			

Unleaded Transparent Vitreous
Glass Composition And Articles

This invention relates to unleaded transparent vitreous glass compositions and articles, and more particularly to unleaded single addition intermediate oxide, alkali borosilicate based vitreous glass compositions which are usable to form transparent, durable, decorative/functional glass articles and glass materials for applications including tableware, container, window, architectural, light bulb, radiation absorbing, protective, additive, release, and waste containment categories, glass crystal glass fibres, and dental porcelains.

Lead has long been recognized as a toxic substance, and adverse health effects such as damage to the liver, the kidneys, and the nervous, reproductive, cardiovascular, immune, and gastrointestinal systems may well result from exposure over months or years to lead. Infants and children are the most sensitive to lead exposure. Several recent studies have indicated that lead causes behavioural and performance related deficiencies in children exposed to the substance at levels below those which produce physical effects. Other recent studies have shown that the fetus is sensitive to low levels of lead in the mother's blood resulting in impaired fetal development and low birth weight.

The health hazard is perceived in terms of lead release levels from lead-containing glass articles and compositions, which affect the health of the general public which buys the products. Resistance to both acid and alkaline chemical attack and waste disposal aspects is of paramount importance in present day society with the use of such glass containers to store acid food and drinks, and the use of dish-washing machines with alkaline detergents/acidic descalers to clean these glass articles.

For the purposes of classification, the majority of silica

- 2 -

based glasses can be arranged into five categories.

Soda lime glasses (Alkali-Alkaline Earth Silicate Glasses)

5 This represents the oldest of the glass types including the flat glasses (e.g. window glass), and container glasses having a generalized formula:

	SiO ₂	- 65 to 75
	alkaline earth oxides	- 13 to 16
10	(CaO, MgO)	
	alkali oxide	- 12 to 17
	(Na ₂ O, K ₂ O).	

15 The combination of raw materials , i.e. silica sand, soda ash, and limestone, produce a glass that is easily melted and shaped and that has good chemical durability. This group is particularly suited to automatic forming methods. Very small amounts, often less than 1 wt% of the total batch, of alumina and boric oxide and other chemicals are added to act

20 as stabilizers and to increase durability in certain instances. Variants of the basic composition can also contain significant amounts of baria (Alkaline Earth Oxide). On a broader plane, certain crystal glasses (drinking glasses) can also be included in this category.

25

Lead Glasses (Alkali Lead Silicate Glasses)

Lead based glasses were developed and introduced in the United Kingdom in 1674 by George Ravenscroft. Lead oxide was substituted for limestone, and potash for soda ash. Such

30 glasses have found application in crystal glass (decorative, container, and tableware areas) due to high refractive index and slow rate of increase in viscosity with decrease in temperature, making lead crystal particularly suitable for hand-made production. High electrical resistivity (increased

35 by the potash content) has made these glasses important in electrotechnology (lamp stems, cathode ray tube applications). Lead oxide also absorbs X-rays and thus such

- 3 -

glasses find application in radiation shielding and cathode ray tube components. A generalized formula is:

	SiO ₂	-	45 to 58 wt%
	PbO	-	10 to 65 wt%
5	alkali oxides	-	12 to 18 wt%.

Again, small amounts - often less than 1 wt% - of alumina and boric oxide are added to improve chemical durability. Nickel oxide and cobalt oxide are also added in small amounts < 1 wt% to decolourise the glass.

Alkaline Earth Alumina Silicate Glasses

Characteristically, these glasses are free of alkali oxides and have a high alumina content. Typically, properties include very high transformation and softening temperatures. The main applications are for high temperature thermometers, surface layer resistors, combustion tubes and glasses for halogen lamps. A generalized formula is:

20	SiO ₂	-	52 to 60 wt%
	Al ₂ O ₃	-	17 to 25 wt%
	alkaline earth oxides	-	13 to 17 wt%.

Borosilicate Glasses

These glasses were developed in the early part of the 20th century to overcome the problem of cold rain cracking hot railway signal lights. This group which basically incorporates boric oxide with silica has developed into various sub-groups dependent upon the amount of boric oxide introduced and the presence/absence of alkaline earth oxides.

(i) Non Alkaline Earth Borosilicate Glass

High chemical durability, low thermal expansion ($3.3 \times 10^{-6} \text{ }^{\circ}\text{C}^{-1}$) - the lowest of all commercial glasses for large scale technical applications - make this the universal glass for chemical plant, pipeline, laboratory ware, and cook/oven

- 4 -

ware applications. A generalized formula is:

	SiO ₂	-	> 80 wt%
	B ₂ O ₃	-	12 to 13 wt%
5	alumina	-	0 to 3 wt%
	alkali oxide	-	2 to 4 wt%.

(ii) Alkaline Earth Containing Borosilicate Glass

The presence of the alkali earth oxides increases the thermal expansion to between 4 to 5 x 10⁻⁶ °C⁻¹ and slightly softens the glass, yielding more easily formed, but highly chemically durable glass. Applications include ampoules and vials for the pharmaceutical industry. A generalized formula is:

15	SiO ₂	-	75 wt%
	B ₂ O ₃	-	8 to 12 wt%
	alkali oxide	-	0 to 4 wt%
	alkaline earth oxides)		
20	alumina	) -	< 5 wt%

(iii) High Borate Borosilicate Glass

Glasses with a boric oxide content > 15 wt% have lower softening points and low thermal expansion. They can be fused to metals in the expansion range of tungsten - molybdenum acting as sealing glasses. Their high electrical insulation is of prime importance. A generalized formula is:

30	SiO ₂	-	65 to 70 wt%
	B ₂ O ₃	-	15 to 25 wt%
	alkali oxide)		
	alumina	) -	5 to 10 wt%

35

It is commonly accepted that such glasses containing > 15 wt% B₂O₃ have low chemical resistance (Ref: Schott - 'Technical Glasses: Physical and Chemical Properties' 1990).

- 5 -

Another recently developed category of glass which exists in its own right is 'glass-ceramics'. Such materials commonly contain zirconium, titanium, and fluorine in their compositions which are known to act as nucleation sites from which the crystalline phases develop and are grown during a controlled melting, cooling and annealing thermal cycle. Such materials fall outside the scope of the present invention due to their semi-crystalline nature.

It should thus be understood that it is common knowledge that small percentages of Zr, Ti, and Sn are soluble when added as opacifiers in glass compositions. This fact is reinforced by US-A-4 870 034 which states that > 0.5 wt% zirconia added to a borosilicate glass composition causes crystallization and hence opacity.

Tin, zirconium, and titanium are thus perceived by those skilled in the art of glass, when added as major additions to silica based vitreous systems, as opacifying agents.

It should be noted that the present invention is not based upon and does not include in its compositional variations, deliberate major additions of elements of bismuth, barium, strontium, zinc, lanthanum, molybdenum, cerium and/or an inorganic fluoride. This does not, however, preclude that at least one element, and/or inorganic fluoride or other elements being added as minor additions (c) to the present composition, i.e. at levels ≤ 10 wt% based on the total amount of said minor addition of said at least one element, the low alumina alkali borosilicate (a) and the major addition (b), provided that transparency is retained.

It is thus apparent that there is an acute need for an unleaded vitreous glass composition which is usable to form transparent, durable, decorative/functional glass articles and glass materials for applications including tableware, container, window, architectural, light bulb, radiation

absorbant, protective, additive, release and waste containment categories, glass crystal, glass fibres and dental porcelains.

A commercially acceptable system will need to satisfy the following factors:

- (i) Cost,
- 5 (ii) Availability,
- (iii) Effect on processing parameters, i.e. low melting temperature, rapidity of homogenization and exploitation of kinetics,
- (iv) Effect on ultimate properties, i.e. transparency, high refractive index and good chemical resistance.

10 The present invention satisfies all these factors.

In a first embodiment, the present invention thus relates to an unleaded durable transparent vitreous glass composition consisting of a combination of

- (a) a low alumina alkali borosilicate consisting of:
 - 40 to 69wt% silica (SiO_2),
 - 15 10 to 30wt% boric oxide (B_2O_3),
 - 0.5 to 6.0wt% aluminium oxide (Al_2O_3),
 - 0.5 to 6.0wt% calcium oxide (CaO),
 - 10 to 30wt% sodium oxide (Na_2O) and/or potassium oxide (K_2O),
 - 0.1 to 2.0wt% lithium oxide (Li_2O),

20 based on the total amount of the low alumina alkali borosilicate,

- (b) 2-20wt% of a major addition of one element selected from the group of zirconium, tin and titanium, and

- (c) less than 10wt% of at least one element selected from bismuth, barium, strontium, zinc, lanthanum, molybdenum and cerium wherein the amounts of (a), (b) and

25 (c) are calculated on the basis of the total amount of the oxide forms of (a), (b) and (c).

For the purposes of the present invention, the use of the word 'element' shall be taken to include the material in elemental form or in suitable compound form, the latter being an oxide forming compound, and the said word 'element' should be construed accordingly.

30 The present invention relates in a second embodiment to a vitreous glass article consisting wholly or partially of the unleaded, durable, transparent vitreous glass composition according to the first embodiment.

In a third embodiment, the invention relates to a vitreous glass product consisting wholly or partially of the unleaded, durable, transparent vitreous glass composition

35 according to the first embodiment, characterised in that said composition is in monolithic form or powder form.

The present invention relates to a new category of



- 7 -

transparent vitreous glass, i.e. an 'Advanced Intermediate Oxide Vitreous Glass'. There are several elements which may take the role of an intermediate oxide in a vitreous glass structure. However, with regard to health and safety, property optimization, availability, and cost factors, Zr, Sn and Ti represent the most desirable intermediate oxides which, when combined with a low alumina alkaline borosilicate, form the basis of the present invention.

10 The term 'vitreous glass' is taken to mean an inorganic material having no long range crystalline order, thus being considered to be amorphous.

15 The term 'transparent' is taken to mean capable of transmitting useful light without diffusion except that due to refraction. This encompasses glasses which are clear and coloured/stained.

20 According to the present invention there is provided an unleaded transparent vitreous glass composition, comprising in combination a low alumina alkali borosilicate and a major single addition 2 to 20 wt% (calculated on the basis of the oxide form) selected from the group consisting of zirconium, tin and titanium.

25 The low alumina alkali borosilicate will contain a small amount of alumina (intermediate oxide) 0.5 to 6.0 wt%, preferably 0.5 to 4 wt% and calcia (alkaline earth) 0.5 to 6.0 wt%, preferably 0.5 to 4 wt% calculated on the basis of the oxide forms. Strontia and/or baria may be partially or wholly substituted for the Calcia in the role of the minor alkaline earth addition. The amounts given are calculated on basis of the total amount of the low alumina borosilicate.

35 The compositions will incorporate one element from Zr, Sn or Ti and said element will be incorporated into said composition in suitable elemental or compound form, said

- 8 -

element preferably being incorporated into said composition by melting/fritting in order that its solution is optimized, and further, that upon cooling, subsequent processing and usage, devitrification or recrystallization does not occur.

5

The process for the production of the transparent vitreous glass articles or glass compositions is characterized in that it includes mixing together the oxide forming materials of the low alumina alkali borosilicate composition (a), one
10 element (b) selected from the group consisting of zirconium, tin and titanium and optionally the at least one element (c) selected from bismuth, barium, strontium, zinc, lanthanum molybdenum, cerium and/or the fluoride containing inorganic compound and melting at a temperature between 1150-1250 °C
15 for 1 to 4 hours, subsequently fritting and optionally grinding the resulting fragments.

This distinguishes the present invention from processes which simply involve forming articles directly from a glass
20 melt. Such a process necessarily involves a lengthy time period (typically 10 to 24 hours) at an elevated melt temperature and the use of a refining agent (eg. Sb_2O_5 or As_2O_5) to remove entrapped gasses for the glass melt. The fritting process utilized in the present invention however,
25 allows lower melt temperatures to be used (eg., 1150-1250 °C), rapid homogenization of raw materials via short melt times (typically 1 to 4 hours), followed by fritting and optionally subsequent grinding. The grinding action following fritting acts to remove entrapped gases without
30 the need for extended melting times or the use of refining agents.

The term fritting as used in the present invention is taken to mean the quenching (rapid cooling) of the glass melt such
35 that a frit (glass splinters or fragments) is produced.

The term grinding as used in the present invention is taken

- 9 -

to incorporate processes which comminute the glass fragments into a powder, eg. ball milling. This is, however, not taken to limit the invention.

5 This action results in the beneficial properties conferred by the chosen element - zirconium, tin or titanium - on the ultimate processed transparent vitreous glass article or glass composition being optimized.

10 The low alumina alkali borosilicate will preferably be composed of silica, boric oxide, aluminium oxide, calcium oxide, sodium oxide and/or potassium oxide and lithium oxide introduced into the formulation via any element or suitable compound form.

15

As indicated above the calcium oxide can be partially or wholly substituted by strontium oxide and/or barium oxide.

20 The aforementioned elements Zr, Sn or Ti may be introduced into the formulation via any element or suitable compound form. In the main, oxides and silicates are used due to their availability, cost effectiveness, and known purity. This does not, however, preclude the addition of the aforementioned compounds in other forms. Those compound
25 forms most frequently used in the glass industry include, for example, mineral compounds, oxides, hydroxides, silicates, carbonates, sulphates, and nitrates. Elemental forms are not usually used due to the hazardous nature of elements in powder form; this does not, however, preclude
30 their use in such form.

It has not hitherto been appreciated to formulate a transparent, low alumina alkali borosilicate based, vitreous glass composition which is based on the incorporation of a
35 major single addition of one of the aforementioned elements and utilizing process methods outlined in the application mentioned.

- 10 -

The desired properties may thus be 'designed in' dependent upon application requirements, by varying the selection from the aforementioned elements which will comprise the major addition. For example, tin promotes fluidity or fluxing of glasses at relatively low temperatures and also improves the resistance to acids. Additions of zirconium promote gloss and durability, both with regard to alkali chemical and abrasion resistance. Titanium, in addition to promoting gloss and fluidity, also improves acid resistance. All three elements act to confer high refractive indices and promote colour protection/stabilization, in the case of coloured glasses.

It is an attribute of the present invention that the low alumina alkali borosilicate will contain 40 to 69 wt% (based on the total amount of the low alumina borosilicate) silica and is thus described as being silicatic, silicate, or silica based.

Further, the level of boric oxide is set between 10 to 30 wt%, whilst the level of alumina is set between 0.5 to 6.0 wt%.

Small amounts of Al_2O_3 (0.5 to 6.0 wt%) are beneficial to the maintenance of gloss of the transparent glass based upon the present invention. Alumina additions are frequently recommended in the literature in order to promote opacification, and certainly with additions of alumina > 6.0 wt%, this is true.

It is a characteristic of the present invention that the calcia or alternatively SrO and/or BaO as mentioned above is maintained at a level between 0.5 to 6.0 wt%, whilst the level of sodium oxide and/or potassium oxide is set between 10 to 30 wt% and that of lithium oxide at 0.1 to 2.0 wt%, each amount being calculated on basis of the total amount of low alumina alkali borosilicate. This formulation of a low

- 11 -

alumina alkali borosilicate applicable to the full range of application areas specified may be represented as shown in Table I below. It should be noted that the single amounts given for the low alumina alkali borosilicate in Table I and II are based upon the total amount of the low alumina alkali borosilicate.

TABLE I

10	<u>COMPOSITION</u>	<u>WT%</u>
	low alumina	SiO ₂ ... 40 to 69
	alkali borosilicate	B ₂ O ₃ ... 10 to 30
		Al ₂ O ₃ ... 0.5 to 6.0
		CaO ... 0.5 to 6.0
15		Na ₂ O) ... 10 to 30
		K ₂ O)
		Li ₂ O ... 0.1 to 2.0
		Total... up to 98%
20	single major addition	ZrO ₂)
	selected from the group	SnO ₂) ... 2 to 20
		TiO ₂)

A more specific example of the present invention which is applicable to the field of glass crystal may be formulated as shown in Table II below.

TABLE II

30	<u>COMPOSITION</u>	<u>WT%</u>
	low alumina	SiO ₂ ... 45 to 60
	alkali borosilicate	B ₂ O ₃ ... 15 to 25
		Al ₂ O ₃ .. 0.5 to 4.0
		CaO.... 0.5 to 4.0
35		Na ₂ O).. 10 to 20
		K ₂ O)
		Li ₂ O).. 0.5 to 1.0

Total.. up to 92%

single major addition	ZrO ₂)	
selected from the group	SnO ₂) ...	8 to 20
	TiO ₂)	

In the composition outlined in the above Tables I and II it should be noted SrO and/or BaO may be partially or wholly substituted for CaO in the amounts given.

It should further be noted, that the composition can contain less than 10 wt% of at least one element of a minor addition as mentioned above, based on the total amount of said minor addition (c), the low alumina alkali borosilicate (a) and the single major addition (b).

It is a preferred embodiment of the present invention that the range of single major addition selected from the aforementioned elements shall be 8 to 20 wt%, and further that the level of boric oxide is between 15 to 25 wt%.

It will be appreciated then that any low alumina alkali borosilicate based composition which contains low amounts (i.e. < 6.0 wt% and preferably 4 wt%) of alumina, no other listed major addition as has been previously referred to, i.e. bismuth oxide, barium oxide, zinc oxide, lanthanum oxide etc., in conjunction with a single major addition (2 to 20 wt%) of the aforementioned elements (as calculated on basis of the oxide form), will fall within the scope of the present invention. Such glass compositions would thus be described as low alumina alkali borosilicate which contain a single major addition selected from the aforementioned elements in soluble form, which confer the main and above-described benefits to the final silica based composition. The invention would read onto the above composition because a single major addition selected from the aforementioned elements could no longer realistically be described as an

- 13 -

optional/minor addition relative to the other elements (e.g. bismuth, barium, zinc, strontium, and lanthanum) of the composition for which certain property benefits are overriding.

5

It is apparent that the level of boric oxide addition at its maximum preferred value shown in Table II (25 wt%) is relatively high. At these higher levels of addition, it would be assumed by a person skilled in the art of glass that chemical, abrasion, and crazing resistance and colour stabilization properties would deteriorate to such an extent that the composition would be of no commercial value.

10

This is widely referred to as the boric oxide 'anomaly'. This maxima is widely quoted as being within the range 10 to 15 wt%.

15

In the present invention, however, it is contended that the combination of an intermediate oxide selected from the group of elements, Zr, Sn or Ti, in combination with the relatively high amounts of alkali oxides (Na_2O and/or K_2O) contained in the low alumina borosilicate act to raise the boric oxide level to 15 to 25 wt%, while still retaining chemical durability.

20

25

PCT/EP94/00403

TW/ki

Evans et al.

19 APR. 1995

Claims:

5

1. An unleaded durable transparent vitreous glass composition consisting of a combination of

- (a) a low alumina alkali borosilicate consisting of:
- 10 40 to 69 wt% silica (SiO_2),
10 to 30 wt% boric oxide (B_2O_3),
0.5 to 6.0 wt% aluminium oxide (Al_2O_3),
0.5 to 6.0 wt% calcium oxide (CaO),
10 to 30 wt% sodium oxide (Na_2O) and/or potassium
oxide (K_2O),
15 0.1 to 2.0 wt% lithium oxide (Li_2O),

based on the total amount of the low alumina alkali borosilicate,

- (b) 2-20 wt% of a major addition of one element selected
from the group of zirconium, tin and titanium, and
20 (c) less than 10 wt% of at least one element selected
from bismuth, barium, strontium, zinc, lanthanum,
molybdenum and cerium wherein the amounts of (a),
(b) and (c) are calculated on the basis of the total
amount of the oxide forms of (a), (b) and (c).

25

2. A composition according to claim 1, characterized in that
it contains 8 to 20 wt% of (b).

3. A composition according to claim 1, characterized in that
30 the low alumina alkali borosilicate consists of:

- 45 to 60 wt% silica,
15 to 25 wt% boric oxide,
0.5 to 4.0 wt% aluminium oxide,
0.5 to 4.0 wt% calcium oxide,
35 10 to 20 wt% sodium oxide and/or potassium oxide,
0.5 to 1.0 wt% lithium oxide,



AMENDED SHEET

based on the total amount of the low alumina alkali borosilicate.

5 4. A composition according to claim 1 or 3, characterized in that calcium oxide is partially or wholly replaced by strontium oxide and/or barium oxide.

10 5. A composition according to any of claims 1 to 4, characterized in that said elements are introduced as oxide forming materials such as hydroxides, silicates, carbonates, sulphates, or nitrates of said elements.

15 6. A vitreous glass article consisting wholly or partially of the unleaded, durable, transparent vitreous glass composition according to any of claims 1 to 5.

20 7. A vitreous glass product consisting wholly or partially of the unleaded, durable, transparent vitreous glass composition according to any of claims 1 to 5, characterized in that said composition is in monolithic form or powder form.

25 8. A process for the production of the vitreous glass composition according to any of claims 1 to 5, characterized in that it includes mixing together the oxide forming materials of the low alumina alkali borosilicate composition (a), one element selected from the group consisting of zirconium, tin and titanium (b) and optionally the at least one element (c) selected from bismuth, barium, strontium, 30 zinc, lanthanum molybdenum and cerium and melting at a temperature between 1150-1250 °C for 1 to 4 hours, subsequently fritting and optionally grinding the resulting fragments.

35 9. Use of the composition as defined in any one of claims 1 to 5 to form transparent durable decorative/functional glass articles and glass materials for applications including



tableware, container, window, architectural, light bulb, radiation absorbant, protective, additive, release, and waste containment categories, glass crystal, glass fibres, and dental porcelains.



AMENDED SHEET

INTERNATIONAL SEARCH REPORT

Inter. natl Application No

PCT/EP 94/00403

A. CLASSIFICATION OF SUBJECT MATTER
IPC 5 C03C3/091

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 5 C03C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,A	EP,A,0 579 406 (P.A. EVANS ET AL.) 19 January 1994 see the whole document ---	1-10
P,X	GB,A,2 263 478 (CARL ZEISS STIFTUNG) 28 July 1993 see abstract ---	1-10
X	CH,A,359 251 (PPG CO.) 15 February 1962 see the whole document ---	1-10
X	EP,A,0 444 821 (JOHNSON MATTHEY P.L.C.) 4 September 1991 see page 3, line 27 - line 41; claim 1 --- -/--	1-10

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

26 May 1994

Date of mailing of the international search report

09.06.94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 631 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Reedijk, A

INTERNATIONAL SEARCH REPORT

Inter. Appl. Application No.

PCT/EP 94/00403

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DATABASE WPI Week 9148, Derwent Publications Ltd., London, GB; AN 91-347132 & DD,A,291 545 (INST. FESTKORP. ELEKT. ET AL.) 4 July 1991 see abstract ---	1-10
X	DATABASE WPI Week 8850, Derwent Publications Ltd., London, GB; AN 88-258320 & JP,A,63 270 328 (NAKASHIMA KK) 8 November 1988 see abstract ---	1-10
A	US,A,3 801 356 (H.O. MULFINGER ET AL.) 2 April 1974 -----	1-4

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 94/00403

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0579406	19-01-94	NONE	
GB-A-2263478	28-07-93	DE-A- 4201286	22-07-93
		FR-A- 2686333	23-07-93
		NL-A- 9202217	16-08-93
CH-A-359251		BE-A- 551390	
		GB-A- 812576	
EP-A-0444821	04-09-91	AU-A- 7134391	29-08-91
		CN-A- 1055348	16-10-91
		JP-A- 4228452	18-08-92
US-A-3801356	02-04-74	NONE	