



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2035277 C 2001/12/18

(11)(21) **2 035 277**

(12) **BREVET CANADIEN
CANADIAN PATENT**

(13) **C**

(22) Date de dépôt/Filing Date: 1991/01/30

(41) Mise à la disp. pub./Open to Public Insp.: 1991/08/10

(45) Date de délivrance/Issue Date: 2001/12/18

(30) Priorité/Priority: 1990/02/09 (07/478,103) US

(51) Cl.Int.⁵/Int.Cl.⁵ C08G 18/75

(72) Inventeurs/Inventors:
Gracik, Charles S., US;
Sarpeshkar, Ashok M., US

(73) Propriétaire/Owner:
BAYER CORPORATION, US

(74) Agent: SWABEY OGILVY RENAULT

(54) Titre : PRODUIT AMORTISSEUR DE CHOCS

(54) Title: IMPACT ABSORBING MEDIA

(57) Abrégé/Abstract:

The present invention is directed to a solid polyurethane composition having a glass transition temperature of from -20°C to 0°C, having a Bayshore rebound of less than about 20, and having a Shore A hardness of less than 80.



2035277

Mo3343
PU-310B

IMPACT ABSORBING MEDIA

ABSTRACT OF THE DISCLOSURE

The present invention is directed to a solid polyurethane composition having a glass transition temperature of from -20°C to 0°C , having a Bayshore rebound of less than about 20, and having a Shore A hardness of less than 80.

Mo3343

IMPACT ABSORBING MEDIABACKGROUND OF THE INVENTION

Low resiliency elastomers with good impact and shock absorption are potential candidates for shoe insoles, gloves, damping pads, vibration dampers, shock absorber pads or any other application where a soft elastomer with these properties is required. The use of polyurethane elastomers as such energy absorbing media is known. See, e.g., U.S. Patents 4,346,205, 4,476,258, 4,485,719, 4,552,944, 4,567,088, 4,604,940 and 4,722,946. Additionally, elastomers prepared from isocyanate terminated prepolymers and relatively low molecular weight hydroxyl group containing compounds are also known. See, e.g., U.S. Patent 4,551,498. Also known are elastomers made from prepolymers based on cycloaliphatic diisocyanates. See, e.g., U.S. Patents 3,620,905, 4,447,590, and 4,523,005.

While the prior art compositions have properties adequate for some applications, it has heretofore not been possible to produce an elastomer from a two component polyurethane system where the two components could be reacted in a weight ratio of from 1.5:1 to 1:1.5, and which system would yield elastomers with relatively low hardnesses and low rebounds, and with glass transition temperatures of from -20°C to 0°C.

DESCRIPTION OF THE INVENTION

The present invention is directed to an elastomer which satisfies the above criteria. In addition, the systems of the present invention can generally be processed and demolded in relatively short cycle times. Finally, the elastomers of the present invention have overall good physical properties and specifically have good tear strength. More particularly, the present invention is directed to a solid polyurethane composition having a glass transition temperature of from -20°C to 0°C, having a Bayshore rebound of less than about 20, and

having a Shore A hardness of less than 80, and being prepared by reacting:

- 5 a) an isocyanate terminated prepolymer having an isocyanate group content of from about 5 to about 25%, and preferably from about 17 to about 20 % by weight, said prepolymer being prepared by reacting:
- 10 i) a cycloaliphatic diisocyanate with
ii) a polyhydroxyl compound selected from the group consisting of
- 1) diols having molecular weights of from about 450 to about 4000,
2) triols having molecular weights of from about 4000 to about 6000, and
3) mixtures thereof, with
- 15 b) a hydroxyl functional compound selected from the group consisting of
- i) one or more diols having molecular weights of from 62 to about 1000,
ii) one or more triols having molecular weights of
20 from about 500 to about 2000, and
iii) a mixture of
- 1) one or more triols having molecular weights of from more than 300 to about 3000, and
25 2) one or more diols having molecular weights of from about 200 to about 3000,
with the weight ratio component iii)1) to component iii)2) being from 1:0.1 to 1:3,
- 30 c) no more than 10% by weight based on the weight of component b) of one or more triols having molecular weights of 300 or less,
the isocyanate to hydroxyl equivalent ratio being from 0.95:1 to 1.2:1, and the weight ratio of component a)
35 to component b) being from 10:1 to 1:1.5, preferably from

- 3 -

1.5:1 to 1:1.5, and most preferably from 1.2:1 to 1:1.2.

All of the various reactants are known in the art. The polyisocyanates useful as starting components for the production of the elastomers of the present invention may be any cycloaliphatic diisocyanate, such as those described, for example, by W. Siefken in Justus Liebigs Annalen der Chemie, Vol. 562, (December 11, 1948), pages 75 to 136. These include, for example, cyclobutane-1,3-diisocyanate; cyclohexane-1,3- and 1,4-diisocyanate and mixtures of these isomers; 1-isocyanato-3,3,5-trimethyl-5-isocyanatomethyl-cyclohexane (U.S. Patent 3,401,190); hexahydrotolylene-2,4- and -2,6-diisocyanate and mixtures of these isomers; hexahydrophenylene-1,3- and/or 1,4-diisocyanate; perhydrodiphenylmethane-2,4'- and/or 4,4'-diisocyanate; and the like.

The presently preferred isocyanates are methylenebis-(cyclohexyl isocyanates) and isophorone diisocyanate, with methylenebis(cyclohexyl isocyanate) being the most preferred.

The starting components used for the production of the elastomers of the present invention also include a variety of different hydroxyl group containing compounds which contain two or three hydroxyl groups. In the preparation of the prepolymer, the hydroxyl compound is selected from the group consisting of

- 1) diols having molecular weights of from about 450 to about 4000, preferably polyether and polyester diols having molecular weights of from about 450 to about 4000,
- 2) triols having molecular weights of from about 4000 to about 6000, preferably polyether triols having molecular weights of from about 4000 to about 6000, and
- 3) mixtures thereof.

The hydroxyl component to be reacted with the prepolymer component to form the elastomer of the present invention is a

hydroxyl functional compound selected from the group consisting of

- i) one or more diols having molecular weights of from 62 to about 1000,
- 5 ii) one or more triols having molecular weights of from about 500 to about 2000, preferably polyether triols having molecular weights of from about 500 to about 2000, and
- 10 iii) a mixture of
 - 1) one or more triols having molecular weights of from about 300 to about 3000, preferably polyether triols having molecular weights of from about 300 to about 3000,
 - 15 2) one or more diols having molecular weights of from about 200 to about 3000, preferably polyether diols having molecular weights of from about 300 to about 3000,with the weight ratio component iii)1) to component iii)2) being from 1:0.1 to 1:3

20 The hydroxyl compounds useful in producing both the prepolymer and the elastomer itself are generally known in the polyurethane art. All that is necessary is that the molecular weights and amounts of materials be as noted above. Such hydroxyl compounds include, for example, polyesters,

25 polyethers, polythioethers, polyacetals, polycarbonates and polyester amides containing at least 2, and no more than 3 hydroxyl groups, such as those known for the production of polyurethanes. A key to the present invention resides in the proper selection of hydroxyl compound for production of the

30 prepolymer and the elastomer.

Hydroxyl group-containing polyesters used may be, for example, reaction products of polyhydric, preferably dihydric alcohols, optionally with the addition of trihydric alcohols, and polybasic, preferably dibasic carboxylic acids. Instead of

35 using the free polycarboxylic acids, the corresponding

polycarboxylic acid anhydrides or corresponding polycarboxylic acid esters of lower alcohols or mixtures thereof may be used for preparing the polyesters. The polycarboxylic acids may be aliphatic, cycloaliphatic, aromatic and/or heterocyclic and they may be substituted, e.g. with halogen atoms, and/or be unsaturated. The following are mentioned as examples: succinic acid, adipic acid, suberic acid, azelaic acid, sebacic acid, phthalic acid, isophthalic acid, trimellitic acid, phthalic acid anhydride, tetrahydrophthalic acid anhydride, hexahydrophthalic acid anhydride, tetrachlorophthalic acid anhydride, endomethylene tetrahydrophthalic acid anhydride, glutaric acid anhydride, maleic acid, maleic acid anhydride, fumaric acid, dimeric and trimeric fatty acids, optionally mixed with monomeric fatty acids, dimethylterephthalate and terephthalic acid-bis-glycol esters. Suitable polyhydric alcohols to produce such polyesters include, e.g. ethylene glycol; propylene glycol-(1,2) and -(1,3); butylene glycol-(1,4) and -(2,3); hexanediol-(1,6); octanediol-(1,8); neopentyl glycol; cyclohexane dimethanol (1,4-bis-hydroxymethylcyclohexane); 2-methyl-1,3-propanediol; glycerol; trimethylolpropane; hexanetriol-(1,2,6); butanetriol-(1,2,4); trimethylolethane; diethylene glycol; triethylene glycol; tetraethylene glycol; polyethylene glycols; dipropylene glycol; polypropylene glycols; dibutylene glycol and polybutylene glycols. Polyesters of lactones, such as ϵ -caprolactone, and hydroxycarboxylic acids, such as ω -hydroxycaproic acid, may also be used.

The polyethers used according to the present invention contain at least 2 and no more than 3 hydroxyl groups are known. They may be prepared, for example, by the polymerization of epoxides, such as ethylene oxide, propylene oxide, butylene oxide, tetrahydrofuran, styrene oxide or epichlorohydrin, either each on its own, (e.g. in the presence of BF_3) or by chemical addition of these epoxides, optionally as mixtures or successively, to starting components having

Mo3343

reactive hydrogen atoms, such as water, alcohols or amines, e.g. ethylene glycol, propylene glycol-(1,3) or -(1,2), trimethylol propane, 4,4'-dihydroxydiphenylpropane, aniline, ammonia, or ethanolamine. It is frequently preferred to use
5 polyethers which contain predominantly primary OH groups (up to 90%, by weight, based on all the OH groups present in the polyether). Polyethers which have been modified with vinyl polymers, for example the compounds obtained by the polymerization of styrene and acrylonitrile in the presence of
10 polyethers (U.S. Patents 3,383,351; 3,304,273; 3,523,093 and 3,110,695 and German Patent 1,152,536) are also suitable. Polybutadienes containing OH groups may also be used.

Among the polythioethers which should be particularly mentioned are the condensation products obtained from
15 thiodiglycol on its own and/or with other glycols, dicarboxylic acids, formaldehyde, aminocarboxylic acids or amino alcohols. The products obtained are polythio mixed ethers, polythioether esters or polythioether ester amides, depending on the co-components.

20 Suitable polyacetals include, e.g. the compounds which may be obtained from glycols, such as diethylene glycol, triethylene glycol, 4,4'-dioxethoxy-diphenyl-dimethylmethane or hexanediol and formaldehyde. Polyacetals suitable for the purpose of the present invention may also be prepared by
25 polymerizing cyclic acetals.

Suitable polycarbonates containing hydroxyl groups are known and may be prepared, for example, by the reaction of diols, such as 1,3-propanediol, 1,4-butanediol and/or 1,6-hexanediol, diethylene glycol, triethylene glycol or
30 tetraethylene glycol, with diarylcarbonates, e.g. diphenyl carbonate, or phosgene.

Suitable polyester amides and polyamides include, e.g. the predominantly linear condensates obtainable from polybasic saturated and unsaturated carboxylic acids or their anhydrides

and polyvalent saturated and unsaturated amino alcohols, diamines, polyamines or mixtures thereof.

Polyhydroxyl compounds already containing urethane or urea groups as well as modified or unmodified natural polyols, such as castor oil, carbohydrates or starch may also be used. Additionally, products of alkylene oxides and phenol/formaldehyde resins or of alkylene oxides and urea/formaldehyde resins are also suitable according to the present invention.

Also useful are hydroxyl compounds having relatively low molecular weights. They contain 2 or 3 hydroxyl groups. The following are mentioned as examples of such compounds: ethylene glycol; 1,2- and 1,3-propylene glycol; 1,4- and 2,3-butylene glycol; 1,5-pentanediol; 1,6-hexanediol; 1,8-octanediol; neopentylglycol; 1,4-bis-hydroxymethylcyclohexane; 2-methyl-1,3-propanediol; glycerol; trimethylolpropane; 1,2,6-hexanetriol; trimethylolethane; diethylene glycol; triethylene glycol; tetraethylene glycol; polyethylene glycols; polytetramethylene glycols; dipropylene glycol, polypropylene glycols; dibutylene glycol; polybutylene glycols; 4,4'-dihydroxy-diphenylpropane; dihydroxymethylhydroquinone; diethanolamine; triethanolamine; 3-aminopropanol; and the like.

It is presently preferred to use polypropylene glycols and polytetramethylene glycols in preparing the prepolymers and to use polypropylene diols and triols, and polytetramethylene glycols for reaction with the prepolymers to make the elastomers of the present invention.

Representatives of the various hydroxyl group containing compounds which may be used according to the present invention have been described, e.g. in High Polymers, Vol. XVI, "Polyurethanes, Chemistry and Technology", by Saunders-Frisch, Interscience Publishers, New York, London, Volume I, 1962, pages 32-42 and pages 44-54 and Volume II, 1964, pages 5-6 and 198-199 and in Kunststoff-Handbuch, Volume VII, Vieweg-Hochtlén, Carl-Hanser-Verlag, Munich, 1966, e.g. on pages 45 to 71. The only essential requirement in selecting

Mo3343

the particular hydroxyl compound for either the prepolymer production or the elastomer production is that the molecular weight limitations set forth above be observed. It is only in using these narrow ranges of hydroxyl compounds that the elastomers of the present invention can be obtained. In addition, the amounts of components used are essential to produce the elastomers of the present invention.

Both the prepolymer and the elastomer itself are prepared using techniques generally known in the art. In general, the prepolymer is prepared by reacting the hydroxyl compound with an excess of the diisocyanate. This reaction is preferably carried out at elevated temperatures of from 50°C to about 150°C until all the hydroxyl groups of the hydroxyl compound have disappeared. In producing the elastomers of the invention, this prepolymer is then mixed with component b). The resultant mixture can then be cast into molds maintained at temperatures of from about 50°C to about 150°C, where the final curing of the product takes place.

The invention is further illustrated by the following examples in which all parts and percentages are by weight, unless otherwise indicated.

EXAMPLES

In the examples which follow, the following materials were used:

25 ISOCYANATES:

HMDI: 4,4'-methylenebis(cyclohexyl isocyanate)

IPDI: isophorone diisocyanate

HDI: hexamethylene diisocyanate

HYDROXYL COMPOUNDS:

30 DIOL A: a polyoxypropylene glycol having a molecular weight of 1000

DIOL B: a diethylene glycol/ethylene oxide adduct having a molecular weight of 200

DIOL C: a propylene glycol/propylene
35 oxide/ethylene oxide adduct having a

molecular weight of 4000 and containing
about 91% primary hydroxyl groups

DIOL D: a polyoxypropylene glycol having a
molecular weight of 425

5 DIOL E: a polyoxypropylene glycol having a
molecular weight of 2000

DIOL F: a 2000 molecular weight polyester diol
prepared by reacting adipic acid, butane
diol and ethylene glycol (molar ratio of
10 butane diol to ethylene glycol = 1:1).

TRIOL A: a glycerine/propylene oxide adduct having
a molecular weight of about 670

TRIOL B: a trimethylolpropane/propylene oxide
adduct having a molecular weight of 455

15 TRIOL C: a glycerine/propylene oxide/ethylene oxide
adduct having a molecular weight of about
6000 and containing about 88% primary
hydroxyl groups

TRIOL D: a triethanolamine/propylene oxide adduct
20 having a molecular weight of 1122

TRIOL E: a glycerine/propylene oxide/ethylene oxide
adduct having a molecular weight of 4800
and containing about 78% primary hydroxyl
groups

25 TRIOL F: a glycerine/propylene oxide adduct having
a molecular weight of 3000

TRIOL G: a trimethylolpropane/propylene oxide
adduct having a molecular weight of 300

PMEG 650: a polytetramethylene glycol having a
30 molecular weight of 650

PMEG 1000: a polytetramethylene glycol having a
molecular weight of 1000

PMEG 2000: a polytetramethylene glycol having a
molecular weight of 2000

35 PMEG 2900: a polytetramethylene glycol having a

molecular weight of 2900
PEG: a 1000 molecular weight polyoxyethylene glycol

HD: 1,6-hexane diol

5 GENERAL PROCEDURE

A-Side: Prepolymers were prepared by simultaneously heating (60°C) and degassing a mixture of the diisocyanate and the hydroxyl compound in presence of 0.4% of dibutyltin dilaurate catalyst for 2 hours.

10 Using the above procedure, the prepolymers set forth in Table 1 were produced:

TABLE 1				
	<u>Prepolymer</u>	<u>Isocyanate</u>	<u>Hydroxyl Compound</u>	<u>% NCO</u>
15	A	HMDI	DIOL A	18.5
	B	IPDI	DIOL A	18.1
	C	HDI	DIOL A	18.0
	D	HMDI	DIOL E	18.6
	E	HMDI	DIOL C	18.3
20	F	HMDI	TRIOLE E	18.2
	G	HMDI	TRIOLE C	18.6
	H	HMDI	PMEG 650	18.4
	I	HMDI	PMEG 1000	18.6
	J	HMDI	DIOL B	23.2
25	K	HMDI	DIOL F	18.5
	L	HMDI	DIOL A	18.4
	M	HMDI	DIOL A	18.8
	N	HMDI	DIOL A	18.7
	O	HMDI	DIOL A/ DIOL B (wt. ratio of 8:1)	16.3
30	P	HMDI	PMEG-1000	7.82

B-Side: The B-side was prepared by physically blending two or more hydroxyl compounds and degassing the resulting homogeneous mixture. Depending on the composition of the B-side, the amounts were calculated according to the NCO content of the A-Side

35

at an NCO/OH equivalent ratio of from 1.03:1 to 1.07:1.

Processing: A known weight of Side-A was kept stirred at 32°C in a dry metal can. A calculated amount of Side-B, also at 32°C, was added to it. The mixture was stirred for 30 seconds and poured into a mold preheated to 60°C. The cast part was cured in an oven at 60°C for 20 minutes, demolded, and post cured at ambient temperature in open air for 16 hours, before the Shore A/D hardness (ASTM D-2240) and Bayshore Rebound (ASTM D-3574-H) were checked. Where reported, glass transition temperatures were determined using Differential Scanning Calorimetry.

The formulations used and the results obtained were as indicated in the following table:

	Example	Prepoly- mer	B-Side pbw	Weight Ratio, A:B	Hardness Shore A, Shore D	Rebound Bayshore	Tg. °C
	1	A	53 DIOL A 47 TRIOL B	1:1	65A	14	-11.8
20	2	B	57 DIOL A 43 TRIOL B	1:1	51A	5	-9.6
	3	C	57 DIOL A 43 TRIOL B	1:1	57A	57	--
	4	D	54 DIOL A 46 TRIOL B	1:1	66A	12	--
25	5	E	54 DIOL A 46 TRIOL B	1:1	65A	11	--
	6	F	54 DIOL A 46 TRIOL B	1:1	64A	11	--
	7	G	60 DIOL A 40 TRIOL B	1:1.06	46A	10	--
30	8	H	60 DIOL A 40 TRIOL B	1:1.05	67A	11	--

- 12 -

	9	I	60 DIOL A 40 TRIOL B	1:1.0	63A	9	--
	10	J	31 DIOL A 69 TRIOL B	1:1	73D	53	--
5	11	K	59 DIOL A 10 DIOL B 31 TRIOL B	1:1	56A	7	--
	12	L	69 DIOL D 31 TRIOL B	1:1	72A	19	--
10	13	L	54 PEG 46 TRIOL B	1:1	65A	13	--
	14	M	50 PMEG 1000 50 TRIOL B	1:1	64A	9	-2.2
	15	A	24 DIOL E 24 DIOL A 52 TRIOL B	1:1	72A	20	--
15	16	A	44 DIOL E 56 TRIOL B	1:1	75A	23	--
	17	L	46 PMEG 2000 54 TRIOL B	1:1	70A	15	--
	18	L	44 PMEG 2900 56 TRIOL B	1:1	75A	21	--
20	19	L	42 DIOL C 58 TRIOL B	1:1	86A	28	--
	20	A	42 TRIOL E 58 TRIOL B	1:1	79A	25	--
	21	M	73 DIOL A 27 TRIOL B	1:1	64A	12	--
25	22	M	65 DIOL E 35 TRIOL G	1:1	87A	28	--
	23	M	62 DIOL C 38 TRIOL G	1:1	42D	36	--
	24	M	62 TRIOL E 38 TRIOL G	1:1	45D	39	--
30	25	M	10 DIOL A 90 TRIOL A	1:1	68A	11	-12.1

Mo3343

	26	M	TRIOL D	1:1.68	60A	33	--
	27	L	48 DIOL A 52 TRIOL F	1:2.4	15A	25	--
	28	A	55 DIOL A 5 DIOL B 40 TRIOL B	1:1	60A	8	-9.6
5	29	O	63 DIOL A 37 TRIOL B	1:1	60A	7	--
	30	N	61 DIOL A 39 TRIOL B	1:1.1	58A	7	--
	31	N	39 DIOL A 61 TRIOL A	1:1.2	57A	7	--
10	32	M	28 DIOL A 72 TRIOL A	1:1.1	62A	5	--
	33	M	37 DIOL A 63 TRIOL A	1:1.2	59A	5	--
	34	D	10 DIOL A 90 TRIOL A	1:1	65A	8	--
15	35	E	12 DIOL A 88 TRIOL A	1:1	64A	8	-9.1
	36	F	14 DIOL A 86 TRIOL A	1:1	65A	8	-8.2
	37	P	HD	10:1	62A	13	--

20 Although the invention has been described in detail in the foregoing for the purpose of illustration, it is to be understood that such detail is solely for that purpose and that variations can be made therein by those skilled in the art without departing from the spirit and scope of the invention

25 except as it may be limited by the claims.

- 14 -

The embodiments of the invention in which an exclusive property or privilege is claimed are defined as follows:

1. A solid polyurethane composition having a glass transition temperature of from -20°C to 0°C, having a Bayshore rebound of less than 20,
5 and having a Shore A hardness of less than 80, and being prepared by reacting:
 - a) an isocyanate terminated prepolymer having an isocyanate group content of from about 5 to about 25%, said prepolymer being prepared by reacting:
 - i) a cycloaliphatic diisocyanate with
 - 10 ii) a polyhydroxyl compound selected from the group consisting of
 - 1) diols having molecular weights of from about 450 to about 4000,
 - 2) triols having molecular weights of from about 4000 to about 6000, and
 - 15 3) mixtures thereof, with
 - b) a hydroxyl functional compound selected from the group consisting of
 - i) one or more diols having molecular weights of from 62 to about 1000,
 - 20 ii) one or more triols having molecular weights of from about 500 to about 2000, and
 - iii) a mixture of
 - 1) one or more triols having molecular weights of from more than 300 to about 3000, and
 - 25 2) one or more diols having molecular weights of from about 200 to about 3000,
- with the weight ratio component iii)1) to component iii)2) being from 1:0.1 to 1:3,
- 30 c) no more than 10% by weight based on the weight of component b) of one or more triols having molecular weights of 300 or less,

the isocyanate to hydroxyl equivalent ratio being from 0.95:1 to 1.2:1, and the weight ratio of component a) to component b) being from 10:1 to 1:1.5.

5 2. The composition of Claim 1 wherein said prepolymer has an isocyanate group content of from about 17 to about 20% by weight.

3. The composition of Claim 1 wherein the weight ratio of component a) to component b) is from 1.5:1 to 1:1.5.

10 4. The composition of Claim 3 wherein the weight ratio of component a) to component b) is from 1.2:1 to 1:1.2.

5. The composition of Claim 1 wherein said cycloaliphatic diisocyanate is selected from the group consisting of methylenebis(cyclohexyl isocyanate) and isophorone diisocyanate.

15 6. The composition of Claim 1 wherein said polyhydroxyl compound ii) is selected from the group consisting of

- 1) polyether and polyester diols having molecular weights of from about 450 to about 4000,
- 2) polyether triols having molecular weights of
20 from about 4000 to about 6000, and
- 3) mixtures thereof.