

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 405 937 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
26.07.2006 Bulletin 2006/30

(51) Int Cl.:
D01F 8/14 ^(2006.01) **D01F 11/08** ^(2006.01)
D01D 5/22 ^(2006.01) **D06M 15/53** ^(2006.01)
D06M 15/507 ^(2006.01) **D02G 1/12** ^(2006.01)

(21) Application number: **02705398.2**

(86) International application number:
PCT/JP2002/002694

(22) Date of filing: **20.03.2002**

(87) International publication number:
WO 2002/081794 (17.10.2002 Gazette 2002/42)

(54) **POLYESTER BASED THERMALLY ADHESIVE COMPOSITE SHORT FIBER**

THERMOADHÄSIVE VERBUNDKURZFASER AUF POLYESTERBASIS

FIBRE COURTE POUR COMPOSITE THERMO-ADHESIF A BASE DE POLYESTER

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**

• **TASHIRO, Mikio**
c/o Teijin Limited
Osaka-shi, Osaka 541-0054 (JP)

(30) Priority: **04.04.2001 JP 2001105623**

(74) Representative: **Hallybone, Huw George et al**
Carpmaels and Ransford,
43 Bloomsbury Square
London WC1A 2RA (GB)

(43) Date of publication of application:
07.04.2004 Bulletin 2004/15

(73) Proprietor: **TEIJIN LIMITED**
Osaka-shi
Osaka 541-0054 (JP)

(56) References cited:
EP-A- 0 265 221 **EP-A- 0 336 595**
JP-A- 7 003 534 **JP-A- 7 034 327**
JP-A- 2000 178 827 **JP-A- 2000 226 735**
JP-A- 2001 003 256 **JP-A- 2001 288 682**

(72) Inventors:
• **GODA, Hironori**
c/o Teijin Limited
Matsuyama-shi, Ehime 791-8041 (JP)

EP 1 405 937 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

Technical Field

5 **[0001]** The present invention relates to a polyester-based heat-bonding conjugate staple fibers suitable for bonding a fiber structure such as nonwoven fabric or wadding and to a method for producing the same, in more detail to heat-bonding conjugate staple fibers capable of giving a fiber structure which can thermally be bonded at relatively low temperature and has good dimensional stability and to a method for producing the same.

10 Background Art

[0002] Heretofore, as polyester-based heat-bonding conjugate staple fibers, conjugate fibers comprising a polyalkylene terephthalate such as polyethylene terephthalate as a core component and an amorphous polyester comprising isophthalic acid component, terephthalic acid component, or the like as an acid constituent and not having a crystal-melting point as a sheath component have widely been used, because of being capable of being bonded at relatively low temperature of 120 to 150°C to form a fiber structure without needing a thermal treatment at high temperature.

[0003] However, the polyester-based heat-bonding conjugate fibers can form the fiber structure at the relatively low temperature, but has a problem that the obtained fiber structure has insufficient dimensional stability and is therefore largely deformed, when used under a high temperature atmosphere.

20 **[0004]** The present inventors have tried drawing treatments and thermal treatments at high temperature to solve the problem and improve the dimensional stability of the heat-bonding fibers themselves, but it has been found that the fibers are cohered each other at higher temperature than the glass transition point of the amorphous polyester to make the production of yarns difficult.

[0005] From such the reason, it is the fact that heat-bonding conjugate fibers containing an amorphous polyester, especially an amorphous polyester having a glass transition point of 50 to 100°C, as a heat-bonding component and having excellent dimensional stability have still not been proposed.

Disclosure of the Invention

30 **[0006]** The object of the present invention is to provide polyester-based heat-bonding conjugate staple fibers capable of giving a high grade fiber structure, such as nonwoven fabric or wadding, which can thermally be bonded at relatively low temperature without needing a thermal treatment at high temperature, has good dimensional stability and is hardly deformed, even when used in a high temperature atmosphere, and to provide a method for producing the same.

[0007] The present inventors have found that it is effective for the achievement of the above-described object to use an amorphous polyester having a glass transition point of 50 to 100°C as a heat-bonding component and a polyalkylene terephthalate as a fiber-forming component and select heat-drawing conditions for the fibers, and has thus completed the present invention.

[0008] Namely, the polyester-based heat-bonding conjugate staple fibers of the present invention, enabling the achievement of the above-described object is heat-bonding conjugate staple fibers comprising an amorphous polyester having glass transition point of 50 to 100°C and not having a crystal-melting point as a heat-bonding component and a polyalkylene terephthalate having a melting point of not less than 220°C as a fiber-forming component, characterized by having the number of crimps of 3 to 40 crimps / 25 mm, a crimp percent of 3 to 40%, and a web area shrinkage percent of not more than 20% defined as described below.

45 < Web area shrinkage percentage >

[0009] A card web nonwoven fabric comprising 100% of the heat-bonding conjugate staple fibers and having an area of A_0 and a basis weight of 30 g / m² is left in a hot air dryer maintained at 150°C for two minutes, and then the area A_1 of the nonwoven fabric is measured. The web area shrinkage percentage is determined by the following expression.

$$\text{Web area shrinkage percentage (\%)} = (A_0 - A_1) / A_0 \times 100$$

55 **[0010]** In addition, a method for producing polyester-based heat-bonding conjugate staple fibers as the other object of the present invention, are characterized by melting and conjugationally extruding an amorphous polyester having a glass transition point of 50 to 100°C and not having a crystal-melting point and a polyalkylene terephthalate having a melting point of not less than 220°C, cooling and solidifying the conjugationally extruded fibers, taking off the fibers at

a rate of not more than 1,500 m / minute to form the undrawn conjugate fibers, imparting a polyether polyester block copolymer to the undrawn conjugate fibers in an amount of not less than 0.03 percent by weight on the basis of the weight of the fibers, drawing the undrawn conjugate fibers in a draw ratio of 0.72 to 1.25 times the cold maximum draw ratio at a temperature of T_1 to $(T_2 + 30^\circ\text{C})$, and further crimping the drawn fibers so as to give the number of crimps of 3 to 40 crimps / 25 mm and a crimp percent of 3 to 40%. Herein, T_1 is either higher temperature among the glass transition point of the amorphous polyester and the glass transition point of the polyalkylene terephthalate, and T_2 is the glass transition point of the amorphous polyester.

Best Mode for Carrying Out the Invention

[0011] The fiber-forming component of the polyester-based heat-bonding conjugate staple fibers of the present invention is a polyalkylene terephthalate having a melting point of not less than 220°C . When the melting point of the polyester as the fiber-forming component is less than 220°C , it is not only difficult to stably produce the conjugate fibers, but the stability of the conjugate fibers is also deteriorated on a heat-bonding treatment. The preferable concrete examples of the polyalkylene terephthalate are polyethylene terephthalate and polybutylene terephthalate, and may contain one or more copolymerization components and additives such as a delustering agent, a coloring matter, and a lubricant in small amounts within ranges not deteriorating the characteristics, respectively. Especially, the polyethylene terephthalate is more preferable because of being inexpensive and generally used.

[0012] On the other hand, the amorphous polyester used as the heat-bonding component is a polyester having a glass transition point of 50 to 100°C and not having a crystal-melting point. When the glass transition point of said polyester is less than 50°C , the polyester is not preferable, because the fibers are easily cohered each other, when drawn by the production method described later, and because the conjugate fibers having excellent dimensional stability comprising an area shrinkage percent of not more than 20% can not be obtained. When the glass transition point exceeds 100°C , the polyester is also not preferable, because the thermal bonding property is deteriorated at low temperature of 120 to 150°C .

[0013] The amorphous polyester includes random or block copolymers comprising acid components such as terephthalic acid, isophthalic acid, 2, 6-naphthalene dicarboxylic acid, 5-sodium sulfoisophthalic acid, adipic acid, sebacic acid, azelaic acid, dodecane dicarboxylic acid, and 1,4-cyclohexane dicarboxylic acid, and diols such as ethylene glycol, 1,3-propanediol, 1,4-butanediol, 1,5-pentanediol, 1,6-hexanediol, diethylene glycol, 1,4-cyclohexanediol, and 1,4-cyclohexanedimethanol. Especially, an amorphous copolyester comprising terephthalic acid component, isophthalic acid component, ethylene glycol component and diethylene glycol component is preferable from the points of costs and handleability.

[0014] When the above-described copolyester comprising the terephthalic acid component, the isophthalic acid component, the ethylene glycol component and the diethylene glycol component is used as the heat-bonding component, it is necessary to set the copolymerization ratio so that the glass transition point of the copolyester is included within the above-described range. However, the molar ratio of the terephthalic acid component : the isophthalic acid component is suitably $50 : 50$ to $80 : 20$, and the molar ratio of the ethylene glycol component : the diethylene glycol component may arbitrarily be selected within a range of $0 : 100$ to $100 : 0$.

[0015] When the heat-bonding component occupies all parts or a part of the surfaces of the fibers (preferably not less than 40%, especially not less than 60%, of the surfaces of the fibers) in the polyester-based heat-bonding conjugate staple fibers of the present invention, the polyester-based heat-bonding conjugate staple fibers may be produced in any conjugate form selected from a sheath-core type form, an eccentric sheath-core type form, a side-by-side type form, a sea-island type form, a split type form, and the like. In particular, the sheath-core type form, the eccentric sheath-core type form, and the side-by-side type form are more preferable.

[0016] Next, it is necessary that the number of crimps and the crimp percent of the polyester-based heat-bonding conjugate staple fibers of the present invention are 3 to 40 crimps / 25 mm and 3 to 40%, respectively. When the staple fibers have the number of crimps of less than less than 3 crimps / 25 mm or a crimp percent of less than 3%, the fibers are not preferable, because the degree of entanglement between the staple fibers is insufficient to deteriorate the card passage of the staple fibers, whereby the high grade fiber structure is not obtained. On the other hand, when the staple fibers have the number of crimps of more than 40 crimps / 25 mm or a crimp percent of more than 40%, the fibers are also not preferable, because the degree of entanglement between the staple fibers is too large to sufficiently card the staple fibers, whereby a high grade fiber structure is not obtained. The number of crimps and the crimp percent are more preferably 5 to 30 crimps / 25 mm and 5 to 30%, respectively. The form of the crimps includes mechanical crimps and three-dimensional crimps, and may suitably be selected and set in response to the use or aim of the staple fibers.

[0017] The length and single fiber fineness of the polyester-based heat-bonding conjugate staple fibers do not need to be especially limited, and may suitably be set in response to the use and aim of the staple fibers.

[0018] In the heat-bonding conjugate staple fibers of the present invention, it is important that the web area shrinkage percent defined as described below is not more than 20%. Thereby, said conjugate staple fibers can be processed in

the form of 100% or in the form of a blend with other fibers to obtain a fiber structure having excellent dimensional stability even in high temperature atmosphere. When the shrinkage percent exceeds 20%, the fiber structure having excellent dimensional stability in a high temperature atmosphere can not be obtained. The web area shrinkage percent is more preferably not more than 10%.

< Web area shrinkage percentage >

[0019] A card web nonwoven fabric comprising 100% of the heat-bonding conjugate staple fibers and having an area of A_0 and a basis weight of 30 g / m² is left in a hot air dryer maintained at 150°C for two minutes, and then the area A_1 of the nonwoven fabric is measured. The web area shrinkage percentage is determined by the following expression.

$$\text{Web area shrinkage percentage (\%)} = (A_0 - A_1) / A_0 \times 100$$

[0020] The above-mentioned polyester-based heat-bonding conjugate staple fibers of the present invention can efficiently be produced, for example, by the following method. Namely, the above-mentioned amorphous polyester and the polyalkylene terephthalate are conjugated, preferably conjugated in the form of a sheath-core type, an eccentric sheath-core type, or a side-by-side type, melted and extruded. The extruded fibers are taken off at a speed of less than 1,500 m / minute to obtain the undrawn conjugate fibers. Then, the obtained undrawn conjugate fibers are subjected to the addition of a polyether polyester block copolymer in an amount of not less than 0.03 percent by weight on the basis of the weight of said fibers, drawn in a draw ratio of 0.72 to 1.25 times the cold maximum draw ratio at a temperature of T_1 to ($T_2 + 30^\circ\text{C}$), and further crimped into the crimped fibers having the number of crimps of 3 to 40 crimps / 25 mm and a crimp percent of 3 to 40%, and then cut in a desired length, thus enabling to produce the polyester-based heat-bonding conjugate staple fibers. Herein, T_1 is either higher temperature among the glass transition point of the amorphous polyester and the glass transition point of the polyalkylene terephthalate, and T_2 is the glass transition point of the amorphous polyester.

[0021] A take-off speed exceeding 1,500 m / minute is not preferable, because the web area shrinkage percent can not be reduced to not more than 20%, even when the obtained undrawn conjugate fibers are drawn in the above-described conditions.

[0022] The first point on the above-described production method is to add the polyether polyester block copolymer to the surfaces of the conjugate fibers at a stage before the taken undrawn conjugate fibers are drawn. Thereby, even when the undrawn conjugate fibers are drawn at a temperature not less than the glass transition point T_2 of the amorphous polyester (namely, corresponding to the softening point of the amorphous copolyester), the polyester-based heat-bonding conjugate staple fibers having a web area shrinkage percent of not more than 20% can be obtained without causing cohesion between the fibers in the drawing process, when the drawing temperature is not more than $T_2 + 30^\circ\text{C}$. Further, the fiber structure having excellent mechanical characteristics can be obtained, because the heat-bonding property of the conjugate fibers is not deteriorated so much, even when said polyether polyester block copolymer is applied to the surfaces of the conjugate fibers.

[0023] Such the simultaneous achievements of the cohesion-preventing effect and the heat-bonding property-maintaining effect are impossible with an anionic surfactant or its polyoxyalkylene adduct, a cationic surfactant, a nonionic surfactant, a mineral oil, or the like, which has usually been used as an oiling agent for producing staple fibers, or even with a polysiloxane-based treating agent.

[0024] A preferably used polyether polyester block copolymer includes especially a copolymer comprising terephthalic acid component and isophthalic acid component and / or an alkali metal sulfoisophthalic acid component in a molar ratio of 40 : 60 to 100 : 0 as a dicarboxylic acid component and ethylene glycol as a glycol component and copolymerized with 20 to 95 percent by weight of a polyalkylene glycol having a number-average molecular weight of 600 to 10,000, and the copolymer is especially preferable from the point of the stability of an aqueous emulsion and the point of an cohesion generation-preventing effect in a drawing process. An acid component such as adipic acid, sebacic acid, azelaic acid, dodecane dicarboxylic acid, or 1, 4-cyclohexanedicarboxylic acid and / or a diol component such as 1, 3-propanediol, 1, 4-butanediol, 1, 5-pentanediol, 1, 6-hexanediol, diethylene glycol, 1, 4-cyclohexanediol, or 1, 4-cyclohexane dimethanol may be copolymerized in small amounts. Additionally, in order to adjust the molecular weight, one end of the polyalkylene glycol may be sealed with an ether bond such as a monomethyl ether, a monoethyl ether, or a monophenyl ether. The polyalkylene glycol includes polyethylene glycol, ethylene oxide - propylene oxide copolymer, polypropylene glycol, and polytetramethylene glycol. The polyethylene glycol is especially preferable.

[0025] The number-average molecular weight of the polyether polyester block copolymer is preferable to be in the range of 3,000 to 20,000, because of giving a higher cohesion-preventing effect.

[0026] The amount of the polyether polyester block copolymer adhered to the undrawn fibers is necessary to be not

less than 0.03 percent by weight on the basis of said undrawn fibers. An amount of less than 0.03 percent by weight is not preferable, because a sufficient cohesion-preventing effect is not obtained in the drawing process described later. On the other hand, the cohesion-preventing effect reaches the highest limit and does not increase, even when the adhesion amount is increased. Therefore, an amount of not more than 0.5 percent by weight, especially a range of 0.05 to 0.3 percent by weight, is suitable.

[0027] A method for applying the polyether polyester block copolymer to the surfaces of the undrawn conjugate fibers is especially not limited, and the polyether polyester block copolymer may be applied by an arbitrary conventional known method usually in the form of an aqueous emulsion solution. In order to stabilize said emulsion solution, not only an emulsifier but also additives such as an antistatic agent, a lubricant, a rust-preventing agent, an antifungal agent, and an antibacterial agent may be added.

[0028] Next, the second point on the above-described production method is a drawing temperature. Although it is undoubtedly necessary to set the drawing temperature to a temperature of not less than T_2 (glass transition point of the amorphous copolyester), it is simultaneously needed for the thermal setting of the polyalkylene terephthalate of fiber-forming component to set the drawing temperature to a temperature of not less than the glass transition point of the polyalkylene terephthalate. Even if the above-described polyether polyester block copolymer is preliminarily imparted to the surfaces of the undrawn conjugate fibers, the target heat-bonding conjugate staple fibers having the excellent dimensional stability by the present invention may not be obtained, when the drawing temperature is lower than either one of the glass transition points of the amorphous copolyester and the polyalkylene terephthalate. Further, it is also important not to set the drawing temperature to high temperature exceeding T_2 (glass transition point of the amorphous copolyester) + 30°C. When the drawing temperature exceeds T_2 + 30°C, the cohesion of the amorphous copolyester can sufficiently not be prevented, and the generation of fused fiber bundles and the deterioration in the stability of a crimper on the addition of crimps to the fibers by the use of a push type crimper are caused. Thereby, the drawing temperature exceeding T_2 + 30°C is not preferable.

[0029] When the drawing temperature is included in the above-described range, the above-described drawing may be one step drawing or more step drawing, but it is necessary that the total draw ratio is 0.72 to 1.25 times the cold draw ratio. When the draw ratio is less than 0.72 time the cold draw ratio, the draw ratio is not preferable, because the dimensional stability of the produced fiber structure is deteriorated. When the draw ratio is more than 1.25 times the cold draw ratio, the draw ratio is also not preferable, because the decrease in the heat-bonding property as well as the deterioration in the drawing property are caused. The cold draw ratio of the undrawn fibers is obtained by drawing the undrawn conjugate fibers collected within five minutes from the just spun time at a speed 5 cm / second in an initial chuck length of 10 cm in air having a relative humidity of 65% at 25°C, and then dividing the distance between the initial chuck length and the chuck length at a time when the chuck can not be elongated, by the initial chuck length (10 cm).

[0030] In the present invention, it is effective for the improvement of the dimensional stability and for the prevention of the cohesion that the above-described drawing is carried out in a draw ratio of 0.7 to 1.0 time the cold draw ratio of the undrawn conjugate fibers at a temperature of T_1 (either higher temperature among the glass transition point of the amorphous copolyester and the glass transition point of the polyalkylene terephthalate) to $(T_1 + 10^\circ\text{C})$ and then in a draw ratio of 1.03 to 1.25 at a temperature of $(T_1 + 10^\circ\text{C})$ to $[T_2$ (glass transition point of the amorphous copolyester) + 30°C].

[0031] Additionally, it is especially effective to use hot water as a drawing heating medium.

[0032] The drawn conjugate fibers are crimped in conditions giving the number of crimps of 3 to 40 crimps / 25 mm and a crimp percent of 3 to 40% by a known conventional method, and then cut in a desired length. Namely, when the crimping form is a mechanical crimp form, for example, a stuffing type crimper is used, and the conditions of the stuffing pressure and temperature may suitably be controlled. On the other hand, when the crimping form is a three-dimensional crimp form, the conjugate structures of the conjugate fibers and cooling conditions at the spinning time may suitably be selected.

[0033] The obtained polyester-based heat-bonding conjugate staple fibers of the present invention have good dimensional stability, and are suitable for fiber structures such as nonwoven fabrics or wadding. The heat-bonding conjugate staple fibers may singly be used for the fiber structures such as the nonwoven fabrics, or the heat-bonding conjugate staple fibers as main fibers may be blended with other fibers and then used for the fiber structures such as the nonwoven fabrics.

Examples

[0034] The present invention will be explained more concretely hereafter with examples. Therein, evaluation items in Examples obeyed the following methods.

EP 1 405 937 B1

(a) Glass transition point (T_g), melting point (T_m)

[0035] The glass transition point (T_g) and the melting point (T_m) were measured with a differential scanning calorimeter DSC-7 type manufactured by Perkin-Elmer Inc. at a temperature-rising rate of 20°C / minute.

(b) Intrinsic viscosity ([η]).

[0036] The intrinsic viscosity was measured in ortho-chlorophenol as a solvent at a temperature of 35°C.

(c) Number of crimps, crimp percent

[0037] The number of crimps and the crimp percent were measured by a method described in JIS L 1015 7. 12.

(d) Fineness

[0038] The fineness was measured by a method described in JIS L 1015 7. 5.1 A method.

(e) Fiber length

[0039] The fiber length was measured by a method described in JIS L 1015 7. 4. 1 C method.

(f) Oil pickup

[0040] A value obtained by measuring the weight of residues extracted from fibers with 30°C methanol in a bath ratio of 1: 20 for 10 minutes and then dividing the measured weight by a prescribed fiber weight.

(g) Web area shrinkage percent and deformation of fiber structure

[0041] The area shrinkage percent was determined by forming a card web comprising 100% of the heat-bonding conjugate staple fibers having a basis weight of 30 g / m² and an area A₀ (25 cm × 25cm = 625cm²), leaving the formed card web in a hot air drier (hot air circulation constant-temperature drier : 41-S4, manufactured by Satake Kagaku Kikai Kogyo Kabushiki Kaisha) maintained at 150°C for two minutes, measuring the area A₁ of the thermally treated card web and then applying the area A_i to the following expression. The card web having an area shrinkage percent of not more than 20% was accepted.

$$\text{Area shrinkage percent (\%)} = (625 - A_1) / 625 \times 100$$

(h) Cohesion

[0042] When the cohesion was generated on the drawing of the fibers to make the production impossible or when a cohered bonding was confirmed in the card web, the fibers were judged to be defective, and in other cases, the fibers were judged to be good.

[Example 1]

[0043] Polyethylene terephthalate having an intrinsic viscosity of 0.64, a T_g of 67°C and a T_m of 256°C was used as a fiber-forming component. An amorphous copolyester copolymerized from terephthalic acid component and isophthalic acid component in a molar ratio of 60 : 40 as an acid component and ethylene glycol and diethylene glycol in a molar ratio of 95 : 5 as a diol component, and having an intrinsic viscosity of 0.56 and a T_g of 64°C was used as a heat-bonding component. The pellets of the polymers were vacuum-dried, fed into a sheath-core type conjugate melt-spinning device and melt-spun from a spinneret having 450 spinning nozzles in a conjugate ratio comprising a volume ratio of 50 / 50 at a spinning temperature of 290°C in an extrusion rate of 650 g / minute. The spun fibers were cooled with 30°C cold air, subjected to the adhesion of a treating agent comprising the emulsion of a polyether polyester block copolymer copolymerized from terephthalic acid component and isophthalic acid component in a molar ratio of 80 / 20 as an acid component, ethylene glycol as a glycol component, and polyethylene glycol having a number-average molecular weight of 3,000 and having an average molecular weight of 10,000 in a pure content of 0.1 percent by weight on the basis of

EP 1 405 937 B1

the fibers by the use of an oiling roller, and then taken off at a rate of 900 m / minute to obtain the undrawn sheath-core type conjugate fibers. The cold maximum draw ratio (hereinafter, referred to as CDR) of the undrawn fibers was 4.5.

[0044] The undrawn conjugate fibers were bundled to form the tow of 110,000 dtex (100,000 denier). The tow was first drawn in a draw ratio of 3.5 (0.78 time CDR) in 72°C hot water, further drawn in a draw ratio of 1.15 (total draw ratio is 4.0; 0.89 time CDR) in 80°C hot water, oiled with a spinning oil comprising potassium laurylphosphate, naturally cooled to 35°C, crimped with a stuffing type crimper, and then cut in a fiber length of 51 mm to obtain the heat-bonding conjugate staple fibers having a single fiber fineness of 4.4dtex, the number of crimps of 10 crimps / 25 mm and a crimp percent of 15%.

[Examples 2 to 10, Comparative Examples 1 to 6]

[0045] Heat-bonding conjugate stable fibers having a single fiber fineness of 4.4 dtex, a fiber length of 51 mm, the number of crimps of 10 crimps / 25 mm, and a crimp percent of 15% were obtained in the same conditions as in Example 1 except that the heat-bonding component, the fiber-forming component, the treating agent, the drawing ratio, and the drawing temperature were changed.

[0046] The fiber constitutions, treating agent kinds, spinning and drawing conditions, and fiber evaluation results of the Examples and the Comparative Examples are shown in Tables 1, 2, 3, and 4, respectively.

Table 1

Conjugate Type		F 1	F 2	F3	F 4	F 5	F 6	
# I	Acid Component	T A	60	60	55	70	75	60
		I A	40	40	40	30	25	40
		S A	-	-	5	-	-	-
	Glycol Component	E G	95	100	100	62	44	95
		D E G	5	-	-	8	6	5
		H M G	-	-	-	30	50	-
	T g	°C	64	69	59	55	40	64
	Tm	°C	-	-	-	-	-	-
	[η]		0.56	0.57	0.55	0.56	0.56	0.56
# II	Polymer	PET	PET	PET	PET	PET	PBT	
	T g	°C	67	67	67	67	67	25
	Tm	°C	256	256	256	256	256	228
	[η]		0.64	0.64	0.64	0.64	0.64	0.87
# I : Heat-bonding component # II : Fiber-forming component TA : Terephthalic acid IA : Isophthalic acid SA: Sebacic acid EG : Ethylene glycol DEG : Diethylene glycol HMG : Hexamethylene glycol PET : Polyethylene terephthalate PBT : Polybutylene terephthalate								

Table 2

Treating agent	O 1	O2	O3	O4	O5
Polyether polyester block copolymer component				-	-

EP 1 405 937 B1

(continued)

Treating agent		O 1	O2	O3	O4	O5
Acid component	T A	80	90	72		
	I A	20	10	18		
	S I A	-	-	10		
Glycol component	E G	100	100	100		
Polyalkylene glycol	Type	PEG3000	M-PEG3000	PEG4000		
	C D	70	80	70		
Number-average molecular weight		10000	9000	11000		
Other components		-	-	-	Phosphate 1	Phosphate 2
TA: Terephthalic acid IA : Isophthalic acid SIA : 5-Sodium sulfophthalic acid PEG 3000 : Polyethylene glycol having an average molecular weight of 3000 PEG 4000 : Polyethylene glycol having an average molecular weight of 4000 M-PEG 3000 : Polyethylene glycol monophenyl ether having an average molecular weight of 3000 CD : Copolymerization degree % Phosphate 1 : Potassium lauryl phosphate Phosphate 2 : Partial potassium lauryl phosphate having the average ethylene oxide addition number of five moles.						

Table 3

	Spinning			Drawing				
	# 1	Treating agent	C D R	First step		Second step		Total drawing ratio
				# 2	Ratio /CDR	# 2	Ratio /CDR	Ratio(CDR)
Example 1	F1	O1	4.5	72	0.78	72	1.15	4.00(0.89)
Comparative example 1	F1	O1	4.5	65	0.78	60	1.15	4.00(0.89)
Comparative example 2	F1	O4	4.5	65	0.78	60	1.15	4.00(0.89)
Comparative example 3	F1	O4	4.5	72	0.78	72	1.15	4.00(0.89)
Comparative example 4	F1	O5	4.5	72	0.78	72	1.15	4.00(0.89)
Example 2	F1	O1	4.5	72	0.78	80	1.15	4.00(0.89)
Example 3	F1	O1	4.5	72	0.78	85	1.15	4.00(0.89)
Example 4	F1	O1	4.5	72	0.96	80	1.05	4.54(1.01)
Comparative example 5	F1	O1	4.5	72	0.60	72	1.15	3.10(0.69)
Example 5	F1	O2	4.5	72	0.78	72	1.15	4.00(0.89)
Example 6	F1	O3	4.5	72	0.78	72	1.15	4.00(0.89)
Example 7	F2	O1	4.5	72	0.78	72	1.15	4.00(0.89)
Example 8	F3	O1	4.5	72	0.78	72	1.15	4.00(0.89)
Example 9	F4	O1	4.5	72	0.78	72	1.15	4.00(0.89)

EP 1 405 937 B1

(continued)

	Spinning			Drawing				
	# 1	Treating agent	C D R	First step		Second step		Total drawing ratio
				# 2	Ratio /CDR	# 2	Ratio /CDR	Ratio(CDR)
Comparative example 6	F5	O1	4.5	72	0.78	72	1.15	4.00(0.89)
Example 10	F6	O1	3.8	72	0.78	72	1.15	3.38(0.89)
# 1 : Conjugate type # 2 : Temperature								

Table 4

	Fiber		
	Appearance of Un-cohesion	Web area shrinkage percent (%)	Web grade after shrinkage
Example 1	Good	18.5	Good
Comparative example 1	Good	73.9	Defective
Comparative example 2	Good	55.3	Defective
Comparative example 3	Defective	Could not be drawn	-
Comparative example 4	Defective	Could not be drawn	-
Example 2	Good	8.1	Good
Example 3	Good	5.1	Good
Example 4	Good	6.8	Good
Comparative example 5	Defective	Could not be drawn	-
Example 5	Good	17.5	Good
Example 6	Good	18.1	Good
Example 7	Good	18.3	Good
Example 8	Good	16.3	Good
Example 9	Good	16.1	Good
Comparative example 6	Defective	Could not be drawn	-
Example 10	Good	14.8	Good

Utilization in Industry

[0047] The polyester-based heat-bonding conjugate staple fibers of the present invention can provide high-grade fiber structures which have good dimensional stability and hardly cause deformation, even when used under high temperature atmospheres, although the fiber structures can be formed at relative low temperature. In addition, by the production method of the present invention, the above-described heat-bonding conjugate staple fibers can extremely stably and easily be produced without causing cohesion.

Claims

1. Polyester-based heat-bonding conjugate staple fibers comprising an amorphous polyester having a glass transition point of 50 to 100°C and not having a crystal-melting point as a heat-bonding component and a polyalkylene terephthalate having a melting point of not less than 220°C as a fiber-forming component, **characterized by** having the number of crimps of 3 to 40 crimps / 25 mm, a crimp percent of 3 to 40%, and a web area shrinkage percent of not more than 20% defined as described below.

< Web area shrinkage percentage >

A card web nonwoven fabric comprising 100% of the heat-bonding conjugate staple fibers and having an area of A_0 and a basis weight of 30 g / m² is left in a hot air dryer maintained at 150°C for two minutes, and then the area A_1 of the nonwoven fabric is measured. The web area shrinkage percentage is determined by the following expression.

$$\text{Web area shrinkage percentage (\%)} = (A_0 - A_1) / A_0 \times 100$$

2. The polyester-based heat-bonding conjugate staple fibers according to Claim 1, wherein a polyether polyester block copolymer is applied to the surfaces of the fibers in an amount of not less than 0.03 percent by weight on the basis of the weight of the fibers.
3. The polyester-based heat-bonding conjugate staple fibers according to Claim 1 or 2, wherein the heat-bonding component is an amorphous copolyester comprising isophthalic acid component, terephthalic acid component, ethylene glycol component, and diethylene glycol component.
4. The polyester-based heat-bonding conjugate staple fibers according to Claim 1 or 2, wherein the fiber-forming component is polyethylene terephthalate.
5. A method for producing polyester-based heat-bonding conjugate staple fibers, **characterized by** melting and conjugationally extruding an amorphous polyester having a glass transition point of 50 to 100 °C and not having a crystal-melting point and a polyalkylene terephthalate having a melting point of not less than 220°C, cooling and solidifying the conjugationally extruded fibers, taking off the fibers at a rate of not more than 1,500 m/minute to form the undrawn conjugate fibers, applying a polyether polyester block copolymer to the undrawn conjugate fibers in an amount of not less than 0.03 percent by weight on the basis of the weight of the fibers, drawing the undrawn conjugate fibers in a draw ratio of 0.72 to 1.25 times the cold maximum draw ratio at a temperature of T_1 to ($T_2 + 30^\circ\text{C}$), and further crimping the drawn fibers so as to give the number of crimps of 3 to 40 crimps / 25 mm and a crimp percent of 3 to 40%. Herein, T_1 is either higher temperature among the glass transition point of the amorphous polyester and the glass transition point of the polyalkylene terephthalate, and T_2 is the glass transition point of the amorphous polyester.
6. The method for producing the polyester-based heat-bonding conjugate staple fibers according to Claim 5, wherein the drawing is a two step drawing comprising drawing in a draw ratio of 0.70 to 1.00 time the cold maximum draw ratio at a temperature of T_1 to ($T_1 + 10^\circ\text{C}$) and further in a draw ratio of 1.03 to 1.25 at a temperature of ($T_1 + 10^\circ\text{C}$) to ($T_2 + 30^\circ\text{C}$).
7. The method for producing the polyester-based heat-bonding conjugate staple fibers according to Claim 5 or 6, wherein a heating medium used for the drawing is hot water.
8. The method for producing the polyester-based heat-bonding conjugate staple fibers according to Claim 5 or 6, wherein the polyether polyester block copolymer is a block copolymer comprising terephthalic acid component and isophthalic acid component and / or an alkali metal salt sulfoisophthalic acid component in a molar ratio of 40 : 60 to 100 : 0 as the acid component and ethylene glycol as the glycol component and copolymerized with 20 to 95 percent by weight of a polyalkylene glycol having a number-average molecular weight of 600 to 10,000.

Patentansprüche

1. Durch Wärme verbindende konjugierte Stapelfasern auf Polyesterbasis, umfassend einen amorphen Polyester, der

einen Glasübergangspunkt von 50 bis 100°C und keinen Kristallschmelzpunkt aufweist, als eine durch Wärme verbindende Komponente und ein Polyalkylenterephthalat mit einem Schmelzpunkt von nicht weniger als 220°C als eine Faser-bildende Komponente, **gekennzeichnet durch** die Anzahl von Kräuselungen von 3 bis 40 Kräuselungen/25 mm, einen Kräuselgrad von 3 bis 40% und einen Kardenvlies-Flächenschumpfgrad von nicht mehr als 20%, wie nachstehend definiert.

<Kardenvlies-Flächenschumpfgrad>

Ein Kardenvlies-Vliesstoff, der 100% der **durch** Wärme verbindenden konjugierten Stapelfasern umfasst und eine Fläche von A_0 und ein Basisgewicht von 30 g/m² aufweist, wird in einem Heißlufttrockner, gehalten bei 150°C, für zwei Minuten gelassen, und anschließend wird die Fläche A_1 des Vliesstoffes gemessen. Der Kardenvlies-Flächenschumpfgrad wird **durch** folgenden Ausdruck bestimmt.

$$\text{Kardenvlies-Flächenschumpfgrad (\%)} = (A_0 - A_1) / A_0 \times 100$$

2. **Durch** Wärme verbindende konjugierte Stapelfasern auf Polyester-Basis gemäß Anspruch 1, wobei ein Polyetherpolyester-Blockcopolymer auf die Oberflächen der Fasern in einer Menge von nicht weniger als 0,03 Gew.-%, auf der Basis des Gewichts der Fasern, aufgebracht worden ist.
3. Durch Wärme verbindende konjugierte Stapelfasern auf Polyester-Basis gemäß Anspruch 1 oder 2, wobei die durch Wärme verbindende Komponente ein amorpher Copolyester, umfassend eine Isophthalsäurekomponente, eine Terephthalsäurekomponente, eine Ethylenglykolkomponente und eine Diethylenglykolkomponente, ist.
4. Durch Wärme verbindende konjugierte Stapelfasern auf Polyester-Basis gemäß Anspruch 1 oder 2, wobei die Faserbildende Komponente Polyethylenterephthalat ist.
5. Verfahren zur Herstellung durch Wärme verbindender konjugierter Stapelfasern auf Polyester-Basis, **gekennzeichnet durch** das Schmelzen und konjugierte Extrudieren eines amorphen Polyesters, der einen Glasübergangspunkt von 50 bis 100°C und keinen Kristallschmelzpunkt aufweist, und eines Polyalkylenterephthalats mit einem Schmelzpunkt von nicht weniger als 220°C, das Abkühlen und Verfestigen der konjugiert extrudierten Fasern, das Aufnehmen der Fasern mit einer Geschwindigkeit von nicht mehr als 1.500 m/min unter Bildung der nicht-gestreckten konjugierten Fasern, das Aufbringen eines Polyetherpolyester-Blockcopolymer auf die nicht-gestreckten konjugierten Fasern in einer Menge von nicht weniger als 0,03 Gew.-% auf der Basis des Gewichts der Fasern, das Strecken der nicht-gestreckten konjugierten Fasern in einem Streckverhältnis von dem 0,72 bis 1,25-fachen des maximalen Kaltstreckverhältnisses bei einer Temperatur von T_1 bis $(T_2 + 30^\circ\text{C})$ und weiter das Kräuseln der gestreckten Fasern derart, daß die Anzahl der Kräuselungen 3 bis 40 Kräuselungen/25 mm und einen Kräuselgrad von 3 bis 40% ergibt. Darin ist T_1 die jeweils höhere Temperatur von dem Glasübergangspunkt des amorphen Polyesters und dem Glasübergangspunkt des Polyalkylenterephthalats, und T_2 ist der Glasübergangspunkt des amorphen Polyesters.
6. Verfahren zur Herstellung durch Wärme verbindender konjugierter Stapelfasern auf Polyester-Basis gemäß Anspruch 5, wobei das Strecken ein Zweistufenstrecken ist, umfassend das Strecken in einem Streckverhältnis von dem 0,70 bis 1,00-fachen des maximalen Kaltstreckverhältnisses bei einer Temperatur von T_1 bis $(T_1 + 10^\circ\text{C})$ und weiter in einem Streckverhältnis von 1,03 bis 1,25 bei einer Temperatur von $(T_1 + 10^\circ\text{C})$ bis $(T_2 + 30^\circ\text{C})$.
7. Verfahren zur Herstellung durch Wärme verbindender konjugierter Stapelfasern auf Polyester-Basis gemäß Anspruch 5 oder 6, wobei ein für das Strecken verwendetes Wärmemedium heißes Wasser ist.
8. Verfahren zur Herstellung durch Wärme verbindender konjugierter Stapelfasern auf Polyester-Basis gemäß Anspruch 5 oder 6, wobei das Polyetherpolyester-Blockcopolymer ein Blockcopolymer ist, umfassend eine Terephthalsäurekomponente und eine Isophthalsäurekomponente und/oder eine Alkalimetallsalz-Sulfoisophthalsäurekomponente in einem Molverhältnis von 40:60 bis 100:0 als die Säurekomponente und Ethylenglykol als die Glykolkomponente und copolymerisiert mit 20 bis 95 Gew.-% eines Polyalkylenglykols mit einem zahlenmittleren Molekulargewicht von 600 bis 10.000.

Revendications

1. Fibres coupées conjuguées pour thermoliage à base de polyester, comprenant en tant que composant de thermoliage

EP 1 405 937 B1

un polyester amorphe ayant une température de transition vitreuse de 50 à 100°C et n'ayant pas de point de fusion cristalline, et en tant que composant fibrogène un poly(téréphtalate d'alkylène) ayant un point de fusion d'au moins 220°C, **caractérisées en ce qu'**elles présentent un nombre de frisures de 3 à 40 frisures/25 mm, un taux de frisure de 3 à 40 %, et un taux de rétraction de l'aire du voile d'au plus 20 %, tel que défini comme décrit ci-dessous :

taux de rétraction de l'aire du voile : un tissu non tissé formant voile de carte, comprenant 100 % des fibres coupées conjuguées de thermoliage et ayant une aire de A_0 et une masse surfacique de 30 g/m², est abandonné pendant deux minutes dans un séchoir à air chaud maintenu à 150°C, puis on mesure l'aire A_1 du tissu non tissé. Le taux de rétraction de l'aire du voile est déterminé par l'expression suivante :

$$\text{taux de rétraction de l'aire du voile (\%)} = (A_0 - A_1) / A_0 \times 100.$$

2. Fibres coupées conjuguées pour thermoliage à base de polyester selon la revendication 1, dans lesquelles un copolymère séquencé polyéther-polyester est déposé sur les surfaces des fibres à raison d'au moins 0,03 % en poids par rapport au poids des fibres.
3. Fibres coupées conjuguées pour thermoliage à base de polyester selon la revendication 1 ou 2, dans lesquelles le composant de thermoliage est un copolyester amorphe comprenant un composant acide isophtalique, un composant acide téréphtalique, un composant éthylèneglycol et un composant diéthylèneglycol.
4. Fibres coupées conjuguées pour thermoliage à base de polyester selon la revendication 1 ou 2, dans lesquelles le composant fibrogène est le poly(téréphtalate d'éthylène).
5. Procédé de production de fibres coupées conjuguées pour thermoliage à base de polyester, **caractérisé par** la fusion et l'extrusion conjuguée d'un polyester amorphe ayant une température de transition vitreuse de 50 à 100°C et n'ayant pas de point de fusion cristalline, et d'un poly(téréphtalate d'alkylène) ayant un point de fusion d'au moins 220°C, le refroidissement et la solidification des fibres extrudées de façon conjuguée, l'étirage des fibres à une vitesse d'au plus 1500 m/min pour former les fibres conjuguées non étirées, l'application d'un copolymère séquencé polyéther-polyester sur les fibres conjuguées non étirées à raison d'au moins 0,03 % en poids par rapport au poids des fibres, l'étirage des fibres conjuguées non étirées selon un taux d'étirage de 0,72 à 1,25 fois le taux d'étirage maximal à froid à une température comprise entre T_1 et ($T_2 + 30^\circ\text{C}$), et un frisage ultérieur des fibres étirées de façon à arriver à un nombre de frisures de 3 à 40 frisures/25 mm et à un taux de frisure de 3 à 40 %. Ici, T_1 est la température la plus élevée parmi la température de transition vitreuse du polyester amorphe et la température de transition vitreuse du poly(téréphtalate d'éthylène), et T_2 est la température de transition vitreuse du polyester amorphe.
6. Procédé de production des fibres coupées conjuguées pour thermoliage à base de polyester selon la revendication 5, dans lequel l'étirage est un étirage en deux étapes, comprenant un étirage à un taux d'étirage de 0,70 à 1,00 fois le taux d'étirage maximal à froid à une température de T_1 à ($T_1 + 10^\circ\text{C}$), puis à un taux d'étirage de 1,03 à 1,25 à une température comprise entre ($T_1 + 10^\circ\text{C}$) et ($T_2 + 30^\circ\text{C}$).
7. Procédé de production des fibres coupées conjuguées pour thermoliage à base de polyester selon la revendication 5 ou 6, dans lequel le fluide chauffant utilisé pour l'étirage est l'eau chaude.
8. Procédé de production des fibres coupées conjuguées pour thermoliage à base de polyester selon la revendication 5 ou 6, dans lequel le copolymère séquencé polyéther-polyester est un copolymère séquencé comprenant, en tant que composant acide, un composant acide téréphtalique et un composant acide isophtalique et/ou un composant sel d'un métal alcalin de l'acide sulfoisophtalique selon un rapport en moles de 40:60 à 100:0, et de l'éthylèneglycol en tant que composant glycol, et copolymérisé avec 20 à 95 %s en poids d'un polyalkylèneglycol ayant une masse moléculaire moyenne en nombre de 600 à 10 000.