



(51) International Patent Classification:

CI0M 133/22 (2006.01)

(21) International Application Number:

PCT/EP2021/059083

(22) International Filing Date:

07 April 2021 (07.04.2021)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

20315180.8 16 April 2020 (16.04.2020) EP

(71) Applicant: TOTAL MARKETING SERVICES

[FR/FR]; 24 Cours Michelet, 92800 PUTEAUX (FR).

(72) Inventors: DE FEO, Modestino; Total Marketing Services

Centre de recherche de Solaize, Chemin du canal - BP 22, 69360 SOLAIZE (FR). PICHON, Vanessa; Total Marketing Services Centre de recherche de Solaize, Chemin du canal - BP 22, 69360 SOLAIZE (FR). SCHUBERT, Thomas; Servianstrasse 23, 74206 Bad Wimpfen (DE). ILIEV, Boyan; Pappelweg 6, 74081 Heilbronn (DE).

(74) Agent: CORIZZI, Valérie; PACT-IP, 37 rue Royale,

92210 SAINT-CLOUD (FR).

(81) Designated States (unless otherwise indicated, for every

kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, IT, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, WS, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every

kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

— of inventorship (Rule 4.17(iv))

Published:

— with international search report (Art. 21(3))

(54) Title: A GUANIDINIUM-BASED IONIC LIQUID AND ITS USE AS A LUBRICANT ADDITIVE

(57) Abstract: A guanidinium-based ionic liquid compound comprising a 1, 1,3,3- tetramethylguanidinium cation and an alcoholate anion. A lubricant composition comprising it, and its use as a detergent and as anti-corrosion additive in a lubricant composition, in particular a marine lubricant.



A GUANIDINIUM-BASED IONIC LIQUID AND ITS USE AS A LUBRICANT ADDITIVE

Field of the Invention

5 The invention relates to a guanidinium-based ionic liquid. In particular, the invention relates to a guanidinium-based ionic liquid that can be used as detergent in a lubricant composition, in particular for marine engines. It is also directed to a lubricant composition for marine engines comprising said guanidinium-based ionic liquid.

10 Background of the Invention

One of the primary functions of lubricants is to decrease friction. Frequently, however, lubricating oils need additional properties to be used effectively. For example, lubricants used in large diesel engines, such as, for example, marine diesel engines, are often subjected to operating conditions requiring special considerations.

15 The marine oils used in low-speed two-stroke crosshead engines are of two types. On the one hand, cylinder oils ensuring the lubrication of the cylinder-piston assembly and, on the other hand, system oils ensuring the lubrication of all the moving parts apart from the cylinder-piston assembly. Within the cylinder-piston assembly, the combustion residues containing acid gases are in contact with the lubricating oil.

20 The acid gases are formed from the combustion of the fuel oils; these are in particular sulphur oxides (SO_2 , SO_3), which are then hydrolyzed in contact with the moisture present in the combustion gases and/or in the oil. This hydrolysis generates sulphurous (HSO_3) or sulphuric (H_2SO_4) acid. These acids tend to condense in the engine, so it can corrode the metal or wipe out major parts such as joints or lining parts.

25 To protect the surface of piston liners and avoid excessive corrosive wear, these acids must be neutralized, which is generally done by reaction with the basic sites included in the lubricant.

30 An oil's neutralization capacity is measured by its BN or Base Number, characterized by its basicity. It is measured according to standard ASTM D-2896 and is expressed as an equivalent in milligrams of potash per gram of oil (also called "mg of KOH/g" or "BN point"). The BN is a standard criterion making it possible to adjust the basicity of the cylinder oils to the sulphur content of the fuel oil used, in order to

be able to neutralize all of the sulphur contained in the fuel, and capable of being converted to sulphuric acid by combustion and hydrolysis.

Thus, the higher the sulphur content of a fuel oil, the higher the BN of a marine oil needs to be. This is why marine oils with a BN varying from 5 to 140 mg KOH/g are found on the market.

This basicity is generally provided by detergents that are neutral and/or overbased by insoluble metallic salts, in particular metallic carbonates. The detergents, mainly of anionic type, are for example metallic soaps of salicylate, phenate, sulphonate, carboxylate type etc, which form micelles where the particles of insoluble metallic salts are maintained in suspension. The usual neutral detergents intrinsically have a BN typically less than 150 mg KOH per gram of detergent and the usual overbased detergents intrinsically have a BN in a standard fashion comprised between 150 and 700 mg KOH per gram of detergent. Their percentage by mass in the lubricant is fixed as a function of the desired BN level.

Currently, in the presence of fuel oils with a high sulphur content (3.5% w/w and less), marine lubricants having a BN from 70 to 140 are used. In the presence of fuel oils with a low sulphur content (0.5% w/w), marine lubricants having a BN from 10 to 70 are used. In these two cases, a sufficient neutralizing capacity is achieved as the necessary concentration in basic sites provided by the neutral and/or the overbased detergents of the marine lubricant is reached.

There is a need for a marine detergent, which is able to be used in presence of high-sulphur fuels and also low-sulphur fuels and having a good neutralization capacity of sulfuric acid while maintaining a good thermal resistance and thus a lower risk of deposits formation in the hot section of the engine.

There is also a need for a marine detergent, which is able to be used in presence of high-sulphur fuels and also low-sulphur fuels and having good anti-corrosion properties.

There is a need for a marine detergent, which is able to be used in presence of high-sulphur fuels and also low-sulphur fuels, respectively having a BN from 70 to 140 and having a BN from 10 to 70, and having a good neutralization capacity of sulfuric acid while maintaining a good thermal resistance and thus a lower risk of deposits formation in the hot section of the engine.

There is a need for a marine detergent, which is able to be used in presence of high-sulphur fuels and also low-sulphur fuels, respectively having a BN from 70 to 140 and having a BN from 10 to 70, and having good anti-corrosion properties.

5 There is also a need for marine lubricants having improved detergency properties: the capacity to keep the engine clean by limiting deposits ("keep-clean" effect) or by reducing the deposits already present in the internal parts of the combustion engine ("clean-up" effect).

10 An object of the present invention is to provide a lubricant additive overcoming all or part of the aforementioned drawbacks. Another object of the present invention is to provide a lubricant additive whose formulation within lubricant compositions is easy to implement.

Another object of the present invention is to provide a method for lubricating a marine engine, and especially for lubricating a two-stroke marine engine and which can be used with both low-sulphur fuel and high-sulphur fuel.

15 Another object of the present invention is to provide a method for lubricating a marine engine, and especially for a two-stroke marine engine used with very low-sulphur fuel.

20 Another object of the present invention is to provide a method for reducing the formation of deposits in the hot section of a marine engine, notably of a two-stroke marine engine.


WO 02/48212 discloses the use of poly-alpha-olefin-guanidinopolyoxyalkylated compounds as fuel and lubricant additives.

25 Surprisingly, the Applicant has discovered that guanidinium-based ionic liquids of formula (I) described here-under have noteworthy properties as detergent additives in lubricant composition for marine engines, particularly for two-stroke marine engines. The ionic liquids used according to the invention in these lubricant compositions can keep the engine clean, in particular by limiting or preventing the formation of deposits ("keep-clean" effect) or by reducing the deposits already present in the internal parts of the combustion engine ("clean-up" effect).

30 The applicant also discovered that guanidinium-based ionic liquids of formula (I) described here-under have noteworthy properties as anti-corrosive additives in lubricant composition for marine engines, particularly for two-stroke marine engines.


Summary of the Invention

The invention is directed to a guanidinium-based ionic liquid compound of formula (I)



wherein $[\text{CAT}^+]$ represents 1,1,3,3-tetramethylguanidinium,


5 and $[\text{X}^-]$ represents one or more species selected from compounds of formula (II):



wherein

- A represents an aryl group comprising from 6 to 12 carbon atoms;
- 10 - R is selected from the group consisting of hydrogen, linear or branched, alkyl or alkenyl groups comprising from 1 to 30 carbon atoms, aryl groups comprising from 6 to 30 carbon atoms;
- Y represents a linear or branched alkanediyl group comprising from 1 to 6 carbon atoms; and
- 15 - n represents an integer from 1 to 20.

According to a favourite variant, $[\text{X}^-]$ responds to formula (IIA):



wherein

- 20 - R is selected from the group consisting of hydrogen, linear or branched, alkyl or alkenyl groups comprising from 1 to 30 carbon atoms, aryl groups comprising from 6 to 30 carbon atoms; R can be in ortho, para or meta position;
- Y is a linear or branched alkanediyl group comprising from 1 to 6 carbon atoms; and
- 25 - n is an integer from 1 to 15, preferably from 1 to 12.


Advantageously, in formula (IIA), R is selected from the group consisting of hydrogen, linear or branched, alkyl or alkenyl groups comprising from 1 to 30,

preferably from 1 to 18, more preferably from 1 to 12 carbon atoms, R being in ortho, para or meta position.

More advantageously, in formula (IIA), R represents a linear or branched alkyl group comprising from 1 to 12 carbon atoms, R being in para position.

According to a favourite variant, Y is a linear or branched alkanediyl group comprising from 1 to 3 carbon atoms, preferably Y is $-\text{CH}_2-\text{CH}_2-$.

According to a favourite embodiment, $[\text{X}^-]$ responds to formula (IIB):



wherein n is comprised between 4 and 10.

Advantageously, $[\text{X}^-]$ is tert-octylphenylpolyethoxyethanolate with $n = 8$ or 9 .

The invention is also directed to a lubricant composition comprising:

- from 30.0 to 99.95 % of at least one base oil,
- from 0.05 to 15.0 % of at least one guanidinium-based ionic liquid as defined above,

the percentages being defined by weight of component as compared to the total weight of the composition.

According to a favourite embodiment, the lubricant composition comprises at least one detergent selected from neutral and overbased detergents, other than the ionic liquid, having a Total Base Number according to ASTM D2896 of from 20 to 450 mg KOH/g.

According to this favourite embodiment, the lubricant composition advantageously comprises from 1 to 35% weight of neutral and overbased detergents,

other than the ionic liquid, with regards to the total weight of the lubricant composition.

5 According to another favourite embodiment, the percentage by weight of guanidinium-based ionic liquid of formula (I), as defined above, relative to the total weight of lubricant composition is chosen such that the BN provided by the guanidinium-based ionic liquid represents at least 3% of the total BN of said lubricant composition.

10 According to another favourite embodiment, the lubricant composition has a Total Base Number (TBN) value according to ASTM D2896 of above 5 mg KOH/g.

15 The invention is also directed to the use of the guanidinium-based ionic liquid of formula (I) as defined above as detergent in a lubricant composition, notably a marine lubricant, to reduce and/or limit and/or prevent and/or delay the formation of deposits or to reduce the deposits already present in the internal parts of a combustion engine.

20 The invention is also directed to the use of the guanidinium-based ionic liquid of formula (I) as defined above as anti-corrosion additive in a lubricant composition, notably a marine lubricant.

25 The invention is also directed to a method for lubricating a two-stroke marine engine and four-stroke marine engines, preferably two-stroke marine engine, said method comprising application to said marine engine of the guanidinium-based ionic liquid of formula (I) or the lubricant composition as defined above.

30 The guanidinium-based ionic liquid of formula (I) defined above and hereunder greatly improves the detergency properties of a lubricant composition.

The guanidinium-based ionic liquid of formula (I) defined above and hereunder allows keeping clean and cleaning up internal parts of engines in a very efficient way.

Detailed Description of the Invention

The term "consists essentially of" followed by one or more characteristics, means that may be included in the process or the material of the invention, besides explicitly listed components or steps, components or steps that do not materially affect the properties and characteristics of the invention.

The expression "comprised between X and Y" includes boundaries, unless explicitly stated otherwise. This expression means that the target range includes the X and Y values, and all values from X to Y.

A "ionic liquid" is a salt in the liquid state with organic or inorganic cations and anions. Generally ionic liquids have a melting point below 100°C.

"Alkyl" means a saturated hydrocarbyl chain, that can be linear, branched or cyclic.

"Alkenyl" means a hydrocarbyl chain, that can be linear, branched or cyclic and comprises at least one unsaturation, preferably a carbon-carbon double bond.

"Aryl" means an aromatic hydrocarbyl functional group. This functional group can be monocyclic or polycyclic. As examples of an aryl group one can mention: phenyl, naphthalen, anthracen, phenanthren and tetracen.

"Aralkyl" means a hydrocarbyl radical comprising an aromatic hydrocarbon functional group, preferably monocyclic, linked to an alkyl chain, the aralkyl group can be linked to the rest of the molecule through the aryl or the alkyl part of the radical.


"Hydrocarbyl" means a compound or fragment of a compound selected from: an alkyl, an alkenyl, an aryl, an aralkyl. Where indicated, some hydrocarbyl groups include heteroatoms.

"alkanediyl" means a divalent radical derived from aliphatic hydrocarbons by removal of two hydrogen atoms on distinct carbon atoms. Unless specified otherwise, such alkanediyl include substituted alkanediyl.


The guanidinium-based ionic liquid

Ionic liquids are organic salts composed of organic cations and either organic or inorganic anions. The cation and anion can be varied to obtain an ionic liquid with the desired properties. According to the invention, the guanidinium-based ionic liquid, is a salt of a guanidinium cation with an organic anion.

The guanidinium-based ionic liquid is selected from compounds of formula (I):




wherein $[\text{CAT}^+]$ represents 1,1,3,3-tetramethylguanidinium of formula (Ia)



5 and $[\text{X}^-]$ represents one or more anionic species.

Preferably, in formula (I), $[\text{X}^-]$ represents a counter-ion selected from compounds of formula (II):



wherein


- 10 - A represents an aryl group comprising from 6 to 12 carbon atoms;
 - R is selected from the group consisting of hydrogen, linear or branched alkyl or alkenyl groups comprising from 1 to 30 carbon atoms and aryl groups comprising from 6 to 30 carbon atoms;
 - Y represents a linear or branched alkanediyl group comprising from 1 to 6
 15 carbon atoms; and
 - n represents an integer from 1 to 20.

The A group:

In formula (II), A represents an aryl group comprising from 6 to 12 carbon atoms.

20 For example, A can represent a phenyl or a naphthyl group.

According to a favourite embodiment, A represents a phenyl group and the counter-ion $[\text{X}^-]$ responds to formula (IIA):



The R group:

The group R is selected from the group consisting of hydrogen, linear or branched alkyl or alkenyl groups comprising from 1 to 30 carbon atoms and aryl groups comprising from 6 to 30 carbon atoms.

- 5 Preferably, R is selected from the group consisting of hydrogen, linear or branched alkyl or alkenyl groups comprising from 1 to 30, preferably from 1 to 24, more preferably from 1 to 18 carbon atoms.

According to an embodiment, R is chosen such that the total number of carbon atoms of the groups A and R is inferior or equal to 30, preferably, inferior or equal to
10 24, more preferably, inferior or equal to 20.

More preferably, R represents a linear or branched alkyl group comprising from 1 to 18, preferably from 1 to 12 carbon atoms.

For example, and without being limitative, R can be chosen amongst the group consisting of isopropyl, n-propyl, iso-butyl, tert-butyl, n-butyl, tert-pentyl, n-pentyl, n-
15 hexyl, tert-hexyl, n-heptyl, tert-heptyl, n-octyle, tert-octyl, 2-ethyl hexyl, n-nonyl, tert-nonyl and dodecyl.

In formula (IIA), the group R may be in para, ortho or meta position.

According to a favourite embodiment, in formula (IIA), R is in the para position.

The Y group:

- 20 In formula (II), Y represents a linear or branched alkanediyl group comprising from 1 to 6, preferably from 1 to 3 carbon atoms.

For example, Y can be selected from the group consisting of -CH₂-, -CH₂-CH₂-, -CH(CH₃)-CH₂-, -CH₂-CH₂-CH₂-.

Advantageously, Y represents -CH₂-CH₂-.

- 25 ***The integer n:***


In formula (II), n represents an integer from 1 to 20. Preferably, n represents an integer from 1 to 15, more preferably, from 1 to 12.

Advantageously, in formula (II), n represents an integer from 4 to 12, preferably from 6 to 10.

- 30 More advantageously, the integer n and the group Y as defined above are chosen such that they form together a polyalkoxy chain wherein the total number of carbon atoms is inferior or equal to 40, preferably inferior or equal to 30.

Even more advantageously, the integer n and the group Y as defined above are chosen such that they form together a polyalkoxy chain having an average molecular weight comprised between 200 and 600 g mol⁻¹, preferably between 300 and 500 g mol⁻¹.

- 5 According to a favourite embodiment, the counter-ion $[X^-]$ responds to the formula (IIB):



wherein n is comprised between 6 and 10.

- 10 According to a more favourite embodiment, $[X^-]$ is tert-octylphenylpolyethoxyethanolate of formula (IIB) wherein $n = 8$ to 9.

The molecules of formulae (I) and (II) can be prepared by any method known to the skilled professional, as illustrated for example in M. G. Bogdanov et al., Z. Naturforsch. 2010, 65b, 37 – 48; Y. Gao et al., Inorg. Chem. 2005, 44, 1704-1712. An example synthesis is disclosed in the experimental part.

- 15 In order to be used in a lubricant composition, the guanidinium-based ionic liquid must preferably be soluble in the base oil which represents the major part of the lubricant composition. A compound is oil-soluble when it can be solubilized at a concentration of at least 0.01 % by weight with regards to the weight of a base oil, at room temperature. In order to check that the guanidinium-based ionic liquid is oil-
- 20 soluble, a test is disclosed in the experimental part.

- Advantageously, the percentage by weight of guanidinium-based ionic liquid of formula (I) relative to the total weight of lubricant composition is chosen such that the BN provided by these compounds represents a contribution of at least 0.5 milligrams of potash per gram of lubricant, preferably at least 2 milligrams of potash per gram, more preferably at least 3 milligrams of potash per gram, still more preferably from 3
- 25 to 40 milligrams of potash per gram of lubricant, to the total BN of said lubricant composition.

Advantageously, the percentage by weight of guanidinium-based ionic liquid relative to the total weight of lubricant composition is chosen such that the BN

provided by the oil-soluble guanidinium-based ionic liquid represents at least 3%, preferably at least 5%, preferably from 10 to 50% of the total BN of said lubricant composition.

5 In a preferred embodiment of the invention, the weight percentage of guanidinium-based ionic liquid of formula (I) as described above relative to the total weight of the lubricant composition ranges from 0.05 to 15%, preferably from 0.1 to 12%, advantageously from 0.5 to 10%, even more preferably from 1 to 8%.

Lubricant composition

10 The invention is also directed to the use of the guanidinium-based ionic liquids that have been above disclosed as additives in lubricating oil (or lubricant) compositions.

The invention is further directed to some lubricant compositions for two stroke and four stroke marine engines comprising such additives.

15 Advantageously, the lubricant composition comprises, preferably consists essentially of:

- from 30.0 to 99.95 % of at least one base oil,
- from 0.05 to 15.0 % of at least one guanidinium-based ionic liquid of formula (I) as defined above

20 the percentages being defined by weight of component as compared to the total weight of the composition.

Even more advantageously, the lubricant composition comprises, preferably consists essentially of:

- from 50.0 to 99.0 % of at least one base oil
- 25 • from 1.0 to 10.0 % of at least one guanidinium-based ionic liquid of formula (I) as defined above

the percentages being defined by weight of component as compared to the total weight of the composition.

30 According to another favourite embodiment, the invention is directed to a lubricant composition comprising, preferably consisting essentially of:

- at least one base oil,
- at least one guanidinium-based ionic liquid compound of formula (I) as defined above

• at least one detergent selected from neutral and overbased detergents having a Total Base Number according to ASTM D2896 of from 20 to 450 mg KOH/g.

Advantageously, according to this embodiment, the lubricant composition comprises, preferably consists essentially of:

- 5 • from 30.0 to 94.0 % of at least one base oil,
 • from 0.05 to 15 % of at least one guanidinium-based ionic liquid of formula (I) as defined above,

- from 1 to 35 % of at least one detergent selected from neutral and overbased detergents having a Total Base Number according to ASTM D2896 of from 20 to 450
10 mg KOH/g

the percentages being defined by weight of component as compared to the total weight of the composition.

Advantageously, the lubricant composition comprises, preferably consists essentially of:

- 15 • from 50 to 90 % of at least one base oil,
 • from 1 to 10 % of at least one guanidinium-based ionic liquid of formula (I) as defined above,

- from 5 to 35 % at least one detergent selected from neutral and overbased detergents having a Total Base Number according to ASTM D2896 of from 20 to 450,
20 the percentages being defined by weight of component as compared to the total weight of the composition.

Base oils

Generally, the lubricating oil compositions according to the invention comprise
25 as a first component an oil of lubricating viscosity, also called “base oils”. The base oil for use herein can be any presently known or later-discovered oil of lubricating viscosity used in formulating lubricating oil compositions for any of the following applications, e.g., engine oils, marine cylinder oils, functional fluids such as hydraulic oils, gear oils, transmission fluids, like for example automatic transmission fluids,
30 turbine lubricants, trunk piston engine oils, compressor lubricants, metal-working lubricants, and other lubricating oil and grease compositions.

Advantageously, the lubricant compositions according to the invention are marine engine lubricating oil compositions, preferably they are two-stroke marine engine lubricating oil compositions.

5 Generally, the oils also called “base oils” used for formulating lubricant compositions according to the present invention may be oils of mineral, synthetic or plant origin as well as their mixtures. The mineral or synthetic oils generally used in the application belong to one of the classes defined in the API classification as summarized below:

	Saturated substance content (weight percent)	Sulfur content (weight percent)	Viscosity Index
Group 1 Mineral oils	<90%	>0.03%	$80 \leq VI < 120$
Group 2 Hydrocracked oils	$\geq 90\%$	$\leq 0.03\%$	$80 \leq VI < 120$
Group 3 Hydroisomerized oils	$\geq 90\%$	$\leq 0.03\%$	≥ 120
Group 4	PAOs		
Group 5	Other bases not included in the base Groups 1 to 4		

10 These mineral oils of Group 1 may be obtained by distillation of selected naphthenic or paraffinic crude oils followed by purification of these distillates by methods such as solvent extraction, solvent or catalytic dewaxing, hydrotreating or hydrogenation.

15 The oils of Groups 2 and 3 are obtained by more severe purification methods, for example a combination of hydrotreating, hydrocracking, hydrogenation and catalytic dewaxing. Examples of synthetic bases of Groups 4 and 5 include poly-alpha olefins, polybutenes, polyisobutenes, alkylbenzenes.

These base oils may be used alone or as a mixture. A mineral oil may be combined with a synthetic oil.

20 The lubricant compositions of the invention have a viscosity grade of SAE-20, SAE-30, SAE-40, SAE-50 or SAE-60 according to the SAEJ300 classification.

Grade 20 oils have a kinematic viscosity at 100°C of between 5.6 and 9.3 mm²/s.

Grade 30 oils have a kinematic viscosity at 100°C of between 9.3 and 12.5 mm²/s.

Grade 40 oils have a kinematic viscosity at 100°C of between 12.5 and 16.3 mm²/s.

5 Grade 50 oils have a kinematic viscosity at 100°C of between 16.3 and 21.9 mm²/s.

Grade 60 oils have a kinematic viscosity at 100°C of between 21.9 and 26.1 mm²/s.

Preferably, the lubricant composition is a cylinder lubricant.

10 Advantageously, the quantity of base oil in the lubricant composition of the invention is from 30% to 99.95% by weight relative to the total weight of the lubricant composition, preferably from 40% to 99%, more preferably from 50% to 94%.

Detergents

15 The guanidinium-based ionic liquids of formula (I) as defined above play the role of detergent in the lubricant composition. They have the advantage of permitting the use of lower amounts of metal detergents. Therefore, the ionic liquids used according to the invention give access to compositions which have the capacity to neutralize low-sulfur fuel compositions and high-sulfur fuel compositions, but in both
20 cases they avoid the formation of deposits. According to the invention, the guanidinium-based ionic liquids of the invention are preferentially used in combination with at least one detergent that does not belong to the class of ionic liquids, preferably at least one metal detergent.

25 Detergents, other than the guanidinium-based ionic liquids of formula (I), are typically anionic compounds containing a long lipophilic hydrocarbon chain and a hydrophilic head, wherein the associated cation is typically a metal cation of an alkali metal or alkaline earth metal. The detergents are preferably selected from alkali metal salts or alkaline earth metal (particularly preferably calcium, magnesium, sodium or barium) salts of carboxylic acids, sulphonates, salicylates, naphthenates, as well as the
30 salts of phenates. These metal salts may contain the metal in an approximately stoichiometric amount relative to the anion group(s) of the detergent. In this case, one refers to non-overbased or "neutral" detergents, although they also contribute to a certain basicity. These "neutral" detergents typically have a BN measured according to

ASTM D2896, of less than 150 mg KOH/g, or less than 100 mg KOH/g, or less than 80 mg KOH/g of detergent. This type of so-called neutral detergent may contribute in part to the BN of lubricating compositions. For example, neutral detergents are used such as carboxylates, sulphonates, salicylates, phenates, naphthenates of the alkali and alkaline earth metals, for example calcium, sodium, magnesium, barium. When the metal is in excess (amount greater than the stoichiometric amount relative to the anion groups(s) of the detergent), then these are so-called overbased detergents. Their BN is high, higher than 150 mg KOH/g of detergent, typically from 200 to 700 mg KOH/g of detergent, preferably from 250 to 450 mg KOH/g of detergent. The metal in excess providing the character of an overbased detergent is in the form of insoluble metal salts in oil, for example carbonate, hydroxide, oxalate, acetate, glutamate, preferably carbonate. In one overbased detergent, the metals of these insoluble salts may be the same as, or different from, those of the oil soluble detergents. They are preferably selected from calcium, magnesium, sodium or barium. The overbased detergents are thus in the form of micelles composed of insoluble metal salts that are maintained in suspension in the lubricating composition by the detergents in the form of soluble metal salts in the oil. These micelles may contain one or more types of insoluble metal salts, stabilised by one or more types of detergent. The overbased detergents comprising a single type of detergent-soluble metal salt are generally named according to the nature of the hydrophobic chain of the latter detergent. Thus, they will be called a phenate, salicylate, sulphonate, naphthenate type when the detergent is respectively a phenate, salicylate, sulphonate or naphthenate. The overbased detergents are called mixed type if the micelles comprise several types of detergents, which are different from one another by the nature of their hydrophobic chain. The overbased detergent and the neutral detergent may be selected from carboxylates, sulphonates, salicylates, naphthenates, phenates and mixed detergents combining at least two of these types of detergents. The overbased detergent and the neutral detergent include compounds based on metals selected from calcium, magnesium, sodium or barium, preferably calcium or magnesium. The overbased detergent may be overbased by metal insoluble salts selected from the group of carbonates of alkali and alkaline earth metals, preferably calcium carbonate. The lubricating composition may comprise at least one overbased detergent and at least a neutral detergent as defined above.

Advantageously, the composition according to the invention comprises from 1 to 35% weight detergent, more advantageously from 5 to 35%, preferably from 8 to 35%, and even more preferably from 10 to 35%, these percentages being by weight of detergent, other than the ionic liquid, with regards to the total weight of the lubricant composition.

Preferably the composition according to the invention comprises from 1 to 35% weight detergent, more advantageously from 5 to 35%, preferably from 8 to 35%, and even more preferably from 10 to 35%, these percentages being by weight of neutral and overbased detergent, other than the ionic liquid, with regards to the total weight of the lubricant composition, preferably selected from neutral and overbased detergents having a Total Base Number according to ASTM D2896 of from 20 to 450 mg KOH/g.

Advantageously, the percentage by weight of neutral and overbased detergents relative to the total weight of lubricant is chosen such that the BN provided by the neutral and overbased detergents, other than the ionic liquid, represents a contribution of at most 70 milligrams of potash per gram of lubricant, preferably from 5 to 70 milligrams of potash per gram of lubricant, more preferably from 20 to 40 milligrams of potash per gram of lubricant, to the total BN of said lubricant composition.

Additives:

It is optionally possible to substitute the above-described base oils in full or in part by one or more thickening additives whose role is to increase both the hot and cold viscosity of the composition, or by additives improving the viscosity index (VI).

The lubricant composition of the invention may comprise at least one optional additive, chosen in particular from among those frequently used by persons skilled in the art.

In one embodiment, the lubricant composition further comprises an optional additive chosen amongst an anti-wear additive, an oil soluble fatty amine, a polymer, a dispersing additive, an anti-foaming additive or a mixture thereof.

Polymers are typically polymers having a low molecular weight of from 2000 to 50 000 Dalton (M_n). The polymers are selected amongst PIB (of from 2000 Dalton), polyacrylates or polymetacrylates (of from 30 000 Dalton), olefin copolymers, olefin and alpha-olefin copolymers, EPDM, polybutenes, poly alpha-olefin having a high

molecular weight (viscosity 100°C>150), hydrogenated or non-hydrogenated styrene-olefin copolymers.

Anti-wear additives protect the surfaces from friction by forming a protective film adsorbed on these surfaces. The most commonly used is zinc dithiophosphate or ZnDTP. Also in this category, there are various phosphorus, sulphur, nitrogen, chlorine and boron compounds. There are a wide variety of anti-wear additives, but the most widely used category is that of the sulphur phospho additives such as metal alkylthiophosphates, especially zinc alkylthiophosphates, more specifically, zinc dialkyl dithiophosphates or ZnDTP. The preferred compounds are those of the formula $Zn((SP(S)(OR_1)(OR_2)))_2$, wherein R_1 and R_2 are alkyl groups, preferably having 1 to 18 carbon atoms. The ZnDTP is typically present at levels of about 0.1 to 2% by weight relative to the total weight of the lubricating composition. The amine phosphates, polysulphides, including sulphurised olefins, are also widely used anti-wear additives. One also optionally finds nitrogen and sulphur type anti-wear and extreme pressure additives in lubricating compositions, such as, for example, metal dithiocarbamates, particularly molybdenum dithiocarbamate. Glycerol esters are also anti-wear additives. Mention may be made of mono-, di- and trioleates, monopalmitates and monomyristates. In one embodiment, the content of anti-wear additives ranges from 0.01 to 6%, preferably from 0.1 to 4% by weight relative to the total weight of the lubricating composition.

Dispersants are well known additives used in the formulation of lubricating compositions, in particular for application in the marine field. Their primary role is to maintain in suspension the particles that are initially present or appear in the lubricant during its use in the engine. They prevent their agglomeration by playing on steric hindrance. They may also have a synergistic effect on neutralisation. Dispersants used as lubricant additives typically contain a polar group, associated with a relatively long hydrocarbon chain, generally containing 50 to 400 carbon atoms. The polar group typically contains at least one nitrogen, oxygen, or phosphorus element. Compounds derived from succinic acid are particularly useful as dispersants in lubricating additives. Also used are, in particular, succinimides obtained by condensation of succinic anhydrides and amines, succinic esters obtained by condensation of succinic anhydrides and alcohols or polyols. These compounds can then be treated with various compounds including sulphur, oxygen, formaldehyde, carboxylic acids and

boron-containing compounds or zinc in order to produce, for example, borated succinimides or zinc-blocked succinimides. Mannich bases, obtained by polycondensation of phenols substituted with alkyl groups, formaldehyde and primary or secondary amines, are also compounds that are used as dispersants in lubricants. In one embodiment of the invention, the dispersant content may be greater than or equal to 0.1%, preferably 0.5 to 2%, advantageously from 1 to 1.5% by weight relative to the total weight of the lubricating composition. It is possible to use a dispersant from the PIB succinimide family, e.g., boronated or zinc-blocked.

Other optional additives may be chosen from defoamers, for example, polar polymers such as polydimethylsiloxanes, polyacrylates. They may also be chosen from antioxidant and/or anti-rust additives, for example organometallic detergents or thiadiazoles. These additives are known to persons skilled in the art. These additives are generally present in a weight content of 0.01 to 5% based on the total weight of the lubricating composition.

In one embodiment, the lubricant composition according to the invention may further comprise an oil soluble fatty amine.

The optional additives such as defined above contained in the lubricant compositions of the present invention can be incorporated in the lubricant composition as separate additives, in particular through separate addition thereof in the base oils. However, they may also be integrated in a concentrate of additives for marine lubricant compositions.

Method for producing a lubricant composition

The present disclosure provides a method for producing a lubricant composition, especially a marine lubricant, as disclosed above, comprising the step of mixing the base oil with the guanidinium-based ionic liquid component of formula (I) as above defined, and optionally the additives.

Properties of the lubricant composition

The components that have been disclosed above are formulated to provide a composition that advantageously has the following characteristics:

Advantageously, the composition has a Total Base Number (TBN) value according to ASTM D2896 of above 5 mg KOH/g. Preferably, the composition has a

Total Base Number (TBN) value of from 10 to 140 mg KOH/g, better from 15 to 75 mg KOH/g, more preferably from 20 to 60 mg KOH/g.

Preferably, the lubricant composition according to the invention has a kinematic viscosity at 100°C superior or equal to 5.6 mm²/s and inferior or equal to 21.9 mm²/s, preferably superior or equal to 12.5 mm²/s and inferior or equal to 21.9 mm²/s, more preferably superior or equal to 14.3 mm²/s and inferior or equal to 21.9 mm²/s, advantageously comprised between 16.3 and 21.9 mm²/s, wherein kinematic viscosity at 100°C is evaluated according to ASTM D 445.

Preferably, the lubricant composition according to the invention is a cylinder lubricant.

Even more advantageously, the lubricating composition is a cylinder oil for two-stroke diesel marine engines and has a viscosimetric grade SAE-50, equivalent to a kinematic viscosity at 100° C comprised between 16.3 and 21.9 mm²/s.

Typically, a conventional formulation of cylinder lubricant for two-stroke marine diesel engines is of grade SAE 40 to SAE 60, preferentially SAE 50 (according to the SAE J300 classification) and comprises at least 50% by weight of a lubricating base oil of mineral and/or synthetic origin, adapted to the use in a marine engine, for example of the API Group 1 class.

These viscosities may be obtained by mixing additives and base oils, for example base oils containing mineral bases of Group 1 such as Neutral Solvent (for example 150 NS, 500 NS or 600 NS) bases and bright stock. Any other combination of mineral, synthetic bases or bases of plant origin, having, as a mixture with the additives, a viscosity compatible with the chosen SAE grade, may be used.

The Applicant found that it was possible to formulate cylinder lubricants in which a significant part of the BN is provided by oil-soluble guanidinium-based ionic liquid whilst maintaining the level of performance compared with standard formulations with an equivalent BN.

The performances in question here are in particular the capacity to neutralize sulphuric acid, measured using the enthalpy test described in the examples hereafter.

Thanks to the alternative BN provided by the oil-soluble guanidinium-based ionic liquid, which do not form hard deposits leading to wear of the parts, optionally in combination with overbased and neutral detergents, the cylinder lubricants

according to the present invention are suitable both for high-sulphur fuel oils and for low-sulphur fuel oils.

5 Use of the guanidinium-based ionic liquid of formula (I) and of the lubricant composition comprising it

 The invention also relates to the use of a guanidinium-based ionic liquid of formula (I) as defined above for lubricating engines, preferably marine engines. Specifically, the invention is directed to the use of a guanidinium-based ionic liquid of formula (I) as defined above for lubricating two-stroke marine engines and four-stroke marine engines, more preferably two-stroke marine engine.

 In particular, the guanidinium-based ionic liquid of formula (I) is suitable for use in a lubricant composition, as cylinder oil or system oil, for lubricating two-stroke engines and four-stroke marine engines, more preferably two-stroke engines.

 The invention particularly relates to the use of the guanidinium-based ionic liquid of the invention as detergent additive in a lubricant composition, notably a marine lubricant.

 In particular, the guanidinium-based ionic liquid of formula (I) is used in a lubricant composition, notably a marine lubricant, to reduce and/or limit and/or prevent and/or delay the formation of deposits (keep clean effect) and/or to reduce the deposits already present in the internal parts of a marine engine (clean-up effect).

 According to another aspect of the invention, the guanidinium-based ionic liquid of the invention is used as an anti-corrosion additive in a lubricant composition, notably a marine lubricant.

 The invention also relates to the use of the above-described lubricant composition comprising the guanidinium-based ionic liquid of formula (I) and a base oil, for lubricating two-stroke engines and four-stroke marine engines, more preferably two-stroke engines.

 In particular, the above-described lubricant composition is used in marine engines, preferably two-stroke marine engines, to reduce and/or limit and/or prevent and/or delay the formation of deposits (keep clean effect) and/or to reduce the deposits already present in the internal parts of said marine engine (clean-up effect).

According to another aspect of the invention, the lubricant composition of the invention is used in a marine engine, preferably a two-stroke marine engine, to reduce and/or limit and/or prevent and/or delay corrosion.

The invention also relates to a method for lubricating two-stroke marine engines and four-stroke marine engines, more preferably two-stroke marine engines, said method comprising the application to said marine engine of the guanidinium-based ionic liquid or of a lubricant composition as disclosed above.

The invention particularly relates to a method to reduce and/or limit and/or prevent and/or delay the formation of deposits and/or to reduce the deposits already present in the internal parts of a combustion engine, wherein said method comprises at least a step of application to said engine of a guanidinium-based ionic liquid or of a lubricant composition as disclosed above.

The invention also relates to a method to reduce and/or limit and/or prevent and/or delay corrosion in the internal parts of a marine engine, wherein said method comprises at least a step of application to said engine of a guanidinium-based ionic liquid or of a lubricant composition as disclosed above.

In particular, the guanidinium-based ionic liquid or the lubricant composition is applied to the cylinder wall, typically by a pulse lubricating system or by spraying the ionic liquid or the composition onto the piston's rings pack through an injector for lubricating two-stroke engines. It has been observed that applying to the cylinder wall the lubricant composition according to the invention provides increased protection against corrosion and improved engine cleanliness.


Examples

Material and methods:

1,1,3,3-tetramethylguanidine (CAS 80-70-6) is available from Merck.

tert-Octylphenylpolyethoxyethanol (CAS 9002-93-1) is available from Merck.

I- Synthesis of 1,1,3,3-tetramethylguanidinium tert-Octylphenylpolyethoxyethanolate (IL1)



345.6 g (3 mol) of 1,1,3,3-tetramethylguanidine were slowly added under stirring at 0°C to 1.5 L of methanol. The solution was allowed to warm up to room temperature then 1875 g (3 mol) of tert-Octylphenylpolyethoxyethanol were added slowly and under cooling over a period of 2 hours using a piston pump. The temperature of the reaction mixture was kept at all times under 20°C. After completion of the addition, the reaction mixture was stirred at room temperature for 24 hours, then the pH of the medium was adjusted to pH=11 through addition of either 1,1,3,3-tetramethylguanidine or tert-Octylphenylpolyethoxyethanol. 60 ml of activated charcoal were added to the mixture and the latter was further vigorously stirred for 13 hours at room temperature. The charcoal was filtrated over a glass frit filter and the solvent was evaporated at 38°C under reduced pressure. The obtained slightly yellow oil was further dried at 35°C under a vacuum of 10^{-2} mbar until the water content was below 0.1%, as measured by Karl-Fischer titration.

The base number of IL1 is 61 mg KOH/g according to ASTM D2896.

Solubility test:

In order to check that the guanidinium-based ionic liquid is oil-soluble, the following test has been achieved:

100 mL of the lubricant composition comprising IL1 and the base oil is introduced into two reaction tubes. One of the tubes is maintained at room temperature (between 15 and 25°C) and the other reaction tube is placed in an oven at 60°C.

After three months, the lubricant composition of both reaction tubes was limpid. Thus, the prepared ionic liquid IL1 is soluble in the oil.

II- Preparation of the lubricant composition:

Lubricant compositions are prepared by mixing the base oil with the additives listed in Table 1 below at 60°C with the corresponding proportions. The percentages correspond to weight percent with regards to the total weight of the composition.

Composition C1 is a comparative example. Composition C2 is according to the invention.

Table 1: formulation of lubricant compositions

Composition	C1	C2
Base oil ⁽¹⁾ (%)	89.67	88.97
IL1 (%)		2
Dtg 1 ⁽²⁾ (%)	4.6	4
Dtg 2 ⁽²⁾ (%)	5.7	5
AF ⁽³⁾ (%)	0.03	0.03
TBN (Total base number in mg KOH/g of composition according to ASTM D2896)	25.1	23.6

⁽¹⁾ Group I mineral oil 600NS having a viscosity at 40 ° C of 112 cSt measured according to ASTM D7279

5 ⁽²⁾ Detergents: Dtg1: Salicylate of TBN = 225 mg KOH/g according to ASTM D2896, Dtg 2: Phenate of TBN = 260 mg KOH/g according to ASTM D2896

⁽³⁾ AF: anti-foaming agent.

III- Test method 1: Heat resistance and detergency of lubricant compositions:

10 The heat resistance of lubricant compositions according to the invention is evaluated by performing the ECBT test on aged oil.

Principle: the heat resistance of the lubricant composition C₁ was thus evaluated by means of the ECBT test on aged oil, via which the mass of deposits (in mg) generated under given conditions is determined. The lower this mass, the better the heat resistance and thus the better the cleanliness of the engine.

15 This test simulates the behaviour of the lubricant composition when it is injected onto the hot parts of the engine and especially onto the top of the piston.

20 Equipment used: the test was performed at a temperature of 310°C. It uses aluminium beakers which simulate the form of pistons. The beakers were placed in a glass container; the lubricant composition being maintained at a controlled temperature of about 60°C. The lubricant was placed in these containers, which were themselves equipped with a metal brush partially immersed in the lubricant. This brush is driven in a rotary motion at a speed of 1000 rpm, which creates a projection of lubricant onto the inner surface of the beaker. The beaker was maintained at a temperature of 310°C by means of a heating electrical resistance, regulated by a

thermocouple. This projection of lubricant was continued throughout the test for 12 hours.

This procedure makes it possible to simulate the formation of deposits in the piston-ring assembly. The result is the weight of deposits measured in mg on the beaker.

A detailed description of this test is given in the publication “Research and Development of Marine Lubricants in ELF ANTAR France- The relevance of laboratory tests in simulating field performance” by Jean-Philippe ROMAN, Marine Propulsion Conference 2000- Amsterdam- 29-30 Mar. 2000.

Results: the lubricant according to the invention C2 provides 267 mg of deposits whereas the comparative lubricant C1 provides 499 mg of deposits.

Thus, the ionic liquid defined in the present invention has a detergency effect since it allows reducing the deposits in pieces of a motor.

IV: Test method 2: anti-corrosion properties:

Equipment used: The apparatus used to evaluate the passivation of the compounds tested consists of a beaker of suitable size (usually 500 to 1000 mL), a temperature-regulating device such as a hot plate, and a specimen support system. 200 mL of lubricant are continuously mixed by a suitable stirring mechanism, such as a magnetic stirrer or others. Using a dosing syringe or pump, a well-defined amount of sulfuric acid is added to the lubricant drop by drop, to expose the metallic test samples to severely acidic corrosive conditions. The quantity of sulfuric acid is determined to have 90% of the TBN of the oil neutralized.

The effects of corrosion are determined by visual changes on the metallic specimen.


Results: The results obtained with compositions C1 and C2 described above are shown in table 3 below. Corrosion is rated on a scale of 1 to 5. 1 means that the test sample is very corroded and 5 means it is hardly corroded or not corroded at all.

Table 3:


Composition	C1	C2
Corrosion observed	1	4

CLAIMS

1. Guanidinium-based ionic liquid compound of formula (I)




5 wherein $[\text{CAT}^+]$ represents 1,1,3,3-tetramethylguanidinium
and $[\text{X}^-]$ represents one or more species selected from compounds of formula
(II):



wherein

- 10 - A represents an aryl group comprising from 6 to 12 carbon atoms;
- R is selected from the group consisting of hydrogen, linear or branched, alkyl
or alkenyl groups comprising from 1 to 30 carbon atoms, aryl groups comprising from
6 to 30 carbon atoms;
- Y represents a linear or branched alkanediyl group comprising from 1 to 6
15 carbon atoms; and
- n represents an integer from 1 to 20.

2. The guanidinium-based ionic liquid compound according to claim 1 wherein
 $[\text{X}^-]$ responds to formula (IIA):



(IIA)

wherein

- 20 - R is selected from the group consisting of hydrogen, linear or branched, alkyl
or alkenyl groups comprising from 1 to 30 carbon atoms, aryl groups comprising from
6 to 30 carbon atoms; R can be in ortho, para or meta position;
25 - Y is a linear or branched alkanediyl group comprising from 1 to 6 carbon
atoms; and
- n is an integer from 1 to 15, preferably from 1 to 12.

3. The guanidinium-based ionic liquid according to claim 2 wherein in formula (IIA), R is selected from the group consisting of hydrogen, linear or branched, alkyl or alkenyl groups comprising from 1 to 30, preferably from 1 to 18, more preferably from 1 to 12 carbon atoms, R being in ortho, para or meta position.


5

4. The guanidinium-based ionic liquid according to claim 3 wherein in formula (IIA), R represents a linear or branched alkyl group comprising from 1 to 12 carbon atoms, R being in para position.

10

5. The guanidinium-based ionic liquid according to anyone of claims 1 to 4 wherein Y is a linear or branched alkanediyl group comprising from 1 to 3 carbon atoms, preferably Y is $-\text{CH}_2-\text{CH}_2-$.

6. The guanidinium-based ionic liquid according to anyone of claims 1 to 5 wherein $[\text{X}^-]$ responds to formula (IIB):



wherein n is comprised between 4 and 10.

7. The guanidinium-based ionic liquid according to anyone of claims 1 to 6 wherein $[\text{X}^-]$ is tert-octylphenylpolyethoxyethanolate with $n = 8$ or 9 .

8. A lubricant composition comprising:

- from 30.0 to 99.95 % of at least one base oil,
- from 0.05 to 15.0 % of at least one guanidinium-based ionic liquid

defined in claims 1 to 7,

25

the percentages being defined by weight of component as compared to the total weight of the composition.

9. The lubricant composition of claim 8, wherein it comprises at least one detergent selected from neutral and overbased detergents other than the ionic liquid having a Total Base Number according to ASTM D2896 of from 20 to 450 mg KOH/g.

5

10. The lubricant composition of claim 9, wherein it comprises from 1 to 35% weight of neutral and overbased detergents, other than the ionic liquid, with regards to the total weight of the lubricant composition.

10

11. The lubricant composition according to any one of claim 8 to claim 10, wherein the percentage by weight of guanidinium-based ionic liquid of formula (I) relative to the total weight of lubricant composition is chosen such that the BN provided by the guanidinium-based ionic liquid represents at least 3% of the total BN of said lubricant composition.

15

12. The lubricant composition according to any one of claim 8 to claim 11, which has a Total Base Number (TBN) value according to ASTM D2896 of above 5 mg KOH/g.

20

13. Use of the guanidinium-based ionic liquid defined in claims 1 to 6 as detergent in a lubricant composition, to reduce and/or limit and/or prevent and/or delay the formation of deposits or to reduce the deposits already present in the internal parts of a combustion engine.

25

14. Use of the guanidinium-based ionic liquid defined in claims 1 to 6 as anti-corrosion additive in a lubricant composition.

30

15. Method for lubricating a two-stroke marine engine and four-stroke marine engines, preferably two-stroke marine engine, said method comprising application to said marine engine of the guanidinium-based ionic liquid defined in claims 1 to 6 or the lubricant composition as defined in claims 8 to 12.

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2021/059083

A. CLASSIFICATION OF SUBJECT MATTER
INV. C10M133/22
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C10M C10N

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2017/292083 A1 (DIEGELMANN STEPHEN ROBERT [US] ET AL) 12 October 2017 (2017-10-12) paragraphs [0047], [0077], [0078]; claim 1	1-15
A	----- DE 10 2013 201971 A1 (BASF SE [DE]) 14 August 2013 (2013-08-14) paragraph [0002]; claims 1, 4	1-15
A	----- WO 02/48212 A1 (ELF ANTAR FRANCE [FR]; COUTURIER JEAN-LUC [FR] ET AL.) 20 June 2002 (2002-06-20) claims 1, 22	1-15



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

2 June 2021

Date of mailing of the international search report

28/06/2021

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Klaes, Daphne

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2021/059083

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2017292083 A1	12-10-2017	NONE	
DE 102013201971 A1	14-08-2013	NONE	
WO 0248212 A1	20-06-2002	AU 1928102 A FR 2817871 A1 WO 0248212 A1	24-06-2002 14-06-2002 20-06-2002