

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
10 March 2011 (10.03.2011)

PCT

(10) International Publication Number  
**WO 2011/028866 A2**

(51) International Patent Classification:  
C07C 51/367 (2006.01) C08G 73/06 (2006.01)  
C07C 65/21 (2006.01)

(74) Agent: LANGWORTHY, John, A.; E. I. du Pont de Nemours and Company, Legal Patent Records Center, 4417 Lancaster Pike, Wilmington, Delaware 19805 (US).

(21) International Application Number:  
PCT/US2010/047624

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(22) International Filing Date:  
2 September 2010 (02.09.2010)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
61/239,194 2 September 2009 (02.09.2009) US

(71) Applicant (for all designated States except US): E. I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, Delaware 19898 (US).

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and

(75) Inventors/Applicants (for US only): RITTER, Joachim, C. [DE/US]; 121 Broadbent Road, Wilmington, Delaware 19810 (US). MOLOY, Kenneth, G. [US/US]; 549 Cobot Drive, Hockessin, Delaware 19707 (US). POLLINO, Joel, M. [US/US]; 10 Henry Way, Elkton, Maryland 21921 (US). MAHAJAN, Surbhi [IN/US]; 215 Odessa Way, Newark, Delaware 19711 (US).

Published:

— without international search report and to be republished upon receipt of that report (Rule 48.2(g))



WO 2011/028866 A2

(54) Title: PROCESS FOR THE SYNTHESIS OF FLUORINATED ETHERS OF AROMATIC ACIDS

(57) Abstract: Fluorinated ethers of aromatic acids are produced from halogenated aromatic acids in a reaction mixture containing a copper (I) or copper (II) source and a diketone ligand that coordinates to copper. The fluorinated ethers of aromatic acids made using the process described herein can be applied to, e.g., fibers, yarns, carpets, garments, films, molded parts, paper and cardboard, stone, and tile to impart soil, water and oil resistance. By incorporating the fluorinated ethers of aromatic acids, or diesters thereof, into polymer backbones, more lasting soil, water and oil resistance, as well as improved flame retardance, can be achieved.

TITLEPROCESS FOR THE SYNTHESIS OF  
FLUORINATED ETHERS OF AROMATIC ACIDS

5

This application claims priority under 35 U.S.C. §119(e) from, and claims the benefit of, U.S. Provisional Application No. 61/239,194, filed September 2, 2009, which  
10 is by this reference incorporated in its entirety as a part hereof for all purposes.

Technical Field

15

This invention relates to the manufacture of fluorinated ethers of aromatic acids, or hydroxy aromatic acids, which are valuable for a variety of purposes such as use as surfactants, intermediates or as monomers to make polymers.

20

Background

Fluorinated organic compounds have been used in a wide variety of applications, for example, in surface  
25 treatments, as intermediates in the synthesis of, e.g. pharmaceuticals, and as monomers in the synthesis of polymers with highly valued properties. In particular, as compounds or as components of polymers, they are used to impart soil, water and oil resistance, and improved  
30 flame retardancy to materials, especially in fiber-related industries. Generally, the fluorinated compounds are applied as a topical treatment, but their effectiveness


decreases over time because of material loss resulting from wear and washing.

A need thus remains to provide polymeric materials that have improved, more durable soil and oil resistance.

### Summary

The disclosures herein include new fluorinated ethers of aromatic acids, processes for the preparation of a fluorinated ether of an aromatic acid, processes for the preparation of products into which such a fluorinated ether can be converted, the use of such processes, and the products obtained and obtainable by such processes.

One embodiment of the processes hereof provides a process for preparing a fluorinated ether of an aromatic acid, the ether being represented by the structure of the following Formula I:




I

wherein Ar is a C<sub>6</sub>~C<sub>20</sub> monocyclic or polycyclic aromatic nucleus, n and m are each independently a nonzero value, n+m is less than or equal to 8, and wherein R<sub>f</sub> is a

fluorinated alkyl, alkaryl, aralkyl or aryl group,  
 optionally containing one or more ether linkages -O- ,  
 with the proviso that R<sub>f</sub> is not attached to the ether  
 oxygen in Formula I via a CF<sub>2</sub> group or a CF<sub>2</sub>CH<sub>2</sub>CH<sub>2</sub> group,  
 5 comprising:

(a) contacting a halogenated aromatic acid that  
 is represented by the structure of the following Formula  
 II:



10


II

wherein each X is independently Cl, Br or I, and Ar, n and  
 m are as set forth above, with


- 15 (i) a total of from about n+m to about n+m+1  
 equivalents of the alcoholate R<sub>f</sub>O<sup>-</sup>M<sup>+</sup>  
 (wherein M is Na or K) per equivalent of  
 halogenated aromatic acid, in a polar  
 aprotic solvent or in R<sub>f</sub>OH as a solvent;
- 20 (ii) a copper (I) or copper (II) source; and

(iii) a diketone ligand that coordinates to copper, such as is represented by the structure of the following Formula III:

5



10 wherein A is



15  $\text{R}^1$  and  $\text{R}^2$  are each independently selected from substituted and unsubstituted  $\text{C}_1$ - $\text{C}_{16}$  n-alkyl, iso-alkyl and tertiary alkyl groups; and substituted and unsubstituted  $\text{C}_6$  -  $\text{C}_{30}$  aryl and heteroaryl groups;


20  $\text{R}^3$  is selected from H; substituted and unsubstituted  $\text{C}_1$ - $\text{C}_{16}$  n-alkyl, iso-alkyl and tertiary alkyl groups; substituted and unsubstituted  $\text{C}_6$  -  $\text{C}_{30}$  aryl and heteroaryl groups; and a halogen;

25  $\text{R}^4$ ,  $\text{R}^5$ ,  $\text{R}^6$  and  $\text{R}^7$  are each independently H or a substituted or unsubstituted  $\text{C}_1$ - $\text{C}_{16}$  n-alkyl, iso-alkyl or tertiary alkyl group; and

$p = 0$  or  $1$ ;

to form a reaction mixture;

(b) heating the reaction mixture to form the m-basic salt of the product of step (a), as is represented  
5 by the structure of the following Formula III:



III

10

(c) optionally, separating the Formula III m-basic salt from the reaction mixture in which it is formed; and

15

(d) contacting the Formula III m-basic salt with acid to form therefrom a fluorinated ether of an aromatic acid.

Another embodiment of this invention provides a  
20 process for preparing a compound, monomer, oligomer or polymer by preparing a fluorinated ether of an aromatic acid that is described by the structure of Formula I, and then subjecting the ether so produced to a reaction  
(including a multi-step reaction) to prepare therefrom a  
25 compound, monomer, oligomer or polymer.


It has been found that by incorporating fluorinated aromatic diesters into polymer backbones, more lasting soil, water and oil resistance, as well as improved flame retardance, can be achieved.

5

### Detailed Description

This disclosure provides a process for preparing a fluorinated ether of an aromatic acid, the ether being represented by the structure of the following Formula I:

10



I


15

wherein Ar is a C<sub>6</sub>~C<sub>20</sub> monocyclic or polycyclic aromatic nucleus, n and m are each independently a nonzero value, n+m is less than or equal to 8, and wherein R<sub>f</sub> is a fluorinated alkyl, alkaryl, aralkyl or aryl group, optionally containing one or more ether linkages -O-, with the proviso that R<sub>f</sub> is not attached to the ether oxygen in Formula I via a CF<sub>2</sub> group or a CF<sub>2</sub>CH<sub>2</sub>CH<sub>2</sub> group, comprising:

20

25

(a) contacting a halogenated aromatic acid that is represented by the structure of the following Formula II:




5

II

wherein each X is independently Cl, Br or I, and Ar, n and m are as set forth above, with


- 10 (i) a total of from about n+m to about n+m+1 equivalents of the alcoholate  $\text{R}_f\text{O}^-\text{M}^+$  (wherein M is Na or K) per equivalent of halogenated aromatic acid, in a polar aprotic solvent or in  $\text{R}_f\text{OH}$  as a solvent;
- 15 (ii) a copper (I) or copper (II) source; and
- (iii) a diketone ligand that coordinates to copper, such as is represented by the structure of the following Formula III:

20



III

wherein A is



5

R<sup>1</sup> and R<sup>2</sup> are each independently selected from substituted and unsubstituted C<sub>1</sub>-C<sub>16</sub> n-alkyl, iso-alkyl and tertiary alkyl groups; and substituted and unsubstituted C<sub>6</sub> - C<sub>30</sub> aryl and heteroaryl groups;

10

R<sup>3</sup> is selected from H; substituted and unsubstituted C<sub>1</sub>-C<sub>16</sub> n-alkyl, iso-alkyl and tertiary alkyl groups; substituted and unsubstituted C<sub>6</sub> - C<sub>30</sub> aryl and heteroaryl groups; and a halogen;

15

R<sup>4</sup>, R<sup>5</sup>, R<sup>6</sup> and R<sup>7</sup> are each independently H or a substituted or unsubstituted C<sub>1</sub>-C<sub>16</sub> n-alkyl, iso-alkyl or tertiary alkyl group; and


20

p = 0 or 1;

to form a reaction mixture;

(b) heating the reaction mixture to form the m-basic salt of the product of step (a), as is represented by the structure of the following Formula IV:

25



5 (c) optionally, separating the Formula IV m-basic salt from the reaction mixture in which it is formed; and


10 (d) contacting the Formula IV m-basic salt with acid to form therefrom a fluorinated ether of an aromatic acid.

As used herein, the term "alkyl" denotes a univalent group derived from an alkane by removing a hydrogen atom from any carbon atom:  $-C_xH_{2x+1}$  where  $x \geq 1$ .


As used herein, the term "aryl" denotes a univalent group whose free valence is to a carbon atom of an aromatic ring.

20

As used herein, the term "aralkyl" denotes an alkyl group which bears an aryl group. One such example is the benzyl group, i.e., the radical,



As used herein, the term "alkaryl" denotes an aryl group which bears an alkyl group. Some examples are the 4-methylphenyl radical,



the mesityl group (i.e., 2,4,6-trimethylphenyl) and the 2,6-diisopropylphenyl group (i.e., the  $(\text{CH}_3\text{CHCH}_3)_2\text{C}_6\text{H}_3$ -radical).

10 Examples of  $R_f$  include without limitation:

$\text{CF}_3(\text{CF}_2)_a(\text{CH}_2)_b$  - wherein a = an integer from 0 to 15 and b = 1, 3 or 4;

$\text{HCF}_2(\text{CF}_2)_c(\text{CH}_2)_d$  - wherein c = an integer from 0 to 15 and d = 1, 3, or 4;

15  $\text{CF}_3\text{CF}_2\text{CF}_2\text{OCFHCF}_2(\text{OCH}_2\text{CH}_2)_e$  - and

$\text{CF}_3\text{CF}_2\text{CF}_2\text{OCF}_2\text{CF}_2(\text{OCH}_2\text{CH}_2)_e$  -, wherein e = an integer from 1 to 12;

$(\text{CF}_3)_2\text{CH}-$  ,

$(\text{CF}_3\text{CF}_2\text{CFH})(\text{F})(\text{CF}_3)\text{C}-$  ,

20  $(\text{CF}_3\text{CF}_2\text{CFH})(\text{F})(\text{CF}_3)\text{CCH}_2-$  ,


$(\text{CF}_3)_2(\text{H})\text{C}(\text{CF}_3\text{CF}_2)(\text{F})\text{C}-$  , and

$(\text{CF}_3)_2(\text{H})\text{C}(\text{CF}_3\text{CF}_2)(\text{F})\text{CCH}_2-$  ; and

pentafluorophenyl.

25 In Formulae I, II and IV, Ar is a  $\text{C}_6\sim\text{C}_{20}$  monocyclic or polycyclic aromatic nucleus; n and m are each independently a nonzero value and n+m is less than or equal to 8; and in Formula II, each X is independently Cl, Br or I.

The radical denoted by




5

is an  $n+m$  valent  $C_6 \sim C_{20}$  monocyclic or polycyclic aromatic nucleus formed by the removal of  $n+m$  hydrogens from different carbon atoms on the aromatic ring, or on the aromatic rings when the structure is polycyclic. The radical "Ar" may be substituted or unsubstituted; when  
10 unsubstituted, it contains only carbon and hydrogen.


One example of a suitable Ar group is phenylene, as shown below, wherein  $n=m=1$ .

15



A preferred Ar group is shown below, wherein  $n=m=2$ .

20


















An "m-basic salt", as the term is used herein, is the salt formed from an acid that contains in each molecule  $m$  acid groups having a replaceable hydrogen atom.

25

Various halogenated aromatic acids, to be used as a starting material in the process of this invention, are commercially available. For example, 2-bromobenzoic acid is available from Aldrich Chemical Company (Milwaukee, Wisconsin). It can be synthesized, however, by oxidation of bromomethylbenzene as described in Sasson *et al*, *Journal of Organic Chemistry* (1986), 51(15), 2880-2883. Other halogenated aromatic acids that can be used include without limitation 2,5-dibromobenzoic acid, 2-bromo-5-nitrobenzoic acid, 2-bromo-5-methylbenzoic acid, 2-chlorobenzoic acid, 2,5-dichlorobenzoic acid, 2-chloro-3,5-dinitrobenzoic acid, 2-chloro-5-methylbenzoic acid, 2-bromo-5-methoxybenzoic acid, 5-bromo-2-chlorobenzoic acid, 2,3-dichlorobenzoic acid, 2-chloro-4-nitrobenzoic acid, 2,5-dichloroterephthalic acid, 2-chloro-5-nitrobenzoic acid, 2,5-dibromoterephthalic acid, and 2,5-dichloroterephthalic acid, all of which are commercially available. Preferably, the halogenated aromatic acid is 2,5-dibromoterephthalic acid or 2,5-dichloroterephthalic acid.

Other halogenated aromatic acids useful as a starting material in the process of this invention include those shown in the left column of the table below, wherein X = Cl, Br or I, and wherein the corresponding ether of an aromatic acid produced therefrom by the process of this invention is shown in the right column:

$(\text{COOH})_m\text{-Ar-(X)}_n$	$(\text{COOH})_m\text{-Ar-(OR}_f)_n$
	
	
	
	
	
	
	



In step (a), a halogenated aromatic acid is contacted with the alcoholate  $R_fO^-M^+$ , wherein  $R_f$  is as defined above and M is Na or K, in a polar aprotic solvent or in  $R_fOH$  as a solvent; a copper (I) or copper (II) source; and a ligand that coordinates to copper, wherein the ligand comprises a Schiff base.

The alcohol may be  $R_fOH$ , which is preferred, or it may be an alcohol that is not more acidic than  $R_fOH$ . Examples of suitable alcohols include without limitation methanol, ethanol, i-propanol, i-butanol, and phenol, with the proviso that the alcohol is not more acidic than  $R_fOH$ .

The solvent may also be a polar protic or polar aprotic solvent or a mixture of protic or polar aprotic solvent. A polar solvent, as used herein, is a solvent whose constituent molecules exhibit a nonzero dipole moment. A polar protic solvent, as used herein, is a polar solvent whose constituent molecules contain an O-H or N-H bond. A polar aprotic solvent, as used herein, is a polar solvent whose constituent molecules do not contain an O-H or N-H bond. Non-limiting examples of polar solvents other than an alcohol suitable for use herein include tetrahydrofuran, N-methylpyrrolidone,

dimethylformamide, and dimethylacetamide.


In step (a), a halogenated aromatic acid is preferably contacted with a total of from about  $n+m$  to  $n+m+1$  equivalents of the alcoholate  $RO^-M^+$  per equivalent of halogenated aromatic acid. Between  $m$  and  $m+1$  equivalents is used for forming the  $m$ -basic salt and between  $n$  and  $n+1$  equivalents is used for the displacement reaction. It is preferred that the total amount of alcoholate not exceed  $m+n+1$ . It is also preferred that the total amount of alcoholate not be less than  $m+n$  in order to avoid reduction reactions. One "equivalent" as used in this context is the number of moles of alcoholate  $RO^-M^+$  that will react with one mole of hydrogen ions; for an acid, one equivalent is the number of moles of acid that will supply one mole of hydrogen ions.

As mentioned above, in step (a), the halogenated aromatic acid is also contacted with a copper (I) or (II) source in the presence of a diketone ligand that coordinates to copper. The copper source and the ligand may be added sequentially to the reaction mixture, or may be combined separately (for example, in a solution of water or acetonitrile) and added together.


The copper source is a Cu(I) salt, a Cu(II) salt, or mixtures thereof. Examples include without limitation CuCl, CuBr, CuI, Cu<sub>2</sub>SO<sub>4</sub>, CuNO<sub>3</sub>, CuCl<sub>2</sub>, CuBr<sub>2</sub>, CuI<sub>2</sub>, CuSO<sub>4</sub>, and Cu(NO<sub>3</sub>)<sub>2</sub>. The selection of the copper source may be made in relation to the identity of the halogenated aromatic acid used. For example, if the starting halogenated aromatic acid is a bromobenzoic acid,

CuCl, CuBr, CuI, Cu<sub>2</sub>SO<sub>4</sub>, CuNO<sub>3</sub>, CuCl<sub>2</sub>, CuBr<sub>2</sub>, CuI<sub>2</sub>, CuSO<sub>4</sub>, and Cu(NO<sub>3</sub>)<sub>2</sub> will be included among the useful choices. If the starting halogenated aromatic acid is a chlorobenzoic acid, CuBr, CuI, CuBr<sub>2</sub> and CuI<sub>2</sub> will be included among the useful choices. Optionally, prior to step (a), a measured amount (~0.25 mol of O<sub>2</sub>/mol of CuI) may be added to dissolve CuI in the diamine/alcohol solution. CuBr and CuBr<sub>2</sub> are in general preferred choices for most systems. The amount of copper used is typically about 0.1 to about 5 mol% based on moles of halogenated aromatic acid.

The ligand may be a diketone as represented by the structure of the following Formula III:



wherein A is



R<sup>1</sup> and R<sup>2</sup> are each independently selected from substituted and unsubstituted C<sub>1</sub>-C<sub>16</sub> n-alkyl, iso-alkyl and tertiary alkyl groups; and substituted and unsubstituted C<sub>6</sub> - C<sub>30</sub> aryl and heteroaryl groups;

$R^3$  is selected from H; substituted and unsubstituted  $C_1$ - $C_{16}$  n-alkyl, iso-alkyl and tertiary alkyl groups; substituted and unsubstituted  $C_6$  -  $C_{30}$  aryl and heteroaryl groups; and a halogen;

5

$R^4$ ,  $R^5$ ,  $R^6$  and  $R^7$  are each independently H or a substituted or unsubstituted  $C_1$ - $C_{16}$  n-alkyl, iso-alkyl or tertiary alkyl group; and  $p = 0$  or 1.


10

The term "unsubstituted", as used with reference to an alkyl or aryl group in a diketone as described above, means that the alkyl or aryl group contains no atoms other than carbon and hydrogen. In a substituted alkyl or aryl group, however, one or more O or S atoms may optionally be substituted for any one or more of the in-chain or in-ring carbon atoms, provided that the resulting structure contains no -O-O- or -S-S- moieties, and provided that no carbon atom is bonded to more than one heteroatom. In a preferred embodiment,  $R^3$  is H.

15

In one embodiment, a diketone suitable for use herein as the ligand is 2,2',6,6'-tetramethylheptanedione-3,5 (Formula V):

20



V


Other diketones suitable for use herein as the ligand include, without limitation, 2,4-pentanedione and 2,3-pentanedione.

5           A ligand suitable for use herein may be selected as any one or more or all of the members of the whole population of ligands described by name or structure above.

10           Various copper sources and ligands suitable for use herein may be made by processes known in the art, or are available commercially from suppliers such as Alfa Aesar (Ward Hill, Massachusetts), City Chemical (West Haven, Connecticut), Fisher Scientific (Fairlawn, New Jersey), Sigma-Aldrich (St. Louis, Missouri) or Stanford  
15           Materials (Aliso Viejo, California).

          In various embodiments, the ligand may be provided in an amount of about 1 to about 8, preferably  
20           about 1 to about 2, molar equivalents of ligand per mole of copper. In those and other embodiments, the ratio of molar equivalents of ligand to molar equivalents of halogenated aromatic acid may be less than or equal to about 0.1. As used herein, the term "molar equivalent"  
25           indicates the number of moles of ligand that will interact with one mole of copper.

          In step (b), the reaction mixture is heated to form the m-basic salt as represented by the structure of  
30           the following Formula IV:



IV

5                   The reaction temperature for steps (a) and (b) is preferably between about 40 and about 120°C, more preferably between about 50 and about 90°C. Typically, the time required for step (a) is from about 0.1 to about 1 hour. The time required for step (b) is typically from  
 10 about 1 to about 100 hours. Optimal times and temperatures may vary depending on the specific materials. Oxygen may be desirably excluded during the reaction. The solution is typically allowed to cool before optional step (c) and before the acidification in step (d) is  
 15 carried out.

                  The m-basic salt of the ether of the aromatic acid is then contacted in step (d) with acid to convert it to the hydroxy aromatic acid product. Any acid of  
 20 sufficient strength to protonate the m-basic salt is suitable. Examples include without limitation hydrochloric acid, sulfuric acid and phosphoric acid.

                  In one embodiment, the copper (I) or copper (II) source is selected from the group consisting of CuBr,  
 25 CuBr<sub>2</sub> and mixtures thereof; the ligand is selected from the group consisting of N,N'-dimesityl-2,3-diiminobutane

and N,N'-di(trifluoromethylbenzene)-2,3-diiminoethane; and the copper (I) or copper (II) source is combined with two molar equivalents of the ligand.

5           The fluorinated ethers of aromatic acids made using the process described herein can be fabricated as fibers, yarns, carpets, garments, films, molded parts, paper and cardboard, stone, and tile to impart soil, water and oil resistance. By incorporating the fluorinated  
10 ethers of aromatic acids, or diesters thereof, into polymer backbones, more lasting soil, water and oil resistance, as well as improved flame retardance, can be achieved.

15           The process described above also allows for effective and efficient synthesis of products made from the resulting fluorinated ethers of aromatic acids such as a compound, a monomer, or an oligomer or polymer thereof. These produced materials may have one or more of ester  
20 functionality, ether functionality, amide functionality, imide functionality, imidazole functionality, thiazole functionality, oxazole functionality, carbonate functionality, acrylate functionality, epoxide functionality, urethane functionality, acetal  
25 functionality, or anhydride functionality.

A Formula I compound may, as desired, be isolated and recovered as described above. It may also be subjected with or without recovery from the reaction  
30 mixture to further steps to convert it to another product such as another compound (e.g. a monomer), or an oligomer or a polymer. Another embodiment of a process hereof thus

provides a process for converting a Formula I compound, through one or more reactions, into another compound, or into an oligomer or a polymer. A Formula I compound may be made by a process such as described above, and then may  
5 be subjected, for example, to a polymerization reaction to prepare an oligomer or polymer therefrom, such as those having ester functionality or amide functionality, or a pyridobisimidazole-2,6-diyl(2,5-dihydroxy-p-phenylene) polymer.

10

The compounds of Formula I made by the process disclosed herein, or their diesters, in particular dimethyl esters, can be used in condensation polymerizations to produce fluorinated condensation  
15 polymers, e.g., including without limitation polyesters, polyamides, polyimides, and polybenzimidazoles. Representative reactions involving a material of this invention, or a derivative of such material, such as a diester, include, for example, making a polyester from one  
20 or more compounds of Formula I and either diethylene glycol or triethylene glycol in the presence of 0.1% of  $Zn_3(BO_3)_2$  in 1-methylnaphthalene under nitrogen, according to the method taught in US 3,047,536 (which is incorporated in its entirety as a part hereof for all  
25 purposes). Similarly, a fluorinated ether of aromatic acid is suitable for copolymerization with a dibasic acid and a glycol to prepare a heat-stabilized fluorinated polyester according to the method taught in US 3,227,680 (which is incorporated in its entirety as a part hereof  
30 for all purposes), wherein representative conditions involve forming a prepolymer in the presence of titanium tetraisopropoxide in butanol at 200~250°C, followed by

solid-phase polymerization at 280°C at a pressure of 0.08 mm Hg.

Other diols useful to make from a polyester from  
5 a Formula I compound are those that are derived from a fermentation process, and another embodiment of this invention thus involves a process for making from a Formula I compound an oligomer or polymer that further includes a step of providing a diol to such a process from  
10 a fermentation process.

A Formula I compound may be converted into a polyamide oligomer or polymer by reaction with a diamine in a process in which, for example, the polymerization  
15 takes place in solution in an organic compound that is liquid under the conditions of the reaction, is a solvent for both the Formula I compound and the diamine, and has a swelling or partial solvation action on the polymeric product. The reaction may be effected at moderate  
20 temperatures, e.g. under 100°C, and is preferably effected in the presence of an acid acceptor that is also soluble in the chosen solvent. Suitable solvents include methyl ethyl ketone, acetonitrile, N,N-dimethylacetamide dimethyl formamide containing 5% lithium chloride, and N-methyl  
25 pyrrolidone containing a quaternary ammonium chloride such as methyl tri-n-butyl ammonium chloride or methyl-tri-n-propyl ammonium chloride. Combination of the reactant components causes generation of considerable heat and the agitation, also, results in generation of heat energy.  
30 For that reason, the solvent system and other materials are cooled at all times during the process when cooling is necessary to maintain the desired temperature. Processes

similar to the foregoing are described in US 3,554,966;  
US 4,737,571; and CA 2,355,316.

5 A Formula I compound may also be converted into  
a polyamide oligomer or polymer by reaction with a diamine  
in a process in which, for example, a solution of the  
diamine in a solvent may be contacted in the presence of  
an acid acceptor with a solution of the Formula I compound  
10 in a second solvent that is immiscible with the first to  
effect polymerization at the interface of the two phases.  
The diamine may, for example, be dissolved or dispersed in  
a water containing base with the base being used in  
sufficient quantities to neutralize the acid generated  
during polymerization. Sodium hydroxide may be used as  
15 the acid acceptor. Preferred solvents for the  
diacid(halide) are tetrachloroethylene, methylenechloride,  
naphtha and chloroform. The solvent for the Formula I  
compound should be a relative non-solvent for the amide  
reaction product, and be relatively immiscible in the  
20 amine solvent. A preferred threshold of immiscibility is  
as follows: an organic solvent should be soluble in the  
amine solvent not more than between 0.01 weight percent  
and 1.0 weight percent. The diamine, base and water are  
added together and vigorously stirred. High shearing  
25 action of the stirrer is important. The solution of acid  
chloride is added to the aqueous slurry. Contacting is  
generally carried out at from 0°C to 60°C, for example,  
for from about 1 second to 10 minutes, and preferably from  
5 seconds to 5 minutes at room temperature.  
30 Polymerization occurs rapidly. Processes similar to the  
foregoing are described in US 3,554,966 and US 5,693,227.

A fluorinated ether of aromatic acid can also be polymerized with the trihydrochloride-mono-hydrate of tetraaminopyridine in a condensation polymerization in strong polyphosphoric acid under slow heating above 100°C up to about 180°C under reduced pressure, followed by precipitation in water, as disclosed in US 5,674,969 (which is incorporated in its entirety as a part hereof for all purposes); or by mixing the monomers at a temperature from about 50°C to about 110°C, and then 145°C to form an oligomer, and then reacting the oligomer at a temperature of about 160°C to about 250°C as disclosed in U.S. Provisional Application No. 60/665,737, filed March 28, 2005 (which is incorporated in its entirety as a part hereof for all purposes), published as WO 2006/104974.

The polymer that may be so produced may be a pyridobisimidazole-2,6-diyl(2,5-dialkoxy-p-phenylene) polymer or a pyridobisimidazole-2,6-diyl(2,5-diareneoxy-p-phenylene) polymer such as a poly(1,4-(2,5-diareneoxy)phenylene-2,6-pyrido[2,3-d:5,6-d']bisimidazole) polymer.

The pyridobisimidazole portion thereof may, however, be replaced by any one or more of a benzobisimidazole, benzobisthiazole, benzobisoxazole, pyridobisthiazole and a pyridobisoxazole; and the 2,5-dialkoxy-p-phenylene portion thereof may be replaced by an alkyl or aryl ether of one or more of isophthalic acid, terephthalic acid, 2,5-pyridine dicarboxylic acid, 2,6-naphthalene dicarboxylic acid, 4,4'-diphenyl dicarboxylic acid, 2,6-quinoline dicarboxylic acid, and 2,6-bis(4-carboxyphenyl)pyridobisimidazole, wherein such a fluorinated ether is produced according to the methods disclosed herein.

The polymer prepared in such manner may, for example, contain one or more of the following units:

pyridobisimidazole-2,6-diyl(2,5-dialkoxy-p-phenylene) and/or pyridobisimidazole-2,6-diyl(2,5-diphenoxy-p-phenylene) units;

5 units selected from the group consisting of pyridobisimidazole-2,6-diyl(2,5-dimethoxy-p-phenylene), pyridobisimidazole-2,6-diyl(2,5-diethoxy-p-phenylene), pyridobisimidazole-2,6-diyl(2,5-dipropoxy-p-phenylene),  
10 pyridobisimidazole-2,6-diyl(2,5-dibutoxy-p-phenylene) and pyridobisimidazole-2,6-diyl(2,5-diphenoxy-p-phenylene);

pyridobisthiazole-2,6-diyl(2,5-dialkoxy-p-phenylene) and/or pyridobisthiazole-2,6-diyl(2,5-diphenoxy-p-phenylene) units;

15 units selected from the group consisting of pyridobisthiazole-2,6-diyl(2,5-dimethoxy-p-phenylene), pyridobisthiazole-2,6-diyl(2,5-diethoxy-p-phenylene), pyridobisthiazole-2,6-diyl(2,5-dipropoxy-p-phenylene), pyridobisthiazole-2,6-diyl(2,5-dibutoxy-p-phenylene) and  
20 pyridobisthiazole-2,6-diyl(2,5-diphenoxy-p-phenylene);

pyridobisoxazole-2,6-diyl(2,5-dialkoxy-p-phenylene) and/or pyridobisoxazole-2,6-diyl(2,5-diphenoxy-p-phenylene) units;

25 units selected from the group consisting of pyridobisoxazole-2,6-diyl(2,5-dimethoxy-p-phenylene), pyridobisoxazole-2,6-diyl(2,5-diethoxy-p-phenylene), pyridobisoxazole-2,6-diyl(2,5-dipropoxy-p-phenylene), pyridobisoxazole-2,6-diyl(2,5-dibutoxy-p-phenylene) and  
pyridobisoxazole-2,6-diyl(2,5-diphenoxy-p-phenylene);

30 benzobisimidazole-2,6-diyl(2,5-dialkoxy-p-phenylene) and/or benzobisimidazole-2,6-diyl(2,5-diphenoxy-p-phenylene) units;


- units selected from the group consisting of  
benzobisimidazole-2,6-diyl(2,5-dimethoxy-p-phenylene),  
benzobisimidazole-2,6-diyl(2,5-diethoxy-p-phenylene),  
benzobisimidazole-2,6-diyl(2,5-dipropoxy-p-phenylene),  
5 benzobisimidazole-2,6-diyl(2,5-dibutoxy-p-phenylene) and  
benzobisimidazole-2,6-diyl(2,5-diphenoxy-p-phenylene);  
benzobisthiazole-2,6-diyl(2,5-dialkoxy-p-  
phenylene) and/or benzobisthiazole-2,6-diyl(2,5-diphenoxy-  
p-phenylene) units;
- 10 units selected from the group consisting of  
benzobisthiazole-2,6-diyl(2,5-dimethoxy-p-phenylene),  
benzobisthiazole-2,6-diyl(2,5-diethoxy-p-phenylene),  
benzobisthiazole-2,6-diyl(2,5-dipropoxy-p-phenylene),  
benzobisthiazole-2,6-diyl(2,5-dibutoxy-p-phenylene) and  
15 benzobisthiazole-2,6-diyl(2,5-diphenoxy-p-phenylene);  
benzobisoxazole-2,6-diyl(2,5-dialkoxy-p-  
phenylene) and/or benzobisoxazole-2,6-diyl(2,5-diphenoxy-  
p-phenylene) units; and/or
- 20 units selected from the group consisting of  
benzobisoxazole-2,6-diyl(2,5-dimethoxy-p-phenylene),  
benzobisoxazole-2,6-diyl(2,5-diethoxy-p-phenylene),  
benzobisoxazole-2,6-diyl(2,5-dipropoxy-p-phenylene),  
benzobisoxazole-2,6-diyl(2,5-dibutoxy-p-phenylene) and  
benzobisoxazole-2,6-diyl(2,5-diphenoxy-p-phenylene).

25

### Examples

The advantageous attributes and effects of the processes hereof may be seen in laboratory examples, as described below. The embodiments of these processes on which the example is based are representative only, and the selection of those embodiments to illustrate the invention does not indicate that conditions, arrangements, approaches, steps, techniques, configurations or reactants not described in the example are not suitable for practicing these processes, or that subject matter not described in the example is excluded from the scope of the appended claims and equivalents thereof.

The meaning of abbreviations is as follows "mL" means milliliter(s), "g" means gram(s), "mmol" means millimole(s), "N" means normal, and "THF" means tetrahydrofuran.



**Example 1:**  $\text{HOR}_f = \text{HOCH}_2\text{CF}_3$

**Example 2:**  $\text{HOR}_f = \text{HOCH}_2\text{CF}_2\text{CF}_2\text{H}$

Example 1 Preparation of 2,5-bis(2,2,2-trifluoroethoxy)terephthalic acid

To a solution of 8 mL 2,2,2-trifluoroethanol  
5 (CF<sub>3</sub>CH<sub>2</sub>OH) in 15 mL of THF is carefully added 0.19 g (7.9 mmol) of sodium hydride. When gas evolution is complete, 0.488 g (1.5 mmol) of 2,5-dibromoterephthalic acid was added to the solution, followed by addition of a solution of CuBr<sub>2</sub> (0.092 mmol) and 2,2',6,6'-  
10 tetramethylheptanedione-3,5 (0.19 mmol) in 1.5 mL of CF<sub>3</sub>CH<sub>2</sub>OH. The resulting pale blue slurry is heated at 60°C for four days. Aqueous HCl (1 N) is added to precipitate the product. The product is washed with water, then dissolved in methanol, and the resulting  
15 solution is filtered. The methanol is removed under vacuum to give the product 2,5-bis(2,2,2-trifluoroethoxy)terephthalic acid as colorless microcrystals.

20

Example 2 . Preparation of 2,5-bis(2,2,3,3-tetrafluoropropoxy)terephthalic acid

A flask is charged with 5 mL of anhydrous THF and 8.1 mmol of sodium hydride. A solution of 1.5 g (11.4 mmol)  
25 of 2,2,3,3-tetrafluoropropanol (HCF<sub>2</sub>CF<sub>2</sub>CH<sub>2</sub>OH) in 5 mL of THF is added dropwise. When gas evolution is complete, 2,5-dibromoterephthalic acid (1.51 mmol) is added to the colorless solution. Next, a mixture of CuBr<sub>2</sub> (0.13 mmol) and 2,4-pentanedione (0.22 mmol) in 0.5 g of HCF<sub>2</sub>CF<sub>2</sub>CH<sub>2</sub>OH  
30 is added to the solution. The resulting pale blue slurry is heated at 60°C for two days. The product 2,5-bis(2,2,3,3-tetrafluoropropoxy)terephthalic acid is isolated by treating the cooled reaction product with 0.5

N HCl, then with water, and washing the precipitate with water.

Each of the formulae shown herein describes each  
5 and all of the separate, individual compounds that can be  
formed in that formula by (1) selection from within the  
prescribed range for one of the variable radicals,  
substituents or numerical coefficients while all of the  
other variable radicals, substituents or numerical  
10 coefficients are held constant, and (2) performing in turn  
the same selection from within the prescribed range for  
each of the other variable radicals, substituents or  
numerical coefficients with the others being held  
constant. In addition to a selection made within the  
15 prescribed range for any of the variable radicals,  
substituents or numerical coefficients of only one of the  
members of the group described by the range, a plurality  
of compounds may be described by selecting more than one  
but less than all of the members of the whole group of  
20 radicals, substituents or numerical coefficients. When  
the selection made within the prescribed range for any of  
the variable radicals, substituents or numerical  
coefficients is a subgroup containing (i) only one of the  
members of the whole group described by the range, or (ii)  
25 more than one but less than all of the members of the  
whole group, the selected member(s) are selected by  
omitting those member(s) of the whole group that are not  
selected to form the subgroup. The compound, or plurality  
of compounds, may in such event be characterized by a  
30 definition of one or more of the variable radicals,  
substituents or numerical coefficients that refers to the  
whole group of the prescribed range for that variable but

where the member(s) omitted to form the subgroup are absent from the whole group.

Where a range of numerical values is recited  
5 herein, the range includes the endpoints thereof and all the individual integers and fractions within the range, and also includes each of the narrower ranges therein formed by all the various possible combinations of those endpoints and internal integers and fractions to form  
10 subgroups of the larger group of values within the stated range to the same extent as if each of those narrower ranges was explicitly recited. Where a range of numerical values is stated herein as being greater than a stated value, the range is nevertheless finite and is bounded on  
15 its upper end by a value that is operable within the context of the invention as described herein. Where a range of numerical values is stated herein as being less than a stated value, the range is nevertheless bounded on its lower end by a non-zero value.

20

In this specification, unless explicitly stated otherwise or indicated to the contrary by the context of usage, amounts, sizes, ranges and other quantities and characteristics recited herein, particularly when modified  
25 by the term "about", may but need not be exact, and may also be approximate and/or larger or smaller (as desired) than stated, reflecting tolerances, conversion factors, rounding off, measurement error and the like, as well as the inclusion within a stated value of those values  
30 outside it that have, within the context of this invention, functional and/or operable equivalence to the stated value.

Where an embodiment of this invention is stated or described as comprising, including, containing, having, being composed of or being constituted by certain  
5 features, it is to be understood, unless the statement or description explicitly provides to the contrary, that one or more features in addition to those explicitly stated or described may be present in the embodiment. An  
10 alternative embodiment of this invention, however, may be stated or described as consisting essentially of certain features, in which embodiment features that would materially alter the principle of operation or the distinguishing characteristics of the embodiment are not present therein. A further alternative embodiment of this  
15 invention may be stated or described as consisting of certain features, in which embodiment, or in insubstantial variations thereof, only the features specifically stated or described are present.


20

CLAIMS

5 What is claimed is:

1. A process for preparing a fluorinated ether of an aromatic acid, the ether being represented by the structure of the following Formula I:


10



I

15 wherein Ar is a C<sub>6</sub>~C<sub>20</sub> monocyclic or polycyclic aromatic nucleus, n and m are each independently a nonzero value, n+m is less than or equal to 8, and wherein R<sub>f</sub> is a fluorinated alkyl, alkaryl, aralkyl, or aryl group, optionally containing one or more ether linkages -O- ,  
 20 with the proviso that R<sub>f</sub> is not attached to the ether oxygen in Formula I via a CF<sub>2</sub> group or a CF<sub>2</sub>CH<sub>2</sub>CH<sub>2</sub> group, comprising:


(a) contacting a halogenated aromatic acid that  
 25 is represented by the structure of the following Formula II:



wherein each X is independently Cl, Br or I, and Ar, n and  
5 m are as set forth above, with


- (i) a total of from about n+m to about n+m+1  
equivalents of the alcoholate  $R_fO^-M^+$   
(wherein M is Na or K) per equivalent of  
halogenated aromatic acid, in a polar  
10 aprotic solvent or in  $R_fOH$  as a solvent;
- (ii) a copper (I) or copper (II) source; and
- (iii) a diketone ligand that coordinates to  
copper, such as is represented by the  
structure of the following Formula III:

15



wherein A is

20



R<sup>1</sup> and R<sup>2</sup> are each independently selected from substituted and unsubstituted C<sub>1</sub>-C<sub>16</sub> n-alkyl, iso-alkyl and tertiary alkyl groups; and substituted and unsubstituted C<sub>6</sub> - C<sub>30</sub> aryl and heteroaryl groups;

5

R<sup>3</sup> is selected from H; substituted and unsubstituted C<sub>1</sub>-C<sub>16</sub> n-alkyl, iso-alkyl and tertiary alkyl groups; substituted and unsubstituted C<sub>6</sub> - C<sub>30</sub> aryl and heteroaryl groups; and a halogen;

10


R<sup>4</sup>, R<sup>5</sup>, R<sup>6</sup> and R<sup>7</sup> are each independently H or a substituted or unsubstituted C<sub>1</sub>-C<sub>16</sub> n-alkyl, iso-alkyl or tertiary alkyl group; and p = 0 or 1;

15

to form a reaction mixture;

(b) heating the reaction mixture to form the m-basic salt of the product of step (a), as represented by the structure of the following Formula IV:

20



IV

(c) optionally, separating the Formula IV m-basic salt from the reaction mixture in which it is formed; and

25

(d) contacting the Formula IV m-basic salt with acid to form therefrom a fluorinated ether of an aromatic acid.

5           2. A process according to Claim 1 wherein  $R_f$  is selected from the group consisting of:

$CF_3(CF_2)_a(CH_2)_b-$ , wherein  $a$  = an integer from 0 to 15 and  $b$  = 1, 3 or 4;

10  $HCF_2(CF_2)_c(CH_2)_d-$ , wherein  $c$  = an integer from 0 to 15 and  $d$  = 1, 3, or 4;

$CF_3CF_2CF_2OCF_2CF_2(OCH_2CH_2)_e-$  and

$CF_3CF_2CF_2OCF_2CF_2(OCH_2CH_2)_e-$ , wherein  $e$  = an integer from 1 to 12;

$(CF_3)_2CH-$  ,

15  $(CF_3CF_2CFH)(F)(CF_3)C-$  ,

$(CF_3CF_2CFH)(F)(CF_3)CCH_2-$  ,

$(CF_3)_2(H)C(CF_3CF_2)(F)C-$  , and

$(CF_3)_2(H)C(CF_3CF_2)(F)CCH_2-$  ; and

pentafluorophenyl.

20

3. A process according to Claim 1 wherein the halogenated aromatic acid is selected from the group consisting of 2-bromobenzoic acid, 2,5-dibromobenzoic acid, 2-bromo-5-nitrobenzoic acid, 2-bromo-5-methylbenzoic acid, 2-chlorobenzoic acid, 2,5-dichlorobenzoic acid, 2-chloro-3,5-dinitrobenzoic acid, 2-chloro-5-methylbenzoic acid, 2-bromo-5-methoxybenzoic acid, 5-bromo-2-chlorobenzoic acid, 2,3-dichlorobenzoic acid, 2-chloro-4-nitrobenzoic acid, 2,5-dichloroterephthalic acid, 2-chloro-5-nitrobenzoic acid, 2,5-dibromoterephthalic acid, and 2,5-dichloroterephthalic acid.

25

30

4. A process according to Claim 1 wherein, in step (a), a total of about  $n+m$  to  $n+m+1$  normal equivalents of  $R_fO^-M^+$  are added to the reaction mixture per equivalent of the halogenated aromatic acid.

5


5. A process according to Claim 1 wherein the copper source comprises a Cu(I) salt, a Cu(II) salt, or a mixture thereof.

10

6. A process according to Claim 5 wherein the copper source is selected from the group consisting of CuCl, CuBr, CuI,  $Cu_2SO_4$ ,  $CuNO_3$ ,  $CuCl_2$ ,  $CuBr_2$ ,  $CuI_2$ ,  $CuSO_4$ ,  $Cu(NO_3)_2$ , and mixtures thereof.

15

7. A process according to Claim 1 wherein the ligand is 2,4-pentanedione, 2,3-pentanedione or 2,2',6,6'-tetramethylheptanedione-3,5 (Formula V)



20

V

8. A process according to Claim 1 further comprising a step of combining the copper source with the ligand before adding them to the reaction mixture.

25

9. A process according to Claim 6 wherein the copper source comprises CuBr or  $CuBr_2$ .

10. A process according to Claim 1 wherein copper is provided in an amount of between about 0.1 and about 5 mol% based on moles of halogenated aromatic acid.

5 11. A process according to Claim 1 wherein the ligand is provided in an amount of between about one and about two molar equivalents per mole of copper.

10 12. A process according to Claim 1 wherein the halogenated aromatic hydroxy acid comprises 2,5-dibromoterephthalic acid or 2,5-dichloroterephthalic acid; the copper source comprises CuBr, CuBr<sub>2</sub> or a mixture of CuBr and CuBr<sub>2</sub>; the copper source is provided in an amount of between about 0.1 and about 5 mol% based on moles of  
15 halogenated aromatic acid; the ligand is 2,4-pentanedione, 2,3-pentanedione or 2,2',6,6'-tetramethylheptanedione-3,5; and the ligand is provided in an amount of between about one and about two molar equivalents per mole of copper.

20 13. A process according to Claim 1 further comprising a step of subjecting the ether of the aromatic acid to a reaction to prepare therefrom a compound, monomer, oligomer or polymer.

25 14. A process according to Claim 13 wherein a polymer prepared comprises at least one member of the group consisting of pyridobisimidazole, pyridobisthiazole, pyridobisoxazole, benzobisimidazole, benzobisthiazole, and benzobisoxazole moieties.

30 15. A process according to Claim 14 wherein a polymer prepared comprises a fluorinated

pyridobisimidazole-2,6-diyl (2,5-dialkoxy-p-phenylene) polymer or a fluorinated pyridobisimidazole-2,6-diyl (2,5-diareneoxy-p-phenylene) polymer.

5