

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
25 October 2007 (25.10.2007)

PCT

(10) International Publication Number
WO 2007/121044 A1

(51) International Patent Classification:
C08L 33/00 (2006.01)

(21) International Application Number:
PCT/US2007/064989

(22) International Filing Date: 27 March 2007 (27.03.2007)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/744,885 14 April 2006 (14.04.2006) US

(71) Applicant (for all designated States except US): **POLY-ONE CORPORATION** [US/US]; 33587 Walker Road, Avon Lake, Ohio 44012 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **RAJARAMAN, Hari** [US/US]; 1585 Beckwidth Drive, Hudson, Ohio 44236 (US). **CRANNEY, Stephen** [US/US]; 2632 White Aster Lane, Dacula, Georgia 30019 (US). **MAJEWSKI, Thomas** [US/US]; 7310 Barton Hills Drive, Parma, Ohio 44129 (US). **PRUSAK, Peter** [US/US]; 2257 W. 7th Street, Cleveland, Ohio 44113 (US).

(74) Agents: **HORNICKEL, John, H.** et al.; Polyone Corporation, 33587 Walker Road, Avon Lake, Ohio 44012 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM,

AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))
- of inventorship (Rule 4.17(iv))

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: LIQUID COLOR CONCENTRATE

(57) Abstract: A liquid color concentrate is disclosed, having a liquid acrylic-based polymer carrier; colorant; and optionally other functional additives. The colorant can be one or more pigments, one or more dyes, or combinations thereof. The liquid polymer is compatible with a variety of plastic resins, especially optically clear plastic resins, such as polycarbonate, polymethyl methacrylate, and styrene-acrylonitrile.



WO 2007/121044 A1

LIQUID COLOR CONCENTRATE

CLAIM OF PRIORITY

[0001] This application claims priority from U.S. Provisional Patent Application Serial Number 60/744,885 bearing Attorney Docket Number 12006014 and filed on April 14, 2006, which is incorporated by reference.

FIELD OF THE INVENTION

[0002] This invention relates to use of a liquid polymer of an acrylic monomer as a carrier for colorants used as a concentrate for making colored plastic articles.

BACKGROUND OF THE INVENTION

[0003] Plastic has taken the place of other materials in a variety of industries. In the packaging industry, plastic has replaced glass to minimize breakage, reduce weight, and reduce energy consumed in manufacturing and transport. In other industries, plastic has replaced metal to minimize corrosion, reduce weight, and provide color-in-bulk products.

[0004] Attracting consumers to purchase individually-sized or family-sized containers includes branding and trade dress. Among the elements of valuable trade dress is the color of the container. Moreover, such color may need to co-exist with translucency, transparency, or other special effects for the bottle.

[0005] Existing liquid color concentrate technology uses carrier systems that are based on surfactants, oils and/or plasticizers. These products are often incompatible with many polymers resulting in loss of physical properties, processing problems like screw slippage. Many of the existing carriers affect the clarity of optically clear polymers, such as polycarbonate (PC), polymethyl methacrylate (PMMA), styrene-acrylonitrile (SAN). Therefore, liquid color concentrates are not used with these plastic resins.

[0006] Also existing color concentrate carriers have limited heat stability and not used to color polymers, such as PC which is processed at about 600°F (315°C).

[0007] Currently, pellet-based concentrates, and pre-colored resins are used. But such uses also present problems. Pellet-based concentrates for tint applications have been used at high dilution or "letdown" ratios to achieve good color distribution. Pre-colored resins are expensive to manufacture and warehouse. Such resins also undergo two heat histories (initial compounding and subsequent molding), which can be detrimental to some polymers..

SUMMARY OF THE INVENTION

[0008] What the art needs is a liquid carrier for color concentrates that need consistent and precise metering of colorant into the compound used to make the plastic article in a single or multi-stage process.

[0009] The present invention solves the problem in the art by using a liquid polymer of an acrylic monomer as a carrier for color concentrates.

[00010] One aspect of the invention is a color concentrate for plastic articles, comprising: (a) a carrier comprising a liquid polymer of an acrylic monomer; (b) colorant; and optionally (c) surfactant, optionally (d) at least one functional additive.

[00011] One feature of the present invention is that compounding the color concentrate of the present invention using an acrylic-based liquid polymer as the carrier permits letdown into the compounding equipment, via a fluid addition to the equipment.

[00012] Another feature of the present invention is that the colorant can include pigment(s), dye(s), or both as needed by the polymer engineer and product designer to achieve desired color effects.

[00013] Other features will become apparent from a description of the embodiments of the invention.

EMBODIMENTS OF THE INVENTION

[00014] Liquid Polymer of an Acrylic Monomer

[00015] The liquid carrier can be a liquid polymer (homopolymer or copolymer) of one or more acrylic monomers having a weight average molecular weight ranging from about 500 to about 200,000, and preferably from about 1000 to about 30,000, and most preferably about 1700.

[00016] The liquid polymer can have a glass transition temperature ranging from about -20°C to about -100°C, and preferably from about -40°C to about -80°C and most preferably about -70°C.

[00017] Non-limiting examples of commercially available liquid polymers of acrylic monomer(s) include Joncryl[®] brand plastic flow additives from BASF (fka Johnson Polymers) of Racine, WI, USA. These branded products are offered to the market as polymeric flow additives to improve plastic processing especially during injection molding. Of those flow additives, Joncryl[®] ADP-1200 and 1230 plastic flow additives are particularly preferred, with the former most preferred because ADP-1200 is a high efficiency acrylic fluid that provides flow with flexibility and can be used with a variety of plastics, such as acrylonitrile-butadiene-styrene (ABS), polyvinyl chloride (PVC), polybutylene terephthalate (PBT), Polycarbonate(PC), polymethyl methacrylate (PMMA), styrene-acrylonitrile (SAN), polyphenylene ether (PPE), styrene-butadiene-styrene (SBS), and, of course, acrylic polymers.

[00018] Colorant

[00019] As explained above, colorant can be a pigment, a dye, a combination of pigments, a combination of dyes, a combination of pigments and dye, a combination of pigment and dyes, or a combination of pigments and dyes. The choice of colorants depends on the ultimate color desired by the designer for the plastic article.

[00020] The science of color is well known to those skilled in the art. Without undue experimentation, one can use color matching techniques to identify a particular location in spherical color space. For example, one skilled

in the art can use the teachings of PCT Patent Application US2004/012233 to digitally map color space using specific polymer carriers and colorants as raw material ingredients. Alternatively, one can make small samples called plaques for visual review.

[00021] Colorants are commercially available from a number of sources well known to those skilled in the art. Commercially available pigments are well known to those skilled in the art and include organic and inorganic colorant chemistries. Commercially available dyes are well known to those skilled in the art and include all organic chemistries. Commercial sources for pigments and dyes include multinational companies such as BASF, Bayer, Ciba-Geigy, Color-Chem International, Sun Chemical, Zhuhai Skyhigh Chemicals, and others identified at Internet Web Sites such as

<http://www.colorpro.com/info/vendors/colorant.html> and

http://dir.yahoo.com/Business_and_Economy/Business_to_Business/Chemicals_and_Allied_Products/Pigments_and_Dyes/

[00022] Table 1 lists 51 commercially available pigment colorants in a variety of primary and secondary colors, 47 chromaties, 3 blacks, and 1 white.

Table 1 Commercial Pigment Colorants				
Raw Material Name	CI_Name	Family	COLOR	FDA*
TIOXIDE R-FC6 WHITE	PIGMENT WHITE 6	INORGANIC	WHITE	Y
REGAL 660R BLACK POWDER	PIGMENT BLACK 7	ORGANIC		N
MPC CHANNEL BLACK	PIGMENT BLACK 7	ORGANIC		Y
BK-5099 BLACK OXIDE	PIGMENT BLACK 11	INORGANIC		N
HELIOGEN BLUE K7090	PIGMENT BLUE 15:3	ORGANIC	BLUE	Y
Heliogen Blue K6903	PIGMENT BLUE B 15:1	ORGANIC	BLUE	Y
34L2000 AZURE BLUE	PIGMENT BLUE 28	INORGANIC	BLUE	Y

Table 1 Commercial Pigment Colorants				
Raw Material Name	CI_Name	Family	COLOR	FDA*
34L2001 AMAZON BLUE	PIGMENT BLUE 36	INORGANIC	BLUE	N
NUBIX G-58 ULTRAMARINE BLUE	PIGMENT BLUE 29	INORGANIC	BLUE	Y
NUBIX C-84 ULTRAMARINE BLUE	PIGMENT BLUE 29	INORGANIC	BLUE	Y
NUBIX E-28 ULTRAMARINE BLUE	PIGMENT BLUE 29	INORGANIC	BLUE	Y
HELIOGEN GREEN K-8730	PIGMENT GREEN 7	ORGANIC	GREEN	Y
HELIOGEN GREEN K 8605	PIGMENT GREEN 7	ORGANIC	GREEN	Y
CHROMIUM OXIDE GREEN G-6099	PIGMENT GREEN 17	INORGANIC	GREEN	Y
CROMOPHTAL ORANGE GP	PIGMENT ORANGE 64	ORGANIC	ORANGE	Y
2920 BRILLIANT ORANGE	PIGMENT ORANGE 79	ORGANIC	ORANGE	Y
NOVAPERM RED F5RKA	PIGMENT RED 170	ORGANIC	RED	N
225-2480 Sunbrite Scarlet 60:1	Pigment Red 60:1	ORGANIC	RED	N
IRGALITE RED LCB	PIGMENT RED 53:1	ORGANIC	RED	N
DCC-2782 Barium 2B Red	Pigment Red 60:1	ORGANIC	RED	N
Lithol Scarlet 4451	Pigment Red 48:2	ORGANIC	RED	N
CROMOPHTAL RED 2020	PIGMENT VIOLET 19	ORGANIC	RED	Y
CROMOPHTAL MAGENTA P	PIGMENT RED 202	ORGANIC	RED	Y
CROMOPHTAL PINK PT	PIGMENT RED 122	ORGANIC	RED	N
PALIOGEN RED K 3911 HD	PIGMENT RED 178	ORGANIC	RED	Y
CROMOPHTAL RED 2030	PIGMENT RED 254	ORGANIC	RED	Y
CROMOPHTAL RED 2028	PIGMENT RED 254	ORGANIC	RED	Y
Colortherm Red 110M	PIGMENT RED 101	INORGANIC	RED	Y
Colortherm Red 130M	PIGMENT RED 101	INORGANIC	RED	Y

Table 1 Commercial Pigment Colorants				
Raw Material Name	CI_Name	Family	COLOR	FDA*
Colortherm Red 180M	PIGMENT RED 101	INORGANIC	RED	Y
CINQUASIA VIOLET RT-891-D	PIGMENT VIOLET 19	ORGANIC	VIOLET	Y
CROMOPHTAL VIOLET GT	PIGMENT VIOLET 23	ORGANIC	VIOLET	N
PREMIER VU UMV (6112)	PIGMENT VIOLET 15	INORGANIC	VIOLET	Y
SICOTAN BROWN K 2750 FG	PIGMENT YELLOW 164	INORGANIC	BROWN	N
FERRITAN FZ-1000	PIGMENT YELLOW 119	INORGANIC	Tan	Y
NUBITERM Y-905K ZINC FERRITE	PIGMENT YELLOW 119	INORGANIC	Tan	Y
PV FAST YELLOW HG	PIGMENT YELLOW 180	ORGANIC	YELLOW	Y
IRGALITE YELLOW WGPB	PIGMENT YELLOW 168	ORGANIC	YELLOW	N
PV FAST YELLOW HGR (11-3071)	PIGMENT YELLOW 191	ORGANIC	YELLOW	Y
PALITOL YELLOW K 2270	PIGMENT YELLOW 183	ORGANIC	YELLOW	Y
CROMOPHTAL YELLOW HRPB	PIGMENT YELLOW 191:1	ORGANIC	YELLOW	Y
CROMOPHTAL YELLOW GRP	PIGMENT YELLOW 95	ORGANIC	YELLOW	Y
IRGALITE YELLOW WSR-P	PIGMENT YELLOW 62	ORGANIC	YELLOW	N
CROMOPHTAL YELLOW 3RLP	PIGMENT YELLOW 110	ORGANIC	YELLOW	Y
9766 FD&C YELLOW # 6	PIGMENT YELLOW 104	ORGANIC	YELLOW	Y
9765 FD&C YELLOW # 5	PIGMENT YELLOW 100	ORGANIC	YELLOW	Y
PALITOL YELLOW K 0961 (HD)	PIGMENT YELLOW 138	ORGANIC	YELLOW	Y
SICOPLAST YELLOW 10-0770	PIG YEL 138 / PIG YEL 183	ORGANIC	YELLOW	Y
SICOTAN YELLOW K 2001 FG	PIGMENT BROWN 24	INORGANIC	YELLOW	Y
SICOTAN YELLOW K 1011	PIGMENT YELLOW 53	INORGANIC	YELLOW	Y
COLORTHERM 10	PIGMENT YELLOW 42	INORGANIC	YELLOW	Y

* As publicized by the commercial producer or as tested by the applicant, or both.

[00023] Table 2 shows 14 commercially available dyes.

Table 2 Commercial Dye Colorants				
Raw Material Name	CI Name	Family	Color	FDA*
Lambdaplast Blue NL	Solvent Blue 59	Anthraquinone	Blue	N
Macrolex Blue RR Granular	Solvent Blue 97	Anthraquinone	Blue	N
Macrolex Green G Granular	Solvent Green 28	Anthraquinone	Green	N
Macrolex Green 5B Granular	Solvent Green 3	Anthraquinone	Green	N
Macrolex Orange R Granular	Disperse Orange 47	Polymethine	Orange	N
Macrolex Orange 3G Granular	Solvent Orange 60	Perinone	Orange	N
Macrolex Red EG Granular	Solvent Red 135	Perinone	Red	N
Macrolex Red E2G Granular	Solvent Red 179	Perinone	Red	N
Thermoplast Red 454	Solvent Red 195	Anthraquinone	Red	N
Macrolex Red Violet R Granular	Disperse Violet 26	Anthraquinone	Violet	N
Macrolex Violet B Granular	Solvent Violet 13	Anthraquinone	Violet	N
Macrolex Violet 3R Granular	Solvent Violet 36	Anthraquinone	Violet	N
Key Plast Yellow 3G	Solvent Yellow 93	Pyrazolone	Yellow	N
Key Plast Yellow AG	Solvent Yellow 114	Quinophthalone	Yellow	N

* As publicized by the commercial producer or as tested by the applicant, or both.

[00024] Preferably, colorants include colorants intended for transparent or translucent plastic articles, although colorants intended for opaque plastic articles are not excluded from consideration.

[00025] Achievement of a color match of a plaque with a desired color from the creativity of a designer or a pre-arranged color standard such as Pantone® color standards from an inventory of commercially available colorants is relatively straightforward for a skilled color matcher, even if a few iterations are required to satisfy the customer.

[00026] The concentration of colorant into a carrier is significant because of the relative cost of the colorant ingredient(s) and the need for that color to consistently and precisely mix and disperse into the carrier and then to

consistently and precisely dilute into the plastic resin and other compound ingredients during "letdown" of the concentrate in mixing equipment prior to formation of the pre-form embryonic bottles or other articles. Letdown ratios depend on the concentration of colorant in the color concentrate and whether the final molded product is intended to be opaque, translucent, or transparent.

[00027] Concentration of concentrate after letdown into the final molded product can range from about 0.05 to about 0.2 weight percent, and preferably from about 0.1 to about 0.5 weight percent.

[00028] The mixing equipment used to make the liquid color concentrate can be any suitable equipment already used in the art of making liquid color. For example, such equipment includes high speed "Cowles" type dispersors, media mills, three-roll mills and rotor-stator type dispersors

[00029] Mixing equipment can operate at mixing speeds ranging from about 100 rpm to about 10,000 rpm, and preferably from about 500 to about 8000 rpm. Mixing equipment can operate at temperatures ranging from about 25°C to about 100°C, and preferably from about 40°C to about 80°C.

[00030] Optional Surfactant

[00031] Surfactants are sometimes desired to aid in dispersion of dyes and pigments. Commercially available surfactants include Surfynol brand defoaming oxirane surfactants from Air Products and Chemicals.

[00032] Optional Functional Additives

[00033] Additives to improve processing or performance of the concentrate of the present invention or the polyester compound, or both, can be added according to preferences of this skilled in the art. For example, functional additives for polyester bottles can include anti-oxidants, anti-stats, acetaldehyde scavengers, blowing agents, biocides, exfoliated nanoclays, and the like. Generally, minor amounts of such additives provide improvement of performance to the color concentrate during processing with the other ingredients in the polyester resin or in performance of the polyester molded

article after manufacturing. One skilled in the art without undue experimentation can determine the appropriate concentration.

[00034] Frequently, the preparation of a colored plastic article does not involve merely color but also special effect features, such as Granite, Translucent, Pearls, Metallics, Fluorescents, Iridescent, Marbles, etc.

[00035] Non-limiting examples of such additives are commercially available from PolyOne Corporation of Avon Lake, Ohio, USA (www.polyone.com) and marketed under the following brands: OnColor FX colorants, PolyOne colorants, etc.

[00036] Plastic articles exposed to natural sunlight are exposed to ultraviolet rays that can harm the color of the article. Therefore, it is customary but not required to include ultraviolet light stabilizers in the color concentrate. This optional additive being included in the color concentrate adds value to that concentrate as a masterbatch in polymer compounding because the ultraviolet stabilizer also helps protect the polymer resin from adverse effects arising from exposure to the ultraviolet rays. Being included in a masterbatch as an additive makes the introduction of the stabilizer easier, due to better dispersion.

[00037] Commercially available stabilizers are well known to those skilled in the art and include thermal stabilizers and Tinuvin brand stabilizers from Ciba-Geigy of Berne, Switzerland. Of the choice of stabilizers, Tinuvin brand stabilizers are preferred, particularly Tinuvin 234 stabilizer.

[00038] Table 3 shows the acceptable, desirable and preferred weight percents of ingredients for color concentrates of the present invention.

Table 3			
Ingredient (Wt. %)	Acceptable Range	Desirable Range	Preferred Range
Liquid polymer of an acrylic monomer	15 -- 98%	20 -- 95%	60 -- 95%
Colorant	2 -- 75%	5 -- 60%	10 -- 40%
Optional Surfactant	0 -- 20%	0 -- 5%	0.5 -- 1.5%
Optional Functional Additives	0 -- 20%	0 -- 10%	0 -- 5%

USEFULNESS OF THE INVENTION

[00039] Color concentrates of the present invention can be letdown into plastic resins and other ingredients useful for making molded or extruded articles in ratios ranging from about 0.01% to about 2.0%, and preferably from about 0.15% to about 0.50%.

[00040] As stated previously, the plastic resins can be such as acrylonitrile-butadiene-styrene (ABS), polyvinyl chloride (PVC), polybutylene terephthalate (PBT), polymethyl methacrylate (PMMA), styrene-acrylonitrile (SAN), polyphenylene ether (PPE), Polycarbonate(PC), styrene-butadiene-styrene (SBS), and, of course, acrylic polymers.

[00041] Because of the versatility of acrylic-based polymer carrier being compatible with so many different resins, consistent and precise dispersion of color into the plastic article is possible with delivery being in a convenient liquid form.

[00042] The plastic article can be opaque, translucent, or transparent even though it has color from concentrates of the present invention. Precise color matching and consistent metering of color in amounts as little as 0.08 weight percent of concentrate can be achieved.

[00043] Other embodiments appear in the examples.

EXAMPLES

[00044] Table 4 shows seven different sets of embodiments of the invention were made by milling, using a three roll mill of lab scale size. Molding trials were conducted in a variety of plastic resins, in which clarity is quite important. Molding was done in an injection molder. PC was molded at about 315°C (600°F). PMMA and SAN were molded at about 218°C (425°F). Color distribution was excellent in all examples, and no screw slippage was observed. Moreover, the liquid dispersions appeared to have no effect on clarity of the base clear resin.

[00045] Viscosities are also reported in Table 4. These viscosities show that the acrylic polymer wets out pigments and dyes very well and stable fluid dispersions can be produced. The viscosity range is optimum for good shelf life and ease of pumping.

[00046] Haze percentages are also reported in Table 4 for all Examples molded in PMMA resin, as compared with neat PMMA. The values show no appreciable change in haze as a result of using the liquid color concentrate of the present invention.

Table 4							
Example/Ingredients	1	2	3	4	5	6	7
Surfynol MD-20 surfactant	1%	1%	1%	1%	1%	1%	0.30%
Joncryl ADP-1200 liquid acrylic polymer	59%	84%	74%	74%	89%	74%	93.39%
Macrolex Red EG granular colorant	40%						
Macrolex Orange 3G granular colorant		15%					
Macrolex Blue RR granular colorant			25%				1.33%
Macrolex Red E2G granular colorant				25%			
Heliogen Blue K-7090 colorant					10%		
Macrolex Violet B granular colorant						25%	
Raven 3500 black powder colorant							2.84%
Macrolex Blue Violet B granular colorant							0.14%
Cab-O-Sil M5 thickener							2%
Total	100%	100%	100%	100%	100%	100%	100%
Molding Trials	Molded at 0.25% by weight in PMMA, PC and SAN resins	Molded at 0.50% by weight in PMMA, PC and SAN resins	Molded at 0.25% by weight in PMMA	Molded at 0.25% by weight in PMMA	Molded at 0.25% by weight in PMMA	Molded at 0.25% by weight in PMMA	Molded at 0.25% by weight in PMMA

Table 4

Example/Ingredients	1	2	3	4	5	6	7
Viscosity	Viscosity of dispersion 8,400 cps	Viscosity of dispersion 11,680 cps	Viscosity of dispersion 4,200 cps	Viscosity of dispersion 10,040 cps	Viscosity of dispersion 3,400 cps	Viscosity of dispersion 6,000 cps	Viscosity of dispersion 4,000 cps
Haze % in PMMA samples*	2.7%	3.0%	3.0%	1.5%	5.5%	1.5%	3.27%

*Neat PMMA was tested also and had a percent haze of 2.8%.

[00047] The invention is not limited to the above embodiments. The claims follow.

What is claimed is:

1. A liquid color concentrate for plastic articles, comprising:
 - (a) a carrier comprising a liquid polymer of an acrylic monomer;
 - (b) colorant; and
 - optionally (c) surfactant, and
 - optionally (d) functional additives.
2. The concentrate of Claim 1, wherein the colorant comprises a pigment, a dye, a combination of pigments, a combination of dyes, a combination of pigments and dye, a combination of pigment and dyes, or a combination of pigments and dyes.
3. The concentrate of Claim 1, wherein the liquid polymer is a homopolymer or a copolymer having a weight average molecular weight ranging from about 500 to about 200,000.
4. The concentrate of Claim 1, wherein the liquid polymer is a homopolymer or a copolymer having a weight average molecular weight ranging from about 1000 to about 30,000.
5. The concentrate of Claim 1, wherein the liquid polymer has a glass transition temperature ranging from about -20°C to about -100°C.
6. The concentrate of Claim 1, wherein the liquid polymer can have a glass transition temperature ranging from about -40°C to about -80°C.
7. The concentrate of Claim 1, wherein the liquid polymer is present in the concentrate in an amount ranging from about 15 to about 98 weight percent, wherein the colorant is present in the concentrate in an amount ranging from about 2 to about 75 weight percent, wherein the optional surfactant is present, if

at all, in an amount ranging up to 20 weight percent, and wherein the optional functional additive is present, if at all, in an amount ranging up to 20 weight percent.

8. The concentrate of Claim 1, wherein the liquid polymer is present in the concentrate in an amount ranging from about 60 to about 95 weight percent, wherein the colorant is present in the concentrate in an amount ranging from about 10 to about 40 weight percent, wherein the optional surfactant is present, if at all, in an amount ranging from about 0.5 to about 1.5 weight percent, and wherein the optional functional additive is present, if at all, in an amount ranging up to 5 weight percent.

9. The concentrate of Claim 1, wherein the concentrate is combined with a plastic resin selected from the group consisting of acrylonitrile-butadiene-styrene (ABS), polyvinyl chloride (PVC), polybutylene terephthalate (PBT), polymethyl methacrylate (PMMA), styrene-acrylonitrile (SAN), polyphenylene ether (PPE), polycarbonate(PC), styrene-butadiene-styrene (SBS), and acrylic polymers, and combinations thereof, wherein the combination forms a colored plastic article.

10. The concentrate of Claim 9, wherein the weight of concentrate in the plastic resin ranges from about 0.01 weight percent to about 2.0 weight percent.

11. The concentrate of Claim 10, wherein the plastic article is opaque, translucent, or transparent.

12. A plastic article, comprising a concentrate of any of Claims 1-8 let down into a plastic resin selected from the group consisting of acrylonitrile-butadiene-styrene (ABS), polyvinyl chloride (PVC), polybutylene terephthalate (PBT), polymethyl methacrylate (PMMA), styrene-acrylonitrile (SAN), polyphenylene

ether (PPE), polycarbonate(PC), styrene-butadiene-styrene (SBS), and acrylic polymers, and combinations thereof.

13. The article of Claim 12, wherein the weight of concentrate in the plastic resin ranges from about 0.01 weight percent to about 2.0 weight percent.

14. The article of Claim 13, wherein the plastic article is opaque, translucent, or transparent.

15. The article of Claim 14, wherein the plastic resin is optically clear.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US2007/064989**A. CLASSIFICATION OF SUBJECT MATTER*****C08L 33/00(2006.01)i***

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC8: C08L 33/00, C08K 5/20

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Korean Utility Models and applications for Utility Models since 1975

Japanese Utility Models and applications for Utility Models since 1975

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

eKIPASS(KIPO internal) "liquid polymer & colorant & plastics & acryl & concentrate"

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 2004/16681 A2 (POLYONE CORPORATION) Feb. 26, 2004 see page 2.	1
A	WO 03/002642 A1 (POLYONE CORPORATION) Jan. 9, 2003 see abstract.	1
A	EP 0370424 A2 (FUJI PHOTO FILM CO., LTD.) May. 30, 1990 see abstract.	1
A	JP 61215248 A2 (NISSAN MOTOR CO LTD) Sep. 25, 1986 see abstract.	1

☐ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

23 AUGUST 2007 (23.08.2007)

Date of mailing of the international search report

23 AUGUST 2007 (23.08.2007)

Name and mailing address of the ISA/KR

Korean Intellectual Property Office
920 Dunsan-dong, Seo-gu, Daejeon 302-701,
Republic of Korea

Facsimile No. 82-42-472-7140

Authorized officer

LEE, Su Hyoung

Telephone No. 82-42-481-8148



INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/US2007/064989

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 2004016681 A2	26.02.2004	AU2003285495A8	03.03.2004
		AU2003285495AH	03.03.2004
		AU2003285495AA	03.03.2004
		US06916770	12.07.2005
		US20020198122A1	26.12.2002
		US2002198122A1	26.12.2002
		US2002198122AA	26.12.2002
		US6916770BB	12.07.2005
		WO2004016681A3	02.09.2004
WO 03002642 A1	09.01.2003	EP01404748A1	07.04.2004
		EP1404748A1	07.04.2004
		US20020193267A1	19.12.2002
		US2002193267AA	19.12.2002
		US2002198121A1	26.12.2002
		US2002198121AA	26.12.2002
		US2002198122A1	26.12.2002
		US2002198122AA	26.12.2002
		US2002198123AA	26.12.2002
		US6617295BB	09.09.2003
EP 0370424 A2	30.05.1990		
		JP2140252 A2	29.05.1990
		DE68924329C0	26.10.1995
		DE68924329T2	29.02.1996
		EP00370424A3	10.06.1992
		EP00370424B1	20.09.1995
		EP370424A3	10.06.1992
		US5262471A	16.11.1993
JP 61215248 A2	25.09.1986		
		None	