



(86) Date de dépôt PCT/PCT Filing Date: 2003/06/04
 (87) Date publication PCT/PCT Publication Date: 2004/04/22
 (85) Entrée phase nationale/National Entry: 2004/12/06
 (86) N° demande PCT/PCT Application No.: CN 2003/000436
 (87) N° publication PCT/PCT Publication No.: 2004/033504
 (30) Priorité/Priority: 2002/06/06 (02120861.1) CN

(51) Cl.Int.⁷/Int.Cl.⁷ C08F 4/65, C08F 10/02
 (71) Demandeurs/Applicants:
 CHINA PETROLEUM & CHEMICAL CORPORATION,
 CN;
 BEIJING RESEARCH INSTITUTE OF CHEMICAL
 INDUSTRY, CHINA PETROLEUM & CHEMICAL
 CORPORATION, CN
 (72) Inventeurs/Inventors:
 WANG, ZHIWU, CN;
 TAN, ZHONG, CN;
 LI, TIANYI, CN;
 LI, XINGBO, CN;
 ZHANG, KAI, CN;
 ...

(54) Titre : COMPOSE DE CATALYSE SOLIDE POUR LA POLYMERISATION DE L'ETHYLENE, PREPARATION
 CORRESPONDANTE ET CATALYSEUR RENFERMANT LEDIT COMPOSE
 (54) Title: A SOLID CATALYST COMPONENT FOR POLYMERIZATION OF ETHYLENE, PREPARATION THEREOF
 AND A CATALYST CONTAINING THE SAME

(57) **Abrégé/Abstract:**

The present invention provides a catalyst component used for homopolymerization or co-polymerization of ethylene, comprising at least one suitable electron donor compound supported on a composition containing magnesium and titanium, wherein the electron donor compound is selected from the group consisting of aliphatic ethers, alicyclic ethers, aromatic ethers, aliphatic ketones and alicyclic ketones, and wherein the composition containing magnesium and titanium is prepared by dissolving a magnesium compound into a solvent system to form a homogeneous solution and then contacting the solution with a titanium compound in the presence of a precipitation aid to precipitate the composition. The present invention also relates to a method for the preparation of said catalyst component and a catalyst comprising thereof, and to use of the catalyst in homopolymerization or co-polymerization of ethylene.



(72) **Inventeurs(suite)/Inventors(continued):** KOU, PENG, CN; CUI, HAIXIANG, CN; GUO, ZHENGYANG, CN;
PAN, LIANG, CN

(74) **Agent:** DENNISON ASSOCIATES

Abstract

The present invention provides a catalyst component used for homopolymerization or co-polymerization of ethylene, comprising at least one suitable electron donor compound supported on a composition containing magnesium and titanium, wherein the electron donor compound is selected from the group consisting of aliphatic ethers, alicyclic ethers, aromatic ethers, aliphatic ketones and alicyclic ketones, and wherein the composition containing magnesium and titanium is prepared by dissolving a magnesium compound into a solvent system to form a homogeneous solution and then contacting the solution with a titanium compound in the presence of a precipitation aid to precipitate the composition. The present invention also relates to a method for the preparation of said catalyst component and a catalyst comprising thereof, and to use of the catalyst in homopolymerization of ethylene or co-polymerization of ethylene with at least one C₃-C₈ α -olefin.

A Solid Catalyst Component for Polymerization of Ethylene, Preparation thereof and a Catalyst containing the same

Cross Reference of Related Application

The present application claims priority CN 02120861.1, filed on June 6, 2002, which is incorporated herein by reference in its entirety and for all purposes.

Technical field

The present invention relates to a solid catalyst component used for polymerization of olefin, in particular, ethylene, its preparation, to a catalyst comprising the same and its use.

Background

It is well known that catalyst component with magnesium, titanium, halogen and electron donor as main ingredients can be widely used in the polymerization of olefins, especially in the polymerization of ethylene or co-polymerization of ethylene and alpha-olefin(s). When such a catalyst component is used in gas phase fluidized bed polymerization process, the catalyst component is typically supported on a carrier, such as silica and the like, in order to ensure the morphology and particle size distribution of the catalyst particles to be suitable for the operation of fluidized state. For example, the catalysts for gas phase fluidized bed process disclosed in US4,302,565, US4,379,759 and CN 1064870A(corresponding to EP0499093) are prepared by impregnating a mother component formed from a titanium compound, a magnesium compound and an electron donor compound onto a carrier, such as silica and the like, and treating the impregnated mother component with an activating compound. The silica used in US4,302,565 and US4,379,759 have an average particle size of from 50 to 150 microns, a surface area greater than 50 m²/g, and an average pore size greater than 80 angstroms.

In the above mentioned patents, in order that the catalyst is suitable for gas phase fluidized bed process for polymerizing ethylene, there is relatively strict requirement in average particle size, surface area and pore size of the carrier, i.e.

silica used. In addition, the carrier material is expensive, and the silica carrier needs to be activated strictly prior to use. Thus the cost of the catalyst is high. Furthermore, since the catalyst active component is supported on carrier by a process such as impregnation and the like, the catalyst efficiency is not satisfactory. Further, the fine powder content of the polyethylene powder produced using said catalyst is relatively larger so that the particles having a particle size less than 150 microns comprise typically about 15 percent by weight of the whole powder, and this is very undesired in commercial production. When the catalyst is used in a plant for gas phase fluidized bed ethylene polymerization, it is usually fed in the form of solid so that the stability in the feeding step is poor and phenomena such as blockage and bridge formation in pipelines are easy to occur.

Chinese patent CN 85100997(corresponding to US4784983) disclosed a catalyst for olefin polymerization, which was prepared by dissolving a magnesium halide into an organic epoxy compound and an organophosphorus compound to form a homogeneous solution and reacting the solution with at least one precipitation aid, a polycarboxylic ester electron donor and titanium halide or derivative thereof. The catalyst exhibits high polymerization activity and good stereoregularity when it is used in propylene polymerization. However, when it is used in ethylene polymerization, the catalyst exhibits low polymerization activity, broad distribution of particle size of polymer and poor hydrogen response.

On the basis of above mentioned Chinese patent CN 85100997, CN 1229092A (corresponding to EP 1083187A1) disclosed a catalyst for ethylene homopolymerization or co-polymerization, which was prepared by dissolving a magnesium halide into an organic epoxy compound and an organophosphorus compound, adding an electron donor activator thereto to form a homogeneous solution, and reacting the solution with at least one precipitation aid and titanium halide or derivative thereof. The catalyst exhibits relatively high polymerization activity and the polymer obtained is good in particle morphology and high in bulk density, when the catalyst is used in slurry polymerization of ethylene. However, when the catalyst component comprising alcohol type of activator is used in gas phase process of ethylene polymerization, especially in fluidized bed process of ethylene polymerization, the results are not satisfactory. The rate of the polymerization reaction is relatively quick, especially in the initial stage, so that the polymer particles produced are fragile and the polymer particles are relatively

fine. In general, the polymer particles having a particle size of from 70 to 150 microns comprise from 50 to 60 percent by weight of the whole powder. In addition, the morphology of the polymer particles and the flowability of the polymer powder are poor.

Therefore, there exists a strong need for providing a high efficient solid catalyst component, which is capable of producing polymer having low content of fine powder, has relatively narrow distribution of particle size and appropriate average particle size, is high in catalytic activity, and is very suitable for ethylene slurry or gas phase polymerization, especially for gas phase fluidized bed process of ethylene polymerization in which catalyst is fed in the form of slurry.

It has been found that a catalyst component, which has appropriate average particle size, relatively narrow distribution of particle size, good particle morphology, particles of which are not easy to break during polymerization reaction, and which therefore is very suitable for ethylene homopolymerization or co-polymerization, especially for gas phase process of ethylene polymerization, can be obtained by supporting a suitable electron donor and optionally a titanium compound onto a composition comprising magnesium and titanium as carrier component, or by supporting a suitable electron donor and a titanium compound onto a magnesium compound-containing composition, and optionally treating the product containing magnesium, titanium and electron donor with an activator, without using silica and the like as carrier. Since the catalytic activity of the catalyst according to the present invention is also improved greatly, it is possible to dilute the catalyst with a inert diluent and achieve homogeneous feeding in liquid state by means of pumping, thereby overcoming the problems encountered in the above catalyst feeding step.

Summary of the invention

One object of the present invention is to provide a catalyst component used for homopolymerization or co-polymerization of ethylene, comprising at least one electron donor compound supported on a composition containing magnesium and titanium, wherein the electron donor compound is selected from the group consisting of aliphatic ethers, cyclic ethers, aromatic ethers, aliphatic ketones and alicyclic ketones, and wherein the composition containing magnesium and titanium is prepared by dissolving a magnesium compound into a solvent system

to form a homogeneous solution and then contacting the solution with a titanium compound in the presence of a precipitation aid to precipitate the composition.

Another object of the present invention is to provide a catalyst component used for homopolymerization or co-polymerization of ethylene, comprising at least one electron donor compound and at least one titanium compound supported on a magnesium compound-containing composition, wherein the electron donor compound is selected from the group consisting of aliphatic ethers, cyclic ethers, aromatic ethers, aliphatic ketones and alicyclic ketones.

A further object of the present invention is to provide a method for the preparation of a catalyst component used for homopolymerization or co-polymerization of ethylene, comprising the steps of:

dissolving a magnesium compound into a solvent system containing an organic epoxy compound and an organophosphorus compound to form a homogeneous solution;

contacting the solution with a titanium compound in the presence of a precipitation aid to precipitate a solid;

treating the obtained solid with an electron donor compound and, optionally, the titanium compound to obtain a product; and

optionally, activating the resultant product with an activator.

A still further object of the present invention is to provide a catalyst for homopolymerization or co-polymerization of ethylene, comprising the reaction product of the following two components:

- (a) catalyst component as defined above; and
- (b) organoaluminum compound as cocatalyst component.

A yet still object of the present invention is to provide a use of the catalyst of the present invention in homopolymerization of ethylene or co-polymerization of ethylene with at least one C₃-C₈ α -olefin. In a preferred embodiment, the present invention provides a use of the catalyst according to the present invention in homopolymerization or co-polymerization of ethylene in gas phase process or slurry process.

A yet still object of the present invention is to provide a method for homopolymerization of ethylene or co-polymerization of ethylene with at least one C₃-C₈ α -olefin, comprising contacting ethylene or ethylene and at least one C₃-C₈ α -olefin with the catalyst of the present invention under polymerization conditions. In a preferred embodiment, the present invention provides a method

for homopolymerization of ethylene or co-polymerization of ethylene with at least one C₃-C₈ α -olefin, comprising contacting ethylene or ethylene and at least one C₃-C₈ α -olefin with the catalyst of the present invention under polymerization conditions in slurry or gas phase process.

Detailed description of the present invention

In one aspect, the present invention provides a catalyst component used for homopolymerization or co-polymerization of ethylene, comprising at least one suitable electron donor compound supported on a composition containing magnesium and titanium.

The composition containing magnesium and titanium can broadly utilize a large number of Ziegler_Natta catalyst components containing magnesium and titanium well known by those skilled in the art. Of them the preferred are those prepared by dissolving a magnesium compound into a solvent system to form a homogeneous solution and then contacting the solution with a titanium compound and, optionally, a suitable precipitation aid to precipitate a composition containing magnesium and titanium.

The magnesium compound can be selected from the group consisting of magnesium dihalides, hydrates or alcohol adducts of magnesium dihalide, derivatives formed by replacing one halogen atom of magnesium dihalide with hydrocarbyloxy group or halo-hydrocarbyloxy group, or their mixture.

Said solvent system can comprise any of a large number of electron donor compounds which have been disclosed by prior art and are capable of dissolving magnesium compounds, such as, for example organic alcohols, carboxylic acids, aldehydes, amines, transition metal alkoxides and the like. Such electron donor compounds capable of converting solid magnesium compounds into solution are disclosed in, for example, US6,111,038, which is incorporated herein by reference.

Preferably, said solvent system comprises an organic epoxy compound and an organophosphorus compound, and if appropriate, it further comprises an alkane or an arene as diluent. Thus, in a preferred embodiment of the present invention, the composition containing magnesium and titanium can be prepared by dissolving a magnesium compound into a solvent system containing an organic epoxy compound and an organophosphorus compound to form a homogeneous solution, and contacting then the solution with a titanium halide or derivative

thereof in the presence of a precipitation aid to precipitate a solid. The preparation method is disclosed in details in Chinese Patent CN85100997 (corresponding to US4,784,983), which is incorporated herein by reference. It is possible to incorporate an activity promoter, such as, alcohols, ethers, etc. into the magnesium-containing solution prior to contacting the solution with the titanium halide or derivative thereof, and reference can be made to CN 1229092A (corresponding to EP 1083187A1), which is incorporated herein by reference, for related content.

In another preferred embodiment of the present invention, the composition containing magnesium and titanium can be prepared by dissolving a magnesium compound into a solvent system containing an branched aliphatic alcohol to form a homogeneous solution, and contacting then the solution with a titanium halide or derivative thereof in the presence of a precipitation aid to precipitate a solid.

The organic epoxy compound useful in the present invention can be at least one selected from the group consisting of oxides of aliphatic olefin, diene or halogenated aliphatic olefin or diene, glycidyl ethers and cyclic ethers, having from 2 to 8 carbon atoms. Examples thereof comprise, but are not limited to, ethylene oxide, propylene oxide, butylene oxide, butadiene oxide, butadiene dioxide, epichlorohydrin, glycidyl methyl ether, and diglycidyl ether.

The organophosphorus compound useful in the present invention can be at least one selected from the group consisting of hydrocarbyl esters or halohydrocarbyl esters of ortho-phosphoric acid or phosphorous acid. Examples thereof comprise, but are not limited to, trimethyl phosphate, triethyl phosphate, tributyl phosphate, triphenyl phosphate, trimethyl phosphite, triethyl phosphite, tributyl phosphite, and triphenyl phosphite.

One example of the suitable branched aliphatic alcohol is 2-ethylhexanol.

In general, the solvent system further comprises inert hydrocarbon diluent, including, but not limited to, aromatic hydrocarbon, for example benzene, toluene, xylene and ethylbenzene; aliphatic hydrocarbon, for example heptane, octane, nonane, decane, kerosene, solvent oil and white oil.

The precipitation aids useful in the present invention can be selected from the group consisting of organic acids, organic acid anhydrides, ethers, ketones, and mixture thereof. Examples thereof comprise, but are not limited to, acetic anhydride, phthalic anhydride, succinic anhydride, maleic anhydride, 1,2,4,5-benzene tetracarboxylic acid dianhydride, acetic acid, propionic acid, butyric acid,

acrylic acid, methacrylic acid, acetone, methyl ethyl ketone, benzophenone, dimethyl ether, diethyl ether, dipropyl ether, dibutyl ether and dipentyl ether.

One main characteristic of the catalyst component of the present invention is to support further at least one of suitable electron donors and, optionally, a titanium halide or derivative thereof onto, for example, the composition containing magnesium and titanium.

The electron donor compounds useful in the present invention can be selected from the group consisting of aliphatic ethers, alicyclic ethers, aromatic ethers, aliphatic ketones and alicyclic ketones. Preferably, the electron donor compounds can be selected from the group consisting of aliphatic ethers having total from 2 to 12 carbon atoms, cyclic ethers having from 3 to 5 carbon atoms, aromatic ethers having total from 7 to 8 carbon atoms, saturated or unsaturated aliphatic ketones having from 3 to 6 carbon atoms, alicyclic ketones having from 5 to 10 carbon atoms. Examples thereof comprise, but are not limited to, diethyl ether, di-n-butyl ether, dihexyl ether, ethyl phenyl ether, tetrahydrofuran (THF), acetone, butanone, isobutyl methyl ketone, 4-methyl-3-penten-2-one, hexadione, and cyclohexanone. These electron donors can be used alone or in a combination.

The titanium compounds useful in the present invention can preferably have a general formula $Ti(OR)_aX_b$, in which R is C_1-C_{14} aliphatic hydrocarbyl or aromatic hydrocarbyl, X is halogen, a is 0, 1 or 2, b is an integer of from 1 to 4, and the sum of $a + b$ is 3 or 4. Specifically, the titanium compound used can be one or more selected from the group consisting of titanium tetrachloride, titanium tetrabromide, titanium tetraiodide, tetrabutyl titanate, tetraethyl titanate, titanium monochloride triethoxide, titanium dichloride diethoxide, titanium trichloride monoethoxide, and titanium trichloride, preferably titanium tetrachloride, titanium trichloride monoethoxide, and titanium trichloride.

In another aspect, the present invention provides a catalyst component used for homopolymerization or co-polymerization of ethylene, comprising at least one suitable electron donor compound and at least one titanium compound supported on a magnesium compound-containing composition, wherein the electron donor compound is selected from the group consisting of aliphatic ethers, alicyclic ethers, aromatic ethers, aliphatic ketones and alicyclic ketones. The electron donor compounds and titanium compounds used are those described above. The magnesium compound-containing composition can be, for example, so-called "spherical carrier" well known in the art, which is a complex of magnesium

dichloride and ethanol. Reference can be made to EP395083, which is incorporated herein by reference, for details of the method for the preparation of the spherical carrier.

The catalyst component of the present invention can be treated with at least one activator based on the requirement to the catalyst activity during the actual application.

The activators that can be used have a general formula $AlR'_cX'_dH_e$, in which R' is saturated hydrocarbyl having 1 to 14 carbon atoms, X' is a halogen, d is 1 or 2, e is 0 or 1, and the sum of $c+d+e$ is 3. Examples of the activators include, but are not limited to, $AlEt_3$, $Al(n-C_6H_{13})_3$, $Al(n-Bu)_3$, $Al(i-Bu)_3$, $AlEt_2Cl$, $Al(n-C_8H_{17})_3$, $AlEt_2H$.

In a preferred embodiment, the present invention provides a method for the preparation of a catalyst component used for homopolymerization or copolymerization of ethylene, comprising the steps of:

(i) preparing a composition containing magnesium and titanium by dissolving a magnesium compound into a solvent system containing an organic epoxy compound and an organophosphorus compound to form a homogeneous solution, and then contacting the solution with a titanium compound in the presence of a precipitation aid to precipitate a solid,

wherein individual raw material can be used in the amount of from 0.2 to 10 mole for the organic epoxy compound, from 0.1 to 3 mole for the organophosphorus compound, from 0.03 to 1.0 mole for the precipitation aid, from 0.5 to 120 mole for the titanium compound, based on per mole magnesium compound;

(ii) treating the solid obtained in step (i) with an electron donor compound and, optionally, the titanium compound, wherein individual raw material can be used in the amount of from 0 to 30 mole, preferably from 0.5 to 10 mole for the titanium compound, from 0.01 to 10 mole, preferably from 0.05 to 1 mole for the electron donor compound, based on per mole magnesium compound; and

(iii) optionally, activating the treated product obtained in step (ii) with an activator having a general formula $AlR'_cX'_dH_e$, in which R' is saturated hydrocarbyl having 1 to 14 carbon atoms, X' is a halogen, d is 1 or 2, e is 0 or 1, and the sum of $c+d+e$ is 3, wherein the activator can be used in the amount of from 0.1 to 10 mole, based on per mole magnesium compound.

In the method described above, preferably the titanium compound used has a

general formula $Ti(OR)_aX_b$, in which R is C_1-C_{14} aliphatic hydrocarbyl or aromatic hydrocarbyl, X is halogen, a is 0, 1 or 2, b is an integer of from 1 to 4, and the sum of a + b is 3 or 4, and examples thereof are listed hereinbefore.

Generally, the catalyst component of the present invention comprises from 5 to 30 percent by weight of magnesium, from 0.1 to 10 percent by weight of titanium, from 15 to 65 percent by weight of halogen, and from 1 to 60 percent by weight of electron donor, based on the total weight of the catalyst component.

The average particle size of the catalyst component of the present invention, expressed as D50 value, is typically from 5 to 35 microns, preferably from 10 to 25 microns.

The present invention also relates to a catalyst for homopolymerization or copolymerization of ethylene, comprising the reaction product of catalyst component described above and organoaluminum compound as cocatalyst component. The organoaluminum compounds used in the polymerization of olefins as cocatalyst are well known in the art. In one embodiment, the organoaluminum compound used is alkylaluminum compounds having a formula of AlR''_3 , in which R'' , which may be identical with or different from one another, represent alkyl having 1 to 8 carbon atoms or chlorine with the proviso that R'' are not chlorine simultaneously. The alkylaluminum compounds can be used alone or in a combination, and are preferably $AlEt_3$, $Al(i-Pro)_3$, $Al(n-Bu)_3$, $Al(i-Bu)_3$, $Al(n-C_6H_{13})_3$, $Al(n-C_8H_{17})_3$, $AlEt_2Cl$.

The ratio of the catalyst component to the organoaluminum compound can be from 1: 5 to 1:100, preferably from 1:8 to 1:30, counted on the molar ratio of titanium: aluminum.

The catalysts of the invention are suitable for use in homopolymerization of ethylene or copolymerization of ethylene with other alpha-olefin(s). The alpha-olefin can be one or more selected from the group consisting of propylene, 1-butene, 1-pentene, 1-hexene, 1-octene and 4-methyl-1-pentene. Polymerization process can employ gas phase, slurry or solution process, preferably gas phase fluidized bed process, in particular, gas phase fluidized bed process operated in condensing technology. Since the catalytic activity of the catalyst according to the present invention is very high, it is possible to dilute the catalyst with an inert diluent, such as mineral oil, and achieve homogeneous catalyst feeding in slurry form by means of pumping so that the operation is stable.

Embodiments of the Invention

The following examples further describe the invention, but do not make limitation to the invention in any way. Unless indicated otherwise, all operations were carried out under nitrogen atmosphere.

Testing methods:

1. Melt index (MI): measured according to ASTM D1238-99, at 190_, under 2.16kg loading .
2. Flow index (FI): measured according to ASTM D1238-99, at 190_, under 21.6kg loading.
3. Melt-Flow Ratio (MFR): the ratio of Melt index to Flow index measured according to above procedure.
4. Density of the polymer: measured according to ASTM D1505-98.
5. Distribution of the particle size: measured using a Malvern Instr. 2600, available from Malvern Company, England, according to a method based on the diffraction of monochromatic laser.

Example 1

1. Preparation of the catalyst component

To a reactor which was completely purged with N₂ were added successively 4.8g of anhydrous magnesium chloride, 93ml of toluene, 4.0ml of epichlorohydrin, and 12.5ml of tributyl phosphate. With stirring at 450 rpm, the mixture was heated to 60°C and held at the temperature for 2 hours for reaction, then 1.4g of phthalic anhydride was added thereto and the reaction mixture was held at that temperature for further one hour for reaction. The reaction mixture was cooled to -28°C and 56ml TiCl₄ was added dropwise thereto over one hour, then the temperature was increased slowly to 85°C over 4 hours and maintained for further one hour. Solid was precipitated gradually during the heating. After removing the mother liquid by filtration, the filter cake was washed with toluene and hexane individually twice and then dried to give solid A containing magnesium and titanium.

To another reactor completely purged with N₂ were added successively 10 g of solid A, 90 ml of isopentane, 0.3 g of titanium trichloride and 30 ml of

tetrahydrofuran. The mixture was allowed to react for one hour at room temperature. After removing the mother liquid by filtration, to the filter cake were added 90 ml of isopentane and 3.5 ml of 26.43 percent by volume solution of monochlorodiethylaluminium in isopentane, and the mixture was allowed to react for one hour at room temperature, then dried by evaporation to give 11.5 g of particulate solid component B. Solid component B was found to contain 1.43 percent by weight of titanium, 12.8 percent by weight of magnesium, and 49.1 percent by weight of tetrahydrofuran.

2. Slurry polymerization of ethylene

With stirring, to a 2 liters stainless steel autoclave, which had been well evacuated and replaced with hydrogen, were added about 0.5 liter of hexane by means of nitrogen pressure, 2ml of 1mmol/ml solution of AlEt_3 in hexane using a syringe and about 30mg of the above solid component B. Then to the reactor was supplemented hexane to 1 liter of total amount. Upon completion, the reactor was heated to 85°C , introduced hydrogen to make the fractional pressure of hydrogen in the autoclave be 0.28MPa, then introduced ethylene gas to make its fractional pressure be 0.75MPa. The polymerization reaction was continued for 2 hours at constant temperature of 85°C and ethylene was made up during the polymerization to maintain the fractional pressure of ethylene. Then the temperature of the autoclave was reduced, the pressure was relieved and the polymer slurry was discharged. After removing hexane, the polymer was dried in air under an infrared lamp to give polyethylene powder. The results of ethylene polymerization were listed in Table 1. The particle sizes of the polymer obtained and the catalyst component B were respectively determined, and the results were listed in Tables 2 and 3.

Example 2

To a reactor completely purged with N_2 were added successively 10 g of solid A obtained in example 1 and 90 ml of isopentane. 0.7 ml of titanium tetrachloride and 5 ml of tetrahydrofuran were added dropwise at room temperature, and the mixture was allowed to react for one hour at room temperature. To the reaction mixture was further added 2 ml of 26.43 percent by volume solution of monochlorodiethylaluminium in isopentane, and the mixture was allowed to react for one hour at room temperature, then dried by evaporation to give 11.3 g of solid

component B, which was found to contain 2.90 percent by weight of titanium, 12.0 percent by weight of magnesium, and 20.6 percent by weight of tetrahydrofuran.

The catalyst component was evaluated and the polymerization procedure and conditions were same as that described in example 1. The results were showed in Table 1.

Example 3

To a reactor completely purged with N₂ were added successively 10 g of solid A obtained in example 1, 60ml of toluene and 40ml of titanium tetrachloride. 8.3 ml of tetrahydrofuran was added dropwise at room temperature, and the mixture was heated to 120_ and held at that temperature to react for one hour. After removing the mother liquid by filtration, the filter cake was washed with hexane thrice and then dried under vacuum to give 10.6 g of solid component B, which was found to contain 3.61 percent by weight of titanium, 13.5 percent by weight of magnesium, and 24.1 percent by weight of tetrahydrofuran.

The catalyst component was evaluated and the polymerization procedure and conditions were same as that described in example 1. The results were showed in Table 1.

Example 4

To a reactor which was completely purged with N₂ were added successively 4.8g of anhydrous magnesium chloride, 92ml of toluene, 4.0ml of epichlorohydrin, and 12.5ml of tributyl phosphate. With stirring at 450 rpm, the mixture was heated to 60°C and held at the temperature for 2 hours for reaction, then 1.4g of phthalic anhydride was added thereto and the reaction was continued for further one hour. The reaction mixture was cooled to -28°C and 56ml of TiCl₄ was added dropwise thereto over one hour, then the temperature was increased slowly to 85°C over 4 hours and maintained for further one hour for reaction. Solid was precipitated gradually during the heating. After removing the mother liquid by suction filtration, the filter cake was washed with hexane twice to give solid A containing magnesium and titanium. To the reactor containing the solid A was added 60ml of hexane, and 2.4 ml of tetrahydrofuran was added with stirring. The mixture was allowed to react at room temperature for one hour, then washed twice with hexane and dried under vacuum to give 6.72g of particulate solid

component B. The solid component B was found to contain 2.54 percent by weight of titanium, 17.3 percent by weight of magnesium, and 16.9 percent by weight of tetrahydrofuran.

The catalyst component was evaluated and the polymerization procedure and conditions were same as that described in example 1. The results were showed in Table 1.

Example 5

To a reactor which was completely purged with N₂ were added successively 4.8g of anhydrous magnesium chloride, 92ml of toluene, 4.0ml of epichlorohydrin, and 12.5ml of tributyl phosphate. With stirring at 450 rpm, the mixture was heated to 60°C and held at the temperature for 2 hours for reaction, then 1.4g of phthalic anhydride was added thereto and the reaction was continued for further one hour. The reaction mixture was cooled to -28°C and 56ml of TiCl₄ was added dropwise thereto over one hour, then the temperature was increased slowly to 85°C over 4 hours and maintained for further one hour for reaction. Solid was precipitated gradually during the heating. After removing the mother liquid by suction filtration, the filter cake was washed with hexane twice to give solid A containing magnesium and titanium. To the reactor containing the solid A was added 90ml of hexane, and 10ml of titanium tetrachloride was added with stirring. The mixture was allowed to react at 60_ for 0.5 hour. After suction filtering, to the residue was added 60ml of hexane, and 1.5ml of tetrahydrofuran was added with stirring. The mixture was allowed to react at room temperature for one hour, then washed twice with hexane and dried under vacuum to give 7.68g of particulate solid component B. The solid component B was found to contain 8.32 percent by weight of titanium, 17.9 percent by weight of magnesium, and 10.2 percent by weight of tetrahydrofuran.

The catalyst component was evaluated and the polymerization procedure and conditions were same as that described in example 1. The results were showed in Table 1.

Example 6

To a reactor which was completely purged with N₂ were added successively 4.8g of anhydrous magnesium chloride, 93ml of toluene, 4.0ml of epichlorohydrin, and 12.5ml of tributyl phosphate. With stirring at 450 rpm, the

mixture was heated to 60°C and held at the temperature for 2 hours, then 1.4g of phthalic anhydride was added thereto and the reaction mixture was held at that temperature for further one hour. The reaction mixture was cooled to -28°C and 56ml of TiCl₄ was added dropwise thereto over one hour while maintaining constant temperature, then the temperature was increased slowly to 85°C over 4 hours and maintained for further one hour. Solid was precipitated gradually during the heating. After removing the mother liquid by suction filtration, the filter cake was washed twice with hexane and sucking filtered to give solid A containing magnesium and titanium.

To the reactor containing above solid A was added 60ml of hexane, then 1.5 ml of tetrahydrofuran was added dropwise with stirring, and the mixture was allowed to react for one hour at room temperature. After suction filtration, the solid residue was washed twice with hexane, then to the reactor was added 60ml of hexane, and the temperature was cooled to -10 °C. Then, 1.5ml of 26.43 percent by volume solution of monochlorodiethylaluminium in hexane was added slowly to the reactor while maintaining constant temperature. The mixture was slowly warmed to room temperature, followed by suction filtration and washing twice with hexane. Drying under vacuum gave 7.58 g of particulate solid component B, which was found to contain 2.30 percent by weight of titanium, 17.6 percent by weight of magnesium, and 12.2 percent by weight of tetrahydrofuran.

The catalyst component was evaluated and the polymerization procedure and conditions were same as that described in example 1. The results were showed in Table 1.

Comparative Example 1

A catalyst component was prepared according to the procedure disclosed in US4,302,565 and US4,379,759.

Activating silica: 948 grade spherical silica, available from Grace Davison_US, was activated at 600_ for 4 hours.

Under nitrogen atmosphere, to a reactor were added 100ml THF, 0.74g of titanium trichloride and 1.13g of anhydrous magnesium chloride. The mixture was heated to 70_ and allowed to react for 1 hour to give a mother stock ready for use. To another reactor were added 60ml of isopentane, 10g of the above activated silica and 4.3ml of triethyl aluminum. The mixture was allowed to react at room temperature for 30 minutes. Then the isopentane in the reactor was evaporated at

55_ to such an extent that the content of aluminum in the material contained in the reactor was 1.65wt%. Thereafter, the mother stock prepared above was transferred to the reactor, and the temperature was increased so that reflux occurred. After maintaining constant temperature for 1 hour, the THF in the reactor was evaporated to such an extent that the content of THF in the material contained in the reactor was 12.6wt%. Then 86ml of isopentane and 5.3ml of monochlorodiethylaluminium were added thereto, and the reaction was continued at room temperature for 30 minutes. Next, 3.3ml of tri-n-hexylaluminium was added thereto, and the reaction was continued at room temperature for 30 minutes. Particulate solid was obtained by drying under vacuum. The final catalyst component was found to contain 0.78 percent by weight of titanium, 1.58 percent by weight of magnesium, and 10.9 percent by weight of tetrahydrofuran.

The catalyst component was evaluated and the polymerization procedure and conditions were same as that described in example 1. The results were showed in Table 1.

Comparative Example 2

A catalyst component was prepared according to the procedure disclosed in CN 1229092A (corresponding to EP 1083187A1).

To a reactor which was completely replaced with high pure N₂ were added successively 4g of anhydrous magnesium chloride, 60ml of toluene, 2.2ml of epichlorohydrin, 4.6ml of tributyl phosphate and 1.0ml of ethanol. The mixture was heated to 80°C with stirring and held at the temperature for 15 minutes to dissolve the solid completely thereby giving a homogeneous solution. Then 1.1g of phthalic anhydride was added thereto and the temperature was maintained for further one hour. The solution was cooled to -25°C and added dropwise 0.5mol of TiCl₄. Then the temperature was increased slowly to 80°C and maintained for 3 hours for reaction. After filtration, the cake was washed with toluene for six times and then hexane for six times, and dried under vacuum to give a solid catalyst component.

The catalyst component was evaluated and the polymerization procedure and conditions were same as that described in example 1. The results were showed in Table 1. The particle sizes of the polymer obtained and the catalyst component were respectively determined, and the results were listed in Tables 2 and 3.

Table 1 The results of polymerization for examples and comparative examples

Ex. No.	Activity_gPE /gcat_	Bulk Density_g/c m ³ _	Content of fine powder less than 150_m_Wt%_	MI _g/10min_
Example 1	6677	0.350	5.2	2.02
Example 2	11196	0.353	10.8	0.56
Example 3	8060	0.417	10.7	0.22
Example 4	7547	0.343	0.7	0.91
Example 5	9863	0.328	1.6	0.60
Example 6	9750	0.45	1.4	1.3
Comparative Example 1	840	0.36	14.7	0.48
Comparative Example 2	30700	0.37	54.6	0.51

Table 2 Comparison of the distribution of particle size of the polymer between example 1 and comparative example 2

	>800 μ m	800_350 μ m	350_150 μ m	150_75 μ m	<75 μ m
Example 1	8.6	57.8	28.4	4.1	1.1
Comparative Example 2	8.0	11.0	26.4	44.6	10.0

Table 3 Comparison of the distribution of particle size of the catalyst component between example 1 and comparative example 2

	d10, μ m	d50, μ m	d90, μ m
Example 1	3.443	19.23	31.032
Comparative Example 2	2.549	7.682	15.019

Example 7

A slurry mixture with a catalyst component concentration of 1mgTi/ml was prepared by mixing 1g of solid catalyst component B obtained in example 3 with white oil, tri-n-hexyl aluminum and monochlorodiethylaluminium, wherein tri-n-hexyl aluminum and monochlorodiethylaluminium were used in such amount that

the molar ratio of tri-n-hexyl aluminum to tetrahydrofuran was equal to 0.2 and the molar ratio of monochlorodiethylaluminium to tetrahydrofuran was equal to 0.5.

Gas phase co-polymerization of ethylene and 1-butene

Co-polymerization of ethylene and 1-butene was carried out using the slurry mixture prepared above and cocatalyst, i.e. triethyl aluminum. The co-polymerization experiment was performed in a fluidized bed pilot plant of 150 mm operated in batch mode. The conditions for copolymerization and some results were as follows:

- Polymerization Temperature: 88°C
- Amount of Catalyst: 1ml of the above slurry mixture
- Amount of Cocatalyst: 2.5g , triethyl aluminum
- Total Pressure: 1700kPa
- Molar Ratio of 1-Butene to Ethylene: 0.146
- Molar Ratio of Hydrogen to Ethylene: 0.149
- Reaction Time: 3.0 hours
- Flow Rate of the Gases: 0.28m/sec
- Density of the Polymer: 0.922 g/cm³
- Melt Index of the Polymer: 0.75g/10mins
- Flow Index of the Polymer: 22.2g/10mins
- MFR of the Polymer: 29.6
- Yield of Polymer: 6999gPE/gCat.
- Bulk Density of the Polymer Powder: 0.31g/cm³

Example 8

1. Preparation of the catalyst component

To a reactor which was completely purged with N₂ were added successively 6.5kg of anhydrous magnesium chloride, 124.6 liters of toluene, 5.4 liters of epichlorohydrin, and 16.9 liters of tributyl phosphate. With stirring at 130 rpm, the mixture was heated to 60°C and held at the temperature for 3.5 hours, then 1.89kg of phthalic anhydride was added thereto and the reaction mixture was held at that temperature for further one hour. The reaction mixture was cooled to -28°C and 75.8 liters of TiCl₄ was added dropwise thereto, then the temperature was increased slowly to 80°C over 4 hours and maintained for further one hour. Solid

was precipitated gradually during the heating. After removing the mother liquid by filtration, the filter cake was washed with toluene and hexane individually for three to five times and then dried to give solid A containing magnesium and titanium.

To a dissolving reactor were added 2 liters of tetrabutyl titanate and 6.8 liters of THF. After homogenizing by stirring, 680 grams of titanium trichloride was added and dissolved with a stirring speed of 200 rpm to give a titanium compound-containing solution.

The above prepared solid A was transferred to another reactor completely purged with N₂, and 100 liters of hexane was added thereto. With stirring at 130 rpm, 8.26 liters of titanium compound-containing solution prepared above was added dropwise at 10_. The mixture was allowed to react for one hour at room temperature. After removing the mother liquid by filtration and washing the solid residue twice with hexane, 80 liters of hexane and 4.4 liters of 14 percent by volume solution of monochlorodiethylaluminium in hexane were added thereto, and the mixture was allowed to react for one hour, then dried under vacuum to give 16.0 kilograms of particulate solid component B. Solid component B was found to contain 3.13 percent by weight of titanium, 17.1 percent by weight of magnesium, 0.73 percent by weight of aluminum, and 30.2 percent by weight of tetrahydrofuran.

2. Slurry polymerization

The catalyst component was evaluated and the polymerization procedure and conditions were same as that described in example 1. The results were showed in Table 4.

3. Gas phase co-polymerization of ethylene and 1-butene

A slurry mixture with a catalyst component concentration of 1mgTi/ml was prepared by mixing 1g of solid catalyst component B prepared above with white oil, tri-n-hexyl aluminum and monochlorodiethylaluminium, wherein tri-n-hexyl aluminum and monochlorodiethylaluminium were used in such amount that the molar ratio of tri-n-hexyl aluminum to tetrahydrofuran was equal to 0.2 and the molar ratio of monochlorodiethylaluminium to tetrahydrofuran was equal to 0.5.

Co-polymerization of ethylene and 1-butene was carried out using the slurry mixture prepared above and cocatalyst, i.e. triethyl aluminum. The co-

polymerization experiment was performed in a fluidized bed pilot plant of 150 mm operated in batch mode. The conditions for copolymerization and some results were as follows:

Polymerization Temperature: 88°C
Amount of Catalyst: 1ml of the above slurry mixture
Amount of Cocatalyst: 2.5g , triethyl aluminum
Total Pressure: 1700kPa
Molar Ratio of 1-Butene to Ethylene: 0.31
Molar Ratio of Hydrogen to Ethylene: 0.12
Reaction Time: 3.0 hours
Flow Rate of the Gases: 0.28m/sec
Density of the Polymer: 0.919 g/cm³
Melt Index: 1.84g/10min
MFR: 30.2
Yield: 14100gPE/gCat.
Bulk Density of the Polymer Powder: 0.32g/cm³

Example 9

1. Preparation of the catalyst component

To a reactor which was completely purged with N₂ were added successively 4.8g of anhydrous magnesium chloride, 93ml of toluene, 4.0ml of epichlorohydrin, and 12.5ml of tributyl phosphate. With stirring at 450 rpm, the mixture was heated to 60°C and held at the temperature for 2 hours for reaction, then 1.4g of phthalic anhydride was added thereto and the reaction was continued for further one hour. The reaction mixture was cooled to -28°C and 56ml of TiCl₄ was added dropwise thereto, then the temperature was increased slowly to 85°C over 4 hours and maintained for further one hour for reaction. Solid was precipitated gradually during the heating. After removing the mother liquid by suction filtration, the filter cake was washed with toluene and hexane individually twice, then dried to give solid A containing magnesium and titanium. To the reactor containing the solid A were added 100ml of hexane, and then 1.5ml of cyclohexanone with stirring. The mixture was allowed to react at room temperature for one hour, then washed thrice with hexane and dried under vacuum to give 5.2g of particulate solid component B. The solid component B was found to contain 2.0 percent by weight of titanium, 17.5 percent by weight of

magnesium, and 14.5 percent by weight of cyclohexanone.

2. Slurry polymerization

The catalyst component was evaluated in slurry polymerization process and the polymerization procedure and conditions were same as that described in example 1. The results were showed in Table 4.

Example 10

The procedure of example 9 was repeated, except substituting 1.7ml of 4-methyl-3-penten-2-one for 1.5ml of cyclohexanone, thereby giving 7.3g of particulate solid component B, which was found to contain 3.44 percent by weight of titanium, 17.4 percent by weight of magnesium, and 17.8 percent by weight of 4-methyl-3-penten-2-one.

The catalyst component was evaluated in slurry polymerization process and the polymerization procedure and conditions were same as that described in example 1. The results were showed in Table 4.

Example 11

The procedure of example 9 was repeated, except substituting 1.5ml of phenyl ethyl ether for 1.5ml of cyclohexanone, thereby giving 5.6g of particulate solid component B, which was found to contain 1.46 percent by weight of titanium, 17.2 percent by weight of magnesium, and 2.22 percent by weight of phenyl ethyl ether.

The catalyst component was evaluated in slurry polymerization process and the polymerization procedure and conditions were same as that described in example 1. The results were showed in Table 4.

Example 12

The procedure of example 9 was repeated, except substituting 1.5ml of di-n-butyl ether for 1.5ml of cyclohexanone, thereby giving 6.3g of particulate solid component B, which was found to contain 1.77 percent by weight of titanium, 18.1 percent by weight of magnesium, and 2.71 percent by weight of di-n-butyl ether.

The catalyst component was evaluated in slurry polymerization process and the polymerization procedure and conditions were same as that described in

example 1. The results were showed in Table 4.

Example 13

The procedure of example 9 was repeated, except substituting 1.5ml of butanone for 1.5ml of cyclohexanone, thereby giving 7.3g of particulate solid component B, which was found to contain 3.38 percent by weight of titanium, 17.7 percent by weight of magnesium, and 15.8 percent by weight of butanone.

The catalyst component was evaluated in slurry polymerization process and the polymerization procedure and conditions were same as that described in example 1. The results were showed in Table 4.

Example 14

The procedure of example 9 was repeated, except substituting 1.5ml of 2,5-hexadione for 1.5ml of cyclohexanone, thereby giving 7.2g of particulate solid component B, which was found to contain 1.79 percent by weight of titanium, 17.2 percent by weight of magnesium, and 15.7 percent by weight of 2,5-hexadione.

The catalyst component was evaluated in slurry polymerization process and the polymerization procedure and conditions were same as that described in example 1. The results were showed in Table 4.

Example 15

The procedure of example 9 was repeated, except substituting 1.5ml of tetrahydropyran for 1.5ml of cyclohexanone, thereby giving 10.5g of particulate solid component B, which was found to contain 1.79 percent by weight of titanium, 17.6 percent by weight of magnesium, and 13.4 percent by weight of tetrahydropyran.

The catalyst component was evaluated in slurry polymerization process and the polymerization procedure and conditions were same as that described in example 1. The results were showed in Table 4.

Example 16

1. Preparation of the catalyst component

To a reactor which was completely purged with N₂ were added successively 9.6g of anhydrous magnesium chloride, 50ml of toluene, 46.8ml of 2-

ethylhexanol. With stirring at 450 rpm, the mixture was heated to 110°C and held at the temperature for 2 hours, then 2.22g of phthalic anhydride was added thereto and the reaction was continued for further one hour to give a homogeneous solution. With continuous stirring, 50ml of said homogeneous solution was added slowly to a reactor containing 200ml of titanium tetrachloride with the temperature of the reactor being maintained at -20_ during the addition. Upon completing the addition, the reaction mixture was gradually heated to 110°C over about 3 hours and maintained at that temperature for further 2 hours. Solid was precipitated gradually during the heating. After removing the mother liquid by suction filtration, solid component A was obtained.

To the reactor containing the solid component A was added 200ml of titanium tetrachloride. The temperature was increased to 110_ and maintained there for 2 hours. After removing mother liquid, the solid residue was washed thrice with hexane at 60_, then 90ml of hexane was added thereto followed by 3.0ml of THF slowly added, and the reaction was performed for 1 hour. After washing twice with hexane and drying under vacuum, 6.1g of particulate solid component B containing 1.96 percent by weight of titanium, 17.7 percent by weight of magnesium and 29.9 percent by weight of THF was obtained.

2. Slurry polymerization

The catalyst component B was evaluated in slurry polymerization process and the polymerization procedure and conditions were same as that described in example 1. The results were showed in Table 4.

Example 17

The procedure of example 16 was repeated, except substituting decane for toluene as solvent, thereby giving 6.2g of particulate solid component B, which was found to contain 1.95 percent by weight of titanium, 17.9 percent by weight of magnesium and 24.2 percent by weight of THF.

The catalyst component was evaluated in slurry polymerization process and the polymerization procedure and conditions were same as that described in example 1. The results were showed in Table 4.

Table 4 Polymerization results

Example	Activity (gPE/gCat)	Bulk Density (g/cm ³)	Content of fine powder less than 150_μm_Wt%_	MI (g/10min)
Example 8	6190	0.39	2.8	1.44
Example 9	4788	0.38	3.8	1.13
Example 10	5397	0.33	6.4	1.28
Example 11	4935	0.33	10.4	0.26
Example 12	4826	0.32	11.9	0.30
Example 13	6548	0.29	5.1	1.32
Example 14	3740	0.36	8.8	0.39
Example 15	4641	0.34	4.9	0.43
Example 16	6871	0.34	4.2	0.75
Example 17	5432	0.33	5.7	0.56

Example 18

1. Preparation of the catalyst component

A spherical carrier consisting of the adduct of magnesium chloride and alcohol was prepared according to the method disclosed in EP395083. Partial alcohol was removed by heat treatment at 95_ so that the molar ratio of alcohol to magnesium chloride was 0.83. To a reactor were added 10g of the carrier and 90ml of hexane, and with stirring at 450rpm, 6ml of 26.43 percent by volume solution of monochlorodiethylaluminium in hexane and 5ml of titanium tetrachloride were added at room temperature. The mixture was heated to 60_ and maintained at that temperature for 2 hours. After removing the mother liquid in the reactor and adding 90ml of hexane to the reactor, 5ml of tetrahydrofuran was added dropwise with stirring, and the mixture was allowed to react for one hour at room temperature. After the solid residue had been washed twice with hexane, drying under vacuum gave 10.2 g of spherical solid component B, which was found to contain 1.96 percent by weight of titanium, 17.7 percent by weight of magnesium, and 29.9 percent by weight of tetrahydrofuran.

2. Slurry polymerization of ethylene

With stirring, to a 2 liters stainless steel autoclave, which had been well evacuated and replaced with hydrogen, were added about 0.5 liter of hexane by means of nitrogen pressure, 2ml of 1mmol/ml solution of AlEt₃ in hexane using a

syringe and about 30mg of the above spherical solid component B. Then to the reactor was supplemented hexane to about 1 liter of total amount. Upon completion, the reactor was heated to 85°C, introduced hydrogen to make the fractional pressure of hydrogen in the autoclave be 0.28MPa, then introduced ethylene gas to make its fractional pressure be 0.75MPa. The polymerization reaction was continued for 2 hours at constant temperature of 85°C and ethylene was made up during the polymerization to maintain the fractional pressure of ethylene. Then the temperature of the autoclave was reduced, the pressure was relieved and the polymer slurry was discharged. After removing hexane, the polymer was dried in air under an infrared lamp to give polyethylene powder. The activity of the catalyst was 7053 gPE/gcat._bulk density of the polymer powder was 0.348 g/cm³_the content of fine powder less than 150µm was 1.1 percent by weight_and melt index of the polymer was 1.47g/10min_

What is claimed is:

1. A catalyst component used for homopolymerization or co-polymerization of ethylene, comprising at least one electron donor compound supported on a composition containing magnesium and titanium, wherein the electron donor compound is selected from the group consisting of aliphatic ethers, cyclic ethers, aromatic ethers, aliphatic ketones and alicyclic ketones, and wherein the composition containing magnesium and titanium is prepared by dissolving a magnesium compound into a solvent system to form a homogeneous solution and then contacting the solution with a titanium compound in the presence of a precipitation aid to precipitate the composition.

2. A catalyst component used for homopolymerization or co-polymerization of ethylene, comprising at least one electron donor compound and at least one titanium compound supported on a magnesium compound-containing composition, wherein the electron donor compound is selected from the group consisting of aliphatic ethers, cyclic ethers, aromatic ethers, aliphatic ketones and alicyclic ketones.

3_ A catalyst component used for homopolymerization or co-polymerization of ethylene according to claim 1 or claim 2, wherein the catalyst component comprises from 5 to 30 percent by weight of magnesium, from 0.1 to 10 percent by weight of titanium, from 15 to 65 percent by weight of halogen, and from 1 to 60 percent by weight of electron donor, based on the total weight of the solid catalyst component; and the average particle size of the catalyst component, expressed as D50 value, is from 5 to 35 microns.

4. A catalyst component used for homopolymerization or co-polymerization of ethylene according to claim 1 or claim 2, wherein the titanium compound has a general formula $Ti(OR)_aX_b$, in which R is C_1-C_{14} aliphatic hydrocarbyl or aromatic hydrocarbyl, X is halogen, a is 0, 1 or 2, b is an integer of from 1 to 4, and the sum of $a + b$ is 3 or 4.

5. A catalyst component used for homopolymerization or co-polymerization of ethylene according to claim 1 or claim 2, wherein the magnesium compound is selected from the group consisting of magnesium dihalides, hydrates or alcohol adducts of magnesium dihalide, derivatives formed by replacing one halogen atom of

magnesium dihalide with hydrocarbyloxy group or halo-hydrocarbyloxy group, or their mixture.

6. A catalyst component used for homopolymerization or co-polymerization of ethylene according to claim 1, wherein the solvent system comprises an organic epoxy compound and an organophosphorus compound.

7. A catalyst component used for homopolymerization or co-polymerization of ethylene according to claim 6, wherein the organic epoxy compound comprises at least one selected from the group consisting of oxides of aliphatic olefin, diene or halogenated aliphatic olefin or diene, glycidyl ethers and cyclic ethers having from 2 to 8 carbon atoms.

8. A catalyst component used for homopolymerization or co-polymerization of ethylene according to claim 6, wherein the organophosphorus compound is at least one selected from the group consisting of hydrocarbyl esters or halo-hydrocarbyl esters of ortho-phosphoric acid or phosphorous acid.

9. A catalyst component used for homopolymerization or co-polymerization of ethylene according to claim 1, wherein the solvent system comprises a branched aliphatic alcohol compound.

10. A catalyst component used for homopolymerization or co-polymerization of ethylene according to claim 9, wherein the solvent system comprises 2-ethylhexanol.

11. A catalyst component used for homopolymerization or co-polymerization of ethylene according to claim 1, wherein the precipitation aid is at least one selected from the group consisting of organic carboxylic anhydrides, organic carboxylic acids, ethers and ketones.

12. A catalyst component used for homopolymerization or co-polymerization of ethylene according to claim 1, wherein the precipitation aid is at least one selected from the group consisting of acetic anhydride, phthalic anhydride, succinic anhydride, maleic anhydride, 1,2,4,5-benzene tetracarboxylic acid dianhydride, acetic acid, propionic acid, butyric acid, acrylic acid, methacrylic acid, acetone, methyl ethyl ketone, benzophenone, dimethyl ether, diethyl ether, dipropyl ether, dibutyl ether and dipentyl ether.

13. A catalyst component used for homopolymerization or co-polymerization of ethylene according to claim 1 or claim 2, wherein the electron donor compound is at

least one selected from the group consisting of aliphatic ethers having total from 2 to 12 carbon atoms, cyclic ethers having from 3 to 5 carbon atoms, aromatic ethers having total from 7 to 8 carbon atoms, saturated or unsaturated aliphatic ketones having from 3 to 6 carbon atoms, alicyclic ketones having from 5 to 10 carbon atoms.

14. A catalyst component used for homopolymerization or co-polymerization of ethylene according to claim 1 or claim 2, wherein the electron donor compound is selected from the group consisting of diethyl ether, di-n-butyl ether, dihexyl ether, ethyl phenyl ether, tetrahydrofuran, acetone, butanone, isobutyl methyl ketone, 4-methyl-3-penten-2-one, hexadione, cyclohexanone and any combinations of any above compounds.

15. A catalyst component used for homopolymerization or co-polymerization of ethylene according to claim 1 or claim 2, wherein the electron donor compound is a cyclic ether having from 3 to 5 carbon atoms.

16. A catalyst component used for homopolymerization or co-polymerization of ethylene according to claim 1 or claim 2, wherein the electron donor compound is tetrahydrofuran.

17. A catalyst component used for homopolymerization or co-polymerization of ethylene according to claim 1 or claim 2, wherein it further comprises at least one activator having a general formula $AlR'_cX'_dH_e$, in which R' is saturated hydrocarbyl having 1 to 14 carbon atoms, X' is a halogen, d is 1 or 2, e is 0 or 1, and the sum of $c+d+e$ is 3.

18. A catalyst component used for homopolymerization or co-polymerization of ethylene according to claim 17, wherein the activator is one or more selected from the group consisting of $AlEt_3$, $Al(n-Bu)_3$, $Al(n-C_6H_{13})_3$, $Al(i-Bu)_3$, $AlEt_2Cl$, $Al(n-C_8H_{17})_3$, and $AlEt_2H$.

19. A method for the preparation of a catalyst component used for homopolymerization or co-polymerization of ethylene claimed in claim 1, comprising the steps of:

dissolving a magnesium compound into a solvent system containing an organic epoxy compound and an organophosphorus compound to form a homogeneous solution;

contacting the solution with a titanium compound in the presence of a

precipitation aid to precipitate a solid;

treating the obtained solid with an electron donor compound and, optionally, the titanium compound to obtain a product; and

optionally, activating the resultant product with an activator.

20. A method according to claim 19, wherein individual raw material can be used in the amount of from 0.2 to 10 mole for the organic epoxy compound, from 0.1 to 3 mole for the organophosphorus compound, from 0.03 to 1.0 mole for the precipitation aid, from 0.5 to 150 mole for the total titanium compound, from 0.01 to 10 mole for the electron donor compound, and from 0.1 to 10 mole for the activator, based on per mole magnesium compound.

21. A catalyst for homopolymerization or co-polymerization of ethylene, comprising the reaction product of the following two components:

- (a) catalyst component according to any one of claims 1-18; and
- (b) organoaluminum as cocatalyst component.

22. A use of the catalyst according to claim 21 in homopolymerization of ethylene or co-polymerization of ethylene with at least one C₃-C₈ α-olefin.

23. A use of the catalyst according to claim 21 in homopolymerization or co-polymerization of ethylene in gas phase process or slurry process.

24. A method for homopolymerization of ethylene or co-polymerization of ethylene with at least one C₃-C₈ α-olefin, comprising contacting ethylene or ethylene and at least one C₃-C₈ α-olefin with the catalyst according to claim 21 under polymerization conditions.

25. A method for homopolymerization of ethylene or co-polymerization of ethylene with at least one C₃-C₈ α-olefin, comprising contacting ethylene or ethylene and at least one C₃-C₈ α-olefin with the catalyst according to claim 21 under polymerization conditions in slurry or gas phase process.