



US007479688B2

(12) **United States Patent**  
**Deshpande et al.**

(10) **Patent No.:** **US 7,479,688 B2**  
(45) **Date of Patent:** **Jan. 20, 2009**

(54) **STI STRESS MODIFICATION BY NITROGEN PLASMA TREATMENT FOR IMPROVING PERFORMANCE IN SMALL WIDTH DEVICES**

4,655,415 A 4/1987 Miller et al.

(Continued)

(75) Inventors: **Sadanand V. Deshpande**, Fishkill, NY (US); **Bruce B. Doris**, Brewster, NY (US); **Werner A. Rausch**, Stormville, NY (US); **James A. Slinkman**, Montpelier, VT (US)

FOREIGN PATENT DOCUMENTS

EP 01/62362 6/1989

(73) Assignee: **International Business Machines Corporation**, Armonk, NY (US)

(Continued)

OTHER PUBLICATIONS

(\* ) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

Rim et al., "Transconductance Enhancement in Deep Submicron Strained-Si n-MOSFETs", International Electron Devices Meeting, 26, 8, 1, IEEE, Sep. 1998.

(Continued)

(21) Appl. No.: **10/751,831**

(22) Filed: **Jan. 5, 2004**

*Primary Examiner*—Edward Wojciechowicz  
(74) *Attorney, Agent, or Firm*—Scully, Scott, Murphy & Presser, P.C.; Joseph P. Abate, Esq.

(65) **Prior Publication Data**

US 2004/0238914 A1 Dec. 2, 2004

(57) **ABSTRACT**

**Related U.S. Application Data**

(62) Division of application No. 10/250,047, filed on May 30, 2003, now Pat. No. 6,887,798.

(51) **Int. Cl.**  
**H01L 29/72** (2006.01)

(52) **U.S. Cl.** ..... **257/510**; 257/513; 257/E21.59; 257/E21.166; 257/E21.279; 257/E21.507; 257/E21.546; 257/E21.549; 257/E21.633; 257/E21.651

(58) **Field of Classification Search** ..... 257/510, 257/511, 512, 296, 513  
See application file for complete search history.


(56) **References Cited**

U.S. PATENT DOCUMENTS

3,602,841 A 8/1971 McGroddy

A method for modulating the stress caused by bird beak formation of small width devices by a nitrogen plasma treatment. The nitrogen plasma process forms a nitride liner about the trench walls that serves to prevent the formation of bird beaks in the isolation region during a subsequent oxidation step. In one embodiment, the plasma nitridation process occurs after trench etching, but prior to trench fill. In yet another embodiment, the plasma nitridation process occurs after trench fill. In yet another embodiment, a block mask is formed over predetermined active areas of the etched substrate prior to the plasma nitridation process. This embodiment is used in protecting the PFET device area from the plasma nitridation process thereby providing a means to form a PFET device area in which stress caused by bird beak formation increases the device performance of the PFET.

**18 Claims, 5 Drawing Sheets**



U.S. PATENT DOCUMENTS

4,853,076 A 8/1989 Tsauro et al.  
 4,855,245 A 8/1989 Neppel et al.  
 4,952,524 A 8/1990 Lee et al.  
 4,958,213 A 9/1990 Eklund et al.  
 5,006,913 A 4/1991 Sugahara et al.  
 5,060,030 A 10/1991 Hoke  
 5,081,513 A 1/1992 Jackson et al.  
 5,108,843 A 4/1992 Ohtaka et al.  
 5,134,085 A 7/1992 Gilgen et al.  
 5,310,446 A 5/1994 Konishi et al.  
 5,354,695 A 10/1994 Leedy  
 5,371,399 A 12/1996 Burroughes et al.  
 5,391,510 A 2/1995 Hsu et al.  
 5,459,346 A 10/1995 Asakawa et al.  
 5,471,948 A 12/1995 Burroughes et al.  
 5,557,122 A 9/1996 Shrivastava et al.  
 5,561,302 A 10/1996 Candelaria  
 5,565,697 A 10/1996 Asakawa et al.  
 5,571,741 A 11/1996 Leedy  
 5,592,007 A 1/1997 Leedy  
 5,592,018 A 1/1997 Leedy  
 5,670,798 A 9/1997 Schetzina  
 5,679,965 A 10/1997 Schetzina  
 5,683,934 A 11/1997 Candelaria  
 5,780,346 A 7/1998 Arghavani et al.  
 5,811,347 A 9/1998 Gardner et al.  
 5,840,593 A 11/1998 Leedy  
 5,861,651 A 1/1999 Brasen et al.  
 5,880,040 A 3/1999 Sun et al.  
 5,940,717 A \* 8/1999 Rengarajan et al. .... 438/435  
 5,940,736 A 8/1999 Brady et al.  
 5,946,559 A 8/1999 Leedy  
 5,960,297 A 9/1999 Saki  
 5,989,978 A 11/1999 Peidous  
 6,008,126 A 12/1999 Leedy  
 6,025,280 A 2/2000 Brady et al.  
 6,046,464 A 4/2000 Schetzina  
 6,066,545 A 5/2000 Doshi et al.  
 6,090,684 A 7/2000 Ishitsuka et al.  
 6,107,143 A 8/2000 Park et al.  
 6,117,722 A 9/2000 Wu et al.  
 6,118,168 A 9/2000 Moon et al.  
 6,156,620 A \* 12/2000 Puchner et al. .... 438/400  
 6,165,383 A 12/2000 Chou  
 6,221,735 B1 4/2001 Manley et al.  
 6,228,694 B1 5/2001 Doyle et al.  
 6,246,095 B1 6/2001 Brady et al.  
 6,255,169 B1 7/2001 Li et al.  
 6,261,925 B1 7/2001 Arghavani et al.  
 6,261,964 B1 7/2001 Wu et al.  
 6,265,317 B1 7/2001 Chiu et al.  
 6,274,444 B1 8/2001 Wang  
 6,281,532 B1 8/2001 Doyle et al.  
 6,284,623 B1 9/2001 Zhang et al.  
 6,284,626 B1 9/2001 Kim  
 6,319,794 B1 11/2001 Akatsu et al.  
 6,348,394 B1 \* 2/2002 Mandelman et al. .... 438/424  
 6,361,885 B1 3/2002 Chou  
 6,362,082 B1 3/2002 Doyle et al.  
 6,368,931 B1 4/2002 Kuhn et al.  
 6,403,846 B1 6/2002 Sekiya et al.  
 6,403,975 B1 6/2002 Brunner et al.

6,406,973 B1 6/2002 Lee  
 6,436,790 B2 8/2002 Ito  
 6,461,934 B2 10/2002 Nishida et al.  
 6,476,462 B2 11/2002 Shimizu et al.  
 6,479,367 B2 11/2002 Park  
 6,493,497 B1 12/2002 Ramdani et al.  
 6,498,358 B1 12/2002 Lach et al.  
 6,498,383 B2 12/2002 Beyer et al.  
 6,501,121 B1 12/2002 Yu et al.  
 6,506,652 B2 1/2003 Jan et al.  
 6,509,618 B2 1/2003 Myers et al.  
 6,521,964 B1 2/2003 Jan et al.  
 6,531,369 B1 3/2003 Ozkan et al.  
 6,531,740 B2 3/2003 Bosco et al.  
 2001/0009784 A1 7/2001 Ma et al.  
 2002/0074598 A1 6/2002 Doyle et al.  
 2002/0086472 A1 7/2002 Roberds et al.  
 2002/0086497 A1 7/2002 Kwok  
 2002/0090791 A1 7/2002 Doyle et al.  
 2002/0155730 A1 \* 10/2002 Mukai et al. .... 438/787  
 2003/0015736 A1 1/2003 Beyer et al.  
 2003/0032261 A1 2/2003 Yeh et al.  
 2003/0040158 A1 2/2003 Saitoh  
 2003/0057184 A1 3/2003 Yu et al.  
 2003/0067035 A1 4/2003 Tews et al.  
 2004/0155275 A1 \* 8/2004 Divakaruni et al. .... 257/296  
 2004/0212035 A1 \* 10/2004 Yeo et al. .... 257/510

FOREIGN PATENT DOCUMENTS

EP 0 967 636 \* 12/1999 ..... 257/400  
 EP 0 9867 636 A2 12/1999  
 EP 1 174 928 A1 1/2002  
 EP 1 213 757 \* 6/2002  
 JP 1-283859 11/1989  
 WO WO 94/27317 5/1993  
 WO WO 02/454156 A2 6/2002

OTHER PUBLICATIONS

Rim, et al. "Characteristics and Device Design of Sub-100nm Strained Si N- and PMOSFETs", 2002 Symposium On VLSI Technology Digest of Technical Papers, IEEE, pp. 98-99.  
 Scott, et al. "NMOS Drive Current Reduction Caused by Transistor Layout and Trench Isolation Induced Stress", International Electron Devices Meeting, 34.4.1, IEEE, Sep. 1999.  
 Ootsuka, et al. "A Highly Dense, High-Performance 130nm node CMOS Technology for Large Scale System-on-a-Chip Application", International Electron Device Meeting, 23.5.1, IEEE, Apr. 2000.  
 Ito, et al. "Mechanical Stress Effect of Etch-Stop Nitride and its Impact on Deep Submicron Transistor Design", International Electron Devices Meeting, 10.7.1, IEEE, Apr. 2000.  
 Shimizu, et al. "Local Mechanical-Stress Control (LMC): A New Technique for CMOS-Performance Enhancement", International Electron Device Meetings, IEEE, Mar. 2001.  
 Oto, et al. "Novel Locally Strained Channel Technique of high Performance 55nm CMOS", International Electron Devices Meeting, 2.2.1, IEEE, Feb. 2002.  
 Ouyang, et al. "Two-Dimensional Bandgap Engineering In a Novel Si/SiGe pMOSFETS with Enhanced Device Performance and Scalability", Microelectronic Research Center, pp. 151-154, 2000 IEEE.  
 Sayama et al., "Effect of <Channel Direction for High Performance SCE Immune pMOSFET with Less Than 0.15um Gate Length" ULSI Development Center, pp.27.5.1-27.5.4, 1999 IEEE.

\* cited by examiner




FIG. 1A (Prior Art)




FIG. 1B (Prior Art)




FIG. 1C (Prior Art)




FIG.2 (Prior Art)




FIG.3A




FIG.3B




FIG. 3C




FIG. 3D




FIG. 3E




FIG. 4A




FIG. 4B




FIG. 5A




FIG. 5B




FIG. 5C

**STI STRESS MODIFICATION BY NITROGEN  
PLASMA TREATMENT FOR IMPROVING  
PERFORMANCE IN SMALL WIDTH  
DEVICES**

RELATED APPLICATION

This application is a divisional of U.S. application Ser. No. 10/250,047, filed May 30, 2003 now U.S. Pat. No. 6,887,798.

DESCRIPTION

1. Field of the Invention

The present invention generally relates to semiconductor processing, and more particularly to a method of fabricating isolation regions, such as shallow trench isolation (STI), in which the stress of the isolation region has been modulated by a nitrogen plasma treatment. The isolation regions created in the present invention, which are particularly useful in small width devices (on the order of about 0.25  $\mu\text{m}$  or less), have substantially little or no bird beaks in the isolation region.

2. Background of the Invention

In the semiconductor industry, it is well known to isolate one or more device regions present on a semiconductor structure using isolation regions such as shallow trench isolation (STI) regions. A standard STI process is shown, for example, in FIGS. 1A-1C. Specifically, prior art FIG. 1A illustrates an initial processing step in which a pad stack comprising an oxide **12** and a nitride **14** is formed atop a surface of a semiconductor substrate **10**. An optional hard mask (not shown) may also be formed atop the nitride layer **14** of the pad stack.

Next, lithography is employed in providing a trench pattern to the structure. Specifically, the trench pattern is formed by first applying a photoresist on the upper surface of the pad stack. The photoresist is then exposed to a pattern of radiation and thereafter the pattern in the photoresist is developed using a resist developer. An etching step is used to transfer the pattern from the photoresist into the nitride layer **14**. After the initial pattern transfer, the photoresist is removed utilizing a stripping process and then etching continues through the oxide layer **12** stopping atop an upper surface of the semiconductor substrate **10** so as to provide a structure having an opening **16** in the oxide layer **12** as shown, for example, in FIG. 1B.

After providing the structure shown in FIG. 1B, a trench is formed in the semiconductor substrate **10** via etching through the opening **16**. A trench liner (not shown) is typically formed via oxidation on the bare sidewalls of the trench including the sidewalls of the oxide layer **12**. The trench is then filled with a trench dielectric material **22** such as  $\text{SiO}_2$ , tetraethylorthosilicate (TEOS) or a high-density plasma oxide and thereafter the structure is planarized to the upper surface of the nitride layer **14**. A deglazing process may follow the trench fill step. After deglazing, the nitride layer **14** is removed providing a structure having an STI region **24** formed in the surface of the semiconductor substrate **10**. The structure including STI region **24** is shown, for example, in FIG. 1C.

The oxide layer **12** may be removed prior to CMOS (complementary metal oxide semiconductor) device fabrication. CMOS device fabrication may include the following processing steps:

- A conventional gate oxidation pre-clean, and gate dielectric formation;
- Gate electrode formation and patterning;
- Gate reoxidation;
- Source/drain extension formation;
- Sidewall spacer formation by deposition and etching;

- Source/drain formation;
- Silicide formation; and
- Back-end-of-the-line (BEOL) process.

During the oxidation procedures used in steps 1 and 3, bird beaks **26** begin to form in the STI regions **24** at or near the interface between the STI **24** and the semiconductor substrate **10**; bird beaks are oxide regions that are formed during CMOS device oxidation processes that encroach upon and, in some instances, enter the islands of the semiconductor substrate **10** which lie adjacent to the STI regions. This encroachment and subsequent entry into the semiconductor islands causes the semiconductor substrate **10** to exhibit uneven stress in the active device areas. This uneven stress may negatively impact some of the devices, while positively affecting other devices present on the semiconductor substrate. Bird beak formation is particularly relevant for small width semiconductor devices that have a width of about 0.25  $\mu\text{m}$  or less.

Specifically, stress caused by bird beak formation is known to lead to device degradation for NFET devices and device improvements for PFETs. In particular, the device drive current and the device on-current can be affected (either negatively or positively) by bird beak formation. To date, applicants are unaware of any prior art method that seeks a means to tailor the stress caused by bird beak formation so as to improve the device performance of NFETs and PFETs.

In view of the drawbacks mentioned above with the prior art process of fabricating STI regions, there is a need for providing a method of forming isolation regions such as STIs, in which bird beak formation is substantially prevented thereby reducing the stress in the semiconductor substrate. There is also a need for providing a method in which stress formation is controlled such that improved device performance, in terms of drive current and on-current, can be achieved for a structure containing both NFETs and PFETs.

SUMMARY OF THE INVENTION

An object of the present invention is to provide a method of fabricating isolation regions, such as shallow trench isolation regions, for use in small width devices (on the order of about 0.25  $\mu\text{m}$  or less).

A further object of the present invention is to provide a method of fabricating isolation regions that exhibit substantially little or no bird beak formation during a subsequent CMOS oxidation process.

A yet further object of the present invention is to provide a method of fabricating isolation regions in which the stress caused by bird beak formation has been modulated to enhance device performance.

An even further object of the present invention is to provide a method of fabricating isolation regions in which the stress caused by bird peak formation is reduced for NFETs.

A still further object of the present invention is to provide a method in which stress formation caused by bird beak formation is controlled such that improved device performance, in terms of drive current and on-current, can be achieved for a structure containing both NFETs and PFETs.

It is noted that the term "isolation regions" as used throughout the instant application denotes trench isolation regions. The isolation regions formed in the present invention can be classified in accordance to their depth. In particular, the present invention contemplates the formation of shallow trench isolation (STI) regions having a depth, as measured from the top surface of the substrate to the bottom of the trench, of about 1.0  $\mu\text{m}$  or less, medium trench isolation regions having a depth, as measured from the top surface of

the substrate to the bottom of the trench, of about 1.0  $\mu\text{m}$  to about 3.0  $\mu\text{m}$ , and deep trench isolation (DTI) regions having a depth, as measured from the top surface of the substrate to the bottom of the trench, of about 3.0  $\mu\text{m}$  or greater.

The isolation regions formed in the present invention may, or may not, have a high aspect ratio associated therewith. When a high aspect ratio trench isolation region is formed, the aspect ratio (height:width) is about 0.5 or greater.

The aforementioned objects and advantages are achieved in the present invention by forming a nitride liner, i.e., a surface nitrided layer, about the trench walls (bottom and sidewalls) by using a plasma nitridation process. Because of the plasma nitridation used in the present invention, the nitride liner penetrates the bottom and sidewalls of the trench so as to form a liner that is present in the interior as well as the exterior of the trench walls. The nitride liner formed using the plasma nitridation process of the present invention serves to prevent the formation of bird beaks in the isolation region during a subsequent CMOS oxidation step.

The plasma nitridation process of the present invention may occur during the formation of the isolation region. In one embodiment, the plasma nitridation process may occur after trench etching, but prior to trench fill. In yet another embodiment of the present invention, the plasma nitridation process occurs after filling the trench with a trench dielectric material. In yet another embodiment of the present invention, a block mask is formed over predetermined active areas of the etched substrate prior to the plasma nitridation process. This embodiment is used in protecting the PFET device area from the plasma nitridation process thereby providing a means to form a PFET device area in which compression stress caused by bird beak formation increases the device performance of the PFET.

In broad terms, the method of the present invention comprises the steps of:

providing a structure having a patterned material stack located on top of a surface of a semiconductor substrate, said patterned material stack having at least one opening that exposes a portion of the semiconductor substrate;

forming at least one trench into the exposed portion of the semiconductor substrate, each trench having sidewalls that extend to a common bottom wall; and

subjecting at least one of the sidewalls of each trench and a portion of the common bottom wall of each trench to a plasma nitridation process.

As stated above, the plasma nitridation process may occur prior to trench fill, or after the trench has been filled with a dielectric fill material. In some instances, and after the trench fill has been performed, portions of the patterned material stack are removed and a block mask is formed over active areas of the semiconductor substrate in which PFETs are to be formed. In this embodiment, the block mask is formed atop the structure after the dielectric fill step. The block mask is located predominately over the active device region in which the NFET devices will be formed. Edge portions of the block mask typically extend over the sidewalls of at least two neighboring trenches.

Another aspect of the present invention relates to a semiconductor structure which comprises

a semiconductor substrate having at least one trench isolation region located therein, said at least one trench isolation region having sidewalls that extend to a common bottom wall; and

a nitride liner present at least on portions of the sidewalls, said nitride liner protecting the sidewalls of the at least one trench so as to reduce stress in the semiconductor substrate.

#### DETAILED DESCRIPTION OF THE DRAWINGS

FIGS. 1A-1C are pictorial representations (through cross sectional views) illustrating the prior art process of forming a shallow trench isolation (STI) region.

FIG. 2 is a pictorial representation (through a cross sectional view) illustrating the formation of a bird beak in the STI region provided by FIGS. 1A-1C.

FIGS. 3A-3E are pictorial representations (through cross sectional views) illustrating the basic processing steps in one embodiment of the present invention.

FIG. 4A-4B are pictorial representations (through cross sectional views) illustrating the basic processing steps in another embodiment of the present invention.

FIGS. 5A-5C are pictorial representation (through cross sectional views) illustrating another embodiment of the present invention for providing a structure in which portions of the trenches are treated with the plasma nitridation process of the present invention, while other portions of the trenches are protected with a block mask.

#### DETAILED DESCRIPTION OF THE INVENTION

The present invention, which provides a method for modifying the stress caused by bird beak formation in the isolation regions of small width CMOS devices, will now be described in greater detail by referring to the drawings that accompany the present application. In the drawings representing the present invention, like reference numerals are used in describing like and/or corresponding elements.

Reference is first made to the embodiment depicted in FIGS. 3A-3E. In this embodiment of the present invention, the trench is subjected to a plasma nitridation process prior to filling the trench with a trench fill material. Specifically, FIG. 3A shows an initial structure of the first embodiment of the present application. In FIG. 3A, there is shown a semiconductor substrate 50 having a material stack 52 located on a surface of the semiconductor substrate 50. Material stack 52 comprises at least a pad oxide 54 and a pad nitride 56. As shown, the pad oxide 54 is located on an upper surface of the semiconductor substrate 50, while the pad nitride 56 is typically applied on top of the pad oxide 54.

The semiconductor substrate employed in the present invention is any semiconducting material well known to those skilled in the art. This includes Si-containing semiconductor materials as well as Ge, GaAs, InP and other III/V compound semiconductors. Preferred semiconductor substrates employed in the present invention are Si-containing semiconductor materials which include, but are not limited to: Si, SiGe, SiGeC, SiC, a silicon-on-insulator (SOI) and combinations thereof, e.g., a stack of Si/SiGe or Si/SOI. The SOI substrate includes a buried oxide layer that electrically isolates a top Si-containing layer, i.e., the SOI layer, from a bottom Si-containing layer.

When an SOI substrate is employed in the present invention, the top Si-containing layer of the SOI substrate may have a vertical thickness,  $t_v$ , i.e., height, of less than about 300 nm, with a vertical thickness of from about 50 nm to about 100 nm being more highly preferred. The thickness of the buried oxide may vary, but typically, the buried insulating layer has a thickness of less than about 350 nm, with a thickness of from about 1 nm to about 100 nm being more highly preferred. The thickness of the bottom Si-containing layer of the SOI substrate is inconsequential to the present invention.

The SOI substrate is fabricated using techniques that are well known to those skilled in the art. For example, the SOI substrate may be fabricated using a thermal bonding process,

or alternatively the SOI substrate may be fabricated by an ion implantation process that is referred to in the art as separation by ion implantation of oxygen (SIMOX). When a thermal bonding process is employed in fabricating the SOI substrate, an optional thinning step may be utilized to thin the top Si-containing layer into an ultra-thin regime which is on the order of less than 50 nm.

The pad oxide **54** is formed on the upper surface of the semiconductor substrate **50** using either a thermal oxidation process or a deposition process such as chemical vapor deposition (CVD), plasma-assisted CVD, chemical solution deposition, atomic layer deposition or evaporation. The thickness of the pad oxide **54** may vary depending upon the technique used in forming the same. Typically, however, the pad oxide **54** has a thickness of from about 1 nm to about 40 nm.

After the pad oxide **54** has been formed on the semiconductor substrate **50**, the pad nitride **56** is typically formed on top of the pad oxide **54** using a conventional deposition process such as CVD, plasma-assisted CVD, chemical solution deposition, atomic layer deposition, or evaporation. The thickness of the pad nitride **56** may vary depending on the technique used in forming the same. Typically, the pad nitride **56** has a thickness of from about 60 nm to about 150 nm.

After providing the material stack **52** to the semiconductor substrate **50**, a photoresist (not shown) is applied to the upper exposed surface layer of the material stack **52**, i.e., on the pad nitride **56**, by a deposition process such as CVD, plasma-assisted CVD, spin-on coating, or evaporation. The photoresist is then patterned by lithography which includes the steps of exposing the photoresist to a pattern of radiation and developing the pattern by using a conventional resist developer. The pattern formed in the present invention is a trench pattern. The trench pattern is then transferred into the material stack **52** utilizing one or more etching steps.

In particular, the pattern transfer is accomplished by first etching through exposed portions of the patterned photoresist utilizing an etching process that is selective in removing nitride (in this instance, etching stops atop the pad oxide **54**). Once the trench pattern has been transferred into the pad nitride **56**, the patterned photoresist is typically removed from the structure utilizing a conventional resist stripping process that is well known to those skilled in the art. Etching of the trench pattern continues into the underlying pad oxide **54** utilizing an etching process that is selective in removing oxide. This etching step stops atop an upper surface of the semiconductor substrate **50**.

The resultant structure, which is formed after the patterning and etching steps have been performed, is shown, for example, in FIG. 3B. Specifically, FIG. 3B illustrates a structure comprising the semiconductor substrate **50** containing a patterned material stack **52** having at least one opening **58** that exposes portions of the semiconductor substrate **50**.

Next, the exposed portions of the semiconductor substrate that are not protected with the patterned material stack, i.e., the patterned pad oxide **54** and pad nitride **56**, are then removed utilizing an etching process that is highly selective in removing semiconductor substrate material providing the structure shown in FIG. 3C. The illustrated structure shown in FIG. 3C includes at least one trench **60** in the semiconductor substrate **50**. Each of the trenches **60** formed in this step of the present invention have sidewalls **62** that extend to a common bottom wall **64**.

The depth of the trenches is controlled by the conditions used to etch the exposed portions of the semiconductor substrate **50**. The trenches **60** formed in the present invention may be shallow trenches, medium trenches and deep trenches. The shallow trenches have a depth, as measured from the top

surface of the substrate to the bottom of the trench, of about 1.0  $\mu\text{m}$  or less, the medium trenches have a depth, as measured from the top surface of the substrate to the bottom of the trench, of about 1.0  $\mu\text{m}$  to about 3.0  $\mu\text{m}$ , and deep trenches have a depth, as measured from the top surface of the substrate to the bottom of the trench, of about 3.0  $\mu\text{m}$  or greater.

At this point of the present invention, the structure shown in FIG. 3C may be subjected to a nitrogen plasma treatment step. That is, a plasma nitridation process may now be performed on the structure shown in FIG. 3C. The structure formed during the nitrogen plasma treatment is shown in FIG. 3D.

As shown in FIG. 3D, the structure is treated by a plasma of nitrogen **66** that is capable of forming a nitride liner **68** about the interior and exterior sidewalls and bottom walls of the trench. The nitride liner **68** may be referred to herein as a surface nitrided layer since some of the nitride layer forms inward into the surrounding islands of semiconductor substrate **50**. Semiconductor islands are defined as the pillar regions of semiconductor material that lies adjacent to each of the trenches provided during the above patterning and etching steps. The terms "nitride liner" and "nitrided surface layer" are interchangeable in the present invention. As shown in the embodiment depicted in FIG. 3D, nitride liner **68** lines the sidewalls **62** and the bottom wall **64** of each trench **60**. Although not shown, some of nitride liner **68** enters into the semiconductor substrate **50** surrounding the trenches **60**.

The plasma nitridation is carried out in a nitrogen-containing atmosphere such as  $\text{N}_2$ ,  $\text{NO}$ ,  $\text{N}_2\text{O}$ , and  $\text{NH}_3$ . Mixtures of the aforementioned nitrogen-containing atmospheres are also contemplated herein. The present invention also contemplates plasma nitridation processes wherein the nitrogen-containing gas is admixed with an inert gas such as He, Ar, Ne, Kr or Xe. Mixtures of inert gasses such as He and Ar are also contemplated herein. When an inert gas is present, the plasma contains a concentration of nitrogen-containing gas of about 5 to about 70%. A highly preferred nitrogen plasma employed in the present invention is  $\text{N}_2$  in He.

The plasma nitridation process of the present invention is carried out using a plasma having a temperature of about 80° C. or below, with a plasma temperature of from about 25° C. to about 50° C. being more highly preferred. The substrate during the plasma nitridation process is maintained at a temperature of from about 20° C. to about 100° C., with a substrate temperature of from about 25° C. to about 80° C. being more highly preferred. The substrate temperature is maintained within the foregoing ranges using a backside cooling process in which an inert gas such as He is flow over the back surface of the substrate.

The nitrogen species used in the present invention will form ions that react with the semiconductor surface and form a nitrogen rich surface layer on the trench sidewalls and bottom walls.

The plasma nitridation process may be carried out using rapid thermal conditions wherein short heating times (on the order of about 120 seconds or less) are employed. Hence, the present invention contemplates rapid thermal (RT) nitridation processes such as RTNH, RTNO, RTNO<sub>2</sub>, rapid plasma nitridation (RPN) or a decoupled plasma nitridation (DPN) process.

A preferred plasma nitridation process employed in the present invention is a DPN process in which the following preferred conditions are employed:

- Pressure range: 50-100 mTorr;
- Gas composition: 2-10%  $\text{N}_2$  in He;
- Power range: 50-200 Watts;
- Plasma exposure time: 10-50 seconds;
- Wafer temperature: 50° C.-100° C.

Notwithstanding which technique is employed in forming the nitrated surface layer **68**, the nitrated surface layer **68** formed has a thickness of from about 0.1 to about 2 nm, with a thickness of from about 1.0 to about 1.5 nm being more highly preferred. Some of the nitride thickness may form inward into the semiconductor substrate **50**.

Following the nitridation process shown in FIG. 3D, each of the trenches is then filled with a trench dielectric material **70** such as SiO<sub>2</sub>, tetraethylorthosilicate (TEOS) or a high-density plasma oxide and thereafter the structure is planarized to the upper surface of the nitride pad **56**. In an optional step, an oxide liner (not shown) may be formed in the trench prior to trench fill. A deglazing process may follow the trench fill step. After deglazing, the nitride pad **56** and the pad oxide **54** are removed providing a structure having isolation regions **72** formed in the surface of the semiconductor substrate **50**. The resultant structure formed after these steps have been performed is shown, for example, in FIG. 3E.

After stripping the pad nitride and the pad oxide from the structure, conventional CMOS device fabrication processes may now be performed which include at least the following: conventional gate oxidation pre-clean, and gate dielectric formation; gate electrode formation and patterning; gate reoxidation; source/drain extension formation; sidewall spacer formation by deposition and etching; source/drain formation; silicide formation; and a back-end-of-the-line (BEOL) process.

During the oxidation procedures used above in forming the CMOS device, bird beaks form in conventional STI regions at or near the interface between the STI and substrate. In the present invention, nitrated surface layer **68** substantially prevents bird beaks from forming. In the embodiment shown in FIGS. 3A-3E, the stress in the active areas is reduced since bird beak formation is substantially eliminated.

In addition to the embodiment shown in FIGS. 3A-3E, the present invention also contemplates an embodiment in which the plasma nitridation process occurs after the trenches have been filled. This embodiment of the present invention is shown in FIGS. 4A-4B. In this embodiment of the present invention, the structure shown in FIG. 3C is first provided using the procedures described above. Instead, of conducting a plasma nitridation process after the trenches have been etched into the semiconductor substrate **50** (as is the case in FIG. 3D), the trenches **60** are filled with a trench dielectric material **70** such as SiO<sub>2</sub>, tetraethylorthosilicate (TEOS) or a high-density plasma oxide and thereafter the structure is planarized to the upper surface of the nitride pad **56** and then recessed to the upper surface of pad oxide **54**. Prior to trench fill, an optional oxide liner may be formed. A deglazing process may follow the trench fill step. FIG. 4A shows the structure formed at this point of the present invention.

After deglazing, the nitrogen plasma treatment step described above can be performed on the structure shown in FIG. 4A. The structure formed during the nitrogen plasma treatment is shown in FIG. 4B. As shown, the structure is treated by a plasma of nitrogen **66** that is capable of forming a nitride liner **68** about the interior and exterior sidewalls and bottom walls of the trench. As shown in the embodiment depicted in FIG. 4B, nitride liner **68** lines the sidewalls **62** and the bottom wall **64** of each trench **60**.

Next, the pad nitride **56** and the pad oxide **54** are removed providing a structure having isolation regions formed in the surface of the semiconductor substrate. The resultant structure formed after the foregoing steps have been performed is similar to that shown in FIG. 3E. After stripping the pad nitride and the pad oxide from the structure, conventional CMOS device fabrication processes may now be performed which include at least the following: conventional gate oxidation pre-clean, and gate dielectric formation; gate electrode formation and patterning; gate reoxidation; source/drain

extension formation; sidewall spacer formation by deposition and etching; source/drain formation; silicide formation; and a back-end-of-the-line (BEOL) process.

During the oxidation procedures used above in forming the CMOS device, bird beaks form in conventional STI regions at or near the interface between the STI and substrate. In the present invention, nitrated surface layer **68** substantially prevents bird beaks from forming. In the embodiment shown in FIGS. 4A-4B, the stress in the active areas is reduced since bird beak formation is substantially eliminated.

In addition to the above mentioned embodiments shown in FIGS. 3A-3E and FIGS. 4A-4B, the present invention also contemplates an embodiment in which a block mask is used to tailor which portions of the trenches are subjected to nitrogen plasma treatment. This embodiment of the present invention is shown in FIGS. 5A-5C. In this embodiment of the present invention, the structure shown in FIG. 3C is first provided using the procedures described above. Instead, of conducting a plasma nitridation process after the trenches have been etched into the semiconductor substrate **50** (as is the case in FIG. 3D), the trenches **60** are filled with a trench dielectric material **70** such as SiO<sub>2</sub>, tetraethylorthosilicate (TEOS) or a high-density plasma oxide and thereafter the structure is planarized to the upper surface of the nitride pad **56** and then recessed to the upper surface of the pad oxide **54**. An optional oxide liner may be formed prior to trench fill. A deglazing process may follow the trench fill step. FIG. 5A shows the structure formed at this point of this embodiment of the present invention.

After deglazing, preselected portions of remaining pad nitride **56** are removed and a block mask is formed in those areas in which PFET devices are to be formed. The block mask, which is formed atop preselected semiconductor islands, is comprised of a photoresist material and it is formed utilizing conventional deposition and lithography. In this embodiment, the block mask protects the PFET device areas from being nitrated. As shown, in FIG. 5B, edge portions **75e** of block mask **75** extend over the sidewalls **62** of two neighboring isolation regions. The structure is then subjected to a nitrogen plasma treatment as is also shown in FIG. 5B. As illustrated, the structure is treated by a plasma of nitrogen **66** that is capable of forming a nitride liner **68** about the interior and exterior sidewalls and bottom walls of the trenches that are not protected with block mask **75**. In this embodiment of the present invention, the nitride liner **68** lines portions of the sidewalls **62** and the bottom wall **64** of each trench **60**, while the trench walls in other portions protected by the block mask are bare, i.e., no nitride liner is formed.

Next, the remaining pad nitride **56** and the pad oxide **54** are removed providing a structure having isolation regions formed in the surface of the semiconductor substrate. The resultant structure formed after the foregoing steps have been performed is shown in FIG. 5C. After stripping the pad nitride and the pad oxide from the structure, conventional CMOS device fabrication processes may now be performed which include at least the following: conventional gate oxidation pre-clean, and gate dielectric formation; gate electrode formation and patterning; gate reoxidation; source/drain extension formation; sidewall spacer formation by deposition and etching; source/drain formation; silicide formation; and a back-end-of-the-line (BEOL) process.

During the oxidation procedures used above in forming the CMOS device, bird beaks form in conventional STI regions at or near the interface between the STI and substrate. In the present invention, nitrated surface layer **68** substantially prevents bird beaks from forming on some portions of the isolation regions, while bird beak formation is allowed to occur in those portions in which no surface nitrated layer is present, i.e., in the PFET device area. In the embodiment shown in FIGS. 5A-5C, the stress in the active areas for NFET device is reduced since bird beak formation is substantially eliminated,

while the stress in the active areas for PFET occurs since bird beak formation is not prevented therein. This embodiment of the present invention thus allows one to tailor the stress caused by bird beak formation depending upon whether such stress degrades or improves the device performance. For example, bird beak formation in NFET devices leads to device performance degradation, while bird beak formation in PFET devices leads to enhanced device performance. In the foregoing example, bird beak formation causes a 17% decrease in current-on performance at a fixed current off for NFET devices, while a 17% increase in the same is observed for PFET devices.

While the present invention has been particularly shown and described with respect to preferred embodiments thereof, it will be understood by those skilled in the art that the foregoing and other changes in forms and details may be made without departing from the spirit and scope of the present invention. It is therefore intended that the present invention not be limited to the exact forms and details described and illustrated, but fall within the scope of the appended claims.

What is claimed is:

1. A semiconductor structure comprising:
  - a first semiconductor active area having, and laterally surrounded by, a first sidewall and located in a semiconductor substrate;
  - a first trench isolation region laterally abutting said first sidewall and surrounding said first semiconductor active area and comprising silicon oxide, wherein a first portion of a bottom surface of said first trench isolation region and said first sidewall does not contact any nitride liner;
  - a second semiconductor active area having, and laterally surrounded by, a second sidewall and located in said semiconductor substrate;
  - a nitride liner laterally abutting said second sidewall and a second portion of said first trench isolation region, wherein said second portion laterally abuts said first portion, and wherein an edge of said nitride liner is located at a bottom surface of said first trench isolation region underneath a boundary between said first portion and said second portion; and
  - a second trench isolation region laterally abutting said nitride liner and surrounding said second semiconductor active area and comprising silicon oxide, wherein another edge of said nitride liner is located at a bottom surface of said second trench isolation region.
2. The semiconductor structure of claim 1, wherein said first semiconductor active area is under a first compression stress and said second semiconductor active area is under a second compression stress and the level of first compression stress is higher than the level of second compression stress.
3. The semiconductor structure of claim 1, wherein said nitride liner is present on the entirety of said second sidewall surrounding said second semiconductor active area.
4. The semiconductor structure of claim 1, wherein any bird's beak structure comprising a dielectric material and having a taper in lateral width is absent between said first semiconductor active area and said first trench isolation region.
5. The semiconductor structure of claim 1, further comprising at least one bird's beak structure including a dielectric material and having a taper in lateral width and located between said second semiconductor active area and said second trench isolation region.
6. The semiconductor structure of claim 1, further comprising at least one bird's beak structure comprising a dielec-

tric material and having a taper in lateral width and located between said second semiconductor active area and said second trench isolation region, wherein any bird's beak structure comprising a dielectric material and having a taper in lateral width is absent between said first semiconductor active area and said first trench isolation region.

7. The semiconductor structure of claim 1, wherein said first semiconductor active area includes at least one PFET and said second semiconductor active area includes at least one NFET.

8. The semiconductor structure of claim 1, wherein said nitride liner is a nitride surface layer that has a thickness of about 0.1 nm to about 2.0 nm.

9. The semiconductor structure of claim 1, wherein a nitride liner is present on at least a portion of a bottom of said first trench isolation region.

10. The semiconductor structure of claim 1, wherein at least a portion of a bottom of said second trench isolation region is void of any nitride liner.

11. A semiconductor structure comprising:
 

- a trench isolation region located in a semiconductor substrate;
- a first semiconductor active area having, and laterally surrounded by, a first sidewall that laterally abuts said trench isolation region and is located in said semiconductor substrate, wherein said first sidewall does not contact any nitride liner;
- a second semiconductor active area having, and laterally surrounded by, a second sidewall and located in said semiconductor substrate; and
- a nitride liner laterally abutting said second sidewall and said trench isolation region wherein an edge of said nitride liner is located at a bottom surface of said trench isolation region.

12. The semiconductor structure of claim 11, wherein said first semiconductor active area is under a first compression stress and said second semiconductor active area is under a second compression stress and the level of first compression stress is higher than the level of second compression stress.

13. The semiconductor structure of claim 11, wherein the entirety of said first sidewall is void of any nitride liner and said nitride liner is present on the entirety of said second sidewall.

14. The semiconductor structure of claim 11, wherein any bird's beak structure including a dielectric material and having a taper in lateral width is absent between said first semiconductor active area and said first trench isolation region.

15. The semiconductor structure of claim 11, further comprising at least one bird's beak structure including a dielectric material and having a taper in lateral width and is located between said second semiconductor active area and said second trench isolation region.

16. The semiconductor structure of claim 11, wherein said first semiconductor active area includes at least one PFET and said second semiconductor active area includes at least one NFET.

17. The semiconductor structure of claim 11, wherein said nitride liner is a nitrated surface layer that has a thickness of about 0.1 nm to about 2.0 nm.

18. The semiconductor structure of claim 11, wherein said first sidewall does not adjoin said second sidewall.