



(11) **EP 1 894 945 A2**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
05.03.2008 Bulletin 2008/10

(51) Int Cl.:
C07K 14/78 (2006.01)

(21) Application number: **07111303.9**

(22) Date of filing: **26.03.2004**

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IT LI LU MC NL PL PT RO SE SI SK TR**

(30) Priority: **28.03.2003 EP 03075906**

(62) Document number(s) of the earlier application(s) in
accordance with Art. 76 EPC:
04723872.0 / 1 608 681

(71) Applicant: **FUJIFILM Manufacturing Europe B.V.
5047 TK Tilburg (NL)**

(72) Inventors:
• **Bouwstra, Jan Bastiaan
3721 AJ Bilthoven (NL)**

• **van Es, Andries Johannes Jozef
4849 BE Dorst (NL)**
• **Toda, Yuzo
Senzu 3-1-17-1104 (JP)**

(74) Representative: **Swinkels, Bart Willem
Nederlandsch Octrooibureau
P.O. Box 29720
2502 LS The Hague (NL)**

Remarks:

This application was filed on 28.06.2007 as a
divisional application to the application mentioned
under INID code 62.

(54) **RGD-enriched gelatine-like proteins with enhanced cell binding**

(57) The invention concerns a cell support comprising an RGD-enriched gelatine that has a more even distribution of RGD sequences than occurring in a natural gelatine and with a minimum level of RGD sequences. More precisely the percentage of RGD sequences related to the total number of amino acids is at least 0.4 and if the RGD-enriched gelatine comprises 350 amino acids or more, each stretch of 350 amino acids contains at least one RGD motif. Preferably the RGD-enriched gelatines are prepared by recombinant technology, and have a sequence that is derived from a human gelatine or collagen

amino acid sequence. The invention also relates to RGD-enriched gelatines that are used for attachment to integrins. In particular the RGD-enriched gelatines of the invention are suitable for coating a cell culture support for growing anchor-dependant cell types. Further, the RGD-enriched gelatines of the invention may find use in medical applications, in particular as a coating on implant or transplant material or as a component of drug delivery systems.

EP 1 894 945 A2

Description

FIELD OF THE INVENTION

[0001] The invention relates to RGD-enriched gelatines that are used for attachment to integrins. The invention further relates to cell supports coated with RGD-enriched gelatines. Said cell supports may be of use in cell culture work and applications involving cell cultures of anchor dependent cells and also in a large variety of medical applications.

BACKGROUND OF THE INVENTION

[0002] Cell culture of animal cells, in particular mammalian cells, is important for the production of many important (genetically engineered) biological materials such as vaccines, enzymes, hormones and antibodies. The majority of animal cells are anchorage-dependent and require attachment to a surface for their survival and growth.

[0003] Routinely, anchorage-dependent cells have been cultivated on the walls of for instance tissue culture flasks and roller bottles. As the necessity has developed to provide large amounts of certain antiviral vaccines, genetically engineered proteins, and other cell-derived products, improvements have been made to develop new systems for larger scale production of cells.

[0004] One such an improvement started with the development of microcarriers in 1967 by Van Wezel (Van Wezel, A. L. Nature 216:64-65 (1967)). Van Wezel made microcarriers composed of cross-linked dextran beads charged with tertiary amine groups (DEAE). He demonstrated the attachment and growth of cells on these positively charged DEAE-dextran beads suspended in culture media in a stirred vessel. Thus, in microcarrier cell cultures cells grow as monolayers on small spheres which are in suspension. By using microcarriers it is possible to achieve yields of several million cells per millilitre. Over the years various types of microcarriers have been developed. For instance glass beads and polystyrene beads have been described. Cross-linked dextran, like the first microcarriers, is still the most popular bead material.

[0005] Some advantages of microcarrier cultures over other methods of large-scale cultivation are: i) high surface area to volume ratio can be achieved which can be varied by changing the microcarrier concentration leading to high cell densities per unit volume with a potential for obtaining highly concentrated cell products; ii) cell propagation can be carried out in a single high productivity vessel instead of using many low productivity units, thus achieving a better utilisation and a considerable saving of medium; iii) since the microcarrier culture is well mixed, it is easy to monitor and control different environmental conditions such as pH, pO₂ pCO₂ etc.; iv) cell sampling is easy; v) since the beads settle down easily, cell harvesting and downstream processing of products is easy; vi) microcarrier cultures can be relatively easily scaled up using conventional equipment like fermenters that have been suitably modified.

[0006] When developing further improvements the following requirements for an optimum microcarrier should be met: i) the surface properties of the beads should be such that cells can adhere and proliferate rapidly, preferably the contour should be even; ii) the density of the beads should be slightly more than that of the culture medium, so as to facilitate easy separation; conventional culture media are aqueous in nature and have densities ranging from 1.03-1.09 g/cc, however, the density should not exceed a certain limit the optimum range being 1.03-1.045 g/ml; gentle stirring, which will not harm the shear-sensitive cells, should be sufficient to keep them in suspension, if the beads settle cell growth will be prevented; iii) the size-distribution of the beads should be narrow so that an even suspension of all microcarriers is achieved and cells attain confluency at approximately the same time; also, clustering of microcarriers in solution should be prevented; iv) the optical properties should enable easy microscopic observation; v) they should be non-toxic not only for the survival and good growth of the cells but also for cell culture products that are used for veterinary or clinical purposes; vi) the matrix of the beads should be such that collisions, which occur during stirring of the culture, do not cause fragmentation of the beads.

[0007] An important modification in the development of improved microcarriers is the coating of core particles with collagen. The advantage of using collagen is that it is a promoter for both cell attachment and cell growth. In addition cells can be easily detached by proteolytic enzymes. Also microcarriers coated with fibronectin, which is a cell adhesion promoter, have been described.

[0008] Cell surface receptors that are involved in binding are identified as integrins. More than 20 integrins are known, each having different ligand specificities. Many integrins can recognise the amino acid sequence RGD (arginine - glycine - aspartic acid). The number of proteins known to comprise an RGD sequence is limited, estimated to be approximately 400. Also not every occurring RGD sequence is involved in a binding function. In particular RGDS is known to be involved in cell adhesion. It is known that natural native collagens comprise the amino acid sequence RGD. Examples are for instance murine COL1A1-1, COL1A1-2, COL1A1-3, rat COL3A1, human COL1A-1, COL2A-1, COL3A-1 and COL1A1-2. Cell attachment to collagen follows a highly specific mechanism, as cells secrete the protein fibronectin which has a specific affinity for collagen. After attachment to collagen, the fibronectin binds subsequently to the integrin proteins in the cell.

[0009] Gelatine is a degradation product of collagen, and the term truly reflects a heterogeneous mixture of proteins

and peptides with MW's ranging from 5,000 up to more than 400,000 daltons. A certain fraction of these gelatine polymers will contain an RGD motive and a certain fraction of hydrolysed molecules will not have such an RGD motif.

[0010] Burgess and Myles describe the chemical coupling of RGD containing peptides to type I collagen, which method is complicated and introduces impurities into the target materials and has limited modification freedom (Ann Biomed Eng 2000 Jan;28(1):1 10-118).

[0011] US 5,512,474 aims at a good cell adhesion by combining cell adhesion factors and positively charged molecules to the surface of a cell culture support. Fibronectin is identified as a cell adhesion intermediate.

[0012] US 5,514,581 is concerned with the production of substantially new polypeptides by using automated methods for the chemical synthesis of DNA in combination with recombinant DNA technology. The patent describes non-natural polypeptides which may be of use in commercial applications for which known, naturally occurring polypeptides are not appropriate. Although the artificial proteins could contain an RGD sequence, the resulting bio-polymers have little resemblance with naturally occurring proteins, and will cause immunological problems in case of medical applications.

[0013] Cell attachment also plays an important role in medical applications such as wound treatment (including artificial skin materials), bone and cartilage (re)growth and implantations and artificial blood vessel materials. Thus in medical applications often the demand is that a material has a biocompatible coating in terms of cell attachment. In general collagen is preferred over structures like those described in US 5,514,581 since collagen has a low antigenicity and is present in both skin and bone or cartilage. Microcarriers coated with gelatine are applied, but also porous matrixes of collagen are used. An example is collagen coated beads to grow keratinocytes and the subsequent transplantation of the beads containing keratinocytes to promote healing of wounds is described in US 5,972,332. Another area of interest in relation to cell attachment is the blocking of attachment receptors of cells. For instance by blocking the attachment receptors cancer metastasis may be influenced or inhibited. Also smaller peptides with RGD sequences are used to block the binding sites on cells thus preventing unwanted interactions like aggregation or coagulation as described for example in EP 0,628,571.

[0014] There is however an urgently felt need for further improvements of materials for use in applications involving cell attachment. The fibronectin-mediated cell attachment mechanism is effectuated to attach cells to natural gelatines. However, natural gelatines are not safe in terms of prion and virus impurities. The RGD mediated mechanism for cell attachment is effectuated by several artificial bio-polymers, produced by chemical or by recombinant DNA technologies. However, these materials have non-natural sequences and have a risk of initiating an immunological response which could result in serious medical problems.

[0015] Whereas often the terms 'collagen', 'collagen-related', collagen-derived' or the like are also used in the art, the term 'gelatine' or 'gelatine-like' protein will be used throughout the rest of this description. Natural gelatine is a mixture of individual polymers with MW's ranging from 5,000 up to more than 400,000 daltons. The terms cell adhesion and cell attachment are used interchangeably. Also the terms RGD sequence and RGD motif are used interchangeably.

SUMMARY OF THE INVENTION

[0016] It is an object of the invention to provide polypeptides or peptides which have an improved, preferably a high cell binding capacity and selectivity. A further object of the invention is to provide cell binding peptides or polypeptides with no risk for viral infection or other pathogens or health related hazards such as prions. It is also an object of the invention to provide peptides or polypeptides which do not evoke any immune response when being in contact, directly or indirectly, with the human immune system.

[0017] Surprisingly it was found that all these objectives were met by an RGD-enriched gelatine with a more even distribution of RGD sequences than occurring in a natural gelatine and with a minimum level of RGD sequences. The level of RGD sequences is expressed as a percentage. This percentage is calculated by dividing the number of RGD motifs divided by the total number of amino acids and multiplying the result with 100. Note that the highest percentage of RGD motifs, i.e. in a gelatine consisting solely of RGD motifs, would be 33.33. Also, the number of RGD motifs is an integer starting from 1, 2, 3, ...etc.

[0018] The RGD-enriched gelatine of the invention is highly suitable for coating a cell culture support for growing anchor-dependant cell types. Thus the invention relates to a cell support comprising an RGD-enriched gelatine in which the percentage of RGD motifs related to the total number of amino acids is at least 0.4 and if the RGD-enriched gelatine comprises 350 amino acids or more, each stretch of 350 amino acids contains at least one RGD motif.

[0019] The invention provides RGD-enriched gelatine for binding to integrins in which the percentage of RGD motifs related to the total number of amino acids is at least 0.4 and if the RGD-enriched gelatine comprises 350 amino acids or more, each stretch of 350 amino acids contains at least one RGD motif and said gelatine consists for at least 80% of one or more parts of native human collagen sequences and said parts of native human collagen sequences have a length of at least 30 amino acids.

[0020] Also the invention relates to the use of an RGD-enriched gelatine according to the invention as a coating on scaffolds for tissue engineering or on implant or transplant materials.

[0021] Further the RGD-enriched gelatine of the invention is designed for use in medical applications, in particular as a coating on implant or transplant material or as a component of drug delivery systems, for inhibition of cancer metastasis, for prevention of platelet aggregation, for use as an antithrombic agent, for use as tissue adhesive, for dental products, for use as artificial skin matrix material and for use after surgery to prevent tissue adhesion.

DESCRIPTION OF THE INVENTION

[0022] The present invention is directed to peptides polypeptides or proteins, in particular to gelatines or gelatine-like proteins, which are highly suitable for cell adhesion and can be used in medical or biotechnological applications. More specifically the invention is directed to cell binding peptides or polypeptides that have a low antigenicity and that can be used without the risk of transferring pathological factors such as viruses, prions and the like.

[0023] It was found, surprisingly, that it is possible to obtain peptides or polypeptides with excellent cell attachment properties and which do not display any health related risks by production of RGD-enriched gelatines in which the percentage of RGD motifs related to the total number of amino acids is at least 0.4. If the RGD-enriched gelatine comprises 350 amino acids or more, each stretch of 350 amino acids contains at least one RGD motif. Preferably the percentage of RGD motifs is at least 0.6, more preferably at least 0.8, more preferably at least 1.0, more preferably at least 1.2 and most preferably at least 1.5. Such (recombinant) gelatines are very suitable for coating cell culture supports which can be used in biotechnological processes or in medical applications. In the context of this invention a "cell support" is a substance that gives support to cells to facilitate their growth and multiplication.

[0024] A percentage RGD motifs of 0.4 corresponds with at least 1 RGD sequence per 250 amino acids. The number of RGD motifs is an integer, thus to meet the feature of 0.4%, a gelatine consisting of 251 amino acids should comprise at least 2 RGD sequences. Preferably the RGD-enriched recombinant gelatine of the invention comprises at least 2 RGD sequence per 250 amino acids, more preferably at least 3 RGD sequences per 250 amino acids, most preferably at least 4 RGD sequences per 250 amino acids. In a further embodiment an RGD-enriched gelatine according to the invention comprises at least 4 RGD motifs, preferably 6, more preferably 8, even more preferably 12 up to and including 16 RGD motifs.

[0025] The term 'RGD-enriched gelatine' in the context of this invention means that the gelatines of this invention have a certain level of RGD motifs, calculated as a percentage of the total number of amino acids per molecule and a more even distribution of RGD sequences in the amino acid chain than a natural gelatine. In humans up to date 26 distinct collagen types have been found on the basis of protein and or DNA sequence information (see K. Gelse et al, Collagens-structure, function and biosynthesis, Advanced Drug Delivery reviews 55 (2003) 1531-1546). Sequences of natural gelatines, both of human and non-human origin, are described in the Swiss-Prot protein database. Herebelow follows a list of suitable human native sequences, identified by their entry name and primary accession number in the Swiss-Prot database, that may serve as a source of parts of natural sequences comprised in the RGD-enriched gelatines of this invention.

CA11 HUMAN (P02452) Collagen alpha 1(I) chain precursor. {GENE: COL1A1} - Homo sapiens (Human)

CA12 HUMAN (P02458) Collagen alpha 1(II) chain precursor [Contains: Chondrocalcin]. {GENE: COL2A1} - Homo sapiens (Human)

CA13 HUMAN (P02461) Collagen alpha 1(III) chain precursor. {GENE: COL3A1} - Homo sapiens (Human)

CA14 HUMAN (P02462) Collagen alpha 1(IV) chain precursor. {GENE: COL4A1} - Homo sapiens (Human)

CA15 HUMAN (P20908) Collagen alpha 1(V) chain precursor. {GENE: COL5A1} - Homo sapiens (Human)

CA16 HUMAN (P12109) Collagen alpha 1(VI) chain precursor. {GENE: COL6A1} - Homo sapiens (Human)

CA17 HUMAN (Q02388) Collagen alpha 1(VII) chain precursor (Long-chain collagen) (LC collagen). {GENE: COL7A1} - Homo sapiens (Human)

CA18 HUMAN (P27658) Collagen alpha I(VIII) chain precursor (Endothelial collagen). {GENE: COL8A1} - Homo sapiens (Human)

CA19 HUMAN (P20849) Collagen alpha 1(IX) chain precursor. {GENE: COL9A1} - Homo sapiens (Human)

CA1A HUMAN (Q03692) Collagen alpha 1(X) chain precursor. {GENE: COL10A1} - Homo sapiens (Human)

CA1B HUMAN (P12107) Collagen alpha 1(XI) chain precursor. {GENE: COL11A1} - Homo sapiens (Human)

CA1C HUMAN (Q99715) Collagen alpha 1(XII) chain precursor. {GENE: COL12A1} - Homo sapiens (Human)

CA1E HUMAN (P39059) Collagen alpha 1(XV) chain precursor. {GENE: COL15A1} - Homo sapiens (Human)

CA1F HUMAN (Q07092) Collagen alpha 1(XVI) chain precursor. {GENE: COL16A1} - Homo sapiens (Human)

CA1G HUMAN (Q9UMD9) Collagen alpha 1(XVII) chain (Bullous pemphigoid antigen 2) (180 kDa bullous pemphigoid antigen 2). {GENE: COL17A1 OR BPAG2 OR BP180} - Homo sapiens (Human)

CA1H HUMAN (P39060) Collagen alpha 1(XVIII) chain precursor [Contains: Endostatin]. {GENE: COL18A1} - Homo sapiens (Human)

CA1I HUMAN (Q14993) Collagen alpha 1(XIX) chain precursor (Collagen alpha 1(Y) chain). {GENE: COL19A1} -

Homo sapiens (Human)

CA21 HUMAN (P08123) Collagen alpha 2(I) chain precursor. {GENE: COL1A2} - Homo sapiens (Human)

CA24 HUMAN (P08572) Collagen alpha 2(IV) chain precursor. {GENE: COL4A2} - Homo sapiens (Human)

CA25 HUMAN (P05997) Collagen alpha 2(V) chain precursor. {GENE: COL5A2} - Homo sapiens (Human)

CA26 HUMAN (P12110) Collagen alpha 2(VI) chain precursor. {GENE: COL6A2} - Homo sapiens (Human)

CA28 HUMAN (P25067) Collagen alpha 2(VIII) chain precursor (Endothelial collagen). {GENE: COL8A2} - Homo sapiens (Human)

CA29 HUMAN (Q14055) Collagen alpha 2(IX) chain precursor. {GENE: COL9A2} - Homo sapiens (Human)

CA2B HUMAN (P13942) Collagen alpha 2(XI) chain precursor. {GENE: COL11A2} - Homo sapiens (Human)

CA34 HUMAN (Q01955) Collagen alpha 3(IV) chain precursor (Goodpasture antigen). {GENE: COL4A3} - Homo sapiens (Human)

CA35 HUMAN (P25940) Collagen alpha 3(V) chain precursor. {GENE: COL5A3} - Homo sapiens (Human)

CA36 HUMAN (P12111) Collagen alpha 3(VI) chain precursor. {GENE: COL6A3} - Homo sapiens (Human)

CA39 HUMAN (Q14050) Collagen alpha 3(IX) chain precursor. {GENE: COL9A3} - Homo sapiens (Human)

CA44 HUMAN (P53420) Collagen alpha 4(IV) chain precursor. {GENE: COL4A4} - Homo sapiens (Human)

CA54 HUMAN (P29400) Collagen alpha 5(IV) chain precursor. {GENE: COL4A5} - Homo sapiens (Human)

CA64 HUMAN (Q14031) Collagen alpha 6(IV) chain precursor. {GENE: COL4A6} - Homo sapiens (Human)

EMD2 HUMAN (Q96A83) Collagen alpha 1(XXVI) chain precursor (EMI domain containing protein 2) (Emu2 protein) (Emilin and multimerin-domain containing protein 2). {GENE: EMD2 OR COL26A1 OR EMU2} - Homo sapiens (Human)

[0026] Natural gelatines are known to comprise RGD sequences. It is important however that a gelatine molecule does not contain too large parts without RGD motifs. Too large parts of gelatines without RGD sequence reduce the possibility of cell attachment when such a gelatine is used for instance as a coating on a microcarrier. Apparently not all RGD sequences in a gelatine are under all circumstances available for cell attachment. It was found that cell attachment was remarkably improved in gelatines according to the invention compared to gelatines having a stretch of amino acids of more than 350 without an RGD sequence. For gelatines of less than 350 amino acids it is sufficient to have a percentage of RGD sequences of at least 0.4. Note that for a gelatine of 251-350 amino acids this means that at least 2 RGD motifs are present.

[0027] In a preferred embodiment the RGD-enriched gelatine is prepared by recombinant DNA technology. Recombinant gelatines of this invention are preferably derived from collageneous sequences. Nucleic acid sequences encoding collagens have been generally described in the art. (See, e. g., Fuller and Boedtker (1981) Biochemistry 20: 996-1006; Sandell et al. (1984) J Biol Chem 259: 7826-34; Kohno et al. (1984) J Biol Chem 259: 13668-13673; French et al. (1985) Gene 39: 311-312; Metsaranta et al. (1991) J Biol Chem 266: 16862-16869; Metsaranta et al. (1991) Biochim Biophys Acta 1089: 241-243; Wood et al. (1987) Gene 61: 225-230; Glumoff et al. (1994) Biochim Biophys Acta 1217: 41-48; Shirai et al. (1998) Matrix Biology 17: 85-88; Tromp et al. (1988) Biochem J 253: 919-912; Kuivaniemi et al. (1988) Biochem J 252: 633640; and Ala-Kokko et al. (1989) Biochem J 260: 509-516.).

[0028] For pharmaceutical and medical uses, recombinant gelatines with amino acid sequences closely related to or identical to amino acid sequences of natural human collagens are preferred. More preferably the amino acid sequence of the inventive gelatine is designed by a repetitive use of a selected amino acid sequence of a human collagen. A part of a natural collagen sequence comprising an RGD motif is selected. The percentage of RGD motifs in such a selected sequence depends on the chosen length of the selected sequence, selection of a shorter sequence results in a higher RGD percentage. Repetitive use of a selected amino acid sequence results in a gelatine with a higher molecular weight, which is non-antigenic and with an increased number of RGD motifs (compared to natural gelatines or collagens). Natural non-human sources include non-human mammalian sources, such as bovine, porcine, and equine sources, and other animal sources, such as chicken, murine, rat and piscine sources.

[0029] Thus in a preferred embodiment the RGD-enriched gelatine according to the invention comprises a part of a native human collagen sequence. Preferably the RGD-enriched gelatine consists for at least 80 % of one or more parts of one or more native human collagen sequences. Each of such parts of human collagen sequences should have a length of at least 30 amino acids, more preferably at least 45 amino acids, most preferably at least 60 amino acids, up to e.g. 240, preferably up to 150, most preferably up to 120 amino acids, each part preferably containing one or more RGD sequences. Preferably the RGD-enriched gelatine consists of one or more parts of one or more native human collagen sequences.

[0030] An example of a suitable source of a gelatine according to this invention is human COL1A1-1. A part of 250 amino acids comprising an RGD sequence is given in SEQ ID NO: 1.

[0031] RGD sequences in gelatines can adhere to specific receptors on the cell wall called integrins. These integrins differ in their specificity in recognising cell binding amino acid sequences. Although both natural gelatine and, for example, fibronectin may contain RGD sequences, gelatine can bind cells that will not bind to fibronectin and vice versa. Therefore

fibronectin comprising RGD sequences cannot always replace gelatine for cell adhesion purposes.

[0032] Recombinantly produced gelatine does not suffer from the disadvantage of contamination with pathogens originating from the animal from which the gelatine was derived.

[0033] When used as or in combination with a cell culture support, gelatine functions as a cell binding polypeptide. It has the advantage over other polypeptides that it can also be metabolised by the cells growing on it. A further advantage is that it can be easily digested enzymatically so that cells can be harvested with almost 100% yield.

A further advantage of recombinantly produced gelatines is that the molecular weight (MW) can be kept uniform. Natural gelatines unavoidably have a broad molecular weight distribution with peptides smaller than 5,000 kD up to large polymers with a molecular weight larger than 400,000 kD, resulting from the production method. In particular in combination with microcarrier core beads as cell culture support, a disadvantage of smaller peptides is that they will adhere inside finer pores of the microcarrier which cannot be reached by the cells so that part of the added gelatine is not used. With recombinant production methods the gelatine can be designed with the desired molecular weight, preventing this undesired loss of material.

[0034] In a further embodiment the gelatine of the invention has a molecular weight of about 30 kDa to about 200 kDa to coat a core bead resulting in a cell culture support in the form of a microcarrier.

[0035] In addition to the presence of RGD sequences, the molecular weight range of the gelatine offers striking advantages and provides the resulting microcarriers with advantageous properties. A key problem in the process of coating microcarrier core beads is the clumping together of beads. In particular such clumping reduces the available surface area for cell attachment and disturbs the size distribution of the microcarriers rendering them unusable.

[0036] It was found that the relatively small fraction of high MW gelatine polymer molecules within a natural gelatine batch is to a large extent responsible for the clumping together of beads during the microcarrier production process. It was concluded that when such a gelatine polymer with high molecular weight adheres to a core bead, a part of the peptide chain may point away from the surface of the core bead and as such be an anchor for other beads and thus induce coagulation.

[0037] It is therefore preferred according to the present invention to coat core beads with gelatine having a molecular weight of less than 200 kDa, more preferably less than 150 kDa.

[0038] Furthermore, it was found that the small MW fraction of a natural gelatine shows unfavourable microcarrier coating characteristics. This small MW fraction showed a lower adsorption force to the microcarrier beads, and, thus, when not being adsorbed it promotes microcarrier clumping after the chemical cross-linking step. Additionally, in case of the use of lower concentrations of the gelatine in the microcarrier coating process to prevent clumping, the small MW fraction is at first instance adsorbed to the microcarrier but has the unfavourable characteristic of entering the small pores of a microcarrier porous core beads, thereby not contributing to the attachment of the cells on the microcarrier during the cell culture step. Thus, the molecular weight of the gelatine should be high enough to perform the actual coating process effectively resulting in efficient coating, to prevent clumping of the core beads and to prevent loss of the gelatine. Thus the molecular weight of the gelatine should be higher than 30 kDa, preferably higher than 60 kDa, most preferably higher than 70 kDa.

[0039] Preferably the molecular weight of the gelatine or gelatine-like protein is uniform, with more than 75%, preferably more than 85%, more preferably more than 95% or even at least 98% of the gelatine or gelatine-like protein having a uniform MW within 20% from the selected molecular weight.

[0040] By selecting a molecular weight, within the above specified range, in a coating process the viscosity of the gelatine or gelatine-like protein coating solution can be accurately controlled. Complete or, more important, partial gelling of such a gelatine solution can be prevented while being able to select a high as possible concentration of the gelatine.

[0041] The uniform gelatine ensures a process of identically coated microcarriers. The uniform coating process allows the use of a minimum amount of gelatine and the use of a minimum volume of gelatine coating solution. All this results in a far more efficient coating process than that is known in the art.

[0042] In one embodiment of the invention non-porous core beads are coated with gelatine of the invention. Suitably non-porous core beads are made of polystyrene or glass. Other suitable non-porous materials are known to those skilled in the art.

[0043] A particular advantageous embodiment is the process of the invention wherein porous core beads, such as beads from modified dextran or cross-linked cellulose, or (porous) polystyrene, in particular DEAE-dextran, are coated with gelatine of the invention. Other suitable porous materials are known to those skilled in the art, and include e.g. other chemically modified or non-modified polysaccharides. The lower molecular weight limit prevents that gelatine or gelatine-like protein enters the pores of the porous core beads thereby preventing inefficient coating of the beads and unnecessary loss of gelatine or gelatine-like protein.

[0044] The size of the beads may vary from 50 μm to 500 μm . Typical mean microcarrier bead sizes are about 100, about 150 or about 200 μm in physiological saline. Size ranges with at least 90% of the beads lying within the range may vary from 80-120 μm , 100-150 μm , 125-175 μm or 150-200 μm .

[0045] A wide range of cells may be cultured on microcarriers. For instance, cells from invertebrates, from fish, birds

and cells of mammalian origin may be cultivated on microcarriers. Transformed and normal cell lines, fibroblastic and epithelial cells and even genetically engineered cells may be cultivated on microcarriers for various biological applications such as for the production of immunologicals like interferons, interleukins, growth factors etc. Cells cultured on microcarriers also serve as hosts for a variety of viruses that are used as vaccines like foot and mouth disease or rabies.

[0046] Microcarrier cultures have a wide number of applications other than mass cultivation as well. Cells growing on microcarriers serve as an excellent tool for studying different aspects of cell biology such as cell-to-cell or cell-to-substratum interactions. Cell differentiation and maturation, metabolic studies may also be carried out using microcarriers. Such cells can also be used for electron microscopic studies or for the isolation of cell organelles such as the cell membrane. Also, this system is essentially a three-dimensional system and serves as a good 3-D model. Similarly, co-cultivation of cells can be done using this system. Thus applications include the production of large quantities of cells, viruses and cell products (e.g. interferon, enzymes, nucleic acids, hormones), studies on cell adhesion, differentiation and cell function, perfusion column culture systems, microscopy studies, harvesting mitotic cells, isolation of cells, membrane studies, storage and transport of cells, assays involving cell transfer and studies on uptake of labelled compounds.

[0047] Microcarriers may also be used for the depletion of macrophages from a population of spleen cells. DEAE-dextran microcarriers can potentiate stimulation of lymphocytes by concanavalin A (con A). Microcarrier beads confluent with allogenic tumour cells can be injected in mice to increase humoral and cell-mediated immunity. Plant protoplasts can be immobilised on DEAE-dextran microcarriers.

[0048] As a result of the large surface area to volume ratio provided by microcarriers, they can successfully be used for a variety of biological productions on a laboratory scale as well as an industrial scale of for instance even 4000 litres or more.

[0049] Large scale production of expressed products can be accomplished with gelatine-coated microcarriers. Loading of microcarriers in production scale bioreactors is generally 20 g/l, but may be increased up to 40 g/l. Microcarriers may be used in batch and perfusion systems, in stirred cultures, and wave bioreactors, as well as to increase the surface area of traditional stationary monolayers and roller cultures.

[0050] In a further preferred embodiment the gelatine or gelatine-like protein is in essence free of hydroxyproline residues. Hydroxylation is a requirement for the formation of triple helices in collagen and plays a role in gelation of gelatine. In particular less than 10%, more preferably less than 5% of the amino acid residues of the recombinant gelatines are hydroxyprolines, preferably the recombinant gelatine is free from hydroxyprolines in applications where the gelling capability of the recombinant gelatine is unfavourable. The hydroxyproline-free recombinant gelatines can be used in higher concentrations, and the solutions will be less viscous requiring less vigorous agitation, resulting in less shear forces on the cultured cells. As described in WO 02/070000 A1, recombinant gelatines which are in essence free from hydroxyprolines do not show immune reactions involving IgE in contrast to natural gelatine.

[0051] A process for the preparation of collagen coated microcarriers is described in US 4,994,388. In short providing a core bead with a collagen coating is performed in two steps: coating and fixing. The core beads are suspended in an acidic, aqueous collagen solution (0.01-0.1N acetic acid), and the solution is evaporated to dryness. The dry, collagen-coated beads are then suspended in a solution which contains a protein cross-linking agent such as glutaraldehyde, thus cross-linking the collagen coating. Alternatively, the core beads wetted with the collagen solution are not dried entirely before the start of the fixing step. Variations in coating conditions and alternative coating processes are well within the competence of those skilled in the art.

[0052] Recombinant structures can also be designed to incorporate additional positively charged groups, as in US 5,512,474, by building in additional arginines, lysines or histidines. Recombinant production of gelatines allows easy manipulation of the number of positively charged amino acids, meaning positively charged at the pH of the cell culture, in the produced protein. In particular arginine, lysine and histidine carry positive charges. It is well within the reach of the skilled person to design a gelatine with a net positive charge at the pH of the particular cell culture of interest. Cells are normally cultured at a pH of 7-7.5. Thus in a further embodiment of the invention a gelatine or gelatine-like protein is used that has a net positive charge at pH 7-7.5. Preferably the net positive charge is +2, +3, +4, +5, +10 or higher. Thus in a further embodiment the invention relates to a gelatine that has a net positive charge at pH 7-7.5. Preferably the net positive charge is +2, +3, +4, +5, +10 or higher.

[0053] In a further embodiment the invention relates to RGD-enriched gelatines of at most 10 kDa, preferably at most 5 kDa. Such an RGD-enriched gelatine containing at least one RGD sequence can be used to block surface receptors on cells. Blocking of receptors of cells is applied in for example inhibiting angiogenesis or in blocking integrins on cardiac fibroblasts.

[0054] Cell supports coated with recombinant gelatine according to the invention, on which cells have been grown can be applied during, for example, transplantation of skin or wound treatment or to enhance bone or cartilage (re) growth. It is also possible to coat implant materials with recombinant gelatine of the invention to adhere cells which promote implantation.

[0055] Thus a specific embodiment is a cell support according to this invention, said cell support being a microcarrier

[0056] Other particular embodiments are cell supports selected from the group consisting of an RGD-enriched coated implant or transplant material, an RGD-enriched coated scaffold for tissue engineering, (part of) a dental product, (part of) a wound healing product, (part of) artificial skin matrix material and (part of) a tissue adhesive.

[0057] A natural gelatine molecule in its primary amino acid sequence basically consists of repeats of GXY triplets, thus approximately one third of the total number of amino acids is a glycine. The molecular weight of gelatine is typically large, values of the molecular weight vary from 10,000 to 300,000 Dalton and higher.

[0058] In a further embodiment the invention relates to RGD-enriched gelatines which are not glycosylated. Glycosylation takes place at the amino acids Asn (N-glycosydic structures), or Ser or Thr (O-glycosydic structures). Glycosylation should be preferably prevented for applications where no immune response is desired. The absence of Asn, Ser and Thr amino acids in the primary sequence is an effective way to prevent the glycosylation in biotechnological production systems using for instance yeast cell cultures.

[0059] Furthermore, characteristic for gelatine is the unusual high content of proline residues. Even more characteristic is that in natural gelatine a number of the proline residues is hydroxylated. Most prominent site of hydroxylation is the 4-position resulting in the presence in the gelatine molecule of the unusual amino acid 4-hydroxyproline. In a triplet 4-hydroxyproline is always found in the Y position. The presence of the hydroxyproline residues is responsible for the fact that a gelatine molecule in its secondary structure can adopt a helical conformation. Thus, it is preferred that the gelatines to be used according to the invention in applications in which the gelling property is unfavourable contain less than 5%, preferably less than 3%, most preferably less than 1% of hydroxyproline residues.

[0060] In this invention gelatine-like proteins are to be understood as proteins in which GXY triplets or stretches of GXY triplets are separated by one or more amino acids.

[0061] The RGD-enriched gelatines according to the invention can be produced by recombinant methods as disclosed in EP-A-0926543, EP-A-1014176 or WO01/34646. Also for enablement of the production and purification of gelatines of the invention reference is made to the examples in EP-A-0926543 and EP-A-1014176.

[0062] The preferred method for producing an RGD-enriched gelatine is by starting with a natural nucleic acid sequence encoding a part of the collagen protein that includes an RGD amino acid sequence. By repeating this sequence an RGD-enriched gelatine is obtained.

[0063] If X-RGD-Y is a part of the natural collagen amino acid sequence, a (part of a) gelatine with three RGD amino acid sequences would have the structure -X-RGD-Y-(GXY)_n-GX-RGD-Y-(GXY)_n-GX-RGD-Y-, with n being an integer starting from 0. By varying n the number of RGD sequences on the total amino acids number can be controlled. A clear advantage of this method is that the amino acid sequence remains most natural and thus has the lowest risk of inducing immunological response in clinical applications.

[0064] Starting from a natural nucleic acid sequence encoding (part of) a collagen, also point mutations can be applied so as to yield a sequence encoding an RGD sequence. Based on the known codons a point mutation can be performed so that an RGX sequence after mutation will yield an RGD sequence, alternatively also an YGD sequence can be mutated to yield an RGD sequence. Also it is possible to carry out two mutations so that an YGX sequence will give an RGD sequence. Also it may be possible to insert one or more nucleotides or delete one or more nucleotides giving rise to a desired RGD sequence.

[0065] Thus the gelatine-like proteins can be produced by expression of nucleic acid sequence encoding such polypeptide by a suitable micro-organism. The process can suitably be carried out with a fungal cell or a yeast cell. Suitably the host cell is a high expression host cells like *Hansenula*, *Trichoderma*, *Aspergillus*, *Penicillium*, *Saccharomyces*, *Kluyveromyces*, *Neurospora* or *Pichia*. Fungal and yeast cells are preferred to bacteria as they are less susceptible to improper expression of repetitive sequences. Most preferably the host will not have a high level of proteases that attack the collagen structure expressed. In this respect *Pichia* or *Hansenula* offers an example of a very suitable expression system. Use of *Pichia pastoris* as an expression system is disclosed in EP-A-0926543 and EP-A-1014176. In one embodiment the micro-organism is free of active post-translational processing mechanism such as in particular hydroxylation of proline and also hydroxylation of lysine. In another embodiment the host system has an endogenous proline hydroxylation activity by which the recombinant gelatine is hydroxylated in a highly effective way. The selection of a suitable host cell from known industrial enzyme producing fungal host cells specifically yeast cells on the basis of the required parameters described herein rendering the host cell suitable for expression of recombinant gelatine-like proteins suitable in compositions according to the invention in combination with knowledge regarding the host cells and the sequence to be expressed will be possible by a person skilled in the art.

EXAMPLES

EXAMPLE 1:

[0066] An RGD-enriched gelatine was produced by starting with the nucleic acid sequence that encodes for a part of the gelatine amino acid sequence of human COL1A1-1. The methods as disclosed in EP-A-0926543, EP-A-1014176

and WO01/34646 were used. The sequence of this RGD-enriched gelatine according to the invention is given in SEQ ID NO: 2. A total of four RGD sequences are present in the molecule which corresponds to a level of four RGD sequences per 250 amino acids. In a similar way gelatines with one and two RGD sequences per 250 amino acids were made.

EXAMPLE 2:

Preparation of Microcarriers Beads

[0067] Polystyrene beads with an average diameter of 100 micrometers are used. The heterobifunctional cross-linking agent, BBA-EAC-NOS, is used to covalently immobilise gelatine onto polystyrene beads. The BBA-EAC-NOS is added to the polystyrene beads and allowed to adsorb. Next, gelatine is added and is allowed to react with the NOS synthetic polymer to produce covalent coupling to the spacer. Then the beads are photoactivated (at 320 nm) to covalently immobilise the spacer (and covalently coupled gelatine) to the polystyrene beads. Finally, loosely adherent gelatine is removed by overnight washing with the mild detergent Tween 20 in phosphate buffered saline (pH 7.2).

Cell Types and Culture Conditions

[0068] Green monkey kidney (Vero) cells, Chinese hamster ovary (CHO) cells, normal rat kidney fibroblast (NRK-49F) cells, and Madin Darby canine kidney (MDCK) cells were purchased from ATCC. All four cell types were passaged and maintained in 75 cm² flasks at 37 DEG C. in a 5 % CO₂ environment. Vero and NRK-49F cells were cultured in Dulbecco's Modified Eagles's Medium (DMEM), CHO cells were cultured in Ham's F-12 Nutrient Mixture, and MDCK cells were cultured in Minimum Essential Medium (MEM) with Earle's salts.

[0069] With the Vero and CHO cells, the medium was supplemented with 10% fetal bovine serum (FBS), 2 mM L-glutamine, 20 mM HEPES buffer, 1 mM sodium pyruvate, 100 ug/ml streptomycin, and 100 units/ml penicillin (final pH 7.1). With the NRK-49F cells, the DMEM was supplemented with 5% FBS, 2 mM L-glutamine, 1 mM sodium pyruvate, non-essential amino acids (0.1 mM each), 100 ug/ml streptomycin, 100 units/ml penicillin, and 0.25 ug/ml of amphotericin B (final pH 7.1). With the MDCK cells, the MEM was supplemented with 10% FBS, 2 mM L-glutamine, non-essential amino acids (0.1 mM each), and 100 ug/ml streptomycin, 100 units/ml penicillin, and 0.25 ug/ml of amphotericin B (final pH 7.1).

[0070] In order to standardise the physiology of cells prior to each experiment, cells were passed into 150 cm² flasks 2 to 3 days prior to inoculation of microcarrier beads. Cells were trypsinised (0.05 % trypsin, 0.53 mM EDTA in PBS) for removal from the flasks. For the microcarrier experiments, the cells were centrifuged to remove the trypsin medium and resuspended to about 1.times.10⁶ cells/ml in culture medium. The viable cell concentration was determined by Trypan dye exclusion (0.4 % Trypan blue in 0.9% saline).

Cell Culture and Assays in Spinner Flasks

[0071] For the cell attachment assay, 20 mg/ml of coated polystyrene beads were used and the cell concentration was 1.5.times.10⁵ cells/ml for each cell type.

Microcarriers were cultured with 100 ml cultures being maintained in 250 ml spinner vessels and stirred with suspended magnetic impellers (50 rpm).

[0072] The kinetics of cell attachment were assayed as a decrease in supernatant cell concentration. For sample removal the agitation was stopped briefly (about 30 seconds) at which time the microcarriers settled and a supernatant sample was removed for cell quantitation as described below.

For the cell counts, the cells were stained by mixing with an equal volume of crystal violet (0.1% w/w) in 0.1 M citric acid, and then counted with a hemocytometer. Cell depletion from the medium was used as an indicator of cells attached to beads

[0073] To verify that cells removed from the medium were indeed attached to microcarriers (and not lysed), cells attached to microcarriers were quantitated at the end of each cell attachment assay. One ml aliquots of well-agitated carrier medium were removed, the microcarriers were allowed to settle, and the settled microcarriers were resuspended in crystal violet/citric acid as described above. After incubating 1 hour at 37 DEG C., the suspension was sheared by sucking into and out of a Pasteur pipet to release nuclei, which were quantitated with a hemocytometer.

[0074] Gelatines with different RGD content were used as a microcarrier coating according to the foregoing procedure. Recombinant gelatines with no, one, two and four RGD sequences per 250 amino acids were tested. A clear correlation was found between the number of RGD sites and the cell attachment. Best results were obtained at a level of four RGD sites per 250 amino acids.

[0075] EXAMPLE 3: An RGD-enriched gelatine was produced by starting with the nucleic acid sequence that encodes for a part of the gelatine sequence of human COL5A2. The methods as disclosed in EP-A-0926543, EP-A-1014176 and

EP 1 894 945 A2

WO01/34646 were used. The sequence of this RGD-enriched gelatine according to the invention is given in SEQ ID NO: 3. The percentage of RGD motifs in this sequence is 0.8 and a stretch of 435 amino acids without an RGD sequence is present.

[0076] The above mentioned gelatine was used as a microcarrier coating according to the procedure in example 2. The cell attachment of this gelatine was compared with a gelatine with two RGD motifs per 250 amino acids as mentioned in example 1. Although the percentage of RGD motifs in both gelatines is the same (0.8%) the gelatine from example 1 clearly gave a much better cell attachment. This is attributed to the more even distribution of RGD motifs.

10

15

20

25

30

35

40

45

50

55

EP 1 894 945 A2

SEQUENCE LISTING

<110> Fuji Photo Film B.V.
 5 <120> RGD-enriched gelatine-like proteins with enhanced cell binding
 <130> P206294PCT
 <160> 3
 10 <170> PatentIn version 3.1
 <210> 1
 <211> 250
 <212> PRT
 15 <213> Human partial COL1A1-sequence
 <400> 1
 Pro Pro Gly Pro Ala Gly Pro Ala Gly Glu Arg Gly Glu Gln Gly Pro
 1 5 10 15
 20 Ala Gly Ser Pro Gly Phe Gln Gly Leu Pro Gly Pro Ala Gly Pro Pro
 20 25 30
 25 Gly Glu Ala Gly Lys Pro Gly Glu Gln Gly Val Pro Gly Asp Leu Gly
 35 40 45
 Ala Pro Gly Pro Ser Gly Ala Arg Gly Glu Arg Gly Phe Pro Gly Glu
 50 55 60
 30 Arg Gly Val Gln Gly Pro Pro Gly Pro Ala Gly Pro Arg Gly Ala Asn
 65 70 75 80
 35 Gly Ala Pro Gly Asn Asp Gly Ala Lys Gly Asp Ala Gly Ala Pro Gly
 85 90 95
 Ala Pro Gly Ser Gln Gly Ala Pro Gly Leu Gln Gly Met Pro Gly Glu
 100 105 110
 40 Arg Gly Ala Ala Gly Leu Pro Gly Pro Lys Gly Asp Arg Gly Asp Ala
 115 120 125
 45 Gly Pro Lys Gly Ala Asp Gly Ser Pro Gly Lys Asp Gly Val Arg Gly
 130 135 140
 Leu Thr Gly Pro Ile Gly Pro Pro Gly Pro Ala Gly Ala Pro Gly Asp
 145 150 155 160
 50 Lys Gly Glu Ser Gly Pro Ser Gly Pro Ala Gly Pro Thr Gly Ala Arg
 165 170 175
 55

EP 1 894 945 A2

Gly Ala Pro Gly Asp Arg Gly Glu Pro Gly Pro Pro Gly Pro Ala Gly
 180 185 190

5 Phe Ala Gly Pro Pro Gly Ala Asp Gly Gln Pro Gly Ala Lys Gly Glu
 195 200 205

10 Pro Gly Asp Ala Gly Ala Lys Gly Asp Ala Gly Pro Pro Gly Pro Ala
 210 215 220

Gly Pro Ala Gly Pro Pro Gly Pro Ile Gly Asn Val Gly Ala Pro Gly
 225 230 235 240

15 Ala Lys Gly Ala Arg Gly Ser Ala Gly Pro
 245 250

20 <210> 2
 <211> 252
 <212> PRT
 <213> Artificial sequence

25 <220>
 <223> Repeated partial human COL1A1-1 sequence
 <400> 2

30 Gly Ala Pro Gly Ser Gln Gly Ala Pro Gly Leu Gln Gly Met Pro Gly
 1 5 10 15

Glu Arg Gly Ala Ala Gly Leu Pro Gly Pro Lys Gly Asp Arg Gly Asp
 20 25 30

35 Ala Gly Pro Lys Gly Ala Asp Gly Ser Pro Gly Lys Asp Gly Val Arg
 35 40 45

40 Gly Leu Thr Gly Pro Ile Gly Pro Pro Gly Pro Ala Gly Ala Pro Gly
 50 55 60

Ala Pro Gly Ser Gln Gly Ala Pro Gly Leu Gln Gly Met Pro Gly Glu
 65 70 75 80

45 Arg Gly Ala Ala Gly Leu Pro Gly Pro Lys Gly Asp Arg Gly Asp Ala
 85 90 95

50 Gly Pro Lys Gly Ala Asp Gly Ser Pro Gly Lys Asp Gly Val Arg Gly
 100 105 110

55 Leu Thr Gly Pro Ile Gly Pro Pro Gly Pro Ala Gly Ala Pro Gly Ala
 115 120 125

EP 1 894 945 A2

	Pro Gly Ser Gln Gly Ala Pro Gly Leu Gln Gly Met Pro Gly Glu Arg	
	130	135 140
5	Gly Ala Ala Gly Leu Pro Gly Pro Lys Gly Asp Arg Gly Asp Ala Gly	
	145	150 155 160
10	Pro Lys Gly Ala Asp Gly Ser Pro Gly Lys Asp Gly Val Arg Gly Leu	
		165 170 175
15	Thr Gly Pro Ile Gly Pro Pro Gly Pro Ala Gly Ala Pro Gly Ala Pro	
		180 185 190
20	Gly Ser Gln Gly Ala Pro Gly Leu Gln Gly Met Pro Gly Glu Arg Gly	
		195 200 205
25	Ala Ala Gly Leu Pro Gly Pro Lys Gly Asp Arg Gly Asp Ala Gly Pro	
		210 215 220
30	Lys Gly Ala Asp Gly Ser Pro Gly Lys Asp Gly Val Arg Gly Leu Thr	
		225 230 235 240
35	Gly Pro Ile Gly Pro Pro Gly Pro Ala Gly Ala Pro	
		245 250
40	<210> 3	
	<211> 625	
	<212> PRT	
	<213> Artificial sequence	
45	<220>	
	<223> Human Partial COL5A2 sequence	
50	<400> 3	
55	Gln Gly Pro Ile Gly Pro Pro Gly Glu Glu Gly Lys Arg Gly Pro Arg	
	1	5 10 15
60	Gly Asp Pro Gly Thr Leu Gly Pro Pro Gly Pro Val Gly Glu Arg Gly	
		20 25 30
65	Ala Pro Gly Asn Arg Gly Phe Pro Gly Ser Asp Gly Leu Pro Gly Pro	
		35 40 45
70	Lys Gly Ala Gln Gly Glu Arg Gly Pro Val Gly Ser Ser Gly Pro Lys	
		50 55 60
75	Gly Ser Gln Gly Asp Pro Gly Arg Pro Gly Glu Pro Gly Leu Pro Gly	
		65 70 75 80

EP 1 894 945 A2

	Ala Arg Gly Leu Thr Gly Asn Pro Gly Val Gln Gly Pro Glu Gly Lys	85	90	95
5	Leu Gly Pro Leu Gly Ala Pro Gly Glu Asp Gly Arg Pro Gly Pro Pro	100	105	110
10	Gly Ser Ile Gly Ile Lys Gly Gln Pro Gly Thr Met Gly Leu Pro Gly	115	120	125
	Pro Lys Gly Ser Asn Gly Asp Pro Gly Lys Pro Gly Glu Ala Gly Asn	130	135	140
15	Pro Gly Val Pro Gly Gln Arg Gly Ala Pro Gly Lys Asp Gly Lys Val	145	150	155
	Gly Pro Tyr Gly Pro Pro Gly Pro Pro Gly Leu Arg Gly Glu Arg Gly	165	170	175
20	Glu Gln Gly Pro Pro Gly Pro Thr Gly Phe Gln Gly His Pro Gly Pro	180	185	190
25	Pro Gly Pro Pro Gly Glu Gly Gly Lys Pro Gly Asp Gln Gly Val Pro	195	200	205
30	Gly Gly Pro Gly Ala Val Gly Pro Leu Gly Pro Arg Gly Glu Arg Gly	210	215	220
	Asn Pro Gly Glu Arg Gly Glu Pro Gly Ile Thr Gly Leu Pro Gly Glu	225	230	235
35	Lys Gly Met Ala Gly Gly His Gly Pro Asp Gly Pro Lys Gly Ser Pro	245	250	255
40	Gly Pro Ser Gly Thr Pro Gly Asp Thr Gly Pro Pro Gly Leu Gln Gly	260	265	270
45	Met Pro Gly Glu Arg Gly Ile Ala Gly Thr Pro Gly Pro Lys Gly Asp	275	280	285
	Arg Gly Gly Ile Gly Glu Lys Gly Ala Glu Gly Thr Ala Gly Asn Asp	290	295	300
50	Gly Ala Gly Gly Leu Pro Gly Pro Leu Gly Pro Pro Gly Pro Ala Gly	305	310	315
	Leu Leu Gly Glu Lys Gly Glu Pro Gly Pro Arg Gly Leu Val Gly Pro	325	330	335
55				

EP 1 894 945 A2

Pro Gly Ser Arg Gly Asn Pro Gly Ser Arg Gly Glu Asn Gly Pro Thr
 340 345 350
 5
 Gly Ala Val Gly Phe Ala Gly Pro Gln Gly Ser Asp Gly Gln Pro Gly
 355 360 365
 10
 Val Lys Gly Glu Pro Gly Glu Pro Gly Gln Lys Gly Asp Ala Gly Ser
 370 375 380
 15
 Pro Gly Pro Gln Gly Leu Ala Gly Ser Pro Gly Pro His Gly Pro Asn
 385 390 395 400
 Gly Val Pro Gly Leu Lys Gly Gly Arg Gly Thr Gln Gly Pro Pro Gly
 405 410 415
 20
 Ala Thr Gly Phe Pro Gly Ser Ala Gly Arg Val Gly Pro Pro Gly Pro
 420 425 430
 25
 Ala Gly Ala Pro Gly Pro Ala Gly Pro Leu Gly Glu Pro Gly Lys Glu
 435 440 445
 Gly Pro Pro Gly Pro Arg Gly Asp Pro Gly Ser His Gly Arg Val Gly
 450 455 460
 30
 Val Arg Gly Pro Ala Gly Pro Pro Gly Gly Pro Gly Asp Lys Gly Asp
 465 470 475 480
 35
 Pro Gly Glu Asp Gly Gln Pro Gly Pro Asp Gly Pro Pro Gly Pro Ala
 485 490 495
 Gly Thr Thr Gly Gln Arg Gly Ile Val Gly Met Pro Gly Gln Arg Gly
 500 505 510
 40
 Glu Arg Gly Met Pro Gly Leu Pro Gly Pro Ala Gly Thr Pro Gly Lys
 515 520 525
 45
 Val Gly Pro Thr Gly Ala Thr Gly Asp Lys Gly Pro Pro Gly Pro Val
 530 535 540
 Gly Pro Pro Gly Ser Asn Gly Pro Val Gly Glu Pro Gly Pro Glu Gly
 545 550 555 560
 50
 Pro Ala Gly Asn Asp Gly Thr Pro Gly Arg Asp Gly Ala Val Gly Glu
 565 570 575
 55
 Arg Gly Asp Arg Gly Asp Pro Gly Pro Ala Gly Leu Pro Gly Ser Gln
 580 585 590

EP 1 894 945 A2

5 Gly Ala Pro Gly Thr Pro Gly Pro Val Gly Ala Pro Gly Asp Ala Gly
595 600 605

10 Gln Arg Gly Asp Pro Gly Ser Arg Gly Pro Ile Gly His Leu Gly Arg
610 615 620

15 Ala
625

20

25

30

35

40

45

50

55

EP 1 894 945 A2

SEQUENCE LISTING<110> Fuji Photo Film B.V.<120> RGD-enriched gelatine-like proteins with enhanced cell binding<130> P206294<160> 3
 5 <170> PatentIn version 3.1<210> 1<211> 250<212> PRT<213> Human partial COL1A1-sequence<400> 1

Pro Pro Gly Pro Ala Gly Pro Ala Gly Glu Arg Gly Glu Gln Gly Pro
 1 5 10 15

10 Ala Gly Ser Pro Gly Phe Gln Gly Leu Pro Gly Pro Ala Gly Pro Pro
 20 25 30

15 Gly Glu Ala Gly Lys Pro Gly Glu Gln Gly Val Pro Gly Asp Leu Gly
 35 40 45

Ala Pro Gly Pro Ser Gly Ala Arg Gly Glu Arg Gly Phe Pro Gly Glu
 50 55 60

20 Arg Gly Val Gln Gly Pro Pro Gly Pro Ala Gly Pro Arg Gly Ala Asn
 65 70 75 80

25 Gly Ala Pro Gly Asn Asp Gly Ala Lys Gly Asp Ala Gly Ala Pro Gly
 85 90 95

Ala Pro Gly Ser Gln Gly Ala Pro Gly Leu Gln Gly Met Pro Gly Glu
 100 105 110

30 Arg Gly Ala Ala Gly Leu Pro Gly Pro Lys Gly Asp Arg Gly Asp Ala
 115 120 125

35 Gly Pro Lys Gly Ala Asp Gly Ser Pro Gly Lys Asp Gly Val Arg Gly
 130 135 140

Leu Thr Gly Pro Ile Gly Pro Pro Gly Pro Ala Gly Ala Pro Gly Asp
 145 150 155 160

40 Lys Gly Glu Ser Gly Pro Ser Gly Pro Ala Gly Pro Thr Gly Ala Arg
 165 170 175

45 Gly Ala Pro Gly Asp Arg Gly Glu Pro Gly Pro Pro Gly Pro Ala Gly
 180 185 190

Phe Ala Gly Pro Pro Gly Ala Asp Gly Gln Pro Gly Ala Lys Gly Glu
 195 200 205

50

55

EP 1 894 945 A2

Pro Gly Asp Ala Gly Ala Lys Gly Asp Ala Gly Pro Pro Gly Pro Ala
210 215 220

5

Gly Pro Ala Gly Pro Pro Gly Pro Ile Gly Asn Val Gly Ala Pro Gly
225 230 235 240

10

Ala Lys Gly Ala Arg Gly Ser Ala Gly Pro
245 250

15

<210> 2<211> 252<212> PRT<213> Artificial sequence<220><223> Repeated
partial human COL1A1-1 sequence

<400> 2

20

Gly Ala Pro Gly Ser Gln Gly Ala Pro Gly Leu Gln Gly Met Pro Gly
1 5 10 15

Glu Arg Gly Ala Ala Gly Leu Pro Gly Pro Lys Gly Asp Arg Gly Asp
20 25 30

25

Ala Gly Pro Lys Gly Ala Asp Gly Ser Pro Gly Lys Asp Gly Val Arg
35 40 45

30

Gly Leu Thr Gly Pro Ile Gly Pro Pro Gly Pro Ala Gly Ala Pro Gly
50 55 60

35

Ala Pro Gly Ser Gln Gly Ala Pro Gly Leu Gln Gly Met Pro Gly Glu
65 70 75 80

40

Arg Gly Ala Ala Gly Leu Pro Gly Pro Lys Gly Asp Arg Gly Asp Ala
85 90 95

45

Gly Pro Lys Gly Ala Asp Gly Ser Pro Gly Lys Asp Gly Val Arg Gly
100 105 110

50

Leu Thr Gly Pro Ile Gly Pro Pro Gly Pro Ala Gly Ala Pro Gly Ala
115 120 125

55

Pro Gly Ser Gln Gly Ala Pro Gly Leu Gln Gly Met Pro Gly Glu Arg
130 135 140

Gly Ala Ala Gly Leu Pro Gly Pro Lys Gly Asp Arg Gly Asp Ala Gly
145 150 155 160

EP 1 894 945 A2

5 Pro Lys Gly Ala Asp Gly Ser Pro Gly Lys Asp Gly Val Arg Gly Leu
 165 170 175
 Thr Gly Pro Ile Gly Pro Pro Gly Pro Ala Gly Ala Pro Gly Ala Pro
 180 185 190
 10 Gly Ser Gln Gly Ala Pro Gly Leu Gln Gly Met Pro Gly Glu Arg Gly
 195 200 205
 15 Ala Ala Gly Leu Pro Gly Pro Lys Gly Asp Arg Gly Asp Ala Gly Pro
 210 215 220
 Lys Gly Ala Asp Gly Ser Pro Gly Lys Asp Gly Val Arg Gly Leu Thr
 225 230 235 240
 20 Gly Pro Ile Gly Pro Pro Gly Pro Ala Gly Ala Pro
 245 250
 25 <210> 3<211> 625<212> PRT<213> Artificial sequence<220><223> Human Partial
 COL5A2 sequence
 <400> 3
 30 Gln Gly Pro Ile Gly Pro Pro Gly Glu Glu Gly Lys Arg Gly Pro Arg
 1 5 10 15
 Gly Asp Pro Gly Thr Leu Gly Pro Pro Gly Pro Val Gly Glu Arg Gly
 20 25 30
 35 Ala Pro Gly Asn Arg Gly Phe Pro Gly Ser Asp Gly Leu Pro Gly Pro
 35 40 45
 40 Lys Gly Ala Gln Gly Glu Arg Gly Pro Val Gly Ser Ser Gly Pro Lys
 50 55 60
 Gly Ser Gln Gly Asp Pro Gly Arg Pro Gly Glu Pro Gly Leu Pro Gly
 65 70 75 80
 45 Ala Arg Gly Leu Thr Gly Asn Pro Gly Val Gln Gly Pro Glu Gly Lys
 85 90 95
 50 Leu Gly Pro Leu Gly Ala Pro Gly Gly Asp Gly Arg Pro Gly Pro Pro
 100 105 110

55

EP 1 894 945 A2

Gly Ser Ile Gly Ile Lys Gly Gln Pro Gly Thr Met Gly Leu Pro Gly
 115 120 125
 5
 Pro Lys Gly Ser Asn Gly Asp Pro Gly Lys Pro Gly Glu Ala Gly Asn
 130 135 140
 10
 Pro Gly Val Pro Gly Gln Arg Gly Ala Pro Gly Lys Asp Gly Lys Val
 145 150 155 160
 Gly Pro Tyr Gly Pro Pro Gly Pro Pro Gly Leu Arg Gly Glu Arg Gly
 165 170 175
 15
 Glu Gln Gly Pro Pro Gly Pro Thr Gly Phe Gln Gly His Pro Gly Pro
 180 185 190
 20
 Pro Gly Pro Pro Gly Glu Gly Gly Lys Pro Gly Asp Gln Gly Val Pro
 195 200 205
 Gly Gly Pro Gly Ala Val Gly Pro Leu Gly Pro Arg Gly Glu Arg Gly
 210 215 220
 25
 Asn Pro Gly Glu Arg Gly Glu Pro Gly Ile Thr Gly Leu Pro Gly Glu
 225 230 235 240
 30
 Lys Gly Met Ala Gly Gly His Gly Pro Asp Gly Pro Lys Gly Ser Pro
 245 250 255
 35
 Gly Pro Ser Gly Thr Pro Gly Asp Thr Gly Pro Pro Gly Leu Gln Gly
 260 265 270
 40
 Met Pro Gly Glu Arg Gly Ile Ala Gly Thr Pro Gly Pro Lys Gly Asp
 275 280 285
 Arg Gly Gly Ile Gly Glu Lys Gly Ala Glu Gly Thr Ala Gly Asn Asp
 290 295 300
 45
 Gly Ala Gly Gly Leu Pro Gly Pro Leu Gly Pro Pro Gly Pro Ala Gly
 305 310 315 320
 50
 Leu Leu Gly Glu Lys Gly Glu Pro Gly Pro Arg Gly Leu Val Gly Pro
 325 330 335
 55
 Pro Gly Ser Arg Gly Asn Pro Gly Ser Arg Gly Glu Asn Gly Pro Thr

EP 1 894 945 A2

			340					345					350				
5		Gly	Ala	Val	Gly	Phe	Ala	Gly	Pro	Gln	Gly	Ser	Asp	Gly	Gln	Pro	Gly
				355					360					365			
10	Val	Lys	Gly	Glu	Pro	Gly	Glu	Pro	Gly	Gln	Lys	Gly	Asp	Ala	Gly	Ser	
		370					375						380				
15	Pro	Gly	Pro	Gln	Gly	Leu	Ala	Gly	Ser	Pro	Gly	Pro	His	Gly	Pro	Asn	
		385				390					395					400	
20	Gly	Val	Pro	Gly	Leu	Lys	Gly	Gly	Arg	Gly	Thr	Gln	Gly	Pro	Pro	Gly	
					405					410					415		
25	Ala	Thr	Gly	Phe	Pro	Gly	Ser	Ala	Gly	Arg	Val	Gly	Pro	Pro	Gly	Pro	
				420					425					430			
30	Ala	Gly	Ala	Pro	Gly	Pro	Ala	Gly	Pro	Leu	Gly	Glu	Pro	Gly	Lys	Glu	
			435					440					445				
35	Gly	Pro	Pro	Gly	Pro	Arg	Gly	Asp	Pro	Gly	Ser	His	Gly	Arg	Val	Gly	
		450					455					460					
40	Val	Arg	Gly	Pro	Ala	Gly	Pro	Pro	Gly	Gly	Pro	Gly	Asp	Lys	Gly	Asp	
		465				470					475					480	
45	Pro	Gly	Glu	Asp	Gly	Gln	Pro	Gly	Pro	Asp	Gly	Pro	Pro	Gly	Pro	Ala	
					485					490					495		
50	Gly	Thr	Thr	Gly	Gln	Arg	Gly	Ile	Val	Gly	Met	Pro	Gly	Gln	Arg	Gly	
				500					505					510			
55	Glu	Arg	Gly	Met	Pro	Gly	Leu	Pro	Gly	Pro	Ala	Gly	Thr	Pro	Gly	Lys	
			515					520					525				
60	Val	Gly	Pro	Thr	Gly	Ala	Thr	Gly	Asp	Lys	Gly	Pro	Pro	Gly	Pro	Val	
		530					535					540					
65	Gly	Pro	Pro	Gly	Ser	Asn	Gly	Pro	Val	Gly	Glu	Pro	Gly	Pro	Glu	Gly	
		545				550					555					560	
70	Pro	Ala	Gly	Asn	Asp	Gly	Thr	Pro	Gly	Arg	Asp	Gly	Ala	Val	Gly	Glu	
				565						570					575		

Arg Gly Asp Arg Gly Asp Pro Gly Pro Ala Gly Leu Pro Gly Ser Gln
580 585 590

Gly Ala Pro Gly Thr Pro Gly Pro Val Gly Ala Pro Gly Asp Ala Gly
595 600 605

Gln Arg Gly Asp Pro Gly Ser Arg Gly Pro Ile Gly His Leu Gly Arg
610 615 620

Ala
625

Claims

1. An RGD-enriched gelatine in which the percentage of RGD motifs related to the total number of amino acids is at least 0.4 and if the RGD-enriched gelatine comprises 350 amino acids or more, each stretch of 350 amino acids contains at least one RGD motif, said RGD-enriched gelatine consisting for at least 80% of one or more parts of native human collagen sequences and said parts of native human collagen sequences having a length of at least 30 amino acids.
2. The RGD-enriched gelatine according to claim 1, in which the percentage of RGD motifs related to the total number of amino acids is at least 0.6, preferably at least 0.8, more preferably at least 1.0, more preferably at least 1.2 and most preferably at least 1.5.
3. The RGD-enriched gelatine according to claim 1 or 2 in which the number of RGD motifs is at least 4 per 250 amino acids.
4. The RGD-enriched gelatine according to any of the preceding claims said RGD-enriched gelatine comprising at least 4 RGD motifs, preferably 6, more preferably 8, even more preferably 12 up to and including 16 RGD motifs.
5. The RGD-enriched gelatine according to any of the preceding claims said RGD-enriched gelatine having a molecular weight of about 30 kDa to about 200 kDa.
6. The RGD-enriched gelatine according to any of claims 1-4 said RGD-enriched gelatine having a molecular weight of at most 10 kDa, preferably at most 5 kDa.
7. The RGD-enriched gelatine according to any of the preceding claims in which the RGD-enriched gelatine comprises less than 5% hydroxyproline residues, preferably less than 3%.
8. The RGD-enriched gelatine according to any of the preceding claims said RGD-enriched gelatine having a net positive charge at pH 7-7.5.
9. The RGD-enriched gelatine according to any of the preceding claims said RGD-enriched gelatine consisting of one or more parts of one or more native human collagen sequences.

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 5512474 A [0011] [0052]
- US 5514581 A [0012] [0013]
- US 5972332 A [0013]
- EP 0628571 A [0013]
- WO 02070000 A1 [0050]
- US 4994388 A [0051]
- EP 0926543 A [0061] [0061] [0065] [0066] [0075]
- EP 1014176 A [0061] [0061] [0065] [0066] [0075]
- WO 0134646 A [0061] [0066] [0075]

Non-patent literature cited in the description

- **VAN WEZEL, A. L.** *Nature*, 1967, vol. 216, 64-65 [0004]
- **K. GELSE et al.** Collagens-structure, function and biosynthesis. *Advanced Drug Delivery reviews*, 2003, vol. 55, 1531-1546 [0025]
- **FULLER ; BOEDTKER.** *Biochemistry*, 1981, vol. 20, 996-1006 [0027]
- **SANDELL et al.** *J Biol Chem*, 1984, vol. 259, 7826-34 [0027]
- **KOHNO et al.** *J Biol Chem*, 1984, vol. 259, 13668-13673 [0027]
- **FRENCH et al.** *Gene*, 1985, vol. 39, 311-312 [0027]
- **METSARANTA et al.** *J Biol Chem*, 1991, vol. 266, 16862-16869 [0027]
- **METSARANTA et al.** *Biochim Biophys Acta*, 1991, vol. 1089, 241-243 [0027]
- **WOOD et al.** *Gene*, 1987, vol. 61, 225-230 [0027]
- **GLUMOFF et al.** *Biochim Biophys Acta*, 1994, vol. 1217, 41-48 [0027]
- **SHIRAI et al.** *Matrix Biology*, 1998, vol. 17, 85-88 [0027]
- **TROMP et al.** *Biochem J*, 1988, vol. 253, 919-912 [0027]
- **KUIVANIEMI et al.** *Biochem J*, 1988, vol. 252, 633640 [0027]
- **ALA-KOKKO et al.** *Biochem J*, 1989, vol. 260, 509-516 [0027]