

19



Europäisches Patentamt
European Patent Office
Office européen des brevets



11 Publication number:

0 357 574 B1

12

EUROPEAN PATENT SPECIFICATION

- 45 Date of publication of patent specification: **22.12.93** 51 Int. Cl.⁵: **D21H 23/76**, D21H 17/33,
D21H 17/63
- 21 Application number: **89850252.1**
- 22 Date of filing: **09.08.89**

54 **A process for the production of paper.**

30 Priority: **01.09.88 SE 8803065**

43 Date of publication of application:
07.03.90 Bulletin 90/10

45 Publication of the grant of the patent:
22.12.93 Bulletin 93/51

84 Designated Contracting States:
AT BE CH DE ES FR GB IT LI NL SE

56 References cited:
WO-A-86/00100
WO-A-86/05826
WO-A-88/06659
WO-A-89/06638
US-A- 4 795 531

73 Proprietor: **Eka Nobel Aktiebolag**

S-445 01 Surte(SE)

72 Inventor: **Johansson, Hans Erik**
Madängsgatan 5
S-442 33 Kungälv(SE)

74 Representative: **Schöld, Zaid**
Nobel Industries AB
Patent Department
Box 11554
S-100 61 Stockholm (SE)

EP 0 357 574 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

Description

The present invention relates to a process for the production of paper utilizing an improved retention- and dewatering system. More particularly the invention relates to the use of a combination of a cationic synthetic polymer, an anionic inorganic colloid and aluminate as retention- and dewatering system in papermaking.

It is previously known to use combinations of cationic retention agents and inorganic colloids as retention- and dewatering agents in the production of paper. The European patent application 0218674 discloses the use of polyacrylamide in combination with anionic silica sols as binders and retention agents.

It is assumed that the colloidal particles of the sols with their strong charges produce a cross-linking of the polymeric retention agents and that very good retention and dewatering effect is obtained through this. From the British patent 2015614 it is further known to use polymeric cationic retention agents in combination with polyaluminum compounds. It is further known from the US patent 4,643,801 to use a combination of a cationic starch, an anionic silica sol and an anionic high molecular weight polymer, particularly an anionic polyacrylamide, as a binder in papermaking. The three component system according to the US patent can be used with additional aluminum compounds, such as alum, sodium aluminate or polyhydroxyaluminum chloride.

According to the present invention it has been found that the retention- and dewatering effect in papermaking is improved if an aluminate is used in combination with cationic, synthetic polymer and an anionic inorganic colloid. As the dewatering effect is increased the speed of the papermachine can be increased and, further, less water will have to be dried off in the drying section of the paper machine.

The present invention thus relates to a process for the production of paper by forming and dewatering a suspension of cellulose containing fibres, and optionally fillers, on a wire whereby the forming and dewatering takes place in the presence of an anionic inorganic colloid, an aluminate and a cationic synthetic polymer.

The three components can be added to the fibre stock in arbitrary order. The best effect is obtained if the aluminate is added to the stock first, followed by addition of cationic synthetic polymer and then the anionic inorganic colloid. A considerable improvement, in comparison with known technique, is obtained also when the anionic inorganic colloid is first added to the stock and the cationic polymer and the aluminate are added subsequently, in any order. Separate addition of the three respective components is preferred although it is possible to pre-mix two of the components before the addition.

As cationic synthetic polymers for use according to the present invention such cationic, organic nitrogen containing polymers which are conventionally used as retention agents and/or wet strength agents in papermaking are suitable. Particularly suitable are cationic polyacrylamides, polyethyleneimines, polyamine resins and polyamidoamine resins etc. Polyamine resins and polyamidoamine resins are suitably used in their epichlorohydrine modified form. Other cationic synthetic polymers which can also be used are the cationic melamine-formaldehyde and urea-formaldehyde wet strength resins. The amount of the cationic synthetic polymer should suitably be within the range of from 0.01 to 3 per cent by weight, preferably within the range of from 0.03 to 2 per cent by weight, based on dry fibres and optional fillers.

The anionic inorganic colloids which are used are per se previously known for use in papermaking. As examples of such colloids can be mentioned montmorillonite, bentonite, titanyl sulphate sols, silica sols, aluminum modified silica sols or aluminum silicate sols. The terms colloid and colloidal indicate very small particles. The particles of the anionic substances should suitably have a specific surface area above 50 m²/g, more suitably above 100 m²/g, and preferably within the range of 50 to 1000 m²/g. Silica based colloids are the preferred anionic inorganic colloid.

Particularly suitable silica based colloids are the silica sols with colloidal particles as disclosed in the European patent 41056, which is hereby incorporated by reference in this application, and the aluminum containing silica sols which are disclosed in the European patent application 0218674, which likewise is incorporated by reference. The colloidal silica in the sols should preferably have a specific surface area of 50 to 1000 m²/g and more preferably of about 100 to 1000 m²/g, and the best results have been obtained when the specific surface area has been about 300 to 700 m²/g. It has been found that the colloidal silica particles should suitably have a particle size below 20 nm and preferably from about 10 down to about 1 nm (a colloidal silica particle having a specific surface area of about 550 m²/g corresponds to an average particle size of about 5 nm). Good results are obtained with the mentioned silica sols in the form of an alkali stabilized sol which contains about 2 to 60 per cent by weight of SiO₂, preferably from about 4 to 30 per cent by weight of SiO₂. The silica sol can be stabilized with alkali in a molar ratio of SiO₂:M₂O of from 10:1 to 300:1, preferably 15:1 to 100:1 (M is an ion from the group Na, K, Li and NH₄). As mentioned above good results are obtained using colloidal particles which have at least a surface layer of aluminum silicate or

aluminum modified silica sol, so that the surface groups of the particles contain silicon and aluminum atoms in a ratio of from 9.5:0.5 to 7.5:2.5 and the given surfaces and particle sizes also apply to these sols. Silica sols which fulfil the above given specifications are available commercially, eg from Eka Nobel AB.

The amount of anionic colloid which is added to the stock should suitably be within the range of from 5 0.005 to 2 per cent by weight, preferably from 0.01 to 0.4 per cent by weight, based on dry cellulose fibres and optional fillers. The concentration of the colloid, preferably colloidal silica, in the sol added to the stock is not critical. From a practical point of view it is suitable that the sols at the addition to the stock have a concentration of from 0.05 to 5.0 per cent by weight.

Aluminate refers to alkali aluminate which per se is well-known for use in paper production, particularly 10 for hydrophobing with rosin. Sodium aluminate ($\text{Na}_2\text{Al}_2\text{O}_4$) is preferably used, but potassium aluminate can of course also be used even if is less advantageous from an economical point of view. The amount of aluminate can vary within wide limits. The addition of aluminate to the stock is suitably made in the form of aqueous solutions and the concentration in the solutions is not critical but is adjusted with regard to practical considerations. According to the invention it has been found that already very small amounts of 15 aluminate, with regard to the amount of anionic inorganic colloid, give considerable improvements in the dewatering effect. An improvement is obtained already at a weight ratio aluminate, calculated as Al_2O_3 , to inorganic colloid of 0.01:1. The upper limit is not critical. However, no improvements worth mentioning are obtained when the ratio of aluminate to inorganic colloid exceeds 3:1. The ratio is suitably within the range of from 0.02:1 to 1.5:1 and preferably from 0.05:1 to 0.7:1. The given ratios all relate to weight ratio between 20 aluminate, calculated as Al_2O_3 , and the inorganic colloid.

The improved retention- and dewatering effect with the system of the invention is obtained over a broad pH range for the stock. The pH can be within the range from about 4 to about 10. The pH is suitably above 5 and preferably within the range of from 6 to 9. If the desired pH is not reached by the addition of the aluminate solution, which in itself is alkaline, the pH of the stock can be adjusted for example by addition of 25 sodium hydroxide. If alkaline buffering fillers are used, for example chalk, a suitable pH is normally reached without adjustments. Other fillers than chalk can of course also be used, but then care has to be taken so that the pH of the stock is kept within the above given limits.

At paper production according to the invention mineral fillers of conventional types can be used, for example kaolin, titanium dioxide, gypsum, chalk and talcum. The term "mineral filler" is herein used to 30 include, in addition to these fillers, also wollastonite and glass fibres and also mineral low density fillers, such as expanded perlite. The mineral filler is usually added in the form of an aqueous slurry in conventional concentrations used for such fillers. The filler can optionally be treated before the addition to the stock with components of the dewatering- and retention- system of the invention, for example by treatment with the cationic synthetic polymer and the aluminate or the inorganic colloid, whereafter the 35 remaining component is added to the stock.

The three-component system of the invention can be used at production of paper from different types of stocks of cellulose containing fibres. The stocks should suitably contain at least 50 per cent by weight of cellulose containing fibres. The three-component system can for example be used for stocks of fibres from 40 chemical pulp, such as sulphate and sulphite pulp, thermomechanical pulp, refiner pulp and groundwood pulp from as well hardwood as softwood. It can of course also be used for stocks from recycled fibres. The terms paper and papermaking, which are used herein do of course not only include paper and its production, but also other cellulose fibre containing sheet or web form products, such as pulp sheet, board and cardboard and their production.

The process according the invention can be carried out in per se known manner and with other 45 additions to the fibre stock, such as sizing agents etc.

The invention is further illustrated in the following examples wherein parts and per cent relate to parts by weight and per cent by weight unless otherwise stated.

Example 1

50 In the following tests the dewatering effect was investigated by means of a "Canadian Freeness Tester", which is the usual method for characterizing the dewatering capability according to SCAN-C 21:65.

The stock was based on bleached birch/pine sulphate pulp (60:40) and contained 30 per cent by weight of chalk. The pH of the stock was 8.5 and CSF was 300 ml.

55 In the table amounts for the chemical additions refer to ton dry stock system (fibres + fillers). The anionic colloid was an alkali stabilized silica sol with a specific surface area of $500 \text{ m}^2/\text{g}$. The cationic synthetic polymer was a cationic polyacrylamide of medium cationicity sold by Allied Colloids under the name Percol 292. The sodium aluminate was added in the form of a 0.025% aqueous solution and the

EP 0 357 574 B1

given amounts of aluminate are expressed as kg Al₂O₃. The additions of chemicals were made to 1 l diluted stock (about 0.3%) with intervals of 15 seconds under agitation in the order aluminate, cationic polymer, inorganic colloid. The flocced stock was transferred to the freeness apparatus and measurements were made 15 seconds after the last addition. The water which is collected is a measurement of the dewatering effect and is expressed in ml Canadian Standard Freeness (CSF). The water obtained in the tests using the three components was very clear and this shows that a good retention of the fines material to the flocks had also been obtained.

Test No.	Al ₂ O ₃ kg/t	Cationic polymer kg/t	Anionic Colloid kg/t	CSF ml
1	-	-	-	300
2	-	0.3	-	370
3	-	0.6	-	385
4	-	0.9	-	390
5	0.15	-	-	290
6	0.15	0.3	-	350
7	-	-	1.0	295
8	0.15	-	1.0	290
9	-	0.3	0.5	420
10	-	0.3	1.0	430
11	-	0.3	1.5	440
12	0.075	0.3	0.5	495
13	0.15	0.3	1.0	520
14	0.225	0.3	1.5	515

Test No.	Al ₂ O ₃ kg/t	Cationic polymer kg/t	Anionic Colloid kg/t	CSF ml
15	-	0.6	0.5	425
16	-	0.6	1.0	490
17	-	0.6	1.5	510
18	0.075	0.6	0.5	495
19	0.15	0.6	1.0	570
20	0.225	0.6	1.5	585

As evident also use of very small amounts of aluminate gives a considerably improved dewatering effect for the system of cationic polymer and anionic colloid. The corresponding effect of the aluminate is not obtained if it is used in combination with only cationic polymer or only anionic colloid.

Example 2

This example corresponded entirely to example 1 with the only difference that other cationic synthetic polymers were used. These were A) an epichlorohydrine modified polyamidoamine resin sold by Hercules Inc. under the name Kymene 557 H and B) a modified polyamine resin sold by Hercules Inc. under the name Delfloc-50.

EP 0 357 574 B1

Test No.	Al ₂ O ₃ kg/t	Cat. Polymer type;kg/t	Anionic Colloid kg/t	CSF ml
1	-	-	-	300
2	-	A; 0.6	-	305
3	-	A; 1.2	-	315
4	-	A; 2.4	-	315
5	-	A; 1.2	0.5	325
6	-	A; 1.2	1.0	330
7	-	A; 1.2	1.5	310
8	0.075	A; 1.2	0.5	360
9	0.15	A; 1.2	1.0	390
10	0.225	A; 1.2	1.5	410
11	0.30	A; 1.2	2.0	395
12	-	B; 1.2	-	290
13	-	B; 1.2	1.5	280
14	0.225	B; 1.2	1.5	335

Example 3

In this example a groundwood stock was used which did not contain any fillers. To the stock 0.5 g/l of Na₂SO₄.10H₂O had been added to give an ion strength corresponding to the one under large scale conditions. The cationic polymer was the same polyacrylamide as in Example 1. The anionic colloid was an aluminum modified, 15% alkali stabilized, silica sol where the surface of the colloidal particles had been modified with 9% aluminum atoms and the surface area of the particles was 500 m²/g. The order of addition was sodium aluminate, cationic polymer followed by anionic colloid. Tests were made both with a stock pH of 6 and a stock pH of 7.5 whereby the pH had been adjusted with diluted H₂SO₄ and diluted NaOH respectively.

EP 0 357 574 B1

Test No	Al ₂ O ₃ kg/t	Cationic polymer kg/t	Anionic colloid kg/t	CSF ml
<u>pH 6.0</u>				
5	1	-	-	120
	2	-	0.3	190
	3	-	0.6	220
10	4	-	0.9	245
	5	-	1.2	250
	6	-	0.6	275
	7	-	0.6	305
15	8	-	0.6	300
	9	0.075	0.6	325
	10	0.15	0.6	345
20	11	0.225	0.6	350
<u>pH 7.5</u>				
	12	-	0.6	220
25	13	-	0.6	245
	14	-	0.6	270
	15	-	0.6	275
	16	0.075	0.6	295
30	17	0.15	0.6	325
	18	0.225	0.6	340
	19	-	0.9	310
35	20	0.225	0.9	370

Example 4

40

In these tests a groundwood stock with addition of 0.5 g/l of Na₂SO₄·10H₂O was used as in Example 3. The pH of the stock was 6.5 and the added chemicals were sodium aluminate, a cationic polyethylene imine sold by BASF under the name Polymin SK and an anionic colloid which was a bentonite colloid having a specific surface area of from about 400 to 800 m²/g in water.

45

50

55

Test No.	Al ₂ O ₃ kg/t	Cationic polymer kg/t	Anionic colloid kg/t	CSF ml
1	-	-	-	120
2	-	0.3	-	175
3	-	0.6	-	230
4	-	0.9	-	300
5	-	1.2	-	310
6	-	0.6	0.5	260
7	-	0.6	1.0	280
8	-	0.9	1.0	340
9	0.075	0.6	0.5	295
10	0.15	0.6	1.0	335
11	0.15	0.9	1.0	390

Claims

1. A process for the production of paper by forming and dewatering a suspension of cellulose containing fibres on a wire, characterized in that the forming and dewatering takes place in the presence of an anionic inorganic colloid, with the proviso that the anionic inorganic colloid is not a polymeric silicic acid having a specific surface area of at least 1050 m²/g, an aluminate and a cationic synthetic polymer.
2. A process according to claim 1, characterized in that the anionic colloid is a silica based colloid.
3. A process according to claim 1 or 2, characterized in that the colloid is a silica sol, a silica sol with particles having at least a surface layer of aluminum silicate or an aluminum modified silica sol.
4. A process according to claim 1, 2 or 3, characterized in that the particles of the colloid have a specific surface area within the range of from 50 to 1000 m²/g.
5. A process according to claim 3, characterized in that the particle size of the colloid is 20 nm at the most.
6. A process according to claim 1, characterized in that the cationic synthetic polymer is a cationic polyacrylamide, polyethyleneimine, polyamine or polyamidoamine.
7. A process according to any of the preceding claims, characterized in that the aluminate is added to the fibre suspension before the anionic inorganic colloid and the cationic synthetic polymer.
8. A process according to any of claims 1, 2, 3, 4 or 5, characterized in that the amount of anionic inorganic colloid is within the range of from 0.005 to 2 per cent by weight, based on dry fibres and optional fillers.
9. A process according to claim 1 or 6, characterized in that the amount of cationic synthetic polymer is within the range of from 0.01 to 3 per cent by weight, based on dry fibres and optional fillers.
10. A process according to claim 1, characterized in that the weight ratio of aluminate, calculated as Al₂O₃, to anionic inorganic colloid is within the range of from 0.01:1 to 3:1.

Patentansprüche

1. Verfahren zur Herstellung von Papier durch Formen und Entwässern einer Suspension Cellulose enthaltender Fasern auf einem Drahtnetz, dadurch gekennzeichnet, daß das Formen und Entwässern in Gegenwart eines anionischen anorganischen Kolloids, eines Aluminats und eines kationischen synthetischen Polymers stattfindet, mit der Maßgabe, daß das anionische anorganische Kolloid keine polymere Kieselsäure mit einer spezifischen Oberfläche von mindestens 1050 m²/g ist.

EP 0 357 574 B1

2. Verfahren nach Anspruch 1, dadurch gekennzeichnet, daß das anionische Kolloid ein Kolloid auf Kieselerdebasis ist.
3. Verfahren nach Anspruch 1 oder 2, dadurch gekennzeichnet, daß das Kolloid ein Kieselerdesol, ein
5 Kieselerdesol mit Teilchen, die mindestens eine Oberflächenschicht aus Aluminiumsilikat aufweisen, oder ein aluminiummodifiziertes Kieselerdesol ist.
4. Verfahren nach Anspruch 1, 2 oder 3, dadurch gekennzeichnet, daß die Teilchen des Kolloids eine
10 spezifische Oberfläche im Bereich von 50 bis 1000 m²/g aufweisen.
5. Verfahren nach Anspruch 3, dadurch gekennzeichnet, daß die Teilchengröße des Kolloids höchstens
20 nm ist.
6. Verfahren nach Anspruch 1, dadurch gekennzeichnet, daß das kationische synthetische Polymer ein
15 kationisches Polyacrylamid, Polyethylenimin, Polyamin oder Polyamidoamin ist.
7. Verfahren nach einem der vorstehenden Ansprüche, dadurch gekennzeichnet, daß das Aluminat vor
dem anionischen anorganischen Kolloid und dem kationischen synthetischen Polymer der Fasersu-
sension zugefügt wird.
- 20 8. Verfahren nach einem der Ansprüche 1, 2, 3, 4 oder 5, dadurch gekennzeichnet, daß die Menge
anionischen anorganischen Kolloids im Bereich von 0,005 bis 2 Gewichtsprozent, bezogen auf trockene
Fasern und gegebenenfalls Füllstoffe, liegt.
- 25 9. Verfahren nach Anspruch 1 oder 6, dadurch gekennzeichnet, daß die Menge des kationischen
synthetischen Polymers im Bereich von 0,01 bis 3 Gewichtsprozent, bezogen auf trockene Fasern und
gegebenenfalls Füllstoffe, liegt.
- 30 10. Verfahren nach Anspruch 1, dadurch gekennzeichnet, daß das Gewichtsverhältnis des Aluminats,
berechnet als Al₂O₃, zum anionischen anorganischen Kolloid im Bereich von 0,01:1 bis 3:1 liegt.

Revendications

- 35 1. Procédé pour la production du papier par formation et élimination de l'eau d'une suspension de
cellulose contenant des fibres sur une toile, caractérisé en ce que la formation et l'élimination de l'eau
sont effectuées en présence d'un colloïde inorganique anionique, sous la condition que le colloïde
inorganique anionique ne soit pas un acide silicique polymère ayant une aire de surface spécifique d'au
moins 1050 m²/g, avec un aluminat et un polymère synthétique cationique.
- 40 2. Procédé selon la revendication 1, caractérisé en ce que le colloïde anionique est un colloïde à base de
silice.
3. Procédé selon la revendication 1 ou 2, caractérisé en ce que le colloïde est un sol de silice, un sol de
silice avec des particules ayant au moins une couche superficielle de silicate d'aluminium ou un sol de
45 silice modifié par de l'aluminium.
4. Procédé selon la revendication 1, 2 ou 3, caractérisé en ce que les particules du colloïde ont une aire
de surface spécifique dans la plage allant de 50 à 1000 m²/g.
- 50 5. Procédé selon la revendication 3, caractérisé en ce que la taille des particules du colloïde est au plus
égale à 20 nm.
6. Procédé selon la revendication 1, caractérisé en ce que le polymère synthétique cationique est un
polyacrylamide cationique, une polyéthylèneimine, une polyamine ou une polyamidoamine.
- 55 7. Procédé selon l'une quelconque des revendications précédentes, caractérisé en ce que l'aluminat est
ajouté à la suspension fibreuse avant le colloïde inorganique anionique et le polymère synthétique
cationique.

EP 0 357 574 B1

8. Procédé selon l'une quelconque des revendications 1, 2, 3, 4 ou 5, caractérisé en ce que la quantité de colloïde inorganique anionique est comprise dans la plage allant de 0,005 à 2 pour cent en poids, en se fondant sur des fibres sèches ou des charges facultatives.
- 5 9. Procédé selon la revendication 1 ou 6, caractérisé en ce que la quantité de polymère synthétique cationique est comprise dans la plage allant de 0,01 à 3 pour cent en poids, en se fondant sur des fibres sèches ou des charges facultatives.
- 10 10. Procédé selon la revendication 1, caractérisé en ce que le rapport de poids de l'aluminate, exprimé en Al_2O_3 , par rapport au colloïde inorganique anionique, est compris dans la plage allant de 0,01:1 à 3:1.

15

20

25

30

35

40

45

50

55