

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 684 900 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
12.08.1998 Bulletin 1998/33

(51) Int. Cl.⁶: **B29C 47/00**
// **B29K23:00**

(21) Application number: **94909626.7**

(86) International application number:
PCT/US94/01610

(22) Date of filing: **17.02.1994**

(87) International publication number:
WO 94/19168 (01.09.1994 Gazette 1994/20)

(54) METHOD FOR PROCESSING POLYOLEFINS AT HIGH SHEAR RATES

VERFAHREN ZUM BEARBEITEN VON POLYOLEFINEN BEI HOHEN
SCHERGESCHWINDIGKEITEN

PROCEDE DE TRAITEMENT DE POLYOLEFINES SOUS DES GRADIENTS DE CISAILLEMENT
ELEVES

(84) Designated Contracting States:
BE DE ES FR GB IT NL SE

(74) Representative:
Dew, Melvyn John et al
Exxon Chemical Europe Inc.
P.O.Box 105
1830 Machelen (BE)

(30) Priority: **17.02.1993 US 18605**

(43) Date of publication of application:
06.12.1995 Bulletin 1995/49

(56) References cited:
US-A- 2 991 508

(73) Proprietor:
EXXON CHEMICAL PATENTS INC.
Baytown, TX 77520-5200 (US)

- **JOURNAL OF APPLIED POLYMER SCIENCE** vol. 28 , 1983 , NEW YORK pages 3503 - 3511 G. **ATTALLA ET AL.** 'Comparison between a linear and a branched low-density polyethylene' see page 3505, line 3 - line 6 see page 3506, line 9 - line 16; figures 2,6; table 1

(72) Inventors:

- **CHAMBON, François**
Houston TX 77005 (US)
- **DEKONONCK, Jean-Marc**
Houston, TX 77059 (US)

EP 0 684 900 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

DescriptionBACKGROUND OF THE INVENTION

5 1. FIELD OF INVENTION

This invention relates generally to processing of polyolefins, and more particularly processing through a die of polyethylene polymers and copolymers.

10 2. DESCRIPTION OF THE RELEVANT ART

The processing of polyethylene and extrusion of polyethylene or polyolefins is a multi-talented skill long studied in the art. There are many different parameters that influence whether a polymer is processable or not at high speeds. Such parameters include the melt index (MI), the molecular weight (Mw), the molecular weight distribution (Mw/Mn) and such. For example, it is assumed in the art that low MI polymers need high temperatures for processability, and if these conditions are not maintained, then the extrudate will have defects. Likewise even at low shear rates, high molecular weight, low MI polyethylenes extruded through a die produce a rough surface extrudate considered defective, typically called sharkskin or melt fracture. Appearance of this surface defect usually sets the maximum throughput for most processing equipments, such as film-blowing, profile extrusion or film-casting. Thus, the processing may go no faster than that point at which the sharkskin melt fracture typically appears. Some polyethylenes, for example HDPE, are also known to show what is called a "slipstick transition" when extruded at very high shear rates, which are too high for most practical purposes, typically over 1000, even above 2000 sec⁻¹. This slipstick transition is the point at which the sharkskin or stick region converts to a slip or fast-moving wavy extrudate surface and is typically characterized by a pressure fluctuation over time. Some polymers exhibit sharp slipstick transitions characterized by high pressure fluctuations when pressure is compared to time. Other polymers do not display harsh slipstick transitions. For example, LDPE is not believed to undergo a typical slipstick transition, and if it does, it is greatly above a shear rate of 2000 sec⁻¹.

When increasing the shear rate of a polymer extruded through a die, several transitions may be observed. For example, at low shear rate, the extrudate is smooth, and the shear stress is typically constant with time at any particular shear rate. This is the traditional operating range where most polymers are processed in industry today. With increasing shear rate, the extrudate surface becomes matt then deformed. This is typically called the sharkskin region and like the "smooth" region, shear stress is apparently constant with time at any particular shear rate. In the literature polyethylene is reported to display sharkskin beginning at shear rates for which the shear stress is higher than ~0.2 MPa.

At high shear stress, typically 0.5 MPa and above, the extrudate surface is wavy and highly distorted. This region is often called the wavy region or gross distortion region.

For some polymers, one or two additional regions are observed. One is called the slipstick region, and is typically characterized by the following: (1) the shear stress versus shear rate is essentially flat; (2) the measured pressure oscillates periodically over time; and/or (3) the surface of the extrudate consists of two distinct regions, one (typically sharkskin) corresponding with increasing pressure, and one (typically smooth) corresponding with decreasing pressure. The actual surface appearance depends upon the shear stress at which slipstick occurs. At shear rates above the slipstick region, and as long as the shear stress is below the onset of the wavy region, the extrudate is smooth and glossy. This is called the glossy region.

The glossy region is an acceptable operating region in terms of extrudate surface appearance, and extrusion stability. It is highly desirable in terms of throughput and melt viscosity (high throughput, low melt viscosity). Unfortunately, the shear rates required to be in the glossy region are usually too high for most practical application such as film/coating applications. Likewise, the shear stress at which the slipstick occurs is also typically too high, so that the glossy region is not observed, and the extrudate is wavy at shear rates immediately above the slipstick region.

U.S. Patent 4,859,398 to Su, herein describes a method to process polyethylene, particularly LLDPE, at high shear rates, preferably above 1000 sec⁻¹. By reducing the extrusion temperature to just above the melting temperature of the polyethylene (140°C) and processing at shear rates above 1000 sec⁻¹, Su found a smooth surface in the extrudate.

U.S. Patent 2,991,508 to Fields, discloses the "super extrusion" of high density polyethylene at melt temperatures over 235°C and shear rates up to 8,000 sec⁻¹. The super extrusion is disclosed to vary with die temperature.

Journal of Applied Polymer Science, Vol 28, 3503-3511 (1983).

Discloses the superextrusion LLDPE having a broad Mw/Mn greater than 3.7.

Speeds above 1000 sec⁻¹ are impractical, however, for most polyolefin processing. Thus it would be desirable to develop a process for processing polyolefins at speeds faster than those currently in commercial use but less than 1000 sec⁻¹ without obtaining sharkskin melt fracture.

SUMMARY OF THE INVENTION

This invention relates to a process for processing a polyolefin comprising heating a polyolefin having a molecular weight distribution Mw/Mn of less than 3.3, a melt index less than 5 g/10 min; extruding said polyolefin at a shear stress of less than 0.5 MPa, at an extrusion temperature less than 200°C and at a shear rate between the shear rate immediately above the shear rate at the end of the slipstick region and 2000 sec⁻¹.

This invention further relates to a process according to claim 8, to a process according to claim 9 and to a method according to claim 10.

Particular embodiments of the invention are disclosed in the dependent claims.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

It has been discovered that certain polyolefins, particularly copolymers and polymers of ethylene, having a low melt index, a narrow molecular weight distribution, and an extrusion temperature less than 200°C exhibit a slipstick transition at a relatively low shear rate. It has also been discovered that by extruding these polyolefins at a shear rate immediately above the shear rate at the end of the slipstick region, transition smooth extrudates and low melt viscosities can be obtained. This is a highly desirable characteristic because it permits extruding resins at high throughput with minimum power consumption. It has further been discovered that these polyolefins show their slipstick transition at low shear rates and low temperatures.

Polyolefins useful in the process of this invention are homopolymers and copolymers of polyolefins, particularly ethylene or propylene copolymers, even more particularly ethylene homo and copolymers. The ethylene polymers can have comonomers of C₃ and above. The term copolymer as used herein is defined to include polymers of 2, 3, 4 or more different monomers.

The polyolefins useful in this invention preferably have a density above 0.87 g/cm³, more preferably between 0.88 and less than ~0.95 g/cm³, even more preferably between 0.89 and less than ~0.95 g/cm³, as measured by American Society for Testing and Materials (ASTM) method D792. The polyolefins useful in this invention further have molecular weight distribution (Mw/Mn) less than 3.3, preferably less than 3.0. The lower the molecular weight distribution, the better. Furthermore, the polyolefins useful in this invention have a melt index as measured by ASTM method D1238 of 0.01 to 5 g/10 min, preferably from 0.01 to 4 g/10 min, even more preferably from 0.01 to 2 g/10 min. Again, the lower the melt index, the better. Molecular weight distribution is herein defined to be the ratio of weight average molecular weight to number average molecular weight. The molecular weights are measured by GPC, gel permeation chromatography. Molecular weight determinations for polyolefin products are made by gel permeation chromatography (GPC) according to the following technique. Molecular weights and molecular weight distributions are measured using a Waters 150 gel permeation chromatograph equipped with a differential refractive index (DRI) detector and a Chromatix KMX-6 on-line light scattering photometer. The system is used at 135°C with 1,2,4-trichlorobenzene as the mobile phase. Shodex (Showa Denko America, Inc.) polystyrene gel columns 802, 803, 804 and 805 are used. This technique is discussed in "Liquid Chromatography of Polymers and Related Materials III", J. Cazes editor, Marcel Dekker, 1981, p. 207 which is incorporated herein by reference. No corrections for column spreading are employed; however, data on generally accepted standards, e.g. National Bureau of Standards Polyethylene 1484 and anionically produced hydrogenated polyisoprenes (an alternating ethylene-propylene copolymer) demonstrated that such corrections on Mw/Mn (=MWD) were less than 0.05 units. Mw/Mn was calculated from elution times. The numerical analyses were performed using the commercially available Beckman/CIS customized LALLS software in conjunction with the standard Gel Permeation package, run on a HP 1000 computer. Furthermore, the process of this invention is characterized by a shear rate higher than the slipstick transition of the polymer but lower than 2000 sec⁻¹, preferably lower than 1000 sec⁻¹. The following are defined for a cylindrical die: shear rate (sec⁻¹) = 32(v)/πd³ in sec⁻¹ (v=volumetric flow of polymer through the die (cc/s), d=die diameter (cm)); shear stress (MPa) = P(d)/4l (P=entrance die pressure (MPa), d=die diameter (cm), l=die length (cm)); and melt viscosity = shear stress/shear rate.

Slipstick region, Smooth stable region and skarkskin region are discussed in "Wall Slip and Extrudate Distortion in Linear Low-density Polyethylene" by Douglass S. Kalika and Morton M. Denn, Journal of Rheology, 31 (8), p815-834, (1987) which is incorporated by reference herein. Slipstick as used in this invention is measured by the following method: (1) using a capillary rheometer with a cylindrical die of length=10mm, diameter=1mm; (2) setting the temperature at the value of interest i.e., anywhere between the polymer melting temperature and 200°C.; (3) measuring the flow curve by increasing the shear rate from 1 to 2000 sec⁻¹; (4) measuring the shear stress; (5) observing the surface appearance of the extrudate; and (6) noting shear rate and shear stress just after slipstick region. Slipstick region can be determined by any one of or a combination of the following: (1) shear stress is constant vs. shear rate; (2) there is a periodic fluctuation of head pressure; or (3) there is a periodic fluctuation in extrudate surface appearance.

The materials and process of this invention are such that shear rate just after the slipstick transition is typically less than 2000 sec⁻¹, preferably less than 1000 sec⁻¹ and shear stress just after slipstick region is less than 0.50 MPa, pref-

erably less than 0.45 MPa. The temperature range at which the processing of these polymers is conducted is typically less than 200°C, preferably less than 190°C, even more preferably between 60°C and 170°C.

We have discovered that some polyolefins when processed under specific extrusion conditions, do have a glossy region attainable in practical film/coating application. The conditions required for the products and processes of this invention are that the glossy region starts at shear rates below 2000 sec⁻¹ preferably below 1000⁻¹ and at shear stress below 0.50 MPa, preferably below 0.45 MPa. This is typically achieved through a combination of narrow MWD and low melt index with low extrusion temperatures. It has been discovered that the polyolefins processed according to this invention provide the unique advantage of being able to process a low melt index polymer at low temperatures and a high shear rate. Thus, the instant process produces a polymer with a visibly smooth, non-sharkskin, non-wavy surface at lower operating temperatures and viscosities.

A method to produce the polyolefins used in this invention includes using an activated cyclopentadienyl group 4 transition metal complex as a catalyst in gas phase, solution phase, high pressure, medium pressure, low pressure, in bulk, or other such conditions typically known in the art. The catalysts capable of producing polyolefins useful in this invention are disclosed in: U.S. Patents 5,055,438; 5,198,401; 5,057,475; 5,153,157; 5,017,714; U.S. application serial no. 542,236, filed June 22, 1990, U.S. application serial no. 468,382, filed February 28, 1990, European Patent Application 129,368, published December 17, 1984, European Patent Application 520, 732, published December 30, 1992, U.S. application serial no. 885,170, filed May 18, 1992, European Patent Application 277,003, published June 3, 1988, European Patent Application 277,004, published June 3, 1988, U.S. application serial no. 926,006 filed August 5, 1992, which are herein incorporated by reference as if fully set forth.

Another method to produce the polyolefins useful in this invention would be selective extraction or separation methods known in the art. Homogeneous catalysis is also known to produce narrow MWD polymers and would produce polyolefins useful in this invention.

The polymer produced can be used for wire and cable coating, for casting applications, for blown film, cast film, extrusion coating, extrusion-coated wire, extrusion-coated cables, laminates and the like. The following examples are intended to illustrate process and product properties of specific embodiments of the invention and are not intended to limit the scope of the invention.

EXAMPLES

Examples 1 - 8 were run in a Goettfert Capillary Rheometer with a cylindrical die diameter of 1mm. Runs 1 and 8 are for comparative purposes.

The polymers were tested at shear rates from 10 up to 2000 s⁻¹.

The viscosity is the shear stress/shear rate.

The extrudate surface is continually observed and is assessed as an operating range if the surface is smooth, absent of apparent defects, and if the shear stress is stable over time.

The equipment conditions were:

Equipment: Goettfert Rheograph 2002

Melting time: 4 minutes

Test piston diameter: 15 mm

Test temperature: see table

Die diameter: 1 mm

Die length: see table

The data are presented in Table 1.

Traditional operating range is the shear rate range starting from 0 sec⁻¹ and ending at the shear rate at which shark-skin melt fracture starts. New operating range is the shear rate range immediately above the shear rate at the end of the slip-stick region and where the surface remains without defects which normally occur as long as the shear stress is below ~0.5 MPa. Minimum viscosity is the minimum viscosity observed in the range. This is typically the viscosity at the higher shear rate of the range.

Run #	polymer	co-monomer	MWD	MI (g/10min)	Density (g/cc)	Capillary die l (cm)	Extrusion Temp. (°C)	Trad. Operating Range		New Operating Range	
								Shear rate (s ⁻¹)	Min. Vis. (Pa.s)	Shear rate (s ⁻¹)	Min. Vis. (Pa.s)
1	LL1004	Butene	3.7	2.8	0.92	1.0	190	0-400	590	> 2000	--
2	Exact 3010	Butene	2.0	3.5	0.91	1.0	150	0-60	2730	650-2000	400
3	Exact 3010	Butene	2.0	3.5	0.91	1.0	190	0-250	950	2000	440
4	Exp 1	Hexene	2.3	4.0	0.945	1.0	150	0-200	1070	800-2000	300
5	Exp 2	Hexene	2.2	0.6	0.88	1.0	150	0-10	17900	400-2000	490
6	Exp 2	Hexene	2.2	0.6	0.88	1.0	190	0-20	10950	500-2000	500
7	Exp 3	Hexene	2.4	1.4	0.90	3.0	150	0-60	4600	700-2000	460
8	Exp 3	hexene	2.4	1.4	0.90	1.0	240	0-300	830	> 2000	--

TABLE 1

* minimum viscosity is the smallest apparent melt
viscosity observed

5

Example 1 is a conventional LLDPE with a broad molecular weight distribution, a broad composition distribution and a slipstick region ends above 2000 sec^{-1} . Example 8 is a polyolefin made by an activated cyclopentadienyl transition metal catalyst having narrow MWD, narrow composition distribution and extruded at 240°C . Neither example exhibits this new operating range below a shear rate of 2000 sec^{-1} . Examples 2-7 can be processed in a new operating range below 2000 sec^{-1} , and preferably below 1000 sec^{-1} , giving smooth and glossy extrudates without sharkskin or wavy surfaces and at a very low melt viscosity. It is also interesting that in the new operating range the melt viscosity is almost independent of the initial MI and the extrusion temperature. For example, note that in column 9, under new operating range, the viscosity at 1000 sec^{-1} shear rate for examples 2-7 fall within close range of one another, whereas under the traditional operating range the minimum viscosity fluctuates from approximately 600 to 17,000.

15

LL1004 is a commercially available LLDPE with a molecular weight distribution of 3.7 and a slipstick region that ends above 2000 sec^{-1} . Examples 2-7 are polyethylene copolymers with a MWD below 3.5.

20 EXAMPLE 9

Exact 3010 D, an ethylene/butene copolymer having an MI of 1g/10 min and a density of 0.90g/cc, produced commercially by Exxon Chemical Company was used. The trial was generated on a Haake Extrusion Rheometer (Rheocord Model E). The temperature profile within the barrel was $40^\circ/70^\circ/105^\circ\text{C}$. A rod die with final land section of 0.635 cm was used. Head pressure and torque were measured. Data are summarized in Table 2.

25

Table 2

Head Pressure (psi)	900	1350	1250	1300
RPM	20	80	170	300
Torque (kg.m)	26	51	53	38
Surface appearance	Smooth	Slight Sharkskin	Severe Sharkskin	Smooth Glossy
Note that the glossy region was observed in this experiment at 300 RPM, while the traditional operating window was limited at around 80 RPM. Note also that the torque was very low in the glossy region which is highly desirable.				

30

35

40 Melt index was measured according to ASTM D1238. Density was measured according to ASTM D792.

As is apparent from the foregoing description, the materials prepared and the procedures followed relate to specific preferred embodiments of the broad invention. It is apparent from the foregoing general description and the specific embodiments that while forms of the invention have been illustrated and described, various modifications can be made without departing from the scope of this invention as defined by the following claims.

45

Claims

1. A process for processing a polyolefin comprising heating a polyolefin having a molecular weight distribution, Mw/Mn, of less than 3.3 and a melt index less than 5 g/10 min, extruding said polyolefin at a shear stress of less than 0.5 MPa, at an extrusion temperature less than 200°C and at a shear rate between the shear rate immediately above the shear rate at the end of the slipstick region and 2000 sec^{-1} .
2. The process of claim 1 wherein the polyolefin has a melt index of less than 4 g/10 min, preferably from 0.01 to 2 g/10 min, an Mw/Mn less than 3 and the extrusion temperature is less than 190°C .
3. The process of claim 1 or 2 wherein the polyolefin is an ethylene polymer with a density between 0.88 and less than 0.95 g/cm^3 , a melt index less than 4 g/10 minutes and a molecular weight distribution less than 3.

55

4. The process of any of the above claims wherein the polyolefin is a copolymer of ethylene and butene or hexene.
5. The process of any of the above claims wherein the shear rate is between the shear rate at the end of the slipstick region of said polyolefin and 1000 sec^{-1} and the shear stress is less than 0.45 MPa
- 5 6. The process of any of the above claims wherein the extrusion temperature is from 60 to 190°C
7. A process for extrusion coating a polyolefin about a wire or cable comprising:
- 10 heating a polyolefin having a molecular weight distribution less than 3.3 and an MI less than 5 g/10 min; and extruding said polyolefin at an extrusion temperature of less than 200°C , at a shear rate higher than the shear rate at the end of the slipstick region but lower than 2000 sec^{-1} , and at a shear stress of 0.5 MPa or less, onto a wire or cable.
- 15 8. A process for producing film comprising heating a polyolefin with a molecular weight distribution less than 3.3, a melt index less than 5 g/10 min, and extruding said polyolefin at an extrusion temperature less than 200°C , at a shear rate higher than the shear rate at the end of the slipstick region of the polyolefin but lower than 2000 sec^{-1} and at a shear stress of 0.5 MPa or less, and blowing or casting said polyolefin into a film.
- 20 9. A process for coating a substrate comprising heating a polyolefin with a molecular weight distribution less than 3.3, a melt index less than 5 g/10 min, extruding said polyolefin at an extrusion temperature less than 200°C and at a shear rate higher than the shear rate at the end of the slipstick region of the polyolefin but less than 2000 sec^{-1} , and coating the polymer onto a substrate.
- 25 10. A method for producing a polyolefin extrudate substantially free from sharkskin melt fracture comprising the steps of:
- selecting a polyolefin having a MWD less than 3.3 and a melt index less than 5 g/10 min; and
extruding the polyolefin at a shear stress of less than 0.5 MPa, an extrusion temperature of less than 200°C
30 and at a shear rate higher than the shear rate at the end of the slipstick region of the polyolefin but less than 1000 sec^{-1} .

Patentansprüche

- 35 1. Verfahren zur Verarbeitung eines Polyolefins, bei dem ein Polyolefin mit einer Molekulargewichtsverteilung, M_w/M_n , von weniger als 3,3 und einem Schmelzindex von weniger als 5 g/10 Min erwärmt wird, das Polyolefin mit einer Scherspannung von weniger als 0,5 MPa bei einer Extrusionstemperatur von weniger als 200°C und mit einer Scherrate zwischen der Scherrate unmittelbar über der Scherrate am Ende des Gleit-Haft-Bereichs und 2000 s^{-1} extrudiert wird.
- 40 2. Verfahren nach Anspruch 1, bei dem das Polyolefin einen Schmelzindex von weniger als 4 g/10 Min, vorzugsweise 0,01 bis 2 g/10 Min, und ein M_w/M_n von weniger als 3 aufweist und die Extrusionstemperatur weniger als 190°C beträgt.
- 45 3. Verfahren nach Anspruch 1 oder 2, bei dem das Polyolefin ein Ethylenpolymer mit einer Dichte zwischen 0,88 und weniger als $0,95 \text{ g/cm}^3$, einem Schmelzindex von weniger als 4 g/10 Min und einer Molekulargewichtsverteilung von weniger als 3 ist.
- 50 4. Verfahren nach einem der vorhergehenden Ansprüche, bei dem das Polyolefin ein Copolymer aus Ethylen und Buten oder Hexen ist.
5. Verfahren nach einem der vorhergehenden Ansprüche, bei dem die Scherrate zwischen der Scherrate am Ende des Gleit-Haft-Bereichs des Polyolefins und 1000 s^{-1} liegt und die Scherspannung weniger als 0,45 MPa beträgt.
- 55 6. Verfahren nach einem der vorhergehenden Ansprüche, bei dem die Extrusionstemperatur 60 bis 190°C beträgt.
7. Verfahren zum Extrusionsbeschichten eines Polyolefins auf einen Draht oder ein Kabel, bei dem ein Polyolefin mit einer Molekulargewichtsverteilung von weniger als 3,3 und einem MI von weniger als 5 g/10 Min erwärmt wird und

das Polyolefin mit einer Extrusionstemperatur von weniger als 200°C mit einer Scherrate, die höher als die Scherrate am Ende des Gleit-Haft-Bereichs, aber geringer als 2000 s⁻¹ ist, und mit einer Scherspannung von 0,5 MPa oder weniger auf einen Draht oder ein Kabel extrudiert wird.

- 5 8. Verfahren zur Herstellung von Folie, bei dem ein Polyolefin mit einer Molekulargewichtsverteilung von weniger als 3,3 und einem Schmelzindex von weniger als 5 g/10 Min erwärmt wird und das Polyolefin mit einer Extrusionstemperatur von weniger als 200°C mit einer Scherrate, die höher als die Scherrate am Ende des Gleit-Haft-Bereichs des Polyolefins, aber geringer als 2000 s⁻¹ ist, und mit einer Scherspannung von 0,5 MPa oder weniger extrudiert wird und dieses Polyolefin zu einer Folie geblasen oder gegossen wird.
- 10 9. Verfahren zum Beschichten eines Substrats, bei dem ein Polyolefin mit einer Molekulargewichtsverteilung von weniger als 3,3 und einem Schmelzindex von weniger als 5 g/10 Min erwärmt wird, das Polyolefin mit einer Extrusionstemperatur von weniger als 200°C und mit einer Scherrate, die höher als die Scherrate am Ende des Gleit-Haft-Bereichs des Polyolefins, aber geringer als 2000 s⁻¹ ist, extrudiert wird und das Polymer auf ein Substrat beschichtet wird.
- 15 10. Verfahren zur Herstellung von Polyolefinextrudat, das im wesentlichen frei von Haileder-Schmelzbruch ist, bei dem ein Polyolefin mit einer MWD von weniger als 3,3 und einem Schmelzindex von weniger als 5 g/10 Min gewählt wird und das Polyolefin mit einer Scherspannung von weniger als 0,5 MPa, einer Extrusionstemperatur von weniger als 200°C und mit einer Scherrate, die höher als die Scherrate am Ende des Gleit-Haft-Bereichs des Polyolefins, aber geringer als 1000 s⁻¹ ist, extrudiert wird.
- 20

Revendications

- 25 1. Procédé pour le traitement d'une polyoléfine, comprenant le chauffage d'une polyoléfine ayant une distribution des poids moléculaires, Mw/Mn inférieure à 3,3 et un indice de fluidité inférieur à 5 g/10 min, l'extrusion de ladite polyoléfine à une tension de cisaillement inférieure à 0,5 MPa, à une température d'extrusion inférieure à 200°C et à une vitesse de cisaillement comprise entre la vitesse de cisaillement immédiatement au-dessus de la vitesse de cisaillement à l'extrémité de la région d'effet de glissement et d'adhérence et 2000 s⁻¹.
- 30 2. Procédé suivant la revendication 1, dans lequel la polyoléfine a un indice de fluidité inférieur à 4 g/10 min, de préférence de 0,01 à 2 g/10 min, un rapport Mw/Mn inférieur à 3, la température d'extrusion étant inférieure à 190°C.
- 35 3. Procédé suivant la revendication 1 ou 2, dans lequel la polyoléfine est un polymère d'éthylène ayant une masse volumique comprise dans l'intervalle de 0,88 à moins de 0,95 g/cm³, un indice de fluidité inférieur à 4 g/10 minutes et une distribution des poids moléculaires inférieure à 3.
- 40 4. Procédé suivant l'une quelconque des revendications précédentes, dans lequel la polyoléfine est un copolymère d'éthylène et de butène ou d'hexène.
5. Procédé suivant l'une quelconque des revendications précédentes, dans lequel la vitesse de cisaillement est comprise entre la vitesse de cisaillement à l'extrémité de la région d'effet de glissement et d'adhérence de la polyoléfine et 1000 s⁻¹ et la tension de cisaillement est inférieure à 0,45 MPa.
- 45 6. Procédé suivant l'une quelconque des revendications précédentes, dans lequel la température d'extrusion est comprise dans l'intervalle de 60 à 190°C.
7. Procédé pour le revêtement par extrusion d'un fil ou d'un câble avec une polyoléfine, comprenant :
- 50 le chauffage d'une polyoléfine ayant une distribution des poids moléculaires inférieure à 3,3 et un IF inférieur à 5 g/10 min ;
et l'extrusion de ladite polyoléfine à une température d'extrusion inférieure à 200°C, à une vitesse de cisaillement supérieure à la vitesse de cisaillement à l'extrémité de la région d'effet de glissement et d'adhérence mais inférieure à 2000 s⁻¹, et à une tension de cisaillement égale ou inférieure à 0,5 MPa, sur un fil ou un câble.
- 55 8. Procédé pour la production d'un film, comprenant le chauffage d'une polyoléfine ayant une distribution des poids moléculaires inférieure à 3,3, et un indice de fluidité inférieur à 5 g/10 min, et l'extrusion de ladite polyoléfine à une température d'extrusion inférieure à 200°C, à une vitesse de cisaillement supérieure à la vitesse de cisaillement à

EP 0 684 900 B1

l'extrémité de la région d'effet de glissement et d'adhérence de la polyoléfine mais inférieure à 2000 s^{-1} et à une tension de cisaillement égale ou inférieure à 0,5 MPa, et la transformation de ladite polyoléfine en un film par soufflage ou coulée.

5 9. Procédé pour le revêtement d'un substrat, comprenant le chauffage d'une polyoléfine ayant une distribution des poids moléculaires inférieure à 3,3 et un indice de fluidité inférieur à 5 g/10 min, l'extrusion de ladite polyoléfine à une température d'extrusion inférieure à 200°C et à une vitesse de cisaillement supérieure à la vitesse de cisaillement à l'extrémité de la région d'effet de glissement et d'adhérence de la polyoléfine mais inférieure à 2000 s^{-1} , et le revêtement du substrat avec le polymère.

10

10. Procédé pour la production d'un extrudat polyoléfinique pratiquement dépourvu de fragilité de fusion en peau de requin, comprenant les étapes consistant :

15

à choisir une polyoléfine ayant une DPM inférieure à 3,3 et un indice de fluidité inférieur à 5 g/10 min ; et à extruder la polyoléfine à une tension de cisaillement inférieure à 0,5 MPa, une température d'extrusion inférieure à 200°C et à une vitesse de cisaillement supérieure à la vitesse de cisaillement à l'extrémité de la région d'effet de glissement et d'adhérence de la polyoléfine et inférieure à 1000 s^{-1} .

20

25

30

35

40

45

50

55