



EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention of the grant of the patent:
07.03.2018 Bulletin 2018/10

(21) Application number: **15786456.2**

(22) Date of filing: **01.05.2015**

(51) Int Cl.:
C08G 79/14 ^(2006.01) **C08J 5/18** ^(2006.01)
C07D 401/14 ^(2006.01) **C07D 213/22** ^(2006.01)
C08G 79/00 ^(2006.01) **C08G 73/00** ^(2006.01)
G01N 27/04 ^(2006.01) **G02F 1/15** ^(2006.01)
H01B 1/06 ^(2006.01) **H01M 8/02** ^(2016.01)

(86) International application number:
PCT/JP2015/063084

(87) International publication number:
WO 2015/167010 (05.11.2015 Gazette 2015/44)

(54) **ORGANIC/HETEROMETALLIC HYBRID POLYMER, PROCESS FOR PRODUCING SAME, FILM OF ORGANIC/HETEROMETALLIC HYBRID POLYMER, ORGANIC/MULTIMETALLIC HYBRID POLYMER, PROCESS FOR PRODUCING SAME, AND FILM OF ORGANIC/MULTIMETALLIC HYBRID POLYMER**

ORGANISCHES/HETEROMETALLISCHES HYBRIDPOLYMER, VERFAHREN ZUR HERSTELLUNG DAVON, FILM AUS ORGANISCHEM/HETEROMETALLISCHEM HYBRIDPOLYMER, ORGANISCHES/MULTIMETALLISCHES HYBRIDPOLYMER, VERFAHREN ZUR HERSTELLUNG DAVON UND FILM AUS ORGANISCHEM/MULTIMETALLISCHEM HYBRIDPOLYMER

POLYMÈRE HYBRIDE ORGANIQUE/HÉTÉROMÉTALLIQUE, SON PROCÉDÉ DE PRODUCTION, FILM DE POLYMÈRE HYBRIDE ORGANIQUE/HÉTÉROMÉTALLIQUE, POLYMÈRE HYBRIDE ORGANIQUE/MULTIMÉTALLIQUE, SON PROCÉDÉ DE PRODUCTION, ET FILM DE POLYMÈRE HYBRIDE ORGANIQUE/MULTIMÉTALLIQUE

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

(30) Priority: **02.05.2014 JP 2014095275**
26.01.2015 JP 2015012448

(43) Date of publication of application:
08.03.2017 Bulletin 2017/10

(73) Proprietor: **National Institute for Materials Science Tsukuba-shi, Ibaraki 305-0047 (JP)**

(72) Inventors:
• **HIGUCHI Masayoshi**
Tsukuba-shi
Ibaraki 305-0047 (JP)
• **SATO Takashi**
Tsukuba-shi
Ibaraki 305-0047 (JP)

(74) Representative: **V.O.**
P.O. Box 87930
Carnegieplein 5
2508 DH Den Haag (NL)

(56) References cited:
EP-A1- 2 444 839 WO-A1-2014/021208
JP-A- 2012 153 714 US-A1- 2009 270 589

- **MASAYOSHI HIGUCHI: 'Yuki Kinzoku Hybrid Polymer no Denshi Hikari Kino' SOCIETY OF NANO SCIENCE AND TECHNOLOGY TAIKAI KOEN YOKOSHU 06 June 2013, XP008185707**
- **MASAYOSHI HIGUCHI: 'Creation of Organic-Metallic Hybrid Polymers with Electrochromic Properties and the Device Application to Displays' JOURNAL OF SOCIETY OF SYNTHETIC ORGANIC CHEMISTRY vol. 69, no. 3, 01 March 2011, JAPAN, pages 229 - 235, XP008184459**

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

- **MASAYOSHI HIGUCHI: 'Cho Bunshi Material no Shin Choryu Display Devices with Organic-Metallic Hybrid Polymers' KAGAKU KOGYO vol. 62, no. 12, 01 December 2011, pages 910 - 915, XP008185274**

Description

[Technical Field]

[0001] The present invention relates to an organic/heterometallic hybrid polymer, a method for producing the same, an organic/heterometallic hybrid polymer film, an organic/multimetallc hybrid polymer, a method for producing the same and an organic/multimetallc hybrid polymer film.

[0002] Priority is claimed on Japanese Patent Application No. 2014-095275, filed May 2, 2014, and Japanese Patent Application No. 2015-012448, filed January 26, 2015, the contents of which are incorporated herein by reference.

[Background Art]

[0003] Organic/metallic hybrid polymers are supramolecular polymers in which metals are arranged precisely in a polymer main chain structure, and are known to exhibit electrical and optical functions by the electronic interaction between the organic ligand and the metal, or by the electronic interaction between adjacent metals.

[0004] For example, organic/metallic hybrid polymers containing a transition metal such as iron (Fe) or ruthenium (Ru) exhibit electrochromic properties in the visible region, and have been studied as display device materials (Non-Patent Document 1). It should be noted that the electrochromic property refers to a property to change its color by applying a charge to the material.

[0005] Further, organic/heterometallic hybrid polymers into which europium (Eu) and Fe are precisely introduced alternately using asymmetric organic ligands have been reported to function as display devices of the luminescence switching of Eu corresponding to the electrochromic properties by the oxidation-reduction of Fe (Non-Patent Document 2).

[0006] In addition, several organic/metallic hybrid polymers having electrochromic properties have been synthesized (Patent Documents 1 and 2).

[0007] Although the research and development of electrochromic materials in the visible light region have advanced as described above, the research and development of electrochromic materials in the ultraviolet region or infrared region have not advanced much. In particular, if the electrochromic materials in the infrared region can be developed, they can be applied to a near infrared light-shielding electrochromic window which can freely shield near infrared light of sunlight entering inside the room, thereby enhancing the cooling effect of the room and saving energy. Further, with respect to near infrared light used in optical communications, development of products in the form of an optical device for a near infrared optical shutter may also be possible.

[0008] Accordingly, the inventors of the present invention have newly synthesized an organic/heterometallic hybrid polymer in which hetero metals are closely arranged within the polymer via a π -conjugated organic portion, aimed at electrochromism in the near infrared region using the electronic interaction between the metals. The organic/heterometallic hybrid polymer exhibited an intervalence charge transfer (IVCT) absorption between hetero metals (zinc (Zn)-Ru) in the near infrared region by the application of a voltage. Since the absorbance of the absorption changes in a reversible manner by the ON/OFF of the voltage application, the potential as an optical device material was shown.

[0009] However, since the energy of IVCT occurring between hetero metals is relatively large, the absorption wavelength is limited to the near infrared region from 900 nm to 1,500 nm. Therefore, it is difficult to realize electrochromism in the infrared region with a wavelength longer than 1,500 nm.

[0010] Further, because the electrochromism itself is a simple ON/OFF of the absorption, switching of a plurality of absorption wavelengths required in the optical device of the near infrared optical shutter is difficult.

[0011] Furthermore, with respect to the above linear organic/heterometallic hybrid polymers, when the ON/OFF of the voltage application is repeated, the polymer film is gradually dissolved. In other words, durability of the polymer film to the repetitive electrochromic changes is not sufficient.

[Citation List]

[Patent Documents]

[0012]

[Patent Document 1] Japanese Unexamined Patent Application, First Publication No. 2012-188517

[Patent Document 2] Japanese Unexamined Patent Application, First Publication No. 2009-265437

[Non-Patent Documents]

[0013]

[Non-Patent Document 1] Higuchi M. Polym. J. 2009, 41, 511-520.

[Non-Patent Document 2] Sato T; Higuchi M. Chem. Commun. 2013, 49, 5256-5258.

[Summary of Invention]

[Technical Problem]

[0014] An object of the present invention is to provide a linear and stable organic/heterometallic hybrid polymer having electrochromic properties (in particular, electrochromic properties in the near infrared region), a method for producing the same, and an organic/heterometallic hybrid polymer film.

[0015] Further, the present invention also has an object of providing an organic/multimetallic hybrid polymer exhibiting electrochromism in the infrared region with a wavelength equal to or longer than 1,500 nm, which has a light blocking function by switching ON/OFF at least two wavelengths within a range from the near infrared region to the infrared region, and forms a film exhibiting high durability against repetitive electrochromic changes, a method for producing the same and an organic/multimetallic hybrid polymer film.

[Solution to Problem]

[0016] In one aspect of the present invention, the inventors of the present invention have synthesized a novel organic/heterometallic hybrid polymer and a film thereof by trial and error in view of the above circumstances. In particular, materials in which hetero metals are closely arranged within a conductive polymer can be converted to a structure that exhibits an intervalence charge transfer (IVCT) between hetero metals by the application of a voltage, and can freely convert the optical absorption spectrum from the visible light region to the near infrared light region. In addition, the present inventors have completed the present invention by discovering that the above organic/heterometallic hybrid polymer can be used as a near infrared light-blocking electrochromic window or a near infrared optical shutter.

[0017] In view of the above circumstances, by trial and error, the inventors of the present invention have synthesized an organic metal ligand having two transition metals, and by causing it to form a complex with another metal, synthesized a linear organic/multimetallic hybrid polymer. The organic/multimetallic hybrid polymer refers to a supramolecular polymer in which an organic compound and two or more different kinds of metals or a metal having two or more different coordination states are linked. In addition, one aspect of the organic/multimetallic hybrid polymer is a supramolecular polymer in which a plurality of organic compounds containing at least two ligands and at least one metal in a molecule are linked by forming a complex with a transition metal outside the aforementioned organic compound. Further, in another aspect of the organic/multimetallic hybrid polymer, at least two metals in the aforementioned organic compound are included. The organic/heterometallic hybrid polymer refers to a supramolecular polymer in which the aforementioned metal and the transition metal outside the organic compound are different.

[0018] Furthermore, in yet another aspect of the present invention, the present inventors have formed a film of the organic/multimetallic hybrid polymer on a glass substrate and an ITO substrate. The film of the organic/multimetallic hybrid polymer containing Zn and two Ru in the unit structure exhibited not only an IVCT absorption between hetero metals (Zn-Ru) but also an IVCT absorption between the same metal (Ru-Ru) within the near infrared to infrared regions by changing the applied voltage. That is, from an initial state having no absorption within the near infrared to infrared regions, by applying an oxidation potential, an IVCT absorption between the same metal (Ru-Ru) was exhibited. Furthermore, when an even higher oxidation potential was applied, the IVCT absorption between the same metal (Ru-Ru) disappeared, and the IVCT absorption between hetero metals (Zn-Ru) appeared. As a result, it was found that by changing the applied voltage, a state having no absorption within the near infrared to infrared regions can be electrochemically switched in a reversible manner to a state in which absorptions at two different wavelengths are exhibited.

[0019] Furthermore, in yet another aspect of the present invention, a branched organic/multimetallic hybrid polymer having a three-dimensional network structure was synthesized by introducing a branched portion into the polymer using a branched-type organic ligand that can be linked in three directions, when causing the organic metal ligand having two organic metals to form a complex with another metal. In addition, these were deposited on a glass substrate and an ITO substrate.

[0020] Films of these organic/multimetallic hybrid polymers stably exhibited reversible electrochromic changes for at least 50 repetitions of ON/OFF of the voltage application. Further, when the mixing ratio of the branched-type organic ligand that can be linked in three directions was increased, compared to the IVCT absorption by the film of the linear organic/multimetallic hybrid polymer having no branched portion, the absorption intensity increased, and it was possible to increase the absorbance difference (contrast) in the electrochromism.

[0021] As described above, the inventors of the present invention have synthesized a novel organic metal ligand and used it to synthesize a novel organic/multimetallic hybrid polymer. The present inventors have completed the present invention by discovering that the film of the organic/multimetallic hybrid polymer exhibits electrochromic properties in

the infrared region, has a light blocking function by switching ON/OFF at two wavelengths within the near infrared to infrared region, and stably exhibits reversible electrochromic changes even when ON/OFF of the voltage application is repeated if the branched portion is introduced to the polymer by using a branched organic ligand.

[0022] For example, the present invention includes the following configurations.

[0023]

[1] An organic/heterometallic hybrid polymer including a plurality of organic metal complexes and a plurality of transition metals, wherein

the aforementioned plurality of organic metal complexes are linked in a linear manner by sandwiching each of the aforementioned plurality of transition metals therebetween,

the aforementioned organic metal complexes include two ligands each having a terpyridyl group and one connector having $\text{Ru}(\text{dppe})_2$ and two ethynylene groups, and the two ligands are linked by the connector, so that a nitrogen atom at position 1' of the aforementioned terpyridyl group is directed toward the terminal side of the molecule of the aforementioned organic metal complex, and

the terpyridyl groups of at least two different organic metal complexes of the aforementioned plurality of organic metal complexes are bound to one of the aforementioned transition metals through a coordinate bond, thereby linking the aforementioned plurality of organic metal complexes while sandwiching the aforementioned plurality of transition metals alternately therebetween.

[2] The organic/heterometallic hybrid polymer according to [1], wherein the aforementioned transition metal is any one of Ru, Fe or Zn.

[3] The organic/heterometallic hybrid polymer according to [1] or [2], wherein a molecular weight M_w is at least 10.5×10^4 and not more than 29.2×10^4 .

[4] A method of producing an organic/heterometallic hybrid polymer, the method including a step of synthesizing an organic metal complex having $\text{Ru}(\text{dppe})_2$ and a terminal terpyridyl group by reacting a terpyridine compound having an ethynyl group and a terpyridyl group with a compound containing $\text{Ru}(\text{dppe})_2$ in an organic solvent, and

a step of synthesizing the organic/heterometallic hybrid polymer by reacting the aforementioned organic metal complex and a transition metal compound in an organic solvent.

[5] The method of producing an organic/heterometallic hybrid polymer according to [4], wherein 1.0 molar equivalent or more of the transition metal compound is reacted with respect to the aforementioned organic metal complex.

[6] The method of producing an organic/heterometallic hybrid polymer according to [4] or [5], wherein the aforementioned transition metal compound is any one of RuCl_2 , $\text{Fe}(\text{BF}_4)_2$, or $\text{Zn}(\text{NTf}_2)_2$.

[7] The method of producing an organic/heterometallic hybrid polymer according to any one of [4] to [6], wherein a reaction time of the aforementioned organic metal complex and the aforementioned transition metal compound is equal to or more than 12 hours.

[8] An organic/heterometallic hybrid polymer film including the organic/heterometallic hybrid polymer according to any one of [1] to [3].

[9] The organic/heterometallic hybrid polymer film according to [8], wherein a film thickness is at least 100 nm and not more than 1 mm.

[10] The organic/heterometallic hybrid polymer film according to [8] or [9], wherein a transition metal contained in the aforementioned organic/heterometallic hybrid polymer is a transition metal of any one of Fe or Zn.

[11] An organic/multimetallic hybrid polymer including a plurality of organic metal ligands and a plurality of transition metals, wherein

a linear portion in which the aforementioned plurality of organic metal ligands are linked in a linear manner by sandwiching each of the aforementioned plurality of transition metals therebetween is included, the aforementioned organic metal ligand is formed by linking two ligands to one connector, the aforementioned connector is formed with a benzene ring at the center by linking two $\text{Ru}(\text{dppe})_2$ via two ethynylene groups bonded to the benzene ring, while connecting two phenyl groups to the aforementioned two $\text{Ru}(\text{dppe})_2$ via other two ethynylene groups,

the aforementioned ligands are terpyridyl groups and are formed by being connected respectively to the aforementioned two phenyl groups of the aforementioned connector, and

the aforementioned terpyridyl groups of at least two different organic metal ligands of the aforementioned plurality of organic metal ligands are bound to one of the aforementioned transition metals through a coordinate bond, thereby linking the aforementioned plurality of organic metal ligands while alternately sandwiching the aforementioned plurality of transition metals therebetween.

[12] The organic/multimetallic hybrid polymer according to [11], wherein the aforementioned transition metal is Fe, Zn, Co or Ru.

[13] The organic/multimetallic hybrid polymer according to [11] or [12] which is linear

[14] The organic/multimetallic hybrid polymer according to [11] or [12] which is branched.

[15] The organic/multimetallic hybrid polymer according to [14], including a branched portion composed of 1,3,5-Tris[4-(2,2':6',2''-terpyridin-4'-yl)phenyl]benzene.

[16] The organic/multimetallic hybrid polymer according to [14] or [15], wherein a content of the aforementioned branched portion is at least 10 molar parts and not more than 30 molar parts, relative to the total number of moles of linear portions and branched portions constituting the organic/multimetallic hybrid polymer.

[17] A method of synthesizing an organic/multimetallic hybrid polymer, the method including a step of synthesizing a binuclear organometallic site containing two $\text{Ru}(\text{dppe})_2$ by reacting 1 molar equivalent of diethynylbenzene and 2 molar equivalents of $\text{Ru}(\text{dppe})_2\text{Cl}(\text{OTf})$ in an organic solvent, a step of synthesizing an organic metal ligand having a terpyridyl group at the terminal and two $\text{Ru}(\text{dppe})_2$ by reacting 2 molar equivalents of a terpyridine compound having an ethynyl group and a terpyridyl group with one molar equivalent of a binuclear organometallic site in an organic solvent, and a step of synthesizing a linear organic/multimetallic hybrid polymer by reacting the aforementioned organic metal ligand and a transition metal compound in an organic solvent.

[18] The method of synthesizing an organic/multimetallic hybrid polymer according to [17], wherein a branched organic/multimetallic hybrid polymer is synthesized by reacting the aforementioned linear organic/multimetallic hybrid polymer, a branched compound branched into three or more directions with a branch element at the center and having a ligand at a branched molecule end, and a transition metal compound.

[19] The method of synthesizing an organic/multimetallic hybrid polymer according to [18], wherein the aforementioned branched compound is 1,3,5-Tris[4-(2,2':6',2''-terpyridin-4'-yl)phenyl]benzene.

[20] The method of synthesizing an organic/multimetallic hybrid polymer according to [18] or [19], wherein a mixing amount of the aforementioned branched compound is at least 10 molar parts and not more than 30 molar parts, relative to the combined total of 100 molar parts of linear portions constituting the linear organic/multimetallic hybrid polymer.

[21] The method of synthesizing an organic/multimetallic hybrid polymer according to [17], wherein 1.0 molar equivalent or more of the transition metal compound is reacted with respect to the aforementioned organic metal ligand.

[22] The method of synthesizing an organic/multimetallic hybrid polymer according to any one of [17] to [21], wherein the aforementioned transition metal compound is $\text{Fe}(\text{BF}_4)_2$ or $\text{Zn}(\text{NTf}_2)_2$.

[23] The method of synthesizing an organic/multimetallic hybrid polymer according to any one of [17] to [22], wherein a reaction time of the aforementioned organic metal ligand and the aforementioned transition metal compound is equal to or more than 6 hours.

[24] An organic/multimetallic hybrid polymer film, including the organic/multimetallic hybrid polymer according to any one of [11] to [16].

[25] The organic/multimetallic hybrid polymer film according to [24], wherein a film thickness is at least 100 nm and not more than 1 mm.

[0024] In addition, the present invention includes the following aspects.

(1) An organic/heterometallic hybrid polymer which is a polymer obtained by linking a plurality of organic metal complexes in a linear manner while sandwiching a transition metal therebetween, wherein the aforementioned organic metal complex is formed in such a manner that two ligands having a terpyridine group are linked by a connector having $\text{Ru}[\text{PPh}_2]_4$ and acetylene so as to direct the aforementioned terpyridine group toward the outside, and terpyridine groups of different organic metal complexes are connected by being bound to one transition metal through a coordinate bond.

(2) The organic/heterometallic hybrid polymer according to (1), wherein the aforementioned transition metal is any one of Ru, Fe or Zn.

(3) The organic/heterometallic hybrid polymer according to (1) or (2), wherein a molecular weight M_w is at least 10.5×10^4 and not more than 29.2×10^4 .

(4) A method of producing an organic/heterometallic hybrid polymer, the method including:

a step of synthesizing an organic metal complex having a terminal terpyridine group by mixing and stirring a terpyridine having an ethynyl group with a Ru complex in an organic solvent, and a step of synthesizing the organic/heterometallic hybrid polymer by mixing and stirring the aforementioned organic metal complex and a transition metal compound in an organic solvent.

(5) The method of producing an organic/heterometallic hybrid polymer according to (4), wherein 1.0 equivalent or more of the transition metal compound is used with respect to the aforementioned organic metal complex.

(6) The method of producing an organic/heterometallic hybrid polymer according to (4) or (5), wherein the afore-

mentioned transition metal compound is any one of RuCl_2 , $\text{Fe}(\text{BF}_4)_2$, or $\text{Zn}(\text{NTf}_2)_2$.

(7) The method of producing an organic/heterometallic hybrid polymer according to any one of (4) to (6), wherein a mixing and stirring time of the organic metal complex and the transition metal compound is equal to or more than 12 hours.

(8) An organic/heterometallic hybrid polymer film, including the organic/heterometallic hybrid polymer according to any one of (1) to (3).

(9) The organic/heterometallic hybrid polymer film according to (8), wherein a film thickness is at least 100 nm and not more than 1 mm.

(10) The organic/heterometallic hybrid polymer film according to (8) or (9), wherein a transition metal contained in the aforementioned organic/heterometallic hybrid polymer is Fe or Zn.

(11) An organic/multimetallic hybrid polymer, wherein a linear portion in which organic metal ligands are linked in a linear manner by sandwiching transition metals therebetween is included, the aforementioned organic metal ligands are formed by linking ligands to a connector, the aforementioned connector is formed with a benzene ring at the center and linking two $\text{Ru}[1,2\text{-bis}(\text{diphenylphosphino})\text{ethane}]_2$ (hereinafter, abbreviated as $\text{Ru}(\text{dppe})_2$) via acetylene, while connecting phenyl groups to each of $\text{Ru}(\text{dppe})_2$ via acetylene, respectively, the aforementioned ligands are terpyridine groups and are formed by being connected to the phenyl groups of the aforementioned connector, and the aforementioned terpyridine groups are linked to a transition metal through a coordinate bond.

(12) The organic/multimetallic hybrid polymer according to (11), wherein the aforementioned transition metal is Fe, Zn, Co or Ru.

(13) The organic/multimetallic hybrid polymer according to (11) or (12), having a linear structure.

(14) The organic/multimetallic hybrid polymer according to (11) or (12), having a branched structure.

(15) The organic/multimetallic hybrid polymer according to (14), including a branched portion composed of 1,3,5-Tris[4-(2,2':6',2''-terpyridin-4'-yl)phenyl]benzene.

(16) The organic/multimetallic hybrid polymer according to (14) or (15), wherein a content of the aforementioned branched portion is at least 10 molar parts and not more than 30 molar parts.

(17) A method of synthesizing an organic/multimetallic hybrid polymer, the method including a step of synthesizing a binuclear organometallic site containing two $\text{Ru}(\text{dppe})_2$ by mixing and stirring 1 equivalent of diethynylbenzene and 2 equivalents of $\text{Ru}(\text{dppe})_2\text{Cl}(\text{OTf})$ in an organic solvent,

a step of synthesizing an organic metal ligand having a terpyridine group at the terminal and two $\text{Ru}(\text{dppe})_2$ by mixing and stirring 2 equivalents of terpyridine having an ethynyl group and one equivalent of a binuclear organometallic site in an organic solvent, and

a step of synthesizing a linear organic/multimetallic hybrid polymer by mixing and stirring the aforementioned organic metal ligand and a transition metal compound in an organic solvent.

(18) The method of synthesizing an organic/multimetallic hybrid polymer according to (17), including synthesizing a branched organic/multimetallic hybrid polymer by mixing and stirring of the aforementioned linear organic/multimetallic hybrid polymer together with a branched compound branched into three or more directions and having a ligand at the branched end, and a transition metal compound.

(19) The method of synthesizing an organic/multimetallic hybrid polymer according to (18), wherein the aforementioned branched compound is 1,3,5-Tris[4-(2,2':6',2''-terpyridin-4'-yl)phenyl]benzene.

(20) The method of synthesizing an organic/multimetallic hybrid polymer according to (18) or (19), wherein a mixing amount of the aforementioned branched compound is at least 10 molar parts and not more than 30 molar parts, relative to the linear organic/multimetallic hybrid polymer.

(21) The method of synthesizing an organic/multimetallic hybrid polymer according to (17), wherein 1.0 equivalent or more transition metal compound is used with respect to the aforementioned organic metal ligand.

(22) The method of synthesizing an organic/multimetallic hybrid polymer according to any one of (17) to (21), wherein the aforementioned transition metal compound is $\text{Fe}(\text{BF}_4)_2$ or $\text{Zn}(\text{NTf}_2)_2$.

(23) The method of synthesizing an organic/multimetallic hybrid polymer according to any one of (17) to (22), wherein a mixing and stirring time of the organic metal ligand and the transition metal compound is equal to or more than 6 hours.

(24) An organic/multimetallic hybrid polymer film, including the organic/multimetallic hybrid polymer according to any one of (11) to (16).

(25) The organic/multimetallic hybrid polymer film according to (24), wherein a film thickness is at least 100 nm and not more than 1 mm.

[Advantageous Effects of Invention]

[0025] The organic/heterometallic hybrid polymer of the present invention is composed of a plurality of organic metal complexes and a plurality of transition metals. In the organic/heterometallic hybrid polymer of the present invention, the

plurality of organic metal complexes are linked linearly by sandwiching each transition metal of the plurality of transition metals therebetween. The aforementioned organic metal complexes include two ligands each having a terpyridyl group and one connector having $\text{Ru}(\text{dppe})_2$ and two ethynylene groups, and are formed by linking the two ligands by the connector, so that a nitrogen atom at position 1' of the aforementioned terpyridyl group is directed toward the terminal side of the molecule of the organic metal complex. The terpyridyl groups of at least two different organic metal complexes of the plurality of organic metal complexes are bound to one transition metal through a coordinate bond, thereby linking the plurality of organic metal complexes while alternately and respectively sandwiching the plurality of transition metals therebetween. Therefore, it is possible to prepare a linear supramolecular polymer that links the organic metal complexes and the transition metals alternately and is capable of causing an electrochromic reaction.

[0026] The method of producing an organic/heterometallic hybrid polymer according to the present invention is configured to include a step of synthesizing an organic metal complex having a terpyridyl group at the terminal by reacting a terpyridine compound having an ethynyl group and a terpyridyl group with a compound containing $\text{Ru}(\text{dppe})_2$ in an organic solvent, and a step of synthesizing the organic/heterometallic hybrid polymer by reacting the aforementioned organic metal complex and a transition metal compound in an organic solvent. Therefore, it is possible to synthesize a linear supramolecular polymer with high yield that links the organic metal complexes and the transition metals alternately and is capable of causing an electrochromic reaction.

[0027] The organic/heterometallic hybrid polymer film according to the present invention is configured to include the organic/heterometallic hybrid polymer described earlier. Therefore, it can be made into a film capable of causing an electrochromic reaction and can be applied to an optical device. In particular, if it is configured so that a transition metal contained in the aforementioned organic/heterometallic hybrid polymer is Fe or Zn, it can be made into a film capable of causing an electrochromic reaction in the near infrared light region and can be applied to an optical device.

[0028] The organic/multimetallic hybrid polymer of the present invention includes a plurality of organic metal ligands and a plurality of transition metals. The organic/multimetallic hybrid polymer of the present invention has a linear portion in which the plurality of organic metal ligands are linked in a linear manner by sandwiching each transition metal of the plurality of transition metals therebetween, and the aforementioned organic metal ligands are formed by linking two ligands to one connector. The aforementioned connector is formed with a benzene ring at the center by linking two $\text{Ru}[1,2\text{-bis}(\text{diphenylphosphino})\text{ethane}]_2$ (sometimes abbreviated as $\text{Ru}(\text{dppe})_2$ in the present description) via two ethynylene groups bonded to the benzene ring, while connecting two phenyl groups to the aforementioned two $\text{Ru}(\text{dppe})_2$ via other ethynylene groups. The aforementioned ligands are terpyridyl groups and are connected respectively to the phenyl groups of the aforementioned connector. It is configured so that the aforementioned terpyridyl groups of at least two different organic metal ligands of the plurality of organic metal ligands are bound to one of the aforementioned transition metals through a coordinate bond, thereby linking the plurality of organic metal ligands by alternately sandwiching the plurality of transition metals therebetween. For this reason, it is possible to provide electrochromic properties in the infrared light region and increase the repetition stability.

[0029] The method of synthesizing an organic/multimetallic hybrid polymer according to the present invention is configured to include a step of synthesizing a binuclear organometallic site containing two $\text{Ru}(\text{dppe})_2$ by reacting 1 equivalent of diethynylbenzene and 2 equivalents of $\text{Ru}(\text{dppe})_2\text{Cl}(\text{OTf})$ in an organic solvent, a step of synthesizing an organic metal ligand having a terpyridyl group at the terminal and two $\text{Ru}(\text{dppe})_2$ by reacting 2 equivalents of a terpyridine compound having an ethynyl group and a terpyridyl group with 1 equivalent of a binuclear organometallic site in an organic solvent, and a step of synthesizing a linear organic/multimetallic hybrid polymer by reacting the aforementioned organic metal ligand and a transition metal compound in an organic solvent. For this reason, it is possible to synthesize an organic/multimetallic hybrid polymer exhibiting electrochromic properties in the infrared light region and high repetition stability with high yield.

[0030] Since the organic/multimetallic hybrid polymer film of the present invention is configured to include the organic/multimetallic hybrid polymer described earlier, it is possible to form a film exhibiting electrochromic properties in the infrared light region and high repetition stability. As a result, it can be applied to an optical device capable of light blocking by switching ON/OFF at two wavelengths within the near infrared to infrared region.

[Brief Description of Drawings]

[0031]

FIG. 1 is a diagram showing an example of an organic/heterometallic hybrid polymer according to an embodiment of the present invention.

FIG. 2 is a diagram showing an example of an organic metal complex.

FIG. 3 is a diagram showing an example of a redox reaction of the organic/heterometallic hybrid polymer according to an embodiment of the present invention.

FIG. 4 is a chemical reaction formula in a step of synthesizing the organic/heterometallic hybrid polymer.

FIG. 5 is a graph showing the titration test result in the ultraviolet and visible absorption spectrum.

FIG. 6 is a graph showing the relationship between the optical absorption change at 605 nm and the added amount.

FIG. 7 is a diagram comparing the ^1H -NMR measurement result of Ru(II)-M (organic metal complex 10) in chloroform and the ^1H -NMR measurement result of polyRuZn in dimethyl sulfoxide.

FIG. 8 is a graph showing a measurement result of SEC-RALLS-Viscometry.

FIG. 9A is a graph showing an electrochemical measurement result in a solution state by the cyclic voltammetry (CV) measurement.

FIG. 9B is a graph showing an electrochemical measurement results in a solution state by the differential pulse voltammetry (DPV) measurement.

FIG. 10A is a graph showing the applied voltage dependence of the ultraviolet/visible/near infrared absorption spectrum of polyRuRu in a solution state.

FIG. 10B is a graph showing the applied voltage dependence of the ultraviolet/visible/near infrared absorption spectrum of polyRuFe in a solution state.

FIG. 10C is a graph showing the applied voltage dependence of the ultraviolet/visible/near infrared absorption spectrum of polyRuZn in a solution state.

FIG. 11 is a perspective view showing an example of a working electrode. FIG. 12A is a graph showing the scan rate dependence of the CV measurement result of a polyRuZn film which is a graph showing measurement data.

FIG. 12B is a graph showing the scan rate dependence of the CV measurement result of a polyRuZn film which is a graph showing the relationship between the scan rate and the current value.

FIG. 13 is a graph showing an electric spectroscopy measurement result of polyRuZn in a film state, which shows the change in absorbance (Abs) before and after the voltage application.

FIG. 14 is a photograph showing the outer appearance of polyRuZn in a film state at the time when no voltage was applied (0 V) and when a voltage of 0.5 V was applied.

FIG. 15A is a graph showing a change in the physical property values of polyRuZn in a film state due to the on/off of a voltage, which is a change in the current value due to the on/off of a voltage.

FIG. 15B is a graph showing a change in the physical property values of polyRuZn in a film state due to the on/off of a voltage, which is a change in the light transmittance at a wavelength of 1,147 nm.

FIG. 16 is a graph showing a change in the light transmittance of polyRuZn in a film state at a wavelength of 1,147 nm due to the on/off of a voltage, when intervals for changing the voltage between 0 V and 0.5 V are set to 20 seconds.

FIG. 17 is a graph showing a change in the transmittance when the voltage was changed 600 times between 0 V and 0.5 V during 3,000 s, for an organic/heterometallic hybrid polymer (polyRuZn) film.

FIG. 18A is a diagram showing an example of an organic/multimetallic hybrid polymer film according to an embodiment of the present invention.

FIG. 18B is a diagram showing an example of an organic/multimetallic hybrid polymer film according to the present invention.

FIG. 19 is a diagram showing an example of an enlarged view of a portion B in FIG. 18A.

FIG. 20 is a diagram showing an example of a structural formula of a linear organic/multimetallic hybrid polymer constituting a portion C in FIG. 19.

FIG. 21 is a chemical formula showing an example of a linear organic/multimetallic hybrid polymer 5' according to an embodiment of the present invention.

FIG. 22 is an example of a chemical reaction formula for the synthesis of a binuclear organometallic site.

FIG. 23 is an example of a chemical reaction formula for the synthesis of an organic metal ligand.

FIG. 24 is an example of a chemical reaction formula for the synthesis of a linear organic/multimetallic hybrid polymer.

FIG. 25 is a diagram showing another example of an enlarged view of a portion B in FIG. 18A.

FIG. 26 is a diagram showing an example of a structural formula of a branched organic/multimetallic hybrid polymer constituting a portion D in FIG. 25.

FIG. 27 is a chemical formula showing an example of a branched organic/multimetallic hybrid polymer 6' according to an embodiment of the present invention.

FIG. 28 is a chemical reaction formula in a step of synthesizing the branched organic/multimetallic hybrid polymer.

FIG. 29 is a graph showing a TGA measurement result of poly(Ru₂Zn)₁₀₀, poly(Ru₂Zn)₉₀, poly(Ru₂Zn)₈₀ and poly(Ru₂Zn)₇₀.

FIG. 30A is an AFM image of a poly(Ru₂Zn)₁₀₀ film.

FIG. 30B is an AFM image of a poly(Ru₂Zn)₉₀ film.

FIG. 30C is an AFM image of a poly(Ru₂Zn)₈₀ film.

FIG. 30D is an AFM image of a poly(Ru₂Zn)₇₀ film.

FIG. 31 is a CV spectrum showing an electrochemical measurement result of a poly(Ru₂Zn)₇₀ film.

FIG. 32 is a CV spectrum showing the scan rate dependence of a poly(Ru₂Zn)₇₀ film.

FIG. 33 is a graph showing the relationship between the scan rate and the current value.

FIG. 34 is a graph showing spectroelectrochemical measurements of a poly(Ru₂Zn)₁₀₀ film, which shows the change in the ultraviolet/visible/near infrared absorption spectrum before and after the voltage application.

FIG. 35 is a graph showing spectroelectrochemical measurements of a poly(Ru₂Zn)₉₀ film, which shows the change in the ultraviolet/visible/near infrared absorption spectrum before and after the voltage application.

FIG. 36 is a graph showing spectroelectrochemical measurements of a poly(Ru₂Zn)₇₀ film, which shows the change in the ultraviolet/visible/near infrared absorption spectrum before and after the voltage application.

FIG. 37 is a graph showing the application interval dependence of the light transmittance change at 1,844 nm of a poly(Ru₂Zn)₇₀ film due to the on/off of voltage.

FIG. 38 is a graph showing the repetition characteristics of the light transmittance change at 1,844 nm of a poly(Ru₂Zn)₇₀ film due to the on/off of voltage.

FIG. 39 is a graph showing the application interval dependence of the light transmittance change at 1,174 nm of a poly(Ru₂Zn)₇₀ film due to the on/off of voltage.

FIG. 40 is a graph showing the repetition characteristics of the light transmittance change at 1,174 nm of a poly(Ru₂Zn)₇₀ film due to the on/off of voltage.

FIG. 41 is a graph showing the change in the current value of a poly(Ru₂Zn)₇₀ film due to the on/off of voltage by the change in the optical absorption at 1,844 nm.

FIG. 42 is a graph showing the change in the current value of a poly(Ru₂Zn)₇₀ film due to the on/off of voltage by the change in the optical absorption at 1,174 nm.

FIG. 43A is a graph showing the applied voltage dependence of the ultraviolet and visible absorption spectrum of an organic/multimetallic hybrid polymer (poly(Ru₂Zn)₇₀) film, when the applied voltage was changed from -0.20 V to 0.05 V in a stepwise manner.

FIG. 43B is a graph showing the applied voltage dependence of the ultraviolet and visible absorption spectrum of an organic/multimetallic hybrid polymer (poly(Ru₂Zn)₇₀) film, when the applied voltage was changed from 0.10 V to 0.40 V in a stepwise manner.

FIG. 44A is a graph showing the applied voltage dependence of the ultraviolet and visible absorption spectrum of an organic/multimetallic hybrid polymer (poly(Ru₂Zn)₇₀) film, when the applied voltage was changed from 0.05 V to -0.20 V in a stepwise manner.

FIG. 44B is a graph showing the applied voltage dependence of the ultraviolet and visible absorption spectrum of an organic/multimetallic hybrid polymer (poly(Ru₂Zn)₇₀) film, when the applied voltage was changed from 0.40 V to 0.10 V in a stepwise manner.

[Description of Embodiments]

(Organic/heterometallic hybrid polymer)

[0032] First, an organic/heterometallic hybrid polymer according to a first embodiment of the present invention will be described.

[0033] FIG. 1 is a diagram showing an example of a structural formula of the organic/heterometallic hybrid polymer according to the first embodiment of the present invention. In FIG. 1, n is an integer of 2 or more.

[0034] As shown in FIG. 1, an organic/heterometallic hybrid polymer 20 according to the first embodiment of the present invention is a supramolecular polymer having a plurality of organic metal complexes 10 are linked in a linear manner while sandwiching a transition metal M therebetween. The terpyridyl groups of at least two different organic metal complexes of the plurality of organic metal complexes 10 are bound to one transition metal M through a coordinate bond, thereby linking the plurality of organic metal complexes via the transition metal M. As shown in FIG. 1, the organic/heterometallic hybrid polymer 20 has a unit structure containing the organic metal complex 10 and the transition metal M (a structure enclosed in parentheses).

[0035] The transition metal M is any one of Ru, Fe or Zn. As a result, it is possible to efficiently link the organic metal complexes 10 and to form the organic/heterometallic hybrid polymer 20 which is linear.

[0036] A molecular weight M_w of the organic/heterometallic hybrid polymer 20 is preferably at least 10.5×10^4 and not more than 29.2×10^4 . As a result, it is possible to form a stable film. Here, the molecular weight of the supramolecular polymer refers to the average molecular weight per one polymer chain. The molecular weight can be measured by a SEC-RALLS-Viscometry method.

[0037] FIG. 2 is a diagram showing an example of an organic metal complex.

[0038] As shown in FIG. 2, in the organic metal complex 10, two ligands 11A and 11B having a terpyridyl group are linked by a single connector 13 having Ru(dppe)₂ and an ethynylene group, so that a nitrogen atom at position 1' of the aforementioned terpyridyl group is directed toward the terminal side of the molecule of the organic metal complex. In FIG. 2, the ligand is a 4-(2,2':6',2''-terpyridin-4'-yl) phenyl group. Here, the phenyl groups in the ligands 11A and 11B and the ethynylene groups in the connector 13 are connected.

[0039] FIG. 3 is a diagram showing an example of a redox reaction of the organic/heterometallic hybrid polymer according to an embodiment of the present invention.

[0040] By oxidizing the organic/heterometallic hybrid polymer 20 according to an embodiment of the present invention, Ru(II) is oxidized to Ru(III) to form an oxidized organic/heterometallic hybrid polymer 20OX in which anions in the electrolyte are in close proximity.

[0041] By selecting Fe or Zn as the transition metal M which is a dissimilar transition metal to Ru, it is possible to absorb near infrared light by the intervalence charge transfer (IVCT) between Ru(III) and Fe(II) or Ru(III) and Zn(II).

(Production method of organic/heterometallic hybrid polymer)

[0042] Next, an example of a method for producing an organic/heterometallic hybrid polymer according to an embodiment of the present invention will be described.

[0043] The method for producing an organic/heterometallic hybrid polymer according to the embodiment of the present invention includes an organic metal complex synthesis step S1 and an organic/heterometallic hybrid polymer synthesis step S2.

(Organic metal complex synthesis step S1)

[0044] In this step, a terpyridine compound having an ethynyl group and a terpyridyl group is reacted with a compound containing Ru(dppe)₂ in an organic solvent, thereby synthesizing an organic metal complex having Ru(dppe)₂ and a terpyridyl group at the terminal. As a reaction method, stirring and mixing can be employed.

[0045] Examples of the compound containing Ru(dppe)₂ include Ru(dppe)₂Cl(OTf).

[0046] Examples of the organic solvent include methylene chloride.

[0047] Examples of the additive include sodium hexafluorophosphate and triethylamine.

[0048] The reaction temperature is preferably from 10 to 40°C.

[0049] The reaction time is preferably from 2 to 36 hours.

[0050] As a post-treatment process after completion of the reaction, it is preferable to perform column chromatography.

[0051] Here, examples of the terpyridine compound include 4'-(4-ethynylphenyl)-2,2':6',2"-terpyridine.

(Organic/heterometallic hybrid polymer synthesis step S2)

[0052] In this step, the organic metal complex and a transition metal compound are reacted in an organic solvent, thereby synthesizing the organic/heterometallic hybrid polymer.

[0053] Examples of the organic solvent include ethylene glycol, ethanol, methanol, chloroform, NMP, dimethylformamide and dimethyl sulfoxide.

[0054] The reaction temperature is preferably from 60 to 140°C.

[0055] As a post-treatment process after completion of the reaction, it is preferable to perform filtration and washing.

[0056] FIG. 4 is a chemical reaction formula in the organic/heterometallic hybrid polymer synthesis step. The terpyridyl groups in the ligand form a complex with the transition metal M, thereby linking a plurality of organic metal complexes via the transition metal M in a linear manner.

[0057] It is preferable to react the transition metal compound in an amount from 1.0 molar equivalent or more to 1.1 molar equivalent or less, with respect to the aforementioned organic metal complex. As a result, the organic/heterometallic hybrid polymer can be synthesized with high yield.

[0058] The aforementioned transition metal compound is preferably any one of RuCl₂, Fe(BF₄)₂, or Zn(NTf₂)₂. As a result, it is possible to synthesize a polymer having a corresponding transition metal.

[0059] Zn(NTf₂)₂ is zinc di[bis(trifluoromethanesulfonyl)imide] (zinc di[(trifluoromethylsulfonyl)imide])).

[0060] The reaction time of the organic metal complex and the transition metal compound is preferably at least 12 hours and not more than 36 hours. As a result, the organic/heterometallic hybrid polymer can be synthesized with an increased yield of 90% or higher.

(Organic/heterometallic hybrid polymer film)

[0061] Next, an organic/heterometallic hybrid polymer film according to an embodiment of the present invention will be described.

[0062] The organic/heterometallic hybrid polymer film according to an embodiment of the present invention is made of the organic/heterometallic hybrid polymer according to an embodiment of the present invention. As a result, it can be made into a film capable of causing an electrochromic reaction and can be applied to an optical device.

[0063] The film thickness is preferably at least 100 nm and not more than 1 mm, and more preferably at least 100 nm

and not more than 400 nm. By ensuring that the film thickness is equal to or more than 100 nm, it is possible to stably retain the film. In addition, by ensuring that the film thickness is equal to or less than 1 mm, when used by being connected to the electrode, it is possible to increase the response speed of the electrochromic reaction with respect to the voltage control. It should be noted that the film thickness can be measured by observing the cross section with a scanning electron microscope.

[0064] It is preferred that the transition metal contained in the organic/heterometallic hybrid polymer is Fe or Zn. As a result, it is possible to cause an electrochromic reaction in the near infrared light region.

[0065] In the organic/heterometallic hybrid polymer film, a counter anion may be included as an optional component. Examples of the counter anion include a chloride ion, a tetrafluoroborate anion, a hexafluorophosphate anion, a bis(trifluoromethanesulfonyl)imide anion, a perchlorate ion, and an acetate ion.

[0066] The organic/heterometallic hybrid polymer film can be produced by dissolving an organic/heterometallic hybrid polymer in an organic solvent, and applying, and drying, the resultant onto a transparent electrode substrate.

[0067] Examples of the organic solvent include methanol, acetonitrile, dimethyl sulfoxide and dimethylformamide.

[0068] The organic/heterometallic hybrid polymer according to an embodiment of the present invention is a polymer in which a plurality of organic metal complexes are linked in a linear manner by sandwiching the transition metal therebetween. The aforementioned organic metal complex is formed by linking two ligands having a terpyridyl group by one connector having Ru(dppe)₂ and two ethynylene groups, so that a nitrogen atom at position 1' of the aforementioned terpyridyl group is directed toward the terminal side of the molecule of the organic metal complex. In addition, the terpyridyl groups of at least two different organic metal complexes of the plurality of organic metal complexes are bound to one transition metal through a coordinate bond, thereby linking the plurality of organic metal complexes by alternately sandwiching a plurality of transition metals therebetween. Therefore, it is possible to prepare a linear supramolecular polymer that links the organic metal complexes and the transition metals alternately and is capable of causing an electrochromic reaction.

[0069] The organic/heterometallic hybrid polymer according to an embodiment of the present invention may be configured so that the aforementioned transition metal is any one of Ru, Fe or Zn. As a result, it is possible to prepare a linear supramolecular polymer that links the organic metal complexes and the transition metals alternately and is capable of causing an electrochromic reaction.

[0070] The organic/heterometallic hybrid polymer according to an embodiment of the present invention may be configured so as to have a molecular weight M_w of at least 10.5×10^4 and not more than 29.2×10^4 . As a result, it is possible to form a stable film capable of causing an electrochromic reaction.

[0071] The method of producing an organic/heterometallic hybrid polymer according to an embodiment of the present invention is configured to include a step of synthesizing an organic metal complex having a terpyridyl group at the terminal by reacting a terpyridine compound having an ethynyl group and a terpyridyl group with a compound containing Ru(dppe)₂ in an organic solvent, and a step of synthesizing the organic/heterometallic hybrid polymer by reacting the aforementioned organic metal complex and a transition metal compound in an organic solvent. Therefore, it is possible to synthesize a linear supramolecular polymer with high yield that links the organic metal complexes and the transition metals alternately and is capable of causing an electrochromic reaction.

[0072] The method of producing an organic/heterometallic hybrid polymer according to an embodiment of the present invention may be configured so as to react 1.0 equivalent or more transition metal compound with respect to the aforementioned organic metal complex. As a result, it is possible to synthesize a linear supramolecular polymer with high yield that links the organic metal complexes and the transition metals alternately and is capable of causing an electrochromic reaction.

[0073] The method of producing an organic/heterometallic hybrid polymer according to an embodiment of the present invention may be configured so that the aforementioned transition metal compound is any one of RuCl₂, Fe(BF₄)₂, or Zn(NTf₂)₂. As a result, it is possible to synthesize a linear supramolecular polymer with high yield that links the organic metal complexes and the transition metals alternately and is capable of causing an electrochromic reaction.

[0074] The method of producing an organic/heterometallic hybrid polymer according to an embodiment of the present invention may be configured so that a reaction time of the organic metal complex and the transition metal compound is equal to or more than 12 hours. As a result, it is possible to synthesize a linear supramolecular polymer with high yield that links the organic metal complexes and the transition metals alternately and is capable of causing an electrochromic reaction.

[0075] The organic/heterometallic hybrid polymer film according to an embodiment of the present invention is configured to include the organic/heterometallic hybrid polymer described earlier. Therefore, it can be made into a film capable of causing an electrochromic reaction and can be applied to an optical device.

[0076] The organic/heterometallic hybrid polymer film according to an embodiment of the present invention may be configured so that the film thickness is at least 100 nm and not more than 1 mm. As a result, it is possible to stably retain the film and increase the response speed of the electrochromic reaction.

[0077] The organic/heterometallic hybrid polymer film according to an embodiment of the present invention may be

configured so that a transition metal contained in the aforementioned organic/heterometallic hybrid polymer is a transition metal of Fe or Zn. As a result, it can be made into a film capable of causing an electrochromic reaction in the near infrared light region and can be applied to an optical device.

(Film of linear organic/multimetallic hybrid polymer)

[0078] First, a film of a linear organic/multimetallic hybrid polymer according to a second embodiment of the present invention will be described.

[0079] FIGS. 18A and 18B are diagrams showing an example of a linear organic/multimetallic hybrid polymer film according to a second embodiment of the present invention.

[0080] A linear organic/multimetallic hybrid polymer film 1' according to the second embodiment of the present invention is formed in a substantially rectangular shape in plan view on a transparent conductive film 51' of a glass substrate 50'. The plan view shape is not limited thereto. Also, it is not limited to the above embodiment to be formed on the transparent conductive film 51'. As the transparent conductive film 51', an ITO film or the like can be used.

[0081] The thickness of the linear organic/multimetallic hybrid polymer film is preferably at least 100 nm and not more than 1 mm, and more preferably at least 100 nm and not more than 400 nm. By ensuring that the film thickness is equal to or more than 100 nm, it is possible to stably retain the film. In addition, by ensuring that the film thickness is equal to or less than 1 mm, when used by being connected to the electrode, it is possible to increase the response speed of the electrochromic reaction with respect to the voltage control.

[0082] FIG. 19 is a diagram showing an example of an enlarged view of a portion B in FIG. 18A.

[0083] As shown in FIG. 19, a film 1' of a linear organic/multimetallic hybrid polymer according to an embodiment of the present invention is formed by mixing the linear organic/multimetallic hybrid polymer 5' according to an embodiment of the present invention in a mesh shape.

[0084] The film of the linear organic/multimetallic hybrid polymer film can be produced by dissolving a linear organic/multimetallic hybrid polymer in an organic solvent, and applying, and drying, the resultant onto a transparent electrode substrate.

[0085] Examples of the organic solvent include methanol, acetonitrile, dimethyl sulfoxide and dimethylformamide.

(Linear organic/multimetallic hybrid polymer)

[0086] Next, a linear organic/multimetallic hybrid polymer according to a second embodiment of the present invention will be described.

[0087] FIG. 20 is a diagram showing an example of a structural formula of a linear organic/multimetallic hybrid polymer constituting a portion C in FIG. 19.

[0088] As shown in FIG. 20, the linear organic/multimetallic hybrid polymer 5' according to an embodiment of the present invention is a linear supramolecular polymer. More specifically, the linear organic/multimetallic hybrid polymer 5' according to an embodiment of the present invention is schematically configured to include only a linear portion 31' in which organic metal ligands 21' are linearly linked while sandwiching the transition metals M' therebetween.

[0089] The organic metal ligand 21' is formed by linking a connector 13' with ligands 11'A and 11'B.

[0090] The connector 13' is formed with a benzene ring at the center by linking two Ru(dppe)₂ via two ethynylene groups bonded to the benzene ring, while respectively connecting other ethynylene groups to each Ru(dppe)₂ and connecting phenyl groups to the ethynylene groups.

[0091] The ligands 11'A and 11'B are terpyridyl groups and are formed by connecting 4' position of the terpyridyl group to the para position of the phenyl group at both ends of the terminal of the connector 13'.

[0092] The aforementioned terpyridyl group forms a coordinate bond with the transition metal M' to connect a plurality of organic metal ligands 21'.

[0093] FIG. 21 is a chemical formula showing an example of a linear organic/multimetallic hybrid polymer 5' according to an embodiment of the present invention.

[0094] As shown in FIG. 21, the linear organic/multimetallic hybrid polymer 5' according to an embodiment of the present invention is denoted as a plurality of organic metals poly(Ru₂Zn)_X. X represents the proportion of linear portions (mol%) when the sum of the linear portions and branched portions constituting the organic/multimetallic hybrid polymer is defined as 100 mol%. In FIG. 21, since the organic/multimetallic hybrid polymer is linear, X = 100. In other words, it represents poly(Ru₂Zn)₁₀₀. In FIG. 21, n is a natural number of 2 or more. As shown in FIG. 21, the linear organic/multimetallic hybrid polymer 5' includes a unit structure derived from the linear portion, i.e., a unit structure containing the organic metal ligand 21' and the transition metal M' (a structure enclosed in parentheses).

[0095] By oxidizing the linear organic/multimetallic hybrid polymer 5' according to an embodiment of the present invention, Ru(II) is oxidized to Ru(III) to form an oxidized organic/multimetallic hybrid polymer in which anions in the electrolyte are in close proximity.

[0096] Examples of the transition metal M' include Fe, Zn, Co, or Ru. As a result, it is possible to absorb near infrared light and to cause an electrochromic reaction in the near infrared light region by the intervalence charge transfer (IVCT) between Ru(III) and Fe(II) or Ru(III) and Zn(II).

[0097] Since the linear organic/multimetallic hybrid polymer 5' according to an embodiment of the present invention is configured so that not only hetero transition metals Zn and Ru are closely arranged, but also the same transition metals Ru and Ru are closely arranged, for example, not only the absorption of IVCT between hetero metals Zn-Ru, but also the absorption of IVCT between the same metals Ru-Ru are observed. As a result, it can be made into a film capable of causing an electrochromic reaction at two wavelengths within the near infrared to infrared region. In addition, it is possible to reduce the absorbance at one absorption peak wavelength while increasing the absorbance at the other absorption peak wavelength, and vice versa, by the ON/OFF of the voltage application, and to block the light by switching ON/OFF at two wavelengths within the near infrared to infrared region.

(Synthesis method of linear organic/multimetallic hybrid polymer)

[0098] Next, a method for synthesizing a linear organic/multimetallic hybrid polymer according to an embodiment of the present invention will be described.

[0099] The method for producing a linear organic/multimetallic hybrid polymer according to an embodiment of the present invention includes a binuclear organometallic site synthesis step S1, an organic metal ligand synthesis step S2 and a linear organic/multimetallic hybrid polymer synthesis step S3.

(Binuclear organometallic site synthesis step S1)

[0100] FIG. 22 represents a chemical reaction formula for the synthesis of a binuclear organometallic site.

[0101] First, a diethynylbenzene and $\text{Ru}(\text{dppe})_2\text{Cl}(\text{OTf})$ are reacted in an organic solvent.

[0102] Examples of the organic solvent include methylene chloride, chloroform, carbon tetrachloride and chlorobenzene. Among them, methylene chloride and chloroform are preferred.

[0103] The reaction temperature is preferably from room temperature to 80°C, and more preferably from room temperature to 40°C.

[0104] The reaction time is preferably from 24 to 72 hours, and more preferably from 24 to 48 hours.

[0105] Then, the resulting precipitate is collected by filtration and washed with an organic solvent (for example, cold methylene chloride), followed by drying to obtain $[\text{ClRu}(\text{II})(\text{dppe})_2=\text{C}=\text{CH}-\text{Ph}-\text{CH}=\text{C}=(\text{dppe})_2\text{Ru}(\text{II})\text{Cl}](\text{OTf})_2$ which is a salt of $\text{Ru}(\text{II})(\text{dppe})_2=\text{C}=\text{CH}-\text{C}_6\text{H}_4-\text{HC}=\text{C}=\text{Ru}(\text{II})(\text{dppe})_2\text{Cl}_2$. This is the binuclear organometallic site.

(Organic metal ligand synthesis step S2)

[0106] FIG. 23 represents a chemical reaction formula for the synthesis of an organic metal ligand.

[0107] In an organic solvent, a terpyridine compound having an ethynyl group and a terpyridyl group is reacted with $[\text{ClRu}(\text{II})(\text{dppe})_2=\text{C}=\text{CH}-\text{Ph}-\text{CH}=\text{C}=(\text{dppe})_2\text{Ru}(\text{II})\text{Cl}](\text{OTf})_2$ in a nitrogen atmosphere under the presence of a base and an inorganic salt.

[0108] Here, examples of the terpyridine compound include 4'-(4-ethynylphenyl)-2,2':6',2''-terpyridine.

[0109] Examples of the organic solvent include methylene chloride, chloroform, carbon tetrachloride and chlorobenzene. Among them, methylene chloride and chloroform are preferred.

[0110] Examples of the base include triethylamine, tripropylamine, tributylamine, trihexylamine and dimethylaniline. Among them, triethylamine is preferred.

[0111] Examples of the inorganic salt include sodium hexafluorophosphate, lithium hexafluorophosphate, ammonium hexafluorophosphate, sodium tetrafluoroborate, sodium perchlorate, and ammonium perchlorate. Among them, sodium hexafluorophosphate is preferred.

[0112] The reaction time is preferably from 1 to 14 days, and more preferably from 5 to 9 days.

[0113] The reaction temperature is preferably from 10 to 60°C, and more preferably from room temperature to 40°C.

[0114] Then, a poor solvent is added to the reaction solution for precipitation, followed by filtration to wash the resulting solid with the poor solvent, thereby synthesizing an organic metal ligand ($\text{L}-\text{Ru}(\text{II})_2-\text{L}$) having a terpyridyl group at the terminal and including two $\text{Ru}(\text{dppe})_2$.

[0115] Examples of the poor solvent include diethyl ether and acetone. Among them, diethyl ether is preferred.

(Linear organic/multimetallic hybrid polymer synthesis step S3)

[0116] FIG. 24 represents a chemical reaction formula for the synthesis of a linear organic/multimetallic hybrid polymer.

[0117] In this step, the organic metal ligand ($\text{L}-\text{Ru}(\text{II})_2-\text{L}$) and a transition metal compound (for example, $\text{Zn}(\text{NTf}_2)_2$)

are reacted in an organic solvent to synthesize a linear organic/multimetallic hybrid polymer (poly(Ru₂Zn)X, X = 100) composed only of linear portions.

[0118] It is preferable to react 1.0 molar equivalent to 2.0 molar equivalents of the transition metal compound, with respect to the aforementioned organic metal ligand.

As a result, the linear organic/multimetallic hybrid polymer can be synthesized with high yield.

[0119] In FIG. 24, the degree of polymerization (the number of n) can be adjusted by changing the number of molar equivalents of the transition metal compound to be added, with respect to the organic metal ligand. That is, when 1.0 molar equivalent of the transition metal compound is reacted with respect to the aforementioned organic metal ligand, the degree of polymerization (n) is increased, and the degree of polymerization (n) becomes smaller as the number of molar equivalents of the transition metal compound to be reacted is increased.

[0120] As the aforementioned transition metal compound, in addition to Zn(NTf₂)₂, Zn(BF₄)₂, Zn(OAc)₂, ZnCl₂, and the like can be employed. Among them, Zn(NTf₂)₂ is preferred.

[0121] Zn(NTf₂)₂ is zinc di[bis(trifluoromethanesulfonyl)imide] (zinc di[(trifluoromethylsulfonyl)imide]).

[0122] In addition, as the aforementioned transition metal compound, Fe(BF₄)₂, Fe(OAc)₂, and FeCl₂ can also be used. As a result, it is possible to synthesize a polymer containing Fe.

[0123] The reaction time of the organic metal ligand and the transition metal compound is preferably from 3 to 24 hours, and more preferably from 6 to 12 hours. As a result, the linear organic/multimetallic hybrid polymer can be synthesized with an increased yield of 80% or higher.

[0124] As the organic solvent, NMP, dimethylformamide, dimethyl sulfoxide, chlorobenzene and propylene carbonate are preferred, and among these, NMP and dimethylformamide are more preferred.

[0125] The reaction temperature is preferably from 80 to 160°C, and more preferably from 100 to 120°C.

[0126] As a post-treatment process after completion of the reaction, it is preferable to perform precipitation in a poor solvent and filtration, followed by washing with a poor solvent.

[0127] Examples of the poor solvent include diethyl ether, acetone, methylene chloride, chloroform and water. Among them, diethyl ether, chloroform and water are preferred.

(Film of branched organic/multimetallic hybrid polymer)

[0128] Next, a film of a branched organic/multimetallic hybrid polymer according to an embodiment of the present invention will be described.

[0129] FIG. 25 is a diagram showing another example of an enlarged view of a portion B in FIG. 18A.

[0130] As shown in FIG. 25, a film 2' of a branched organic/multimetallic hybrid polymer according to an embodiment of the present invention may be configured so as to be formed by mixing the branched organic/multimetallic hybrid polymer 6' according to an embodiment of the present invention in a mesh shape.

[0131] The branched organic/multimetallic hybrid polymer 6' has a branched portion 41' linking the linear portion with 2 or more different linear portions and branching into three or more directions, and can form a mesh structure more firmly. As a result, the heat resistance improves, and the stability of the film is increased.

[0132] The film of the branched organic/multimetallic hybrid polymer can be produced by dissolving a branched organic/multimetallic hybrid polymer in an organic solvent, and applying, and drying, the resultant onto a transparent electrode substrate.

[0133] Examples of the organic solvent include heated dimethyl sulfoxide, heated dimethylformamide, and heated chlorobenzene.

(Branched organic/multimetallic hybrid polymer)

[0134] Next, a branched organic/multimetallic hybrid polymer according to an embodiment of the present invention will be described.

[0135] FIG. 26 is a diagram showing an example of a structural formula of a branched organic/multimetallic hybrid polymer constituting a portion D in FIG. 25.

[0136] As shown in FIG. 26, the branched organic/multimetallic hybrid polymer 6' according to an embodiment of the present invention is a branched supramolecular polymer. More specifically, the branched organic/multimetallic hybrid polymer 6' according to an embodiment of the present invention is schematically configured to include not only a linear portion 31' in which organic metal ligands 21' are linearly linked while sandwiching the transition metals M' therebetween, but also a branched portion 41' which connects the linear portion 31' with two different linear portions (31'), (31').

[0137] The branched portion 41' is formed by linking a ligand 11'C to a branch element (triphenylbenzene) 15', has a structure branched into three or more directions with the branch element at the center, and has ligands at the branched ends. As a result, it is possible to prepare an organic/multimetallic hybrid polymer branched in three or more directions and in which the linear portion is linked to two or more different linear portions.

[0138] The organic metal ligand 21' is configured to have the same configuration as shown in the description of the linear organic/multimetallic hybrid polymer according to an embodiment of the present invention. That is, the organic metal ligand is formed by linking one connector 13' with two ligands 11'A and 11'B. The connector 13' is formed with a benzene ring at the center by linking two $\text{Ru}(\text{dppe})_2$ via two ethynylene groups bonded to the benzene ring, while respectively coupling other ethynylene groups to each $\text{Ru}(\text{dppe})_2$ and respectively connecting phenyl groups to the ethynylene groups. The ligands 11'A and 11'B are terpyridyl groups and 4' position of the terpyridyl group is connected to the para position of the phenyl group at both ends of the terminal of the connector 13'. The aforementioned terpyridyl groups of at least two different organic metal ligands 21' of the plurality of organic metal ligands 21' are bound to one transition metal M' through a coordinate bond, thereby linearly linking the plurality of organic metal ligands 21' by alternately sandwiching the plurality of transition metals M' therebetween.

[0139] FIG. 27 is a chemical formula showing an example of a branched organic/multimetallic hybrid polymer 6' according to an embodiment of the present invention.

[0140] As shown in FIG. 27, the branched organic/multimetallic hybrid polymer 6' according to an embodiment of the present invention is denoted as $\text{poly}(\text{Ru}_2\text{Zn})_X$, where X is $70 \leq X < 100$. In FIG. 27, n and m are natural numbers of 2 or more. n corresponds to a linear moiety, whereas m corresponds to a branched moiety. Therefore, X , n , and m are associated by the formula: $X = 100n / (n + m)$.

[0141] Examples thereof include $\text{poly}(\text{Ru}_2\text{Zn})_{90}$, $\text{poly}(\text{Ru}_2\text{Zn})_{80}$, $\text{poly}(\text{Ru}_2\text{Zn})_{70}$, and the like. As shown in FIG. 27, the branched organic/multimetallic hybrid polymer 6' includes a unit structure derived from the linear portion, (i.e., a unit structure containing the organic metal ligand 21' and the transition metal M'), and a unit structure derived from the branched portion.

[0142] By oxidizing the branched organic/multimetallic hybrid polymer 6' according to an embodiment of the present invention, $\text{Ru}(\text{II})$ is oxidized to $\text{Ru}(\text{III})$ to form an oxidized organic/multimetallic hybrid polymer in which anions in the electrolyte are in close proximity.

[0143] Examples of the transition metal M include Fe or Zn. As a result, it is possible to absorb near infrared light and to cause an electrochromic reaction in the near infrared light region by the intervalence charge transfer (IVCT) between $\text{Ru}(\text{III})$ and $\text{Fe}(\text{II})$ or $\text{Ru}(\text{III})$ and $\text{Zn}(\text{II})$.

[0144] Since the branched organic/multimetallic hybrid polymer 6' according to an embodiment of the present invention is configured so that not only hetero transition metals Zn and Ru are closely arranged, but also the same transition metals Ru and Ru are closely arranged, for example, not only the absorption of IVCT between hetero metals Zn-Ru, but also the absorption of IVCT between the same metals Ru-Ru are observed. As a result, it can be made into a film capable of causing an electrochromic reaction at two wavelengths within the near infrared to infrared region. In addition, it is possible to reduce the absorbance at one absorption peak wavelength while increasing the absorbance at the other absorption peak wavelength, and vice versa, by the ON/OFF of the voltage application, and to block the light by switching ON/OFF at two wavelengths within the near infrared to infrared region.

(Synthesis method of branched organic/multimetallic hybrid polymer)

[0145] Next, a method for synthesizing a branched organic/multimetallic hybrid polymer according to an embodiment of the present invention will be described.

[0146] The method for producing a branched organic/multimetallic hybrid polymer according to an embodiment of the present invention includes a binuclear organometallic site synthesis step S1, an organic metal ligand synthesis step S2, a linear organic/multimetallic hybrid polymer synthesis step S3, and a branched organic/multimetallic hybrid polymer synthesis step S4.

(Binuclear organometallic site synthesis step S1)

[0147] A binuclear organometallic site is synthesized in the same manner as in the binuclear organometallic site synthesis step S1 described in the method for producing a linear organic/multimetallic hybrid polymer according to an embodiment of the present invention.

(Organic metal ligand synthesis step S2)

[0148] An organic metal ligand is synthesized in the same manner as in the organic metal ligand synthesis step S2 described in the method for producing a linear organic/multimetallic hybrid polymer according to an embodiment of the present invention.

(Linear organic/multimetallic hybrid polymer synthesis step S3)

[0149] A linear organic/multimetallic hybrid polymer is synthesized in the same manner as in the linear organic/multimetallic hybrid polymer synthesis step S3 of the method for producing a linear organic/multimetallic hybrid polymer according to an embodiment of the present invention.

(Branched organic/multimetallic hybrid polymer synthesis step S4)

[0150] FIG. 28 is a chemical reaction formula in a step of synthesizing the branched organic/multimetallic hybrid polymer.

[0151] In this step, the branched organic/multimetallic hybrid polymer is synthesized by reacting the linear organic/multimetallic hybrid polymer 5', a transition metal compound (for example, $\text{Zn}(\text{NTf}_2)_2$) and a branched compound connectable in three directions (for example, 1,3,5-Tris[4-(2,2':6',2''-terpyridin-4'-yl)phenyl]benzene) in an organic solvent (for example, NMP).

[0152] The mixing amount of the transition metal compound (for example, $\text{Zn}(\text{NTf}_2)_2$) may be at least 10 molar parts and not more than 60 molar parts, with respect to the combined total of 100 molar parts of the same type of the transition metal constituting the linear organic/multimetallic hybrid polymer (for example, refers to Zn in the case of mixing $\text{Zn}(\text{NTf}_2)_2$) and the transition metal to be mixed (for example, refers to Zn in the case of mixing $\text{Zn}(\text{NTf}_2)_2$). Of the various possibilities, the mixing amount is preferably at least 10 molar parts and not more than 30 molar parts.

[0153] As the aforementioned transition metal compound, in addition to $\text{Zn}(\text{NTf}_2)_2$, $\text{Zn}(\text{BF}_4)_2$, $\text{Zn}(\text{OAc})_2$, ZnCl_2 , and the like can be employed. Among them, $\text{Zn}(\text{NTf}_2)_2$ is preferred.

[0154] In addition, as the aforementioned transition metal compound, $\text{Fe}(\text{BF}_4)_2$, $\text{Fe}(\text{OAc})_2$, and FeCl_2 can also be used. As a result, it is possible to synthesize a polymer containing Fe in the branched portion.

[0155] The reaction time of the organic metal ligand and the transition metal compound is preferably from 6 to 48 hours, and more preferably from 12 to 24 hours. As a result, the branched organic/multimetallic hybrid polymer can be synthesized with an increased yield of 80% or higher.

[0156] Examples of the organic solvent include NMP: N-Methyl-pyrrolidone, dimethylformamide, dimethyl sulfoxide, chlorobenzene and propylene carbonate. Among them, NMP and dimethylformamide are preferred.

[0157] The reaction temperature is preferably from 80 to 150°C, and more preferably from 100 to 120°C.

[0158] The branched compound is branched into three or more directions with the branch element at the center, and has ligands at the ends of the branched molecule. Examples of the branched compound include 1,3,5-Tris[4-(2,2':6',2''-terpyridin-4'-yl)phenyl]benzene (hereinafter, sometimes referred to as "3D-M"), and the like.

[0159] As the branch element, triphenylmethane can be used other than triphenyl benzene. In addition, tetraphenylmethane which is a branched compound branched in four or more directions may also be used.

[0160] The mixing amount of the branched compound is preferably at least 10 molar parts and not more than 30 molar parts, relative to the combined total of 100 molar parts of the linear portion and the branched compound constituting the linear organic/multimetallic hybrid polymer.

[0161] The linear organic/multimetallic hybrid polymer 5' or branched organic/multimetallic hybrid polymer 6' according to an embodiment of the present invention includes a linear portion 31' in which organic metal ligands 21' are linearly linked while sandwiching the transition metals M' therebetween. The organic metal ligand 21' is formed by linking a connector 13' with ligands 11'A and 11'B. In the connector 13', with a benzene ring at the center, two $\text{Ru}(\text{dppe})_2$ are linked via two ethynylene groups bonded to the benzene ring, other ethynylene groups are respectively bonded to each $\text{Ru}(\text{dppe})_2$, and phenyl groups are respectively connected to the ethynylene groups. The ligands 11'A and 11'B are terpyridyl groups and connected to the phenyl groups of the connector 13'. It is configured so that the aforementioned terpyridyl groups of at least two different organic metal ligands 21' of the plurality of organic metal ligands 21' are bound to one transition metal M' through a coordinate bond, thereby linking the plurality of organic metal ligands 21' by alternately sandwiching the plurality of transition metals M' therebetween. For this reason, it is possible to prepare a linear or branched polymer, enhance the film stability, provide electrochromic properties in the infrared light region and increase the repetition stability.

[0162] The linear organic/multimetallic hybrid polymer 5' or branched organic/multimetallic hybrid polymer 6' according to an embodiment of the present invention may be configured so that the transition metal M is Fe, Zn, Co or Ru. As a result, it is possible to enhance the film stability by making the linear portion into a long chain, provide electrochromic properties in the infrared light region and increase the repetition stability.

[0163] The linear organic/multimetallic hybrid polymer 5' according to an embodiment of the present invention may be configured so as to be linear. As a result, it is possible to provide electrochromic properties in the infrared light region and increase the repetition stability.

[0164] The branched organic/multimetallic hybrid polymer 6' according to an embodiment of the present invention may be configured so as to be branched. As a result, it is possible to increase the film stability and increase the repetition

stability.

[0165] The branched organic/multimetallic hybrid polymer 6' according to an embodiment of the present invention may be configured to have a branched portion 41' composed of 1,3,5-Tris[4-(2,2':6',2"-terpyridin-4'-yl)phenyl]benzene. As a result, it is possible to link the linear portion with two or more different linear portions so as to branch into three or more directions, increase the film stability and increase the repetition stability.

[0166] The branched organic/multimetallic hybrid polymer 6' according to an embodiment of the present invention may be configured so that the content of the branched portion 41' is at least 10 molar parts and not more than 30 molar parts, relative to the total number of moles of the linear portions and branched portions constituting the organic/multimetallic hybrid polymer. As a result, it is possible to increase the film stability and increase the repetition stability.

[0167] The method of synthesizing the linear organic/multimetallic hybrid polymer 5' or branched organic/multimetallic hybrid polymer 6' according to an embodiment of the present invention is configured to include a step S1 of synthesizing a binuclear organometallic site containing two Ru(dppe)₂ by reacting 1 equivalent of diethynylbenzene and 2 equivalents of Ru(dppe)₂Cl(OTf) in an organic solvent, a step S2 of synthesizing an organic metal ligand having a terpyridyl group at the terminal and two Ru(dppe)₂ by reacting 2 equivalents of a terpyridine compound having an ethynyl group and a terpyridyl group with 1 equivalent of a binuclear organometallic site in an organic solvent, and a step S3 of synthesizing a linear organic/multimetallic hybrid polymer by reacting the aforementioned organic metal ligand and a transition metal compound in an organic solvent. For this reason, it is possible to synthesize an organic/multimetallic hybrid polymer exhibiting electrochromic properties in the infrared light region and high repetition stability with high yield.

[0168] The method of synthesizing the branched organic/multimetallic hybrid polymer 6' according to an embodiment of the present invention is configured to synthesize a branched organic/multimetallic hybrid polymer by reacting the aforementioned linear organic/multimetallic hybrid polymer, a branched compound branched into three or more directions with a branch element at the center and having a ligand at the end of the branched molecule, and a transition metal compound. For this reason, it is possible to synthesize a branched organic/multimetallic hybrid polymer exhibiting electrochromic properties in the infrared light region and high repetition stability with high yield.

[0169] The method of synthesizing the branched organic/multimetallic hybrid polymer 6' according to an embodiment of the present invention may be configured so that the aforementioned branched compound is 1,3,5-Tris[4-(2,2':6',2"-terpyridin-4'-yl)phenyl]benzene. As a result, it is possible to synthesize a branched organic/multimetallic hybrid polymer exhibiting electrochromic properties in the infrared light region and high repetition stability with high yield.

[0170] The method of synthesizing the branched organic/multimetallic hybrid polymer 6' according to an embodiment of the present invention may be configured so that a mixing amount of the aforementioned branched compound is at least 10 molar parts and not more than 30 molar parts, relative to the combined total of 100 molar parts of the linear portions constituting the linear organic/multimetallic hybrid polymer. As a result, it is possible to synthesize a branched organic/multimetallic hybrid polymer exhibiting electrochromic properties in the infrared light region and high repetition stability with high yield.

[0171] The method of synthesizing the linear organic/multimetallic hybrid polymer 5' or branched organic/multimetallic hybrid polymer 6' according to an embodiment of the present invention may be configured so as to react 1.0 equivalent or more transition metal compound with respect to the aforementioned organic metal ligand. As a result, it is possible to synthesize an organic/multimetallic hybrid polymer exhibiting electrochromic properties in the infrared light region and high repetition stability with high yield.

[0172] The method of synthesizing the linear organic/multimetallic hybrid polymer 5' or branched organic/multimetallic hybrid polymer 6' according to an embodiment of the present invention may be configured so that the aforementioned transition metal compound is Fe(BF₄)₂ or Zn(NTf₂)₂. As a result, it is possible to synthesize an organic/multimetallic hybrid polymer exhibiting electrochromic properties in the infrared light region and high repetition stability with high yield.

[0173] The method of synthesizing the linear organic/multimetallic hybrid polymer 5' or branched organic/multimetallic hybrid polymer 6' according to an embodiment of the present invention may be configured so that a reaction time of the organic metal ligand and the transition metal compound is equal to or more than 6 hours. As a result, it is possible to synthesize an organic/multimetallic hybrid polymer exhibiting electrochromic properties in the infrared light region and high repetition stability with high yield.

[0174] A film 1' of a linear organic/multimetallic hybrid polymer or film 2' of a branched organic/multimetallic hybrid polymer according to an embodiment of the present invention is configured to include the linear organic/multimetallic hybrid polymer 5' or branched organic/multimetallic hybrid polymer 6'. For this reason, it is possible to form a film exhibiting electrochromic properties in the infrared light region and high repetition stability. As a result, it can be applied to an optical device capable of light blocking by switching ON/OFF at two wavelengths within the near infrared to infrared region.

[0175] The film 1' of a linear organic/multimetallic hybrid polymer or film 2' of a branched organic/multimetallic hybrid polymer according to an embodiment of the present invention may be configured so that the film thickness is at least 100 nm and not more than 1 mm. As a result, it is possible to form a film exhibiting electrochromic properties in the infrared light region and high repetition stability. As a result, it can be applied to an optical device capable of light blocking by switching ON/OFF at two wavelengths within the near infrared to infrared region.

[Examples]

[0176] An organic/heterometallic hybrid polymer, a method for producing the same, and an organic/heterometallic hybrid polymer film according to embodiments of the present invention are not limited to the above embodiments, and can be implemented with various modifications within the technical scope of the present invention. Specific examples of the present invention are shown in the following Examples. However, the present invention is not limited to these Examples.

[0177] An organic/multimetallic hybrid polymer, a method for producing the same, and an organic/multimetallic hybrid polymer film according to embodiments of the present invention are not limited to the above embodiments, and can be implemented with various modifications within the technical scope of the present invention. Specific examples of the present invention are shown in the following Examples. However, the present invention is not limited to these Examples.

(Example 1)

[0178] First, a terpyridine compound having an ethynyl group and a terpyridyl group (4'-(4-ethynylphenyl)-2,2':6',2''-terpyridine) (100 mg) and Ru(dppe)₂Cl(OTf) (153.6 mg) were stirred for 24 hours at room temperature in methylene chloride (20 mL) in the presence of sodium hexafluorophosphate (126 mg) and triethylamine (110 μL). After completion of the reaction, the resultant was filtered, and the resulting filtrate was concentrated. Then, the resulting solid was washed with diethyl ether and then purified by column chromatography on alumina to synthesize an organic metal complex 10 having a terpyridyl group at the terminal (283 mg, yield: 55.5%).

[0179] Then, ¹H- and ¹³C-NMR, and MS spectra measurements were performed to confirm the structure of the organic metal complex 10.

[0180] Then, a methanol solution obtained by dispersing 0.1 equivalents of Fe(BF₄)₂ was added to a 10 μM chloroform solution of the organic metal complex 10 in a stepwise manner to carry out a titration test of the organic metal complex 10 in the ultraviolet and visible absorption spectrum.

[0181] FIG. 5 is a graph showing the titration test result in the ultraviolet and visible absorption spectrum. Further, FIG. 6 is a graph showing the relationship between the absorbance change at 605 nm and the added amount in FIG. 5.

[0182] As shown in FIGS. 5 and 6, when Fe(BF₄)₂ was added to the organic metal complex 10, characteristic metal-to-ligand charge transfer (MLCT) absorption appeared in the vicinity of 605 nm, and the absorbance increased as the amount added increased and the absorbance became constant when the amount reached 1.0 equivalent or more.

[0183] The titration test results in the ultraviolet and visible absorption spectrum indicated that the organic metal complex 10 formed a complex with 1.0 equivalent of a transition metal, thereby forming an organic/heterometallic hybrid polymer (polyRuFe).

[0184] A methanol solution obtained by dispersing 1.0 molar equivalent of Fe(BF₄)₂ was added to the chloroform solution of the organic metal complex 10 in a stepwise manner, and the resulting mixture was stirred for 12 hours under reflux at about 60°C, thereby obtaining an organic/heterometallic hybrid polymer (polyRuFe) with a yield of 94%.

[0185] The obtained polyRuFe dissolved in dimethyl sulfoxide, dimethylformamide, acetonitrile and methylene chloride.

(Example 2)

[0186] An organic/heterometallic hybrid polymer (polyRuRu) was obtained in the same manner as in Example 1 at a yield of 92%, with the exception that 1.0 molar equivalent of RuCl₂ was added to an ethylene glycol solution of the organic metal complex 10, and the resulting mixture was stirred for 24 hours at 120°C.

[0187] The obtained polyRuRu dissolved in dimethyl sulfoxide, dimethylformamide, acetonitrile and methylene chloride.

(Example 3)

[0188] An organic/heterometallic hybrid polymer (polyRuZn) was obtained in the same manner as in Example 1 at a yield of 92%, with the exception that 1.0 molar equivalent of Zn(NTf₂)₂ was added to an NMP (N-Methyl-pyrrolidone) solution of the organic metal complex 10, and the resulting mixture was stirred for 24 hours at 100°C.

[0189] The obtained polyRuZn was dissolved in dimethyl sulfoxide and dimethylformamide, but was insoluble in acetonitrile and methylene chloride.

<NMR measurement

[0190] The structure of polyRuZn was confirmed by ¹H-NMR spectrum.

[0191] FIG. 7 is a diagram comparing the ¹H-NMR spectrum of the organic metal complex 10 (here, represented as Ru(II)-M) in chloroform and the ¹H-NMR spectrum of polyRuZn in dimethyl sulfoxide.

[0192] It became apparent from the upfield shift of the proton at 6,6" position of the terpyridyl group and the downfield shift of other protons of the terpyridine that Zn and terpyridine formed a complex, and it became clear that an organic/heterometallic hybrid polymer had been synthesized.

5 <SEC-RALLS- Viscometry>

[0193] The molecular weight of each polymer was calculated by the SEC-RALLS-Viscometry method.

[0194] FIG. 8 shows a measurement result of SEC-RALLS-Viscometry.

[0195] The molecular weight M_w of the polymer was 10.5×10^4 for polyRuRu, 24.3×10^4 for polyRuFe, and 29.2×10^4 for polyRuZn, respectively.

<Electrochemical properties of solution>

[0196] Each organic/heterometallic hybrid polymer solution was prepared, and the cyclic voltammetry (CV) measurement and differential pulse voltammetry (DPV) measurement were conducted.

[0197] The measurement conditions were set as follows: working electrode: Pt mesh electrode; counter electrode: Pt wire electrode; reference electrode: Ag/Ag⁺; in a 0.1 M dimethylformamide solution of tetrabutylammonium perchlorate (TBAP). The solution was saturated with nitrogen before measurement. The scan rate was 100 mVs⁻¹.

[0198] FIG. 9A is a graph showing an electrochemical measurement result in a solution state by the CV measurement. FIG. 9B is a graph showing an electrochemical measurement results in a solution state by the DPV measurement.

[0199] Each polymer exhibited a reversible oxidation-reduction wave of Ru in the organic metal complex 10 around 0.25 V. Moreover, polyRuRu showed a reversible oxidation-reduction wave of Ru forming a complex with the terpyridine site at 0.72 V. Similarly, polyRuFe showed a reversible oxidation-reduction wave of Fe forming a complex with the terpyridine site at 0.70 V.

[0200] Next, the solution before and after the voltage application was placed in a quartz cell having a thickness of 1 mm, and UV/visible/near infrared absorption spectrum of the solution were measured while applying a voltage.

[0201] FIG. 10A is a graph showing the applied voltage dependence of the ultraviolet/visible/near infrared absorption spectrum of polyRuRu in a solution state. FIG. 10B is a graph showing the applied voltage dependence of the ultraviolet/visible/near infrared absorption spectrum of polyRuFe in a solution state. FIG. 10C is a graph showing the applied voltage dependence of the ultraviolet/visible/near infrared absorption spectrum of polyRuZn in a solution state.

[0202] In polyRuFe and polyRuZn, the absorption was observed in the near infrared region when a voltage of 0.5 V was applied. In polyRuFe, the absorption in the near infrared region disappeared when the voltage value was further increased and a voltage of 1.0 V was applied. The electrochromism phenomenon in the near infrared region is presumed to be caused due to the absorption by the intervalence charge transfer (IVCT) between Ru(III)/Fe(II) and Ru(III)/Zn(II) by the oxidation reaction of Ru. In polyRuFe and polyRuZn, the electrochromism phenomenon in the near infrared region appeared more than 30 times in a reversible manner.

[0203] On the other hand, in polyRuRu, the electrochromism phenomenon in the near infrared region could not be observed.

40 <Electrochemical properties of thin film>

[0204] Then, 2.5 mg of a dimethylformamide solution of an organic/heterometallic hybrid polymer (polyRuRu) was prepared, and by using this, a thin film of the organic/heterometallic hybrid polymer (polyRuRu) was formed on an ITO glass by the solvent casting method. The film thickness was 25 μm.

[0205] Next, a wire was connected to an ITO film (transparent electrode film) to produce a polyRuRu working electrode.

[0206] FIG. 11 is a perspective view showing an example of the working electrode.

[0207] A polyRuFe working electrode and a polyRuZn working electrode were prepared in the same manner, with the exception that the type of the organic/heterometallic hybrid polymer was changed.

[0208] Next, cyclic voltammetry (CV) and spectroelectrochemical measurements were carried out in a film state.

[0209] The measurement conditions were set as follows: working electrode: ITO glass + organic/heterometallic hybrid polymer thin film; counter electrode: ITO glass; reference electrode: Ag/Ag⁺; in a 0.1 M acetonitrile solution of tetrabutylammonium perchlorate (TBAP).

[0210] FIG. 12A is a graph showing measurement data of the scan rate dependence of the CV measurement result of the polyRuZn film. FIG. 12B is a graph showing the relationship between the scan rate and the current value.

[0211] The scan rate was set to 10, 20, 50, 100, 200, 300, 400, 500, 600, 800, 1,000, 1,200 or 1,500 mVs⁻¹. As the rate increased, the value of the flowing current increased.

[0212] The current value showed a first order linear dependence on the one-half power of the scan rate. As a result, it became clear that the electron transfer in this system is not limited by the electron transfer between the polymer and

the electrodes, but is controlled by the diffusion limitation due to the process in which negative ions in the solution come into contact with Ru(II) in the polymer.

[0213] Then, spectroelectrochemical measurements of polyRuZn in a film state were carried out.

[0214] FIG. 13 is a graph showing the electrical spectroscopy measurement result of polyRuZn in the film state, which shows the change in absorbance (Abs) before and after the application of a voltage. With the application of 0 V and 0.01 V, an absorption in the vicinity of 350 nm and an absorption in the vicinity of 510 nm were observed, although almost no absorption appeared in the vicinity of 1,147 nm. On the other hand, when a voltage of 0.5 V was applied, the absorption at 510 nm reduced, and the absorption at 1,147 nm increased. A change ΔT in transmittance in the near infrared region during application of 0 V and 0.5 V was equal to or greater than 60%.

[0215] FIG. 14 is a photograph showing the outer appearance of polyRuZn in the film state at the time when no voltage was applied (0 V) and when a voltage of 0.5 V was applied. The film had a transparent red purple color when no voltage was applied (0 V), whereas the film had a transparent thin yellow color when a voltage of 0.5 V was applied.

<Reproducibility test>

[0216] Then, by repeatedly applying voltages of 0.5 V and 0.01 V alternately at 5 second intervals to the organic/heterometallic hybrid polymer (polyRuZn), a change in the light absorption at 1,147 nm was observed.

[0217] FIG. 15A is a graph showing a change in the physical property values of polyRuZn in a film state due to the on/off of a voltage, which is a change in the current value due to the on/off of a voltage. FIG. 15B shows a change in the light transmittance at a wavelength of 1,147 nm. The transmittance changed in response to the current value. The change in the current value and the change in the light transmittance at a wavelength of 1,147 nm corresponded with high reproducibility.

[0218] FIG. 16 is a graph showing a change in the light transmittance of polyRuZn in a film state at a wavelength of 1,147 nm due to the on/off of a voltage, when intervals for changing the voltage between 0 V and 0.5 V are set to 20 seconds. The transmittance changed from 80% to 20% at a high speed of about 3 seconds, and the change from 20% to 89% also occurred at a comparably high speed.

[0219] FIG. 17 is a graph showing a change in the transmittance when the voltage was changed 600 times between 0 V and 0.5 V during 3,000 s, for a film of an organic/heterometallic hybrid polymer (polyRuZn). The change in the transmittance was reversible and stable, and the transmittance (absolute value) gradually attenuated. However, the change ΔT in the transmittance was substantially constant, and the change ΔT in the transmittance in the near infrared (NIR) region was equal to or more than 60% even after 3,000 seconds.

(Example 4)

[0220] $[\text{ClRu}(\text{dppe})_2\text{C}=\text{CH}-\text{C}_6\text{H}_4-\text{HC}=\text{C}=(\text{dppe})_2\text{RuCl}](\text{OTf})_2$ (binuclear organometallic site) which was a salt of $\text{Ru}(\text{II})(\text{dppe})_2\text{C}=\text{CH}-\text{C}_6\text{H}_4-\text{HC}=\text{C}=\text{Ru}(\text{dppe})_2\text{Cl}_2$ was synthesized according to the following previous report.

[0221] Benameur, A.; Brignou, P.; Di Piazza, E.; Hervault, Y.-M.; Norel, L.; Rigaut, S., New J. Chem. 2011, 35 (10), 2105-2113.

[0222] A terpyridine compound having an ethynyl group and a terpyridyl group (4'-(4-ethynylphenyl)-2,2':6',2"-terpyridine) (308.2 mg) and $[\text{ClRu}(\text{dppe})_2\text{C}=\text{CH}-\text{C}_6\text{H}_4-\text{HC}=\text{C}=(\text{dppe})_2\text{RuCl}](\text{OTf})_2$ (708.7 mg) were stirred at room temperature under a nitrogen atmosphere for 7 days in methylene chloride (80 mL) in the presence of triethylamine (1.85 mL) and sodium hexafluorophosphate (206.5 mg). Thereafter, diethyl ether was added thereto, and after filtering the precipitates, the resultant was washed with diethyl ether. The resultant was purified by column chromatography on alumina to isolate an organic metal ligand having a terpyridyl group at the terminal (L-Ru(II)₂-L) as a yellow solid (744 mg, yield: 80.8%).

[0223] ¹H- and ³¹P-NMR, and high-resolution mass spectrum (HRMS) measurement were performed to confirm the structure of the organic metal ligand (L-Ru(II)₂-L).

[0224] Then, under an argon atmosphere, an NMP (N-Methyl-pyrrolidone) solution obtained by dispersing an equimolar amount of $\text{Zn}(\text{NTf}_2)_2$ was added to an NMP solution of the organic metal ligand (L-Ru(II)₂-L) in a stepwise manner, and the resulting mixture was stirred for 6 hours under reflux at about 120°C, thereby obtaining a linear organic/multimetallic hybrid polymer (poly(Ru₂Zn)₁₀₀) in the form of a dark red solid with an yield of 82%.

[0225] The obtained poly(Ru₂Zn)₁₀₀ dissolved in dimethylformamide and dimethyl sulfoxide.

[0226] Next, the linear organic/multimetallic hybrid polymer was dissolved in dimethyl sulfoxide to produce a solution having a concentration of 0.5 mg/mL, and a film of the linear organic/multimetallic hybrid polymer (poly(Ru₂Zn)₁₀₀) was formed on a glass slide by the drop-coating method.

[0227] Then, 2.5 mg of the organic/multimetallic hybrid polymer was dissolved in dimethyl sulfoxide to produce a solution having a concentration of 0.5 mg/mL, and a film of the linear organic/multimetallic hybrid polymer (poly(Ru₂Zn)₁₀₀) was formed on an ITO glass (active area: 0.8 × 2.5 cm²) by the drop-coating method, thereby producing a working

electrode.

[0228] The film thickness was 25 μm .

(Example 5)

[0229] Then, an NMP solution of 3D-M which had been prepared in advance so as to be 10 molar parts with respect to the combined total of 100 molar parts of the linear portion constituting $\text{poly}(\text{Ru}_2\text{Zn})_{100}$ was added to the linear organic/multimetallic hybrid polymer ($\text{poly}(\text{Ru}_2\text{Zn})_{100}$) in the form of a dark red solid.

[0230] Next, $\text{Zn}(\text{NTf}_2)_2$ was mixed in an equimolar amount relative to 3D-M, and the resulting mixture was stirred for 18 hours under reflux at about 120°C, precipitated in diethyl ether, and washed with chloroform, water, and diethyl ether, followed by drying, thereby obtaining a branched organic/multimetallic hybrid polymer ($\text{poly}(\text{Ru}_2\text{Zn})_{90}$) in the form of a dark red solid with a yield of 85%.

[0231] The obtained $\text{poly}(\text{Ru}_2\text{Zn})_{90}$ dissolved in heated dimethyl sulfoxide. However, it was insoluble in dimethylformamide and dimethyl sulfoxide at room temperature. It was speculated that the heat resistance was improved by the 3D network structure.

[0232] Next, the branched organic/multimetallic hybrid polymer was dissolved in dimethyl sulfoxide to produce a solution having a concentration of 0.5 mg/mL, and a film of the branched organic/multimetallic hybrid polymer ($\text{poly}(\text{Ru}_2\text{Zn})_{90}$) was formed on a glass slide by the drop-coating method.

[0233] Then, 2.5 mg of the branched organic/multimetallic hybrid polymer was dissolved in dimethyl sulfoxide to produce a solution having a concentration of 0.5 mg/mL, and a film of the branched organic/multimetallic hybrid polymer ($\text{poly}(\text{Ru}_2\text{Zn})_{90}$) was formed on an ITO glass (active area: $0.8 \times 2.5 \text{ cm}^2$) by the drop-coating method, thereby producing a working electrode.

[0234] The film thickness was 25 μm .

(Example 6)

[0235] Then, an NMP solution of 3D-M which had been prepared in advance so as to be 20 molar parts with respect to the combined total of 100 molar parts of the linear portion constituting $\text{poly}(\text{Ru}_2\text{Zn})_{100}$ was added to the linear organic/multimetallic hybrid polymer ($\text{poly}(\text{Ru}_2\text{Zn})_{100}$) in the form of a dark red solid.

[0236] Next, $\text{Zn}(\text{NTf}_2)_2$ was mixed in an equivalent amount relative to 3D-M, and the resulting mixture was stirred for 18 hours under reflux at about 120°C, precipitated in diethyl ether, and washed with chloroform, water, and diethyl ether, followed by drying, thereby obtaining a branched organic/multimetallic hybrid polymer ($\text{poly}(\text{Ru}_2\text{Zn})_{80}$) in the form of a dark red solid with a yield of 80%.

[0237] The obtained $\text{poly}(\text{Ru}_2\text{Zn})_{80}$ dissolved in heated dimethyl sulfoxide. However, it was insoluble in dimethylformamide and dimethyl sulfoxide at room temperature. It was speculated that the heat resistance was improved by the 3D network structure.

[0238] Next, the branched organic/multimetallic hybrid polymer was dissolved in dimethyl sulfoxide to produce a solution having a concentration of 0.5 mg/mL, and a film of the branched organic/multimetallic hybrid polymer ($\text{poly}(\text{Ru}_2\text{Zn})_{80}$) was formed on a glass slide by the drop-coating method.

[0239] Then, 2.5 mg of the branched organic/multimetallic hybrid polymer was dissolved in dimethyl sulfoxide to produce a solution having a concentration of 0.5 mg/mL, and a film of the branched organic/multimetallic hybrid polymer ($\text{poly}(\text{Ru}_2\text{Zn})_{80}$) was formed on an ITO glass (active area: $0.8 \times 2.5 \text{ cm}^2$) by the drop-coating method, thereby producing a working electrode.

[0240] The film thickness was 25 μm .

(Example 7)

[0241] Then, an NMP solution of 3D-M which had been prepared in advance so as to be 30 molar parts with respect to the combined total of 100 molar parts of the linear portion constituting $\text{poly}(\text{Ru}_2\text{Zn})_{100}$ was added to the linear organic/multimetallic hybrid polymer ($\text{poly}(\text{Ru}_2\text{Zn})_{100}$) in the form of a dark red solid.

[0242] Next, $\text{Zn}(\text{NTf}_2)_2$ was mixed in an equivalent amount relative to 3D-M, and the resulting mixture was stirred for 18 hours under reflux at about 120°C, precipitated in diethyl ether, and washed with chloroform, water, and diethyl ether, followed by drying, thereby obtaining a branched organic/multimetallic hybrid polymer ($\text{poly}(\text{Ru}_2\text{Zn})_{70}$) in the form of a dark red solid with a high yield of 81%.

[0243] The obtained $\text{poly}(\text{Ru}_2\text{Zn})_{70}$ dissolved in heated dimethyl sulfoxide. However, it was insoluble in dimethylformamide and dimethyl sulfoxide at room temperature. It was speculated that the heat resistance was improved by the 3D network structure.

[0244] Next, the branched organic/multimetallic hybrid polymer was dissolved in dimethyl sulfoxide to produce a

solution having a concentration of 0.5 mg/mL, and a film of the branched organic/multimetallic hybrid polymer (poly(Ru₂Zn)₇₀) was formed on a glass slide by the drop-coating method.

[0245] Then, 2.5 mg of the branched organic/multimetallic hybrid polymer was dissolved in dimethyl sulfoxide to produce a solution having a concentration of 0.5 mg/mL, and a film of the branched organic/multimetallic hybrid polymer (poly(Ru₂Zn)₇₀) was formed on an ITO glass (active area: $0.8 \times 2.5 \text{ cm}^2$) by the drop-coating method, thereby producing a working electrode.

[0246] The film thickness was 25 μm .

<Thermogravimetric analysis: TGA measurement

[0247] Then, TGA measurement was carried out.

[0248] FIG. 29 is a graph showing a TGA measurement result of poly(Ru₂Zn)₁₀₀, poly(Ru₂Zn)₉₀, poly(Ru₂Zn)₈₀ and poly(Ru₂Zn)₇₀.

[0249] Mass was reduced in all samples when heated.

[0250] T_{d10} is a heating temperature at which the mass is reduced by 10%.

[0251] T_{d10} of poly(Ru₂Zn)₁₀₀ was 321.5°C, which was the lowest.

[0252] The T_{d10} values increased as the proportion of Zn increased, and T_{d10} of poly(Ru₂Zn)₇₀ was 372.4°C, which was the highest.

<Atomic force microscopy: AFM observation>

[0253] Next, the surface of each organic/multimetallic hybrid polymer film formed on a glass slide was observed by atomic force microscopy (AFM).

[0254] FIG. 30A is an AFM image of a poly(Ru₂Zn)₁₀₀ film. FIG. 30B is an AFM image of a poly(Ru₂Zn)₉₀ film. FIG. 30C is an AFM image of a poly(Ru₂Zn)₈₀ film. FIG. 30D is an AFM image of a poly(Ru₂Zn)₇₀ film.

[0255] The poly(Ru₂Zn)₁₀₀ film was a porous film. The root-mean square roughness (R_{rms}) was as small as 1.1 nm.

[0256] Films from the poly(Ru₂Zn)₉₀ film to the poly(Ru₂Zn)₇₀ film were completely different from the poly(Ru₂Zn)₁₀₀ film, and were rough films.

[0257] R_{rms} of the poly(Ru₂Zn)₉₀ film was 1.3 nm, R_{rms} of the poly(Ru₂Zn)₈₀ film was 1.4 nm, and R_{rms} of the poly(Ru₂Zn)₇₀ film was 4.3 nm. The poly(Ru₂Zn)₇₀ film was the most porous film.

<Electrochemical properties of film>

[0258] Next, the cyclic voltammetry (CV) measurement of each of the organic/multimetallic hybrid polymer films formed on the ITO glass was carried out.

[0259] The measurement conditions were set as follows: working electrode: poly(Ru₂Zn)₇₀/ITO electrode; counter electrode: ITO electrode; reference electrode: Ag/Ag⁺; in a 0.1 M CH₃CN solution of LiClO₄. The solution was saturated with nitrogen before measurement. The scan rate was 20 mVs⁻¹.

[0260] FIG. 31 is a CV spectrum showing an electrochemical measurement result of the poly(Ru₂Zn)₇₀ film. Reversible peaks were observed at 21 mV and 255 mV. These are due to the oxidation-reduction between Ru(II)/(III) in the Ru-acetylide complex.

[0261] A potential ΔE between oxidation peaks was 234 mV, and $K_c = \exp(\Delta E F / RT)$ was 1.1×10^4 . This indicates that species in which one side is oxidized is stable. It was presumed to be because electrons were delocalized along the conjugated chain.

[0262] FIG. 32 is a CV spectrum showing the scan rate dependence of the poly(Ru₂Zn)₇₀ film.

[0263] Cases in which the scan rate was set to 10, 20, 50, 100, 300, 400, 500, 600, 800, 1,000, 1,200 and 1,500 mVs⁻¹ are shown.

[0264] The peak current value increased as the scan rate increased.

[0265] FIG. 33 is a graph showing the relationship between the scan rate and the current value.

[0266] Each current value of the First oxidize current, Second oxidize current, First reduced current and Second reduced current was obtained from the first order linear relationship with the one-half power of the scan rate. The square root R² of the scan rate was 0.99791, 0.99717, 0.99926 and 0.99839.

[0267] From these results, it could be speculated that the oxidation-reduction reaction of Ru is not limited by the electron transfer between the polymer and the electrodes, but is controlled by the diffusion limitation due to the process in which negative ions in the solution come into contact with Ru(II) in the polymer.

[0268] On the other hand, the films of other polymers showed no electrochemical properties. This is because they were readily dissolved in an electrolytic solution containing an electrolyte such as LiClO₄.

<Spectroelectrochemical measurements in the UV/Visible/near infrared region>

[0269] Then, spectroelectrochemical measurements of the poly(Ru₂Zn)₁₀₀ film were carried out.

[0270] FIG. 34 is a graph showing the spectroelectrochemical measurements of the poly(Ru₂Zn)₁₀₀ film, which shows the change in the ultraviolet/visible/near infrared absorption spectrum before and after the voltage application. With the application of 0.50 V, an absorption in the vicinity of 1,174 nm was observed, although almost no absorption appeared in the vicinity of 1,844 nm. On the other hand, when voltages of 0.05 V and -0.50 V were applied, the absorption at 1,174 nm reduced, and the absorption at 1,844 nm slightly increased.

[0271] Then, spectroelectrochemical measurements of the poly(Ru₂Zn)₉₀ film were carried out.

[0272] FIG. 35 is a graph showing the spectroelectrochemical measurements of the poly(Ru₂Zn)₉₀ film, which shows the change in the ultraviolet/visible/near infrared absorption spectrum before and after the voltage application. With the application of 0.50 V, an absorption in the vicinity of 1,174 nm was observed, although almost no absorption appeared in the vicinity of 1,844 nm. On the other hand, when a voltage of 0.05 V was applied, the absorption at 1,174 nm reduced, and the absorption at 1,844 nm rose slightly. When a voltage of -0.50 V was applied, the absorption at 1,174 nm greatly reduced, and the absorption at 1,844 nm increased greatly.

[0273] Then, spectroelectrochemical measurements of the poly(Ru₂Zn)₇₀ film were carried out.

[0274] FIG. 36 is a graph showing the spectroelectrochemical measurements of the poly(Ru₂Zn)₇₀ film, which shows the change in the ultraviolet/visible/near infrared absorption spectrum before and after the voltage application. With the application of 0.40 V, an absorption in the vicinity of 1,174 nm was observed, although almost no absorption appeared in the vicinity of 1,844 nm. On the other hand, when a voltage of 0.05 V was applied, the absorption at 1,174 nm reduced, and the absorption at 1,844 nm increased slightly. When a voltage of -0.20 V was applied, the absorption at 1,174 nm greatly reduced, and the absorption at 1,844 nm increased greatly.

<Reproducibility test>

[0275] Then, by repeatedly applying voltages of 0.05 V and 0.4 V alternately at 5 second intervals, 10 second intervals, 15 second intervals and 20 second intervals to the film of the branched organic/multimetallic hybrid polymer (poly(Ru₂Zn)₇₀), a change in the light transmittance at 1,844 nm was observed.

[0276] FIG. 37 is a graph showing the applied voltage dependence of the light transmittance change at 1,844 nm of the poly(Ru₂Zn)₇₀ film due to the on/off of voltage.

[0277] Then, by repeatedly applying voltages of 0.05 V and -0.2 V alternately 50 times at 20 second intervals to the film of the branched organic/multimetallic hybrid polymer (poly(Ru₂Zn)₇₀), a change in the light transmittance at 1,844 nm was observed.

[0278] FIG. 38 is a graph showing the repetition characteristics of the light transmittance change at 1,844 nm of the poly(Ru₂Zn)₇₀ film due to the on/off of voltage.

[0279] The result showed that the coloration efficiency $\eta = 337 \text{ (cm}^2/\text{C)}$, and $\Delta T > 60\%$.

[0280] It should be noted that the coloration efficiency η is defined by the following equation (1). The coloration efficiency η is an index indicating the extent of area in which the absorbance can be varied. Here, ΔOD represents a change in optical density, Q_d represents a change in the injected/ejected electrons, T_b is (81.5), and T_c is (19.5).

[Equation 1]

$$\eta = \frac{\Delta OD}{Q_d} = \log \frac{T_b}{T_c} / Q_d \quad \dots (1)$$

[0281] Then, by repeatedly applying voltages of 0.05 V and 0.4 V alternately at 5 second intervals, 10 second intervals and 15 second intervals to the film of the branched organic/multimetallic hybrid polymer (poly(Ru₂Zn)₇₀), a change in the light transmittance at 1,174 nm was observed.

[0282] FIG. 39 is a graph showing the applied voltage dependence of the light transmittance change at 1,174 nm of the poly(Ru₂Zn)₇₀ film due to the on/off of voltage.

[0283] Then, by repeatedly applying voltages of 0.05 V and 0.4 V alternately 50 times at 15 second intervals to the film of the branched organic/multimetallic hybrid polymer (poly(Ru₂Zn)₇₀), a change in the light transmittance at 1,174 nm was observed.

[0284] FIG. 40 is a graph showing the repetition characteristics of the light transmittance change at 1,174 nm of the poly(Ru₂Zn)₇₀ film due to the on/off of voltage.

[0285] The result showed that the coloration efficiency $\eta = 272$ (cm²/C), and $\Delta T > 70\%$.

[0286] As described above, the change in the light transmittance was fast, which was highly reproducible.

[0287] FIG. 41 is a graph showing the change in the current value of the poly(Ru₂Zn)₇₀ film due to the on/off of voltage by the change in the optical absorption at 1,844 nm.

[0288] FIG. 42 is a graph showing the change in the current value of the poly(Ru₂Zn)₇₀ film due to the on/off of voltage by the change in the optical absorption at 1,174 nm.

[0289] FIG. 43A is a graph showing the applied voltage dependence of the ultraviolet/visible/near infrared absorption spectrum of the film of the branched organic/multimetallic hybrid polymer (poly(Ru₂Zn)₇₀), when the applied voltage was changed from -0.20 V to 0.05 V in a stepwise manner. FIG. 43B is a graph showing the applied voltage dependence of the ultraviolet/visible/near infrared absorption spectrum of the film of the branched organic/multimetallic hybrid polymer (poly(Ru₂Zn)₇₀), when the applied voltage was changed from 0.10 V to 0.40 V in a stepwise manner.

[0290] FIG. 44A is a graph showing the applied voltage dependence of the ultraviolet/visible/ near infrared absorption spectrum of the film of the branched organic/multimetallic hybrid polymer (poly(Ru₂Zn)₇₀), when the applied voltage was changed from 0.05 V to -0.20 V in a stepwise manner. FIG. 44B is a graph showing the applied voltage dependence of the ultraviolet/visible/ near infrared absorption spectrum of the film of the branched organic/multimetallic hybrid polymer (poly(Ru₂Zn)₇₀), when the applied voltage was changed from 0.40 V to 0.10 V in a stepwise manner.

[0291] Table 1 shows electrochemical properties of the organic/multimetallic hybrid polymer (poly(Ru₂Zn)₇₀) film in a 0.1 M acetonitrile solution of LiClO₄.

[Table 1]

Sample	T _{bleached} [%][a]	T _{colored} [%][a]	ΔT [%][a]	t _{coloring} [s][b]	t _{bleaching} [s][b]	Charge/Discharge [mC][c]	η [cm ² /C][d]
poly(Ru ₂ Zn) ₇₀ (at 1844 nm)	81.5	19.5	62.0	20	20	3.7/1.8	272
poly(Ru ₂ Zn) ₇₀ (at 1174 nm)	75.3	6.1	69.2	15	15	8.0/6.4	337

[a]The transmittances (T_{bleached} and T_{colored}) of the NIR absorption at 1844 and 1174 nm in the bleached and colored states of the polymer film coated on an ITO glass were measured by *in-situ* UV/vis/NIR spectroscopy between - 0.02 and + 0.05, and + 0.05 and + 0.40 V vs. Ag/Ag⁺ with a interval time of 20 s and 15 s, respectively (electrolyte: 0.1 M LiClO₄/ CH₃CN the ITO working area: 0.8 × 2.5 cm²). The difference (ΔT) was calculated from T_{bleached} and T_{colored}.

[b]The times for coloring and bleaching (t_{coloring} and t_{bleaching}) were defined as the time taken 95% of ΔT to change.

[c]The charge/discharge values were the integration of the coulomb number in the current response during the redox.

[d]The coloration efficiency(η) was defined as the relationship between electron charge used and the change of ΔT .

[Industrial Applicability]

[0292] An organic/heterometallic hybrid polymer, a method for producing the same, and an organic/heterometallic hybrid polymer film according to the present invention exhibit electrochromic properties and relate to a linear and stable organic/heterometallic hybrid polymer. In particular, it is possible to freely convert the optical absorption spectrum from the visible light region to the near infrared light region. Therefore, they can be used as a near infrared light-blocking electrochromic window or a near infrared light shutter, and is industrially applicable in the optical communication industry, optical device industry, window industry, and the like.

[0293] The organic/multimetallic hybrid polymer of the present invention is a newly synthesized compound, which is an organic/multimetallic hybrid polymer constituted of an organic metal ligand obtained by linking two Ru(dppe)₂, exhibiting electrochromic properties in the infrared light region, and highly stable to repetitive oxidation-reduction of metals. In particular, it can be used as an optical communication device capable of blocking light by switching at two wavelengths of 1,310 nm and 1,550 nm that are used in optical communication. For this reason, it is industrially applicable in the optical communication industry, optical device industry, smart window industry, and the like. The method for producing the same and the film of the organic/multimetallic hybrid polymer are also industrially applicable in the above industries and the like.

[Reference Signs List]

[0294]

5 10: Organic metal complex; 11A, 11B: Ligand; 13: Connector; 13: Porous film; 20: Organic/heterometallic hybrid polymer; 20OX: Oxidized organic/heterometallic hybrid polymer; 1': Linear organic/multimetallic hybrid polymer film; 2': Branched organic/multimetallic hybrid polymer film; 5': Linear organic/multimetallic hybrid polymer; 6': Branched organic/multimetallic hybrid polymer; 11'A, 11'B, 11'C: Ligand; 13': Connector; 15': Branch element (triphenylbenzene); 21': Organic metal ligand; 31': Linear portion; 41': Branched portion (branched compound); 50': Glass substrate; 51': Transparent conductive film; M': Transition metal.

Claims

- 15 1. An organic/heterometallic hybrid polymer comprising a plurality of organic metal complexes and a plurality of transition metals,
wherein said plurality of organic metal complexes are linked in a linear manner by sandwiching each of said plurality of transition metals therebetween,
said organic metal complexes include two ligands each having a terpyridyl group and one connector having $\text{Ru}(\text{dppe})_2$
20 and two ethynylene groups, and the two ligands are linked by the connector, so that a nitrogen atom at position 1' of said terpyridyl group is directed toward a terminal side of a molecule of said organic metal complex, and the terpyridyl groups of at least two different organic metal complexes of said plurality of organic metal complexes are bound to one of said transition metals through a coordinate bond, thereby linking said plurality of organic metal complexes while sandwiching said plurality of transition metals alternately therebetween.
- 25 2. The organic/heterometallic hybrid polymer according to Claim 1, wherein said transition metal is any one of Ru, Fe or Zn.
- 30 3. The organic/heterometallic hybrid polymer according to Claim 1 or 2, wherein a molecular weight M_w is at least 10.5×10^4 and not more than 29.2×10^4 .
- 35 4. A method of producing an organic/heterometallic hybrid polymer, the method comprising:
a step of synthesizing an organic metal complex having $\text{Ru}(\text{dppe})_2$ and a terminal terpyridyl group by reacting a terpyridine compound having an ethynyl group and a terpyridyl group with a compound containing $\text{Ru}(\text{dppe})_2$ in an organic solvent; and
a step of synthesizing the organic/heterometallic hybrid polymer by reacting said organic metal complex and a transition metal compound in an organic solvent.
- 40 5. The method of producing an organic/heterometallic hybrid polymer according to Claim 4, wherein 1.0 molar equivalent or more of the transition metal compound is reacted with respect to said organic metal complex.
- 45 6. The method of producing an organic/heterometallic hybrid polymer according to Claim 4 or 5, wherein said transition metal compound is any one of RuCl_2 , $\text{Fe}(\text{BF}_4)_2$, or $\text{Zn}(\text{NTf}_2)_2$.
7. The method of producing an organic/heterometallic hybrid polymer according to any one of Claims 4 to 6, wherein a reaction time of said organic metal complex and said transition metal compound is equal to or more than 12 hours.
- 50 8. An organic/heterometallic hybrid polymer film comprising the organic/heterometallic hybrid polymer according to any one of Claims 1 to 3.
9. The organic/heterometallic hybrid polymer film according to Claim 8, wherein a film thickness is at least 100 nm and not more than 1 mm.
- 55 10. The organic/heterometallic hybrid polymer film according to Claim 8 or 9, wherein a transition metal contained in said organic/heterometallic hybrid polymer is either Fe or Zn.
11. An organic/multimetallic hybrid polymer comprising a plurality of organic metal ligands and a plurality of transition

metals,

wherein a linear portion in which said plurality of organic metal ligands are linked in a linear manner by sandwiching each of said plurality of transition metals therebetween is included,

said organic metal ligand is formed by linking two ligands to one connector,

said connector is formed with a benzene ring at the center by linking two $\text{Ru}(\text{dppe})_2$ via two ethynylene groups bonded to the benzene ring, while connecting two phenyl groups to said two $\text{Ru}(\text{dppe})_2$ via other two ethynylene groups,

said ligands are terpyridyl groups and are formed by being connected respectively to said two phenyl groups of said connector, and

said terpyridyl groups of at least two different organic metal ligands of said plurality of organic metal ligands are bound to one of said transition metals through a coordinate bond, thereby linking said plurality of organic metal ligands while alternately sandwiching said plurality of transition metals therebetween.

12. The organic/multimetallic hybrid polymer according to Claim 11, wherein said transition metal is Fe, Zn, Co or Ru.

13. The organic/multimetallic hybrid polymer according to Claim 11 or 12 which is linear.

14. The organic/multimetallic hybrid polymer according to Claim 11 or 12 which is branched.

15. The organic/multimetallic hybrid polymer according to Claim 14 comprising a branched portion composed of 1,3,5-Tris[4-(2,2':6',2''-terpyridin-4'-yl)phenyl]benzene.

16. The organic/multimetallic hybrid polymer according to Claim 14 or 15, wherein a content of said branched portion is at least 10 molar parts and not more than 30 molar parts, relative to the total number of moles of linear portions and branched portions constituting the organic/multimetallic hybrid polymer.

17. A method of synthesizing an organic/multimetallic hybrid polymer, the method comprising:

a step of synthesizing a binuclear organometallic site comprising two $\text{Ru}(\text{dppe})_2$ by reacting 1 molar equivalent of diethynylbenzene and 2 molar equivalents of $\text{Ru}(\text{dppe})_2\text{Cl}(\text{OTf})$ in an organic solvent;

a step of synthesizing an organic metal ligand having a terpyridyl group at the terminal and two $\text{Ru}(\text{dppe})_2$ by reacting 2 molar equivalents of a terpyridine compound having an ethynyl group and a terpyridyl group with one molar equivalent of a binuclear organometallic site in an organic solvent; and

a step of synthesizing a linear organic/multimetallic hybrid polymer by reacting said organic metal ligand and a transition metal compound in an organic solvent.

18. The method of synthesizing an organic/multimetallic hybrid polymer according to Claim 17, wherein a branched organic/multimetallic hybrid polymer is synthesized by reacting said linear organic/multimetallic hybrid polymer, a branched compound branched into three or more directions with a branch element at the center and having a ligand at a branched molecule end, and a transition metal compound.

19. The method of synthesizing an organic/multimetallic hybrid polymer according to Claim 18, wherein said branched compound is 1,3,5-Tris[4-(2,2':6',2''-terpyridin-4'-yl)phenyl]benzene.

20. The method of synthesizing an organic/multimetallic hybrid polymer according to Claim 18 or 19, wherein a mixing amount of said branched compound is at least 10 molar parts and not more than 30 molar parts, relative to the combined total of 100 molar parts of linear portions constituting the linear organic/multimetallic hybrid polymer.

21. The method of synthesizing an organic/multimetallic hybrid polymer according to Claim 17, wherein 1.0 molar equivalent or more of the transition metal compound is reacted with respect to said organic metal ligand.

22. The method of synthesizing an organic/multimetallic hybrid polymer according to any one of Claims 17 to 21, wherein said transition metal compound is $\text{Fe}(\text{BF}_4)_2$ or $\text{Zn}(\text{NTf}_2)_2$.

23. The method of synthesizing an organic/multimetallic hybrid polymer according to any one of Claims 17 to 22, wherein a reaction time of said organic metal ligand and said transition metal compound is equal to or more than 6 hours.

24. An organic/multimetallic hybrid polymer film comprising the organic/multimetallic hybrid polymer according to any

one of Claims 11 to 16.

25. The organic/multimetallic hybrid polymer film according to Claim 24, wherein a film thickness is at least 100 nm and not more than 1 mm.

Patentansprüche

1. Organisches/ heterometallisches Hybridpolymer, umfassend eine Vielzahl von organischen Metallkomplexen und eine Vielzahl von Übergangsmetallen, wobei die Vielzahl von organischen Metallkomplexen in einer linearen Weise durch Einbetten jede der Vielzahl von Übergangsmetallen dazwischen verbunden sind, die organischen Metallkomplexe zwei Liganden mit jeweils einer Terpyridylgruppe und einem Konnektor mit $\text{Ru}(\text{dppe})_2$ und zwei Ethinylengruppen einschließen, und die zwei Liganden durch den Konnektor verbunden sind, sodass ein Stickstoffatom an Position 1' der Terpyridylgruppe zu einer terminalen Seite eines Moleküls des organischen Metallkomplexes hin gerichtet ist, und die Terpyridylgruppen von mindestens zwei verschiedenen organischen Metallkomplexen von der Vielzahl von organischen Metallkomplexen an eines der Übergangsmetalle durch eine koordinative Bindung gebunden sind, dadurch Verknüpfen der Vielzahl von organischen Metallkomplexen, während die Vielzahl von Übergangsmetallen alternierend dazwischen eingebettet wird.
2. Organisches/ heterometallisches Hybridpolymer gemäß Anspruch 1, wobei das Übergangsmetall irgendeines von Ru, Fe oder Zn ist.
3. Organisches/ heterometallisches Hybridpolymer gemäß Anspruch 1 oder 2, wobei ein Molekulargewicht M_w mindestens $10,5 \times 10^4$ und nicht mehr als $29,2 \times 10^4$ ist.
4. Verfahren zur Herstellung eines organischen/ heterometallischen Hybridpolymers, das Verfahren umfassend:
 - einen Schritt des Synthetisierens eines organischen Metallkomplexes mit $\text{Ru}(\text{dppe})_2$ und einer terminalen Terpyridylgruppe durch Umsetzen einer Terpyridinverbindung mit einer Ethinylgruppe und einer Terpyridylgruppe mit einer Verbindung enthaltend $\text{Ru}(\text{dppe})_2$ in einem organischen Lösungsmittel; und
 - einen Schritt des Synthetisierens des organischen/ heterometallischen Hybridpolymers durch Umsetzen des organischen Metallkomplexes und einer Übergangsmetallverbindung in einem organischen Lösungsmittel.
5. Verfahren zur Herstellung eines organischen/ heterometallischen Hybridpolymers gemäß Anspruch 4, wobei 1,0 Moläquivalent oder mehr der Übergangsmetallverbindung in Bezug auf den organischen Metallkomplex umgesetzt wird.
6. Verfahren zur Herstellung eines organischen/ heterometallischen Hybridpolymers gemäß Anspruch 4 oder 5, wobei die Übergangsmetallverbindung irgendeine von RuCl_2 , $\text{Fe}(\text{BF}_4)_2$, oder $\text{Zn}(\text{NTf}_2)_2$ ist.
7. Verfahren zur Herstellung eines organischen/ heterometallischen Hybridpolymers gemäß einem der Ansprüche 4 bis 6, wobei eine Reaktionszeit des organischen Metallkomplexes und der Übergangsmetallverbindung gleich oder mehr als 12 Stunden ist.
8. Organischer/ heterometallischer Hybridpolymerfilm, umfassend das organische/ heterometallische Hybridpolymer gemäß einem der Ansprüche 1 bis 3.
9. Organischer/ heterometallischer Hybridpolymerfilm gemäß Anspruch 8, wobei eine Filmdicke mindestens 100 nm und nicht mehr als 1 mm beträgt.
10. Organischer/ heterometallischer Hybridpolymerfilm gemäß Anspruch 8 oder 9, wobei ein in dem organischen/ heterometallischen Hybridpolymer enthaltenes Übergangsmetall entweder Fe oder Zn ist.
11. Organisches/ multimetalliches Hybridpolymer, umfassend eine Vielzahl von organischen Metallliganden und eine Vielzahl von Übergangsmetallen, wobei ein linearer Abschnitt eingeschlossen ist, in welchem die Vielzahl von organischen Metallliganden in einer

linearen Weise, durch Einbetten jede der Vielzahl von Übergangsmetallen dazwischen, verbunden sind, der organische Metallligand durch Verknüpfen zweier Liganden an einen Konnektor gebildet wird, der Konnektor mit einem Benzolring in der Mitte durch Verknüpfen zweier $\text{Ru}(\text{dppe})_2$ durch zwei Ethinylengruppen, gebunden an den Benzolring, gebildet wird, während zwei Phenylgruppen an die zwei $\text{Ru}(\text{dppe})_2$ durch andere zwei Ethinylengruppen verbunden werden, die Liganden Terpyridylgruppen sind und durch jeweiliges Verbinden an die zwei Phenylgruppen des Konnektors gebildet werden, und die Terpyridylgruppen von mindestens zwei verschiedenen organischen Metallliganden von der Vielzahl von organischen Metallliganden an eines der Übergangsmetalle durch eine koordinative Bindung gebunden sind, dadurch Verknüpfen der Vielzahl von organischen Metallliganden, während die Vielzahl von Übergangsmetallen alternierend dazwischen eingebettet wird.

12. Organisches/ multimetallisches Hybridpolymer gemäß Anspruch 11, wobei das Übergangsmetall Fe, Zn, Co oder Ru ist.

13. Organisches/ multimetallisches Hybridpolymer gemäß Anspruch 11 oder 12, welches linear ist.

14. Organisches/ multimetallisches Hybridpolymer gemäß Anspruch 11 oder 12, welches verzweigt ist.

15. Organisches/ multimetallisches Hybridpolymer gemäß Anspruch 14, umfassend einen verzweigten Abschnitt, gebildet aus 1,3,5-Tris[4-(2,2':6',2''-terpyridin-4'-yl)phenyl]benzol.

16. Organisches/ multimetallisches Hybridpolymer gemäß Anspruch 14 oder 15, wobei ein Gehalt des verzweigten Abschnitts mindestens 10 Molteile und nicht mehr als 30 Molteile, bezogen auf die Gesamtanzahl von linearen Abschnitten und verzweigten Abschnitten, bildend das organische/multimetallische Hybridpolymer, beträgt.

17. Verfahren zum Synthetisieren eines organischen/ multimetallischen Hybridpolymers, das Verfahren umfassend:

einen Schritt des Synthetisierens einer zweikernigen organometallischen Stelle, umfassend zwei $\text{Ru}(\text{dppe})_2$ durch Umsetzen von 1 Moläquivalent von Diethinylbenzol und 2 Moläquivalenten von $\text{Ru}(\text{dppe})_2\text{Cl}(\text{OTf})$ in einem organischen Lösungsmittel;

einen Schritt des Synthetisierens eines organischen Metallliganden mit einer Terpyridylgruppe an dem Terminus und zwei $\text{Ru}(\text{dppe})_2$ durch Umsetzen von 2 Moläquivalenten von einer Terpyridinverbindung mit einer Ethinylgruppe und einer Terpyridylgruppe mit einem Moläquivalent einer zweikernigen organometallischen Stelle in einem organischen Lösungsmittel; und

einen Schritt des Synthetisierens eines linearen organischen/ multimetallischen Hybridpolymers durch Umsetzen des organischen Metallliganden und einer Übergangsmetallverbindung in einem organischen Lösungsmittel.

18. Verfahren zum Synthetisieren eines organischen/ multimetallischen Hybridpolymers gemäß Anspruch 17, wobei ein verzweigtes organisches/ multimetallisches Hybridpolymer durch Umsetzen des linearen organischen/ multimetallischen Hybridpolymers, einer verzweigten Verbindung, verzweigt in drei oder mehrere Richtungen mit einem Abzweigungselement in der Mitte und mit einem Liganden an einem verzweigten Moleküle, und einer Übergangsmetallverbindung synthetisiert wird.

19. Verfahren zum Synthetisieren eines organischen/ multimetallischen Hybridpolymers gemäß Anspruch 18, wobei die verzweigte Verbindung 1,3,5-Tris[4-(2,2':6',2''-terpyridin-4'-yl)phenyl]benzol ist.

20. Verfahren zum Synthetisieren eines organischen/ multimetallischen Hybridpolymers gemäß Anspruch 18 oder 19, wobei eine Mischung der verzweigten Verbindung mindestens 10 Molteile und nicht mehr als 30 Molteile, bezogen auf die Gesamtheit von 100 Molteilen von linearen Abschnitten, die das lineare organische/ multimetallische Hybridpolymer bilden, beträgt.

21. Verfahren zum Synthetisieren eines organischen/ multimetallischen Hybridpolymers gemäß Anspruch 17, wobei 1,0 Moläquivalent oder mehr der Übergangsmetallverbindung in Bezug auf den organischen Metallliganden umgesetzt wird.

22. Verfahren zum Synthetisieren eines organischen/ multimetallischen Hybridpolymers gemäß einem der Ansprüche

17 bis 21, wobei die Übergangsmetallverbindung $\text{Fe}(\text{BF}_4)_2$ oder $\text{Zn}(\text{NTf}_2)_2$ ist.

23. Verfahren zum Synthetisieren eines organischen/ multimetallischen Hybridpolymers gemäß einem der Ansprüche 17 bis 22, wobei eine Reaktionszeit des organischen Metallliganden und der Übergangsmetallverbindung gleich oder mehr als 6 Stunden ist.

24. Organischer/ multimetallischer Hybridpolymerfilm, umfassend das organische/ multimetallische Hybridpolymer gemäß einem der Ansprüche 11 bis 16.

25. Organischer/ multimetallischer Hybridpolymerfilm gemäß Anspruch 24, wobei eine Filmdicke mindestens 100 nm und nicht mehr als 1 mm beträgt.

Revendications

1. Polymère hybride organique/hétérométallique comportant plusieurs complexes organo-métalliques et plusieurs atomes de métal de transition, dans lequel

- lesdits plusieurs complexes organo-métalliques sont reliés, de manière linéaire, en prenant en sandwich entre eux chacun desdits plusieurs atomes de métal de transition,

- lesdits complexes organo-métalliques comprennent deux ligands, qui comportent chacun un groupe terpyridyle, et un connecteur qui comporte un fragment $\text{Ru}(\text{dppe})_2$ et deux groupes éthyndiyle, et les deux ligands sont raccordés par le connecteur, de telle sorte que les atomes d'azote en position 1' desdits groupes terpyridyle sont orientés vers les extrémités de la molécule dudit complexe organo-métallique,

- et les groupes terpyridyle d'au moins deux différents desdits plusieurs complexes organo-métalliques sont liés à l'un desdits atomes de métal de transition par une liaison de coordinence, ce qui fait que lesdits plusieurs complexes organo-métalliques sont raccordés tout en prenant en sandwich entre eux lesdits plusieurs atomes de métal de transition, en alternant avec ceux-ci.

2. Polymère hybride organique/hétérométallique conforme à la revendication 1, dans lequel ledit métal de transition est l'un des ruthénium, fer et zinc.

3. Polymère hybride organique/hétérométallique conforme à la revendication 1 ou 2, dont la masse molaire M_w vaut au moins $10,5 \cdot 10^4$ et au plus $29,2 \cdot 10^4$.

4. Procédé de production d'un polymère hybride organique/hétérométallique, lequel procédé comporte les étapes suivantes :

- synthétiser un complexe organo-métallique comportant un fragment $\text{Ru}(\text{dppe})_2$ et un groupe terpyridyle terminal, en faisant réagir un dérivé de terpyridine comportant un groupe éthyne et un groupe terpyridyle avec un composé comportant un fragment $\text{Ru}(\text{dppe})_2$, dans un solvant organique,

- et synthétiser le polymère hybride organique/hétérométallique en faisant réagir ledit complexe organo-métallique avec un composé de métal de transition, dans un solvant organique.

5. Procédé de production d'un polymère hybride organique/hétérométallique, conforme à la revendication 4, dans lequel on fait réagir 1,0 équivalent molaire du composé de métal de transition ou plus, par rapport audit complexe organo-métallique.

6. Procédé de production d'un polymère hybride organique/hétérométallique, conforme à la revendication 4 ou 5, dans lequel ledit composé de métal de transition est l'un des composés de formule RuCl_2 , $\text{Fe}(\text{BF}_4)_2$ ou $\text{Zn}(\text{NTf}_2)_2$.

7. Procédé de production d'un polymère hybride organique/hétérométallique, conforme à l'une des revendications 4 à 6, dans lequel la durée de la réaction dudit complexe organo-métallique et dudit composé de métal de transition est supérieure ou égale à 12 heures.

8. Film de polymère hybride organique/hétérométallique, comprenant un polymère hybride organique/hétérométallique conforme à l'une des revendications 1 à 3.

9. Film de polymère hybride organique/hétérométallique, conforme à la revendication 8, dont l'épaisseur vaut au moins 100 nm et au plus 1 mm.

10. Film de polymère hybride organique/hétérométallique, conforme à la revendication 8 ou 9, dans lequel le métal de transition contenu dans ledit polymère hybride organique/hétérométallique est du fer ou du zinc.

11. Polymère hybride organique/multimétallique comportant plusieurs ligands organo-métalliques et plusieurs atomes de métal de transition, dans lequel

- il y a une partie linéaire dans laquelle lesdits plusieurs ligands organo-métalliques sont reliés, de manière linéaire, en prenant en sandwich entre eux chacun desdits plusieurs atomes de métal de transition,
- lesdits ligands organo-métalliques sont formés par raccordement de deux ligands à un connecteur,
- ledit connecteur est constitué d'un cycle benzénique central auquel deux fragments Ru(dppe)₂ sont raccordés par l'intermédiaire de deux groupes éthyne-diyle liés au cycle benzénique, et de deux groupes phényle raccordés auxdits deux fragments Ru(dppe)₂ par l'intermédiaire de deux autres groupes éthyne-diyle,
- lesdits ligands sont formés par des groupes terpyridyle raccordés respectivement auxdits deux groupes phényle dudit connecteur,
- et les groupes terpyridyle d'au moins deux différents desdits plusieurs ligands organo-métalliques sont liés à l'un desdits atomes de métal de transition par une liaison de coordination, ce qui fait que lesdits plusieurs ligands organo-métalliques sont raccordés tout en prenant en sandwich entre eux lesdits plusieurs atomes de métal de transition, en alternant avec ceux-ci.

12. Polymère hybride organique/multimétallique conforme à la revendication 11, dans lequel ledit métal de transition est le fer, le zinc, le cobalt ou le ruthénium.

13. Polymère hybride organique/multimétallique conforme à la revendication 11 ou 12, qui est linéaire.

14. Polymère hybride organique/multimétallique conforme à la revendication 11 ou 12, qui est ramifié.

15. Polymère hybride organique/multimétallique conforme à la revendication 14, comportant une partie ramifiée formée avec du 1,3,5-tris-[4-(2,2':6',2''-terpyridin-4'-yl)-phényl]-benzène.

16. Polymère hybride organique/multimétallique conforme à la revendication 14 ou 15, dans lequel la proportion de ladite partie ramifiée est d'au moins 10 parties en moles et d'au plus 30 parties en moles, par rapport au nombre total de moles de la partie linéaire et de la partie ramifiée constituant le polymère hybride organique/multimétallique.

17. Procédé de synthèse d'un polymère hybride organique/multimétallique, lequel procédé comporte les étapes suivantes :

- synthétiser un complexe organo-métallique binucléaire comportant deux fragments Ru(dppe)₂ en faisant réagir 1 équivalent molaire de diéthynyl-benzène et 2 équivalents molaires du composé de formule Ru(dppe)₂Cl(OTf), dans un solvant organique,
- synthétiser un ligand organo-métallique comportant un groupe terpyridyle terminal et deux fragments Ru(dppe)₂ en faisant réagir 2 équivalents molaires d'un dérivé de terpyridine comportant un groupe éthyne et un groupe terpyridyle avec 1 équivalent molaire de complexe organométallique binucléaire, dans un solvant organique,
- et synthétiser un polymère hybride organique/multimétallique linéaire en faisant réagir ledit ligand organo-métallique avec un composé de métal de transition, dans un solvant organique.

18. Procédé de synthèse d'un polymère hybride organique/multimétallique, conforme à la revendication 17, dans lequel on synthétise un polymère hybride organique/multi-métallique ramifié en faisant réagir ledit polymère hybride organique/multi-métallique linéaire, un composé ramifié en trois directions ou plus, comportant un motif ramificateur en son centre et un ligand à l'extrémité d'une ramification, et un composé d'un métal de transition.

19. Procédé de synthèse d'un polymère hybride organique/multimétallique, conforme à la revendication 18, dans lequel le composé ramifié est du 1,3,5-tris-[4-(2,2':6',2''-terpyridin-4'-yl)-phényl]-benzène.

20. Procédé de synthèse d'un polymère hybride organique/multimétallique, conforme à la revendication 18 ou 19, dans lequel la proportion de mélangeage dudit composé ramifié vaut au moins 10 parties en moles et au plus 30 parties

en moles pour 100 parties en moles, au total, de parties linéaires constituant le polymère hybride organique/multimétallique linéaire.

21. Procédé de synthèse d'un polymère hybride organique/multimétallique, conforme à la revendication 17, dans lequel on fait réagir 1,0 équivalent molaire du composé de métal de transition ou plus, par rapport audit ligand organo-métallique.
22. Procédé de synthèse d'un polymère hybride organique/multimétallique, conforme à l'une des revendications 17 à 21, dans lequel ledit composé de métal de transition est l'un des composés de formule $\text{Fe}(\text{BF}_4)_2$ ou $\text{Zn}(\text{NTf}_2)_2$.
23. Procédé de synthèse d'un polymère hybride organique/multimétallique, conforme à l'une des revendications 17 à 22, dans lequel la durée de la réaction dudit ligand organo-métallique et dudit composé de métal de transition est supérieure ou égale à 6 heures.
24. Film de polymère hybride organique/multimétallique, comprenant un polymère hybride organique/multimétallique conforme à l'une des revendications 11 à 16.
25. Film de polymère hybride organique/multimétallique, conforme à la revendication 24, dont l'épaisseur vaut au moins 100 nm et au plus 1 mm.

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9A




FIG. 9B




FIG. 10A




FIG. 10B




FIG. 10C




FIG. 11




FIG. 12A




FIG. 12B




FIG. 13




FIG. 14




FIG. 15A




FIG. 15B




FIG. 16




FIG. 17




FIG. 18A




FIG. 18B




FIG. 19




FIG. 20





FIG. 21



poly (Ru₂Zn)_x
X=100

FIG. 22




FIG. 23






FIG. 24



L-Ru(II)₂-L

$\text{Zn}(\text{NTf}_2)_2$
NMP, 24 h, 120 °C



$\text{poly}(\text{Ru}_2\text{Zn})_x$
X=100

FIG. 25




FIG. 26




FIG. 27




FIG. 28




FIG. 29




FIG. 30A




FIG. 30B




FIG. 30C




FIG. 30D




FIG. 31




FIG. 32




FIG. 33




FIG. 34




FIG. 35




FIG. 36




FIG. 37




FIG. 38




FIG. 39




FIG. 40




FIG. 41




FIG. 42




FIG. 43A




FIG. 43B




FIG. 44A





FIG. 44B



REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP 2014095275 A [0002]
- JP 2015012448 A [0002]
- JP 2012188517 A [0012]
- JP 2009265437 A [0012]

Non-patent literature cited in the description

- **HIGUCHI M.** *Polym. J.*, 2009, vol. 41, 511-520 [0013]
- **SATO T ; HIGUCHI M.** *Chem. Commun.*, 2013, vol. 49, 5256-5258 [0013]
- **BENAMEUR, A. ; BRIGNOU, P. ; DI PIAZZA, E. ; HERVAULT, Y.-M. ; NOREL, L. ; RIGAUT, S.** *New J. Chem.*, 2011, vol. 35 (10), 2105-2113 [0221]