



US 20170062718A1


(19) **United States**(12) **Patent Application Publication**
NUMATA et al.(10) **Pub. No.: US 2017/0062718 A1**(43) **Pub. Date: Mar. 2, 2017**(54) **ORGANIC LIGHT-EMITTING DEVICE**(71) Applicant: **Samsung Electronics Co., Ltd.**,
Suwon-si (KR)(72) Inventors: **Masaki NUMATA**, Suwon-si (KR);
Hiroshi MIYAZAKI, Suwon-si (KR);
Soonok JEON, Seoul (KR); **Hosuk KANG**,
Suwon-si (KR); **Sooghang IHN**, Hwaseong-si (KR)(21) Appl. No.: **15/012,222**(22) Filed: **Feb. 1, 2016**(30) **Foreign Application Priority Data**

Aug. 31, 2015 (KR) 10-2015-0123190

Publication Classification(51) **Int. Cl.****H01L 51/00** (2006.01)**C09K 11/02** (2006.01)**C09K 11/06** (2006.01)(52) **U.S. Cl.**CPC **H01L 51/005** (2013.01); **H01L 51/0072**
(2013.01); **H01L 51/0067** (2013.01); **H01L**
51/0055 (2013.01); **H01L 51/006** (2013.01);
C09K 11/06 (2013.01); **C09K 11/025**
(2013.01); **H01L 51/5016** (2013.01)(57) **ABSTRACT**An organic light-emitting device including a first electrode,
a second electrode facing the first electrode, and an organiclayer disposed between the first electrode and the second
electrode, wherein the organic layer comprises an emission
layer and satisfies Equations 1 and 2,

$$E_{T1(HOST)} - E_{T1(AD)} > 0.05 \text{ eV} \quad \text{Equation 1}$$

$$E_{S1(FD)} - E_{S1(AD)} < 0 \text{ eV}, \quad \text{Equation 2}$$

wherein in Equation 1, $E_{T1(HOST)}$ is a triplet energy (eV)
of the host, and $E_{T1(AD)}$ is a triplet energy (eV) of the
auxiliary dopant, and wherein in Equation 2, $E_{S1(FD)}$ is
a singlet energy (eV) of the fluorescent dopant, and
 $E_{S1(AD)}$ is a singlet energy (eV) of the auxiliary dopant,
wherein the emission layer comprises a host, an aux-
iliary dopant, and a fluorescent dopant, and wherein the
auxiliary dopant is selected from compounds repre-
sented by Formula 1:

Formula 1



wherein in Formula 1, Ar₁ and R₁₁ to R₁₆ are the same as
described in the specification.

FIG. 1



ORGANIC LIGHT-EMITTING DEVICE

CROSS-REFERENCE TO RELATED APPLICATION

[0001] This application claims priority to and the benefit of Korean Patent Application No. 10-2015-0123190, filed on Aug. 31, 2015, in the Korean Intellectual Property Office, the content of which is incorporated herein in its entirety by reference.

BACKGROUND

[0002] 1. Field

[0003] The present disclosure relates to organic light-emitting devices.

[0004] 2. Description of the Related Art

[0005] Compared to devices of the related art, organic light emitting devices (OLEDs) are self-emission devices that, have wider viewing angles, higher contrast ratios, shorter response times, and excellent brightness. OLEDs also exhibit excellent driving voltage, and response speed characteristics, and produce full-color images.

[0006] In an example, an organic light-emitting device may include an anode, a cathode, and an organic layer disposed between the anode and the cathode, wherein the organic layer may include an emission layer. A hole transport region may be disposed between the anode and the emission layer, and an electron transport region may be disposed between the emission layer and the cathode. Holes provided from the anode may move toward the emission layer through the hole transport region, and electrons provided from the cathode may move toward the emission layer through the electron transport region. Carriers, such as the holes and the electrons, recombine in the emission layer, thereby producing excitons. When these excitons change from an excited state to a ground state, light is generated.

[0007] Different types of organic light emitting devices are known. However, there still remains a need in OLEDs having low driving voltage, high efficiency, high brightness, and long lifespan.

SUMMARY

[0008] Provided are organic light-emitting devices having low driving voltage, high efficiency, high luminance, and long lifespan.

[0009] Additional aspects will be set forth in part in the description which follows and, in part, will be apparent from the description, or may be learned by practice of the presented exemplary embodiments.

[0010] According to an aspect of an exemplary embodiment, an organic light-emitting device includes:

[0011] a first electrode,

[0012] a second electrode facing the first electrode, and

[0013] an organic layer disposed between the first electrode and the second electrode,

[0014] wherein the organic layer includes an emission layer, and

[0015] wherein the organic layer satisfies Equations 1 and 2,

[0016] wherein the emission layer includes a host, an auxiliary dopant, and a fluorescent dopant, and


[0017] wherein the auxiliary dopant is selected from compounds represented by Formula 1:

$$E_{T1(HOST)} - E_{T1(AD)} > 0.05 \text{ electron Volts} \quad \text{Equation 1}$$


$$E_{S1(FD)} - E_{S1(AD)} < 0 \text{ electron Volts} \quad \text{Equation 2}$$

[0018] wherein in Equation 1, $E_{T1(HOST)}$ is a triplet energy (electron Volts) of the host, and $E_{T1(AD)}$ is a triplet energy (electron Volts) of the auxiliary dopant,


[0019] in Equation 2, $E_{S1(FD)}$ is a singlet energy (electron Volts) of the fluorescent dopant, and $E_{S1(AD)}$ is a singlet energy (electron Volts) of the auxiliary dopant,



Formula 1



Formula 2



Formula 2A



Formula 2B

[0020] Ar_1 in Formula 1 is a group represented by Formula 2,

[0021] ring A_1 in Formula 2 is a group represented by Formula 2A,

[0022] ring A_2 in Formula 2 is a group represented by Formula 2B,

[0023] X_1 in Formula 2B is $N(R_{17})$, O, or S,

[0024] R_1 to R_{17} in Formulae 1, 2, 2A, and 2B are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_1 - C_{60} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a sub-

stituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁)(Q₂)(Q₃), —N(Q₄)(Q₅), and —B(Q₆)(Q₇).

[0025] * in Formula 2 indicates a binding site to a neighboring atom,

[0026] at least one of substituents of the substituted C₁-C₆₀ alkyl group, substituted C₂-C₆₀ alkenyl group, substituted C₂-C₆₀ alkynyl group, substituted C₁-C₆₀ alkoxy group, substituted C₃-C₁₀ cycloalkyl group, substituted C₁-C₁₀ heterocycloalkyl group, substituted C₃-C₁₀ cycloalkenyl group, substituted C₁-C₁₀ heterocycloalkenyl group, substituted C₆-C₆₀ aryl group, substituted C₆-C₆₀ aryloxy group, substituted C₆-C₆₀ arylthio group, substituted C₁-C₆₀ heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, and substituted monovalent non-aromatic condensed heteropolycyclic group is selected from:

[0027] a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

[0028] a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₄)(Q₁₅), and —B(Q₁₆)(Q₁₇);

[0029] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

[0030] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic

acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₄)(Q₂₅), and —B(Q₂₆)(Q₂₇); and

[0031] —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₄)(Q₃₅), and —B(Q₃₆)(Q₃₇), and

[0032] Q₁ to Q₇, Q₁₁ to Q₁₇, Q₂₁ to Q₂₇, and Q₃₁ to Q₃₇ are each independently selected from a hydrogen, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.

BRIEF DESCRIPTION OF THE DRAWING

[0033] These and/or other aspects will become apparent and more readily appreciated from the following description of the exemplary embodiments, taken in conjunction with FIG. 1, which is a schematic cross-sectional view of an organic light-emitting device according to an embodiment.

DETAILED DESCRIPTION

[0034] Reference will now be made in detail to exemplary embodiments, examples of which are illustrated in the accompanying drawings, wherein like reference numerals refer to like elements throughout. In this regard, the present exemplary embodiments may have different forms and should not be construed as being limited to the descriptions set forth herein. Accordingly, the exemplary embodiments are merely described below, by referring to the FIGURES, to explain aspects. As used herein, the term “and/or” includes any and all combinations of one or more of the associated listed items. Expressions such as “at least one of,” “at least one selected from,” “one selected from,” and “one of,” when preceding a list of elements, modify the entire list of elements and do not modify the individual elements of the list.

[0035] It will be understood that when an element is referred to as being “on” another element, it can be directly in contact with the other element or intervening elements may be present therebetween. In contrast, when an element is referred to as being “directly on” another element, there are no intervening elements present.

[0036] It will be understood that, although the terms first, second, third etc. may be used herein to describe various elements, components, regions, layers, and/or sections, these

elements, components, regions, layers, and/or sections should not be limited by these terms. These terms are only used to distinguish one element, component, region, layer, or section from another element, component, region, layer, or section. Thus, a first element, component, region, layer, or section discussed below could be termed a second element, component, region, layer, or section without departing from the teachings of the present embodiments.

[0037] The terminology used herein is for the purpose of describing particular embodiments only and is not intended to be limiting. As used herein, the singular forms “a,” “an,” and “the” are intended to include the plural forms as well, unless the context clearly indicates otherwise.

[0038] The term “or” means “and/or.” It will be further understood that the terms “comprises” and/or “comprising,” or “includes” and/or “including” when used in this specification, specify the presence of stated features, regions, integers, steps, operations, elements, and/or components, but do not preclude the presence or addition of one or more other features, regions, integers, steps, operations, elements, components, and/or groups thereof.

[0039] Unless otherwise defined, all terms (including technical and scientific terms) used herein have the same meaning as commonly understood by one of ordinary skill in the art to which this general inventive concept belongs. It will be further understood that terms, such as those defined in commonly used dictionaries, should be interpreted as having a meaning that is consistent with their meaning in the context of the relevant art and the present disclosure, and will not be interpreted in an idealized or overly formal sense unless expressly so defined herein.

[0040] Exemplary embodiments are described herein with reference to cross section illustrations that are schematic illustrations of idealized embodiments. As such, variations from the shapes of the illustrations as a result, for example, of manufacturing techniques and/or tolerances, are to be expected. Thus, embodiments described herein should not be construed as limited to the particular shapes of regions as illustrated herein but are to include deviations in shapes that result, for example, from manufacturing. For example, a region illustrated or described as flat may, typically, have rough and/or nonlinear features. Moreover, sharp angles that are illustrated may be rounded. Thus, the regions illustrated in the figures are schematic in nature and their shapes are not intended to illustrate the precise shape of a region and are not intended to limit the scope of the present claims.

[0041] “About” or “approximately” as used herein is inclusive of the stated value and means within an acceptable range of deviation for the particular value as determined by one of ordinary skill in the art, considering the measurement in question and the error associated with measurement of the particular quantity (i.e., the limitations of the measurement system). For example, “about” can mean within one or more standard deviations, or within $\pm 30\%$, 20% , 10% , 5% of the stated value.

[0042] An organic light-emitting device according to an embodiment of the present disclosure includes:

[0043] a first electrode,

[0044] a second electrode facing the first electrode, and

[0045] an organic layer disposed between the first electrode and the second electrode,

[0046] wherein the organic layer includes an emission layer, and

[0047] wherein the emission layer includes a host, an auxiliary dopant, and a fluorescent dopant.

[0048] The organic light-emitting device satisfies Equations 1 and 2:

$$E_{T1(HOST)} - E_{T1(AD)} > 0.05 \text{ electron Volts (eV)} \quad \text{Equation 1}$$

$$E_{S1(FD)} - E_{S1(AD)} < 0 \text{ eV.} \quad \text{Equation 2}$$

[0049] In Equations 1 and 2,

[0050] $E_{T1(HOST)}$ is a triplet energy (eV) of the host in the emission layer, and

[0051] $E_{T1(AD)}$ is a triplet energy (eV) of the auxiliary dopant in the emission layer, and


[0052] $E_{S1(FD)}$ is a singlet energy (eV) of the fluorescent dopant in the emission layer, and

[0053] $E_{S1(AD)}$ is a singlet energy (eV) of the auxiliary dopant in the emission layer.

[0054] The organic light-emitting device satisfies Equation 1 (for example, $E_{T1(HOST)} - E_{T1(AD)}$ equal to or greater than 0.10 eV and less than or equal to 0.65 eV), which allows to prevent energy of triplet excitons generated from the auxiliary dopant in the emission layer, from travelling to the host in the emission layer, thereby decreasing a probability of losing the triplet excitons along a route other than a light-emitting route. Accordingly, the organic light-emitting device may have high efficiency.


[0055] The organic light-emitting device satisfies Equation 2 (for example, $E_{S1(FD)} - E_{S1(AD)}$ equal to or greater than -0.4 eV and less than or equal to -0.05 eV), which allows energy of singlet excitons generated from the auxiliary dopant in the emission layer, to rapidly travel to the fluorescent dopant. Accordingly, substantially, light is emitted from only the fluorescent dopant in the emission layer of the organic light-emitting device, and thus, a fluorescence spectrum having excellent color purity based on the fluorescent dopant may be realized. Moreover, fluorescence having a relatively short exciton lifespan may occur, and thus, a decline in efficiency under high luminance conditions (generally referred to as a roll-off phenomenon), which may occur due to interaction between a plurality of excitons (exciton-exciton interaction) or interaction between an exciton and a charge (a hole or electron) (exciton-polaron interaction), may be limited. Accordingly, the organic light-emitting device may have high efficiency. Further, the auxiliary dopant comes to have a short exciton lifespan, and therefore, a probability of chemical or physical degradation which may occur in an exciton state of the auxiliary dopant may decrease. Accordingly, the organic light-emitting device satisfying Equation 2 may have improved durability.

[0056] The auxiliary dopant in the emission layer may be selected from compounds represented by Formula 1:




Formula 1

-continued



Formula 2



Formula 2A




Formula 2B

[0057] Ar₁ in Formula 1 is a group represented by Formula 2. Formula 2 may be understood by referring to a description thereof provided later.


[0058] Ring A₁ in Formula 2 is condensed sharing carbons with a neighboring 5-membered ring and ring A₂. Ring A₁ is a group represented by Formula 2A.

[0059] Ring A₂ in Formula 2 is condensed sharing carbons with ring A₁ and a neighboring 6-membered ring. Ring A₂ is a group represented by Formula 2B.

[0060] For example, Ar₁ in Formula 1 may be selected from groups represented by Formulae 2-1 to 2-6:




Formula 2-1




Formula 2-2


-continued




Formula 2-3



Formula 2-4



Formula 2-5



Formula 2-6

[0061] In Formulae 2-1 to 2-6, descriptions of R₁ to R₁₀ and X₁ are the same as provided herein, and * indicates a binding site to a neighboring atom.

[0062] X₁ in Formulae 2B and 2-1 to 2-6 is N(R₁₇), O, or S.

[0063] For example, X₁ in Formulae 2B and 2-1 to 2-6 may be N(R₁₇), but is not limited thereto.

[0064] R₁ to R₁₇ in Formulae 1, 2, 2A, 2B, and 2-1 to 2-6 may be each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or

unsubstituted C_1 - C_{60} alkyl group, a substituted or unsubstituted C_2 - C_{60} alkenyl group, a substituted or unsubstituted C_2 - C_{60} alkynyl group, a substituted or unsubstituted C_3 - C_{10} alkoxy group, a substituted or unsubstituted C_3 - C_{10} cycloalkyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkyl group, a substituted or unsubstituted C_3 - C_{10} cycloalkenyl group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenyl group, a substituted or unsubstituted C_6 - C_{60} aryl group, a substituted or unsubstituted C_6 - C_{60} aryloxy group, a substituted or unsubstituted C_6 - C_{60} arylthio group, a substituted or unsubstituted C_1 - C_{60} heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, $-\text{Si}(\text{Q}_1)(\text{Q}_2)(\text{Q}_3)$, $-\text{N}(\text{Q}_4)(\text{Q}_5)$, and $-\text{B}(\text{Q}_6)(\text{Q}_7)$.

[0065] For example, X_1 in Formulae 2B and 2-1 to 2-6 may be $\text{N}(\text{R}_{17})$,

[0066] R_{17} may be selected from

[0067] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group; and

[0068] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group, each substituted with at least one selected from a deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, and $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, and

[0069] Q_{31} to Q_{33} may be each independently selected from a hydrogen, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0070] According to an embodiment, X_1 in Formulae 2B and 2-1 to 2-6 may be $\text{N}(\text{R}_{17})$, O, or S,

[0071] R_{17} may be selected from

[0072] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group; and

[0073] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group, each substituted with at least one selected from a deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, and $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, and

[0074] Q_{31} to Q_{33} may be each independently selected from a hydrogen, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0075] In another example, R_1 to R_{14} in Formulae 1, 2, 2A, and 2-1 to 2-6 may be each independently selected from

[0076] a hydrogen, a deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

[0077] a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from a deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof;

[0078] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group, each substituted with at least one selected from a deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, and $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, and

benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group;

[0079] a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, and —Si(Q₃₁)(Q₃₂)(Q₃₃); and

[0080] —Si(Q₁)(Q₂)(Q₃), and

[0081] Q₁ to Q₃ and Q₃₁ to Q₃₃ may be each independently selected from a hydrogen, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0082] According to an embodiment, R₁ to R_{1,4} in Formulae 1, 2, 2A, and 2-1 to 2-6 may be each independently selected from

[0083] a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, and a C₁-C₂₀ alkoxy group;

[0084] a phenyl group, a biphenyl group, and a terphenyl group;

[0085] a phenyl group, a biphenyl group, and a terphenyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, and —Si(Q₃₁)(Q₃₂)(Q₃₃); and

[0086] —Si(Q₁)(Q₂)(Q₃), and

[0087] Q₁ to Q₃ and Q₃₁ to Q₃₃ may be each independently selected from a hydrogen, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, but embodiments are not limited thereto.

[0088] In another example, R_{1,5} and R_{1,6} in Formula 1 may be each independently selected from

[0089] a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl


group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group; and

[0090] a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a cyclopentyl group, a cyclohexyl group, a

cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, and


[0091] Q_{31} to Q_{33} may be each independently selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

[0092] The auxiliary dopant in the emission layer may be selected from Compounds 1 to 39:




1


-continued



2




3




4

-continued




5


-continued




8




6



9




7




10

-continued




11


-continued




14




12



15




13




16

-continued




17


-continued




20




18



19




21




22

-continued




23


-continued




27




24




28



25




26




29

-continued




30


-continued




34




31




35




32



36





33




37

38




[0095] The host may be selected from compounds including a fluorene ring, a carbazole ring, a dibenzofuran ring, a dibenzothiophene ring, an indenocarbazole ring, an indolocarbazole ring, a benzofurocarbazole ring, a benzothienocarbazole ring, an acridine ring, a dihydroacridine ring, a triindolobenzene ring, or any combination thereof. Alternatively, the host may be a silicon compound or a phosphine oxide compound.


Formula 11-1




Formula 11-2




Formula 11-3



Formula 13



Formula 14



[0104] a phenylene group, a pyridinylene group, a pyrimidinylene group, a pyrazinylene group, a pyridazinylene group, a triazinylene group, a naphthylene group, a fluorenylene group, a carbazoylene group, a dibenzofuranylene group, and a dibenzothiophenylene group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, —CF₃, —CF₂H, —CFH₂, a phenyl group, a phenyl group substituted with a cyano group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl

group, a triazinyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and $-\text{Si}(\text{Q}_{71})(\text{Q}_{72})(\text{Q}_{73})$.

[0105] a_{11} to a_{13} and a_{21} are each independently an integer selected from 0 to 5, two or more groups L_{11} are identical to or different from each other when a_{11} is 2 or more, two or more groups L_{12} are identical to or different from each other when a_{12} is 2 or more, two or more groups L_{13} are identical to or different from each other when a_{13} is 2 or more, and two or more groups L_{21} are identical to or different from each other when a_{21} is 2 or more.

[0106] CY_3 and CY_4 are each independently selected from a benzene, a naphthalene, a fluorene, a carbazole, a benzocarbazole, an indolocarbazole, a dibenzofuran, and a dibenzothiophene.

[0107] A_2 is selected from

[0108] a single bond, a $\text{C}_1\text{-C}_4$ alkylene group, and a $\text{C}_2\text{-C}_4$ alkenylene group; and

[0109] a $\text{C}_1\text{-C}_4$ alkylene group and a $\text{C}_2\text{-C}_4$ alkenylene group, each substituted with at least one selected from a deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a $\text{C}_1\text{-C}_{10}$ alkyl group, a $\text{C}_1\text{-C}_{10}$ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and $-\text{Si}(\text{Q}_{81})(\text{Q}_{82})(\text{Q}_{83})$.

[0110] T_{11} to T_{16} , R_{22} , R_{30} , and R_{40} are each independently selected from a hydrogen, a deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group (CN), a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ alkyl group, a substituted or unsubstituted $\text{C}_2\text{-C}_{60}$ alkenyl group, a substituted or unsubstituted $\text{C}_2\text{-C}_{60}$ alkynyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ alkoxy group, a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a substituted or unsubstituted $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a substituted or unsubstituted $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ aryl group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ aryloxy group, a substituted or unsubstituted $\text{C}_6\text{-C}_{60}$ arylthio group, a substituted or unsubstituted $\text{C}_1\text{-C}_{60}$ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and $-\text{Si}(\text{Q}_{91})(\text{Q}_{92})(\text{Q}_{93})$.

[0111] b_3 and b_4 are each independently an integer selected from 0 to 10,

[0112] c_1 is 0, 1, 2, or 3,

[0113] * indicates a binding site to a neighboring atom,


[0114] at least one of substituents of the substituted $\text{C}_1\text{-C}_{60}$ alkyl group, substituted $\text{C}_2\text{-C}_{60}$ alkenyl group, substituted $\text{C}_2\text{-C}_{60}$ alkynyl group, substituted $\text{C}_3\text{-C}_{10}$ cycloalkyl group, substituted $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, substituted $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, substituted $\text{C}_1\text{-C}_{10}$ heterocy-

cloalkenyl group, substituted $\text{C}_6\text{-C}_{60}$ aryl group, substituted $\text{C}_6\text{-C}_{60}$ aryloxy group, substituted $\text{C}_6\text{-C}_{60}$ arylthio group, substituted $\text{C}_1\text{-C}_{60}$ heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, and substituted monovalent non-aromatic condensed heteropolycyclic group is selected from a deuterium, $-\text{F}$, $-\text{Cl}$, $-\text{Br}$, $-\text{I}$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_2\text{-C}_{60}$ alkenyl group, a $\text{C}_2\text{-C}_{60}$ alkynyl group, a $\text{C}_1\text{-C}_{60}$ alkoxy group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_6\text{-C}_{60}$ aryloxy group, a $\text{C}_6\text{-C}_{60}$ arylthio group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, and $-\text{Si}(\text{Q}_{101})(\text{Q}_{102})(\text{Q}_{103})$, and


[0115] Q_{41} to Q_{43} , Q_{51} , Q_{52} , Q_{61} , Q_{62} , Q_{71} to Q_{73} , Q_{81} to Q_{83} , Q_{91} to Q_{93} , and Q_{101} to Q_{103} are each independently selected from a hydrogen, a deuterium, a $\text{C}_1\text{-C}_{60}$ alkyl group, a $\text{C}_1\text{-C}_{60}$ alkoxy group, a $\text{C}_3\text{-C}_{10}$ cycloalkyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkyl group, a $\text{C}_3\text{-C}_{10}$ cycloalkenyl group, a $\text{C}_1\text{-C}_{10}$ heterocycloalkenyl group, a $\text{C}_6\text{-C}_{60}$ aryl group, a $\text{C}_1\text{-C}_{60}$ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

[0116] Ar_{11} and Ar_{12} in Formula 11-1 may be each independently selected from groups represented by Formulae 13-1 to 13-8 and 14-1 to 14-8:

Formula 13-1




Formula 13-2




-continued


Formula 13-3




Formula 13-4




Formula 13-5



Formula 13-6




Formula 13-7




-continued


Formula 13-8




Formula 14-1




Formula 14-2




Formula 14-3




Formula 14-4




-continued




Formula 14-5



Formula 14-6



Formula 14-7



Formula 14-8

[0117] In Formulae 13-1 to 13-8 and 14-1 to 14-8,

[0118] X_{12} and X_{14} are each independently $C(R_{37})(R_{38})$, $N(R_{39})$, O, or S,

[0119] X_{15} and A_2 may be understood by referring to descriptions thereof provided herein,

[0120] R_{31} to R_{39} may be each independently understood by referring to a description of R_{30} provided herein,

[0121] R_{41} to R_{44} may be each independently understood by referring to a description of R_{40} provided herein, and

[0122] * indicates a binding site to a neighboring atom.

[0123] According to an embodiment, in Formulae 13, 14, 13-1 to 13-8, and 14-1 to 14-8,

[0124] A_2 may be selected from

[0125] a single bond, a C_1 - C_2 alkenylene group, and a C_2 alkenylene group; and

[0126] a C_1 - C_2 alkenylene group and a C_2 alkenylene group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a carbazolyl group, a dibenzofuran group, a dibenzothiophenyl group, and —Si(Q_{81})(Q_{82})(Q_{83}),

[0127] R_{22} , R_{30} to R_{39} , and R_{40} to R_{44} may be each independently selected from

[0128] a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

[0129] a C_1 - C_{20} alkyl group and a C_1 - C_{20} alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuran group, and a dibenzothiophenyl group;

[0130] a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuran group, and a dibenzothiophenyl group;

[0131] a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuran group, and a dibenzothiophenyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuran group, and a dibenzothiophenyl group; and


[0132] —Si(Q_{91})(Q_{92})(Q_{93}), and

[0133] Q_{81} to Q_{83} and Q_{91} to Q_{93} may be each independently selected from a hydrogen, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, but embodiments are not limited thereto.


[0134] According to another embodiment, Ar_{11} and Ar_{12} in Formula 11-1 may be each independently selected from

groups represented by Formulae 17-1 to 17-19 and 18-1 to 18-8, but embodiments are not limited thereto:


-continued




Formula 17-1




Formula 17-2




Formula 17-3




Formula 17-4




Formula 17-5




Formula 17-6




Formula 17-7




Formula 17-8




Formula 17-9




Formula 17-10



Formula 17-11




Formula 17-12




Formula 17-13


-continued




Formula 17-14




Formula 17-15




Formula 17-16



Formula 17-17




Formula 17-18




Formula 17-19


-continued




Formula 18-1




Formula 18-2




Formula 18-3




Formula 18-4




Formula 18-5



Formula 18-6



Formula 18-7



Formula 18-8

[0135] In Formulae 17-1 to 17-19 and 18-1 to 18-8,

[0136] X_{12} and X_{14} are each independently $C(R_{37})(R_{38})$, $N(R_{39})$, O, or S,

[0137] X_{15} is $N(R_{17})$, O, or S,

[0138] R' and R'' are each independently selected from a hydrogen, a deuterium, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group,

[0139] R_{22} , R_{30} , and R_{40} may be understood by referring to descriptions thereof provided herein,

[0140] R_{30a} to R_{30c} may be understood by referring to the description of R_{30} , and

[0141] * indicates a binding site to a neighboring atom.

[0142] For example, in Formulae 17-1 to 17-19 and 18-1 to 18-8,

[0143] R_{22} , R_{30} , R_{30a} to R_{30c} , and R_{40} may be each independently selected from

[0144] a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, —CF₃, —CF₂H, and —CFH₂;


[0145] a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

[0146] a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, —CF₃, —CF₂H, —CFH₂, a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and


[0147] —Si(Q₉₁)(Q₉₂)(Q₉₃), and

[0148] Q₉₁ to Q₉₃ may be each independently selected from a hydrogen, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, but embodiments are not limited thereto.


[0149] L₁₁ to L₁₃ and L₂₁ in Formulae 11-1 to 11-3 may be each independently selected from a single bond, O, S, Si(Q₆₁)(Q₆₂), and a group represented by one of Formulae 3-1 to 3-56:




Formula 3-1




Formula 3-2




Formula 3-3




Formula 3-4




Formula 3-5




Formula 3-6




Formula 3-7




Formula 3-8




Formula 3-9




Formula 3-10




Formula 3-11



Formula 3-12















Formula 3-13



Formula 3-14

-continued

-continued



Formula 3-15

Formula 3-16

Formula 3-17

Formula 3-18

Formula 3-19

Formula 3-20

Formula 3-21

Formula 3-22










Formula 3-23

Formula 3-24

Formula 3-25

Formula 3-26

-continued



Formula 3-27

Formula 3-28

Formula 3-29

Formula 3-30

Formula 3-31










Formula 3-32

Formula 3-33

Formula 3-34


Formula 3-35

-continued




-continued

Formula 3-36




Formula 3-45

Formula 3-37




Formula 3-46

Formula 3-38




Formula 3-47

Formula 3-39




Formula 3-48

Formula 3-40




Formula 3-49

Formula 3-41




Formula 3-50

Formula 3-42




Formula 3-51

Formula 3-43




Formula 3-52

Formula 3-44




Formula 3-53


-continued



Formula 3-54



Formula 3-55



Formula 3-56

[0150] In Formulae 3-1 to 3-56,

[0151] Y_1 is selected from O, S, $C(Z_3)(Z_4)$, and $N(Z_5)$,

[0152] Z_1 to Z_5 are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, —CF₃, —CF₂H, —CFH₂, a phenyl group, a phenyl group substituted with a cyano group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and —Si(Q_{71})(Q_{72})(Q_{73}),

[0153] Q_{71} to Q_{73} are each independently selected from a hydrogen, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group,

[0154] d_4 is an integer selected from 0 to 4,

[0155] d_3 is an integer selected from 0 to 3,


[0156] d_2 is an integer selected from 0 to 2, and

[0157] * and *' each indicate a binding site to a neighboring atom.


[0158] According to an embodiment, L_{11} to L_{13} and L_{21} in Formulae 11-1 to 11-3 may be each independently selected from a single bond, O, S, Si(Q_{61})(Q_{62}), and a group represented by one of Formulae 3-1 to 3-56, and at least one of L_{11} in the number of a_{11} , at least one of L_{12} in the number of a_{12} , at least one of L_{13} in the number of a_{13} , or at least one of L_{21} in the number of a_{21} may be each independently selected from O, Si(Q_{61})(Q_{62}), and a group represented by one of Formulae 3-15 to 3-56.

[0159] According to another embodiment, a group represented by $*(L_{11})_{a_{11}}*$, $*(L_{12})_{a_{12}}*$, $*(L_{13})_{a_{13}}*$, and $*(L_{21})_{a_{21}}*$ may be selected from groups represented by Formulae 3-41 to 3-56, but embodiments are not limited thereto.


[0160] In some embodiments, a group represented by $*(L_{11})_{a_{11}}*$, $*(L_{12})_{a_{12}}*$, $*(L_{13})_{a_{13}}*$, and $*(L_{21})_{a_{21}}*$ may be a single bond or a group represented by one of Formulae 4-1 to 4-42, but embodiments are not limited thereto:




Formula 4-1




Formula 4-2




Formula 4-3




Formula 4-4




Formula 4-5




Formula 4-6




Formula 4-7



Formula 4-8




Formula 4-9




Formula 4-10


-continued




Formula 4-11




Formula 4-12




Formula 4-13




Formula 4-14




Formula 4-15




Formula 4-16




Formula 4-17




Formula 4-18




-continued




Formula 4-19




Formula 4-20




Formula 4-21




Formula 4-22




Formula 4-23




Formula 4-24




Formula 4-25




-continued




Formula 4-26




Formula 4-27




Formula 4-28



Formula 4-29




Formula 4-30




Formula 4-31


-continued




Formula 4-32




Formula 4-33




Formula 4-34



Formula 4-35




Formula 4-36




Formula 4-37

-continued


Formula 4-38




Formula 4-39




Formula 4-40



Formula 4-41



Formula 4-42



[0161] In Formulae 4-1 to 4-42,

[0162] X_{21} is N or C(Z_{21}), X_{22} is N or C(Z_{22}), X_{23} is N or C(Z_{23}), X_{24} is N or C(Z_{24}), X_{31} is N or C(Z_{31}), X_{32} is N or C(Z_{32}), X_{33} is N or C(Z_{33}), X_{34} is N or C(Z_{34}), X_{41} is N or C(Z_{41}), X_{42} is N or C(Z_{42}), X_{43} is N or C(Z_{43}), and X_{44} is N or C(Z_{44}), wherein each of X_{21} to X_{24} is not simultaneously N, and wherein each of X_{31} to X_{34} is not simultaneously N, and wherein each of X_{41} to X_{44} is not simultaneously N,

[0163] Z_{21} to Z_{24} , Z_{31} to Z_{34} , and Z_{41} to Z_{44} are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, —CF₃, —CF₂H, —CFH₂, a phenyl group, a phenyl group substituted with a cyano group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a triazinyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and —Si(Q_{71})(Q_{72})(Q_{73}),

[0164] Q_{71} to Q_{73} are each independently selected from a hydrogen, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, and

[0165] * and *' each indicate a binding site to a neighboring atom.

[0166] Two of X_1 to X_3 or all three of X_1 to X_3 in Formula 11-2 may be N.

[0167] For example, T_{11} to T_{16} in Formula 11-2 may be each independently selected from

[0168] a hydrogen, a deuterium, —F, a cyano group, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, —CF₃, —CF₂H, and —CFH₂;

[0169] a C_1 - C_{10} alkyl group and a C_1 - C_{10} alkoxy group, each substituted with at least one selected from a deuterium, —F, a cyano group, —CF₃, —CF₂H, and —CFH₂;

[0170] a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

[0171] a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from a deuterium, —F, a cyano group, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, —CF₃, —CF₂H, —CFH₂, a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and

[0172] —Si(Q_{91})(Q_{92})(Q_{93}), and

[0173] Q_{91} to Q_{93} may be each independently selected from a hydrogen, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, but embodiments are not limited thereto.

[0174] T_{21} and T_{22} in Formula 11-3 may be each independently selected from *(L_{21})_{a21}-Si(Q_{41})(Q_{42})(Q_{43}) and *(L_{21})_{a21}-P(=O)(Q_{51})(Q_{52}), and Q_{41} to Q_{43} , Q_{51} , and Q_{52} may be each independently selected from

[0175] a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and


[0176] a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from a deuterium, —F, a cyano group, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, —CF₃, —CF₂H, —CFH₂, a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group,

[0177] but embodiments are not limited thereto.


[0178] According to an embodiment, the host may include at least one cyano group.

For example, the host may be a compound represented by one of Formulae 11-1 to 11-3 and having at least one cyano group, but is not limited thereto.


[0179] For example, the host may be selected from Compounds H1 to H24:




H1




H5




H2




H6




H3



H7




H4




H8

-continued




H9

-continued




H14


H10




H11




H15




H12



H16




H13




H17


-continued




H18



H19




H20




H21


-continued



H22



H23




H24

[0180] The emission layer further includes a fluorescent dopant in addition to the host and auxiliary dopants as described above. The organic light-emitting device satisfies Equation 2, and therefore, the fluorescent dopant in the emission layer substantially contributes to light-emitting of the emission layer. Accordingly, the organic light-emitting device may have high efficiency due to use of the auxiliary dopant, which is a thermally activated delayed fluorescence emitter, and may emit light having excellent color purity due to use of the fluorescent dopant.


[0181] The fluorescent dopant may be selected from a condensed polycyclic compound and a styryl compound.

[0182] For example, the fluorescent dopant may include a naphthalene core, a fluorene core, a spiro-bifluorene core, a benzofluorene core, a dibenzofluorene core, a phenanthrene core, an anthracene core, a fluoranthene core, a triphenylene core, a pyrene core, a chrysene core, a naphthacene core, a picene core, a perylene core, a pentaphene core, an indenoanthracene core, a tetracene core, a bisanthracene core, a core represented by one of Formulae 501-1 to 501-18, or any combination thereof, but is not limited thereto:


-continued




Formula 501-1




Formula 501-2




Formula 501-3




Formula 501-4




Formula 501-5




Formula 501-6




Formula 501-7



Formula 501-8




Formula 501-9




Formula 501-10

-continued




Formula 501-11


-continued




Formula 501-15




Formula 501-12




Formula 501-16



Formula 501-13




Formula 501-17




Formula 501-18

[0183] Alternatively, the fluorescent dopant may be selected from a styryl-amine compound and a styryl-carbazole compound, but is not limited thereto.

[0184] According to an embodiment, the fluorescent dopant may be selected from compounds represented by Formula 501:



Formula 501-14



Formula 501

[0185] In Formula 501,

[0186] Ar_{501} is selected from

[0187] a naphthalene group, a fluorene group, a spirobifluorene group, a benzofluorene group, a dibenzofluorene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a tetracene group, a bisanthracene group, and a group represented by one of Formulae 501-1 to 501-18; and

[0188] a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a tetracene group, a bisanthracene group, and a group represented by one of Formulae 501-1 to 501-18, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{60} alkyl group, a C_2 - C_{60} alkenyl group, a C_2 - C_{60} alkynyl group, a C_1 - C_{60} alkoxy group, a C_3 - C_{10} cycloalkyl group, a C_1 - C_{10} heterocycloalkyl group, a C_3 - C_{10} cycloalkenyl group, a C_1 - C_{10} heterocycloalkenyl group, a C_6 - C_{60} aryl group, a C_6 - C_{60} aryloxy group, a C_6 - C_{60} arylthio group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q_{501})(Q_{502})(Q_{503}) (wherein Q_{501} to Q_{503} are each independently selected from a hydrogen, a C_1 - C_{60} alkyl group, a C_1 - C_{60} alkoxy group, a C_6 - C_{60} aryl group, a C_1 - C_{60} heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group),

[0189] L_{501} to L_{503} are each independently selected from a substituted or unsubstituted C_3 - C_{10} cycloalkylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkylene group, a substituted or unsubstituted C_3 - C_{10} cycloalkenylene group, a substituted or unsubstituted C_1 - C_{10} heterocycloalkenylene group, a substituted or unsubstituted C_6 - C_{60} arylene group, a substituted or unsubstituted C_1 - C_{60} heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

[0190] R_{501} and R_{502} are each independently selected from

[0191] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazole group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and

[0192] a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl

group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group,

[0193] $xd1$ to $xd3$ are each independently selected from 0, 1, 2, and 3, and

[0194] $xd4$ is selected from 0, 1, 2, 3, 4, 5, and 6.

[0195] For example, in Formula 501,

[0196] Ar_{501} may be selected from

[0197] a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a tetracene group, a bisanthracene group, and a group represented by one of Formulae 501-1 to 501-18; and


[0198] a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenanthrene group, an anthracene group, a fluoranthene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a tetracene group, a bisanthracene group, and a group represented by one of Formulae 501-1 to 501-18, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a carbazolyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a quinolinyl group, an isoquinolinyl group, and —Si(Q_{501})(Q_{502})(Q_{503}) (wherein Q_{501} to Q_{503} may be each independently selected from a hydrogen, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group),

[0199] L_{501} to L_{503} may be understood by referring to a description of L_{11} provided herein,


[0200] $xd1$ to $xd3$ may be each independently selected from 0, 1, and 2,

[0201] $xd4$ may be selected from 0, 1, 2, and 3, but embodiments are not limited thereto.


[0202] The fluorescent dopant may include, for example, at least one compound selected from Compounds FD(1) to FD(14) and FD1 to FD13:




Compound FD(1)




Compound FD(2)



Compound FD(3)




Compound FD(4)




Compound FD(5)

-continued

Compound FD(6)





Compound FD(7)





Compound FD(8)

Compound FD(9)




Compound FD(10)

Compound FD(11)




-continued


Compound FD(12)




Compound FD(13)




Compound FD(14)




FD1




FD2




-continued
FD3




FD4




FD5




FD6



FD7





[0203] FIG. 1 is a schematic cross-sectional view of an organic light-emitting device **10** according to an embodiment. Hereinafter, the structure of an organic light-emitting device according to an embodiment and a method of manufacturing an organic light-emitting device, according to an embodiment, will be described in connection with FIG. 1. The organic light-emitting device **10** includes a first electrode **11**, an organic layer **15**, and a second electrode **19**, which are sequentially stacked on each other in this order.

[0204] A substrate may be additionally disposed under the first electrode **11** or on the second electrode **19**. As the substrate, any substrate that is used in a general organic light-emitting device may be used, and the substrate may be a glass or transparent plastic substrate with excellent mechanical strength, thermal stability, transparency, surface smoothness, ease of handling, and water-resistance.

[0205] For example, the first electrode **11** may be formed by depositing or sputtering a material for forming a first electrode on the substrate. The first electrode **11** may be an anode. The material for forming a first electrode may be selected from materials having a high work function to facilitate hole injection. The first electrode **11** may be a reflective electrode, a semi-transmissive electrode, or a

transmissive electrode. The material for forming a first electrode may be, for example, indium tin oxide (ITO), indium zinc oxide (IZO), tin oxide (SnO_2), or zinc oxide (ZnO). Alternatively, the material for forming a first electrode may be metal, such as magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag).

[0206] The first electrode **11** may have a single-layer structure or a multi-layer structure including two or more layers. For example, the first electrode **11** may have a three-layered structure of ITO/Ag/ITO, but the structure of the first electrode **11** is not limited thereto.

[0207] The organic layer **15** is disposed on the first electrode **11**.

[0208] The organic layer **15** may include a hole transport region, an emission layer, and an electron transport region.

[0209] The hole transport region may be disposed between the first electrode **11** and the emission layer.

[0210] The hole transport region may include at least one of a hole injection layer, a hole transport layer, an electron blocking layer, and a buffer layer.

[0211] The hole transport region may include only either a hole injection layer or a hole transport layer. Alternatively,

the hole transport region may have a structure of hole injection layer/hole transport layer or a structure of hole injection layer/hole transport layer/electron blocking layer, wherein layers of each structure are sequentially stacked in this stated order from the first electrode 11.


[0212] When the hole transport region includes a hole injection layer, the hole injection layer may be formed on the first electrode 11 by using any one of various methods, such as vacuum deposition, spin coating, casting, and Langmuir-Blodgett (LB) method.

[0213] When the hole injection layer is formed by vacuum deposition, the deposition conditions may vary according to the material that is used to form the hole injection layer and the structure and thermal characteristics of the hole injection layer. For example, the deposition conditions may include a deposition temperature of about 100 to about 500° C., a vacuum pressure of about 10^{-8} to about 10^{-3} torr, and a deposition rate of about 0.01 to about 100 angstrom per second (Å/sec), but are not limited thereto.

[0214] When the hole injection layer is formed using spin coating, coating conditions may vary according to the material that is used to form the hole injection layer and the structure and thermal characteristics of the hole injection layer. For example, a coating speed may be from about 2,000 revolutions per minute (rpm) to about 5,000 rpm, and a temperature at which heat treatment is performed to remove a solvent after coating may be from about 80° C. to about 200° C. However, the coating conditions are not limited thereto.


[0215] Conditions for forming the hole transport layer and the electron blocking layer may be understood by referring to the conditions for forming the hole injection layer.

[0216] The hole transport region may include, for example, at least one selected from m-MTDATA, TDATA, 2-TNATA, NPB, β -NPB, TPD, Spiro-TPD, Spiro-NPB, methylated NPB, TAPC, HMTPD, 4,4',4"-tris(N-carbazolyl) triphenylamine (TCTA), polyaniline/dodecylbenzenesulfonic acid (Pani/DBSA), poly(3,4-ethylenedioxythiophene)/poly(4-styrenesulfonate) (PEDOT/PSS), polyaniline/camphor sulfonic acid (Pani/CSA), (polyaniline)/poly(4-styrenesulfonate) (PANI/PSS), a compound represented by Formula 201, and a compound represented by Formula 202:




m-MTDATA


-continued



TDATA





2-TNATA




NPB


-continued

 β -NPB


TPD



Spiro-TPD




Spiro-NPB




methylated NPB

-continued




TAPC




HMTPD

Formula 201



Formula 202



[0217] Ar_{101} and Ar_{102} in Formula 201 may be each independently selected from

[0218] a phenylene group, a pentalenylene group, an indenylene group, a naphthylene group, an azulenylene group, a heptalenylene group, an acenaphthylene group, a fluorenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylene group, a fluoranthenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene-

nylene group, a naphthacenylenylene group, a picenylene group, a perylenylene group, and a pentacenylene group; and

[0219] a phenylene group, a pentalenylenylene group, an indenylene group, a naphthylene group, an azulenylenylene group, a heptalenylene group, an acenaphthylenylene group, a fluorenylenylene group, a phenalenylene group, a phenanthrenylene group, an anthracenylenylene group, a fluoranthenylenylene group, a triphenylenylene group, a pyrenylene group, a chrysenylene group, a naphthacenylenylene group, a picenylene group, a perylenylene group, and a pentacenylene group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

[0220] xa and xb in Formula 201 may be each independently an integer selected from 0 to 5, or 0, 1 or 2. For example, xa may be 1, and xb may be 0, but embodiments are not limited thereto.

[0221] R₁₀₁ to R₁₀₈, R₁₁₁ to R₁₁₉, and R₁₂₁ to R₁₂₄ in Formulae 201 and 202 may be each independently selected from

[0222] a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group (for example, a methyl group, an ethyl group, a propyl group, a butyl group, a pentyl group, a hexyl group, and so on), and a C₁-C₁₀ alkoxy group (for example, a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a pentoxy group, and so on);

[0223] a C₁-C₁₀ alkyl group and a C₁-C₁₀ alkoxy group, each substituted with one or more selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof;

[0224] a phenyl group, a naphthyl group, an anthracenyl group, a fluorenyl group, and a pyrenyl group; and

[0225] a phenyl group, a naphthyl group, an anthracenyl group, a fluorenyl group, and a pyrenyl group, each substituted with one or more selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, and a C₁-C₁₀ alkoxy group, but embodiments are not limited thereto.

[0226] R₁₀₉ in Formula 201 may be selected from


[0227] a phenyl group, a naphthyl group, an anthracenyl group, and a pyridinyl group; and

[0228] a phenyl group, a naphthyl group, an anthracenyl group, and a pyridinyl group, each substituted with one or

more selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, an anthracenyl group, and a pyridinyl group.

[0229] According to an embodiment, the compound represented by Formula 201 may be represented by Formula 201A, but is not limited thereto:


Formula 201A



[0230] R₁₀₁, R₁₁₁, R₁₁₂, and R₁₀₉ in Formula 201A may be understood by referring to the descriptions thereof provided above.


[0231] For example, the compound represented by Formula 201 and the compound represented by Formula 202 may include Compounds HT1 to HT20, but are not limited thereto:

HT1




-continued

HT2




-continued


HT4



HT3




HT5




-continued

HT6




-continued

HT8




HT9

HT7




HT10




-continued

HT11




-continued


HT14




HT15




HT12




HT16



HT13




HT17




-continued


HT18



HT19



HT20




[0232] A thickness of the hole transport region may range from about 100 angstrom (Å) to about 10,000 Å, for example, from about 100 Å to about 1,000 Å. When the hole transport region includes a hole injection layer and a hole transport layer, a thickness of the hole injection layer may range from about 100 Å to about 10,000 Å, for example, from about 100 Å to about 1,000 Å, and a thickness of the hole transport layer may range from about 50 Å to about 2,000 Å, for example, from about 100 Å to about 1,500 Å. While not wishing to be bound by theory, it is understood that when the thicknesses of the hole transport region, the hole injection layer, and the hole transport layer are within these ranges, satisfactory hole transport characteristics may be obtained without a substantial increase in driving voltage.


[0233] The hole transport region may further include, in addition to the materials as described above, a charge-generation material for the improvement of conductive properties. The charge-generation material may be homogeneously or non-homogeneously dispersed in the hole transport region.

[0234] The charge-generation material may be, for example, a p-dopant. The p-dopant may be one of a quinone derivative, a metal oxide, and a cyano group-containing compound, but is not limited thereto. For example, non-limiting examples of the p-dopant may include a quinone derivative such as tetracyanoquinonodimethane (TCNQ) or 2,3,5,6-tetrafluoro-tetracyano-1,4-benzoquinonodimethane (F4-TCNQ), a metal oxide such as a tungsten oxide or a molybdenum oxide, and a cyano group-containing compound such as Compound HT-D1 and HP-1, but embodiments are not limited thereto.


Compound HT-D1



F4-TCNQ




HP-1



[0235] The hole transport region may further include a buffer layer.

[0236] The buffer layer may compensate for an optical resonance distance according to a wavelength of light emitted from the emission layer, thereby improving efficiency of a formed organic light-emitting device.

[0237] The hole transport region may further include an electron blocking layer. The electron blocking layer may include a known material, for example, mCP, but is not limited thereto.



[0238] The emission layer may be formed on the hole transport region by a method such as vacuum deposition, spin coating, casting, or LB method. When the emission layer is formed by vacuum deposition or spin coating, the deposition and coating conditions may vary according to the compound that is used to form the emission layer but may be generally selected from condition ranges that are almost the same as those for the formation of the hole injection layer.

[0239] When the organic light-emitting device is a full color organic light-emitting device, the emission layer may be patterned into a red emission layer, a green emission layer, and a blue emission layer. Alternatively, the emission layer may have a structure in which a red emission layer, a green emission layer, and/or a blue emission layer are stacked on one another and thus may emit white light.

[0240] The emission layer includes a host that may satisfy Equations 1 and 2 as described above, an auxiliary dopant selected from compounds represented by Formula 1, and a fluorescent dopant that may satisfy Equations 1 and 2.

[0241] According to an embodiment, when the emission layer includes a host and a blue fluorescent dopant that may satisfy Equations 1 and 2, the three conditions: i) Equation 1, ii) Equation 2, iii) an auxiliary dopant selected from compounds represented by Formula 1 are "all" satisfied. Accordingly, a blue fluorescence organic light-emitting device which has "all" of low driving voltage, high efficiency, and long lifespan and emits blue light having excellent color purity (for example, blue light having an x-coordinate that is equal to or less than 0.2) may be provided.

[0242] According to another embodiment, when the emission layer includes a host and a green fluorescent dopant that may satisfy Equations 1 and 2, a green fluorescence organic light-emitting device having high efficiency and long lifespan may be provided.

[0243] An amount of the fluorescent dopant in the emission layer, in general, may range from about 0.01 to about 20 parts by weight based on about 100 parts by weight of the host and the auxiliary dopant, but is not limited thereto.

[0244] A thickness of the emission layer may range from about 100 Å to about 1,000 Å, for example, from about 200 Å to about 600 Å. When the thickness of the emission layer is within this range, excellent light-emission characteristics may be obtained without a substantial increase in driving voltage.


[0245] Next, an electron transport region is disposed on the emission layer.

[0246] The electron transport region may include at least one selected from a hole blocking layer, an electron transport layer, and an electron injection layer, but is not limited thereto.

[0247] For example, the electron transport region may have a structure of hole blocking layer/electron transport layer/electron injection layer or a structure of electron transport layer/electron injection layer. However, the structure of the electron transport region is not limited thereto. The electron transport layer may have a single-layer structure or a multi-layer structure including two or more different materials.

[0248] Conditions for forming the hole blocking layer, the electron transport layer, and the electron injection layer of the electron transport region may be understood by referring to the conditions for forming the hole injection layer.


[0249] When the electron transport region includes a hole blocking layer, the hole blocking layer may include, for example, at least one of BCP and Bphen, but is not limited thereto.




[0250] Alternatively, the hole blocking layer may include a compound selected from the host. For example, the hole blocking layer may include Compound H24, but is not limited thereto.



[0251] A thickness of the hole blocking layer may range from about 20 Å to about 1,000 Å, for example, from about 30 Å to about 300 Å. While not wishing to be bound by theory, it is understood that when the thickness of the hole blocking layer is within this range, excellent hole blocking characteristics may be obtained without a substantial increase in driving voltage.

[0252] The electron transport layer may include at least one of BCP, Bphen, Alq₃, Balq, TAZ, and NTAZ.






[0253] Alternatively, the electron transport layer may include at least one of Compounds ET1, ET2, and ET3, but is not limited thereto.



[0254] A thickness of the electron transport layer may range from about 100 Å to about 1,000 Å, for example, from about 150 Å to about 500 Å. While not wishing to be bound by theory, it is understood that when the thickness of the electron transport layer is within this range, satisfactory electron transport characteristics may be obtained without a substantial increase in driving voltage.


[0255] The electron transport layer may further include, in addition to the materials as described above, a metal-containing material.

[0256] The metal-containing material may include a Li complex. The Li complex may include, for example, Compound ET-D1 (lithium quinolate, LiQ) or ET-D2.



-continued

ET-D2



[0257] Also, the electron transport region may include an electron injection layer which facilitates injection of electrons from the second electrode 19.

[0258] The electron injection layer may include at least one selected from LiF, NaCl, CsF, Li₂O, and BaO.

[0259] A thickness of the electron injection layer may range from about 1 Å to about 100 Å, for example, from about 3 Å to about 90 Å. While not wishing to be bound by theory, it is understood that when the thickness of the electron injection layer is within this range, satisfactory electron injection characteristics may be obtained without a substantial increase in driving voltage.

[0260] The second electrode 19 is disposed on the organic layer 15. The second electrode 19 may be a cathode. A material for forming the second electrode 19 may be selected from metal, an alloy, an electrically conductive compound, and a combination thereof, which have a relatively low work function. For example, lithium (Li), magnesium (Mg), aluminum (Al), aluminum-lithium (Al—Li), calcium (Ca), magnesium-indium (Mg—In), or magnesium-silver (Mg—Ag) may be used as the material for forming the second electrode 19. Alternatively, in order to manufacture a top emission type light-emitting device, a transmissive electrode formed using ITO or IZO may be used as the second electrode 19.

[0261] The organic light-emitting device has been described above with reference to FIG. 1, but is not limited thereto.

[0262] A C₁-C₆₀ alkyl group as used herein refers to a linear or branched aliphatic hydrocarbon monovalent group having 1 to 60 carbon atoms. Detailed examples thereof are a methyl group, an ethyl group, a propyl group, an iso-butyl group, a sec-butyl group, a tert-butyl group, a pentyl group, an iso-amyl group, and a hexyl group. A C₁-C₆₀ alkenylene group as used herein refers to a divalent group having the same structure as the C₁-C₆₀ alkyl group.

[0263] A C₁-C₆₀ alkoxy group as used herein refers to a monovalent group represented by —OA₁₀₁ (wherein A₁₀₁ is the C₁-C₆₀ alkyl group). Detailed examples thereof are a methoxy group, an ethoxy group, and an iso-propyloxy group.

[0264] A C₂-C₆₀ alkenyl group as used herein has a structure including at least one carbon double bond in the middle or at the terminal of the C₂-C₆₀ alkyl group. Detailed examples thereof are an ethenyl group, a propenyl group, and a butenyl group. A C₂-C₆₀ alkenylene group as used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkenyl group.

[0265] A C₂-C₆₀ alkynyl group as used herein has a structure including at least one carbon triple bond in the

middle or at the terminal of the C₂-C₆₀ alkyl group. Detailed examples thereof are an ethynyl group and a propynyl group. A C₂-C₆₀ alkynylene group as used herein refers to a divalent group having the same structure as the C₂-C₆₀ alkynyl group.

[0266] A C₃-C₁₀ cycloalkyl group as used herein refers to a monovalent saturated hydrocarbon monocyclic group having 3 to 10 carbon atoms. Detailed examples thereof are a cyclopropyl group, a cyclobutyl group, a cyclopentyl group, a cyclohexyl group, and a cycloheptyl group. A C₃-C₁₀ cycloalkylene group as used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkyl group.

[0267] A C₂-C₁₀ heterocycloalkyl group as used herein refers to a monovalent monocyclic group including at least one heteroatom selected from N, O, P, and S as a ring-forming atom and 2 to 10 carbon atoms. Detailed examples thereof are a tetrahydrofuranlyl group and a tetrahydrothiophenyl group. A C₂-C₁₀ heterocycloalkylene group as used herein refers to a divalent group having the same structure as the C₂-C₁₀ heterocycloalkyl group.

[0268] A C₃-C₁₀ cycloalkenyl group as used herein refers to a monovalent monocyclic group that has 3 to 10 carbon atoms and at least one double bond in the ring thereof, and which is not aromatic. Detailed examples thereof are a cyclopentenyl group, a cyclohexenyl group, and a cycloheptenyl group. A C₃-C₁₀ cycloalkenylene group as used herein refers to a divalent group having the same structure as the C₃-C₁₀ cycloalkenyl group.

[0269] A C₂-C₁₀ heterocycloalkenyl group as used herein refers to a monovalent monocyclic group that has at least one heteroatom selected from N, O, P, and S as a ring-forming atom, 2 to 10 carbon atoms, and at least one double bond in its ring. Detailed examples of the C₂-C₁₀ heterocycloalkenyl group are a 2,3-dihydrofuranlyl group and a 2,3-dihydrothiophenyl group. A C₂-C₁₀ heterocycloalkenylene group as used herein refers to a divalent group having the same structure as the C₂-C₁₀ heterocycloalkenyl group.

[0270] A C₆-C₆₀ aryl group as used herein refers to a monovalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms, and a C₆-C₆₀ arylene group used herein refers to a divalent group having a carbocyclic aromatic system having 6 to 60 carbon atoms. Detailed examples of the C₆-C₆₀ aryl group are a phenyl group, a naphthyl group, an anthracenyl group, a phenanthrenyl group, a pyrenyl group, and a chrysenyl group. When the C₆-C₆₀ aryl group and the C₆-C₆₀ arylene group each include two or more rings, the rings may be fused to each other.

[0271] A C₂-C₆₀ heteroaryl group as used herein refers to a monovalent group having a carbocyclic aromatic system that includes at least one heteroatom selected from N, O, P, and S as a ring-forming atom and has 2 to 60 carbon atoms. A C₂-C₆₀ heteroarylene group as used herein refers to a divalent group having a carbocyclic aromatic system that includes at least one heteroatom selected from N, O, P, and S as a ring-forming atom and 2 to 60 carbon atoms. Examples of the C₂-C₆₀ heteroaryl group are a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a quinolinyl group, and an isoquinolinyl group. When the C₂-C₆₀ heteroaryl group and the C₂-C₆₀ heteroarylene group each include two or more rings, the rings may be fused to each other.

[0272] A C₆-C₆₀ aryloxy group as used herein indicates —OA₁₀₂ (wherein A₁₀₂ is the C₆-C₆₀ aryl group), and a

C₆-C₆₀ arylthio group used herein indicates —SA₁₀₃ (wherein A₁₀₃ is the C₆-C₆₀ aryl group).

[0273] A monovalent non-aromatic condensed polycyclic group used herein refers to a monovalent group that has two or more rings condensed to each other, includes only carbon atoms as a ring forming atom (for example, having 8 to 60 carbon atoms), and which is non-aromatic in the entire molecular structure. A detailed example of the monovalent non-aromatic condensed polycyclic group is a fluorenyl group. A divalent non-aromatic condensed polycyclic group as used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed polycyclic group.

[0274] A monovalent non-aromatic condensed heteropolycyclic group as used herein refers to a monovalent group that has two or more rings condensed to each other, includes a heteroatom selected from N, O, P, and S, in addition to carbon atoms (for example, 2 to 60 carbon atoms), as a ring forming atom, and which is non-aromatic in the entire molecular structure. An example of the monovalent non-aromatic condensed heteropolycyclic group is a carbazolyl group. A divalent non-aromatic condensed heteropolycyclic group as used herein refers to a divalent group having the same structure as the monovalent non-aromatic condensed heteropolycyclic group.

[0275] At least one of substituents of the substituted C₁-C₆₀ alkyl group, substituted C₂-C₆₀ alkenyl group, substituted C₂-C₆₀ alkynyl group, substituted C₁-C₆₀ alkoxy group, substituted C₃-C₁₀ cycloalkyl group, substituted C₁-C₁₀ heterocycloalkyl group, substituted C₃-C₁₀ cycloalkenyl group, substituted C₁-C₁₀ heterocycloalkenyl group, substituted C₆-C₆₀ aryl group, substituted C₆-C₆₀ aryloxy group, substituted C₆-C₆₀ arylthio group, substituted C₁-C₆₀ heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, and substituted monovalent non-aromatic condensed heteropolycyclic group may be selected from

[0276] a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

[0277] a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₄)(Q₁₅), and —B(Q₁₆)(Q₁₇);

[0278] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;

[0279] a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₄)(Q₂₅), and —B(Q₂₆)(Q₂₇); and

[0280] —Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₄)(Q₃₅), and —B(Q₃₆)(Q₃₇); and

[0281] Q₁ to Q₇, Q₁₁ to Q₁₇, Q₂₁ to Q₂₇, and Q₃₁ to Q₃₇ may be each independently selected from a hydrogen, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.

[0282] When a group containing a specified number of carbon atoms is substituted with any of the groups listed in the preceding paragraph, the number of carbon atoms in the resulting “substituted” group is defined as the sum of the carbon atoms contained in the original (unsubstituted) group and the carbon atoms (if any) contained in the substituent. For example, when the term “substituted C₁-C₁₀ alkyl” refers to a C₁-C₃₀ alkyl group substituted with C₆-C₆₀ aryl group, the total number of carbon atoms in the resulting aryl substituted alkyl group is C₇-C₉₀.

[0283] The term, “room temperature” used herein refers to a temperature of about 25° C.

[0284] Hereinafter, a compound and an organic light-emitting device according to embodiments are described in detail with reference to Examples. However, the organic light-emitting device is not limited thereto.

EXAMPLE

Example 1

[0285] A glass substrate on which an indium tin oxide (ITO) electrode (first electrode, anode) having a thickness of 1,500 Å was formed was cleaned with distilled water. After being cleaned with distilled water, the substrate was sonicated using a solvent, such as iso-propyl alcohol, acetone, or methanol, dried, and then carried to a plasma cleaner. The substrate was cleaned for 5 minutes using oxygen plasma and then carried to a vacuum deposition apparatus.

[0286] Compound HT3 and Compound HP-1 were co-deposited on the ITO electrode of the glass substrate to form a hole injection layer having a thickness of 100 Å. Then, Compound HT3 was deposited on the hole injection layer to form a hole transport layer having a thickness of 1,300 Å, and mCP was deposited on the hole transport layer to form an electron blocking layer having a thickness of 150 Å, thereby forming a hole transport region.

[0287] Compound H23 (host), Compound 2 (auxiliary dopant), and Compound FD(5) were co-deposited on the hole transport region at a volume ratio of 85:15:1 to form an emission layer having a thickness of 300 Å.

[0288] Compound H24 was vacuum-deposited on the emission layer to form a hole blocking layer having a thickness of 100 Å, and Compound ET3 and Liq were vacuum-deposited on the hole blocking layer together to form an electron transport layer having a thickness of 250 Å. Then, Liq was deposited on the electron transport layer to form an electron injection layer having a thickness of 5 Å, and an Al second electrode (cathode) having a thickness of 1,000 Å was formed on the electron injection layer, thereby completing the manufacture of an organic light-emitting device.

Examples 2 to 4 and Comparative Examples A to D

[0289] Devices were manufactured in the same manner as in Example 1, except that the composition of the emission layer was changed as shown in Table 1.


TABLE 1

	Host	Auxiliary dopant	Fluorescent dopant	Volume ratio
Example 1	Compound H23	Compound 2	Compound F(5)	85:15:1
Example 2	Compound H23	Compound 2	Compound F9	85:15:1
Example 3	Compound H7	Compound 2	Compound F9	85:15:1
Example 4	Compound H19	Compound 2	Compound F(5)	85:15:1
Comparative Example A	Compound H23	Compound A	Compound F(5)	85:15:1
Comparative Example B	Compound H23	Compound 2	—	85:15
Comparative Example C	Compound B	Compound 2	Compound F(5)	85:15:1


TABLE 1-continued

	Host	Auxiliary dopant	Fluorescent dopant	Volume ratio
Comparative Example D	Compound H23	Compound C	Compound F(5)	85:15:1


H23



H7



H19



2




TABLE 1-continued







Host	Auxiliary dopant	Fluorescent dopant	Volume ratio
FD(5)			
			
FD9			
			
A			
			
B			
			

TABLE 1-continued

Host	Auxiliary dopant	Fluorescent dopant	Volume ratio
			
C			
			

Evaluation Example 1

Evaluation on Triplet (T₁) Energy Level and Singlet (S₁) Energy Level

[0290] Triplet (T₁) energy levels and/or singlet (S₁) energy levels of compounds used in Examples 1 to 4 and Comparative Examples A to D were evaluated according to the method indicated in Table 2, and results thereof are shown in Table 3.

TABLE 2

T ₁ energy level evaluation method	A mixture of 2-MeTHF and each compound (in which each compound was dissolved in an amount of 1 milligram (mg) in 3 cubic centimeters (cc) of 2-MeTHF) was loaded into a quartz cell. The resultant quartz cell was loaded into liquid nitrogen (77 Kelvins (K)) and a photoluminescence spectrum thereof was measured by using a device for measuring photoluminescence. T ₁ energy levels were calculated from a starting wavelength on a short wavelength side of the photoluminescence spectrum.
S ₁ energy level evaluation method	A mixture of 2-MeTHF and each compound (in which each compound was mixed at a concentration of 10 ⁻⁴ molar [M] in 2-MeTHF) was loaded into a quartz cell. A fluorescence spectrum thereof was measured at room temperature by using a device (F7000, the product from Hitachi, Ltd.) for measuring photoluminescence, and S ₁ energy levels were calculated from a starting wavelength on a short wavelength side of the fluorescence spectrum.

TABLE 3

Compound No.	T ₁ energy level (eV) (Measured value)	S ₁ energy level (eV) (Measured value)
Compound H23	3.52	4.02
Compound H7	2.97	3.52
Compound H19	3.12	3.77
Compound B	2.82	3.22
Compound 2	2.89	2.98
Compound A	2.96	3.03
Compound C	2.89	2.92
Compound FD(5)	—	2.78
Compound FD9	—	2.58

[0291] Calculation results of $E_{T1(HOST)} - E_{T1(AD)}$ and calculation results of $E_{S1(FD)} - E_{S1(AD)}$ of the organic light-emitting devices manufactured according to Examples 1 to 4 and Comparative Examples A to D, which are obtained by using the data of Table 3, are shown in Table 4:

TABLE 4

	Host	Auxiliary dopant	Fluorescent dopant	Calculation result (eV) of $E_{T1(HOST)} - E_{T1(AD)}$	Calculation result (eV) of $E_{S1(FD)} - E_{S1(AD)}$
Example 1	Compound H23	Compound 2	Compound F(5)	0.63	-0.2
Example 2	Compound H23	Compound 2	Compound F9	0.63	-0.4
Example 3	Compound H7	Compound 2	Compound F9	0.08	-0.4
Example 4	Compound H19	Compound 2	Compound F(5)	0.23	-0.2
Comparative Example A	Compound H23	Compound A	Compound F(5)	0.56	-0.25
Comparative Example B	Compound H23	Compound 2	—	0.63	—
Comparative Example C	Compound B	Compound 2	Compound F(5)	-0.07	-0.2
Comparative Example D	Compound H23	Compound C	Compound F(5)	0.63	-0.14

[0292] From Tables 3 and 4, it may be confirmed that the organic light-emitting devices of Examples 1 to 4 satisfy both of Equations 1 and 2.

$$E_{T1(HOST)} - E_{T1(AD)} > 0.05 \text{ eV} \quad \text{Equation 1}$$

$$E_{S1(FD)} - E_{S1(AD)} < 0 \text{ eV} \quad \text{Equation 2}$$

Evaluation Example 2

Evaluation on Device Data

[0293] The driving voltage, current density, color purity, and external quantum efficiency (EQE) of the organic light-emitting devices manufactured according to Examples 1 to 4 and Comparative Examples A to D were measured by using a current-voltage meter (Keithley 2400) and a luminance meter (Minolta Cs-1000A), and results thereof are shown in Table 5. All the data except maximum values of external quantum efficiency was measured at 500 candelas per square meter (cd/m²).

[0294] The lifespan (T_{95}) of the organic light-emitting devices manufactured according to Examples 1 and 4 and Comparative Example D was evaluated, and results thereof are shown in Table 6. Lifespan (T_{95}) (at 500 cd/m²) data in Table 6 was obtained by evaluating a time (hr) that lapses

when luminance is decreased to 95% of the initial luminance, which is 100%. The lifespan data regarding Examples 1 and 4 in Table 6 are expressed as relative values when the lifespan of the organic light-emitting device manufactured according to Comparative Example D is "1."

TABLE 5

Example No.	Driving voltage (V)	Current density (mA/cm ²)	Maximum emission wavelength (nm)	CIE x, y	Emission color	External quantum efficiency (%) @ 500 cd/m ²	Maximum value
Example 1	6.4	3.1	464	0.19, 0.32	blue	7.3	9.2

TABLE 5-continued

Example No.	Driving voltage (V)	Current density (mA/cm ²)	Maximum emission wavelength (nm)	CIE x, y	Emission color	External quantum efficiency (%) @ 500 cd/m ²	Maximum value
Example 2	6.6	2.0	540	0.31, 0.54	green	7.2	10.9
Example 3	6.4	3.3	532	0.28, 0.50	green	4.8	6.3
Example 4	5.9	3.3	468	0.18, 0.30	blue	7.3	8.2
Comparative Example A	7.0	4.1	464	0.20, 0.32	blue	5.6	7.2
Comparative Example B	6.4	1.6	476	0.21, 0.35	blue	13.5	17.4
Comparative Example C	6.3	3.4	465	0.20, 0.34	blue	1.6	3.8
Comparative Example D	6.6	3.6	460	0.18, 0.29	blue	7.1	9.3

TABLE 6

Example No.	LT ₉₅ @ 500 cd/m ² (Relative value)
Example 1	2
Example 4	45
Comparative Example D	1

[0295] According to Table 5, it may be confirmed that the organic light-emitting devices (blue light-emitting OLEDs) of Examples 1 and 4 have lower driving voltage and higher external quantum efficiency than the organic light-emitting device (blue light-emitting OLED) of Comparative Example A, have higher external quantum efficiency than the organic light-emitting device (blue light-emitting OLED) of Comparative Example C, and have better color purity than the organic light-emitting devices (blue light-emitting OLEDs) of Comparative Examples A to C (that is, CIE x and y coordinate values of Examples 1 and 4 are respectively smaller than CIE x and y coordinate values of Comparative Examples A to C).

[0296] Also, from Table 6, it may be confirmed that the organic light-emitting devices of Examples 1 and 4 have higher lifespan characteristics than the organic light-emitting device (blue light-emitting OLED) of Comparative Example D.

[0297] From Tables 5 and 6, it may be confirmed that an organic light-emitting device that satisfies “all” three conditions, i) Equation 1, ii) Equation 2, iii) an auxiliary dopant selected from compounds represented by Formula 1 may have “all” of low driving voltage, high efficiency, and long lifespan and may also emit blue light having high color purity (for example, blue light having an x-coordinate that is equal to or less than 0.2). (Referring to Example 1 and 4 and Comparative Examples A to D)

[0298] Further, from Table 5, it may be confirmed that the organic light-emitting devices (green light-emitting OLEDs) of Examples 2 and 3 also have low driving voltage and high luminescent efficiency.

[0299] According to one or more embodiments of the present disclosure, an organic light-emitting device may have high color purity and luminescent efficiency.

[0300] It should be understood that exemplary embodiments described herein should be considered in a descriptive sense only and not for purposes of limitation. Descriptions of features or aspects within each exemplary embodiment should typically be considered as available for other similar features or aspects in other exemplary embodiments.

[0301] While one or more exemplary embodiments have been described with reference to the FIGURES, it will be understood by those of ordinary skill in the art that various changes in form and details may be made therein without departing from the spirit and scope of the present inventive concept as defined by the following claims.

What is claimed is:

1. An organic light-emitting device comprising:
 - a first electrode,
 - a second electrode facing the first electrode, and
 - an organic layer disposed between the first electrode and the second electrode,
 wherein the organic layer comprises an emission layer and satisfies Equations 1 and 2,
 wherein the emission layer comprises a host, an auxiliary dopant, and a fluorescent dopant, and

wherein the auxiliary dopant is selected from compounds represented by Formula 1:

$$E_{T1(Host)} - E_{T1(AD)} > 0.05 \text{ electron Volts} \quad \text{Equation 1}$$

$$E_{S1(FD)} - E_{S1(AD)} < 0 \text{ electron Volts}, \quad \text{Equation 2}$$

wherein in Equation 1,


$E_{T1(Host)}$ is a triplet energy (electron Volts) of the host, and

$E_{T1(AD)}$ is a triplet energy (electron Volts) of the auxiliary dopant, and


wherein in Equation 2,

$E_{S1(FD)}$ is a singlet energy (electron Volts) of the fluorescent dopant, and


$E_{S1(AD)}$ is a singlet energy (electron Volts) of the auxiliary dopant,



Formula 1



Formula 2



Formula 2A



Formula 2B

wherein

Ar_1 in Formula 1 is a group represented by Formula 2, ring A_1 in Formula 2 is a group represented by Formula 2A,

ring A_2 in Formula 2 is a group represented by Formula 2B,

X_1 in Formula 2B is N(R_{17}), O, or S,

R_1 to R_{17} in Formulae 1, 2, 2A, and 2B are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a

substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁)(Q₂)(Q₃), —N(Q₄)(Q₅), and —B(Q₆)(Q₇),

* in Formula 2 indicates a binding site to a neighboring atom,

at least one of substituents of the substituted C₁-C₆₀ alkyl group, substituted C₂-C₆₀ alkenyl group, substituted C₂-C₆₀ alkynyl group, substituted C₁-C₆₀ alkoxy group, substituted C₃-C₁₀ cycloalkyl group, substituted C₁-C₁₀ heterocycloalkyl group, substituted C₃-C₁₀ cycloalkenyl group, substituted C₁-C₁₀ heterocycloalkenyl group, substituted C₆-C₆₀ aryl group, substituted C₆-C₆₀ aryloxy group, substituted C₆-C₆₀ arylthio group, substituted C₁-C₆₀ heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, and substituted monovalent non-aromatic condensed heteropolycyclic group is selected from:

a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group;

a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, and a C₁-C₆₀ alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₁₁)(Q₁₂)(Q₁₃), —N(Q₁₄)(Q₁₅), and —B(Q₁₆)(Q₁₇);

a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group;


a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, —Si(Q₂₁)(Q₂₂)(Q₂₃), —N(Q₂₄)(Q₂₅), and —B(Q₂₆)(Q₂₇); and

—Si(Q₃₁)(Q₃₂)(Q₃₃), —N(Q₃₄)(Q₃₅), and —B(Q₃₆)(Q₃₇), and

Q₁ to Q₇, Q₁₁ to Q₁₇, Q₂₁ to Q₂₇, and Q₃₁ to Q₃₇ are each independently selected from a hydrogen, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group.


2. The organic light-emitting device of claim 1, wherein Ar₁ in Formula 1 is selected from groups represented by Formulae 2-1 to 2-6:

Formula 2-1




-continued


Formula 2-2




Formula 2-3




Formula 2-4



Formula 2-5



Formula 2-6



R_1 to R_{10} and X_1 in Formulae 2-1 to 2-6 are the same as in claim 1, and

* indicates a binding site to a neighboring atom.

3. The organic light-emitting device of claim 1, wherein X_1 in Formula 2B is $N(R_{17})$.

4. The organic light-emitting device of claim 1, wherein X_1 in Formula 2B is $N(R_{17})$, and R_{17} is selected from

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group; and

a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, a C_1 - C_{20} alkoxy group, a phenyl group, a naphthyl group, and —Si(Q_{31})(Q_{32})(Q_{33}), and

Q_{31} to Q_{33} are each independently selected from a hydrogen, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.

5. The organic light-emitting device of claim 1, wherein R_1 to R_{14} are each independently selected from


a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{20} alkyl group, and a C_1 - C_{20} alkoxy group;

- a C₁-C₂₀ alkyl group and a C₁-C₂₀ alkoxy group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, and a phosphoric acid group or a salt thereof;
- a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, a benzofuranyl group, a benzothiophenyl group, a benzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group;
- a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, a benzofuranyl group, a benzothiophenyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, and a dibenzocarbazolyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a naphthyl group, and —Si(Q₃₁)(Q₃₂)(Q₃₃); and —Si(Q₁)(Q₂)(Q₃), and
- Q₁ to Q₃ and Q₃₁ to Q₃₃ are each independently selected from a hydrogen, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.
6. The organic light-emitting device of claim 1, wherein R₁₅ and R₁₆ are each independently selected from
- a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group; and
- a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthrenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a thiophenyl group, a furanyl group, a carbazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a dibenzosilolyl group, a thiadiazolyl group, an imidazopyridinyl group, and an imidazopyrimidinyl group; and


alkoxy group, a cyclopentyl group, a cyclohexyl group, a cycloheptyl group, a cyclopentenyl group, a cyclohexenyl group, a phenyl group, a biphenyl group, a terphenyl group, a pentalenyl group, an indenyl group, a naphthyl group, an azulenyl group, a heptalenyl group, an indacenyl group, an acenaphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenalenyl group, a phenanthrenyl group, an anthracenyl group, a fluoranthenyl group, a triphenylenyl group, a pyrenyl group, a chrysenyl group, a naphthacenyl group, a picenyl group, a perylenyl group, a pentaphenyl group, a hexacenyl group, a pentacenyl group, a rubicenyl group, a coronenyl group, an ovalenyl group, a pyrrolyl group, a thiophenyl group, a furanyl group, an imidazolyl group, a pyrazolyl group, a thiazolyl group, an isothiazolyl group, an oxazolyl group, an isoxazolyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, an isoindolyl group, an indolyl group, an indazolyl group, a purinyl group, a quinolinyl group, an isoquinolinyl group, a benzoquinolinyl group, a phthalazinyl group, a naphthyridinyl group, a quinoxalinyl group, a quinazolinyl group, a cinnolinyl group, a carbazolyl group, a phenanthridinyl group, an acridinyl group, a phenanthrolinyl group, a phenazinyl group, a benzoimidazolyl group, a benzofuranyl group, a benzothiophenyl group, an isobenzothiazolyl group, a benzoxazolyl group, an isobenzoxazolyl group, a triazolyl group, a tetrazolyl group, an oxadiazolyl group, a triazinyl group, a dibenzofuranyl group, a dibenzothiophenyl group, a benzocarbazolyl group, a dibenzocarbazolyl group, a thiadiazolyl group, an imidazopyridinyl group, an imidazopyrimidinyl group, and $-\text{Si}(\text{Q}_{31})(\text{Q}_{32})(\text{Q}_{33})$, and

Q_{31} to Q_{33} are each independently selected from a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group.


7. The organic light-emitting device of claim 1, wherein the auxiliary dopant is selected from Compounds 1 to 39:




1



2




3




4

-continued




5


-continued




8




6



9




7




10

-continued




11

-continued





14

12




13




15

16




-continued


17



18




19




-continued


20




21









22




-continued



-continued




-continued




30


-continued




34




31




35




32



36




33




37

-continued




38


-continued




Formula 11-3



Formula 13



Formula 14



39

wherein, in Formulae 11-1 to 11-3, 13, and 14,

Ar_{11} and Ar_{12} are each independently selected from groups represented by Formulae 13 and 14,

$X_{1,5}$ is $N(R_{22})$, O , or S .

X_1 is N or C(T_{14}), X_2 is N or C(T_{15}), X_3 is N or C(T_{16}),
and at least one of X_1 to X_3 is N.

T₂₁ and T₂₂ are each independently selected from *-_{a21}(L₂₁)_{a21}-Si(Q₄₁)(Q₄₂)(Q₄₃) and *-_{a21}(L₂₁)_{a21}-P(=O)(Q₅₁)(Q₅₂),

L_{11} to L_{13} and L_{21} are each independently selected from a single bond, O, S, Si(Q_{61})(Q_{62}), a phenylene group, a pyridinylene group, a pyrimidinylene group, a pyrazinylene group, a pyridazinylene group, a triazinylene group, a naphthylene group, a fluorenylene group, a carbazolyene group, a dibenzofuranylene group, and a dibenzothiophenylenylene group; and

a phenylene group, a pyridinylene group, a pyrimidinylene group, a pyrazinylene group, a pyridazinylene group, a triazinylene group, a naphthylene group, a fluorenylene group, a carbazolyene group, a dibenzofuranylene group, and a dibenzothiophenylene group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, —CF₃, —CF₂H, —CFH₂, a phenyl group, a phenyl group substituted with a cyano group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a carbazoly group, a dibenzofuranyl group, a dibenzothiophenyl group, and —Si(Q₇₁)(Q₇₂)(Q₇₃).


a11 to a13 and a21 are each independently an integer selected from 0 to 5, two or more groups L_{11} are identical to or different from each other when a11 is 2 or more, two or more groups L_{12} are identical to or different from each other when a12 is 2 or more, two or more groups L_{13} are identical to or different from each other when a13 is 2 or more, and two or more groups L_{21} are identical to or different from each other when a21 is 2 or more.

8. The organic light-emitting device of claim 1, wherein the host has a triplet energy level of 2.9 electron Volts or greater.


9. The organic light-emitting device of claim 1, wherein the host comprises a fluorene ring, a carbazole ring, a dibenzofuran ring, a dibenzothiophene ring, an indenocarbazole ring, an indolocarbazole ring, a benzofurocarbazole ring, a benzothienocarbazole ring, an acridine ring, a dihydroacridine ring, a triindolobenzene ring, or any combination thereof, or

the host is a silicon compound or a phosphine oxide compound.

10. The organic light-emitting device of claim 1, wherein the host is selected from compounds represented by Formulae 11-1 to 11-3:



Formula 11-1



Formula 11-2

CY₃ and CY₄ are each independently selected from a benzene, a naphthalene, a fluorene, a carbazole, a benzocarbazole, an indolocarbazole, a dibenzofuran, and a dibenzothiophene,

A₂ is selected from

a single bond, a C₁-C₄ alkylene group, and a C₂-C₄ alkenylene group; and

a C₁-C₄ alkylene group and a C₂-C₄ alkenylene group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and —Si(Q₈₁)(Q₈₂)(Q₈₃),

T₁₁ to T₁₆, R₂₂, R₃₀, and R₄₀ are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group (CN), a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a substituted or unsubstituted C₁-C₆₀ alkyl group, a substituted or unsubstituted C₂-C₆₀ alkenyl group, a substituted or unsubstituted C₂-C₆₀ alkynyl group, a substituted or unsubstituted C₁-C₆₀ alkoxy group, a substituted or unsubstituted C₃-C₁₀ cycloalkyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkyl group, a substituted or unsubstituted C₃-C₁₀ cycloalkenyl group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenyl group, a substituted or unsubstituted C₆-C₆₀ aryl group, a substituted or unsubstituted C₆-C₆₀ aryloxy group, a substituted or unsubstituted C₆-C₆₀ arylthio group, a substituted or unsubstituted C₁-C₆₀ heteroaryl group, a substituted or unsubstituted monovalent non-aromatic condensed polycyclic group, a substituted or unsubstituted monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q₉₁)(Q₉₂)(Q₉₃),

b3 and b4 are each independently an integer selected from 0 to 10,

c1 is 0, 1, 2, or 3,

* indicates a binding site to a neighboring atom,


at least one of substituents of the substituted C₁-C₆₀ alkyl group, substituted C₂-C₆₀ alkenyl group, substituted C₂-C₆₀ alkynyl group, substituted C₃-C₁₀ cycloalkyl group, substituted C₁-C₁₀ heterocycloalkyl group, substituted C₃-C₁₀ cycloalkenyl group, substituted C₁-C₁₀ heterocycloalkenyl group, substituted C₆-C₆₀ aryl group, substituted C₆-C₆₀ aryloxy group, substituted C₆-C₆₀ arylthio group, substituted C₁-C₆₀ heteroaryl group, substituted monovalent non-aromatic condensed polycyclic group, and substituted monovalent non-aromatic condensed heteropolycyclic group is selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid

group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q₁₀₁)(Q₁₀₂)(Q₁₀₃), and


Q₄₁ to Q₄₃, Q₅₁, Q₅₂, Q₆₁, Q₆₂, Q₇₁ to Q₇₃, Q₈₁ to Q₈₃, Q₉₁ to Q₉₃, and Q₁₀₁ to Q₁₀₃ are each independently selected from a hydrogen, a deuterium, a C₁-C₆₀ alkyl group, a C₁-C₆₀ alkoxy group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group.

11. The organic light-emitting device of claim 10, wherein Ar₁₁ and Ar₁₂ are each independently selected from groups represented by Formulae 13-1 to 13-8 and 14-1 to 14-8:


Formula 13-1



Formula 13-2




Formula 13-3




-continued


Formula 13-4




Formula 13-5




Formula 13-6



Formula 13-7




Formula 13-8




-continued


Formula 14-1




Formula 14-2




Formula 14-3




Formula 14-4




Formula 14-5




-continued



Formula 14-6



Formula 14-7



Formula 14-8

wherein, in Formulae 13-1 to 13-8 and 14-1 to 14-8,
 X_{12} and X_{14} are each independently $C(R_{37})(R_{38})$, $N(R_{39})$,
 O , or S ,


X_{15} and A_2 are the same as in claim 10,

R_{31} to R_{39} are each independently the same as R_{30} in claim 10,

R_{41} to R_{44} are each independently the same as R_{40} in claim 10, and


* indicates a binding site to a neighboring atom.

12. The organic light-emitting device of claim 10, wherein
 Ar_{11} and Ar_{12} are each independently selected from groups
 represented by Formulae 17-1 to 17-19 and 18-1 to 18-8:




Formula 17-1


-continued




Formula 17-2




Formula 17-3




Formula 17-4




Formula 17-5



Formula 17-6




Formula 17-7




Formula 17-8

-continued




Formula 17-9


-continued




Formula 17-15




Formula 17-10




Formula 17-16




Formula 17-11




Formula 17-17




Formula 17-12




Formula 17-18




Formula 17-13



Formula 17-19




Formula 17-14




Formula 18-1


-continued




Formula 18-2




Formula 18-3




Formula 18-4




Formula 18-5



Formula 18-6



Formula 18-7



Formula 18-8

wherein, in Formulae 17-1 to 17-19 and 18-1 to 18-8, X_{12} and X_{14} are each independently $C(R_{37})(R_{38})$, $N(R_{39})$, O, or S,

X_{15} is $N(R_{17})$, O, or S,

R' and R'' are each independently selected from a hydrogen, a deuterium, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group,

R_{22} , R_{30} , R_{30a} to R_{30c} , and R_{40} are each independently selected from

a hydrogen, a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt

thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, $-CF_3$, $-CF_2H$, and $-CFH_2$;

a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;


a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, $-CF_3$, $-CF_2H$, $-CFH_2$, a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a naphthyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and

$-Si(Q_{91})(Q_{92})(Q_{93})$,


Q_{91} to Q_{93} are each independently selected from a hydrogen, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, and a naphthyl group, and

* indicates a binding site to a neighboring atom.


13. The organic light-emitting device of claim 11, wherein L_{11} to L_{13} and L_{21} are each independently selected from a single bond, O, S, $Si(Q_{61})(Q_{62})$, and a group represented by one of Formulae 3-1 to 3-56:




Formula 3-1




Formula 3-2



Formula 3-3














Formula 3-4



Formula 3-5

-continued



Formula 3-6

Formula 3-7

Formula 3-8

Formula 3-9

Formula 3-10

Formula 3-11

Formula 3-12












Formula 3-13

Formula 3-14

Formula 3-15

Formula 3-16

-continued



Formula 3-17

Formula 3-18

Formula 3-19

Formula 3-20

Formula 3-21

Formula 3-22

Formula 3-23










Formula 3-24

Formula 3-25


Formula 3-26

Formula 3-27


-continued




Formula 3-28




Formula 3-29




Formula 3-30




Formula 3-31




Formula 3-32




Formula 3-33




Formula 3-34



Formula 3-35



Formula 3-36



-continued

Formula 3-37

Formula 3-38

Formula 3-39

Formula 3-40

Formula 3-41


Formula 3-42

Formula 3-43


Formula 3-44

Formula 3-45


-continued




Formula 3-46




Formula 3-47




Formula 3-48




Formula 3-49




Formula 3-50




Formula 3-51



Formula 3-52




Formula 3-53




Formula 3-54

-continued



Formula 3-55



Formula 3-56

wherein, in Formulae 3-1 to 3-56,

Y_1 is selected from O, S, $C(Z_3)(Z_4)$, and $N(Z_5)$,

Z_1 to Z_5 are each independently selected from a hydrogen, a deuterium, $-F$, $-Cl$, $-Br$, $-I$, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, $-CF_3$, $-CF_2H$, $-CFH_2$, a phenyl group, a phenyl group substituted with a cyano group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and $-Si(Q_{71})(Q_{72})(Q_{73})$,

Q_{71} to Q_{73} are each independently selected from a hydrogen, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group,


d_4 is an integer selected from 0 to 4,

d_3 is an integer selected 0 to 3,


d_2 is an integer selected 0 to 2, and

* and *' each indicate a binding site to a neighboring atom.

14. The organic light-emitting device of claim 10, wherein a group represented by $*(L_{11})_{a11}-*'$, $*(L_{12})_{a12}-*'$, $*(L_{13})_{a13}-*'$, and $*(L_{21})_{a21}-*'$ is selected from a single bond and groups represented by Formulae 4-1 to 4-42:













Formula 4-1



Formula 4-2


-continued



-continued


Formula 4-3

Formula 4-13




Formula 4-4

Formula 4-14




Formula 4-5

Formula 4-15




Formula 4-6

Formula 4-16




Formula 4-7

Formula 4-8




Formula 4-9

Formula 4-17




Formula 4-10

Formula 4-18




Formula 4-11


Formula 4-19




Formula 4-12




-continued




Formula 4-20




Formula 4-21




Formula 4-22




Formula 4-23



Formula 4-24




Formula 4-25




Formula 4-26


-continued




Formula 4-27




Formula 4-28




Formula 4-29




Formula 4-30



Formula 4-31




Formula 4-32




Formula 4-33


-continued



Formula 4-34




Formula 4-35




Formula 4-36



Formula 4-37




Formula 4-38




Formula 4-39


-continued



Formula 4-40



Formula 4-41



Formula 4-42

wherein, in Formulae 4-1 to 4-42,

X_{21} is N or C(Z_{21}), X_{22} is N or C(Z_{22}), X_{23} is N or C(Z_{23}), X_{24} is N or C(Z_{24}), X_{31} is N or C(Z_{31}), X_{32} is N or C(Z_{32}), X_{33} is N or C(Z_{33}), X_{34} is N or C(Z_{34}), X_{41} is N or C(Z_{41}), X_{42} is N or C(Z_{42}), X_{43} is N or C(Z_{43}), and X_{44} is N or C(Z_{44}), wherein each of X_{21} to X_{24} is not simultaneously N, wherein each of X_{31} to X_{34} is not simultaneously N, and wherein X_{41} to X_{44} is not simultaneously N,

Z_{21} to Z_{24} , Z_{31} to Z_{34} and Z_{41} to Z_{44} are each independently selected from a hydrogen, a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, —CF₃, —CF₂H, —CFH₂, a phenyl group, a phenyl group substituted with a cyano group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, a dibenzothiophenyl group, and —Si(Q_{71})(Q_{72})(Q_{73}),

Q_{71} to Q_{73} are each independently selected from a hydrogen, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a pyridinyl group, a pyrimidinyl group, a pyrazinyl group, a pyridazinyl group, a triazinyl group, a fluorenyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, and

* and *' each indicate a binding site to a neighboring atom.

15. The organic light-emitting device of claim 10, wherein T_{11} to T_{16} are each independently selected from

a hydrogen, a deuterium, —F, a cyano group, a C_1 - C_{10} alkyl group, a C_1 - C_{10} alkoxy group, —CF₃, —CF₂H, and —CFH₂;

a C_1 - C_{10} alkyl group and a C_1 - C_{10} alkoxy group, each substituted with at least one selected from a deuterium, —F, a cyano group, —CF₃, —CF₂H, and —CFH₂;

a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group;

a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from a deuterium, —F, a cyano group, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, —CF₃, —CF₂H, —CFH₂, a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and —Si(Q₉₁)(Q₉₂)(Q₉₃), and

Q₉₁ to Q₉₃ are each independently selected from a hydrogen, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group.


16. The organic light-emitting device of claim 10, wherein

Q₄₁ to Q₄₃, Q₅₁, and Q₅₂ are each independently selected from


a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and

a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from a deuterium, —F, a cyano group, a C₁-C₁₀ alkyl group, a C₁-C₁₀ alkoxy group, —CF₃, —CF₂H, —CFH₂, a phenyl group, a biphenyl group, a terphenyl group, a pyridinyl group, a pyrimidinyl group, a triazinyl group, a carbazolyl group, a dibenzofuranyl group, and a dibenzothiophenyl group.

17. The organic light-emitting device of claim 1, wherein the host is selected from Compounds H1 to H24:




H1




-continued


H2




H3



H4




H5




H6

-continued


H7




H8




H9



H10




H11




-continued


H12




H13




H14




H15



H16




-continued




H17


-continued




H21




H18




H22




H19



H23




H20




H24

18. The organic light-emitting device of claim 1, wherein the fluorescent dopant comprises a naphthalene core, a fluorene core, a spiro-bifluorene core, a benzofluorene core, a dibenzofluorene core, a phenanthrene core, an anthracene core, a fluoranthene core, a triphenylene core, a pyrene core, a chrysene core, a naphthacene core, a picene core, a perylene core, a pentaphene core, an indenoanthracene core, a tetracene core, a bisanthracene core, a core represented by one of Formulae 501-1 to 501-18, or any combination thereof:


-continued




Formula 501-1




Formula 501-2




Formula 501-3




Formula 501-4




Formula 501-5




Formula 501-6




Formula 501-7



Formula 501-8




Formula 501-9



Formula 501-10


-continued

Formula 501-11




-continued


Formula 501-15




Formula 501-16




Formula 501-12




Formula 501-17



Formula 501-18




Formula 501-13




19. The organic light-emitting device of claim 1, wherein the fluorescent dopant is selected from compounds represented by Formula 501:


Formula 501




Formula 501-14



Formula 501-1




-continued




Formula 501-2

-continued




Formula 501-7


Formula 501-3




Formula 501-8




Formula 501-4




Formula 501-9




Formula 501-5




Formula 501-10



Formula 501-6




-continued




Formula 501-11

-continued




Formula 501-15

Formula 501-16




Formula 501-17




Formula 501-18


Formula 501-12



Formula 501-13



Formula 501-14



wherein, in Formula 501,

Ar₅₀₁ is selected from

a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenanthrene group, an anthracene group, a fluoanthrene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a tetracene group, a bisanthracene group, and a group represented by one of Formulae 501-1 to 501-18; and

a naphthalene group, a fluorene group, a spiro-bifluorene group, a benzofluorene group, a dibenzofluorene group, a phenanthrene group, an anthracene group, a fluoanthrene group, a triphenylene group, a pyrene group, a chrysene group, a naphthacene group, a picene group, a perylene group, a pentaphene group, an indenoanthracene group, a tetracene group, a bisanthracene group, and a group represented by one of Formulae 501-1 to 501-18, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₆₀ alkyl group, a C₂-C₆₀ alkenyl group, a C₂-C₆₀ alkynyl group, a C₁-C₆₀ alkoxy

group, a C₃-C₁₀ cycloalkyl group, a C₁-C₁₀ heterocycloalkyl group, a C₃-C₁₀ cycloalkenyl group, a C₁-C₁₀ heterocycloalkenyl group, a C₆-C₆₀ aryl group, a C₆-C₆₀ aryloxy group, a C₆-C₆₀ arylthio group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, a monovalent non-aromatic condensed heteropolycyclic group, and —Si(Q₅₀₁)(Q₅₀₂)(Q₅₀₃) (wherein Q₅₀₁ to Q₅₀₃ are each independently selected from a hydrogen, a C₁-C₆₀ alkyl group, a C₁-C₆₀ alkoxy group, a C₆-C₆₀ aryl group, a C₁-C₆₀ heteroaryl group, a monovalent non-aromatic condensed polycyclic group, and a monovalent non-aromatic condensed heteropolycyclic group),

L₅₀₁ to L₅₀₃ are each independently selected from a substituted or unsubstituted C₃-C₁₀ cycloalkylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkylene group, a substituted or unsubstituted C₃-C₁₀ cycloalkenylene group, a substituted or unsubstituted C₁-C₁₀ heterocycloalkenylene group, a substituted or unsubstituted C₆-C₆₀ arylene group, a substituted or unsubstituted C₁-C₆₀ heteroarylene group, a substituted or unsubstituted divalent non-aromatic condensed polycyclic group, and a substituted or unsubstituted divalent non-aromatic condensed heteropolycyclic group,

R₅₀₁ and R₅₀₂ are each independently selected from

a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazole group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group; and


a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazolinyl group, a carbazolyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, each substituted with at least one selected from a deuterium, —F, —Cl, —Br, —I, a hydroxyl group, a cyano group, a nitro group, an amino group, an amidino group, a hydrazine group, a hydrazone group, a carboxylic acid group or a salt thereof, a sulfonic acid group or a salt thereof, a phosphoric acid group or a salt thereof, a C₁-C₂₀ alkyl group, a C₁-C₂₀ alkoxy group, a phenyl group, a biphenyl group, a terphenyl group, a naphthyl group, a fluorenyl group, a spiro-bifluorenyl group, a benzofluorenyl group, a dibenzofluorenyl group, a phenanthrenyl group, an anthracenyl group, a pyrenyl group, a chrysenyl group, a pyridinyl group, a pyrazinyl group, a pyrimidinyl group, a pyridazinyl group, a quinolinyl group, an isoquinolinyl group, a quinoxalinyl group, a quinazoli-

nyl group, a carbazolyl group, a triazinyl group, a dibenzofuranyl group, and a dibenzothiophenyl group, xd1 to xd3 are each independently selected from 0, 1, 2, and 3, and


xd4 is selected from 0, 1, 2, 3, 4, 5, and 6.

20. The organic light-emitting device of claim 1, wherein the fluorescent dopant comprises any one of Compounds FD(1) to FD(14), any one of Compounds FD1 to FD13, or any combination thereof:


Compound FD(1)




Compound FD(2)




Compound FD(3)



Compound FD(4)




-continued




Compound FD(5)

-continued




Compound FD(10)


Compound FD(6)




Compound FD(7)




Compound FD(8)




Compound FD(11)




Compound FD(9)



Compound FD(12)




Compound FD(13)




-continued


Compound FD(14)



FD1




FD2




-continued

FD3




FD4




-continued

FD5




-continued


FD9




FD10




FD6




FD11




FD7



FD8




FD12



-continued

FD13



* * * * *