



(86) Date de dépôt PCT/PCT Filing Date: 2006/09/20

(87) Date publication PCT/PCT Publication Date: 2007/06/14

(45) Date de délivrance/Issue Date: 2011/12/13

(85) Entrée phase nationale/National Entry: 2008/06/06

(86) N° demande PCT/PCT Application No.: US 2006/036427

(87) N° publication PCT/PCT Publication No.: 2007/067242

(30) Priorité/Priority: 2005/12/08 (US11/298,321)

(51) Cl.Int./Int.Cl. *H01M 4/86* (2006.01),
C23C 4/12 (2006.01), *H01M 4/88* (2006.01),
H01M 8/12 (2006.01)


(72) Inventeurs/Inventors:
HUANG, KEQIN, US;
HARTER, HAROLD D., US;
TURKAL, PAUL G., US

(73) Propriétaire/Owner:
SIEMENS ENERGY, INC., US

(74) Agent: SMART & BIGGAR

(54) Titre : ELECTRODE A COMBUSTIBLE A GRADIENTS A PALIERS ET SON PROCEDE DE FABRICATION

(54) Title: STEPPED GRADIENT FUEL ELECTRODE AND METHOD FOR MAKING THE SAME



(57) Abrégé/Abstract:

The present invention provides a method of depositing a stepped-gradient fuel electrode onto a fuel cell support 2 and the resulting fuel cell, that comprises placing a solid oxide fuel cell support that has at least an air electrode layer 4 and an electrolyte layer 6 into an atmospheric plasma sparging chamber and measuring spray parameters of an atmospheric plasma spray to obtain reactive oxides, conductive metal and graphite phases. Then spraying the spray parameters onto the solid oxide fuel cell support to produce multiple sub-layers 8 on the solid oxide fuel cell support, and adjusting usage of the atmospheric plasma spray. The adjusting of the hydrogen usage comprises using high hydrogen levels for the initial spraying of the sub-layers producing a first gradient region, and as lower hydrogen level for subsequent spraying of the sub-layers, producing a second gradient region.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
14 June 2007 (14.06.2007)

PCT

(10) International Publication Number
WO 2007/067242 A1

(51) International Patent Classification:

H01M 4/86 (2006.01) *H01M 8/12* (2006.01)
H01M 4/88 (2006.01) *C23C 4/12* (2006.01)

(74) Agents: STAUDT, Daniel J. et al.; SIEMENS CORPORATION- INTELLECTUAL PROPERTY DEPT., 170 Wood Avenue South, Iselin, NJ 08830 (US).

(21) International Application Number:

PCT/US2006/036427

(22) International Filing Date:

20 September 2006 (20.09.2006)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

11/298,321 8 December 2005 (08.12.2005) US

(71) Applicant (for all designated States except US):
SIEMENS POWER GENERATION, INC. [US/US];
4400 Alafaya Trail, Orlando, FL 32826-2399 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **HUANG, Kegin**
[CN/US]; 2364 Mount Vernon Avenue, Export, PA 15632
(US). **HARTER, Harold D.** [US/US]; 163 Summerfield
Drive, Munhall, PA 15120 (US). **TURKAL, Paul G.**
[US/US]; 419 Laurel Drive, McMurray, PA 15317 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.


(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: STEPPED GRADIENT FUEL ELECTRODE AND METHOD FOR MAKING THE SAME



(57) Abstract: The present invention provides a method of depositing a stepped-gradient fuel electrode onto a fuel cell support 2 and the resulting fuel cell, that comprises placing a solid oxide fuel cell support that has at least an air electrode layer 4 and an electrolyte layer 6 into an atmospheric plasma sparging chamber and measuring spray parameters of an atmospheric plasma spray to obtain reactive oxides, conductive metal and graphite phases. Then spraying the spray parameters onto the solid oxide fuel cell support to produce multiple sub-layers 8 on the solid oxide fuel cell support, and adjusting usage of the atmospheric plasma spray. The adjusting of the hydrogen usage comprises using high hydrogen levels for the initial spraying of the sub-layers producing a first gradient region, and as lower hydrogen level for subsequent spraying of the sub-layers, producing a second gradient region.

WO 2007/067242 A1

Stepped Gradient Fuel Electrode and Method for Making the Same

[0001] The U.S. Government has a paid-up license in this invention and the right in limited circumstances to require the patent owner to license others on reasonable terms as provided for by the terms of DE-FC26-97FT34139 awarded by DOE.

Field of the Invention

[0002] The field of the invention relates to solid oxide fuel cells, and more particularly to the making of the fuel electrodes on the fuel cell.

Background

[0003] Solid oxide fuel cells (SOFC) offer power generation in designs that produce energy cleanly and efficiently, and as the technology marches towards maturity the wide-spread use of fuel cells becomes closer. Inventions such as the standard package design by Gillett, US Patent 6,764,784 have help this advancement.

[0004] An example of a typical tubular SOFC design is illustrated in cross-section in Fig. 1 with an exaggerated scale. Air flows along the inside of the support tube **2**, which has layers on it first a cathode or air electrode substrate **4**, then a thin solid electrolyte layer **6**, and finally an anode or fuel electrode **8**. Finally, there is an interconnection **10** that received electron flow from adjoining fuel cells. Hydrocarbon fuels flowing along the outside of the cell mixes with oxygen delivered by the thin solid electrolyte layer **6** from the air, to form water, carbon dioxide and electrons.

[0005] Fig. 2 illustrates a scaled cross-sectional close-up of the anode layers. Oxygen transports through the air electrode substrate **4** and the electrolyte **6** to mix with the hydrocarbon fuels in the fuel electrode **8** to produce water, carbon dioxide and electrons.

[0006] The composition of the various anode layers necessarily needs to be different from one another. The electrolyte layer **6** is composed of Y_2O_3 or Sc_2O_3 doped ZrO_2 , or Sm-doped CeO_2 or an equivalent (collectively referred to herein as YSZ/ScSZ) where Y and Sc are rare earth elements. The air electrode substrate **4**, is porous, about 30% porosity, and a homogeneous mix of Ca and Ce doped $LaMnO_3$. The fuel electrode **8** is also porous, about 30% porosity, and is a homogeneous mix of about 25 wt%YSZ/ScSZ and 75 wt% conductive metal.

54106-98

[0007] However, the layers of the fuel electrode perform multiple functions which can be at odds with each other. For example, in the fuel electrode layer, the YSZ/ScSZ content helps the fuel oxidation reaction, but hinders the conduction of the electron flow. Therefore, the prior art has sought to maximize the net benefit of reaction versus conduction in the percentages given above, which, of course involves a compromise on each aspect.

[0008] The fuel electrode layers are deposited onto the support tube by slurry-coating techniques such as screen-printing and dip-coating, which give the homogenous layers discussed above.

[0009] What is needed is a method and apparatus that will produce fuel cells with layers that have a facile fuel oxidation reaction, as well as a better electronic conduction.

[0010] Other difficulties with the prior art also exist, some of which will be apparent upon further reading.

Summary of the Invention

[0011] With the foregoing in mind, methods and apparatuses consistent with the present invention, which inter alia facilitates generation of power from fuel cells by providing stepped gradient electrodes. The fuel electrode of the prior art is a homogenous material, while the present invention provides for a heterogeneous fuel electrode. The fuel electrode comprises two or more distinct regions that vary in base composition and porosity. This allows for greater fuel oxidization and electron flow. Particularly, the regions are made up of one or more sub-layers that have been deposited by APS.

54106-98

[0011a] In one method aspect, the invention relates to a method for depositing a stepped-gradient fuel electrode onto a fuel cell support, comprising: placing a solid oxide fuel cell support into an atmospheric plasma spraying chamber, the solid oxide fuel cell support comprising an air electrode layer and an electrolyte layer; measuring spray parameters of an atmospheric plasma spray to obtain reactive oxides, conductive metal and graphite phases; spraying said spray parameters onto said solid oxide fuel cell support to produce a plurality of sub-layers on said solid oxide fuel cell support, the plurality of sub-layers forming the stepped-gradient fuel electrode; and adjusting a hydrogen gas flow rate of said atmospheric plasma spray; wherein the adjusting of said hydrogen gas flow rate comprises (i) using a first hydrogen gas level to produce initial sub-layers of the plurality of sub-layers, the initial sub-layers comprising a first gradient region of the stepped-gradient fuel electrode, and (ii) using a second lower hydrogen gas level to produce subsequent sub-layers of the plurality of sub-layers, the subsequent sub-layers comprising a second gradient region of the stepped-gradient fuel electrode; wherein the first gradient region has a greater reactive oxides content than the second gradient region; wherein said first gradient region has a reactive oxides content of 25-50% by weight; wherein said second gradient region has a reactive oxides content of 10-25% by weight; wherein said reactive oxides and said conductive metal constitute the stepped-gradient fuel electrode and said graphite is sublimated to create pores in the stepped-gradient fuel electrode; and wherein the porosity of the stepped-gradient fuel electrode is less in the first gradient region than the second gradient region due to the higher hydrogen gas level used to produce the first gradient region.

[0012] These and other aspects, features, and advantages in accordance with the present invention are provided particular embodiments by a method of depositing a stepped-gradient fuel electrode onto a fuel cell support, that comprises placing a solid oxide fuel cell support that has an air electrode layer and an electrolyte layer into an atmospheric plasma spraying chamber and measuring spray parameters of an atmospheric spray to obtain reactive oxides,

54106-98

conductive metal and graphite phases. Then spraying fuel electrode with the spray parameters onto the solid oxide fuel cell support to produce multiple sub-layers on the solid oxide fuel cell support, and adjusting a hydrogen usage of the atmospheric plasma spray. The adjusting of the hydrogen usage comprises using

5 high hydrogen levels for the initial spraying of

the sub-layers producing a first gradient region, and a lower hydrogen level for subsequent spraying of the sub-layers, producing a second gradient region. The first gradient region has a reactive oxides content of 25-50% by weight, and the second gradient region has a reactive oxides content of 10-25% by weight.

[0013] In other related embodiments the first gradient region comprises 1-4 sub-layers. The first gradient region has a porosity of not greater than 20%, and the second gradient region has a porosity of at least 30%. In some embodiments the fuel electrode comprises more than two gradient regions, and the application is performed by indexing the solid oxide fuel cell support.

[0014] In another embodiment the present invention provides for a method for spraying a fuel electrode layer onto a solid oxide fuel cell support, that comprises using an atmospheric plasma sprayer to spray multiple sub-layers onto the fuel cell support, the sub-layers comprise a reactive YSZ/ScSZ phase, a nickel conductive metal and graphite for porosity, and the sub-layers form the fuel electrode layer. Then making multiple adjustments to a hydrogen flow to the plasma sprayer during the spraying of the sub-layers. Each adjustment of the hydrogen flow uses a proportionally greater hydrogen amount than each subsequent adjustment of the hydrogen flow, where sub-layers produced with proportionally greater hydrogen flow have proportionally greater reactive oxides content.

[0015] In another embodiment the present invention for a stepped-gradient fuel electrode deposited on a support tube that comprises multiple sub-layers and multiple gradient regions, each of the gradient regions comprises at least one of the sub-layers. Also the sub-layers comprise a homogenous mixture of reactive oxides and conductive metal, and the sub-layers have a porosity. Initial gradient regions comprise greater reactive oxides concentration than succeeding gradient regions.

[0016] In related embodiments the initial gradient regions comprise 25-50% by weight reactive oxides. The succeeding gradient regions comprise 10-25% by weight reactive oxides. In some embodiments the reactive oxides are YSZ/ScSZ, and the conductive metal is nickel. Also, the initial gradient regions comprise a lesser porosity than succeeding regions.

[0017] Other embodiments of the present invention also exist, which will be apparent upon further reading of the detailed description.

54106-98

Brief Description of the Figures

[0018] The invention is explained in more detail by way of example with reference to the following drawings:

[0019] Figure 1 illustrates a cross-sectional view of a tubular solid oxide fuel cells (SOFC) with an exaggerated scale.

[0020] Figure 2 illustrates a close up view of the fuel electrode layers with an exaggerated scale.

[0021] Figure 3 illustrates the YSZ/ScSZ and graphite contents in plasma sprayed fuel electrode as a function of secondary gas H₂ usage.

[0021a] Figure 4 illustrates the measured YSZ/ScSZ content as a function of flow rate of secondary H₂ gas at a fixed 15kW_e gun power level.

Detailed Description of the Invention

[0022] The present invention provides a method and apparatus for depositing a stepped-gradient fuel electrode layer onto a fuel cell support tube. Particularly, the present invention uses atmospheric plasma spraying (APS) to deposit the stepped-gradient fuel electrode layer. In the prior art, fuel electrode layers are formed from homogenous mixtures of a metal phase and an oxide phase, referred to as a cermet. However, the fuel electrode layer can perform multiple functions that require conflicting chemical make-up. For example, the fuel electrode requires a strong YSZ/ScSZ content to aid in the fuel oxidation reaction. However, the greater the YSZ/ScSZ content, the lower the conductive metal content, so the weaker the electron flow. A balance, therefore, between the electrochemical reaction and electronic conduction needed to be reached in the fuel electrode composition.

[0023] The present invention deposits the fuel electrode layer onto a support tube in a stepped-gradient manner. The complete layer is approximately 100μm thick, but comprises many sub-layers. For example, a 100μm fuel electrodes being layered by an APS will comprise 8-14 sub-layers. The content of the sub-layers can be gradually or quickly varied to produce a heterogeneous complete fuel electrode layer rather than a homogeneous layer of the prior art. The prior taught away from using the APS because of the basic design of fuel cells. For a majority of SOFC developers, fuel-electrode is used as the fuel cell support; it requires certain thickness, typically 0.5 to 1 mm, to provide sufficient mechanical strength. Traditional methods for making this substrate are tape-casting and die-pressing. APS is not suitable for making the substrate.

[0024] Each sub-layer itself is homogeneous, and will contain a different pre-determined mixture of reactive components, such as YSZ/ScSZ, conductive metal, such as nickel, and porosity, which is initially a graphite that is later sublimated to create the pores. The sub-layers may be graded in groups, so that the fuel electrode contains at least two different regions, or each of the sub-layers may have their content altered to produce as many different gradients as there are sub-layers. In most embodiments, the number of gradients will be less than the total number of sub-layers, so that at least some sub-layers will be homogenous.

[0025] The oxidation reaction of fuel occurs mainly within the region of the fuel electrode that is right next to the electrolyte layers. This region is only about 10-20 μ m thick, and the rest of the fuel electrode layer is used for gas diffusion and current conduction. The stepped-gradient of the present invention increases the proportion of oxides in the sub-layers close to the electrolyte side, or bottom, of the fuel electrode, and decreases the proportion of oxides in the sub-layers close to the fuel side, or top, of the fuel electrode. In addition, the porosity, initially controlled by graphite content, can also be decreased on the bottom and increased on the top.

[0026] Fig. 3 illustrates an embodiment of the present invention of a fuel electrode that contains at least two distinct sub-layer regions. The fuel electrode **8** is comprised of multiple sub-layers **9**. The bottom layers **12** consisting in this case of approximately 3 sub-layers, will have a high proportion of oxides, for example, 25-50wt% YSZ/ScSZ, and may even have a porosity of less than 20vol%. The top layers **14** which comprise the bulk of the fuel electrode, will be higher in conductive metal, for example 75-90wt% nickel, and may have a porosity of 30vol% or more.

[0027] Therefore, in one embodiment of the present invention, the stepped-gradient comprises at least two distinct sub-layer regions **12**, **14**, the bottom region being 25-50wt% of oxides and the top region being 75-90wt conductive metal. In further embodiments, the bottom region is 20vol% or less pores, and the top region is 30vol% or greater pores. In still further embodiments the bottom region comprises 1-4 sub-layers.

[0028] If more than two distinct sub-layer regions are used, then the oxide content in the reactive components should be the highest at the bottom and the lowest at the top, with intermediate regions following this trend. If porosity is also altered, then the porosity should increase from bottom to top.

[0029] A particular embodiment of depositing the stepped-gradient sub-layers is by use of atmospheric plasma spraying (APS). Atmospheric Plasma Spray is the process presently used in the manufacturing of SOFC's. This implies that the atmosphere into which the plasma is discharged, and in which the target (cylindrical, air electrode tube) resides is ambient air. APS is the most used of all of the thermal spray processes as it can develop sufficient energy to melt almost any material. The plasma gun incorporates a cathode (electrode) and an anode (nozzle) separated by a small gap. For APS used in this application, Hydrogen and Argon gases are used. As power is applied to the plasma gun, these gases pass through this small gap. An electrical arc is present and strips the gases of their electrons and a plasma is formed. As the unstable plasma recombines back to the gaseous state, energy is released. By introducing coating material in the form of powder into the gas plume, it is melted and propelled towards the target, after which this powder solidifies on the target surface forming a coating. Since the flow of each of the gases along with power can be accurately controlled, repeatable coating results can be obtained. The advantages of using APS to manufacture various thin layers for SOFCs are best reflected by its capability to achieve a high as-spray density, strong bonding strength and productivity. When using YSZ/ScSZ and Ni, the lower melting point Ni has a higher material utilization than higher melting point YSZ/ScSZ. By altering the plume temperature and particle velocity of the APS, the material utilization and final chemistry of the sub-layers can be adjusted. Referring to Fig. 4, the measured YSZ/ScSZ content as a function of flow rate of secondary H₂ gas at a fixed 15kWe gun power level is illustrated. As shown YSZ/ScSZ content gradually increases with hydrogen below 0.35 slpm and quickly raises to 24wt% at 1.25 slpm H₂, followed by a leveling off at about 1.5 slpm H₂. As the plume temperature of the plasma increases with H₂ flow, more YSZ/ScSZ melts at higher H₂ usage, leading to a higher YSZ/ScSZ content in the deposited sub-layers. The graphite (porosity) content decreases with the usage of hydrogen, since the higher plume temperature helps consume the graphite. Therefore varying the hydrogen flow according to Fig. 4 can produce the sub-layering discussed above.

[0030] A particular deposition pattern used by APS known as indexing can be used for particular embodiments. Indexing rotates the cell being sprayed in distinct, 12° turn increments. This can produce a more consistent layer than continuous rotation.

[0031] In one embodiment the present invention provides for a method of depositing a stepped-gradient fuel electrode onto a fuel cell support, that comprises placing a solid oxide fuel cell support that has at least an air electrode layer and an electrolyte layer into a atmospheric plasma spraying chamber and measuring spray parameters of an atmospheric plasma spray to obtain reactive oxides, conductive metal and graphite phases. Then applying the spray parameters onto the solid oxide fuel cell support to produce multiple sub-layers on the solid oxide fuel cell support, and adjusting a hydrogen usage of the atmospheric plasma spray. The adjusting of the hydrogen usage comprises using high hydrogen levels for the initial spraying of the sub-layers producing a first gradient region, and a lower hydrogen level for subsequent spraying of the sub-layers, producing a second gradient region. The first gradient region has a reactive oxides content of 25-50% by weight, and the second gradient region has a reactive oxides content of 10-25% by weight.

[0032] In related embodiments, the reactive oxides are YSZ/ScSZ, and the conductive metal is nickel. A gun power of the atmospheric plasma sprayer is 10-20 kWe, with an average of 15 kWe. Varying the gun power will change the ratios of oxide, metal and graphite in the as-sprayed fuel electrode.

[0033] In other related embodiments the first gradient region comprises 1-4 sub-layers. The first gradient region has a porosity of not greater than 20vol%, and the second gradient region has a porosity of at least 30vol%. In some embodiments the fuel electrode comprises more than two gradient regions, and the spraying is done by indexing the solid oxide fuel cell support.

[0034] In another embodiment the present invention provides for a method for spraying a fuel electrode layer onto a solid oxide fuel cell support, that comprises using an atmospheric plasma sprayer to spray multiple sub-layers onto the fuel cell support, the sub-layers comprise a reactive YSZ/ScSZ phase, a nickel conductive metal and graphite for porosity, and the sub-layers form the fuel electrode layer. Then making adjustments to a hydrogen flow to the plasma sprayer during the spraying of the sub-layers. Each adjustment of the hydrogen flow uses a proportionally greater hydrogen amount than each subsequent adjustment of the hydrogen flow, where sub-layers produced with proportionally greater hydrogen flow have proportionally greater reactive oxides content.

[0035] In related embodiments the method further comprises indexing the fuel cell support during the method. There are 8-14 sub-layers, 7-11 μm in thickness

each. In some embodiments 2-5 multiple adjustments are made, where 2-5 gradient regions are produced.

[0036] In another embodiment the present invention for a stepped-gradient fuel electrode deposited on a support tube that comprises multiple sub-layers and multiple gradient regions, each of the gradient regions comprises at least one of the sub-layers. Also the sub-layers comprise a homogenous mixture of reactive oxides and conductive metal, and the sub-layers have a porosity. Initial gradient regions comprise greater reactive oxides concentration than succeeding gradient regions.

[0037] In related embodiments the initial gradient regions comprise 25-50% by weight reactive oxides. The succeeding gradient regions comprise 10-25% by weight reactive oxides. In some embodiments the reactive oxides are YSZ/ScSZ, and the conductive metal is nickel. Also, the initial gradient regions comprise a lesser porosity than succeeding regions.

[0038] While specific embodiments of the invention have been described in detail, it will be appreciated by those skilled in the art that various modifications and alternatives to those details could be developed in light of the overall teachings of the disclosure. Accordingly, the particular arrangements disclosed are meant to be illustrative only and not limiting as to the scope of the inventions which, is to be given the full breadth of the claims appended and any and all equivalents thereof.

54106-98

CLAIMS:

1. A method for depositing a stepped-gradient fuel electrode onto a fuel cell support, comprising:

5 placing a solid oxide fuel cell support into an atmospheric plasma spraying chamber, the solid oxide fuel cell support comprising an air electrode layer and an electrolyte layer;

measuring spray parameters of an atmospheric plasma spray to obtain reactive oxides, conductive metal and graphite phases;

10 spraying said spray parameters onto said solid oxide fuel cell support to produce a plurality of sub-layers on said solid oxide fuel cell support, the plurality of sub-layers forming the stepped-gradient fuel electrode; and

adjusting a hydrogen gas flow rate of said atmospheric plasma spray;

15 wherein the adjusting of said hydrogen gas flow rate comprises (i) using a first hydrogen gas level to produce initial sub-layers of the plurality of sub-layers, the initial sub-layers comprising a first gradient region of the stepped-gradient fuel electrode, and (ii) using a second lower hydrogen gas level to produce subsequent sub-layers of the plurality of sub-layers, the subsequent sub-layers comprising a second gradient region of the stepped-gradient fuel
20 electrode;

wherein the first gradient region has a greater reactive oxides content than the second gradient region;

wherein said first gradient region has a reactive oxides content of 25-50% by weight;

25 wherein said second gradient region has a reactive oxides content of 10-25% by weight;

54106-98

wherein said reactive oxides and said conductive metal constitute the stepped-gradient fuel electrode and said graphite is sublimated to create pores in the stepped-gradient fuel electrode; and

5 wherein the porosity of the stepped-gradient fuel electrode is less in the first gradient region than the second gradient region due to the higher hydrogen gas level used to produce the first gradient region.

2. The method of claim 1, wherein said reactive oxides are YSZ/ScSZ.

3. The method of claim 1 or 2, wherein said conductive metal is nickel.

4. The method of any one of claims 1 to 3, wherein a gun power of said
10 atmospheric plasma spray is 10-20 kW.

5. The method of any one of claims 1 to 4, wherein said first gradient region comprises 1-4 sub-layers.

6. The method of any one of claims 1 to 5, wherein said first gradient region has a porosity of not greater than 20%, and said second gradient region
15 has a porosity of at least 30%.

7. The method of any one of claims 1 to 6, wherein said stepped-gradient fuel electrode comprises more than two gradient regions.

8. The method of any one of claims 1 to 7, wherein said spraying is done by indexing said solid oxide fuel cell support.

1/2




FIG. 1
PRIOR ART




FIG. 2
PRIOR ART

2/2




FIG. 3




FIG. 4

