

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5






FIG. 7A




FIG. 7B





FIG. 7C






FIG. 8A




FIG. 8B




FIG. 9

SEMICONDUCTOR DEVICE AND METHOD FOR MANUFACTURING THE SAME

CROSS-REFERENCE TO RELATED APPLICATION

This application is based upon and claims the benefit of priority from Japanese Patent Application No. 2015-165586, filed on Aug. 25, 2015; the entire contents of which are incorporated herein by reference.

FIELD

Embodiments described herein relate generally to a semiconductor device and a method for manufacturing the same.

BACKGROUND

A gate electrode of a memory device and an interconnect of a cross-point memory require high melting point and low resistance. For such an electrode (interconnect) material, tungsten or molybdenum is under investigation. However, they have higher bulk resistivity than e.g. copper, which is typically used for low-resistance interconnect in a semiconductor device.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a schematic perspective view of a semiconductor device of an embodiment;

FIG. 2 is a schematic sectional view of the semiconductor device of the embodiment;

FIG. 3 is a partially enlarged sectional view of FIG. 2;

FIG. 4 and FIG. 5 are schematic sectional views showing a method for manufacturing the semiconductor device of the embodiment;

FIGS. 6A to 6F are schematic views of body-centered cubic structures and main plane orientations of the body-centered cubic structures;

FIG. 7A is a grain size distribution diagram of a crystal of Mo film formed on TaAl film, FIG. 7B is a grain size distribution diagram of a crystal of Mo film formed on WZr film, and FIG. 7C is a grain size distribution diagram of a crystal of Mo film formed on SiO₂ film;

FIG. 8A is a characteristic diagram showing how a specific resistance of Mo film formed on TaAl film depends on Al content in the TaAl film, and FIG. 8B is a characteristic diagram showing how a specific resistance of Mo film formed on WZr film depends on Zr content in the WZr film; and

FIG. 9 is a characteristic diagram showing how a specific resistance of Mo film formed on WTi film depends on Ti content in the WTi film.

DETAILED DESCRIPTION

According to one embodiment, a semiconductor device includes an underlying metal film and a metal film. The underlying metal film is a tantalum-aluminum film having an aluminum content of more than 50 atomic % and less than 85 atomic %, a tungsten-zirconium film having a zirconium content of less than 40 atomic %, a tungsten-titanium film having a titanium content of less than 80 atomic %, or a tungsten film. The metal film is provided on the underlying metal film and in contact with the underlying metal film. The metal film contains at least one of tungsten and molybdenum, and has a main orientation of (100) or (111).

Embodiment will now be described with reference to the drawings. In the drawings, like elements are labeled with like reference numerals.

The semiconductor device of the embodiments is e.g. a semiconductor memory device including a memory cell array.

FIG. 1 is a schematic perspective view of the memory cell array 1 of the embodiment.

In FIG. 1, two directions parallel to the major surface of the substrate 10 and orthogonal to each other are referred to as X-direction (first direction) and Y-direction (second direction). The direction orthogonal to both the X-direction and the Y-direction is referred to as Z-direction (third direction, stacking direction).

The memory cell array 1 includes a substrate 10, a stacked body 100 provided on the major surface of the substrate 10, a plurality of columnar parts CL, a plurality of conductive members LI, and an upper interconnect provided on the stacked body 100. FIG. 1 shows a bit line BL and a source layer SL as the upper interconnect.

The columnar part CL is formed like a circular column or elliptical column extending in the stacking direction (Z-direction) in the stacked body 100. The conductive member LI extends in the stacking direction (Z-direction) of the stacked body 100 and the X-direction between the upper interconnect and the substrate 10. The conductive member LI separates the stacked body 100 in the Y-direction.

The plurality of columnar parts CL are arranged in e.g. a staggered arrangement. Alternatively, the plurality of columnar parts CL may be arranged in a square lattice along the X-direction and the Y-direction.

A plurality of bit lines (e.g., metal films) BL are provided on the stacked body 100. The plurality of bit lines BL are separated from each other in the X-direction. Each bit line BL extends in the Y-direction.

The upper end part of the columnar part CL is connected to the bit line BL through a contact part Cb. The plurality of columnar parts CL, each of which is selected from each of areas (blocks) separated in the Y-direction by the conductive member LI, are connected to one common bit line BL.

FIG. 2 is a schematic sectional view of the substrate 10 and the stacked body 100. FIG. 2 shows a cross section parallel to the Y-Z plane in FIG. 1.

The stacked body 100 includes a plurality of metal films 70, a plurality of insulating films 40, and a plurality of underlying metal films 71. The metal films 70, the insulating films 40, and the underlying metal films 71 are stacked in the direction (Z-direction) perpendicular to the major surface of the substrate 10.

The metal films 70 are stacked in the Z-direction at a prescribed pitch via the insulating film 40. The insulator between the metal films 70 adjacent in the Z-direction is not limited to the insulating film 40, but may be an air gap. In the example shown in FIG. 2, a stacked film of the underlying metal film 71 and the metal film 70 is stacked in a plurality at a prescribed pitch via the insulating film 40.

The underlying metal film 71 is provided between the lower surface of the metal film 70 and the insulating film 40. The underlying metal film 71 is in contact with the lower surface of the metal film 70. The insulating film 40 is provided between the underlying metal film 71 and the upper surface of the metal film 70 located one layer below the underlying metal film 71. The underlying metal film 71 is not provided on the upper surface of the metal film 70. The underlying metal film 71 is provided for each metal film 70. The number of underlying metal films 71 is equal to the number of metal films 70. The plurality of underlying metal

films **71** are not connected in the stacking direction of the stacked body **100**, but are separated from each other in the stacking direction.

The metal film **70** contains at least one of tungsten (W) and molybdenum (Mo). The metal film **70** is a tungsten film primarily containing tungsten, or a molybdenum film primarily containing molybdenum. The insulating film **40** primarily contains e.g. silicon oxide (SiO₂).

The underlying metal film **71** is a tantalum-aluminum film primarily containing tantalum-aluminum (TaAl) alloy. Alternatively, the underlying metal film **71** is a tungsten-zirconium film primarily containing tungsten-zirconium (WZr) alloy. Alternatively, the underlying metal film **71** is a tungsten-titanium film primarily containing tungsten-titanium (WTi) alloy. Alternatively, the underlying metal film **71** is a tungsten film (an element film of tungsten) primarily containing tungsten (W).

The metal film **70** is crystallized. The metal film **70** is thicker than the underlying metal film **71**.

The underlying metal film **71** is amorphous. Alternatively, the underlying metal film **71** is a microcrystalline film having an average grain size of the crystal smaller than an average grain size of the crystal of the metal film **70**.

Here, an amorphous film has a broad diffraction intensity, or halo peak, observed by diffraction measurement for electron beam diffraction and X-ray diffraction such as RHEED (reflection high energy electron diffraction). It may be observed diffraction lines from intermetallic compound microcrystals due to incomplete amorphousness. Furthermore, the underlying metal film **71** does not need to be entirely amorphous. The underlying metal film **71** may have a structure in which part of the crystalline thin film is made amorphous.

The aluminum (Al) content in the tantalum-aluminum (TaAl) film as the underlying metal film **71** is more than 50 atomic % and less than 85 atomic %. The metal film (Mo film or W film) **70** formed on such a TaAl film has a main orientation of (100). The main orientation of the plane of the metal film **70** along the interface with the underlying metal film (TaAl film) **71** is (100).

The main orientation of (100) means that the diffraction intensity in the plane orientation (100) is the strongest in the diffraction measurement for e.g. the surface of the metal film **70** or the aforementioned interface of the metal film **70**.

The zirconium (Zr) content in the tungsten-zirconium (WZr) film as the underlying metal film **71** is less than 40 atomic %. The metal film (Mo film or W film) **70** formed on such a WZr film has a main orientation of (111). The main orientation of the plane of the metal film **70** along the interface with the underlying metal film (WZr film) **71** is (111).

The main orientation of (111) means that the diffraction intensity in the plane orientation (111) is the strongest in the diffraction measurement for e.g. the surface of the metal film **70** or the aforementioned interface of the metal film **70**.

The titanium (Ti) content in the tungsten-titanium (WTi) film as the underlying metal film **71** is less than 80 atomic %. The metal film (Mo film or W film) **70** formed on such a WTi film has a main orientation of (111). The main orientation of the plane of the metal film **70** along the interface with the underlying metal film (WTi film) **71** is (111).

The metal film (Mo film or W film) **70** formed on the tungsten (W) film as the underlying metal film **71** has a main orientation of (111). The main orientation of the plane of the metal film **70** along the interface with the underlying metal film (W film) **71** is (111).

As shown in FIG. 2, the columnar part CL includes a memory film **30**, a semiconductor film **20**, and a core insulating film **50**.

The memory film **30** and the semiconductor film **20** extend like a pipe in the stacking direction (Z-direction) in the stacked body **100**. The memory film **30** is provided between the stacked body **100** and the semiconductor film **20**. The memory film **30** surrounds the semiconductor film **20** from the outer peripheral side. The core insulating film **50** is provided inside the pipe-shaped semiconductor film **20**. The upper end part of the semiconductor film **20** is electrically connected to the bit line BL through the contact part Cb shown in FIG. 1.

FIG. 3 is a partially enlarged sectional view of FIG. 2.

The memory film **30** includes a block insulating film **33**, a charge storage film **32**, and a tunnel insulating film **31**. The block insulating film **33**, the charge storage film **32**, the tunnel insulating film **31**, and the semiconductor film **20** extend continuously in the stacking direction of the stacked body **100**. The block insulating film **33**, the charge storage film **32**, and the tunnel insulating film **31** are provided sequentially from the stacked body **100** side between the stacked body **100** and the semiconductor film **20**.

The block insulating film **33** is in contact with the metal film **70**. The tunnel insulating film **31** is in contact with the semiconductor film **20**. The charge storage film **32** is provided between the block insulating film **33** and the tunnel insulating film **31**.

The semiconductor film **20**, the memory film **30**, and the metal film **70** constitute a memory cell MC. The memory cell MC has a vertical transistor structure in which the metal film **70** surrounds the semiconductor film **20** via the memory film **30**.

The semiconductor film **20** functions as a channel of the memory cell MC of the vertical transistor structure. The metal film **70** functions as a control gate (control electrode). The charge storage film **32** functions as a data storage layer for storing charge injected from the semiconductor film **20**.

The semiconductor memory device of the embodiment is a nonvolatile semiconductor memory device capable of electrically and freely erasing/programming data and retaining its memory content even when powered off.

The memory cell MC is e.g. a charge trap type memory cell. The charge storage film **32** includes a large number of trap sites for trapping charge in the insulating film, and includes e.g. silicon nitride film.

The tunnel insulating film **31** serves as a potential barrier when charge is injected from the semiconductor film **20** into the charge storage film **32**, or when the charge stored in the charge storage film **32** is released into the semiconductor film **20**. The tunnel insulating film **31** includes e.g. silicon oxide film.

The block insulating film **33** prevents the charge stored in the charge storage film **32** from releasing into the metal film **70**. The block insulating film **33** includes a stacked film of e.g. a silicon oxide film and a film having higher dielectric constant (silicon nitride film, aluminum oxide film, hafnium oxide film, or yttrium oxide film) than the silicon oxide film.

As shown in FIG. 1, a drain side select transistor STD is provided in the upper end part of the columnar part CL. A source side select transistor STS is provided in the lower end part of the columnar part CL. At least the lowermost metal film **70** of the plurality of metal films **70** functions as a control gate (control electrode) of the source side select transistor STS. At least the uppermost metal film **70** of the plurality of metal films **70** functions as a control gate (control electrode) of the drain side select transistor STD.

The drain side select transistor STD and the source side select transistor STS are vertical transistors like the memory cell MC. A current flows in the stacking direction (Z-direction) of the stacked body **100**.

A plurality of memory cells MC are provided between the drain side select transistor STD and the source side select transistor STS. The memory cells MC, the drain side select transistor STD, and the source side select transistor STS are series connected through the semiconductor film **20** and constitute one memory string. Such memory strings are arranged in e.g. a staggered arrangement in the plane direction parallel to the X-Y plane. Thus, the plurality of memory cells MC are provided three-dimensionally in the X-direction, the Y-direction, and the Z-direction.

As shown in FIG. 2, an insulating film **62** is provided on both sidewalls of the conductive member LI separating the stacked body **100** in the Y-direction. The insulating film **62** is provided between the stacked body **100** and the conductive member LI. In FIG. 1, the insulating film **62** is not shown.

The conductive member LI is a metal member primarily containing e.g. tungsten. The upper end part of the conductive member LI is connected to the source layer SL, shown in FIG. 1, provided on the stacked body **100**. The lower end of the conductive member LI is in contact with the substrate **10** as shown in FIG. 2. The lower end of the semiconductor film **20** is in contact with the substrate **10**. The substrate **10** is e.g. a silicon substrate doped with impurity and having conductivity. Thus, the lower end of the semiconductor film **20** is electrically connected to the source layer SL through the substrate **10** and the conductive member LI.

Next, a method for manufacturing a semiconductor memory device of the embodiment is described with reference to FIGS. 4 and 5.

As shown in FIG. 4, a stacked body **100** is formed on a substrate **10**. An insulating film **40** is formed on the major surface of the substrate **10**. An underlying metal film **71** is formed on the insulating film **40**. A metal film **70** is formed on the underlying metal film **71**. An insulating film **40** is formed again on the metal film **70**. Then, a similar step for forming an underlying metal film **71** on the insulating film **40**, forming a metal film **70** on the underlying metal film **71**, and forming an insulating film **40** on the metal film **70** is repeated a plurality of times.

After the stacked body **100** is formed on the substrate **10**, as shown in FIG. 5, a plurality of memory holes MH are formed in the stacked body **100**. The memory hole MH is formed by reactive ion etching (RIE) technique using a mask layer, not shown, formed on the stacked body **100**. The memory hole MH penetrates through the stacked body **100** to the substrate **10**.

The films constituting the columnar part CL shown in FIG. 2 are formed in the memory hole MH. First, a memory film **30** is formed conformally on the side surface and bottom of the memory hole MH. The memory film **30** at the bottom of the memory hole MH is removed by e.g. RIE technique. Thus, the substrate **10** is exposed at the bottom of the memory hole MH. Then, a semiconductor film **20** is formed inside the memory film **30** in the memory hole MH. The lower end of the semiconductor film **20** is in contact with the substrate **10** at the bottom of the memory hole MH. After the semiconductor film **20** is formed, a core insulating film **50** is formed inside the semiconductor film **20**.

A slit is formed in the portion of the stacked body **100** in which the conductive member LI is to be provided. The slit extends in the stacking direction (Z-direction) and the depth

direction (X-direction) of the page in FIG. 2. Thus, the slit separates the stacked body **100** in the Y-direction.

A conductive member LI is formed in the slit via an insulating film **62**. The insulating film **62** is formed conformally on the side surface and bottom of the slit. The insulating film **62** at the bottom of the slit is removed by e.g. RIE technique. Thus, the substrate **10** is exposed at the bottom of the slit. Then, the conductive member LI is formed inside the insulating film **62** in the slit. The lower end of the conductive member LI is in contact with the substrate **10**.

The slit and the conductive member LI may be formed after the memory hole MH and the columnar part CL are formed. Alternatively, the memory hole MH and the columnar part CL may be formed after the slit and the conductive member LI are formed. Alternatively, the memory hole MH and the slit may be simultaneously formed by RIE technique.

After the stacked body **100**, the columnar part CL, and the conductive member LI are formed, an upper interconnect of e.g. the bit lines BL and the source layer SL shown in FIG. 1 is formed on the stacked body **100**.

In the following, a method for forming the underlying metal film **71** and the metal film **70** is described.

First, a method for forming the underlying metal film **71** is described.

The underlying metal film **71** is formed on the insulating film **40**. As the underlying metal film **71**, for instance, a TaAl film is formed by sputtering technique. In a sputtering chamber of a gas atmosphere containing argon (Ar), a Ta target and an Al target are placed on the cathode side and sputtered simultaneously.

The composition of the TaAl film is controlled by adjusting the power applied to the Ta target (cathode) and the power applied to the Al target (cathode). According to the embodiment, the application power is adjusted so that the Al content in the TaAl film is more than 50 atomic % and less than 85 atomic %.

Next, a metal film **70** primarily containing at least one of W and Mo is formed on the underlying metal film **71** by physical vapor deposition (PVD) technique, chemical vapor deposition (CVD) technique, atomic layer deposition (ALD) technique, or coating technique. The metal film **70** undergoes crystal growth on the underlying metal film **71**.

For instance, a Mo film as the metal film **70** is formed by sputtering technique on the TaAl film as the underlying metal film **71**.

Here, the crystal structure of Mo and W is described. Mo and W have a body-centered cubic structure.

FIGS. 6A, 6C, and 6E are schematic perspective views of the body-centered cubic structure. FIGS. 6B, 6D, and 6F are schematic views showing the main plane orientation of the body-centered cubic structure.

The plane shaded in FIG. 6A is a (110) plane. FIG. 6B shows the extracted (110) plane.

The plane shaded in FIG. 6C is a (100) plane. FIG. 6D shows the extracted (100) plane.

The plane shaded in FIG. 6E is a (111) plane. FIG. 6F shows the extracted (111) plane.

When the Mo film or W film is formed on the SiO₂ film by sputtering technique or CVD technique, the main orientation of the plane of the Mo film or W film along the interface with the SiO₂ film tends to be (110), which is the close-packed plane with low surface energy. Here, the main orientation of (110) means that the diffraction intensity in the

plane orientation (110) is the strongest in the diffraction measurement for the surface of the Mo film or W film, or its interface with the SiO₂ film.

In contrast, according to the embodiment, the Mo film (metal film **70**) is formed on the TaAl film (underlying metal film **71**) under composition control such that the Al content is more than 50 atomic % and less than 85 atomic %. Thus, the main orientation of the Mo film can be set to (100).

The average grain size of the crystal of such a Mo film with a main orientation of (100) is larger than the average grain size of the crystal of a Mo film with a main orientation of (110). In the body-centered cubic structure, the (100) plane has lower in-plane atomic density and higher surface energy than the (110) plane. The crystal grows so as to minimize the sum of the surface energy and the strain energy. On the other hand, the energy contributing to crystal growth is constrained by the energy at the time of film formation. That is, in the case where the Mo film is formed in the orientation of the (110) plane having low surface energy, a small amount of energy is used for crystal grain growth. Thus, the crystal grain in the formed film is likely to be small.

In contrast, in the (100) plane having higher surface energy than the (110) plane, a larger amount of energy is used for grain growth in the film than in the (110) plane. Thus, the crystal grain growth advances so as to make the strain energy lower. Accordingly, it is considered that the grain size is made larger.

The crystal grain in the formed film can be analyzed by e.g. electron back scatter diffraction pattern (EBSD) technique. More specifically, a tilted sample is irradiated with an electron beam. Then, diffraction electron beams at each crystal plane are obtained from the sample surface, and can be used to monitor the orientation of the crystal. Furthermore, the grain size of the crystal can be calculated from the spatial distribution of the crystal orientation at this time.

Here, FIG. 7A is a grain size distribution diagram of the crystal of the Mo film formed on the TaAl film with an Al content of approximately 77-82 atomic %. FIG. 7C is a grain size distribution diagram of the crystal of the Mo film formed on the SiO₂ film.

As the result of EBSD analysis, the Mo film formed on the TaAl film has a main orientation of (100). The Mo film formed on the SiO₂ film has a main orientation of (110). By comparison between FIGS. 7A and 7C, it is confirmed that the Mo film on the TaAl film includes more crystals with a larger size than the Mo film on the SiO₂ film.

The crystal having a larger grain size decreases the specific resistance. That is, the specific resistance of the Mo film with a main orientation of (100) is lower than the specific resistance of the Mo film with a main orientation of (110).

FIG. 8A is a characteristic diagram showing how the specific resistance of the Mo film formed on the TaAl film depends on the Al content in the TaAl film. FIG. 8A also shows the specific resistance of the Mo film formed on the SiO₂ film (plotted on the axis at which the Al content is 0 atomic %).

From the result of FIG. 8A, it is found that the specific resistance of the Mo film on the TaAl film is lower than the specific resistance of the Mo film on the SiO₂ film when the Al content in the TaAl film is more than 50 atomic % and less than 85 atomic %.

Thus, it is considered that the Mo film formed on the TaAl film with an Al content of more than 50 atomic % and less than 85 atomic % has a main orientation of (100) and has a large grain size. That is, when the Mo film is formed on the

TaAl film with a suitably controlled composition ratio, the specific resistance of the Mo film can be decreased.

The same also applies to tungsten having a body-centered cubic structure like molybdenum. That is, the W film formed on the TaAl film with an Al content of more than 50 atomic % and less than 85 atomic % has a main orientation of (100), has a large grain size, and has a lower specific resistance than the W film on the SiO₂ film.

The metal film (Mo film or W film) **70** is for a control electrode of the memory cell MC and the select transistor STD, STS. Thus, the resistance of the control electrode of the memory cell MC and the select transistor STD, STS having the metal film (Mo film or W film) **70** formed on the underlying metal film **71** made of TaAl film with an Al content of more than 50 atomic % and less than 85 atomic % can be made lower than the resistance of the control electrode of the memory cell MC and the select transistor STD, STS having the Mo film or W film formed directly on the SiO₂ film.

The metal film (Mo film or W film) **70** has a melting point enough to withstand e.g. annealing at approximately 1000° C. performed after forming the semiconductor film **20**. The metal film **70** is not melted at the time of the annealing. Furthermore, no metal diffusion occurs.

The underlying metal film **71**, including the TaAl film and the other films described below, is an amorphous or micro-crystalline film at least immediately after film formation. The underlying metal film **71** may be recrystallized by annealing in the post-process. However, the recrystallized underlying metal film **71** does not include a larger crystal grain than the metal film **70**. The average grain size of the underlying metal film **71** is smaller than the average grain size of the metal film **70**. Furthermore, the crystal grain of the underlying metal film **71** and the crystal grain of the metal film **70** are not united into one crystal grain by annealing.

Next, an alternative example of the underlying metal film **71** is described.

As the underlying metal film **71**, for instance, a WZr film is formed by sputtering technique. In a sputtering chamber of a gas atmosphere containing argon (Ar), a W target and a Zr target are placed on the cathode side and sputtered simultaneously.

The composition of the formed WZr film is controlled by adjusting the power applied to the W target (cathode) and the power applied to the Zr target (cathode). The application power is adjusted so that the Zr content in the WZr film is less than 40 atomic %.

For instance, a Mo film is formed as the metal film **70** by sputtering technique on the WZr film. The Mo film (metal film **70**) is formed on the WZr film (underlying metal film **71**) under composition control such that the Zr content is less than 40 atomic %. Thus, the main orientation of the Mo film can be set to (111).

The average grain size of the crystal of such a Mo film with a main orientation of (111) is larger than the average grain size of the crystal of a Mo film with a main orientation of (110). In the body-centered cubic structure, the (111) plane has lower in-plane atomic density and higher surface energy than the (110) plane. The crystal grows so as to minimize the sum of the surface energy and the strain energy under the constrained amount of available energy. Thus, in the (111) plane having higher surface energy than the (110) plane, the crystal grain growth advances so as to make the strain energy lower than in the (110) plane. Accordingly, it is considered that the grain size is made larger.

FIG. 7B is a grain size distribution diagram of the crystal of the Mo film formed on the WZr film with a Zr content of approximately 5-10 atomic %. As the result of EBSD analysis, the Mo film formed on the WZr film has a main orientation of (111). As described above, FIG. 7C shows a crystal grain size distribution of the Mo film on the SiO₂ film. By comparison between FIGS. 7B and 7C, it is confirmed that the Mo film on the WZr film includes more crystals with a larger size than the Mo film on the SiO₂ film.

The crystal having a larger grain size decreases the specific resistance. That is, the specific resistance of the Mo film with a main orientation of (111) is lower than the specific resistance of the Mo film with a main orientation of (110).

FIG. 8B is a characteristic diagram showing how the specific resistance of the Mo film formed on the WZr film depends on the Zr content in the WZr film. FIG. 8B also shows the specific resistance of the Mo film formed on the SiO₂ film (plotted on the axis at which the Zr content is 0 atomic %). The WZr film having a Zr content of 0 atomic % corresponds to an elemental film of tungsten.

From the result of FIG. 8B, it is found that the specific resistance of the Mo film on the WZr film is lower than the specific resistance of the Mo film on the SiO₂ film when the Zr content in the WZr film is less than 40 atomic %.

Thus, it is considered that the Mo film formed on the WZr film with a Zr content of less than 40 atomic % has a main orientation of (111) and has a large grain size. That is, when the Mo film is formed on the WZr film with a suitably controlled composition ratio, the specific resistance of the Mo film can be decreased.

The same also applies to tungsten having a body-centered cubic structure like molybdenum. That is, the W film formed on the WZr film with a Zr content of less than 40 atomic % has a main orientation of (111), has a large grain size, and has a lower specific resistance than the W film on the SiO₂ film.

Thus, the resistance of the control electrode of the memory cell MC and the select transistor STD, STS having the metal film (Mo film or W film) 70 formed on the underlying metal film 71 made of WZr film with a Zr content of less than 40 atomic % can be made lower than the resistance of the control electrode of the memory cell MC and the select transistor STD, STS having the Mo film or W film formed directly on the SiO₂ film.

Next, a further alternative example of the underlying metal film 71 is described.

As the underlying metal film 71, for instance, a WTi film is formed by sputtering technique. In a sputtering chamber of a gas atmosphere containing argon (Ar), a W target and a Ti target are placed on the cathode side and sputtered simultaneously.

The composition of the formed WTi film is controlled by adjusting the power applied to the W target (cathode) and the power applied to the Ti target (cathode). The application power is adjusted so that the Ti content in the WTi film is less than 80 atomic %.

For instance, a Mo film is formed as the metal film 70 by sputtering technique on the WTi film. The Mo film (metal film 70) is formed on the WTi film (underlying metal film 71) under composition control such that the Ti content is less than 80 atomic %. Thus, the main orientation of the Mo film can be set to (111).

As in the aforementioned case where the Mo film is formed on the WZr film, in the (111) plane having higher surface energy than the (110) plane, the crystal grain growth advances so as to make the strain energy lower than in the

(110) plane. Accordingly, it is considered that the grain size of the Mo film formed on the WTi film is made larger.

The crystal having a larger grain size decreases the specific resistance. That is, the specific resistance of the Mo film with a main orientation of (111) is lower than the specific resistance of the Mo film with a main orientation of (110).

FIG. 9 is a characteristic diagram showing how the specific resistance of the Mo film formed on the WTi film depends on the Ti content in the WTi film. FIG. 9 also shows the specific resistance of the Mo film formed on the SiO₂ film (plotted on the axis at which the Ti content is 0 atomic %). The WTi film having a Ti content of 0 atomic % corresponds to an elemental film of tungsten.

From the result of FIG. 9, it is found that the specific resistance of the Mo film on the WTi film is lower than the specific resistance of the Mo film on the SiO₂ film when the Ti content in the WTi film is less than 80 atomic %.

Thus, it is considered that the Mo film formed on the WTi film with a Ti content of less than 80 atomic % has a main orientation of (111) and has a large grain size. That is, when the Mo film is formed on the WTi film with a suitably controlled composition ratio, the specific resistance of the Mo film can be decreased.

The same also applies to tungsten having a body-centered cubic structure like molybdenum. That is, the W film formed on the WTi film with a Ti content of less than 80 atomic % has a main orientation of (111), has a large grain size, and has a lower specific resistance than the W film on the SiO₂ film.

Thus, the resistance of the control electrode of the memory cell MC and the select transistor STD, STS having the metal film (Mo film or W film) 70 formed on the underlying metal film 71 made of WTi film with a Ti content of less than 80 atomic % can be made lower than the resistance of the control electrode of the memory cell MC and the select transistor STD, STS having the Mo film or W film formed directly on the SiO₂ film.

Next, a further alternative example of the underlying metal film 71 is described.

As the underlying metal film 71, an elemental film of tungsten (W film) is formed by sputtering technique. In a sputtering chamber of a gas atmosphere containing argon (Ar), a W target is placed on the cathode side and sputtered.

For instance, a Mo film is formed as the metal film 70 by sputtering technique on the W film as the underlying metal film 71. Thus, the Mo film (metal film 70) is formed on the W film (underlying metal film 71). Accordingly, the main orientation of the Mo film can be set to (111).

As described above, in the (111) plane having higher surface energy than the (110) plane, the crystal grain growth advances so as to make the strain energy lower than in the (110) plane. Accordingly, it is considered that the grain size of the Mo film formed on the W film is made larger.

The crystal having a larger grain size decreases the specific resistance. That is, the specific resistance of the Mo film with a main orientation of (111) is lower than the specific resistance of the Mo film with a main orientation of (110).

FIGS. 8B and 9 show the specific resistance of the Mo film on the W film. The specific resistance of the Mo film on the W film is lower than the specific resistance of the Mo film on the SiO₂ film plotted on the same FIGS. 8B and 9.

Thus, it is considered that the Mo film formed on the W film has a main orientation of (111) and has a large grain size. That is, when the Mo film is formed on the W film, the specific resistance of the Mo film can be decreased.

The same also applies to tungsten having a body-centered cubic structure like molybdenum. That is, the W film as the metal film 70 formed on the W film as the underlying metal film 71 has a main orientation of (111), has a large grain size, and has a lower specific resistance than the W film on the SiO₂ film.

Here, the W film as the metal film 70 has a thickness enough to function as a control electrode of e.g. the memory cell MC, and has a large grain size. In contrast, the W film as the underlying metal film 71 is thinner than the metal film 70, and is an amorphous film, or a microcrystalline film having a smaller grain size than the metal film 70.

The resistance of the control electrode of the memory cell MC and the select transistor STD, STS having the metal film (Mo film or W film) 70 formed on the underlying metal film 71 made of W film can be made lower than the resistance of the control electrode of the memory cell MC and the select transistor STD, STS having the Mo film or W film formed directly on the SiO₂ film.

It is noted that a W film was formed as the metal film 70 by sputtering technique on the W film as the underlying metal film 71 formed by CVD technique, then the main orientation of the metal film (W film) 70 was (110).

The process for forming a W film as the underlying metal film 71 by CVD technique alternately performs e.g. the step of supplying a gas containing WF₆, and the step of supplying a gas containing a hydrogen compound such as SiH₄ and B₂H₆. In this case, the formed W film is mixed with impurity originating from the source gas such as B and F.

The W film with a large amount of impurity may have a low surface energy due to coupling between the impurity and W. The surface energy of the metal film 70 is denoted by γ_f . The surface energy of the underlying metal film 71 is denoted by γ_s . The interfacial energy of the underlying metal film 71 and the metal film 70 is denoted by γ_i . Then, the relation of $\gamma_f \leq \gamma_s - \gamma_i$ holds among them.

From this relation, it is considered that the metal film (Mo film or W film) is less likely to assume a main orientation of (111) having high surface energy when the surface energy γ_s of the underlying metal film 71 is low. Here, the metal film (Mo film or W film) formed on the W film formed by CVD technique can have a main orientation of (111) if the composition of the films can be suitably controlled.

On the other hand, the sputtering technique enables formation of a W film as the underlying metal film 71 having high purity close to the target composition. Thus, the metal film (Mo film or W film) 70 formed on the W film as the underlying metal film 71 formed by sputtering technique can assume a main orientation of (111) having high surface energy. Thus, the specific resistance can be decreased by a larger grain size.

In the case of forming a metal film (Mo film or W film) 70 by sputtering technique, the sputtering film formation performed simultaneously with heating the substrate 10 side facilitates migration of metal atoms and facilitates increasing the crystal grain size.

Furthermore, the DC power applied to the target (cathode) is decreased to e.g. 0.5 W/cm² or less. This decreases the deposition rate of the film. Thus, film formation can be performed in a state closer to the thermal equilibrium state. This also facilitates increasing the crystal grain size.

Preferably, the underlying metal film 71 and the metal film 70 are formed continuously in a vacuum atmosphere (reduced-pressure atmosphere) without exposure to the ambient air. The continuous film formation of the underlying metal film 71 and the metal film 70 in a vacuum atmosphere suppresses the decrease of surface energy due to oxidation

of the underlying metal film 71. According to the aforementioned relation of $\gamma_f \leq \gamma_s - \gamma_i$, the metal film (Mo film or W film) is more likely to assume a main orientation of (111), (100) having high surface energy when the surface energy γ_s of the underlying metal film 71 is high.

The underlying metal film 71 may contain W, and the metal film 70 may be a W film. In this case, the underlying metal film 71 and the metal film 70 can be formed continuously without opening to the ambient air by using the same W target in the same sputtering chamber. Alternatively, the underlying metal film 71 may be a WZr film or WTi film. In this case, at the time of sputtering film formation of the metal film (W film) 70, no power is applied to the target of the compositional element (Zr or Ti) other than W in the underlying metal film 71.

Alternatively, sputtering film formation of the underlying metal film 71 may be performed in a first chamber. Then, the wafer may be transported to a second chamber through a space of reduced-pressure atmosphere not opened to the ambient air. Thus, sputtering film formation of the metal film 70 may be performed in the second chamber.

In the example described in the above embodiment, the interface of the underlying metal film 71 and the metal film 70 is generally parallel to the major surface of the substrate 10, or lies along the major surface of the substrate 10. However, the embodiment is not limited thereto. The interface of the underlying metal film 71 and the metal film 70 may be perpendicular or oblique to the major surface of the substrate 10. Also in this case, the metal film 70 can be formed on the aforementioned underlying metal film 71. Thus, the main orientation of the plane of the metal film 70 along the interface with the underlying metal film 71 can be set to (100) or (111). Accordingly, the specific resistance of the metal film 70 can be reduced.

The underlying metal film 71 and the metal film 70 are not limited to the shape spread like a layer or plane, but may be shaped in a line pattern.

While certain embodiments have been described, these embodiments have been presented by way of example only, and are not intended to limit the scope of the inventions. Indeed, the novel embodiments described herein may be embodied in a variety of other forms; furthermore, various omissions, substitutions and changes in the form of the embodiments described herein may be made without departing from the spirit of the inventions. The accompanying claims and their equivalents are intended to cover such forms or modification as would fall within the scope and spirit of the inventions.

What is claimed is:

1. A stacked semiconductor memory device comprising:
 - a stacked body comprising:
 - a plurality of underlying metal films comprising:
 - a tantalum-aluminum film having an aluminum content of more than 50 atomic % and less than 85 atomic %,
 - a tungsten-zirconium film having a zirconium content of less than 40 atomic %, a tungsten-titanium film having a titanium content of less than 80 atomic %, or
 - a tungsten film;
 - a plurality of metal films provided on the underlying metal films and in contact with the underlying metal films, the metal films containing at least one of tungsten and molybdenum, and having a main orientation of (100) or (111); and
 - a plurality of insulator films,
- wherein

13

the underlying metal films are provided between a lower surface of the metal films and the insulator films, and the underlying metal films are not provided on an upper surface of the metal-films, and

at least one of the plurality of insulator films contacts at least one of the plurality of underlying metal films and at least one the plurality of metal films.

2. The device according to claim 1, wherein the plurality of underlying metal films are amorphous.

3. The device according to claim 1, wherein an average grain size of the plurality of underlying metal films is smaller than an average grain size of the plurality of metal films.

4. The device according to claim 1, wherein the plurality of underlying metal films are thinner than the plurality of metal films.

5. The device according to claim 1, further comprising: a semiconductor film extending in the stacked body in a stacking direction of the stacked body; and a charge storage film provided between the semiconductor film and at least one of the plurality of metal films.

6. The device according to claim 1, wherein the plurality of underlying metal films are not connected in a stacking direction of the stacked body, and the plurality of underlying metal films are separated from each other in the stacking direction.

7. The device according to claim 1, wherein the plurality of underlying metal films, the plurality of metal films, and the plurality of insulator films are stacked above a major surface of a substrate in a direction perpendicular to the major surface.

8. A method for manufacturing a stacked semiconductor memory device, comprising:

forming a stacked body comprising a plurality of insulator films, a plurality of amorphous or microcrystalline metal films, and plurality metal films by:

forming an amorphous or microcrystalline metal film on an insulator film, the amorphous or microcrystalline metal film contacting the insulator film, the amorphous or microcrystalline metal film being a tantalum-aluminum film having an aluminum content of more than 50 atomic % and less than 85 atomic %, a tungsten-zirconium film having a zirconium content of less than 40 atomic %, a tungsten-titanium film having a titanium content of less than 80 atomic %, or a tungsten film;

performing crystal growth of a metal film on the amorphous or microcrystalline metal film, the metal film containing at least one of tungsten and molybdenum and having a main orientation of (100) or (111); and

repeating the forming of the amorphous or microcrystalline metal film on the insulator film and the performing of crystal growth of the metal film on the amorphous or microcrystalline metal film a plurality of times,

wherein the plurality of amorphous or microcrystalline metal films are formed between a lower surface of at

14

least one of the plurality of metal films and at least one of the plurality of insulator films, and the plurality of amorphous or microcrystalline metal films are not provided on an upper surface of the plurality of metal films.

9. The method according to claim 8, wherein the tantalum-aluminum film is formed as the amorphous or microcrystalline metal film by sputtering technique using a tantalum target and an aluminum target.

10. The method according to claim 8, wherein the tungsten-zirconium film is formed as the amorphous or microcrystalline metal film by sputtering technique using a tungsten target and a zirconium target.

11. The method according to claim 8, wherein the tungsten-titanium film is formed as the amorphous or microcrystalline metal film by sputtering technique using a tungsten target and a titanium target.

12. The method according to claim 8, wherein the metal film is formed on the amorphous or microcrystalline metal film by sputtering technique.

13. The method according to claim 12, wherein DC power applied to a target is set to 0.5 W/cm² or less when the metal film is formed by sputtering technique.

14. The method according to claim 12, wherein the metal film is formed by sputtering technique on the amorphous or microcrystalline metal film above a heated substrate.

15. The method according to claim 8, wherein the amorphous or microcrystalline metal film and the metal film are formed continuously in a vacuum atmosphere.

16. The method according to claim 12, further comprising:

forming a hole in the stacked body, the hole extending in a stacking direction of the stacked body;

forming a film including a charge storage film on a side surface of the hole; and

forming a semiconductor film on a side surface of the film including the charge storage film.

17. A stacked semiconductor memory device comprising: a stacked body comprising:

a plurality of underlying metal films comprising:

a tantalum-aluminum film having an aluminum content of more than 50 atomic % and less than 85 atomic %, a tungsten-zirconium film having a zirconium content of less than 40 atomic %, a tungsten-titanium film having a titanium content of less than 80 atomic %, or

a tungsten film; and

a plurality of metal films provided on the underlying metal films and in contact with the underlying metal films, the metal films containing at least one of tungsten and molybdenum, and having a main orientation of (100); and

a plurality of insulator films,

wherein the underlying metal films are provided between a lower surface of the metal films and the insulator films, and the underlying metal films are not provided on an upper surface of the metal films.