

(12) STANDARD PATENT
(19) AUSTRALIAN PATENT OFFICE

(11) Application No. **AU 2007200601 B2**

(54) Title
Method for generation of hydrogen gas from borohydride

(51) International Patent Classification(s)
C01B 3/04 (2006.01) **C01B 3/06** (2006.01)

(21) Application No: **2007200601** (22) Date of Filing: **2007.02.12**

(30) Priority Data

(31) Number **60774258** (32) Date **2006.02.16** (33) Country **US**

(43) Publication Date: **2007.08.30**
(43) Publication Journal Date: **2007.08.30**
(44) Accepted Journal Date: **2012.02.23**

(71) Applicant(s)
Rohm and Haas Company

(72) Inventor(s)
Yamamoto, John Hiroshi

(74) Agent / Attorney
Phillips Ormonde Fitzpatrick, 367 Collins Street, Melbourne, VIC, 3000

(56) Related Art
US 2005/0238573

2007200601 12 Feb 2007

ABSTRACT OF THE DISCLOSURE

A method for generation of hydrogen by combining a solid composition containing a borohydride compound and a base with an aqueous solution of an acid.

AUSTRALIA
PATENTS ACT 1990
COMPLETE SPECIFICATION

NAME OF APPLICANT(S)::

Rohm and Haas Company

ADDRESS FOR SERVICE:

DAVIES COLLISON CAVE
Patent Attorneys
1 Nicholson Street, Melbourne, 3000, Australia

INVENTION TITLE:

Method for generation of hydrogen gas from borohydride

The following statement is a full description of this invention, including the best method of performing it known to me/us:-

This invention relates to a method for generation of hydrogen gas from a borohydride-containing formulation. This method is useful for hydrogen generation in fuel cells.

Borohydride-containing compositions are known as hydrogen sources for hydrogen fuel cells, usually in the form of aqueous solutions. Solid borohydride-containing compositions also have been used. For example, U.S. Pub. No. 2005/0238573 discloses the use of solid sodium borohydride, which is combined with aqueous acid to produce hydrogen. However, the problem of quickly stopping the generation of hydrogen is not adequately addressed by this reference.

The problem addressed by this invention is to find a method for generation of hydrogen gas from a borohydride-containing formulation that allows hydrogen generation to be stopped relatively rapidly.

STATEMENT OF INVENTION

The present invention provides a method for generation of hydrogen comprising: (a) providing a solid composition comprising from 3% to 50% of at least one base; and 50% to 97% of at least one borohydride compound; and (b) adding to the solid composition an aqueous solution of at least one acid; said aqueous solution comprising from 0.01 to 2 equivalents of acid; wherein the solid composition and the aqueous solution are substantially free of transition metals from groups 8, 9 and 10, and wherein the acid is malic acid.

DETAILED DESCRIPTION

Percentages are weight percentages and temperatures are in °C, unless specified otherwise. An "organic acid" is an acidic compound, i.e., one with a $pK_a < 6$, which contains carbon and hydrogen. An "inorganic acid" is an acid which does not contain carbon. A "base" is a compound with a $pK_a > 8$ which is solid at 40°C.

In one embodiment, the amount of borohydride compound(s) in the solid composition is at least 75%, alternatively at least 85%, alternatively at least 86%, alternatively at least 87%; the amount of base(s) is no more than 25%, alternatively no more than 15%, alternatively no more than 14%, alternatively no more than 13%. In one embodiment of the invention, the amount of base in the solid composition is at least 5%; the amount of borohydride compound is no more than 95%. Preferably, the borohydride compound is a metal salt which has a metal cation from groups 1, 2, 4, 5, 7, 11, 12 or 13 of the periodic table, or a mixture thereof. In one embodiment, the borohydride compound is an alkali metal borohydride or mixture thereof; alternatively it comprises sodium borohydride (SBH) or potassium borohydride or a mixture thereof, alternatively sodium borohydride. Preferably, the base is an alkali metal hydroxide or mixture thereof, alkali metal alkoxide or alkaline earth alkoxide or combination thereof; alternatively it is an alkali metal hydroxide or sodium or potassium methoxide, or mixture thereof; alternatively sodium, lithium or potassium hydroxide or sodium or potassium methoxide, or a mixture thereof; alternatively sodium hydroxide or potassium hydroxide; alternatively sodium hydroxide. More than one alkali metal borohydride and more than one base may be present.

Preferably, the acid is an organic acid and/or an inorganic acid. In one embodiment of the invention, the acid is an organic acid. Preferably, the organic acid is a carboxylic acid. In one embodiment of the invention, the organic acid is a C₂-C₅ dicarboxylic acid, a C₂-C₅ hydroxy carboxylic acid, a C₂-C₅ hydroxy dicarboxylic acid or a combination thereof. More than one organic acid may be present in the aqueous solution. Especially preferred organic acids include malic acid, citric acid, tartaric acid, malonic acid and oxalic acid. In another embodiment of the invention, the acid is an inorganic acid. Preferably, the inorganic acid is a concentrated mineral acid, e.g., hydrochloric acid, sulfuric acid and/or phosphoric acid. Preferably the inorganic acid is not nitric acid or another strongly oxidizing acid. More than one inorganic acid may be present in the aqueous solution. Both organic and inorganic acids may be present in the aqueous solution.

In one embodiment of the invention, the aqueous solution contains from 0.1 to 1 equivalents of acid. For this purpose, equivalents are measured as equivalents of hydrogen ion for reaction with borohydride. The aqueous solution also may contain small amounts of additives, e.g., anti-foaming agents, surfactants, etc. Preferably, the aqueous solution contains no more than 10% of anything other than water and acid, alternatively no more than 5%, alternatively no more than 1%.

The solid composition of this invention may be in any convenient form. Examples of suitable solid forms include powder, granules, and compressed solid material. Preferably, powders have an average particle size less than 80 mesh (177 μm). Preferably, granules have an average particle size from 10 mesh (2000 μm) to 40 mesh (425 μm). Compressed solid material may have a size and shape determined by the equipment comprising the hydrogen generation system. In one embodiment of the invention, compressed solid material is in the form of a typical caplet used in other fields. The compaction pressure used to form compressed solid material is not critical.

The solid composition is substantially free of substances that catalyze hydrolysis of borohydride, e.g., salts of transition metals in groups 8, 9 and 10; such as Co, Ru, Ni, Fe, Rh, Pd, Os, Ir, Pt, or mixtures thereof; and borides of Co and/or Ni.

Preferably, the water content of the solid composition is no more than 0.5%, alternatively no more than 0.2%, alternatively no more than 0.1%. Preferably, the solid composition contains less than 20% of anything other than the borohydride compound and the base, alternatively less than 15%, alternatively less than 10%, alternatively less than 5%. Other possible constituents of the solid composition include, e.g., catalysts, acids, anti-foam agents and surfactants.

Preferably, the temperature of the solid composition and the aqueous solution are in the range from -60°C to 100°C , alternatively from -40°C to 50°C .

The rate of addition may vary depending on the desired rate of hydrogen generation. Preferably, the mixture formed when the solid composition contacts the aqueous solution is not agitated.

The method of this invention allows generation of hydrogen with the capability of stopping said generation relatively quickly after stopping the addition of the aqueous solution. This capability is important in hydrogen fuel cells, where power generation on demand is a key concern. Inability to stop the
5 flow of hydrogen is detrimental to rapid on/off operation of the fuel cell. Linearity of hydrogen generation over time and/or the amount of aqueous solution added is also an important capability in a hydrogen fuel cell.

EXAMPLES

Example 1: Generation of Hydrogen Gas from SBH and Aqueous Malic Acid or CoCl_2

Mixtures of SBH and NaOH were prepared, as listed in Table 1 below. Approximately 0.5-0.7 grams of each mixture was compacted at 10,000 psi (68.9 kPa) and placed in a reactor that was connected to a reservoir of water. The water in the reservoir was displaced when hydrogen gas was evolved. A solution of 25 wt % malic acid was syringe pumped to the solid at a rate of 100 microliters per minute for ten minutes at which time the pumps were turned off and the amount of water that continued to be displaced was monitored and recorded as a measure of the amount of time (in seconds unless otherwise indicated) elapsed until the hydrogen flow stopped. For times less than 30 minutes, times for two runs are listed.

Table 1

SBH Additive	Aqueous Solution	Time to Stop Flow
none	25% malic acid	> 30 min.
2% NaOH	25% malic acid	> 30 min.
5% NaOH	25% malic acid	627, 613
10% NaOH	25% malic acid	390, 399
13% NaOH	25% malic acid	108, 80
15% NaOH	25% malic acid	62, 65
20% NaOH	25% malic acid	40, 37
25% NaOH	25% malic acid	30, 25
50% NaOH	25% malic acid	5, 10
none	4.6% CoCl_2	> 30 min.
13% NaOH	4.6% CoCl_2	> 30 min.
20% polyacrylic acid	25% malic acid	> 30 min.
20% polyacrylic acid	4.6% CoCl_2	> 30 min.
20% IRP-64*	25% malic acid	> 30 min.
20% IRP-64*	4.6% CoCl_2	> 30 min.
20% Angelic acid	25% malic acid	> 30 min.
20% Angelic acid	4.6% CoCl_2	> 30 min.

* IRP-64 is a copolymer of methacrylic acid and divinylbenzene.

Example 2: Generation of H₂ vs. Time from SBH and Aqueous Malic Acid

Mixtures of SBH and NaOH were prepared, as listed in Table 2 below.

Generation of hydrogen was performed as described in Example 1. Volume of hydrogen gas evolved was noted at regular time intervals (in minutes) and correlated with time to determine linearity. The correlation coefficients, R², obtained from data from 1 minute to 20 minutes, also are listed for each material.

2007200601 12 Feb 2007

Table 2

	5% NaOH	15% NaOH	10% NaOH	2% NaOH	13% NaOH	100% SBH
1 min.	0	40	39	56	57	0.4
2 min.	0	78	88	110	120	0
3 min.	0	132	144	184	181	0
4 min.	47	188	196	246	239	0
5 min.	112	243	246	310	298	136
6 min.	167	297	292	370	338	102
7 min.	217	353	340	435	386	164
8 min.	271	398	391	501	440	227
9 min.	335	446	458	581	521	282
10 min.	371	485	520	649	596	327
11 min.	409	527	582	716	671	368
12 min.	454	574	636	769	746	422
13 min.	508	641	691	802	817	466
14 min.	569	710	741	853	875	519
15 min.	602	754	780	915	939	579
16 min.	638	770	805	970	983	630
17 min.	666	796	822	1031	1012	673
18 min.	700	809	835	1108	1051	711
19 min.	726	823	845	1152	1101	754
20 min.	732	834	849	1182	1121	807
21 min.	736	843	851	1214	1137	864
22 min.	736	848	853	1230	1150	923
23 min.	736	853	853	1239	1155	979
24 min.	736	855	853	1247	1157	1026
25 min.	736	856	853	1254	1159	1067
26 min.	736	856	853	1259	1161	1095
27 min.	736	856	853	1263	1161	1095
R ²	0.99	0.98	0.98	0.99	0.99	0.99

Example 3: Generation of H₂ vs. Time from SBH and 4.6% CoCl₂

Mixtures of SBH and NaOH were prepared, as listed in Table 3 below. Generation of hydrogen was performed as described in Example 1, except that 4.6 wt % CoCl₂ in water was added in place of aqueous malic acid. Volume of hydrogen gas evolved was noted at regular time intervals (in minutes) and correlated with time to determine linearity. The correlation coefficients, R², obtained from data from 1 minute to 20 minutes, also are listed for each material.

The results demonstrate that the method of this invention generates hydrogen with a good linear relationship between volume of aqueous solution added and the volume of hydrogen generated, as shown by the higher correlation coefficients in Table 2, relative to those in Table 3. The method also provides better capability for stopping hydrogen generation when flow of aqueous phase is stopped, as shown in Table 1.

Table 3

	5% NaOH	15% NaOH	25% NaOH	100% SBH
1 min.	0	0	9	3
2 min.	0	0	78	37
3 min.	10	30	182	71
4 min.	42	121	228	115
5 min.	167	207	292	174
6 min.	387	261	352	250
7 min.	487	331	387	430
8 min.	583	398	439	611
9 min.	664	472	438	695
10 min.	730	556	438	733
11 min.	800	649	605	799
12 min.	865	729	665	885
13 min.	895	832	710	950
14 min.	918	899	714	974
15 min.	952	924	729	989
16 min.	984	942	745	996
17 min.	992	954	766	999
18 min.	999	970	791	1003
19 min.	1006	985	825	1006
20 min.	1012	992	855	1008
21 min.	1016	1001	875	
22 min.	1018	1014	886	
23 min.	1019	1030	894	
24 min.	1022	1051	901	
25 min.	1023	1085	906	
26 min.	1023	1111	909	
27 min.	1023	1132	911	
28 min.	1023	1150	913	
R ²	0.90	0.96	0.95	0.9

The reference in this specification to any prior publication (or information derived from it), or to any matter which is known, is not, and should not be taken as an acknowledgment or admission or any form of suggestion that that prior publication (or information derived from it) or known matter forms part of the common general knowledge in the field of endeavour to which this specification relates.

Throughout this specification and the claims which follow, unless the context requires otherwise, the word "comprise", and variations such as "comprises" and "comprising", will be understood to imply the inclusion of a stated integer or step or group of integers or steps but not the exclusion of any other integer or step or group of integers or steps.

THE CLAIMS DEFINING THE INVENTION ARE AS FOLLOWS:

1. A method for generation of hydrogen comprising:
 - (a) providing a solid composition comprising from 3% to 50% of at least one
5 base; and 50% to 97% of at least one borohydride compound; and
 - (b) adding to the solid composition an aqueous solution of at least one acid;
said aqueous solution comprising from 0.01 to 2 equivalents of acid;
wherein the solid composition and the aqueous solution are substantially free of
transition metals from groups 8, 9 and 10, and wherein the acid is malic acid.
- 10 2. The method of claim 1 in which said at least one borohydride compound is at least one alkali metal borohydride, and said at least one base is sodium, lithium or potassium hydroxide, sodium or potassium methoxide, or a combination thereof.
- 15 3. The method of claim 2 in which the solid composition comprises at least 5% of said at least one base and no more than 95% alkali metal borohydride.
- 20 4. The method of claim 3 in which said at least one alkali metal borohydride is sodium borohydride, potassium borohydride or a combination thereof.
- 25 5. The method of claim 4 in which the alkali metal borohydride is sodium borohydride and the base is sodium hydroxide.
6. The method of claim 1 in which the aqueous solution comprises from 0.1 to 1
molar equivalents of acid hydrogen ion for reaction with borohydride.
7. The method of claim 6 in which the solid composition comprises from 5% to 15% of sodium hydroxide and from 85% to 95% sodium borohydride.
- 30 8. The method of claim 1, substantially as hereinbefore described with reference to any one of the Examples.