

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau




(43) International Publication Date
19 April 2001 (19.04.2001)

PCT

(10) International Publication Number
WO 01/27372 A1

- (51) International Patent Classification⁷: **D04H 1/42**, A61F 13/15
- (21) International Application Number: PCT/US00/27134
- (22) International Filing Date: 2 October 2000 (02.10.2000)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
99120174.0 8 October 1999 (08.10.1999) EP
- (71) Applicant (for all designated States except US): **THE PROCTER & GAMBLE COMPANY** [US/US]; One Procter & Gamble Plaza, Cincinnati, OH 45202 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **RIEGER, Bernhard** [DE/DE]; Johann-Stockar-Weg 8, 89075 Ulm (DE). **ORROTH, Mike** [US/GB]; Flat 3, 122 Richmond Hill, Richmond, Surrey TW10 6RJ (GB). **DE BELDER, Gian** [BE/BE]; Oever 33 bus 2, B-2500 Lier (BE).
- (74) Agents: **REED, T., David** et al.; The Procter & Gamble Company, 5299 Spring Grove Avenue, Cincinnati, OH 45217-1087 (US).
- (81) Designated States (national): AE, AG, AL, AM, AT, AT (utility model), AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, CZ (utility model), DE, DE (utility model), DK, DK (utility model), DM, DZ, EE, EE (utility model), ES, FI, FI (utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KR (utility model), KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (utility model), SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- Published:**
- With international search report.
 - Before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments.
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 01/27372 A1

(54) Title: FIBROUS MATERIAL COMPRISING FIBERS MADE FROM LINEAR, ISOTACTIC POLYMERS

(57) Abstract: The present invention relates to fibrous web materials comprising polymeric material wherein the structure of the polymeric material contains elastic amorphous areas of nano-scale-size reinforced with self arranged crystalline domains of nano-crystals.

FIBROUS MATERIAL COMPRISING FIBERS MADE FROM LINEAR, ISOTACTIC POLYMERS

FIELD OF THE INVENTION

The present invention relates to fibrous web materials such as nonwoven materials used for example in hygienic articles. Specifically, the present invention relates to elastic fibrous web materials.

BACKGROUND

Fibrous materials and in particular nonwoven web materials comprising olefinic polymers are well known in the art and enjoy widespread usage throughout the industry. Typical areas of application of such fibrous web material include for example hygienic articles and in particular disposable absorbent articles.

Fibrous web materials made from commonly used polyolefins such as PP, PE, PS, PIB have a number of useful properties. They are bio-compatible and food compatible, chemically stable, inert, non toxic materials. However, most of them have poor mechanical properties including insufficient strength/tear resistance, insufficient stretchability/elasticity and the like.

Several approaches have been proposed in the prior art to provide elastic properties to such fibrous web materials. The most commonly used approach - besides providing laminates of fibrous web material with for example elastic films - is based on changing the chemical structure of the polymer by introducing hinged joints/moieties into the main chain of the polymer. These hinges provide more flexibility to the polymeric backbone preventing crystallization of polymer, lowering the glass transition temperature (T_g) and improving the elasticity of the resulting material. Usually, the hinge groups contain heteroatoms providing

flexibility such as oxygen, nitrogen or chlorine placed into the main chain or into bulky side groups. Another approach is mastication of the polymer by blending with special plasticizing agents. Both approaches, however, require heteroatoms to be introduced into the molecule or into the bulk of the coating material.

The third approach proposed in the prior art to provide elastic properties to such fibrous web materials, which is more close to the present invention, is to exploit the formation of hetero-phases which reinforce the bulk material by forming a physical net. To do this the block-co-polymerization of two or more different monomers has been used leading to polymeric backbones comprising blocks with different Tg. This results in micro-phase separation in the bulk with formation of reinforcing crystalline domains of one co-polymer linked with each other by flexible chains of the second co-polymer.

In essence, conventional polymeric web materials carry a wide variety of inherent disadvantages including but not being limited to insufficient strength/tear resistance, insufficient stretchability/elasticity, not being bio-compatible, not being food compatible, comprising heteroatoms such as chlorine and hence leading to toxic residues when burnt, and the like.

It is an object of the present invention to provide fibrous web materials which overcome the disadvantages of the prior art fibrous web materials.

It is a further object of the present invention to provide articles which comprise fibrous web materials.

It is a further object of the present invention to provide a method for manufacturing fibrous web material of the present invention.

It is a further object of the present invention to provide a method for processing a fibrous web material of the present invention.

SUMMARY OF THE INVENTION

The present invention provides a fibrous web material comprising a plurality of fibers. The fibrous web material is characterized in that the fibers comprise a

polyolefinic homopolymer having an isotacticity of less than 60% of [mmmm] pentad concentration.

The present invention further provides a method for manufacturing fibers from the aforementioned polymeric material comprising a step of processing the polymeric material selected from the group of wet spinning, dry spinning, melt spinning, semi dry spinning (solvent evaporation or sedimentation), and combinations thereof.

The present invention further provides a method for manufacturing a fibrous web material comprising the steps of providing fibers of the aforementioned polymeric material and of combining the fibers into a web material.

The present invention further provides a method for stabilizing a fibrous web material according to the present invention comprising the steps of providing a fibrous web material and of stabilizing step the fibrous web material.

DETAILED DESCRIPTION OF THE INVENTION

The present invention provides fibrous web materials comprising polyolefinic homopolymers.

The term "polyolefinic homopolymer" as used herein refers to those polyolefins which comprise only one phase of molecules all of which exhibiting a similar stereochemical configuration. For example, blends of atactic and isotactic polymers where the two phases have polymerized simultaneously are excluded when this term is used. The term homopolymer includes copolymers where all molecules exhibit a similar stereochemical configuration.

The polyolefinic homopolymer of the present invention may comprise linear isotactic polymers having a structure of one or several C₃ to C₂₀ olefinic monomers, having an isotacticity of less than 60%, preferably less than 55%, more preferably less than 50%, and most preferably less than 45% of [mmmm]

pentad concentration, and having an isotacticity of more 15%, preferably more than 20%, more preferably more than 25%, and most preferably more than of [mrrm] pentad concentration. Preferably, the polyolefinic homopolymer is polypropylene.

The isotacticity of the homopolymers may be reduced compared to the isotactic polypropylenes of the prior art due to a statistic distribution of stereoscopic errors in the polymer chain. The term "stereoscopic error" refers to a stereoscopic sequence characterized by a [mrrm] pentad. In this case, the central monomer has a stereo configuration opposed to the other four monomers in this pentad. The [mrrm] pentad concentration of this polymer therefore is above the statistical probability of $p^2 (1-p)^2$ where $p=[m]$ and hence $1-p=[r]$ and $p^4=[mrrm]$. Preferably, the pentad concentration is at least $[p (1-p)]^q p (1-p)$ with q being 0.8, more preferably q being 0.6, yet more preferably q being 0.4, yet more preferably q being 0.2, most preferably q being 0.1.

In some embodiments of the homopolymer and in particular in those embodiments where the crystallinity is reduced by means of single stereo errors, a low content of atactic sequences has proven beneficial to the properties of the fiber of the present invention. Preferably, the [rmrm] pentad concentration is below 6%, more preferably below 5%, yet more preferably below 4%, yet more preferably below 3%, most preferably below 2.5%.

In some embodiments of the homopolymer and in particular in those embodiments where the crystallinity is reduced by means of single stereo errors, a low content of syndiotactic sequences has proven beneficial to the properties of the fiber of the present invention. Preferably, the [rrrr] pentad concentration is below 6%, more preferably below 5%, yet more preferably below 4%, yet more preferably below 3%, most preferably below 2.5%.

Alternatively, the homopolymer of the present invention may include sequences of atactic and isotactic blocks of polymer.

Preferably, the mean molecular weight M_w of the polymer is above 100000 g/mol, more preferably above 200000 g/mol, yet more preferably above 250000 g/mol, yet more preferably more than 300000 g/mol, most preferably more than 350000 g/mol.

The glass temperature T_g is between -50 and +30 °C. Preferably the glass temperature is below 10°C, more preferably below 5°C, yet more preferably below 0°C, most preferably below -6°C. The melt temperature of the polymer is obtained after heating the sample 150°C and subsequently cooling the polymer to -50°C.

Without wishing to be bound by this theory, the polyolefinic polymers exhibit a semi-crystalline structure. The structure contains elastic amorphous areas of nano-scale-size reinforced with self arranged crystalline domains of nano-crystals. The formation of brittle macro-crystalline material from the polymer is achieved by introducing the defects into the polymeric backbone. Isolated monomer units with opposite stereo configuration have been used as the defects, i.e. single stereo errors.

Suitable polymers and a process for manufacturing such polymers are described in PCT patent application EP99/02379 incorporated herein by reference. A catalyst combination suitable for the preparation of such polymers is described in PCT patent application EP99/02378 incorporated herein by reference. Preferably, the process of PCT patent application EP99/02378 is carried out by temperatures of less than 30°C, more preferably less than 25°C, yet more preferably less than 20°C, most preferably less than 15°C to increase the molecular weight of the resulting polymer. In order to increase the molecular weight, the polymerization

is preferably carried out in liquid monomer such as in liquid propene. In order to increase the molecular weight, the catalyst is preferably used in combination with the boron activators mentioned in PCT patent application EP99/02378.

Other suitable polymers and a process for manufacturing such polymers is described in WO99/20664 incorporated herein by reference.

It is preferred to use homopolymers for the fibers of the present invention since during manufacture of homopolymers the batch to batch variability is greatly reduced in comparison to multi phase polymers where the phases are polymerized in a single reaction.

Preferably, the polymers used in manufacturing the fiber materials of the present invention have a distinctive rubber-elastic plateau in their stress strain curves.

The polymers used for the fiber of the present invention are bio-compatible may be burnt without toxic residues since they contain no heteroatoms such as chlorine. The further do not contain toxic monomer residues.

The fiber materials of the present invention have been found to be able exhibit superior softness. Preferably, the fiber material has a Shore hardness on the A scale of less than 30, more preferably, of less than 25, yet more preferably of less than 20, yet more preferably of less than 15, most preferably of less than 10. The softness of the fiber material of the present invention can be increased by manufacturing the fiber by reducing the isotacticity ([mmmm] pentad concentration).

The fiber material has been found to exhibit increased temperature stability compared to prior art fiber materials. This is partly due to the fact that for the fibers of the present invention a homopolymer is used and is partly due to the high molecular weight of the homopolymer. Preferably, the fiber material of the

present invention has a melting point of at least 100°C, more preferably of at least 110°C, more preferably of at least 120°C, most preferably of at least 130°C. The melt temperature of the polymer is obtained after heating the sample 150°C and subsequently cooling the polymer to -50°C. Higher melting point may be achieved by blending the homopolymer for example with conventional isotactic polymer such as polypropylene.

The fiber of the present invention have been found to be stretchable as well as elastic. The stretchability of the fiber versus its elastic behavior can be adjusted by means of the tacticity of the homopolymer of the present invention. The fiber material of the present invention has been found to be stretchable without tearing to at least 500% of its original length, more preferably 1000% of its original length, yet more preferably to at least 1500% of its original length, most preferably to at least 2000% of its original length. In addition, the fiber material of the present invention preferably recovers within 10 minutes after being stretched and held for 1 minute to 500% of its original length back to less than 300% its original length, preferably less than 200% its original length, most preferably less than 150% of its original length. In addition, the fiber of the present invention has been found to exhibit a low compressive set. The fiber of the present invention recovers within 10 minutes after a compression to 50% of its original thickness for 1 minute to at least 60% of its original thickness, more preferably at least 70% of its original thickness, yet more preferably to at least 80% of its original thickness, yet more preferably to at least 90% of its original thickness, most preferably to at least 95% of its original thickness. The compressibility of the fiber of the present invention can be adjusted by increasing the tacticity of the homopolymer or by blending the low tacticity homopolymer with conventional isotactic polymer such as polypropylene.

The fiber of the present invention has been found to exhibit a relative low tackiness at room temperature due to the high molecular weight of the polymer.

Various additives may be added to the homopolymer of the present invention to change the properties of the polymer such as is well known in the art.

There are known in the art a wide variety of suitable methods to manufacture and /or processing fibers from the polymer of the present invention including but not being limited to wet spinning, dry spinning, melt spinning, semi dry spinning (solvent evaporation or sedimentation), crazing, and combinations thereof. Fibers suitable for the web materials of the present invention may be mono fibers or the may comprise filaments.

For at least some of the spinning processes, it has been found that the amount of the low isotacticity homopolymer of the present invention present in the fiber of the present invention needs to be reduced in order to accelerate crystallization of the fibers after spinning. Preferably, the fiber of the present invention comprises less than 80% of the low isotacticity homopolymer, more preferably less than 60%, yet more preferably less than 40%, most preferably less than 30%. Alternatively, a high isotacticity polymer having a broader molecular weight distribution may be used in order to accelerate crystallization times.

Compared to spinning of conventional, isotactic polypropylene, the addition of the low isotacticity homopolymer of the present invention reduces the requires forces, pressures, or torques respectively to process the polymer.

There are known in the art a wide variety of suitable methods to manufacture fibrous web material according to the present invention from fibers including but not being limited to meltblowing, spunbonding, carding, air laying, wet laying, weaving, knitting, bailing, and the like. There are further known in the prior art a wide variety of suitable methods for optional stabilization of the fibrous web material of the present invention including but not being limited to

hydroentangling, thermo bonding, pressure bonding, air through bonding, needling, resin bonding, combinations thereof, and the like.

It is a further aspect of the present invention to provide an article comprising a fibrous web material according to the present invention.

The article according to the present invention may be a hygienic article. The term "hygienic article" as used herein refers to articles which are intended to be used in contact with or in proximity to the body of a living being. Such hygienic articles may absorbent or non-absorbent. Such hygienic articles may be disposable or intended for multiple or prolonged use. Such hygienic articles include but are not limited to disposable absorbent article (diapers, sanitary napkins, adult incontinence devices such as briefs, bed mats, wound plasters, underarm sweat pads, and the like), medical supply items (coverings, gowns, drapes, face masks, bandages, body implants, and the like), and other hygienic articles such as toys, bed covers, and the like. Having regard to the specific advantages of the polymers used for the articles of the present invention, it will be readily apparent to the skilled practitioner to apply the fibrous web materials according to the present invention in the above and similar hygienic articles.

The article of the present invention may also be a clothing article or a household article including but not being limited to bed covers, underwear, tights, socks, gloves, sport clothing, outdoor clothing, low temperature clothing, shoes and shoe covers, protective clothing such as for motor biking, blankets, covers, bags, items of furniture, and the like. Having regard to the specific advantages of the polymers used for the articles of the present invention, it will be readily apparent to the skilled practitioner to apply and to optionally modify the fibrous web materials according to the present invention in the above and similar articles.

The fibrous web material according to the present invention may also be used as a construction element in an article. Thereby, the functionalities of the fibrous web material includes but is not limited to supporting, carrying, fixing, protecting other elements of the article and the like. Such articles include but are not limited to adhesive tapes, protective wraps, complex constructions such as buildings (floor coverings, house wraps, and the like), cars, household appliances, horticultural and agricultural constructions (geotextiles), and the like. Having regard to the specific advantages of the polymers used for the articles of the present invention, it will be readily apparent to the skilled practitioner to apply and to optionally modify the fibrous web materials according to the present invention as construction elements in the above and similar articles.

The article of the present invention may further a membrane such as in filters, car batteries, and the like. Having regard to the specific advantages of the polymers used for the articles of the present invention, it will be readily apparent to the skilled practitioner to apply and to optionally modify the fibrous web materials according to the present invention in the above and similar articles.

CLAIMS

1. A fibrous web material comprising a plurality of fibers characterized in that said fibers comprise a polyolefinic homopolymer having a an isotacticity of less than 60% of [mmmm] pentad concentration.
2. An article according to Claim wherein said homopolymer is polypropylene.
3. An article comprising a fibrous web material according to Claim .
4. An article according to Claim wherein said article is a hygienic article.
5. A hygienic article according to Claim wherein said article is a disposable absorbent article.
6. An article according to Claim wherein said first element is a construction element of the article.
7. A method for manufacturing fibers from polymeric material comprising a step of processing said polymeric material selected from the group of wet spinning, dry spinning, melt spinning, semi dry spinning (solvent evaporation or sedimentation), and combinations thereof characterized in that said polymeric material comprises a polyolefinic homopolymer having a an isotacticity of less than 60% of [mmmm] pentad concentration.

8. A method for manufacturing a fibrous web material comprising the steps of
 - providing fibers of polymeric material
 - combining said fibers into a web materialcharacterized in that
said fibrous web material comprises a polyolefinic homopolymer having a an isotacticity of less than 60% of [mmmm] pentad concentration.
9. A method for manufacturing a fibrous web material according to Claim wherein
said step of combining fibers is selected from the group of meltblowing, spunbonding, carding, air laying, wet laying, weaving, knitting, bailing, and combinations thereof.
10. A method for stabilizing a fibrous web material comprising the steps of
 - providing a fibrous web material
 - stabilizing step said fibrous web materialcharacterized in that
said fibrous web material comprises a polyolefinic homopolymer having a an isotacticity of less than 60% of [mmmm] pentad concentration.
11. A method for stabilizing a fibrous web material according to Claim wherein
said step of stabilizing is selected from the group of hydroentangling, thermo bonding, pressure bonding, air through bonding, needling, resin bonding, combinations thereof.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/27134

A. CLASSIFICATION OF SUBJECT MATTER IPC 7 D04H1/42 A61F13/15				
According to International Patent Classification (IPC) or to both national classification and IPC				
B. FIELDS SEARCHED				
Minimum documentation searched (classification system followed by classification symbols) IPC 7 D04H A61F C08F				
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched				
Electronic data base consulted during the international search (name of data base and, where practical, search terms used) EPO-Internal, WPI Data, PAJ				
C. DOCUMENTS CONSIDERED TO BE RELEVANT				
Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.		
P, X	DE 198 16 154 A (RIEGER BERNHARD) 21 October 1999 (1999-10-21) cited in the application claim 18 ---	1, 7, 8		
A	US 5 888 607 A (ROGERS JOHN J ET AL) 30 March 1999 (1999-03-30) the whole document column 10, line 56 - column 11, line 26; claim 1 ---	1-11		
A	US 5 594 080 A (COATES GEOFFREY W ET AL) 14 January 1997 (1997-01-14) column 9, line 56 - line 59 ---	1-11		
-/--				
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.				
° Special categories of cited documents :				
<table style="width: 100%; border: none;"> <tr> <td style="width: 50%; border: none; vertical-align: top;"> <ul style="list-style-type: none"> *A* document defining the general state of the art which is not considered to be of particular relevance *E* earlier document but published on or after the international filing date *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) *O* document referring to an oral disclosure, use, exhibition or other means *P* document published prior to the international filing date but later than the priority date claimed </td> <td style="width: 50%; border: none; vertical-align: top;"> <ul style="list-style-type: none"> *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. * & * document member of the same patent family </td> </tr> </table>			<ul style="list-style-type: none"> *A* document defining the general state of the art which is not considered to be of particular relevance *E* earlier document but published on or after the international filing date *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) *O* document referring to an oral disclosure, use, exhibition or other means *P* document published prior to the international filing date but later than the priority date claimed 	<ul style="list-style-type: none"> *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. * & * document member of the same patent family
<ul style="list-style-type: none"> *A* document defining the general state of the art which is not considered to be of particular relevance *E* earlier document but published on or after the international filing date *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) *O* document referring to an oral disclosure, use, exhibition or other means *P* document published prior to the international filing date but later than the priority date claimed 	<ul style="list-style-type: none"> *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. * & * document member of the same patent family 			
Date of the actual completion of the international search <p style="text-align: center; font-weight: bold;">24 January 2001</p>		Date of mailing of the international search report <p style="text-align: center; font-weight: bold;">08/02/2001</p>		
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer <p style="text-align: center; font-weight: bold;">Barathe, R</p>		

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 00/27134

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>WO 99 20664 A (MINNESOTA MINING & MFG) 29 April 1999 (1999-04-29) cited in the application the whole document</p> <p style="text-align: center;">---</p>	1-11
A	<p>DIETRICH ET AL: "Control of Stereoerror Formation with High-Activity Dual-Side Zirconocene Catalysts: A Novel Strategy To Design the Properties of Thermoplastic Elastic Polypropenes" 21 March 1999 (1999-03-21) , JOURNAL OF THE AMERICAN CHEMICAL SOCIETY,US,AMERICAN CHEMICAL SOCIETY, WASHINGTON, DC, VOL. 121, NR. 18, PAGE(S) 4348-4355 XP002110148 ISSN: 0002-7863 the whole document</p> <p style="text-align: center;">---</p>	1-11
A	<p>RIEGER ET AL: "Novel metallocene catalyzed polypropene homo- and brush-copolymers: control of new morphologies and beyond" 4 March 1999 (1999-03-04) , POLYMERIC MATERIALS SCIENCE AND ENGINEERING,US,WASHINGTON, DC, VOL. 80, PAGE(S) 51-52 XP002110149 ISSN: 0743-0515 the whole document</p> <p style="text-align: center;">-----</p>	1-11

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/US 00/27134

Patent document cited in search report	Publication date	Patent family member(s)	Publication date		
DE 19816154 A	21-10-1999	AU 3420999 A	01-11-1999		
		AU 3706899 A	01-11-1999		
		WO 9952950 A	21-10-1999		
		WO 9952955 A	21-10-1999		
		EP 1070087 A	24-01-2001		
		EP 1070089 A	24-01-2001		
US 5888607 A	30-03-1999	AU 5708298 A	25-01-1999		
		EP 1018905 A	19-07-2000		
		WO 9901048 A	14-01-1999		
US 5594080 A	14-01-1997	AU 697375 B	01-10-1998		
		AU 2191195 A	09-10-1995		
		BR 9507184 A	07-10-1997		
		CA 2186105 A	28-09-1995		
		CN 1172488 A	04-02-1998		
		CZ 9602773 A	12-03-1997		
		EP 0802935 A	29-10-1997		
		JP 9510745 T	28-10-1997		
		PL 316415 A	06-01-1997		
		WO 9525757 A	28-09-1995		
		US 5969070 A	19-10-1999		
		WO 9920664 A	29-04-1999	AU 9808198 A	10-05-1999
				EP 1023339 A	02-08-2000