

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
7 June 2001 (07.06.2001)

PCT

(10) International Publication Number
WO 01/39612 A1

(51) International Patent Classification⁷:
A23P 1/08, 1/10, A21D 2/36, 8/06, 13/00

A23L 1/10,

(21) International Application Number: PCT/PL00/00084

(22) International Filing Date:
23 November 2000 (23.11.2000)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
P.336969 6 December 1999 (06.12.1999) PL
P.340816 16 June 2000 (16.06.2000) PL

(71) Applicant and

(72) Inventor: WYSOCKI, Jerzy [PL/PL]; ul. Ostrowska 58,
PL-18-300 Zambrów (PL).

(74) Agent: BOCHENSKA, Joanna; ul. Noakowskiego
18/20, PL-00-668 Warszawa (PL).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

- With international search report.
- Before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments.

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: MATERIAL FOR MAKING BIODEGRADABLE MOULDINGS FROM BRAN AND METHOD THEREOF

(57) **Abstract:** Material for making biodegradable mouldings, in particular table utensils and packaging containers according to this invention consists in 95-100 % w/w of loose bran, in particular the wheat one, constituting a selected bran fraction of grain size from 0.01 to 2.80 mm containing from 7 % to 45 % of structurally bonded water in the form of moisture and possibly in up to 5 % w/w of a mixture of impregnating substances and/or fragrance and/or aroma giving additives and/or non-fibrous fillers and/or moisture retaining agents and/or colouring additives. Method of making biodegradable mouldings, in particular table utensils and packaging containers, using grain grinding products consists in that the loose bran, in particular wheat one, of grain size 0.01 to 2.80 mm in amount of 96-100 % w/w containing 7 % to 45 % structurally bound water in the form of moisture are dry-mixed with a mixture impregnating substances and/or fragrance and/or aroma giving additives and/or non-fibrous fillers and/or moisture retaining agents and/or colouring additives in amount of up to 5 % w/w; a metered quantity of the moulding material obtained is placed on part of a multipartite, preferably bipartite, mould, the mould is being closed with simultaneous exposure of moulding material placed there for several tens of seconds to temperature within a range from 20 to 450° C and pressure within a range of 1-10 MPa and/or compressive force of up to 100 MT/cm² at pressure of up to 320 MPa acting of a mould closing piston.

WO 01/39612 A1

MATERIAL FOR MAKING BIODEGRADABLE MOULDINGS FROM BRAN AND METHOD THEREOF

The invention refers to a material for making biodegradable mouldings, in particular table utensils and packaging containers and to a method of making such biodegradable mouldings, in particular vessels and packaging containers.

The packaging industry since a long time attempts to find alternative solutions enabling to eliminate the use of plastic materials. This problem becomes to be of particularly sharp nature in case of plastic packaging containers and disposable table utensils. Disposable table utensils and packaging containers, despite of unquestionable advantages resulting from simplicity and rentability of manufacturing processes, present today a very serious problem associated with their disposal as wastes. Lack of effective recycling processes in respect to waste plastic materials and large-scale character of using disposable plastic table utensils results in avalanche-like increase in globally produced quantities of non-biodegradable and environment polluting plastic wastes.

The increasingly higher interest in production of packaging containers disposable table utensils of biodegradable materials allows to hope that they will progressively eliminate the use of plastics in this field.

Paper as commonly known material used in production of packaging containers and disposable can be regarded as environment friendly to some extent. Paper wastes are not environmentally harmful ones but its use as material for packaging containers and table utensils does not solve the problem littering and the very nature of paper production process causes considerable pollution and contamination of natural environment.

Biodegradable packaging containers constitute a separate group of packages. Various method and materials enabling to obtain biodegradable packaging containers and disposable table utensils are already known. The product so obtained undergo natural

degradation under influence of various environmental factors such as oxygen, moisture, light and micro-organisms. Packaging containers of that type are used increasingly more frequently because of environmental regulations being in force in some European countries and imposing direct constraints on production of conventional packaging containers or special taxation on their manufacturers. The cost of their production, however, still remains by about 15% higher than that of conventional packaging containers.

There are known biodegradable packaging materials containing starch and cellulose as their components. Polyethylene-based packaging materials containing 6 to 11% corn starch readily undergoes biodegradation caused by bacteria and amylolytic enzymes. To speed up their biodegradation process special additives facilitating oxidation of polyethylene are being used. This solution, however, still requires to use a biodegradation assisting system and makes necessary to implement various supplementary measures such as segregation of wastes.

The starch-based thermoplastic materials are obtained by heating up under pressure water-containing starch in presence of plastifying additives also contained therein. The article made of these materials are manufactured by extrusion process employing conventional tooling similar to that used in production of plastic extrusion-moulded articles. For example two German companies „Biopack” and „Sandoz” have introduced a starch-based packaging material. This material is obtained by adding to starch powder various mouldability improving additives and cellulose. The mixture so obtained is used to mould required products under pressure at 190°C by extrusion. The extrusion process carried out under such process conditions does not allow to achieve exact repeatability of shape which results from the fact that moulded material after leaving the extrusion die, because of sudden change in pressure and surrounding temperature, tends to expand. The product obtained has a honeycomb-like structure formed by bundles of fused proteinous monofilaments. As result of processes taking place inside the extruder, because of combined effect of high temperature and pressure, important physicochemical changes are occurring in uncontrollable manner thus affecting repeatability of material properties. Furthermore the extrusion process is of continuous nature and its progress is not fully controllable.

To known prior-art materials belongs also that containing starch and a water-

soluble polymer obtained from petroleum. Amount of starch contained in that material is from 10 to 70%. One of possible application of that material is to use it for packing animal fodder. Such package after being emptied can be disintegrated and added to animal fodder as fully digestible one.

As an environment friendly material of biological origin the wafer dough is well known and commonly used. It finds application mainly to make disposable cups for serving ice-cream. Production of such cups consists in baking them in special moulds from thin slurry-like dough made of wheat flour and water. Such wafer cups, however, readily absorb water and are becoming soft and incoherent which greatly restrains potentialities of their applications.

From the Polish patent specification No. 171 872 a material containing 30-85% by weight of polysaccharide-based biodegradable synthetic material and 15-70% by weight of starch or non-modified cellulose as a biodegradable additive as well as minute amounts of ancillary ingredients. This material is obtained by fusing its polysaccharide base and adding starch or cellulose thereto. This mixture has initially the form of dispersion of starch having moisture content not more than 25% or of cellulose in its polysaccharide base. Then this mixture is pelletised and pellets are used to mould desired products. This process is relatively complex one and involves many stages.

A process is also known from the European patent application EP 0 51 589 according to which a packaging container is obtained in a single stage from a dough containing potato starch, small amount of cereal starch, vegetable oil, stabilisers, emulsifiers and water. The packaging container is obtained by press-forming in a suitable mould and maintaining the mould for 60-120 seconds at 65-105°C. Thereafter the mould is slowly cooled down and a moulding so obtained removed from the mould. Obtained packaging container is highly resistant to liquids and is suitable to store cold and hot articles of food.

From the Polish patent specification No. 167 213 a method of making thin-walled degradable mouldings is known. This method consists in that a mixture comprising 30 to 63% w/w water, 27-69% w/w starch base, anti-adhesive agent, thickening agent, up to 16% w/w cellulose-rich raw materials, up to 10% w/w non-fibrous fillers, moisture retaining agent, colorant, structure hardening agent, preservative and antioxidant is baked in a mould for 25-230 seconds at 145-230°C and subsequently conditioned so as

to achieve moisture content of 6-22% w/w in a moulding obtained. This method can be used to make disposable cups, plates fast-food serving/packaging boxes, food package inserts as well as paper- or cardboard-like sheets or webs. The products obtained by this method have a wall thickness being on one part sufficiently thick to ensure, while observing prescribed direction for use, required resistance to breaking and cracking and on the other sufficiently thin to enable efficient baking between two halves of a conventional mould used in ordinary automatic wafer-baking machines.

In the another Polish patent specification No 174 592 an environment friendly material and a process for making disposable table utensils and packaging containers are disclosed. Dry mixture of that material contains grain grinding products in amount of 50-95% w/w of dry substance, products of grinding potatoes, soybeans and other plants in amount of 0-90% w/w of dry substance and animal protein as a binder in amount of up to 30% w/w of dry substance as well as fragrance and aroma giving additives, preservatives and colorants. The ingredients as above are mixed together and with water and kneaded until a homogenous dough is obtained; then the dough is extruded and baked in conventional manner for several minutes. During baking process water contained in dough evaporates resulting in destruction of inhomogenous fibrous structure of mouldings. Thus the final products show numerous cracks and identically dimensioned which makes this material and process not suitable in making thin-walled packaging containers and disposable utensils as highly strict standardisation requirements must be satisfied by such articles.

This invention aims to avoid above mentioned disadvantages of prior art biodegradable materials described above.

This objective has been achieved by the material for making biodegradable mouldings, in particular table utensils and packaging container and method of making such biodegradable mouldings according to the present invention.

This method of making such biodegradable mouldings consists in that from dry bran the fractions sized from 0.01 to 2.80 mm are selected by a known segregation process, the selected bran fractions are mixed together and with dry additives needed as required and necessary metered quantity of that mixture is placed into a suitable preheated mould; the metered portion of mixture placed into mould is subsequently exposed for 1 to 25 seconds to temperature within a range from 20 to 450°C and

5

pressure within a range from 5 to 450 kg/m² in successive cycles of up to 5 seconds duration each alternately with pressure relieving during intervals between two cycles following each other. Preferably the dry mixture, after preparing same and before placing it into the mould, is exposed to temperature within a range from 20 to 450°C and pressure within a range from 5 to 450 kg/m² and thereafter, while maintaining it under pressure, the mixture is introduced into a preheated mould.

The material according to present invention for making biodegradable mouldings, in particular disposable table utensils and packaging containers, consists of 95-100% w/w of loose bran, in particular wheat bran and possibly of 5% w/w of a mixture of impregnating substances and/or fragrance and/or aroma giving additives and/or non-fibrous fillers and/or moisture retaining agents and/or colouring additives. The loose bran used in the material according to the invention constitute a by-product of grain grinding process. Usually in known flour-making processes in order to separate bran from grain the last one is moistened with water. As bran has fibrous structure it is able to absorb water in amount of up to 45% its weight in the form of structurally bonded moisture without losing its loose form. At the same time the material according to present invention should not contain less than 7% of structurally bonded moisture. If its moisture content is insufficient the bran should be additionally moistened so as to keep its moisture content within 7-45%. Remaining additives constitute optional ingredients which may or may not be added depending on actual needs and intended application of final product. The bran, in particular the wheat one, used as a main constituent of material according to this invention constitute a specific selected fraction of bran sized from 0.01 to 2.80 mm. The material according to this invention does not contain any additives, such as e.g. flour, which would make necessary to bake it for a long time.

In a modification of the method according to this invention the loose bran, in particular wheat one, of grain size 0.01 to 2.80 mm in amount of 96-100% w/w containing 7% to 45% structurally bound water in the form of moisture are dry-mixed with a mixture impregnating substances and/or fragrance and/or aroma giving additives and/or non-fibrous fillers and/or moisture retaining agents and/or colouring additives in amount of up to 5% w/w. A metered quantity of the moulding material obtained is placed onto part of a multipartite, preferably bipartite, mould, the mould is being closed with simultaneous exposure of moulding material placed there for up to several tens

seconds to temperature within a range from 20 to 450°C and pressure within a range of 1-10 MPa and/or compressive force of up to 100 MT/cm² at pressure of up to 320 MPa acting of a mould closing piston. If pressure of 1-10 MPa is to be used this is achieved by sealing the mould before closing it completely and thereafter the mould is closed completely to produce pressure therein. Application of compressive force is achieved preferably by use of hydraulic presses, mechanical presses, hydraulic hammer or dedicated system specifically designed for that purpose. The material mixture after preparing same but before placing it into a mould is, preferably, exposed to temperature within a range of 20-450°C and pressure of 1-10 MPa. All parts of the mould are to be preheated and preferably temperatures of upper and lower parts of the mould are different so as to enable to control direction of flow of steam generated. This also enable to chose which surface of a moulding in question (top or bottom one) is to be less porous one. The exposure material to temperature and pressure or compressive force, lasting up to several tens of seconds can be accomplished either in a single cycle or in several cycles, each being of several seconds long, with relieving pressure during intervals between any two successive cycles. The single-cycle mode of bringing the method according to the invention into effect is possible if a mould in question is provided with small slits, orifices or open pores enabling to vent off steam generated during exposure to high temperature. Preferably final products are coated with a film-forming substance in any known manner. It is also desirable to pelletise or subject to briquetting the material before placing it into a mould. In case when briquetting has been chosen it is desirable when weight of each briquette is equal to that of a portion of material required to make a given moulding or to a fraction of that portion obtained by dividing it by an integer, which greatly facilitates the production process. The actual figures of process variables such as temperature, pressure, compressive force, moisture content of bran as well as grain size of bran use are chose, within their respective ranges specified, in dependence on moulding size, wall thickness and shape of final products.

It has been found that bran, in particular that form wheat grain, containing structural water in the form of moisture, when processed by the method according to this invention enable to obtain mouldings of their material structure quite different from that obtained using a material prepared in the form of dough from bran mixed with water and then baked in conventional manner. Sudden evaporation of structural moisture results in

quite different mechanism of final product structure formation than that observed in case of similar material containing bran and not bonded water. It should be stated finally that the method of this invention enables to obtain quite new natural material of mouldings obtained thereby.

The method as per this invention enables achieve exceptionally high repeatability of final products as far as their dimensions and strength parameters are concerned. The final products obtained thereby have high and uniform mechanical strength, are free of cracks, show very little rate of production rejects, are resistant to soaking with water, give very good thermal insulation when used to serve hot dishes. At the same time when used as packaging containers for particulate matter they exhibit exceptionally good container content ventilation properties as compared with any prior art packaging materials owing to the specific structure of final products.

As compared with prior-art conventional plastic packaging containers or those made of partially biodegradable plastic the moulding according to this invention are characterised by exceptionally high biodegradation rate not longer than 30 days. On the other hand, as compared with wholly biodegradable prior-art mouldings, these made of material and using the method according to present invention have much better mechanical, utility and aesthetic properties. The method according to this invention does not give rise to generation of production wastes and allows to use a completely natural raw material. Furthermore the material and method according to this invention allow to obtain practically any disposable mouldings. The field of application for these mouldings can be expanded far beyond the typical application of end product of that type known from the prior art. The material and method according to this invention can be successfully used to make mouldings for packaging, practically irrespective of overall dimensions and purpose of packaging containers, for wide range of commodities as well as those constituting disposable utensils in broadest meaning of this word i.e. also as medical containers for example.

Example I. From loose bran of structurally bonded moisture content amounting to 17%, obtained from wheat grain grinding process the following granularity fractions in amounts as follows have been selected by sifting: 0.1/0.2 - 33% w/w, 0.2/0.4 - 25% w/w, 0.4/0.8 mm - 40%. The moulding material for making biodegradable moulding has been prepared by mixing 99% w/w of so selected bran with 0.3% w/w of sorbite, 0.4% of

roasted sugar and 0.3% w/w of certified food colour.

Example II. Similar moulding material as that of Example I has been prepared, with the only difference that moisture content in wheat bran was 7%. Before mixing that bran with remaining ingredients it was additionally moistened to increase humidity up to final content of 28% without affecting bran friability.

Example III. From loose bran of structurally bonded moisture content amounting to 17%, obtained from wheat grain grinding process the following granularity fractions in amounts as follows have been selected by sifting: 0.1/0.2 - 35% w/w, 0.2/0.4 - 25% w/w, 0.4/0.8 mm - 40%. The moulding material for making biodegradable mouldings has been prepared by mixing 96.6% w/w of so selected bran with 0.3% w/w of glycerine, 0.4% of powdered hen egg white, 0.7% w/w of cocoa powder and 2% w/w of impregnating substance.

Example IV. From loose bran of structurally bonded moisture content amounting to 12%, obtained from wheat grain grinding process the following granularity fractions in amounts as follows have been selected by sifting: 0.1/0.2 - 40% w/w, 0.2/0.4 - 40% w/w, 0.4/0.8 mm - 20%. The moulding material for making biodegradable mouldings has been prepared by additionally moistening the bran used so as to increase its humidity up to final content of 18% without affecting bran friability.

Example V. A metered portion of material obtained in Example I has been placed on the lower half of mould mounted on a hydraulic press. Prior to that placement the both halves of the mould were preheated up to 430°C. After placing the material it has been exposed for 15 second to that temperature and compressive force of 75 MT/cm² at pressure exerted on the mould closing piston amounting to 240 MPa. The moulding process was conducted in three compression cycles each lasting 5 seconds with pressure relieving during intervals between cycles. The moulding so obtained in the form of a tray has been subsequently coated with casein.

Example VI. The material obtained in Example I has been subjected to a pre-treatment in bulk by exposing it to temperature of 200°C and pressure of 4 MPa during 20 seconds. From so pre-treated material a metered portion thereof has been taken and placed on lower half of a mould previously preheated up to 350°C. Upper half of the mould has been preheated up to 380°C. Material placed into the mould has been exposed for 10 seconds in a single cycle to temperatures as above and compressive force of 50 MT/cm²

at pressure exerted onto the mould closing piston amounting to 60 MPa. The mouldings obtained were the disposable plates of 350 mm in diameter.

Example VII. The material prepared as in Example III has been placed on lower half of a mould with a cup-shaped mould cavity. The both halves of that mould have been previously preheated up to and maintained at equal temperatures of 400°C. Before closing the mould completely its interior has been sealed by means of a collar and closed by pressing upper half against the lower one and producing pressure of 7 MPa inside the mould. A disposable cup obtained has been internally coated with albumin.

Example VIII. The material obtained in Example has been briquette by extrusion using a typical extrusion moulding machine. The briquettes weighing 25 g each have been obtained which constitutes 1/3 of the weight of material necessary to mould a plate of 235 mm in diameter. Further proceeding was identical as in Example VI with the only exception that on the lower mould half 3 briquettes were placed before moulding.

Example IX. The whole procedure was essentially identical as in Example VII but the material, before placing it into a mould, was pelletised using a typical pelletising machine.

Example X. A metered portion of material obtained in Example I has been placed on the lower half of mould mounted on a hydraulic press. Prior to that placement the both halves of the mould were preheated up to 430°C. After placing the material into the mould it has been exposed for 20 second to that temperature and compressive force of 75 MT/cm² at pressure exerted on the mould closing piston amounting to 240 MPa. The moulding process was conducted in four compression cycles each lasting 5 seconds with pressure relieving during intervals between cycles.

Example XI. The round trays of 235 mm in diameter made from the material and using the method according to this invention have been tested at the Central Research and Development Institute of the Packaging Industry. This testing included water and oil absorbability tests, axial compressive strength test and sensory assessment.

- The water and oil absorbability tests were conducted in accordance with Institute's proprietary methodology. The both tests were carried on in the following manner: the trays placed on blotting paper have been filled separately with 200 ml water at temperature of 20±2°C and 80±2°C and edible oil at temperature 20±2°C and then time was measured between an instant of tray placement on the blotting paper and that of observed liquid leakage onto blotting paper. Before testing the trays were

conditioned by keeping them for 48 hrs at temperature of $23\pm1^{\circ}\text{C}$ and relative humidity of surrounding air amounting to $50\pm2\%$ in accordance with conditions specified in the Polish standard specification PN-92/P-50067. „Paper, cardboard and fibrous materials. Standardised conditioning conditions”.

- Determination of axial compressive strength has been performed in accordance with internal testing procedure of said R&D Institute No. PBn/DOJ/03.11 „Determination of axial compressive strength” developed on the basis of the Polish standard specification PN-75/O-79172 „Plastic unit packages. Determination of axial compressive strength”. The tests were performed using the strength testing machine INSTRON, model TM-M for four trays obtained as described above. During each test a load vs. deformation diagram was recorded until destruction of material tested took place.
- The sensory assessment was performed in accordance with internal testing procedure of said R&D Institute No. PBn/DOJ/04.05 „Determination of odour and taste transfer in direct contact” developed on the basis of the Polish standard specification PN-87/O-79114 „Determination of odour and taste transfer in direct contact”. The sensory assessment was performed by means of triangle method using powdered sugar and flour as standard substances.

The results of water and oil absorbability tests have been summarised in the Table 1 whereas these concerning the axial compressive strength test and sensory assessment in the Table 2. The figure attached shows a diagram of compressive force vs. deformation relationship obtained during the axial compressive strength test of trays mentioned above.

Table 1.

Results of testing the trays made of wheat bran

Seq. No.	Test description	Time lapsed	Symptoms observed
1.	Water absorbability test for water at 20°C	After lapse of 3 minutes	Swelling of material layer in contact with water, separation of single bran particles from tray surface
		After lapse of 12 minutes	Pulping of whole water contacting surface of tray tested.
		After lapse of 30 minutes	Further pulping of water contacting surface without any traces of leakage
		After lapse of 70 minutes	Leakage traces noticeable on blotting paper underlay, water penetrates through the tray material
2.	Oil absorbability test for oil at 20°C	During 60 minutes	Not any changes in material structure were observed
		After lapse of 60 minutes	Leaking oil traces are noticeable on the blotting paper underlay, oil penetrates through the tray material

Table 2.

Results of axial compressive strength determination test and sensory assessment


Seq. No.	Test description	Unit of measure	Average value
1.	Determination of axial compressive strength	N	359±78
2.	Sensory assessment for the standard substance - powdered sugar	sensory changes in standard substance in question: distinctly perceivable taste and odour of bran	
3.	Sensory assessment for the standard substance - flour	sensory changes in standard substance in question: distinctly perceivable taste and odour of bran	

Claims

1. A method of making biodegradable mouldings, in particular table utensils and packaging containers, of bran, especially wheat one, used as primary raw material, consisting in preparing from bran a moulding material by mixing the last mentioned one, depending on needs, with appropriate additives and exposing such mixture to elevated temperature, characterised in that from dry bran the fractions sized from 0.01 to 2.80 mm are selected by a known segregation process, the selected bran fractions are mixed together and with dry additives needed as required and necessary metered quantity of that mixture is placed into a suitable preheated mould; the metered portion of mixture placed into mould is subsequently exposed for 1 to 25 seconds to temperature within a range from 20 to 450°C and pressure within a range from 5 to 450 kg/m² in successive cycles of up to 5 seconds duration each alternately with pressure relieving during intervals between two cycles following each other.
2. A method as claimed in Claim 1 characterised in that the moulding material mixture, after preparing same but before placing it into a mould, is exposed during 1 to 20 seconds to elevated temperature within a range from 20 to 450°C and pressure within a range from 5 to 450 kg/cm² and thereafter, while maintaining it still under pressure the material is introduced into the preheated mould.
3. A material for making biodegradable mouldings, in particular table utensils and packaging containers, containing grain grinding products and possibly up to 5% w/w of a mixture of impregnating substances and/or fragrance and/or aroma giving additives and/or non-fibrous fillers and/or moisture retaining agents and/or colouring additives, characterised in that it consists in 95-100% w/w of loose bran, in particular the wheat one, constituting a selected bran fraction of grain size from 0.01 to 2.80 mm containing from 7% to 45% of structurally bonded water in the form of moisture.

4. A method of making biodegradable mouldings, in particular table utensils and packaging containers, characterised in that the loose bran, in particular wheat one, of grain size 0.01 to 2.80 mm in amount of 96-100% w/w containing 7% to 45% structurally bound water in the form of moisture are dry-mixed with a mixture impregnating substances and/or fragrance and/or aroma giving additives and/or non-fibrous fillers and/or moisture retaining agents and/or colouring additives in amount of up to 5% w/w; a metered quantity of the moulding material obtained is placed on one part of a multipartite, preferably bipartite, mould, the mould is being closed with simultaneous exposure of moulding material placed there for several tens of seconds to temperature within a range from 20 to 450°C and pressure within a range of 1-10 MPa and/or compressive force of up to 100 MT/cm² at pressure of up to 320 MPa acting of a mould closing piston.
5. A method as claimed in Claim 4, characterised in that the mixture of moulding material is exposed simultaneously to elevated temperature and pressure and/or compressive force for a time from 5 to 25 seconds.
6. A method as claimed in Claim 4, characterised in that the mould, before completely closing it, is being sealed and thereafter its halves are urged towards each other producing thereby appropriate pressure within the mould cavity.
7. A method as claimed in Claim 4, characterised in that upper and lower halves of the mould are preheated to different temperatures.
8. A method as claimed in Claim 4, characterised in that the material placed into the mould is exposed to elevated temperature and pressure and/or compressive force in a single cycle or in several successive cycles, each of several seconds duration with pressure relieving during intervals between said cycles.
9. A method as claimed in Claim 4, characterised in that the final products are coated with a film-forming substance in any known manner.
10. A method as claimed in Claim 4, characterised in that the moulding material mixture, after preparing same but before placing it into a mould, is exposed during several tens of seconds to elevated temperature within a range from 20 to 450°C and pressure within a range from 1 to 10 MPa.
11. A method as claimed in Claim 4, characterised in that the moulding material mixture is being pelletised prior to placing it into the mould

12. A method as claimed in Claim 4, characterised in that the moulding material mixture is being briquetted prior to placing it into the mould
13. A method as claimed in Claim 12, characterised in that the briquettes having weight equal to that of material portion need to mould a single moulding or to that of integer denominator fraction of such material portion.



INTERNATIONAL SEARCH REPORT

International Application No

PCT/PL 00/00084

A. CLASSIFICATION OF SUBJECT MATTER IPC 7 A23L1/10 A23P1/08 A23P1/10 A21D2/36 A21D8/06 A21D13/00		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 7 A21D A23L A23P B65D A21B B27N		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used) WPI Data, EPO-Internal, PAJ, FSTA		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 556 774 A (NISSEI KK) 25 August 1993 (1993-08-25) page 2, line 51 -page 3, line 17 page 3, line 38-46 claim 1	1,4,5,8
X	EP 0 401 117 A (ARD SA) 5 December 1990 (1990-12-05) page 2, paragraphs 11,12 example 1 claims 1,2,5	3
X	GB 1 507 867 A (NORGINE LTD) 19 April 1978 (1978-04-19) page 1, line 42-48 page 2, line 31-43	3
-/--		
☒ Further documents are listed in the continuation of box C. ☒ Patent family members are listed in annex.		
° Special categories of cited documents :		
A document defining the general state of the art which is not considered to be of particular relevance *E* earlier document but published on or after the international filing date *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) *O* document referring to an oral disclosure, use, exhibition or other means *P* document published prior to the international filing date but later than the priority date claimed *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. *Z* document member of the same patent family		
Date of the actual completion of the international search	Date of mailing of the international search report	
15 March 2001	27/03/2001	
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Authorized officer Piret-Viprey, E	

INTERNATIONAL SEARCH REPORT

International Application No

PCT/PL 00/00084

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 556 577 A (VOEWA WERTSTOFFTECHNIK GMBH ;KRICKL LUDWIG (DE)) 25 August 1993 (1993-08-25) column 4, line 18-23 claims 1,3,18-20 -----	1,4
A	DE 42 03 211 A (RINDERLE KARL) 12 August 1993 (1993-08-12) column 1, line 36-48 claim 1 ----	1
A	PATENT ABSTRACTS OF JAPAN vol. 1999, no. 11, 30 September 1999 (1999-09-30) & JP 11 166055 A (SHOKUHIN SANGYO KANKYO HOZEN GIJUTSU KENKYU KUMIAI), 22 June 1999 (1999-06-22) abstract -----	1,4

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/PL 00/00084

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0556774 A	25-08-1993	JP 3085554 B JP 5228460 A AU 664728 B AU 3310693 A CA 2089809 A,C NZ 245926 A US 5470382 A US 5716440 A	11-09-2000 07-09-1993 30-11-1995 26-08-1993 20-08-1993 26-05-1995 28-11-1995 10-02-1998
EP 0401117 A	05-12-1990	FR 2647640 A	07-12-1990
GB 1507867 A	19-04-1978	NONE	
EP 0556577 A	25-08-1993	DE 9200610 U DE 9208683 U	19-11-1992 01-10-1992
DE 4203211 A	12-08-1993	NONE	
JP 11166055 A	22-06-1999	NONE	