



US008281489B2

(12) **United States Patent**
Zobel et al.

(10) **Patent No.:** **US 8,281,489 B2**
(45) **Date of Patent:** **Oct. 9, 2012**

(54) **FLAT TUBE, FLAT TUBE HEAT EXCHANGER, AND METHOD OF MANUFACTURING SAME**

(75) Inventors: **Werner Zobel**, Boeblingen (DE); **Jens Nies**, Holzgerlingen (DE); **Roland Straehle**, Unterensingen (DE); **Siegfried Eisele**, Schoenaich (DE); **Bernhard Stephan**, Altenriet (DE)

(73) Assignee: **Modine Manufacturing Company**, Racine, WI (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 298 days.

(21) Appl. No.: **12/176,929**

(22) Filed: **Jul. 21, 2008**

(65) **Prior Publication Data**

US 2009/0019689 A1 Jan. 22, 2009

Related U.S. Application Data

(63) Continuation of application No. PCT/US2007/060774, filed on Jan. 19, 2007.

(30) **Foreign Application Priority Data**

Jan. 19, 2006	(DE)	10 2006 002 627
Jan. 20, 2006	(DE)	10 2006 002 789
Jan. 21, 2006	(DE)	10 2006 002 932
Feb. 14, 2006	(DE)	10 2006 006 670
Apr. 8, 2006	(DE)	10 2006 016 711
Jun. 27, 2006	(DE)	10 2006 029 378
Jul. 13, 2006	(DE)	10 2006 032 406
Jul. 20, 2006	(DE)	10 2006 033 568
Jul. 29, 2006	(DE)	10 2006 035 210
Sep. 2, 2006	(DE)	10 2006 041 270
Sep. 9, 2006	(DE)	10 2006 042 427

(51) **Int. Cl.**
B21D 33/00 (2006.01)

(52) **U.S. Cl.** **29/890.053**; 29/890.049; 29/890.045; 29/890.04; 83/39; 83/42

(58) **Field of Classification Search** 29/890.053, 29/890.032, 890.038, 890.045, 890.049; 83/30, 39, 40, 42, 44
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

1,242,652 A 9/1917 Capell
(Continued)

FOREIGN PATENT DOCUMENTS

DE 273441 7/1912
(Continued)

OTHER PUBLICATIONS

PCT/US2007/060790 International Preliminary Report on Patentability dated Jul. 31, 2008 (4 pages).

(Continued)

Primary Examiner — David Bryant


Assistant Examiner — Christopher Besler

(74) *Attorney, Agent, or Firm* — Michael Best & Friedrich LLP

(57) **ABSTRACT**

A number of flat tubes, flat tube heat exchangers, and methods of manufacturing both are described and illustrated. The flat tubes can be constructed of one, two, or more pieces of sheet material. A profiled insert integral with the flat tube or constructed from another sheet of material can be used to define multiple flow channels through the flat tube. The flat tubes can be constructed of relatively thin material, and can be reinforced with folds of the flat tube material and/or of an insert in areas subject to higher pressure and thermal stresses. Also, the relatively thin flat tube material can have a corrosion layer enabling the material to resist failure due to corrosion. Heat exchangers having such flat tubes connected to collection tubes are also disclosed, as are manners in which such tubes can be provided with fins.

21 Claims, 49 Drawing Sheets



U.S. PATENT DOCUMENTS

1,599,395	A	9/1926	Hards	
2,222,842	A	11/1940	Humphrey	
2,252,210	A	8/1941	Seemiller	
2,373,218	A	4/1945	Arnold	
2,444,463	A	7/1948	Nordquist	
2,757,628	A	8/1956	Johnston	
2,912,749	A	11/1959	Bauernfeind et al.	
3,021,804	A *	2/1962	Simpelaar	29/890.046
3,053,511	A	9/1962	Godfrey	
3,229,760	A	1/1966	Hurter et al.	
3,687,193	A	8/1972	Wright	
3,734,135	A	5/1973	Mosier	
4,197,625	A	4/1980	Jahoda	
4,215,744	A	8/1980	Bowles	
4,470,452	A	9/1984	Rhodes	
4,501,321	A	2/1985	Real et al.	
4,570,700	A	2/1986	Ohara et al.	
4,805,693	A	2/1989	Flessate	
4,901,908	A	2/1990	Negura et al.	
4,949,543	A	8/1990	Cottone et al.	
5,036,909	A	8/1991	Whitehead et al.	
5,058,266	A	10/1991	Knoll	
5,179,770	A *	1/1993	Block et al.	29/17.3
5,185,925	A	2/1993	Ryan et al.	
5,186,250	A	2/1993	Ouchi et al.	
5,351,750	A	10/1994	Garcia	
5,386,629	A	2/1995	Ouchi et al.	
5,441,106	A	8/1995	Yukitake	
5,456,006	A	10/1995	Study	
5,457,885	A	10/1995	Ohashi et al.	
5,692,300	A	12/1997	Conn et al.	
5,799,727	A	9/1998	Liu	
6,119,341	A	9/2000	Kato et al.	
6,192,977	B1	2/2001	Dey et al.	
6,209,202	B1	4/2001	Rhodes et al.	
6,261,706	B1	7/2001	Fukuda et al.	
6,308,775	B1	10/2001	Naumann	
6,425,261	B2	7/2002	Burk et al.	
6,467,170	B2	10/2002	Kato et al.	
6,470,570	B2	10/2002	Prater et al.	
6,475,301	B1	11/2002	Grab et al.	
6,502,305	B2	1/2003	Martins et al.	
6,513,586	B1	2/2003	Haussmann	
6,527,045	B1	3/2003	Osakabe et al.	
6,537,388	B1	3/2003	Wynns et al.	
6,546,774	B2	4/2003	Granetzke	
6,640,886	B2	11/2003	Lamich	
6,640,887	B2	11/2003	Abell et al.	
6,666,265	B1	12/2003	Kato et al.	
6,988,539	B2	1/2006	Kato et al.	
7,107,680	B2	9/2006	Ueda	
7,117,936	B2	10/2006	Ohata et al.	
7,135,239	B2	11/2006	Rajagopalan	
7,152,671	B2	12/2006	Shibagaki et al.	
7,204,302	B2	4/2007	Shibagaki et al.	
7,487,589	B2	2/2009	Smith et al.	
7,665,512	B2	2/2010	Brost et al.	
2003/0024694	A1	2/2003	Lamich	
2004/0035910	A1	2/2004	Dockus et al.	
2004/0108305	A1 *	6/2004	Harnisch et al.	219/121.72
2004/0194943	A1	10/2004	Yamauchi	
2004/0206482	A1	10/2004	Bang	
2005/0006082	A1	1/2005	Brost et al.	
2005/0077033	A1	4/2005	Schmalzried	
2005/0092476	A1	5/2005	Hu et al.	
2005/0133210	A1	6/2005	Inagaki et al.	
2005/0247444	A1 *	11/2005	Ohata et al.	165/177
2006/0086491	A1	4/2006	Ueda	
2006/0230617	A1	10/2006	Kent et al.	
2006/0243429	A1	11/2006	Chu et al.	
2006/0265874	A1	11/2006	Hashimoto et al.	
2006/0283585	A1	12/2006	Smith et al.	
2007/0095514	A1	5/2007	Inoue et al.	
2009/0014164	A1	1/2009	Zobel et al.	
2009/0014165	A1	1/2009	Zobel et al.	
2009/0019694	A1	1/2009	Zobel et al.	
2009/0019695	A1	1/2009	Zobel et al.	
2009/0019696	A1	1/2009	Zobel et al.	

2009/0020277	A1	1/2009	Zobel et al.
2009/0020278	A1	1/2009	Zobel et al.
2009/0056927	A1	3/2009	Zobel et al.
2009/0218085	A1	9/2009	Rogers et al.
2009/0260794	A1	10/2009	Minami et al.
2010/0243225	A1	9/2010	Zobel et al.

FOREIGN PATENT DOCUMENTS

DE	401893	9/1924
DE	934644	11/1955
DE	935487	11/1955
DE	2113581	12/1972
DE	3809944	10/1989
DE	4031577	4/1992
DE	4340378	6/1994
DE	29614186	12/1997
DE	19641144	4/1998
DE	19753724	6/1999
DE	10137334	2/2003
DE	10200586	7/2003
DE	102004057407	8/2005
EP	0179646	4/1986
EP	0765701	4/1997
EP	0859209	8/1998
EP	0907062	4/1999
EP	1074807	2/2001
EP	1306156	5/2003
EP	1362649	11/2003
EP	1640684	3/2006
EP	1684041	7/2006
FR	2690233	10/1993
FR	2811746	1/2002
GB	444964	3/1936
GB	683161	11/1952
GB	2203677	10/1988
GB	2354960	4/2001
GB	2426727	12/2006
JP	57105690	7/1982
JP	58000094	1/1983
JP	60247426	12/1985
JP	7019779	1/1995
JP	10160375	6/1998
JP	2001050677	2/2001
JP	2002350083	12/2002
JP	2004092940	3/2004
JP	2005214511	8/2005
JP	2006064345	3/2006
RU	2032878	4/1995
SU	340209	1/1972
SU	616521	7/1978
WO	03/060412	7/2003
WO	2004/080640	9/2004
WO	2004/085948	10/2004
WO	2005/033606	4/2005
WO	2006/116857	11/2006
WO	2007/009588	1/2007
WO	2008/011115	1/2008

OTHER PUBLICATIONS

PCT/US2007/060790 International Search Report and Written Opinion dated Nov. 20, 2007 (6 pages).

PCT/US2007/060789 International Preliminary Report on Patentability dated Jul. 22, 2008 (8 pages).

PCT/US2007/060789 International Search Report and Written Opinion dated Nov. 15, 2007 (10 pages).

PCT/US2007/060774 International Preliminary Report on Patentability dated Jul. 22, 2008 (5 pages).

PCT/US2007/060774 International Search Report and Written Opinion dated Oct. 3, 2007 (8 pages).

PCT/US2007/060785 International Search Report and Written Opinion dated Apr. 1, 2008 (7 pages).

PCT/US2007/060785 International Preliminary Report on Patentability dated Jul. 31, 2008 (5 pages).

PCT/US2007/060769 International Preliminary Report on Patentability dated Jul. 22, 2008 (5 pages).

PCT/US2007/060769 International Search Report and Written Opinion dated May 30, 2008 (6 pages).

Extended European Search Report for Application No. 07717324.3 dated Apr. 29, 2010 (5 pages).

PCT/US07/16396 International Search Report and Written Opinion dated Aug. 20, 2008 (8 pages).

PCT/US2007/016396 International Preliminary Report on Patentability dated Jan. 20, 2009 (7 pages).

First Office Action from the State Intellectual Property Office of China for Application No. 200780009794.6 dated Jan. 8, 2010 (English Translation—7 pages).

First Office Action from the State Intellectual Property Office of China for Application No. 200810174245.0 dated Apr. 28, 2010 (English Translation—5 pages).

First Office Action from the State Intellectual Property Office of China for Application No. 200780009801.2 dated Nov. 27, 2009 (English Translation—5 pages).

First Office Action from the State Intellectual Property Office of China for Application No. 200780009913.8 dated Jan. 8, 2010 (English Translation—6 pages).

Office Action from the United States Patent Office for U.S. Appl. No. 12/176,186 dated Jun. 9, 2010 (9 pages).

Office Action from the United States Patent Office for U.S. Appl. No. 12/176,188 dated Jun. 14, 2010 (7 pages).

Office Action from the United States Patent Office for U.S. Appl. No. 12/176,943 dated May 27, 2010 (15 pages).

Office Action from the United States Patent Office for U.S. Appl. No. 12/176,933 dated May 27, 2010 (7 pages).

Office Action from the United States Patent Office for U.S. Appl. No. 12/176,937 dated May 24, 2010 (14 pages).

* cited by examiner





FIG. 2

FIG. 1
























FIG. 3












FIG. 24




FIG. 25












FIG. 26










FIG. 34




FIG. 35




FIG. 36




FIG. 37







FIG. 38






FIG. 42




FIG. 43




FIG. 44




FIG. 45




FIG. 46





FIG. 47








FIG. 49








FIG. 52





FIG. 53






FIG. 55

1927, 1933, 1935




FIG. 55A




FIG. 55B

1949




FIG. 55C

1949




FIG. 55D




FIG. 57A




FIG. 57B




FIG. 56




FIG. 58




FIG. 59




FIG. 60







FIG. 60a






FIG. 64




FIG. 65




FIG. 66




FIG. 67




FIG. 68




FIG. 69




FIG. 70

FIG. 70A








FIG. 71








FIG. 76




FIG. 77




FIG. 78









FIG. 79












FIG. 84








FIG. 88




FIG. 90




FIG. 89




FIG. 91




FIG. 92




FIG. 93




FIG. 94




FIG. 95




FIG. 96

1

FLAT TUBE, FLAT TUBE HEAT EXCHANGER, AND METHOD OF MANUFACTURING SAME

CROSS-REFERENCE TO RELATED APPLICATIONS

This is a continuation application of International Patent Application No. PCT/US2007/060774, filed 19 Jan. 2007. Priority is hereby claimed to German Patent Application No. DE 10 2006 002 627.6, filed Jan. 19, 2006, and to German Patent Application No. DE 10 2006 002 789.2, filed on Jan. 20, 2006, and to German Patent Application No. DE 10 2006 002 932.1, filed on Jan. 21, 2006, and to German Patent Application No. DE 10 2006 006 670.7, filed Feb. 14, 2006, and to German Patent Application No. DE 10 2006 016 711.2, filed Apr. 8, 2006, and to German Patent Application No. DE 10 2006 029 378.9, filed Jun. 27, 2006, and to German Patent Application No. DE 10 2006 032 406.4, filed Jul. 13, 2006, and to German Patent Application No. DE 10 2006 033 568.6, filed Jul. 20, 2006, and to German Patent Application No. DE 10 2006 035 210.6, filed Jul. 29, 2006, and to German Patent Application No. DE 10 2006 041 270.2, filed Sep. 2, 2006, and to German Patent Application No. DE 10 2006 042 427.1, filed Sep. 9, 2006, the entire contents of which are incorporated herein by reference.

SUMMARY

In some embodiments, the present invention provides a heat exchanger tube including a sheet of material at least partially forming a tube body having a thickness of less than about 0.15 mm, the tube body defining an interior space and having an arcuately-shaped interior side, and an insert extending through the interior space of the tube body and separating a first flow path and a second flow path, a portion of the insert being nested in the arcuately-shaped interior side of the tube body.

The present invention also provides a heat exchanger tube including a first sheet of material and a second sheet of material together at least partially forming a tube body, each of the first sheet of material and the second sheet of material having a thickness of less than about 0.15 mm, the tube body defining an interior space and having a narrow side and a broad side. The heat exchanger can also include an insert supported in the interior space of the tube body between the first sheet of material and the second sheet of material, a portion of the insert being received in the narrow side of the tube body.

In addition, the present invention provides a method of forming a heat exchanger tube including the acts of shaping a sheet of material having a thickness of less than about 0.15 mm to form at least a portion of a tube body defining an interior space and having an arcuately-shaped side, and nesting a portion of an insert in the arcuately-shaped interior side of the tube body, the insert separating a first flow path and a second flow path.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a side view of a tube according to some embodiments of the present invention.

FIG. 2 is an enlarged view of an end of the tube shown in FIG. 1.

FIG. 3 schematically illustrates a set of exemplary manufacturing steps that can be used to form the tube shown in FIG. 1.

2

FIG. 4 is an enlarged view of a narrow side of the tube shown in FIG. 1.

FIG. 5 is another enlarged view of the narrow side shown in FIG. 1.

FIG. 6 is an enlarged view of a narrow side of a tube according to another embodiment of the present invention.

FIG. 7 is an enlarged view of a narrow side of a tube according to yet another embodiment of the present invention.

FIG. 8 is an enlarged view of a narrow side of a tube according to still another embodiment of the present invention.

FIG. 9 is an enlarged view of a narrow side of a tube according to another embodiment of the present invention.

FIG. 10 is an enlarged view of a narrow side of a tube according to yet another embodiment of the present invention.

FIG. 11 a narrow side of a tube according to still another embodiment of the present invention.

FIG. 12 is an enlarged view of a portion of a tube including internal folds according another embodiment of the present invention.

FIG. 13 is an enlarged view of a portion of a tube including internal folds according to yet another embodiment of the present invention.

FIG. 14 is an enlarged view of a portion of a tube including an insert according to still another embodiment of the present invention.

FIG. 15 is an enlarged view of a portion of a tube including an insert according to another embodiment of the present invention.

FIG. 16 schematically illustrates a set of exemplary manufacturing steps that can be used to form a tube including first and second portions formed from a common piece of folded material.

FIG. 17 is an enlarged view of a tube including first and second portions formed from a common piece of folded material according to still another embodiment of the present invention.

FIG. 18 is an enlarged view of a tube including first and second portions formed from a common piece of folded material according to another embodiment of the present invention.

FIG. 19 is a side view of a tube including first and second portions formed from a common piece of folded material according to yet another embodiment of the present invention.

FIG. 20 is a side view of a tube including first and second portions formed from a common piece of folded material according to still another embodiment of the present invention.

FIG. 21 is a side view of a tube including first and second portions formed from a common piece of folded material according to another embodiment of the present invention.

FIG. 22 is a side view of a tube including first and second portions formed from a common piece of folded material according to yet another embodiment of the present invention.

FIG. 23 is a side view of a tube including first and second portions formed from a common piece of folded material according to still another embodiment of the present invention.

FIG. 24 is an enlarged view of a tube including first and second portions formed from a common piece of folded material according to another embodiment of the present invention.

3

FIG. 25 is an exploded view of a tube including first and second portions and an insert positioned between the first and second portions according to some embodiments of the present invention.

FIG. 26 is an exploded view of the tube shown in FIG. 25.

FIG. 27 is an exploded view of a tube including first and second portions and an insert positioned between the first and second portions according to still another embodiment of the present invention.

FIG. 28 is a side view of the tube including first and second portions and an insert positioned between the first and second portions according to yet another embodiment of the present invention.

FIG. 29 is an enlarged view of a portion of the tube shown in FIG. 28.

FIG. 30 is a side view of a tube including first and second portions and an insert positioned between the first and second portions according to still another embodiment of the present invention.

FIG. 31 is an enlarged view of a portion of the tube shown in FIG. 30.

FIG. 32A is a side view of a tube including first and second portions and an insert positioned between the first and second portions according to yet another embodiment of the present invention.

FIG. 32B is an enlarged view of a portion of the tube shown in FIG. 32A.

FIG. 33 is a side view of a portion of a tube including first and second portions and an insert positioned between the first and second portions according to another embodiment of the present invention.

FIG. 34 illustrates ten embodiments of tubes according to some embodiments of the present invention.

FIG. 35 is a side view of a tube according to some embodiments of the present invention.

FIG. 36 is a side view of an internal insert for the tube shown in FIG. 35.

FIG. 37 is a top view of the internal insert shown in FIG. 36.

FIG. 38 is a perspective view of a portion of the internal insert shown in FIG. 35.

FIG. 39 is a side view of a tube according to some embodiments of the present invention.

FIG. 40 is an enlarged perspective view of an internal insert for the tube shown in FIG. 39.

FIG. 41 is a perspective view of a portion of the internal insert shown in FIG. 40.

FIG. 42 is an enlarged perspective view of the internal insert shown in FIG. 40.

FIG. 43 is a top view of a portion of an internal insert for a tube according to some embodiments of the present invention.

FIG. 44 is a side view of a an insert according to an embodiment of the present invention, shown within a flat tube in phantom.

FIG. 45 is a side view of another insert according to an embodiment of the present invention, shown within a flat tube in phantom.

FIG. 46 schematically illustrates a set of exemplary manufacturing steps that can be used to form a tube according to some embodiments of the present invention.

FIG. 47 is a partially exploded side view of the tube shown in FIG. 46.

FIG. 48 schematically illustrates a set of exemplary manufacturing steps that can be used to form a tube according to some embodiments of the present invention.

4

FIG. 49 is a roll press manufacturing line that can be used to manufacture tubes according to some embodiments of the present invention.

FIG. 50 schematically illustrates a set of exemplary manufacturing steps that can be used to form a tube according to some embodiments of the present invention.

FIG. 51 schematically illustrates a set of exemplary manufacturing steps that can be used to form a tube according to other embodiments of the present invention.

FIG. 52 schematically illustrates a set of exemplary manufacturing steps that can be used to form a tube according to still other embodiments of the present invention.

FIG. 53 schematically illustrates a set of exemplary manufacturing steps that can be used to form a tube according to yet other embodiments of the present invention.

FIG. 54 schematically illustrates a set of exemplary manufacturing steps that can be used to form a tube according to other embodiments of the present invention.

FIG. 55 illustrates an exemplary manufacturing line that can be used to manufacture tubes according to some embodiments of the present invention.

FIG. 55A is a sectional view showing a perforation station of the manufacturing line shown in FIG. 55.

FIG. 55B is a side view showing the perforation station shown in FIG. 55A.

FIG. 55C is a sectional view showing a breaking roller and a bar of the manufacturing line shown in FIG. 55.

FIG. 55D is a side view of a breaking roller and a bar of the manufacturing line shown in FIG. 55.

FIG. 56 is a side view of a portion of the perforation station shown in FIG. 55A.

FIG. 57A is a side view showing a sheet of material traveling through a portion of the perforation station shown in FIG. 55A.

FIG. 57B is a top view showing a sheet of material traveling through a portion of the perforation station shown in FIG. 55A.

FIG. 58 is a side view of a breaking roller and a bar of the manufacturing line shown in FIG. 55.

FIG. 59 is a series of schematic end views of the manufacturing line shown in FIG. 55, shown in different stages of forming a flat tube with insert.

FIG. 60 is a schematic top view of a folding roller portion of the manufacturing line shown in FIG. 55.

FIG. 60A is an end view of the folding roller portion shown in FIG. 60.

FIG. 61 is a schematic end view of a finned flat tube manufacturing line according to an embodiment of the present invention.

FIG. 62 is an exploded view of a heat exchanger having finned flat tubes according to an embodiment of the present invention.

FIG. 63 shows partial views of fin sets according to different embodiments of the present invention.

FIG. 64 is a schematic view of a finned tube manufacturing process according to an embodiment of the present invention.

FIG. 65 is a perspective side view of a portion of the manufacturing process shown in FIG. 64.

FIG. 66 is a detail view of a heat exchanger having finned flat tubes according to an embodiment of the present invention.

FIG. 67 is a detail view of a flat tube that can be used in producing a finned flat tube according to an embodiment of the present invention.

FIG. 68 is a detail side view of a heat exchanger having finned flat tubes according to another embodiment of the present invention.

FIG. 69 is a detail perspective view of the part of the heat exchanger shown in FIG. 68.

FIG. 70 is a side view of a collection tank according to an embodiment of the present invention.

FIG. 70A is an end view of the collection tank shown in FIG. 70.

FIG. 71 is a detail view of a heat exchanger having the collection tank illustrated in FIGS. 70 and 70A.

FIG. 72 is a perspective view of a collection tank according to another embodiment of the present invention.

FIG. 73 is a detail perspective view of a heat exchanger having the collection tank illustrated in FIG. 72.

FIG. 74 is another detail perspective view of the heat exchanger shown in FIG. 73.

FIG. 75 is a detail perspective view of the collection tank shown in FIG. 72.

FIG. 76 is another detail view of a heat exchanger having the collection tank illustrated in FIGS. 70-71.

FIG. 77 is an elevational view of the heat exchanger illustrated in FIGS. 71 and 76.

FIG. 78 is a detail side view of a heat exchanger having a collection tank according to another embodiment of the present invention.

FIG. 79 is a detail end view of the heat exchanger illustrated in FIG. 78.

FIG. 80 is a detail side view of the collection tank of the heat exchanger illustrated in FIGS. 78 and 79.

FIG. 80A is an end view of the collection tank illustrated in FIGS. 78-80.

FIG. 81 is a detail side view of a heat exchanger having a collection tank according to another embodiment of the present invention.

FIG. 82 is a detail end view of a heat exchanger having a collection tank according to another embodiment of the present invention.

FIG. 83 is a detail side view of the collection tank of the heat exchanger illustrated in FIG. 81.

FIG. 84 is a flowchart of a heat exchanger manufacturing process according to an embodiment of the present invention.

FIG. 84A is a schematic view of a heat exchanger manufactured according to the flowchart of FIG. 84.

FIG. 85 is an exploded perspective view of a heat exchanger according to another embodiment of the present invention.

FIG. 86 is an exploded perspective view of a heat exchanger according to another embodiment of the present invention.

FIG. 87 is an end view of a flat tube of the heat exchanger illustrated in FIG. 86.

FIG. 88 is an exploded perspective view of a heat exchanger according to another embodiment of the present invention.

FIG. 89 illustrate end views of alternative flat tube embodiments according to the present invention.

FIG. 90 is an exploded perspective view of a heat exchanger according to another embodiment of the present invention.

FIG. 91 are views of a flat tube according to another embodiment of the present invention, shown in different stages of formation.

FIGS. 92-95 illustrate methods of connecting portions of a heat exchanger according to some embodiments of the present invention.

FIG. 96 is a graph showing silicon diffusion depths for heat exchangers connected according to some embodiments of the present invention.

DETAILED DESCRIPTION

Before any embodiments of the invention are explained in detail, it is to be understood that the invention is not limited in its application to the details of construction and the arrangement of components set forth in the following description or illustrated in the following drawings. The invention is capable of other embodiments and of being practiced or of being carried out in various ways. Also, it is to be understood that the phraseology and terminology used herein is for the purpose of description and should not be regarded as limiting. The use of "including," "comprising," or "having" and variations thereof herein is meant to encompass the items listed thereafter and equivalents thereof as well as additional items. Unless specified or limited otherwise, the terms "mounted," "connected," "supported," and "coupled" and variations thereof are used broadly and encompass both direct and indirect mountings, connections, supports, and couplings. Further, "connected" and "coupled" are not restricted to physical or mechanical connections or couplings.

As described in greater detail below, many embodiments of the present invention relate to or are based upon the use of tubes having a substantially flat cross-sectional shape taken along a plane perpendicular to a longitudinal axis of the tube. In particular, each such tube can have a major dimension and a smaller minor dimension perpendicular to the major dimension. These dimensions are sometimes referred to herein as being "diameters", although the use of the term "diameter" is not intended to alone indicate or imply that the feature referred to is round, rotund, or otherwise has any particular shape. Rather, the term "diameter" is only used to refer to a largest dimension of the tube in the direction and location indicated. Each such tube can have two opposing walls defining the faces of the tube (referred to herein as the "broad sides" of the tube), and two shorter and more stable walls (referred to herein as the "narrow sides" of the tube) joining the broad sides. Collectively, the broad and narrow sides of the tube define an interior space through which fluid can flow in any state, including without limitation gas, liquid, vapor, and any combination thereof at any pressure or vacuum (including no pressure or vacuum).

Another feature of the flat tubes employed in many embodiments of the present invention (described in greater detail below) is the relatively low thickness of material used to construct at least some of the walls of the flat tubes. In some embodiments, the wall material of the flat tubes has a thickness of no greater than about 0.20 mm (0.007874 in). In still other embodiments, the wall material of the flat tubes has a thickness of no greater than about 0.15 mm (0.0059055 in). The relatively low wall material thickness can result in good thermal properties of the flat tubes. Also, by utilizing one or more of the flat tube features described herein, the inventors have discovered that a number of different flat tubes having various characteristics adapted for a variety of applications can be constructed using significantly reduced material while retaining strength and heat exchange properties of heavier conventional flat tubes. In some embodiments, a wall material thickness of the flat tubes of no less than about 0.050 mm (i.e., no less than about 0.0019685 in) provides good strength and corrosion resistance performance, while in other embodiments, a wall material thickness of the flat tubes of no less than about 0.030 mm (0.00118 in) can be used.

As explained in greater detail below, the heat exchanger tubes and other portions of heat exchangers described herein can be manufactured using a number of manufacturing techniques and processes and can include corrosion protection features, such as, for example, those techniques and processes

described below and illustrated in FIGS. 92-95. A number of manufacturing processes and techniques and the corrosion protection features referenced hereinafter are particularly advantageous when applied to heat exchanger tubes and portions of heat exchangers having significantly reduced material thickness. In addition, such techniques, processes, and corrosion protection features provide significant advantages relating to the overall performance of flat tubes and heat exchangers made from such material.

Many embodiments of the present invention utilize flat tubes having major and minor diameters as described above (indicated as D and d, respectively, in the following text) that provide unique advantages in many applications. When used, for example, in conjunction with the material thicknesses just described and in conjunction with other features of the flat tubes described in the various embodiments below, flat tubes adapted for a number of different applications can be produced. Also, the ability to produce flat tubes having some of the major and minor dimensions D, d described herein is facilitated by the use of the relatively thin wall material described above.

For example, in some embodiments of the present invention, the major dimension D (i.e., the width of the flat tube in the illustrated embodiments herein) is no less than about 10 mm (0.39370 in). Also, this major dimension D is no greater than about 300 mm (3.9370 in) in some embodiments. In other embodiments, the major dimension D is no greater than about 200 mm (7.87402 in). As another example, in some embodiments of the present invention, the minor diameter d (i.e., the thickness of the flat tube in the illustrated embodiments herein) is no less than about 0.7 mm (0.02756 in). Also, this minor dimension d is no greater than about 10 mm (0.39370 in) in some embodiments. In other embodiments, the minor dimension d is greater than about 7 mm (0.2756 in). Such major and minor dimensions apply to any of the flat tube embodiments described and/or illustrated herein.

In many embodiments, the major and minor dimensions D, d are dependent at least in part upon the applications of the flat tubes. For example, in condenser applications, the major diameter D of the flat tube is no less than about 10 mm (0.39370 in) in some embodiments. Also, a major diameter D of the flat tube in some condenser applications is no greater than about 20 mm (0.78740 in). The minor diameter d for some condenser applications of the flat tube is no less than about 1.0 mm (0.039370 in). Also, a minor diameter d of the flat tube in some condenser applications is no greater than about 2.0 mm (0.078740 in). As another example, in radiator applications, the major diameter D of the flat tube is no less than about 10 mm (0.39370 in) in some embodiments. Also, a major diameter D of the flat tube in some radiator applications is no greater than about 200 mm (7.8740 in). The minor diameter d for some radiator applications of the flat tube is no less than about 0.7 mm (0.027559 in). Also, a minor diameter d of the flat tube in some radiator applications is no greater than about 2.0 mm (0.078740 in). As another example, in charge air cooler applications, the major diameter D of the flat tube is no less than about 20 mm (0.78740 in) in some embodiments. Also, a major diameter D of the flat tube in some charge air cooler applications is no greater than about 160 mm (6.29921 in). The minor diameter d for some charge air cooler applications of the flat tube is no less than about 4.0 mm (0.15748 in). Also, a minor diameter d of the flat tube in some charge air cooler applications is no greater than about 10.0 mm (0.39370 in).

Still other applications of flat tubes according to any of the embodiments described herein include oil coolers. In oil cooler applications, the major diameter D of the flat tube is no

less than about 10 mm (0.49470 in) in some embodiments. Also, a major diameter D of the flat tube in some oil cooler applications is no greater than about 150 mm (5.90551 in). The minor diameter d for some oil cooler applications of the flat tube is no less than about 1.5 mm (0.05906 in). Also, a minor diameter d of the flat tube in some oil cooler applications is no greater than about 4.0 mm (0.15748 in). As yet another example, in evaporator applications, the major diameter D of the flat tube is no less than about 30 mm (1.18110 in) in some embodiments. Also, a major diameter D of the flat tube in some evaporator applications is no greater than about 75 mm (2.95276 in). The minor diameter d for some evaporator applications of the flat tube is no less than about 1.0 mm (0.039370 in). Also, a minor diameter d of the flat tube in some evaporator applications is no greater than about 2.0 mm (0.078740 in). It should be noted that further applications (e.g., gas coolers) of the flat tubes described and/or illustrated herein are possible, and fall within the spirit and scope of the present invention.

Many of the flat tube embodiments described below and illustrated herein are constructed of a metal including aluminum (e.g., aluminum or an aluminum alloy). However, a number of other types of metals can instead be utilized while still providing the strength, heat transfer, and manufacturability characteristics desired for use in heat exchange devices. In some embodiments, the metal material of the flat tubes is provided with a brazing material coating. The brazing material coating can have a number of different possible thicknesses, and in some embodiments is no less than about 10% of the thickness of the flat tube wall material to produce good performance results. Also, in some embodiments, the brazing material coating is no greater than about 30% of the thickness of the flat tube wall material. In other embodiments where the flat tubes are to be soldered rather than brazed, the metal material of the flat tubes can be provided with a soldering material coating. A number of different securing operations (brazing, welding, soldering, and the like) can be used to construct any of the various flat tubes and heat exchanger assemblies described and/or illustrated herein. However, portions of the following text refer only to brazing, although it should be understood that other types of securing operations (including welding and soldering) are equally applicable in such embodiments.

A number of the flat tube features mentioned above relate to the construction of the tube walls using relatively thin sheet material. In some embodiments, significant enhancements to thin-walled flat tube performance is generated by providing either or both of the stable narrow sides with folds that are substantially perpendicular or substantially parallel to the broad sides of the flat tube. Such folds can be formed, for example, by rolling or folding adjacent longitudinal edges of sheet metal upon or into one another. In those embodiments of the present invention in which either or both narrow sides of the flat tube have folds that are substantially parallel to the broad sides of the flat tube, such folds can have the same or different lengths with respect to one another. As will also be described in greater detail below, folds at the narrow sides of a flat tube can be shaped to hook or inter-engage with one another—a feature that can be helpful in the manufacture of the flat tube and/or of a heat exchanger employing the flat tube.

In many of the following embodiments, flat tubes are disclosed having folded narrow sides and also having other folds and/or deformations formed within the flat tubes. In a manufacturing process, the folds that form the narrow sides can be produced subsequent to the manufacture of such other folds and/or deformations, although other manufacturing alterna-

tives are possible. Also, it should be noted that the folds formed within the flat tube can be multiple folds, and in some embodiments are arranged tightly against or abutting one another.

A first embodiment of a flat tube **10** according to the present invention is illustrated in FIGS. 1-5. The flat tube **10** is constructed of two portions of sheet material **12**, **14** shaped to define internal flow channels **16**. Each of the two portions **12**, **14** can be formed from one endless strip of material or coil passed through a manufacturing line having a material cutting device (e.g., laser, saw, water jet, blade, and the like) for producing two strips that are then joined together as will be described below. Alternatively, the two portions **12**, **14** can be formed from two endless strips of material or coils passed through a manufacturing line. In either case, the manufacturing line can be equipped with roll sets (as illustrated by way of example below) or other sheet forming elements to shape the strips as will be described in greater detail below. As used herein and in the appended claims, the term "endless" does not literally mean that the element or product referred to has a limitless supply. Rather, the term "endless" means only that the element or product is received from a much greater supply of continuous material in some upstream bulk form, such as in supply coils of material.

Although the portions **12**, **14** can have thicknesses falling within any of the ranges described above, the portions **12**, **14** in the illustrated embodiment of FIGS. 1-5 have a wall thickness of about 0.10 mm (0.0039369 in) by way of example. In some embodiments, the portions **12**, **14** include material formed of aluminum or an aluminum alloy. However, other portion materials (described above) can instead be utilized in other embodiments. Either or both sides of the portions **12**, **14** can be coated with a brazing material coating, such as a layer of brazing coating that is about 10-30% of the portion thickness.

As shown in FIG. 2, the flat tube **10** of the illustrated embodiment defines a small diameter d . Using the wall thicknesses described earlier, the inventors have discovered that a small diameter d of at least about 0.8 mm (0.031496 in) provides good performance results in many applications. Also using the wall thicknesses described earlier, the inventors have discovered that a small diameter d of no greater than about 2.0 mm (0.07874 in) provides good performance results in many applications. However, in some embodiments, a maximum small tube diameter d of no greater than about 1.5 mm (0.059055 in) is used. As shown in FIG. 1, the flat tube **10** of the illustrated embodiment also defines a large diameter D . Using the wall thicknesses described earlier, the inventors have discovered that a large diameter D of at least about 40 mm (1.5748 in) provides good performance results in many applications. Also using the wall thicknesses described earlier, the inventors have discovered that a large diameter D of no greater than about 45 mm (1.7717 in) provides good performance results in many applications. However, it is possible for the flat tube **10** to define a large diameter D and a small diameter d with other dimensions, including those described above with reference to all of the flat tubes disclosed herein, based at least in part upon the manufacturing processes used, the intended application of the tubes, and/or the use of thicker or thinner wall materials. For this purpose, the portions **12**, **14** of particular widths can be made available, and the installations of the manufacturing line can be adjusted according to the desired diameters D and d .

The flat tube **10** in the illustrated embodiment of FIGS. 1-5 includes a first narrow side **18**, a second narrow side **20**, a first broad side **22**, and a second broad side **24**. The first broad side

22 and the second broad side **24** correspond to the portions **12** and **14**, respectively. With particular reference to FIG. 1, the first broad side **22** and the second broad side **24** define a number of folds **28**. The folds **28** extend from the first broad side **22** and the second broad side **24** to define four flow channels **16**. In other embodiments, the flat tube **10** can include more or fewer flow channels **16** defined between the folds **28**. Although the folds **28** can run in an uninterrupted and continuous manner along the entire length of the flat tube **10** to isolate adjacent flow channels **16** from one another. However, in other embodiments, the folds **28** can be interrupted or breached in one or more locations along their length in order to permit flow between flow channels **16**. Regardless of whether the folds **28** are uninterrupted or interrupted, the folds **28** can strengthen the flat tube **10** against compression, and can strengthen the flat tube **10** against expansion in those embodiments in which the distal ends of the folds **28** are attached to a broad side **24** of the flat tube **10** (e.g., by brazing or in any other suitable manner). The folds **28** can also serve a rigidifying function in order to resist bending of the flat tube **10**.

With reference now to FIGS. 1 and 2, the first broad side **22** and the second broad side **24** also define a number of protrusions **26**. In other embodiments, neither side **22**, **24** has such protrusions **26**. The illustrated protrusions are generally convex bumps extending into the flow channels **16** of the flat tube **10**, and can have any footprint desired, such as a round footprint, square, triangular or other polygonal footprint, any elongated footprint (e.g., elongated ribs running along any desired length of the flow channels, running transverse to the flow channels, and the like), irregular footprints, or footprints of any other shape (e.g., serpentine, zig-zag, chevron, and the like). Where used, the protrusions **26** can function to induce or sustain turbulence in the flat tube **10**, thereby increasing heat transfer in such locations. Also, like the folds **28** described above, the protrusions **26** can serve a rigidifying function to help stiffen the broad sides **22**, **24** of the flat tube **10**. The protrusions **26** can be located in any pattern or patternless manner in the flat tube **10**, and in some embodiments are located only in particular areas of the flow channels **16** to produce desired flow and heat transfer effects.

FIG. 3 schematically illustrates a set of exemplary manufacturing steps that can be used to form a flat tube **10** such as that illustrated in FIGS. 1, 2, 4, and 5. Starting with a first portion of material **12** defining a width W and a second portion of material **14** defining a smaller width w , a desired number of folds **28** are formed, and will help to define the flow channels **16**. The folds **28** in the illustrated embodiment are formed on both portions **12**, **14**. In other embodiments, folds **28** are formed in only one of the portions **12**, **14**. Similarly, the protrusions **26** in the illustrated embodiment are formed on both portions **12**, **14**, although in other embodiments the protrusions **26** are formed in only one of the portions **12**, **14**. The folds **28** and protrusions **26** are located between the longitudinal edges of the material defining the portions **12**, **14** (e.g., the longitudinal edges of the sheet metal defining the portions **12**, **14**).

The width W of the first portion **12** and the width w of the second portion **14** in the illustrated embodiment of FIGS. 1-5 are reduced during the course of forming the folds **28** and protrusions **26**. It is to be understood that other deformations can be included in the exemplary manufacturing steps of FIG. 3 to generate other features of the flat tube **10**, as desired. With continued reference to the manufacturing example of FIG. 3, an additional set of folds **30** is formed at each of the longitudinal edges of the portions **12**, **14** subsequent to forming the necessary folds **28** and protrusions **26**, thereby defining the

11

narrow sides **18** and **20** of the flat tube **10**. In other embodiments, either or both of the additional sets of folds **30** can be produced prior to or at the same time as the folds **28** and protrusions **26**, although the process illustrated in FIG. 3 can provide significant manufacturing advantages based upon manufacturing line setup and operation. As best illustrated in FIGS. 4 and 5, the additional folds **30** of each of the portions **12**, **14** engage one another to define the first narrow side **18** and the second narrow side **20** of the tube, respectively. By virtue of this engagement between the longitudinal edges of the portions **12**, **14** of the two-piece flat tube **10**, the portions **12**, **14** can be held together even before the brazing or other securing operations on the portions **12**, **14**. More specifically, FIGS. 4 and 5 illustrate the folds **30** of one portion **14** defining a larger length than the folds **30** of the other portion **12**. Thus, the folds **30** of one portion **12** can fold around the folds **14** of the other portion, as is also shown in FIG. 2.

As the illustrated embodiment of FIGS. 1-5 shows, in some embodiments, one of the portions **12** is sufficiently long to wrap around and thereby receive the longitudinal edge of the other portion **14** (e.g., whereby the longitudinal edge of one portion **14** is nested in the folded longitudinal edge of the other portion **12**). In other embodiments, one of the portions **12** is instead only sufficiently long to overlap the longitudinal edges of the other portion **14**. However, the embodiments described above in connection with FIGS. 1-5 can provide significant advantages relating to the assembly and manufacture of the flat tube **10**, including the retention of the portions **12**, **14** as described above, and a greater degree of narrow side reinforcement and strength based upon the greater thickness of material at the narrow sides **18**, **20**. In the illustrated embodiment of FIGS. 1-5, both narrow sides **18**, **20** are provided with the same folded structure best show in FIGS. 2-5. However, in other embodiments, only one of the two narrow sides **18**, **20** of the flat tube **10** has any of the folded structures described above. In such embodiments, the connection between the two portions **12**, **14** at the other narrow side **20**, **18** can be made in any other manner desired.

FIGS. 6-11 illustrate alternative constructions of flat tubes according to additional embodiments of the present invention. These embodiments employ much of the same structure and have many of the same properties as the embodiments of the flat tube described above in connection with FIGS. 1-5. Accordingly, the following description focuses primarily upon the structure and features that are different than the embodiments described above in connection with FIGS. 1-5. Reference should be made to the description above in connection with FIGS. 1-5 for additional information regarding the structure and features, and possible alternatives to the structure and features of the flat tubes illustrated in FIGS. 6-11 and described below. Structure and features of the embodiments shown in FIGS. 6-11 that correspond to structure and features of the embodiments of FIGS. 1-5 are designated hereinafter in respective hundreds series of reference numbers (e.g., **112**, **212**, **312**, and the like).

FIGS. 6-11 illustrate other constructions of a narrow side **118**, **218**, **318**, **418**, **518**, **618** and/or **120**, **220**, **320**, **420**, **520**, **620**. For ease of description, reference herein is made only to one of the narrow sides **118**, **218**, **318**, **418**, **518**, **618** of each tube **110**, **210**, **310**, **410**, **510**, **610**, it being understood that the other narrow side **120**, **220**, **320**, **420**, **520**, **620** can have the same or different structure, as desired. The narrow sides **118**, **218**, **318**, **418**, **518**, **618** shown in FIGS. 6-11 can be manufactured in steps similar to those described above with reference to FIG. 3. Furthermore, each of the narrow sides **118**, **218**, **318**, **418**, **518**, **618** shown in FIGS. 6-11 provide strength and/or stability to the tube **110**, **210**, **310**, **410**, **510**, **610**

12

compared with conventional flat tube designs, taking into consideration the relatively small thickness of the material used to construct the tube walls in some embodiments: about 0.050-0.15 mm (0.0019685-0.0059055 in) in some embodiments as described above, and about 0.030-0.15 mm (0.00118-0.0059055 in) in other embodiments, and other material thickness ranges described herein.

The narrow sides **118**, **218**, **418** of the flat tubes **110**, **210**, **310** shown in FIGS. 6, 7, and 9 can be formed by folding or rolling together adjacent longitudinal edges of the two tube portions **112**, **212**, **412** and **114**, **214**, **414**, thereby defining a number of folds **130**, **230**, **330**, **430**, **530**, **630**. It should be noted that forms are referred to herein and in the appended claims as "folds" regardless of whether they were made by rolling or folding operations, and regardless of whether the resulting shapes are rotund (e.g., FIG. 6), stacked (e.g., FIGS. 7-9) or angular (e.g., FIGS. 10 and 11). With continued reference to FIGS. 6, 7, and 9, each narrow side **118**, **218**, **418** provides unique heat transfer, strength, and stability characteristics, and can be formed using different techniques. At least a portion of the folded or rolled longitudinal edges (and in the case of the narrow sides **218**, **418** illustrated in FIGS. 7 and 9, the majority of the folded or rolled longitudinal edges) are formed to be approximately perpendicular to the broad sides **122**, **222**, **422** and **124**, **224**, **424** of the flat tube **110**, **210**, **410**.

With reference to the narrow sides **518**, **618** of the flat tubes **510**, **610** shown in FIGS. 10 and 11, the longitudinal edges of portions **512**, **612** and **514**, **614** can also be formed by folding or rolling together the adjacent longitudinal edges of the two tube portions **512**, **612** and **514**, **614**. Once again, each of the narrow sides **518**, **618** of the flat tubes **510**, **610** provides unique heat transfer, strength, and stability characteristics, and can be formed using different techniques. In both cases, the longitudinal edges of the portions **512**, **612** and **514**, **614** can be folded upon itself to define a serpentine edge of the flat tube **510**, **610**. Although the folds **530**, **630** of this serpentine edge can abut one another with little or no space between adjacent folds **530**, **630**, in some embodiments (see FIGS. 10 and 11), a space exists between adjacent portions of each fold. The heat transfer, firmness, strength, and/or size of the flat tubes **510**, **610** can be selected as desired, based upon the orientation of the folds **530**, **630** in such embodiments (e.g., substantially perpendicular to the broad sides **522**, **622** and **524**, **624**, or at a significant angle less than 90 degrees with respect to the broad sides **522**, **622** and **524**, **624**) and the space between adjacent portions of each fold **530**, **630**.

The illustrated embodiment of FIG. 8 provides an example of how at least a portion of the folds **330** (and in some cases, the majority of the folds **330**) of the narrow side **318** can be parallel or substantially parallel to the broad sides **322**, **324** of the flat tube **310**. Some or all of these folds **330** can lie against one another for improved heat transfer therebetween. In some embodiments, the folds **330** of the narrow side **318** can be substantially the same length **L**, such as in cases where a particular flow channel shape is desired adjacent the narrow side **318** of the flat tube **310**. However, in other embodiments (such as that shown in FIG. 8), at least some of the narrow side folds **330** parallel to the broad sides **322**, **324** have a different length than others. For example, the differently-sized folds can define a generally concave (FIG. 8) or convex side of an adjacent flow channel **316**, such as for defining a desired flow channel shape adjacent the narrow side **318**. With reference to the illustrated embodiment of FIG. 8, the length **L** of each fold **330** decreases from the outside of the flat tube **310** towards the inside of the flat tube **310** (i.e., the first fold **330** that lies against the broad side **322** has a greater length **L** than the

13

subsequent fold 330, and the last fold 330 that lies against the other broad side 324 has a greater length L than the previous fold 330). In these embodiments, such shapes of the narrow side 318 can help avoid sudden temperature transitions across the flat tube 310, an issue that can otherwise contribute to tube failure in many applications. As another example, differently-sized folds can define a wedge-shaped narrow side 318, which can provide a non-symmetrical heat transfer bridge across the distance between the broad sides 322, 324. Still other shapes of the narrow side 318 defined by differently-sized folds 330 parallel to the broad sides 322, 324 are possible, and fall within the spirit and scope of the present invention.

In those embodiments in which folds 330 of the narrow side 318 are parallel or substantially parallel to the broad sides 322, 324 of the two-piece flat tube 310, the folds 330 formed of the first portion 312 can be hooked together or inter-engaged with the folds 330 formed of the second portion 314 (see FIG. 8, for example). As a result, the formed flat tube 310 can be held together before brazing or other securing operations on the portions 312, 314, which can facilitate assembly of the flat tubes 310 into banks and/or of heat exchangers having such flat tubes 310, as it is further explained below. It will be appreciated that similar advantages exist in the other narrow side embodiments described above with reference to FIGS. 6, 7, and 9-11.

In those embodiments of the present invention in which either or both narrow sides 18, 118, 218, 318, 418, 518, 618, 20, 120, 220, 320, 420, 520, 620 have folds 30, 130, 230, 330, 430, 530, 630 as described above, such folds 30, 130, 230, 330, 430, 530, 630 can generally provide increased stability to the narrow sides 18, 118, 218, 318, 418, 518, 618, 20, 120, 220, 320, 420, 520, 620 despite the relatively small wall thickness of the flat tube 10, 110, 210, 310, 410, 510, 610 mentioned earlier. A greater number of folds 30, 130, 230, 330, 430, 530, 630 at the narrow sides 18, 118, 218, 318, 418, 518, 618, 20, 120, 220, 320, 420, 520, 620 can also provide better protection for the flat tube 10, 110, 210, 310, 410, 510, 610 against damage due to high internal pressures, impact from objects, and corrosion, for example. This can be of great importance when using such flat tubes 10, 110, 210, 310, 410, 510, 610 in heat exchangers for motor vehicles.

Although not required in the flat tube embodiments described above, the first and/or second portions 12, 112, 212, 312, 412, 512, 612 and 14, 114, 214, 314, 414, 514, 614 can have one or more folds 28 located between the narrow sides 18, 118, 218, 318, 418, 518, 618 and 20, 120, 220, 320, 420, 520, 620 of the flat tube 10, 110, 210, 310, 410, 510, 610. In this regard, the description of such folds 28 in the illustrated embodiment of FIGS. 1-5 is applicable equally to the other embodiments described above. For ease of description, further information regarding these folds 28 will now be made with reference to the illustrated embodiments of FIGS. 12 and 13 using the reference numbers of the embodiment of FIGS. 1-5.

In some embodiments, the inventors have discovered that locations of the internal folds 28 can be selected to define flow channels 16 of varying size to enable different fluid and/or flow characteristics (e.g., flow rates and/or directions, pressures, multiple fluid types, and the like) in different locations of the same flat tube 10, and to enable different manners of heat transfer in the different locations. With reference to the illustrated embodiment of FIG. 12, the width or distance "a" between interior folds 28 is defined substantially parallel to the first and second broad sides 22, 24 of the flat tube 10, and varies based upon the desired degree of resistance to temperature change along the width of the flat tube 10.

14

In some embodiments, such as that shown in FIG. 12, the distance "a" between interior folds 28 can become larger starting from either or both narrow sides 18 and 20 of the flat tube 10 toward the center of the flat tube 10. Accordingly, in some embodiments, the distance "a" increases from interior fold 28 to interior fold 28, starting from one narrow side 18, 20 in the direction of the middle of the flat tube 10, and subsequently decreases again in the direction of the other narrow side 20, 18. In such embodiments, the cross-sectional area of the individual flow channels 16 formed by the interior folds 28 increases and decreases, respectively. In some embodiments, the distance "a" begins at either or both narrow sides 18, 20 at a magnitude of about 0.5 mm (0.019685 in) and increments to a few millimeters.

For example, in such cases, a flat tube 10 with a width of approximately 42 mm (approx. 1.6634 in) can include a large number of interior folds 28 and flow channels 16. It is conceivable that a flat tube 10 can include relatively wider flow channels 16 substantially adjacent either or both narrow sides 18, 20, with narrower flow channels 16 near the center of the flat tube 10. Also, although the flow channels 16 in many embodiments have widths "a" of the sizes described above, such widths can be significantly larger in other embodiments, including ranges of at least 1 cm (0.3937 in).

In some embodiments, the flat tube 10 can include interior folds 28 immediately adjacent one another, wherein such interior folds are abutting or in intimate contact with one another immediately following formation of the interior folds 28 or after brazing or other securing operations on the portions 12, 14. For example, multiple interior folds 28 can be arranged tightly against one another. In any of these cases, two or more interior folds 28 can define a set 32 of interior folds 28. The flat tube 10 can have any number of such sets 32 of interior folds 28, such as those shown in FIG. 13, either alone or in conjunction with any number of single folds 28. Each set 32 of interior folds 28 shown in FIG. 13 includes three individual interior folds 28. However, in other embodiments, two interior folds 28 can be sufficient to form a set 32, and/or four or more interior folds 28 can form a set 32. Accordingly, the number of interior folds 28 that form the set 32 is freely selectable based upon the intended application of the flat tube 10 and other factors. In this regard, either or both portions 12, 14 of the flat tube 10 can have fold sets 32 having any number of interior folds 28 and any combination of sets 32 with different numbers of interior folds 28.

The single interior folds 28 and/or sets 32 of interior folds 38 can all be located on the same portion 12 or 14, or on both portions 12, 14 of the flat tube 10 in any arrangement desired. For example, multiple sets 32 of interior folds 28 can be symmetrically arranged about a central location of the flat tube 10 (such as the arrangement of interior fold sets 32 shown in FIG. 13), wherein corresponding sets 32 on opposite sides of the central location extend from the same portion 12, 14 or from a different portion 12, 14 (e.g., FIG. 13). Also, in some embodiments, one or more single interior folds 28 and/or one or more sets 32 of interior folds 28 on one portion 12, 14 of the flat tube 10 can be nested within the interior folds 28 of a set 32 on the opposite portion 14, 12 of the flat tube 10.

Sets 32 of interior folds 28 as described above can be utilized to provide flat tubes 10 with higher resistance to pressure and greater load-bearing capacity, and can also be used to vary the cross-sectional shape of flow channels 16. It should be noted that the features described above regarding varying flat tubes 10 with varying flow channel widths apply equally to embodiments in which sets 32 of interior folds 28 are utilized. Also, in those embodiments in which the flat tube 10 is formed with a brazing process, the interior folds 28 on

15

one broad side **22, 24** (whether in single form or in sets **32**) can form brazed joints with the other broad side **24, 22**, thus improving bonding within the flat tube **10**.

FIGS. **14** and **15** illustrate two additional constructions of flat tubes according to additional embodiments of the present invention. These embodiments employ much of the same structure and have many of the same properties as the embodiments of the flat tube described above in connection with FIGS. **1-13**. Accordingly, the following description focuses primarily upon the structure and features that are different than the embodiments described above in connection with FIGS. **1-13**. Reference should be made to the description above in connection with FIGS. **1-13** for additional information regarding the structure and features, and possible alternatives to the structure and features of the flat tubes illustrated in FIGS. **14** and **15** and described below. Structure and features of the embodiments shown in FIGS. **14** and **15** that correspond to structure and features of the embodiments of FIGS. **1-13** are designated hereinafter in the 700 and 800 series of reference numbers, respectively.

The flat tubes **10, 110, 210, 310, 410, 510, 610** illustrated in FIGS. **1-13** above each have internal walls defined by interior folds **28** of the first and/or second portions **12, 112, 212, 312, 412, 512, 612, 14, 114, 214, 314, 414, 514, 614**. In any of these embodiments, however, these walls at least partially defining the flow channels **16, 116, 216, 316, 416, 516, 616** can be defined by a separate portion of material that is connected to either or both of the first and second portions **12, 112, 212, 312, 412, 512, 612, 14, 114, 214, 314, 414, 514, 614** in the manufacture of the flat tubes **10, 110, 210, 310, 410, 510, 610**. Although different from the flat tubes **10, 110, 210, 310, 410, 510, 610** described above in this manner, such alternative flat tubes can have any of the construction features described above in connection with FIGS. **1-13** (e.g., exterior wall thicknesses and materials, tube diameters, interior wall shapes, locations, spacings, and sets, and narrow side constructions).

For example, the flat tubes **710, 810** shown in FIGS. **14** and **15** are each constructed using two portions **712, 714** and **812, 814**, respectively between and which is located an insert **734, 834** defined by another portion of material. In both cases, the insert **734, 834** has a corrugated shape, whereby corrugations of the insert **734, 834** can form flow channels **716, 816** in the flat tube **710, 810**. Either or both narrow sides **718, 720** and **818, 820** of the flat tube **710, 810** (only one of which is shown in each of FIGS. **14** and **15**) can incorporate a portion of the insert **734, 834** by commonly folding the edges of the first and second portions **712, 714** and **812, 814** with the edges of the insert **734, 834**. For example, in some embodiments, the flat tube **710** has serpentine narrow sides **718, 720** as shown in FIG. **14**, wherein the edges of the insert **734** are folded with and into the longitudinal sides of the first and second portions **712, 714**. In other embodiments, the narrow sides **818, 820** of the flat tube **810** are folded tightly against one another as shown in FIG. **15**, wherein the edges of the insert **834** are again folded with and into the longitudinal sides of the first and second portions **812, 814**. In yet other embodiments, the longitudinal edges of an insert can be rolled into those of the first and second portions in any of the narrow side structures shown in FIGS. **6-10**.

The embodiments of the present invention described above each utilize two separate pieces of material to define the first and second portions **12, 112, 212, 312, 412, 512, 612, 712, 812, and 14, 114, 214, 314, 414, 514, 614, 714, 814** of the flat tubes **10, 110, 210, 310, 410, 510, 610, 710, 810**. Although such tube constructions have unique advantages, including some portion-to-portion inter-engagement features and

16

manufacturing advantages, flat tubes according to the present invention can also be formed of one part, such as by a single or undivided endless sheet metal strip. By deforming the single part, free longitudinal edges of the single part can be brought together and joined by brazing, welding, or other securing operations. In other words, some embodiments of the flat tubes according to the present invention can be formed from one part (e.g., sheet metal strip) while still defining two stable narrow sides. Various embodiments of such one-part flat tubes are described in detail below. With the exception of those features of the one-part flat tubes described below that are inconsistent or incompatible with the tube features described above with reference to the two-piece embodiments of FIGS. **1-15**, the one-part flat tubes described below can have any of the construction features described above in connection with FIGS. **1-15** (e.g., exterior wall thicknesses and materials, tube diameters, interior wall shapes, locations, spacings, and sets, and narrow side constructions).

The one-piece tubes described below can have improved thermal properties over conventional flat tubes based at least in part upon the use of the relatively thin tube wall material (described above) that can be employed. Additionally, assembly of the flat tubes within a heat exchanger can also be simplified.

Like the two-piece flat tubes described above, folds formed at the narrow sides of the one-piece flat tubes described below can be substantially perpendicular or substantially parallel to the broad sides. For example, a first narrow side of the flat tube can be formed of a continuous portion of a single sheet of metal and can include a set of multiple folds. In some embodiments, these folds can define multiple lengths (e.g., similar to those described above in connection with FIG. **8**), which can help avoid the formation of cracks due to thermal fatigue. A second narrow side of the flat tube can be formed by the free longitudinal edges of the single sheet of metal, and can also have multiple folds. In spite of the sheet metal thickness of 0.05-0.15 mm (0.0019685-0.00591 in) in some embodiments, and 0.03-0.15 mm (0.00118-0.00591 in) in other embodiments, the longitudinal edges of the single piece of material forming the second narrow side can be coupled by brazing, welding, or other securing operations. Also like the two-piece flat tubes described above, either or both broad sides of the one-piece flat tubes can include interior folds and other deformations (e.g., inwardly-directed beads, ribs, or other protrusions that need not reach across the interior of the flat tubes). The interior folds can form flow channels within the flat tube, and can be arranged in any of the manners described above with reference to the two-piece flat tubes. By way of example only, the interior folds can be in sets, can be at particular spacings that may or may not vary across the width of the flat tube, and can increase in the direction from either or both narrow sides toward the middle of the flat tube. As a result of such interior folds and interior fold arrangements, the capability of the one-piece flat tube to resist high temperature change loads can be significantly improved.

Examples of one-piece flat tubes having some of these features are illustrated in FIGS. **16-24**, each of which have first and second portions **912, 914, 1012, 1014, 1112, 1114, 1212, 1214, 1312, 1314, 1412, 1414, 1512, 1514, 1612, 1614, 1712, 1714** formed of a common piece of material folded to the shapes illustrated. Although other materials and material thicknesses can be employed as described in greater detail above in connection with the two-piece flat tubes, the illustrated first and second portions **912, 914, 1012, 1014, 1112, 1114, 1212, 1214, 1312, 1314, 1412, 1414, 1512, 1514, 1612, 1614, 1712, 1714** are formed of aluminum or aluminum alloy sheet metal strip having a material thickness of about 0.10

17

mm (0.003937 in). Any of the flat tubes **910**, **1010**, **1110**, **1210**, **1310**, **1410**, **1510**, **1610**, **1710** can have a brazing material coating on either or both sides, wherein each layer of the brazing material coating can have a thickness of about 10-20% of the thickness of the sheet metal strip.

Using the wall thicknesses described earlier, the inventors have discovered that a small diameter *d* of at least 0.8 mm (0.031496 in) for the illustrated flat tubes **910**, **1010**, **1110**, **1210**, **1310**, **1410**, **1510**, **1610**, **1710** provides good performance results in many applications. Also using the wall thicknesses described earlier, the inventors have discovered that a small diameter *d* of no greater than about 2.0 mm (0.07874 in) for the illustrated flat tubes **910**, **1010**, **1110**, **1210**, **1310**, **1410**, **1510**, **1610**, **1710** provides good performance results in many applications. However, in some embodiments, a maximum small diameter *d* of no greater than about 1.5 mm (0.059055 in) for the illustrated flat tubes **910**, **1010**, **1110**, **1210**, **1310**, **1410**, **1510**, **1610**, **1710** is used. Moreover, a large diameter *D* for any of the illustrated flat tubes **910**, **1010**, **1110**, **1210**, **1310**, **1410**, **1510**, **1610**, **1710** is usually freely selectable within certain manufacturing limits. In some embodiments, one example, the large diameter *D* is approximately 50 mm (1.969 in). However, one-piece flat tubes **910**, **1010**, **1110**, **1210**, **1310**, **1410**, **1510**, **1610**, **1710** having larger or smaller diameters *D*, *d* (including those described above with regard to all flat tube embodiments disclosed herein) and the wall thicknesses described earlier can also be manufactured, in which cases the original width *W* of the material (see FIG. 16, for example) used to form the flat tubes **910**, **1010**, **1110**, **1210**, **1310**, **1410**, **1510**, **1610**, **1710** is made available at the manufacturing line.

As mentioned above, the various types of narrow side folds and interior folds described in connection with the embodiments of FIGS. 1-15 can be employed in the one-piece tubes described herein. In some one-piece tube embodiments, such as those shown in FIGS. 19-24, either or both narrow sides **1218**, **1220**, **1318**, **1320**, **1418**, **1420**, **1518**, **1520**, **1618**, **1620**, **1718**, **1720** of the flat tube **910**, **1010**, **1110**, **1210**, **1310**, **1410**, **1510**, **1610**, **1710** can include multiple folds **1230**, **1330**, **1430**, **1530**, **1630**, **1730**, which can provide relatively more stable and strong narrow tube sides **1218**, **1220**, **1318**, **1320**, **1418**, **1420**, **1518**, **1520**, **1618**, **1620**, **1718**, **1720**. As a result, the relatively more stable narrow sides **1218**, **1220**, **1318**, **1320**, **1418**, **1420**, **1518**, **1520**, **1618**, **1620**, **1718**, **1720** can provide sufficient protection of the flat tubes **910**, **1010**, **1110**, **1210**, **1310**, **1410**, **1510**, **1610**, **1710** against damage due to temperature and/or pressure fatigue, impact from objects, and corrosion, thereby providing better performance when used in a heat exchanger for motor vehicles (for example).

With reference now to FIG. 16, an example of the manner in which a one-piece tube **910** can be manufactured is shown. In particular, FIG. 16 illustrates at least part of a manufacturing process to form a one-piece flat tube **910**. Single and/or multiple folds are made in a sheet of starting material, and will at least partially define interior folds **928** of the flat tube **910**, and flow channels **916** within the flat tube **910**. In some embodiments, the sheet of starting material is an endless sheet, such as that fed from a coil of material upstream of the manufacturing elements used to produce the folds. At the same or different time, additional folds are created that will at least partially define folds at a narrow side **920** of the flat tube **910**. For example, a set **932** of multiple folds **930** is produced at or near the center of the one-piece metal strip illustrated in FIG. 16 to define a narrow side **920** by folding the strip in the direction shown by arrow substantially adjacent the set **932** of multiple folds **930**. As a result of this fold indicated by arrow, first and second broad sides **912**, **914** of the flat tube **910** are

18

defined. The other narrow side **918** and the folds **930** of the other narrow side **918** can take any of the forms shown in FIGS. 19-23 or those described and/or illustrated above in connection with the narrow sides of the two-piece flat tubes **10**, **110**, **210**, **310**, **410**, **510**, **610**, **710**, **810**. FIGS. 17 and 18 illustrate features of alternate one-piece flat tube constructions (narrow sides not shown) that can be employed. More specifically, FIG. 17 provides an example of how single interior folds **1028** and sets **1032** of multiple interior folds **1028** on either or both broad sides **1022**, **1024** can be utilized in the same one-piece flat tube **1010** to define flow channels **1016** of the same or different size. FIG. 18 provides an example of how a number of single interior folds **1128** can be made at particular locations on either or both broad sides **1122**, **1124** to define flow channels **1116** of varying cross-sectional size, such as gradually increasing cross-sectional sizes in a direction along the width of the one-piece flat tube **1110**.

FIGS. 19-24 show still further examples of one-piece flat tubes **1210**, **1310**, **1410**, **1510**, **1610** according to other embodiments of the preset invention. Like the one-piece tube embodiments illustrated in FIGS. 16-18, each of the one-piece flat tubes **1210**, **1310**, **1410**, **1510**, **1610** illustrated in FIGS. 19-24 have interior folds **1228**, **1328**, **1428**, **1528**, **1628**, **1728** arranged individually and/or in sets to define flow channels **1216**, **1316**, **1416**, **1516**, **1616**, **1716**. In some cases, the arrangement of individual interior folds **1228**, **1328**, **1428**, **1528**, **1628**, **1728** and/or sets **1232**, **1332**, **1532** of such folds **1228**, **1328**, **1528** is determined based upon one or more factors (e.g., single or multiple fluids through the tubes **1210**, **1310**, **1410**, **1510**, **1610**, **1710** anticipated temperatures, thermal stresses, and thermal cycling to which the different portions of the tube width and/or length will be exposed, internal fluid pressures, and the like).

With particular reference first to FIG. 19, multiple interior folds **1228** near the center of the flat tube **1210** define a material thickness of four times that of the unfolded tube material (i.e., two single folds **1228** arranged tightly or immediately adjacent one another, such as in an abutting fashion). The one-piece flat tube **1210** illustrated in FIG. 19 has two such sets **1232** of interior folds **1228**, each of which is formed in a different broad side **1222**, **1224** of the flat tube **1210**. In the embodiment of FIG. 20, four sets **1332** of multiple interior folds **1328** each define a material thickness of six times that of the unfolded tube material (i.e., three single folds **1328** arranged tightly or immediately adjacent one another, such as in an abutting fashion). The interior folds **1328** in the embodiment of FIG. 20 are positioned to define flow channels **1316** of varying size, unlike those of FIG. 19, which have substantially the same size. It will be appreciated that any other number of interior fold sets **1232**, **1332** can be provided on either or both broad sides **1222**, **1224**, **1322**, **1324** of the one-piece flat tubes **1210**, **1310** illustrated in FIGS. 19 and 20, with or without additional individual interior folds **1228**, **1328** (i.e., interior folds **1228**, **1328** not in sets **1232**, **1332** as also shown in FIGS. 19 and 20).

The embodiments of FIGS. 21, 22, and 23 provide examples of one-piece flat tubes **1410**, **1510**, **1610** in which only single folds **1428**, **1528**, **1628** are used to form the flow channels **1416**, **1516**, **1616**. By way of example, the interior folds **1428**, **1528** of the one-piece flat tubes **1410**, **1510** illustrated in FIGS. 21 and 22 are positioned to define flow channels **1416**, **1516** of varying size (increasing toward the center of each flat tube **1410**, **1510**, **1610**), unlike those of FIG. 23, which have substantially the same size, with the exception of a slightly larger flow channel **1616** immediately adjacent either or both narrow sides **1618**, **1620**. It should be noted that the interior folds **1228**, **1328**, **1428**, **1528**, **1628**, **1728** of any

of the one-piece flat tubes **1210**, **1310**, **1410**, **1510**, **1610**, **1710** illustrated in FIGS. **19-24** can be positioned to define flow channels **1216**, **1316**, **1416**, **1516**, **1616**, **1716** of the same or different size, and that the widths of the flow channels **1216**, **1316**, **1416**, **1516**, **1616**, **1716** can increase or decrease toward the center of the flat tubes **1210**, **1310**, **1410**, **1510**, **1610**, **1710** gradually in the same direction across the majority or all of the tube width, or in any other manner desired. Also, other constructions of the flat tubes **1210**, **1310**, **1410**, **1510**, **1610**, **1710** can include different numbers of single folds **1228**, **1328**, **1428**, **1528**, **1628**, **1728** and sets of multiple interior folds **1228**, **1328**, **1428**, **1528**, **1628**, **1728** as desired.

With continued reference to the one-piece flat tube embodiments illustrated in FIGS. **19-24**, each flat tube **1210**, **1310**, **1410**, **1510**, **1610**, **1710** has one narrow side **1220**, **1320**, **1420**, **1520**, **1620**, **1720** defined by a continuous folded portion of the sheet of material used to construct the flat tube **1210**, **1310**, **1410**, **1510**, **1610**, **1710**, and an opposite narrow side **1218**, **1318**, **1418**, **1518**, **1618**, **1718** where two free longitudinal edges of the sheet of material are brought together and folded to close the flat tube **1210**, **1310**, **1410**, **1510**, **1610**, **1710**. This opposite narrow side **1218**, **1318**, **1418**, **1518**, **1618**, **1718** and the folds **1230**, **1330**, **1430**, **1530**, **1630**, **1730** of the opposite narrow side **1218**, **1318**, **1418**, **1518**, **1618**, **1718** can take any of the forms shown in FIGS. **19-24** or those described and/or illustrated above in connection with the narrow sides of the two-piece flat tubes **10**, **110**, **210**, **310**, **410**, **510**, **610**, **710**, **810**.

With regard to the narrow side **1220**, **1320**, **1420**, **1520**, **1620**, **1720** formed by the continuous folded portion as described above, this narrow side can take any of the forms shown in FIGS. **19-24**. However, this same narrow side **1220**, **1320**, **1420**, **1520**, **1620**, **1720** can also take any of the shapes described and/or illustrated above in connection with the narrow sides of the two-piece flat tubes **10**, **110**, **210**, **310**, **410**, **510**, **610**, **710**, **810**, in which cases the terminal ends of the first and second portions **12**, **14**, **112**, **114**, **212**, **214**, **312**, **314**, **412**, **414**, **512**, **514**, **612**, **614**, **712**, **714**, **812**, **814** at the narrow sides **18**, **118**, **218**, **318**, **418**, **518**, **618**, **718** of the flat tubes **10**, **110**, **210**, **310**, **410**, **510**, **610**, **710**, **810** would be joined as part of the same continuous piece of sheet material. Accordingly, the unique benefits of each narrow side form described above in connection with FIGS. **1-11**, **14**, and **15** can exist for either or both narrow sides **1218**, **1220**, **1318**, **1320**, **1418**, **1420**, **1518**, **1520**, **1618**, **1620**, **1720** of the embodiments illustrated in FIGS. **19-24**.

With particular reference to the illustrated embodiment of FIG. **19**, the one-piece flat tube **1210** illustrated therein has narrow sides **1218**, **1220** formed with folds **1230** that are arranged substantially perpendicularly to the broad sides **1222**, **1224** of the flat tube **1210**. The multiple folds **1230** forming the narrow sides **1218**, **1220** are differentiated from each other in that the folds **1230** forming the second narrow side **1220** are formed from a continuous portion of the one-piece strip of material used to create the flat tube **1210**, while the folds **1230** forming the first narrow side **1218** are formed from the two longitudinal edges of the one-piece strip of material. In other embodiments, however, the flat tube **1210** can instead have first and second narrow sides **1218**, **1220** with folds **1230** that are substantially parallel to the broad sides **1222**, **1224** of the flat tube **1210**.

The one-piece flat tube **1310** illustrated in FIG. **20** also has a second narrow side **1320** with multiple folds **1330** substantially perpendicular to the broad sides **1322**, **1324** of the flat tube **1310**, whereas the first narrow side **1318** has multiple folds **1330** arranged substantially parallel to the broad sides **1322**, **1324** of the flat tube **1310**. In other embodiments,

however, the flat tube **1310** can instead have a first narrow side **1318** with folds **1330** that are substantially perpendicular to the broad sides **1322**, **1324**, and a second narrow side **1320** with folds **1330** that are substantially parallel to the broad sides **1322**, **1324**.

The one-piece flat tube **1410** illustrated in FIG. **21** has first and second narrow sides **1418**, **1420** with multiple folds **1430** that are substantially parallel to the broad sides **1422**, **1424** of the flat tube **1410**. In other embodiments, the multiple folds **1430** of either or both narrow sides **1418**, **1420** are instead substantially perpendicular to the broad sides **1422**, **1424** of the flat tube **1410**. Although each of the multiple folds **1430** at both of the narrow sides **1418**, **1420** illustrated in FIG. **21** are substantially the same length, those of either or both narrow sides **1418**, **1420** can instead be of different lengths *L* (e.g., see FIGS. **22** and **23**). In such embodiments, the varying lengths of the narrow sides **1518**, **1520**, **1618** can take any of the forms described above in connection with the embodiment of FIG. **8**, and can therefore produce any of the benefits also described therein. With reference to the embodiments of FIGS. **22** and **23**, the illustrated arrangement of varying-length folds **1530**, **1630** of the narrow sides **1518**, **1520**, **1630** (i.e., shorter folds **1530**, **1630** flanked by longer folds **1530**, **1630**), can be generally effective in supporting temperature change loads. Also, sudden transitions in pressure from the narrow sides **1518**, **1520**, **1618** to the broad sides **1522**, **1524**, **1622**, **1624** can be avoided with this arrangement. Additionally, as with the other one-piece flat tube embodiments described herein, one or more sets of multiple interior folds **1528** (such as the single set shown in FIG. **22**) and/or a relatively high number of flow channels **1616** (such as those shown in FIG. **23**) can be utilized to help support temperature change loads and to help withstand sudden transitions in pressure. Yet another measure aimed to improve temperature change load resistance is varying the distance “*a*” between folds to define increasingly wider flow channels **1516** toward the center of the flat tube **1510**.

FIG. **24** shows an example of the manner in which any of the narrow side constructions shown in the two-piece flat tube embodiments of FIGS. **6-11**, **14**, and **15** can be employed in the narrow side of a one-piece flat tube having a continuous sheet of material as mentioned above. The narrow side **1718** shown in FIG. **24** is similar in many respects to that of FIG. **11** described above, with the exception of abutting adjacent folds **1730** and a single continuous sheet of material defining the folds **1730** rather than two overlapping sheets of material (or two overlapping portions of the same sheet of material). In this particular example, the distances “*a*” between the folds **1730** and the first interior fold **1728**, and between the other interior folds **1728** are relatively small, and can range in some embodiments from 0.5 mm (0.019685 in) to 2 mm (0.07874 in) or more—even as large as 1 cm (2.54 in). Furthermore, in some embodiments, this flat tube **1610** has a width of about 42 mm (0.16535 in) allowing for multiple folds **1728** and flow channels **1716**.

Flat tubes according to the some embodiments of the present invention can include an internal insert that reinforces at least one of the narrow sides of the flat tube while also potentially performing one or more other functions (e.g., reinforcing the broad sides of the tube, defining multiple flow channels in fluid communication or not in fluid communication with one another, defining flow turbulators, and the like). The insert can be defined by a separate portion of material that is connected to the sheet or sheets of material defining the exterior tube walls in the manufacture of the flat tubes, and can be used as a complement to or instead of interior folds as described in a number of the embodiments above. Examples

of inserts have already been provided in connection with the illustrated embodiments of FIGS. 14 and 15.

Although inserts can be employed with one-piece flat tubes according to some embodiments of the present invention (described in greater detail below), a number of unique advantages are gained by the use of inserts in two-piece flat tubes. In some embodiments, such advantages are gained in the use of inserts in two-piece flat tubes constructed of sheet material having a relatively small thickness. In some embodiments, the wall material of the flat tubes has a thickness of no greater than about 0.20 mm (0.007874 in). However, in other embodiments, the inventors have discovered that a wall material of the flat tubes having a thickness of no greater than about 0.15 mm (0.0059055 in) provides significant performance results relating to the overall performance of the heat exchanger, manufacturability, and possible wall constructions (as disclosed herein) that are not possible using thicker wall materials. The relatively small wall material thickness can result in good thermal properties of the two-piece flat tubes having inserts. In some embodiments, a wall material thickness of such flat tubes of no less than about 0.050 mm (i.e., no less than about 0.0019685 in) provides good strength and corrosion resistance performance, whereas in other embodiments, a wall material thickness of such flat tubes of no less than about 0.030 mm (i.e., no less than about 0.00118 in) can be used. Also, the two-piece flat tubes having inserts described below can have dimensions similar to the two-piece flat tubes described above in connection with FIGS. 1-15.

As explained in greater detail below, the heat exchanger tubes and other portions of heat exchangers described herein can be manufactured using a number of manufacturing techniques and processes and can include corrosion protection features, such as, for example, those techniques and processes described below and illustrated in FIGS. 92-95. A number of manufacturing processes and techniques and the corrosion protection features referenced hereinafter are particularly advantageous when applied to heat exchanger tubes and portions of heat exchangers having significantly reduced material thickness. In addition, such techniques, processes, and corrosion protection features provide significant advantages relating to the overall performance of flat tubes and heat exchangers made from such material.

FIGS. 25-34 illustrate various two-piece flat tubes 1810, 1810A, 1910, 2010, 2110, 2210, 2310, 2410, 2510, 2610, 2710, 2810, 2910, 3010, 3110, 3210 each including a first portion 1812, 1812A, 1912, 2012, 2112, 2212, 2312, 2412, 2512, 2612, 2712, 2812, 2912, 3012, 3112, 3212, a second portion 1814, 1814A, 1914, 2014, 2114, 2214, 2314, 2414, 2514, 2614, 2714, 2814, 2914, 3014, 3114, 3214, and an insert 1834, 1834A, 1934, 2034, 2134, 2234, 2334, 2434, 2534, 2634, 2734, 2834, 2934, 3034, 3134, 3234, all of which can be constructed of sheets of material, such as strips of metal or other material. For ease of description, the following description refers only to the illustrated embodiment of FIGS. 25 and 26, it being understood that the following description applies equally to all of the embodiments illustrated in FIGS. 25-34 (barring inconsistent or incompatible description).

In some embodiments of the two-piece flat tube 1810 illustrated in FIGS. 25 and 26, the first and second portions 1812, 1814 and the insert 1834 can be constructed of a material (e.g., aluminum, aluminum alloy, or other material described herein) having a relatively low sheet thicknesses. For example, the inventors have discovered that a material thickness for these elements of no greater than about 0.15 mm (0.0098425 in) provides good performance results in many applications. In some embodiments, the material for these elements also has a thickness no less than about 0.03 mm

(0.0011811 in). In many embodiments, it is preferred that a relatively smaller sheet thickness be used for the insert 1834 than for the first and second portions 1812, 1814 of the two-piece flat tube 1810. In spite of the relatively small sheet thicknesses, the narrow sides 1818, 1820 of the two-piece flat tube 1810 can have relatively improved stability, particularly when used in conjunction with features of the two-piece flat tube 1710 described below.

In the illustrated embodiment of FIGS. 25 and 26, each broad side 1822, 1824 of the flat tube 1810 is formed of a separate portion of material (such as a separate strip). The portions of material overlap in two locations to define two longitudinal seams 1844, 1846. These longitudinal seams 1844, 1846 of the two-piece flat tube 1810 extend from respective narrow sides 1818, 1820 of the flat tube 1810 to opposite broad sides 1822, 1824, in contrast to other illustrated embodiments (e.g., see FIG. 27 described in greater detail below), where the longitudinal seams extend from respective narrow sides of the flat tube to the same broad side of the flat tube. In the illustrated embodiment of FIGS. 25 and 26, the longitudinal seams 1844, 1846 are both located at and extend from a respective narrow side 1818, 1820 of the flat tube 1810 into the broad sides 1822, 1824 of the flat tube 1810. More specifically, the longitudinal seams 1844, 1846, namely those portions of the flat tube 1810 at which the sheet material of the flat tube 1810 is overlapped, extend about at least part of (and in some embodiments a majority or all of) the narrow sides 1818, 1820, and lie partially in a corresponding broad side 1822, 1824 of the flat tube 1810. The width of the seam 1844, 1846 can be determined according to desirable manufacturing purposes.

In some embodiments, the longitudinal seams 1844, 1846 of the flat tube 1810 present a flush or substantially flush outer surface of the flat tube 1810 (e.g., provide a substantially flat broad side 1822, 1824 of the flat tube 1810). For this purpose, that longitudinal edge of each longitudinal seam 1844, 1846 that is overlapped by the other longitudinal edge can be recessed by forming the overlapped longitudinal edge with an offset 1848, 1850. Accordingly, the longitudinal edge of one tube portion 1812, 1814 can be wrapped by and receive the corresponding longitudinal edge of the other tube portion 1814, 1812 in a recess 1848, 1850 to define the longitudinal seam 1844, 1846. Thus, for both seams 1844, 1846, the underlying longitudinal edge of the two overlapping tube portions 1812, 1814 can terminate within the interior of the flat tube 1810, and can be free prior to brazing, welding, or other securing techniques. As a result of this construction, flat tubes 1810 can be produced with precise desired widths (even without cutting or other machining operations, in some embodiments) despite the fact that looser tolerances are maintained for the widths of starting material for the individual tube portions 1812, 1814, since the overlapped longitudinal seams 1844, 1846 permit relative lateral positioning of the first and second tube portions 1812, 1814 in an assembled state. In particular, in some embodiments, a terminal longitudinal edge 1854, 1856 of each tube portion 1812, 1814 does not abut the other tube portion 1812, 1814, thereby permitting such adjustment.

The use of overlapping longitudinal seams such as those illustrated in the embodiment of FIGS. 25 and 26 provides significant reinforcement of the flat tube 1810 at the first and second narrow sides 1818, 1820—a feature that can be highly important in many applications where thermal stresses, temperature change loads, and failures due to pressure loading and debris impact are common in conventional flat tubes. In some embodiments, further reinforcement of the first and/or second narrow sides 1818, 1820 is provided by one or more

folds of the first and/or second tube portions **1812**, **1814** at the narrow sides **1818**, **1820** (i.e., at the longitudinal edges of such portions **1812**, **1814**). Generally, folding the longitudinal edges of the first and/or second tube portions **1812**, **1814** can increase the strength of the flat tube **1810** and resistance of the flat tube **1810** to damage. In those embodiments in which a narrow side **1818**, **1820** is defined at least in part by overlapping longitudinal edges of the first and second tube portions **1812**, **1814** (one extending about, receiving, or encompassing the other), either one or both of the overlapped longitudinal edges (e.g., the encompassed and encompassing edges) can be folded back to increase the thickness of that longitudinal edge at the narrow side **1818**, **1820**.

For example, it is envisioned that either or both overlapping longitudinal edges of tube portions **1812**, **1814** at either or both narrow sides **1818**, **1820** can include folds adjacent the corresponding gradation **1858**, **1860** (described in greater detail below). For example, in some embodiments, the combined thickness of the first and second tube portions **1812**, **1814** can be about 0.25 mm (0.0098425 in) or smaller in some embodiments, with either or both overlapping longitudinal edges having at least one fold to thicken the narrow side **1818**, **1820**, and with the material thickness of the insert **1834** being about 0.10 mm (0.003937 in) or less. In such embodiments, the thickness of the first and second tube portions **1818**, **1820** can each be in the range of 0.05-0.15 mm (0.0019685-0.0059055 in), and can be in the range of 0.03-0.15 mm (0.0019685-0.0059055 in) in other embodiments.

It should also be noted that the overlapped longitudinal seam construction of the two-piece flat tube illustrated in FIGS. **25** and **26** can be employed in flat tube embodiments having no internal insert. For example, such a longitudinal seam construction can be employed in two-piece flat tubes having interior folds such as those described above in connection with the embodiments of FIGS. **113** and **16-24**, or in other two-piece flat tubes.

Although not required, in many embodiments the tube portions (e.g., tube portions **1812**, **1814** in FIGS. **25** and **26**) have substantially the same shape, and can even be identical. When assembled as described above, the tube portions **1812**, **1814** are arranged with their longitudinal edges reversed with respect to one another. For example, one longitudinal edge of one of the two tube portions **1812**, **1814** includes a gradation **1856**, **1860** defining a recess **48**, **50** as described above, followed by a portion defining an arc **1862**, **1864**, while a corresponding overlapping longitudinal edge of the other tube portion **1814**, **1812** includes a portion with a larger arc **1866**, **1868** receiving the smaller arc **1862**, **1864**. Accordingly, in the illustrated embodiment of FIGS. **25** and **26**, one smaller arc portion **1862**, **1864** and one larger arc portion **1866**, **1868** form one of the narrow sides **1818**, **1820** as part of the manufacturing process of the two-piece flat tube **1810**. It is to be understood that the term "arc" as used herein and in the appended claims is not restricted to a half round form. Moreover, the term "arc" as used herein and in the appended claims is inclusive of any suitable geometry for forming the narrow sides **1818**, **1820**, which can include square, triangular, or other open polygonal shapes, wave shapes, and other formations.

By employing tube portions that are substantially the same shape or identical, fewer part types (and in some cases, a single part type) can be used to construct the two-piece flat tube **1810**, resulting in lower inventory, simpler assembly, and significant cost reductions.

The internal insert **1834** partially illustrated in FIG. **25** and fully illustrated in FIG. **26** is formed of a third piece of material, and generally includes two longitudinal edges **1838**,

1840, either or both of which can lie substantially within a respective narrow side **1818**, **1820** of the flat tube **1810**. In some embodiments, the longitudinal edges **1838**, **1840** are formed with a shape for this purpose, such that the longitudinal edges **1838**, **1840** can be received within the interior shape of the narrow sides **1818**, **1820**. Also in some embodiments, at least part of either or both longitudinal edges **1838**, **1840** have a shape corresponding to that of the narrow sides **1818**, **1820**. For example, either or both longitudinal edges **1838**, **1840** can be formed into the shape of a loop **1842** such that at least part of the loop **1842** matches the shape of the corresponding narrow side **1818**, **1820** of the flat tube **1810**. In some embodiments, this shape correspondence can result in a reinforcement of the flat tube at the narrow sides **1818**, **1820**. Further reinforcement can be obtained by connecting either or both longitudinal edges **1838**, **1840** with the narrow sides **1818**, **1820**, such as by brazing, welding, or in any other suitable manner.

With reference to FIG. **26**, which illustrates the manner in which the two-piece flat tube **1810** can be assembled, the internal insert **1834** is shown received within arc portions **1862**, **1864** of the first and second tube portions **1812**, **1814** as the first and second tube portions **1812**, **1814** are brought together during assembly. More particularly, the longitudinal edges **1838**, **1840** of the internal insert **1834** are supported by the arc portions **1862**, **1864** of the first and second tube portions **1812**, **1814**, and will be within the later-defined narrow sides **1818**, **1820** of the tube **1810** to reinforce the narrow sides **1818**, **1820** once assembly is complete. The resulting two-piece flat tube **1810** has narrow sides **1818**, **1820** with a double wall thickness due to the overlapping longitudinal seams **1844**, **1846** extending over and beyond the narrow sides **1818**, **1820**, and can also have further thickness defined by the that of the nested longitudinal edges **1838**, **1840** of the internal insert **1834**. In some cases, for example, the two-piece flat tube **1810** includes first and second tube portions **1812**, **1814** collectively defining a wall thickness of about 0.20 mm (0.007874 in) to help prevent corrosion or deterioration, and/or to provide resistance against debris impact, and pressure and temperature change loads.

As explained in greater detail below, the heat exchanger tubes and other portions of heat exchangers described herein can be manufactured using a number of manufacturing techniques and processes and can include corrosion protection features, such as, for example, those techniques and processes described below and illustrated in FIGS. **92-95**. A number of manufacturing processes and techniques and the corrosion protection features referenced hereinafter are particularly advantageous when applied to heat exchanger tubes and portions of heat exchangers having significantly reduced material thickness. In addition, such techniques, processes, and corrosion protection features provide significant advantages relating to the overall performance of flat tubes and heat exchangers made from such material.

The internal insert **1834** illustrated in the embodiment of FIGS. **25** and **26** has a number of corrugations **1852** across the width of the flat tube **1810**. These corrugations **1852** can be joined to the interior of the broad sides **1822**, **1824** of the first and second tube portions **1812**, **1814** to form flow channels **1816** running in the longitudinal direction of the flat tube **1810**. By using this arrangement, flow channels **1816** can be defined in the flat tube **1810** in a cost-effective manner, while also simplifying the manufacturing process of the two-piece flat tube **1810**. In spite of the low wall thickness of the internal insert **1834** (which can be the same or smaller than the above-described thicknesses of the first and second tube portions **1812**, **1814** described above), the flow channels **1816** formed

25

within the two-piece flat tube **1810** can provide improved stability to internal pressure of the flat tube **1810**.

The hydraulic diameter of the flow channels **1816** can be determined by appropriate design of the corrugations **1852** described above. In some embodiments, for example, the hydraulic diameter of the flow channels **1816** is relatively small considering that the small diameter *d* of the two-piece flat tube **1810** can be about 0.8 mm (0.031496 in), and that the number of corrugations **1852** can be relatively large.

In some embodiments, at least some of the corrugations **1852** are shaped to have one corrugation flank perpendicular or substantially perpendicular to the broad sides **1822**, **1824** of the two-piece flat tube **1810**, and an adjacent corrugation flank inclined with respect to the broad sides **1822**, **1824** (e.g., see the center corrugations **1852** illustrated in FIG. 25, for example). In other embodiments, at least some of the corrugations **1852** are shaped to each have both corrugation flanks at a substantial incline with respect to the broad sides **1822**, **1824** (e.g., see the left corrugations **1852** illustrated in FIG. 25, for example). In still other embodiments, at least some of the corrugations **1852** are shaped to have both flanks perpendicular or substantially perpendicular to the broad sides **1822**, **1824** of the two-piece flat tube **1810**.

An example of such an embodiment is shown in FIG. 33, which illustrates a two-piece flat tube **2210** that is substantially the same as that of FIGS. 25 and 26 with the exception of the insert shape. Like the embodiment of FIGS. 25 and 26, the insert **2234** illustrated in FIG. 33 reinforces the narrow sides **2218**, **2220** by longitudinal edges **2238**, **2240** of the insert **2234** lining at least a portion of the inner surface of each tube portion **2212**, **2214** at the narrow sides **2218**, **2220**. In other embodiments, only one of the longitudinal edges **2238**, **2240** of the insert **2234** extends into a corresponding narrow side **2218**, **2220**. It should be noted that the two-piece flat tube assembly shown in FIG. 33 can have any of the same features described herein in connection with the embodiment of FIGS. 25 and 26. In still other embodiments, at least some of the corrugations **1852** can define a curved wave pattern (e.g., sinusoidal), or any other profiled surface in which the corrugations are identical or different across the width of the two-piece flat tube **1810**.

In some embodiments, the insert **1834** defines a number of flow channels **1816** having the same shape and size across the width of the two-piece flat tube **1810**. In other embodiments, the insert **1834** can be shaped so that the shape and/or size of the flow channels **1816** varies across the width of the two-piece flat tube **1810** (e.g., by using an insert **1834** with different types of corrugations **1852** at different locations across the width of the two-piece flat tube **1810**). An example of this is shown in FIG. 25, where both types of corrugations described above for the illustrated insert **1834** are used. In other embodiments, any number of different corrugation shapes and sizes can be used across the width of the two-piece flat tube **1810**. This variance across the width can provide significant advantages over conventional flat tubes by adapting different portions of the flat tube **1810** for different flow and/or environmental conditions (e.g., different fluids or flow directions through different sections of the same flat tube **1810**, different internal or external flow rates, temperatures, and/or pressures at different locations across the width of the flat tube **1810**, and the like).

The internal insert **1834** illustrated in FIGS. 25 and 26 are formed of a single piece of material. However, it should be noted that in other embodiments, the internal insert **1834** can instead be formed of more than one part (in which case the flat tube assembly illustrated in FIGS. 25 and 26 can include four or more parts).

26

With continued reference to the embodiment of FIGS. 25 and 26, the thickness of at least one narrow side **1818**, **1820** generally corresponds to the sum of the thicknesses of the two broad sides **1822**, **1824** (and, more precisely, of the longitudinal edges of the first and second portions **1812**, **1814**) and the insert **1834**. For example, the combined thickness of the overlapping longitudinal edges of the first and second portions **1812**, **1814** and the insert **1834** can be about 0.25 mm (0.0098425 in) or less in some embodiments. It should also be noted that in some cases, each of the first and second tube portions **1812**, **1814** and the insert **1834** can have substantially the same thickness (in any of the thickness ranges described above), such as in cases in which the same sheet material is used to construct all three pieces. In such cases, either or both narrow sides **1818**, **1820** can be defined by a thickness that is approximately three times the material thickness of either first and second tube portion **1812**, **1814** (i.e., when a loop **1842** on either or both longitudinal edges of the insert **1834** is received within a corresponding narrow side **1818**, **1820** to increase the thickness thereof as described above). In some embodiments, either or both longitudinal edges of the insert **1834** can be folded over upon itself and then provided with a loop **1842** or otherwise shaped to at least partially correspond to the interior of the narrow side **1818**, **1820**, thereby reinforcing the wall material of the first and second portions **1812**, **1814** at the narrow sides **1818**, **1820**. Any number of such longitudinal edge folds for the insert **1834** can be made to achieve a desired thickness, reinforcement, and stability of the narrow sides **1818**, **1820**.

In some embodiments having a narrow side reinforcing insert **1834** as described above, each of the first and second tube portions **1812**, **1814** can have a thickness of less than 0.15 mm (0.00591 in), and the thickness of the insert **1834** can be no greater than about 0.10 mm (0.003937 in), such as a flat tube **1810** in which the first and second tube portions **1812**, **1814** each have a thickness of about 0.12 mm (0.0047224 in), and in which the insert **1834** has a thickness of no greater than about 0.10 mm (0.003937 in). In other embodiments, the thickness of each of the first and second tube portions **1812**, **1814** and the insert **1834** can be no less than about 0.05 mm (0.0019685 in) and no greater than about 0.15 mm (0.0059055 in) to provide a relatively cost-effective heat exchanger with good heat transfer and strength properties. In other embodiments, the thickness of each of the first and second tube portions **1812**, **1814** and the insert **1834** can be no less than about 0.03 mm (0.00118 in) in other embodiments.

At least one of the first and second portions **1812**, **1814** and the insert **1834** can have a brazing material coating on either or both sides thereof in order to permit such parts of the illustrated tube assembly to be joined by brazing. In the illustrated embodiment of FIGS. 25 and 26 by way of example only, the first and second portions **1812**, **1814** and the insert **1834** of the flat tube **1810** is manufactured from aluminum or aluminum alloy sheeting made available in endless strips of material coated on at least one side with brazing material.

As shown in FIGS. 25 and 26, the two-piece flat tube **1810** of the illustrated embodiment defines a small diameter *d* and a large diameter *D*. Using the wall thicknesses described earlier, the inventors have discovered that a small diameter *d* of at least about 0.7 mm (0.027559 in) provides good performance results in many applications, such as in radiators. Also using the wall thicknesses described earlier, the inventors have discovered that a small diameter *d* of no greater than about 1.5 mm (approx. 0.059055 in) provides good performance results in many applications, such as in radiators. In the case of charge air coolers and other applications, the

inventors have discovered that the small diameter d can be larger than about 1 cm (0.3937 in) to provide good performance results. Although such small diameter dimensions can be employed in various embodiments, any of the small diameter dimensions described above with regard to all of the flat tube embodiments disclosed herein can be used. The large diameter D of the two-piece flat tube **1810** illustrated in FIGS. **25** and **26** can have any size desired (including those also described above with regard to all of the flat tube embodiments disclosed herein), based at least in part upon the width of the starting material used to construct the flat tube **1810**.

As mentioned above, in some embodiments, either or both longitudinal edges of the insert **1834** can be provided with any number of folds to achieve a desired thickness for increased reinforcement and stability of the first and second portions **1812**, **1814** at the narrow sides **1818**, **1820**. An example of such an embodiment is illustrated in FIGS. **28** and **29**. The two-piece flat tube **1910** illustrated in FIGS. **28** and **29** is substantially the same as that of FIGS. **25** and **26** with the exception of the insert shape.

FIG. **28** illustrates the flat tube **1910** with a narrow side **1918** at a stage in which the large arc portion **1968** has not been completely manufactured. In other words, one longitudinal edge of the second tube portion **1914** is not wrapped around the already-formed smaller arc portion **1962** formed by a corresponding longitudinal edge of the first tube portion **1912**. This longitudinal edge of the second tube portion **1914** is displaced or moved around the smaller arc portion **1962** to complete the narrow side **1918**. As a consequence, the resulting longitudinal seam **1944** lies in one broad side **1922**, with another of the two longitudinal seams **1946** lying in the other broad side **1924**. These longitudinal seams **1944**, **1946** are located at the narrow sides **1918**, **1920** of the two-piece flat tube **1910** as described in earlier embodiments.

In the illustrated embodiment of FIGS. **28** and **29**, the longitudinal edges **1938**, **1940** of the insert **1934** have been folded several times, as best shown in FIG. **29**. The longitudinal edges **1938** with these folds **1970** are received within the narrow sides **1918**, **1920** of the two-piece flat tube **1910**, and can provide significant reinforcement to the overlapped longitudinal edges of the first and second tube portions **1912**, **1914** at the narrow sides **1918**, **1920**. In other embodiments, only one of the longitudinal edges **1938**, **1940** of the insert **1934** has such folds **1970**.

The number of folds **1970** of the longitudinal edges **1938**, **1940** can depend at least in part upon the dimensions of the flat tube **1910**. In some embodiments by way of example only, the two-piece flat tube **1910** has a small diameter d of about 1.0 mm (0.03937 in), the first and second tube portions **1912**, **1914** each have a material thickness of about 0.15 mm (0.0059055 in), and the material thickness of the insert **1934** is about 0.05 mm (0.0019685 in), wherein about 10 folds are created on each longitudinal edge **1938**, **1940** of the insert **1934**. Although these multiple folds **1970** can have varying lengths, in some embodiments the maximum length L of these folds is about 1.0 mm (0.03937 in). Also, these multiple folds **1970** can run in a direction parallel or substantially parallel to the broad sides **1922**, **1924** of the two-piece flat tube **1910** in some embodiments (see FIGS. **28** and **29**), and can run in other directions (e.g., perpendicular to the broad sides **1922**, **1924**) in other embodiments. It is to be understood that the wall thicknesses of the first and second tube portions **1912**, **1914** and the insert **1934** can vary, as can the distances d and L based upon desired specifications of the flat tube **1910**.

It should be noted that the two-piece flat tube assembly shown in FIGS. **28** and **29** can have any of the same features described herein in connection with the embodiment of FIGS. **25** and **26**.

FIG. **27** illustrates a two-piece flat tube according to an additional embodiment of the present invention. This embodiment employs much of the same structure and has many of the same properties as the embodiments of the flat tube described above in connection with FIGS. **25**, **26**, **28**, **29** and **33**. Accordingly, the following description focuses primarily upon the structure and features that are different than the embodiments described above in connection with FIGS. **25**, **26**, **28**, **29** and **33**. Reference should be made to the description above in connection with FIGS. **25**, **26**, **28**, **29** and **33** for additional information regarding the structure and features, and possible alternatives to the structure and features of the two-piece flat tube illustrated in FIG. **27** and described below. Structure and features of the embodiment shown in FIG. **27** that correspond to structure and features of the embodiments of FIGS. **25**, **26**, **28**, **29** and **33** are designated hereinafter in the 1800 series of reference numbers.

Like the embodiments of the present invention described in connection with FIGS. **25** and **26**, the tube assembly illustrated in FIG. **27** has first and second portions **1812A**, **1814A** and an insert **1834A**. The opposite longitudinal edges **1838A**, **1840A** of the insert **1834A** line the inner surfaces of both pairs of overlapped longitudinal sides of the first and second tube portions **1812A**, **1814A**, thereby reinforcing the narrow sides **1818A**, **1820A** of the flat tube **1810A**.

The two-piece flat tube **1810A** illustrated in FIG. **27** is an example of the manner in which both longitudinal seams **1844A**, **1846A** joining the first and second portions **1812A**, **1814A** of the flat tube **1810A** can extend to and on the same broad side **1822A**, **1824A** of the flat tube **1810A**. In the illustrated embodiment of FIG. **27**, both longitudinal seams **1844A**, **1846A** extend to and on the second broad side **1824A** of the flat tube **1810A**. Alternatively, the longitudinal seams **1844A**, **1846A** can be formed in the first broad side **1822A**, if desired. In the illustrated embodiment, the second broad side **1824A** defined primarily by the second tube portion **1814A** is capable of absorbing relatively loose tolerances (i.e., is capable of tolerance equalization) at its opposite longitudinal edges. However, in some embodiments, the first broad side **1822A** defined primarily by the first tube portion **1812A** does not have the same capability or degree of capability, because each of its longitudinal edges can lie against or immediately adjacent a gradation **1858A**, **1860A** of the second tube portion **1814A**.

With continued reference to the illustrated embodiment of FIG. **27**, the longitudinal seams **1844A**, **1846A** extend from respective narrow sides **1818A**, **1820A** in directions toward the center of the flat tube **1810A**. A significant portion of each longitudinal seam **1818A**, **1820A** (i.e., the gradations **1858A**, **1860A**), however, lies in the same broad side **1824A**, where the cross-sectional length e of each gradation **1858A**, **1860A** measured to the distal edge of the narrow sides **1818A**, **1820A** can be determined according to the desired manufacturing process used to produce the tube portions **1812A**, **1814A**. In the illustrated embodiment of FIG. **27**, the small diameter d of the two-piece flat tube **1810A** is in the range of about 0.7-1.5 mm (0.027559-0.059055 in) when the two-piece flat tube **1810A** is incorporated in a radiator, although other small diameters d are possible for the same and different applications, including the diameters d described above in connection with the embodiment of FIGS. **25** and **26**, and those described above in connection with the small and large diameters for all of the flat tubes of the present invention disclosed

herein. For example, in other constructions, the small diameter *d* of the flat tube **1810A** can be greater than 1.0 cm (approx. 0.3937 in).

As with the other two-piece flat tube embodiments described herein, it is envisioned that a manufacturing process of the flat tube **1910** includes at least partially forming the two tube portions **1912**, **1914** from respective strips of sheet material, and then joining the at least partially formed strips to one another as described herein by the end of the manufacturing line.

FIGS. **30-32** illustrate two additional constructions of flat tubes according to additional embodiments of the present invention. These embodiments employ much of the same structure and have many of the same properties as the embodiments of the flat tube described above in connection with FIGS. **25-29** and **33**. Accordingly, the following description focuses primarily upon the structure and features that are different than the embodiments described above in connection with FIGS. **25-29** and **33**. Reference should be made to the description above in connection with FIGS. **25-29** and **33** for additional information regarding the structure and features, and possible alternatives to the structure and features of the flat tubes illustrated in FIGS. **30-32** and described below. Structure and features of the embodiments shown in FIGS. **30-31**, and **32** that correspond to structure and features of the embodiments of FIGS. **25-29** and **33** are designated hereinafter in the 2000 and 2100 series of reference numbers, respectively.

The tube assembly illustrated in FIGS. **30** and **31** is substantially the same as that shown in FIG. **27**, with the exception of the insert shape. In particular, the tube assembly illustrated in FIGS. **30** and **31** is an example of the manner in which the insert **2034** can take different shapes to define flow channels **2016** of different shapes and sizes. By way of example, the illustrated internal insert **2034** includes corrugations **2052** having flanks that are substantially perpendicular to the broad sides **2022**, **2024** of the two-piece flat tube **2010**. The corrugation flanks are joined together by substantially flat sections that can be brazed, welded, or secured in any other suitable manner to the inside surfaces of the broad sides **2022**, **2024** of the first and second tube portions **2012**, **2014**. This particular construction of lamellae or internal insert **2034** is generally referred to as flat-top lamellae.

With continued reference to FIGS. **30** and **31**, the longitudinal edges **2038**, **2042** of the internal insert **2034** are shaped to each include a gradation **2072** and a connecting arc **2074** received substantially within and reinforcing the narrow sides **2018**, **2020** of the two-piece flat tube **2010**. In other embodiments, only one of the longitudinal edges **2038**, **2042** is provided with these features.

In any of the insert embodiments described herein, the inserts can be provided with features that increase or sustain turbulence within the flow channels defined at least in part by the inserts. An example of such features is shown in FIGS. **32A** and **32B**. In this embodiment, the flanks and flat sections of the corrugations **2152** in the illustrated insert **2134** include winglets **2176** (not shown in FIG. **32A**) positioned to increase or sustain flow turbulence within the flow channels **2116**. The winglets **2176** can be arranged or distributed at intervals along the length of the flat tube **2110** in any patterned or patternless manner, and can be located in any feature or combination of features of the corrugations **2152**. Also, it should be noted that the winglets **2176** can include shapes other than those shown in FIGS. **32A** and **32B**.

The flat tube assembly illustrated in FIGS. **32A** and **32B** also provides an example of how either or both longitudinal edges of an insert in any of the embodiments herein need not

necessarily be received or otherwise located within the overlapped longitudinal edges of the first and second tube portions, and need not necessarily be part of or extend to the narrow sides of the flat tube. In the particular construction shown in FIGS. **32A** and **32B** by way of example, the internal insert **2134** includes at least one longitudinal edge **2140** that ends before the narrow side **2120**. Instead, the longitudinal edge **2140** is adjacent one of the broad sides **2124**. Other constructions of the insert **2124** can include either or both longitudinal edges **2138**, **2140** adjacent the other broad side **2122** of the flat tube **2110**, either or both rolled longitudinal edge **2138**, **2140** not within or nested in a corresponding narrow side **2118**, **2120** of the flat tube **2110**, and the like.

FIG. **34** illustrates ten constructions of flat tubes according to additional embodiments of the present invention. These embodiments employ much of the same structure and have many of the same properties as the embodiments of the flat tube described above in connection with FIGS. **25-33**. Accordingly, the following description focuses primarily upon the structure and features that are different than the embodiments described above in connection with FIGS. **25-33**. Reference should be made to the description above in connection with FIGS. **25-33** for additional information regarding the structure and features, and possible alternatives to the structure and features of the flat tubes illustrated in FIG. **34** and described below. Structure and features of the embodiments shown in FIG. **34** that correspond to structure and features of the embodiments of FIGS. **25-33** are designated hereinafter in respective series of reference numbers beginning with 2300.

As described above in connection with the illustrated embodiment of FIGS. **25** and **26**, further reinforcement of the first and/or second narrow sides of a flat tube can be provided by one or more folds of the first and/or second tube portions at the narrow sides (i.e., at the longitudinal edges of such portions). Generally, folding the longitudinal edges of the first and/or second tube portions can increase the strength of the flat tube and resistance of the flat tube to damage. This feature can be employed in any of the embodiments described in connection with FIGS. **25-33**. Examples of flat tubes having longitudinal folded edges are illustrated in FIG. **34**, wherein inserts defining generally rectangular flow channels and not extending into or folded within the folds of the narrow tube sides are illustrated by way of example only. Any of the other types of inserts (or no inserts at all) or longitudinal insert construction and position described herein can instead be used as desired.

Each of the flat tubes **2310**, **2410**, **2510**, **2610**, **2710**, **2810**, **2910**, **3010**, **3110**, **3210** illustrated in FIG. **34** includes at least one longitudinal edge of at least one of the first and second tube portions **2312**, **2412**, **2512**, **2612**, **2712**, **2812**, **2912**, **3012**, **3112**, **3212** and **2314**, **2414**, **2514**, **2614**, **2714**, **2814**, **2914**, **3014**, **3114**, **3214** having a fold **2330**, **2430**, **2530**, **2630**, **2730**, **2830**, **2930**, **3030**, **3130**, **3230**. Each of the constructions illustrated in FIG. **34** have an encompassed edge **2380**, **2382** . . . **3280**, **3282** (that is, the longitudinal edge **2380**, **2382** . . . **3280**, **3282** that is at least partially surrounded by a longitudinal edge **2378**, **2384** . . . **3278**, **3284** of the other tube portion **2312**, **2314** . . . **3212**, **3214**) with at least one fold **2330** . . . **3230**. Some of the constructions in FIG. **34** illustrate an encompassing edge **2978**, **2984**, **3078**, **3074**, **3178**, **3174**, **3278**, **3274** (that is, the longitudinal edge **2978**, **2984**, **3078**, **3074**, **3178**, **3174**, **3278**, **3274** that at least partially surrounds a longitudinal edge **2980**, **2982**, **3080**, **3082**, **3180**, **3182**, **3280**, **3282** of the other tube portion **2912**, **2914**, **3012**, **3014**, **3112**, **3114**, **3212**, **3214**) with at least one fold **2930**, **3030**, **3130**, **3230**. Although the opposite narrow ends of each two-

piece flat tube illustrated in FIG. 34 employ the same folded construction, in other embodiments (with or without inserts) only one of the two narrow ends has such a construction, in which case the other narrow end can have any of the other folded constructions described herein or has no longitudinal folded tube edge portions at all. In other embodiments, each of the longitudinal edges of at least one of the narrow ends of the two-piece flat tube (with or without an insert) has at least one fold.

In some embodiments, one of the narrow ends of any of the flat tubes illustrated in FIG. 34 can have any of the longitudinal folded edge constructions described and/or illustrated herein, while the other narrow end can have any of the folded constructions described above and/or illustrated in connection with any of the embodiments shown in FIGS. 1-24 (with or without inserts). In such cases, the other narrow end can be defined by a folded continuous sheet of material as described in detail above in connection with the one-piece tube embodiments of FIGS. 16-22, thereby resulting in a one-piece tube.

The combination of the longitudinal folded constructions of the first and second tube portions described herein with the relatively small thickness dimensions of the material that can be employed in some embodiments (as described above) can produce flat tubes having a significantly reduced weight without compromise of strength and stability.

For ease of description, the constructions of the flat tubes 2310 . . . 3210 illustrated in FIG. 34 include a similar configuration as the flat tube 1810 shown in FIGS. 25 and 26 with respect to the orientation of the first and second portions 2312, 2314 . . . 3212, 3214, and are classified into three groups: B, C, and D. Each of the groups B, C, and D illustrates alternative characteristics of the flat tube 2310 . . . 3210. As mentioned above, it is to be understood that the features illustrated in FIG. 34 are also applicable to other configurations of two-piece and one-piece flat tubes described and/or illustrated herein, and can be utilized with or without an insert. The flat tubes 2310, 2410, 2510, 2610, 2710, 2810 of Groups B and C each include a non-folded encompassing longitudinal edge 2378, 2384, 2478, 2484, 2578, 2584, 2678, 2684, 2778, 2784, 2878, 2884 of the first and second tube portions 2312, 2314, 2412, 2414, 2512, 2514, 2612, 2614, 2712, 2714, 2812, 2814 respectively. More specifically, the encompassing edges 2378, 2384, 2478, 2484, 2578, 2584, 2678, 2684, 2778, 2784, 2878, 2884 at least partially enclose encompassed edges 2382, 2380, 2482, 2480, 2582, 2580, 2682, 2680, 2782, 2780, 2882, 2880 having at least one fold 2330, 2430, 2530, 2630, 2730, 2830. The folds 2330, 2430, 2530, 2630, 2730, 2830 of the encompassed edges 2382, 2380, 2482, 2480, 2582, 2580, 2682, 2680, 2782, 2780, 2882, 2880 can be substantially parallel to the broad sides 2322, 2324, 2422, 2424, 2522, 2524, 2622, 2624, 2722, 2724, 2822, 2824 (e.g., Groups B and C). Also, the folds 2330, 2430, 2530 can include a portion parallel to the encompassing edge 2378, 2384, 2478, 2484, 2578, 2584 (e.g., Group B).

The flat tubes 2910, 3010, 3110 of Group D include narrow sides 2918, 2920, 3018, 3020, 3118, 3120, wherein both the encompassing edges 2978, 2984, 3078, 3084, 3178, 3184 and the encompassed edges 2982, 2980, 3082, 3080, 3182, 3180 of the first and second tube portions 2912, 2914, 3012, 3014, 3112, 3114 have folds 2930, 3030, 3130. As a result, the stability of the narrow sides 2918, 2920, 3018, 3020, 3118, 3120 can be increased with respect to the narrow sides 2318, 2320, 2418, 2420, 2518, 2520, 2618, 2620, 2718, 2720, 2818, 2820 of the flat tubes 2310, 2410, 2510, 2610, 2710, 2810 in Groups B and C. Furthermore, the encompassed and encompassing edges 2982, 2980, 3082, 3080, 3182, 3180 and 2978, 2984, 3078, 3084, 3178, 3184 of each of the flat tubes 2910,

3010, 3110 in Group D define only one fold 2930, 3030, 3130 (although more folds are possible in other embodiments), whereas the encompassed edges 2382, 2380, 2482, 2480, 2582, 2580, 2682, 2680, 2782, 2780, 2882, 2880 of the Group B and C flat tubes 2310, 2410, 2510, 2610, 2710, 2810 define more than one fold 2330, 2430, 2530, 2630, 2730, 2830. Also with reference to the Group D flat tubes 2910, 3010, 3110, the one fold 2930, 3030, 3130 of each encompassing edge 2978, 2984, 3078, 3084, 3178, 3184 is substantially parallel to the outermost portion of the flat tube 2910, 3010, 3110, and at least a portion of the fold 2930, 3030, 3130 of each encompassed edge 2982, 2980, 3082, 3080, 3182, 3180 is substantially parallel to the broad sides 2922, 2924, 3022, 3024, 3122, 3124 of the flat tubes 2910, 3010, 3110.

With continued reference to the various flat tube embodiments illustrated in FIG. 34, it is to be understood that the number of folds 2330 . . . 3230 at the encompassing and encompassed edges 2382, 2380 . . . 3282, 3280 and 2378, 2384 . . . 3278, 3284, and the design or shape of the folds 2330 . . . 3230 can be adjusted according to a desired set of parameters. Furthermore, although the internal insert 2334 . . . 3234 of the flat tube embodiments illustrated in FIG. 34 is not used for reinforcing the narrow sides 2318, 2320 . . . 3218, 3220, in other embodiments, either or both longitudinal edges 2338, 2340 . . . 3238, 3240 of the insert 2334 . . . 3234 is folded with and within the longitudinal edges 2382, 2380 . . . 3282, 3280 and 2378, 2384 . . . 3278, 3284 of the first and second tube portions 2312, 2314 . . . 3212, 3214. Yet other constructions of the flat tube can include forming folds with the longitudinal edges of a one-piece strip as mentioned above.

In any of the two-piece tube flat tube embodiments described in connection with FIGS. 25-34, it is envisioned that throughout the manufacturing process of the flat tube 1710 . . . 3210, the width of any of the longitudinal seams 1744, 1746 . . . 3244, 3246 or of the gradations 1716 . . . 3216 can be adjusted for different tubes 1710 . . . 3210. As a result, an abrupt thickness change of the broad sides 1722, 1724 . . . 3222, 3224 can be compensated, reduced, or even avoided. For purposes of illustration, it can be observed that the distance *e* illustrated in FIGS. 31 and 32B (representing the distance from the terminal longitudinal edge 2156, 2256 to the distal end of the corresponding narrow tube side 2120, 2220) is significantly larger in the embodiment of FIG. 31 than it is in the embodiment of FIGS. 32A and 32B. This distance *e* can be varied in any of the embodiments as desired.

FIGS. 35-45 illustrate several flat tube inserts according to various embodiments of the present invention, any of which can be used in any of the flat tube embodiments described and/or illustrated herein. In many embodiments, an insert can be described as having a number of hills and valleys at least partially defining flow channels along a flat tube.

The flat tubes 3310, 3410, 3510, 3610 illustrated in FIGS. 35-45 each include an internal insert 3334, 3434, 3534, 3634 with a number of elongated openings 3386, 3486, 3586, 3686 generally defined in the hills 3388, 3488, 3588, 3688 and/or valleys 3390, 3490, 3590, 3690 of the insert 3334, 3434, 3534, 3634. The elongated openings 3386, 3486, 3586, 3686 extend in a generally longitudinal direction along the insert 3334, 3434, 3534; 3634 (i.e., in a direction that will extend generally longitudinally along the inside of a flat tube 3310, 3410, 3510, 3610 in which the insert 3334, 3434, 3534, 3634 will be installed). In some constructions of the flat tube 3310, 3410, 3510, 3610, the elongated openings 3386, 3486, 3586, 3686 can be interrupted by bridges 3392, 3492, 3592, 3692. The bridges 3392, 3492, 3592, 3692 can be oriented to be substantially parallel to the broad sides 3312, 3314, 3412,

3414, 3512, 3514, 3612, 3614 of the flat tube 3310, 3410, 3510, 3610, and can be spaced at any desired regular or irregular interval along the longitudinal direction of the insert 3334, 3434, 3534, 3634.

By providing elongated openings 3386, 3486, 3586, 3686 in the insert 3334, 3434, 3534, 3634 as described above, the weight of the insert 3334, 3434, 3534, 3634 (and consequently of a heat exchanger equipped with flat tubes 3310, 3410, 3510, 3610 having such inserts 3334, 3434, 3534, 3634) can be significantly reduced in relation an insert 3334, 3434, 3534, 3634 that does not include such elongated openings 3386, 3486, 3586, 3686. Based on the design of the internal insert 3334, 3434, 3534, 3634, it is envisioned that the weight of an internal insert 3334, 3434, 3534, 3634 can be reduced by up to 50% with the inclusion of the elongated openings 3386, 3486, 3586, 3686, compared to a continuously corrugated internal insert 3334, 3434, 3534, 3634 of similar dimensions.

In some embodiments, the inserts 3334, 3434, 3534, 3634 described above and illustrated in FIGS. 35-45 are produced by cutting a sheet of material (e.g., endless or discrete lengths of aluminum, aluminum alloy, copper, brass or other metal, or other material), and bending portions of the cut sheet out of plane with respect to the original sheet. For example, in the constructions of the inserts 3334, 3434, 3534, 3634 shown in FIGS. 35-45, the internal inserts 3334, 3434, 3534, 3634 can be produced from a relatively thin sheet metal thickness of about 0.03 mm (0.0011811 in). The bent portions can include elongated slits which are opened by bending sheet material adjacent the slits out of plane with respect to the original sheet. The bends can be made in both directions out of the plane of the original sheet, or in only one direction out of the plane, thereby producing inserts 3334, 3434, 3534, 3634 having different shapes. Further cuts can be made to facilitate this bending, such as slits perpendicular to and joined with the elongated slits just described. In some embodiments, the bent portions include arc-like edges 3394, 3494, 3594, 3694 as illustrated in the embodiments of FIGS. 35-45, for example. In some embodiments, the cuts made in the sheet of material (prior to bending) and the resulting elongated openings 3386, 3486, 3586, 3686 and bridges 3392, 3492, 3592, 3692 define a double-T shape.

The inventors have discovered that desired internal pressure stability can be achieved within flat tubes including the inserts 3334, 3434, 3534, 3634 illustrated in FIGS. 35-45. More specifically, the brazing surfaces of the inserts 3334, 3434, 3534, 3634 illustrated in FIGS. 35-45 (defined by the upper portions of the arc-like edges 3394, 3494, 3594, 3694) are sufficiently large to provide strong bonds between the inserts 3334, 3434, 3534, 3634 and the broad sides 3322, 3324, 3422, 3424, 3522, 3524 of the flat tube 3310, 3410, 3510, 3610. The flanks of the arc-like edges 3394, 3494, 3594, 3694 can also be joined together by brazing the arc-like edges 3394, 3494, 3594, 3694 to the corresponding broad sides 3322, 3324, 3422, 3424, 3522, 3524, 3622, 3624 of the flat tube 3310, 3410, 3510, 3610. Such constructions of lamellae or internal inserts 3334, 3434, 3534, 3634 are frequently called flat-top lamellae.

The use of the inserts 3334, 3434, 3534, 3634 described above in conjunction with the flat tubes illustrated in FIGS. 35-45 and described elsewhere herein provides excellent results. For example, the bonds just described provide further strength to those flat tubes of the present invention constructed of the relatively thin sheet material having dimensions described earlier. Advantages were also found regarding the pressure loss experienced when using such internal inserts 3334, 3434, 3534, 3634. Furthermore, internal inserts

3334, 3434, 3534, 3634 having the elongated openings 3386, 3486, 3586, 3686 and bridges 3392, 3492, 3592, 3692 as described above can help prevent the first and second portions 3312, 3314, 3412, 3414, 3512, 3514, 3612, 3614 of the flat tube 3310, 3410, 3510, 3610 from being easily transversely shifted away from one another. For example, this structure can help prevent one of the first and second flat tube portions 3312, 3412, 3512, 3612 from shifting in the longitudinal direction of the flat tube 3310, 3410, 3510, 3610 with respect to the other flat tube portion 3314, 3414, 3514, 3614 in the course of manufacturing processes performed to create the completed flat tube assembly. One reason is that the hills 3388, 3488, 3588, 3688 and valleys 3390, 3490, 3590, 3690 having the elongated openings 3386, 3486, 3596, 3696 described above can exert an elastic force from the inside of the flat tube 3310, 3410, 3510, 3610 onto the broad sides 3322, 3324, 3422, 3424, 3522, 3524, 3622, 3624, thus placing the broad sides 3322, 3324, 3422, 3424, 3522, 3524, 3622, 3624 under tension to prevent or reduce such shifting.

In each of the embodiments illustrated in FIGS. 35-45 the inserts 3334, 3434, 3534, 3634 are received within two-piece flat tubes 3310, 3410, 3510, 3610 in which the longitudinal seams 3344, 3346, 3444, 3446, 3544, 3546, 3644, 3646 joining the two portions of the flat tube 3310, 3410, 3510, 3610 extend to and are at least partially located on different portions 3312, 3314, 3412, 3414, 3512, 3514, 3612, 3614. In each embodiment, the two portions 3312, 3314, 3412, 3414, 3512, 3514, 3612, 3614 are substantially identical to each other. However, in other embodiments, the inserts 3334, 3434, 3534, 3634 can be utilized in any of the other one-piece or two-piece flat tubes of the present invention described herein. For example, the two portions 3312, 3314, 3412, 3414, 3512, 3514, 3612, 3614 can be arranged such that one longitudinal seam 3344, 3444, 3544, 3644 is in one broad side 3324, 3424, 3524, 3624 and the other longitudinal seam 3346, 3446, 3546, 3646 is in the other broad side 3322, 3422, 3522, 3622 of the flat tube 3310, 3410, 3510, 3610, such as in the embodiment of the present invention illustrated in FIGS. 25 and 26. In such embodiments, one longitudinal edge 3354, 3356, 3454, 3456, 3554, 3556, 3654, 3656 of each of the two portions 3312, 3314, 3412, 3414, 3512, 3514, 3612, 3614 extends freely substantially within the flat tube 3310, 3410, 3510, 3610. As a consequence, the two portions 3312, 3314, 3412, 3414, 3512, 3514, 3612, 3614 can have relatively large tolerances in their widths as described earlier in connection with the illustrated embodiment of FIGS. 25 and 26. In other embodiments, both longitudinal seams 3344, 3346, 3444, 3446, 3544, 3546, 3644, 3646 are located to extend into the same broad side 3322, 3422, 3522, 3622 or 3324, 3424, 3524, 3624, such as the embodiment of the present invention illustrated in FIG. 27.

In some embodiments, either or both longitudinal edges 3338, 3340, 3448, 3440, 3548, 3540, 3648, 3640 of the insert 3334, 3434, 3534, 3634 can extend into a corresponding narrow side 3318, 3320, 3418, 3420, 3518, 3520, 3618, 3620, and can be shaped to line at least a portion of the interior of the narrow side 3318, 3320, 3418, 3420, 3518, 3520, 3618, 3620 in any of the manners described above in connection with the illustrated embodiments of FIGS. 25-34. For example, either or both longitudinal edges 3338, 3340, 3448, 3440, 3548, 3540, 3648, 3640 of the insert 3334, 3434, 3534, 3634 can include a gradation 3472, 3672 (see, for example, the embodiments of FIGS. 39-42 and 45) and/or an arc-shaped edge 3374, 3474, 3574, 3674 to reinforce either or both narrow sides 3318, 3320, 3418, 3420, 3518, 3520, 3618, 3620.

Such a relationship between the insert 3334, 3434, 3534, 3634 and the flat tube 3310, 3410, 3510, 3610 can provide

35

significant strength and stability advantages as described earlier. In such embodiments, the thickness of the reinforced narrow sides 3318, 3320, 3418, 3420, 3518, 3520, 3618, 3620 corresponds to the sum of the thicknesses of the first and second tube portions 3312, 3314, 3412, 3414, 3512, 3514, 3612, 3614 and the thickness of the insert 3334, 3434, 3534, 3634. In some embodiments having this relationship, each of the first and second tube portions 3312, 3314, 3412, 3414, 3512, 3514, 3612, 3614 can have a thickness of no greater than about 0.15 mm (0.00591 in). Furthermore, each of the first and second tube portions 3312, 3314, 3412, 3414, 3512, 3514, 3612, 3614 can have a thickness greater than about 0.10 mm (0.003937 in). Also or alternatively, in such embodiments the thickness of the insert 3334, 3434, 3534, 3634 is no greater than about 0.10 mm (0.003937 in). For example, the flat tube 3310, 3410, 3510, 3610 can have first and second tube portions 3312, 3314, 3412, 3414, 3512, 3514, 3612, 3614 each with a thickness of about 0.12 mm (0.0047224 in), and in which the insert 3334, 3434, 3534, 3634 has a thickness of no greater than about 0.10 mm (0.003937 in). In other embodiments, the thickness of each of the first and second tube portions 3312, 3314, 3412, 3414, 3512, 3514, 3612, 3614 and the insert 3334, 3434, 3534, 3634 is no greater than about 0.15 mm (0.0059055) to provide a relatively cost-effective heat exchanger with good heat transfer and strength properties. Also, in some embodiments the thickness of each of the first and second tube portions 3312, 3314, 3412, 3414, 3512, 3514, 3612, 3614 and/or of the insert 3334, 3434, 3534, 3634 is no less than about 0.03 mm (0.0011811 in). In other embodiments, the inserts 3334, 3434, 3534, 3634 can have any of the insert thicknesses described above in connection with the illustrated embodiments of FIGS. 25-34.

As best shown in FIGS. 35, 39, 44, and 45, in some embodiments the inserts 3334, 3434, 3534, 3634 illustrated in FIGS. 35-45 are shaped such that the hills 3388, 3488, 3588, 3688 and valleys 3390, 3490, 3590, 3690 described above define corrugations 3352, 3452, 3552, 3652 running in the longitudinal direction of the inserts 3334, 3434, 3534, 3634. The flanks of these corrugations 3352, 3452, 3552, 3652 can be perpendicular or substantially perpendicular to the broad sides 3322, 3324, 3422, 3424, 3522, 3524 of the flat tubes 3310, 3410, 3510 (see FIGS. 35, 39, and 44) or can form an angle of inclination with respect to the broad sides 3622, 3624 of the flat tube 3610. In any of the illustrated embodiments of FIGS. 35-45, perpendicular or angled corrugation flanks can be used as desired. Additionally, the internal insert 3334, 3434, 3534, 3634 can be made of more than one part, such that the resulting flat tube assembly includes four or more parts in some embodiments.

In some embodiments (including embodiments in which the internal insert 3334, 3434, 3534, 3634 is constructed from a single sheet of material as described above), the internal insert 3334, 3434, 3534, 3634 is generally rolled in the longitudinal direction of the internal insert 3334, 3434, 3534, 3634 or of the flat tube 3310, 3410, 3510, 3610. In some manufacturing processes of the flat tube 3310, 3410, 3510, 3610, for example, two types of rolls are provided to roll the internal insert 3334, 3434, 3534, 3634 and generate the elongated openings 3386, 3486, 3586, 3686, the hills 3388, 3488, 3588, 3688 and the valleys 3390, 3490, 3590, 3690 in the longitudinal direction as described above. A first roll can be a cutting roll for forming slits on the substantially planar sheet. A second roll can be a forming roll for forming the hills 3388, 3488, 3588, 3688 and valleys 3390, 3490, 3590, 3690 defining the arc-like edges 3394, 3494, 3594, 3694 in FIGS. 35-45. Similar to the constructions described above, the longitudinal seams 3344, 3346, 3444, 3446, 3544, 3546, 3644, 3646 of the

36

first and second tube portions 3312, 3314, 3412, 3414, 3512, 3514, 3612, 3614 forming the flat tube 3310, 3410, 3510, 3610 reach from the narrow sides 3318, 3320, 3418, 3420, 3518, 3520, 3618, 3620 into the broad sides 3322, 3324, 3422, 3424, 3522, 3524, 3622, 3624 of the flat tube 3310, 3410, 3510, 3610. As with the earlier-described two-piece tube embodiments, the gradations 3316, 3416, 3516, 3616 however, can lie in the broad sides 3322, 3324, 3422, 3424, 3522, 3524, 3622, 3624. As also described in earlier embodiments, the width of the gradation 3316, 3416, 3516, 3616 (measured to the distal end of the corresponding narrow side 3318, 3320, 3418, 3420, 3518, 3520, 3618, 3620) can be determined based on the manufacturing process and desired specifications of the flat tube 3310, 3410, 3510, 3610.

With continued reference to the illustrated embodiments of FIGS. 35-45, in some constructions of the flat tube 3310, 3410, 3510, 3610 having an insert 3334, 3434, 3534, 3634 with the elongated openings 3386, 3486, 3586, 3686 and bridges 3390, 3492, 3590, 3690 as described herein (including those embodiments having the relatively thin tube wall materials described above), the inventors have discovered that a flat tube small diameter d of at least about 0.7 mm (0.027559 in) provides good performance results in many applications, such as in radiators. The inventors have also discovered that a flat tube small diameter d of no greater than about 1.5 mm (0.059055 in) provides good performance results in many applications, such as in radiators, and particularly in those flat tube embodiments of the present invention having the relatively thin tube wall materials described above. In the case of charge air coolers and other applications, the inventors have discovered that the small diameter d can be greater than about 10.0 mm (0.3937 in) while still providing good performance results. Also, it should be noted that in other embodiments any of the small and large diameters D , d described above in connection with all of the flat tube embodiments disclosed herein can instead be used. The large diameter D of the two-piece flat tubes 3310, 3410, 3510, 3610 illustrated in FIGS. 35, 39, 44, and 45 can have any size desired (also including those described above in connection with all of the flat tube embodiments disclosed herein), based at least in part upon the width of the starting material used to construct the flat tube 3310, 3410, 3510, 3610. In this regard, if rolling rolls are used to produce the flat tubes, such rolls (not shown) can be adjusted to manufacture wider or narrower flat tubes 3310, 3410, 3510, 3610. In other constructions, the rolls for manufacturing the flat tubes 3310, 3410, 3510, 3610 can be replaced according to the desired dimensions of the flat tube 3310, 3410, 3510, 3610.

In some constructions of the flat tubes 3310, 3410, 3510, 3610 illustrated in the embodiments of FIGS. 35-45, the first and second tube portions 3312, 3314, 3412, 3414, 3512, 3514, 3612, 3614 and/or the insert 3334, 3434, 3534, 3634 can include a brazing material coating for the purpose of joining any two or more of these parts, and/or in some cases another element (e.g., a cooling grate of a heat exchanger). Although in some embodiments, the first and second tube portions 3312, 3314, 3412, 3414, 3512, 3514, 3612, 3614 and/or the insert 3334, 3434, 3534, 3634 are constructed of aluminum or an aluminum alloy, in other embodiments any or all of these parts can be constructed from other materials either suitable or not for brazing.

With particular reference now to the illustrated embodiment of FIGS. 35-38, in some embodiments the bridges 3390 interrupting the elongated openings 3386 are not continuous or aligned with other bridges spanning the entire width of the insert 3334. Instead, bridges 3390 interrupting an elongated opening can be staggered (i.e., located at different longitudi-

37

nal positions along the insert **3334**) with respect to adjacent bridges **3390** on either or both sides of the elongated opening **3386**. In other embodiments, such as that shown in FIGS. **39-42**, the bridges **3492** interrupting the elongated openings **3486** can be aligned so that two or more bridges **3492** interrupting adjacent elongated openings **3486** are aligned or substantially aligned at the same longitudinal position along the insert **3444**. In either embodiment, the distance along each flow channel **3316**, **3416** between bridges **3390**, **3492** can be discrete (i.e., not in fluid communication with adjacent flow channels **3316**, **3416**), since the broad sides **3322**, **3324**, **3422**, **3424** can close the elongated openings **3386**, **3486**. Although the bridge arrangements illustrated in the embodiments of FIGS. **35-42** provide advantages from manufacturing standpoints, in still other embodiments, the bridges can be arranged in any other manner desired.

The hydraulic diameter defined by the flow channels **3316**, **3416** are defined by the corresponding design of the hills **3388**, **3488** and valleys **3488**, **3490** of the insert **3334**, **3434**. The hydraulic diameter can be relatively small, considering a small diameter *d* of about 0.8 mm (0.031496 in) and a relatively large number of flow channels **3316**, **3416** across the width of the insert **3334**, **3434**, for example.

With continued reference to the embodiment shown in FIGS. **35-38**, the illustrated corrugations **3352** "oscillate" approximately around a middle plane of the insert **3334** (or flat tube **3310**). In other words, the flanks and arc-shaped edges **3374** of the insert **3334** extend in opposite directions toward the first and second tube portions **3312**, **3314** from a portion of the insert **3334** defined between, and substantially parallel to, the broad sides **3322**, **3324** of the flat tube **3310**. Although this portion between the broad sides **3322**, **3324** can be located at a middle plane of the insert **3334**, such as that shown in FIG. **37**, this portion from which the hills **3390** and valleys **3388** extend can be located anywhere between the extremities of the insert **3334** to either side of the original planar sheet. Also, it should be noted that the construction of the insert **3334** shown in FIG. **35** has elongated openings **3386** formed in the hills **3390** and valleys **3388** of the illustrated corrugations **3352**, although such openings **3386**, **3388** need not necessarily be defined in both the hills **3390** and valleys **3388** in other embodiments.

In the embodiment of FIGS. **38-42**, the corrugations **3452** are instead formed to one side of the insert **3434**. In particular, the insert **3434** is not in a middle plane with respect to the broad sides **3422**, **3424** of the flat tube **3410**, but instead lies approximately at the lower broad side **3424** of the flat tube **3410**. Furthermore, the construction of the insert **3434** shown in FIG. **39** has elongated openings **3486** only in the hills **3488** of the illustrated corrugations **3452**.

In some embodiments, any of the inserts described herein can be separated into two or more sections along the width of the inserts in order to define two or more flow channels that in some embodiments are fluidly isolated from one another. This separation can be produced by one or more longitudinally extending partitions defined in whole or in part by the insert. For example, in the embodiments of FIGS. **44** and **45**, each of the internal inserts **3534**, **3634** is formed with at least one partition **3596**, **3696** to provide the flat tube **3510**, **3610** with at least two flow chambers having any number of flow channels **3516**, **3616** desired. In this manner, a separation of two flow mediums flowing within the flat tube **3510**, **3610** is accomplished. Each of the flat tubes **3510**, **3610** illustrated in FIGS. **44** and **45** includes two such flow chambers, permitting (for example) a medium to flow forward in one flow chamber

38

in one direction, and permitting the same or a different medium to flow backward in the other flow chamber in an opposite direction.

A number of flat tubes according to various embodiment of the present invention have been described above as being constructed of a single piece of material (see, for example, the illustrated embodiments of FIGS. **16-23**, which show a number of flat tubes **910**, **1010**, **1110**, **1210**, **1310**, **1410**, **1510**, **1610** each having a number of interior folds **928**, **1028**, **1128**, **1228**, **1328**, **1428**, **1528**, **1628** defined by first and second portions **912**, **914**, **1012**, **1014**, **1112**, **1114**, **1212**, **1214**, **1312**, **1314**, **1412**, **1414**, **1512**, **1514**, **1612**, **1614** of the same piece of material used to construct the tube **910**, **1010**, **1110**, **1210**, **1310**, **1410**, **1510**, **1610**). As described in greater detail above, the interior folds **928**, **1028**, **1128**, **1228**, **1328**, **1428**, **1528**, **1628** at least partially define a number of flow channels **916**, **1016**, **1116**, **1216**, **1316**, **1416**, **1516**, **1616** through the flat tubes **910**, **1010**, **1110**, **1210**, **1310**, **1410**, **1510**, **1610**.

In other embodiments of the present invention, a one-piece flat tube can be provided with an insert constructed of a separate piece of material received within (and in some embodiments, secured within) the one-piece flat tube. Two examples of such flat tubes **3710**, **3810** having inserts **3734**, **3834** are shown in FIGS. **46-47** and **48**. Like the one-piece flat tubes described earlier, the flat tube **3710**, **3810** can be constructed of a sheet (e.g., strip) of relatively thin material defining the broad sides **3722**, **3724**, **3822**, **3824** and two reinforced narrow sides **3718**, **3720**, **3818**, **3820** of the flat tube **3710**, **3810**. In some embodiments, the inventors have discovered that the thickness of the sheet of material can be less than about 0.15 mm (0.0059055 in) to provide good performance results in many applications. Also, in some embodiments, the inventors have discovered that the thickness of the sheet of material can be greater than about 0.03 mm (approx. 0.0011811 in) to provide good performance results in many applications. It is to be understood that the thickness of the sheet of material can have other dimensions not listed herein.

With continued reference to FIGS. **46-48**, the longitudinal edges **3778**, **3782**, **3878**, **3882** of the sheet of material are shaped and moved together such that one longitudinal edge **3778**, **3878** abuts against the other longitudinal edge **3782**, **3882** to form a narrow side **3718**, **3818** of the flat tube **3710**, **3810**. This narrow side **3718**, **3818** can be defined by at least one 180° bond of the sheet of material at the narrow side **3718**, **3818** or by one or more other types of folds (described in greater detail below) used to close the narrow side **3718**, **3818**. The other narrow side **3720**, **3820** is formed at least in part by folding the sheet of material to bring the first and second longitudinal edges **3778**, **3782**, **3878**, **3882** together as just described. In some embodiments, this other narrow side **3720**, **3820** can include at least a triple wall thickness generated by folding the sheet of material upon itself twice in the location of the narrow side **3720**, **3820**.

In some embodiments, the process of manufacturing the flat tube **3710**, **3810** can include folding or otherwise forming the longitudinal edges **3778**, **3782**, **3878**, **3882** that will be brought together to close the flat tube **3710**, **3810** prior to folding the sheet of material to produce reinforcing folds **3730**, **3830** (indicated at F in FIGS. **46-48**) at the narrow side **3720**, **3820** as described above. In other embodiments, these processes are performed at the same time or substantially the same time.

In some embodiments of the one-piece flat tube, such as the one-piece flat tube **3710** shown in FIGS. **46** and **47**, one longitudinal edge **3778** of the sheet of material used to produce the tube **3710** defines an arch shape larger than an arch

shape of the other longitudinal edge **3782**. One advantage of such a construction is that when the larger arch-shaped longitudinal edge **3778** is shaped around the smaller arch-shaped longitudinal edge **3782**, the finished flat tube **3710** generally does not gape or is resistant to gaping. However, in other embodiments, the longitudinal edges **3778**, **3782** can have shapes other than ones that are arched. For example, the longitudinal edges **3878**, **3882** illustrated in FIG. **48** can be joined together and have a number of different shapes, including without limitation any of the longitudinal edge shapes illustrated and/or described above in connection with FIGS. **2** and **6-11**. Also, the longitudinal edges **3878**, **3882** illustrated in FIG. **48** can be joined together with either or both longitudinal edges **3738**, **3740** and have therewith a number of different shapes, including without limitation any of the longitudinal edge shapes illustrated and/or described above in connection with FIGS. **14** and **15**.

The narrow sides **3718**, **3720**, **3818**, **3820** of the one-piece flat tubes **3710**, **3810** shown in FIGS. **46-48** each have a thickness of at least two times that of the sheet material used to construct the tubes **3710**, **3810**. Two of the illustrated narrow sides **3720**, **3820** have a thickness that is three times that of the sheet material based upon the extra folds **3730**, **3830** created in the areas of these narrow sides **3720**, **3820**. In other embodiments, further reinforcement of either narrow side **3718**, **3720**, **3818**, **3820** can be achieved by forming one or more additional folds **3730**, **3830** at the locations of the narrow sides **3718**, **3720**, **3818**, **3820**. Any of the types of folds described in connection with any of the embodiments of FIGS. **1-24** for reinforcing a narrow side defined by two joined longitudinal edges can be used to reinforce the first narrow side **3718**, **3818** illustrated in FIGS. **46-48**. Similarly, any of the types of folds described in connection with any of the embodiments of FIGS. **16-24** for reinforcing a narrow side defined by a continuous sheet of material can be used to reinforce the second narrow side **3720**, **3820** illustrated in FIGS. **46-48**.

In each of the two illustrated embodiments of FIGS. **46-48**, an internal insert **3734**, **3834** is received within the flat tube **3710**, **3810** as the flat tube **3710**, **3810** is manufactured. In some embodiments, the insert **3734**, **3834** can be inserted after the production of the second narrow side **3720**, **3820** (defining the reinforcing folds **3730**, **3830** described above) while the flat tube **3710**, **3810** is still partially open, as shown in FIGS. **46-48**. Alternatively or in addition, either or both broad sides **3722**, **3724** of the flat tube **3710**, **3810** can have interior folds similar to those illustrated in FIGS. **1-13** and **16-24** (for example) at least partially forming flow channels.

One exemplary process for forming a one-piece flat tube **3710** with an insert **3734** is illustrated in FIG. **46** by way of example. First, a fold **3730** (indicated at F) is created, and the longitudinal edges **3778**, **3782** are shaped simultaneously. Alternatively, only one longitudinal edge **3778**, **3782** is shaped while the other longitudinal edge **3782**, **3778** remains unshaped. In the illustrated embodiment of FIG. **46**, and at the stage of manufacture shown in illustration (a) of FIG. **46**, one longitudinal edge **3782** with an arch **3762** is already completed, and the other longitudinal edge **3778** has been provided with a simple bend which will later be further shaped into a larger arch **3766** extending at least partially around the arch **3762** defined by the first longitudinal edge **3782**.

At the stage of manufacture shown in illustration (b) of FIG. **46**, two reinforcing folds **3730** have been completed by adding a fold **3730** to the fold **3730** shown in illustration (a). Therefore, in the area of these folds **3730**, a triple thickness of the sheet material used to form the one-piece flat tube **3710** is formed.

At the stage of manufacture shown in illustration (c) of FIG. **46**, the folds **3730** are beginning to form the second narrow side **3720** of the flat tube **3710** by bending the folds **3730**. In this intermediate step of the manufacturing process, a gradation **3758** is formed in one of the broad sides **3722** substantially adjacent the folds **3730** to provide a smooth exterior surface of the one-piece flat tube **3710**. A gradation **3758** can also be formed in the other broad side **3724** substantially adjacent the folds **3730** in an alternative construction of the tube **3710**. The smooth surface of the tube **3710** produced by such gradations **3758** and their ability to receive a fold **3730** or a longitudinal edge **3778** in a recessed manner can be advantageous in cases when the tube **3710** needs to be brazed, welded or glued to other elements.

Next, at the stage of manufacture shown in illustration (d) of FIG. **46**, a corrugated internal insert **3734** is inserted into the flat tube **3710**, although inserts having any of the other shapes described herein can instead be used. One of the longitudinal edges **3738** of the corrugated internal insert **3734** can first be placed in the small arch **3762** of the longitudinal edge **3782**. Alternatively, one longitudinal edge **3740** of the internal insert **3734** can be first placed within the narrow side **3720** opposite the small arch **3762**, as shown in FIGS. **46** and **47**. The internal insert **3734** can be under a certain preliminary tension when inserted at the stage shown in illustration (d) of FIG. **46** and in FIG. **47**. More specifically, the insert **3734** can be shaped to have a tension arching the insert **3734** slightly away from the broad side **3724** or urging expansion of the insert **3734** against compression needed to place the insert **3734** within the flat tube **3710**, and is therefore pushed into the narrow sides **3718**, **3720** during the complete closing of the one-piece flat tube **3710**. At the stage of manufacture shown in illustration (e) of FIG. **46**, a large arch **3766** is formed on the longitudinal edge **3778** and is placed around the small arch **3762** on the other longitudinal edge **3782**, thus closing the one-piece flat tube **3710**. The aforementioned small curvature of the internal insert **3734** (if existing) is thereby removed, and both shaped longitudinal edges **3738**, **3740** of the internal insert **3734** are installed within the narrow sides **3718**, **3720** of the flat tube **3710**.

The process for forming the one-piece flat tube **3810** illustrated in FIG. **48** is similar in many respects to that described above with reference to the embodiment of FIGS. **46** and **47**. Therefore, with the exception of features described hereafter and any inconsistent or incompatible description above, reference is hereby made to the description above regarding the manufacture of the flat tube **3710** for more information regarding the manufacture of the flat tube **3810**.

At the stage of manufacture shown in illustration (a) of FIG. **48**, the single sheet of material used to form the flat tube **3810** includes a fold **3830** that will partially define the second narrow side **3820** of the one-piece flat tube **3810**. After producing another overlapping fold at the same location on the single sheet of material, the sheet of material is bent at the location as best shown in illustration (c) of FIG. **48**. The first reinforced narrow side **3818** is at least partially formed from the opposite longitudinal edges **3878**, **3882** brought together to close the one-piece flat tube **3810** (see illustrations (d) and (e) of FIG. **48**). Closing the one-piece flat tube **3810** occurs through a joint bend or folding of the opposite longitudinal edges **3878**, **3882** and a longitudinal edge **3838** of the internal insert **3834**. More specifically, the longitudinal edge **3838** of the internal insert **3834** lies between the two longitudinal edges **3878**, **3882**. It should be noted that the flat tube **3810** shown in illustration (f) of FIG. **48** is not necessarily in a final stage of manufacture. The folds defined by the edges **3878**, **3882**, **3838** can be arranged against each other as shown in

FIGS. 14 and 15. However, as mentioned above, any of the other reinforced narrow side fold constructions described and/or illustrated herein can instead be used as desired. In general, the number of folds or bends made to produce the narrow side 3818 at least partially determines the stability of the narrow side 3818.

If desired, the flat tubes 3710, 3810 illustrated in FIGS. 46-48 can be provided with reinforcements placed in predetermined areas, such as locations on either or both broad sides 3722, 3724, 3822, 3824 of the flat tubes 3710, 3810 where heat exchange is expected to take place. The reinforcements can take a number of different forms, such as one or more layers of sheet material separate from the sheet of material defining the flat tubes 3710, 3810 and attached thereto by brazing, welding, or in any other suitable manner, one or more additional folds of the sheet of material used to construct the flat tubes 3710, 3810, and the like.

By virtue of the relatively thin-walled material described above used in some embodiments to construct the flat tubes 3710, 3810 (with or without reinforcements), the weight of a heat exchanger formed with the flat tubes 3710, 3810 can be significantly reduced while improving the heat exchange capability thereof. Another reason for reduced weight and increased heat exchange capability is that the broad sides 3722, 3724, 3822, 3824 of the flat tube 3710, 3810 are formed such that the tubes 3710, 3810 ensure good brazed connections with fins, ribs, or other heat exchange elements (not shown), which can be arranged in a heat exchanger between two or more of the flat tubes 3710, 3810. Based upon the features of the one-piece flat tube 3710, 3810 described above, the flat tubes 3710, 3810 have substantial planar exterior surface are for connection to such heat exchange elements.

Additionally, it is to be understood that the characteristics of the flat tubes 3710, 3810 described with respect to FIGS. 46-48 can also be applied to any of the other constructions of the flat tubes described in this application.

With regard to the manner in which the flat tubes 3710, 3810 can be manufactured, in some embodiments, two endless strips of sheet material are fed to a roller conveyor line 3701, such as that illustrated in FIG. 49. In many cases, aluminum or an aluminum alloy is considered a preferred material for manufacture of the flat tubes 3710, 3810. However, other metals and material are suitable for manufacturing the flat tube 3710, 3810. With reference to the tubes 3710, 3810 shown in FIGS. 46-48, the sheet of material forming the first and second portions 3712, 3714, 3812, 3814 of the flat tube 3710, 3810 can be received from an endless strip of material (e.g., sheet metal), and the internal insert 3734, 3834 can be formed from another endless strip of material (e.g., sheet metal). At one of the beginning stages of the roller conveyor line 3701 (prior to shaping the strips of material, in some embodiments), perforations can be added to the strips of material in distances that correspond to desired individual tube lengths. In some embodiments, the sheets of material can be shaped after perforating the strips of sheet metal, although such perforation can occur during or after such sheet shaping. As shown in FIG. 49, an insertion area 3703 in which the internal insert 3734, 3834 is inserted into the flat tube 3710, 3810 is located in a downstream part of the roller conveyor line 3701. Before inserting the internal insert 3734, 3834 within the one-piece flat tube 3710, 3810, the above-mentioned perforations should be substantially aligned with one another (i.e., all lying in a common plane substantially perpendicular to the one-piece flat tube 3710, 3810 in some embodiments) so that individual tubes 3710, 3810 can be separated thereafter.

The one-piece flat tube embodiments illustrated in FIGS. 46-48 each have an insert 3734, 3834 that is separate from and received with a respective flat tube 3710, 3810. In other embodiments, however, the inventors have discovered that it is possible to construct a one-piece flat tube having an insert integrally formed with the one-piece tube (i.e., formed of the same unitary piece of sheet material used to construct the flat tube 3710, 3810). Five such flat tubes 3910, 4010, 4110, 4210, 4310 are illustrated in FIGS. 50-54 by way of example. It should be noted that the features described below with reference to FIGS. 50-54 are also applicable to any of the other flat tube embodiments described herein, barring features that are inconsistent or incompatible therewith.

In each of the illustrated embodiments of FIGS. 50-54, a single piece of sheet material (e.g., a sheet metal strip, for example) is formed into both the flat tube 3910, 4010, 4110, 4210, 4310 and an insert 3934, 4034, 4134, 4234, 4334. The flat tubes 3910, 4010, 4110, 4210, 4310 illustrated in FIGS. 50-54 include opposite reinforced narrow sides 3918, 3920, 4018, 4020, 4118, 4120, 4218, 4220, 4318, 4320 and relatively low wall thicknesses. In some embodiments, the inventors have discovered that the thickness of the sheet of material can be less than about 0.15 mm (0.0059055 in) to provide good performance results in many applications. Also, in some embodiments, the inventors have discovered that the thickness of the sheet of material can be greater than about 0.03 mm (approx. 0.0011811 in) to provide good performance results in many applications. It is to be understood that the thickness of the sheet of material can have other dimensions not listed herein. As a result of such relatively thin sheet material thicknesses that can be used in some embodiments, heat exchangers with these flat tubes 3910, 4010, 4110, 4210, 4310 can have a comparably low weight and an improved heat exchange rate. Also, by virtue of the fact that both narrow sides 3918, 3920, 4018, 4020, 4118, 4120, 4218, 4220, 4318, 4320 of the one-piece flat tubes 3910, 4010, 4110, 4210, 4310 can be reinforced as will be described in greater detail below, the need to note the orientation of the one-piece flat tubes 3910, 4010, 4110, 4210, 4310 during assembly of a heat exchanger can be reduced or eliminated.

Each of the tubes described below in connection with FIGS. 50-54 can have any of the dimensions described above with reference to the embodiments of FIGS. 1-34. For example, in some embodiments, any of the one-piece flat tubes 3910, 4010, 4110, 4210, 4310 illustrated in FIGS. 50-54 can have a small diameter d greater than about 0.7 mm (0.027559 in). Also, in some embodiments, any of these tubes 3910, 4010, 4110, 4210, 4310 can have a small diameter d of less than about 15 mm (0.59055 in). As another example, any of the one-piece flat tubes 3910, 4010, 4110, 4210, 4310 illustrated in FIGS. 50-54 can have a large diameter D greater than about 8 mm (0.31496 in). Also, in some embodiments, any of these tubes 3910, 4010, 4110, 4210, 4310 can have a large diameter D of less than about 300 mm (1.811 in). However, it should be noted that in other embodiments, any of the small and large diameters d , D described above in connection with all of the flat tube embodiments disclosed herein can be used.

With particular reference first to the illustrated embodiment of FIG. 50, the flat tube 3910 shown therein is formed of a single sheet of material having a center portion 3905 shaped in a wave-like manner to form flow channels 3916 in the resulting one-piece flat tube 3910. The center portion 3905 of the sheet of material is flanked on both sides by sets of folds 3930 used to reinforce a corresponding narrow side 3918, 3920 of the one-piece flat tube 3910. In other embodiments, the center portion 3905 is flanked on only one side with a set

of folds **3930** (such as in cases where only one narrow side **3918**, **3920** of the one-piece flat tube **3910** needs to be reinforced in this manner. Also, it should be noted that the center portion **3905** can be flanked one either side by any number of reinforcing folds, and that the folds need not necessarily be the same in number, shape, or size on the opposite sides of the center portion **3905**. In the illustrated embodiment of FIG. **50**, the sheet of material also has outer portions **3907** defining the broad sides **3922**, **3924** of the one-piece flat tube **3910**. The outer portions **3907** extend from and are integral with the sets of folds **3930** described above, and are shaped to at least partially encompass the sets of folds **3930**. In other embodiments, the outer portions **3907** do not enclose or do not fully enclose the folds **3930**, in which cases the outer portions **3907** are bent to at least close the flow channels **3916** within the one-piece flat tube **3910**. Also, it should be noted that the sheet of material is formed to define only one outer portion (e.g., extending from the folds on only one of the two sides of the center portion **3905**), which can extend around the center portion **3905** to close the flow chambers **3916**.

In some embodiments, the flat tube **3910** shown in FIG. **50** can be efficiently produced on a roller line (such as the roller line **3701** shown in FIG. **49**) from an endless sheet of material, such as an endless strip or belt **3909** of sheet metal or other suitable material as shown in FIG. **50(a)**. The strip of material **3909** includes two longitudinal edges **3938**, **3940**. First, and as shown in FIG. **50(b)**, two sets of multiple folds **3930** are created in the strip of material **3909** to form narrow sides **3918**, **3920** of the flat tube **3910** to be created later. Each illustrated set of multiple fold **3930** is formed of six 180° bends in the strip of material **3909**, wherein adjacent folds **3930** abut one another with little to no space between the adjacent folds **3930** between the bends defining the folds **3930**. The gaps shown between the folds **3930** illustrated in FIG. **50** are for illustration purposes only to show individual folds **3930** in greater detail. Moreover, although six folds **3930** are shown in each set illustrated in FIG. **50**, it should be noted that any other number of folds **3930** can exist adjacent the center portion **3905** as described earlier, determined in many embodiments at least in part by the desired specifications (e.g. dimensions) of the flat tube **3910**.

As shown in FIG. **50(c)**, a wave-like section **3911** is then formed between the sets of multiple folds **3930**. However, in other embodiments, the wave-like section **3911** can instead be formed at the same time as or subsequent to forming the folds **3930**. The wave-like section **3911** can have any number of corrugations with any shape desired, including without limitation corrugations with flanks inclined with respect to the broad sides **3922**, **3924** of the one-piece flat tube **3910** once assembled, corrugations having a square wave shape, corrugations having a curved wave shape (e.g., sine wave), corrugations having any other shape described herein, and any combination of such shapes.

The manufacturing process for forming the flat tube **3910** in FIG. **50(d)** proceeds according to the two arrows shown with dashed lines. In particular, subsequent to forming the folds **3930** and the wave-like section **3911**, belt sections **3913** connected to the sets of multiple folds **3930** are placed around the corresponding multiple folds **3930** and across the wave-like section **3911**, thereby forming longitudinally-extending flow channels **3916** of the one-piece flat tube. In other words, each belt section **3913** encompasses or at least partially encompasses one set of multiple folds **3930** from the outside, and extends further to cover the wave-like section **3911**. Also, one longitudinal edge **3978** is bent to lie on the first narrow side **3918** and to extend around and encompass the multiple folds **3230** at the first narrow side **3918**, and the other longi-

tudinal edge **3980** is bent to lie on the second narrow side **3920** and to extend around and encompass the multiple folds **3230** at the second narrow side **3920**, as shown in illustrations (c) and (d) of FIG. **50**. In some embodiments of the flat tube **3910**, the longitudinal edges **3978**, **3980** does not cover or only partially covers the corresponding narrow sides **3918**, **3920**, because the narrow sides **3928**, **3920** can be sufficiently stable through the provision of the multiple folds **3930** described above.

In a completed version of the flat tube **3910**, such as the one illustrated in FIG. **50(d)**, the wave peaks and the wave valleys of the wave-like section **3911** (or other features of center portions **3905** having different shapes defining the flow channels **3916**) are brazed, welded, or secured in any other suitable manner to either or both broad sides **3922**, **3924** of the one-piece flat tube **3910**. More specifically, the dots on the wave peaks and wave valleys shown in FIG. **50(d)** schematically illustrate the brazed connections that can be made between the wave-like section **3911** and the adjacent broad sides **3922**, **3924**.

FIG. **51** illustrates a one-piece flat tube with integral insert according to an additional embodiment of the present invention. This embodiment employs much of the same structure and has many of the same properties as the embodiments of the flat tube described above in connection with FIG. **50**. Accordingly, the following description focuses primarily upon the structure and features that are different than the embodiments described above in connection with FIG. **50**. Reference should be made to the description above in connection with FIG. **50** for additional information regarding the structure and features, and possible alternatives to the structure and features of the one-piece flat tube with integral insert illustrated in FIG. **51** and described below. Structure and features of the embodiment shown in FIG. **51** that correspond to structure and features of the embodiment of FIG. **50** are designated hereinafter in the 4000 series of reference numbers.

With particular reference now to FIG. **51** the one-piece flat tube **4010** shown therein is formed from one sheet of material (e.g., a sheet metal strip). In this particular embodiment, a center portion **4005** of the sheet of material is shaped in a wave-like manner to produce a wave-like section at least partially forming the flow channels **4016** located between the broad sides **4022**, **4024** of the flat tube **4010**. The center portion **4005** can have any of the shapes described above with reference to the illustrated embodiment of FIG. **50**.

As an alternative to or in addition to using multiple folds **3930** to reinforce the narrow ends **3918**, **3920** of the one-piece flat tube **3910** (see FIG. **50**), the one-piece flat tube **4010** illustrated in FIG. **51** utilizes profiles **4015** (i.e., coils of wire, mandrels, hollow or solid inserts, and the like) at the narrow sides **4018**, **4020**. A profile **4015** can be located at either or both narrow sides **4018**, **4020**, and in some embodiments can supplement one or more folds produced at either or both narrow sides **4018**, **4020**, wherein such folds are similar to the folds **3930** described above in connection with FIG. **50**. During the manufacturing process of the one-piece flat tube **4010**, the profile **4015** can be uncoiled or otherwise laid longitudinally parallel to the sheet of material **4009**. Subsequent to processing wave-like section **4011** between the placed profiles **4015**, belt sections **4013** of the sheet of material adjacent the profiles **4015** are wrapped around the profiles **4015** from the outside, and are laid across the wave-like section **4011** to form the broad sides **4022**, **4024** of the one-piece flat tube **4010** as shown by the dashed arrows in FIG. **51**. The belt sections **4013** are connected to the wave-like section **4011**, and can also be connected to the profiles **4015** in the narrow

sides **4018**, **4020**. Also, each of the longitudinal edges **4078**, **4080** of the sheet of material **4009** is bent around a corresponding profile **4015** and placed upon a respective narrow side **4018**, **4020**.

Accordingly, the narrow sides **4018**, **4020** of the one-piece flat tube **4010** in FIG. **51** are each formed from one profile **4015** such that the narrow sides **4018**, **4020** are encompassed by one corresponding longitudinal edge **4078**, **4080** of the sheet of material **4009**.

FIGS. **52-54** illustrate one-piece flat tubes with integral inserts according to additional embodiments of the present invention. These embodiments employ much of the same structure and have many of the same properties as the embodiments of the flat tube described above in connection with FIGS. **50** and **51**. Accordingly, the following description focuses primarily upon the structure and features that are different than the embodiments described above in connection with FIGS. **50** and **51**. Reference should be made to the description above in connection with FIGS. **50** and **51** for additional information regarding the structure and features, and possible alternatives to the structure and features of the one-piece flat tubes with integral inserts illustrated in FIGS. **52-54** and described below. Structure and features of the embodiments shown in FIGS. **52**, **53**, and **54** that correspond to structure and features of the embodiments of FIGS. **50** and **51** are designated hereinafter in the **4100**, **4200**, and **4300** series of reference numbers, respectively.

FIGS. **52-54** each illustrate exemplary embodiments of a flat tube **4110**, **4210**, **4310** formed from a single sheet of material **4109**, **4209**, **4309** (e.g., a strip of aluminum, aluminum alloy or other metal or suitable material), and show such flat tubes **4110**, **4210**, **4310** prior to complete formation. In these particular embodiments of the flat tube **4110**, **4210**, **4310**, a portion **4105**, **4205**, **4305** of the sheet of material **4109**, **4209**, **4309** is shaped in a wave-like manner and extends between the broad sides **4122**, **4222**, **4322** of the flat tube **4110**, **4210**, **4310** in order to form flow channels **4116**, **4216**, **4316**. Additionally, each of the narrow sides **4118**, **4120**, **4218**, **4220**, **4318**, **4320** is at least partially formed by a connecting section **4117**, **4119**, **4217**, **4219**, **4317**, **4319** of the sheet of material **4109**, **4209**, **4309** and a longitudinal edge **4178**, **4180**, **4278**, **4280**, **4378**, **4380** encompassing the connecting section **4117**, **4119**, **4217**, **4219**, **4317**, **4319**.

In the illustrated embodiments of FIGS. **52** and **53**, the overlapping longitudinal edges **4178**, **4180**, **4278**, **4280** and connecting sections **4117**, **4119**, **4217**, **4219** provide a doubled wall thickness at the narrow sides **4118**, **4120**, **4218**, **4220**, which is generally stable enough for numerous applications of the flat tube **4110**, **4210**, **4310** in which the relatively thin wall materials (described above) are used. In other embodiments, such as in the illustrated embodiment of FIG. **54**, a relatively stronger reinforcement of the narrow sides **4118**, **4120**, **4218**, **4220** can be achieved through one or more folds **4330** of the connecting sections **4317**, **4319**. In other words, those portions of the sheet of material **4309** that will be overlapped by the longitudinal edges **4378**, **4380** at the narrow sides **4318**, **4320** can be further reinforced by one or more folds **4330**. In such embodiments, these folds **4330** are shaped (e.g., rounded) to at least partially define the narrow sides **4318**, **4320** when the sheet of material **4309** is bent to bring the first and second broad sides **4322**, **4324** to their closed positions. Alternatively or in addition, the longitudinal edges **4378**, **4380** at the narrow sides **4318**, **4320** can be provided with one or more of such reinforcing folds **4330** in a manner similar to the Group D flat tube embodiments illustrated in FIG. **34**, for example. In these embodiments utilizing reinforcing folds **4330**, the narrow sides **4318**, **4320** include a

relatively larger thickness than the thicknesses of the wave like section **4311** and the broad sides **4322**, **4324**. Accordingly, it is possible to provide sufficient reinforcement for relatively more heavily stressed parts of the flat tube **4310**, such as the narrow sides **4318**, **4320**, and leave relatively less stressed parts, such as the broad sides **4322**, **4324** and/or the wave-like section **4311** with relatively thinner walls.

Although reinforcing folds **4330** can be employed in any of the narrow side locations described above for any of the embodiments also described above in connection with FIGS. **52-54**, it should be noted that either of the narrow sides **4118**, **4120**, **4218**, **4220**, **4318**, **4320** can be devoid of such reinforcing folds in other embodiments. Also, the number of such reinforcing folds **4130**, **4230**, **4330** at one of the narrow sides **4138**, **4238**, **4318** can be different from the number at the other narrow side **4120**, **4220**, **4320**, and/or the location of the reinforcing folds **4130**, **4230**, **4330** at one of the narrow sides (e.g., only on the connecting section **4117**, **4119**, **4217**, **4219**, **4317**, **4319** or only on the longitudinal edge **4178**, **4180**, **4278**, **4280**, **4378**, **4380** overlapping the connecting section **4117**, **4119**, **4217**, **4219**, **4317**, **4319**) can be different from the location of the reinforcing folds **4130**, **4230**, **4330** at the other narrow side (e.g., only on the longitudinal edge **4178**, **4180**, **4278**, **4280**, **4378**, **4380** or only on the connecting section **4117**, **4119**, **4217**, **4219**, **4317**, **4319** overlapped by the longitudinal edge **4178**, **4180**, **4278**, **4280**, **4378**, **4380**, respectively).

In any of the embodiments just described in connection with the one-piece flat tubes **4110**, **4210**, **4310** illustrated in FIGS. **52-54**, the overlapping longitudinal edges **4178**, **4180**, **4278**, **4280**, **4378**, **4380** of the sheet of material **4109**, **4209**, **4309** can lie in a wall gradation **4158**, **4160**, **4258**, **4260**, **4358**, **4360**, such as a wall gradation **4158**, **4160**, **4258**, **4260**, **4358**, **4360** located near or at the narrow side **4118**, **4218** at which the longitudinal edge **4178**, **4180**, **4278**, **4280**, **4378**, **4380** lies. In this manner, when the longitudinal edges **4178**, **4180**, **4278**, **4280**, **4378**, **4380** are moved toward their closed positions to form the one-piece flat tube **4110**, **4210**, **4310** (shown by dashed arrows in each of FIGS. **52-54**), the longitudinal edges **4178**, **4180**, **4278**, **4280**, **4378**, **4380** can be received within the wall gradations **4158**, **4160**, **4258**, **4260**, **4358**, **4360** encompassed thereby. In some embodiments, a wall gradation **4158**, **4160**, **4258**, **4260**, **4358**, **4360** is provided on each broad side **4122**, **4124**, **4222**, **4224**, **4322**, **4324** of the flat tube **4110**, **4210**, **4310**.

As with the illustrated embodiment of FIG. **51**, the wave peaks and wave valleys of the wave-like sections **4111**, **4211**, **4311** (or other features of the center portion **4105**, **4205**, **4305** having different shapes defining the flow channels **4116**, **4216**, **4316**) illustrated in FIGS. **52-54** can be brazed, welded, or secured in any other suitable manner to either or both broad sides **4122**, **4124**, **4222**, **4224**, **4322**, **4324** of the one-piece flat tube **4110**, **4210**, **4310**.

As mentioned above, each of the one-piece flat tubes **4110**, **4210**, **4310** illustrated in FIGS. **52-54** have a wave-like section **4111**, **4211**, **4311** for defining the flow channels **4116**, **4216**, **4316**. The portion **4105**, **4205**, **4305** defining this wave-like section **4111**, **4211**, **4311** can have any of the shapes described above with reference to the illustrated embodiment of FIG. **50**. In the illustrated embodiments of FIGS. **52** and **54**, for example, the wave-like section **4111**, **4311** defines a number of flow channels **4116**, **4316** with a generally triangular design and having generally the same cross-sectional shape and size (although either or both can vary across the width of the one-piece flat tube **4110**, **4310**). FIG. **53** illustrates a wave-like section **4211** provided with more than one wave design such that the wave-like section **4211** forms flow chan-

nels **4216** of at least two different cross-sectional sizes. The wave-like section **4211** shown in FIG. **53** includes one group of seven flow channels **4216** each having a relatively large cross-sectional area, and another group of six channels **4216** each having a relatively smaller cross-sectional area. In other embodiments, any other combination of flow channel shapes and sizes arranged in sections of the one-piece flat tube **4210** can be employed. Certain requirements for heat exchange can best be addressed with such illustrations of the heat exchanger tube **4210**. Although the cross-sectional shape of these flow channels **4216** of varying size is generally rectangular in FIG. **53**, it is envisioned that the wave-like section **4216** can define flow channels **4216** with other shapes, based at least in part upon the desired specifications of the flat tube **4210**. As indicated above, the design of the wave-like section **W** is not limited to the design illustrated herein.

Any of the flat tubes described herein can be produced in a number of different manners. However, by utilizing one or more manufacturing improvements discovered by the inventors and described in greater detail below, such tubes can be produced at significant cost savings, with improved efficiency, at greater speed, and/or in a more reliable and reproducible manner compared with many conventional flat tube manufacturing techniques.

One such improvement discovered by the inventors relates to the manner in which flat tubes according to the present invention can be separated from an endless length of flat tubing (i.e., from a continuous supply of materials fed through manufacturing equipment), thereby resulting in discrete flat tubes having desired lengths. As used herein and in the appended claims, the term "endless tube" is used to refer to flat tubing according to any of the embodiments described herein produced by forming one or more sheets of material running from respective supplies (e.g., coils) prior to separation into discrete tubes at desired lengths, and therefore incorporates the earlier definition of "endless" described above. It will be appreciated by those in the art that significant challenges exist in cutting or otherwise separating elements constructed at least in part of relatively thin-walled products without creating deformations, burrs, flashing, or other undesirable features on the end products. Although similar problems exist in products constructed of thicker-walled materials (which can be addressed equally with some improvements described below), in many cases such problems more frequently result in unacceptable thin-walled end products. With reference to the thin-walled flat tube embodiments described herein, many of these embodiments have a tube wall thickness of no greater than about 0.15 mm (0.00591 in). The tube walls can have a thickness of at least about 0.03 mm (0.001181 in) in some embodiments. Also, in those tube assembly embodiments having an insert as described herein, many of these embodiments have an insert material thickness of no greater than about 0.10 mm (0.003937 in). The material thickness of the insert can be no less than about 0.03 mm (0.00118 in) in some embodiments.

The inventors have discovered that individual (i.e., discrete) flat tubes can be produced in a superior manner from endless tubing of one or more sheets of material fed through manufacturing equipment by perforating at least one of the sheets. That is, at least one part of the tube can be perforated to facilitate improved tube separation from the endless tubing. Such perforations can take place before shaping operations are performed on the upstream sheet material, after the sheet material has been formed into a continuous length of flat tubing, or at any other stage or stages therebetween. Also, the locations of such perforations can vary between the different

sheets of materials (or different locations on the same sheet of material) used to produce different parts of the continuous flat tubing.

An advantage of forming perforations in the sheet metal strips for making flat tubes is that in some embodiments, flat tubes can be produced substantially without the formation of deformations, burrs, flashing and/or other undesirable features on the end products. The process of using perforations in a tube separating process can be applied to any of the tube embodiments described herein.

As an example of the perforating and separating process used to produce one-piece flat tubes, reference is hereby made to the process of separating one-piece flat tubes such as those illustrated in FIGS. **19-21**, **52**, and **53**, wherein the one-piece flat tube **1210**, **1310**, **1410**, **4110**, **4210** can be formed from a single endless sheet of material. In FIGS. **52** and **53**, the one-piece flat tubes **4110**, **4210** are shown in a state of the manufacturing process shortly before completion, and must still be closed in the direction of the arrows shown in dashed lines before being separated at perforations already made. Accordingly, perforations can be formed prior to bending the sheet of material as shown in FIGS. **52** and **53**. A similar concept can be applied to the tubes **1210**, **1310**, **1410** shown in FIGS. **19-21** and in other one-piece flat tubes described herein.

As an example of this process used to produce two-piece flat tubes, reference is hereby made to the process of separating two-piece flat tubes such as that illustrated in FIG. **28**. As described in greater detail above, the two-piece flat tube **1910** shown in FIG. **28** has first and second portions **1912**, **1914** defining respective broad sides **1922**, **1924** of the flat tube **1910**, and an insert **1934** received therebetween. As also described above, the first and second portions **1912**, **1914** can be identical or substantially identical, but inverted with respect to each other, where one of longitudinal edges of one tube portion **1914** has a larger arc portion **1968** at least partially encompassing a smaller arc portion **1962** on the longitudinal edge of the other tube portion **1912**. Folds **1970** at either or both longitudinal edges **1938**, **1940** of the insert **1934** can be used to reinforce the narrow sides **1918**, **1920** of the two-piece flat tube **1910**. Although the perforating and separating process described herein can be applied to two-piece flat tubes having any of the tube part and tube dimensions described above in connection with the embodiment of FIG. **19**, the insert **1934** described in connection with FIGS. **55-58** has a thickness of about 0.03-0.09 mm (0.0011811-0.0035433 in), the sheets of material forming the first and second tube portions **1912**, **1914** have a thickness of about 0.03-0.15 mm (0.0011811-0.0059055 in), and the completed two-piece flat tube **1910** has a small diameter d of about 1-10 mm (0.03937-0.3937 in) by way of example only. In FIG. **28**, the two-piece flat tube **1910** is illustrated shortly before completion, wherein the perforations are already formed in the first and second portions **1912**, **1914** and the insert **1934**, and have been reconciled such that the perforations in the first and second portions **1912**, **1914** and the insert **1934** are substantially aligned.

FIGS. **55-58** illustrate an exemplary manufacturing line **1900** similar to the manufacturing line **3701** shown in FIG. **49**. In this particular case, the manufacturing line **1900** is designed to form three-piece flat tube assemblies (i.e., having a two-piece flat tube with first and second portions **1912**, **1914**, and also having an insert **1934**), while manufacturing line **3701** is designed for forming two-piece flat tube assemblies (i.e., having a one-piece flat tube defining first and second portions **1212**, **1214**, **1312**, **1314**, **1412**, **1414**, **4112**, **4114**, **4212**, **4214**, and also having an insert **1234**, **1334**, **1434**,

4134, 4234). Although the manufacturing lines 3701, 1900 are described herein with reference to the production of particular flat tube embodiments also described in this patent application, such is by way of example only. Accordingly, it is to be understood that the processes described with reference to FIG. 49 and FIGS. 55-58 can be applied for the manufacture of all tubes described in this application.

As shown in FIG. 55, manufacturing line 1900 includes three coils of sheet material R1, R2, R3, such as sheets of aluminum, aluminum alloy, or other suitable material for the formation of three-piece flat tube assemblies. In this particular example, sheet material from the first coil R1 is used to produce a first portion 1912 or 1914, sheet material from the third coil R3 is used to produce a second portion 1914 or 1912, and sheet material from the second coil R2 is used to produce the insert 1934 for the two-piece flat tube 1910. Depending at least in part upon the paths of the sheets of material, other possible positions of the coils with respect to a manufacturing line, and the resulting orientation of the flat tube 1910 as it proceeds through the manufacturing process, each coil R1, R2, R3 can have sheet material used to produce any of the portions of the flat tube 1910 in other embodiments.

FIG. 55 illustrates sets of rolls 1921, 1923, 1925 for processing sheet material provided from the coils R1, R2, and R3, respectively. Each set of rolls 1921, 1923, 1925 can be arranged to define a respective loop of traveling sheet material as shown schematically in FIG. 55, although any other arrangement of rolls is possible. Any one or more of the rolls in each set 1921, 1923, 1925 can be driven by a suitable motor or prime mover in order to draw material being provided by the coils R1, R2, and R3. Also, any one or more of the rolls in each set 1921, 1923, 1925 can be idler rolls permitting free travel of a corresponding sheet of material thereover. Furthermore, any of the rolls in each set 1921, 1923, 1925 can perform both functions, such as by being selectively driven through a clutch, or otherwise being selectively driven in any other conventional manner. It will also be appreciated that the coils of material R1, R2, R3 themselves can be driven by suitable motors or other prime movers. By way of example, it is envisioned that the sheets of material supplied from the coils R1, R2, and R3 can move in some embodiments at a linear speed of about 100-200 m/min. (328.08-656.16 ft/min.). Slower or faster speeds are possible in other embodiments.

By controlling the motor(s) driving each coil of material R1, R2, R3 and/or driving any of the rolls in the sets of rolls 1921, 1923, 1925 it is possible to control the maximum speed of each sheet of material, such as by selectively providing a braking force upon any of the sheets of material. In some embodiments, this enables the speed of each sheet of material to be controlled independently of the others—even to the point of stopping one or two of the sheets while moving the others. Also, the sets of rolls 1921, 1923, 1925 can function to permit a certain buffering of the sheet material supplied to downstream locations.

The manufacturing line 1900 illustrated in FIG. 55 includes a first perforation station 1927 for forming perforations 1929 in the sheet of material received from the second coil R2 (for producing the insert 1934 in a later flat tube 1910). This perforation station 1927 is located at the beginning of the manufacturing line 1900 in FIG. 55, but can instead be downstream of this location in other embodiments. Subsequently, the sheet of material forming the insert 1934 is shaped by a set of rollers schematically illustrated in FIG. 55 as forming section 1931. The sheets of material from the first and third coils R1, R3 (for producing the first and second portions 1912, 1914 in a later flat tube 1910) are transported

along the distance defined by the forming section 1931. Subsequently, the sheet of material from the first coil R1 reaches a second perforation station 1933, and the sheet of material from the third coil R3 reaches a third perforation station 1935 adjacent the second perforation station 1933. In other embodiments, the three perforation stations 1927, 1933, 1935 can be in different locations with respect to one another and/or the other portions of the manufacturing line 1900. Also, in other embodiments, one or more of the perforation stations 1927, 1933, 1935 can be used to perforate more than one sheet of material.

With continued reference to the illustrated embodiment of FIG. 55, the second and third perforation stations 1933, 1935 form perforations 1929 on the first and third sheets of material for the first and second portions 1912, 1914 of the flat tube 1910, respectively, while the second sheet for the insert 1934 is passed between the first and third sheets at the second and third perforation stations 1933, 1935. An example of perforations produced at the second and third perforations stations is shown in FIG. 57, and can be similar to the perforations produced in the first perforation station 1927 described above. In the embodiment of FIG. 57, the perforations 1929 are relatively fine openings separated by webs 1937 located at predetermined distances between the perforations 1929. However, in other embodiments the perforations can each be areas of reduced thickness of the material, and need not necessarily be defined by openings through the material. In either case, the description herein regarding the shape, size, and other features of perforations apply equally.

The webs 1937 are broken off as part of the manufacturing process of the flat tube 1910. In some embodiments, the length of the perforations 1929 extending in the transverse direction of the perforated sheets of material (from the first, second, or third coils R1, R2, and R3) is at least 1 cm (0.3937 in). Also, in some embodiments the length of each web 1937 is less than 1 mm (0.03937 in).

The shape (e.g., length) and arrangement of the perforations 1929 illustrated in FIG. 57 are presented by way of example only. Longer or shorter perforations 1929 and longer or shorter webs 1937 can be used as desired in any of the sheets of material used to form the flat tube 1910. For example, each of the perforations 1929 can instead be substantially round or can take other shapes desired, potentially resulting in fewer or more perforations across the sheet of material. Also for example, the length or other shape features of the perforations 1929 can vary across the width of the sheet of material being perforated, such as by providing perforations and/or webs proximate the longitudinal edges of the sheet that are longer than those at the center of the sheet, or vice versa. The types and features of the perforations 1929 depend at least in part upon the material properties of the sheet being perforated.

Based upon the perforation dimensions and the relatively thin sheet materials that can be used as described above, in some embodiments in webs 1937 between perforations 1929 are generally not visible with the naked eye. For many manufacturing operations, advantages can be achieved by locating a web 1937 near each longitudinal edge of a sheet of material being perforated, thereby reducing the opportunity for parts of the sheet of material to accumulate in such locations during later processing of the sheet.

In those flat tube embodiments described herein in which one or more sheets of material (e.g., sheet metal strips) are used to produce a flat tube, sheets of material can be perforated for separation at the perforations. In those embodiments in which two or more sheets of material are used to produce a flat tube, two or more of the sheets can be perforated, after

which time the perforations in the different sheets can be aligned (e.g., in a common plane substantially perpendicular to the sheets, the direction of travel of the sheets, and/or the flat tube produced by the sheets), and individual tubes can be separated at the perforations from the continuous length of upstream material. The perforation alignment just described can be achieved in some embodiments by controlling the speed of one or more drives feeding one or more of the sheets of material through the manufacturing process. More specifically, if perforations of any two or more sheets of material are not already aligned, one or more of the sheets can be moved at different speeds until the perforations are aligned to be able to separate individual tubes at a downstream location. In this regard, it should be noted that this alignment process can take place for any number of perforated sheets of material being used to produce the flat tubes.

For example, and with continued reference to the embodiment of FIGS. 55-58 the perforations 1929 in the three sheets of material from coils R1, R2, and R3 are aligned in an aligning section 1939 of the manufacturing line 1900 by one or more drives controlled to adjust the speeds of the sheets of material with respect to one another. In light of the fact that speed adjustments of one or more sheets may be necessary to align the perforations 1929, the aligning section 1939 of FIG. 55 is generally placed in the manufacturing line 1900 upstream from a merging section 1941. The merging section 1941 is an area of the manufacturing line where the parts of the flat tube 1910 (e.g., first and second portions 1912, 1914 and insert 1934, in the illustrated embodiment) are connected with each other to form the flat tube 1910. The merging section 1941 can include rolls or other sheet forming elements for merging the parts of the flat tube 1910 to form an endless tube 1910. In those embodiments where none or only some of the longitudinal edges of the first and second tube portions 1912, 1914 have not already been formed at one or more upstream locations, the merging section 1941 can also include rolls and/or other sheet forming elements for performing other shaping operations on the longitudinal edges of the first and second portions 1912, 1914.

The continuous length of material immediately upstream of this separating location can be a continuous length of completed flat tubing. Alternatively, the continuous length of material immediately upstream of the separating location can be sheet(s) of material used to form the flat tubing at any stage of such formation. For example, in some embodiments, after perforations in the sheets of material have been aligned, partially-formed sheets of material can be combined into a continuous length of completed flat tubing, such that completed tubes are available after the separation. As a result, individual tubes can be created that have no impressions on the flat tube ends.

In some constructions of a manufacturing line, perforations generally are formed by one or more perforating rollers. For example, a manufacturing line can include at least pair of perforation rollers. One of the rollers of the pair can run with one or more endless sheets of material that will be used to form at least part of the flat tube, and the other roller of the pair can be equipped with a tool (e.g., one or more perforating blades or stamps) for forming perforations in the sheet(s) of material. FIGS. 56 and 57 schematically illustrate a perforation process according to an embodiment of the present invention. For ease of description, the following description is with reference to the first perforation station 1927 described above. However, the same description applies equally to the other perforation stations 1933, 1935 in the illustrated embodiment of FIGS. 55-58, although one or more of the perforation stations can be different in other embodiments

(e.g., can have different blades, use only a single roll rather than two rolls, and the like). As described earlier, the number and type of perforations, and the locations of the perforation stations can vary. Changes to these features can be based at least in part upon desired specifications of the flat tube 1910 produced in the manufacturing line 1900.

With reference to the embodiment of FIGS. 56 and 57, the perforation station 1927 includes a pair of perforation rollers having a first perforation roller 1943 and a second perforation roller 1945. In some embodiments, these perforation rollers 1943, 1945 can be arranged in any other orientation desired, depending at least in part upon the orientation of the sheet perforated by the perforation rollers 1943, 1945 and adjacent portions of the manufacturing line 1900. The first roller 1943 runs parallel to and guides one or more of the passing sheets of material (from coils R1, R2, and R3), while the lower roller 1945 has a protruding perforation stamp 1947.

To prevent sheet accumulation as perforations are created, some embodiments of the present invention utilize perforation rollers with one or more perforation blades or stamps having a standby position. In the standby position, at least one of the perforation rollers is rotated or translated to a position where the sheet(s) of material pass freely through the perforation rollers.

For example, the second roller 1945 illustrated in FIG. 56 has a driving mechanism (not shown), such that the second roller 1945 can hold the perforation stamp 1947 in a standby position in which the perforation stamp 1947 does not engage the passing sheets of material from coils R1, R2, and R3. In the standby position of the second roller 1945, the perforation stamp 1947 can be rotated a distance from the position shown in FIG. 56 to avoid this engagement, such as by being rotated approximately 90 degrees to a substantially horizontally position on the second roller 1945. In other embodiments, either or both rollers 1943, 1945 can be mounted upon respective axles that are moved with respect to the passing sheet, thereby enabling either or both rollers 1943, 1945 to translate with respect to the passing sheet and defining standby and perforation or action positions.

To perforate the sheet of material supplied from the second coil R2 (again with reference to the illustrated embodiment of FIGS. 55-58 by way of example), the second roller 1945 can be actuated to a perforation or action position, such as to the upper and substantially vertical position shown in FIGS. 56 and 57. This actuation can be performed by a motor, actuator, or other drive connected to the second roller to rotate the second roller from the standby position to the perforation or action position at a rotation speed. In the perforating position of the first and second rollers 1943, 1945, the perforation stamp 1947 engages the sheet of material supplied from the second coil R2, and forms perforations 1929 therein. In some embodiments, the rotational speed (and therefore, the circumferential speed) of the second roller 1945 is higher than the transport speed of the sheet of material to insure that the sheet of material does not accumulate during perforation operations. In other embodiments, the rotational speeds (and therefore, the circumferential speeds) of both rollers 1943, 1945 are higher than the transport speed of the sheet of material for this purpose. It should be noted that the terms "action position" or "perforating position" as used herein and in the appended claims do not alone indicate or imply that the subject roller(s) are stationary, but is rather indicative of the positions of the roller(s) at the moment when the perforations are made.

In some embodiments, the rotation speed of either or both roller 1943, 1945 of the perforation station 1927 is faster than that of the passing sheet of material. Following the creation of

perforations in the perforating position, either or both perforating rollers **1943**, **1945** can be moved back to a standby position to be reactivated in the next perforation process. In some embodiments, movement of either or both perforating rollers **1943**, **1945** back to a standby position is performed by rotating the perforating roller(s) **1943**, **1945** in the same direction used to move the roller(s) **1943**, **1945** toward a perforating position (rather than by switching the rotational directions of the roller(s) **1943**, **1945**). Accordingly, driving the pair of perforating rollers **1943**, **1945** as described above can help prevent accumulation of the passing sheet material.

It is envisioned that finished tubes can be separated at the end of a manufacturing process due at least in part to perforations described above. In some embodiments, the tubes are separated at the perforations at or near the end of a manufacturing line. Separation of individual tubes can be accomplished in some embodiments by using a pair of breaking rollers or a single breaking roller. In the embodiment of FIG. **58**, for example, a breaking roller **1949** and a bar **1951** are used to separating endless tubing running between the breaking roller **1949** and the bar **1951** into individual finished flat tubes **1910**. The breaking roller **1949** is equipped with a protruding breaking knife **1951** or other tool used to break the webs **1937** between the perforations **1929** described earlier.

The breaking roller **1949** and/or the bar **1951** can be controlled to include a standby position in which passing tubing is not slowed or otherwise operated upon, and a breaking position in which the breaking roller **1949** and/or bar **1951** is moved to engage the passing tubing and to separate the tube at the perforations **1929**. For example, in the illustrated embodiment of FIG. **58**, the breaking roller **1949** is rotatable to and from a breaking position in which the breaking knife **1951** of the breaking roller **1949** engages flat tubing and passes by the breaking bar **1951**, thereby breaking (and in some embodiments, also cutting) the flat tubing running between the breaking roller **1949** and the breaking bar **1951** at a line of perforations **1929**. In other embodiments, the breaking roller **1949** and/or the breaking bar **1951** are translated with respect to the flat tubing to define breaking and standby positions of a breaking station.

Although flat tubing can be broken by the use of a breaking roller **1949** and a breaking bar **1951** as described above, in other embodiments the webs **1937** defined by perforations **1929** of the flat tubing are not broken or cut by a blade or other similar tool, but are instead ripped by generating a force upon the flat tubing in a general longitudinal direction of the endless tube, thus forming individual flat tubes **1910**. Such a force can be generated, for example, by passing the endless tubing by a roller engaging the tubing and running at a higher speed than the tubing. Through experimentation it has been found that this manner of separation can result in desirable tube ends as described above.

In some embodiments, one or more rollers **1949** in the portion of the manufacturing line used to break the tubing can be used to help advance the tubing along the manufacturing line. This is also true for any of the perforation stations **1927**, **1933**, **1935** described herein. It should also be noted that in any of the embodiments described herein, the stamp, blade, or other tool on a roll of any perforation station **1927**, **1933**, **1935** and/or on the breaking roller **1949** can be retractable to permit the roll to be driven for advancing the tubing without other action thereon. In such cases, the retracted position of the tool can also define the standby position described herein.

Additional aspects of manufacturing flat tubes described herein can also enable such tubes to be produced at significant cost savings, with improved efficiency, at greater speed, and/or in a more reliable and reproducible manner compared with

many conventional flat tube manufacturing techniques. As will now be described, some of these additional aspects relate to the manner in which the parts of the flat tubes are formed and/or to the manner in which these parts are brought together to produce the flat tubes. By way of example only, these processes will now be described and illustrated with reference to the production of two-piece tubes, and more specifically to the two-piece tube **1910** illustrated in FIG. **28** and described above, produced using the manufacturing line **1900** illustrated in FIG. **55** and also described above. The following description and accompanying drawings apply equally to the production of any of the other two-piece tubes (with or without inserts) described herein. Also, with the exception of inconsistent or incompatible description, the following description and accompanying illustrations apply equally to the production of any of the one-piece tubes (with or without inserts) also described herein.

The inventors have discovered that significant advantages can be obtained by certain manners of assembling the first and second portions **1912**, **1914** and insert **1934** of the tube assembly **1910**. In some embodiments for example, the internal insert **1934** is rolled in a corrugated manner in a longitudinal direction of the manufacturing line **1900**, and is inserted between the two flat tube portions **1912**, **1914** of the later flat tube **1910**. The longitudinal edges of the two flat tube portions **1912**, **1914** can be rolled or otherwise formed with arc-like edges in the longitudinal direction, after which time the arc-like edges can be brought together to engage one another in order to form the flat tube **1910** shown in FIG. **28**. This process is illustrated schematically in FIGS. **55**, **59**, and **60**, and will now be described in greater detail.

As described earlier, FIG. **55** shows three coils of sheet material **R1**, **R2**, and **R3** supplying sheet material to be used in producing the flat tube **1910**. As also described above, the sheets of material from coils **R1**, **R2**, and **R3** are used to manufacture a first tube portion **1912**, an insert **1934** (using the widest sheet of material, in some embodiments), and a second tube portion **1914**. The sheets of material used to form these parts run in generally parallel directions with respect to one another through the illustrated manufacturing line **1900**.

Although other manufacturing line arrangements are possible, the manufacture of flat tubes **1910** in manufacturing line **1900** illustrated in FIG. **55** generally begins with the formation of the insert **1934** in the first sections of the manufacturing line **1900**. In some embodiments, the sheets of material used to form the first and second tube portions **1912**, **1914** can be guided without being deformed. In such embodiments, when the process of forming the insert **1934** has been completed, the process of forming the first and second tube portions **1912**, **1914** generally begins. Alternatively, one or more forming operations can be performed on either or both of these sheets of material while the insert **1934** is being formed at one or more of the same locations along the manufacturing line **1900**. In many cases, the process of manufacturing the first and second tube portions **1912**, **1914** can be significantly shorter than that for manufacturing the insert **1934**, due to the fact that the relative amount of deformation of the material used to form the first and second tube portions **1912**, **1914** can be relatively small (see, for example, the flat tube assembly shown in FIG. **28**).

The two-piece flat tube **1910** illustrated in FIG. **28** has identical or substantially identical first and second portions **1912**, **1914**. The manufacturing line **1900** illustrated in FIG. **55** is adapted to produce these portions **1912**, **1914**. By virtue of their identical or substantially identical shapes, one portion **1912** is inverted with respect to the other before the portions **1912**, **1914** are joined together. As described above, the

55

manufacturing line 1900 illustrated in FIG. 55 has forming rolls or other suitable forming devices for producing the arc-shaped edges of the portions 1912, 1914 described above.

In some cases, sets of forming rolls or other suitable forming devices used to create the same type of longitudinal edge in both tube portions 1912, 1914 are located on the same lateral side of the manufacturing line 1900 (e.g., sets used for producing the larger arc-shaped longitudinal edge of both portions 1912, 1914 being located next to one another in the plane of the sheets of material being formed). In these and other embodiments, the forming rolls or other suitable forming devices can be arranged such that the two portions 1912, 1914 have the same orientation after formation of some or all of the longitudinal edges. In such embodiments, the manufacturing line 1900 can be provided with suitable rollers to flip one of the portions 1912, 1914 about a longitudinal axis so that the two portions 1912, 1914 can be joined in the merging section 1941 of the manufacturing line 1900. In other embodiments, the forming rolls or other suitable forming devices can be arranged in the manufacturing line 1900 such that the two portions 1912, 1914 already have orientations that are inverted with respect to one another (i.e., with their longitudinal sides reversed) after formation of some or all of the arc-shaped edges. In such embodiments, the two portions 1912, 1914 can be parallel to one another, and can be combined in the merging section 1941 of the manufacturing line 1900.

As described in greater detail above in connection with FIG. 28, one longitudinal edge of the first tube portion 1912 encompasses a corresponding longitudinal edge of the second tube portion 1914, while an opposite longitudinal edge of the first tube portion encompasses a corresponding opposite longitudinal edge of the second tube portion 1914 to join the tube portions 1912, 1914 together. In these and other embodiments described herein that can be produced in the manufacturing line 1900, the first and second wall portions 1912, 1914 can be identical or substantially identical. In other embodiments described herein that can also be produced in the manufacturing line 1900, the first and second wall portions 1912, 1914 are not identical, such as where each of the first and second tube portions 1912, 1914 includes either two smaller arc portions or two larger arc portions.

With continued reference to the embodiment of FIGS. 55-60 in conjunction with the flat tube assembly illustrated in FIG. 28, the internal insert 1934 of the assembly can be manufacturing on a third roll set for introduction between the first and second tube portions 1912, 1914 of the two-piece tube 1910. This process is illustrated schematically in FIG. 59, and can take place after the first and second tube portions 1912, 1914 have been formed or substantially entirely formed (as is the embodiment in FIG. 59). In this embodiment, the first and second tube portions 1912, 1914 are not in one plane, but are in two planes at a distance from one another, while the set of forming rolls or other suitable forming devices producing the insert 1934 are positioned so that the sheet of material forming the insert 1934 is located between the sheets of material forming the first and second tube portions 1912, 1914. This allows the internal insert 1934 to be "threaded" in and between the two tube portions 1912, 1914. In other words, the layout of the manufacturing line 1900 illustrated in FIG. 55 is such that the sheet of material used to form the insert 1934 is located between the sheets of material used to form the first and second tube portions 1912, 1914.

With reference to FIG. 59, insertion of the internal insert 1934 as just described can be performed between first and second tube portions 1912, 1914 running substantially parallel to one another along a longitudinal section of the first and

56

second tube portions 1912, 1914 in the manufacturing line 1900. In other embodiments, however, the planes in which the first and second broad sides 1922, 1924 of the first and second tube portions 1912, 1914 lie need not necessarily be parallel to one another at any location other than immediately upstream of the merging section 1941 of the manufacturing line 1900.

In the illustrated embodiment (see FIG. 59(a)) and in other embodiments, the sheet of material used to form the insert 1934 is substantially parallel to either or both sheets of material used to form the first and second tube portions 1912, 1914 prior to the process of inserting the insert 1934 into the first and second tube portions 1912, 1914. In other embodiments, other orientations of these three sheets upstream of the insertion process are possible. However, in some embodiments, the process of inserting the internal insert 1934 into the first and second tube portions 1912, 1914 begins by orienting the internal insert 1934 between the first and second tube portions 1912, 1914 at an inclination with respect to at least one of the planes of the first and second broad sides 1922, 1924. For example, in the illustrated embodiment of FIG. 59, the internal insert 1934 is introduced into and between the first and second tube portions 1912, 1914 at an inclination with respect to both of the planes of the first and second broad sides 1922, 1924.

As used herein and in the appended claims, the term "inclined" in its various forms expresses the position of the insert 1934 with respect to the broad sides 1922, 1924 of the tube portions 1912, 1914 (which can be parallel to one another, in some embodiments). In this regard, it should be noted that either or both broad sides 1922, 1924 of the first and second tube portions 1912, 1914 can be in respective planes that are not horizontal, whereby the insert 1934 would be inclined with respect to such non-horizontal orientations.

This inclined insertion can take place in a range of locations upstream of the merging section 1941 of the manufacturing line 1900, and in some embodiments occurs approximately at the beginning stages of the manufacturing line 1900. In some embodiments, the angle of the insert 1934 (with respect to the plane in which a broad side 1922, 1924 of at least one of the tube portions 1912, 1914 lies) can be at least about 25 degrees in at least one location of the insert 1934 between the sheets used to produce the first and second tube portions 1912, 1914, such as at the beginning of the insertion process. In other embodiments, this angle is at least about 30 degrees for good performance results. Also, in some embodiments, the angle of the insert 1934 as described above is no greater than about 45 degrees in at least one location of the insert 1934 between the sheets used to produce the first and second tube portions 1912, 1914, such as at the beginning of the insertion process. In other embodiments, this angle is no greater than about 40 degrees for good performance results.

Subsequently, the internal insert 1934 is brought into an orientation in which the internal insert 1934 is parallel or substantially parallel to the broad sides 1922, 1924 of the first and second tube portions 1912, 1914. FIGS. 59(b)-(e) show an example of the change or decrease of the inclined position of the insert 1934, as well as the gradual converging of the first and second tube portions 1912, 1914 to hold the insert 1934 therebetween.

In those embodiments (like that of FIG. 28) in which the either or both longitudinal edges 1938, 1940 of the internal insert 1934 are received within the narrow side(s) 1918, 1920 of the flat tube 1910, the shape of the longitudinal edges 1938, 1940 can provide a snug fit against the inner surface of the first and second tube portions 1912, 1914 at the narrow sides 1918, 1920. For example, in those embodiments in which either or

57

both longitudinal edges **1938**, **1940** of the insert **1934** are arc-shaped or have a series of folds **1970**, the features can be received within the interior of arc-shaped longitudinal edges of the first and second tube portions **1912**, **1914**. In these and other embodiments of the insert **1934**, one longitudinal edge **1938** of the insert **1934** can be placed into a longitudinal arc-like edge of a first wall portion **1912**, at or after which time the insert **1934** can be inclined with respect to the broad sides **1922**, **1924** of the first and second tube portions **1912**, **1914**.

As mentioned above, the inclination of the insert **1934** can be reduced to zero (i.e., the insert **1934** can be moved to a position parallel or substantially parallel to the broad sides **1922**, **1924** of the first and second tube portions **1912**, **1914**). In this manner the opposite longitudinal edge **1940** of the insert **1934** can assume a qualitatively correct position in the longitudinal arc-like edge of the second tube portion **1914**. Both first and second tube portions **1912**, **1914** can be brought together during any part of this process, after which time the longitudinal edges of the first and second tube portions **1912**, **1914** that surround the internal insert **1914** are closed as schematically illustrated in FIG. **59(e)**. It should be noted that by closing the flat tube **1910** as described herein, the insert **1934** is deformed in some embodiments. The insert **1934** within the closed flat tube **1910** can remain under compression against any of the broad or narrow sides **1922**, **1924**, **1918**, **1920** of the flat tube **1910**, particularly in those embodiments (such as in FIGS. **55-60**) in which the insert **1934** was deformed in order to insert the insert **1934** within the flat tube.

In the illustrated embodiment, closure of the first and second flat tube portions **1912**, **1914** is provided by bending the adjacent longitudinal edges of the first and second tube portions **1912**, **1914** in a manner as described and shown in greater detail above in connection with the embodiments of FIGS. **25**, **26** and **28** (i.e., by bending larger arc portions of the longitudinal edges about smaller arc portions of adjacent longitudinal edges of the tube portions **1912**, **1914**). Accordingly, the manufacturing line **1900** illustrated in FIG. **55** can be used to produce flat tubes **1900** in which either or both longitudinal edges of an insert **1934** arc received within respective corresponding bent edges of tube portions **1912**, **1914** at the narrow sides **1918**, **1920** of the flat tube **1910**.

Following closure of the flat tube **1910** in the manufacturing line **1900**, finished flat tubes **1910** can be attached to one or more sets of fins or other elements (not shown), and can also be secured to the one or more headers of a heat exchanger (also not shown). In many embodiments, the headers of the heat exchanger is brazed in a brazing furnace, as are the fins or other heat exchange elements to the flat tubes **1910**, and the flat tubes **1910** to their inserts **1934**.

The insert **1934** can have any of the shapes and features described herein with regard to flat tube inserts. In many of these embodiments, the insert **1934** is formed from a flat starting sheet of material. Therefore, as the insert **1934** is formed with corrugations or other features to at least partially define the flow channels **1916** through the tube **1910**, the width of the insert **1934** can decrease. This process is shown schematically in FIG. **60**, which illustrates a sheet of material in which corrugations **1952** are successively created by forming rolls **1955** as the sheet advances in a longitudinal direction (indicated by the straight arrow in FIG. **60**) through the manufacturing line **1900**. Although three of such forming rolls **1955** are shown in FIG. **60**, the manufacturing line **1900** can have any number of forming rolls **1955** to produce any number of desired corrugations **1952** or other insert features as described with respect to the various insert embodiments herein. The type and location of the corrugations or other wall

58

features can at least partially determine how many forming rolls **1955** are needed in the manufacturing line **1900**. For example, in some embodiments where the insert **1934** includes continuous corrugations **1952**, such as those illustrated in FIGS. **25-34**, a corresponding number of forming roll sets (e.g., each roll set defined by a pair of rolls—one on each side of the sheet of material) can be necessary to form the corrugations **1952** successively as described herein. Accordingly, in some embodiments, the manufacturing line **1900** can extend over a length of about 20 m (65.62 ft.) or more.

The manufacturing line **1900** can also include more than one type of roll **1955** for forming the insert **1934**. For example, different rolls **1955** can be used to form different types of corrugations **1952** across the width of the insert **1934**. As another example, one or more rolls **1955** can be cutting rolls used to create slits in a sheet of material for later formation of corrugations in the sheet of material, such as by bending portions of the sheet next to the slits as described above in connection with any of the embodiments of FIGS. **35-45**. Any number of such rolls **1955** can be used in conjunction with any number of other types of rolls (e.g., for bending portions of the sheet of material) to create any insert type described herein.

In some embodiments, such as that shown in FIG. **60**, the manufacturing process of the insert **1934** includes first forming one or more central corrugations **1952** in the sheet of material, and subsequently forming further corrugations **1952** closer to the longitudinal edges of the insert **1934**. More specifically, and with reference to the embodiment of FIG. **60** by way of example, a first set of rolls **1955** (i.e., the left-most set of rolls in FIG. **60**) includes two grooves **1957** to form corresponding corrugations **1952** in the passing sheet of material. The next set of rolls **1955** includes four grooves **1957** forming corresponding corrugations **1952** in the sheet of passing material. This process can continue for producing as many corrugations in the sheet of material as desired. At any point before, during, or after such corrugation formation, either or both longitudinal edges **1938**, **1940** of the insert **1934** can be formed to take any shape, including any of the shapes described and/or illustrated herein. For example, both longitudinal edges **1938**, **1940** of the insert **1934** produced in the embodiment of FIGS. **55-60** are provided with arc-like shapes subsequent to forming all the corrugations **1952**, as best shown in FIG. **28**.

In some embodiments, the width of the sheet used to form the insert **1934** is reduced to a greater extent than the width of the sheets used to form the first and second tube portions **1912**, **1914**. This can be the case, for example, when the sheets used to form the first and second tube portions **1912**, **1914** are deformed only (or primarily) at their opposite longitudinal edges, such as in the case of the two-piece flat tube embodiment illustrated in FIG. **28**. An advantage of such a flat tube construction is that smooth broad sides **1922**, **1924** of the flat tube **1910** can provide relatively better surfaces for brazing joints between the broad sides **1922**, **1924** of the flat tube **1910** and the insert **1934** and/or between the broad sides **1922**, **1924** of the flat tube **10** and fins or other elements (not shown) attached to the flat tube **1910**.

In those embodiments in which an insert **1934** is threaded between two tube portions **1912**, **1914** (and possibly also moved from an inclined position to a parallel or substantially parallel position as described above), the forming rolls or other suitable forming devices for producing the insert **1934** can be located upstream of the location at which the two tube portions **1912**, **1914** are brought together to close the flat tube **1910**. Therefore, some or all of the features of the insert **1934** can be formed prior to this location. In other embodiments,

however, some or all of the insert-forming devices can be located in the same part of the manufacturing line at which the two tube portions **1912**, **1914** are brought together to close the flat tube **1910**. Accordingly, the insert **1934** can still be in the process of being formed as the tube portions **1912**, **1914** are brought together for closure, and/or as the insert **1934** is changed from an inclined position to a position parallel or substantially parallel to the broad sides **1922**, **1924** of the tube portions **1912**, **1914** as described above.

In some embodiments of the manufacturing line **1900**, roll sets used to produce any one or more of the various parts of the flat tube **1910** and insert **1934** can be adjustable to produce flat tubes **1910** and/or inserts **1934** with different cross-sectional dimensions and characteristics. Alternatively or in addition, an advantage of some of the embodiments of the manufacturing line **1900** is that one or more roll sets (also identified as roll banks) used to produce any of the flat tube assembly parts can be fully exchanged for other sets to form flat tubes **1910** and/or inserts **1934** with different dimensions and characteristics. It should be noted that roll sets without individual adjustability can often be produced in a relatively more cost-effective and efficient manner.

Another feature of the manufacturing line **1900** that can define significant manufacturing advantages relates to flexibility in the widths of sheets used to create flat tubes according to embodiments of the present invention. In some embodiments, one or more of the sheets of material can be formed with additional folds and/or to define additional flow channels as needed to use an entire width of the sheets. For example (and with continued reference to the machine line embodiment illustrated in FIGS. **55-60**), the width of the sheet of material used to produce the internal insert **1934** is generally larger than the width of the sheets of material used to manufacture the first and second tube portions **1912**, **1914**. This can be the result of the insert **1934** having corrugations **1952** and deformed longitudinal edges **1938**, **1942**, while the first and second tube portions **1912**, **1914** has only deformed longitudinal edges or otherwise requires less material width to form the tube portions **1912**, **1914**, in some embodiments. Any additional width of the sheet of material used to form the insert **1934** can be used to create further features of the insert **1934**, such as one or more additional folds at the narrow sides **1918**, **1920** of the flat tube **1910**, and/or one or more additional folds defining the flow channels **1916** through the flat tube **1910**.

Still other features of the present invention also relate to the manner in which flat tubes described herein can be produced, flat tube and fin assemblies and the manner in which such assemblies can be produced, and/or flat tubes and fin assemblies incorporated into heat exchange devices. By way of example only, these aspects of the present invention will now be described and illustrated with reference to the production of two-piece tubes, and more specifically to the two-piece tube **1910** illustrated in FIG. **28** and described above. The following description and accompanying drawings apply equally to the production of any of the other two-piece tubes (with or without inserts) described herein. Also, with the exception of inconsistent or incompatible description, the following description and accompanying illustrations apply equally to the production of any of the one-piece tubes (with or without inserts) also described herein.

Some advantages of forming tubes **1910** with fins according to the present invention include a relatively simpler method of manufacturing such assemblies for manufacturing different types of heat exchangers. In some embodiments of the present invention, an endless tube **1910** (i.e., created by the continuous supply of sheet material from one or more

upstream locations and the formation of the sheet material into a continuous flat tube **1910**), such as the endless tube **1910** illustrated in FIGS. **61**, **64**, and **65**, can be transported along a manufacturing line to attach the endless tube **1910** to at least one set of fins **1959**. It is to be understood that reference to the process of coupling fins **1959** to a flat tube or to an endless tube can be used interchangeably herein (barring any indication to the contrary) without limiting the scope of the present invention. In some embodiments, only one of two broad sides **1922**, **1924** of the endless tube **1910** is provided with a set of fins **1959** in this manner. Flat tubes **1910** produced with fins **1959** on only one side can be used, for example, at edges of a heat exchanger core **1965**, in which cases the flat tube **1910** can be positioned to face inward so that the flat tube **1910** is adjacent a set of fins **1959** of an adjacent tube **1910**, or outward so that the set of fins **1959** is adjacent a set of fins **1959** of an adjacent tube **1910**. In other embodiments, such as that shown in FIGS. **61-66**, both broad sides **1922**, **1924** of the endless tube **1910** are provided with a respective set of fins **1959** in this manner. In both cases, the set(s) of fins **1959** can define a two-dimensional interface with the broad side(s) **1922**, **1924** of the flat tube **1910**.

Many of the flat tube and fin embodiments described below and illustrated herein are constructed of sheets of metal including aluminum (e.g., aluminum or an aluminum alloy), although other metallic and non-metallic sheet materials can instead be used in other embodiments. In some embodiments, the sheet of material used to produce the flat tubes **1910** is provided with a braze layer (not shown) on at least one side thereof, whereas the sheet of material for the manufacture of the fins **1959** does not have a braze coating. In other embodiments, different locations of braze coatings are possible.

Although the various aspects of finned tube production and finned tube features described herein can be applied to flat tubes having any dimensions, unique advantages are obtained in their application to flat tubes **1910** formed of the relatively thin material also described herein. By way of example only, the relatively thin tube material can enable continuous line production of finned flat tubes **1910** (described in greater detail below) where previously not possible. In some embodiments, the wall material of the flat tube has a thickness of no greater than about 0.20 mm (0.007874 in). However, in other embodiments, the inventors have discovered that a wall material of the flat tube having a thickness of no greater than about 0.15 mm (0.0059055 in) provides significant performance results relating to the overall performance of heat exchangers using the flat tube, manufacturability, and possible wall constructions (as disclosed herein) that are not possible using thicker wall materials. Also, in some embodiments, a wall material thickness of the flat tube of no less than about 0.050 mm (i.e., no less than about 0.0019685 in) provides good strength and corrosion resistance performance, although a wall material thickness of no less than about 0.30 mm (0.00118 in) can be used in other embodiments.

As explained in greater detail below, the heat exchanger tubes and other portions of heat exchangers described herein can be manufactured using a number of manufacturing techniques and processes and can include corrosion protection features, such as, for example, those techniques and processes described below and illustrated in FIGS. **92-95**. A number of manufacturing processes and techniques and the corrosion protection features referenced hereinafter are particularly advantageous when applied to heat exchanger tubes and portions of heat exchangers having significantly reduced material thickness. In addition, such techniques, processes, and corrosion protection features provide significant advantages

relating to the overall performance of flat tubes and heat exchangers made from such material.

The flat tube **1910** in the illustrated embodiment is a two-piece flat tube with an insert. With reference to the illustrated embodiment of FIG. **66** by way of example, each of the illustrated flat tubes **1910** can have a small diameter d of at least about 0.8 mm (0.031496 in) to provide good performance results in many applications. Also, a small diameter d of no greater than about 2.0 mm (0.07874 in) provides good performance results in many applications. However, in some embodiments, a maximum small tube diameter d of no greater than about 1.5 mm (0.059055 in) is used. Any of the other flat tube embodiments described herein (e.g., constructed of only a single piece or any number of additional pieces) can be used to create the finned tubes of the present invention. Also, in other embodiments, any of the other small and large diameters d , D described above in connection with all of the flat tube embodiments disclosed herein can instead be used.

The manufacture of the flat tubes **1910** and sets of fins **1959** in the illustrated embodiment is shown schematically in FIG. **61** only by a few roll pairs **1971**, **1973**, which represent part of an upstream manufacturing line not shown in more detail. This upstream manufacturing line can also include intermediate buffers (e.g., roll sets, not shown) for controlling the feed rate of the flat tube **1910** and/or fins **1959**. Furthermore, although two pairs of rolls **1973** are shown in FIG. **61** to schematically represent the production of two sets of fins **1959**, it should be noted that a single upstream fin manufacturing line can instead be used in some embodiments.

Flat tubes that can be used to create finned tubes can be closed by brazing, welding, soldering, or in any other suitable manner described herein along one or more longitudinal seams upstream of the location at which fins are attached to the flat tubes. Such tube production can be used, for example, in those embodiments in which a flat joint between the flat tube **1910** and a set of fins **1959** is an adhesive joint. Alternatively, the flat tube **1910** can be joined by brazing, welding, or soldering in the course of production of the finned tubes.

The flat tubes **1910** illustrated in FIGS. **61-66**, **68**, and **69** are described in greater detail above in connection with FIG. **28**. As noted above, the description and accompanying drawings regarding finned flat tubes and their manufacture apply equally to the production of any of the other one- and two-piece tubes (with or without inserts) described herein. By way of example only, FIG. **67** illustrates another flat tube **310** that can be used in any of the finned tube embodiments described herein, and is described in greater detail above in connection with FIG. **7**. In some embodiments, the flat tube **310** shown in FIG. **67** has a wall thickness of about 0.10 mm (0.003937 in). One characteristic of this particular flat tube **310** is that the narrow sides **318**, **320** are designed to the very stable. For example, the narrow side **318** includes a set of folds **330**. Another characteristic of this flat tube **310** is that the flat tube **310** is divided into a number of flow channels **316** by single folds **328**, or by sets **332** of multiple folds **328** in other embodiments. In some embodiments, the distance between the folds **330** can be less than 1.0 mm (0.003937 in). However, this distance can be increased into the centimeter range. As described in greater detail above in connection (for example), with the embodiments illustrated in FIGS. **1-13**, it should be noted that the folds **330** that form the narrow side **318** can be designed with different lengths and/or shapes, thus relatively increasing the temperature change load resistance, pressure strength, and/or impact strength of the flat tube **310**.

The fins **1959** described herein can have any thickness desired, and can be produced from an endless sheet of material in some embodiments. However, the use of fins **1959**

formed from a sheet of material with a thickness no greater than about 0.09 mm (0.0035433 in) can provide good performance results in many applications. Also, fins **1959** formed from a sheet of material with a thickness no less than about 0.03 mm (0.0011811 in) can provide good performance results in many applications.

FIG. **63** illustrates alternative constructions of the fins **1959** that can be used in the various embodiments of the present invention. The fins **1959** illustrated in FIGS. **61**, **62**, **64-66**, and **68-69** correspond to the fins **1959** illustrated in FIG. **63**. However, it is to be understood that other designs of the fins **1959** are possible, and fall within the spirit and scope of the present invention.

With reference to FIG. **66** by way of example, the wall thickness of the fins **1959** can be about 0.06 mm (0.0023622 in), and can have a height H of about 3.00 mm (0.011811 in). It can be observed that a distance $2H$ between two flat tubes **1910** can therefore be about 6.0 mm (0.023622 in) subsequent to the manufacturing process described herein in which adjacent fin sets **1959** of adjacent flat tubes **1910** abut one another.

The sets of fins **1959** can be secured to the broad sides **1922**, **1924** of the flat tube **1910** by adhesive or by a metallic joint (e.g., welding, brazing, or soldering), wherein flat surfaces of the broad sides **1922**, **1924** provide significant surface area for such attachments. In some embodiments, the flat joint between the flat tube **1910** and one or more sets of fins **1959** defines less surface area than that of the flat broad sides **1922**, **1924** of the flat tube **1910**.

The sets of fins **1959** joined to the flat tubes **1910** as described herein can be oriented in a number of different manners with respect to the flat tubes **1910**. For example, the longitudinal direction of fins **1959** on a flat tube **1910** can be substantially perpendicular to the longitudinal direction of the flat tube **1910**. However, the inventors have discovered that sets of fins **1959** can instead be joined to the flat tube (i.e., on the broad sides **1922**, **1924** thereof) such that the longitudinal direction of the fins **1959** is inclined with respect to the longitudinal direction of the flat tube **1910** and a direction perpendicular thereto (i.e., in the direction of air flow, in many applications). Examples of such fins **1959** are shown in FIGS. **68** and **69**, which show one fin set **1959** brazed to the broad side **1924** of one flat tube **1910** (transparent in FIG. **69**), and another fin set **1959** brazed to the broad side **1922** of another flat tube **1910**. Accordingly, and as indicated by the arrows in FIG. **68**, airflow through one fin set **1959** is not parallel to air flow through the other fin set **1959**. In those embodiments in which FIG. **68** represents an elevational view of the fin sets **1959** in use, cooling air in one fin set **1959** is deflected down from the incoming horizontal and cooling air, while cooling air in the other fin set **1959** is directed upward from the incoming horizontal and cooling air.

In some embodiments, the angle of inclination for each fin set as described above is no less than about 8° (measured between the longitudinal direction of the fins **1959** and that of the flat tube **1910**) for good performance results in many applications. Also, in some embodiments, this angle of inclination is no greater than about 8° for good performance results in many applications. In some embodiments, including those in which a set of fins **1959** on one flat tube **1910** is adjacent another set of fins **1959** on another flat tube **1910** as described in greater detail below, this inclination of one set of fins **1959** can be in a direction that is different from an inclination of another adjacent set of fins **1959** (see, for example, FIGS. **68** and **69**).

In some embodiments of the present invention, a brazing method can be used where the endless flat tube **1910** and one or more sets of fins **1959** are transported continuously or in

63

any interrupted manner through a joining station 1969, an example of which is shown schematically in FIGS. 61 and 64. The sets of fins 1959 can be brazed to the endless flat tube 1910 at one or more of such joining stations 1969, any or all of which are located at the later stages of a finned tube manufacturing line in some embodiments. Generally, a joining station can be a relatively small device producing the necessary brazing temperature with an induction coil, for example. It should be noted that brazing parameters (and therefore the type and power of the joining station(s) 1969 used) can vary according to desired parameters of the flat tube 1910.

In some embodiments, the sets of fins 1959 are held against the broad sides 1922, 1924 of the flat tube 1910 with a predetermined force while the sets of fins 1959 are brazed thereto as described above. Although the tube manufacturing process can occur upstream of the fin attachment process, significant advantages can be achieved by brazing or otherwise joining various parts of the flat tube (e.g., the insert 1934 to the flat tube 1910, at least one longitudinal edge of the flat tube 1910 for tube closure, and the like) at the same time as the sets of fins 1959 are attached to the flat tube 1910, such as through the same brazing process described herein. In cases wherein one or more longitudinal seams of the flat tube 1910 have already been completed by the time the flat tube 1910 reaches the fin attachment portion of the manufacturing line, however, the flat tube 1910 can be used within the framework of the manufacturing process. For example, with reference to FIGS. 64 and 65, sets of fins 1959 can be joined in an endless manner to the broad sides 1922, 1924 of a completed endless flat tube 1910 in any of the manners described herein.

In some embodiments, the manufacturing process also includes forming sections of tube and fin assemblies (otherwise referred to herein as “finned tubes”, and indicated generally by reference number 1961) by separation of desired lengths of the finned tubes 1961 from an endless tube 1910 having one or more sets of fins 1959. For example, a set of fins 1959 supplied for connection to an endless flat tube 1910 can be cut to a desired length and removed from the endless flat tube 1910 prior to or after joining the set of fins 1959 to the endless flat tube 1910 (e.g., by brazing or in any other manner described above).

In other embodiments, a continuous supply of fins 1959 from an upstream manufacturing process can be cut to desired lengths, whereby the lengths of fins 1959 can be placed at intervals and joined to a surface of the endless flat tube 1910 in any such manner. With reference to the illustrated embodiment of FIG. 61, in still other embodiments one or more separators 1975 (e.g., blocks) can be placed between sets of fins 1959 on the flat tube 1910, and can thereby be used to position the fins 1959 for establishing a desired distance between the sets of fins 1959 coupled to the same broad side of the endless tube 1910. As shown in FIG. 61, the separators 1975 can be removed from the flat tube 1910 in a downstream location, allowing for the formation of finned tube sections with a free flat tube ends on either or both ends of the flat tube 1910.

In any case, and in still other embodiments, interruptions between the sets of fins 1959 can provide exposed portions of the flat tube 1910 that can be useful for cutting or other tube separation processes between the intervals formed, and/or for perforation or other operations performed upon the flat tube 1910 at such locations. Accordingly, the individual finned tube sections formed can include a flat tube 1910 and sets of fins 1959 located on either or both flat sides of the flat tube 1910.

Finned tubes 1961 produced in accordance with the present invention can be incorporated into a wide variety of heat

64

exchangers in any desired manner. In some embodiments, however, unique heat exchanger characteristics and heat exchanger assembly features have been identified by the inventors. For example, the heat exchanger 1963 illustrated in FIGS. 61, 62, and 66 can include finned tubes as described above, wherein a set of fins 1959 of one finned tube 1961 is positioned next to another set of fins 1959 of an adjacent finned tube 1961. FIG. 62 (which is an exploded view of a tube and fin block or core 1965) illustrates four finned tubes 1961 of a fin core 1965. The number of finned tubes 1961 can be determined at least in part upon a particular application of the heat exchanger. Accordingly, the finned tube arrangement described above can be repeated as many times as desired to define the core 1965 of finned tubes 1961. Such a core 1965 can be assembled and then fitted to one or more collecting tanks 1967. In particular, the ends of the flat tubes 1910 of the core 1965 can be free and can engage the collecting tanks 1967 (e.g., received within respective slots or other openings in the collecting tanks 1967 or connected in fluid communication with the interiors of the collecting tanks 1967 in any other suitable manner) for being fastened and sealed thereto using any suitable adhesive or sealant. For example, FIG. 62 includes arrows indicating the general direction to mount the collecting tanks 1967 onto the core 1965 of finned tubes 1959.

As described above, finned tubes can be arranged in a heat exchanger such that a set of fins 1959 of one finned tube 1961 is positioned next to another set of fins 1959 of an adjacent finned tube 1961. These sets of fins 1959 can be in contact with one another. In some heat exchanger embodiments employing this arrangement of finned tubes 1961, there is a neutral zone of this structure which does not participate in heat exchange because the temperature of the finned tubes 1959 at the neutral zone is substantially similar, or in some embodiments is even the same. Depending upon the number of finned tubes 1961 arranged in this manner, any number of such neutral zones can exist in a core 1965 between adjacent fin sets 1959.

As a result, when assembling a heat exchanger 1963 from a number of finned tubes 1961 in these and other embodiments, it is possible to attach a set of fins on a finned tube 1961 to the fins 1959 of another adjacent finned tube 1961, thereby enabling a heat exchanger core 1965 having such a finned tube construction to be handled as a single structural unit. In relatively large heat exchangers, an advantage of joining the adjacent sets of fins 1959 in this manner is that vibrations or oscillations (and noise generated thereby) between adjacent finned tubes 1961 can be suppressed. The attachment of adjacent finned tubes 1959 as just described can be achieved in some embodiments by a bonding material (e.g., adhesive, soldering, brazing, welding, and the like) applied between the adjacent sets of fins 1959 of adjacent finned tubes 1961, such that the heat exchanger core 1965 can be handled as a single structural unit. In other cases, the fin sets 1959 of adjacent finned tubes 1961 can be joined in other manners to produce heat exchanger cores 1965 from such finned tubes 1961. For example, in some embodiments, an intermediate sheet (e.g., a relatively thin sheet of metal or other material) can be located between and join the adjacent fin sets 1959. In other embodiments, a narrow air gap can exist between the adjacent fin sets 1959 of adjacent finned tubes 1961. In other words, a set of fins 1959 from one finned tube 1961 can be “adjacent” a set of fins 1959 from another finned tube 1961 in a heat exchanger according to some embodiments of the present invention, even without a layer of material or element joining the sets of fins 1959.

Once a number of finned tubes 1961 have been assembled in a desired arrangement, the assembly can be secured

65

together in a number of different manners, such as by soldering, welding, and/or brazing. In some embodiments, the manufacturing process of a tube-fin core **1965** can include the use of CAB brazing technology. Tube-fin cores **1965** as described herein can be manufactured with relatively reduced energy consumption. In those embodiments in which the tube-fin cores **1965** are constructed with flat tubes **1910** formed from the relatively thin sheet materials described herein, the various stages of securing the finned tubes **1961** together (e.g., in a CAB brazing process) can be significantly reduced. For example, the travel velocity or velocities of such tube-fin cores **1965** through the different temperature zones of a CAB brazing furnace can be significantly increased relative to those needed for conventional tube-fin cores. One reason for such faster securing processes is the relatively low wall thickness of the flat tubes **1910** (and also of the fins **1959**), allowing for brazing temperatures (or elevated temperatures needed for other securing processes) to be reached significantly faster than in cases when thicker sheet materials are brazed. Transport velocities and/or exposure times in various stages of the manufacturing process can be optimized by selectively adjusting temperature settings, for example, based upon the use of such thinner materials. Additionally, the use of suitable hangings, fixtures, or auxiliary devices in the manufacturing process can help reduce the opportunity and/or degree of tube-fin core deformation, such as subsequent to the conclusion of a brazing process to secure the tube-fin assembly. More specifically, expansion and contraction of tube-fin cores **1965** occurring during heating and cooling need not cause unacceptable delays.

Further aspects of the present invention relate to the use of flat tubes disclosed herein in heat exchangers having one or more tanks used to establish fluid communication between the flow channels of the various flat tubes and/or to a fluid supply or exit connecting the heat exchanger to other equipment. These aspects of the present invention are adapted for the flat tubes disclosed herein having the relatively thin wall materials described above (e.g., no greater than about 0.20 mm (0.007874 in) in some embodiments, and no greater than about 0.15 mm (0.0059055 in) in other embodiments). However, the inventors have discovered that the aspects of the present invention described in greater detail below can be utilized in applications where flat tubes constructed of thicker materials are used. Therefore, the various features of the present invention described below apply to heat exchangers having other types of flat tubes, including any of the flat tubes described and/or illustrated herein.

As explained in greater detail below, the heat exchanger tubes and other portions of heat exchangers described herein can be manufactured using a number of manufacturing techniques and processes and can include corrosion protection features, such as, for example, those techniques and processes described below and illustrated in FIGS. **92-95**. A number of manufacturing processes and techniques and the corrosion protection features referenced hereinafter are particularly advantageous when applied to heat exchanger tubes and portions of heat exchangers having significantly reduced material thickness. In addition, such techniques, processes, and corrosion protection features provide significant advantages relating to the overall performance of flat tubes and heat exchangers made from such material.

As described above, the flat tubes described and illustrated herein can be used in conjunction with heat exchangers having one or more tanks. These tanks can include collection tanks, headers, and other fluid enclosures adapted to establish fluid communication between the flat tubes and/or between the flat tubes and a fluid supply or exit of the tanks. Such tanks

66

are collectively referred to herein as "collection tanks" for ease of description, it being understood that such tanks can perform other functions, can be larger or smaller, and can have any other shape desired while still incorporating aspects of the present invention described below.

One embodiment of a collection tank according to the present invention is illustrated in FIGS. **70**, **70A**, **71**, **76**, and **77**, and is indicated generally by reference numeral **4467**. Although the heat exchanger **4463** illustrated in FIG. **77** is shown with two collection tanks **4467**, it should be noted that any number of collection tanks **4467** can be employed in various possible heat exchangers, including a single collection tank **4467** and more than two collection tanks **4467**. Both collection tanks **4467** shown in FIG. **77** have substantially the same features and are connected to the flat tube **4410** in substantially the same way as described below and illustrated in FIGS. **70**, **70A**, **71**, **76**, and **77**.

The collection tank **4467** can be constructed from any number of different parts. For example, the collection tank **4467** illustrated in FIGS. **70**, **70A**, **71**, **76**, and **77** is formed as a single unitary body, such as by injection molding or another suitable process. In this and other embodiments, at least one row of receiving openings **4479** (described in greater detail below) is integrally formed with the collection tank **4467**. In other constructions, such as the collection tank embodiment illustrated in FIGS. **72-75** and described below, the collection tank is formed from two or more separate pieces by injection molding or any other suitable manner and connected together, and having at least one row of receiving openings in one or more of the pieces. In such embodiments for example, the collection tank **4467** can have one or more walls in which the receiving openings **4479** are defined, and one or more other walls defined by separate parts of the collection tank **4467**, such that the other walls can be assembled at a stage later than that in which flat tubes **4410** are received within the receiving openings **4479**.

The illustrated collection tank **4467** includes a series of receiving openings **4479** along a surface thereof. Each receiving opening **4479** is surrounded by a wall integrally formed with at least a portion of the collection tank **4467** and shaped to receive a corresponding free end **4477** of a flat tube **4410**. The flat tubes **4410** can take any of the forms described herein, and can be cut to length specified by the desired parameters of the flat tube **4410** or corresponding application. With reference to FIGS. **70**, **7A**, and **71**, part of the process of manufacturing a heat exchanger **4463** includes setting free ends **4477** of flat tubes **4410** (according to any of the embodiments described herein) into receiving openings **4479** of the collection tank **4467**. In some embodiments, this process can be performed by pushing the collection tank **4467** onto the free flat tube ends **4477** in a manner similar to that shown schematically in FIG. **62**. Alternatively, the free ends **4477** of the flat tubes **4410** can be pushed into the receiving openings **4479**, or the flat tubes **4410** and the collection tank **4467** can be moved toward one another and pushed together to establish these connections.

In some embodiments, the flat tubes **4410** connected to the collection tank **4467** can have one or more sets of fins **4459** (see FIG. **77**) according to any of the embodiments described herein. By way of example only, finned tubes **4461** already assembled and brazed in upstream manufacturing steps (such as any of those described above) can have fins **4559** with wall thicknesses of about 0.030-0.090 mm (0.0011811-0.0035423 in.), and can subsequently be secured to a collection tank **4467**. For example, protruding free ends **4477** of individual flat tubes **4410** with fins **4459** already brazed thereto or of such finned tubes **4461** already assembled and brazed into a

67

block or core **4465** can remain free during brazing (e.g., while in a brazing furnace), and therefore have no fins **4559** to interfere with their later insertion into receiving openings **4479** of a collection tank **4467**. Both ends of the flat tubes **4410** in any such embodiment can protrude and be free as just described for connection to opposite collection tanks **4467**.

In those embodiments in which the core **4465** is connected as just described, the core **4465** can be formed from flat tubes **4410** and fins sets **4459** by alternate stacking of the flat tubes **4410** and fins sets **4459**. An example of such a core construction is illustrated in FIG. 77, which shows a brazed flat tube-fin core **4465** having two collection tanks **4467** each with a port for connection to other equipment, wherein cooling air flows through the fins **4459** to cool fluid within the flat tubes **4410**. The heat exchanger **4463** illustrated in FIG. 77 is only one of many types of possible heat exchangers to which one of more of the collection tanks **4467** can be connected. By way of example only, either of the illustrated collection tanks **4467** can be a reversing tank, such that both inlet and outlet ports are arranged on the same collection tank **4467**.

The flat tubes **4410** (with or without fins connected thereto as described in earlier embodiments above) can be individually inserted into respective receiving openings **4479** of a collection tank **4467**. However, significant advantages can be achieved by inserting two or more of the flat tubes **4410**, and in some cases all of the flat tubes **4410** of a core **4465**, into their respective receiving openings **4479** at the same or substantially the same time, such as in a single step. This process can be performed when two or more of the flat tubes are **4410** are already connected together, such as by a brazing or other attachment processes (including those described herein) to define an entire flat tube heat exchanger core **4465** or portion thereof. Such a process can make possible the use of a larger number of collection tank materials. However, depending at least in part upon the material used for the collection tank **4467** and the process used to secure the fins **4459** to the flat tubes **4410**, in some embodiments it is desirable to introduce the free ends **4477** of the flat tubes **4410** into respective receiving openings **4479** of the collection tank **4467** subsequent to post-brazing cooling of the tube-fin core **4465**.

Many heat exchanger manufacturing processes require the exposure of the tubes and the collection tank to elevated temperatures for soldering, welding, brazing, and other attachment processes, such as receiving the flat tubes and the collection tank in a furnace or other heated environment to join the flat tubes to the collection tank. Such processes therefore prevent the use of many collection tank materials—at least those materials used for the parts of collection tanks defining the connection locations for the flat tubes (e.g., the collection tank wall or walls defining the receiving openings). Therefore, these parts of collection tanks are typically comprise metal. By connecting the collection tank to two or more flat tubes that have already been soldered, welded, brazed, or otherwise already joined together as described above, plastic or other lower temperature materials can be used for many parts, all, or substantially all of the collection tank **4467**. For example, the part or parts of the collection tank **4467** defining the receiving openings **4479** can comprise plastic. The entire collection tank **4467** in the illustrated embodiment of FIGS. 70, 70A, 71, 76, and 77 is manufactured from a plastic material, although other materials can be used in other embodiments. In those embodiments in which part or all of the collection tank **4467** comprises plastic, such parts can be manufactured by injection-molding, for example.

With reference again to FIGS. 70 and 71, the receiving openings **4479** of the collection tank **4467** shown therein have curved surfaces **4481** to aid insertion of the flat tube ends

68

4477. In other embodiments, other shapes (e.g., flat inclined surfaces, perpendicular corner surfaces, and the like) are used instead.

When fully inserted into their respective receiving openings **4479**, the flat tube ends **4477** reach to respective locations below the inner surface **4483** of the collection tank **4467**, as best shown in FIG. 71, thereby preventing an undesirable pressure drop created by the flat tube ends **4477** during operation of the heat exchanger **4463**.

In the illustrated embodiment of FIGS. 70, 70A, 71, 76, and 77, the receiving openings **4479** of the collection tank **4467** are shaped to define a rear portion **4485** (with reference to the direction of flat tube insertion in FIGS. 70, 70A, 71, 76, and 77) that is substantially the same as the cross-sectional shape of the flat tube ends **4477**. Although the rear portion **4485** of each receiving opening **4479** can be dimensioned to define a clearance fit with a flat tube end **4477**, in other embodiments (such as that shown in FIGS. 70, 70A, 71, 76, and 77) an interference fit is used. In those embodiments in which an interference fit is employed, a slight pressure can be exerted upon the collection tank **4467** and/or on the flat tube **4410** to fully insert the flat tube end **4477** into the rear portion **4485** of the receiving opening **4479**, thereby providing a seal between the collection tank **4467** and the flat tube end **4477** that can be fluid tight or substantially fluid tight.

In some embodiments, a feature of the collection tank **4467** and/or of the flat tube ends **4477** is used to control or limit the amount of insertion of the flat tube ends **4477** into the receiving openings **4479**. For example, a stop (not shown in FIGS. 70, 70A, 71, 76, and 77, but visible in FIG. 80, indicated by reference numeral **4675**) can be formed on the flat tube end **4477** and/or on the inside surface of the receiving opening **4479** to limit the depth of insertion of the flat tube end **4477**.

In other embodiments, one or more of flat tube ends **4477** can extend through a corresponding receiving opening **4479** and into an interior chamber **4487** of the collection tank **4467**. In such embodiments, the flat tube end **4477** can be deformed in any manner, such as by being bent over the surfaces of the interior chamber walls **4483** adjacent the receiving opening **4479** to at least partially match the shape of such surfaces.

In the illustrated embodiment of FIGS. 70, 70A, 71, 76, and 77, adhesive **4489** is used to secure the flat tube ends **4477** within the receiving openings **4479** (see FIG. 71) of the collection tank **4467**. A number of different adhesives can be used, including those that harden immediately or over time, and those that retain a degree of flexibility after setting. For example, silicone adhesives produced by Dow Corning® can be used in many embodiments. In some embodiments, the adhesive **4489** insures a permanent and tight joint between the flat tube ends **4477** and the interior surfaces of the receiving openings **4479**.

The adhesive **4489** can further function as a sealant to prevent loss of fluid from the collection tank **4467**. In other embodiments, the flat tube ends **4477** are sufficiently secured within the receiving openings **4479** by their insertion in the rear portions **4485** of the receiving openings **4479**, in which cases sealant having no or substantially no adhesive properties can be used in place of adhesive **4489**. For ease of description, the term “adhesive” with reference to the flat tube-to-collection tank connections refers to adhesive that may or may not function as a sealant, it being understood that in other embodiments such material can instead function only or primarily as a sealant.

As best shown in FIG. 71, the adhesive **4489** can substantially cover a significant portion of the flat tube end **4477**, and in some embodiments surrounds the entire periphery of the flat tube end **4477** in at least one location along the length

thereof. In the illustrated embodiment of FIGS. 70, 70A, 71, 76, and 77, a terminal portion of the flat tube end 4477 is not covered with adhesive 4489 due to its location within the rear portion 4485 of the of the receiving opening 4479. By virtue of the relatively close fit between the rear portions 4485 of the receiving openings 4479 and the flat tube ends 4477 as described above, fluid passing through the collection tank 4467 (e.g., liquid coolant or other fluid used as a heat exchange medium) can be prevented from coming into contact with the adhesive 4489.

Adhesive 4489 can be introduced between the flat tube ends 4477 and the interior surfaces of the receiving openings 4479 in a number of different manners according to various embodiments of the present invention, many of which include the introduction of adhesive 4489 after or while the flat tube ends 4477 are received within their respective receiving openings 4479. Before further description of such embodiments, however, it should be noted that adhesive 4489 can be applied to the interior of the receiving openings 4479 and/or to the exterior of the flat tube ends 4477 in any manner (e.g., spray, roller, or other applicator, and the like) prior to insertion of the flat tube ends 4477 within the receiving openings 4479.

Introduction of adhesive 4489 between the flat tube ends 4477 and interior surfaces of the receiving openings 4479 during or after tube end insertion can provide greater control over the amount and/or resulting locations of adhesive 4489 in the finished heat exchanger 4463, and can result in more reliable connection and/or seals between the flat tube ends 4477 and the collection tank 4467.

In order to provide space for adhesive 4489 to be introduced between the flat tube ends 4477 and the interior surfaces of the receiving openings 4479, the receiving openings 4479 and/or flat tube ends 4477 can be shaped to define one or more gaps 4493 therebetween. For ease of description, the term "gap" (when used herein to refer to the space where adhesive 4489 is received as described herein) refers to one or more of such gaps, regardless of particular peripheral location about a flat tube end 4477 and regardless of whether two or more of such gaps for the same flat tube end 4477 are in fluid communication with one another.

In some embodiments, the gap 4493 between the flat tube end 4477 and the adjacent interior surface defining the receiving opening 4479 can have a width of at least about 0.3 mm (0.011811 in) to permit proper adhesive injection (described below). Also, through experimentation, the inventors have discovered that this gap width of no greater than about 1.0 mm (0.03937 in) provides good performance results. A number of considerations can at least partially define the size of the gap 4493, such as the amount of adhesive needed, characteristics of the adhesive (e.g., viscosity and set time), and limitations on the distance between adjacent flat tubes 4410. Another consideration relates to the need in some embodiments for the collection tank 4467 to have a thickness or depth that is minimized. For example, in some embodiments the collection tank 4467 overhangs the flat tube core 4465 by a minimum amount in order to reduce the amount of space wasted by the heat exchanger 4463 within a vehicle.

In some constructions, the collection tanks 4467 have substantially no overhang in the direction of the depth of the tube-fin core 4465 to avoid waste of the available space required for installation of a heat exchanger 4463 into a vehicle. For example, in the illustrated embodiment of FIGS. 70, 70A, 71, 76, and 77, and with particular reference to FIG. 76, an undeformed flat tube end 4477 requires a minimum or substantially no overhang of the collection tank 4467 past the flat tube-fin core 4465, which addresses the need for a reduced space requirement of the heat exchanger 4463. In

some embodiments, the overhang can also be reduced (e.g., on the order of a few millimeters) when the manufacturing process of the heat exchanger 4463 includes the use of deformed flat tube ends 4477 (described below).

In some embodiments, the adhesive 4489 is introduced by injection through one or more openings in the collection tank 4467 or through one or more gaps between the flat tube ends 4477 and the collection tank 4467 accessible from the exterior of the collection tank 4467 and flat tubes 4410 once these parts are at least partially assembled. For example, the collection tank 4467 illustrated in FIGS. 70, 70A, 71, 76, and 77 has a number of injection openings 4491, each extending through a wall 4495 of the collection tank 4467 to a gap 4493 defined between the flat tube end 4477 and one or more walls defining the receiving opening 4479.

Such injection openings 4491 can be located on either or both longitudinal sides of the collection tank 4467. Also, more than one injection opening 4491 can extend to the same receiving opening 4479. In such cases, adhesive 4489 can be injected simultaneously to the same receiving opening 4479, such as through two injection openings 4491 on opposite longitudinal sides of the collection tank 4467. Adhesive can be injected into the gap 4493 corresponding to each flat tube 4410 one at a time, in banks of gaps 4493 (corresponding to respective flat tubes 4410) at the same time or substantially the same time, or in all of the gaps 4493 of a core 4465 at the same time or substantially the same time. In some embodiments, the adhesive 4489 coats the entire periphery of each flat tube end 4477, and/or can fill the gap 4493 between the flat tube end 4477 and the adjacent walls defining the receiving opening 4479. Also, in some embodiments (e.g., that of FIGS. 70, 70A, 71, 76, and 77) the terminal ends of the flat tubes 4410 can be left uncoated with adhesive 4489.

An alternative manner in which to introduce adhesive between a flat tube end 4477 and interior walls of the receiving openings 4479 is to inject adhesive through a bottom opening or gap 4497 between these parts and in fluid communication with the gap 4493 described above. This type of adhesive introduction can be used in addition to or in place of injection through injection openings 4491 as also described above, and can eliminate the need for the injection openings 4491.

FIG. 84 is a block diagram describing a manufacturing process of a heat exchanger 4463 according to an embodiment of the present invention, and referencing stations or steps of manufacturing, and is accompanied by a schematic view of a heat exchanger 4463 manufacturing by this process. The term "station" is used herein only for ease of description, and does not alone indicate or imply that there is a physical separation between such "stations" in a manufacturing line. For example, the collection tanks 4467 can be placed on the free flat tube ends 4477 (Station III) at the same or different location as the process of applying the adhesive 4489 (Station IV).

FIG. 72-75 illustrate a collection tank 4467 according to an additional embodiment of the present invention. This embodiment employs much of the same structure and has many of the same properties as the embodiments of the collection tank 4467 described above in connection with FIGS. 70, 70A, 71, 76, and 77. Accordingly, reference should be made to the description above in connection with FIGS. 70, 70A, 71, 76, and 77 for additional information regarding the structure and features, and possible alternatives to the structure and features of the collection tank illustrated in FIGS. 72-75 and described below. Structure and features of the embodiment shown in FIGS. 72-75 that correspond to struc-

ture and features of the embodiments of FIGS. 70, 70A, 71, 76, and 77 are designated hereinafter in the 4500 series of reference numbers.

Like the collection tank 4467 illustrated in FIGS. 70, 70A, 71, 76, and 77, the collection tank 4567 shown in FIGS. 72-75 has an interior chamber 4587 for fluid communication with flat tubes 4510, a number of receiving openings 4579 each having a rear portion 4585 for receiving the ends 4577 of flat tubes 4510, and a number of injections openings 4591 along the longitudinal sides (only one visible in FIGS. 72-75) of the collection tank 4567. FIG. 75 provides additional detail regarding the receiving openings 4579, including the rear portions 4585 used to receive and support the ends 4577 of the flat tubes 4510 (not shown in FIG. 75), and the injection openings 4591 in fluid communication with the receiving openings 4579.

The flat tubes 4510 received through the receiving openings 4579 define corresponding gaps 4593 between the interior surfaces of the receiving openings 4579 and the flat tube ends 4577. With particular reference to FIG. 73, the flow channels 4516 of each flat tube 4510 within a respective receiving opening 4579 are in fluid connection with the interior chamber 4587 of the collection tank 4567. FIG. 73 also illustrates the connections between the injection openings 4591 and the receiving openings 4579 for injecting adhesive 4589 (not shown) into the gap 4593 as described above.

As best shown in FIG. 74, the entrance of the receiving openings 4579 can be closed or substantially closed on one or more sides of each flat tube end 4477 by entrance walls 4599 (not shown in FIG. 75). The entrance walls 4599 can be defined by one or more elements of the collection tank 4567, such as by a plate in which are defined multiple openings that define the entrance of each receiving opening 4579 when the plate is installed with the multiple openings aligned with the receiving openings 4579. Alternatively, the entrance walls 4499 can be defined by terminal ends of the receiving opening walls that have been enlarged, flared, bent, or otherwise shaped to at least partially close the gaps 4593 described above. In some embodiments, the entrance walls 4599 are shaped to match or substantially match the cross-sectional shape of the flat tube ends 4577 received therein. Also, the entrance walls 4599 can be dimensioned to define a clearance fit with a flat tube end 4577, or can instead define an interference fit such that slight pressure can be exerted upon the collection tank 4567 and/or on the flat tubes 4510 to push the flat tubes 4510 past the entrance walls 4599 and into the rest of the receiving openings 4579. In this manner, seals at the entrances of the receiving openings 4579 can be provided between the collection tank 4567 and the flat tube ends 4577. These seals can be fluid light or substantially fluid tight in some embodiments, and can prevent adhesive leakage during adhesive injection in some embodiments.

It should be noted that the construction of the collection tank 4567 illustrated in FIGS. 72-75 (and in the other figures) is only exemplary, and is not limiting to the scope of the present invention.

In some embodiments, the flat tube ends 4477, 4577 can be deformed. For example, the flat tube ends 4477, 4577 can be deformed such that the large diameter D of the flat tube 4410, 4510 is increased and the small diameter d of the flat tube 4410, 4510 is decreased at the flat tube ends 4477, 4577. Considering the relatively small wall thickness of the flat tubes 4410, 4510 in some embodiments, such deformation can be performed without a significant load on the walls of the flat tube 4410, 4510. In some embodiments, the dimensions of the periphery of the undeformed flat tube end 4477, 4577 remain substantially the same as those of the deformed flat

tube end 4477, 4577. As a result, the walls of the flat tube 4410, 4510 in such embodiments do not undergo a significant expansion or contraction.

In some embodiments in which the flat tube ends 4477, 4577 are deformed, such deformation can be performed before the introduction of the flat tube ends 4477, 4577 into the corresponding receiving openings 4479, 4579 of the collection tank 4467, 4567. Examples of flat tube-to-collection tank connections in which the flat tube ends have been deformed will now be described in connection with FIGS. 78-83.

FIGS. 78-83 illustrate flat tube-to-collection tank connections according to three additional embodiments of the present invention. These embodiments employ much of the same structure and have many of the same properties as the flat tube-to-collection tank connection embodiments described above in connection with FIGS. 70-77. Accordingly, the following description focuses primarily upon the structure and features that are different than the embodiments described above in connection with FIGS. 70-77. Reference should be made to the description above in connection with FIGS. 70-77 for additional information regarding the structure and features, and possible alternatives to the structure and features of the connection embodiments illustrated in FIGS. 78-83 and described below. Structure and features of the embodiments shown in FIGS. 78-83 that correspond to structure and features of the embodiments of FIGS. 70-77 are designated hereinafter in the 4600, 4700, and 4800 series of reference numbers, respectively.

In each of the embodiments illustrated in FIGS. 78-84, the flat tube ends 4677, 4777, 4877 are deformed, with the collection tanks 4667, 4767, 4867 having correspondingly shaped receiving openings 4679, 4779, 4879. Deformation of the flat tube ends 4677, 4777, 4877 shown in FIGS. 78-84 has been carried out after the conclusion of the brazing process (Station II in FIG. 84)—before setting the flat tube ends 4677, 4777, 4877 into the receiving openings 4679, 4779, 4879.

In the embodiment of FIGS. 78-80, each flat tube 4610 has an end 4677 that is received snugly into a corresponding rear portion 4685 of a receiving opening 4679. In this embodiment, the broad sides 4622, 4624 of each flat tube 4610 have been expanded (i.e., bent away from one another) to define a flared flat tube end 4677, whereas the narrow sides 4618, 4620 have been compressed (i.e., bent toward one another). Also, each receiving opening 4679 also has a stop 4675 (see FIG. 80) for limiting insertion of the flat tubes 4610 to a desired distance.

Like the embodiment of FIGS. 78-80, in the embodiments of FIGS. 81-83, the broad sides 4722, 4724, 4822, 4824 of each flat tube 4710, 4810 have been expanded to define a flared flat tube end 4777, 4877, whereas the narrow sides 4718, 4720, 4818, 4820 have been compressed. However, that part of the collection tank 4767, 4867 defining the receiving openings 4779, 4879 has one or more slits 4773, 4873 extending alongside at least a portion of the receiving openings 4779, 4879, and in some embodiments extending around the receiving opening 4779, 4879. In either case, the slits 4773, 4873 are positioned and dimensioned to receive the free ends 4777, 4877 of the flat tubes 4710, 4810. The slits 4773, 4873 also function as stops to limit the depth of insertion of the flat tube ends 4777, 4877.

Following the insertion of the flat tube ends 4777, 4877 into the receiving openings 4779, 4879 and slits 4773, 4873, adhesive 4789, 4889 (not shown) can be injected into gaps 4793, 4893 between the flat tube ends 4777, 4877 and the interior surfaces of the receiving openings 4779, 4879. This injection can be performed in any of the manners described herein, and

is performed by injection through injection openings **4791**, **4891** in the illustrated embodiments of FIGS. **81-83** by way of example. In some embodiments, including those in which deformed flat tube ends are utilized, one or more inserts **4771** can be placed between the flat tube ends **4777** to help prevent deformation of the flat tube ends **4777** when the flat tube ends **4777** are exposed to internal pressure loads. For example, interior folds formed in the embodiment of FIGS. **1-5** can be protected from deformation when exposed to internal pressures by use of such inserts **4771**. In the illustrated embodiment of FIGS. **81** and **83**, for example, the inserts **4771** have a generally trapezoidal cross-sectional shape, although any other cross-sectional shape can be used depending at least in part upon the adjacent shapes of the flat tube ends **4777**. The inserts **4771** can be introduced to their positions adjacent the flat tube ends **4777** before or after application of the adhesive **4789** (e.g., after Station III, or before or after Station IV in FIG. **84**).

If used, the inserts **4771** can be manufactured of any material, including without limitation plastic or metal, can be solid or hollow, and in some embodiments can be defined by an easily deformable or flowable mass that is later hardened. Also, multiple inserts **4771** can be connected prior to and during insertion, such as to a common bar or rail to define a comb-like shape (not shown). This type of insertion, such as by a common bar or rail, can permit two or more, and in some embodiments all of the inserts **4771** to be placed in one step. In some embodiments, the connections between the common bar or rail and the inserts **4771** is frangible, enabling the common bar or rail to be removed subsequent to the insertion of the inserts **4771**.

To enable insertion of the inserts **4771** in desired locations between adjacent flat tube ends **4777**, either or both of the opposite longitudinal walls **4795** of the collection tank **4767** can have apertures (see FIG. **83**, for example) aligned with these locations and dimensioned to enable insertion of the inserts **4771**. In this regard, it should be noted that the inserts **4771** need not necessarily occupy an entire space between adjacent flat tube ends **4777**, and need only occupy sufficient space between the flat tube ends **4777** to support the ends under pressure as needed.

It should be noted that the various manners of introducing adhesive to locations between the flat tube ends **4477**, **4577**, **4677**, **4777**, **4877** and the interior surfaces of the receiving openings **4479**, **4579**, **4679**, **4779**, **4879** described herein can be utilized regardless of whether the flat tube ends **4477**, **4577**, **4677**, **4877** are deformed or undeformed.

In some embodiments of the present invention, the collection tank **4467**, **4567**, **4667**, **4767**, **4867** can include stiffening walls **4469**, **4569**, **4669**, **4769**, **4869** extending between and/or at least partially defining walls of the receiving openings **4469**, **4569**, **4679**, **4779**, **4879** of the collection tank **4467**, **4567**, **4667**, **4767**, **4877**. These stiffening walls **4469**, **4569**, **4669**, **4769**, **4869** can be used to strengthen parts of the collection tank **4467**, **4567**, **4667**, **4767**, **4867** as needed, and are not visible in all illustrated collection tank embodiments. For example, one or more stiffening walls **4669**, **4769**, **4869** can extend in the transverse direction of the collection tank **4667**, **4767**, **4867** (e.g., connecting the opposite longitudinal walls **4695**, **4795**, **4895** of the collection tank **4667**, **4767**, **4867**), and can provide added strength and/or rigidity to the collection tank **4667**, **4767**, **4867**. The stiffening walls **4669**, **4769**, **4869** can be formed in any manner, and can be integral to collection tank **4667**, **4767**, **4867** or separate elements connected thereto in any suitable manner. In some embodiments, the stiffening walls **4669**, **4769**, **4869** are formed dur-

ing injection molding of the collection tank **4667**, **4767**, **4867**, and are thus an integral part of the collection tank **4667**, **4767**, **4867**.

Some embodiments of collection tanks **4667**, **4767**, **4867** according to the present invention can also or instead have stiffening walls extending longitudinally with respect to the collection tank **4667**, **4767**, **4867**. For example, such stiffening walls can be formed between and connect walls defining receiving openings **4679**, **4779**, **4879** of the collection tank **4667**, **4767**, **4867**. A cross-section of one such longitudinal stiffening wall **4469** is shown in FIG. **70A** by way of example, and is located mid-way between the front and rear faces of the collection tank **4667**, **4767**, **4867** (although such longitudinal stiffening walls can be located in other positions as desired). Such longitudinally-extending stiffening walls **4469** can extend along any part or all of the length of the collection tank **4667**, **4767**, **4867** (interrupted as needed by the receiving openings **4679**, **4779**, **4879**).

As mentioned above, the collection tank can be constructed of any number of parts connected together in any suitable manner. By way of example, FIGS. **72** and **82** illustrate collection tanks **4467**, **4867** in which the collection tank **4467**, **4867** is formed of two parts **4467a**, **4467b**, and **4867a**, **4867b**. In both illustrated embodiments, the parts **4467a**, **4467b**, and **4867a**, **4867b** are joined along a Z-shaped interface, and can be joined by welding or adhesive. Still other manners of establishing this connection are possible based at least in part upon the material used to form the collection tank **4467**, **4867**. In some embodiments, this connection is releasable, such as that shown in the embodiments of FIGS. **72-75** where clips on the collection tank **4467** can be used to releasably secure part of the collection tank **4467a** in place with respect to the remainder of the collection tank **4467b**.

The various flat tube embodiments described herein can be utilized in a number of different heat exchangers adapted for different uses. In so doing, the flat tubes can be modified from the embodiments illustrated in FIGS. **1-54** and/or can be assembled in heat exchangers in a variety of different manner to adapt the heat exchangers for particular applications.

FIGS. **85-90** illustrate four constructions of heat exchangers according to different embodiments of the present invention. Although still other heat exchanger embodiments are possible by modifying the number and arrangement of flat tubes and/or by modifying the types of flat tubes (e.g., tube size and shape, insert size and shape, and the like), each of the heat exchangers illustrated in FIGS. **85-91** provides unique advantages in many applications.

Before describing each of the heat exchangers **4963**, **5053**, **5163**, **5263** illustrated in FIGS. **85-90** in greater detail, it should be noted that each of the flat tubes **4910**, **5010**, **5110**, **5210** illustrated therein can be replaced with flat tubes **4910**, **5010**, **5110**, **5210** having any of the shapes and constructed in any of the manners described above with reference to the embodiments of FIGS. **1-54**, and that any of the heat exchanger assembly features and methods of assembly (e.g., regarding the flat tubes, core construction, and core-to-header attachment) also described herein in connection with the embodiments of FIGS. **1-84** can be utilized in the construction and manufacture of the heat exchangers **4963**, **5063**, **5163**, **5263** illustrated in FIGS. **85-90**. For example, each of the flat tubes **4910**, **5010**, **5110**, **5210** illustrated in FIGS. **85-90** is a two-piece flat tube **4910**, **5010**, **5110**, **5210** with insert **4934**, **5034**, **5134**, **5234**, wherein two separate pieces of sheet material are used to form each illustrated tube **4910**, **5010**, **5110**, **5210**, and wherein a third separate piece of sheet material is used to form the internal insert **4934**, **5034**, **5134**, **5234**. Although the particular two-piece flat tube construc-

tions (with inserts) illustrated in FIGS. **85-90** are desirable for the applications described and still other applications, any of these flat tubes **4910, 5010, 5110, 5210** can be replaced by any of the one-piece or other two-piece flat tubes (with inserts) described above and/or illustrated herein in order to adapt the flat tubes **4910, 5010, 5110, 5210** and the resulting heat exchangers **4963, 5063, 5163, 5263** for any desired application. In this regard, a combination of flat tubes **4910, 5010, 5110, 5210** with inserts formed of different numbers of sheets can be used in the same heat exchanger **4963, 5063, 5163, 5263**.

In the illustrated tube constructions of FIGS. **85-91** and any of the alternative tube constructions just mentioned, either or both narrow sides of the flat tube can be formed by adjacent overlapping longitudinal edges of material, depending at least in part upon the number of sheets of material used to construct the flat tube. Each pair of overlapping longitudinal edges therefore defines a reinforced narrow side of the flat tube. In some embodiments, either or both of the overlapping longitudinal edges of the flat tube can be folded one or more times to define even further material thickness at the narrow side(s) of the flat tube. In some of these embodiments, a reinforcing sheet of material defining the insert can have one or both longitudinal edges shaped to lie adjacent the overlapping longitudinal edges of the flat tube, thereby providing an additional layer of material for tube reinforcement at the narrow sides. Also, either or both longitudinal edges of the insert can be folded to have a multiple-layered thickness lying adjacent the overlapping longitudinal edges of the flat tube, thereby providing still further reinforcement at either or both narrow sides. Accordingly, either or both narrow sides of the flat tubes can exhibit a thickness which amounts to at least twice, and in some embodiments more than twice the thickness of the sheet material used to form the flat tube walls, which can be formed by rolling thicker sheet material, in some embodiments.

As described in greater detail above, in those embodiments in which flat tubes are constructed of a single part (with or without an insert), reinforcement of the narrow sides can be achieved by rounding one or more folds of the sheet of material to form the first narrow side of the flat tube, and overlapping the opposite longitudinal edges of the sheet of material to form the second narrow side of the flat tube (e.g., by receiving or encompassing a bend of one longitudinal edge into a larger bend of the other longitudinal edge, or in other manners described herein).

In some one-piece flat tube embodiments, one sheet of material can form the exterior walls of the flat tube as well as the interior flow channels. In such embodiments, a gradation can be located at bends of the sheet of material (defining the narrow sides of the flat tube) at which a longitudinal edge of the sheet of material comes to rest so that the exterior surface of the flat tube remains as smooth as possible. Additionally, in those embodiments in which the insert is defined by a separate sheet of material, the two longitudinal edges of this separate sheet of material can be rounded or otherwise shaped to be received within the narrow sides of the flat tube (e.g., see the illustrated embodiment of FIG. **46**).

As also described in greater detail above, in those embodiments in which flat tubes are constructed of two separate parts (with or without an insert), the two separate parts can be constructed identically, in which cases one longitudinal edge of each part can have a bend encompassing a smaller bend of an adjacent longitudinal edge of the other part. These two separate parts can therefore be transposed with respect to one another in order to form the flat tube. In other embodiments, the two separate parts are not identical to one another, and

have opposite longitudinal edges joined together in any of the manners described herein (including without limitation nested arc-shaped longitudinal edges).

Also, the substantially planar broad sides of any of the tube embodiments described and/or illustrated herein can be used to provide improved brazed joints for fins attached thereto, thereby resulting in improved heat exchange efficiency of the heat exchanger **4963, 5053, 5163, 5263**.

Also in any of the two-piece and three-piece flat tube constructions that can be employed in the heat exchangers of FIGS. **85-89**, the internal insert can be corrugated or otherwise shaped to define two or more flow channels through the flat tube. The internal insert can have corrugations with different shapes and/or sizes at different locations across the width of the insert in order to define two or more laterally disposed regions of flow channels having different shapes and/or sizes (e.g., see FIGS. **85-89**, for example). More broadly, the internal insert can be shaped to define regions of flow channels having different shapes and/or sizes in different locations across the width of the two-piece or three-piece flat tube. In some embodiments, the different regions of flow channels can be isolated from one another, whereas in other embodiments the different regions are in fluid communication with one another (e.g., at one or more locations along the length of one or more flow channels). Also, in some embodiments, each of the flow channels in a region is isolated from the other flow channels in the same region along the length of the flat tube, whereas in other embodiments, the flow channels within the same region are in fluid communication with one another (e.g., via openings between adjacent flow channels), but are isolated from other flow channels in other regions.

It will be appreciated that many of the advantages of using the flat tubes **4910, 5010, 5110, 5210** according to the present invention in the illustrated embodiments of FIGS. **85-89** relate to the ability to manufacture such flat tubes at lower cost, with reduced amounts of material, and/or with improved heat exchange performance. These advantages are realized by the use of sheet materials having the relatively low thicknesses described above for forming the flat tubes and inserts. Although any of the material thicknesses of the flat tubes described above can be used in the embodiments of FIGS. **85-89**, the sheet material used to form the walls of the flat tubes in the illustrated embodiments has a thickness of no greater than about 0.15 mm (0.0059055 in). Also, this sheet material has a thickness of no less than about 0.03 mm (0.0011811 in.). These types of wall thicknesses can be used to withstand compressive loads and can exhibit relatively good internal pressure stability in many embodiments in light of the fact that the insert can be brazed to the broad walls of the flat tube. Similarly, although any of the material thicknesses of the inserts described above can be used in the embodiments of FIGS. **85-89**, the sheet material used to form the inserts in the illustrated embodiments has a thickness of no greater than about 0.09 mm (0.003543 in). Also, this sheet material has a thickness of no less than about 0.03 mm (0.0011811 in.).

By utilizing the various flat tube constructions for the illustrated heat exchangers **4963, 5053, 5163, 5263** and for other heat exchanger designs, advantages of increased production speed and/or reduced material and assembly costs can be realized. For example, based upon the relatively low amount of sheet deformation needed to form the various one- or two-piece flat tubes according to the present invention described above, the flat tubes can be produced more economically on a tube mill (e.g., manufacturing lines **3701** and **1900**, for example) even at high operating speeds using end-

less sheets of material. Moreover, with relatively low modification expenditure, heat exchangers having nearly any depth can be manufacturing using the same source of flat tubing (e.g., continuous or endless tubing and finned tubing produced as described above, for example).

The heat exchangers **4963**, **5063**, **5163**, **5264** illustrated in FIGS. **85-90** are presented not only to illustrate heat exchanger embodiments that provide good performance results in many applications, but also to illustrate a number of heat exchanger features that can be utilized alone or in combination in heat exchangers according to other embodiments of the present invention. Such features include, without limitation, collection tanks that are internally divided to direct separate flows through different internal regions of the same flat tubes, and possible flow arrangements through the heat exchanger.

With reference now to the heat exchanger **4963** illustrated in FIG. **85**, the heat exchanger **4963** has a single row of flat tubes **4910** having a depth *T* (generally similar to the large diameter *D* of each flat tube **4910**). Although any of the other large and small diameters *D*, *d* described above can be used for the flat tubes **4910**, the large diameter *D* of the flat tubes **4910** shown in FIG. **85** is no greater than about 300 mm (11.811 in). In some embodiments, a large diameter *D* of no less than about 10 mm (0.3937 in) is used to provide good performance results. Also, the small diameter *d* of the flat tubes **4910** shown in FIG. **85** is no greater than about 15 mm (0.59055 in). In some embodiments, a small diameter *d* of no less than about 0.7 mm (0.02756 in) is used to provide good performance results. These dimensions of the flat tubes **4910** in the illustrated embodiment of FIG. **85** are particularly suitable for heat exchangers **4963** in motor vehicles. However, other applications are possible and fall within the spirit and scope of the present invention.

The heat exchanger **4963** illustrated in FIG. **85** is adapted to cool two or three fluids by means of a common flow of cooling fluid (e.g., air) passing between the flat tubes **4910**. The cooling air is illustrated in FIG. **86** as a double block arrow which flows through fins (not shown) between the flat tubes **4910**.

According to the illustrated embodiment of FIG. **86**, cooling air can flow either from left to right or vice versa through the cooling network defined by the tube-fin block **4965**. Each of the flat tubes **4910** includes four interior regions **4975a**, **4975b**, **4975c**, **4975d** at different locations along the width of the flat tube **4910**. The four illustrated interior regions **4975a**, **4975b**, **4975c**, **4975d** have the same or substantially the same width, although interior regions **4975a**, **4975b**, **4975c**, **4975d** of different widths are possible in other embodiments. Also, each illustrated interior region **4975a**, **4975b**, **4975c**, **4975d** has a number of flow channels **4916a**, **4916b**, **4916c**, **4916d**, each having a different shape and/or size from the flow channels **4916a**, **4916b**, **4916c**, **4916d** of the other interior regions **4975a**, **4975b**, **4975c**, **4975d**. The shape and size of the flow channels **4916a**, **4916b**, **4916c**, **4916d** in each interior region **4975a**, **4975b**, **4975c**, **4975d** is at least partially defined by the shape of the insert **4934** in that interior region **4975a**, **4975b**, **4975c**, **4975d**. Although the insert varies in shape from interior region to interior region **4975a**, **4975b**, **4975c**, **4975d** in the illustrated embodiment, each flat tube **4410** is substantially the same as the others in the heat exchanger **4963**.

Although four interior regions **4975a**, **4975b**, **4975c**, **4975d** are employed in the heat exchanger **4963** illustrated in FIG. **85**, any number of interior regions **4975a**, **4975b**, **4975c**, **4975d** can be defined by one or more of the flat tubes **4910** in other embodiments, and can have any relative sizes desired. Also, although each portion of the insert **4934** in each interior

region **4975a**, **4975b**, **4975c**, **4975d** of the flat tube **4910** illustrated in FIG. **85** has a shape different from that in the other interior regions **4975a**, **4975b**, **4975c**, **4975d** (thereby defining flow channels **4916a**, **4916b**, **4916c**, **4916d** that are different in each interior region **4975a**, **4975b**, **4975c**, **4975d**), in other embodiments two or more of the interior regions **4975a**, **4975b**, **4975c**, **4975d** can have identical or substantially identical flow channels **4916a**, **4916b**, **4916c**, **4916d**.

With continued reference to FIG. **85**, in some embodiments, each flat tube **4410** in a heat exchanger **4963** or section of the heat exchanger **4963** has the same number of interior regions **4975a**, **4975b**, **4975c**, **4975d** with flow channels **4916a**, **4916b**, **4916c**, **4916d** having the same or substantially the same shape and size. However, this is not necessarily the case in other embodiments. The number, size and shapes of regions within each flat tube **4910** and in a set of flat tubes **4910** can be determined based at least in part upon the requirements of the application.

The heat exchanger **4963** of FIG. **85** includes two collection tanks **4967a** and **4967b**. One collection tank **4967a** includes three dividing walls **4973a**, **4973b**, and **4973c**, which extend in a direction substantially perpendicular to the depth *T* of the heat exchanger **4963**, and which run lengthwise with respect to the collection tanks **4967a**, **4967b**. The other collection tank **4967b** includes two dividing walls **4973d** and **4973e**.

FIG. **85** illustrates a number of arrows indicating the directions of flow through the heat exchanger **4963**. On the left side (with respect to FIG. **85**), a medium flows into the first collection tank **4967a** and through the first interior region **4975a** of each flat tube **4910**. A second medium flows in the first collection tank **4967a** and through the second interior region **4975b** of each flat tube **4910**, and is separated from the flow of the first medium through the first interior regions **4975a** by a first dividing wall **4973a** therein. The second medium is also separated from the first medium at the second collection tank **4967b** by the first dividing wall **4973d** therein, and from a third medium (which can be a second pass of the first medium through the heat exchanger **4963**, in some embodiments, or another medium in other embodiments) at the second collection tank **4967b** by the second dividing wall **4973e** therein. The middle dividing wall **4973b** of the first collection tank **4967a** separates the flow of the second medium entering the heat exchanger **4963** from the return flow of the second medium exiting the heat exchanger **4963** after passing through the third interior region **4975c** of each flat tube **4910**. The third medium passes through the heat exchanger **4963** by flowing through the fourth interior region **4975d** of each flat tube **4910**, and is separated from the second medium in the first collection tank **4967a** by the third dividing wall **4973c** therein.

In some applications of the heat exchanger **4963** just described, the left section of the heat exchanger **4963** (with reference to the perspective of FIG. **85**) can be a high temperature region for charge air. Charge air exiting this section of the heat exchanger **4963** after passing through the first interior region **4975a** of each flat tube **4910** can flow back into the heat exchanger **4963** in some embodiments, passing through the fourth interior region **4975b** of each flat tube **4910** in the right section of the heat exchanger **4963**. Accordingly, this return flow can then be a low temperature region for charge air. In such embodiments, cooling fluid passing between the flat tubes **4910** can flow from right to left in the illustrated embodiment of FIG. **85**. In the middle section of the heat exchanger **4963**, a high temperature cooling fluid can enter into the first collection tank **4967a**, pass through the second interior region **4975b** of each flat tube **4910**, and

return via the second collection tank **4967b** and through the third interior region **4975c** of each flat tube **4910** to exit the heat exchanger **4963**. The return pass of this fluid (upstream of the first pass, as referenced with respect to the direction of flow of cooling fluid passing between the flat tubes **4910**) therefore defines a low temperature coolant region. In some embodiments, 10% of this fluid passing through the second and third interior regions **4975b**, **4975c** can flow through these regions again in order to further reduce its temperature, although other percentages (including none) are possible in other embodiments. Also, in other embodiments, any number of dividing walls **4973a**, **4973b**, **4973c**, **4973d**, **4973e** in any number of collection tanks **4967a**, **4967b** having any number of fluid inlet and outlet ports can be arranged in other manners to provide other heat exchanger designs and functions.

FIG. **86** illustrates a heat exchanger **5063** according to another embodiment of the present invention, in which flat tubes **5010** having the features shown in FIG. **87** are used. The illustrated heat exchanger **5063** is adapted for use in a vehicular cooling fluid radiator, although other applications for the heat exchanger **5063** are possible. This heat exchanger **5063** includes an interior region **5075a**, which can be a high temperature region in some embodiments, based upon the fact that the temperature of the cooling fluid therein is relatively high. The heat exchanger **5063** can also include a low temperature interior region **5075b**, in which the temperature of at least part of the cooling fluid leaving the first interior region **5075a** can be further decreased.

More detail regarding the flat tubes **5010** illustrated in FIG. **86** can be seen in FIG. **87**, which shows a flat tube **5010** according to an embodiment of the present invention that can be used in the heat exchanger **5063** of FIG. **86**. Although the flat tube **5010** illustrated in FIG. **87** provides unique performance results, it should be noted that any of the other flat tube embodiments disclosed herein can instead be used. The flat tube **5010** illustrated in FIG. **87** is formed of two separate sheets of material, each of which form first and second portions **5012**, **5014** of the two-piece tube **5010**. A third sheet of material is used to form the insert **5034**. The first and second portions **5012**, **5014** in the illustrated embodiment are identical or substantially identical, but are transposed with respect to one another. In the manufacturing process, a larger bend defining a larger arc portion is formed on one longitudinal edge of each portion **5012**, **5014**, and encompasses a smaller arc portion formed on a corresponding longitudinal edge of the other portion **5014**, **5012**, so that the two narrow sides **5018**, **5020** of the flat tube **5010** each have a double wall thickness. Furthermore, the opposite longitudinal edges **5038**, **5040** of the insert **5034** are shaped to fit within the inside narrow sides **5018**, **5020** of the flat tube **5010**. In this particular construction, a three-layer thickness is defined on one narrow side **5018**. This thickness can be three times that of the material used to form the first and second portions **5012**, **5014** in those embodiments in which the material thickness of the insert **5034** is the same as that used for the first and second portions **5012**, **5014**, although the insert **5034** can be made of thinner material in other embodiments. It should be noted that the features shown in FIG. **87** can be applied in any of the other flat tube embodiments described and/or illustrated herein.

The two interior regions **5075a**, **5075b** of the flat tubes **5010** in the heat exchanger of FIG. **86** are defined at least in part by the corresponding section of the insert **5034** within each interior region **5075a**, **5075b**. The first interior region **5075a** can be utilized in some embodiments to support relatively higher pressures than fluid in the second interior region **5075b**, by virtue of the relatively narrow flow channels **5016**

defined by the narrower spaces between corrugations of the insert **5034** in the first interior region **5075a**. Also, the second narrow side **5020** corresponding to the second interior region **5075b** has greater reinforcement than the opposite (first) narrow side **5018**. This reinforcement is formed by a longitudinal edge **5040** of the insert **5034** having two additional folds at the second narrow side **5020**, thereby providing the second narrow side **5020** with five layers of material. This design provides an example of how flat tubes **5010** according to the present invention can be reinforced where necessary due to anticipated stresses in selected areas of the flat tubes **5010**, and can be provided with thinner wall areas (e.g., 0.03 mm-0.15 mm (0.0011811-0.0059055) in some embodiments) in other areas where anticipated stresses are relatively low. The weight of materials used to construct the flat tubes **5010** and manufacturing losses of the heat exchanger **5010** can therefore be considerably reduced.

FIG. **88** illustrates a heat exchanger according to another embodiment of the present invention, utilizing the flat tubes **5110** illustrated in FIG. **89**. In the illustrated embodiment of FIGS. **88** and **89**, the inside region **5175** of each flat tube **5110** has a number of flow channels **5116** defined at least in part by an insert **5134** that is uniformly shaped or substantially uniformly shaped across the width of the insert **5134**. However, the heat exchanger **5163** is provided with two different groups **G1**, **G2** of flat tubes **5110** having flow channels **5116** that are different from one another. In other embodiments, any number of such groups are possible. Fluid flowing into or out of each group **G1**, **G2** of flat tubes **5110** is separated from that of the other group **G2**, **G1** by a transverse dividing wall **5173** in the collection tank **5167** extending in the direction of the depth of the heat exchanger **5163**. Different fluids can flow in each group **G1**, **G2** of flat tubes **5110**. For example, in one group **G1**, a first media (e.g. oil) can flow, while in the other group **G2**, a second media (e.g. cooling fluid) can flow. The flat tubes **5110** of group **G2** are generally adapted for a medium which is under higher pressure than that in the flat tubes **5110** of group **G1**, as can be seen from the use of narrower flow channels **5116** and smaller distances between walls of the insert **5134** in the flat tubes **5110** of group **G2**, and the larger degree of reinforcement of the narrow sides **5118**, **5120** in the flat tubes **5110** of group **G2** for relatively more stability. In some applications, the flat tubes **5110** of the group **G2** can define a low temperature cooling fluid radiator portion of the heat exchanger **5163**, while the flat tubes **5110** of the group **G1** can define a high temperature cooling fluid radiator portion of the heat exchanger **5163**.

Under the assumption that the medium in the flat tubes **5110** of group **G2** is under a higher pressure than the medium in the flat tubes **5110** of group **G1**, the broad sides **5122**, **5124** and the narrow sides **5118**, **5120** of the flat tubes **5110** of group **G2** are reinforced by the design of the insert **5134** used therein. In particular, the corrugations of the inserts **5134** in the flat tubes **5110** of group **G2** are significantly narrower than those of the flat tubes **5110** in group **G1**. Additionally, the narrow sides **5118**, **5120** of the flat tubes **5110** in group **G2** have five layers of material (two defined by overlapping longitudinal edges of the first and second tube portions **5112**, **5114** at the narrow sides **5118**, **5120**, and three defined by two folds on each longitudinal edge **5138**, **5140** of the insert **5134**), whereas only three layers of material are located at the narrow sides **5118**, **5120** of the flat tubes **5110** in group **G1** based upon the lack of such insert folds. It should be noted that the flat tubes **5110** within both groups **G1**, **G2** can be identical or substantially identical, and can both be equally adapted to receive the different types of inserts **5134** shown in FIG. **89**. Accordingly, the two different interior regions **5175**

in the flat tubes **5110** are created in this particular embodiment by different inserts **5134** defining two different groups of flat tubes **5110** for the heat exchanger **5163**.

FIG. **90** illustrates a heat exchanger according to yet another embodiment of the present invention, utilizing flat tubes **5210** similar to that of FIG. **53**. In this particular embodiment, the relative sizes of the interior regions **5275a**, **5275b** varies between the flat tubes **5210** of the heat exchanger **5263**. In some embodiments (including the illustrated embodiment of FIG. **90**, for example), the relative sizes of the interior regions **5275a**, **5275b** varies gradually from flat tube **5210** to flat tube **5210** across at least a portion of the heat exchanger **5263**. Accordingly, a collection tank **5267** secured to the flat tubes **5210** can have a dividing wall **5273a** extending obliquely with respect to the ends of the flat tubes **5210**. The position of this dividing wall **5273a** can correspond to the changing size of the interior regions **5275a**, **5275b** in the flat tubes **5210**. If desired, one or more additional dividing walls (e.g., dividing wall **5273b** shown in FIG. **90**) can be included in the collection tank **5267** to provide further separations of flow through the heat exchanger **5263** as desired.

An example of a one-piece flat tube **5310** that can be utilized in any of the heat exchanger embodiments described above is shown in FIG. **91** by way of example. The one-piece flat tube **5310** in FIG. **91** is substantially the same as that shown in FIG. **54** described earlier, with the exception of insert corrugations **5252** that are substantially rectangular in the embodiment of FIG. **91** (as opposed to the substantially triangular corrugations **4352** in the embodiment of FIG. **54**), and with the exception of flow channels **4316**, **5316** having the same size in FIG. **54**, and having different sizes in FIG. **91**. Accordingly, reference is hereby made to the description accompanying FIG. **54** for more information regarding the flat tube embodiment illustrated in FIG. **91**.

The flat tubes **4310**, **5310** in FIGS. **54** and **91** can be produced from a single sheet of material, and can be used in place of any of the flat tubes in the embodiments described above in connection with FIGS. **85-90**. It should also be noted that any of the other one-piece and two-piece flat tubes disclosed herein can be used in place of any of the flat tubes in the embodiments described above in connection with FIGS. **85-90**. The narrow sides **4318**, **4320**, **5318**, **5320** of both flat tubes **4310**, **5310** illustrated in FIGS. **54** and **91** include a double thickness of the sheet of material used to form the flat tube **4310**, **5310**. The sheet of material can be folded twice in the two areas of the sheet of material that will be bent to form the narrow sides **4318**, **4320**, **5318**, **5320** of the flat tube **4310**, **5310** (i.e., the areas adjacent and flanking that portion of the sheet of material shaped to define the integral insert **4334**, **5334**), thereby increasing the thickness of the narrow areas by three times that of the original material thickness. Furthermore, each longitudinal edge of the sheet of material can be bent and moved to encompass a respective reinforced section in the manner shown in FIGS. **54** and **91**. Both of these reinforced sections can be provided with a gradation **4358**, **4360** (not visible in FIG. **91**, but visible in FIG. **54**) for receiving the corresponding longitudinal edges in a recessed manner. In order to further reinforce the narrow sides **4318**, **4320**, **5318**, **5320** of the flat tube **4310**, **5310**, additional folds can be incorporated into the reinforced sections shown in FIGS. **54** and **91**. In the flat tube **5310** illustrated in FIG. **91**, two groups of flow channels **5316** are defined, each having a size that is different from those of the other group. In contrast, all the flow channels **4316** in the illustrated embodiment of FIG. **54** are substantially the same in size.

FIGS. **19-23** show a number of different flat tubes that can be produced from a single sheet of material. Like the other

one-piece flat tubes illustrated herein, each of the embodiments shown in FIGS. **19-23** are especially suitable for the heat exchangers **4963**, **5063**, **5163**, **5263** discussed in connection with FIGS. **85-90**. In particular, the flat tubes described above in connection with FIGS. **19-23** include narrow sides that are reinforced by the provision of vertical or horizontal folds. Additionally, FIG. **46** illustrates a flat tube **3710** that can be produced from a single piece of sheet material, with an insert **3734** that can be produced from another separate sheet of material. This particular flat tube **3710** can also serve as a replacement for any of the flat tubes **4910**, **5010**, **5110**, **5210** described above with respect to FIGS. **85-90**. As described in greater detail above, in the embodiment of FIG. **46**, one reinforced narrow side **3718** is formed by bending a portion of the sheet of material having additional folds. The other reinforced narrow side **3720** is formed by one longitudinal edge of the sheet of material encompassing the opposite longitudinal edge of the same sheet of material. This other narrow side **3720** can also be distinguished by the fact that either or both longitudinal edges of the sheet of material can be folded for further reinforcement. The second sheet of material can be provided with a number of corrugations as described above, and can also be provided with bends or folds at either or both longitudinal edges **3738**, **3740** for further interior reinforcement of either or both narrow sides **3718**, **3720**.

FIGS. **92-95** illustrate exemplary heat exchanger structures and methods for connecting sheets of material to form a heat exchanger or a portion of a heat exchanger (e.g., a heat exchanger core, a portion of a heat exchanger core, a tube insert, heat exchanger tubes, the ribs or fins of a heat exchanger, the header of a heat exchanger, and the like). For example, in the illustrated embodiments of FIGS. **93-95**, fins **8313** are brazed to a heat exchanger tube **8310**. In these illustrated embodiments, the heat exchanger tubes **8310** are formed from a generally planar first sheet of material **8317**, and the fins **8313** are formed from a second sheet of material **8333** having a corrugated shape. In other embodiments, the sheets of material being brazed are different portions of the same sheet of material. Also, in other embodiments and as explained in greater detail below, the heat exchanger tubes **8310** and/or the fins **8313** can have different shapes.

Although the methods described herein are with reference to the production of particular heat exchanger embodiments described in this patent application, such is by way of example only. Accordingly, it is to be understood that the processes described with reference to FIGS. **92-95** can be applied for the manufacture of all heat exchangers and portions of heat exchangers described in this application.

As explained above, the relatively small sheet material thickness of the heat exchanger tubes **8310** and/or the fins **8313** in some embodiments of the present invention can provide significant advantages relating to the overall performance of the heat exchanger, manufacturability, and possible wall constructions (as disclosed herein) that are not possible using thicker wall materials. Also, by utilizing one or more of the flat tube features described herein, the inventors have discovered that a number of different flat tubes having various characteristics adapted for a variety of applications can be constructed using significantly reduced material while retaining strength and heat exchange properties of heavier conventional flat tubes. Moreover, while reference is made herein to flat heat exchanger tubes, the present invention can also or alternatively be applied to heat exchanger tubes having different cross-sectional shapes including without limitation round, rectangular, triangular, or other polygonal shapes, irregular shapes, and the like.

83

In some embodiments, the heat exchanger tubes **8310**, the heat exchanger fins **8313**, and/or other portions of a heat exchanger can be formed from sheets of material having the same or substantially the same thickness. Alternatively, in other embodiments, two or more portions of the heat exchanger can be formed from sheets of material having different thicknesses. In some of these other embodiments, the heat exchanger tubes **8310** can be formed from sheets of material **8317** having a first thickness, and the heat exchanger fins **8313** can be arranged between adjacent tubes **8310** and can be formed from sheets of material **8333** having a different thickness. In such embodiments, a first portion of the heat exchanger (e.g., a header) can be formed from sheets of material having a first thickness, a second portion of the heat exchanger (e.g., at least one of the tubes) can be formed from sheets of material having a second thickness, and a third portion of the heat exchanger (e.g., the fins **8333**) can be formed from sheets of material having a third thickness.

For example, in some embodiments of the present invention, a flat tube **8310** can be formed from sheets of material **8317** having a thickness of no greater than about 0.20 mm (0.007874 in). However, in other embodiments and as mentioned above, the inventors have discovered that heat exchanger tubes formed from sheets of material having a thickness of no greater than about 0.15 mm (0.0059055 in) provides significant advantages relating to the overall performance of flat tubes and heat exchangers made from such material, manufacturability, and possible wall constructions (as disclosed herein) that are not possible using thicker wall materials. Alternatively or in addition, the fins **8313** can be formed from sheets of material **8333** having a thickness of no greater than about 0.20 mm (0.007874 in). In other embodiments, the fins **8313** can be formed from sheets of material **8333** having a thickness of no greater than about 0.15 mm (0.0059055 in). In still other embodiments, the fins **8313** can be formed from sheets of material **8333** having a thickness in the range of approximately 0.03-0.15 mm (0.0011811-0.0059055 in) or slightly higher. In yet other embodiments, heat exchanger fins **8313** can be formed from sheets of material **8333** having a thickness of no greater than about 0.03-0.09 mm (0.0011811-0.0035433 in).

As shown in FIGS. **92-95**, a first sheet of material **8317** manufactured according to some embodiments of the present invention can include a braze layer **8335** providing at least a portion of an outer surface **X1** of the first sheet of material **8317**, an inner sacrificial layer or corrosion protection layer **8337** disposed under the braze layer **8335** or a portion of the braze layer **8335**, and a core **8315** disposed under the sacrificial layer **8337** (shown as a single layer in FIGS. **92** and **94**, and as having two or more layers in FIGS. **93** and **95**). As used herein and in the appended claims, terms such as “under”, “beneath”, “over”, and “above” are used only for ease of description, and do not alone indicate or imply that the structure referred to must have any particular orientation taken alone or employed in any structure.

The core **8315** in the illustrated embodiments of FIGS. **92-95** comprise an aluminum alloy by way of example. The aluminum alloy can have suitable amounts of one or more other materials, such as manganese, magnesium, titanium, copper, and the like, used to increase the strength and/or corrosion resistance of the core **8315**, or for changing one or more other characteristics of the core **8315** as desired.

In some embodiments, the core **8315** is changed to produce a layer **8339** (sometimes referred to herein as a sub-layer of the core **8315**) having one or more different properties than the rest of the core **8315**. For example, by diffusing silicon within an upper portion of the core **8315** at an elevated tem-

84

perature, such as during a brazing process, the structure and/or composition of the aluminum alloy in the upper portion can change to define the layer **8339** in which the silicon diffused (see FIG. **93**, which illustrates such a process performed on the structure of FIG. **92**). In some embodiments, this change can occur by the production of intermetallic compounds comprising the silicon, such as a silicon-manganese aluminum intermetallic compound. In so doing, one or more components of the aluminum alloy in the layer **8339** (e.g., manganese, by way of example only) can accumulate while the sheet of material **8317** is heated sufficiently to permit such accumulation, resulting in a modified layer **8339** of the core **8315** in which intermetallic compound has accumulated in locations throughout the modified layer **8339**. In some embodiments, the silicon can facilitate this accumulation, such as by drawing one or more of the alloy components out of solid solution, or facilitating this accumulation in other manner.

The thickness of the modified layer **8339** can be dependent upon the temperature at which the above-referenced diffusion occurs and the time permitted for such diffusion to occur (e.g., the duration of a brazing cycle). In some embodiments, the modified layer **8339** is anodic with respect to the rest of the core **8315**. For example, in those embodiments in which manganese has been drawn out of solid solution and has accumulated as an intermetallic as a result of silicon diffusion into the core **8315**, the resulting modified layer **8339** can be anodic with respect to the rest of the core **8315**.

With continued reference to the embodiments of FIGS. **91-95**, and as described above, the illustrated sheet of material **8317** includes one or more sacrificial layers **8337** (one in FIGS. **92** and **93**, and two in FIGS. **94** and **95**). Each sacrificial layer **8337** can include a metal material, and can be a relatively pure or unalloyed metal material. In some embodiments, the sacrificial layer **8337** comprises an aluminum alloy through which silicon diffuses at a slower rate than that through the underlying core material **8315**, and has a corrosion potential as described herein. For example, in some embodiments, the sacrificial layer **8337** comprises an aluminum alloy through which silicon diffuses at no more than 50% of the rate at which silicon diffuses through the underlying core material **8315**. In other embodiments, the sacrificial layer **8337** comprises an aluminum alloy through which silicon diffuses at no more than 70% of the rate at which silicon diffuses through the underlying core material **8315**. In this regard, the sacrificial layer **8337** can have trace amounts of one or more additional materials (e.g., iron, copper, zinc, manganese, magnesium, like metals, and combinations of such metals, by way of example). In some embodiments, the sacrificial layer **8337** has a corrosion potential that is substantially similar to the corrosion potential of the adjacent residual braze material of the braze layer **8335** following a brazing process. In this regard, it should be noted that following a brazing process, a residual amount of braze material can remain on any portion or all of the sheet of material **8317**. Also in some embodiments, the material of the sacrificial layer **8337** is anodic to the material of the core **8315** (e.g., to the modified layer **8339** and/or to the rest of the core **8315**).

In some embodiments, the braze layer **8335** comprises an aluminum-silicon alloy brazing material. In other embodiments, other brazing materials can also or alternatively be used, some of which comprise silicon. The braze layer **8335** can extend across substantially the entire outer surface of the sheet of material **8317**, or can instead extend across less than the entire outer surface (e.g., across intended brazing locations only) of the sheet of material **8317**. The braze layer **8335** can be part of the sheet of material **8317** to be used in a brazing operation, or can be deposited upon and/or formed by a por-

tion of the sheet of material **8317** during the brazing process. In either case, the residual brazing material of the braze layer **8335** following a brazing process can be anodic to the material of the sacrificial layer **8337**.

Any of the layers and/or sub layers of the sheet of material **8317** described herein and/or illustrated in FIGS. **92-95** can be secured together by roll bonding. By way of example only, the sub-layer **8339** of the core **8315** described above can be produced by roll bonding a layer of material having the sub-layer properties described above onto another layer of material to produce the core **8317** illustrated in FIG. **93**.

As will now be explained, sheets of material **8317** formed according to the present invention can reduce and/or prevent corrosion (such as pitting corrosion, by way of example). In some embodiments, one or more of the layers and sub layers of the sheet of material **8317** (e.g., the braze layer **8335**, the sacrificial layer **8337**, the sub layer **8339**, and/or the rest of the core **8315**) can be formed from a material or alloyed with a material such that it is anodic to one or more of the underlying layers or sub layers of the sheet of material **8317**. For example, in some embodiments, each of the layers and sub layers of the sheet of material **8317** (i.e., residual braze material of the braze layer **8335** following a brazing process, the sacrificial layer **8337**, the sub layer **8339**, and/or the rest of the core **8315**) can be formed from a material or alloyed with a material such that it is anodic to an underlying layer or sub layer and is cathodic to an adjacent overlying layer or sub layer after brazing.

In some embodiments, one or more layers and sub layers of the sheet of material **8317** (i.e., the braze layer **8335**, the sacrificial layer **8337**, the sub layer **8339**, and/or the rest of the core **8315**) is formed from a material or alloyed with a material such that there is a difference of at least about 30 millivolts between one or more of the underlying layers or sub layers. For example, in some embodiments, each of the layers and sub layers of the sheet of material **8317** (e.g., the braze layer **8335**, the sacrificial layer **8337**, the sub layer **8339**, and/or the rest of the core **8315**) can be formed from a material or alloyed with a material such that there is a difference of at least about 30 millivolts between each adjacent layer, or between layers or sub-layers separated from one another.

As mentioned above, in some embodiments the core **8315** include titanium. In sufficient quantities, titanium can form dendrites during casting of the core **8315**, resulting in layers of titanium-rich aluminum disbursed throughout the core **8315**. Depending at least in part upon the manner in which the sheet of material defining the core **8315** is produced, the titanium-rich aluminum can be located primarily in the sacrificial layer **8337**, primarily in the rest of the core **8315**, or fully throughout the core **8315**. In some embodiments, the titanium-rich aluminum can form sub-layers in the core **8315**, and can serve as another measure of resistance to core material corrosion. Such sub-layers can also be cathodic to adjacent portions of the core **8315** for further corrosion resistance.

In those embodiments in which titanium-rich aluminum is formed in sub-layers of the core material as just described, the titanium-rich aluminum can help increase corrosion resistance by forcing corrosion to propagate in directions parallel or substantially parallel to the core **8315**, or in directions parallel or substantially parallel to the titanium-rich aluminum sub-layers, thereby helping to slow or reduce pitting corrosion. In some embodiments, the material of the core **8315** comprises about 0.05-0.30 wt-% titanium. In other embodiments, a core layer **8315** having about 0.10-0.25 wt-% of titanium provides good strength and corrosion resistance performance. However, in many embodiments, a sheet of material **8317** having a core **8315** with a core layer **8315**

having a titanium content of approximately 0.20 wt-% or slightly higher provides improved overall performance.

In some embodiments, the sheet of material **8317** has a thickness of no greater than about 0.15 mm (it being noted that any of the relatively thin tube wall and insert material thicknesses disclosed herein can be used). For example, the sheet of material in the illustrated embodiment of FIGS. **92** and **93** has a thickness of approximately 100 μm (3.937 mil). As described above, some embodiments of the present invention have a modified core sub-layer **8339** that can be produced by diffusion of silicon therein. The silicon can diffuse from the sacrificial layer **8337** or from the brazing material **8335** into the core **8315** in such embodiments. Such diffusion can take place during a brazing process. In light of the fact that the rate of diffusion into the core **8315** can at least partially determine the resulting depth of the modified core sub-layer **8339**, control of such diffusion is possible by the sacrificial layer **8337**. In this regard, the sacrificial layer **8337** can function to impede (but not stop) such silicon diffusion, and can comprise a material (e.g., an aluminum alloy more resistant to silicon diffusion and having the corrosion potential as described above) in which silicon diffuses at a slower rate than the material of the core **8315**. By utilizing such a sacrificial layer **8337**, silicon diffusion can be limited to a depth of 50 μm (1.969 mil) while still permitting sufficient brazing time at a sufficiently high brazing temperature to braze the fin **8313** to the sheet of material **8317**. In some embodiments, the manufacturing process described herein can prevent or significantly reduce diffusion beyond a depth of 30 μm (1.181 mil).

In embodiments in which two or more portions of the heat exchanger are secured together, a second portion of the heat exchanger (e.g., the fins **8313**) can also or alternatively include a braze layer formed on or applied to an outer surface, an inner sacrificial layer disposed under the braze layer or a portion of the braze layer, and a core disposed under the sacrificial layer. Alternatively or in addition, a core of the sheet of material used for forming the second portion of the heat exchanger (e.g., the fins **8313**) can include an outer portion or layer of modified core material as described above. Moreover, each of the layers and sub layers of the sheets of material used for forming the second portion of the heat exchanger (e.g., the fins **8313**) can be anodic to one or more underlying layers or sub layers. In some such embodiments, each of the layers and sub layers of the sheets of material **8333** used for forming the second portion of the heat exchanger (e.g., the fins **8313**) is formed from a material or alloyed with a material such that there is a difference of at least about 30 millivolts between each adjacent layer of the second portion of the heat exchanger.

In some embodiments in which two or more portions of the heat exchanger are secured together, a first portion of the heat exchanger can be formed from a sheet of material having an outer portion or layer which is substantially anodic to an outer layer or portion of a second portion of the heat exchanger. For example, as shown in FIGS. **92-95**, in some such embodiments, an outer portion or layer of the fin **8313** can be formed from a sheet of material **8333** which is anodic to a sheet of material **8317** used to form the heat exchanger tube **8310**.

Alternatively or in addition, the outer portion or layer of the fin **8313** can be formed from a sheet of material **8333** which is anodic to a residual alpha-phase layer **8341** formed from the brazing material between the outer surfaces of the heat exchanger tube **8310** and the fin **8313**. In some such embodiments, the residual alpha-phase layer **8341** is anodic to the sacrificial layer **8337** of the sheet of material **8317** forming the heat exchanger tube **8310**.

In some embodiments of the present invention, first and second portions of a heat exchanger can be connected to opposite sides of a third portion of the heat exchanger. For example, in the illustrated embodiment of FIGS. 94 and 95, a heat exchanger tube 8310 having first and second outer surfaces X1, X2 is formed from a first sheet of material 8317. As shown in FIGS. 94 and 95, each side of the sheet of material 8317 can include a braze layer 8335 providing at least a portion of the outer surfaces X1, X2 of the first sheet of material 8317, an inner sacrificial layer or corrosion protection layer 8337 disposed under the braze layer 8335 or a portion of the braze layer 8335, and a core 8315 disposed between the sacrificial layers 8337. In some embodiments, the both outer sides of the core 8315 can include a sub layer 8339 of modified core material.

The inventors have found that corrosion protection for heat exchangers or portions of heat exchangers with relatively small wall thicknesses (e.g., wall thicknesses of less than about 0.20 mm (0.007874 in)) can be improved if the brazing time (i.e., the time when the heat exchanger or the portion of the heat exchanger being brazed passes through the brazing furnace) is reduced. The inventors have determined that a reduction of approximately 10% in brazing time shows desired results and can provide, among other advantages, good strength and corrosion resistance. Furthermore, results can be improved if the brazing time is further reduced by approximately one half.

More particularly, the inventors have found that increasing the brazing speed can reduce the diffusion of silicon from the braze layer 8335 into the underlying layers or sub layers of the sheet of material 8317. The diffusion of silicon is illustrated in FIGS. 93 and 95 with dashed arrows. The diffusion depth of the silicon can be less than about 50 μ m (1.969 mil), or in some embodiments, can be significantly less. FIG. 96 graphically illustrates this relationship. The dashed curve in FIG. 96 represents the progression of the diffusion of the silicon, while the solid curve represents the progression of the diffusion in accordance with conventional materials and brazing techniques.

In some embodiments of the present invention, heat exchangers or portions of heat exchangers being brazed are placed on a conveyor or a similar transport device, which passes through different temperature zones of a CAB brazing furnace. In some such embodiments, the temperature of the brazing furnace can be in the range of approximately 577-610° C. (1070-1130° F.).

The optimal brazing time for a specific heat exchanger or for a specific portion of a heat exchanger depends, at least in part, upon the total mass of the heat exchanger or the portion of the heat exchanger being brazed, the temper condition of the sheets of material being brazed, the thickness of the sheets of material being brazed, and the composition of the sheets of material being brazed. For example, in some embodiments, the transport speed for brazing heat exchangers or portions of heat exchangers with wall thicknesses of 0.20 mm (0.007874 in) or more in a CAB brazing furnace is approximately 0.5-1.5 m/min (19.69-59.055 in/min).

Before brazing a heat exchanger or portion of a heat exchanger, the inventors have found that material samples having material properties substantially similar or identical to the heat exchanger or the portion of the heat exchanger being brazed can be used to experimentally determine an optimal temperature profile for the specific material of the heat exchanger or portion of the heat exchanger being brazed. The inventors have also found that by determining an optimal temperature profile, it is possible to increase the transport speed of the heat exchanger or the portion of the heat

exchanger being brazed to about 1.5-4.0 m/min (4.92-13.12 ft/min), thereby reducing the brazing time.

In some embodiments, non-corrosive flux can be applied to the outer surface X1 of one or both aluminum sheets of material 8317, 8333 prior to brazing. In some embodiments, it may not be necessary to apply flux material to the outer surface X1 of one or both sheets of material 8317, 8333 to achieve high quality brazed connections. Moreover, in some embodiments, including embodiments in which flux material is not applied to the surfaces of the sheets of material 8317, 8333 prior to brazing, the inventors have determined that high quality internal brazing connections can be created in a controlled atmosphere by adding one or more alloys, such as, for example, magnesium and/or lithium to the sheets of material 8317, 8333.

Various features and advantages of the invention are set forth in the following claims.

What is claimed is:

1. A method of forming a heat exchanger tube, the method comprising:
 - providing a first sheet of material extending along a first longitudinal direction;
 - providing a second sheet of material extending along a second longitudinal direction;
 - transporting the first sheet of material along a first path using a first drive;
 - transporting the second sheet of material along a second path using a second drive;
 - shaping a longitudinal edge of the first sheet of material while transporting the first sheet of material;
 - shaping a plurality of longitudinally-extending peaks and valleys into the second sheet of material while transporting the second sheet of material to produce an insert for the heat exchanger tube;
 - perforating a first location at which the first sheet of material will be separated;
 - perforating a second location at which the second sheet of material will be separated;
 - after perforating the first and second locations, adjusting at least one of a speed of the first drive to adjust a speed of the first sheet of material with respect to the second sheet of material and a speed of the second drive to adjust a speed of the second sheet of material with respect to the first sheet of material to longitudinally align the first and second locations to desired positions relative to one another during transport;
 - inserting a longitudinal edge of the second sheet of material into the shaped longitudinal edge of the first sheet of material;
 - enclosing the insert within walls of the tube defined at least in part by the first sheet of material; and
 - separating the walls of the tube with the enclosed insert from upstream portions of the first and second sheets of material at the first and second locations during transport of the first and second sheets of material.
2. The method of claim 1, wherein the first and second directions are substantially parallel.
3. The method of claim 1, further comprising:
 - transporting a third sheet of material along a third path;
 - shaping a longitudinal edge of the third sheet of material while transporting the third sheet of material; and
 - inserting the insert into the third sheet of material;
 wherein enclosing the insert within walls of the tube includes enclosing the insert between the first and third sheets of material.
4. The method of claim 3, further comprising nesting opposite longitudinal edges of the first and third sheets of material

with corresponding opposite longitudinal edges of the third and first sheets of material, respectively.

5. The method of claim 1, wherein enclosing the insert within walls of the tube includes enclosing the insert between opposing broad sides of the first sheet of material joined by opposing narrow sides of the first sheet of material.

6. The method of claim 1, further comprising nesting another edge of the first sheet of material into the shaped longitudinal edge of the first sheet of material.

7. The method of claim 1, wherein the step of perforating the first sheet of material comprises:

weakening the first sheet of material in a first line extending laterally across the first sheet of material; and

wherein the step of perforating the second sheet of material comprises weakening the second sheet of material in a second line extending laterally across the second sheet of material.

8. The method of claim 1, wherein shaping the plurality of longitudinally-extending peaks and valleys into the second sheet of material occurs before inserting the longitudinal edge of the second sheet of material.

9. The method of claim 1, further comprising inverting the first sheet of material prior to enclosing the insert within walls of the tube.

10. The method of claim 1, wherein:

the first sheet of material has a cross-sectional shape lying substantially in a first plane; and

the insert has a cross-sectional shape lying substantially in a second plane,

the method further comprising changing a relative rotational position of the insert with respect to the first sheet of material from a first position in which the first plane is at an acute angle with respect to the second plane to a second position in which the first and second planes are substantially parallel while transporting the insert and the second sheet of material.

11. The method of claim 1, wherein the first sheet of material has a thickness no greater than about 0.15 mm.

12. A method of forming a heat exchanger tube, the method comprising:

forming a longitudinally extending first sheet of material to define an exterior of the heat exchanger tube while transporting the first sheet of material along a first travel path using a first drive;

forming a longitudinally extending second sheet of material to define an insert of the heat exchanger tube while transporting the second sheet of material along a second travel path using a second drive;

perforating a first location at which the first sheet of material will be separated;

perforating a second location at which the second sheet of material will be separated;

after perforating the first and second locations, adjusting a speed of at least one of the first and second drives to adjust a speed of at least one of the first and second sheets of material;

changing a longitudinal position of the first location with respect to the second location by adjusting the speed of at least one of the first and second drives;

placing the first and second locations into a desired longitudinal alignment by changing the longitudinal position of the first sheet of material with respect to the second sheet of material by adjusting the speed of at least one of the first and second drives;

inserting the insert into the formed first sheet of material while transporting the first and second sheets of material;

enclosing the insert within exterior walls of the heat exchanger tube at least partially defined by the first sheet of material while transporting the first and second sheets of material; and

separating the insert and the exterior walls of the heat exchanger tube from upstream portions of the first and second sheets of material at the first and the second locations while transporting the first and second sheets of material.

13. The method of claim 12, further comprising:

forming a longitudinally extending third sheet of material to further define the exterior of the heat exchanger tube while transporting the third sheet of material along a third travel path; and

inserting the insert into the formed third sheet of material while transporting the first, second, and third sheets of material;

wherein enclosing the insert within exterior walls of the heat exchanger tube includes enclosing the insert between the first and third sheets of material.

14. The method of claim 13, further comprising nesting opposite longitudinal edges of the first and third sheets of material with corresponding opposite longitudinal edges of the third and first sheets of material, respectively.

15. The method of claim 12, wherein enclosing the insert within exterior walls of the heat exchanger tube includes enclosing the insert between opposing broad sides of the first sheet of material joined by opposing narrow sides of the first sheet of material.

16. The method of claim 12, further comprising nesting opposite edges of the first sheet of material into one another to enclose the insert.

17. The method of claim 12, wherein the step of perforating the first sheet of material comprises:

weakening the first sheet of material in a first line extending laterally across the first sheet of material; and

wherein the step of perforating the second sheet of material comprises weakening the second sheet of material in a second line extending laterally across the second sheet of material.

18. The method of claim 12, further comprising forming the insert prior to inserting the insert.

19. The method of claim 12, further comprising inverting the first sheet of material prior to enclosing the insert.

20. The method of claim 12, wherein:

the first sheet of material has a cross-sectional shape lying substantially in a first plane; and

the insert has a cross-sectional shape lying substantially in a second plane,

the method further comprising changing a relative rotational position of the insert with respect to the first sheet of material from a first position in which the first plane is at an acute angle with respect to the second plane to a second position in which the first and second planes are substantially parallel while transporting the insert and the second sheet of material.

21. The method of claim 12, wherein the first sheet of material has a thickness no greater than about 0.15 mm.