



US 20160228338A9

(19) **United States**
(12) **Patent Application Publication**
DIHORA et al.

(10) **Pub. No.: US 2016/0228338 A9**
(48) **Pub. Date: Aug. 11, 2016**
CORRECTED PUBLICATION

(54) **SHAMPOO COMPOSITIONS WITH
INCREASED DEPOSITION OF
POLYACRYLATE MICROCAPSULES**

(60) Provisional application No. 61/472,898, filed on Apr. 7, 2011.

(71) Applicant: **The Procter & Gamble Company,**
Cincinnati, OH (US)

Publication Classification

(72) Inventors: **Jiten Odhavji DIHORA**, Liberty Twp.,
OH (US); **Mark Anthony BROWN**,
Union, KY (US)

(51) **Int. Cl.**
A61K 8/11 (2006.01)
A61Q 13/00 (2006.01)
A61K 8/81 (2006.01)
A61Q 5/02 (2006.01)

(21) Appl. No.: **14/540,953**

(52) **U.S. Cl.**
CPC ... *A61K 8/11* (2013.01); *A61Q 5/02* (2013.01);
A61Q 13/00 (2013.01); *A61K 8/817* (2013.01);
A61K 2800/56 (2013.01)

(22) Filed: **Nov. 13, 2014**

Prior Publication Data

(15) Correction of US 2015/0071976 A1 Mar. 12, 2015
See (60) Related U.S. Application Data.

(57) **ABSTRACT**

(65) US 2015/0071976 A1 Mar. 12, 2015

Related U.S. Application Data

(63) Continuation of application No. 13/439,525, filed on
Apr. 4, 2012, now Pat. No. 8,927,026.

A shampoo composition that increases the deposition and retention of benefit agent containing polyacrylate microcapsules onto hair during the cleansing process. The shampoo composition is based on the combination of anionic charged polyacrylate microcapsules, cationic deposition polymers, deterative surfactant, and a carrier.

SHAMPOO COMPOSITIONS WITH INCREASED DEPOSITION OF POLYACRYLATE MICROCAPSULES

FIELD OF THE INVENTION

[0001] The present invention relates to shampoo compositions containing polyacrylate microcapsules, wherein the polyacrylate microcapsules have increased deposition onto hair.

BACKGROUND OF THE INVENTION

[0002] Many of the shampoo products in the market today work to deliver benefits to hair by depositing benefit agents such as perfumes, silicones, dyes, and anti-dandruff agents onto the hair during washing. As a result, there is a desire to maximize the effectiveness of such benefit agents by increasing their delivery and retention onto hair. One method of achieving this objective is to encapsulate such benefit agents in microcapsules. While these microcapsules are able to encapsulate a wide variety of benefit agents and deliver them to hair, they are still often washed off of the hair before their benefit can be fully realized. Consumers today desire shampoo compositions that deposit and retain encapsulated benefit agents on the hair and the scalp, even after the rinsing process is complete.

[0003] However, obtaining good deposition of microcapsules onto hair during cleansing is further complicated by the action of deterative surfactants in shampoo. Deterative surfactants are designed to carry away oil, grease, and dirt from the hair and scalp, but can also interfere with the deposition of the encapsulated benefit agents. When microcapsules are washed away, relatively high levels of encapsulated benefit agents may be needed in the shampoo composition to deliver the consumer desired benefit.

[0004] Accordingly, there is a need for a shampoo composition that provides an increased deposition of encapsulated benefit agents onto the hair. In addition, there is a need for a polymer system that associates with microcapsule surfaces, and that when sheared, allows the encapsulated benefit agents to be released. Furthermore, there is a need for a shampoo composition that provides an increased retention of encapsulated benefit agents onto the hair during the rinse-off process.

SUMMARY OF THE INVENTION

[0005] A shampoo composition for cleansing a substrate, comprising: from about 0.001% to about 10% of an anionic charged polyacrylate microcapsule; from about 0.01% to about 2% of a cationic deposition polymer; from about 2% to about 25% of a deterative surfactant; and a carrier.

[0006] A method of making a shampoo composition, wherein the composition is formed by a process comprising the steps of: coating a polyacrylate microcapsule with an anionic emulsifier to form an anionic polyacrylate microcapsule; combining the anionic polyacrylate microcapsule with a cationic deposition polymer to form a premix; adding the premix to a deterative composition comprising surfactant and a carrier.

[0007] A method of making a shampoo composition, wherein the composition is formed by a process comprising the steps of: coating a polyacrylate microcapsule with an anionic emulsifier to form an anionic polyacrylate microcapsule; combining the anionic polyacrylate microcapsule with a cationic deposition polymer to form a premix; adding the

premix to an anionic surfactant; adding the resulting composition of step (c) to a deterative composition comprising surfactant and a carrier.

DETAILED DESCRIPTION OF THE INVENTION

[0008] In all embodiments of the present invention, all percentages are by weight of the total composition, unless specifically stated otherwise. All ratios are weight ratios, unless specifically stated otherwise. All ranges are inclusive and combinable. The number of significant digits conveys neither a limitation on the indicated amounts nor on the accuracy of the measurements. All numerical amounts are understood to be modified by the word “about” unless otherwise specifically indicated. Unless otherwise indicated, all measurements are understood to be made at 25° C. and at ambient conditions, where “ambient conditions” means conditions under about one atmosphere of pressure and at about 50% relative humidity. All such weights as they pertain to listed ingredients are based on the active level and do not include carriers or by-products that may be included in commercially available materials, unless otherwise specified.

Definitions

[0009] As used herein, the term “personal care composition” includes, unless otherwise indicated, any personal care composition that can be applied to the keratinaceous surfaces of the body including the skin and/or hair. The personal cleansing compositions can be, for example, formulated as shampoos, hair tonics, hair colorants, sprays, mousses and/or other styling products.

[0010] As used herein, the term “fluid” includes liquids and gels.

[0011] As used herein, the terms “microcapsule,” “encapsulated benefit agents,” and “solid particulates,” refers to polyacrylate microcapsules.

[0012] As used herein, the term “premix” refers to the combination of anionic polyacrylate microcapsules with cationic deposition polymers.

[0013] As used herein, the term “shampoo composition” refers to the combination of deterative surfactant and carrier.

[0014] As used herein, the articles including “a” and “an” when used in a claim, are understood to mean one or more of what is claimed or described.

[0015] As used herein, the terms “include,” “includes,” and “including,” are meant to be non-limiting.

[0016] The test methods disclosed in the Test Methods Section of the present application should be used to determine the respective values of the parameters of Applicants’ inventions.

[0017] Unless otherwise noted, all component or composition levels are in reference to the active portion of that component or composition, and are exclusive of impurities, for example, residual solvents or by-products, which may be present in commercially available sources of such components or compositions.

[0018] All percentages and ratios are calculated by weight unless otherwise indicated. All percentages and ratios are calculated based on the total composition unless otherwise indicated.

[0019] It should be understood that every maximum numerical limitation given throughout this specification includes every lower numerical limitation, as if such lower numerical limitations were expressly written herein. Every minimum numerical limitation given throughout this speci-

cation will include every higher numerical limitation, as if such higher numerical limitations were expressly written herein. Every numerical range given throughout this specification will include every narrower numerical range that falls within such broader numerical range, as if such narrower numerical ranges were all expressly written herein.

Benefits of Anionic Polyacrylate Microcapsules

[0020] Consumers desire a shampoo that deposits and retains encapsulated benefit agents onto their hair and scalp during the cleansing process. Traditionally, a variety of approaches have been employed to improve deposition of microcapsules, including (1) using specific block copolymers to covalently bind to the microcapsules, and (2) using cationic water soluble polymers to coat the microcapsules in order to increase the affinity of the microcapsules to the substrate of interest. However, it is desired to have improved deposition over the traditional approaches.

[0021] It has been surprisingly found that a synergy exists between anionic emulsifiers and polyacrylate microcapsules, resulting in anionic polyacrylate microcapsules. When such anionic microcapsules are mixed with certain cationic deposition polymers, microstructures are formed at the surface of the anionic polyacrylate. Such anionic microstructures display high viscoelasticity, remain in tact even upon dilution during cleansing, and display strong adhesion to keratinaceous hair surfaces. Combined with shampoo, these properties result in improved delivery efficiency of the encapsulated benefit agents to hair.

[0022] It is believed that the shampoo compositions comprising anionic polyacrylate microcapsules, along with specific cationic deposition polymers, delivers a higher deposition rate than shampoos containing non-anionic polyacrylates. In addition, anionic polyacrylate microcapsules with specific cationic deposition polymers also have a higher retention rate on hair even in the presence of deterative surfactants and carriers found in shampoo compositions. Applicants surprising discovery of adding anionic emulsifier to microcapsules to form anionic microcapsules can be accomplished by either: (1) adding the anionic emulsifier to an already formed microcapsule or (2) allowing the anionic emulsifier to associate with the microcapsule surface during the microcapsule making process. Once formed, the anionic polyacrylate microcapsules are combined with the specific cationic polymer(s) chosen to form a premix for addition to an anionic surfactant containing shampoo composition.

Anionic Emulsifier

[0023] The addition of an anionic emulsifier forms a microstructure with a specified cationic deposition polymer at the external surface of the microcapsules, i.e., the anionic emulsifier is at least a part of the external surface of the microcapsules, or is physically or chemically bound to the external surface of the microcapsules. Such physical bindings include, for example, hydrogen bonding, ionic interactions, hydrophobic interactions, and electron transfer interactions. Such chemical bindings include, for example, covalent bindings such as covalent grafting and crosslinking.

[0024] The anionic emulsifier is present at a level by weight of from about 0.1% to about 40%, from about 0.5% to about 10%, or from about 0.5% to about 5%, by weight of the polyacrylate microcapsules.

[0025] A variety of anionic emulsifiers can be used in the shampoo composition of the present invention as described below. The anionic emulsifiers include, by way of illustrating and not limitation, water-soluble salts of alkyl sulfates, alkyl ether sulfates, alkyl isothionates, alkyl carboxylates, alkyl sulfosuccinates, alkyl succinamates, alkyl sulfate salts such as sodium dodecyl sulfate, alkyl sarcosinates, alkyl derivatives of protein hydrolyzates, acyl aspartates, alkyl or alkyl ether or alkylaryl ether phosphate esters, sodium dodecyl sulphate, phospholipids or lecithin, or soaps, sodium, potassium or ammonium stearate, oleate or palmitate, alkylaryl-sulfonic acid salts such as sodium dodecylbenzenesulfonate, sodium dialkylsulfosuccinates, dioctyl sulfosuccinate, sodium dilaurylsulfosuccinate, poly(styrene sulfonate) sodium salt, isobutylene-maleic anhydride copolymer, gum arabic, sodium alginate, carboxymethylcellulose, cellulose sulfate and pectin, poly(styrene sulfonate), isobutylene-maleic anhydride copolymer, gum arabic, carrageenan, sodium alginate, pectic acid, tragacanth gum, almond gum and agar; semi-synthetic polymers such as carboxymethyl cellulose, sulfated cellulose, sulfated methylcellulose, carboxymethyl starch, phosphorylated starch, lignin sulfonic acid; and synthetic polymers such as maleic anhydride copolymers (including hydrolyzates thereof), polyacrylic acid, polymethacrylic acid, acrylic acid butyl acrylate copolymer or crotonic acid homopolymers and copolymers, vinylbenzenesulfonic acid or 2-acrylamido-2-methylpropanesulfonic acid homopolymers and copolymers, and partial amide or partial ester of such polymers and copolymers, carboxymodified polyvinyl alcohol, sulfonic acid-modified polyvinyl alcohol and phosphoric acid-modified polyvinyl alcohol, phosphorylated or sulfated tristyrylphenol ethoxylates.

[0026] In addition, it is desirable to use anionic emulsifiers that have acrylate functionality since these can be covalently linked to the shell portion of the polyacrylate microcapsules during the microcapsule making process. Anionic emulsifiers useful herein include, but aren't limited to: poly(meth)acrylic acid; copolymers of (meth)acrylic acids and its (meth)acrylates with C1-22 alkyl, C1-C8 alkyl, butyl; copolymers of (meth)acrylic acids and (meth)acrylamide; Carboxyvinylpolymer; acrylate copolymers such as Acrylate/C10-30 alkyl acrylate crosspolymer, Acrylic acid/vinyl ester copolymer/Acrylates/Vinyl Isodecanoate crosspolymer, Acrylates/Palmeth-25 Acrylate copolymer, Acrylate/Steareth-20 Itaconate copolymer, and Acrylate/Celeth-20 Itaconate copolymer; Polystyrene sulphonate, copolymers of methacrylic acid and acrylamidomethylpropane sulfonic acid, and copolymers of acrylic acid and acrylamidomethylpropane sulfonic acid; carboxymethylcellulose; carboxy guar; copolymers of ethylene and maleic acid; and acrylate silicone polymer. Neutralizing agents may be included to neutralize the anionic emulsifiers herein. Non-limiting examples of such neutralizing agents include sodium hydroxide, potassium hydroxide, ammonium hydroxide, monoethanolamine, diethanolamine, triethanolamine, diisopropanolamine, aminomethylpropanol, tromethamine, tetrahydroxypropyl ethylenediamine, and mixtures thereof. Commercially available anionic emulsifiers include, for example, Carbomer supplied from Noveon under the tradename Carbopol 981 and Carbopol 980; Acrylates/C10-30 Alkyl Acrylate Crosspolymer having tradenames Pemulen TR-1, Pemulen TR-2, Carbopol 1342, Carbopol 1382, and Carbopol ETD 2020, all available from Noveon; sodium carboxymethylcellulose supplied from Hercules as CMC series; and Acrylate copolymer having a

tradename Capigel supplied from Seppic. In another embodiment, anionic emulsifiers are carboxymethylcelluloses.

Polyacrylate Microcapsules

[0027] Various processes for microencapsulation, and exemplary methods and materials, are set forth in U.S. Pat. No. 6,592,990; U.S. Pat. No. 2,730,456; U.S. Pat. No. 2,800,457; U.S. Pat. No. 2,800,458; and U.S. Pat. No. 4,552,811. Each patent described throughout this application is incorporated herein by reference to the extent each provides guidance regarding microencapsulation processes and materials.

[0028] The present invention teaches a low permeability microcapsule comprising a core material and a wall material at least partially surrounding, and in another embodiment, completely surrounding, a core material. In the present invention, the polyacrylate microcapsules are benefit agent microcapsule particulates which encapsulate benefit agents by capsule wall materials comprised of polymers.

[0029] Capsule wall materials useful herein include, for example, those formed from melamine-formaldehyde or urea-formaldehyde condensates, melamine-resorcinol or urea-resorcinol condensates, as well as similar types of aminoplasts, gelatin, polyurethane, polyamide, polyolefin, polysaccharide, protein, silicone, lipid, modified cellulose, gums, polyacrylate, polyphosphate, polystyrene, and polyesters, or combinations of these materials. In another embodiment, a wall material that provides low permeability is polyacrylate.

[0030] The benefit agents of said core may comprise a material selected from the group consisting of perfumes; brighteners; enzymes; perfumes; sensates in one aspect a cooling agent; attractants, anti-bacterial agents; dyes; pigments; bleaches; and mixtures thereof.

[0031] In one aspect of said polyacrylate microcapsules, said benefit agent may comprise an anti-dandruff agent. Suitable, non-limiting examples of anti-dandruff agents include: pyridinethione salts, azoles, selenium sulfide, particulate sulfur, and mixtures thereof. Other embodiments include pyridinethione salts, specifically the zinc salt of 1-hydroxy-2-pyridinethione (known as "zinc pyridinethione" or "ZPT"). Such anti-dandruff particulate should be physically and chemically compatible with the essential components of the composition, and should not otherwise unduly impair product stability, aesthetics or performance.

[0032] In addition to the anti-dandruff actives selected from polyvalent metal salts of pyrrhione, the present invention may further comprise one or more anti-fungal or anti-microbial actives. Suitable anti-microbial actives include coal tar, sulfur, whitfield's ointment, castellani's paint, aluminum chloride, gentian violet, octopirox (piroctone olamine), ciclopirox olamine, undecylenic acid and its metal salts, potassium permanganate, selenium sulphide, sodium thiosulfate, propylene glycol, oil of bitter orange, urea preparations, griseofulvin, 8-Hydroxyquinoline ciloquinol, thiobendazole, thiocarbamates, haloprogyn, polyenes, hydroxypyridone, morpholine, benzylamine, allylamines (such as terbinafine), tea tree oil, clove leaf oil, coriander, palmarosa, berberine, thyme red, cinnamon oil, cinnamic aldehyde, citronellic acid, hinokitol, ichthyol pale, Sensiva SC-50, Elestab HP-100, azelaic acid, lyticase, iodopropynyl butylcarbamate (IPBC), isothiazalinones such as octyl isothiazalinone and azoles, and combinations thereof. Examples of anti-microbials include itraconazole, ketoconazole, selenium sulphide and coal tar.

[0033] The polyacrylate microcapsules useful herein are those releasing the benefit agents for a period of time after initial application. Potential trigger mechanisms for release of the encapsulated benefit agents may include, but are not limited to, mechanical forces, dehydration, light, pH, temperature, or even changes in ionic strength.

Process of making Anionic Polyacrylate Microcapsules

[0034] An anionic polyacrylate microcapsule can be formed by either: (1) coating an already formed microcapsule with an anionic emulsifier; or (2) adding the anionic emulsifier to the microcapsule during the microcapsule making process. Any known method for generating a microcapsule is useful herein. Example methods for making polyacrylate microcapsules are disclosed in U.S. Patent Application 61/328,949; U.S. Patent Application 61/328,954; U.S. Patent Application 61/328,962; and U.S. Patent Application 61/328,967.

[0035] In one embodiment, polyacrylate microcapsules are formed from water in oil, or oil in water emulsifications. During the polyacrylate microcapsule making process, a first composition is prepared as an oil phase. The oil phase may comprise oil; an oil soluble or dispersible primary, secondary, or tertiary amine; a multifunctional acrylate or methacrylate monomer or oligomer; an oil soluble acid; an initiator, and combinations thereof. In one embodiment, a nitrogen blanket is employed while the solution is mixed. Gradually, the temperature is increased to create a first composition reaction product. After the first composition reaction product is formed, a second composition is added to the reaction product.

[0036] The second composition is prepared as a water phase. The water phase may comprise water; an emulsifier that may be water soluble or water dispersible polymer or copolymer; at least one water phase initiator; one or more of an alkali or alkali salt, and combinations thereof. By water phase initiator, it is meant that the initiator is soluble or dispersible in water.

[0037] The second composition is then added to the oil solution of the first composition reaction product. This addition creates an oil-in-water emulsion. The reaction of the first composition in the presence of the second composition results in the formation of a low permeability microcapsule wall. The emulsion is further heated for a time and temperature sufficient to decompose the free radicals which are present in either one or both of the oil and water phases.

[0038] Furthermore, the polymerization of the monomers and oligomers in the oil phase causes a precipitation of the polymerized material. The precipitation of microcapsule wall material forms at the interface of the water and oil phases.

[0039] The anionic polyacrylate microcapsule is contained in the composition at a level by weight of from about 0.01% to about 50%, from about 0.05% to about 10%, from about 0.1% to about 8%, or from about 0.25% to 3%.

[0040] The anionic polyacrylate microcapsules useful herein are those having a particle size of from about 1 micron to about 80 microns, from about 2 microns to about 50 microns, and from about 5 microns to about 30 microns.

A. Coating a Microcapsule

[0041] In one embodiment of the invention, the anionic emulsifier is added to an already formed polyacrylate microcapsule. The anionic emulsifier attaches to the surface of the microcapsule through hydrogen bonding, van der Waals forces, ionic interactions, hydrophobic interactions, or

chemical reactions. In one aspect, the anionic emulsifier surrounds at least a part of the external surface of the polyacrylate microcapsule, or is physically or chemically bound to the external surface of the polyacrylate microcapsule.

B. Adding Anionic Emulsifier to a Microcapsule

[0042] In another embodiment, the anionic emulsifier associates with the microcapsule surface during the microcapsule making process. When making the microcapsule, the anionic emulsifier is solubilized in an aqueous phase, which may optionally contain a free radical initiator, prior to emulsification of the oil. The excess aqueous phase is then added to the oil phase to form an oil-in-water emulsion. The emulsion is then heated for a time and at a temperature sufficient to decompose the free radicals which are positioned in one or both of the oil and aqueous phases. Microcapsule wall material is thereby formed at the interface of the water and oil phases. In one embodiment, when the emulsifier is comprised of acrylate moieties, the emulsifier may become chemically bound to the interfacial wall material.

C. Forming the Premix

[0043] Once the anionic polyacrylate microcapsule is formed by either formation step, the anionic polyacrylate microcapsule is added to a cationic deposition polymer to form a premix. It has been surprisingly found that the anionic charge on the polyacrylate microcapsule leads to the formation of a microstructure on the shell of the microcapsule when combined with a cationic deposition polymer in the premix. This premix exhibits anionic polyacrylate microcapsules that have a higher viscoelasticity to the hair than microcapsules without an anionic charge and specific cationic deposition polymer thus giving a benefit to the hair.

Slurry/Agglomerate

[0044] In one embodiment, the anionic polyacrylate microcapsules are contained in a slurry. The slurry may be combined with an adjunct ingredient to form a composition, for example, a shampoo consumer product.

[0045] In one aspect, the slurry may comprise one or more processing aids, selected from the group consisting of water, aggregate inhibiting materials such as divalent salts; particle suspending polymers such as xanthan gum, guar gum, and carboxy methyl cellulose. In another embodiment, said processing aids may be selected from the group consisting of amphoteric surfactants such as cocamidopropyl betaine (CAPB), zwitterionic surfactants, cationic swellable polymers, latex particles such as acrylic based ester Rheovis CDE, and mixtures thereof.

[0046] In one aspect, the slurry may comprise a carrier selected from the group consisting of polar solvents, including but not limited to, water, ethylene glycol, propylene glycol, polyethylene glycol, glycerol; nonpolar solvents, including but not limited to, mineral oil, perfume raw materials, silicone oils, hydrocarbon paraffin oils, and mixtures thereof.

[0047] In another embodiment, the anionic polyacrylate microcapsules are contained in an agglomerate with a second material. In one aspect, said second materials may comprise a material selected from the group consisting of silicas, citric acid, sodium carbonate, sodium sulfate, sodium chloride, and binders such as sodium silicates, modified celluloses, polyethylene glycols, polyacrylates, polyacrylic acids, zeolites and mixtures thereof.

Cationic Deposition Polymer

[0048] The shampoo composition of the present invention comprises a cationic deposition polymer that forms a premix when added to the anionic polyacrylate microcapsules. Any known natural or synthetic cationic deposition polymer can be used herein. Examples include those polymers disclosed in U.S. Pat. No. 6,649,155; U.S. patent application Ser. No. 12/103,902; U.S. Patent Publication 2008/0206355; and U.S. Patent Publication No. 2006/0099167A1.

[0049] The cationic deposition polymer is included in the composition at a level from about 0.01% to about 2%, in one embodiment from about 1.5% to about 1.9%, in another embodiment from about 1.8% to about 2.0%, in view of providing the benefits of the present invention.

[0050] The cationic deposition polymer is a water soluble polymer with a charge density from about 0.5 milliequivalents per gram to about 12 milliequivalents per gram. The cationic deposition polymer used in the composition has a molecular weight of about 100,000 Daltons to about 5,000,000 Daltons. The cationic deposition polymer is a low charge density cationic polymer.

[0051] In one embodiment, the cationic deposition polymer is a synthetic cationic deposition polymer. A variety of synthetic cationic deposition polymers can be used including mono- and di-alkyl chain cationic surfactants. In one embodiment, mono-alkyl chain cationic surfactants are chosen including, for example, mono-alkyl quaternary ammonium salts and mono-alkyl amines. In another embodiment, di-alkyl chain cationic surfactants are used and include, for example, dialkyl (14-18) dimethyl ammonium chloride, ditallow alkyl dimethyl ammonium chloride, dihydrogenated tallow alkyl dimethyl ammonium chloride, distearyl dimethyl ammonium chloride, dicetyl dimethyl ammonium chloride, and mixtures thereof.

[0052] In another embodiment, the cationic deposition polymer is a naturally derived cationic polymer. The term, "naturally derived cationic polymer" as used herein, refers to cationic deposition polymers which are obtained from natural sources. The natural sources may be polysaccharide polymers. Therefore, the naturally derived cationic polymer may be selected from the group comprising starches, guar, cellulose, Cassia, locust bean, Konjac, Tara, galactomannan, tapioca, and synthetic polymers. In a further embodiment, cationic deposition polymers are selected from Mirapol 100S (Rhodia), Jaguar C17, polyDADMAC, Tapioca starch (Akzo), polyTriquat, and mixtures thereof.

Forming a Premix

[0053] The cationic deposition polymer and the anionic polyacrylate microcapsule are mixed to form a premix before addition to the detergent composition comprising a detergent surfactant and a carrier.

[0054] The weight ratio of the anionic polyacrylate microcapsule to the cationic deposition polymer (based on the dry weight of the anionic microcapsules and the dry weight of the cationic deposition polymer) is from about 0.5:30 to about 20:1, from about 5:15 to about 15:1, and from about 5:1 to about 12:1. It is believed that too much cationic polymer may not provide enhanced and/or prolonged benefits to the benefit agent microcapsules due to the formation of excess cationic polymer coating on the capsule wall. This excess coating may prevent the microcapsule wall from breaking and releasing the benefit agents.

[0055] Microcapsules and anionic emulsifiers may be dispersed in solvents such as water while mixing with the cationic deposition polymer. In one embodiment, the amount of water present is from about 90% to about 50%, in another embodiment from about 70% to about 50%, and in another embodiment from about 60% to about 50%. In another embodiment of the invention, the anionic emulsifiers associate with the microcapsule walls to form anionic polyacrylate microcapsules prior to their mixing with cationic deposition polymers.

Deterative Composition

[0056] The deterative composition can be all aqueous phase or may comprise both an oil phase and an aqueous phase. In one embodiment, the deterative composition has both an oil phase and an aqueous phase. After being added to the deterative composition, the polyacrylate microcapsules reside in the aqueous phase of such embodiments.

[0057] The deterative composition may comprise any combination of the following components:

A. Deterative Surfactant

[0058] The shampoo composition of the present invention includes a deterative surfactant. The deterative surfactant provides cleaning performance to the composition. The deterative surfactant in turn comprises anionic deterative surfactant, zwitterionic or amphoteric deterative surfactant, or combinations thereof. Various examples and descriptions of deterative surfactants are set forth in U.S. Pat. No. 6,649,155; U.S. patent application Ser. No. 12/103,902; and U.S. Patent Publication 2008/0206355, and are incorporated herein for reference.

[0059] The concentration of the anionic surfactant component in the shampoo should be sufficient to provide the desired cleaning and lather performance, and generally ranges from about 2% to about 50%, from about 8% to about 30%, from about 10% to about 25%, or from about 12% to about 22%.

[0060] Anionic surfactants suitable for use in the compositions are the alkyl and alkyl ether sulfates. Other suitable anionic deterative surfactants are the water-soluble salts of organic, sulfuric acid reaction products. Still other suitable anionic deterative surfactants are the reaction products of fatty acids esterified with isethionic acid and neutralized with sodium hydroxide. Other similar anionic surfactants are described in U.S. Pat. Nos. 2,486,921; 2,486,922; and 2,396,278.

[0061] Anionic deterative surfactants for use in the shampoo composition include ammonium lauryl sulfate, ammonium laureth sulfate, triethylamine lauryl sulfate, triethylamine laureth sulfate, triethanolamine lauryl sulfate, triethanolamine laureth sulfate, monoethanolamine lauryl sulfate, monoethanolamine laureth sulfate, diethanolamine lauryl sulfate, diethanolamine laureth sulfate, lauric monoglyceride sodium sulfate, sodium lauryl sulfate, sodium laureth sulfate, potassium lauryl sulfate, potassium laureth sulfate, sodium lauryl sarcosinate, sodium lauroyl sarcosinate, lauryl sarcosine, cocoyl sarcosine, ammonium cocoyl sulfate, ammonium lauroyl sulfate, sodium cocoyl sulfate, sodium lauroyl sulfate, potassium cocoyl sulfate, potassium lauryl sulfate, triethanolamine lauryl sulfate, triethanolamine lauryl sulfate, monoethanolamine cocoyl sulfate, monoethanolamine lauryl sulfate, sodium tridecyl benzene sulfonate, sodium dodecyl

benzene sulfonate, sodium cocoyl isethionate and combinations thereof. In a further embodiment of the present invention, the anionic surfactant is sodium lauryl sulfate or sodium laureth sulfate.

[0062] Suitable amphoteric or zwitterionic deterative surfactants for use in the shampoo composition herein include those which are known for use in hair care or other personal care cleansing. Concentrations of such amphoteric deterative surfactants range from about 0.5% to about 20%, and from about 1% to about 10%. Non limiting examples of suitable zwitterionic or amphoteric surfactants are described in U.S. Pat. No. 5,104,646 (Bolich Jr. et al.), U.S. Pat. No. 5,106,609 (Bolich Jr. et al.).

[0063] Amphoteric deterative surfactants suitable for use in the shampoo composition include those surfactants broadly described as derivatives of aliphatic secondary and tertiary amines in which the aliphatic radical can be straight or branched chain and wherein one of the aliphatic substituents contains from about 8 to about 18 carbon atoms and one contains an anionic group such as carboxy, sulfonate, sulfate, phosphate, or phosphonate. Amphoteric deterative surfactants for use in the present invention include cocoamphoacetate, cocoamphodiaceate, lauroamphoacetate, lauroamphodiaceate, and mixtures thereof.

[0064] Zwitterionic deterative surfactants suitable for use in the composition include those surfactants broadly described as derivatives of aliphatic quaternaryammonium, phosphonium, and sulfonium compounds, in which the aliphatic radicals can be straight or branched chain, and wherein one of the aliphatic substituents contains from about 8 to about 18 carbon atoms and one contains an anionic group such as carboxy, sulfonate, sulfate, phosphate or phosphonate. In another embodiment, zwitterionics such as betaines are selected.

[0065] Non limiting examples of other anionic, zwitterionic, amphoteric or optional additional surfactants suitable for use in the compositions are described in McCutcheon's, *Emulsifiers and Detergents*, 1989 Annual, published by M. C. Publishing Co., and U.S. Pat. Nos. 3,929,678, 2,658,072; 2,438,091; 2,528,378.

B. Anti-Dandruff Actives

[0066] The shampoo compositions of the present invention may also contain an anti-dandruff agent. Suitable, non-limiting examples of anti-dandruff agents include: antimicrobial actives, pyridinethione salts, azoles, selenium sulfide, particulate sulfur, keratolytic acid, salicylic acid, octopirox (piroctone olamine), coal tar, and combinations thereof. In one aspect, the anti-dandruff agents typically are pyridinethione salts. Such anti-dandruff agents should be physically and chemically compatible with the essential components of the composition, and should not otherwise unduly impair product stability, aesthetics or performance.

[0067] Pyridinethione anti-dandruff agents are described, for example, in U.S. Pat. No. 2,809,971; U.S. Pat. No. 3,236,733; U.S. Pat. No. 3,753,196; U.S. Pat. No. 3,761,418; U.S. Pat. No. 4,345,080; U.S. Pat. No. 4,323,683; U.S. Pat. No. 4,379,753; and U.S. Pat. No. 4,470,982. It is contemplated that when ZPT is used as the anti-dandruff particulate in the compositions herein, that the growth or re-growth of hair may be stimulated or regulated, or both, or that hair loss may be reduced or inhibited, or that hair may appear thicker or fuller.

C. Aqueous Carrier

[0068] The formulations of the present invention can be in the form of pourable liquids (under ambient conditions). Such compositions will therefore typically comprise an aqueous carrier, which is present at a level of from about 20% to about 95%, or even from about 60% to about 85%. The aqueous carrier may comprise water, or a miscible mixture of water and organic solvent, and in one aspect may comprise water with minimal or no significant concentrations of organic solvent, except as otherwise incidentally incorporated into the composition as minor ingredients of other essential or optional components.

[0069] The carrier useful in the present invention includes water and water solutions of lower alkyl alcohols and polyhydric alcohols. The lower alkyl alcohols useful herein are monohydric alcohols having 1 to 6 carbons, in one aspect, ethanol and isopropanol. The polyhydric alcohols useful herein include propylene glycol, hexylene glycol, glycerin, and propane diol.

D. Other Optional Components

[0070] The shampoo composition may further comprise other optional ingredients that are known for use or otherwise useful in compositions. Such optional ingredients are most typically those described in reference books such as the CTFA Cosmetic Ingredient Handbook, Second Edition, The Cosmetic, Toiletries, and Fragrance Association, Inc. 1988, 1992.

[0071] Further non-limiting examples of such optional ingredients include perfumes or fragrances, coloring agents or dyes, hair bleaching agents, thickeners, moisturizers, emollients, pharmaceutical actives, vitamins or nutrients, anti-dandruff agents, perfumes, hair colorants, hair perming agents, hair growth or restorer agents, and similar other materials.

Method of Manufacture

[0072] The shampoo compositions of the present invention can be prepared by the process comprising: 1) coating a polyacrylate microcapsule with an anionic emulsifier to form an anionic polyacrylate microcapsule; 2) combining the anionic polyacrylate microcapsule with a cationic deposition polymer to form a premix; and 3) adding the premix to a deterative composition comprising surfactant and a carrier.

[0073] In another embodiment, the shampoo compositions of the present invention can be prepared by the process comprising: 1) coating a polyacrylate microcapsule with an anionic emulsifier to form an anionic polyacrylate microcapsule; 2) combining the anionic polyacrylate microcapsule with a cationic deposition polymer to form a premix; 3) adding the premix to an anionic surfactant; and 4) adding the resulting composition of step (3) to a deterative composition comprising surfactant and a carrier.

[0074] It has been unexpectedly found that the association of anionic polyacrylate microcapsules combined with cationic deposition polymers has a higher viscoelasticity than in the absence of the mixed components thus giving a better adhesion of the anionic microcapsules to the hair.

[0075] For example, when an anionic emulsifier comprising a copolymer of acrylic acid and butyl acrylate (molecular weight of 40,000 g/mol), is mixed with various cationic polymers to form a polymer premix, the result is a significant increase in viscoelasticity. This increase indicates a strong

polyelectrolyte interaction which is exemplified in the increase in viscoelastic component G' as the quantity of cationic polymer increases (See Table 1)

TABLE 1

Viscoelasticity as a function of anionic:cationic polymer premix ratio.					
Sample Description	Anionic Emulsifier (wt %)	Cationic Polymer (wt %)	Anionic Surfactant (wt %)	G' at 1 Hz (Pascals)	G'' at 1 Hz (Pascals)
1:5 Anionic:Cationic	5.10%	25.48%	0.00%	0.369	6.55
1:10 Anionic:Cationic	2.78%	27.79%	0.00%	0.178	7.22
1:20 Anionic:Cationic	1.46%	29.12%	0.00%	0.233	7.92

[0076] Furthermore, when an anionic surfactant is added to the polymer premix, a substantial increase in viscoelasticity is also noted. Such an increase in viscoelasticity is influenced by the strength of the association between the cationic deposition polymer and the anionic surfactant. This is exemplified in the increase in viscoelastic component G' upon addition of anionic surfactant to the premix (See Table 2).

TABLE 2

Viscoelasticity as a function of anionic surfactant addition to polymer premix.					
Sample ID	Anionic Emulsifier	Cationic Polymer	Anionic Surfactant	G' at 1 Hz (Pascals)	G'' at 1 Hz (Pascals)
1:5 Anionic:Cationic	3.05%	15.25%	10.87%	42	105.6
1:10 Anionic:Cationic	1.65%	16.48%	11.74%	37.1	7.1
1:20 Anionic:Cationic	0.86%	17.17%	12.23%	118.2	133.9

[0077] In one embodiment of the invention, an anionic emulsifier is covalently bonded to the outer wall of the polyacrylate microcapsule by incorporating the anionic emulsifier during the microcapsule making process. In another embodiment, the anionic emulsifier is added to the slurry comprising a fully formed polyacrylate microcapsule. After forming the anionic polyacrylate microcapsule through either step, a cationic deposition polymer is then added to the anionic microcapsule to form a viscoelastic premix. When this premix is then combined with an anionic surfactant, an association of polymers forms a microstructure on the anionic polyacrylate microcapsule wall. The microstructure forms upon dilution of the shampoo composition. Once formed, the high viscosity of the polymer association microstructure results in an anionic polyacrylate microcapsule that maintains its microcapsule structure even upon dilution of the shampoo during washing. In addition, the microcapsule structure provides multiple points of contact to the substrate which works to resist rinse-off of the microcapsules during the use of the shampoo composition.

[0078] The polyacrylate microcapsules of the present invention can be formulated into any suitable form and prepared by any process chosen by the formulator, non-limiting examples of which are described in U.S. Pat. No. 5,879,584; U.S. Pat. No. 5,691,297; U.S. Pat. No. 5,574,005; U.S. Pat.

No. 5,569,645; U.S. Pat. No. 5,565,422; U.S. Pat. No. 5,516,448; U.S. Pat. No. 5,489,392; U.S. Pat. No. 5,486,303 all of which are incorporated herein by reference.

[0079] Any suitable method of making the shampoo of the present invention may be used non-limiting examples of which are described in U.S. Pat. No. 5,879,584; U.S. Pat. No. 5,691,297; U.S. Pat. No. 5,574,005; U.S. Pat. No. 5,569,645; U.S. Pat. No. 5,565,422; U.S. Pat. No. 5,516,448; U.S. Pat. No. 5,489,392; U.S. Pat. No. 5,486,303 all of which are incorporated herein by reference.

Product Forms

[0080] The shampoo compositions of the present invention can be in the form of rinse-off products or leave-on products, and can be formulated in a wide variety of product forms, including but not limited to creams, gels, emulsions, mousses and sprays.

[0081] In one embodiment, the shampoo composition is in the form of a gel comprising less than about 45% water. In such embodiment, the gel may have a neat viscosity of about 1,000 cps to about 10,000 cps. The neat viscosity of a gel can be defined as the viscosity of the fluid at a shear rate of 1/sec. Scientifically, viscosity is the ratio of shear stress to shear rate. In some embodiments, the range of shear rates for gels is from 0.01/sec to 10/sec.

[0082] Neat viscosity of the gel product form can be measured with a rheometer according to the following method:

[0083] (1) Load the sample onto the plate.

[0084] (2) Establish a gap of 1 millimeter between the 1 degree cone and the plate.

[0085] (3) Perform a shear sweep on the fluid from 0.01/sec to 10/sec.

[0086] (4) Record the shear stress response of the fluid.

[0087] (5) Determine the neat viscosity of the fluid by calculating the ratio of shear stress to shear rate at each shear rate.

Test Methods

[0088] It is understood that the test methods that are disclosed in the Test Methods Section of the present application should be used to determine the respective values of the parameters of Applicants' invention as such invention is described and claimed herein.

A. ClogP

[0089] The "calculated logP" (ClogP) is determined by the fragment approach of Hansch and Leo (cf., A. Leo, in *Comprehensive Medicinal Chemistry*, Vol. 4, C. Hansch, P. G. Sammens, J. B. Taylor, and C. A. Ramsden, Eds. P. 295, Pergamon Press, 1990, incorporated herein by reference). ClogP values may be calculated by using the "CLOGP" program available from Daylight Chemical Information Systems Inc. of Irvine, Calif. U.S.A.

B. Boiling Point

[0090] Boiling point is measured by ASTM method D2887-04a, "Standard Test Method for Boiling Range Distribution of Petroleum Fractions by Gas Chromatography," ASTM International.

C. Median Particle Size

[0091] Particle size is measured using an Accusizer 780A, made by Particle Sizing Systems, Santa Barbara Calif. The instrument is calibrated from 0 to 300 μ m using Duke particle size standards. Samples for particle size evaluation are pre-

pared by diluting about 1 g of capsule slurry in about 5 g of de-ionized water and further diluting about 1 g of this solution in about 25 g of water.

[0092] About 1 g of the most dilute sample is added to the Accusizer and the testing initiated, using the autodilution feature. The Accusizer should be reading in excess of 9200 counts/second. If the counts are less than 9200 additional sample should be added. The accuser will dilute the test sample until 9200 counts/second and initiate the evaluation. After 2 minutes of testing the Accusizer will display the results, including volume-weighted median size.

[0093] The broadness index can be calculated by determining the particle size at which 95% of the cumulative particle volume is exceeded (95% size), the particle size at which 5% of the cumulative particle volume is exceeded (5% size), and the median volume-weighted particle size (50% size—50% of the particle volume both above and below this size). Broadness Index (5) = ((95% size) - (5% size) / 50% size).

D. Olfactive Analysis of Shampoo Product

[0094] Analysis steps include:

[0095] a. 0.4 millileters of Shampoo product is applied to a hair switch (IHL, 4 grams, 8 inches long, moderately damaged grade) that has been combed, wet, and lightly squeegeed. Lather switch 50-60 strokes (30 seconds) in a milking action.

[0096] b. Rinse with stationary shower rinse with no manipulation of hair (100 degrees Fahrenheit water temperature, water flow at 1.5 gallons per minute, for 30 seconds, water hardness of 8 grains per gallon). Lightly squeegee once down the hair switch from top to bottom between fingers after rinsing to remove excess water.

[0097] c. Repeat application of product per step (a), milking, rinsing, and squeegeing per step (b).

[0098] d. Leave hair to dry at ambient temperature by hanging it on a rack. After approximately 3 hours, olfactively grade the hair switch according to the Primavera Grade (0-100 scale for intensity, where a 10 point difference is consumer noticeable). Record this as the Initial Pre-Comb fragrance intensity.

[0099] e. Comb the hair switch 3 times and olfactively grade, record this as the Initial Post-Comb fragrance intensity.

[0100] f. Leave the hair switch under ambient conditions (70 degrees Fahrenheit and 30% relative humidity) for 24 hours. Then, olfactively grade the hair switch according to the Primavera Grade (0-100 scale for intensity, where a 10 point difference is consumer noticeable), record this as the 24 hr aged Pre-Comb olfactive intensity. Comb the hair switch 3 times and assign an olfactive grade, record this as the 24 hr aged Post-Comb olfactive intensity.

E. Fracture Strength Test Method

[0101] Analysis steps include:

[0102] a.) Place 1 gram of particles in 1 liter of distilled deionized (DI) water.

[0103] b.) Permit the particles to remain in the DI water for 10 minutes and then recover the particles by filtration, using a 60 mL syringe filter, 1.2 micron nitrocellulose filter (Millipore, 25 mm diameter).

[0104] c.) Determine the rupture force of 50 individual particles. The rupture force of a particle is determined using the procedure given in Zhang, Z.; Sun, G; "Mechanical Properties of Melamine-Formaldehyde microcapsules," J. Microencapsulation, vol 18, no. 5, pages 593-602, 2001.

Then calculate the fracture strength of each particle by dividing the rupture force (in Newtons) by the cross-sectional area of the respective spherical particle (πr^2 , where r is the radius of the particle before compression), said cross-sectional area being determined as follows: measuring the particle size of each individual particle using the experimental apparatus and method of Zhang, Z.; Sun, G; "Mechanical Properties of Melamine-Formaldehyde microcapsules," J. Microencapsulation, vol 18, no. 5, pages 593-602, 2001.

[0105] d.) Use the 50 independent measurements from c.) above, and calculate the percentage of particles having a fracture strength within the claimed range fracture strength range.

F. Zeta Potential

[0106] (1) Equipment specifications: Malvern Zeata-sizer Nano Model ZEN3600 Sample cell, disposable capillary cell (green cell)

[0107] (2) Use Duke standards to measure the PSD, and use it to measure the zeta potential to assure that the instrument is functioning properly.

[0108] (3) Flush a DTS 1060 capillary cell with 1-2 mL ethanol, the with DI water to prepare the capillary cell.

[0109] (4) Sample preparation: first, filter 20 mL DI water through 0.2 micron filter into a 20 mL vial. Add 1 drop (50 microliters of 30 wt % solids particulate suspension into the vial and invert the sample back and forth gently until the particulate suspension is homogeneously dispersed in the vial. Next, rinse a DTS 1060 green disposable zeta cell with 1-2 mL of DI water, then use a syringe to transfer the sample solution from the vial into the zeta cell, making sure that no air bubbles are present in the cell. Fill the cell to the top, then place a cap on the cell outlet and inlet (again making sure no air bubbles are present in the sample cell). Then, place the cell in the sample chamber, with the electrodes facing the sides of the system. Finally, place the sample cell in the instrument.

[0110] (5) Conditions for the run:

[0111] a. Refractive index=1.35 (this number may vary for suspensions. One can measure the refractive index for any particulate suspension using a refractometer)

[0112] b. Temperature=25 degrees Centigrade

[0113] c. Equilibration time=1 minute

[0114] d. Smoluchowski model to be used to calculate the zeta potential

[0115] (6) Measure each sample in triplicate. The result from the instrument is reported as Zeta Potential in millivolts, with no extrapolation.

EXAMPLES

[0116] While particular embodiments of the present invention have been illustrated and described, it would be obvious to those skilled in the art that various other changes and modifications can be made without departing from the spirit and scope of the invention. It is therefore intended to cover in the appended claims all such changes and modifications that are within the scope of this invention.

[0117] A perfume composition, called Scent A, is utilized to prepare the examples of the invention. The table below lists the ingredients, and their properties. Table 2 provides the ClogP breakdown of the perfume oil composition.

TABLE 1

Material Name	ClogP	Boiling Point ° C.
Beta Gamma Hexenol	1.3	155
Phenyl Ethyl Alcohol	1.32	219
Helional	1.77	329
Triplal Extra	1.78	199
Amyl-Acetate (isomer Blends)	1.87	135
Melonol	2.09	182
Liffarome	2.14	167
Iso Eugenol Acetate	2.17	303
Cis 3 Hexenyl Acetate	2.18	167
Jasmolactone	2.36	219
2'6-nonadien-1-ol	2.43	213
Florosa	2.46	238
Nonalactone	2.66	193
Cis Jasmone	2.81	254
Ethyl Linalool	2.92	223
Pino Acetaldehyde	2.98	261
Methyl Dihydro Jasmonate	3.01	323
Undecavertol	3.06	242
Azurone 10/tec 0015573	3.06	395
Dihydro Myrcenol	3.08	195
Cyclemax	3.23	281
Hivernal	3.29	351
Pomaroze	3.51	214
Undecalactone	3.75	228
Damascenone Total 937459	3.89	267
Acalea (01-1963)	3.9	344
Cis-3-hexenyl Salicylate	4	316
Ionone Beta	4.02	267
Polysantol	4.21	256
Ambroxan	4.58	285
5-cyclohexadecen-1-one	5.04	331
Iso E Super Or Wood	5.05	325
Laevo Muscone	5.48	321
Helvetolide 947650	5.56	309

Example 1

Nonionic Microcapsule (TAS0810101, MVF1837-94B)

[0118] An oil solution, consisting of 75 g Fragrance Oil scenta, 75 g of Isopropyl Myristate, 0.6 g DuPont Vazo-52, and 0.4 g DuPont Vazo-67, is added to a 35° C. temperature controlled steel jacketed reactor, with mixing at 1000 rpm (4 tip, 2" diameter, flat mill blade) and a nitrogen blanket applied at 100 cc/min. The oil solution is heated to 75° C. in 45 minutes, held at 75° C. for 45 minutes, and cooled to 60° C. in 75 minutes.

[0119] A second oil solution, consisting of 37.5 g Fragrance Oil, 0.5 g tertiarybutylaminoethyl methacrylate, 0.4 g 2-carboxyethyl acrylate, and 20 g Sartomer CN975 (hexafunctional urethane-acrylate oligomer) is added when the first oil solution reached 60° C. The combined oils are held at 60° C. for an additional 10 minutes.

[0120] Mixing is stopped and a water solution, consisting of 56 g of 5% active polyvinyl alcohol Celvol 540 solution in water, 244 g water, 1.1 g 20% NaOH, and 1.2 g DuPont Vazo-68WSP, is added to the bottom of the oil solution, using a funnel.

[0121] Mixing is again started, at 2500 rpm, for 60 minutes to emulsify the oil phase into the water solution. After milling is completed, mixing is continued with a 3" propeller at 350 rpm. The batch is held at 60° C. for 45 minutes, the temperature is increased to 75° C. in 30 minutes, held at 75° C. for 4 hours, heated to 90° C. in 30 minutes and held at 90° C. for 8 hours. The batch is then allowed to cool to room temperature.

The finished microcapsules have a median particle size of 6.4 microns, a broadness index of 1.3, and a zeta potential of negative 0.5 millivolts.

Example 2

Anionic Microcapsule, Large Particle Size (TAS1122101)

[0122] Capsules are made using identical materials, compositions, and process conditions as in Example 1 with the following exceptions: 1 gram of Vazo-52, 0.8 grams of Vazo-67, 0.3 grams of tertiarybutylaminoethyl methacrylate, 0.25 grams of 2-carboxyethyl acrylate, and 12 grams of Sartomer CN975 as compositional differences in the oil phase; and 22 grams of 25% active Colloid 351, and 308 grams of water as compositional differences in the water phase. All other mixing and process conditioner remains the same. The finished microcapsules have a median particle size of 10.7 microns, a broadness index of 1.5, and a zeta potential of negative 60 milivolts.

Example 3

Anionic Microcapsule, Small Particle Size (TAS1123101)

[0123] Capsules are made using identical materials, compositions, and process conditions as in Example 1 with the following exceptions: 1 gram of Vazo-52, 0.8 grams of Vazo-67, 1.5 grams of tertiarybutylaminoethyl methacrylate, 1.2 grams of 2-carboxyethyl acrylate, and 60 grams of Sartomer CN975 as compositional differences in the oil phase; and 68 grams of 25% active Colloid 351, and 282 grams of water as compositional differences in the water phase. All other mixing and process conditioner remains the same. The finished microcapsules have a median particle size of 1.4 microns, a broadness index of 1.2, and a zeta potential of negative 60 milivolts.

Example 4

Cationic Microcapsule (TAS0204101)

[0124] An oil solution, consisting of 112.5 g Fragrance Oil Scent A, 37.5 g of Isopropyl Myristate, 0.6 g DuPont Vazo-52, and 0.4 g DuPont Vazo-67, is added to a 35° C. temperature controlled steel jacketed reactor, with mixing at 1000 rpm (4 tip, 2" diameter, flat mill blade) and a nitrogen blanket applied at 100 cc/min. The oil solution is heated to 75° C. in 45 minutes, held at 75° C. for 45 minutes, and cooled to 60° C. in 75 minutes.

[0125] A second oil solution, consisting of 37.5 g Fragrance Oil, 0.5 g tertiarybutylaminoethyl methacrylate, 0.4 g 2-carboxyethyl acrylate, and 20 g Sartomer CN975 (hexafunctional urethane-acrylate oligomer) is added when the first oil solution reached 60° C. The combined oils are held at 60° C. for an additional 10 minutes.

[0126] Mixing is stopped and a water solution, consisting of 5.6 g of poly(dimethylamine-co-epichlorohydrin-co-ethylene diamine) and 360 grams of water, 2.8 g 20% NaOH, and 1.2 g DuPont Vazo-68WSP, is added to the bottom of the oil solution, using a funnel.

[0127] Mixing is again started, at 2500 rpm, for 60 minutes to emulsify the oil phase into the water solution. After milling is completed, mixing is continued with a 3" propeller at 350 rpm. The batch is held at 60° C. for 45 minutes, the temperature is increased to 75° C. in 30 minutes, held at 75° C. for 4 hours, heated to 90° C. in 30 minutes and held at 90° C. for 8

hours. The batch is then allowed to cool to room temperature. The finished microcapsules have a median particle size of 10.5 microns, a broadness index of 1.3, and a zeta potential of 25 milivolts.

Example 5

Anionic Microcapsule (TAS1101101)

[0128] Capsules are made using identical materials, compositions, and process conditions as in Example 2 with the following exceptions: 1 gram of tertiarybutylaminoethyl methacrylate, 0.8 grams of 2-carboxyethyl acrylate, and 40 grams of Sartomer CN975 as compositional differences in the oil phase; and 22 grams of 25% active Colloid 351, and 282 grams of water as compositional differences in the water phase. All other mixing and process conditioner remains the same. The finished microcapsules have a median particle size of 4.8 microns, a broadness index of 1.3, and a zeta potential of negative 60 milivolts.

Example 6

Microcapsule with Cationic Polymer Emulsifier

[0129] Capsules are made using identical materials, compositions, and process conditions as in Example 1 with the following exceptions: 20 grams of 32% active poly(diallyl dimethyl ammonium chloride) added to the water phase, along with 236 grams of water. All other mixing and process conditioner remains the same. The finished microcapsules have a median particle size of 9 microns, and a broadness index of 1.3, and a zeta potential of 38 millivolts.

Example 7

Shampoo Composition

[0130]

Ingredient	EXAMPLE COMPOSITION		
	I	II	III
Water	q.s.	q.s.	q.s.
Polyquaternium 76 ¹	2.50	—	—
Guar, Hydroxylpropyl Trimonium Chloride ²	—	0.25	—
Polyquaterium 6 ³	—	—	0.79
Sodium Laureth Sulfate (SLE3S) ⁴	21.43	21.43	21.43
Sodium Lauryl Sulfate (SLS) ⁵	20.69	20.69	20.69
Silicone ⁶	0.75	1.00	0.5
Cocoamidopropyl Betaine ⁷	3.33	3.33	3.33
Cocoamide MEA ⁸	1.0	1.0	1.0
Ethylene Glycol Distearate ⁹	1.50	1.50	1.50
Sodium Chloride ¹⁰	0.25	0.25	0.25
Fragrance	0.70	0.70	0.70
Preservatives, pH adjusters	Up to 1%	Up to 1%	Up to 1%

¹Mirapol AT-1, Copolymer of Acrylamide(AM) and TRIQUAT, MW = 1,000,000; CD = 1.6 meq./gram; 10% active; Supplier Rhodia

²Jaguar C500, MW-500,000, CD = 0.7, supplier Rhodia

³Mirapol 100S, 31.5% active, supplier Rhodia

⁴Sodium Laureth Sulfate, 28% active, supplier: P&G

⁵Sodium Lauryl Sulfate, 29% active supplier: P&G

⁶Glycidol Silicone VC2231-193C

⁷Tegobetaine F-B, 30% active supplier: Goldschmidt Chemicals

⁸Monamid CMA, 85% active, supplier Goldschmidt Chemical

⁹Ethylene Glycol Distearate, EGDS Pure, supplier Goldschmidt Chemical

¹⁰Sodium Chloride USP (food grade), supplier Morton; note that salt is an adjustable ingredient, higher or lower levels may be added to achieve target viscosity.

Ingredient	EXAMPLE COMPOSITION	
	IV	V
Sodium Laureth Sulfate	10.00	10.00
Sodium Lauryl Sulfate	1.50	1.50
Cocamidopropyl betaine	2.00	2.00
Guar Hydroxypropyl trimonium chloride(1)	0.40	
Guar Hydroxypropyl trimonium chloride(2)		0.40
Dimethicone(3)	2.00	2.00
Gel Network(4)		27.27
Ethylene Glycol Distearate	1.50	1.50
5-Chloro-2-methyl-4-isothiazolin-3-one, Kathon CG	0.0005	0.0005
Sodium Benzoate	0.25	0.25
Disodium EDTA	0.13	0.13
Perfume	0.40	0.40
Citric Acid/Sodium Citrate Dihydrate	pH QS	pH QS
Sodium Chloride/Ammonium Xylene Sulfonate	Visc. QS	Visc. QS
Water	QS	QS

(1) Jaguar C17 available from Rhodia

(2) N-Hance 3269 (with Mol. W. of ~500,000 and 0.8 meq/g) available from Aquila/Hercules

(3) Viscasil 330M available from General Electric Silicones

(4) Gel Networks; See Composition below. The water is heated to about 74° C. and the Cetyl Alcohol, Stearyl Alcohol, and the SLES Surfactant are added to it. After incorporation, this mixture is passed through a heat exchanger where it is cooled to about 35° C. As a result of this cooling step, the Fatty Alcohols and surfactant crystallized to form a crystalline gel network.

Ingredient	Wt. %
Water	86.14%
Cetyl Alcohol	3.46%
Stearyl Alcohol	6.44%
Sodium laureth-3 sulfate (28% Active)	3.93%
5-Chloro-2-methyl-4-isothiazolin-3-one, Kathon CG	0.03%

Example 8

Shampoo with No Premixing of Capsules

[0131] Perfume and/or perfume microcapsules disclosed in the above examples are added on top of a pre-made shampoo formula with a 10 wt % formula hole (shampoo compositions of Example 7 II, formulations with 10% hole). The table below lists the masses of the various ingredients. The mixture is then speed mixed at 1900 RPM for 1 minute using a DAFC 400FVZ speed mixer. The Olfactive Analysis of Shampoo Product test method is utilized to grade hair treated with the prepared shampoo compositions. These results are presented below.

Example Reference	PMC Example ID	Mass of Microcapsule or Perfume (g)	Mass of Shampoo (g)	Mass of Water (g)	4 hr (Pre/Post-Comb)	24 hr (Pre/Post-Comb)
8A	Scent A	0.50	90.0	9.50	10/10	0/0
8B	1	1.81	90.0	8.19	10/15	0/0
8C	2	1.43	90.0	8.57	10/15	0/0
8D	3	2.42	90.0	7.58	10/15	0/0
8E	4	1.48	90.0	8.52	10/10	0/0
8F	5	2.13	90.0	7.87	10/10	0/0
8G	6	2.39	90.0	7.61	0/0	0/0

Example 9

Shampoo with Premixing of Capsules

[0132] The perfume microcapsules of Examples 1 through 6 are first premixed with polyDADMAC (polydiallyl dimethyl ammonium chloride, Mirapol 100S from Rhodia) by preweighing the perfume microcapsules in a jar, then adding the Mirapol 100S, followed by the addition of water. The contents are then mixed at 1950 RPM for 1 minutes using a Hausfeld DAFC 400FVZ speed mixer to achieve a homogeneous suspension of microcapsules. The masses of materials that are premixed are recorded in the table below. The polymer to perfume ratio in the premix is maintained at 1:5 for all of the samples, and the amount of Mirapol 100S polymer is maintained at 0.10 wt % in the finished shampoo formulation.

Premix ID	PMC Example ID	Mass of Microcapsule	Mass of Mirapol 100S Polymer (31.5% active)	Mass of Water (g)	Final Perfume Content wt %
9A	1	10.87	1.90	7.23	15%
9B	2	8.60	1.90	9.50	15%
9C	3	14.49	1.90	3.60	15%
9D	4	8.89	1.90	9.20	15%
9E	5	12.77	1.90	5.33	15%
9F	6	14.32	1.90	3.77	15%

[0133] The cationic polymer/microcapsule premixes are then formulated into a shampoo (example compositions provided in Example 7 II, a formulation with 10% hole was utilized) by preweighing the shampoo in a jar, then adding the premix, followed by addition of water, and then mixing at 1950 RPM for 1 minute using a Hausfeld DAFC 400FVZ Speed Mixer to achieve a homogeneous product.

[0134] The Olfactive Analysis of Shampoo Product test method is utilized to grade hair treated with the prepared shampoo compositions. These results are presented below.

Example Reference	PMC Example ID	Mass of Microcapsule or Perfume (g)	Mass of Shampoo (g)	Mass of Water (g)	4 hr (Pre/Post-Comb)	24 hr (Pre/Post-Comb)
9G	Scent A	0.50	90.0	9.50	10/10	0/0
9H: Nonionic	1	3.33	90.0	6.67	10/15	0/0
9I: Anionic	2	3.33	90.0	6.67	25/35	10/20
9J: Anionic	3	3.33	90.0	6.67	30/45	10/40
9K: Cationic	4	3.33	90.0	6.67	10/10	0/0
9L: Anionic	5	3.33	90.0	6.67	40/50	20/40
9M: Cationic	6	3.33	90.0	6.67	5/5	0/0

Note that the anionic microcapsules provide the best olfactive results.

Example 10

Cationic Polymer Level Study

[0135] Anionic microcapsules of Example 5 are premixed with various amounts of polyDADMAC (Mirapol 100S, Rhodia), see table below. These premixes are agitated at 1950 RPM for 1 minute using a Hausfeld 400 FVZ Speed Mixer. The premixes are then added to shampoo of Example 7 II (formulation with 10% hole), and formulation balanced to 100% with the addition of water. The shampoo mixture is then agitated at 1950 RPM for 1 minute using a Hausfeld 400 FVZ Speed Mixer.

[0136] The Olfactive Analysis of Shampoo Product test method is utilized to grade hair treated with the prepared shampoo compositions. These results are presented below.

Sample ID	Shampoo Premix (g)	Mirapol 100S (g)	Microcapsule of Example 5 (g)	Deionized Water (g)	4 hr Pre/Post Comb	24 hr Pre/Post Comb
10A	90	0	0.00	9.5	10/15	0/0
10B	90	0.00	2.00	8.01	30/35+	10/20
10C	90	0.32	2.00	7.69	40+/55+	20/40
10D	90	0.79	2.00	7.22	40/45+	10/30+
10E	90	1.59	2.00	6.42	40/55	10/35
10F	90	3.17	2.00	4.84	40/60+	20+/35+
10G	90	6.32	2.00	1.68	10/15+	5/10

Notice that very low levels of polymer are required for pre-mixing with the microcapsules to achieve the desired interaction and delivery efficiency.

Example 11

A Variety of Cationic Polymers mixed with Anionic Microcapsules

[0137] Anionic microcapsules of Example 5 are premixed with a variety of cationic polymers, see table below. The powder polymers (100% active in the table below) are first mixed with water at 1950 RPM for 1 minute using a Hausfeld 400 FVZ Speed Mixer. In the case of Tapioca starch, the dispersion is also heated. Subsequently, anionic microcap-

sules of Example 5 are added to the polymer solutions in water, and these premixes are agitated at 1950 RPM for 1 minute using a Hausfeld 400 FVZ Speed Mixer. The premixes are then added to shampoo of Example 7 II, and formulation balanced to 100% with the addition of water. The shampoo mixture is then agitated at 1950 RPM for 1 minute using a Hausfeld 400 FVZ Speed Mixer.

[0138] The Olfactive Analysis of Shampoo Product test method is utilized to grade hair treated with the prepared shampoo compositions. These results are presented below.

Polymer Premix Preparation

[0139]

Sample ID	Polymer Type	Polymer Activity %	Anionic Microcapsule of Example 5 (g)	Polymer (g)	Water (g)	Final Perfume wt %
11A	Mirapol 100S	31.50%	12.43	1.85	5.72	14.60%
11B	70:30 Guar:Aptac	100.00%	12.43	0.58	6.99	14.60%

-continued

Sample ID	Polymer Type	Polymer Activity %	Anionic Microcapsule of Example 5 (g)	Polymer (g)	Water (g)	Final Perfume wt %
11C	HMW, HCD Guar:Maptac	88.00%	12.43	0.66	6.91	14.60%
11D	Triquat	15.50%	12.43	3.77	3.81	14.60%
11E	Jaguar C17	100.00%	12.43	0.58	6.99	14.60%
11F	Tapioca	100.00%	12.43	0.58	6.99	14.60%

Shampoo Preparation and Olfactive Analysis

[0140]

Sample ID	Polymer Type	Perfume Technology (PDT)	Shampoo Mass (g)	PDT Mass (g)	Water (g)	4 hr Pre/Post Comb	24 hr Pre/Post Comb
11G	None	Scent A	45.00	0.250	4.750	25/25	10/10
11H	None	Example 5	45.00	1.064	3.936	15+/15+	10/10
11I	Mirapol 100S	11A	45.00	1.712	3.288	35+/50	20+/35
11G	70:30 Guar:Aptac	11B	45.00	1.712	3.288	30+/45+	20+/35
11H	HMW, HCD Guar:Maptac	11C	45.00	1.712	3.288	25/35/+	10/30
11I	Triquat	11D	45.00	1.712	3.288	30+/60	20+/45
11J	Jaguar C17	11E	45.00	1.712	3.288	30/70	10+/55
11K	Tapioca	11F	45.00	1.712	3.288	35+/60	10/45

Note that the choice of polymer is critical in achieving a favorable interaction between the microcapsule, cationic deposition polymer, and the shampoo formulation.

[0141] The dimensions and values disclosed herein are not to be understood as being strictly limited to the exact numerical values recited. Instead, unless otherwise specified, each such dimension is intended to mean both the recited value and a functionally equivalent range surrounding that value. For example, a dimension disclosed as “40 mm” is intended to mean “about 40 mm.”

[0142] Every document cited herein, including any cross referenced or related patent or application is hereby incorporated herein by reference in its entirety unless expressly excluded or otherwise limited. The citation of any document is not an admission that it is prior art with respect to any invention disclosed or claimed herein or that it alone, or in any combination with any other reference or references, teaches, suggests or discloses any such invention. Further, to the extent that any meaning or definition of a term in this document conflicts with any meaning or definition of the same term in a document incorporated by reference, the meaning or definition assigned to that term in this document shall govern.

[0143] While particular embodiments of the present invention have been illustrated and described, it would be obvious to those skilled in the art that various other changes and modifications can be made without departing from the spirit and scope of the invention. It is therefore intended to cover in the appended claims all such changes and modifications that are within the scope of this invention.

What is claimed is:

1. A composition comprising:

(a) from about 0.01% to about 50%, by weight of the composition of an anionic charged polyacrylate microcapsule

(b) from about 0.01% to about 2%, by weight of the composition of a cationic deposition polymer;

(c) from about 2% to about 50%, by weight of the composition, of a deterative surfactant; and

(d) from about 20% to about 95%, by weight of the composition, of a carrier.

2. The composition of claim 1, wherein the anionic charged polyacrylate microcapsule is made by adding the anionic emulsifier to the polyacrylate microcapsule during the polyacrylate microcapsule making process.

3. The composition of claim 1, wherein the anionic charged polyacrylate microcapsule and the cationic deposition polymer are mixed such that the weight ratio of the anionic charged polyacrylate microcapsule to the cationic deposition polymer is from about 1.0:0.01 to about 1.0:10.

4. The composition of claim 1, wherein the anionic emulsifier is selected from the group consisting of: poly(meth) acrylic acid; copolymers of (meth)acrylic acids and its (meth) acrylates with C1-C22 alkyl; copolymers of (meth)acrylic acids and (meth)acrylamide; and mixtures thereof.

5. The composition of claim 1, wherein the anionic charged polyacrylate microcapsule has a median particle size of from about 1 microns to about 80 microns.

6. The composition of claim 1, wherein the polyacrylate microcapsule has a core and a shell that encapsulates said core.

7. The composition of claim 6, wherein the core comprises from about 6% to about 99.9% of a benefit agent.

8. The composition of claim 7, wherein the benefit agent is selected from the group consisting of perfumes; brighteners; enzymes; sensates; attractants; dyes; pigments; bleaches; anti-dandruff agents; and mixtures thereof.

9. The composition of claim 1, wherein the composition further comprises an anti-dandruff agent.

10. The composition of claim **1**, wherein the cationic deposition polymer is a synthetic polymer or a naturally derived cationic polymer derived from the group consisting of starches, guar, cellulose, cassia, locust bean, konjac, tara, galactomanna, and tapioca starch.

11. The composition of claim **1**, wherein the cationic deposition polymer is a water-soluble polymer with a charge density of from about 0.5 milliequivalents per gram to about 12 milliequivalents per gram, and wherein the cationic deposition polymer has a molecular weight of about 100,000 Daltons to about 5,000,000 Daltons.

12. The composition of claim **1**, wherein the deterative surfactant is selected from the group consisting of anionic surfactants, zwitterionic surfactants, amphoteric surfactants, and combinations thereof.

13. The composition of claim **1**, wherein the carrier comprises either water or water solutions of lower alkyl alcohols and polyhydric alcohols.

14. The composition of claim **1**, wherein the composition is in the form of a gel.

15. The composition of claim **14**, wherein the gel has a neat viscosity of about 1,000 cps to about 10,000 cps.

16. The composition of claim **1**, wherein said anionic polyacrylate microcapsule comprises a perfume oil and isopropyl myristate.

17. A method of making a composition, said method comprising:

combining a premix, said premix comprising an anionic polyacrylate microcapsule and a cationic deposition polymer, with at least one of a deterative surfactant and a carrier to form a composition.

18. The method of claim **17**, wherein said deterative surfactant is an anionic surfactant.

19. The method of claim **18**, wherein the anionic surfactant is selected from the group consisting of alkyl and alkyl ester sulfates, and the water soluble salts of organic and sulfuric acid reaction products.

20. The method of claim **17**, wherein the weight ratio of the anionic polyacrylate microcapsule to the cationic deposition polymer is from about 0.5:30 to about 20:1.

* * * * *