

(12) **Patent Application Publication**
BAZZARELLA et al.

(43) **Pub. Date:** **Mar. 16, 2017**

Publication Classification

(51) **Int. Cl.**
H01M 2/02 (2006.01)
H01M 10/0525 (2006.01)


(52) **U.S. Cl.**
CPC *H01M 2/021* (2013.01); *H01M 2/0287*
(2013.01); *H01M 10/0525* (2013.01); *H01M*
2220/30 (2013.01)

(57) **ABSTRACT**

Electrochemical cells and methods of making electrochemical cells are described herein. In some embodiments, an apparatus includes a multi-layer sheet for encasing an electrode material for an electrochemical cell. The multi-layer sheet including an outer layer, an intermediate layer that includes a conductive substrate, and an inner layer disposed on a portion of the conductive substrate. The intermediate layer is disposed between the outer layer and the inner layer. The inner layer defines an opening through which a conductive region of the intermediate layer is exposed such that the electrode material can be electrically connected to the conductive region. Thus, the intermediate layer can serve as a current collector for the electrochemical cell.

Related U.S. Application Data

(60) Provisional application No. 61/648,967, filed on May 18, 2012.






FIG. 1




FIG. 2





FIG. 3






FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13A




FIG. 13D

FIG. 13C

FIG. 13B




FIG. 13F

FIG. 13E




FIG. 14A




FIG. 14B




FIG. 15A




FIG. 15B




FIG. 15C




FIG. 16A




FIG. 16B




FIG. 16C




FIG. 17B




FIG. 17C





FIG. 17A






FIG. 18B




FIG. 18C

ELECTROCHEMICAL CELLS AND METHODS OF MANUFACTURING THE SAME

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application is a continuation-in-part of and claims priority to U.S. patent application Ser. No. 13/832,836, filed Mar. 15, 2013, entitled “Electrochemical Cells and Methods of Manufacturing the Same,” which claims priority to and the benefit of U.S. Provisional Application No. 61/648,967, filed May 18, 2012, entitled “Simplified Battery Design,” both of which are hereby incorporated by reference in their entirety.

[0002] This application also claims priority to and the benefit of U.S. Provisional Application No. 61/648,967, filed May 18, 2012, entitled “Simplified Battery Design.”

BACKGROUND

[0003] Embodiments described herein relate generally to an apparatus for use within an electrochemical cell that can be used as both an outer casing and a current collector for the electrochemical cell and methods for making such apparatus.

[0004] Some known electrochemical cells (e.g., batteries) can include a variety of shapes and/or sizes, can be based on a wide variety of enabling materials and internal architectures, can be either passive or actively controlled, can be rechargeable or not, and/or can share certain common features that can allow them to convert chemical energy to electrical energy. Some known batteries can include a first electrode having a high electrochemical potential and a second electrode having a lower electrochemical potential relative to the first electrode. Each electrode can include an active material that participates in a chemical reaction and/or physico-chemical transformation during discharge by virtue of a favored thermodynamic change of material states, which can result in the flow of electrical current when a switch is closed. In some cases, for charge transfer to occur, two distinct conductive networks can allow the anode and cathode to be electrically connected. A separator can be used to provide isolation of the anode and cathode such that only ions are able to pass through it, and to prevent short circuiting.

[0005] The manufacture of battery electrodes can be a complex and capital intensive process, and can commonly include material mixing, casting, calendaring, drying, slitting, and working (bending, rolling, etc.) according to the battery architecture being built. Because the electrode is manipulated during assembly, and to ensure conductive networks are in place, all components are compressed into a cohesive assembly, for example, by use of a binding agent. However, binding agents themselves occupy space, can add processing complexity, and can impede ionic and electronic conductivity.

[0006] Thus, there is a need for improvements in electrochemical cells (e.g., batteries) and the manufacture of electrochemical cells, such as eliminating components of the electrochemical cell and/or providing reduced packaging for the electrochemical cell, while maintaining the same energy storage capabilities.

SUMMARY

[0007] Electrochemical cells and methods of making electrochemical cells are described herein. In some embodiments, an apparatus includes a multi-layer sheet for encasing an electrode material of an electrochemical cell. The multi-layer sheet includes an outer layer, an intermediate layer that includes a conductive substrate, and an inner layer disposed on a portion of the conductive substrate. The intermediate layer being disposed between the outer layer and the inner layer. The inner layer defines an opening through which a conductive region of the intermediate layer is exposed such that the electrode material can be electrically connected to the conductive region and the intermediate layer can serve as a current collector for the electrochemical cell.

BRIEF DESCRIPTION OF THE DRAWINGS

[0008] FIG. 1 is a schematic illustration of a laminate sheet for encasing an electrochemical cell, according to an embodiment.

[0009] FIG. 2 is a cross-sectional view of the laminate sheet of FIG. 1 taken along line 2-2 in FIG. 1.

[0010] FIG. 3 is a cross-sectional view of a portion an electrochemical cell, according to an embodiment.

[0011] FIG. 4 is a schematic top view of a portion of a laminate sheet for encasing an electrochemical cell, according to another embodiment.

[0012] FIG. 5 is a schematic top view of a portion of a laminate sheet for encasing an electrochemical cell, according to another embodiment.

[0013] FIG. 6 is a schematic top view of a portion of a laminate sheet for encasing an electrochemical cell, according to another embodiment.

[0014] FIG. 7 is a cross-section view of the portion of a laminate sheet of FIG. 6 taken along line 7-7 in FIG. 6.

[0015] FIG. 8 is a cross-sectional view of a portion of an electrochemical cell, according to another embodiment.

[0016] FIG. 9 is a cross-sectional view of another portion of the electrochemical cell of FIG. 8.

[0017] FIG. 10 is a cross-sectional view of a portion of an electrochemical cell, according to another embodiment.

[0018] FIG. 11 is a cross-sectional view of a portion of an electrochemical cell, according to another embodiment.

[0019] FIG. 12 is a perspective view of a portion of an electrochemical cell, according to another embodiment.

[0020] FIG. 13A is a perspective view of a portion of an electrochemical cell, according to another embodiment.

[0021] FIGS. 13B-13D each illustrates a form angle for a laminate sheet for encasing an electrochemical cell, according to an embodiment.

[0022] FIGS. 13E and 13F each illustrate a portion of a laminate sheet for encasing an electrochemical cell, according to an embodiment.

[0023] FIG. 14A is a perspective view of a portion of a laminate sheet for encasing an electrochemical cell, according to another embodiment.

[0024] FIG. 14B is a cross-sectional view of the laminate sheet of FIG. 14A taken along line 14B-14B in FIG. 14A.

[0025] FIG. 15A is a perspective view of a portion of a laminate sheet for encasing an electrochemical cell, according to another embodiment.

[0026] FIG. 15B is a cross-sectional view of the laminate sheet of FIG. 15A taken along line 15B-15B in FIG. 15A;

and FIG. 15C is a cross-sectional view of the laminate sheet of FIG. 15A taken along line 15C-15C in FIG. 15A.

[0027] FIGS. 16A-16C illustrate steps of a process to manufacture an electrochemical cell, according to an embodiment.

[0028] FIG. 17A is a perspective view of an electrochemical cell, according to another embodiment.

[0029] FIG. 17B is a cross-section view of the electrochemical cell of FIG. 17A taken along line 17B-17B in FIG. 17A; and FIG. 17C is an enlarged view of a portion B of FIG. 17B.

[0030] FIG. 18A is an exploded perspective view of an electrochemical cell, according to another embodiment, with a portion of the electrochemical cell shown transparent.

[0031] FIG. 18B is an enlarged view of a portion of the electrochemical cell of FIG. 18A.

[0032] FIG. 18C is a perspective view of a portion of the electrochemical cell of FIG. 18A shown assembled.

DETAILED DESCRIPTION

[0033] Electrochemical cells, such as batteries, and methods of manufacturing electrochemical cells are described herein in which the “pouch” or “casing” of the electrochemical cell (also referred to as “cell”) can also be used as an electrochemical functional component (e.g., the current collector) of the cell. As described herein, in some embodiments, a cell pouch (e.g., case) can include a laminated sheet formed with an outer layer, an intermediate metal foil layer and an inner layer. The inner layer can include openings to define a cavity in which an electrochemically active material of the electrode of the cell can be electrically connected with the metal foil member. Thus, in such an embodiment, the metal foil layer of the pouch can serve as the current collector of the cell.

[0034] In general, each electrode of an electrochemical cell can include active material(s), which can undergo chemical or physico-chemical change during discharge, and charge in the case of a secondary battery. The electrode can occupy/reside within a cavity of the electrochemical cell. The cavity can be defined as the volume of the cell that contains an electrode, and in some cases can contain additional volume to contain other components of the cell. Thus, in some embodiments, an electrode cavity can include several different regions.

[0035] For example, as described above, a cavity can refer to the entire volume of the cell in which an electrode is contained. In some embodiments, a cavity of a cell can include a fluid region, which can be the collective aggregated volume occupied by fluid suspension in the cavity, and which may or may not be continuous or homogeneous.

[0036] A cavity can also include an active region. The active region can be the collection of fluid substance in which active materials are or would be active (i.e., undergoing chemical or physico-chemical change) during charge/discharge, which may vary with operating conditions (e.g., temperature, state of charge, current, among others), in electrical contact with both a current collector and a separator.

[0037] The cavity may have zero, one, two, or more ports or openings to facilitate fluid exchange, and the ports may reside on any surface defining the cavity including, for example, a side surface and/or a rear surface. The ports may permit insertion and retraction of special equipment used during manufacture of the cell, or as feedthroughs for

instrumentation, for example, during manufacture of the cell, or remaining resident after manufacturing is completed. A portion of the area of a cavity can be bounded by a current collector, and at least some of the area of the cavity can be bounded by a separator. Other portions of the cavity can be bounded by for example, frame seals, port plugs, an electrolytic substance, containment hardware, intra-cavity mechanical supports, instrumentation/sensors, and/or fluids.

[0038] The cavity geometry can be, for example, polygonal (rectangular, hexagonal, etc.), have rounded edges, or other shapes depending on the design objective. The cavity depth/thickness may be uniform, or can vary according to a shape profile. The cavity may only include an active region, or be partitioned into active and inactive regions. The cavity volume may be interrupted by members spanning the volume (for example across the thickness) e.g., for structural, fluid dynamic, or other reasons.

[0039] Some embodiments described herein relate to the fabrication and/or methods of manufacturing electrochemical cells, where the electrodes of the cell can contain an active material(s), electrolytic substance(s), and optionally other materials such as, for example, material participating in conductive networks (e.g., carbon powder or salts), rheology modifiers (e.g. dispersants, fluid stabilizers, and other functional agents). This is distinguished from conventional batteries in that the active materials are mobile (e.g., flowable) in the electrolytic substance (i.e. are not fixed in position relative to one another—at least during manufacturing, and optionally also (i) through a post-assembly period where other processing steps are undertaken, (ii) through a conditioning period of the assembled battery, (iii) throughout a fraction of the battery life, (iv) for the entire battery life cycle, or (v) for discontinuous periods throughout the battery life). The term “during manufacturing” in this context means the period of time from the first introduction of electrode substance or a material component thereof into the cavity region of the battery until the last introduction of electrode substance or a material component thereof into the cavity region. In some embodiments, a method of manufacturing a cell can include sealing, tabbing, and an overall simplified fabrication process.

[0040] As used in this specification, the singular forms “a,” “an” and “the” include plural referents unless the context clearly dictates otherwise. Thus, for example, the term “a port” is intended to mean a single port or a combination of ports.

[0041] Electrode formulations can include, for example, (1) active materials (i.e., the sources and sinks of ions and electrons), (2) carbon (or a mixture of carbons) or other material(s) having the primary, but not necessarily exclusive, function of electronic conduction, and (3) an electrolyte (e.g., a solvent or solvent mixture plus salt(s)) having the primary, but not necessarily exclusive function of ionic conduction. The electrode formulation may optionally include other additives having specific intended chemical, mechanical, electrical, and/or thermal functions. Electrode formulations can include, for example, the active materials, compositions, and/or semi-solid suspensions described in U.S. Provisional Application No. 61/787,382, entitled “[Semi-Solid Electrodes Having High Rate Capability,” and U.S. Provisional Application No. 61/787,372, entitled “Asymmetric Battery Having a Semi-Solid Cathode and High Energy Density Anode,” the entire disclosures of which are hereby incorporated by reference.

[0042] Electrodes of a conventional electrochemical cell are typically prepared by coating a metal foil substrate with a thin (e.g., about 100 μm to about 200 μm) wet slurry that is subsequently dried and calendered to a desired thickness. The slurry components in this method are typically active materials, conductive additives, a binding agent, and a solvent (e.g., commonly N-Methylpyrrolidone (NMP)). When the solvent is evaporated (in a drying oven covering the conveying line), the binder converts to a “glue” that holds all of the solid particles together in a matrix bound to the substrate. It is common for electrodes to be coated with the same materials on both sides of the substrate. As used herein, the term “electrode material” can refer to the slurry described above.

[0043] There are two common battery design approaches, (1) wound, and (2) stacked. In wound battery designs, electrode sheets can be cut to target dimensions, and then, with a separator placed in between, wound into a spiral or jelly-roll, then infiltrated with electrolyte and suitably packaged (typically in a cylindrical or rectangular metal can) to afford containment and electrical connections. In stacked battery designs, electrode sheets can also be cut to target dimension, but can then be stacked on top of one another with separators placed in between, forming a cell composed of physically discrete, rather than continuous in the case of wound cells, anode/cathode pairs. The stacked assembly can then be infiltrated with electrolyte and commonly packaged in either a pouch/bag, a plastic box, or a metal can, which can each also be referred to as a cell or battery casing as described herein.

[0044] In conventional pouch packaging, the pouch can perform several functions. One such function is to provide a hermetic isolation of battery materials from the environment. Thus, the pouch can serve to avoid leakage of hazardous materials such as electrolyte solvents and/or corrosive salts to the ambient environment, and can prevent water and/or oxygen infiltration into the cell. Other functions of the pouch can include, for example, compressive packaging of the internal layers, voltage isolation for safety and handling, and mechanical protection of the battery assembly.

[0045] Typical pouch materials can include laminates (e.g., multi-layer sheets), formed into, for example, two or three solid film-like layers and bound together by adhesive. The word “laminate” as used herein can also refer to layers of material that are not chemically adhered to one another. For example, the layers can be in areal contact with each other and coupled using other coupling methods, such as, for example, heat sealing, UV and/or adhesives (e.g., anaerobic adhesives). The inner layer can be, for example, a plastic layer, such as, for example, a polyolefin (e.g., a cast polypropylene (CPP) or polyethylene). The next or second layer can be a metal foil layer, such as, for example, aluminum, aluminum alloy, copper, nickel, titanium, stainless steel, gold, platinum or carbon. In some pouch configurations, there can be an additional layer(s). The additional layer can be, for example, a protective coating, formed with, for example, a plastic, such as nylon. The metal foil can provide the function of hermeticity, being much less permeable to certain compounds, especially water, than plastics. The inner plastic layer can be thermally bondable to itself, which is the convention regarding pouch closure and admission of electrical pass-throughs. In pouch closure, if the inner layers (e.g. CPP) of two pieces of pouch laminate are brought into physical contact, and heat is applied, the layers will melt and

fuse, creating a robust seal if the processing conditions (e.g., power, temperature, duration) are chosen appropriately. For example, when the sealing is done in a closed loop, an interior volume can be formed that is isolated from the ambient or exterior environment. For electrical pass-throughs, electrical tabs (e.g., strips of conductive metal containing a ring-like wrapping of a select plastic, such as, for example, Surllyn) can be attached to the internal battery assembly (e.g., by ultrasonic weld, clamping fixture, tape, etc) with the plastic ring aligned in the pouch so as to be also thermally sealable.

[0046] The tabbing approach described above can add manufacturing complexity and cost, and may require careful control with respect to quality during manufacture. For example, a polymer material is often used around the area where the electrical tabs pass through from the inside to the outside to the pouch for a better seal and to avoid leaks. Failure to control this aspect adequately can result in increased costs. The pouch laminates described above are known in the battery industry for use as packaging material, but not as an electrochemically functional component of the battery.

[0047] Systems, devices, and methods are described herein related to an electrochemical cell having a casing or pouch that includes multi-layer laminate sheets that include at least a first or inner layer formed with a plastic material and a second layer formed with an electronically conducting material such that the multi-layer sheet can be used as an electrochemically functional element of the cell. For example, in some embodiments, the electronically conducting material (e.g., metal foil) of a pouch can be used as a current collector for the cell. In some embodiments, the metal foil can be used as a pass-through tab. Thus, the multi-layer or laminate sheet(s) of the cell pouch can be used as an electrochemically functional material of the cell, in addition to acting as a packaging material.

[0048] FIGS. 1-3 illustrate a portion of an electrochemical cell (also referred to herein as “energy storage device”), according to an embodiment. An electrochemical cell (e.g., a battery) can include a casing that includes two laminate or multi-layer sheets (also referred to herein as “laminate sheet” or “sheet”) coupled together to encase an electrode material of the cell. As shown in FIGS. 1 and 2, a casing 100 (also referred to as a “pouch”) can include a laminate sheet 110. The laminate sheet 110 can include a first or inner layer 124, a second or intermediate layer 122 and optionally a third or outer layer 120. As shown in FIG. 2, the second layer 122 can be coupled to the third layer 120 and coupled to the first layer 124 with an adhesive 125. In alternative embodiments, the third layer 120, second layer 122 and first layer 124 can be coupled by other methods. For example, the third layer 120, second layer 122, and first layer 124 can be disposed in a stacked relation and then heat sealed, for example, around a periphery of the layers. In some embodiments, the first layer 124 and/or the third layer 120 can be molded onto the second layer. In some embodiments, the first layer 124 and/or the third layer 120 can be spread or coated onto the second layer.

[0049] The third layer 120 can be formed with, for example, a polyamide (e.g., Nylon) and can have a thickness, for example, of about 0.025 mm. The second layer 122 can be formed with an electronically conductive material, such as, for example, aluminum, an aluminum alloy, or copper, and can have a thickness, for example, between of

about 0.025mm and 0.040 mm. The first layer 124 can be formed with, for example, a material that is thermally bondable to itself. For example, the first layer 124 can be formed with a polypropylene (CPP). The first layer 124 can have a thickness of, for example, 0.040 mm.

[0050] In some embodiments, the first layer 124 can define one or more openings 126 such that a portion 142 of the second layer 122 is exposed through the opening 126, as shown in FIG. 1. With the portion 142 of the second layer 122 exposed, an electrochemically active material of the electrode (also referred to as “electrode material”) can be in contact with and electrically connected to the second layer 122, as described in more detail below. Thus, the second layer 122 can serve as the current collector for the cell. The opening(s) 126 can be formed, for example, by laser ablation, die cutting, or a cavity can be formed or molded into the first layer 124.

[0051] As shown in FIG. 3, the casing 100 for an electrochemical cell can include two laminate sheets 110, 110' coupled together, with for example, adhesive, heat sealing or other suitable coupling methods to form a hermetic seal. The laminate sheet 110' shown in FIG. 3 can be formed the same as or similar to the laminate sheet 110. For example, the laminate sheet 110' can include an inner layer 124', an intermediate layer 122' and an outer layer 120' each coupled together with an adhesive 125. A first electrode material (not shown) can be disposed on the exposed portion 142 of the second layer 122, and a second electrode material (not shown) can be disposed on an exposed portion 142' of the second layer 122'. For example, one of the cavities 126, 126' can include an anode electrode and be referred to as the anode cavity of the cell, and the other cavity 126, 126' can include a cathode electrode and be referred to as the cathode cavity of the cell.

[0052] A separator member 130 can be disposed between the laminate sheet 110 and the laminate sheet 110' as shown in FIG. 3. The separator 130 can be used to provide isolation of the anode and cathode portions of the cell such that only ions are able to pass through it, and to prevent short circuiting of the cell.

[0053] In some embodiments, the inner layer 124 of the laminate sheet 110 and the inner layer 124' of the laminate sheet 110' can include a periphery portion (not shown in FIG. 3) that extends beyond a periphery of the separator 130 such that the first layers 124, 124' can be joined to form a seal. In some embodiments, the inner layers 124, 124' are each formed with a material that is thermally bondable to itself (e.g., CPP as described above) such that when the two laminate sheets 110 and 110' are joined, the first layer 124 and the first layer 124' can be joined around their peripheries and thermally bond to each other to form a hermetic seal.

[0054] In some embodiments, the cell can include integrated electrical tabbing, which can obviate the need for (i) a discrete tab component (e.g., an electrical lead), (ii) connecting dedicated tabs to current collectors, and (iii) a dedicated tab sealing operation. Instead, as described herein, in some embodiments, an electrical tab or lead can be provided as an extension of the second layer (e.g., the current collector) of the laminate sheet (e.g., 122 of the laminate sheet 110). Thus, electrical pass-through can be achieved via the cell sealing.

[0055] FIG. 4 illustrates a portion of a laminate sheet 210 that can be cut along the dashed lines to form three separate laminate sheets each for use within a casing of an electro-

chemical cell. As shown in FIG. 4, the laminate sheet 210 can include a first or inner layer 224, a second or intermediate layer 222 and can optionally include a third or outer protective layer (not shown in FIG. 3). As described above for laminate sheet 110, the first layer 224 can be formed with a plastic material, such as, for example, a cast polypropylene, and can define one or more openings 226 to expose a portion 242 of the second layer 222. The second layer 222 can be formed with an electrically conductive material that can be electrically coupled to an electrode material (not shown) disposed on the portion 242 through the opening 226 such that the exposed portion 242 of the second layer 222 can be used as a current collector for the cell. The first layer 224 can also define openings 236 that expose additional portions 232 of the second layer 222. The exposed portions 232 of the second layer 222 can serve as a power connection tab and/or can be coupled to an electrical lead 234 that can be used to provide an electrical current to the cell, as shown in FIG. 4. For example, the electrical lead 234 can be welded, brazed, crimped, etc. onto the exposed portion 232.

[0056] In alternative embodiments, rather than the exposed portion 232 being defined by an opening 236 of the first layer 224, the exposed portion 232 can be integral with the exposed portion 242 of layer 222. For example, in some such embodiments, the exposed portion 232 can extend from the exposed portion 242 as an integral component, and the electrode material can be disposed onto the exposed portion 242 while masking the exposed portion 232. In some such embodiments, the electrode material can be spread onto the exposed portion 242 and exposed portion 232 and then the electrode material on exposed portion 232 can be scraped off or otherwise removed and the electrical lead 234 can be coupled to the exposed portion 232.

[0057] FIG. 5 illustrates a laminate sheet 310 according to another embodiment. In this embodiment, the laminate sheet 310 can include a first or inner layer 324, a second or intermediate layer 322 and a third or outer layer (not shown in FIG. 3). The first layer 324 can be formed with a plastic material such as, for example, a cast polypropylene, and can define one or more openings 326 to expose a portion of the second layer 322. As shown in FIG. 5, in this embodiment, there are three openings 326. The second layer 322 can be formed with an electrically conductive material that can be electrically coupled to an electrode material (not shown) disposed on the exposed portions 342 of the second layer 322 through the openings 326. In this embodiment, the second layer 322 includes an extended portion 327 that extends beyond a peripheral edge of the inner layer 324. The extended portion 327 can function as a power connection tab to provide electrical current to the electrode material disposed on the exposed portion 342 of second layer 222.

[0058] FIG. 6 and 7 illustrate another embodiment of a laminate sheet that can be used within a casing for an electrochemical cell and can also be used as the current collector for the cell. A laminate sheet 410 includes a first layer 424 and a second layer 422. The first layer 424 can be coupled to the second layer 422 with, for example, an adhesive, with heat sealing or other known coupling methods. The second layer 422 can be formed with an electrically conductive material such as, for example, an aluminum or copper material, and the first layer 424 can be formed with, for example, cast polypropylene (CPP) as described above for previous embodiments. In this embodiment, without a third or outer protective layer, it may be desirable for the

second layer **422** to have a greater thickness than embodiments that have a third layer. For example, it may be desirable for the second layer **422** to have a thickness between about 0.075 and 0.100 mm.

[0059] The first layer **424** defines openings **426** such that portions **442** of the conductive second layer **422** are exposed through the openings **426**, as shown in FIG. 6. The exposed portions **442** of the second layer **422** can be electrically connected to an electrochemically active material of an electrode disposed on the second layer **422** within the openings **426**. Thus, the second layer **422** can serve as the current collector for the cell. As described above, the openings **426** can be formed, for example, by laser ablation or die cutting.

[0060] In some embodiments, a laminate sheet as described herein for use as a casing for an electrochemical cell and also as a current conductor for the cell can include a cavity or opening that is formed or molded into the laminate sheet. Such a cell having a formed laminate sheet (s) can be referred to as a “formed cell.” Such laminate sheets can be referred to as “formed laminate sheets.” Such formed laminate sheets can be formed such that at least a portion of the second layer (e.g., metal foil) is formed with a permanent deformation. The deformation can form a cavity within the laminate sheet in which an electrode material of the cell can be disposed. In some embodiments, an upper peripheral surface of the metal foil (e.g., second layer) on which an inner plastic layer is disposed may not be formed. In other words, an upper ledge can be maintained on which the inner layer can at least be disposed. In other embodiments, the inner layer can be disposed on at least a portion of a side wall of the formed cavity region. In some embodiments, the inner layer can be disposed on a portion of the lower surface defining the cavity region of the formed laminate sheet.

[0061] The wall and bottom surface of the formed cavity region of the laminate sheet can have relatively uniform thickness or the thickness can vary. The side wall can be formed at various angles relative to the bottom surface defining the cavity. For example, the angle can be formed with an angle between 0 and 90 degrees. In some embodiments, the angle can vary, for example, around a periphery of the cavity region. In some embodiments, the bottom surface of the cavity region can include raised portions, such as, for example, a dimpled surface, a wavy surface, a protrusion, ridges, etc. that can provide structural reinforcement to the laminate sheet. The cavity region can have a variety of different shapes and sizes. For example, the cavity region can be a polygonal shape (e.g., square, hexagonal, etc.), circular, elliptical or other suitable shapes. In some embodiments, a cell casing can include a first laminate sheet that is a formed laminate sheet and a second laminate sheet that is not formed. In other words, the other side of the cell casing can include an inner layer that defines openings that are, for example, die cut or laser formed, as described above for previous embodiments.

[0062] FIG. 8 illustrates a formed laminate sheet **510** that includes a first or inner layer, a second or intermediate layer and a third or outer layer (each not shown in FIG. 8). As described above for previous embodiments, the second layer can include a metal foil formed with an electrically conductive material, such as, for example, aluminum, an aluminum alloy, or copper. The first layer can define one or more openings (not shown) to expose at least a portion of the

second layer. The formed laminate sheet **510** defines a cavity **528** in which an electrode material can be disposed and be electrically connected to the exposed conductive material of the second layer (e.g., metal foil). In this embodiment, the laminate sheet **510** includes walls **540** that are formed at a substantially 90 degree angle relative to a bottom surface **542** of the cavity **528**. The bottom surface **542** can be the exposed surface of the second conductive layer. The walls **540** and bottom surface **542** define the cavity **528**. A separator **530** is coupled to the laminate sheet **510** and encloses the cavity **528**. The laminate sheet **510** can be coupled to a laminate sheet **510'** on an opposite side of the separator **530** to form a cell pouch or casing **500**, as shown in FIG. 9. The laminate sheet **510'** can be formed the same or similar as described for laminate sheet **510** and can define a cavity **528'**. An anode electrode material can be disposed in none of the cavities **528**, **528'** and a cathode electrode material can be disposed in the other of the cavities **528**, **528'**.

[0063] FIG. 10 illustrates a portion of a framed cell casing **600**. The cell casing **600** includes a laminate sheet **610** that includes a first layer **624** and a second layer **622**, and a separator **630** is coupled to the first layer **624**. A cavity **628** is defined by the side walls **640** of the first layer **624** and a surface **642** of the second layer **622**. As with previous embodiments, the second layer **622** can be formed with an electrically conductive material, such as, for example, aluminum, an aluminum alloy, or copper. An electrode material (not shown) can be disposed within the cavity **628** and be electrically connected to the exposed conductive material of the second layer **622** (e.g., metal foil), such that the second layer **622** can serve as the current collector for the cell.

[0064] FIG. 11 illustrates a portion of another framed cell casing **700**. The cell casing **700** includes a laminate sheet **710** that includes a first layer **724**, a second layer **722**, and a separator **730** is coupled to the first layer **724**. In this embodiment, a third layer **720** is also included. The third layer can be a plastic protective outer layer of the cell casing. A cavity **728** is defined by the side walls **740** of the first layer **724** and a surface **742** of the second layer **722**. As with previous embodiments, the second layer **722** can be formed with an electrically conductive material, such as, for example, aluminum, an aluminum alloy, or copper. An electrode material (not shown) can be disposed within the cavity **728** and be electrically connected to the exposed conductive material of the second layer **722** (e.g., metal foil). The second layer **722** also includes a tab portion **727** that extends beyond an outer perimeter of the inner layer **724**. The tab portion **727** can serve as a power connection tab to provide electrical current to the electrode.

[0065] FIG. 12 illustrates another embodiment of a formed cell casing for an electrochemical cell. A cell casing **900** includes a formed laminate sheet **910** that includes a first layer **924** and a second layer **922**. The laminate sheet **910** can also optionally include a third layer (not shown in FIG. 12). As described above for previous embodiments, the second layer **922** can be formed with an electrically conductive material, such as, for example, aluminum or an aluminum alloy. The first layer **924** defines a first opening **926** to expose at least a portion **942** of the second layer **922**. The formed laminate sheet **910** defines a cavity **928** in which an electrode material can be disposed and be electrically connected to the exposed portion **942** of the second layer **922**. In this embodiment, the laminate sheet **910** includes

walls **940** that are formed at a substantially 90 degree angle relative to a bottom surface **946** of the first layer **924**. The first layer **924** also defines the opening **926** at the periphery of the walls **940**. The walls **940** and bottom surface **946** together with the exposed portion **942** of second layer **922** define the cavity **928**. The first layer **924** also defines a second opening **936** that exposed a second portion **932** of the second layer **922**. The second exposed portion **932** can serve as a power connection tab and be coupled to an electrical lead **934** that can be used to provide electrical current to the cell. As described for previous embodiments, a separator (not shown) can be coupled to the first layer **924** and a second laminate sheet (not shown) can be coupled to the separator and to the laminate sheet **910** to form the cell casing **900**.

[0066] FIG. 13A illustrates a formed laminate sheet for a cell casing, according to another embodiment. A laminate sheet **1010** includes a first layer **1024** and a second layer **1022**. The laminate sheet **1010** can also optionally include a third layer (not shown in FIG. 13A). As described above for previous embodiments, the second layer **1022** can be formed with an electrically conductive material, such as, for example, aluminum or an aluminum alloy. The first layer **1024** defines an opening **1026** to expose at least a surface portion **1042** of the second layer **1022**. The formed laminate sheet **1010** defines a cavity **1028** in which an electrode material can be disposed and be electrically connected to the exposed portion **1042** of the second layer **1022**. In this embodiment, the laminate sheet **1010** includes walls **1040** that are formed at a substantially 90 degree angle relative to the exposed surface portion **1042** of the second layer **1022**. The walls **1040** and surface portion **1042** of second layer **1022** define the cavity **1028**. In this embodiment, the second layer **1022** includes an extended portion **1027** that extends beyond an outer perimeter of the first layer **1024**. The extended portion **1027** can serve as a power connection tab to provide electrical current to the cell. As described for previous embodiments, a separator (not shown) can be coupled to the first layer **1024** and a second laminate sheet (not shown) can be coupled to the separator and to the laminate sheet **1010** to form a cell casing.

[0067] FIG. 13B is an enlarged view of a portion of the laminate sheet **1010** illustrating the formed angle of 90 degrees between the walls **1040** and the surface **1042**. FIGS. 13C and 13D each illustrate alternative embodiments of a laminate sheet **1010A** and **1010B**, respectively. As shown in FIG. 13C, the laminate sheet **1010A** can be formed with a 45 degree angle, and as shown in FIG. 13D, the laminate sheet **1010B** can be formed with a 30 degree angle. FIGS. 13E and 13F each illustrate alternative embodiments of a laminate sheet similar to laminate sheet **1010** with the first layer disposed on different portions of the second layer. In FIG. 13E, the laminate sheet **1010C** illustrates an embodiment with a first layer **1024C** extending onto a portion of the surface **1042C** of the second layer **1022C**. In FIG. 13F, the laminate sheet **1010D** illustrates an embodiment with a first layer **1024D** that does not cover the wall portions **1040D** of the second layer **1022D**.

[0068] FIGS. 14A and 14B illustrate a formed laminate sheet for a cell casing, according to another embodiment that is similar to the embodiment of FIG. 14A. A laminate sheet **1110** includes a first layer **1124** and a second layer **1122**, and can also optionally include a third layer (not shown in FIGS. 14A and 14B). As described above for previous embodi-

ments, the second layer **1122** can be formed with an electrically conductive material, such as, for example, aluminum, an aluminum alloy, or copper. The first layer **1124** defines an opening **1126** to expose at least a portion of a surface **1142** of the second layer **1122**. The formed laminate sheet **1110** defines a cavity **1128** in which an electrode material can be disposed and be electrically connected to the exposed surface portion **1142** of the second layer **1122**. The laminate sheet **1110** includes walls **1140** that are formed at a substantially 90 degree angle relative to the surface **1142** of the second layer **1122**. The walls **1140** and surface **1142** of second layer **1122** define the cavity **1128**. In this embodiment, the second layer **1122** also includes raised portions (e.g., protrusions, dimples, etc.) **1148** that provide structural reinforcement to the laminate sheet **1110**.

[0069] As with the embodiment of FIG. 13A, the second layer **1122** also includes an extended portion **1127** that extends beyond an outer perimeter of the first layer **1124**. The extended portion **1127** can serve as a power connection tab to provide electrical current to the cell. As described for previous embodiments, a separator (not shown) can be coupled to the first layer **1124** and a second laminate sheet (not shown) can be coupled to the separator and to the laminate sheet **1110** to form a cell casing.

[0070] FIGS. 15A-15C illustrate another embodiment of formed laminate sheet for a cell casing that includes structural reinforcement features. A laminate sheet **1210** includes a first layer **1224** and a second layer **1222**, and can also optionally include a third layer (not shown in FIGS. 16A-16C). As described above for previous embodiments, the second layer **1222** can be formed with an electrically conductive material, such as, for example, aluminum, an aluminum alloy, or copper. The first layer **1224** defines an opening **1226** to expose at least a portion of a surface **1242** of the second layer **1222**. The formed laminate sheet **1210** defines a cavity **1228** in which an electrode material can be disposed and be electrically connected to the exposed portion of surface **1242** of the second layer **1222**. In this embodiment, the laminate sheet **1210** includes walls **1240** that are formed at an angle less than 90 degrees relative to the surface **1242** of the second layer **1222**, and the walls **1240** and surface **1242** of second layer **1222** define the cavity **1228**. In this embodiment, the second layer **1222** also includes raised portions **1248** (e.g., protrusions, dimples, etc.) and a raised portion **1250** that provide structural reinforcement to the laminate sheet **1210**.

[0071] FIGS. 16A-16C illustrate various steps in a process of manufacturing an electrochemical cell having a laminate casing that can also function as the current collector for the cell. As shown in FIG. 16A, at step 1, a laminate sheet **1310** is placed within a die to form a cavity within the laminate sheet. The laminate sheet **1310** can include multiple layers as described above. For example, the laminate sheet **1310** includes a first layer **1324** that defines an opening through which a portion of a second layer **1322** is exposed. The laminate sheet **1310** can optionally include a third outer protective layer (not shown) as described herein. The second layer **1322** can be formed with an electrically conductive material and can be used as a current collector for the electrochemical cell. The second layer **1322** includes a power connection tab **1327** such as tabs **327** and **1027** described above. Step 2 illustrates the formed laminate sheet with a cavity **1328** defined therein in which an electrode can be disposed. At step 3, a masking material can be placed

over the first layer such that only the exposed portion of the second layer is visible through the masking.

[0072] As shown in FIG. 16B, at step 4, an electrode (referred to as “slurry” in FIG. 16B) can be placed on the exposed portion of the second layer. At steps 5 and 6, the electrode can be smoothed or spread along the surface of the exposed portion of the second layer. For example, a blade or straight edged instrument can be used to spread the electrode. At step 7, the masking can be removed leaving only the portion of the electrode that has been spread onto the exposed portion of the second layer. As shown in FIG. 16C, at step 8, a separator can be placed on a portion of the first layer such that the separator is covering the electrode. At step 9, the completed laminate sheet and separator of step 8 can be joined with another such completed laminate sheet. For example, the electrode of the laminate sheet of step 8 can be a cathode electrode and the other laminate sheet can include an anode electrode. At step 10, a vacuum and heat seal process can be performed to seal the two laminate sheets together to form the finished cell as shown at step 11.

[0073] In conventional batteries, anodes of different layers (e.g., in wound or stacked configurations) can be electrically connected in parallel to one another, and the same for cathodes, which can dictate that the same media (anodic or cathodic) be on both sides of a single metal foil layer. Such configurations are generally described using single letter abbreviations: ACCAACC . . . AAC or the like where A=anode layer and C=cathode layer. The repeating of letters for internal layers refers to double coating configurations.

[0074] For two layer laminates described above for previous embodiments (e.g., a plastic layer disposed partially on a metal foil layer), in some such embodiments, the cell can be referred to as a bipolar battery or bipolar cell. FIG. 17A illustrates a bipolar cell 1452 that includes four electrochemical cells 1400. In such a bipolar cell, the exposed metal foil layer of one cell 1400 (e.g., an anode-cathode pair) can be disposed adjacent to that of a neighboring cell 1400, as shown in FIG. 17B. Electrical contact between adjacent foil layers can be realized by various methods, such as, for example, mechanical compression, use of an electrically conductive paste, welding, brazing, soldering, or other suitable technique. In such a bipolar stack, the stack voltage reflects the serial connection of all the cells composing it, and is thus substantially equal to the sum of the individual cell voltages.

[0075] FIGS. 18A-18C illustrate another embodiment of a formed cell casing for an electrochemical cell. A cell casing 1500 includes a formed laminate sheet 1510 and a formed laminate sheet 1510'. The laminate sheet 1510 includes a first layer 1524 coupled to a second layer 1522, and the laminate sheet 1510' includes a first layer 1524' coupled to a second layer 1522'. The first layers 1524, 1524' can be coupled to their respective second layers 1522, 1522' with, for example, an adhesive (not shown). The first layers 1524, 1524' can be formed with, for example, a cast polypropylene and the second layers 1522, 1522' can be formed with, for example, an aluminum or copper material. In this embodiment, without having a third protective layer, the second layers 1522, 1522' can be formed with a greater thickness, such as, for example, a thickness of 0.075 to 0.100 mm, and the first layer can have a thickness of for example, 0.040 mm. The first layer 1524' and second layer 1522' of the second laminate sheet 1510' are shown transparent in FIGS. 18A-18C for illustration purposes. As described above for

previous embodiments, the second layers 1522, 1522' can each be formed with an electrically conductive material, such as, for example, aluminum or an aluminum alloy, or copper.

[0076] The first layers 1524, 1524' each define a cavity and an opening 1526, 1526' that exposes a portion 1542, 1542' of the respective second layers 1522, 1522'. The second layers 1522, 1522' each include the exposed portion 1542, 1542' that is exposed on both sides of first layer 1524, 1524', and an extended portion 1527, 1527' that is also exposed on both sides of first layer 1524, 1524'. The formed laminate sheet 1510 defines a cavity 1528 and the second laminate sheet 1510' also defines a cavity (not shown). The cavity 1528 and the cavity of the second laminate sheet 1510' collectively form an electrode cavity in which a stacked electrode 1554 can be disposed and be electrically connected to the exposed portion 1542 of second layer 1522 and the exposed portion 1542' of the second layer 1522'.

[0077] The stacked electrode 1554 can be a conventional electrode that includes multiple electrodes each including an electrode material disposed on a metal foil sheet and a pair of electrical connection tabs 1556 and 1558. The electrode stack 1554 can also include separators (not shown) disposed between the multiple electrodes. The tabs 1556 and 1558 can extend from the metal foil sheets and be welded to the laminate sheets 1510 and 1510'. As shown in FIG. 18C, the tab 1556 can be welded to the exposed portion 1527 of the laminate sheet 1510, and the tab 1558 can be welded to the exposed portion 1527' of the laminate sheet 1510' as shown at weld location 1560. In other words, as shown in FIG. 18C, the tab 1556 is welded on a bottom side to the top surface of the exposed portion 1527, and the tab 1558 is welded on an upper side to a surface of the exposed portion 1527'. The greater thickness of the second layers 1522, 1522' described above, can help facilitate welding of the tabs 1556 and 1558.

[0078] The laminate sheet 1510 and the laminate sheet 1510' can be coupled together with for example, a heat seal with the electrode stack 1554 disposed within the electrode cavity. With the tabs 1556 and 1558 weld to the exposed portions 1527 and 1527', respectively, the second layers 1522 and 1522' can serve as a power connection for the electrochemical cell 1500. Thus, the need for a pass-through electrical tab is eliminated.

[0079] In some embodiments, the electrode material can be cast into the open cavity of the cell using conventional coating, dying, and calendaring processes. The coatings can be continuous or discrete to accommodate wound, prismatic, or other cell geometries. In other embodiments, the inner layer and foil layer, the foil layer and outer layer (in the case of a three layer), or both, may not be chemically bonded by adhesive, rather, they can simply be in physical contact. Adjacent layers of laminates can be sealed and contact between them established using mechanical means, e.g. compressive force imposed by exterior plates, tie rods, or bands. In other embodiments, the laminate may be used only on the end cells of a stacked assembly. In yet another embodiment, the laminate cell design and assembly approach can be used on one of the anode or cathode sides instead of both.

[0080] In another embodiment, the laminate can be fabricated using conventional processes. For example, the foil substrate layer can be coated with electrode materials in a conventional manner (e.g., coated, dried, calendered), and optionally in discrete patches. A framing material can then

be applied to the foil substrate to create a laminate. In this example, the electrode is not a slurry-based electrode; rather the electrode can be a conventional electrode (e.g., cast active material and conductive additive in a solid matrix held together with a binding agent, interspersed with electrolyte within its pores).

[0081] In some embodiments, the laminate current collectors of a cell as described herein can be configured to perform a heat exchange function, i.e. they can also function as heat collectors and dissipaters. In some applications, it may be desirable to maintain the cell operating temperature within a specified range (for example, -40°C to 60°C , or -20°C to 55°C , or 0°C to 55°C , or 15°C to 30°C), and it may be desirable that heat generated during cell operation be collected and conducted away from the active area of the cell to other regions of the cell, which may be at any location outside of the active area, where the heat can be dissipated. Regions of the foil layer can act as (1) cooling fins in the ambient environment, which may be air, a conditioned (e.g., temperature, humidity, etc.) gaseous environment, liquid coolant (e.g., water, water/glycol mixture, heat exchange fluid, etc.) conductive, (2) thermally conductive pathways affixed by suitable methods (e.g., chemical joining such as, e.g., welding, brazing, soldering, or physical contact, such as, e.g., compressive contact, crimping, co-folding) to auxiliary thermal management hardware and systems, or (3) radiant surfaces. Heat conduction in the opposite direction is also possible, for example, to facilitate an operational start or a start sequence from a cold condition (e.g. -100°C , -60°C , -40°C , -20°C , $<0^{\circ}\text{C}$, or $<15^{\circ}\text{C}$) in which case the current collecting portion of the laminate is used to conduct heat into the cell from another heat source. In some embodiments, electrochemical cells as described herein can be connected in series and packaged with an inert gas. For example, multiple cells can be stacked in series and then placed into a housing (e.g., a can). The interior volume of the housing can then be purged with an inert gas and then hermetically sealed. As described herein, the laminate sheet provides a first seal for individual cells and the outer housing provides a second seal from the environment (e.g. zero moisture environments). Furthermore, the inert gas improves safety of the cell, battery and/or module by reducing or preventing sparks and fires.

[0082] While various embodiments have been described above, it should be understood that they have been presented by way of example only, not limitation, and various changes in form and details may be made. Where methods described above indicate certain events occurring in certain order, the ordering of certain events can be modified. Additionally, certain of the events can be performed concurrently in a parallel process when possible, as well as performed sequentially as described above. Any portion of the apparatus and/or methods described herein may be combined in any combination, except mutually exclusive combinations. The embodiments described herein can include various combinations and/or sub-combinations of the functions, components and/or features of the different embodiments described.

[0083] Furthermore, while certain temperatures, pressures, and other measurements, calculations, and/or other values are described in approximate terms, the values used are not meant to be exact and a range of values can be used.

For example, while the formed cell of FIG. 8 is described as including 90° degree angles, in some embodiments, other angles can be used.

1-31. (canceled)

32. An apparatus, comprising:

a first multi-layer sheet having a first layer and a second layer;

a second multi-layer sheet having a first layer and a second layer; and

a separator disposed between the first layer of the first multi-layer sheet and the first layer of the second multi-layer sheet,

the separator configured to encase a first electrode material in a first cavity when the separator is coupled to the first layer of the first multi-layer sheet,

the separator further configured to encase a second electrode material in a second cavity when the separator is coupled to the first layer of the second multi-layer sheet.

33. The apparatus of claim 32, wherein the first layer of the first multi-layer sheet is thermally bondable to the first layer of the second multi-layer sheet.

34. The apparatus of claim 32, wherein the first multi-layer sheet includes a first conductive portion, and the second multi-layer sheet includes a second conductive portion.

35. The apparatus of claim 34, wherein the first conductive portion is at least partially disposed between the first layer and the second layer of the first multi-layer sheet.

36. The apparatus of claim 34, wherein the separator is coupled to the first layer of the first multi-layer sheet to form a seal around the first conductive portion.

37. The apparatus of claim 36, wherein the separator is coupled to the first layer of the second multi-layer sheet to form a seal around the second conductive portion.

38. An apparatus, comprising:

a casing for an electrochemical cell, the casing including a multi-layer sheet including an inner layer and an outer layer, the inner layer formed with a material configured to be thermally bondable to itself,

the multi-layer sheet configured to define a first cavity configured to receive a first electrode material, and to define a second cavity configured to receive a second electrode material; and

a separator disposed between the first cavity and the second cavity and coupled to a portion of the inner layer.

39. The apparatus of claim 38, wherein the outer layer is a heat resistant film.

40. The apparatus of claim 38, wherein the outer layer is a polyamide material.

41. The apparatus of claim 38, wherein the inner layer includes a cast polypropylene material.

42. The apparatus of claim 38, wherein the separator is coupled to the inner layer to form a seal around the first cavity.

43. The apparatus of claim 42, wherein the separator is coupled to the inner layer to form a seal around the second cavity.

44. An apparatus, comprising:

a first multi-layer sheet having a first conductive region and a first sealing region;

a first electrode material disposed on the first conductive region;

a second multi-layer sheet having a second conductive region and a second sealing region;
a second electrode material disposed on the second conductive region; and
a separator disposed between the first multi-layer sheet and the second multi-layer sheet, the first multi-layer sheet coupled to the second multi-layer sheet to form an electrochemical cell such that the separator is coupled to the first sealing region to encase the first electrode material and to the second sealing region to encase the second electrode material.

45. The apparatus of claim **44**, wherein the first sealing region is thermally bondable to the second sealing region.

46. The apparatus of claim **44**, wherein the first multi-layer sheet further includes an outer layer.

47. The apparatus of claim **46**, wherein the outer layer is a heat resistant film.

48. The apparatus of claim **46**, wherein the outer layer is a polyamide material.

49. The apparatus of claim **46**, wherein the first conductive region is at least partially disposed between the first sealing region and the outer layer.

50. The apparatus of claim **44**, wherein the first sealing region and the second sealing region include a cast polypropylene material.

51. The apparatus of claim **44**, wherein the separator is coupled to the first sealing region to form a seal around the first conductive region.

* * * * *