



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 623 636 A1**

(12) **EUROPEAN PATENT APPLICATION**
published in accordance with Art. 158(3) EPC

(43) Date of publication:
08.02.2006 Bulletin 2006/06

(51) Int Cl.:
A24D 1/02 (1968.09)

(21) Application number: **04727107.7**

(86) International application number:
PCT/JP2004/005254

(22) Date of filing: **13.04.2004**

(87) International publication number:
WO 2004/091325 (28.10.2004 Gazette 2004/44)

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IT LI LU MC NL PL PT RO SE SI SK TR**

(30) Priority: **14.04.2003 JP 2003108995**

(71) Applicant: **Japan Tobacco Inc.
Tokyo 105-8422 (JP)**

(72) Inventors:
• **MATSUFUJI, Takaaki**
c/o Japan Tobacco Inc.
Minato-ku, Tokyo 105-8422 (JP)
• **TSUTSUMI, Takeo**
c/o Japan Tobacco Inc.
Minato-ku, Tokyo 105-8422 (JP)

- **KOMINAMI, Takashi**
c/o Japan Tobacco Inc.
Minato-ku, Tokyo 105-8422 (JP)
- **MIURA, Keigo**
c/o Japan Tobacco Inc.
Minato-ku, Tokyo 105-8422 (JP)
- **UYAMA, Ken**
c/o Japan Tobacco Inc.
Minato-ku, Tokyo 105-8422 (JP)

(74) Representative: **Behnisch, Werner**
Reinhard-Skuhra-Weise & Partner GbR,
Friedrichstrasse 31
80801 München (DE)

(54) **CIGARETTE OF ENHANCED LOW FIRE SPREAD**

(57) A cigarette includes a tobacco filler material rod and a cigarette paper wrapping the rod. The cigarette paper has an inherent air permeability of more than 20

CORESTA units but 80 CORESTA units or less and contains a loading material in an amount of 1.0 to 5.0 g/m².

EP 1 623 636 A1

Description

Technical Field

5 **[0001]** The present invention relates to a low flame-spreading cigarette that is unlikely to cause flame spread from the kindling to the surroundings so as not to allow the ignited cigarette to cause fire by, for example, the carelessness of the smoker.

Background Art

10 **[0002]** Cigarettes have been proposed, including, for example, a cigarette having a cellulose paper band, which is 2 to 20 mm wide, formed on the cigarette paper to impart self-extinguishing property(see Japanese Patent Disclosure (Kokai) No. 63-85200), and a cigarette in which a band coated with a flame retardant substance is formed on the cigarette paper (see Japanese Patent Disclosure (Kokai) No. 7-300795), in order to prevent the spread of flame from the kindling to, for example, the floor, where the cigarette is dropped onto, for example, the floor by the carelessness of the smoker. Further, a cigarette paper having a nonflammable substance pasted thereto is also known. These technologies are based on the idea that a region having high flammability and another region having low flammability are formed in the cigarette paper such that ordinary smoking can be performed in the region having high flammability and that the cigarette is extinguished in the region having low flammability.

20 **[0003]** It is also known well in the art that, if the burn rate of the cigarette is lowered in an attempt to decrease the amount of the sidestream smoke per hour, it is possible to provide a cigarette that can be self-extinguished. As such a cigarette, a cigarette has been proposed, in which shredded tobacco are wrapped with a cigarette paper having a small amount of loading material used an inner paper and with an ordinary cigarette paper used as an outer paper (see Japanese Patent No. 2,572,488). Also, as a cigarette with a low sidestream smoke, a cigarette has been proposed, in which a smoking material rod having a loading density of 100 to 260 mg/cm³ is wrapped by a wrapping paper having an air permeability not higher than 7 CORESTA units (see Japanese Patent No. 3,001,582). Further, a cigarette has been proposed, in which the burn rate is lowered by using a wrapping paper having a low air permeability (7 CORESTA units), having a small amount of loading material, and having a small basis weight (see International Publication WO 01/48316).

30 **[0004]** However, in the case of using a cigarette paper including a nonflammable region, the tobacco burn is made nonuniform because the cigarette paper includes a flame retardant region and a flammable region. Also, the smoking taste is made nonuniform. Also, in the method of lowering flame spread by lowering the burn rate, the flame spread is lowered by lowering the air permeability of the cigarette paper for this purpose. As a result, the ventilation effect produced by the cigarette paper is lowered so as to increase the amount of the carbon monoxide (CO) contained in the mainstream smoke, increasing the carbon monoxide/tar ratio (C/T ratio). Further, if the air permeability of the cigarette paper is lowered, the taste of the tobacco is changed so as to give rise to the problem that an ordinary smoker is caused to feel an incompatibility.

35 **[0005]** On the other hand, it is known that a cigarette using a cigarette paper having a low mixing ratio of loading material is lowered in the burn rate. However, it is experimentally known that the cigarette goes out during static burn, and thus the amount of loading material cannot be decreased excessively.

40 **[0006]** Therefore, an object of the present invention is to provide a cigarette, which is substantially equal to an ordinary cigarette in smoking behavior and in the burn rate, and which permits improving the C/T ratio in the mainstream smoke and exhibits low flame spread.

45 Disclosure of Invention

[0007] As a result of research conducted in an effort to develop a low flame-spreading cigarette, the present inventors have found that a cigarette achieving the above object can be obtained merely by setting the inherent air permeability of the cigarette paper wrapping the tobacco filler material rod and the amount of the loading material mixed in the cigarette paper at prescribed values. The amount of loading material can be decreased as much as possible within the range of maintaining the static burn by setting the inherent air permeability of the cigarette paper to fall within a prescribed range. The present invention is based on these findings.

50 **[0008]** According to the present invention, there is provided a cigarette comprising a tobacco filler material rod and a cigarette paper containing pulp and a loading material, wherein the cigarette paper has an inherent air permeability of more than 20 CORESTA units but 80 CORESTA units or less and contains the loading material in an amount of 1.0 to 5.0 g/m².

[0009] The cigarette of the present invention maintains static burn, and can exhibit a low flame spread property such that, when left to stand on a substrate after static burn over a prescribed distance, a median value of a moving distance

of a char line of the cigarette paper in an axial direction of the cigarette until the burn of the cigarette is stopped is not larger than 8 mm.

[0010] According to a preferred aspect of the present invention, there is provided a cigarette comprising a tobacco filler material rod and a cigarette paper wrapping the rod, wherein the cigarette paper has an air permeability of more than 20 CORESTA units but 80 CORESTA units or less, contains a loading material in an amount of 1.4 to 3.7 g/m² and also contains a burn adjusting agent in an amount of 0 to 0.6% by weight, and the tobacco filler material is loaded at a loading density of 130 to 230 mg/cm³.

Best Mode for Carrying Out the Invention

[0011] The present invention will be described in more detail below.

[0012] A cigarette according to the present invention comprises a tobacco filler material rod and a cigarette paper wrapping the tobacco filler material rod. The cigarette of the present invention has an outer appearance and shape similar to those of an ordinary cigarette.

[0013] The tobacco filler material rod used in the cigarette of the present invention is formed of, e.g., ordinary shredded tobacco. The shredded tobacco may contain expanded tobacco and regenerated tobacco, and the central vein of tobacco leaf. It is preferable that the loading density of the shredded tobacco is 130 to 260 mg/cm³. If the loading density fails to fall within the range given above, it may sometime become difficult to suppress sufficiently the flame spread even if the tobacco rod is wrapped in the cigarette paper of the present invention. It is more preferable that the loading density of the tobacco filler material is 130 to 230 mg/cm³, further preferably 140 to 230 mg/cm³. It suffices for the shredding width of the shredded tobacco to be equal to that of ordinary shredded tobacco. However, in view of low flame spread, it is desirable for the shredding width to be relatively large, i.e., 0.5 to 1.5 mm, more preferably 0.8 to 1.2 mm.

[0014] The cigarette paper used in the present invention is based on ordinary pulp such as flax pulp used for forming ordinary cigarette paper and, thus, contains pulp. The cigarette paper used in the present invention has an inherent air permeability (the air permeability of the cigarette paper without any perforations made therein) of more than 20 CORESTA units (C.U.) but 80 CORESTA units or less. If the inherent air permeability of the cigarette paper sheet is not higher than 20 CORESTA units, the C/T ratio is increased in the cigarette mainstream smoke that is generated during the smoking stage. On the other hand, if the inherent air permeability of the cigarette paper exceeds 80 CORESTA units, the nonuniformity of the air permeability is increased. The inherent air permeability of the cigarette paper is desirably more than 20 CORESTA units but 60 CORESTA units or less, and is more desirably 25 to 55 CORESTA units. Incidentally, the cigarette paper may be perforated mechanically or electrically by the ordinary method. The air permeability of the wrapping paper having such holes is not particularly limited.

[0015] The cigarette paper of the present invention contains loading materials. The loading materials that are generally used can be used, including a carbonate salt such as calcium carbonate or potassium carbonate and a hydroxide such as calcium hydroxide or magnesium hydroxide. The loading material is contained in the cigarette paper in an amount of 1.0 to 5.0 g/m². If the amount of the loading material is smaller than 1.0 g/m², the cigarette goes out during static burn. Also, if the loading material is contained in an amount exceeding 5.0 g/m², low flame spread cannot be achieved. It is desirable for the amount of the loading material to be 1.4 to 3.7 g/m², more desirably, 1.6 to 3.3 g/m². Also, the amount of loading material in the cigarette paper is preferably 6 to 25% by weight, more preferably 7 to 21% by weight, and furthermore preferably 8 to 17% by weight.

[0016] The basis weight of the cigarette paper is preferably 17 to 28 g/m². If the basis weight is smaller than 17 g/m², it tends to be difficult to stably manufacture the cigarette paper sheet. Also, if the basis weight exceeds 28 g/m², flame spread tends to be promoted. The basis weight of the cigarette paper is more preferably 18 to 25 g/m², furthermore preferably 18 to 22 g/m².

[0017] It is possible to add a burn adjusting agent such as citric acid or its salt (such as sodium salt or potassium salt) to the cigarette paper. The content of the burn adjusting agent is preferably 0 to 1.0% by weight. If the amount of burn adjusting agent exceeds 1.0% by weight, the C/T ratio tends to become high. The amount of burn adjusting agent is more preferably 0 to 0.6% by weight, furthermore preferably 0.1 to 0.6% by weight.

[0018] Incidentally, the cigarette paper of the present invention, by having a tensile strength of 10 to 20 N/15 mm or more, can make cigarettes, without difficulty, even if applied to a high-speed cigarette making machine that permits manufacturing cigarettes at a rate of 8,000 to 12,000 cigarettes/min. The tensile strength of the cigarette paper can be controlled by controlling the beating degree of the pulp or by controlling the amount of pulp used for manufacturing the cigarette paper sheet. The tensile strength of the cigarette paper increases with increase in the amount of pulp per unit area of the cigarette paper or in the beating degree of the pulp.

[0019] According to the present invention, a cigarette low in flame spread, and generating mainstream smoke having a small C/T ratio is obtained in spite of the relatively high inherent air permeability of the cigarette paper by setting the inherent air permeability of the cigarette paper and the amount of the loading material contained in the cigarette paper to fall within the ranges given above. Also, the cigarette of the present invention permits exhibiting a burn rate substantially

equal to that of an ordinary cigarette. The low flame-spreading property of the cigarette of the present invention may be such that, when left to stand on a substrate (10 superposed filter paper sheets) after static burn over a prescribed distance, a median value of a moving distance of a char line of the cigarette paper in an axial direction of the cigarette until the burn of the cigarette is stopped is not larger than 8 mm, preferably 4 mm or less (measured according to ASTM E 2187-02b method). In a plurality of cigarettes of the present invention, the most frequently obtained value of the moving distance of the char line noted above may be 8 mm or less, preferably 4 mm or less.

[0020] The present invention will now be described with reference to Examples, but the present invention is not limited thereto.

Examples and Comparative Examples

[0021] Shredded tobacco was wrapped in a flax pulp cigarette paper having the specification shown in Table 1 such that the shredded tobacco had the loading density shown in Table 1 so as to fabricate 40 cigarettes for each case. Calcium carbonate was used as the loading material, and sodium citrate was used as the burn adjusting agent. Flue-cured shredded tobacco or blended shredded tobacco were used as the shredded tobacco. Table 1 also shows the inherent air permeability and the tensile strength of the cigarette paper. Incidentally, the tensile strength shown in Table 1 was measured by using a tensile strength tester STROGPAPHE-S manufactured by Toyo Seiki K.K. in accordance with the method specified in Japanese Industrial Standards (JIS) P 8113-1998 (the size of test piece: 15.0 mm X about 250 mm, the gripping distance: 180 ± 2 mm, and the pulling rate: 50 mm/min).

[0022] The static burn rates of the cigarettes thus fabricated were measured by the ordinary method in respect of the fabricated cigarette. Also, the percent full length burn on 10 superposed filter paper sheets was measured by the method specified in ASTM E2187-02b. Further, measurement was made of the median value of the moving distance of the char line of the cigarette paper in the axial direction of the cigarette after the ignited cigarette was placed on the filter papers until the cigarette burning is stopped (or went out). Table 2 shows the results.

[0023] Further, measurement by the ordinary method was made of the amount of total particulate matter (TPM), the amount of carbon monoxide and the amount of tar contained in the tobacco mainstream smoke that was generated during burning of each cigarette, and the C/T ratio was calculated. Also measured was the number of puffs. Table 3 shows the results.

Table 1

Ex. No.	Cigarette Paper						Shredded Tobacco	
	Basis weight (g/m ²)	Amount of loading material in cigarette paper (g/m ²)	Burn adjusting agent (% by weight)	Inherent air permeability (C.U.)	Tensile strength (N/15mm)	Shredding width (mm)	Loading density (mg/cm ³)	
Comp. Ex. 1-1 (Ordinary Cig. 1)	26	7.7	1.0	35	14	0.8	230	
Comp. Ex. 1-2-1	30	8.7	0	10	>14	0.8	220	
Comp. Ex. 1-2-2						1.2		
Comp. Ex. 1-3-1	21	1.9	0	9	24	0.8	220	
Comp. Ex. 1-3-2						1.2		
Ex. 1-1-1	21	2.4	0.2	34	17	0.8	220	
Ex. 1-1-2						1.2		
Ex. 1-2-1	21	3.3	0.2	52	14	0.8	220	
Ex. 1-2-2						1.2		
Comp. Ex. 1-2 (Ordinary Cig. 2)	26	7.7	1.0	35	14	0.8	185	
Ex. 1-1-3	21	2.4	0.2	34	17	1.2	185	
Comp. Ex. 1-2-3	30	8.7	0	10	>14	1.0	140	
Comp. Ex. 1-3-3	21	1.9	0	9	24	1.0	140	
Ex. 1-1-4	21	2.4	0.2	34	17	1.0	140	
Ex. 1-2-3	21	3.3	0.2	52	14	1.0	140	

Table 2

Ex. No.	Cigarette Properties			
	Static burn rate (mm/min)	Static weight burn rate (mg/min)	Percent full length burn (%)	Median value (mm) of moving distance of char line until cigarette went out
Comp. Ex. 1-1 (Ordinary Cig. 1)	4.5	45	100	-
Comp. Ex. 1-2-1	3.2	32	30	4
Comp. Ex. 1-2-2	3.3	33	18	12
Comp. Ex. 1-3-1	Went out		0	-
Comp. Ex. 1-3-2	Went out		0	-
Ex. 1-1-1	3.2	36	8	4
Ex. 1-1-2	2.9	34	0	5
Ex. 1-2-1	3.2	37	18	6
Ex. 1-2-2	3.2	37	18	5
Comp. Ex. 1-2 (Ordinary Cig. 2)	5.5	51	100	-
Ex. 1-1-3	4.1	38	10	6
Comp. Ex. 1-2-3	4.6	31	0	3
Comp. Ex. 1-3-3	Went out		0	-
Ex. 1-1-4	4.0	27	0	3
Ex. 1-2-3	4.2	29	0	4

Table 3

Ex. No.	Components in Mainstream Smoke				Number of puffs (times/cig.)
	TPM (mg/cig.)	Tar (mg/cig.)	CO (mg/cig.)	C/T ratio	
Comp. Ex. 1-1 (Ordinary Cig. 1)	30	23	15	0.64	7.6
Comp. Ex. 1-2-1	38	28	18	0.64	8.6
Comp. Ex. 1-2-2	37	28	18	0.64	8.8
Comp. Ex. 1-3-1	45	33	21	0.59	9.9
Comp. Ex. 1-3-2	45	33	20	0.64	10.2
Ex. 1-1-1	42	31	17	0.56	9.1
Ex. 1-1-2	42	30	17	0.55	9.6
Ex. 1-2-1	40	28	15	0.54	8.9
Ex. 1-2-2	41	29	15	0.53	9.0
Comp. Ex. 1-2 (Ordinary Cig. 2)	28	19	11	0.57	5.3
Ex. 1-1-3	36	25	13	0.51	6.9
Comp. Ex. 1-2-3	36	25	13	0.51	6.2
Comp. Ex. 1-3-3	37	26	13	0.51	6.8
Ex. 1-1-4	33	19	10	0.45	6.0
Ex. 1-2-3	26-	23	9	0.47	5.4

[0024] As is apparent from the results given in Tables 2 and 3, the cigarette fabricated by using the cigarette paper specified in the present invention and tobacco filler materials exhibits excellent low flame spread and a small C/T ratio.

[0025] As described above, the present invention provides a cigarette, which permits a smoking behavior similar to that of an ordinary cigarette, also permits a burn rate substantially equal to that of an ordinary cigarette, further permits exhibiting a low flame spread, and is small in C/T ratio in the generated mainstream smoke. Also, since a special band and a special flame retardant substance are not used in the present invention, the cigarette of the present invention continues to produce a prescribed taste under ordinary smoking behavior.

Claims

- 5 1. A cigarette comprising a tobacco filler material rod and a cigarette paper wrapping the rod, wherein the cigarette paper has an inherent air permeability of more than 20 CORESTA units but 80 CORESTA units or less and contains a loading material in an amount of 1.0 to 5.0 g/m².
2. The cigarette according to claim 1, wherein the cigarette paper has an inherent air permeability of more than 20 CORESTA units but 60 CORESTA units or less.
- 10 3. The cigarette according to claim 1, wherein the cigarette paper has an inherent air permeability of 25 to 55 CORESTA units.
4. The cigarette according to claim 1, wherein the cigarette paper contains the loading material in an amount of 1.4 to 3.7 g/m².
- 15 5. The cigarette according to claim 1, wherein the cigarette paper contains the loading material in an amount of 1.6 to 3.3 g/m².
- 20 6. The cigarette according to claim 1, wherein the cigarette paper contains the loading material in an amount of 6 to 25% by weight.
7. The cigarette according to claim 1, wherein the cigarette paper contains the loading material in an amount of 7 to 21% by weight.
- 25 8. The cigarette according to claim 1, wherein the cigarette paper contains the loading material in an amount of 8 to 17% by weight.
9. The cigarette according to claim 1, wherein the cigarette paper has a basis weight of 17 to 28 g/m².
- 30 10. The cigarette according to claim 1, wherein the cigarette paper has a basis weight of 18 to 25 g/m².
11. The cigarette according to claim 1, wherein the cigarette paper has a basis weight of 18 to 22 g/m².
- 35 12. The cigarette according to claim 1, wherein the cigarette paper contains a burn adjusting agent in an amount of 0.1 to 1.0% by weight.
13. The cigarette according to claim 1, wherein the cigarette paper contains a burn adjusting agent in an amount of 0 to 0.6% by weight.
- 40 14. The cigarette according to claim 1, wherein the cigarette paper contains a burn adjusting agent in an amount of 0.1 to 0.6% by weight.
- 45 15. The cigarette according to claim 1, wherein the tobacco filler material is loaded at a loading density of 130 to 260 mg/cm³.
16. The cigarette according to claim 1, wherein the tobacco filler material is loaded at a loading density of 140 to 230 mg/cm³.
- 50 17. The cigarette according to claim 1, wherein the tobacco filler material comprises shredded tobacco.
18. The cigarette according to claim 17, wherein the shredded tobacco has a width of 0.5 to 1.5 mm.
19. The cigarette according to claim 1, wherein the loading material is selected from the group consisting of calcium carbonate, potassium carbonate, calcium hydroxide and magnesium hydroxide.
- 55 20. A cigarette comprising a tobacco filler material rod, and a cigarette paper wrapping the rod, wherein the cigarette paper has an inherent air permeability of more than 20 CORESTA units but 80 CORESTA units or less, contains a loading material in an amount of 1.4 to 3.7 g/m² and also contains a burn adjusting agent in an amount of 0 to 0.6%

EP 1 623 636 A1

by weight, and the tobacco filler material is loaded at a loading density of 130 to 230 g/cm³.

5 **21.** The cigarette according to claim 20, wherein the cigarette paper has an inherent air permeability of 25 to 55 CORESTA units, contains the loading material in an amount of 1.6 to 3.3 g/m² and also contains the burn adjusting agent in an amount of 0.1 to 0.6% by weight, and the tobacco filler material is loaded at a loading density of 140 to 230 g/cm³.

10 **22.** The cigarette according to claim 1, which exhibits a low flame spread property such that, when left to stand on a substrate after static burn over a prescribed distance, a median value of a moving distance of a char line of the cigarette paper in an axial direction of the cigarette until the burn of the cigarette is stopped is not larger than 8 mm.

15 **23.** The cigarette according to claim 20, which exhibits a low flame spread property such that, when left to stand on a substrate after static burn over a prescribed distance, a median value of a moving distance of a char line of the cigarette paper in an axial direction of the cigarette until the burn of the cigarette is stopped is not larger than 8 mm.

20

25

30

35

40

45

50

55

INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP2004/005254

A. CLASSIFICATION OF SUBJECT MATTER Int.Cl. ⁷ A24D1/02		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols) Int.Cl. ⁷ A24D1/02, D21H27/00		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Jitsuyo Shinan Koho 1926-1996 Toroku Jitsuyo Shinan Koho 1994-2004 Kokai Jitsuyo Shinan Koho 1971-2004 Jitsuyo Shinan Toroku Koho 1996-2004		
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X Y	JP 5-195498 A (Philip Morris Products Inc.), 03 August, 1993 (03.08.93), & DE 69232298 T & NO 921456 A & FI 921624 A & CA 2065788 A & EP 513984 A & US 5168884 A & TR 28898 A & KR 238731 B & AT 210930 T & DK 513984 T & PT 513984 T & ES 2169721 T	1-14, 19 15-18, 20-21
Y	WO 01/48316 A1 (Japan Tobacco Inc.), 05 July, 2001 (05.07.01), & CA 2395465 A & AU 2401801 A & EP 1266996 A & US 2003-34042 A1 & CN 1415038 T	15-18, 20-21
<input checked="" type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention	
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone	
"E" earlier application or patent but published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art	
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family	
"O" document referring to an oral disclosure, use, exhibition or other means		
"P" document published prior to the international filing date but later than the priority date claimed		
Date of the actual completion of the international search 14 June, 2004 (14.06.04)	Date of mailing of the international search report 29 June, 2004 (29.06.04)	
Name and mailing address of the ISA/ Japanese Patent Office	Authorized officer	
Facsimile No.	Telephone No.	

INTERNATIONAL SEARCH REPORT

International application No.
PCT/JP2004/005254

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	JP 9-234049 A (Japan Tobacco Inc.), 09 September, 1997 (09.09.97), (Family: none)	18
A	WO 2002/54891 A1 (Japan Tobacco Inc.), 18 July, 2002 (18.07.02), & TW 513290 B & CA 2434449 A & EP 1352573 A	1-23