



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number: **0 448 332 B1**

(12)

EUROPEAN PATENT SPECIFICATION

- (49) Date of publication of patent specification: **15.11.95** (51) Int. Cl.⁶: **D21H 19/40, D21H 19/38**
- (21) Application number: **91302330.5**
- (22) Date of filing: **18.03.91**

(54) **Paper coating compositions and clay and calcium carbonate suitable for use therein.**

(30) Priority: **19.03.90 US 495547**

(43) Date of publication of application:
25.09.91 Bulletin 91/39

(45) Publication of the grant of the patent:
15.11.95 Bulletin 95/46

(84) Designated Contracting States:
BE DE FR GB IT

(56) References cited:
BE-A- 674 608

DATABASE WPIL,no.86-338167,Derwent Publications & SU-A-1229240(UKR CELL-PAPER IND) 07-05-1986

(73) Proprietor: **THE MEAD CORPORATION**
2000 Courthouse Plaza NE
Dayton
Ohio 45463 (US)

(72) Inventor: **Fugitt, Gary P.**
7271 Lake Bluff 19.4 Road
Gladstone,
Michigan 49837 (US)
Inventor: **Uhrig, Dale B.**
7311 Blain Highway
Chillicothe,
Ohio 45601 (US)
Inventor: **Whalen-Shaw, Michael J.**
7041 Zane Trail Road
Circleville,
Ohio 43113 (US)
Inventor: **Taylor, Dene H.**
38 Wellesley Road
Holyoke,
Massachusetts 01040 (US)

(74) Representative: **Deans, Michael John Percy et al**
Lloyd Wise, Tregear & CO.
Norman House
105-109 Strand
London WC2R OAE (GB)

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

EP 0 448 332 B1

Description

The present invention relates in one aspect to a paper coating composition. The compositions of the present invention are characterized in that they are prepared using a deionized clay and/or deionized calcium carbonate and optionally other low ionic strength components.

Paper coating compositions are widely used in the paper industry to provide high grade printing surfaces. Among the compositions which have been used are compositions comprised essentially of a major proportion of a mineral or organic pigment and a minor proportion of a binder in the form of a latex of a film-forming polymer. Suitable pigments have included finely divided clay, calcium sulfoaluminate also known as satin white, oxides of titanium, aluminium, silicon and zinc, calcium carbonate and microsized particles of high softening point polymers which are insoluble in the binder. Suitable binder polymers have been those which are film-forming at ambient and higher temperatures. The coating is spread over the paper surface by a roll coater, trailing blade, air knife, brush or other known means, after which it is dried and calendered.

We describe below the preparation and use of a low ionic strength kaolin clay or ground calcium carbonate pigments that have been highly washed to remove free salt, coatings containing these pigments, and coating compositions containing the same. We have found resulting low ionic strength pigment slurry to have a reduced degree of flocculation, smaller median particle size and increased colloidal stability of the particles. The low ionic strength pigment slurries we have produced have substantially improved rheology.

Our coatings containing only low ionic strength pigments and coatings using low ionic strength pigments as a substantial component of the pigment portion (i.e., greater than 30% based on pigment) display unique properties. Compared to analogous compositions that do not contain low ionic strength pigments, practical embodiments of coating in accordance with the present invention have substantially reduced viscosities that give them similar rheological properties at 3 to 4% higher solids. Compared to analogous compositions that do not contain low ionic strength pigments, our coatings when applied to paper have substantially higher sheet gloss and porosity.

We have found that coating compositions having improved rheology and glossability can be obtained by using a deionized clay or calcium carbonate in the coating composition. The term "deionized" refers to a low ionic strength clay or calcium carbonate which has been treated to remove at least a portion of the ions it contains. The clay or calcium carbonate starting material from which the ions are removed is herein referred to as "untreated". It is important to emphasize that in this context commercially available clays are considered untreated. Typically our materials are deionized by the use of an ion exchange resin or by multiple washes with deionized or distilled water.

It is well known that clay particle size distribution, shape, and state of aggregation have a major effect on the performance of a paper coating composition. It was in the course of seeking to understand more fully the effect of the state of clay aggregation on paper coatings that the present invention was discovered. This work involved an analysis of the particle size distribution of the clay and required that very dilute slurries (7% solids) of clays be prepared (more concentrated slurries could not be analyzed). In order to determine whether the method of dilution from normal shipping solids of 70% to the measurement solids of 7% affected the particle size of the clay, samples were prepared which had been diluted with deionized water or with the supernatant from the suspended clay. This led to the unexpected discovery that the particle size distribution of a clay diluted with deionized water was substantially different than that of a clay diluted with its original suspending liquid (supernatant) containing all the salts and dispersants present in the clay as supplied by the manufacturer. Clays diluted with deionized water had a much higher population of smaller particles, a narrower particle size distribution and greater colloidal stability.

Part of the effect of deionizing the clay is to eliminate or reduce flocculation and thereby reduce particle size, however, it is only part of the effect. We have found that when coatings are prepared from clays having comparable particle size which are not deionized, gloss is not as high and rheology is not as good. In addition reducing particle size often decreases opacity and brightness and increases viscosity; this does not occur in the present coating compositions. Viscosity decreases and in many cases no decrease in opacity or brightness is observed.

BE-A-674608 discloses methods for coating paper with compositions including clay and/or calcium carbonate and latex. SU-A-1229240 discloses methods of removing univalent ions from an aluminosilicate suspension for use in the preparation of a sorbent for manufacturing capacitor and cable paper.

In accordance with a first aspect of the present invention, we provide a paper coating composition comprising clay and/or calcium carbonate slurry and a latex, characterised in that said clay is deionized and has a conductivity less than about 1500 micromhos as a slurry of 70% solids, and said calcium carbonate is deionized and has a conductivity less than about 700 micromhos as a slurry of 70% solids.

In a second and alternative aspect thereof, the invention provides a slurry of deionized clay, said deionized clay being present in an amount of about 60 to 75%, and said slurry having a conductivity of less than about 1500 micromhos at 70% solids.

The invention provides, in a third alternative aspect thereof, a slurry of deionized calcium carbonate containing about 70 to 80% deionized calcium carbonate, and having a conductivity less than about 700 micromhos at 70% solids.

The invention also extends to the clay or calcium carbonate resulting from drying these slurries.

The low ionic strength clay is suitably a kaolin clay slurry which has been highly washed to give it substantially lower dissolved salt content than a conventional clay. Slurries of this clay range from about 60 to 75% solids with a preferred range of about 70 to 72%. Such deionized clay slurries have conductivities less than 1500 micromhos at 70% solids and more preferably conductivities less than 1300 micromhos at 70% solids. The conventional analog to this clay slurry has a conductivity of greater than 3000 micromhos at 70% solids. The low ionic strength of the liquid phase gives the clay slurry unique properties. The particles have a higher degree of colloidal stability as measured by their zeta potential. This increase in zeta potential causes aggregates that exist in the parent clay slurry to dissociate, resulting in a more monodispersed system of particles with a substantially reduced median particle size. The low ionic strength clay slurry has improved rheology as shown by substantially reduced high shear viscosity and dilatancy. The improved rheology allows a low ionic strength clay slurry to contain about 2% higher solids than its conventional counterpart but have comparable rheology.

Low ionic strength ground calcium carbonate may be prepared by highly washing calcium carbonate to give it substantially lower dissolved salt content than a conventional ground calcium carbonate slurry. Slurries of this material contain 70 to 80% solids with the preferred range being 75 to 80% solids. Such deionized calcium carbonate slurries have conductivities less than 700 micromhos at 70% solids and preferably less than 500 micromhos. The low ionic strength of the liquid phase gives the ground calcium carbonate slurry unique properties. The particles have a higher degree of colloidal stability as measured by zeta potential. This increase in zeta potential causes aggregates that exist in the parent calcium carbonate slurry to dissociate, resulting in a more monodispersed system of particles with a substantially reduced median particle size. The low ionic strength ground calcium carbonate slurry has improved rheology as shown by substantially reduced high shear viscosity and dilatancy. The improved rheology allows a low ionic strength ground calcium carbonate slurry to contain 1 to 2% higher solids than its conventional counterpart but have comparable rheology.

Our coating compositions using these materials are advantageous because for comparable clay or calcium carbonate concentrations, they provided higher gloss and they can be used at higher solids. When applied to optically flat black glass plates, which are used as an ideal substrate to reflect the properties of a pigment or a coating without interference from surface roughness, up to a 20 point improvement in gloss was obtained. On paper, not only can higher gloss be achieved, but comparable gloss levels can be obtained with less calendering.

Accordingly, the present invention provides a coating composition which, in its simplest form comprises deionized clay or deionized calcium carbonate and a latex. The compositions may also generally include those additives commonly used in paper coatings such as dispersants, defoamers, pH modifiers, lubricants and other binders like starch.

In accordance with a preferred embodiment of the invention the deionized clay or deionized calcium carbonate is used in combination with a latex having a low ionic strength. Such latexes can be manufactured to have low salt and free surfactant content, or can be prepared by treating commercially available latexes with an ion exchange resin to remove ions therefrom.

Clays may be provided as calcined, non-calcined, predispersed, non-predispersed or physically delaminated clays. Representative clays for use in practice of the present invention include Ultragloss 90 and Ultrawhite 90 sold by Engelhard Minerals & Chemicals Corporation, Edison, N.J. 08817; Hydragloss 90, Hydratex, and Hydrafine sold by J. M. Huber Corporation, Menlo Park, N.J. 08837; and Nuclay, and Lustra Clay sold by Freeport Kaolin Company, a division of Freeport Sulphur Company, New York, N.Y. 10017. No. 1, No. 2 and fine and delaminated clays may be used.

Other conventional pigments can also be employed along with the paper coating clay. These include titanium dioxide, talc, Satin White, hydrated alumina commonly employed as an extender for titanium dioxide, and calcium carbonate (which is preferably deionized). These pigments are used in amounts up to 30% by weight.

These clays and calcium carbonate may be deionized by suspending a normal process clay filtercake or calcium carbonate in deionized water, filtering the suspension, followed by 0-3 repetitions of the suspension-filtration process and finally deflocculation with about 0.3% sodium polyacrylate having a

molecular weight between 1000 and 5000. Alternatively other traditional dispersants can be used. It is anticipated that other techniques for deionization will also be useful.

The clays and calcium carbonate can also be deionized by preparing a slurry of the clay, water and an ion exchange resin and screening out the ion exchange resin after the clay is deionized. This is shown in Example 4.

About 7 parts by weight water per 3 parts clay or calcium carbonate are used. Washing is typically conducted at room temperatures but higher or lower temperatures are also effective. Washing is continued until the desired level of deionization is achieved.

The deionized clays are characterized by both the median particle size, modal particle size, and the size distribution. These measurements are made by sedimentation and expressed as a mass distribution using the Sedigraph 5100 particle sizer. Samples are diluted to test solids of 7% using their own supernatant. Further, deionized clays are defined by changes in particle size and distribution relative to the non-deionized clays. Typical results are shown in Table 1.

Table 1

Typical Change in Clay Particle Size Due to Deionization				
Median Particle Size μm	#1 Clay	#2 Clay	Fine Clay	Delaminated Clay
Nondeionized	1.15	1.10	0.56	1.55
Deionized	0.38	0.45	0.26	0.60
Percent Reduction	67	53	54	60
Percent Less than 0.5 μm				
Nondeionized	17	15	45	9
Deionized	60	54	75	45
Percent Increase	253	260	67	400

The latexes used in practice of the present invention may also be selected from among those latexes commonly used in this art. Particularly preferred are the resins which exhibit primarily elastomeric properties, often described as the rubbery polymers, such as the copolymers styrene-butadiene and styrene-isoprene, or either of them slightly carboxylated by incorporation of from 3 to 10% acrylic acid. Suitable commercial examples are the latexes sold by Dow Chemical Company No. 316, 620, and 640.

More generally, the latexes may be latexes of homopolymers or copolymers of C_4 - C_{10} dienes such as butadiene, 2-methylbutadiene, pentadiene-1,3, etc. The copolymers may be copolymers of vinyl monomers such as styrene, acrylic acid and its esters, methacrylic acid and its esters, nitriles and amides. If desired, rubbery polymer latexes may be blended with minor proportions of latexes of hard or resinous polymers having a high MFT such as polystyrene, polyacrylonitrile, polymethyl methacrylate, copolymers of the monomers of these resinous polymers such as styrene-acrylonitrile resins and resinous copolymers of these monomers with other copolymerizable monomers such as copolymers of styrene with butadiene in which styrene forms more than 70 weight % of the polymer. Preferred are latexes in which the copolymer is composed of about 0-60 weight % of a C_4 - C_6 conjugated diolefin, 40 to 99% of a styrene and 0.1-5% of a polymerizable unsaturated monomer having a polar group such as a carboxyl group in its structure. The solid content of the latex is generally 20 to 55% by weight.

These latexes can be manufactured using additives which are designed to minimize ionic strength or they can be prepared by treating commercially available latexes to reduce their ionic strength.

A technique which may be used to deionize or reduce the ionic strength of a commercial latex involves diluting the latex to about 34% solids with deionized water and adding a mixed anionic and cationic ion exchange resin such as Dow MR3 or Rohm and Haas Amberlite 150 at a dry weight ratio between 0.1:1 and 2:1 to the latex. After about 1 to 2 hours the ion exchange resin can be strained from the latex.

We have found that the pH of the latex is preferably about 6.0 to 10.0.

Paper coating compositions in accordance with the invention may also contain a hydrocolloid. The hydrocolloid may be deionized as well. Conventional paper coating hydrocolloids may be used such as starch, polyvinyl alcohol, proteins.

The starch optionally used may also be selected from those starches commonly used in this art. Suitable commercial examples include all commercial starches produced for the paper industry. These starches are preferably deionized by diluting to 5% with deionized water and filtering once or diluting to 10-

20% and filtering 2 or 3 times. The slurry need only be mixed for 5-10 minutes before filtering or can be separated by gravity settling. The starch or hydrocolloid has a preferred conductivity of less than 0.5 millimhos at 20% solids and 23 °C.

5 Addition of 1-10% deionized starch to the deionized clay we have found to partially protect the clay from reflocculation by later additives.

The deionized clay may be treated with a dispersing agent to disperse the deionized clay in the latex. Conventional non-ionic dispersing agents such as polyacrylates may be used for this purpose.

10 The compositions may contain about 60 to 85% by weight pigment (of which 50 to 100% is deionized clay and/or calcium carbonate), about 1 to 40 and preferably 3 to 20% latex and about 0 to 5% of starch or other hydrocolloid. Clay and calcium carbonate are often used together in a ratio of clay to calcium carbonate of about 7:1 to 1:3.

15 In addition to the pigment and latex binder components, other usual and known additives may be included in the paper coating composition as required. Other binders, e.g., proteins, viscosity modifiers, e.g., sodium polyacrylates, defoamers, pH modifiers (preferred coatings have a pH of 6 to 10), lubricants, and other film-forming latices, etc. may be included.

Our Clay containing coating compositions (i.e., the combination of clay, latex, and any pigment, starch, or other additive) preferably have a conductivity less than 1.3 millimhos at 23 °C and 60% total solids. Our calcium carbonate containing coating compositions preferably have a conductivity less than 0.8 millimhos at 23 °C and 60% solids.

20 Desirable properties are achieved when the latex and hydrocolloid as well as the clay and calcium carbonate are deionized. However, because deionization of the latex and hydrocolloid adds expense to the composition this may not always be desirable commercially. Accordingly, in the most typical embodiments the clay and calcium carbonate will be deionized, however, further improvements in rheology and gloss may be achieved if commercially desirable by deionizing the latex and hydrocolloid.

25 The compositions can be applied to conventional base stocks using known paper coating techniques and optionally calendered. The compositions can be applied in conventional coat weights.

The present invention is illustrated in more detail by the following non-limiting examples.

Example 1

30

Three samples of deionized clay were prepared. Sample A was a regular #1 clay which was centrifuged then the sediment was resuspended in deionized water. The centrifugation-resuspension process was repeated twice. A polyacrylate dispersant was added to the resulting clay until minimum low shear viscosity was reached.

35 Sample B was prepared by triple washing a regular #1 clay with deionized water. A polyacrylate dispersant was added to the resulting clay until minimum low shear viscosity was reached.

Sample C was prepared by mixing a high brightness #1 clay with a mixed ion exchange resin at a 1:0.1 dry-on-dry ratio. The mixture was blended for 2 hours then screened through a 65 mesh screen to remove the beads. A polyacrylate dispersant was added to the resulting clay until minimum low shear viscosity was reached. The conductivity, Hercules and Brookfield viscosity of each clay is shown in Tables 2 and 3.

40

45

50

55

Table 2

Solids	Conductivity (millimhos)		Clay Sample A Hercules Visc. (1100 RPM)		Brookfield Visc. (100 RPM)	
	Regular	Deionized	Regular	Deionized	Regular	Deionized
75.0	2.25	0.130	5457	2465	410	1360
74.5	2.25	0.122	3697	1200	363	960
74.0	2.25	0.122	3757	1118	292	798
73.5	2.25	0.122	2122	104	245	694
73.0	2.22	0.122	1592	83	217	592
72.5	2.22	0.122	1226	52	192	482
72.0	2.22	0.122	160	42	170	404
71.5	2.22	0.122	118	35	152	350
71.0	2.20	0.122	76	28	140	298
70.5	2.20	0.122	49	28	120	250
70.0	2.20	0.122	42	28	109	222

This example clearly shows that deionized clay has greatly reduced high shear viscosity and this difference is increased as solids level is raised. Since high shear viscosity is the parameter most important to pumpability of a slurry, the deionized clay can be shipped and handled at 2% higher solids without detrimentally affecting the pumpability.

Table 3

	Clay Sample B		Clay Sample C	
	Undeionized	Deionized	Undeionized	Deionized
Solids	70.1	70.1	70.0	70.0
Conductivity	1.65	0.61	1.41	0.59
Brookfield Viscosity (100 RPM)	146	268	106	188
Hercules Viscosity (1100 RPM and ABOB)	278	222	3016	1140

The results in Table 2 and 3 clearly show that high shear viscosity is reduced by deionizing a clay whether the clay is deionized by multiple centrifugation and resuspension, multiple washing, or by use of an ion exchange resin.

Example 2

Clay

Hydrafine clay, a No. 1 kaolin clay from J.M. Huber Corporation, was deionized by washing twice with deionized water.

Latex

Dow RAP316 latex (a styrene butadiene latex available from Dow Chemical Company) was diluted to 34% solids and blended with an ion exchange resin (Dow MR3, a mixed cationic and anionic resin available from Dow Chemical Company) in a dry weight ratio of 1:1. The mixture was mixed for 4 hours and filtered through a 65 mesh screen to remove the ion exchange resin. The resulting latex contained 30% solids and the pH was adjusted to 8.5 with ammonia.

Starch

Coating compositions were prepared by preparing a clay suspension containing 74% solids and blending this with the starch before the latex addition to provide the coating compositions shown in Table 4:

Table 4

Sample No. (wt.%)		
	1 Control	2 Invention
Clay (Hydrofine)	87	-
Deionized Clay (Hydrofine)	-	87
Latex (Dow RAP 316)	10	5
Deionized Latex (Dow RAP 316)	-	5
Starch (PG 250)	3	3
Solids	61.4	61.4

The conductivity of each coating was measured using a YSI Model 32 conductance meter having a range of 0.01 to 20,000 microohms. All testing was done at room temperature. The coatings were drawn down on an optically smooth black glass to measure the optical properties. Gloss was measured using a Hunter 75 degree gloss meter.

The results obtained are provided in Table 5.

Table 5

	Sample #	
	1	2
Conductivity	1.97	1.26
Brookfield Viscosity	960	830
Hercules Viscosity	43.8	36.8
Gloss	36.2	46.0

The foregoing results clearly show that the paper coating compositions comprising deionized clay and deionized latex and deionized starch exhibit higher gloss and better rheology than coatings prepared without deionizing the clay and latex. The deionized coating can be prepared at 4% higher solids and maintain equal or better rheology.

Example 3

The coatings described in Example 3 were applied to paper using a rigid blade coater. The rawstock was a wood-free sheet, and the coater speed was 609.6m (2000 feet) per minute. A precoat made up of a 50:50 blend of #2 clay and coarse calcium carbonate was used. The resulting calendered and uncalendered glosses are recorded in Table 6.

Table 6

Control	Uncalendered	Calendered
As 3.629kg (8 lb)/rm single coat	21.3	57.0
As 2.722kg (6 lb)/rm topcoat	27.1	63.8
Sample #1		
As 3.629kg (8 lb)/rm single coat	25.3	60.4
As 2.722kg (6 lb)/rm topcoat	35.5	69.8
Sample #2		
As 3.629kg (8 lb)/rm single coat	30.0	65.0
As 2.722kg (6 lb)/rm topcoat	42.8	73.3

It can clearly be seen from these results that a deionized coating (Sample #2) gives an increase from 3-8 points of gloss when applied to uncoated or precoated paper.

Example 4

In the lab, 2000 g of a commercial spray dried #1 clay was added to 857 grams of distilled water and mixed on a Cowles mixer for 10 minutes. The resulting 70% solids slurry was blended in a high speed blender for 2 minutes. A second batch of slurry was made in an identical manner.

The first batch was diluted to 40% solids while under a mixer and 200 g of a mixed cationic and anionic ion exchange resin was added. The clay and resin were mixed for 2 hours. After this time, the mixture was poured through a 100 mesh screen to remove the resin. A polyacrylate dispersant was added to the resulting slurry at a level of 0.3% based on dry clay. About half of the resulting dispersed deionized clay slurry was dried and added back to the remaining slurry to create a 73% solids deionized clay slurry. This slurry was used for comparison to the second batch of 70% #1 clay slurry.

Two ground calcium carbonate slurries (90% less than 2 μm) were made at 76% solids using the method described above. One of the slurries was diluted to 50% and the same ion exchange resin was added on a 1:10 basis dry resin:dry carbonate. After 2 hours of mixing, the slurry was screened to remove the resin. A polyacrylate dispersant was added at 0.015% based on dry carbonate.

A portion of the resulting dispersed deionized calcium carbonate slurry was dried and added back to the remaining slurry to produce a 78% solids deionized calcium carbonate slurry. This slurry was compared to the other 76% slurry of undeionized calcium carbonate.

These slurries were tested and the results are shown in Tables 7 and 8. Particle size was measured using the Sedigraph Model 5100. Zeta potential was measured using a Lazer Z instrument. Samples for particle size and zeta potential measurement were diluted using their own supernatant. These results show that the deionized pigments have reduced high shear viscosity and can be increased in solids and have comparable rheology to the conventional pigment slurries. The reduction in particle size indicates deflocculation of the pigment slurries. This deflocculation is due to the increase in colloidal stability indicated by the changes in zeta potential.

Table 7

Evaluation of Deionized and Conventional Clay and Calcium Carbonate Slurries				
	% Solids	Brookfield Low Shear Visc. (cP) (100 rpm)	Hercules Visc. (cP) High Sheer (A bob, 4000 rpm)	Conductivity (micromhos)
Commercial #1 Clay	70.1	153	198	1650
Deionized #1 Clay	70.0	222	43	650
	71.0	417	69	710
	72.0	539	198	750
	73.0	832	1018	830
Ground Calcium Carbonate	76.0	301	496	780
Deionized Calcium Carbonate	76.0	263	167	600
	77.0	359	465	630
	78.0	553	1043	650

Table 8

Evaluation of Deionized and Convention Clay and Calcium Carbonate Slurries				
	% Solids	Particle Size (u)		Zeta Potential (mV)
		(Modal)	(Median)	
Commercial #1 Clay	70.0	0.79	0.76	-50.8
Deionized #1 Clay	70.0	0.37	0.42	-63.3
Ground Calcium Carbonate	76.0	1.18	0.94	-45.5
Deionized Calcium Carbonate	76.0	1.07	0.83	-53.3

Example 5

Deionized clay and calcium carbonate slurries were produced by the method described in Example 1. Deionized latex was produced by diluting a styrene-butadiene latex to 40% solids and adding an ion exchange resin to latex at a 1:10 ratio. This mixture was stirred for one hour and filtered through cheesecloth to remove the ion exchange resin. A deionized polystyrene 3 plastic pigment was produced by the same process. A deionized starch was produced by diluting an uncooked commercial ethylated starch to 5% solids with distilled water and then removing the water by filtration. The resulting deionized starch was cooked by conventional methods.

Five different coating formulations containing various combinations of clay, titanium dioxide, calcium carbonate, plastic pigment, latex and starch were made with deionized and convention components. These coatings were applied to optically smooth glass (an ideal substrate) and the gloss of the dried films was measured. The results in Tables 9 and 10 show that in all cases, the coatings containing deionized components had lower low shear viscosity and higher gloss than their conventional analogs. Generally high shear viscosities were comparable. Coatings B, D, H and K show than coatings with pigment systems that are only partially deionized also show the described benefits.

Table 9

Evaluation of Deionized Coatings and Their Conventional Analogs Containing Pigment Blends						
	A	B	C	D	E	F
Commercial #1 Clay	82		62		80	
Deionized #1 Clay		82		62		80
Titanium Dioxide	5	5	25	25		
Plastic Pigment					7	
Deionized Plastic Pigment						7
Styrene/Butadiene Latex	10		10		10	
Deionized Styrene/Butadiene Latex		10		10		10
Corn Starch	3		3		3	
Deionized Corn Starch		3		3		3
Solids (%)	60	60	60	60	60	60
Conductivity (millimhos)	1.88	0.82	2.18	1.02	2.13	0.56
Brookfield Visc. (100 rpm)	912	504	1000	665	824	335
Hercules Visc. (E bob, 6000 rpm)	31.3	32.7	28.9	59.1	33.3	26.2
Coating Gloss (Ct Wt = 6.804kg(15 lb)/rm	28.2	54.6	30.3	51.2	38.0	63.4

Table 10

Evaluation of Deionized Coatings and Their Analogs Containing Calcium Carbonate						
	G	H	I	J	K	L
Commercial #1 Clay	77			27		
Deionized #1 Clay		77	77		27	27
Ground Carbonate (90%<2 um)	10	10		60	60	
Deionized Ground Carbonate (90%<2μm)			10			60
Styrene/Butadiene Latex	10			10		
Deionized Styrene/Butadiene Latex		10	10		10	10
Corn Starch	3			3		
Deionized Corn Starch		3	3		3	3
Solids (%)	60	60	60	60	60	60
Conductivity (millimhos)	2.05	0.85	0.74	1.08	0.77	0.59
Brookfield Visc. (100 rpm)	720	489	575	1174	691	424
Hercules Visc. (E bob, 6000 rpm)	33.4	38.3	36.9	31.2	45.4	37.7
Coating Gloss (Ct Wt = 6.804kg(15 lb)/rm)	29.1	47.0	44.3	18.6	28.5	36.0

Example 6

A conventional clay based paper coating and its deionized analog were prepared using the formulations shown in Table 11. These two coatings were applied to a wood-free base sheet with a rigid blade at 457.2m (1500 feet) per minute on a high speed pilot coater. Sheets of the coated paper were supercalendered on a handsheet supercalender. The test results in Table 11 show that the deionized coating at 64% solids has higher shear viscosity equivalent to its convention analog at 60. 5% solids. In addition, the supercalendered paper with the deionized coating has higher gloss with improved smoothness and porosity.

Table 11

Comparison of a Deionized Clay Based
Coating and Its Conventional Analog

Values in the Table are percent of total dry weight
(coat weight of about 4.082kg(9 lb)/rm)

Commercial Fine Clay	65	
Deionized Commercial Fine Clay		65
Commercial #2 Clay	11	
Deionized Commercial #2 Clay		11
Titanium Dioxide	4	4
Plastic Pigment	7	
Deionized Plastic Pigment		7
Styrene/Butadiene Latex	12.7	
Deionized Styrene/Butadiene Latex		12.7
Polyvinyl Alcohol	0.3	0.3
Lubricant	1.0	1.0
Crosslinker	0.15	0.15
Coating Solids (%)	60.6	64.2
Conductivity (micromhos)	2370	1060
Brookfield Viscosity, 100 rpm (cP)	688	2164
Hercules Viscosity, E bob, 6000 rpm (cP)	18.4	19.4
Sheet Gloss	68.9	73.1
Smoothness (μ m)	1.04	0.76
(Parker Print Surf, 20 kg)		
High Pressure Porosity (sec/100 cc)	201.2	170.5

Example 7

A conventional calcium carbonate based paper coating and its deionized analog were prepared using the formulations shown in Table 12. These two coatings were applied to a wood-free base sheet with a bent blade at 457.2m(1500 feet)per minute on a high speed pilot coater. Sheets of the coated paper were supercalendered on a handsheet supercalender. The test results in Table 12 show that the deionized coating at 69% solids has lower low shear viscosity and equivalent high shear viscosity to its conventional analog at 67% solids. In addition, the supercalendered coated sheet with the deionized coating has higher gloss.

Table 12

Comparison of a Deionized Calcium Carbonate
Based Coating and Its Conventional Analog

Values in the Table are percent of total dry weight
(coat weight of about 4.536kg(10 lb)/rm

Calcium Carbonate	50	
Deionized Calcium Carbonate		50
Commercial #1 Clay	25	
Deionized Commercial #1 Clay		25
Titanium Dioxide	5	5
Plastic Pigment	7	
Deionized Plastic Pigment		7
Styrene/Butadiene Latex	10	
Deionized Styrene/Butadiene Latex		10
Corn Starch	3.0	
Deionized Corn Starch		3.0
Lubricant	1.0	1.0
Crosslinker	0.25	0.25
Solids (%)	67	69
Conductivity (micromhos)	2170	650
Brookfield Viscosity (100 rpm)	2400	480
Hercules Viscosity (E bob, 6000 rpm)	45.0	48.7
Sheet Gloss	60.5	63.7

Claims

1. A paper coating composition comprising clay and/or calcium carbonate slurry and a latex, characterised in that said clay is deionized and has a conductivity less than about 1500 micromhos as a slurry of 70% solids, said calcium carbonate is deionized and has a conductivity less than about 700 micromhos as a slurry of 70% solids.
2. A paper coating composition according to Claim 1, further characterised in containing about 1 to 35% titanium dioxide as solids.
3. A paper coating composition according to Claim 1, further characterised in that said latex is deionized.
4. A paper coating composition according to Claim 1, further characterised in containing a hydrocolloid.
5. A paper coating composition according to Claim 4, further characterised in that said composition contains 1 to 10% starch based on total solids.
6. A paper coating composition according to Claim 4, further characterised in that said hydrocolloid has a conductivity less than about 0.5 millimhos at 2% total solids and 23 °C.
7. A paper coating composition according to Claim 6, further characterised in that said composition contains about 30 to 100% deionized clay or calcium carbonate based on total pigment present.
8. A paper coating composition according to Claim 1, wherein said composition contains deionized clay, and is further characterised in that the clay exhibits a conductivity less than about 1.3 millimhos when present in an amount of 60% by weight at 23 °C.
9. A paper coating composition according to Claim 1, wherein said composition comprises deionized calcium carbonate, and is further characterised in that said calcium carbonate has a conductivity less than about 0.8 millimhos at 60% total solids and 23 °C.

10. A paper coating composition according to Claim 1, further characterised in that said latex is selected from styrene-butadiene latices, acrylic latices and polyvinyl acetate latices.
- 5 11. A paper coating composition according to Claim 10, further characterised in that said composition contains about 10 to 40% latex based on total solids.
12. A paper coating composition according to Claim 1, comprising deionized clay and being further characterised in that said clay is a kaolin clay.
- 10 13. A slurry of deionized clay, said deionized clay being present in an amount of about 60 to 75%, and said slurry having a conductivity of less than about 1500 micromhos at 70% solids, said slurry not including polyacrylamide.
- 15 14. A deionized clay obtainable by drying the slurry of Claim 13.
- 15 15. A slurry of deionized calcium carbonate containing about 70 to 80% deionized calcium carbonate, and having a conductivity less than about 700 micromhos at 70% solids, said slurry not including polyacrylamide.
- 20 16. A deionized calcium carbonate obtainable by drying the slurry of Claim 15.

Patentansprüche

- 25 1. Papier-Beschichtungsmasse, umfassend eine Ton- und/oder eine Calciumcarbonat-Aufschlämmung und einen Latex, dadurch gekennzeichnet, daß der Ton deionisiert ist und einen Leitwert hat, der geringer ist als 1.500 Micro-Siemens (micromhos) als eine Aufschlämmung mit 70 % Feststoffen, daß das Calciumcarbonat deionisiert ist und einen Leitwert hat, der geringer ist als 700 Micro-Siemens als eine Aufschlämmung mit 70 % Feststoffen.
- 30 2. Papier-Beschichtungsmasse nach Anspruch 1, dadurch gekennzeichnet, daß sie etwa 1 - 35 % Titandioxid als Feststoff enthält.
- 3 3. Papier-Beschichtungsmasse nach Anspruch 1, dadurch gekennzeichnet, daß der Latex deionisiert ist.
- 35 4. Papier-Beschichtungsmasse nach Anspruch 1, dadurch gekennzeichnet, daß sie ein Hydrocolloid enthält.
- 5 5. Papier-Beschichtungsmasse nach Anspruch 4, dadurch gekennzeichnet, daß in der Masse 1 - 10 % Stärke, basierend auf dem Gesamt-Feststoffgehalt, enthalten ist.
- 40 6. Papier-Beschichtungsmasse nach Anspruch 4, dadurch gekennzeichnet, daß das Hydrocolloid einen Leitwert von weniger als etwa 0,5 Micro-Siemens bei 2 % Gesamt-Feststoffgehalt und 23 °C hat.
- 45 7. Papier-Beschichtungsmasse nach Anspruch 6, dadurch gekennzeichnet, daß die Masse etwa 30 - 100 %, basierend auf dem gesamten vorhandenen Pigment-Gehalt, deionisierten Ton oder deionisiertes Calciumcarbonat enthält.
- 50 8. Papier-Beschichtungsmasse nach Anspruch 1, mit einem Gehalt an deionisiertem Ton, dadurch gekennzeichnet, daß der Ton einen Leitwert von weniger als etwa 1,3 Micro-Siemens zeigt, wenn er in einem Anteil von 60 Gew.-% bei 23 °C vorhanden ist.
- 55 9. Papier-Beschichtungsmasse nach Anspruch 1, mit einem Gehalt an deionisiertem Calciumcarbonat, dadurch gekennzeichnet, daß das Calciumcarbonat einen Leitwert von weniger als etwa 0,8 Micro-Siemens zeigt, wenn sein Anteil 60 % an den gesamten Feststoffen bei 23 °C beträgt.
10. Papier-Beschichtungsmasse nach Anspruch 1, dadurch gekennzeichnet, daß der Latex ausgewählt ist aus der Gruppe: Styrol-Butadien Latices, acrylische Latices und Polyvinyl-Acetat Latices.

11. Papier-Beschichtungsmasse nach Anspruch 10, dadurch gekennzeichnet, daß die Masse etwa 10 - 40 % Latex, gemessen am Gesamt-Feststoffgehalt, enthält.

5 12. Papier-Beschichtungsmasse nach Anspruch 1, enthaltend deionisierten Ton, dadurch gekennzeichnet, daß der Ton ein Kaolin-Ton ist.

10 13. Aufschlämmung aus deionisiertem Ton, mit einem Gehalt von etwa 60 - 75 % an deionisiertem Ton und mit einem Leitwert von weniger als etwa 1.500 Micro-Siemens bei einem Feststoffgehalt von 70 %, wobei die Aufschlämmung kein Polyacrylamid enthält.

14. Deionisierter Ton, erhältlich durch Trocknung der Aufschlämmung gemäß Anspruch 13.

15 15. Aufschlämmung von deionisiertem Calciumcarbonat, die etwa 70 - 80 % deionisiertes Calciumcarbonat enthält und einen Leitwert von weniger als 700 Micro-Siemens bei 70 % Feststoffgehalt zeigt, wobei die Aufschlämmung kein Polyacrylamid enthält.

16. Deionisiertes Calciumcarbonat, erhältlich durch Trocknung der Aufschlämmung gemäß Anspruch 15.

Revendications

20 1. Une composition pour enduire le papier comprenant de l'argile et/ou un coulis de carbonate de calcium et un latex, caractérisée en ce que ladite argile est déionisée et possède une conductivité inférieure à environ 1500 microhms pour un coulis à 70% de solides, ledit carbonate de calcium est déionisé et possède une conductivité inférieure à environ 700 microhms pour un coulis à 70% de solides.

25 2. Une composition pour enduire le papier selon la revendication 1, caractérisée en ce qu'elle contient environ 1 à 35% de dionide de titamium en solides.

30 3. Une composition pour enduire le papier selon la revendication 1, caractérisée en ce que le latex est déionisé.

4. Une composition pour enduire le papier selon la revendication 1, caractérisée en ce qu'elle contient un hydrocolloïde.

35 5. Une composition pour enduire le papier selon la revendication 4, caractérisée en ce que ladite composition contient de 1 à 10% d'amidon en poids de solides.

6. Une composition pour enduire le papier selon la revendication 4, caractérisée en ce que l'hydrocolloïde possède une conductivité inférieure à environ 0,5 milliohms pour un total de 2% de solides et à 23 ° C.

40 7. Une composition pour enduire le papier selon la revendication 6, caractérisée en ce que ladite composition contient environ 30 à 100% d'argile déionisée ou de carbonate de calcium par rapport au poids total des pigments présents.

45 8. Une composition pour enduire la papier selon la revendication 1, contenant de l'argile déionisée et caractérisée en ce que l'argile possède une conductivité inférieure à 1,3 millohms lorsqu'elle représente un total de 60% en poids à 23 ° C.

50 9. Une composition pour enduire le papier selon la revendication 1, comprenant du carbonate de calcium déionisé, et caractérisée en ce que ledit carbonate de calcium possède une conductivité inférieure à environ 0,8 milliohms pour 60% de solides et à 23 ° C.

10. Une composition pour enduire le papier selon la revendication 1, caractérisée en ce que le latex est sélectionné à partir de réseaux styrène-butadiène, acryliques et d'acétate de polyvinyle.

55 11. Une composition pour enduire le papier selon la revendication 10, caractérisée en ce qu'elle contient environ 10 à 40% de latex en poids de solides.

12. Une composition pour enduire le papier selon la revendication 1, comprenant de l'argile déionisée et caractérisée en ce que ladite argile est un kaolin.

5 **13.** Un coulis d'argile déionisée, ladite argile déionisée étant présente dans des proportions d'environ 60 à 75%, et ledit coulis possédant une conductivité inférieure à environ 1500 microhms pour 70% de solides, et ne comportant pas de polyacrylamide.

14. Une argile déionisée pouvant être obtenue en séchant le coulis de la revendication 13.

10 **15.** Un coulis de carbonate de calcium déionisé contenant environ 70 à 80% de carbonate de calcium déionisé et possédant une conductivité inférieure à environ 700 microhms pour 70% de solides, ledit coulis ne comprenant pas de polyacrylamide.

15 **16.** Un carbonate de calcium déionisé pouvant être obtenu en séchant le coulis de la revendication 15.

20

25

30

35

40

45

50

55