

UNITED STATES PATENT OFFICE

2,232,352

PRODUCTION OF MAGNETIC MATERIAL

Evert Johannes Willem Verweij, Jan Hendrik de Beer and Theodorus Anthonius Spoor, Eindhoven, Netherlands, assignors, by mesne assignments, to Radio Corporation of America, New York, N. Y., a corporation of Delaware

No Drawing. Application April 26, 1937, Serial No. 139,000. In Germany April 29, 1936

3 Claims. (Cl. 91-68)

It is common to produce magnetic cores for intermediate and high frequency purposes from finely powdered magnetic material, such as iron or ferromagnetic alloys, by compressing the particles by means of a binding agent to form a solid material. For the purpose of avoiding conductive relative contact between the said particles, various methods have been proposed according to which these particles are provided, prior to squeezing, with an insulating film. Thus, for example, it has been described to superficially attack the particles chemically by treating iron particles with a phosphoric acid solution or a solution of a phosphoric acid compound, a ferric phosphate film being formed on the said particles due to the reaction with the iron.

According to the invention, in contradistinction thereto, a film of a phosphoric acid metal compound is mounted on the magnetic particles without these particles assisting genetically in the film formation, which can be ensured by precipitation of the phosphoric acid metal compound from a dispersion which practically does not attack the magnetic particles.

The invention offers the advantage that shape and dimensions of the magnetic particles remain unaltered since for the formation of the insulating film no material of the magnetic particles is chemically transformed. This is particularly conducive to uniform manufacture since the quantity of insulating material per particle of the magnetic material can be controlled without any difficulty to a sufficiently accurate extent, which is substantially more difficult with chemical attack of the surface since the rate and the uniformity of the chemical attack per particle can only be controlled with difficulty. The fact that in accordance with the invention no gas development as a result of chemical reaction arises is also conducive to uniformity.

The invention is consequently particularly adapted for use with magnetic particles the dimensions of which are in the order of magnitude to a few μ , the thickness of the insulating films to be obtained not exceeding 20 μ .

Since in accordance with the invention the magnetic particles have been provided with a thin insulating film, the magnetic powder thus obtained can be given any shape by compression. In order to increase the mechanical strength of the magnet core a binding agent may be used with advantage in a manner known per se after the insulating film is mounted. For this purpose, use may be made, for example, of a synthetic resin which may be capable of being hardened.

In the use of a resin capable of being hardened, even distribution of the magnetic particles in the final product may be assisted by grinding the material after mixture with the resin, by next giving it at ordinary temperatures the desired shape and by then heating it to cause it to harden.

Example I

1 kg. of magnetic powder is introduced into 1 litre of a 2 normal solution of aqua-ammonia containing 60 milliequivalents of zinc ion and 60 milliequivalents of phosphate ion. The excess of aqua-ammonia is then removed by boiling while shaking continuously so that all the zinc phosphate present in the solution is precipitated on the surface of the particles. After being filtered and dried, the powder is squeezed into the desired shape at a pressure of about 5000 kg./cm.²

II

1 kg. of magnetic powder is intimately mixed with about 100 cm.³ of a 2 normal solution of aqua-ammonia containing 30 milliequivalents of zinc ion and 45 milliequivalents of phosphate ion per 100 cm.³ The paste thus obtained is kneaded while evaporating the excess of aqua-ammonia and water, which may be effected while heating to a low extent or in vacuo at ordinary temperatures. The material is then completely dried and ground to form a powder which is mixed with an alcohol solution containing 60 grams of a hardening phenolformaldehyde condensation product. After volatilisation of the solvent the powdering operation is renewed and the powder is then squeezed at 150° C. into the desired shape, it being possible to apply a squeezing pressure of 1500 kg./cm.²

In order to avoid the presence of other electrolytes which would affect the properties of the core, the ammoniacal zinc phosphate solution may be obtained by newly precipitated zinc hydroxide being dissolved in a concentrated solution of aqua-ammonia, by a dilute phosphoric acid solution being next added and by the solution being then given the desired concentration by dilution.

III

1 kg. of magnetic powder is intimately mixed with about 100 cm.³ of a weakly-acid ferric phosphate solution containing 30 milliequivalents of ferri-ion and 30 milliequivalents of phosphate ion per 100 cm.³ The paste is evaporated and dried, while kneading, in the manner described in the second example. The material thus ob-

tained is reduced to the form of a powder and mixed with an acetone solution containing 50 grams of the commercial resin known under the registered trade mark "plastopal H". After volatilisation of the solvent, the material is squeezed into the desired shape at ordinary temperatures, it being possible to apply a pressure of 5000 kg./cm.²

IV

10] 1 kg. of magnetic powder is intimately mixed with about 100 cm.³ of a 2 normal solution of aqua-ammonia containing 30 milliequivalents of cupri-ion and 45 milliequivalents of phosphate ion per 100 cm.³ and the mixture is evaporated to dryness and powdered, while kneading, in the manner described in the second example. The powder is agitated in a solution containing 60 grams of a hardening phenolformaldehyde condensation product and is then evaporated to dryness while shaking. The material thus obtained is reduced to the form of a powder and then squeezed at ordinary temperatures at a pressure of about 5000 kg./cm.² The cores thus obtained are hardened in a furnace by heating for three hours at 130° C.

The quantities, indicated in the examples described, of the substances used are chosen to accord with the specific weight of the iron and an average size of the particles of 3 μ as possessed by certain known commercial powdered iron by means of which the invention yields particularly favourable results.

What we claim is:

35] 1. A process of providing particles of ferro-magnetic-metallic material with a coating of in-

sulation material substantially entirely by precipitation of phosphoric acid metal compound from a dispersion which has substantially no chemical reaction with the magnetic material itself whereby the original size of the magnetic particles is substantially unaffected during the process, which consists in intimately mixing comminuted ferro-magnetic-metallic material with a compound comprising weakly-acid ferric phosphate solution containing substantially equal molecular amounts of ferri-ion and phosphate-ion to form a paste, drying the mixture while subjecting it to a kneading action and thereafter comminuting the resulting material.

2. The process described in the next preceding claim characterized by that each kilogram of ferro-magnetic-metallic material is mixed with approximately 100 cubic centimeters of weakly-acid ferric phosphate solution containing 30 milliequivalents of ferri-ion and 30 milliequivalents of phosphate ion.

3. The steps in a process of providing particles of ferro-magnetic-metallic material with a coating of insulation material which consist in intimately mixing comminuted ferro-magnetic-metallic material with a compound comprising weakly-acid ferric phosphate solution containing substantially equal molecular amounts of ferri-ion and phosphate-ion, and drying the mixture while subjecting it to substantially continuous agitation.

EVERT JOHANNES WILLEM VERWEIJ.
JAN HENDRIK DE BOER.
THEODORUS ANTHONIUS SPOOR.