

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
3 February 2005 (03.02.2005)

PCT

(10) International Publication Number
WO 2005/010069 A1

(51) International Patent Classification⁷: **C08G 18/62**,
18/79, C09D 175/04, C08K 3/22

(21) International Application Number:
PCT/US2004/023668

(22) International Filing Date: 22 July 2004 (22.07.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
10/625,072 22 July 2003 (22.07.2003) US

(71) Applicant (for all designated States except US): **E.I. DUPONT DE NEMOURS AND COMPANY** [US/US];
1007 Market Street, Wilmington, DE 19898 (US).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **MILIC, Richard**
[CZ/CZ]; Uhelna 482, 03 Hradec, CZ-500 Kralov (CZ).

(74) Agent: **BENJAMIN, Steven, C.**; E. I. Du Pont De Nemours and Company, Legal Patent Records Center, 4417 Lancaster Pike, Wilmington, DE 19805 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: AQUEOUS COATING COMPOSITION

(57) Abstract: An aqueous coating composition comprising (a) 10 to 60 wt% of an aqueous dispersion comprising water and one or more water-dilutable binders selected from the group of polymethacrylic, polyacrylic, polyester, polyurethane, hybride polyacrylic/polyester or polyacrylic/polyurethane, epoxy modified binders, with linear, branched or star structure and any mixtures thereof, the amount of said water constituting at least 15 wt% based on the total weight of said component a), (b) 5 to 40 wt% of one or more water-dispersible polyisocyanates or mixtures of water-dispersible and water-emulsifiable polyisocyanates, blocked or unblocked, (c) 5 to 70 wt% of filler material, (d) 1 to 40 wt% of a ground polymer material, (e) 0 to 15 wt% of organic co-solvents, (f) 0.01 to 15 wt% of additives, pigments and fillers, and (g) 3 to 30 wt% of water and the invention is directed to a process for applying the aqueous coating to substrates to form decorative surfaces and to the resulting coated substrates.



WO 2005/010069 A1

AQUEOUS COATING COMPOSITION

Field of the Invention

5 The invention relates to an aqueous coating composition applied as a one-layer coating or a multi-layer coating on a substrate that provides a surface having a stone, marble or granite-like effect and unique aesthetics, and to a process for coating the composition on a substrate.

Background of the Invention

10 Coatings for substrates used in industrial and house-keeping fields, e.g., for surfaces in kitchens, baths and stores or for wall panels, furniture and other articles in home and business sectors, can have a solid color or stone, granite, or marble-like or other unique appearance.

15 Such coatings comprise a filled polymer composition that is cured at ambient temperature or can be force-dried at elevated temperature. The coated articles can be costly to produce and difficult to transport and to install due to their heavy and brittle properties, e.g., they are fragile and easily chipped, broken or abused. The breakage rate at the required
20 thickness makes these articles expensive.

 Examples for known coatings and coated substrates are described as follows: JP 10128911, JP 8295548, JP 55126583, which relate to coating layers based on thermoplastic resins, such as, polyester, acrylic resins, and reinforced fiber.

25 US 5,789,032 relates to a curable composition including polyester resin and filler useful for the production of stone, marble, or granite effect coatings. A vibration action is needed to level the composition and to form an equable coating on the surface.

30 The present invention satisfies the demand for a decorative and robust coating for interior and exterior surfaces, especially for horizontal and vertical working tops, panels; furniture in homes, offices or industrial buildings; counter and dining tables, counter tops, floors; architectural facing of buildings and various articles (lamps, vases, picture frames, etc.) of all types.

Summary of the Invention

The present invention is directed to an aqueous coating composition comprising

- 5 (a) 10 to 60 wt% of an aqueous dispersion comprising water and one or more water-dilutable binders selected from the group of polymethacrylic, polyacrylic, polyester, polyurethane, hybride polyacrylic/polyester or polyacrylic/polyurethane, epoxy modified binders, with linear, branched or star structure and any mixtures
10 thereof, the amount of said water constituting at least 15 wt% based on the total weight of said component a),
- (b) 5 to 40 wt% of one or more water-dispersible polyisocyanates or mixtures of water-dispersible and water-emulsifiable polyisocyanates, blocked or unblocked,
- 15 (c) 5 to 70 wt% of filler material,
- (d) 1 to 40 wt% of a ground polymer material,
- (e) 0 to 15 wt% of organic co-solvents,
- (f) 0.01 to 15 wt% of additives, pigments and fillers, and
- (g) 3 to 30 wt% of water.

20 The composition is formed as a flowable liquid and is cured after application on the substrate. The cured coating can be sanded and polished. The final article can be cut into a desired shape if necessary.

The appearance of the final coating prepared from the coating composition according to the invention is characterized by a solid and/or a
25 stone-, granite-, marble-like appearance or other special aesthetic appearance. The articles produced with the coating composition according to the invention can be used as decorative surfaces, e.g., countertops, wall panels, for furniture, for floors, and for all types of various articles. The coatings and the coated products are robust and stable and are workable
30 and repairable. The coatings can be applied in a factory or on location. They have an appearance of stone, cultured marble or granite, such as the material Corian®.

The present invention is also directed to a process for coating a substrate comprising applying the coating composition according to the

invention on the substrate within a dry thickness layer range from 15 to 25 mils (0.381 to 0.635 mm) by a single application and curing said coating.

The composition can be characterized as a low VOC (Volatile Organic Content) composition.

5

Detailed Description of the Invention

The content of the aqueous dispersion, component a), is from 10 to 60 wt%, preferably from 20 to 50 wt%, based on the coating composition.

10 The aqueous dispersion, component a), is based on water-dilutable binders.

The binders of component a) are functionalized by hydroxy and/or carboxy and/or amino groups. The OH-value and the COOH-value can be, for example, in the range from 10 to 300. Particularly preferred, are hydroxy and/or carboxy functionalized polymers having an OH-value in the
15 range of 10 to 300 and a carboxy value of 10 to 50. If amino groups are present, hindered secondary amino groups are preferred.

The functionalized polymers can be manufactured by emulsion polymerization reactions known by a skilled person, by a radical polymerization but also, e.g., by a polymerization reaction caused by a
20 photochemical reaction or by electromagnetic radiation or by polycondensation reaction followed emulsification in water. Group Transfer Polymerization can also be used. Emulsion polymerization is preferred.

The polymers can be linear, branched or star structured.

Suitable monomers or co-monomers for the manufacture of the
25 acrylic and methacrylic binders of component a) may be, e.g., acrylates, methacrylates, methyl methacrylates, styrene, acrylonitrile, vinyl acetate, butadiene, including monomers, such as, acrylic acid, methacrylic acid, itaconic acid, maleic acid, crotonic acid and/or amides. To obtain the functionalized polymethacrylics and polyacrylics, suitable monomers can be
30 incorporated into the polymer, e.g., carboxy-functionalized monomers, such as, maleic acid, acrylic acid and methacrylic acid, and, for example, hydroxy-functionalized monomers, such as, hydroxy acrylates, hydroxy methyl acrylates, propylene glycol methacrylates, butanediol monoacrylates and the like.

Suitable monomers or co-monomers for the manufacture of the functionalized polyesters or polyurethanes may be, for example, neopentyl glycol, cyclohexanedimethanol, 1,6 hexanediol, trimethylolpropane, pentaerythritol, phthalic anhydride, isophthalic acid, hexahydrophthalic anhydride, adipic acid, azelaic acid and dimer fatty acids.

The polyesters or polyurethanes can be, for example, linear, branched, star structured, chemically modified by silicones, styrene, acrylics, epoxide, and the range of the OH value can be 10 to 300.

Star resins may be used as binders of component a) and are oligomers with a star structure, which have 3 to 6 arms. Oligomers are prepared by reaction of trimethylolpropane, pentaerythritol or other multifunctional compounds with, e.g., compounds containing glycidyl groups. They include polyester bonds and both primary and secondary hydroxyl groups.

As binders of component a) one or more polyacrylic, polymethacrylic, polyester, polyurethane and/or star polymers are preferred.

The polymers of component a) are contained in the range from about 85 to 20 wt%, preferably from about 70 to 25 wt%, based on component a).

The binders can also be used as aqueous dispersion that is directly produced from the emulsion polymerization of the binder monomers or co-monomers, as component a). This use is preferred.

The aqueous dispersion, component a), contains at least 15 wt% of water. An amount of said water in a range of 30 to 75 wt%, based on the dispersion, is preferred.

Examples of polyisocyanates that may be used as component b) are in the free or blocked form as crosslinking agents and may include triisocyanates, diisocyanates, and cycloaliphatic diisocyanates, such as, 1,6-hexane diisocyanate, trimethylhexane diisocyanates, 1,12-dodecanediisocyanates, cyclohexane diisocyanates, isophorones, diisocyanates with cyclohexylmethane diisocyanates or mixtures thereof, and polyisocyanates derived from such diisocyanates, for example, those containing hetero atoms in the radical linking the isocyanates groups. Examples thereof include polyisocyanates containing carbo diimide groups, isocyanurate groups, urethdiol groups, urethane groups and/or biuret groups.

Polyisocyanates that may be used as component b) are hydrophilically modified, water-dispersible products or mixtures of both hydrophilic and hydrophobic polyisocyanates, that means mixtures of both water-dispersible and water-emulsifiable products.

5 Suitable blocking agents for the polyisocyanate crosslinking agents described above may include the conventional, for example, CH-acidic, NH-, SH- or OH-functional blocking agents. Examples include acetyl, acetone, acetoacetic acid acyl esters, valonic acid diacyl esters, aliphatic or cycloaliphatic alcohols, oximes, lactams, imidacoles, pyracoles.

10 Isocyanurates, biurets, uretdions, or allofanates of 1,6-hexane diisocyanate are the preferred compounds of component b).

 When using free (unblocked) polyisocyanates as component b), the coating composition according to the invention is prepared by keeping the polyisocyanate component b) separate from component a) and then shortly
15 before application component b) is thoroughly mixed with component a) and the other components of the coating composition.

 The polyisocyanates, component b), are contained in the range from about 5 to 40 wt%, preferably from about 5 to 20 wt%, based on the coating composition.

20 The coating composition according to the invention contains a filler material as component c). The content of this filler material is from 5 to 70 wt%, preferably 10 to 60 wt%, based on the coating composition. Examples of the filler material are aluminum hydroxide, also known as alumina trihydrate, $\text{Al}_2\text{O}_3 \cdot 3 \text{H}_2\text{O}$, calcium carbonate (CaCO_3), Silica (SiO_2),
25 magnesium hydroxide ($\text{Mg}(\text{OH})_2$), barium sulfate (BaSO_4), clays, talcs, alumina monohydrate ($\text{Al}_2\text{O}_3 \cdot \text{H}_2\text{O}$) or polymeric fillers.

 Preferably, aluminum hydroxide, $\text{Al}_2\text{O}_3 \cdot 3 \text{H}_2\text{O}$, is used as component c).

 The component d) is a small-grained solid material, which is different from component c), and which is a ground polymer material. The content of
30 this component is from 1 to 40 wt%, preferably 2 % to 30 wt%, based on the coating composition.

 This material can be based on polymethyl methacrylate (pMMA), crosslinked unsaturated polyester, epoxide or other polymeric material – filled or unfilled.

This material can be ground or calendered by mills, grinders or calender to small particles like granules, crunchies, flakes, and powder particles. The material can be toned in different colors or in one color. Examples of additives used in this material are, e.g., colorants,

5 antioxidants, catalysts, light stabilizers, and also fillers. One example for the component d) is a filled polymer material consisting of about 40% of polymethyl methacrylate, of about 60% of aluminum hydroxide, colorants, and other additives at low levels, for example, known under the name of Corian[®], which is a product of DuPont.

10 Examples of organic co-solvents that may be used in the coating composition according to the invention as component e) include glycol ether esters, such as, ethyl glycol acetates, butyl diglycol acetates, methoxypropyl acetates; esters, such as, propylenecarbonate(4-methyl-1,3-dioxolan-2-on), ethyl acetate, butyl acetate, isobutyl acetate, amyl acetate;
15 ketones, such as, methyl ethyl ketone, methyl propyl ketone, methyl isopropyl ketone, methyl isobutyl ketone, diisobutyl ketone, methyl amyl ketone, cyclohexanone, isophorones; aromatic hydrocarbons, such as, toluene, xylenes, Solvesso[®] 100 (mixture of aromatic hydrocarbons with a boiling range from 155 to 185°C), Solvesso[®] 150 (mixture of aromatic
20 hydrocarbons with a boiling range from 182 to 202°C), and aliphatic hydrocarbons. The organic co-solvents are contained in the range from 0 to 15 wt%, preferably in a range of 0 to 5 wt%, based on the coating composition.

The coating composition may contain conventional coating additives,
25 pigments and fillers in total amount up to 15 wt.% based on coating composition ready for application, as component f).

Additives are, for example, leveling and anticratering agents, defoamers, dispersing and wetting additives, rheological modifiers, such as, pyrogenic silica, modified clays, polyamides and urea group-containing
30 reaction products of amines (sagging control agents), catalysts, colorants, light stabilizers, UV absorbers, antioxidants and the like.

Depending on the intended use of the coating composition and on the integrated components, the coating composition may be unpigmented (transparent), translucent, or contain pigments. They may therefore contain
35 fillers, which are different from the component c) and/or transparent, color imparting and/or special effect-imparting pigments. Examples of inorganic or organic color-imparting pigments include titanium dioxides, micronized

titanium dioxide, iron oxide pigments, carbon black, azo pigments, phthalocyanine pigments, quinacridone or pyrrolopyrrole pigments.

Examples of special effect-imparting pigments include metallic pigments, interference pigments, e.g., metal oxide coated metallic pigments, e.g.,

- 5 titanium dioxide-coated or mixed oxide-coated aluminum, coated mica, e.g. titanium dioxide-coated mica and graphite effect like special-effect pigments. Examples of suitable fillers include aluminum trihydrate, silica, aluminum silicates, barium sulfates, calcium carbonates, and talc.

Optionally, any material may be added for a decorative effect.

- 10 Decorative additives, such as, crushed stones, gemstones, metal flake or fillings, micas, seashells, pearls, colored or transparent polymeric particles or fibers, mirrored particles and pigments may be added in quantities according to taste or fashion. However, these quantities usually do not exceed 5 wt%, preferably 2 wt%. The decorative additives may be
- 15 thoroughly mixed with the other components or placed on the surface.

The water, component e), is preferably deionized water (d.i.water). The content is from 3 to 30 wt%, preferably from 5 to 20 wt%, based on the coating composition.

- The coating composition according to the invention may have a
- 20 uniform color, a stone-like and/or a special aesthetic appearance.

- The coating composition according to the invention in the state ready for application has a solids content, formed from the polymer solids and the optionally contained non-volatile additives and optionally contained pigments, from 40 to 75 wt%. The coating composition contains water and
- 25 may contain organic co-solvents as mentioned above, as volatile constituents.

- The coating composition can take the form of a one-component coating composition or a two-component composition. In case of a two-component coating composition, one component contains the aqueous
- 30 dispersion, component a), and the other component contains the water-dilutable polyisocyanates, component b). The other components of the coating composition according to the invention, that means the filler material, the ground material, organic co-solvents, additives, pigments, fillers and water may be presented in either one or in both of the two
- 35 components. Preferably they may be present in the component, which contains the dispersion, component a).

The coating composition according to the invention may be used in the preparation of a one-layer coating on any substrates of, for example, metal, plastic, or substrates composed of a mixed construction of metal and plastic and of any other material, for example, clay, tile, woven glass fiber, masonites and the like. Substrates employed include also plywood, particle board, medium-density fiber board (MDF board), tile board. These substrates can be used as products such as existing and in place counter tops, cabinets, wall panels, furniture, slabs board, ceramic tile, high pressure laminate (HPL), low pressure laminate and other such laminates, stainless steel, gypsum board, glass and the like. The coating composition may also be applied directly over ceramic tile/group installations in such a way that a seamless surface is formed with tile-like appearance.

The coating composition according to the invention can be applied directly on the untreated surface of a substrate, for example, of a porous substrate. It is also possible to use the coating composition according to the invention for a multi-layer coating of the substrate whereby the multi-layer coating may consist of several coating layers of the coating composition of the invention. Smooth or glass like surface should be coated, for example, by a 2-pack epoxy primer or other appropriate primer to ensure proper adhesion of the coating composition according to the invention. Preferably, the coating composition is used as a direct coating of the untreated surface of a porous substrate.

In the event the coating composition is used for outdoor purposes, for example, on the exterior of a building, the weatherability of the composition can be improved by the addition of an ultraviolet light stabilizer or a combination of ultraviolet light stabilizers in the amount of 0.1 to 5 wt%, based on the weight of the composition. Such stabilizers include ultraviolet light absorbers, screeners, quenchers, and specified hindered amine light stabilizers. Also, an antioxidant can be added, in the amount 0.1 to 2 wt%, based on the weight of the composition.

Typical ultraviolet light stabilizers that are useful include benzophenones, triazoles, triazines, benzoates, hindered amines and mixtures thereof. Specific examples of ultraviolet stabilizers are disclosed in U.S. Patent 4,591,533. Typically useful hindered amine light stabilizers that can be used are, for example, Tinuvin® 1130 and Tinuvin®292 or mixtures thereof, commercially available from Ciba Specialty Chemicals, Tarrytown, New York.

The coating composition according to the invention can be applied by known methods, e.g., via commercial spray gun equipment, preferably, by spray gun with pressured upper container. Particularly, it can be sprayed in a dry layer thickness of 10 to 25 mils (0.250 to 0.635 mm),
5 preferred 15 to 25 mils (0.381 to 0.635 mm) regarding a one-layer application. The final coating thickness of a multi-layer coating can be designed to be, for example, 40 to 80 mils (1.016 to 2.032 mm) or thicker, preferred 50 to 60 mils (1.270 to 1.524 mm), and can be built in 15 to 25 mils (0.381 to 0.635 mm) increments per single spray application
10 depending on the intended use.

The applied coating composition according to the invention can be cured by crosslinking at ambient temperature as well as at elevated temperature. It is desirable, but not necessarily, to have a short flash-off phase before start of the curing step at elevated temperature. The curing
15 temperature can vary from 15 to 100°C, particularly from 25 to 80°C. The curing times are, for example, of the order of magnitude of 20 min. to 24 hours. Preferably, the coating composition according to the invention is crosslinked at ambient temperature in the range of 15 to 35°C, preferably of 20 to 30°C in the time range to 24 hours. If forced drying is applied for
20 curing, temperature range 60 to 100°C is recommended, preferably of 60 to 80°C, in a time range of 20 to 60 minutes. A hard, crosslinked surface is obtained with a glossy lacquer-like appearance having good resistance to chemicals, outstanding mar resistance and very good optical properties.

The cured coating can be sanded and/or polished to achieve a
25 smooth surface of a desired thickness. The coated substrate or article can be cut into desired shapes.

The cured surface has a high quality that means scratch-resistance, stain-resistance, heat-resistance, chip-resistance and superior hardness.

It is possible to replace solid and/or cast materials, such as, marble
30 or granite slabs, walls, panels and the like by substrates coated with the coating composition according to the invention with a high stability and strength as well as a high weather-proof property with a good heat and stain resistance.

The coating composition can also be used for store fixtures, vertical
35 surfacing on substrates of all types and also horizontal surfacing. It could

replace wallpaper. Formulations can be used outdoors as architectural facings, for example, with a proper UV stabilization.

The following examples illustrate the invention. All parts and percentages are on a weight basis unless otherwise noted. Molecular weights are determined by gel permeation chromatography using polymethylmethacrylate as the standard.

Examples

Example 1

10 Preparation of coating compositions of the invention

Composition 1:

	Part A	Wt. %
1	Setalux® 6501 AQ-42 (Acrylic polyol with 4.2 % of OH groups, 42 wt.% emulsion in water, manufactured by AkzoNobel)	38.25
2	D.I. Water (deionized water)	9.67
3	Additol® XW 330 (30 wt.% aqueous solution of an ammonium salt of a low molecular weight polyacrylic acid, manufactured by Solutia)	0.38
4	Preventol® D7 (Aqueous, formaldehyde-free formulation of various isothiazolinones, manufactured by Bayer)	0.30
5	BYK® 028 (mixture of hydrophobic solids and foam destroying polysiloxanes, manufactured by BYK-Chemie GmbH)	0.96
6	Tego® Airex 901 W (deareator for water-based coating systems, manufactured by Degussa)	0.48
7	Bentone® EW (purified Hecorite clay used to thicken water based systems, manufactured by Elementis)	0.19
8	Aerosil® R972 (Fumed silica hydrophobically modified rheological additive having a BET value of 110 m ² /g, manufactured by Degussa)	1.92
9	Surfynol® 104 DPM (Mixture of acetylenic diols, manufactured by Air Products)	1.34
10	Solvesso® 100 (mixture of aromatic hydrocarbons with a boiling range from 155 to 185°C, manufactured by Shell)	1.82

11	Aluminum trihydrate, filler	24.55
12	Hindered Amine Light Stabilizer [Bis(1,2,2,6,6-pentamethyl-4-piperidyl) sebacate and methyl(1,2,2,6,6-pentamethyl-4-piperidyl) sebacate]	0.96
13	UV absorber (Methyl-3-[3-(2H-benzotriazol-2-yl)-5-tert.butyl-4-hydroxyphenyl]propionate)	0.48
14	Corian [®] Crunchies (Ground polymer material of polymethymethacrylate filled with alumina trihydrate and various fillers)	16.30
15	BYK [®] 346 (Solution of a polyether modified poly-dimethyl-siloxane, 45 wt% in Dowanol DPM, manufactured by BYK-Chemie GmbH)	0.96
16	DSX [®] 3290 (Associative rheology modifier, 50 wt.% in mixture butyl glycol/water 1:3, manufactured by Cognis)	1.44
Part B		
	Activator (Water-dispersible aliphatic polyisocyanate, 18 % NCO, manufactured by Bayer)	15.0

- Components 1 to 13 are premixed by high-speed disperser and then ground in bead mill to fineness of grinding 6 of Hegman scale. The resulting composition is immediately mixed stepwise with components 14 to 15 and then the rheology modifier (16) is carefully added. The final mixture is homogenized for about 20 minutes.

Before application, Part A is mixed with Part B in weight ratio 100 : 15.0. The composition is ready to use. If necessary it can be thinned with water.

10

Composition 2:

	Part A	Wt. %
1	Acrylic core-shell emulsion with composition MMA/EHA/HEMA/HPMA/TBAEMA/MAA, OH 4.1%, Solids 54.1%, Visco 440 cps, pH 8.6, Mn/Mw=3200/6100	29.41
2	D.I. Water	18.47
3	Pigment Disperser - A (30 wt.% aqueous solution of an	0.34

	ammonium salt of a medium molecular weight polyacrylic acid, manufactured by BASF)	
4	Preventol® D7 (Aqueous, formaldehyde-free formulation of various isothiazolinones, manufactured by Bayer)	0.30
5	Tego® Foamex 810 (foamer for water-based coating systems, 50 wt.% in Dovanol DPM, manufactured by Degussa)	0.49
6	Tego® Airex 901 W (deareator for water-based coating systems, manufactured by Degussa)	0.49
7	Bentone® EW (purified Hecorite clay used to thicken water based systems, manufactured by Elementis)	0.20
8	Aerosil® R972 (Fumed silica hydrophobically modified rheological additive having a BET value of 110 m ² /g, manufactured by Degussa)	2.00
9	Surfynol® 104 DPM (Mixture of acetylenic diols, manufactured by Air Products)	1.39
10	Kodaflex® TXiB (plasticizer, manufactured by Eastman)	0.89
11	Aluminum trihydrate, filler	26.20
12	Corian® Crunchies (Ground polymer material of polymethymethacrylate filled with alumina trihydrate and various fillers)	17.60
13	BYK® 346 (Solution of a polyether modified poly-dimethyl-siloxane, 45 wt% in Dowanol DPM, manufactured by BYK-Chemie GmbH)	1.02
14	DSX® 3290 (Associative rheology modifier, 50 wt.% in mixture butyl glycol/water 1:3, manufactured by Cognis)	1.20
Part B		
	Bayhydur 3100 (Water-dispersible aliphatic polyisocyanate, 17.4 % NCO, manufactured by Bayer)	1.83
	Desmodur® 3600 (Aliphatic polyisocyanate, 23.0 % NCO, manufactured by Bayer)	4.26
	Dowanol® PMA	1.51

Components 1 to 11 are premixed by high-speed disperser and then ground in bead mill to fineness of grinding 6 of Hegman scale. The resulting composition is immediately mixed stepwise with components 12 to

13 and then the rheology modifier (14) is carefully added. The final mixture is homogenized for about 20 minutes.

Before application, Part A is mixed with Part B in weight ratio 100 :

7.6. The composition is ready to use. If necessary it can be thinned with
5 water.

Composition 3:

	Part A	Wt. %
1	Luhdran® LR 8837 (Acrylic polyol with 2.0 % of OH groups, 40 wt.% emulsion in water, manufactured by BASF)	48.67
2	D.I. Water	9.36
3	Pigment Disperser - A (30 wt.% aqueous solution of an ammonium salt of a medium molecular weight polyacrylic acid, manufactured by BASF)	0.41
4	Preventol® D7 (Aqueous, formaldehyde-free formulation of various isothiazolinones, manufactured by Bayer)	0.36
5	BYK® 011 (mixture of hydrophobic solids and foam destroying polysiloxanes, manufactured by BYK-Chemie GmbH)	1.16
6	Tego® Airex 901 W (deareator for water-based coating systems, manufactured by Degussa)	0.59
7	Bentone® EW (purified Hecorite clay used to thicken water based systems, manufactured by Elementis)	0.24
8	Aerosil® R972 (Fumed silica hydrophobically modified rheological additive having a BET value of 110 m ² /g, manufactured by Degussa)	2.42
9	Surfynol® 104 DPM (Mixture of acetylenic diols, manufactured by Air Products)	1.85
10	Aluminum trihydrate, filler	31.72
11	BYK® 346 (Solution of a polyether modified poly-dimethyl-siloxane, 45 wt% in Dowanol® DPM, manufactured by BYK-Chemie GmbH)	1.23
12	DSX® 3290 (Associative rheology modifier, 50 wt.% in mixture butyl glycol/water 1:3, manufactured by Cognis)	1.97

	Part B	
	Basonat HW 180 PC (Water-emulsifiable polyfunctional isocyanurate, 80 wt.% in propylencarbonate, 14% NCO manufactured by BASF)	21.47
	Propylencarbonate	2.73
	Corian® Crunchies (Ground polymer material of polymethymethacrylate filled with alumina trihydrate and various fillers)	21.80

All components of Part A are premixed by high-speed disperser and then ground in bead mill to fineness of grinding 6 of Hegman scale.

Part B preparation: Corian® Crunchies are added in small amounts to the solution of Activator in propylencarbonate and the mixture is homogenized by high-speed dissolver.

Before application, Part A is mixed with Part B in weight ratio 100 : 46. The composition is ready to use. If necessary it can be thinned with water.

Example 2

Application on plywood substrate:

A mixture of both part A and B of Composition 2 from Example 1 is applied by spray gun with pressured upper container and jet nozzle diameter 2.3 mm on a plywood substrate. The pressure on spray gun jet nozzle is about 0.2 MPa and the overpressure in upper container is about 7 kPa. Wet thickness of the first layer should be maximally 10 mils (0.250 mm) to ensure good adhesion and low content of entrapped solvents close to the surface. After 1 hour of drying at ambient temperature, the film is force-dried in oven for one hour at 60°C. The second and the next layers are sprayed on the force-dried film after the substrate is cooled to room temperature and the thickness is about 15 mils (0.381mm). The resulting film is force dried at 60°C for 1 hour or can be dried at room temperature for at least 24 hours before the next layer is applied. When the required thickness is reached, about 60 mils (1.524 mm), the films are post-cured at 60 to 80°C for several hours to accelerate the hardness development and to improve sandability.

Example 3

Application on glazed ceramic tiles:

Commercially available two-pack epoxy primer was mixed with hardener and thinned to an application viscosity (flow time 18 to
5 20 seconds at Ford Cup with jet diameter 4 mm). A layer of film is applied by spraying on the tile substrate with a spray gun having a jet nozzle diameter of 18 mm and a jet nozzle pressure 0.17 to 0.2 MPa.

The primer was applied on smooth glazed ceramic tiles in wet thickness about 0.100 mm. This film was allowed to dry at ambient
10 temperature for 24 hours.

The mixture of both part A and B of Composition 1 from Example 1 was applied by spray gun with pressured upper container and jet nozzle diameter 2.3 mm. The pressure on spray gun jet nozzle is about 0.2 MPa and the overpressure in upper container is about 7 kPa. Each applied layer
15 has a dry film thickness about 15 mils (0.381 mm).

The first layer is dried for 1 hour at ambient temperature and then the film is force-dried in oven for one hour at 60°C. The second and the next layers are sprayed on the force-dried film after the substrate is cooled to room temperature. Forced drying at 60°C for 1 hour or room temperature
20 drying for at least 24 hours is necessary before the next layer is applied. When the required thickness is reached, about 60 (1.524), the coated films are cured at ambient temperature for several days to achieve appropriate film hardness for good sandability.

Example 4

Application on particle board substrate:

A mixture of both part A and B of Composition 3 from Example 1 is applied by spray gun with pressured upper container and jet nozzle diameter 2.3 mm on a substrate. The pressure on spray gun jet nozzle is
30 about 0.2 MPa; the overpressure in upper container is about 7 kPa.

Wet thickness of the first layer should be maximally 10 mils (0.250 mm) to ensure good adhesion and low content of entrapped solvents close to the surface. After 1 hour of drying at ambient temperature, the film is force-dried in oven for one hour at 60°C. The second and the next layers
35 are sprayed on the force-dried film after the substrate is cooled to room

- temperature and can be thicker - about 15 mils (0.381 mm). The film layers are forced dried at 60°C for 1 hour or can be dried at room temperature drying for at least 24 hours before the next layer is applied. When the required thickness is reached about 60 mils (1.524 mm), the coated films
- 5 are post-cured at 60 to 80°C for several hours to accelerate the hardness development.

CLAIMS**What is claimed is:**

1. An aqueous coating composition comprising
 - (a) 10 to 60 wt % of an aqueous dispersion comprising water and at least one water-dilutable binders selected from the group consisting of polymethacrylic, polyacrylic, polyester, polyurethane, hybride polyacrylic/polyester or polyacrylic/polyurethane, epoxy modified binders, with linear, branched or star structure and mixtures thereof, the amount of said water constituting at least 15 wt% based on the total weight of said component
 - (b) 5 to 40 wt% of at least one water-dispersible polyisocyanates or mixtures of water-dispersible and water-emulsifiable polyisocyanates, blocked or unblocked,
 - (c) 5 to 70 wt% of filler material,
 - (d) 1 to 40 wt% of a ground polymer material,
 - (e) 0 to 15 wt% of organic co-solvents,
 - (f) 0.01 to 15 wt% of additives, pigments and fillers, and
 - (g) 3 to 30 wt% of water.
2. The composition according to claim 1 wherein one or more binders selected from the group consisting of polyacrylics, polymethacrylics , polyesters, polyurethanes and polymers with star structure are used as component (a).
3. The composition according to claim 1 wherein component (b) is selected from the group consisting of isocyanurates, biurets, uretdions and allofanates of 1,6-hexane diisocyanate.
4. The composition according to claim 1 wherein component (c) comprises 10 to 60 wt. % of the coating composition.

5. The composition according to claim 4 wherein component c) is aluminium hydroxide.

6. The composition according to claim 1 wherein component d)
5 comprises 2 to 30 wt.% polymethyl methacrylate containing filler.

7. The composition according to claim 6 wherein component d) consists of about 40 wt. % polymethyl methacrylate, and 60 wt. % of aluminum hydroxide, colorants, and other additives at low levels.

10

8. The composition according to claim 1 wherein the amount of the water, component (g), is from 5 to 20 wt.%.

9. The composition according to claim 1 wherein the amount of the
15 organic co-solvents, component (e), is from 0 to 5 wt. %.

10. The composition according to claim 1, wherein component a) is directly manufactured from the emulsion polymerization of the binder monomers or co-monomers.

20

11. A process for coating a substrate which comprises applying a one-coat layer on a substrate within a dry thickness layer range from 15 to 25 mils (0.381 to 0.635 mm) using a coating composition according to claim 1 and curing said coating.

25

12. A process for forming a multi-layer coating which comprises applying several coating layers to a substrate within a dry thickness layer range from 15 to 25 mils (0.381 to 0.635 mm) for each layer using a coating composition according to claim 1 and curing said coating layers.

30

13. A process for forming a coating layer as one-coating layer of a multi-layer coating which comprises applying to a substrate a coating layer selected from the group consisting of externally pigmented top coat layer

and transparent clear coat layer said coating layer being applied from the coating composition according to claim 1 within a dry thickness layer range from 15 to 25 mils (0.381 to 0.635 mm) and curing said coating layer.

- 5 14. A substrate coated with the coating composition according to claim 1 and then cured.

INTERNATIONAL SEARCH REPORT

Int. Application No
PCT/US2004/023668

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08G18/62 C08G18/79 C09D175/04 C08K3/22

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08G C09D C08K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2003/096120 A1 (ARZT ANTON ET AL) 22 May 2003 (2003-05-22)	1,2,4,8, 9,14
Y	claims 1,2 page 10; table 1 paragraph '0080! paragraph '0085! paragraph '0101!	1,2,4,8, 9,11-14
Y	US 2003/049457 A1 (KOBOR FRANK ET AL) 13 March 2003 (2003-03-13) claims 9-12 page 5; examples 5,6	1,2,4,8, 9,11-14
Y	US 6 562 894 B1 (BLUM HARALD ET AL) 13 May 2003 (2003-05-13) claims 1,11,16 column 14, line 63	1-5,8,9, 11-14
	----- -/-- -----	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

9 November 2004

Date of mailing of the international search report

24/11/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Öhm, M

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US2004/023668

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 4 609 690 A (GRUBER NORMA J ET AL) 2 September 1986 (1986-09-02) column 6 - column 7; table 1 column 3, line 42 - line 46 -----	1,2,4,8, 10-14
Y	DE 43 38 265 C (HERBERTS GMBH) 8 December 1994 (1994-12-08) claim 1 examples column 2, line 49 - line 53 column 6, line 17 - line 35 column 6, line 48 - column 7, line 17 -----	1-5,8-14
P,A	EP 1 362 874 A (DU PONT) 19 November 2003 (2003-11-19) page 6 - page 8; example 1 claims -----	1-14
A	WO 97/40113 A (ADVANCED ADHESIVE TECHNOLOGY I) 30 October 1997 (1997-10-30) claims 1,6,7,9,11 -----	1-14

INTERNATIONAL SEARCH REPORT

 Inter. Application No
 PCT/US2004/023668

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 2003096120	A1	22-05-2003	AT 411062 B	25-09-2003
			AT 18192001 A	15-02-2003
			BR 0204696 A	16-09-2003
			CA 2411892 A1	19-05-2003
			CZ 20023755 A3	14-01-2004
			EP 1312629 A1	21-05-2003
			JP 2003213206 A	30-07-2003
			PL 357175 A1	02-06-2003
US 2003049457	A1	13-03-2003	DE 10138765 A1	20-02-2003
			CN 1405253 A	26-03-2003
			EP 1283230 A2	12-02-2003
US 6562894	B1	13-05-2003	DE 19858817 A1	29-06-2000
			DE 19858818 A1	29-06-2000
			AT 238365 T	15-05-2003
			AT 249486 T	15-09-2003
			AU 1972800 A	12-07-2000
			AU 1973000 A	12-07-2000
			CN 1331707 T	16-01-2002
			CN 1131876 B	24-12-2003
			CZ 20012260 A3	12-09-2001
			CZ 20012272 A3	12-09-2001
			DE 59905247 D1	28-05-2003
			DE 59906975 D1	16-10-2003
			DK 1144472 T3	11-08-2003
			DK 1144474 T3	15-12-2003
			WO 0037519 A1	29-06-2000
			WO 0037523 A1	29-06-2000
			EP 1144472 A1	17-10-2001
			EP 1144474 A1	17-10-2001
			ES 2198981 T3	01-02-2004
			ES 2207319 T3	16-05-2004
			HR 20010547 A1	31-08-2002
			HR 20010548 A1	31-08-2002
			HU 0104695 A2	28-03-2002
			HU 0200677 A2	29-06-2002
			PL 349447 A1	29-07-2002
			PL 358971 A1	23-08-2004
			PT 1144472 T	30-09-2003
			PT 1144474 T	27-02-2004
			SI 1144472 T1	31-12-2003
			SI 1144474 T1	29-02-2004
			SK 8412001 A3	06-11-2001
			SK 8422001 A3	03-12-2001
			TR 200101814 T2	21-12-2001
			TR 200101815 T2	21-11-2001
			TW 510916 B	21-11-2002
			US 6706801 B1	16-03-2004
US 4609690	A	02-09-1986	US 4491646 A	01-01-1985
			AU 548554 B2	19-12-1985
			AU 3366984 A	04-04-1985
			CA 1267992 A1	17-04-1990
			DE 3435777 A1	11-04-1985
			DK 463784 A ,B,	30-03-1985
			FI 843811 A ,B,	30-03-1985
			JP 60092376 A	23-05-1985

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US2004/023668

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4609690 A		NO 843873 A ,B, SE 463923 B SE 8404842 A	01-04-1985 11-02-1991 30-03-1985
DE 4338265 C	08-12-1994	DE 4338265 C1	08-12-1994
EP 1362874 A	19-11-2003	US 2004147671 A1 EP 1362874 A2 US 2004014864 A1	29-07-2004 19-11-2003 22-01-2004
WO 9740113 A	30-10-1997	US 5652288 A US 5721302 A CA 2251837 A1 EP 0894120 A1 WO 9740113 A1	29-07-1997 24-02-1998 30-10-1997 03-02-1999 30-10-1997