




(22) Date de dépôt/Filing Date: 2013/04/23
(41) Mise à la disp. pub./Open to Public Insp.: 2013/10/31
(45) Date de délivrance/Issue Date: 2021/05/18
(62) Demande originale/Original Application: 2 964 106
(30) Priorités/Priorities: 2012/04/23 (US61/636,869);
2013/01/22 (US61/755,151)

(51) Cl.Int./Int.Cl. *C01D 15/06* (2006.01),
B01J 47/00 (2017.01), *C01D 15/02* (2006.01),
C22B 3/04 (2006.01), *C22B 3/20* (2006.01),
C25B 15/08 (2006.01)
(72) Inventeurs/Inventors:
BOURASSA, GUY, CA;
PEARSE, GARY, CA;
MACKIE, STEPHEN CHARLES, CA;
GLADKOVAS, MYKOLAS, CA;
GENDERS, J. DAVID, US;
SYMONS, PETER, US;
MAGNAN, JEAN-FRANCOIS, CA
(73) Propriétaire/Owner:

(54) Titre : PROCEDES DE PREPARATION DE SULFATE DE LITHIUM
(54) Title: PROCESS FOR PREPARING LITHIUM SULPHATE



(57) Abrégé/Abstract:

There are provided processes for preparing lithium sulphate. For example, such processes can comprise reacting an aqueous composition comprising Li^+ and at least one metal ion with a base and thereby at least partially precipitating the at least one metal

(73) Propriétaires(suite)/Owners(continued):NEMASKA LITHIUM INC., CA

(74) Agent: BERESKIN & PARR LLP/S.E.N.C.R.L.,S.R.L.

(57) Abrégé(suite)/Abstract(continued):

ion under the form of at least one hydroxide so as to obtain a precipitate and an aqueous composition; reacting the aqueous composition with another base, adding at least one metal carbonate thereby at least partially precipitating at least one metal ion under the form of at least one carbonate so as to obtain a precipitate comprising the at least one carbonate and an aqueous composition; and contacting the aqueous composition with an ion-exchange resin so as to at least partially remove at least one metal ion from the composition, thereby obtaining an aqueous composition comprising the lithium sulphate.

ABSTRACT

There are provided processes for preparing lithium sulphate. For example, such processes can comprise reacting an aqueous composition comprising Li^+ and at least one metal ion with a base and thereby at least partially precipitating the at least one metal ion under the form of at least one hydroxide so as to obtain a precipitate and an aqueous composition; reacting the aqueous composition with another base, adding at least one metal carbonate thereby at least partially precipitating at least one metal ion under the form of at least one carbonate so as to obtain a precipitate comprising the at least one carbonate and an aqueous composition; and contacting the aqueous composition with an ion-exchange resin so as to at least partially remove at least one metal ion from the composition, thereby obtaining an aqueous composition comprising the lithium sulphate.

PROCESS FOR PREPARING LITHIUM SULPHATE

[0001]

[0002] The present disclosure relates to improvements in the field of chemistry applied to the manufacture of lithium hydroxide. For example, such processes are useful for preparing lithium hydroxide from lithium-containing materials. For example, the disclosure also relates to the production of other lithium products such as lithium carbonate and lithium sulphate.

[0003] The demand for lithium hydroxide is growing rapidly. The market for lithium hydroxide is expanding and the current world production capacity will likely not meet the expected increase in demand. For example, lithium hydroxide is used for purification of gases and air (as a carbon dioxide absorbent), as a heat transfer medium, as a storage-battery electrolyte, as a catalyst for polymerization, in ceramics, in Portland cement formulations, in manufacturing other lithium compounds and in esterification, especially for lithium stearate.

[0004] Lithium batteries have become the battery of choice in several existing and proposed new applications due to their high energy density to weight ratio, as well as their relatively long useful life when compared to other types of batteries. Lithium batteries are used for several applications such as laptop computers, cell phones, medical devices and implants (for example cardiac pacemakers). Lithium batteries are also an interesting option in the development of new automobiles, e.g., hybrid and electric vehicles, which are both environmentally friendly and "green" because of reduced emissions and decreased reliance on hydrocarbon fuels.

[0005] High purity can be required for lithium hydroxide that is used, for example, for various battery applications. There is a limited number of lithium hydroxide producers. As a direct result of increased demand for lithium

products, battery manufacturers are looking for additional and reliable sources of high quality lithium products, for example lithium hydroxide.

[0006] Few methods have been proposed so far for preparing lithium hydroxide. One of them being a method that uses natural brines as a starting material. Battery applications can require very low levels of impurities, notably sodium, calcium and chlorides. The production of lithium hydroxide product with a low impurities content can be difficult unless one or more purification steps are performed. These additional purification steps add to the time and cost of the manufacture of the desired lithium hydroxide product. Natural brines are also associated with high concentrations of magnesium or other metals which can make lithium recovery uneconomical. Thus, the production of lithium hydroxide monohydrate from natural brines can be a difficult task.

[0007] There is thus a need for providing an alternative to the existing solutions for preparing lithium hydroxide.

[0008] According to one aspect, there is provided a process for preparing lithium hydroxide, the process comprising :

submitting an aqueous composition comprising a lithium compound to an electrodialysis under conditions suitable for converting at least a portion of the lithium compound into lithium hydroxide.

[0009] According to another aspect, there is provided a process for preparing lithium hydroxide, the process comprising :

submitting an aqueous composition comprising a lithium compound to an electrolysis under conditions suitable for converting at least a portion of the lithium compound into lithium hydroxide.

[0010] According to another aspect, there is provided a process for preparing lithium hydroxide, the process comprising :

submitting an aqueous composition comprising a lithium compound to an electrodialysis under conditions suitable for converting at least a portion of the lithium compound into lithium hydroxide, wherein during the electrodialysis, the aqueous composition comprising the lithium compound

is at least substantially maintained at a pH having a value of about 9.5 to about 12.5.

[0011] According to another aspect, there is provided a process for preparing lithium hydroxide, the process comprising :

submitting an aqueous composition comprising lithium sulphate to an electrolysis under conditions suitable for converting at least a portion of the lithium sulphate into lithium hydroxide, wherein during the electrolysis, the aqueous composition comprising lithium sulphate has a pH of greater than 7.

[0012] According to another aspect, there is provided a process for preparing lithium hydroxide, the process comprising :

submitting an aqueous composition comprising a lithium compound to an electrolysis under conditions suitable for converting at least a portion of the lithium compound into lithium hydroxide, wherein during the electrolysis, the aqueous composition comprising the lithium compound is at least substantially maintained at a pH having a value of about 9.5 to about 12.5.

[0013] According to another aspect, there is provided a process for preparing lithium hydroxide, the process comprising :

submitting an aqueous composition comprising lithium sulphate to an electrodialysis under conditions suitable for converting at least a portion of the lithium sulphate into lithium hydroxide, wherein during the electrodialysis, the aqueous composition comprising lithium sulphate is at least substantially maintained at a pH having a value of about 9.5 to about 12.5.

[0014] According to another aspect, there is provided a process for preparing lithium hydroxide, the process comprising :

submitting an aqueous composition comprising lithium sulphate to an electrolysis under conditions suitable for converting at least a

portion of the lithium sulphate into lithium hydroxide, wherein during the electrolysis, the aqueous composition comprising lithium sulphate is at least substantially maintained at a pH having a value of about 9.5 to about 12.5.

[0015] According to another aspect, there is provided a process for preparing lithium hydroxide, the process comprising :

leaching an acid roasted lithium-containing material with water so as to obtain an aqueous composition comprising Li^+ and at least one metal ion;

reacting the aqueous composition comprising Li^+ and the at least one metal ion with a base so as to obtain a pH of about 4.5 to about 6.5 and thereby at least partially precipitating the at least one metal ion under the form of at least one hydroxide so as to obtain a precipitate comprising the at least one hydroxide and an aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion, and separating the aqueous composition from the precipitate;

contacting the aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion with an ion exchange resin so as to at least partially remove at least one metal ion from the composition, thereby obtaining an aqueous composition comprising a lithium compound; and

submitting the aqueous composition comprising the lithium compound to an electrodialysis under conditions suitable for converting at least a portion of the lithium compound into lithium hydroxide.

[0016] According to another aspect, there is provided a process for preparing lithium hydroxide, the process comprising :

leaching an acid roasted lithium-containing material with water so as to obtain an aqueous composition comprising Li^+ and at least one metal ion;

reacting the aqueous composition comprising Li^+ and the at least one metal ion with a base so as to obtain a pH of about 4.5 to about 6.5 and thereby at least partially precipitating the at least one metal ion under the form of at least one hydroxide so as to obtain a precipitate comprising the at least one hydroxide and an aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion, and separating the aqueous composition from the precipitate;

contacting the aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion with an ion exchange resin so as to at least partially remove at least one metal ion from the composition, thereby obtaining an aqueous composition comprising a lithium compound; and

submitting the aqueous composition comprising the lithium compound to an electrolysis under conditions suitable for converting at least a portion of the lithium compound into lithium hydroxide.

[0017] According to another aspect, there is provided a process for preparing lithium hydroxide, the process comprising :

leaching a base-baked lithium-containing material with water so as to obtain an aqueous composition comprising Li^+ and at least one metal ion;

reacting the aqueous composition comprising Li^+ and the at least one metal ion with a base so as to obtain a pH of about 4.5 to about 6.5 and thereby at least partially precipitating the at least one metal ion under the form of at least one hydroxide so as to obtain a precipitate comprising the at least one hydroxide and an aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion, and separating the aqueous composition from the precipitate;

optionally reacting the aqueous composition comprising Li^+ and having the reduced content of the at least one metal ion with another

base so as to obtain a pH of about 9.5 to about 11.5, and with optionally at least one metal carbonate, thereby at least partially precipitating at least one metal ion optionally under the form of at least one carbonate so as to obtain a precipitate optionally comprising the at least one carbonate and an aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion, and separating the aqueous composition from the precipitate;

contacting the aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion with an ion exchange resin so as to at least partially remove at least one metal ion from the composition, thereby obtaining an aqueous composition comprising a lithium compound; and

submitting the aqueous composition comprising the lithium compound to an electrodialysis under conditions suitable for converting at least a portion of the lithium compound into lithium hydroxide.

[0018] According to another aspect, there is provided a process for preparing lithium hydroxide, the process comprising :

leaching a base-baked lithium-containing material with water so as to obtain an aqueous composition comprising Li^+ and at least one metal ion;

reacting the aqueous composition comprising Li^+ and the at least one metal ion with a base so as to obtain a pH of about 4.5 to about 6.5 and thereby at least partially precipitating the at least one metal ion under the form of at least one hydroxide so as to obtain a precipitate comprising the at least one hydroxide and an aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion, and separating the aqueous composition from the precipitate;

optionally reacting the aqueous composition comprising Li^+ and having the reduced content of the at least one metal ion with another base so as to obtain a pH of about 9.5 to about 11.5, and with optionally at

least one metal carbonate, thereby at least partially precipitating at least one metal ion optionally under the form of at least one carbonate so as to obtain a precipitate optionally comprising the at least one carbonate and an aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion, and separating the aqueous composition from the precipitate;

contacting the aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion with an ion exchange resin so as to at least partially remove at least one metal ion from the composition, thereby obtaining an aqueous composition comprising a lithium compound; and

submitting the aqueous composition comprising the lithium compound to an electrolysis under conditions suitable for converting at least a portion of the lithium compound into lithium hydroxide.

[0019] According to another aspect, there is provided a process for preparing lithium hydroxide, the process comprising :

leaching a base-baked lithium-containing material with water so as to obtain an aqueous composition comprising Li^+ and at least one metal ion;

optionally reacting the aqueous composition comprising Li^+ and the at least one metal ion with a base so as to obtain a pH of about 4.5 to about 6.5;

at least partially precipitating the at least one metal ion under the form of at least one hydroxide so as to obtain a precipitate comprising the at least one hydroxide and an aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion, and separating the aqueous composition from the precipitate;

optionally reacting the aqueous composition comprising Li^+ and having the reduced content of the at least one metal ion with another base so as to obtain a pH of about 9.5 to about 11.5, and with optionally at

least one metal carbonate, thereby at least partially precipitating at least one metal ion optionally under the form of at least one carbonate so as to obtain a precipitate optionally comprising the at least one carbonate and an aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion, and separating the aqueous composition from the precipitate;

contacting the aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion with an ion exchange resin so as to at least partially remove at least one metal ion from the composition, thereby obtaining an aqueous composition comprising a lithium compound; and

submitting the aqueous composition comprising the lithium compound to an electrodialysis under conditions suitable for converting at least a portion of the lithium compound into lithium hydroxide.

[0020] According to another aspect, there is provided a process for preparing lithium hydroxide, the process comprising :

leaching a base-baked lithium-containing material with water so as to obtain an aqueous composition comprising Li^+ and at least one metal ion;

optionally reacting the aqueous composition comprising Li^+ and the at least one metal ion with a base so as to obtain a pH of about 4.5 to about 6.5;

at least partially precipitating the at least one metal ion under the form of at least one hydroxide so as to obtain a precipitate comprising the at least one hydroxide and an aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion, and separating the aqueous composition from the precipitate;

optionally reacting the aqueous composition comprising Li^+ and having the reduced content of the at least one metal ion with another base so as to obtain a pH of about 9.5 to about 11.5, and with optionally at

least one metal carbonate, thereby at least partially precipitating at least one metal ion optionally under the form of at least one carbonate so as to obtain a precipitate optionally comprising the at least one carbonate and an aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion, and separating the aqueous composition from the precipitate;

contacting the aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion with an ion exchange resin so as to at least partially remove at least one metal ion from the composition, thereby obtaining an aqueous composition comprising a lithium compound; and

submitting the aqueous composition comprising the lithium compound to an electrolysis under conditions suitable for converting at least a portion of the lithium compound into lithium hydroxide.

[0021] According to another aspect, there is provided a process for preparing lithium hydroxide, the process comprising :

leaching an acid roasted lithium-containing material with water so as to obtain an aqueous composition comprising Li^+ and at least one metal ion;

reacting the aqueous composition comprising Li^+ and the at least one metal ion with a base so as to obtain a pH of about 4.5 to about 6.5 and thereby at least partially precipitating the at least one metal ion under the form of at least one hydroxide so as to obtain a precipitate comprising the at least one hydroxide and an aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion, and separating the aqueous composition from the precipitate;

optionally reacting the aqueous composition comprising Li^+ and having the reduced content of the at least one metal ion with another base so as to obtain a pH of about 9.5 to about 11.5, and with optionally at least one metal carbonate, thereby at least partially precipitating at least one

metal ion optionally under the form of at least one carbonate so as to obtain a precipitate optionally comprising the at least one carbonate and an aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion, and separating the aqueous composition from the precipitate;

contacting the aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion with an ion exchange resin so as to at least partially remove at least one metal ion from the composition, thereby obtaining an aqueous composition comprising a lithium compound; and

submitting the aqueous composition comprising the lithium compound to an electrodialysis under conditions suitable for converting at least a portion of the lithium compound into lithium hydroxide.

[0022] According to another aspect, there is provided a process for preparing lithium hydroxide, the process comprising :

leaching an acid roasted lithium-containing material with water so as to obtain an aqueous composition comprising Li^+ and at least one metal ion;

reacting the aqueous composition comprising Li^+ and the at least one metal ion with a base so as to obtain a pH of about 4.5 to about 6.5 and thereby at least partially precipitating the at least one metal ion under the form of at least one hydroxide so as to obtain a precipitate comprising the at least one hydroxide and an aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion, and separating the aqueous composition from the precipitate;

optionally reacting the aqueous composition comprising Li^+ and having the reduced content of the at least one metal ion with another base so as to obtain a pH of about 9.5 to about 11.5, and with optionally at least one metal carbonate, thereby at least partially precipitating at least one metal ion optionally under the form of at least one carbonate so as to obtain a

precipitate optionally comprising the at least one carbonate and an aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion, and separating the aqueous composition from the precipitate;

contacting the aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion with an ion exchange resin so as to at least partially remove at least one metal ion from the composition, thereby obtaining an aqueous composition comprising a lithium compound; and

submitting the aqueous composition comprising the lithium compound to an electrolysis under conditions suitable for converting at least a portion of the lithium compound into lithium hydroxide.

[0023] According to another aspect, there is provided a process for preparing lithium sulphate, the process comprising :

leaching an acid roasted lithium-containing material with water so as to obtain an aqueous composition comprising Li^+ and at least one metal ion, wherein the lithium-containing material is a material that has been previously reacted with H_2SO_4 ;

reacting the aqueous composition comprising Li^+ and the at least one metal ion with a base so as to obtain a pH of about 4.5 to about 6.5 and thereby at least partially precipitating the at least one metal ion under the form of at least one hydroxide so as to obtain a precipitate comprising the at least one hydroxide and an aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion, and separating the aqueous composition from the precipitate; and

contacting the aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion with an ion-exchange resin so as to at least partially remove at least one metal ion from the composition, thereby obtaining an aqueous composition comprising a lithium sulphate.

[0024] According to another aspect, there is provided a process for preparing lithium sulphate, the process comprising :

leaching an acid roasted lithium-containing material with water so as to obtain an aqueous composition comprising Li^+ and at least one metal ion, wherein the lithium-containing material is a material that has been previously reacted with H_2SO_4 ;

reacting the aqueous composition comprising Li^+ and the at least one metal ion with a base so as to obtain a pH of about 4.5 to about 6.5 and thereby at least partially precipitating the at least one metal ion under the form of at least one hydroxide so as to obtain a precipitate comprising the at least one hydroxide and an aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion, and separating the aqueous composition from the precipitate;

optionally reacting the aqueous composition comprising Li^+ and having the reduced content of the at least one metal ion with another base so as to obtain a pH of about 9.5 to about 11.5 and with at least one metal carbonate thereby at least partially precipitating at least one metal ion under the form of at least one carbonate so as to obtain a precipitate comprising the at least one carbonate and an aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion, and separating the aqueous composition from the precipitate; and

contacting the aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion with an ion-exchange resin so as to at least partially remove at least one metal ion from the composition, thereby obtaining an aqueous composition comprising a lithium sulphate.

[0025] In the following drawings, which represent by way of example only, various embodiments of the disclosure :

[0026] Figure 1 is a block diagram concerning an example of a process according to the present disclosure;

[0027] Figure 2 is a flow sheet diagram concerning another example of a process according to the present disclosure;

[0028] Figure 3 is a plot showing lithium tenor as a function of time in another example of a process according to the present disclosure;

[0029] Figure 4 is a plot showing iron tenor as a function of time in another example of a process according to the present disclosure;

[0030] Figure 5 is a plot showing aluminum tenor as a function of time in another example of a process according to the present disclosure;

[0031] Figure 6 is a diagram showing various metals tenor as a function of time in another example of a process according to the present disclosure;

[0032] Figure 7 is a plot showing various metals tenor as a function of time in another example of a process according to the present disclosure;

[0033] Figure 8 is a plot showing calcium tenor as a function of molar excess of sodium carbonate in another example of a process according to the present disclosure;

[0034] Figure 9 is a plot showing magnesium tenor as a function of molar excess of sodium carbonate in another example of a process according to the present disclosure;

[0035] Figure 10 is a schematic representation of another example of a process according to the present disclosure;

[0036] Figure 11 is a plot showing calcium tenor as a function of bed volumes in an ion exchange process in another example of a process according to the present disclosure;

[0037] Figure 12 is a plot showing magnesium tenor as a function of bed volumes in an ion exchange process in another example of a process according to the present disclosure;

[0038] Figure 13 is a plot showing calcium tenor as a function of bed volumes in another example of a process according to the present disclosure;

[0039] Figure 14 is a plot showing magnesium tenor as a function of bed volumes in another example of a process according to the present disclosure;

[0040] Figure 15 is a plot showing lithium tenor as a function of bed volumes in another example of a process according to the present disclosure;

[0041] Figure 16 is a plot showing various metals tenor as a function of bed volumes in another example of a process according to the present disclosure;

[0042] Figure 17 is a schematic representation of an example of a membrane electrolysis cell that can be used for carrying out an example of a process according to the present disclosure;

[0043] Figure 18 is a flow sheet diagram concerning another example of a process according to the present disclosure;

[0044] Figure 19 is a plot showing lithium tenor as a function of time in another example of a process according to the present disclosure;

[0045] Figure 20 is a plot showing lithium tenor as a function of time in another example of a process according to the present disclosure;

[0046] Figure 21 is a plot showing sulphate tenor as a function of time in another example of a process according to the present disclosure;

[0047] Figure 22 is a plot showing sulphate tenor as a function of time in another example of a process according to the present disclosure;

[0048] Figure 23 is a schematic representation of an example of a membrane electrolysis cell that can be used for carrying out another example of a process according to the present disclosure;

[0049] Figure 24 shows plots relating to a process according to the present disclosure using N324/AHA membranes at about 60 °C: Figure 24A is a plot showing current and voltage as a function of charge passed, Figure 24B is a plot showing feed conductivity, current density and acid pH as a function of

charge passed, Figure 24C is a plot showing the concentration in the "acid" compartment, feed and base of various ions as a function of charge passed and Figure 24D is a plot showing sulfate current efficiency as a function of charge passed;

[0050] Figure 25 shows plots relating to a process according to the present disclosure using N324/AHA membranes at about 60 °C: Figure 25A is a plot showing current and voltage as a function of charge passed, Figure 25B is a plot showing feed conductivity, voltage, feed pH and acid pH as a function of charge passed, Figure 25C is a plot showing a current/voltage ramp, Figure 25D is a plot showing the concentration in the feed of various ions as a function of charge passed, Figure 25E is a plot showing the concentration of ammonium and sulfate in the acid compartment (or anolyte compartment) as a function of charge passed, Figure 25F is a plot showing the concentration of various ions in the base as a function of charge passed, and Figure 25G is a plot showing sulfate current efficiency as a function of charge passed;

[0051] Figure 26 shows plots relating to a process according to the present disclosure using N324/AHA membranes at about 60 °C: Figure 26A is a plot showing current and voltage as a function of charge passed; Figure 26B is a plot showing feed conductivity, voltage, feed pH and acid pH as a function of charge passed, Figure 26C is a plot showing the concentration of various ions in the feed as a function of charge passed, Figure 26D is a plot showing the concentration of various ions in the base as a function of charge passed, Figure 26E is a plot showing the concentration of ammonium and sulfate in the "acid" compartment as a function of charge passed, Figure 26F is a plot showing sulfate current efficiency as a function of charge passed, and Figure 26G is a plot showing the concentration of various ions in the feed as a function of charge passed;

[0052] Figure 27 shows plots relating to a process according to the present disclosure using N324/AHA membranes at about 60 °C and about 200 mA/cm²: Figure 27A is a plot showing current and voltage as a function of charge passed, Figure 27B is a plot showing feed conductivity, voltage, feed

pH and acid pH as a function of charge passed, Figure 27C is a plot showing the concentration of various ions in the feed as a function of charge passed, Figure 27D is a plot showing the concentration of ammonium and sulfate in the "acid" compartment as a function of charge passed, Figure 27E is a plot showing the concentration of various ions in the base as a function of charge passed, and Figure 27F is a plot showing sulfate current efficiency as a function of charge passed;

[0053] Figure 28 shows plots relating to a process according to the present disclosure using N324/AHA membranes at about 80 °C and about 200 mA/cm²: Figure 28A is a plot showing current and voltage as a function of charge passed, Figure 28B is a plot showing feed conductivity, voltage, feed pH and acid pH as a function of charge passed, Figure 28C is a plot showing a current/voltage ramp, Figure 28D is a plot showing the concentration of various ions in the feed as a function of charge passed, Figure 28E is a plot showing the concentration of ammonium and sulfate in the "acid" compartment as a function of charge passed, Figure 28F is a plot showing the concentration of various ions in the base as a function of charge passed, and Figure 28G is a plot showing sulfate current efficiency as a function of charge passed;

[0054] Figure 29 shows plots relating to a process according to the present disclosure using N324/AHA membranes at about 60 °C and about 200 mA/cm²: Figure 29A is a plot showing current and voltage as a function of charge passed; Figure 29B is a plot showing the concentration of various ions in the feed as a function of charge passed, Figure 29C is a plot showing feed conductivity, voltage, feed pH and acid pH as a function of charge passed, Figure 29D is a plot showing the concentration of various ions in the feed as a function of charge passed, Figure 29E is a plot showing the concentration of ammonium and sulfate in the "acid" compartment as a function of charge passed, Figure 29F is a plot showing the concentration of various ions in the base as a function of charge passed, and Figure 29G is a plot showing sulfate current efficiency as a function of charge passed; and

[0055] Figure 30 is a plot showing the current density, pH and conductivity as a function of charge passed in an example of a process according to the present disclosure using N324/AHA membranes at about 60 °C and about 200 mA/cm².

[0056] Further features and advantages will become more readily apparent from the following description of various embodiments as illustrated by way of examples.

[0057] The term "suitable" as used herein means that the selection of the particular conditions would depend on the specific manipulation or operation to be performed, but the selection would be well within the skill of a person trained in the art. All processes described herein are to be conducted under conditions sufficient to provide the desired product.

[0058] In understanding the scope of the present disclosure, the term "comprising" and its derivatives, as used herein, are intended to be open ended terms that specify the presence of the stated features, elements, components, groups, integers, and/or steps, but do not exclude the presence of other unstated features, elements, components, groups, integers and/or steps. The foregoing also applies to words having similar meanings such as the terms, "including", "having" and their derivatives. The term "consisting" and its derivatives, as used herein, are intended to be closed terms that specify the presence of the stated features, elements, components, groups, integers, and/or steps, but exclude the presence of other unstated features, elements, components, groups, integers and/or steps. The term "consisting essentially of", as used herein, is intended to specify the presence of the stated features, elements, components, groups, integers, and/or steps as well as those that do not materially affect the basic and novel characteristic(s) of features, elements, components, groups, integers, and/or steps.

[0059] Terms of degree such as "about" and "approximately" as used herein mean a reasonable amount of deviation of the modified term such that the end result is not significantly changed. These terms of degree should be construed as including a deviation of at least $\pm 5\%$ or at least $\pm 10\%$ of the

modified term if this deviation would not negate the meaning of the word it modifies.

[0060] The expression "at least one metal ion", as used herein refers, for example, to at least one type of ion of at least one metal. For example, the at least one metal ion can be M^{X+} . In this example, M^{X+} is an ion of the metal M, wherein X^+ is a particular form or oxidation state of the metal M. Thus, M^{X+} is at least one type of ion (oxidation state X^+) of at least one metal (M). For example, M^{Y+} can be another type of ion of the metal M, wherein X and Y are different integers.

[0061] The expression "is at least substantially maintained" as used herein when referring to a value of a pH or a pH range that is maintained during a process of the disclosure or a portion thereof (for example heating, electrodialysis, electrolysis, etc.) refers to maintaining the value of the pH or the pH range at least 75, 80, 85, 90, 95, 96, 97, 98 or 99 % of the time during the process or the portion thereof.

[0062] The expression "is at least substantially maintained" as used herein when referring to a value of a concentration or a concentration range that is maintained during a process of the disclosure or a portion thereof (for example heating, electrodialysis, electrolysis, etc.) refers to maintaining the value of the concentration or the concentration range at least 75, 80, 85, 90, 95, 96, 97, 98 or 99 % of the time during the process or the portion thereof.

[0063] The expression "is at least substantially maintained" as used herein when referring to a value of a temperature or a temperature range that is maintained during a process of the disclosure or a portion thereof (for example heating, electrodialysis, electrolysis, etc.) refers to maintaining the value of the temperature or the temperature range at least 75, 80, 85, 90, 95, 96, 97, 98 or 99 % of the time during the process or the portion thereof.

[0064] The expression "is at least substantially maintained" as used herein when referring to a value of an oxidation potential or an oxidation potential range that is maintained during a process of the disclosure or a portion thereof (for example heating, electrodialysis, electrolysis, etc.) refers to

maintaining the value of the oxidation potential or the oxidation potential range at least 75, 80, 85, 90, 95, 96, 97, 98 or 99 % of the time during the process or the portion thereof.

[0065] The expression "is at least substantially maintained" as used herein when referring to a value of an electrical current or an electrical current range that is maintained during a process of the disclosure or a portion thereof (for example electrodialysis, electrolysis, etc.) refers to maintaining the value of the electrical current or the electrical current range at least 75, 80, 85, 90, 95, 96, 97, 98 or 99 % of the time during the process or the portion thereof.

[0066] The expression "is at least substantially maintained" as used herein when referring to a value of a voltage or a voltage range that is maintained during a process of the disclosure or a portion thereof (for example electrodialysis, electrolysis, etc.) refers to maintaining the value of the voltage or the voltage range at least 75, 80, 85, 90, 95, 96, 97, 98 or 99 % of the time during the process or the portion thereof.

[0067] The below presented examples are non-limitative and are used to better exemplify the processes of the present disclosure.

[0068] The processes of the present disclosure can be effective for treating various lithium-containing materials. The lithium-containing material can be a lithium-containing ore, a lithium compound, or a recycled industrial lithium-containing entity. For example, the lithium-containing ore can be, for example, α -spodumene, β -spodumene, lepidolite, pegmatite, petalite, eucryptite, amblygonite, hectorite, smectite, clays, or mixtures thereof. The lithium compound can be, for example, LiCl, Li_2SO_4 , LiHCO_3 , Li_2CO_3 , LiNO_3 , $\text{LiC}_2\text{H}_3\text{O}_2$ (lithium acetate), LiF, lithium stearate or lithium citrate. The lithium-containing material can also be a recycled industrial lithium-containing entity such as lithium batteries, other lithium products or derivatives thereof.

[0069] A person skilled in the art would appreciate that various reaction parameters, will vary depending on a number of factors, such as the nature of the starting materials, their level of purity, the scale of the reaction as well as

all the parameters since they can be dependent from one another, and could adjust the reaction conditions accordingly to optimize yields.

[0070] For example, during the electrodialysis or the electrolysis, the pH of the composition comprising lithium sulfate or the lithium compound can be at least substantially maintained at a value of about 9.5 to about 12.5, about 10 to about 12, about 10.5 to about 12.5, about 11 to about 12.5, about 11 to about 12, about 9.8 to about 10.8, about 9.8 to about 10.2, about 10 to about 10.5, or about 10.

[0071] For example, during the electrodialysis or the electrolysis, the pH of the composition comprising lithium sulfate or the lithium compound can be at least substantially maintained at a value between 7 and 14.5, 7 and 14, 7 and 10; or 7 and 9.

[0072] For example, the pH of the wherein during the electrodialysis or electrolysis, the aqueous composition comprising lithium sulfate or the lithium compound can have a pH between 7 and 14.5, 7 and 14, 7 and 10; or 7 and 9.

[0073] For example, the pH of the wherein during the electrodialysis or electrolysis, the aqueous composition comprising lithium sulfate or the lithium compound can have a pH of about 9.5 to about 12.5, about 10 to about 12, about 10.5 to about 12.5, about 11 to about 12, about 9.8 to about 10.8, about 9.8 to about 10.2, about 10 to about 10.5, or about 10.

[0074] For example, the electrodialysis or the electrolysis can be carried out in a three-compartment membrane electrolysis cell.

[0075] For example, the electrodialysis or the electrolysis can be carried out in a two-compartment membrane electrolysis cell.

[0076] For example, the electrodialysis or the electrolysis can be carried out in a three-compartment membrane cell.

[0077] For example, the electrodialysis or the electrolysis can be carried out in a two-compartment membrane cell.

[0078] For example, the electrolysis can be carried out in a monopolar electrolysis cell. For example, the electrolysis can be carried out in a monopolar three-compartment electrolysis cell.

[0079] For example, the electrolysis can be carried out in a bipolar electrolysis cell. For example, the electrolysis can be carried out in a bipolar three-compartment electrolysis cell.

[0080] For example, the electrodialysis can be carried out in a bipolar electrodialysis cell. For example, the electrodialysis can be carried out in a bipolar three-compartment electrodialysis cell.

[0081] For example, the aqueous composition comprising the lithium sulphate or the lithium compound can be submitted to a monopolar membrane electrolysis process.

[0082] For example, the aqueous composition comprising the lithium sulphate or the lithium compound can be submitted to a monopolar three compartment membrane electrolysis process.

[0083] For example, the aqueous composition comprising the lithium sulphate or lithium compound can be submitted to a bipolar membrane electrodialysis process.

[0084] For example, the aqueous composition comprising the lithium sulphate or lithium compound can be submitted to a bipolar three compartment electrodialysis process.

[0085] For example, the electrodialysis or the electrolysis can be carried out in an electrolytic cell in which a cathodic compartment is separated from the central or anodic compartment by a cathodic membrane.

[0086] For example, the electrodialysis can be carried out in a bipolar membrane. For example such a membrane is a membrane that splits water molecules (H^+ and OH^-) and wherein acid and base solution are produced, for example, at low concentration.

[0087] For example, the electrolysis can be carried out by using a monopolar membrane. For example, it can be carried out by using an

electrolysis stack comprising three compartment cells equipped with monopolar membranes and bipolar electrodes. For example, such electrodes are effective for evolving gaseous hydrogen (H_2) at the cathodic electrode and gaseous oxygen (O_2) or chlorine gas (Cl_2) at the anodic electrode. For example, such electrodes are effective for splitting water molecules.

[0088] For example, the membrane can be a perfluorinated membrane or a styrene/divinylbenzene membrane.

[0089] For example, the membrane can be a cation exchange membrane, PEEK-reinforced membrane.

[0090] For example, the electrodialysis or the electrolysis can be carried out by introducing the aqueous composition comprising the lithium compound (for example $LiCl$, LiF , Li_2SO_4 , $LiHCO_3$, Li_2CO_3 , $LiNO_3$, $LiC_2H_3O_2$ (lithium acetate), lithium stearate or lithium citrate) into a central compartment, an aqueous composition comprising lithium hydroxide into a cathodic compartment, and generating an aqueous composition comprising an acid (for example HCl , H_2SO_4 , HNO_3 or acetic acid) in an anodic compartment (or acid compartment). The person skilled in the art would understand that, for example, when $LiCl$ is introduced in the central compartment, HCl is generated in the anodic compartment, for example a monopolar membrane electrolysis cell. For example, when LiF is used in the central compartment, HF is generated in the anodic compartment. For example, when Li_2SO_4 is used in the central compartment, H_2SO_4 is generated in the anodic compartment. For example, when $LiHCO_3$ is used in the central compartment, H_2CO_3 is generated in the anodic compartment. For example, when $LiNO_3$ is used in the central compartment, HNO_3 is generated in the anodic compartment. For example, when $LiC_2H_3O_2$ is used in the central compartment, acetic acid is generated in the anodic compartment. For example, when lithium stearate is used in the central compartment, stearic acid is generated in the anodic compartment. For example, when lithium citrate is used in the central compartment, citric acid is generated in the anodic compartment.

[0091] For example, the electrodialysis or the electrolysis can be carried out by introducing the lithium sulphate into a central compartment, an aqueous composition comprising lithium hydroxide into a cathodic compartment, and generating an aqueous composition comprising sulphuric acid in an anodic compartment.

[0092] For example, an anolyte used during the process can comprise ammonia, ammonium bisulfate, ammonium sulfate and/or NH_4OH . For example, an anolyte used during the process can comprise ammonia, ammonium bisulfate, ammonium sulfate and/or NH_4OH , thereby generating an ammonium salt.

[0093] For example, the process can further comprise adding ammonia and/or NH_4OH , for example gaseous or liquid ammonia, for example NH_3 and/or NH_4OH , in an anolyte compartment, in an acid compartment, in the anolyte, at an anode or adjacently thereof, wherein the anode is used for the process.

[0094] For example, the process can further comprise adding ammonia and/or NH_4OH , in an anolyte compartment, in an anolyte at an anode or adjacently thereof, thereby generating an ammonium salt, wherein the anode is used for the process.

[0095] For example, the process can further comprise adding ammonia and/or NH_4OH in an anolyte compartment or in an anolyte used for the process.

[0096] For example, the process can further comprise adding ammonia and/or NH_4OH in an anolyte used for the process, thereby generating an ammonium salt.

[0097] For example, the ammonium salt can be $(\text{NH}_4)_2\text{SO}_4$.

[0098] For example, concentration of the produced ammonium salt can be about 1 to about 4 M, about 1 to about 3 M, or about 1.5 M to about 2.5 M.

[0099] For example, concentration of the ammonium bisulfate present in the anolyte can be at a concentration of about 1 to about 4 M, about 1 to about 3 M, or about 1.5 M to about 3.5 M.

[00100] For example, concentration of the ammonium sulfate present in the anolyte can be at a concentration of about 1 to about 4 M, about 1 to about 3 M, or about 1.5 M to about 3.5 M.

[00101] For example, pH of the anolyte is maintained at a value of about -0.5 to about 4.0, about -0.5 to about 3.5, about -0.25 to about 1.5 or about -0.25 to about 1.0.

[00102] For example, ammonia can be added in a substoichiometric quantity as compared to sulfuric acid produced.

[00103] For example, ammonia can be added in a molar ratio ammonia : sulfuric acid comprised between 0.5 :1 and 2:1 or between 1 :1 and 1.9:1.

[00104] For example, the electrodialysis or the electrolysis can be carried out by introducing the aqueous composition comprising the lithium compound (for example LiCl, LiF, Li₂SO₄, LiHCO₃, Li₂CO₃, LiNO₃, LiC₂H₃O₂ (lithium acetate), lithium stearate or lithium citrate) into a central compartment, an aqueous composition comprising lithium hydroxide into a cathodic compartment, and an aqueous composition comprising NH₃ into an anodic compartment. For example, when an aqueous composition comprising NH₃ is introduced into the anodic compartment, proton-blocking membranes may not be required and membranes which are capable, for example of running at a temperature of about 80 °C and which may, for example, have lower resistance can be used. For example, the aqueous composition comprising the lithium compound can further comprise Na⁺.

[00105] For example, during the electrodialysis or the electrolysis, the aqueous composition comprising lithium hydroxide can be at least substantially maintained at a concentration of lithium hydroxide of about 30 to about 90 g/L, about 40 to about 90 g/L, about 35 to about 70 g/L, about 40 to about 66 g/L, about 45 to about 65 g/L, about 48 to about 62 g/L or about 50 to about 60 g/L.

[00106] For example, during the electrodialysis or the electrolysis, the aqueous composition comprising lithium hydroxide can be at least substantially maintained at a concentration of lithium hydroxide of about 1 to about 5 M, about 2 to about 4 M, about 2.5 to about 3.5 M, about 2.7 to about 3.3 M, about 2.9 to about 3.1 M or about 3 M.

[00107] For example, during the electrodialysis or the electrolysis, the aqueous composition comprising sulphuric acid can be at least substantially maintained at a concentration of sulphuric acid of about 30 to about 100 g/L, about 40 to about 100 g/L, about 40 to about 100 g/L, about 60 to about 90 g/L, about 20 to about 40 g/L, about 20 to about 50 g/L, about 25 to about 35 g/L, or about 28 to about 32 g/L.

[00108] For example, during the electrodialysis or the electrolysis, the aqueous composition comprising sulphuric acid can be at least substantially maintained at a concentration of sulphuric acid of about 0.1 to about 5 M, about 0.2 to about 3M, about 0.3 to about 2 M, about 0.3 to about 1.5 M, about 0.4 to about 1.2 M, about 0.5 to about 1 M, or about 0.75 M.

[00109] For example, during the electrodialysis or the electrolysis, the aqueous composition comprising lithium sulphate can be at least substantially maintained at a concentration of lithium sulphate of about 5 to about 30 g/L, about 5 to about 25 g/L, about 10 to about 20 g/L, or about 13 to about 17 g/L.

[00110] For example, during the electrodialysis or the electrolysis, the aqueous composition comprising lithium sulphate can be at least substantially maintained at a concentration of lithium sulphate of about 0.2 to about 3 M, about 0.4 to about 2.5 M, about 0.5 to about 2 M, or about 0.6 to about 1.8 M.

[00111] For example, during the electrodialysis or the electrolysis, temperature of the aqueous composition comprising lithium sulphate or lithium compound can be at least substantially maintained at a value of about 20 to about 80 °C, about 20 to about 60 °C, about 30 to about 40 °C, about 50 to about 60 °C, or about 46 to about 54 °C.

[00112] For example, when an aqueous composition comprising NH_3 is introduced into the anodic compartment during the electrodialysis or the

electrolysis, temperature of the aqueous composition comprising lithium sulphate can be at least substantially maintained at a value of about 20 to about 80 °C, about 75 to about 85 °C, about 20 to about 60 °C, about 30 to about 40 °C, about 35 to about 65 °C, about 40 to about 60 °C, about 35 to about 45 °C, about 55 to about 65 °C, about 50 to about 60 °C or about 46 to about 54 °C.

[00113] For example, during the electrodialysis or the electrolysis, electrical current can be at least substantially maintained at a density of about 400 to about 3000 A/m², about 500 to about 2500 A/m², about 1000 to about 2000 A/m², about 400 to about 1200 A/m², about 400 to about 1000 A/m², about 300 to about 700 A/m², about 400 to about 600 A/m², about 425 to about 575 A/m², about 450 to about 550 A/m², or about 475 to about 525 A/m².

[00114] For example, during the electrodialysis or the electrolysis, electrical current can be at least substantially maintained at a density of about 30 to about 250 mA/cm², 50 to about 250 mA/cm², about 75 to about 200 mA/cm² or about 100 to about 175 mA/cm².

[00115] For example, during the electrodialysis or the electrolysis, electrical current can be at least substantially maintained at a constant value.

[00116] For example, during the electrodialysis or the electrolysis, voltage can be at least substantially maintained at a constant value.

[00117] For example, during the process, voltage can be at least substantially maintained at a constant value that is about 3 to about 10 V or about 4 to about 7 V. For example, the cell voltage can be at least substantially maintained at a value of about 1.0 V to about 8.5 V, about 1.0 V to about 3.0 V, about 2.0 V to about 3.0 V, about 3.0 V to about 8.5 V, about 6.5 V to about 8 V, about 5.5 V to about 6.5 V or about 6 V.

[00118] For example, during the electrodialysis or the electrolysis, the overall current efficiency can be about 50% to about 90%, about 60% to about 90%, about 60% to about 85%, about 60% to about 70%, about 60% to about 80%, about 65% to about 85%, about 65% to about 80%, about 65% to about 75%, about 70% to about 85% or about 70% to about 80%.

[00119] For example, during the electrodialysis or the electrolysis, the overall LiOH current efficiency can be about 50% to about 90%, about 60% to about 90%, about 60% to about 70%, about 60% to about 80%, about 65% to about 85%, about 65% to about 80%, about 65% to about 75%, about 70% to about 85% or about 70% to about 80%.

[00120] For example, during the electrodialysis or the electrolysis, the overall H₂SO₄ current efficiency can be about 55% to about 95%, 55% to about 90%, about 60% to about 85%, about 65% to about 80%, about 85 % to about 95 % or about 70% to about 80%.

[00121] For example, the aqueous composition comprising Li⁺ and at least one metal ion can be reacted with the base so as to obtain a pH of about 4.8 to about 6.5, about 5.0 to about 6.2, about 5.2 to about 6.0, about 5.4 to about 5.8 or about 5.6.

[00122] For example, the aqueous composition comprising Li⁺ and at least one metal ion can be reacted with lime.

[00123] For example, the at least one metal ion comprised in the aqueous composition that is reacted with the base so as to obtain a pH of about 4.5 to about 6.5 can be chosen from Fe²⁺, Fe³⁺ and Al³⁺.

[00124] For example, the at least one metal ion comprised in the aqueous composition that is reacted with the base so as to obtain a pH of about 4.5 to about 6.5 can comprise Fe³⁺.

[00125] For example, the at least one metal ion comprised in the aqueous composition that is reacted with the base so as to obtain a pH of about 4.5 to about 6.5 can comprise Al³⁺.

[00126] For example, the at least one metal ion comprised in the aqueous composition that is reacted with the base so as to obtain a pH of about 4.5 to about 6.5 can comprise Fe³⁺ and Al³⁺.

[00127] For example, the at least one hydroxide comprised in the precipitate can be chosen from Al(OH)₃ and Fe(OH)₃.

[00128] For example, the precipitate can comprise at least two hydroxides that are $\text{Al}(\text{OH})_3$ and $\text{Fe}(\text{OH})_3$.

[00129] For example, the base used so as to obtain a pH of about 4.5 to about 6.5 can be lime.

[00130] For example, lime can be provided as an aqueous composition having a concentration of about 15 % by weight to about 25 % by weight.

[00131] For example, the processes can further comprise maintaining the aqueous composition comprising Li^+ and the at least one metal ion that is reacted with a base so as to obtain a pH of about 4.5 to about 6.5 at an oxidative potential of at least about 350 mV.

[00132] For example, the aqueous composition can be at least substantially maintained at an oxidative potential of at least about 350 mV by sparging therein a gas comprising O_2 . For example, the gas can be air. Alternatively, the gas can be O_2 .

[00133] For example, the processes can comprise reacting the aqueous composition comprising Li^+ and having the reduced content of the at least one metal ion with the another base so as to obtain a pH of about 9.5 to about 11.5, about 10 to about 11, about 10 to about 10.5, about 9.8 to about 10.2 or about 10.

[00134] For example, the base used so as to obtain a pH of about 9.5 to about 11.5 can be NaOH or KOH or LiOH .

[00135] For example, the base used so as to obtain a pH of about 9.5 to about 11.5 can be NaOH .

[00136] For example, the base and metal carbonate can be a mixture of aqueous NaOH , NaHCO_3 , LiOH and LiHCO_3 .

[00137] For example, the at least one metal carbonate can be chosen from Na_2CO_3 , NaHCO_3 , and $(\text{NH}_4)_2\text{CO}_3$.

[00138] For example, the at least one metal carbonate can be Na_2CO_3 .

[00139] For example, the aqueous composition comprising Li^+ and having the reduced content of the at least one metal ion can be reacted with the another base over a period of time sufficient for reducing the content of the at least one metal ion in the aqueous composition below a predetermined value. For example, the at least one metal ion can be chosen from Mg^{2+} , Ca^{2+} and Mn^{2+} . For example, the reaction can be carried out over a period of time sufficient for reducing the content of Ca^{2+} below about 250 mg/L, about 200 mg/L, about 150 mg/L, or about 100 mg/L. For example, the reaction can be carried out over a period of time sufficient for reducing the content of Mg^{2+} below about 100 mg/L, about 50 mg/L, about 25 mg/L, about 20 mg/L, about 15 mg/L or about 10 mg/L.

[00140] For example, the ion exchange resin can be a cationic resin.

[00141] For example, the ion exchange resin can be a cationic resin that is substantially selective for divalent and/or trivalent metal ions.

[00142] For example, contacting with the ion exchange resin can allow for reducing a content of Ca^{2+} of the composition below about 10 mg/L, about 5 mg/L, about 1 mg/L or about 0.5 mg/L.

[00143] For example, contacting with the ion exchange resin can allow for reducing total bivalent ion content such as Ca^{2+} , Mg^{2+} and Mn^{2+} of the composition below about 10 mg/L, about 5 mg/L, about 1 mg/L or about 0.5 mg/L.

[00144] For example, the acid roasted lithium-containing material can be leached with water so as to obtain the aqueous composition comprising Li^+ and at least three metal ions chosen from the following metals iron, aluminum, manganese and magnesium.

[00145] For example, the acid roasted lithium-containing material can be leached with water so as to obtain the aqueous composition comprising Li^+ and at least three metal ions chosen from Al^{3+} , Fe^{2+} , Fe^{3+} , Mg^{2+} , Ca^{2+} , Cr^{2+} , Cr^{3+} , Cr^{6+} , Zn^{2+} and Mn^{2+} .

[00146] For example, the acid roasted lithium-containing material can be leached with water so as to obtain the aqueous composition comprising Li^+ and at least four metal ions chosen from Al^{3+} , Fe^{2+} , Fe^{3+} , Mg^{2+} , Ca^{2+} , Cr^{2+} , Cr^{3+} , Cr^{6+} , Zn^{2+} and Mn^{2+} .

[00147] For example, the acid roasted lithium-containing material can be β -spodumene that has been previously reacted with H_2SO_4 .

[00148] For example, the acid roasted lithium-containing material can be obtained by using a process as described in CA 504,477.

[00149] For example, the acid roasted lithium-containing material can be α -spodumene, β -spodumene, lepidolite, pegmatite, petalite, amblygonite, hectorite, smectite, clays, or mixtures thereof, that has been previously reacted with H_2SO_4 .

[00150] For example, the base-baked lithium-containing material can be β -spodumene that has been previously reacted with Na_2CO_3 and with CO_2 , and eventually heated.

[00151] In the processes of the present disclosure, the pH can thus be controlled by further adding some base, some acid or by diluting. The ORP can be controlled as previously indicated by sparging air.

[00152] For example, when reacting the aqueous composition comprising Li^+ and the at least one metal ion with a base so as to obtain a pH of about 4.5 to about 6.5 and thereby at least partially precipitating the at least one metal ion under the form of at least one hydroxide so as to obtain a precipitate, the metal of the at least one metal ion can be Fe, Al, Cr, Zn or mixtures thereof.

[00153] For example, when reacting the aqueous composition comprising Li^+ and having the reduced content of the at least one metal ion with another base so as to obtain a pH of about 9.5 to about 11.5, and with optionally at least one metal carbonate, thereby at least partially precipitating at least one

metal ion, the metal of the at least one metal ion can be Mn, Mg, Ca or mixtures thereof.

[00154] For example, when contacting the aqueous composition comprising Li^+ and having a reduced content of the at least one metal ion with an ion-exchange resin so as to at least partially remove at least one metal ion, the at least one metal ion can be Mg^{2+} , Ca^{2+} or a mixture thereof.

Example 1

[00155] As shown in the exemplary process 10 of Figure 1, lithium hydroxide 12 can be obtained, for example, by using such a process 10 and by using a pre-leached lithium-containing material as a starting material. For example, the exemplary process 10 can comprise concentrate leach 14, primary impurity removal 16, secondary impurity removal 18, ion exchange 20 and membrane electrolysis 22. For example, various leached ores such as acid roasted β -spodumene can be used. The process shown in Figure 1 can also be used for producing lithium carbonate 24. According to another embodiment, the starting material can be a lithium compound such as lithium sulphate, lithium chloride or lithium fluoride. In such a case, the process would be shorter and would be starting at membrane electrolysis 22.

Acid Roasted β -Spodumene (AR β -spodumene)

[00156] Two different blends of the AR β -spodumene were tested. The samples were composed of different ratios of the flotation and dense media separation (DMS) concentrates. The samples were identified as 75/25 and 50/50. The former sample contained about 75% by weight of the flotation concentrate and about 25% by weight of the DMS concentrate. The latter sample contained substantially equal portions by mass of the two concentrates. The assay data of the feed samples is summarized in Table 1. The two samples had very similar analytical profiles. The 75/25 sample had higher levels of Fe, Mn, Mg, Ca and K than the 50/50 sample. Both samples had typical compositions for AR β -spodumene.

Table 1. Assay Data of the AR β -Spodumene Samples

Sample	Li	Si	Al	Fe	Na	S
	%					
75/25 Comp	2.24	25.0	10.5	1.04	0.39	6.09
50/50 Comp	2.29	24.4	10.4	0.96	0.36	6.06
Sample	Cr	Zn	Mn	Mg	Ca	K
	g/t					
75/25 Comp	167	134	1962	1186	3431	3653
50/50 Comp	163	103	1755	905	2311	3376

Concentrate Leach (CL) and Primary Impurity Removal (PIR)

[00157] The objectives of the Concentrate Leach (CL) and the Primary Impurity Removal (PIR) were 1) to dissolve lithium sulphate contained in the AR β -spodumene and 2) to remove the major impurities from the process solution that co-leach with lithium from the feed solids.

[00158] Figure 2 shows another embodiment of an exemplary process of the present disclosure. In the exemplary process 100 of Figure 2, acid roasted β -spodumene 102 was subjected to concentrate leach (CL; 104) and primary impurity removal (PIR; 106, 108 and 110). As shown in Figure 2, a four tank cascade was used (Bailey trending in all tanks) for the combined CL and PIR process circuit. The AR β -spodumene 102 was added using a feed hopper that was equipped with a vibratory feeder. Each of the reactors 104, 106, 108 and 110 was equipped with the following: an overhead mixer motor (0.5 hp; 112, 114, 116 and 118) with a 4-blade pitch impeller attached (120, 122, 124 and 126), pH and ORP (Oxidation Reduction Potential) probes. The PIR reactors 106, 108 and 110 also had air spargers located directly below the impeller. The process slurry flowed by gravity from one reactor to the next through overflow ports. The overflow port of the CL reactor 104 was set such that the active volume of the tank was about 32 L. The PIR reactors 106, 108 and 110 each had an active volume of about 14 L. The overflow from PIR Tank 3 (110; the last reactor of the tank train) was pumped (PIR P5; 128) to the filtration station (pan filter 130).

[00159] About 1,200 kg of the 75/25 and about 1,400 kg of the 50/50 AR β -spodumene samples 102 were leached in about 85 hours of operation. The

change over from one feed to the other occurred at the 37th hour of operation. Time zero of the operation was when pulp began to overflow from the CL reactor 104.

[00160] In the CL step, water and solids were combined in an agitated tank 104 at a 50:50 weight ratio and mixed for about 30 to about 45 minutes under ambient conditions. Lithium was extracted along with undesirable gangue metals such as, for example, iron, aluminum, silicon, manganese, and magnesium. The obtained slurry (CL slurry) thus comprised a solid composition and an aqueous (liquid) composition containing solubilized Li^+ (lithium ions) as well as solubilized ions of the above-mentioned metals. The CL slurry pH and ORP were monitored but not controlled. Alternatively, the pH can eventually be controlled by further adding some base, some acid or by diluting. The ORP can also be controlled as previously indicated by sparging air 132. The CL slurry flowed by gravity to the PIR Tank 1 106. The aqueous composition can alternatively be separated from the solid composition before being introduced in the PIR Tank 1 106 (or before carrying out PIR. In such a case, the aqueous composition (instead of the whole CL slurry as it is the case for the present example) would be inserted into PIR Tank 1 106.

[00161] After 9 hours of operation there was sufficient volume of the Wash 1 fraction 134 (the first displacement wash fraction generated when washing the combined CL and PIR solids residue) to recycle back to the CL. The initial recycle rate of the Wash 1 134 was set to about 50% of the water addition requirement of the CL. After 37 hours of operation, this amount was increased to make-up 60% of the water addition to the process. This wash stream contained on average about 12 g/L Li (about 95 g/L of Li_2SO_4).

[00162] Primary Impurity Removal (PIR) was carried out, for example, to substantially remove Fe, Al and Si from the aqueous composition while substantially not precipitating any lithium. In this process, the pH of the concentrate leach slurry (comprising the aqueous composition and the solid composition) was elevated to about 5.6 by lime 136 slurry addition to the three PIR tanks (106, 108 and 110). The lime 136 was added as a slurry having a

concentration of about 20 wt%. The CL slurry was thus converted into a precipitate and an aqueous composition. The impurities such as Fe, Al and Si were at least substantially precipitated as insoluble metal hydroxides and found in the precipitate while the lithium ions were substantially found in the aqueous composition. The retention time for the PIR circuit was about 45 to about 60 minutes. Air 132 was sparged into the PIR tanks 106, 108 and 110 in order to maintain the oxidative potential of the process slurry at or above about 350 mV. At this level, iron present in the ferrous (Fe^{2+}) form would likely oxidize to ferric iron (Fe^{3+}), a form suitable for precipitation at such a pH. Thus, a precipitate comprising, for example, metal hydroxides of Fe, Al and Si was obtained and eventually separated from the aqueous composition comprising lithium ions. In the PIR, the pH can thus be controlled by further adding some base, some acid or by diluting. The ORP can be controlled as previously indicated by sparging air 132.

[00163] The resulting slurry (comprising the aqueous composition and the solid composition (comprising the precipitate)) was filtered on pan filters 130. The filtrate (aqueous composition comprising lithium ions and having a reduced content of the above mentioned metals (such as Fe, Al and Si)) proceeded to Secondary Impurity Removal (SIR). The PIR filter cake underwent three displacement washes. The first wash fraction 134 was collected separately from the second two washes 138. The first wash stream was recycled to the CL process as a portion of the water feed stream to recover the contained lithium. Wash fractions 2 and 3 138 were combined and stored as a solution. This solution can be used for lime 136 slurry make-up to recover the lithium units.

[00164] The lithium tenors in CL and PIR are presented in Figure 3. At hour 9, the first wash fraction 134 from PIR was recycled back to the CL tank to make-up half of the water addition to the leach. Lithium tenors increased throughout the circuit to about 18 g/L (about 142.6 g/L of Li_2SO_4) as a result. At hour 37.5, the recycle rate was increased to make-up 60% of the water to the leach and lithium tenors increased to about 25 g/L (about 198 g/L of Li_2SO_4). The PIR first wash 134 lithium tenors ranged from about 12 to about 15 g/L (about 95 g/L to about 118.8 g/L of Li_2SO_4).

[00165] The pH was substantially steady throughout the operation once the throughput was reduced. The ORP of the slurry in PIR tank 3 110 was substantially steady and above about 350 mV during the operation. The iron tenors for CL and PIR are presented in Figure 4. At hours 10 and 54, the pH of PIR3 110 was near a value of about 5.6 and yet the iron tenor in the PIR3 110 liquor increased.

[00166] Iron and aluminum profiles are presented in Figures 4 and 5. Both iron and aluminum showed increasing levels in the CL tank 104 throughout the run. Iron levels maintained below about 5 mg/L in PIR3 110 for most of the run regardless of the increase observed in CL. Aluminum in PIR3 110 was less than about 10 mg/L for the first 40 hours, and then ranged between about 20 and about 65 mg/L for the remainder of the operating time.

[00167] A mass balance for the CL and PIR circuits is shown in Table 2. Lithium extraction and impurity precipitation is calculated based on solids assays. The mass balance shows that overall about 82% of the lithium present in the AR β -spodumene 102 feed proceeded to Secondary Impurity Removal (SIR). Specifically, about 79% lithium extraction was achieved for the 75/25 blend and about 86% for the 50/50 blend. The portions of aluminum and iron that either did not leach or precipitated totaled about 96 % and about 99%, respectively.

Table 2. Mass Balance of CL and PIR circuits

Process Streams	Quantity, kg	Metal Content, mg/L or %				
		Li	Al	Fe	Cr	Zn
INPUTS Op Hr		% or mg/L	g/t or mg/L			
AR B-Spodumene						
13.5	485	2.25	106909	9792	173	130
25.5	436	2.19	102675	10072	192	154
37.5	323	2.15	101087	10352	211	177
49.5	407	2.21	104792	11261	212	148
61.5	435	2.28	106909	8883	212	119
73.5	363	2.31	107438	8813	182	88
80.0	205	2.31	107438	8813	182	88
PIR Wash 1						
13.5	113	11200	77	11.2	< 0.2	5.6
25.5	252	11200	77	11.2	< 0.2	5.6
37.5	214	11200	77	11.2	< 0.2	5.6
49.5	273	15300	65	4.3	< 0.2	5.9
61.5	273	15300	65	4.3	< 0.2	5.9
73.5	249	12300	64	3.1	< 0.2	3.5
80.0	157	12600	62	1.5	< 0.2	3.6
OUTPUTS		Li	Al	Fe	Cr	Zn
PIR3 Solids						
13.5	536	0.60	126491	11960	247	133
25.5	277	0.40	121198	11471	229	160
37.5	268	0.58	119611	13219	211	187
49.5	333	0.31	123315	13079	211	164
61.5	294	0.46	126491	11051	210	140
73.5	282	0.48	124374	10771	201	141
80.0	169	0.50	125962	11051	201	141
PIR3 Solution						
13.5	600	10700	37.3	60.5	< 0.2	5.5
25.5	642	20100	6.95	1.05	< 0.2	3.9
37.5	470	16400	1.3	0.8	< 0.2	1.7
49.5	515	24550	36.45	3.3	< 0.2	5.4
61.5	582	23550	71	3.2	< 0.2	4.6
73.5	484	22800	19.5	2.15	< 0.2	3.45
80.0	290	25900	65.5	3.4	< 0.2	4.8

* Averages if shown in italics

Process Streams	Density, kg/L	% Solids	Metal Units, g				
			Li	Al	Fe	Cr	Zn
INPUTS Op Hr							
AR B-Spodumene							
13.5			10912	51847	4749	84	63
25.5			9555	44797	4394	84	67
37.5			6938	32621	3340	68	57
49.5			8995	42653	4583	86	60
61.5			9907	46455	3860	92	52
73.5			8397	39053	3203	66	32
80.0			4732	22007	1805	37	18
PIR Wash 1							
13.5	1.06		1195	8	1	0	1
25.5	1.07		2631	18	3	0	1
37.5	1.06		2262	15	2	0	1
49.5	1.10		3800	16	1	0	1
61.5	1.12		3748	16	1	0	1
73.5	1.09		2821	15	1	0	1
80.0	1.08		1829	9	0	0	1
OUTPUTS			Li	Al	Fe	Cr	Zn
PIR3 Solids							
13.5		47.2	3218	67836	6414	132	71
25.5		30.1	1107	33534	3174	63	44
37.5		36.3	1556	32094	3547	57	50
49.5		39.3	1032	41042	4353	70	54
61.5		33.6	1354	37238	3253	62	41
73.5		36.8	1353	35070	3037	57	40
80.0		36.8	844	21268	1866	34	24
PIR3 Solution							
13.5	1.07		5995	21	34	0	3
25.5	1.12		11477	4	1	0	2
37.5	1.11		6970	1	0	0	1
49.5	1.15		10953	16	1	0	2
61.5	1.15		11926	36	2	0	2
73.5	1.15		9580	8	1	0	1
80.0	1.16		6464	16	1	0	1
Units IN							
13.5			12107	51855	4750	84	64
25.5			12186	44815	4397	84	68
37.5			9200	32636	3343	68	58
49.5			12795	42669	4585	86	62
61.5			13655	46471	3861	92	53
73.5			11218	39068	3204	66	33
80.0			6560	22017	1805	37	19
TOTAL			77722	279532	25945	517	356
Units OUT							
13.5			9212	67857	6448	132	74
25.5			12584	33538	3174	63	46
37.5			8527	32095	3547	57	51
49.5			11985	41058	4355	70	57
61.5			13281	37274	3255	62	44
73.5			10934	35078	3038	57	41
80.0			7308	21284	1867	34	25
TOTAL			73830	268184	25684	475	338

Extraction							
13.5			71				
25.5			88				
37.5			78				
49.5			89				
61.5			86				
73.5			84				
80.0			82				
TOTAL			82				
Precipitation							
13.5				131	135	158	113
25.5				75	72	76	66
37.5				98	106	83	88
49.5				96	95	81	90
61.5				80	84	67	80
73.5				90	95	86	124
80.0				97	103	91	132
TOTAL				96	99	92	93
Accountability, OUT/IN %							
			76	131	136	158	117
			103	75	72	76	68
			93	98	106	83	87
			94	96	95	81	92
			97	80	84	67	82
			97	90	95	86	126
			111	97	103	91	135
TOTAL			95	96	99	92	95

Secondary Impurity Removal

[00168] Secondary Impurity Removal (SIR) was performed on the PIR filtrate (aqueous composition comprising lithium ions and having a reduced content of the above mentioned metals (such as Fe, Al and Si)) to substantially precipitate and remove Ca, Mg and Mn impurities therefrom. Feed addition to the SIR circuit started at operating hour 6 (six hours after

overflow from the CL tank 104). As shown in Figure 2, there are four process tanks arranged in a cascade 142, 144, 146 and 148. The tank volumes could be adjusted during the run from about 11.8 to about 17.5 L by changing the tank overflow ports. All tanks are baffled and agitated by overhead mixers 150, 152, 154 and 156. pH, ORP and temperature were monitored in all tanks 142, 144, 146 and 148 (Bailey™ trending in all tanks).

[00169] In the first two agitated tanks 142 and 144, the pH was increased to about 10 using about 2 M sodium hydroxide 158 (NaOH) (another base). Following this pH adjustment, an excess of sodium carbonate 160 (Na₂CO₃) based on levels of targeted impurities in the feed was added to the third tank 146 to convert the remaining divalent impurities to insoluble carbonates. The slurry from the third tank 146 was pumped (SIR P6; 162) to a clarifier 164. Underflow solids were removed and recovered by filtration (pan filter 166) while the overflow solution was collected in an about 1000 L tote 168.

[00170] Averaged impurity tenors of solutions from the Concentrate Leach stage 104 through to the final tank 148 of Secondary Impurity Removal are shown in Table 3 and Figure 6.

Table 3. Profile of Selected Impurities

Stream	Li mg/L	Al mg/L	Fe mg/L	Cr mg/L	Zn mg/L	Mn mg/L	Mg mg/L	Ca mg/L
CL	23880	1737	985	5.9	9.1	178	109	468
PIR1	21290	34	9	0.0	4.3	174	153	435
PIR2	21240	28	8	0.0	4.0	173	175	433
PIR3	21140	30	8	0.0	4.2	174	179	434
SIR1	20093	1	0	0.0	0.0	2	43	426
SIR2	22500	0	0	0.0	0.0	1	19	352
SIR3	19050	1	0	0.0	0.0	1	16	322
SIR4	22400	0	0	0.0	0.0	1	14	241

[00171] Impurities introduced in the leach stage 104 included iron, aluminum, chromium, zinc, magnesium, manganese and calcium. Substantially all of the chromium and over about 98% of the iron and aluminum substantially precipitated in the first PIR tank (PIR1 106). Minimal precipitation occurred in the next two tanks of PIR (PIR2 108 and PIR3 110). By the first tank of SIR (SIR1 142), the only impurities substantially remaining

in solution were magnesium and calcium. All other elements were less than about 1 mg/L. Although most of the precipitation occurred in SIR1 142, the extra retention time of SIR2 144 dropped the magnesium tenor from about 40 to about 20 mg/L. From SIR2 144 through SIR4 148, magnesium and calcium tenors showed a steady decline with more retention time. Impurity levels for SIR4 148 averaged to about 1 mg/L Mn, about 14 mg/L Mg and about 241 mg/L Ca during the pilot plant run. However, levels as low as about 200 mg/L Ca and about 2 mg/L Mg were attained by the optimization of key parameters.

[00172] pH and ORP were monitored throughout the operation. pH was only controlled in the first two tanks 142 and 144. Initially, the selected pH for SIR2 144 was about 10. At operating hour 30, the pH in SIR2 144 was increased to about 10.5. With the exception of a 2 hour period at hour 50, where the pH in SIR2 144 dropped to about 10, pH remained at about 10.5 for the remainder of the run. The average pH values achieved over the two periods were about 10.1 and about 10.5 and the resulting sodium hydroxide consumptions were about 0.022 and about 0.024 kg sodium hydroxide per hour, respectively. The overall sodium hydroxide consumption was about 10 kilograms of sodium hydroxide solution per about 1000 kg of lithium carbonate equivalent (LCE).

[00173] The impurity tenors of SIR2 144 solutions are plotted over time in Figure 7. These solutions have been pH adjusted by sodium hydroxide 158 to above 10, but have not yet been dosed with sodium carbonate 160. Magnesium tenors are lower after the adjustment, but the levels show a gradual trend downwards that appears to begin prior to the set point change. It should be noted that later in the pilot plant, the retention time was increased for all SIR tanks 142, 144, 146 and 148, which may have also contributed to improved precipitation performance.

[00174] Calcium and magnesium tenors in solutions leaving SIR4 148 are plotted in Figures 8 and 9. These Figures relate impurity tenor (Mg and Ca only) with the sodium carbonate dosage used at the time the sample was taken. Additionally, the data are plotted based on the retention times of the entire SIR circuit 140 at the time of each sample. Within the range tested, as

the sodium carbonate 160 increased, metal tenors decreased. It should be noted that the lowest impurity tenors also corresponded with greater circuit 140 retention time. Sodium carbonate 160 dosage is expressed as molar excess of calcium impurities present prior to sodium carbonate addition (using assays from SIR2 144). The data indicated that the solution tenor of Ca can decrease to below about 200 mg/L.

[00175] Product from the SIR circuit 140 was assayed every about 4 hours as it left the final tank (SIR4 148) (see Figure 2). The SIR4 148 product was pumped into an about 100 L clarifier 164 and the overflow from the clarifier was filtered through an about 0.5 μm spiral wound cartridge filter (1.0 μm) 170 and then collected in about 1000 L plastic totes 168 (pH/ORP/T Bailing trending). These totes 168 were assayed again to confirm bulk calcium feed tenors for Ion Exchange (IX). When the totes 168 were sampled light brown solids were observed in the bottom of each tote 168. Assays revealed a significant drop in calcium tenor from the solutions leaving the final tank of the circuit 140 (SIR4 148) to the solution sitting unmixed in the totes 168. A comparison of the average assays for both streams is presented in Table 4, below.

Table 4. Effect of Aging on SIR Product

Stream	Mg mg/L	Ca mg/L
SIR4 Product	17	286
IX Feed Tote	15	140

[00176] A mass balance for the SIR circuit 140 is shown in Table 5. The mass balance shows that overall about 92% of the magnesium and all of the manganese reported to the solids. The distribution of lithium to the solids is about 0.9% for an overall SIR lithium recovery of about 99.1%.

Table 5. Mass Balance of SIR circuit

Process Streams		Quantity, kg	Metal Content, mg/L or %		
			Mn	Mg	Ca
INPUTS	Op Hr		g/t or mg/L		
SIR Feed					
	13.5	600	72	69	438
	25.5	642	109	111	463
	37.5	470	146	209	459
	49.5	515	199	216	451
	61.5	582	227	181	415
	73.5	484	203	154	441
	80.0	290	195	150	443
OUTPUTS			Mn	Mg	Ca
SIR Solids					
	Solids Pail 1	3.17	64700	63600	86300
	Solids Pail 2	4.03	68000	54700	85200
SIR4 Solution					
	13.5	176	0.7	18	309
	25.5	383	1.2	21	358
	37.5	426	1.6	48	370
	49.5	395	0.1	20	325
	61.5	208	0.2	7.6	191
	73.5	214	0.2	1.4	220
	80.0	206	0.4	1.5	225

Process Streams		Density, kg/L	Metal Units, g		
			Mn	Mg	Ca
INPUTS	Op Hr				
SIR Feed					
	13.5	1.08	40	38	242
	25.5	1.03	68	69	288
	37.5	1.12	62	88	193
	49.5	1.14	90	97	203
	61.5	1.10	121	96	220
	73.5	1.20	81	62	177
	80.0	1.17	48	37	109
OUTPUTS			Mn	Mg	Ca
SIR Solids					
	Solids Pail 1		205	201	273
	Solids Pail 2		274	221	343
SIR4 Solution					
	13.5	1.05	0	3	52
	25.5	1.09	0	7	126
	37.5	1.11	1	18	143
	49.5	1.15	0	7	112
	61.5	1.15	0	1	35
	73.5	1.20	0	0	39
	80.0	1.21	0	0	38

Precipitation = (1 - SIR4 solution / SIR Feed)*100				
13.5		100	92	79
25.5		99	89	56
37.5		99	79	26
49.5		100	93	45
61.5		100	99	84
73.5		100	100	78
80.0		100	99	65
TOTAL		100	92	62
Accountability, OUT/IN %		94	94	81
Distribution to Solids		100	92	53

SIR Lithium Recovery

SIR solids, kg Li	0.3
SIR total out, kg Li	36.3
Lithium Recovery, %	99.1

Ion Exchange

[00177] The SIR product is processed through an ion-exchange (IX) circuit to further reduce the Ca and Mg tenors prior to lithium product production. The IX circuit 172 comprises three columns packed with Purolite™ S950, a cationic resin that can be used in the sodium form that is selective towards divalent and trivalent metal ions. Purolite™ S950 comprises an aminophosphonic resin supported on a macroporous cross-linked polymer. It can be used for the removal of heavy metal cations. At high pH it can be active in the removal of Group 2 metal cations (Mg, Ca and Ba) and Cd, Ni and Co. At high pH divalent metal cations are preferentially absorbed over monovalent metal cations (e.g. Li, Na, K). Any ion exchange resin that would be suitable for substantially selectively removing divalent metal cations such as Ca²⁺ and Mg²⁺ and/or trivalent metal cations could be alternatively used in the present disclosure. Alternatively, more than one type of resin can be used to selectively remove the various metal cations. Thus, different ion exchange resins can be used for different metal cations.

[00178] The operating philosophy used for the IX circuit was a Lead-Lag Regeneration process (see Figures 2 and 10). Two of the IX columns of the circuit are involved with Ca and Mg removal, while the resin regeneration cycle is conducted on the third column. A schematic illustrating the solution flow through the IX circuit 400 and the lead-lag regeneration operation is provided in Figure 10. As shown in Figure 10, the loading 402 (upper schematic) and 404 (lower schematic) of Ca and Mg (Feed Wash) will take place on two columns; lead [upper schematic: Column 1 (406); lower schematic: Column 2 (408)] and lag [upper schematic: Column 2 (410); lower schematic: Column 3 (412)] and will produce an effluent (upper schematic: 414; lower schematic: 416) having both Ca and Mg solution tenors below about 10 mg/L which travels to the product carboy (174 in Figure 2). The loaded column [Figure 10, upper schematic: Column 3 (418); lower schematic: Column 1 (420)] undergoes stripping and regeneration stages (upper schematic: 422; lower schematic: 424) prior to being reintroduced as the lag column for the next loading cycle. The columns were constructed from clear PVC pipe. Each column had a diameter of about 15 cm and a height of about 76 cm. The bed volume of each column was about 10 L.

[00179] The parameters for the IX operation are summarized in Table 6. These parameters were based on the laboratory tests results and the Lead-Lag column configuration was designed to process 75 bed volumes (BV) of feed solution before the Ca and Mg tenors in the Lag effluent exceeded established upper limit that was about 10 mg/L that was established for each cation. After processing 75 BV's of feed solution the combined absorption capacity of the resin in the Lead and Lag columns would not be sufficient to produce a final effluent with the Ca and Mg tenors each below about 10 mg/L. At this point the loading cycle is complete. The Lead column is promoted to the Regeneration stage. The Lag column takes the Lead position. The Regenerated column becomes the Lag column. As shown in Figures 2 and 10, effluent from the Strip/Regeneration stage travels to a waste solution drum (Figure 10, upper schematic: 426; lower schematic: 428; Figure 2, 176).

[00180] Referring to Figure 2, the Regeneration stage involved washing the Lead column with reverse osmosis (RO) water 178 to flush out the Li rich solution within the column. This solution is passed to the Lag column. The Feed Wash stage is followed by Acid Strip using about 2 M HCl 180. This removes the absorbed Ca, Mg, Li and other metal cations from the resin. The resin is now in the acid form. An Acid Wash stage (RO water 178) follows to rinse the remaining HCl(aq) from the column. The resin is then converted to the Na form by passing about 2 M NaOH 182 through the column (Regeneration Stage). The final step involves washing the excess NaOH from the column using reverse osmosis (RO) water 178. The resin is now regenerated and ready to be promoted to the Lag position for the next Loading cycle. The effluent from the Acid Strip cycle was collected separately. The effluents from the Acid Wash, Regeneration and Regeneration Wash cycles were all captured in the same drum.

[00181] The Acid Strip stage produces a solution that contains Li, Ca, and Mg. The data indicated that Li elutes from the column first followed by Ca and Mg. It can be possible to separately capture the Li fraction and as a result produce a lithium chloride solution.

Table 6. IX Pilot Operation Parameters

IX Stage	Solution	Bed Volume (BV)	Rate, BV/h
Loading	IX Feed	75	5
Feed Wash	RO Water	1.5	5
Acid Strip	2 M HCl	3	5
Acid Wash	RO Water	5	5
Regeneration	2 M NaOH	3	5
Regeneration Wash	RO Water	3	5

1 BV = 10 L

[00182] A total of about 2154 L of SIR Product solution was processed through the IX circuit in four cycles. The average Li, Ca, and Mg tenors of the feed solutions for each cycle are summarized in Table 7.

Table 7. IX – Average Feed Solution Li, Ca and Mg Tenors

IX Cycle	Average Feed Solution Tenor, mg/L		
	Li	Ca	Mg
C1	16480	176	28.2
C2	17600	140	12.9
C3 & C4	21940	78.7	3.6

[00183] A cycle was initially designed to operate the Loading stage for 75 BV's. The average loading flow rate was about 832 mL/min (about 49.9 L/h). Cycle 1 was the only cycle where 75 BVs of feed solution was passed through the Lead-Lag columns.

[00184] The Ca Loading curve for Cycle 1, where the Ca tenor of the effluents from the Lead and Lag columns are plotted against cumulative bed volume processed, is presented in Figure 11. Also plotted on this plot is the average Ca tenor in the feed solution and the selected limit for Ca tenor in the Lag effluent (about 10 mg/L) for the present example. The breakthrough point for Ca of the Lead column occurred at 7.5 BV. The Ca tenor of the Lead effluent was about 82.3 mg/L after 75 BV's indicating that the loading capacity of the Lead column was not reached for Ca. The breakthrough point for Ca of the Lag column occurred at about 35 BV. The Ca tenor in the Lag effluent increased above about 10 mg/L between the 60th and 65th BV. It was decided to continue the Loading stage of Cycle 1 through to the 75th BV point even though the Lag effluent was above about 10 mg/L of Ca. The effluent from the 65th to 75th BV point was diverted to an about 200 L drum and kept separate from the main product solution of Cycle 1. The diverted solution was later combined with the main Cycle 1 product when it was determined that the Ca tenor in the resulting combined solution would not exceed about 10 mg/L.

[00185] A similar loading profile for Mg for Cycle 1 is presented in Figure 12. The average Mg tenor in the feed solution and for example an upper limit of Mg tenor in the Lag effluent (about 10 mg/L) are also included in this plot. The breakthrough point for Mg of the Lead column occurred at 7.5 BV's. After 75 BV's the Mg tenor of the Lead effluent was about 9.5 mg/L. The breakthrough point for Mg of the Lag column occurred at 52.5 BV's. After 75 BV's the Mg

tenor of the Lag effluent was about 0.8 mg/L, well below the selected limit level for Mg in the IX product solution, according to this example.

[00186] Cycles 2 and 3 had to be stopped before 75 BV's of feed solution could be processed through the columns. The Ca tenors of the Lag effluent for each IX cycle are plotted against cumulative BV in Figure 13. In the case of Cycle 2 the Ca breakthrough points for the Lead and Lag columns occurred at < about 7.5 and about 23 BV, respectively. Cycle 2 was stopped after about 68 BV. The Ca in the Lag effluent had reached about 13 mg/L at after about 60 BV's. Breakthrough of Ca for the Lag column of Cycle 3 occurred within the first 5 BV's. Cycle 3 was stopped after about 30 BV's. The tenor of the Ca in the Lag effluent at the 30 BV point was about 7.7 mg/L.

[00187] The balance of the Cycle 3 feed solution was processed over about 36.4 BV's in Cycle 4. The Ca breakthrough points for the Lead and Lag columns for Cycle 4 occurred at < about 7.5 and about 7.5 BV, respectively. Extrapolation of the Cycle 4 Lag effluent Ca tenor data indicated that the product solution would have a Ca tenor > about 10 mg/L after 60 BV's.

[00188] The Mg tenors of the Lag effluent for each IX cycle are plotted against cumulative BV in Figure 14. It is clear that the Mg tenor in the Lag effluent never approached a level close to the level of about 10 mg/L.

[00189] The average Li tenors of the Lead effluent for each IX cycle are plotted against cumulative BV in Figure 15. Also included in this plot are the average Li tenors of the feed solutions. The data indicated that substantially no Li loaded onto the resin.

[00190] The Li, Ca and Mg tenors in the Acid Strip effluents of Cycle 1 and 2 are plotted against cumulative BV in Figure 16. The data indicate that Li is stripped first from the resin and reaches for example an upper limit tenor in the range of about 0.5 and about 1.5 BV's. The Ca and Mg eluted from the resin starting around 1 BV and both reach for example an upper limit tenor at

about 2 BV. The three metals are eluted from the resin after 3 BV's. The Ca and Mg profiles for Cycle 3 and 4 were similar.

[00191] Reagent consumptions are reported relative to the LCE produced on a kg per about 1000 kg basis. The lithium sulphate stream produced from Ion Exchange contained about 39.1 kg of Li (this includes 100% of the lithium units in a PIR PLS sample (Figure 2, 184) that did not undergo SIR and IX). The equivalent mass of lithium carbonate that could be produced given no losses in downstream processes would equal about 187.7 kg.

[00192] The IX circuit 172 produced about 2006 L of product solution. The assay data of the IX Product solutions are summarized in Table 8. The Li tenor ranged from about 15.7 to about 21.9 g/L. The ranges of the Ca and Mg tenors were about 2.4 to about 5.7 mg/L and < about 0.07 to about 0.2 mg/L, respectively. Other constituents of note were Na and K at about 3.5 g/L and about 0.1 g/L on average, respectively. The elements that assayed below the detection limits of the analytical technique are also listed in Table 8.

Table 8. IX Product Solution Assays

IX Product	Solution Tenor, mg/L								
	Li	SO ₄	Cl	Na	K	Ca	Sr	Mg	Ba
Carboy 1	15700	120000	5	3980	107	3.8	0.61	0.2	0.03
Carboy 2	16700	120000	4	1990	105	5.7	0.9	0.18	0.043
Carboy 3	21900	160000	5	4470	117	2.4	0.74	< 0.07	0.05
Elements Assaying below Detection (Detection Limits provided in mg/L)									
Ag	Al	As	Be	Bi	Cd	Co	Cr	Cu	Fe
< 0.5	< 0.8	< 3	< 0.002	< 1	< 0.3	< 0.3	< 0.2	< 0.1	< 0.2
Mn	Mo	Ni	P	Pb	Sb	Se	Sn	Ti	Tl
< 0.04	< 0.6	< 1	< 5	< 2	< 1	< 3	< 2	< 0.1	< 3
U	V	W	Y	Zn					
< 1	< 0.07	< 2	< 0.02	< 0.7					

[00193] The mass balance for the IX circuit 172 is provided in Table 9. Good accountability for Li was obtained. About 2.7% of the Li was lost in the Strip/Regeneration process solution. The process removed about 97.6% of the Ca and about 99.0% of the Mg contained in the feed solutions.

[00194] The IX circuit 172 met the process objectives by reducing the Ca and Mg tenors in the product solution to below about 10 mg/L for each metal cation. Further, a high quality lithium sulphate solution was produced.

Table 9. IX Mass Balance

		Assays, mg/L or %		
Process Stream	kg or L	Li	Ca	Mg
SIR Feed C1	750	16480	176	28.2
SIR Feed C2	682	17600	140	12.9
SIR Feed C3	359	21940	78.7	3.6
SIR Feed C4	364	21940	78.7	3.6
IX Product Carboy 1	914	15700	3.8	0.2
IX Product Carboy 2	478	16700	5.7	0.18
IX Product Carboy 3	614	21900	2.4	< 0.07
IX Regen Reject Drum 1	202	16.9	35.5	2.47
IX Regen Reject Drum 2	208	12.2	16.7	< 0.07
IX Strip - Solids	0.8	0.002	26.5	0.0004
IX Strip - Solution	111	8760	718	229
Elemental Masses IN, kg				
Process Stream		Li	Ca	Mg
SIR Feed C1		12.36	0.13	0.02
SIR Feed C2		11.99	0.10	0.01
SIR Feed C3		7.87	0.03	0.00
SIR Feed C4		7.99	0.03	0.00
Total IN, kg		40.2	0.28	0.03
Elemental Masses OUT, kg				
Process Stream		Li	Ca	Mg
IX Product Carboy 1		14.35	0.00	0.00
IX Product Carboy 2		7.99	0.00	0.00
IX Product Carboy 3		13.45	0.00	0
IX Regen Reject Drum 1		0.00	0.01	0.00
IX Regen Reject Drum 2		0.00	0.00	0
IX Strip - Solids		0.00	0.22	0.00
IX Strip - Solution		0.97	0.08	0.03
Total OUT, kg		36.8	0.32	0.03
Distribution, %				
Product		97.3	2.4	1.0
Tails		2.7	97.6	99.0
Distribution Total		100.0	100.0	100.0
OUT/IN, %		91.4	112.4	80.3
Li Loss, %		2.7		
M Removed, %			97.6	99.0

[00195] Examination of the semi-quantitative x-ray diffraction (SQ-XRD) data of composite samples of the CL/PIR residues showed that each sample contains both α - and β -spodumene. The SQ-XRD data for the CL/PIR residues generated from each of the two feed samples (75/25 and 50/50) are summarized in Table 10. The presence of α -spodumene indicates that the phase transition step that was conducted by a third party vendor (acid roast of

α -spodumene) was not 100% efficient. Any Li present in this form would thus not be chemically available to the hydrometallurgical process. It should be noted that the efficiency of the phase transition step (conversion from α -spodumene to β -spodumene) is not 100% and therefore a percentage of the contained Li in the feed to the Hydrometallurgical process is as α -spodumene.

Table 10. SQ-XRD Data of the two CL/PIR Residue Types

Chemical Composition	75/25 CL/PIR Residue Drum 1- 5, wt%	50/50 CL/PIR Residue Drum 7- 14, wt%
$H(AlSi_2)O_6$	60.6	67.3
<i>Spodumene beta</i>	12.0	9.4
SiO_2	11.6	7.5
$NaAlSi_3O_8$	3.6	3.8
$CaSO_4 \cdot (H_2O)$	2.7	4.4
$KAlSi_3O_8$	1.6	3.6
$LiAlSi_2O_6$	2.2	2.5
$Ca(SO_4)(H_2O)_{0.5}$	2.5	-
$\alpha FeO \cdot OH$	1.9	-
Fe_3O_4	-	1.6
$CaSO_4 \cdot 2H_2O$	1.1	-
$\gamma\text{-}Mn_3O_4$	0.3	-
	100.1	100.1
Li Bearing Mineral	Relative Distribution of Li, %	
<i>Spodumene beta</i>	94.9	92.7
$LiAlSi_2O_6$	5.1	7.3

[00196] The Li units that are in the CL/PIR residues as β -spodumene were never available to the process and as a result provide a false low Li recovery value.

[00197] An adjusted Li recovery was calculated that did not consider the Li units tied up as β -spodumene in the CL/PIR residue. The data for this calculation are summarized in Table 11. The total Li in all of the out process streams was about 63.2 kg. This included about 11.7 kg of Li in the CL/PIR residue that was present as β -spodumene. The adjusted total Li out value thus becomes about 51.6 kg.

The total recoverable Li by the overall process was about 46.9 kg. The adjusted total Li recovery is then calculated to be about 95.8%.

Table 11. Adjusted Total Li Recovery

	Li Mass, g
Total Li OUT based on Assays	60615
Total Li Recovered	46884
Total Li in CL/PIR Residue as β -Spodumene	11655
Total Li OUT minus Li as β -Spodumene	48960
Adjusted Total Li Recovery, %	95.8

[00198] A high grade lithium sulphate solution was thus produced. In accordance with Figure 1, this solution can be used, for example, as the lithium source in the production of a solution of high quality lithium hydroxide and/or high quality lithium carbonate. This high grade lithium sulphate solution can also be used as a feed in the production of other high grade lithium products. For example, as shown in Figure 2, the lithium sulphate solution can be pumped (ME P1; 186) to an LiOH membrane electrolysis (ME) cell 188. The LiOH•H₂O product 190 can optionally be obtained by evaporative crystallization 192. Li₂CO₃ can optionally be precipitated (PPT) 194 and polished 196 to obtain the Li₂CO₃ product 198.

[00198A] Figure 2 also shows the following pumps: PIR WSH P1 (200); PIR P1 (202); PIR P1-P2 (204); PIR P6 (206); SIR P1 (208); SIR P2 (210); SIR P3 (212); SIR P4 (214); SIR P7 (216); SIR P8 (218); SIR P9 (220) and IX P1 (222); and the following surge tanks: PIR PLS (224; pH/ORP/T Bailey trending); SIR (226); and clarifier (228). Figure 2 also shows PLS (230) and site water (232).

Example 2

Electrolysis : conversion of Li₂SO₄ into LiOH

[00198B] The electrolysis was conducted using an electrolysis method in a monopolar three-compartment membrane electrolysis (ME) cell. The central compartment of the ME cell was separated from the cathodic compartment by a cationic membrane and from the anodic compartment by an anionic membrane. The cathodes comprised stainless steel (316) and the anode

comprised a Ti mixed metal oxide (MMO) layer. The basic schematic of the ME cell is provided in Figure 17. The central compartment of the cell was charged with low concentration lithium sulphate solution. The cathodic compartment was filled with lithium hydroxide solution. The anodic compartment was charged with dilute sulphuric acid solution at about 30 g/L. Under the influence of an electric field, lithium ions from the central compartment were transported through the cationic membrane into the cathodic compartment. In parallel the sulphate ions move through the anionic membrane into the anodic compartment. Meanwhile, hydroxyl ions are produced on the cathode and hence lithium hydroxide is formed in the catholyte. The anodic reaction generated protons resulting in the production of sulphuric acid as the anolyte. As a result the lithium concentration increases in the catholyte and drops in the central compartment during membrane electrolysis. During operation the Li tenor in the central compartment was maintained by the controlled addition of a concentrated lithium sulphate solution.

[00199] The cathodic and anodic compartments are fed with deionized water in order to keep the lithium hydroxide and sulphuric acid concentrations at predetermined levels.

[00200] The synthesis of lithium hydroxide was conducted using a stacked ME cell consisting of two three-compartment cells. The process flow diagram 500 of the ME circuit is provided in Figure 18. The main components of the cell were fabricated with high density polypropylene (HDP). The cathodes 502, 504 comprised 316 stainless steel and were about 100 cm x about 50 cm. The anode 506 was coated with titanium mixed metal oxide (MMO) and was about 100 cm x about 50 cm. The anode 506 was purchased from De Nora Tech (part number: *DNT-DX-09-118 Electrowinning Anodes sheet, coating code DN-475E both sides*).

[00201] The stack design of the ME cell allowed for essentially two ME cells that operated in parallel (left cell 508; right cell, 510). Further, the stacked configuration allowed for the anode 506 to be shared by the two cells. Each

cell 508, 510 comprises a cathodic compartment 512, 514 equipped with a cathode 502, 504, a central compartment 516, 518 and an anodic compartment 520, 522 with the shared electrode 506. The central compartment 516, 518 of the cell was separated from cathodic compartment 512, 514 by a cationic membrane 524, 526 Lanxess Ionac™-MC-3470 and from the anodic compartment 520, 522 by an anionic membrane 528, 530 Lanxess Ionac™-MA-7500. Effective working area of each membrane was about 0.84 m². The void space within each compartment was filled with polypropylene mesh to aid in dispersing the solution flow.

[00202] The electricity to the ME cell was supplied by a direct current rectifier unit 532, type SR DDS-5C024-02 manufactured by Hanson. The rectifier 532 had both an amp meter and a volt meter that were used for monitoring the voltage and current applied to the cell. The rectifier 532 was set on current control mode.

[00203] The lithium sulphate solution produced in the previous sections was used as a lithium source for the ME pilot plant (electrolysis). The composition of the feed solution is provided in Table 12.

Table 12. Composition of Feed Solution

Sample ID	Tenor of solution components, mg/L						
	Li	Na	K	Ca	Mg	Fe	Zn
IX Product Carboy 1	15700	3980	107	3.8	0.2	< 0.2	< 0.7
	Ag	Al	As	Ba	Be	Bi	Cd
	< 0.5	< 0.8	< 3	0.03	< 0.002	< 1	< 0.3
	Co	Cr	Cu	Mn	Mo	Ni	P mg/L
	< 0.3	< 0.2	< 0.1	< 0.04	< 0.6	< 1	< 5
	Pb	Sb	Se	Sn	Sr	Ti	Tl
	< 2	< 1	< 3	< 2	0.61	< 0.1	< 3
	U	V	W	Y		SO ₄	Cl
	< 1	< 0.07	< 2	< 0.02		120000	5

[00204] The ME cell was pre-filled prior to the start of the pilot plant. The central compartment 516, 518 of the cell was charged with an aqueous composition comprising lithium sulphate Feed solution that had been diluted down to about 2 g/L Li with RO water (thus about 15.8 g/L of Li₂SO₄). The

cathodic compartment 512, 514 was filled up with an aqueous composition comprising lithium hydroxide. About sixty litres of an aqueous composition comprising sulphuric acid (about 30 g/L) was prepared from reagent acid and used to fill the anodic compartment 520, 522. The composition of the starting material compositions were thus as follows (see Table 13).

Table 13. Compositions of Starting Material Compositions

Sample ID	Tenor of solution components, mg/L						
	Li	Na	K	Ca	Mg	Fe	Zn
Spent-Init	1300	452	14	< 0.9	< 0.07	< 0.2	< 0.7
Ca-Init	3100	740	30	< 0.9	< 0.2	< 0.07	< 0.7
An-Init	0.07	< 2	< 1	< 0.9	< 0.07	< 0.2	< 0.7
	Ag	Al	As	Ba	Be	Bi	Cd
Spent-Init	< 0.5	< 0.8	< 3	< 0.007	< 0.002	< 1	< 0.3
Ca-Init	< 0.5	< 0.8	< 3	< 0.007	< 0.002	< 1	< 0.3
An-Init	< 0.5	< 0.8	< 3	< 0.007	< 0.002	< 1	< 0.3
	Co	Cr	Cu	Mn	Mo	Ni	P
Spent-Init	< 0.3	< 0.2	< 0.1	< 0.04	< 0.6	< 1	< 5
Ca-Init	< 0.3	< 0.2	< 0.1	< 0.04	< 0.6	< 1	< 5
An-Init	< 0.3	< 0.2	< 0.1	< 0.04	< 0.6	< 1	< 5
	Pb	Sb	Se	Sn	Sr	Ti	Tl
Spent-Init	< 2	< 1	< 3	< 2	0.077	< 0.02	< 3
Ca-Init	< 2	< 1	< 3	< 2	0.049	< 0.02	< 3
An-Init	< 2	< 1	< 3	< 2	< 0.002	< 0.02	< 3
	U	V	W	Y		SO ₄	Cl
Spent-Init	< 1	< 0.2	< 2	< 0.02		13000	< 1
Ca-Init	< 1	< 0.2	< 2	< 0.02			
An-Init	< 1	< 0.2	< 2	< 0.02		24000	< 1

[00205] The central compartment 516, 518 of the cell was fed with the fresh aqueous composition comprising lithium sulphate (Feed). The feed flow rate was controlled to maintain about 2 g/L of Li in the central compartment 516, 518 (about 15.8 g/L of Li₂SO₄). The pH of the aqueous composition comprising lithium sulphate in the central compartment 516, 518 was maintained at a value of about 10 to about 12.

[00206] The spent electrolyte from central compartment was bled to the spent bleed tank 534. The bleed was taken from recirculation tubing before reaching spent reservoir 536 to ensure a low lithium tenor in the spent

electrolyte. The spent reservoir 536 had a cooling coil 538 cooled with river water 540. The bleed flow rate was controlled to maintain a constant level in the reservoir tank. The anolyte had both a bleed flow from anolyte reservoir 542 to anolyte bleed tank 544 and a dilution water 546 flow to the reservoir 542. The bleed flow rate was controlled to maintain level in the anolyte reservoir 542 by having the bleed tubing at a fixed level in the tank and ensuring the pump was set higher than the dilution water flow rate. The anolyte reservoir 542 had a cooling coil 548 cooled with river water 550. The dilution water flow rate was controlled to maintain a concentration of about 30 g/L concerning the aqueous composition comprising sulphuric acid (in the anodic cell 520, 522 (as monitored by free acid titrations)). The catholyte also had both a bleed flow to catholyte bleed tank 552 and a dilution water 554 flow to the catholyte reservoir 556. The catholyte reservoir 556 had a cooling coil 558 cooled with river water 560. The bleed flow rate for the catholyte was controlled to maintain the level in the reservoir. The bleed was taken from the recirculation tubing before reaching the reservoir 556 to ensure a high Li tenor and no contamination. Dilution water 554 for the catholyte was added to maintain lithium tenor at about 15 g/L (about 51.8 g/L in terms of LiOH) in the catholyte product (aqueous composition comprising LiOH). These flows are illustrated in Figure 18. Figure 18 also shows pumps 562, 564, 566 (anolyte recirculation pump), 568 (catholyte recirculation pump), 570, 572 (central recirculation pump), 574 and 576.

[00207] Grab samples from the central compartment 516, 518 (the spent solution) were taken every about 4 hours, profile samples were taken every about 6 hours and composite samples were taken every about 12 hours of the anolyte and every about 24 hours for the spent and catholyte. Titrations for lithium hydroxide in the catholyte and free acid titrations for the anolyte were done once an hour.

[00208] The ME pilot plant ran in two 5 day sections: Week 1 and Week 2. Each section operated continuously for the five days. Hourly readings were taken to monitor current, voltage, temperature, the flow rates, and product and feed weights. All of the readings were recorded in an Operation Log sheet.

At start-up a current of about 400 A was applied to the cell. The recirculation flow rate was set at about 3 L/min and the temperature set points on the cooling water for the circulation tanks was set to about 40 °C. During the operation of the pilot plant several changes were made to operating conditions in order to determine the effect the changes would have on production. The first change involved increasing the amperage from about 400 A to about 440 A, to see if it would be possible to increase the feed flow rate without decreasing the product Li tenor. Next the recirculation speed was increased from about 3 to about 6 L/min, to see if this would improve the efficiency of the cell. Another test carried out was to operate on voltage control rather than amperage control, by trying to achieve and maintain about 10 to about 12 V. Finally, the temperature set point on the cooling water for

the recirculation tanks was changed to about 50 °C and about 35 °C. Membrane electrolysis operation conditions are summarized in Tables 14 and 15.

Table 14. ME Pilot Plant Operation Conditions. Week One

	Time		Current A	Electrolysis time h	Current quantity Ah	Power Wh	Circ. Rate L/min	Temp. °C
	From	To						
Day 1	12-11 23:47	12-11 23:59	400	0.2	85	710	3	40
	12-05 10:43	12-05 23:59	400	13.3	5287	44837	3	40
	12-06 0:00	12-06 6:00	400	6.0	2398	19040	3	40
	Total			19.5	7770	64586		
Day 2	12-06 6:01	12-06 14:28	400	8.4	3373	31638	3	40
	12-06 14:29	12-06 23:59	440	9.5	4164	43448	3	40
	12-07 0:00	12-07 5:59	440	6.0	2619	28855	3	40
	Total			23.9	10156	103941		
Day 3	12-07 6:00	12-07 10:37	440	4.6	2026	24327	3	40
	Run 440 A			20.1	8809	96629		
	12-07 11:40	12-07 23:59	400	12.3	4915	51481	3	40
	12-08 0:00	12-08 5:59	400	6.0	2390	27229	3	40
	Total			22.9	9332	103037		
Day 4	12-08 6:00	12-08 11:59	400	6.0	2392	31380	3	40
	12-08 12:00	12-08 19:25	400	7.4	2959	27988	6	40
	12-08 19:54	12-08 21:08	400	1.2	490	4274	6	40
	12-08 21:16	12-08 23:59	400	2.6	1029	9107	6	40
	12-09 0:00	12-09 5:54	400	5.9	2357	21190	6	40
	Total			23.1	9227	93939		
Day 5	12-09 5:55	12-09 11:59	400	6.1	2423	22159	6	40
	Run 6 L/min			23.2	9259	84717		
	12-09 12:00	12-09 15:29	400	3.5	1394	17566	3	40
	12-09 15:30	12-09 23:59	400	8.5	3385	37798	3	40
	12-10 0:00	12-10 5:00	400	5	1987	18703	3	40
	Total			23.0	9190	96226		
	Total Week 1			113.0	45856	464366		

Table 15. ME Pilot Plant Operation Conditions. Week Two

	Time		Current A	Electrolysis time h	Current quantity Ah	Power Wh	Circ. Rate L/min	Temp. °C
	From	To						
Day 6	12-11 23:47	12-12 0:00	400	0.2	85	710	3	40
	12-12 0:00	12-12 5:54	400	5.9	2359	20381	3	40
	Total			6.1	2444	21091		
Day 7	12-12 5:55	12-12 11:58	400	6.0	2422	21166	3	40
	12-12 11:58	12-12 23:59	420	12.00	5029	49732	3	40
	12-13 0:00	12-13 5:53	420	5.9	2468	26658	3	40
	Total			23.9	9920	97556		
Day 8	12-13 5:54	12-13 17:55	420	12.0	5036	49160	3	40
	12-13 17:56	12-13 23:59	420	6.05	2539	25817	3	40
	12-14 0:00	12-14 5:53	420	5.9	2470	24367	3	40
	Total			24.0	10044	99344		
Day 9	12-14 5:54	12-14 7:58	420	2.1	869	8335	3	40
	12-14 8:37	12-14 18:00	420	9.4	3933	38591	3	40
	12-14 18:01	12-14 23:59	420	6.0	2502	25998	3	40
	12-15 0:00	12-15 5:51	420	5.9	2456	24553	3	40
	Total			23.3	9761	97477		
Day 10	12-15 5:52	12-15 17:59	420	12.1	5078	42651	3	40 - 50
	12-15 18:00	12-15 19:15	420	1.3	529	4793	3	35
	12-15 19:16	12-15 22:14	360 - 450	3.0	1273	12735	3	35
	12-15 22:15	12-15 23:59	420	1.7	733	6854	3	35
	12-16 0:00	12-16 5:52	420	5.9	2466	22448	3	35
	Total			23.9	10079	89480		
Day 11	12-16 5:53	12-16 21:00	420	15.1	6337	61175	3	35
	Test t=35°C			26.9	11338	108004		
	Total			15.1	6337	61175		
Total Week 2				116.3	48585	466122		

[00211] During the two 5-day pilot plants about 621 litres of the aqueous composition comprising lithium hydroxide and having a concentration of about 14.6 g/L of lithium (or about 49.9 g/L of lithium hydroxide) and about 2239 litres of the aqueous composition comprising sulphuric acid at a concentration of about 20 to about 30 g/L were produced. A total of about 675.8 litres of the aqueous composition comprising lithium sulphate was processed and about 425 litres of spent electrolyte containing about 2 to about 3 g/L of lithium was produced. Masses, volumes and densities of products produced are provided in Tables 16 and 17. The ME process was conducted for about 228 hours. During the operation about 930.5 kWh of electrical energy was consumed for lithium sulphate conversion to lithium hydroxide.

Table 16. ME Pilot Plant Products. Week One

Time	Anolyte		Spent		Catholyte		Feed	
	Mass	Volume	Mass	Volume	Mass	Volume	Mass	Volume
	kg	L	kg	L	kg	L	kg	L
Initial solution	60	59.1	50.2	59.5	40	39.5		
Day 1	235.8	231.7	70.8	69.6	6.6	6.3	87.3	78.9
Day 2	274.5	269.8	42.84	42.2	80.7	75.9	93.5	84.5
Day 3	270.5	266.0	40.61	40.1	83.0	78.6	88.7	80.2
Day 4	261.2	257.2	35.94	35.5	74.6	70.6	81.4	73.5
Day 5	225.8	222.1	35.10	34.6	65.2	61.6	74.1	66.9
Final solution	60	59.0	60.2	59.4	53.6	50.6		
Total Week 1	1267.8	1246.7	225.3	221.9	310.2	315.1	425.0	384.0

Table 17. ME Pilot Plant Products. Week Two.

Time	Anolyte		Spent		Catholyte		Feed	
	Mass	Volume	Mass	Volume	Mass	Volume	Mass	Volume
	kg	L	kg	L	kg	L	kg	L
Initial solution	60	59.0	60.2	59.4	53.5	50.5		
Day 6	64.5	63.6	10.3	10.0	13.4	12.7	19.6	17.7
Day 7	238.5	234.6	42.50	41.9	74.9	70.8	76.4	69.1
Day 8	233.4	229.5	48.01	44.3	75.3	71.1	75.3	68.1
Day 9	206.8	203.6	56.67	56.0	56.1	53.1	60.9	55.0
Day 10	165.2	162.7	53.2	52.5	46.2	43.7	54.1	48.9
Day 11	116.6	114.6	35.3	34.9	34.5	32.7	36.6	33.1
Final solution	43.6	42.9	24.0	23.8	76.0	72.0		
Total Week 2	1008.6	992.6	206.8	204.0	322.9	305.6	268.9	291.9

[00212] At the beginning, the starting material aqueous composition in the cathodic compartment contained only about 3.1 g/L Li (about 10.5 g/L of LiOH). During electrolysis the lithium tenor in the catholyte increased. It took about 13 hours for the Li tenor to reach the level of about 15 g/L (about 51.8 g/L of LiOH).

[00213] When the Li concentration in the catholyte approached about 15 g/L (about 51.8 g/L of LiOH), reverse osmosis water addition to the cathodic compartment was started. The continuous mode of ME was then started. The Li concentration in the catholyte was maintained by adjusting the dilution water flow to the catholyte reservoir. The Li concentration in catholyte grab samples was about 14 to about 18 g/L during the process (about 48.3 to about 62.1 g/L of LiOH). The Li tenor in the catholyte is plotted against electrolysis time during continuous electrolysis period in the first week of pilot plant operations in Figure 19. During the second week of pilot plant

operations the Li tenor was about 15 to about 16.3 g/L (about 51.8 to about 56.2 g/L of LiOH) (Figure 20). The Li assays for the profile samples differ from Li tenor in grab samples. This happened because the results were obtained by different methods. The Li tenors in the grab samples were determined by titration with hydrochloric acid. The Li tenors in the profile samples were measured using atomic absorption spectroscopy (AAS). The titration results indicate the total hydroxide in solution, including hydroxides of Li, Na and K. The AAS results only report Li in solution.

[00214] Assay results of selected metals for the profile samples collected from the left and right line of the catholyte stream are listed in Table 18 and Table 19. The catholytes of the left and right compartments were close in composition. The similarity of these values indicated that electrical current was distributed to both cathodes equally and both cells were working with the same effectiveness.

Table 18. Assays for catholyte profile samples - Week One.

Sampling time	Tenor, mg/L									
	Li		Na		K		Ca		Mg	
	Left	Right	Left	Right	Left	Right	Left	Right	Left	Right
05Dec 1800	8580	10900	2330	2770	82	101	1.6	1.9	<0.07	<0.07
06Dec 0200	14100	14200	4090	4150	131	115	2.2	2.3	<0.07	<0.07
06Dec 1000	15000	14800	4070	4020	107	107	<0.9	2.1	<0.07	0.08
06Dec 1800	16100	16100	4450	4720	123	128	2.6	2.4	<0.07	<0.07
07Dec 0200	17200	17500	4050	4470	119	119	2.7	2.7	<0.07	<0.07
07Dec 1000	17300	17700	3790	4130	139	137	2.9	2.9	<0.07	<0.07
07Dec 1800	15400	15900	3550	3470	114	123	2.6	2.5	<0.07	<0.07
08Dec 0200	13900	13800	3220	3590	115	114	2.6	2.6	<0.07	<0.07
08Dec 1000	13300	13700	3450	3680	111	115	2.9	3.2	<0.07	<0.07
08Dec 1800	13900	14100	3540	3650	102	104	3.2	3.2	<0.07	<0.07
09Dec 0200	14900	15000	3940	4150	123	117	3.1	3.2	<0.07	<0.07
09Dec 1000	16100	15800	4380	4580	127	118	3.8	3.5	<0.07	<0.07
09Dec 1800	15500	15600	3840	3660	103	101	3.6	3.4	<0.07	<0.07
10Dec 0200	16500	13700	3920	3880	114	117	3.8	3.6	<0.07	<0.07

Table 19. Assays for Catholyte Profile Samples - Week Two

Sampling time	Tenor, mg/L									
	Li		Na		K		Ca		Mg	
	Left	Right	Left	Right	Left	Right	Left	Right	Left	Right
12Dec 0200	15300	14900	3410	3360	115	124	3.3	3.7	< 0.07	< 0.07
12Dec 1000	13900	14400	6110	3820	111	114	3.6	3.7	< 0.07	< 0.07
12Dec 1800	16100	16500	4240	3690	118	116	4	3.9	< 0.07	< 0.07
13Dec 0200	16200	16400	3480	3510	114	110	3.5	3.3	< 0.07	< 0.07
13Dec 1000	14500	14600	3430	3170	118	109	4	3.6	< 0.07	< 0.07
13Dec 1800	14600	14400	4070	4020	119	157	4.2	3.9	< 0.07	< 0.07
14Dec 0200	16200	16600	3810	3700	126	129	3.8	3.7	< 0.07	< 0.07
14Dec 1000	16000	15700	3770	3720	124	135	3.7	4.1	< 0.07	< 0.07
14Dec 1800	15200	14800	3690	3870	133	134	3.9	3.9	< 0.07	< 0.07
15Dec 0200	14700	14400	3560	3720	101	109	3.7	3.8	< 0.07	< 0.07
15 Dec 1000	14400	14300	3870	3980	125	128	3.7	3.8	< 0.07	< 0.07
15Dec 1800	14800	15300	4040	4240	138	141	3.8	3.9	< 0.07	< 0.07
16Dec 0200	14700	14700	3870	3860	129	125	3.6	3.4	< 0.07	< 0.07
16Dec 1000	13900	14000	3900	3880	124	126	3.9	3.8	< 0.07	< 0.07
16Dec 1800	14000	15600	4120	4270	130	132	4	4	< 0.07	< 0.07

[00215] Lithium hydroxide solution was collected in batches over a 24 h period. The batches were switched out during the Day shift operation. A sample from each drum was taken as day composite sample. Assay results for composite samples are listed in Tables 20 and 21.

[00216] The LiOH concentration in product batches starting the second day of pilot plant operation were about 47.3 to about 55.6 g/L (about 14 to about 16 g/L of Li). The obtained aqueous composition also comprised about 3.3 to about 4.5 g/L of Na, about 0.11 to about 0.18 g/L of K and about 2 to about 3.9 ppm Ca. Other impurities were present in non-significant amounts or were below the detection limit of the analytical method.

Table 20. Assays for Catholyte Composite Samples: Week One

Sampling time	Tenor, mg/L							
	Li	Na	K	Ca	Mg	Ba	Sr	Fe
11Dec-Init	14800	3630	108	3.5	< 0.07	0.06	0.56	0.5
12Dec 0600	14500	3260	117	3.9	0.55	0.058	0.63	0.7
13Dec 0600	14600	3640	117	3.7	< 0.07	0.047	0.646	< 0.2
14 Dec 0600	15500	3560	110	3.8	0.16	0.04	0.61	< 0.2
15Dec 0600	14100	3570	129	3.9	< 0.07	0.037	0.629	< 0.2
16Dec 0600	13700	3640	124	4	< 0.07	0.035	0.63	< 0.2
16Dec 2100	14200	3550	182	3.7	< 0.07	0.02	0.6	< 0.2
16Dec Final	16100	3390	119	3.6	< 0.07	0.03	0.59	0.2

Table 21. Assays for Catholyte Composite Samples: Week Two

Sampling time	Tenor, mg/L							
	Li	Na	K	Ca	Mg	Ba	Sr	Fe
11Dec-Init	14800	3630	108	3.5	< 0.07	0.06	0.56	0.5
12Dec 0600	14500	3260	117	3.9	0.55	0.058	0.63	0.7
13Dec 0600	14600	3640	117	3.7	< 0.07	0.047	0.646	< 0.2
14 Dec 0600	15500	3560	110	3.8	0.16	0.04	0.61	< 0.2
15Dec 0600	14100	3570	129	3.9	< 0.07	0.037	0.629	< 0.2
16Dec 0600	13700	3640	124	4	< 0.07	0.035	0.63	< 0.2
16Dec 2100	14200	3550	182	3.7	< 0.07	0.02	0.6	< 0.2
16Dec Final	16100	3390	119	3.6	< 0.07	0.03	0.59	0.2

[00217] At the beginning of pilot plant operation the Li tenor in the spent electrolyte fluctuated between about 1.5 and about 3.5 g/L. The Li tenor was stabilized by adjusting of feed flow rate to the central compartment of the cell. Spent electrolyte collected from the central compartment of the cell at steady state conditions contained about 2.1 to about 2.7 g/L of Li, about 0.36 to about 0.49 g/L of Na and about 8 to about 14 mg/L of K.

[00218] The sulphate tenors in anolyte profile samples are plotted in Figures 21 and 22. The sulphate tenor in the anolyte solution fluctuated through the range of about 26 to about 39 g/L during the first week of pilot plant operation. The level of sulphuric acid, during the second week, ranged from about 26 g/L to about 32 g/L.

[00219] Data obtained during pilot plant operation were used for calculations of lithium conversion rate, electrical current utilization efficiency,

current quantity and power consumption for synthesis of lithium hydroxide. Calculations have been done for each day and week of pilot plant operations as well as for each period of different operation conditions. Calculations were based on amounts of materials produced during the pilot plant campaign and were based on concentration changes in solutions floating in the membrane electrolysis cell. Lithium hydroxide synthesis conditions and calculated parameters are summarized in Tables 22 and 23.

Table 22. Lithium Hydroxide and Sulphuric Acid Synthesis Parameters - Week One

Test ID	Current	Electrolysis time	Current quantity	Power	Circ. Rate	Temp.	Compartment	Li transferred	Current effic.	Formed LiOH/H ₂ SO ₄				
	A	h	A*h	Wh	L/min	°C		g	%	g	g/h	g/A*h	g/kWh	
Day 1	400	19.5	7770	64586	3	40	Cathodic	734	36.5	2532	130	0.33	39.2	
							Central	1014	50.4	3497	180	0.45	54.2	
							Anodic		51.7	7353	377	0.95	113.8	
Day 2	400 - 440	23.9	10156	103941	3	40	Cathodic	1241	47.2	4281	179	0.42	41.2	
							Central	1179	48.1	4068	170	0.40	39.1	
							Anodic		48.3	8980	375	0.88	86.4	
440 A	440	20.1	8809	96629	3	40	Cathodic	1006	44.1	3471	173	0.39	35.9	
							Central	1078	47.3	3720	185	0.42	38.5	
							Anodic		45.1	7272	362	0.83	75.3	
Day 3	400 - 440	22.9	9332	103037	3	40	Cathodic	939	38.9	3241	141	0.35	31.5	
							Central	1167	48.3	4025	176	0.43	39.1	
							Anodic		43.3	7390	322	0.79	71.7	
Day 4	400	23.1	9227	93939	3 - 6	40	Cathodic	1112	46.5	3836	166	0.42	40.8	
							Central	1165	41.3	3407	147	0.37	36.3	
							Anodic		39.6	6681	289	0.72	71.1	
6 L/min	400	23.2	9259	84717	6	40	Cathodic	998	41.6	3443	148	0.37	40.6	
							Central	958	39.9	3305	142	0.36	39.0	
							Anodic		37.8	6403	276	0.69	75.6	
Day 5	400	23.0	9190	96226	6 - 3	40	Cathodic	868	36.5	2996	130	0.33	31.1	
							Central	971	40.8	3351	145	0.36	34.8	
							Anodic		39.1	6581	286	0.72	68.4	
Total Week 1	400 - 440	113.0	45856	464366	3 - 6	40	Cathodic	4894	41.2	16887	149	0.37	36.4	
							Central	5445	45.9	18788	166	0.41	40.5	
							Anodic		44.0	36893	327	0.80	79.4	

[00220] The membrane electrolysis stack of two cells equipped with Lanxess IonacTM membrane, with an effective working area of about 0.84 m², provided the possibility to produce up to about 179 g of lithium hydroxide per hour. The lithium conversion process performed with a current efficiency of about 43.5% during the first week and at about 34.9% during the second

week of pilot plant operation. The average amount of lithium hydroxide produced by per about 1 kWh of electrical energy was about 38.4 g and about 32.5 g for first and second week of pilot plant operation, respectively.

Table 23. Lithium Hydroxide and Sulphuric Acid Synthesis Parameters – Week Two

Test ID	Current	Electrolysis time	Current quantity	Power	Circ. Rate	Temp.	Compartment	Li transferred	Current eff.	Formed LiOH/H ₂ SO ₄				
	A	h	A*h	Wh	L/min	°C		g	%	g	g/h	g/A*h	g/kWh	
Day 6	400	6.1	2444	21091	3	40	Cathodic	228	36.0	787	129	0.32	37.3	
							Central	293	46.3	1012	166	0.41	48.0	
							Anodic		40.4	1569	257	0.64	74.4	
Day 7	400 - 420	23.9	9920	97556	3	40	Cathodic	1077	41.9	3716	155	0.37	38.1	
							Central	1086	42.3	3749	157	0.38	38.4	
							Anodic		39.6	7186	300	0.72	73.7	
Day 8	420	24.0	10044	99344	3	40	Cathodic	1140	43.8	3933	164	0.39	39.6	
							Central	940	36.1	3243	135	0.32	32.6	
							Anodic		37.3	6850	286	0.68	69.0	
Day 9	420	23.3	9761	97477	3	40	Cathodic	659	26.1	2274	98	0.23	23.3	
							Central	765	30.3	2639	113	0.27	27.1	
							Anodic		33.4	5964	256	0.61	61.2	
Day 10	360 - 450	23.9	10079	89480	3	35 - 50	Cathodic	592	22.7	2044	85	0.20	22.8	
							Central	598	22.9	2062	86	0.20	23.0	
							Anodic		25.5	4703	197	0.47	52.6	
t=35°C	420	26.9	11338	108004	3	35	Cathodic	755	25.7	2605	97	0.23	24.1	
							Central	803	27.3	2769	103	0.24	25.6	
							Anodic		34.0	7059	262	0.62	65.4	
t=50°C	420	6.0	2525	20022	3	50	Cathodic	231	35.4	798	133	0.32	39.8	
							Central	147	22.5	509	85	0.20	25.4	
							Anodic		22.4	1035	173	0.41	51.7	
Day 11	420	15.1	6337	61175	3	35	Cathodic	856	52.1	2952	195	0.47	48.3	
							Central	548	33.4	1891	125	0.30	30.9	
							Anodic		27.0	3134	207	0.49	51.2	
Total Week 2	400 - 420	116.3	48585	466122	3	35 - 50	Cathodic	4544	36.1	15678	135	0.32	33.6	
							Central	4229	33.6	14593	125	0.30	31.3	
							Anodic		37.0	32933	283	0.68	70.7	

[00221] It can thus be seen that various parameters have been tested. The person skilled in the art can thus infer that such tests provide a factual basis for making a sound prediction concerning various modifications that can be done to this process and obtaining the same utility. When selecting parameters concerning the temperature, the person skilled in the art will understand that such values can be selected as a function of the tolerance of the membranes and the materials of construction of the ME cell. Tables 24 and 25 provide mass balance for both weeks of tests.

Table 24. Mass Balance. Week One.

Materials	Vol	Assays, mg/L				
IN	L	Li	Na	K	Ca	Mg
Catholyte Initial	39.5	3100	740	30	<0.9	<0.07
Anolyte Initial	59.1	0.07	<2	<1	<0.9	<0.07
Central Initial	59.5	1880	452	14	<0.9	<0.07
Feed to Central	384.0	15700	3980	107	3.8	0.2
Water to catholyte	228.3	0	0	0	0	0
Water to anolyte	1314	0	0	0	0	0
OUT	L	Li	Na	K	Ca	Mg
Catholyte Final	53.6	15100	3900	116	3.7	<0.07
Anolyte Final	59.0	0	0	0	0	0
Central Final	59.4	3015	588	12.7	<0.9	<0.07
Product	293.0	14040	3792	124	2.68	< 0.07
Anolyte product	1247	0	0	0	0	0
Spent	222	2340	505.7	11.1	< 0.9	< 0.07
Materials	Mass	Elemental Mass, g				
IN	kg	Li	Na	K	Ca	Mg
Catholyte Initial	40.0	122	29.2	1.2	0	0
Anolyte Initial	60.0	0	0	0	0	0.0
Central Initial	60.2	112	27	1	0	0
Feed to Central	425	6029	1520	41	1.5	0.08
Water to catholyte	228	0	0	0	0	0
Water to anolyte	1314	0	0	0	0	0
OUT	kg	Li	Na	K	Ca	Mg
Catholyte Final	53.6	809	209	6	0.2	0
Anolyte Final	60.0	0	0	0	0	0.0
Central Final	60.2	179	35	1	0	0
Product	310	4208	1144	37	1	0.00
Anolyte product	1268	0	0	0	0	0
Spent	225	515	112	2	0	0
Sum IN	2128	6263	1584	43	2	0
Sum OUT	1977	5712	1500	47	1	0
Accountability %	92.9	91.2	94.7	107.9	67.3	n/a
Distribution (Calculated Head), %						
		Li	Na	K	Ca	Mg
Catholyte		87.8	90.2	93.1	100	n/a
Spent		12.2	9.8	6.9	0	n/a
Sumcheck		100	100	100	100	n/a

Table 25. Mass Balance. Week Two.

Materials	Vol	Assays, mg/L				
IN	L	Li	Na	K	Ca	Mg
Catholyte Initial	50.5	14800	3630	108	3.5	< 0.07
Anolyte Initial	59.0	446	199	10	< 0.9	< 0.07
Central Initial	59.4	5180	1500	55	< 0.9	< 0.07
Feed to Central	291.9	15700	3980	107	3.8	0.2
Water to catholyte	284.6	0	0	0	0	0
Water to anolyte	986	0	0	0	0	0
OUT	L	Li	Na	K	Ca	Mg
Catholyte Final	72.0	16100	3390	119	3.6	<0.07
Anolyte Final	42.9	0	2	0	0	0
Central Final	23.8	2300	356	8	<0.9	<0.07
Product	284	14433	3537	130	3.8	0.4
Anolyte product	993	0	0	0	0	0
Spent	239.6	2783	517	13	< 0.9	< 0.07
Materials	Mass	Elemental Mass, g				
IN	kg	Li	Na	K	Ca	Mg
Catholyte Initial	53.5	747	183.3	5.5	0.2	0
Anolyte Initial	60.0	26	12	1	0	0
Central Initial	60.2	308	89	3	0	0
Feed to Central	269	4583	1162	31	1.1	0.06
Water to catholyte	285	0	0	0	0	0
Water to anolyte	986	0	0	0	0	0
OUT	kg	Li	Na	K	Ca	Mg
Catholyte Final	76	1159	244	9	0.3	0
Anolyte Final	43.6	0	0	0	0	0
Central Final	24	55	8	0	0	0
Product	300	4132	1017	36	1.1	0.02
Anolyte product	1009	0	0	0	0	0
Spent	243	606	109	2.6	0	0
Sum IN	1713	5664	1446	40.5	1.3	0.06
Sum OUT	1696	5952	1378	47.2	1.4	0.02
Accountability %	99.0	105.1	95.3	116.3	105.3	31.5
Distribution (Calculated Head), %						
		Li	Na	K	Ca	Mg
Catholyte		88.9	91.5	94.1	99.2	100
Spent		11.1	8.5	5.9	0.8	0.0
Sumcheck		100	100	100	100	100

[00222] In view of the above examples, it can be the the that the contained lithium sulphate in the AR β -spodumene was leached with an efficiency of about 100%. It was observed that a retention time in the range of about 30 to about 45 minutes was sufficient for the CL. It was demonstrated that the CL

and PIR circuits can operate without necessarily having a liquid-solid separation step between the two circuits. The lime consumption was about 350 kg dry equivalent mass of lime per about 1000 kg of lithium carbonate equivalent (LCE).

[00223] It was also demonstrated that the SIR circuit can be operated in a continuous manner. Impurities such as calcium and magnesium were reduced to levels that can efficiently be processed through ion exchange columns. The consumption of NaOH was about 10 kg per about 1000 kg LCE. It was determined that calcium continued to precipitate from solution after this solution had left the SIR circuit. In one such example the calcium tenor in the SIR 4 reactor was about 286 mg/L. The filtrate of this solution on sitting for several hours had a calcium tenor of about 140 mg/L. The SIR product slurry was approximately about 0.4% solids by weight. These solids had a Li content of about 4.4% and accounted for about 0.5% of the total Li processed.

[00224] The processes were effective for reducing the calcium and magnesium tenors in the lithium sulphate solution to below about 10 mg/L.

[00225] The processes were effective for removing about 97.6% of the contained calcium and about 99.0% of the contained magnesium from the lithium sulphate solution. Therefore, a high purity and high quality lithium sulphate was produced. Only about 2.7% of the lithium was removed by the processes.

[00226] The processes involving the electrolysis carried out by membrane electrolysis in the three-compartment cell was effective for converting lithium sulphate to lithium hydroxide. It was demonstrated that the lithium hydroxide production from lithium sulphate could operate in a continuous manner using a three-compartment membrane electrolysis cell. The aqueous composition comprising lithium hydroxide was produced in the cathodic compartment, sulphuric acid was formed in the anodic compartment and a composition having a low tenor in lithium sulphate overflowed from the central compartment. The pilot plant produced about 621 litres of an aqueous

composition comprising lithium hydroxide having a concentration of about 14.6 g/L of lithium (about 50.4 g/L of lithium hydroxide) and about 2239 litres of sulphuric acid having a concentration of about 20 to 30 g/L. The lithium hydroxide that was produced was of a good quality. The aqueous composition comprising lithium hydroxide solution contained about 3.7 g/L of sodium and about 121 mg/L of potassium. The trace impurities present at levels of less than about 10 mg/L in the lithium hydroxide were Ba, Ca, Cr, Cu, Fe, Mg, Mn and Sr.

Example 3

Alternate process using ammonia to neutralize acid.

[00227] Applicant has previously shown in US 61/788292 that lithium hydroxide can be successfully recovered at high efficiencies from a lithium sulfate process stream at temperatures of about 40°C or about 60°C, using electrolysis with a Nafion 324 cation exchange membrane and either an Asahi AAV or a Fumatech FAB anion exchange membrane. In both cases, sulfuric acid was produced as a coproduct. An alternate process where ammonium sulfate is produced instead of sulfuric acid may be useful and the present disclosure details work demonstrating its feasibility. Tests were performed using a similar electrolysis cell as in US 61/788292, except that the highly resistive proton-blocking Fumatech™ FAB membrane was replaced with a Neosepta™ AHA membrane. The AHA membrane is an anion membrane manufactured by Astom™ (Japan) with a higher temperature stability (about 80 °C) and is expected to, for example have good electrical resistance for sulfate transport.

[00228] Current efficiency for hydroxide production (about 80% at about 3 M) matched the highest obtained in the previous studies when the feed was kept at an about neutral pH. Salt production at very high efficiency was initially possible. However, as the batch proceeded the hydroxide inefficiency (about 20%) caused an increase in the feed pH and the hydroxide in the feed competed with sulfate transport across the AHA membrane.

[00229] Based on the testing performed in the present studies, a continuous process using Nafion 324 and AHA membranes at about 60 °C would be expected to have the following characteristics, and is compared with results for the known Sulfuric Acid Process in Table 26 below.

Table 26. Comparison of Sulfuric Acid and Ammonium Sulfate Processes

	Sulfuric Acid Process	Ammonium Sulfate Process
Recommended Process	Batch	Continuous
Membranes	N324/FAB	N324/AHA
Sulfuric Acid / Ammonium Sulfate	0.75 M	3 M
Lithium Hydroxide	3 – 3.2 M	3 – 3.2 M
Average Current Density	100 mA/cm ²	150 mA/cm ²
Current Efficiency for Hydroxide	75%	80%
Cell Voltage in Custom Cell	6 V	4.6 V
Water Transport : Feed to Base	8 mol water per mol cation	8 mol water per mol cation
Water Transport: Feed to Acid	< 1 mol water per mol cation	12 mol water per mol cation

[00230] Previous studies (US 61/788292) have shown that lithium hydroxide can be successfully recovered at high efficiencies from a lithium sulfate process stream at temperatures of about 40°C or about 60°C, using electrolysis with a Nafion 324 cation exchange membrane and either an Asahi AAV or a Fumatech FAB anion exchange membrane. In both cases, sulfuric acid was produced as a coproduct. The production of sulfuric acid can limit, for example the choice of anion membrane in the system, the acid concentration which can be achieved and the temperature of operation.

[00231] Certain anion exchange membranes such as a proton-blocking membrane which has a high resistance especially for sulfate transport such as the Fumatech FAB membrane or a similar membrane, may, for example limit the current density achieved in a process for preparing lithium hydroxide. However, these membranes can be limited to a temperature of about 60 °C.

[00232] Highly concentrated ammonium sulfate (> about 2 M) can be produced in a similar electrolysis cell, and due, for example to the buffering capacity of bisulfate and the ability to dissolve ammonia in solution, it is possible to make the anolyte solution non-acidic as shown in Figure 23. In this

way, proton-blocking anion exchange membranes, for example may not be required and alternative membranes, for example a Neosepta AHA membrane which is capable of running at a temperature of about 80°C and that should have lower resistance can be used.

[00233] Such a process may, for example remove the higher resistance FAB membrane possibly allowing operation at either higher current density (thereby reducing membrane area), lower voltage (thereby reducing power consumption) or a combination of the two. It may also, for example, generate an alternate commercial material. Ammonium sulfate can be sold as an ingredient for fertilizer and should have a higher value than the sulfuric acid. It is also, for example expected to remove more water during the electrolysis from the feed thereby allowing more efficient operation over a wider range of feed conversion. It may also, for example, allow operation of the process at a higher temperature requiring less cooling of solutions. Solutions and membranes are also less resistive at these higher temperatures decreasing power consumption.

[00234] The tests performed on this system, where the anion membrane used in the previous process (Fumatech FAB) is replaced by a Neosepta AHA (Astom Corp.) membrane and ammonia is used to control the pH of the "acid" compartment of the cell are summarized below.

[00235] The experiments were carried out in an Electrocell™ MP cell similarly equipped to that used in the previous studies (US 61/788292) but wherein the anion membrane was replaced with a Neosepta AHA (Astom Corp.) membrane.

[00236] The various electrolyte circuits were similar to those used in the previous studies (US 61/788292), except that pH control was added to the anolyte (acid/salt) circuit. The pH controller actuated a solenoid valve which allowed addition of ammonia gas directly to the anolyte reservoir. Care was taken to not allow the anolyte pH to increase above about 5 as the DSA-O₂ coating can be removed at high pH. In addition to those analyses previously

performed, ammonium ion was analyzed by cation ion chromatography. All other aspects of the experimental setup were the same as described previously.

[00237] During the course of the present studies, experiments of varying duration were performed. These experiments evaluated the effect of temperature, current density, feed conversion, acid/salt concentration, base concentration and pH control strategy on current efficiencies, voltage and water transport. Concentration ranges and current efficiencies are summarized in Table 27. In the first two experiments, the concentration of base and acid/salt were allowed to increase from their starting values. The second experiment ran over two days to provide a greater amount of sulfate removal. In this case, due to volume limitations of the setup, water had to be added to the feed to obtain more than about 90% removal. In the remaining experiments water was only added to the acid and base compartments in an effort to maintain about constant salt and base concentrations (simulating continuous production). Experiments 856-81 through 856-86 were run under about constant acid (about 2.5-3 M sulfate) and base (about 2.8-3.1 M hydroxide) to probe the effect of varying temperature and current density. The final two experiments varied the control pH of the acid compartment in an effort to mediate problems with the resulting feed pH.

Table 27: Summary of Results for Ammonium Sulfate Production.
Sulfate current efficiency (CE) reported for each of the product streams.

Experiment	Conditions	FEED			ACID		BASE	
		[SO ₄ ²⁻] / M	SO ₄ ²⁻ CE ³	% REMOVAL	[SO ₄ ²⁻] / M	SO ₄ ²⁻ CE ³	[OH ⁻] / M	OH ⁻ CE
856-71	150 mA/cm ² , 60°C, no water	1.60 – 1.06	94%	61%	1.00 – 1.26	93%	1.43 – 2.97	76%
856-78	150 mA/cm ² , 60°C, water to base and feed	1.74 – 0.18	84%	95%	2.69 – 3.37	77%	2.34 – 3.38	77%
856-81	150 mA/cm ² , 60°C, water to base and acid	1.77 – 0.78	91%	80%	2.95 – 2.74	88%	2.97 – 2.79	79%
856-84	200 mA/cm ² , 60°C, water to base and acid	1.56 – 0.67	80%	83%	2.47 – 2.38	88%	2.79 – 3.08	83%
856-86	200 mA/cm ² , 80°C, water to base and acid	1.67 – 0.63	83%	86%	2.39 – 2.63	88%	3.08 – 2.97	80%

856-88	200 mA/cm ² , 60°C, lower acid pH	1.73 – 0.82	83%	78%	2.53 – 2.70	87%	2.97 – 3.20	80%
856-90	cont. 856-88 with new feed	1.73 – 0.75	72%	81%	2.70 – 3.72	75%	3.20 – 3.49	73%

[00238] Typically the sulfate current efficiency in the feed should equal the sulfate current efficiency in the acid. As shown in Table 27, there is a discrepancy of up to about 8% in some of the experiments. While not wishing to be limited by theory, the majority of this error is likely due to volume measurement error due to hold in the setup, for example when dealing with solutions of high concentration.

[00239] Figures 24-30 are plots relating to the experiments summarized in Table 27; Figures 24A-D relate to experiment 856-71; Figures 25A-G relate to experiment 856-78; Figures 26A-G relate to experiment 856-81; Figures 27A-F relate to experiment 856-84; Figures 28A-G relate to experiment 856-86; Figures 29A-G relate to experiment 856-88; and Figure 30 relates to experiment 856-90. The following sections further discuss the results of the present studies and aspects of the processes.

Lithium Hydroxide Production

[00240] The process produced lithium hydroxide at hydroxide concentrations of about 3 M. The efficiency was fairly consistent throughout the testing, giving numbers slightly below about 80% at about 150 mA/cm², increasing to over about 80% at the higher current density. In the last experiment, the lithium hydroxide concentration was allowed to increase to

about 3.5 M and the current efficiency decreased by about 7%. In these experiments, the efficiency is predominantly hydroxide back migration as, unlike the previous studies, the pH of the feed was always greater than about 7 eliminating any proton transport. However, there may also be some inefficiency associated with ammonium transport. As shown in Figure 26D, the composition of the hydroxide was mostly as lithium/sodium hydroxide with the ratio of lithium and sodium similar to that found in the feed.

Ammonium Sulfate Production

[00241] In the majority of the experiments, the ammonium sulfate concentration was kept at about 2.5 to about 3 M sulfate as shown in Figure 26E, which provided current efficiencies of about 90%. The loss of efficiency could not be accounted for by ammonium back migration. In the first experiment where the ammonium sulfate was at low concentration, very little ammonium was found in the feed (< about 20 mM) which accounts for less than about 1% of the charge. When the ammonium concentration was increased, the ammonium concentration increased to about 100 mM, which is still less than about 2% of the charge. Further analysis suggests that the remaining charge was due to hydroxide transport from the feed to the acid. The hydroxide back migration across the N324 membrane caused the feed pH to increase. Since experiment 856-78 was run to a greater percent removal, the experiment ran for a longer period of time at the higher hydroxide concentration, thereby decreasing the current efficiency of sulfate across the AHA membrane. Further details of this effect and its consequences are discussed in the next section.

Lithium Sulfate Feed Depletion

[00242] In the majority of the experiments (except 856-78), no water was added to the feed. Due to limitations of the setup (and time required for larger batches), most experiments were stopped after about 80% conversion. With the amount of water transport, the lithium sulfate concentration was still high at the end of the test as shown in Figure 26G. If no water transport had occurred, that the end sulfate concentration would have been about 0.35 M.

[00243] Figure 26G also shows the hydroxide concentration in the feed as a function of the charge passed. As shown, even at the end of the experiment, the hydroxide concentration is still increasing as hydroxide back migrates across the N324 membrane from the base. By the end of the experiment, the hydroxide concentration was similar to the sulfate concentration which decreased the efficiency of the process. Eventually, the amount of hydroxide leaving the feed to the acid compartment will equal the amount entering from base and the hydroxide concentration will reach a steady-state. This concentration may approach about 1 M hydroxide concentration.

Experimental Trial at Lower Acid pH (anolyte pH)

[00244] For example, in some experiments of the present studies, the feed pH was allowed to increase due to the hydroxide back migration in the feed. One control method that could be used to circumvent this issue is to add sulfuric acid into the feed to maintain its pH between about 7 and 10. Since the hydroxide production efficiency is about 80%, acid equaling about 20% of the charge would be required.

[00245] Alternatively, the pH setpoint on the acid/salt could be modified to allow for some proton back migration. In this case, if the feed pH is above a certain measured setpoint (for example about 9.5, about 9.7 or about 10), then the ammonia addition to the acid is stopped. The pH on the acid drops allowing for proton back migration until the feed pH decreases below the required setpoint. Ammonia is then added to the acid to increase the pH and the process is repeated. The above method allows for self-correction of the process and does not require any external sulfuric acid. It will be appreciated that pH measurement in solutions of high concentration salt may be inaccurate, as the sodium (and lithium) ions may, for example interfere with the measured pH. Typically the measured pH can be a couple of pH units different than the actual pH; typically lower in alkaline salt solutions and higher in acid. It will be appreciated that care must be taken to calibrate and offset for this effect, for example when using pH as a control algorithm. Graphs shown in the present disclosure are as measured.

[00246] The last two experiments used this type of control. 856-88 started with about 2.5 M ammonium sulfate at a pH of about 3.5 and was allowed to run without any further ammonia addition. As shown in Figure 29B, the hydroxide concentration in the feed continued to increase until about half way through the run, and then the concentration started to decrease slightly. This occurred with a measured feed pH of about 10 and a measured acid pH of about 0.5 as shown in Figure 29C. However, there still had not been enough proton transport to eliminate the feed pH increase. The point at which some conversion had occurred also corresponds to the point where all of the sulfate in the feed had been converted to bisulfate thereby producing some free acid. As shown in Figure 29E, the ammonium concentration equaled the sulfate concentration at about 1.9 mol of charge (about 2.5 M $(\text{NH}_4)\text{HSO}_4$).

[00247] The final experiment, 856-90, was a continuation of the previous experiment, except that new feed solution was used. As shown in Figure 30, the feed pH increased slightly and then stabilized before dropping to a pH of about 7, while the acid pH continued to decrease. At about a recorded acid pH of -0.25, the feed pH started to decrease rapidly, and ammonia addition was restarted. The acid pH increased again to a point where proton back migration was limited and the feed pH started to increase. Samples of the acid were taken just before ammonia addition was restarted and after it was stopped. The sample before addition was analyzed as about 3.4 M sulfate with about 0.6 M proton (indicating about 3.1 M NH_4HSO_4 plus about 0.3 M H_2SO_4). After ammonia addition, the solution was again about 3.4 M sulfate, but contained about 3.3 M bisulfate and about 0.1 M sulfate, indicating that the free proton had been neutralized.

[00248] The present tests demonstrated that it is possible to run the process in this way. The current efficiencies for hydroxide production, feed sulfate removal and acid sulfate production (as shown in Table 27) were more closely balanced. However, the caustic strength was slightly higher for this run, making the overall current efficiency closer to about 73%.

[00249] The concentration of ammonium in the salt running at a measured pH of about zero is about half the concentration of the same sulfate concentration solution running at a pH of about 3.5 (i.e. NH_4HSO_4 instead of $(\text{NH}_4)_2\text{SO}_4$) which would decrease the amount of ammonium back migration and therefore the amount of ammonium transport into the base.

Cell Voltage and Water Transport

[00250] An advantage of the ammonium sulfate system over the sulfuric acid system was the potentially higher current density and lower cell voltage that could be obtained when the highly resistive Fumatech FAB membrane was removed from the process.

[00251] Table 28 shows the cell voltage ranges obtained for the current work, requiring about 6 V at about 150 mA/cm^2 and about 6.5 V at about 200 mA/cm^2 . In previous work, a constant cell voltage of about 7.8 V was used to obtain an average current density of about 100 mA/cm^2 . Therefore higher current densities have been obtained at lower voltages. a cell with about 2 mm solution gaps run as low as about 4.6 V at about 60°C . It will be appreciated that there is less change from the Prodcell to the commercial cell since the feed can be run at higher conductivity. Running the cell at about 80°C decreased the cell voltage by about 0.6 V when running at about 200 mA/cm^2 . However, this impact may be less in the commercial cells as the main improvement is in solution conductivity and the commercial cell has smaller solution gaps.

Table 28: Cell Voltage Range and Water Transport Numbers.

Experiment	Conditions	Voltage / V	Water Transport ($\text{mol H}_2\text{O} / \text{mol Q}$) ⁵		
			Feed	Acid	Base
856-71	150 mA/cm^2 , 60°C , no water addition	6.4 – 5.5	9.3	4.4	4.7
856-78	150 mA/cm^2 , 60°C , water addition to base and feed	5.6 – 6.3	10.9	4.4	6.2
856-81	150 mA/cm^2 , 60°C , water addition to base and acid	5.9 – 5.8	9.6	8.8	5.9
856-84	200 mA/cm^2 , 60°C , water addition to base and acid	6.8 – 6.4	10.7	5.9	7.5

856-86	200 mA/cm ² , 80°C, water addition to base and acid	6.0 – 5.7	10.2	3.8	6.5
856-88	200 mA/cm ² , 60°C, lower acid pH	6.0 – 6.3	9.0	4.6	6.3
856-90	cont. 856-88 with new feed	6.5 – 6.8	8	2.4	7.7

[00252] Water transport in this system was fairly high, averaging about 10 mol of water transport per mol of charge (about 22 mol water per mol of lithium sulfate transport). This is about half the water required in order to maintain a constant feed concentration and therefore allow the system to run in a completely continuous process. It may be possible to incorporate a reverse osmosis unit on the feed stream to remove the remaining water, thereby allowing full conversion of the feed. The experiments running at lower acid pH had lower associated water transport. While not wishing to be limited by theory, this effect is likely due to some water transport associated with proton back migration and lower osmotic drag into the acid. Although the sulfate concentration was about the same in the two solutions, there was much less ammonium in the last two experiments.

[00253] The water transport numbers are quoted per mole of charge. Per mole of cation in the base, these numbers need to be divided by the current efficiency. Per mole of sulfate into the acid, these numbers need to be multiplied by two and divided by the current efficiency.

[00254] Based on the testing performed in the present studies, the process may, for example produce ammonium sulfate at a concentration of about 3 M or higher if lower pH control was used, produce lithium hydroxide at a concentration of about 3 M, have an average current density of about 150 mA/cm², have a current efficiency of about 80% for hydroxide production, have a cell voltage of about 4.6 V for a custom-designed cell, have water transport from feed to base of about 8 mol water per mol cation and have water transport from feed to acid/salt of about 12 mol water per mol sulfate or less if a lower pH on acid is used, for example.

[00255] When compared to the previous sulfuric acid process, these conditions may, for example decrease the required cell area for a plant producing about 3 tonne/hour of LiOH, by over about 35%. It may also, for example decrease the power consumption for a commercially designed cell from about 8.9 kWh/kg of LiOH to about 6.4 kWh/kg of LiOH (in an about 3 M solution). It also may, for example produce between about 8-10 tonne/hour of ammonium sulfate (dry basis) depending on the feed pH control regime.

[00256] Hydroxide back migration across the N324 membrane increases the pH of the feed. This transport may affect the overall process and different control strategies may be used to provide steady operation. Three different control strategies may, for example be used:

[00257] For example sulfuric acid may be used to control the feed pH around a neutral to slightly basic pH (about 7-9). This method, for example require an additional control circuit and may, for example require purchase of sulfuric acid. The additional sulfuric acid purchased is converted into ammonium sulfate. Lithium hydroxide production may still be at about 80% current efficiency and ammonium sulfate may be between about 90%-100%. An inefficiency may be ammonium back-migration across the AHA. This option may be useful if, for example a suitable sulfuric acid source, and an outlet for the ammonium sulfate produced exists.

[00258] For example, no remediation may be performed and the feed pH may increase until the inefficiency of hydroxide across the AHA matches that of hydroxide across the N324. This may, for example make both lithium hydroxide and ammonium sulfate efficiencies the same. Although it may be the easiest to implement, the stability of the anion exchange membrane in high pH solution and temperature may, for example need to be considered. For example, a base stable anion exchange membrane may be used..

[00259] For example, variation in the pH of the ammonium sulfate may be allowed so that some proton back-migration is allowed. If the feed pH increases the amount of ammonia added to the acid/salt is stopped, proton is produced at the anode until enough proton has migrated across the AHA to bring the feed pH lower, and then ammonia addition occurs again. This method again matches lithium hydroxide and ammonium sulfate production, but may keep the pH at the AHA low. It also, for example has a benefit of running the acid/salt with a lower ammonium concentration. For example, an about 3 M sulfate solution might comprise about 0.5 M sulfuric acid with about 2.5 M ammonium bisulfate at a pH of about zero, but may comprise almost about 6 M ammonium sulfate at pH of about 4. This may, for example decrease the amount of ammonium back migration on the AHA membrane. The acid/salt solution could then, for example be post neutralized with ammonia to produce the required about 3 M $(\text{NH}_4)_2\text{SO}_4$ solution. Higher sulfate concentrations could also, for example be used.

[00260] While a description was made with particular reference to the specific embodiments, it will be understood that numerous modifications thereto will appear to those skilled in the art. Accordingly, the above description and accompanying drawings should be taken as specific examples and not in a limiting sense.

WHAT IS CLAIMED IS:

1. A process for preparing lithium sulphate, said process comprising:

leaching an acid roasted lithium-containing material with water so as to obtain an aqueous composition comprising Li^+ and at least one metal ion, wherein the lithium-containing material is a material that has been previously reacted with H_2SO_4 ;

reacting said aqueous composition comprising Li^+ and said at least one metal ion with a base so as to obtain a pH of about 4.5 to about 6.5, monitoring and controlling the oxidative reductive potential of said aqueous composition comprising Li^+ and said at least one metal ion at about or above 350 mV by sparging a gas therein, and thereby at least partially precipitating said at least one metal ion under the form of at least one hydroxide so as to obtain a precipitate comprising said at least one hydroxide and an aqueous composition comprising Li^+ and having a reduced content of said at least one metal ion, and separating said aqueous composition from said precipitate;

reacting said aqueous composition comprising Li^+ and having said reduced content of said at least one metal ion with another base so as to obtain a pH of about 9.5 to about 11.5, adding at least one metal carbonate thereby at least partially precipitating at least one metal ion under the form of at least one carbonate so as to obtain a precipitate comprising said at least one carbonate and an aqueous composition comprising Li^+ and having a reduced content of said at least one metal ion, and separating said aqueous composition from said precipitate; and

contacting said aqueous composition comprising Li^+ and having a reduced content of said at least one metal ion with an ion-exchange resin so as to at least partially remove at least one metal ion

from said composition, thereby obtaining an aqueous composition comprising said lithium sulphate.

2. The process of claim 1, wherein said aqueous composition comprising Li^+ and at least one metal ion is reacted with said base so as to obtain a pH of about 5.0 to about 6.2.
3. The process of claim 1, wherein said aqueous composition comprising Li^+ and at least one metal ion is reacted with said base so as to obtain a pH of about 5.2 to about 6.0.
4. The process of claim 1, wherein said aqueous composition comprising Li^+ and at least one metal ion is reacted with said base so as to obtain a pH of about 5.4 to about 5.8.
5. The process of any one of claims 1 to 4, wherein said base that said aqueous composition comprising Li^+ and at least one metal ion is reacted with is lime.
6. The process of any one of claims 1 to 4, wherein said at least one metal ion comprised in said aqueous composition that is reacted with said base so as to obtain said pH of about 4.5 to about 6.5 comprises Fe^{3+} .
7. The process of any one of claims 1 to 4, wherein said at least one metal ion comprised in said aqueous composition that is reacted with said base so as to obtain said pH of about 4.5 to about 6.5 comprises Al^{3+} .
8. The process of any one of claims 1 to 7, wherein said at least one hydroxide comprised in said precipitate is chosen from $\text{Al}(\text{OH})_3$ and $\text{Fe}(\text{OH})_3$.
9. The process of any one of claims 1 to 8, wherein said process comprises reacting said aqueous composition comprising Li^+ and having said reduced content of said at least one metal ion with said another base so as to obtain a pH of about 10 to about 11.

10. The process of any one of claims 1 to 8, wherein said process comprises reacting said aqueous composition comprising Li^+ and having said reduced content of said at least one metal ion with said another base so as to obtain a pH of about 10 to about 10.5.
11. The process of any one of claims 1 to 8, wherein said process comprises reacting said aqueous composition comprising Li^+ and having said reduced content of said at least one metal ion with said another base so as to obtain a pH of about 9.8 to about 10.2.
12. The process of any one of claims 1 to 11, wherein said another base is NaOH.
13. The process of any one of claims 1 to 12, wherein said at least one metal carbonate is chosen from Na_2CO_3 , NaHCO_3 , and $(\text{NH}_4)_2\text{CO}_3$.
14. The process of any one of claims 1 to 13, wherein said aqueous composition comprising Li^+ and having said reduced content of said at least one metal ion is reacted with said another base over a period of time sufficient for reducing the content of said at least one metal ion in said aqueous composition below a predetermined value.
15. The process of any one of claims 1 to 14, wherein said ion exchange resin is a cationic resin.
16. The process of any one of claims 1 to 14, wherein said ion exchange resin is a cationic resin that is substantially selective for divalent and/or trivalent metal ions.
17. The process of any one of claims 1 to 16, wherein said acid roasted lithium-containing material is leached with water so as to obtain said aqueous composition comprising Li^+ and at least three metal ions chosen from iron, aluminum, manganese and magnesium.
18. The process of any one of claims 1 to 16, wherein said acid roasted lithium-containing material is leached with water so as to obtain said

aqueous composition comprising Li^+ and at least four metal ions chosen from Al^{3+} , Fe^{2+} , Fe^{3+} , Mg^{2+} , Ca^{2+} , Cr^{2+} , Cr^{3+} , Cr^{6+} , Zn^{2+} and Mn^{2+} .

19. The process of any one of claims 1 to 18, wherein said acid roasted lithium-containing material is β -spodumene that has been previously reacted with H_2SO_4 .
20. The process of any one of claims 1 to 18, wherein said acid roasted lithium-containing material is α -spodumene, β -spodumene, lepidolite, pegmatite, petalite, amblygonite, hectorite, smectite, clays, or mixtures thereof, that has been previously reacted with H_2SO_4 .
21. The process of any one of claims 1 to 20, wherein the gas comprises O_2 .
22. The process of claim 21, wherein the gas is selected from air and O_2 .




FIG. 1




FIG. 2

3/62




FIG. 3

4/62




FIG. 4

5/62




FIG. 5

6/62




FIG. 6




FIG. 7

8/62




FIG. 8

9/62




FIG. 9

10/62




FIG. 10

11/62




FIG. 11

12/62




FIG. 12

13/62




FIG. 13

14/62




FIG. 14

15/62




FIG. 15

16/62




FIG. 16

17/62




FIG. 17

500




FIG. 18

19/62




FIG. 19

20/62




FIG. 20

21/62




FIG. 21

22/62




FIG. 22

23/62




FIG. 23

24/62




FIG. 24A

25/62




FIG. 24B

26/62




FIG. 24C

27/62

856-71, N324/AHA, 60°C,
Sulfate Current Efficiency vs Charge Passed




FIG. 24D

28/62




FIG. 25A

29/62





FIG. 25B

30/62



31/62




FIG. 25D

32/62




FIG. 25E

33/62




FIG. 25F

34/62




FIG. 25G

35/62




FIG. 26A

36/62




FIG. 26B

37/62




FIG. 26C

38/62




FIG. 26D

39/62




FIG. 26E

40/62




FIG. 26F

41/62




FIG. 26G

42/62




FIG. 27A

43/62




FIG. 27B

44/62




FIG. 27C

45/62




FIG. 27D

46/62




FIG. 27E

47/62

856-84, N324/AHA, 60°C, 200 mA/cm²
Sulfate Current Efficiency vs Charge Passed




FIG. 27F

48/62




FIG. 28A

49/62




FIG. 28B

50/62





FIG. 28C

51/62



52/62





FIG. 28E

53/62



54/62

856-84, N324/AHA, 80°C, 200 mA/cm²
Sulfate Current Efficiency vs Charge Passed




FIG. 28G

55/62




FIG. 29A

56/62




FIG. 29B

57/62




FIG. 29C

58/62




FIG. 29D

59/62




FIG. 29E

60/62

856-88, N324/AHA, 60°C, 200 mA/cm²
Base Concentration vs Charge Passed




FIG. 29F

61/62




FIG. 29G

62/62




FIG. 30

