

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
9 March 2006 (09.03.2006)

PCT

(10) International Publication Number
WO 2006/026064 A2

(51) International Patent Classification:
B01D 67/00 (2006.01)

(21) International Application Number:
PCT/US2005/027833

(22) International Filing Date: 5 August 2005 (05.08.2005)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/599,118 5 August 2004 (05.08.2004) US

(71) Applicant (for all designated States except US): **UNIVERSITY OF WYOMING** [US/US]; 1000 E. University Avenue, Research Products Center, Laramie, Wyoming 82071 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **SHEN, Youqing** [CA/US]; 3330 Joanna Brunner Dr., B9, Laramie, Wyoming 82072 (US). **RADOSZ, Marciej** [US/US]; 2818 Dover Drive, Laramie, Wyoming 82072 (US).

(74) Agent: **HERINK, Kent**; Davis, Brown, Koehn, Shors & Roberts, P.C., The Financial Center, 666 Walnut Street, Suite 2500, Des Moines, Iowa 50309 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.


(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: NOVEL IONIC LIQUIDS AND POLY(IONIC LIQUID)S AS NEW MATERIALS FOR GAS SEPARATION AND OTHER APPLICATIONS



(57) Abstract: Polymerizable ionic liquid monomers and their corresponding polymers (poly(ionic liquid)s) are created and found to exhibit high CO₂ sorption. The poly(ionic liquid)s have enhanced and reproducible CO₂ sorption capacities and sorption/desorption rates relative to room-temperature ionic liquids. Furthermore, these materials exhibit selectivity relative to other gases such as nitrogen, methane, and oxygen. They are useful as efficient separation agents, such sorbents and membranes. Novel radical and condensation polymerization approaches are used in the preparation of the poly(ionic liquids).

NOVEL IONIC LIQUIDS AND POLY(IONIC LIQUID)S AS NEW MATERIALS FOR GAS SEPARATION AND OTHER APPLICATIONS

Background of the Invention

The invention relates generally to novel materials, namely polymers made from ionic liquids, referred to herein as poly(ionic liquid)s, and, more specifically, to poly(ionic liquid)s for separating gases, particularly carbon dioxide (CO₂).

Global warming resulting from the increased CO₂ concentration in the atmosphere due to emissions of CO₂ from fossil fuel combustion is becoming one of most important environmental issues.^{1,2} Recently, CO₂ capture and sequestration are receiving significant attention. For carbon sequestration, because the cost of capture and separation are estimated to make up three-fourths of total costs of ocean or geologic sequestration, it is important to develop new materials and methods to separate and capture CO₂ from flue gas^{3,4,5} and other gas mixtures.

Ionic liquids, which are organic salts that become liquids usually below about 200 °C, have attracted attention because of their unique chemical and physical properties and wide application potentials.⁶⁻¹² Recently, CO₂ was found to be remarkably soluble in ionic liquids, and thus ionic liquids have been explored as non-volatile, and reversible absorbents for CO₂ separation.¹³⁻²¹ For instance, at 15 bar of CO₂ pressure, the CO₂ solubility in 1-butyl-3-methylimidazolium hexafluorophosphate ([bmim][PF₆]) is about 23 mol.%.¹⁹ The CO₂ solubility in the ionic liquids is dependent on their cations and substituents, and especially on their anions.¹⁹ For example, fluorine-containing anions (e.g. bis(trifluoromethylsulfonyl)imide, Tf₂N),¹⁹ or cations,²² or amine groups²³ tend to increase the CO₂ solubility. Ionic liquids have also been impregnated into porous materials for developing supported liquid membranes. Such membranes have high CO₂ selectivity and permeance because of the selective sorption of CO₂ in ionic liquids.²⁴⁻²⁶

We have found that poly(ionic liquid)s, the polymers prepared from ionic liquid monomers, have higher CO₂ sorption capacity than room temperature ionic liquids. Most importantly, the CO₂ sorption and desorption of the polymers are much faster than those of ionic liquids and the sorption/desorption is completely reversible. These poly(ionic liquid)s are thus promising as sorbent and membrane materials for CO₂ separation.

Summary of the Invention

The invention consists of a class of new materials consisting of novel ionic liquids and polymers made from ionic liquids. The poly(ionic liquid)s are polymerized ionic liquid monomers and have been found to have a CO₂ absorption rate and/or a CO₂ absorption capacity higher than that of the ionic liquid monomer. Certain of the poly(ionic liquid)s have a CO₂ absorption capacity almost ten times that of the ionic liquid monomer from which they are made. The sorption/desorption rates of the poly(ionic liquid)s are much faster than those of the corresponding ionic liquid monomers, and the poly(ionic liquid)s retain their sorption/desorption properties after going through sorption/desorption cycling. The polymers are made primarily through radical polymerization, but other methods of polymerization may also be used.

The ionic liquid monomers include: (a) Imidazolium-based ionic liquids, such as (a) 1-[2-(methacryloyloxy)ethyl]-3-butyl-imidazolium tetrafluoroborate ([MABI][BF₄]), 1-(*p*-vinylbenzyl)-3-butyl-imidazolium tetrafluoroborate ([VBBI][BF₄]), 1-(*p*-vinylbenzyl)-3-methyl-imidazolium tetrafluoroborate [VBMI][BF₄], 1-(*p*-vinylbenzyl)-3-butyl-imidazolium hexafluorophosphate [VBBI][PF₆], 1-(*p*-vinylbenzyl)-3-butyl-imidazolium *o*-benzoic sulphimide ([VBBI][Sac]), 1-(*p*-vinylbenzyl)-3-butyl-imidazolium trifluoromethane sulfonamide([VBBI][BF₄]), and (1-butylimidazolium-3)methyl-ethylene oxide ([BIEO][BF₄]); (b) Ammonium-based ionic liquids, such as (*p*-vinylbenzyl)trimethyl ammonium tetrafluoroborate ([VBTMA][BF₄]), (*p*-vinylbenzyl)triethyl ammonium tetrafluoroborate ([VBTEA][BF₄]), (*p*-vinylbenzyl)tributyl ammonium tetrafluoroborate ([VBTEA][BF₄]), 2-(methacryloyloxy)ethyltrimethylammonium tetrafluoroborate ([MATMA][BF₄]), (*p*-vinylbenzyl)trimethyl ammonium hexafluorophosphate ([VBTMA][PF₆]), (*p*-vinylbenzyl)trimethyl ammonium *o*-benzoic sulphimide ([VBTMA][Sac]), and (*p*-vinylbenzyl)trimethyl ammonium trifluoromethane sulfonamide ([VBTMA][Tf₂N]); (c) Phosphonium-based ionic liquids, such as (*p*-vinylbenzyl)triethyl phosphonium tetrafluoroborate ([VBTEP][BF₄]), and (*p*-vinylbenzyl)triphenyl phosphonium tetrafluoroborate ([VBTPP][BF₄]); (d) Pyridinium-based ionic liquids, such as 1-(*p*-vinylbenzyl) pyridinium tetrafluoroborate ([VBP][BF₄]); and (e) Condensation polymerization ionic monomers, such as bis(2-hydroxyethyl)dimethyl ammonium

tetrafluoroborate ([BHEDMA][BF₄]), 2,2-bis(methylimidazolium methyl)-1,3-propanediol tetrafluoroborate ([BMIMP][BF₄]), and 2,2-bis(butylimidazolium methyl)-1,3-propanediol tetrafluoroborate ([BBIMP][BF₄]).

The invention also consists of a process for the separation and recovery of gases that are soluble in the ionic liquid monomers and have sorption capacities and/or rates in the poly(ionic liquid)s that are higher than those in the corresponding ionic liquid monomer. In the specific example of CO₂, the process includes the steps of contacting a CO₂-containing gas mixture with a solid sorbent that includes at least one poly(ionic liquid) compound under such conditions as to obtain a gas product having a lower concentration of CO₂ than the initial gas mixture and a solid sorbent containing absorbed carbon dioxide which has been removed from said gas mixture. Preferably, the solid sorbent is treated under conditions as to substantially desorb the CO₂ contained in the solid sorbent so as to obtain a regenerated solid sorbent.

Brief Description of the Figures

Figure 1 is a graphical representation of the CO₂ sorption of the poly(ionic liquid)s (P[VBBI][BF₄](a), P[VBBI][Tf₂N](b), P[MABI][BF₄](c), P[VBBI][Sac](d)), with their corresponding monomers ([VBBI][Tf₂N](e), [MABI][BF₄](g), [VBBI][BF₄](h), [VBBI][Sac](i)), and an ionic liquid [bmim][BF₄] (f) as a function of time (592.3 mmHg CO₂, 22 °C).

Figure 2 is a graphical representation of the CO₂ sorption of poly(ionic liquid)s with different polymer backbones (592.3 mmHg of CO₂ and 22 °C).

Figure 3 is a graphical representation of the CO₂ sorption of poly(ionic liquid)s with different substituents (592.3 mmHg of CO₂ and 22 °C).

Figure 4 is a graphical representation of the CO₂ sorption of poly(ionic liquid)s with different anions (592.3 mmHg of CO₂ and 22 °C).

Figure 5 is a graphical representation of the gas (CO₂, O₂, N₂) sorption of P[VBBI][BF₄] as a function of time at 592.3 mmHg, 22 °C.

Figure 6 is a graphical representation of the weight change of P[VBBI][BF₄] (1 g) (without buoyancy correction) after introducing CO₂ into the system, and then replacing CO₂ with N₂ (total pressure 592.3 mmHg, 22 °C).

Figure 7 is a graphical representation of the isothermal sorption of P[VBBI][BF₄] and P[MABI][BF₄] at different CO₂ pressures (22 °C).

Figure 8 is a graphical representation of the (a) cycles of CO₂ sorption (592.3 mmHg CO₂, 22 °C) and desorption of P[VBBI][BF₄] and P[MABI][BF₄] under vacuum; (b) CO₂ sorption (592.3 mmHg CO₂, 22 °C) and desorption of a typical ionic liquid [bmim][BF₄] under vacuum.

Figures 9A and 9B are scanning electron micrographs of P[VBBI][BF₄] particles.

Figure 10 is a graphical representation of the CO₂ sorption of P[VBBI][BF₄] with different particle sizes (592.3 mmHg, 22 °C).

Figure 11 is a graphical representation of the CO₂ sorption of poly(ionic liquid)s with different types of cation.

Figure 12 is a graphical representation of the CO₂ sorption of poly(ionic liquid)s with different types of anion.

Figure 13 is a graphical representation of the CO₂ sorption in poly(ionic liquid)s with different backbones

Figure 14 is a graphical representation of the CO₂ sorption in poly(ionic liquid)s with different substituents.

Figure 15 is a graphical representation of the effect of crosslinking on CO₂ sorption in poly(ionic liquid)s.

Figure 16 is a graphical representation of the CO₂/CH₄ selectivity for P[VBTMA][BF₄]-co-PEG and P[MATMA][BF₄]-co-PEG.

Figure 17 is a graphical representation of the CO₂/CH₄ selectivity for representative polymers and poly(ionic liquids) (♦: representative polymers; •: P[MATMA][BF₄]-co-PEG at 35°C, 50°C and 70°C; ▲: P[VBTMA][BF₄]-co-PEG at 35°C, 50°C and 70°C)

Figure 18 is a graphical representation of the CO₂/N₂ selectivity for P[VBTMA][BF₄]-co-PEG and P[MATMA][BF₄]-co-PEG

Figure 19 is a graphical representation of the CO₂/N₂ selectivity for representative polymers and poly(ionic liquids) (♦: representative polymers; •: P[MATMA][BF₄]-co-PEG at 35°C, 50°C and 70°C; ▲: P[VBTMA][BF₄]-co-PEG at 35°C, 50°C and 70°C)

Detailed Description of Preferred Embodiments

In this description, each material is introduced by its full chemical name followed by a shortened name in parenthesis, for example, 1-[2-(methacryloyloxy)ethyl]-3-butyl-imidazolium tetrafluoroborate ([MABI][BF₄]). Following the initial introduction, only the shortened name is used.

Ionic liquids are organic salts with melting points usually below 200 °C, often below room temperature. They can be substitutes for the traditional organic solvents in chemical reactions. The most common examples are imidazolium and pyridinium derivatives, but phosphonium or tetralkylammonium compounds have also been explored.

Ionic liquid monomers of the present application are ionic liquids that are suitable for polymerization of the ionic liquid monomers to form poly(ionic liquid)s. Specific examples of ionic liquid monomers of the present application have a double bond that forms a radical when broken. The ionic liquid monomers may include an inorganic moiety. Specific examples of ionic liquid monomers used for polymer synthesis and other applications include but are not limited to:

(1) Ionic liquid monomers based on imidazolium, such as 1-[2-(methacryloyloxy)ethyl]-3-butyl-imidazolium tetrafluoroborate ([MABI][BF₄]), 1-(*p*-vinylbenzyl)-3-butyl-imidazolium tetrafluoroborate ([VBBI][BF₄]), 1-(*p*-vinylbenzyl)-3-methyl-imidazolium tetrafluoroborate ([VBMi][BF₄]), 1-(*p*-vinylbenzyl)-3-butyl-imidazolium hexafluorophosphate ([VBBI][PF₆]), 1-(*p*-vinylbenzyl)-3-butyl-imidazolium *o*-benzoic sulphimide ([VBBI][Sac]), 1-(*p*-vinylbenzyl)-3-butyl-imidazolium trifluoromethane sulfonamide ([VBBI][BF₄]), (1-butylimidazolium-3)methyl-ethylene oxide ([BIEO][BF₄]);

(2) Ionic liquid monomers based on ammonium, such as (*p*-vinylbenzyl)trimethyl ammonium tetrafluoroborate ([VBTMA][BF₄]), (*p*-vinylbenzyl)triethyl ammonium tetrafluoroborate ([VBTEA][BF₄]), (*p*-vinylbenzyl)tributyl ammonium tetrafluoroborate ([VBTBA][BF₄]), [2-(methacryloyloxy)ethyl]trimethylammonium tetrafluoroborate ([MATMA][BF₄]), (*p*-vinylbenzyl)trimethyl ammonium hexafluorophosphate ([VBTMA][PF₆]), (*p*-vinylbenzyl)trimethyl ammonium *o*-benzoic sulphimide ([VBTMA][Sac]), (*p*-vinylbenzyl)trimethyl ammonium trifluoromethane sulfonamide ([VBTMA][Tf₂N]);

(3) Ionic liquid monomers based on phosphonium, such as (*p*-vinylbenzyl)triethyl phosphonium tetrafluoroborate ([VBTEP][BF₄]), (*p*-vinylbenzyl)triphenyl phosphonium tetrafluoroborate ([VBTPP][BF₄]);

5 (4) Ionic liquid monomers based on pyridinium, such as 1-(*p*-vinylbenzyl) pyridinium tetrafluoroborate ([VBP][BF₄]);

(5) Ionic liquid monomers for condensation polymerization, such as bis(2-hydroxyethyl)dimethyl ammonium tetrafluoroborate ([BHEDMA][BF₄]), 2,2-bis(methylimidazolium methyl)-1,3-propanediol tetrafluoroborate ([BMIMP][BF₄]), and 2,2-bis(butylimidazolium methyl)-1,3-propanediol tetrafluoroborate ([BBIMP][BF₄]).

10 Poly(ionic liquid)s as used in this specification means polymers formed using ionic liquids as monomers via radical polymerization or other kind of polymerization. Certain of the poly(ionic liquid)s have a gas sorption capacity and/or rate that is greater than that of the corresponding ionic liquid monomer for the corresponding gas.

Radical polymerization is a common and useful reaction for making polymers from
15 vinyl monomers, that is, from small molecules containing carbon-carbon double bonds. Polymers made by radical polymerization include polystyrene, poly(methyl methacrylate), poly(vinyl acetate) and branched polyethylene. Radical polymerization begins with a molecule called an initiator; common initiators are benzoyl peroxide or 2,2'-azo-*bis*-isobutyronitrile (AIBN).

20

EXAMPLE 1


Materials

4-Vinylbenzyl chloride, methacryloyl chloride, 1-butyylimidazole, 2-bromoethanol, lithium trifluoromethane sulfonimide, potassium hexafluorophosphate, sodium
25 tetrafluoroborate, 2,6-di-*tert*-butyl-4-methyl phenol (DBMP), 2,2'-azobisisobutyronitrile (AIBN), aluminum isopropoxide, epichlorohydrin, *N,N*-dimethylformamide (DMF), acetonitrile, and acetone were purchased from Aldrich. 1-Methylimidazole, and *o*-benzoic sulphimide sodium salt hydrate were purchased from Lancaster Synthesis Inc. These chemicals were used without further purification.


30

Synthesis and Characterization

1-[2-(Methylacryloyloxy)ethyl]-3-butyl-imidazolium tetrafluoroborate ([MABI][BF₄]) and 1-(*p*-vinylbenzyl)-3-butyl-imidazolium tetrafluoroborate ([VBBI][BF₄]) were synthesized according to our published reports,^{27,28} as shown in Schemes 1 and 2. 1-(*p*-Vinylbenzyl)-3-butyl-imidazolium hexafluorophosphate ([VBBI][PF₆]), 1-(*p*-vinylbenzyl)-3-butyl-imidazolium *o*-benzoic sulphimide ([VBBI][Sac]), 1-(*p*-vinylbenzyl)-3-butyl-imidazolium trifluoromethane sulfonamide ([VBBI][Tf₂N]) were synthesized by a similar procedure except using NaPF₆, *o*-benzoic sulphimide sodium salt hydrate (NaSac) or lithium trifluoromethane sulfonamide (LiTf₂N) for anion exchange reactions. The yields were 93.0%, 49.6%, 39.9%, respectively.



Scheme 1



Scheme 2

1-(*p*-Vinylbenzyl)-3-methyl-imidazolium tetrafluoroborate ([VBMI][BF₄]) was
 5 synthesized as follows: To a 50 ml flask, *p*-vinylbenzyl chloride (10 ml, 0.064 mole), a small
 amount of DBMP, and 1-methylimidazole (5.14 ml, 0.064 mole) were added and heated at 45
 °C overnight. The solution became gradually viscous. NaBF₄ (5.2 g, 0.47 mole) and dry
 acetone (30 ml) were added. The mixture was stirred at room temperature. The viscous liquid
 dissolved gradually while a white solid precipitated. After 12 h reaction, the precipitate was
 10 removed by filtration. The solvent was removed under vacuum. The solid was washed with

water and ether, and dried by vacuuming at room temperature, producing 14 g of white crystals (yield 76.5%).

[VBBI][BF₄]: ¹H NMR (400 MHz, DMSO-d₆, ppm): δ 9.24 (1H, s), 7.80 (2H, s),
 5 7.51 (2H, d) 7.35 (2H, d), 6.73 (1H, m), 5.89(1H,d) 5.27 (1H, d), 5.40 (2H, s), 4.14 (2H, t),
 1.78 (2H, m), 1.24 (2H, m), 0.88 (3H, t). mp: 67–68 °C.

[VBBI][PF₆]: ¹H NMR (400 MHz, DMSO-d₆, ppm): δ 9.22 (1H, s), 7.80 (2H, s), 7.48
 (2H, d) 7.35 (2H, d), 6.73 (1H, m), 5.89(1H, d), 5.30 (1H, d), 5.46 (2H, s), 4.14 (2H, t), 1.79
 (2H, m), 1.22 (2H, m), 0.87 (3H, t). mp: 87–88.5 °C.

10 [VBBI][Sac] ¹H NMR (400 MHz, DMSO-d₆, ppm) δ 9.38 (1H, s), 7.80 (2H, s) 7.66
 (1H, d), 7.61(1H, d), 7.59 (2H, d), 7.49 (2H, d), 7.40 (2H,d), 6.72 (1H, m) 5.84 (1H, d), 5.42
 (2H, s), 5.26 (2H, d) 4.16 (2H, m) 1.73 (2H, m), 1.21(2H, m), 0.84 (3H, m). mp: -36 – -38 °C

[VBBI][Tf₂N] ¹H NMR (400 MHz, DMSO-d₆, ppm): δ 8.83 (1H, s), 7.44 (2H, s),
 7.34 (2H, d) 7.27 (2H, d), 6.70 (1H, m), 5.79(1H,d) 5.33 (1H, d), 5.31 (2H, s), 4.17 (2H, t),
 15 1.84 (2H, m), 1.35 (2H, m), 0.94 (3H, t). mp: -61 – -62°C

[VBMi][BF₄]: ¹H NMR (400 MHz, DMSO-d₆, ppm): 9.13 (1H, s), 7.71 (1H, s), 7.63
 (1H, s), 7.52 (1H, d), 7.42 (2H, d), 6.75 (1H, m), 5.88 (1H, d), 5.41(2H, s), 5.26 (1H, d),
 3.86 (3H, s). mp: 42-44 °C.

Poly(ionic liquid)s were prepared from above ionic liquid monomers by free radical
 20 polymerization. A typical example is as the following: [VBBI][BF₄] (3 g), AIBN (30 mg)
 and DMF (3 ml) were charged into a reaction tube. The tube was tightly sealed, and degassed.
 It was immersed in an oil bath at 60 °C for 6 h. The solution was poured into methanol to
 precipitate out the polymer. The polymer was dried under vacuum at 100 °C. The yield was
 2.3 g (75%).

25 Poly[1-(*p*-Vinylbenzyl)-3-butyl-imidazolium tetrafluoroborate] (P[VBBI][BF₄]): ¹H
 NMR (DMSO-d₆, 400 MHz, ppm): δ 9.12 (s, 1H), 7.8 (br, 1H), 7.4 (br, 1H), 7.1 (br, 2 H), 6.4
 (br, 2H), 5.6-4.9 (br, 2H), 4.1 (br, 2H), 2.1-1.0 (m, 7H), 0.8 (s, 3 H). Anal. Calcd for
 (C₁₆H₂₁BF₄N₂)_n: C, 58.56%; H, 6.45%; N, 8.54%. Found: C, 58.35%; H, 6.43%; N, 8.50%.

Poly[1-(*p*-Vinylbenzyl)-3-butyl-imidazolium hexafluorophosphate] (P[VBBI][PF₆]):
 30 ¹H NMR (DMSO-d₆, 400 MHz, ppm): δ 9.16 (s, 1H), 7.72 (br, 1H), 7.47 (br, 1H), 7.04 (br, 2

H), 6.42 (br, 2H), 5.23 (br, 2H), 4.15 (br, 2H), 2.1-0.8 (m, 10H) Anal. Calcd for $(C_{16}H_{21}F_6N_2P)_n$: C, 49.75%; H, 5.48%; N, 7.25%; Found: C, 49.70%; H, 5.37%; N, 7.12%.

Poly[1-(*p*-Vinylbenzyl)-3-butyl-imidazolium *o*-benzoic sulphimide] (P[VBBI][Sac]):
 1H NMR (DMSO- d_6 , 400 MHz, ppm): δ 9.44 (s, 1H), 7.5-7.9 (br, 6H), 7.19 (br, 2H), 6.35 (br,
 5 2H), 5.35 (br, 2H), 4.15 (br, 2H), 1.9-0.5 (m, 10H) Anal. Calcd for $(C_{23}H_{25}N_3O_3S)_n$: C, 65.25;
 H, 5.91; N, 9.93. Found: C, 64.11; H, 6.05; N, 9.68.


Poly[1-(*p*-Vinylbenzyl)-3-butyl-imidazolium trifluoromethane sulfonamide]
 (P[VBBI][Tf $_2$ N]): 1H NMR (DMSO- d_6 , 400 MHz, ppm): δ 9.20 (s, 1H), 7.73 (br, 1H), 7.44
 (br, 1H), 6.94 (br, 2H), 6.33 (br, 2H), 5.19 (br, 2H), 4.13 (br, 2H), 2.0-1.0 (m, 7H), 0.81 (s, 3
 10 H). Anal. Calcd for $(C_{18}H_{21}N_3F_6O_4S_2)_n$: C, 41.46; H, 4.03; N, 8.06. Found: C, 41.46; H, 4.13;
 N, 7.94.

Poly{1-[2-(Methylacryloyloxy)ethyl]-3-butyl-imidazolium tetrafluoroborate}
 (P[MABI][BF $_4$]): 1H NMR (DMSO- d_6 , 400 MHz, ppm): δ 9.1 (br, 1H), 7.9-7.6 (d, 2H), 4.8-
 3.8 (m, 6H), 2.0-0.2 (m, 12H). Anal. Calcd for $(C_9H_{18}BF_4NO_2)_n$: C, 48.17; H, 6.49; N, 8.65.
 15 Found: C, 47.68; H, 6.48; N, 6.48.

Poly[1-(*p*-vinylbenzyl)-3-methyl-imidazolium tetrafluoroborate] (P[VBMI][BF $_4$]):
 1H NMR (DMSO- d_6 , 400 MHz, ppm): δ 9.10 (1H, br), 7.60-7.30 (2H, br), 7.10 (2H, br),
 6.40 (2H, br), 5.30 (2H, br), 3.70 (2H, br) 2.1-0.5 (3H, br). Anal. Calcd for $(C_{13}H_{15}BF_4N_2)_n$:
 C, 54.58; H, 5.25; N, 9.80. Found: C, 52.74; H, 5.33; N, 9.38.

20 The poly(ionic liquid) with poly(ethylene oxide) backbone was synthesized from
 poly(epichlorohydrin) (Scheme 3). Aluminum isopropoxide (0.18 g, 0.88 mmol) was added
 into a 100 mL flask. The flask was degassed by repeated vacuum/nitrogen purging (5 cycles).
 Degassed THF (25mL) and epichlorohydrin (5.0 mL, 66 mmol) was added by degassed
 syringes. After the reaction flask was immersed into a 40 °C oil bath for 12 hours, the
 25 poly(epichlorohydrin) was precipitated out by adding a large amount of hexane. 3.3 g of
 poly(epichlorohydrin) was dissolved in 50 mL of DMF. N-butylimidazole (5.0g, 40 mmol)
 was added to the DMF solution. This solution was stirred at 80 °C for 5 days, and then
 NaBF $_4$ (4.4 g, 40 mmol) was added. After the mixture was stirred at room temperature for 2
 days, sodium chloride precipitate was removed by filtration. Anhydrous ethyl ether was
 30 added to the filtrate to precipitate the poly(ionic liquid). The obtained P[BIEO][BF $_4$] was
 washed with ethyl ether and dried in vacuum oven at 50 °C for one day. 1H -NMR (acetone-

δ 8.86 (1H, s), 7.69 (2H, br), 4.44-4.31 (4H, br), 3.97 (1H, br), 3.67 (2H, br), 1.88 (2H, br), 1.34 (2H, br), 0.93 (3H, br). Anal. Calcd for $(C_{10}H_{17}BF_4N_2O)_n$: C, 44.80; H, 6.34; N, 10.46. Found: C, 44.66; H, 6.26; N, 10.11.



Scheme 3

The syntheses of ionic liquid monomers are shown in Schemes 1 - 3. Two steps were generally involved in the preparations: the quaternization reaction of 1-butylimidazole or 1-methylimidazole with 4-vinylbenzyl chloride or 2-bromoethyl methacrylate, and the anion exchange reaction of the halide ions with tetrafluoroborate, hexafluorophosphate, Sac or Tf_2N anions.

The quaternization with 4-vinylbenzyl chloride was fast with a high yield. The anion exchange of the resulting chloride $[VBBI][Cl]$ and $[VBMI][Cl]$ with BF_4^- produced the monomers, $[VBBI][BF_4]$ and $[VBMI][BF_4]$, as crystalline solids, which are soluble in acetone, acetonitrile, dichloromethane, DMF, and DMSO, but insoluble in diethyl ether. $[VBBI][PF_6]$ is also a solid with similar solubility. $[VBBI][Sac]$ and $[VBBI][Tf_2N]$ are liquid at room temperature and soluble in acetone, acetonitrile, DMF, and DMSO. $[VBBI][Tf_2N]$ is also soluble in ethyl ether.

The quaternization of *N*-butylimidazole with 2-bromoethyl methacrylate was slow and difficult to get high yield of $[MABI][Br]$. After the anion exchange, $[MABI][BF_4]$ is also a liquid at room temperature and soluble in above polar solvents but insoluble in ethyl ether and other nonpolar solvents.

All above ionic liquid monomers, unlike their corresponding chloride salts, are insoluble in water. So unreacted chloride salts could be easily removed by washing with

water. Silver nitrate tests indicated that no chloride was present in all the ionic liquid monomers.

The poly(ionic liquid)s, except for P[BIEO][BF₄] which was synthesized by the polymer reaction shown in Scheme 3, were prepared by free radical polymerization of the ionic liquid monomers using AIBN as initiators. DMF was used as solvent because all poly(ionic liquid)s are soluble in it. All these ionic liquid monomers are easily polymerized with high conversions. Poly(ionic liquid)s were precipitated in methanol to remove unreacted monomers. DMF residue in polymers was removed by drying at 100 °C under vacuum. All poly(ionic liquid)s can dissolve in DMF, DMSO, acetonitrile, but are insoluble in water, dichloromethane and toluene. H¹ NMR and element analysis indicated the poly(ionic liquid)s were pure.

CO₂ Sorption and Desorption

The CO₂ sorption of the poly(ionic liquid)s was measured using a Cahn 1000 Electrobalance. The sample pan and the counterweight of the balance were configured symmetrically to minimize buoyancy effects. The microbalance has 100 g capacity and 1.0 µg sensitivity and is suitable for study of sorption and diffusion of gases on/in solid or liquid materials. CO₂ gas (99.995%) was dried by passing two drying columns (length × diameter: 15 in × 2 in) packed with P₂O₅. The fine powder of the ionic liquid polymer was dried and degassed at 70 °C under vacuum for 12 h to remove moisture or other volatile contaminants. It was further dried in the balance by evacuating the chamber at high vacuum until its weight reached constant for at least 30 min. CO₂ was introduced into the chamber and the sample weight increase was recorded until the weight did not change significantly in 30 min. The buoyancy effects in these measurements were corrected according to the literature.²⁹ The system was validated by measuring the CO₂ sorption of an ionic liquid, 1-n-butyl-3-methylimidazolium tetrafluoroborate ([bmim][BF₄]). The measured CO₂ sorption capacity of [bmim][BF₄] was identical to the reported.¹⁹

CO₂ has remarkable solubility in imidazolium-based ionic liquids because of its interactions with the anions and cations of ionic liquids.¹⁹ The CO₂ sorption of (P[VBBI][BF₄](a), P[VBBI][Tf₂N](b), P[MABI][BF₄](c), P[VBBI][Sac](d)), with their corresponding monomers ([VBBI][Tf₂N](e), [MABI][BF₄](g), [VBBI][BF₄](h), [VBBI][Sac](i)), and an ionic liquid [bmim][BF₄] (f) as a function of time (592.3 mmHg CO₂,

22 °C) is shown in Figure 1. The CO₂ solubility of [bmim][BF₄] was tested first and found consistent with that reported in the literature,¹⁹ which validated the setup of the apparatus.

At the equilibrium, P[VBBI][BF₄], P[VBBI][Tf₂N], P[MABI][BF₄] and P[VBBI][Sac], respectively, took up 2.27 mol%, 2.23 mol%, 1.78 mol% and 1.55 mol% of CO₂ in terms of their monomer units. In comparison, room temperature ionic liquid [bmim][BF₄] absorbed 1.34 mol% of CO₂ under the same conditions. [VBBI][BF₄] monomer had no measurable sorption of CO₂ because of its crystalline structure. [MABI][BF₄], [VBBI][Sac] and [VBBI][Tf₂N] monomers are liquid at room temperature. [MABI][BF₄] had the same CO₂ sorption capacity as [bmim][BF₄]. [VBBI][Tf₂N] had a CO₂ sorption capacity of 1.96 mol%, higher than that of [bmim][BF₄], which is consistent with the report that the ionic liquid with Tf₂N anions had higher capacity than ionic liquids with BF₄ anions.¹⁴ [VBBI][Sac] did not take up any CO₂ when it was exposed to CO₂ (Figure 1). This comparison shows that polymerizing ionic liquids can increase the CO₂ sorption capacity.

Meanwhile, the CO₂ sorption of the poly(ionic liquid)s was much faster than that of ionic liquids. It takes only several minutes for the poly(ionic liquid)s to reach their 90 % capacity and less than 30 minutes to reach their equilibrium capacity. In contrast, room temperature ionic liquids [MABI][BF₄] and [bmim][BF₄] needed more than 400 min to reach their equilibrium capacity (Figure 1).

The CO₂ sorption of poly(ionic liquid)s with different backbones, cations, and anions was compared to understand the factors affecting the CO₂ sorption. The CO₂ sorption kinetics of poly(ionic liquid)s with different backbones are shown in Figure 2. At the equilibrium, the polymers sorbed 2.27 mol% (P[VBBI][BF₄]), 1.78 mol% (P[MABI][BF₄]) and 1.06 mol% (P[BIEO][BF₄]), respectively, in terms of their monomer units at 592.3 mmHg of CO₂ and 22 °C. With the same butylimidazolium cation and BF₄⁻ anion, the polymer with polystyrene backbone had a higher CO₂ sorption capacity than those with polymethylmethacrylate and polyethylene glycol backbones. The polymer with polyethylene glycol backbone had the lowest capacity.

The effect of substituent of the imidazolium cation on the CO₂ sorption is shown in Figure 3. P[VBMI][BF₄], which has a methyl substituent on its imidazolium cation, had a higher capacity (3.05 mol.%) than P[VBBI][BF₄] (2.27 mol.%) with butyl group. This indicates that a large substituent on the imidazolium cation may block the CO₂ sorption.

The effect of the anions on the CO₂ sorption capacity of the poly(ionic liquid)s is shown in Figure 4. The CO₂ sorption capacity the P[VBBI]-based polymers depends on the type of the anions: it was 2.80 mol.% for P[VBBI][PF₆], 2.27 mol% for P[VBBI][BF₄], 2.23 mol.% for P[VBBI][Tf₂N] and 1.55 mol.% for P[VBBI][Sac], respectively, in terms of their monomer units at 592.3 mmHg of CO₂ and 22 °C. This trend is different from that of ionic liquids. The CO₂ solubility in ionic liquids with Tf₂N⁻ anions is much higher than those with PF₆⁻ or BF₄⁻ anions.¹⁹ By contrast, the poly(ionic liquid) with PF₆⁻ anions ([PVBBI][PF₆]) had the highest sorption capacity, and those with BF₄⁻ and Tf₂N⁻ anions had a similar capacity. The poly(ionic liquid) with Sac⁻ anions could take up 1.55mol% of CO₂ even though the anion contains no fluorine atoms. These results indicate that for poly(ionic liquid)s, fluorine-atoms are not a decisive factor for CO₂ sorption but fluorine-atoms in the anions indeed enhance the CO₂ sorption.

The CO₂ sorption of the polymers is very selective, as shown in Figure 5. There was no weight increase when the polymers were exposed to N₂ or O₂ under the same conditions, which means that poly(ionic liquid)s can selectively absorb CO₂.

The selective CO₂ sorption of the poly(ionic liquid)s was also confirmed by a gas-replacement experiment. The CO₂ sorption of P[VBBI][BF₄] (1 gram) and desorption by replacing CO₂ with N₂ are shown in Figure 6. After introducing CO₂ into the balance, the sample weight increased rapidly until it became constant after 12 min. The weight increase was 2.1 mg, and the actual weight increase was 3.10 mg after a buoyancy correction. When N₂ was introduced into the chambers while maintaining the total pressure in the chambers at ambient pressure (592.3 mmHg), the sample weight decreased gradually, and finally reached -0.56 mg, which was equal to the buoyancy of the sample under N₂. This experiment indicates that the poly(ionic liquid) does not take up N₂. Similar experiments conformed that there was no O₂ sorption.

The sorption isotherms of P[VBBI][BF₄] and P[MABI][BF₄] at different CO₂ partial pressures and 22 °C are shown in Figure 7. The different CO₂ partial pressures were obtained by adjusting the N₂ /CO₂ ratio of the mixed gas charged to the balance chambers because P[VBBI][BF₄] and P[MABI][BF₄] had no N₂ sorption. As shown in Figure 7, the CO₂ mole fraction in the polymers increased with the increase of CO₂ partial pressure.

Henry's constant is defined as $H = \lim_{x \rightarrow 0} \frac{P}{x}$ where H is Henry's constant, x is the mole fraction of gas sorbed in the polymer in term of monomeric unit, and P is the CO₂ partial pressure. Since the x vs. P plots were not linear in the entire pressure range, Henry's constants were calculated by fitting the data and extrapolating the slope to the zero CO₂ partial pressure.¹⁶ Henry's constant was 26.0 bar for P[VBBI][BF₄] and 37.7 bar for P[MABI][BF₄], which is lower than that of room temperature ionic liquid [bmim][PF₆] (38.7 bar at 10°C and 53.4 bar at 25°C).¹⁶

Stable sorption capacity after repeated sorption/desorption is important for materials used for CO₂ separation. Four cycles of CO₂ sorption and desorption of P[VBBI][BF₄] and P[MABI][BF₄] were tested by filling the chambers with CO₂ and then vacuuming (Figure 8a). The sorption and desorption of P[VBBI][BF₄] and P[MABI][BF₄] were all very fast. It took only about 30 min to take up CO₂ and to have a complete desorption of CO₂. The desorption was complete, suggesting that the sorption/desorption was reversible. No change in sorption/desorption kinetics and sorption capacity was observed after the four cycles. By contrast, the desorption of CO₂ from room temperature ionic liquids [bmim][BF₄] was very slow (Figure 8b)

The enhanced sorption capacity and fast sorption/desorption rates of the poly(ionic liquid)s were unexpected because all polymers are solid at room temperature. An immediate question is whether the sorption occurred on the surface (adsorption) or in the bulk (absorption) or both. The BET surface area of P[VBBI][BF₄] was measured by nitrogen sorption and its morphology was examined by SEM. The measured BET surface area of P[VBBI][BF₄] sample was 0.295 m²/g. The calculated CO₂-adsorption assuming a monolayer of CO₂ on this surface was only 0.0128 wt%, much less than the measured CO₂ sorption capacities. The SEM (Figures 9A, B) indicated that the particles had a nonporous structure, and the average diameter of the particles was about 100 μm.

The CO₂ sorption of P[VBBI][BF₄] samples with different particle sizes was tested (Figure 10). The particle size did not significantly affect the capacity of CO₂ sorption and the sample with a big size even had a slightly higher sorption capacity. However, the particle size affected the rate of CO₂ sorption. The CO₂ sorption of the sample with big particle sizes (>250 μm in diameter) was slow, and needed about 120 minutes to reach its full sorption capacity, while those with the particle diameters less than 125 μm in diameter only needed

less than 30 mins.

Without being bound to any particular theory, it appears that the CO₂ sorption of the polymer particles involves more absorption (the bulk) but less adsorption (the surface). Their CO₂ sorption capacity mainly depends on the chemical structure of poly(ionic liquid)s, while
 5 the rate of CO₂ sorption depends on the particle size due to the CO₂ diffusion in the polymers.

EXAMPLE 2

Materials

4-vinylbenzyl chloride (90 %), 1-methylimidazole (98 %), lithium trifluoromethane
 10 sulfonimide 99.95%, potassium hexafluorophosphate 98%, sodium tetrafluoroborate (98%),
 2, 6-Di-tert-butyl-4-methyl phenol (98%) (DBMP), N,N-Dimethylformamide (99.8%)
 (DMF), acetonitrile (99.5+%), acetone (99.5+%), aqueous [2-
 (methacryloyloxy)ethyl]trimethyl ammonium chloride solution (75 wt.%), (p-
 vinylbenzyl)trimethylammonium chloride (98%), triethylamine (99.5%), tributylamine
 15 (99.5%) triphenylphosphine 99%, α,α' -azobis(isobutyronitrile)(AIBN) (98%) were
 purchased from Aldrich. 1-methyl imidazole 99%, o-Benzoic sulphimide sodium salt hydrate
 (97%) were purchased from Lancaster Synthesis Inc. Pyridine was purchased from Fisher
 scientific. All chemicals were used as received.

Synthesis and characterization

20 (*p*-vinylbenzyl)trimethyl ammonium tetrafluoroborate ([VBTMA][BF₄]) and 2-
 (methacryloyloxy)ethyltrimethylammonium tetrafluoroborate ([MATMA][BF₄]) were
 synthesized as described previously³⁰ using (*p*-vinylbenzyl)triethyl phosphonium
 tetrafluoroborate ([VBTEP][BF₄]), (*p*-vinylbenzyl)triphenyl phosphonium tetrafluoroborate
 ([VBTPP][BF₄]).

25 The synthesis of (*p*-vinylbenzyl)triphenyl phosphonium tetrafluoroborate
 ([VBTPP][BF₄]), 1-(*p*-vinylbenzyl) pyridinium tetrafluoroborate ([VBP][BF₄]) and 1-(*p*-
 vinylbenzyl)-3-methyl-imidazolium tetrafluoroborate ([VBMI][BF₄]) is similar to 1-(*p*-
 vinylbenzyl)-3-butyl-imidazolium tetrafluoroborate ([VBBI][BF₄]) [VBBI][BF₄] (VBBI), as
 reported previously,²⁸ using triphenylphosphine, pyridine and 1-methyl imidazole instead of
 30 1-butylimidazole, respectively.

The synthesis of (*p*-vinylbenzyl)triethylammonium tetrafluoroborate [VBTEA][BF₄] and (*p*-vinyl benzyl)tributylammonium tetrafluoroborate [VBTBA][BF₄] was follows: In a 50 ml flask, 4-vinylbenzyl chloride (6.1 g, 0.04 mol) and triethylamine (4.2 g, 0.042 mol) mol were mixed and heated at 50 °C under N₂ atmosphere for 2 days. The formed solid was washed with diethyl ether. The resultant white solid (8.5 g, 0.033 mol) was mixed with NaBF₄ (3.8 g, 0.035) in 50 acetonitrile and stirred at room temperature for 2 days. The salt precipitate was removed by filtration. The filtrate was concentrated and poured into 200 ml diethyl ether to precipitate out product. White crystal precipitate was formed, collected by filtration, and dried under vacuum. The total yield was 9.2 g (75%). [VBTBA][BF₄] was synthesized according to a similar procedure with yield of 64%.

In the synthesis of bis[(*p*-vinylbenzyl)dimethylammonium]ethane, [BVDEA][BF₄], which is an ionic liquid crosslinker, tetramethylethylenediamine (5.8 g, 0.05 mol), 4-vinylbenzyl chloride (16.0 g, 0.105 mol) and 0.1 g DBMP were mixed in 50 ml DMF. The resulting solution was heated at 50 °C for 2 days. The solution was poured into 400 ml diethyl ether to precipitate out the product. After filtration and drying under vacuum, 15.8 g white crystal product was obtained. The product was reacted with NaBF₄ (4.3 g, 0.04 mol) in 50 ml dried acetonitrile for 2 days. After the reaction, the insoluble chloride salt was removed by filtration. The product was collected by filtration and dried under vacuum. The overall yield was 16.7 g (63.7%).

Poly(ionic liquid)s were synthesized by free radical polymerization using AIBN as initiator in DMF as described previously.³⁰ The crosslinked P[VBTMA][BF₄] was synthesized in the same way except for adding 5 wt% of the crosslinker.


The polymers were characterized by ¹H NMR on a Bruker Advance DRX-400 spectrometer using d⁶-dimethylsulfoxide (DMSO-d⁶) as solvent. The elemental analyses of polymers were tested by Midwest Microlab LLC (US). The CO₂ sorption of the poly(ionic liquid)s was measured using a Cahn 1000 Electrobalance.

The structures of poly(ionic liquid)s are shown in Schemes 4 and 5. Two steps were generally involved in the preparation of ionic liquid monomers: the quaternization reaction and the anion exchange reaction of the halide ions with tetrafluoroborate, hexafluorophosphate, Sac or Tf₂N anions. The resulting monomers are soluble in polar solvents, such as DMF, acetone, or acetonitrile. All monomers based on ammonium except


for P[VBTMA][Tf₂N] are soluble in H₂O. The ionic liquid monomers based on phosphonium, pyridium, imidazolium are insoluble in H₂O. The poly(ionic liquid)s are soluble in DMF.

The ¹H NMR and elemental analyses indicated that the ionic liquid monomers and poly(ionic liquid)s obtained were pure.

5



Scheme 4



Scheme 5 - Structure of crosslinked P[VBTMA][BF₄]

5

CO₂ Sorption and Desorption

Figure 11 shows the effect of cation types on CO₂ sorption of poly(ionic liquid)s. The CO₂ sorption capacity of poly(ionic liquid)s with different cations is as follows:

P[VBTMA][BF₄] (10.2 mol.%) < P[VBTPP][BF₄] (7.8 mol.%) < P[VBP][BF₄] (3.6%) <

10 P[VBMI][BF₄] (3.0 %). The solubility increases with increasing cation polarity. The polymer based on ammonium has the highest solubility because of its highest cation polarity. The polymer based on imidazolium, with the lowest cation polarity, has the lowest solubility.

Figure 12 shows the effect of anion types on the CO₂ solubility of poly(ionic liquid)s.

The four polymers have the same cation structure, but different anions. P[VBTMA][PF₆] and

15 P[VBTMA][BF₄] have a similar CO₂ solubility of 10.7 mol.% and 10.2 mol.%, respectively.

P[VBTMA][[Sac] and P[VBTMA][Tf₂N] have a solubility of 2.8 mol.% and 2.7%,

respectively. The two poly(ionic liquid)s with inorganic anion have much higher solubility than the two with an organic anion, which can be explained in terms of the anion polarity effect on the interaction between the poly(ionic liquid)s with CO₂; the higher the anion polarity, the higher the affinity to CO₂. As a result the poly(ionic liquid) with high anion

20 polarity exhibit a higher CO₂ solubility.

The CO₂ sorption kinetics of poly(ionic liquid)s with different backbones are shown in Figure 13. At the equilibrium, the polymers took up 10.22 mol%

(P[VBtMA][BF₄]), 7.99 mol% (P[MatMA][BF₄]), respectively, in terms of their monomer units at 592.3 mmHg of CO₂ and 22 °C. With the same ammonium cation and BF₄⁻ anion, the polymer with polystyrene backbone had a higher CO₂ sorption capacity than that with polymethylmethacrylate backbone.

The effect of substituent of the ammonium cation on the CO₂ sorption is shown in Figure 14. Their CO₂ sorption capacities are as follows: P[VBtMA][BF₄] (10.2 mol.%) > P[VBTEA][BF₄] (4.85 mol.%) > P[VBtBA][BF₄] (3.1 mol.%). Obviously, the CO₂ sorption capacity decreases with increasing length of the substituent, which indicates that a large substituent on the ammonium cation blocks CO₂ sorption.

Figure 15 shows the effect of crosslinking on CO₂ sorption of poly(ionic liquid). Compared with P[VBtMA][BF₄] without crosslinking, the CO₂ sorption capacity of 5%-crosslinked P[VBtMA][BF₄] decreased by 17.3%.


EXAMPLE 3

Materials

Bis(2-hydroxyethyl)dimethyl ammonium chloride (Acros, 99%), 2,2-Bis(bromomethyl)-1,3-propanediol (Aldrich, 98%), 1-Methylimidazole (Lancaster, 99%), 1-Butylimidazole (Aldrich, 98%), 1,1-Carbonyldiimidazole (Aldrich, reagent grade), terephthaloyl chloride (Aldrich, 99+%), sodium tetrafluoroborate (Aldrich, 98%, NaBF₄), dimethyl sulfoxide (Aldrich, 99.9+%, DMSO) and methanol (A.C.S. reagent) were used as received. Acetonitrile (Aldrich, 99.5+%), *N,N*-Dimethylformamide (Aldrich, 99.8%, DMF) and triethylamine (EMD, 99.5%, Et₃N) were used after removing water by molecular sieves.

Synthesis and Characterization

The synthesis of the monomers, Bis(2-hydroxyethyl)dimethyl ammonium tetrafluoroborate ([BHEDMA][BF₄]) **1**, 2,2-Bis(methylimidazolium methyl)-1,3-propanediol tetrafluoroborate ([BMIMP][BF₄]) **2** and 2,2-Bis(butylimidazolium methyl)-1,3-propanediol tetrafluoroborate ([BBIMP][BF₄]) **3** is shown in Scheme 6. The reagents and conditions were: a) NaBF₄, acetonitrile, room temperature, 48h, 96%; b) 1-Methylimidazole, N₂, 60 °C, 24h, 98%; c) NaBF₄, acetonitrile, room temperature, 48h, 96%; d) 1-Butylimidazole, N₂, 80 °C, 24h, 97%; d) NaBF₄, acetonitrile, room temperature, 48h, 96%. Monomer **1** is an ammonium-based ionic liquid, while **2** and **3** are imidazolium-based ionic liquids.



Scheme 6

5

The synthesis of polycarbonate (PC) and polyethylene terephthalate (PET) types of ionic liquid polymers by condensation polymerization is as follows. The PC type of ionic liquid polymers can be synthesized using the monomers **1** (**2** or **3**) reacted with 1,1-carbonyldiimidazole. The PET type of ionic liquid polymers can be synthesized using the monomers **1** (**2** or **3**) reacted with terephthaloyl chloride, respectively. Both kinds of condensation polymerizations required a strict 1:1 ratio of the reagents with different difunctional groups. All the reactions were carried out in DMF at 60 °C for 24 h. All the polymers were precipitated by methanol after polymerization and dried under vacuum at 50 °C.


15

The ionic liquid monomer **1** is colorless, while **2** and **3** have a light yellow color. Synthesis of **2** and **3** in a N₂ atmosphere is necessary because the imidazole group is liable to be oxidized by the O₂ in the air, which will make the product have a brown color. For the 1-

methylimidazole is more active than 1-butylimidazole, it will react with 2,2-Bis(bromomethyl)-1,3-propanediol at a lower temperature (60 °C) than that of the 1-Butylimidazole (80 °C). All the monomers (1, 2 and 3) are viscous liquids, and they all absorb moisture quickly when contacting air, so all of them need to be dried in a rotating
5 evaporator before the polymerization.


The polycondensation synthesis of the PC type polymers, poly(bis(2-hydroxyethyl)dimethyl ammonium tetrafluoroborate) carbonate (P[BHEDMA][BF₄]C) **4**, poly(2,2-Bis(methylimidazolium methyl)-1,3-propanediol tetrafluoroborate) carbonate (P[BMIMP][BF₄]C) **5**, and poly(2,2-Bis(butylimidazolium methyl)-1,3-propanediol
10 tetrafluoroborate) carbonate (P[BBIMP][BF₄]C) **6** is shown in Scheme 7. Polymer **4** is white, while **5** and **6** have a light yellow color. At room temperature, all polymers are easily crashed into fine powders. Polymer **4** is soluble in acetonitrile, and polymer **5** and **6** are soluble in chloroform. They all can be cast into membranes for CO₂ separation using a solvent
evaporation method.

15



Scheme 7

- 5 The synthesis of the PET type polymers, poly(Bis(2-hydroxyethyl)dimethyl ammonium tetrafluoroborate) terephthalate (P[BHEDMA][BF₄]T) 7, poly(2,2-Bis(methylimidazolium methyl)-1,3-propanediol tetrafluoroborate) terephthalate (P[BMIMP][BF₄]T) 8 and poly(2,2-Bis(butylimidazolium methyl)-1,3-propanediol tetrafluoroborate) terephthalate (P[BBIMP][BF₄]T) 9, is shown in Scheme 8. Triethylamine
- 10 was added to the reaction system slowly to remove the hydrogen chloride. The obtained three polymers (7, 8 and 9) are all white powders. But the solubilities of them are not as good as those for the corresponding PC types because their phenyl groups increase the rigidity of the polymer chains greatly. Because they are only soluble in solvents with strong polarity and high boiling points, such as DMSO and DMF, it is difficult to fabricate them into membranes
- 15 using the solvent evaporation method.



Scheme 8

5

EXAMPLE 4Poly(ionic liquid) Membranes for CO₂/CH₄ and CO₂/N₂ Separations³¹

Copolymers of ionic liquid and polyethylene glycol (PEG), for example P[VB TMA][BF₄]-co-PEG and P[MATMA][BF₄]-co-PEG were synthesized as follows: Ionic liquid monomer ([VB TMA][BF₄] or [MATMA][BF₄]) (2 gram), poly(ethylene glycol)methyl ether methacrylate (M_n = 2000) (2 g), AIBN (40 mg) and DMF (8 ml) are charged into a reaction tube. The tube is tightly sealed, degassed, and immersed in an oil bath at 60 °C for 12 h to get complete polymerization. These copolymer solutions were used to cast membranes for CO₂/CH₄ and CO₂/N₂ separations at 35 °C, 50 °C and 70 °C, all at 40 psig. These membranes were tested for permeability and selectivity. Figure 16 shows the CO₂/CH₄ selectivity. Figure 17 shows that our copolymers have better properties than the previously studied representative polymers for CO₂/CH₄ separation. Figure 18 shows the selectivity of CO₂/N₂ for both P[VB TMA][BF₄]-co-PEG and P[MATMA][BF₄]-co-PEG at

35°C, 50°C and 70°C. Figure 19 illustrates that both P[VBTMA][BF₄]-co-PEG and P[MATMA][BF₄]-co-PEG membranes exhibit better ideal separation performance than the representative polymers because the data lie well above the upper limit bound curve, particularly for P[MATMA][BF₄]-co-PEG.

5

The foregoing description and drawings comprise illustrative embodiments of the present inventions. The foregoing embodiments and the methods described herein may vary based on the ability, experience, and preference of those skilled in the art. Merely listing the steps of the method in a certain order does not constitute any limitation on the order of the steps of the method. The foregoing description and drawings merely explain and illustrate the invention, and the invention is not limited thereto, except insofar as the claims are so limited. Those skilled in the art who have the disclosure before them will be able to make modifications and variations therein without departing from the scope of the invention.

10

References

1. Azar, C.; Rodhe, H. *Science* **1997**, *276*, 1818-1819.
2. Ruether, J. A. FETC Programs for Reducing Greenhouse Gas Emissions. Report No. DOE/EFTC-98/1058, U.S. Department of Energy: Pittsburgh, PA, **1999**.
- 5 3. DOE/OS-FE. Carbon sequestration. State of the Science; Office of Science and Office of Fossil Energy; U.S. Department of Energy: Washington, DC, **1999**.
4. U.S. Department of Energy. Carbon Sequestration-Research and Development; **1999**.
http://www.fe.doe.gov/coal_power/sequestration/reports/rd/index.html.
5. White, C.M.; Strazisar, B.R.; Granite, E.J. Hoffman; Pennline, H. W. J. *Air & Waste*
10 *Manage. Assoc.* **2003**, *53*: 645-715
6. Huddleston, J. G.; Willauer, H. D.; Swatloski, R. P.; Rogers, R. D. *Chem Commun* **1998**, *16*, 1765-1766.
7. Wasserscheid, P.; Keim, W. *Angew Chem Int Ed* **2000**, *39*, 3772-3789.
8. Welton, T. *Chem Rev* **1999**, *99*, 2071-2084.
- 15 9. Rogers, R. D. and Seddon, K. R. (ed), *Ionic Liquids as Green Solvents: Progress and Prospects*, American Chemical Society: Washington, DC, **2003**.
10. Ding, J.; Zhou, D.; Spinks, G.; Wallace, G; Forsyth, S.; Forsyth, M.; MacFarlane, D. *Chem. Mater* **2003**; *15*, 2392-2398.
11. Liang, C.; Yuan, C-Y.; Warmack, R. J.; Barnes, C. E. and Dai, S. *Anal Chem* **2002**,
20 *74*, 2172-2176.
12. Pernak, J.; Czepukowicz, A.; Poz'niak, R. *Ind Eng Chem Res* **2001**, *40*, 2379-2383.
13. Blanchard, L. A.; Hancu, D.; Beckman, E. J.; Brennecke, J. F. *Nature* **1999**, *399*, 28-29.
14. Blanchard, L. A.; Gu, Z. Y.; Brennecke, J. F. *J Phys Chem B* **2001**, *105*, 2437-2444.
- 25 15. Blanchard, L.A.; Brennecke, J. F. *Ind Eng Chem Res* **2001**, *40*, 287-292.
16. Anthony, J. L.; Maginn, E. J.; Brennecke, J. F. *J Phys Chem B* **2002**, *106*, 7315-7320.
17. Kamps, A. P.-S.; Tuma, D.; Xia, J.; Maurer, G. *J Chem Eng Data* **2003**, *48*, 746-749.
18. Husson-Borg, P.; Majer, V.; Costa Gomes, M. F. *J Chem Eng Data* **2003**, *48*, 480-485.
19. Cadena, C.; Anthony, J. L.; Shah, J. K.; Morrow, T. I.; Brennecke, J. F. and Maginn,
30 E. J. *J Am Chem Soc* **2004**, *126*, 5300-5308.

20. Scovazzo, P.; Camper, D.; Kieft, J.; Poshusta, J.; Koval, C.; Noble, R. D. *Ind Eng Chem Res* 2004, 43, 6855-6860.
21. Camper, D.; Scovazzo, P.; Koval, C.; Noble, R. D. *Ind Eng Chem Res* 2004, 43, 3049-3054.
- 5 22. Baltus, R. E.; Culbertson, B. H.; Dai, S.; Luo, H.; DePaoli, D. W. *J Phys Chem B* 2004, 108, 721-727
23. Bates, E. D.; Mayton, R. D.; Ntai, I.; Davis Jr., J. H. *J Am Chem Soc* 2002, 124, 926.
24. Scovazzo, P.; Kieft, J.; Finan, D. A.; Koval, C.; DuBois, D. L.; Noble, R. D. *J Memb Sci* 2004, 238, 57-63;
- 10 25. Scovazzo, P.; Visser, A. E.; Davis, J. H., Jr.; Rogers, R. D.; Koval, C. A.; DuBois, D. L.; Noble, R. D. *ACS Symp Ser* 2002, 818, 69-87;
26. Fortunato, R.; Afonso, C. A. M.; Reis, M. A. M.; Crespo, J. G. *J Memb Sci* 2004, 242, 197-209.
27. Ding, S.; Tang, H. Radosz, M.; Shen, Y. *J Polym Sci Part A: Poly Chem* 2004, 42, 5794-5801.
- 15 28. Tang, H.; Tang, J.; Radosz, M.; Shen, Y. *J Polym Sci Part A: Poly Chem* 2005, 43, 1432-1443.
29. Macedonia, M. D.; Moore, D. D. and Maginn, E. J. *Langmuir* 2000, 16, 3823-3834
30. Tang, J. B.; Sun, W. L.; Tang, H. D. Radosz, M.; Shen, Y. *Chem. Commun.* 2005, 3325-3327.
- 20 31. Hu, X.; Tang, J.; Blasig, A.; Shen, Y.; Radosz, M. *J. Membrane Science* 2005, in preparation.

We claim:

1. A composition of matter for forming polymers, comprising an ionic liquid monomer.
2. A composition of matter as defined in claim 1, wherein the ionic liquid monomer comprises an inorganic moiety.
3. A polymer, comprising a polymerized ionic liquid monomer.
4. A polymer as defined in claim 3, further comprising a co-polymer.

4. A polymer as defined in claim 2, wherein the ionic liquid monomer is selected from the group consisting of:

(a) imidazolium-based ionic liquids, consisting of 1-[2-(methacryloyloxy)ethyl]-3-butyl-imidazolium tetrafluoroborate ([MABI][BF₄]), 1-(*p*-vinylbenzyl)-3-butyl-imidazolium tetrafluoroborate ([VBBI][BF₄]), 1-(*p*-vinylbenzyl)-3-methyl-imidazolium tetrafluoroborate [VBMI][BF₄], 1-(*p*-vinylbenzyl)-3-butyl-imidazolium hexafluorophosphate [VBBI][PF₆], 1-(*p*-vinylbenzyl)-3-butyl-imidazolium *o*-benzoic sulphimide ([VBBI][Sac]), 1-(*p*-vinylbenzyl)-3-butyl-imidazolium trifluoromethane sulfonamide ([VBBI][BF₄]), and (1-butylimidazolium-3)methyl-ethylene oxide ([BIEO][BF₄]);

(b) ammonium-based ionic liquids, consisting of (*p*-vinylbenzyl)trimethyl ammonium tetrafluoroborate ([VBTMA][BF₄]), (*p*-vinylbenzyl)triethyl ammonium tetrafluoroborate ([VBTEA][BF₄]), (*p*-vinylbenzyl)tributyl ammonium tetrafluoroborate ([VBTBA][BF₄]), 2-(methacryloyloxy)ethyltrimethylammonium tetrafluoroborate ([MATMA][BF₄]), (*p*-vinylbenzyl)trimethyl ammonium hexafluorophosphate ([VBTMA][PF₆]), (*p*-vinylbenzyl)trimethyl ammonium *o*-benzoic sulphimide ([VBTMA][Sac]), and (*p*-vinylbenzyl)trimethyl ammonium trifluoromethane sulfonamide ([VBTMA][Tf₂N]);

(c) phosphonium-based ionic liquids, consisting of (*p*-vinylbenzyl)triethyl phosphonium tetrafluoroborate ([VBTEP][BF₄]), and (*p*-vinylbenzyl)triphenyl phosphonium tetrafluoroborate ([VBTPP][BF₄]);

(d) pyridinium-based ionic liquids, consisting of 1-(*p*-vinylbenzyl) pyridinium tetrafluoroborate ([VBP][BF₄]) and

(e) condensation polymerization ionic monomers, consisting of bis(2-hydroxyethyl)dimethyl ammonium tetrafluoroborate ([BHEDMA][BF₄]), 2,2-bis(methylimidazolium methyl)-1,3-propanediol tetrafluoroborate ([BMIMP][BF₄]), and 2,2-bis(butylimidazolium methyl)-1,3-propanediol tetrafluoroborate ([BBIMP][BF₄]).

5. A polymer as defined in claim 2, wherein the ionic liquid monomer has a gas sorption capacity and rate and wherein either the gas sorption capacity or rate, or both, of the polymer are higher than those of the corresponding ionic liquid.
6. A polymer as defined in claim 5, wherein the gas is carbon dioxide.
7. A polymer as defined in claim 2, wherein the polymerization is a polymerization method selected from the group consisting of radical polymerization and condensation polymerization.
8. A method of forming a polymer, comprising the step of polymerizing an ionic liquid monomer.
9. A method as defined in claim 8, wherein the polymerization step is selected from the group consisting of radical polymerization and condensation polymerization.
10. A process for the separation of a gas, comprising the steps of:
 - (a) contacting a mixture containing the gas with a sorbent comprising at least one poly(ionic liquid) compound under such conditions as to obtain a product having a lower concentration of the gas than the mixture and a sorbent containing absorbed gas which has been removed from the mixture; and
 - (b) treating the solid sorbent under conditions as to substantially desorb the gas contained in the solid sorbent so as to obtain a regenerated solid sorbent.
11. A method as defined in claim 10, wherein the treatment step is one or more steps selected from the group consisting of heating, depressurizing, and displacing the gas.

12. A process as defined in claim 10, wherein the gas is carbon dioxide.
13. A process for the separation of carbon dioxide, comprising the step of contacting a gas mixture containing carbon dioxide with a membrane comprising at least one poly(ionic liquid) compound under such conditions as to obtain a CO₂-rich gas product that permeates through the membrane and a CO₂-lean gas product that does not permeate through the membrane.




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6






FIG. 7





a



b

FIGS. 8



FIGS. 9A, B




FIG. 10




FIG 11




FIG 12




FIG 13




FIG 14




FIG. 15




FIG. 16




FIG. 17




FIG. 18




FIG. 19