

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
23 February 2006 (23.02.2006)

PCT

(10) International Publication Number
WO 2006/020785 A1

(51) International Patent Classification:
C08F 216/06 (2006.01) **C11D 17/04** (2006.01)

(21) International Application Number:
PCT/US2005/028583

(22) International Filing Date: 10 August 2005 (10.08.2005)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/600,483 10 August 2004 (10.08.2004) US

(71) Applicant (for all designated States except US): **E.I. DUPONT DE NEMOURS AND COMPANY** [US/US];
1007 MARKET STREET, WILMINGTON, Delaware
19898 (US).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **MORKEN, Peter, A.**
[US/US]; 6 Weilers Bend, Wilmington, Delaware 19810
(US).

(74) Agent: **DOBSON, Kevin, S.**; E. I. DU PONT DE
NEMOURS AND COMPANY, LEGAL PATENT
RECORDS CENTER, 4417 Lancaster Pike, Wilmington,
Delaware 19805 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: COPOLYMERS OF VINYL ALCOHOL AND ITACONIC ACID AND USES THEREOF

(57) Abstract: The present invention is a film that is soluble in cold water, and useful in such applications as detergent sachets. Films of the present invention are PVOH copolymers that comprise itaconic acid.



WO 2006/020785 A1

Copolymers of Vinyl Alcohol and Itaconic Acid and Uses Thereof

This application claims the benefit of U.S. Provisional Application
5 No. 60/600,483, filed August 10, 2004.

BACKGROUND OF THE INVENTION

Field of the Invention

This invention relates to uses of polyvinyl alcohol copolymers.

Description of the Prior Art

10 There is a consumer need for water-soluble packaging, which offers the consumer convenience and can reduce packaging waste persistent in the environment when the packaging material is ultimately degraded by microorganisms at sewage treatment plants. This convenience to the consumer can also include the benefit of unit-dose
15 packaging, which does not require measurement or handling of package contents. It can be particularly attractive to package laundry detergent in such a manner, and in fact such packaging is in use today to deliver liquid laundry detergent and automatic dishwasher cleaning agents.

Water-soluble packaging material commonly used for liquid laundry
20 detergent is often based on polyvinyl alcohol (PVOH) films. PVOH is manufactured commercially by polymerization of vinyl acetate monomer (VAM) to afford polyvinyl acetate (PVAc). The PVAc is then transesterified -- in most commercial processes with methanol -- to afford PVOH and methyl acetate. PVOH that is >98% hydrolyzed (that is, less
25 than 2% residual vinyl acetate) is unacceptable for this application because it does not dissolve at practical temperatures, usually requiring temperatures in excess of 50 °C to dissolve. This temperature is inconvenient for consumers. Of greater utility to consumers are packaging materials that dissolve in cold water, that is, water at a
30 temperature of from 10-25 °C. This can be accomplished by modifying PVOH to reduce crystallinity and/or increase hydrophilicity of the polymer. The crystallinity of the polymer is conveniently and conventionally

reduced by carrying out the transesterification of PVAc in such a manner as to not complete the conversion to PVOH and obtain a product that is conventionally known as partially hydrolyzed PVOH (phPVOH).

Commercial grades of phPVOH include Celvol 523 from Celanese

5 Chemicals and Kuraray POVAL PVA 217 sold by Kuraray Co., Ltd. The degree of conversion (loosely referred in the industry as "hydrolysis") in most cases varies from 78-99.8%, and 88% hydrolyzed is an especially common grade for water soluble packaging. Post-polymerization or post-copolymerization modifications of PVOH can reduce crystallinity. Adding
10 polar groups to the polymer can increase the hydrophilicity of the polymer. This can be accomplished by post-polymerization reaction or by copolymerization method. Post polymerization reactions have been reviewed (*Polyvinyl Alcohol- Developments*; Finch, C.A., Ed.; John Wiley & Sons: New York, 1992). One known copolymerization
15 method to increase hydrophilicity is to copolymerize VAM with an acid-containing monomer such as acrylic acid or others as described in US 4,885,105. After transesterification of such a copolymer a hydrophilic carboxylic acid or carboxylic acid salt remains. Inclusion of up to 10 mol% comonomer can modify the film solubility adequately to satisfy consumers.
20 A cold water soluble film can be obtained by copolymerization of VAM with a monomer that later undergoes a chemical reaction to render it hydrophilic. For example, VAM/methyl acrylate (MA) copolymer is known to undergo transesterification reaction to a PVOH copolymer where the MA carboxyl group has formed a lactone structure with a neighboring
25 alcohol unit (*Polyvinyl Alcohol- Developments*; Finch, C.A., Ed.; John Wiley & Sons: New York, 1992). This lactone-containing polymer is not soluble in cold water. However, after treatment with alkali such as sodium hydroxide the lactone is converted to the ring-opened, sodium carboxylate form which is cold water soluble.

30 In order to be practical and useful, the films should be compatible with the chemicals they contain, at least for enough time that premature rupture of the package does not occur. For example, a film made from

phPVOH is sensitive to high or low pH chemicals, as they cause hydrolysis of the residual vinyl acetate, effecting change to cold-water insoluble PVOH.

PVOH copolymers from monomers containing carboxylate or
5 carboxylate precursor groups are stable to high pH. However at lower pH the carboxylic acid can undergo ion-exchange with protons in the film's encapsulate. If the number of carbon atoms separating the carboxylate carbon and oxygen atom of a neighboring alcohol group is equal to three, then the groups can undergo lactonization to afford the water-insoluble
10 lactone-containing copolymer. This package then does not completely dissolve, leading to consumer dissatisfaction. The pH where lactonization reaction begins to occur is about <8, depending on the concentration of the ions in the encapsulate.

It has been found that a copolymer that includes itaconic acid (IA),
15 which is convenient to manufacture due to its high conversion during polymerization, can be a useful carboxylate copolymer. WO 94/04656 describes use of 2-8 mol% IA copolymer in water soluble packaging application. This copolymer retains cold water solubility to a better extent than a methyl acrylate copolymer that has been converted to sodium
20 carboxylate form by caustic. For example, a film using greater than or equal to 4 mol% IA gave good solubility stability after prolonged contact with Ariel liquid laundry detergent. However a film with 2.8% IA had inadequate solubility stability, surprising in view of the fact that WO 94/04656 teaches that 2-8 mol% IA copolymer has desirable solubility
25 properties. However, the IA monomer has some disadvantages. It is a higher cost monomer than VAM. Also most commercial transesterification processes utilize a basic catalyst. The IA in the copolymer is neutralized in an acid-base reaction with the basic catalyst, which adds cost to the process. The increased catalyst demand can also exceed the feeding
30 capability of existing facilities, necessitating costly modifications. Thus it can be desirable to manufacture an IA copolymer having good cold water solubility with the lowest possible IA content.

SUMMARY OF THE INVENTION

In one aspect the present invention is a film useful as a cold-water soluble detergent sachet comprising a terpolymer composition comprising vinyl alcohol, methyl acrylate, and itaconic acid moieties, wherein: (i) the
5 terpolymer comprises less than about 5 mol% of vinyl acetate moieties;
(ii) the methyl acrylate is present in an amount of at least about 1 mol% up to about 9 mol%; (iii) the itaconic acid is present in an amount of at least about 1 mol% up to about 9 mol%, and, (iv) the methyl acrylate is in the form of a lactone.

DETAILED DESCRIPTION OF THE INVENTION

10 PVA copolymers of the present invention can be obtained by known and conventional methods. PVA is typically obtained by copolymerization of ethylene and vinyl acetate comonomers, followed by hydrolysis of the vinyl acetate copolymer to the vinyl alcohol copolymer.
15 As used herein, the term complete hydrolysis, or 100% hydrolysis, shall be taken to mean that a stoichiometrically sufficient amount of reagent has been added to hydrolyze 100 mol% of the acetate groups of a polyvinyl acetate. A PVA copolymer of the present invention can comprise some residual un-hydrolyzed acetate moieties. Preferably a PVA copolymer of
20 the present invention comprises less than about 5 mol% residual acetate moieties, more preferably less than about 3 mol%, most preferably less than about 2 mol%.

The PVA/acid copolymer of the present invention comprises from at least about 1 mol% to about 10 mol% itaconic acid (IA). Preferably the
25 PVA acid copolymer comprises from about 1 to about 9 mol% itaconic acid, more preferably from about 1 to about 5 mol%, and most preferably from about 1 to about 3 mol% itaconic acid. In a particularly preferred embodiment, the itaconic acid is present in an amount of at least about 2 mol%.

30 The degree of polymerization of the PVA acid copolymer is from about 400 to about 4000. Preferably the degree of polymerization of the PVA copolymer is from about 500 to about 2000.

In another embodiment, the PVA acid copolymer of the present invention is a terpolymer comprising vinyl alcohol and itaconic acid constituents, and additionally comprising a second acid polymer constituent that is either an acrylic or a methyl acrylate unit. A PVA mixed acid terpolymer of the present invention can be preferred in some cases.

In still another embodiment, the present invention is a polyvinyl alcohol terpolymer composition wherein the terpolymer comprises vinyl alcohol, methyl acrylate, and itaconic acid moieties, wherein the vinyl alcohol is present in an amount of at least about 90 mol%. Preferably the vinyl alcohol is present in an amount of at least about 92 mol%, and most preferably at least about 94 mol%.

Of the remaining terpolymer, itaconic acid is present in an amount of from at least about 1.0 mol% up to about 9 mol%, and methyl acrylate is present in an amount of from at least about 1 mol% up to about 9 mol%.

It can be desirable to reduce the IA content of the copolymer, for cost reasons, to a level of less than about 2.8% by incorporating more of the methyl acrylate. Incorporating functional equivalents of MA or IA is also contemplated as within the scope of the present invention. For example, alkyl (meth)acrylates such as methylmethacrylate, butyl acrylate, or ethyl (meth)acrylate (wherein "(meth)acrylate" is shorthand for either a methacrylate or an acrylate) are considered functional equivalents of methyl acrylate.

A film can be prepared from a composition of the present invention by conventional methods known to one of ordinary skill in the art. For example, a film can be prepared as a cast film. Other methods of preparing a film from the composition described herein would be known to one of ordinary skill in the art.

A film comprising the terpolymer composition described herein is soluble in a cold aqueous solution at a temperature of less than or equal to about 25°C. Preferably the film is soluble in water that is at a temperature of from about 10°C to about 25°C. The terpolymer comprises

methyl acrylate that essentially exists in the lactone form rather than in the acid or carboxylate form.

The cold-water solubility of a film described herein can be useful in practical applications such as for detergent sachets or pouches that
5 dissolve in cold water to allow the detergent contents to mix with the water, without leaving an insoluble polymer residue from the package. A cold-water soluble pouch of the present invention can also be used to contain other cleaning chemicals, insecticides, herbicides, and similar materials, with the caveat that the contents of the pouch should be
10 compatible or otherwise not readily degrade or react with the pouch composition.

EXAMPLES

The Examples are for illustrative purposes only, and are not intended to limit the scope of the invention.

Examples 1-4

A 2 L polymer kettle was assembled with an overhead stirrer, a Claisen head with a multi-inlet port fitting connected to 2 syringe pumps and a tap-H₂O condenser further attached to a N₂ bubbler, an overhead thermowell with a thermocouple device, and a septum. The agitator was a
20 single PTFE paddle and the stir rate was set to 80 rpm. The kettle was charged with 1000 g vinyl acetate (Aldrich Chemical co., Milwaukee, WI, USA) 401 g MeOH (EM Science), 1.5 g itaconic acid (Aldrich), and 0.6 g methyl acrylate (Aldrich) then degassed at rt for 20 minutes with a sparging tube. The kettle was then heated to reflux (ca. 65 °C) with an oil
25 bath. Syringe pump #1 was charged with neat methyl acrylate. Syringe pump #2 was charged with a 24.7 wt% solution of itaconic acid in MeOH. 2 g of VAZO-64 (DuPont, Wilmington, DE, USA) dissolved in 100 g of MeOH was added to the reactor. Syringe pump #1 was then activated to feed at 0.0262 cc/min and syringe pump #2 was activated to
30 feed at 0.46 cc/min. The polymerization was refluxed for 159 minutes, then a solution of sodium nitrite (Aldrich) in 80 g of MeOH was added all at once to halt the polymerization. The solids were determined to be 17.8%

at this time. The polymer is thus 4.1 mol% itaconic acid and 1.6 mol% methyl acrylate. The polyvinyl acetate terpolymer was transferred to a 3 L round bottom flask. The flask was attached to a rotary evaporator and MeOH/vinyl acetate azeotrope was removed at reduced pressure.

- 5 Addition of 500 g of MeOH followed by azeotropic distillation was repeated 3 times, at which time removal of vinyl acetate was judged substantially complete. The polyvinyl acetate was dissolved in 700 g of MeOH and charged to a 1 gallon explosion-proof stainless steel blender (Eberbach Corp., Ann Arbor, MI). The blender was set to stir at 10,000 rpm then
- 10 430 g of 25 wt% sodium methoxide in methanol (Aldrich) was added through a small hole in the blender's cover. The ensuing heterogeneous mixture was stirred for 10 minutes, then 143 g of glacial acetic acid (EM Science) was slowly added. The mixture was stirred 2 minutes, then filtered. The polymer product was rinsed 3 times with MeOH and once
- 15 with acetone, then dried in a vacuum oven at 80 °C overnight. 151 g of white terpolymer powder were isolated. The viscosity was determined to be 21.8 mPa-s (cP) (4% solids aqueous solution at 20 °C (68 °F), determined by Hoeppler falling ball method). Infrared analysis in ATR mode of the polymer showed the presence of a lactone carbonyl peak at
- 20 1745 cm^{-1} , an acid carboxyl at 1705 cm^{-1} , and a sodium carboxylate at 1572 cm^{-1} . Examples 5-9 were prepared in the same manner, except that the polymerization time was 175 minutes and the precharge and feed rates of itaconic acid (IA) and methyl acrylate (MA) were modified as shown in Table 1.

Examples 5-9**Table 1**

Ex No.	IA Precharge (g)	MA Precharge (g)	MeOH Precharge (g)	Pump 1 (cc/min.)	Pump 2 (cc/min.)	IA mol%	MA mol%
5	1.24	0.72	400	0.0314	0.368	2.3	1.4
6	1.51	0.83	400	0.0380	0.442	2.8	1.7
7	1.49	1.47	400	0.064	0.442	3.0	3.0
8	1.00	2.50	400	0.11	0.300	2.1	5.4
9	1.40	1.48	420	0.066	0.425	2.7	2.9

5

Comparative Examples:

Itaconic acid copolymers were prepared by the same method, with the exception that only one syringe pump was utilized.

10

Example	IA Precharge (g)	MeOH Precharge (g)	IA Pump (cc/min.)	IA mol%
Comparative Example 1	2.4	400	0.49	4.0
Comparative Example 2	2.0	400	0.46	2.8

Film Fabrication and Testing:

Polymers were dissolved to 13% solids in 80 °C H₂O. Plasticizers, surfactants, antiblock agents, and other components were added.

15 Carbowax™ polyethylene glycol 200 (Union Carbide, Danbury, Ct.) was also added. The final compositions excluding H₂O contained polymer, additive package, and polyethylene glycol in a ratio of 65:33.7:1.3. The solution was cooled to room temperature, and a film was cast on a glass plate using an 8" wide knife with a 10 mil gate (Gardner Laboratory, Silver
20 Spring, Maryland, USA). The film was allowed to dry at room temperature

overnight. A 14 oz round, plastic container with diameter of 5" was charged with 100 mL of Ariel Essential liquid laundry detergent (Proctor & Gamble Co.; pH of the neat detergent was 7.3 and of the aqueous (tap water) 5 wt% solution was 7.9). A 3 mil film of the previous example with
 5 a diameter ca. 0.5" greater than the diameter of the container was placed on top of the container, then the lid was attached to the container, thus forming a seal. The container was then inverted and placed in a 38 °C oven for accelerated aging. Samples were removed periodically, and the time for an 8 cm² piece of film to dissolve in 500 mL of stirred, room
 10 temperature water was determined.

Example	IA mol%	MA mol%	Dissolution Time 0 weeks aging (sec.)	Dissolution Time 4 weeks aging (sec.)
5	2.3	1.4	83	205
6	2.8	1.7	50	120
7	3.0	3.0	44	107
8	2.1	5.4	71	123
9	2.7	2.9	57	121
Comparative Example 1	4.0	0	54	128
Comparative Example 2	2.8	0	110	156

As can be seen in the table, lower dissolution times than 4.0 mol% IA
 15 (Comparative Example 1) can be achieved with less IA provided MA termonomer is incorporated.

WHAT IS CLAIMED IS:

1. A film that is soluble in cold water comprising a terpolymer
5 composition comprising vinyl alcohol, an alkyl acrylate, and itaconic acid
moieties, wherein: (i) the terpolymer comprises less than about 5 mol% of
vinyl acetate moieties; (ii) the alkyl acrylate is present in an amount of at
least about 1 mol% up to about 9 mol%; (iii) the itaconic acid is present in
an amount of at least about 1 mol% up to about 10 mol%, and, (iv) the
10 alkyl acrylate is in the form of a lactone.
2. The film of Claim 1 wherein the film comprises less than about 3
mol% acetate moieties.
3. The film of Claim 2 wherein the film comprises less than about 2
mol% acetate moieties.
- 15 4. The film of Claim 3 wherein the itaconic acid is present in an
amount of from about 1 mol% to about 9 mol%.
5. The film of Claim 4 wherein the itaconic acid is present in an
amount of from about 1 mol% to about 5 mol%.
6. The film of Claim 5 wherein the itaconic acid is present in an
20 amount of from about 1 mol% to about 3 mol%.
7. An article comprising a film that is soluble in cold water wherein the
film comprises a terpolymer composition comprising vinyl alcohol, an alkyl
acrylate, and itaconic acid moieties, wherein: (i) the terpolymer comprises
less than about 5 mol% of vinyl acetate moieties; (ii) the alkyl acrylate is
25 present in an amount of at least about 1 mol% up to about 9 mol%; (iii) the
itaconic acid is present in an amount of at least about 1 mol% up to about
10 mol%, and, (iv) the alkyl acrylate is in the form of a lactone.
8. The article of Claim 7 wherein the article is a sachet or pouch.
9. The article of Claim 8 wherein the pouch contains detergent.
- 30 10. The article of Claim 9 wherein the detergent is a liquid.

11. A process for dispersing detergent in cold water comprising the steps: (1) dispensing detergent into a pouch comprising a film that is soluble in cold water wherein the film comprises a terpolymer composition comprising vinyl alcohol, an alkyl acrylate, and itaconic acid moieties,
- 5 wherein: (i) the terpolymer comprises less than about 5 mol% of vinyl acetate moieties; (ii) the alkyl acrylate is present in an amount of at least about 1 mol% up to about 9 mol%; (iii) the itaconic acid is present in an amount of at least about 1 mol% up to about 10 mol%, and, (iv) the alkyl acrylate is in the form of a lactone; and (2) placing the pouch in contact
- 10 with water at a temperature of less than or equal to about 25 °C.

INTERNATIONAL SEARCH REPORT

International Application No

US2005/028583

A. CLASSIFICATION OF SUBJECT MATTER

C08F216/06 C11D17/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C08F C11D D21H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	WO 2005/059248 A (E.I. DUPONT DE NEMOURS AND COMPANY; ECHT, ELLIOTT; MORKEN, PETER, A; C) 30 June 2005 (2005-06-30) claims 1,10-14 page 6, lines 19-28 examples 5-11	1-7
P,A	WO 2004/085600 A (MONOSOL, LLC; VERRALL, ANDREW, P; BENING, SCOTT, P; KUGLER, KAREN, A) 7 October 2004 (2004-10-07) table 2	1-11
A	EP 0 291 198 A (THE CLOROX COMPANY) 17 November 1988 (1988-11-17) cited in the application examples A,B & US 4 885 105 A (YANG ET AL) 5 December 1989 (1989-12-05)	1-11



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

10 January 2006

Date of mailing of the international search report

16/01/2006

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Knutzen-Mies, K

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US2005/028583

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 2005059248	A	30-06-2005	NONE	
WO 2004085600	A	07-10-2004	AU 2004223907 A1 CA 2519576 A1 EP 1604004 A1 US 2004186034 A1 US 6787512 B1	07-10-2004 07-10-2004 14-12-2005 23-09-2004 07-09-2004
EP 0291198	A	17-11-1988	AR 245748 A1 AU 604890 B2 AU 1608288 A BR 8802311 A CA 1309924 C DE 3885507 D1 DE 3885507 T2 ES 2059512 T3 JP 1014244 A MX 166114 B US 4885105 A	28-02-1994 03-01-1991 17-11-1988 13-12-1988 10-11-1992 16-12-1993 03-03-1994 16-11-1994 18-01-1989 21-12-1992 05-12-1989
US 4885105	A	05-12-1989	AR 245748 A1 AU 604890 B2 AU 1608288 A BR 8802311 A CA 1309924 C DE 3885507 D1 DE 3885507 T2 EP 0291198 A2 ES 2059512 T3 JP 1014244 A MX 166114 B	28-02-1994 03-01-1991 17-11-1988 13-12-1988 10-11-1992 16-12-1993 03-03-1994 17-11-1988 16-11-1994 18-01-1989 21-12-1992