




(86) Date de dépôt PCT/PCT Filing Date: 2001/09/21
 (87) Date publication PCT/PCT Publication Date: 2002/04/18
 (85) Entrée phase nationale/National Entry: 2003/08/06
 (86) N° demande PCT/PCT Application No.: US 2001/029612
 (87) N° publication PCT/PCT Publication No.: 2002/030393
 (30) Priorités/Priorities: 2000/09/21 (09/666,174) US;
 2000/11/13 (09/711,758) US

(51) Cl.Int.⁷/Int.Cl.⁷ A61K 9/00, A61K 47/34, A61K 38/09
 (71) Demandeur/Applicant:
 ATRIX LABORATORIES, INC., US
 (72) Inventeurs/Inventors:
 DUNN, RICHARD L., US;
 GARRETT, JOHN S., US;
 RAVIVARAPU, HARISH, US;
 CHANDRASHEKAR, BHAGYA L., US
 (74) Agent: GOUDREAU GAGE DUBUC

(54) Titre : FORMULATIONS D'ADMINISTRATION DE LEUPROLIDE PAR POLYMERE AVEC UNE EFFICACITE ACCRUE

(54) Title: POLYMERIC DELIVERY FORMULATIONS OF LEUPROLIDE WITH IMPROVED EFFICACY

Serum leuprolide levels in dogs after administering ATRIGEL[®] - 6% w/w drug and LUPRON[®] formulations



(57) Abrégé/Abstract:

A flowable composition for use as a controlled release implant, comprising a biodegradable thermoplastic polyester that is at least substantially insoluble in aqueous medium or body fluid, a biocompatible polar aprotic solvent, miscible to dispersible in aqueous medium or body fluid and leuprolide acetate, an implant or a kit comprising such composition, a method for forming the

(57) **Abrégé(suite)/Abstract(continued):**

flowable composition. The present invention is also directed to a biodegradable implant formed in situ, in a patient, to a method of forming a biodegradable implant in situ, in a living patient which includes injecting a flowable composition within the body of a patient and allowing the biocompatible polar aprotic solvent to dissipate to produce a solid biodegradable implant and a method of treating cancer in a patient by administering to the patient in need of such treatment an effective amount of a flowable composition of the present invention or a method of reducing LHRH levels in a patient.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
18 April 2002 (18.04.2002)


PCT

(10) International Publication Number
WO 02/30393 A3

- (51) International Patent Classification⁷: A61K 9/00, 38/09, 47/34 94587 (US). CHANDRASHEKAR, Bhagya, L. [US/US]; 3600 San Luis Court, Fort Collins, CO 80525 (US).
- (21) International Application Number: PCT/US01/29612 (74) Agent: VIKSNINS, Ann, S.; Schwegman, Lundberg, Woessner & Kluth, P.O. Box 2938, Minneapolis, MN 55402 (US).
- (22) International Filing Date: 21 September 2001 (21.09.2001) (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (25) Filing Language: English (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- (26) Publication Language: English
- (30) Priority Data:
09/666,174 21 September 2000 (21.09.2000) US
09/711,758 13 November 2000 (13.11.2000) US
- (71) Applicant (*for all designated States except US*): ATRIX LABORATORIES, INC. [US/US]; 2579 Midpoint Drive, Fort Collins, CO 80525 (US). (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- (72) Inventors; and
(75) Inventors/Applicants (*for US only*): DUNN, Richard, L. [US/US]; 5021 Kitchell Drive, Fort Collins, CO 80524 (US). GARRETT, John, S. [US/US]; 7113 Silver Moon Lane, Fort Collins, CO 80525-4417 (US). RAVIVARAPU, Harish [US/US]; 4605 Dinuba Street, Union City, CA
- Published:
— with international search report

[Continued on next page]

(54) Title: POLYMERIC DELIVERY FORMULATIONS OF LEUPROLIDE WITH IMPROVED EFFICACY

Serum leuprolide levels in dogs after administering ATRIGEL[®] - 6% w/w drug and LUPRON[®] formulations

(57) Abstract: A flowable composition for use as a controlled release implant, comprising a biodegradable thermoplastic polyester that is at least substantially insoluble in aqueous medium or body fluid, a biocompatible polar aprotic solvent, miscible to dispersible in aqueous medium or body fluid and leuprolide acetate, an implant or a kit comprising such composition, a method for forming the flowable composition. The present invention is also directed to a biodegradable implant formed in situ, in a patient, to a method of forming a biodegradable implant in situ, in a living patient which includes injecting a flowable composition within the body of a patient and allowing the biocompatible polar aprotic solvent to dissipate to produce a solid biodegradable implant and a method of treating cancer in a patient by administering to the patient in need of such treatment an effective amount of a flowable composition of the present invention or a method of reducing LHRH levels in a patient.



WO 02/30393 A3

WO 02/30393 A3



(88) Date of publication of the international search report:
27 June 2002

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

**POLYMERIC DELIVERY FORMULATIONS OF LEUPROLIDE
WITH IMPROVED EFFICACY**

Background of the Invention

Leuprolide acetate is an LHRH agonist analog that is useful in the
5 palliative treatment of hormonal related prostate cancer, mammary cancer,
endometriosis, and precocious puberty. With continued use, leuprolide acetate
causes pituitary desensitizing and down-regulation to affect the pituitary-gonadal
axis, leading to suppressed circulating levels of luteinizing and sex hormones. In
patients with advanced prostate cancer, achieving circulating testosterone levels
10 of less than or equal to 0.5 ng/ml (chemical castration level) is a desired
pharmacological indicator of therapeutic action.

Originally, leuprolide acetate was launched in the United States
as a daily subcutaneous (s.c.) injection of the analog solution. The
inconvenience of chronic repetitive injections was later eliminated by the
15 development of a one month sustained release depot product based on poly(DL-
lactide-co-glycolide) microspheres (Lupron® Depot). Currently, one, three, and
four month formulations are widely available as intramuscular (i.m.) injections
of microspheres.

Although the current Lupron® Depot microspheres appear to be
20 effective, the microsphere products are difficult to manufacture, and they all
require a deep intramuscular (i.m.) injection using large volumes of fluid to
ensure that all of the microspheres are properly administered to the patient.
These injections are often painful and lead to tissue damage.

Biodegradable polymers other than Lupron® Depot have been
25 employed in many medical applications, including drug delivery devices. The
drug is generally incorporated into the polymeric composition and formed into
the desired shape outside the body. This solid implant is then typically inserted
into the body of a human, animal, bird, and the like through an incision.
Alternatively, small discrete particles composed of these polymers can be
30 injected into the body by a syringe. Preferably, however, certain of these
polymers can be injected via syringe as a liquid polymeric composition.

Liquid polymeric compositions useful for biodegradable controlled release drug delivery systems are described, e.g., in U.S. Pat. Nos. 4,938,763; 5,702,716; 5,744,153; 5,990,194; and 5,324,519. These compositions are administered to the body in a liquid state or, alternatively, as a solution, typically via syringe. Once in the body, the composition coagulates into a solid. One type of polymeric composition includes a nonreactive thermoplastic polymer or copolymer dissolved in a body fluid-dispersible solvent. This polymeric solution is placed into the body where the polymer congeals or precipitatively solidifies upon the dissipation or diffusion of the solvent into the surrounding body tissues. It is expected that these compositions would be as effective as Lupron® Depot, since leuprolide of these compositions is the same as are in the Lupron® Depot and the polymers are similar.

Surprisingly, however, it has been discovered that the liquid polymeric compositions according to the present invention are more effective in delivering leuprolide acetate than Lupron® Depot. Specifically, the testosterone levels obtained with the liquid polymeric compositions of the present invention containing the leuprolide acetate are lower at extended times in dogs compared to Lupron® Depot, and also at the six month point in humans, compared to the value reported in the literature for Lupron® Depot (Sharifi, R., *J. Urology*, Vol. 143, Jan., 68 (1990)).

Summary of the Invention

The present invention provides a flowable composition that is suitable for use as a controlled release implant of leuprolide acetate. The flowable composition includes a biodegradable thermoplastic polyester that is at least substantially insoluble in an aqueous medium or body fluid. The flowable composition also includes a biocompatible polar aprotic solvent. The biocompatible polar aprotic solvent can be an amide, an ester, a carbonate, a ketone, an ether, or a sulfonyl. The biocompatible polar aprotic solvent is miscible to dispersible in aqueous medium or body fluid. The flowable composition also includes leuprolide acetate. The leuprolide acetate is

preferably present in about 2 wt.% to about 4 wt.% of the composition or in about 4 wt.% to about 8 wt.% of the composition. Preferably, the flowable composition is formulated as an injectable subcutaneous delivery system. The injectable composition preferably has a volume of about 0.20 mL to about 5 0.40 mL or about 0.30 mL to about 0.50 mL. The injectable composition is preferably formulated for administration about once per month, about once per three months, or about once per four months to about once per six months. Preferably, the flowable composition is a liquid or a gel composition, suitable for injection into a patient.

10 Preferably, the biodegradable thermoplastic polyester is a polylactide, a polyglycolide, a polycaprolactone, a copolymer thereof, a terpolymer thereof, or any combination thereof. More preferably, the biodegradable thermoplastic polyester is a polylactide, a polyglycolide, a copolymer thereof, a terpolymer thereof, or a combination thereof. More 15 preferably, the suitable biodegradable thermoplastic polyester is 50/50 poly (DL-lactide-co-glycolide) having a carboxy terminal group or is 75/25 poly (DL-lactide-co-glycolide) with a carboxy terminal group that is protected. The suitable biodegradable thermoplastic polyester can be present in any suitable amount, provided the biodegradable thermoplastic polyester is at least 20 substantially insoluble in aqueous medium or body fluid. The suitable biodegradable thermoplastic polyester is preferably present in about 30 wt.% to about 40 wt.% of the flowable composition or is present in about 40 wt.% to about 50 wt.% of the flowable composition. Preferably, the biodegradable thermoplastic polyester has an average molecular weight of about 23,000 to 25 about 45,000 or about 15,000 to about 24,000.

 Preferably, the biocompatible polar aprotic solvent is N-methyl-2-pyrrolidone, 2-pyrrolidone, N, N-dimethylformamide, dimethyl sulfoxide, propylene carbonate, caprolactam, triacetin, or any combination thereof. More preferably, the biocompatible polar aprotic solvent is N-methyl-2-pyrrolidone. 30 Preferably, the polar aprotic solvent is present in about 60 wt.% to about 70

wt.% of the composition or is present in about 45 wt.% to about 55 wt.% of the composition.

The present invention also provides for a method for forming a flowable composition. The flowable composition is useful as a controlled
5 release implant. The method includes mixing, in any order, a biodegradable thermoplastic polyester, a biocompatible polar aprotic solvent, and leuprolide acetate. These ingredients, their properties, and preferred amounts are as disclosed above. The mixing is performed for a sufficient period of time effective to form the flowable composition for use as a controlled release
10 implant. Preferably, the biocompatible thermoplastic polyester and the biocompatible polar aprotic solvent are mixed together to form a mixture and the mixture is then combined with the leuprolide acetate to form the flowable composition.

The present invention also provides for a biodegradable implant
15 formed in situ, in a patient. The biodegradable implant product is prepared by the process of injecting a flowable composition within the body of the patient and allowing the biocompatible polar aprotic solvent to dissipate to produce a solid biodegradable implant. These ingredients, their properties, and preferred amounts are as disclosed above. Preferably, the patient is a human. The solid
20 implant preferably releases the effective amount of leuprolide as the solid implant biodegrades in the patient.

The present invention also provides for a method of forming a biodegradable implant in situ, in a living patient. The method includes injecting the flowable composition of the present invention within the body of a patient
25 and allowing the biocompatible polar aprotic solvent to dissipate to produce a solid biodegradable implant. The flowable composition includes an effective amount of a biodegradable thermoplastic polyester, an effective amount of a biocompatible polar aprotic solvent, and an effective amount of leuprolide acetate. These ingredients, their properties, and preferred amounts are as
30 disclosed above. Preferably, the solid biodegradable implant releases the

effective amount of leuprolide acetate by diffusion, erosion, or a combination of diffusion and erosion as the solid implant biodegrades in the patient.

The present invention also provides a method of treating or preventing cancer in a patient. The method includes administering to the patient
5 in need of such treatment or prevention an effective amount of a flowable composition of the present invention. Specifically, the cancer can be prostate cancer. In addition, the patient can be a human.

The present invention also provides a method of reducing LHRH levels in a patient. The method includes administering to the patient in need of
10 such LHRH reduction an effective amount of a flowable composition of the present invention. Specifically, the reduction of LHRH levels can be useful to treat endometriosis. In addition, the patient can be a human.

The present invention also provides a kit. The kit includes a first container and a second container. The first container includes a composition that
15 includes the biodegradable thermoplastic polyester and the biocompatible polar aprotic solvent. The second container includes leuprolide acetate. These ingredients, their properties, and preferred amounts are as disclosed above. Preferably, the first container is a syringe and the second container is a syringe. In addition, the leuprolide acetate is preferably lyophilized. The kit can
20 preferably include instructions. Preferably, the first container can be connected to the second container. More preferably, the first container and the second container are each configured to be directly connected to each other.

The present invention also provides a solid implant. The solid implant includes a biocompatible thermoplastic polyester and leuprolide acetate.
25 The biocompatible thermoplastic polyester is at least substantially insoluble in aqueous medium or body fluid. The solid implant has a solid or gelatinous microporous matrix, wherein the matrix is a core surrounded by a skin. The solid implant can further include a biocompatible organic solvent. The biocompatible organic solvent is preferably miscible to dispersible in aqueous or
30 body fluid. In addition, the biocompatible organic solvent preferably dissolves the thermoplastic polyester. The amount of biocompatible organic solvent, if

present, is preferably minor, such as from 0 wt.% to about 20 wt.% of the composition. In addition, the amount of biocompatible organic solvent preferably decreases over time. The core preferably contains pores of diameters from about 1 to about 1000 microns. The skin preferably contains pores of smaller diameters than those of the core pores. In addition, the skin pores are preferably of a size such that the skin is functionally non-porous in comparison with the core.

Brief Description of the Figures

- 10 Figure 1 illustrates serum leuprolide levels in dogs after administering ATRIGEL® - 6% w/w drug and Lupron® formulations.
- Figure 2 illustrates testosterone suppression in dogs with ATRIGEL® and Lupron® 90 day formulations.
- Figure 3 illustrates serum leuprolide levels after ATRIGEL® and
15 LUPRON® 90 day formulations administration in dogs (n=8), dosed at 22.5 mg LA.
- Figure 4 illustrates serum testosterone levels after ATRIGEL® and LUPRON® 90 day formulations administration in dogs (n=8), dosed at 22.5 mg LA.
- 20 Figure 5 illustrates serum testosterone levels in rats - 4 month formulations, 14,860 daltons vs. 26,234 daltons.

Detailed Description of the Invention

Specific and preferred biodegradable thermoplastic polyesters and
25 polar aprotic solvents; ranges of thermoplastic polyesters, polar aprotic solvents, leuprolide acetate, and flowable compositions; molecular weights of the thermoplastic polyester; and ranges of the solid implant described herein below are for illustration only; they do not exclude other biodegradable thermoplastic polyesters and polar aprotic solvents; ranges of thermoplastic polyesters, polar
30 aprotic solvents, leuprolide acetate, and flowable compositions; molecular weights of the thermoplastic polyester; and ranges of the solid implant.

The present invention provides a flowable composition suitable for use as a controlled release implant, a method for forming the flowable composition, a method for using the flowable composition, the biodegradable implant that is formed in situ from the flowable composition, a method of forming the biodegradable implant in situ, a method for using the biodegradable implant that is formed in situ, a kit that includes the flowable composition, and the solid implant. The flowable composition may be used to provide a biodegradable or bioerodible microporous in situ formed implant in animals. The flowable composition is composed of a biodegradable thermoplastic polymer or copolymer in combination with a suitable polar aprotic solvent. The biodegradable thermoplastic polyesters or copolymers are substantially insoluble in water and body fluid, biocompatible, and biodegradable and/or bioerodible within the body of an animal. The flowable composition is administered as a liquid or gel to tissue wherein the implant is formed in situ. The composition is biocompatible and the polymer matrix does not cause substantial tissue irritation or necrosis at the implant site. The implant can be used to deliver leuprolide acetate.

Preferably, the flowable composition can be a liquid or a gel, suitable for injection in a patient (e.g., human). As used herein, "flowable" refers to the ability of the composition to be injected through a medium (e.g., syringe) into the body of a patient. For example, the composition can be injected, with the use of a syringe, beneath the skin of a patient. The ability of the composition to be injected into a patient will typically depend upon the viscosity of the composition. The composition will therefore have a suitable viscosity, such that the composition can be forced through the medium (e.g., syringe) into the body of a patient. As used herein, a "liquid" is a substance that undergoes continuous deformation under a shearing stress. Concise Chemical and Technical Dictionary, 4th Enlarged Ed., Chemical Publishing Co., Inc., p. 707, NY, NY (1986). As used herein, a "gel" is a substance having a gelatinous, jelly-like, or colloidal properties. Concise Chemical and Technical Dictionary, 4th Enlarged Ed., Chemical Publishing Co., Inc., p. 567, NY, NY (1986).

Biodegradable Thermoplastic Polyester

A thermoplastic composition is provided in which a solid, biodegradable polyester and leuprolide acetate are dissolved in a biocompatible polar aprotic solvent to form a flowable composition, which can then be administered via a syringe and needle. Any suitable biodegradable thermoplastic polyester can be employed, provided the biodegradable thermoplastic polyester is at least substantially insoluble in aqueous medium or body fluid. Suitable biodegradable thermoplastic polyesters are disclosed, e.g., in U.S. Patent Nos. 5,324,519; 4,938,763; 5,702,716; 5,744,153; and 5,990,194; wherein the suitable biodegradable thermoplastic polyester is disclosed as a thermoplastic polymer. Examples of suitable biodegradable thermoplastic polyesters include polylactides, polyglycolides, polycaprolactones, copolymers thereof, terpolymers thereof, and any combinations thereof. Preferably, the suitable biodegradable thermoplastic polyester is a polylactide, a polyglycolide, a copolymer thereof, a terpolymer thereof, or a combination thereof.

The type, molecular weight, and amount of biodegradable thermoplastic polyester present in the composition will typically depend upon the desired properties of the controlled release implant. For example, the type, molecular weight, and amount of biodegradable thermoplastic polyester can influence the length of time in which the leuprolide acetate is released from the controlled release implant. Specifically, in one embodiment of the present invention, the composition can be used to formulate a one month delivery system of leuprolide acetate. In such an embodiment, the biodegradable thermoplastic polyester can preferably be 50/50 poly (DL-lactide-co-glycolide) having a carboxy terminal group; can be present in about 30 wt.% to about 40 wt.% of the composition; and can have an average molecular weight of about 23,000 to about 45,000. Alternatively, in another embodiment of the present invention, the composition can be used to formulate a three month delivery system of leuprolide acetate. In such an embodiment, the biodegradable thermoplastic polyester can preferably be 75/25 poly (DL-lactide-co-glycolide) without a carboxy terminal group; can be present in about 40 wt.% to about 50 wt.% of the

composition; and can have an average molecular weight of about 15,000 to about 24,000.

The carboxy terminal group of the 75/25 poly (DL-lactide-co-glycolide) can be protected with any suitable protecting group. Suitable carboxy protecting groups are known to those skilled in the art (See for example, T.W. Greene, Protecting Groups In Organic Synthesis; Wiley: New York, 1981, and references cited therein). Suitable exemplary carboxy protecting groups include (C₁-C₁₂)alkyl and (C₆-C₁₀)aryl (C₁-C₁₂)alkyl, wherein any alkyl or aryl can optionally be substituted with one or more (e.g., 1, 2, or 3) hydroxy. Preferred protecting groups include, e.g., methyl, dodecyl, and 1-hexanol.

Thermoplastic Polyester Molecular Weight

The molecular weight of the polymer used in the present invention can affect the rate of leuprolide acetate release as long as the flowable composition has been used as an intermediate. Under these conditions, as the molecular weight of the polymer increases, the rate of leuprolide acetate release from the system decreases. This phenomenon can be advantageously used in the formulation of systems for the controlled release of leuprolide acetate. For relatively quick release of leuprolide acetate, low molecular weight polymers can be chosen to provide the desired release rate. For release of a leuprolide acetate over a relatively long period of time, a higher polymer molecular weight can be chosen. Accordingly, a polymer system can be produced with an optimum polymer molecular weight range for the release of leuprolide acetate over a selected length of time.

The molecular weight of a polymer can be varied by any of a variety of methods. The choice of method is typically determined by the type of polymer composition. For example, if a thermoplastic polyester is used that is biodegradable by hydrolysis, the molecular weight can be varied by controlled hydrolysis, such as in a steam autoclave. Typically, the degree of polymerization can be controlled, for example, by varying the number and type of reactive groups and the reaction times.

Polar Aprotic Solvent

Any suitable polar aprotic solvent can be employed, provided the suitable polar aprotic solvent is miscible to dispersible in aqueous medium or body fluid. Suitable polar aprotic solvents are disclosed, e.g., in Aldrich
5 Handbook of Fine Chemicals and Laboratory Equipment, Milwaukee, WI (2000); U.S. Patent Nos. 5,324,519; 4,938,763; 5,702,716; 5,744,153; and 5,990,194. The suitable polar aprotic solvent should be able to diffuse into body fluid so that the flowable composition coagulates or solidifies. It is also preferred that the polar aprotic solvent for the biodegradable polymer be non-
10 toxic and otherwise biocompatible. The polar aprotic solvent is preferably biocompatible. Examples of suitable polar aprotic solvents include polar aprotic solvents having an amide group, an ester group, a carbonate group, a ketone, an ether, a sulfonyl group, or a combination thereof. Preferably, the polar aprotic solvent can be N-methyl-2-pyrrolidone, 2-pyrrolidone, N, N-dimethylformamide,
15 dimethyl sulfoxide, propylene carbonate, caprolactam, triacetin, or any combination thereof. More preferably, the polar aprotic solvent can be N-methyl-2-pyrrolidone.

The polar aprotic solvent can be present in any suitable amount, provided the polar aprotic solvent is miscible to dispersible in aqueous medium
20 or body fluid. The type and amount of biocompatible polar aprotic solvent present in the composition will typically depend upon the desired properties of the controlled release implant. For example, the type and amount of biocompatible polar aprotic solvent can influence the length of time in which the leuprolide acetate is released from the controlled release implant. Specifically,
25 in one embodiment of the present invention, the composition can be used to formulate a one month delivery system of leuprolide acetate. In such an embodiment, the biocompatible polar aprotic solvent can preferably be N-methyl-2-pyrrolidone and can preferably present in about 60 wt.% to about 70 wt.% of the composition. Alternatively, in another embodiment of the
30 present invention, the composition can be used to formulate a three month delivery system of leuprolide acetate. In such an embodiment, the biocompatible

polar aprotic solvent can preferably be N-methyl-2-pyrrolidone and can preferably present in about 50 wt.% to about 60 wt.% of the composition.

The solubility of the biodegradable thermoplastic polyesters in the various polar aprotic solvents will differ depending upon their crystallinity, their hydrophilicity, hydrogen-bonding, and molecular weight. Thus, not all of the biodegradable thermoplastic polyesters will be soluble in the same polar aprotic solvent, but each biodegradable thermoplastic polymer or copolymer should have its appropriate polar aprotic solvent. Lower molecular-weight polymers will normally dissolve more readily in the solvents than high-molecular-weight polymers. As a result, the concentration of a polymer dissolved in the various solvent will differ depending upon type of polymer and its molecular weight. Conversely, the higher molecular-weight polymers will normally tend to coagulate or solidify faster than the very low-molecular-weight polymers. Moreover the higher molecular-weight polymers will tend to give higher solution viscosities than the low-molecular-weight materials.

For example, low-molecular-weight polylactic acid formed by the condensation of lactic acid will dissolve in N-methyl-2-pyrrolidone(NMP) to give a 73% by weight solution which still flows easily through a 23-gauge syringe needle, whereas a higher molecular-weight poly(DL-lactide) (DL-PLA) formed by the additional polymerization of DL-lactide gives the same solution viscosity when dissolved in NMP at only 50% by weight. The higher molecular-weight polymer solution coagulates immediately when placed into water. The low-molecular-weight polymer solution, although more concentrated, tends to coagulate very slowly when placed into water.

It has also been found that solutions containing very high concentrations of high-molecular-weight polymers sometimes coagulate or solidify slower than more dilute solutions. It is suspected that the high concentration of polymer impedes the diffusion of solvent from within the polymer matrix and consequently prevents the permeation of water into the matrix where it can precipitate the polymer chains. Thus, there is an optimum

concentration at which the solvent can diffuse out of the polymer solution and water penetrates within to coagulate the polymer.

The leuprolide acetate is preferably lyophilized prior to use. Typically, the leuprolide acetate can be dissolved in an aqueous solution, sterile
5 filtered, and lyophilized in a syringe. The polymer/solvent solution can be filled into another syringe. The two syringes can then be coupled together and the contents can be drawn back and forth between the two syringes until the polymer/solvent solution and the leuprolide acetate are effectively mixed together, forming a flowable composition. The flowable composition can be
10 drawn into one syringe. The two syringes can then be disconnected. A needle can be inserted onto the syringe containing the flowable composition. The flowable composition can then be injected through the needle into the body. The flowable composition can be formulated and administered to a patient as described in, e.g., U.S. Patent Nos. 5,324,519; 4,938,763; 5,702,716; 5,744,153;
15 and 5,990,194; or as described herein. Once in place, the solvent dissipates, the remaining polymer solidifies, and a solid structure is formed. The solvent will dissipate and the polymer will solidify and entrap or encase the leuprolide acetate within the solid matrix.

The release of leuprolide acetate from these solid implants will
20 follow the same general rules for release of a drug from a monolithic polymeric device. The release of leuprolide acetate can be affected by the size and shape of the implant, the loading of leuprolide acetate within the implant, the permeability factors involving the leuprolide acetate and the particular polymer, and the degradation of the polymer. Depending upon the amount of leuprolide acetate
25 selected for delivery, the above parameters can be adjusted by one skilled in the art of drug delivery to give the desired rate and duration of release.

The amount of leuprolide acetate incorporated into the flowable, in-situ, solid forming implant depends upon the desired release profile, the concentration of leuprolide acetate required for a biological effect, and the length
30 of time that the leuprolide acetate has to be released for treatment. There is no critical upper limit on the amount of leuprolide acetate incorporated into the

polymer solution except for that of an acceptable solution or dispersion viscosity for injection through a syringe needle. The lower limit of leuprolide acetate incorporated into the delivery system is dependent simply upon the activity of the leuprolide acetate and the length of time needed for treatment. Specifically, 5 in one embodiment of the present invention, the composition can be used to formulate a one month delivery system of leuprolide acetate. In such an embodiment, the leuprolide acetate can preferably be present in about 2 wt.% to about 4 wt.% of the composition. Alternatively, in another embodiment of the present invention, the composition can be used to formulate a three month 10 delivery system of leuprolide acetate. In such an embodiment, the leuprolide acetate can preferably be present in about 4 wt.% to about 8 wt.% of the composition. The solid implant formed from the flowable system will release the leuprolide acetate contained within its matrix at a controlled rate until the leuprolide acetate is effectively depleted.

15

Dosages

The amount of flowable composition administered will typically depend upon the desired properties of the controlled release implant. For example, the amount of flowable composition can influence the length of time in 20 which the leuprolide acetate is released from the controlled release implant. Specifically, in one embodiment of the present invention, the composition can be used to formulate a one month delivery system of leuprolide acetate. In such an embodiment, about 0.20 mL to about 0.40 mL of the flowable composition can be administered. Alternatively, in another embodiment of the present invention, 25 the composition can be used to formulate a three month delivery system of leuprolide acetate. In such an embodiment, about 0.30 mL to about 0.50 mL of the flowable composition can be administered.

Surprisingly, it has been discovered that the liquid polymeric compositions according to the present invention are more effective in delivering 30 leuprolide acetate than Lupron® Depot. Specifically, as shown in the Examples below, the testosterone levels obtained with the liquid polymeric compositions of

the present invention containing the leuprolide acetate are lower at extended times in dogs compared to Lupron® Depot, and also at the six month point in humans, compared to the value reported in the literature for Lupron® Depot (Sharifi, R., *J. Urology*, Vol. 143, Jan., 68 (1990)).

5 All publications, patents, and patent documents are incorporated by reference herein, as though individually incorporated by reference. The invention will now be illustrated with the following non-limiting examples.

Examples

10

Example 1

Poly(DL-lactide-co-glycolide) having a 50/50 ratio of lactide to glycolide and a terminal carboxyl group (RG 504H from Boehringer Ingelheim) was dissolved in N-methyl-2-pyrrolidone (NMP) to give a 34% by weight
15 polymer solution. This ATRIGEL® polymer solution was filled into 1.25 cc polypropylene syringes with a female luer lock fitting at a volume of 330 mL and terminally sterilized by exposure to gamma irradiation at 20 kilograys. The molecular weight of the polymer after gamma irradiation was 32,000 daltons. Leuprolide acetate was dissolved in water, sterile filtered through a 0.2 mm
20 filter, and filled into a 1.00 cc polypropylene syringe with a male luer-lock fitting. The aqueous solution was frozen and the water removed under vacuum to give a 10.2 mg lyophilized cake of the peptide. The two syringes were coupled just prior to use and the contents mixed back and forth between the two syringes for 30 cycles. The formulation was drawn back into the syringe with
25 the male coupling, the two syringes separated, and a one-half inch 20 gauge needle was attached. The contents of the syringe were then injected subcutaneously into 7 male beagle dogs to give a total of 250 mg of polymer formulation containing 7.5 mg of leuprolide acetate. Lupron® Depot microspheres with 7.5 mg of leuprolide acetate were injected intramuscularly
30 into a second set of 7 beagle dogs. Serum samples were collected from all of the dogs at baseline and days 1, 3, 7, 14, 21, 28, 35, 42, 49, 55, 63, 77, and 91.

The serum samples were analyzed for testosterone using an RIA method. The results given in Table 1 show that both products are effective in lowering the testosterone concentrations below the human castrate level of 0.5 ng/mL after about 14 days, and maintaining this effect out to day 42. Overall, it appeared that the testosterone levels obtained with the Lupron® Depot were slightly lower than those observed with the ATRIGEL® polymer system.

Table 1. Serum Testosterone Data in Dogs

	<u>Time, Days</u>	<u>Testosterone Levels, ng/mL</u>	
		<u>ATRIGEL®</u>	<u>Lupron®</u>
10	1	2.23	3.52
	3	5.50	4.85
	7	0.47	1.05
	14	0.60	0.39
15	21	0.36	0.07
	28	0.24	0.08
	35	0.15	0.07
	42	0.51	0.31
	49	2.09	0.30
20	55	2.85	1.08
	63	4.95	0.77
	77	4.82	1.22
	91	2.23	2.84

25

Example 2

The same polymer solution as described in Example 1 was sterile filtered through a 0.2 mm filter to give a polymer formulation with a molecular weight of 48,000 daltons. The sterile polymer solution was then filled aseptically into the female polypropylene syringes. Also, the same bulk polymer solution before sterile filtration was divided into four different samples, filled into polypropylene syringes and exposed to gamma irradiation at four irradiation levels to degrade the polymer to different molecular weights. The polymer after

irradiation at the different dosage levels had molecular weights of 33,500, 26,500, 23,000, and 20,000 daltons. All five formulations were combined with leuprolide acetate as described above and injected subcutaneously into male beagle dogs. Determination of serum testosterone over a 45-day period showed
5 that all of the formulations were effective in reducing the testosterone concentrations below castrate levels except for the formulation with the lowest molecular weight of 20,000 daltons. Thus, the ATRIGEL® polymer formulation containing leuprolide acetate is effective in reducing testosterone for 1 month over a wide range of polymer molecular weights ranging from 23,000 to 45,000
10 daltons.

Example 3

The polymer formulation described in Example 1 after gamma irradiation at 20 kilograys was combined with leuprolide acetate and injected
15 subcutaneously into 8 male beagle dogs. Lupron® Depot containing 7.5 mg of leuprolide acetate was injected intramuscularly into 8 male beagle dogs. Samples of serum were collected at baseline and days 1, 2, 3, 7, 14, 22, 28, 30, 32, 34, and 36. The serum samples were analyzed for serum testosterone and serum leuprolide by RIA. The values for the serum testosterone concentrations
20 given in Table 2 show that both products were effective in dogs in reducing the testosterone to below human castrate levels with the Lupron® Depot product appearing to be slightly more effective at the later time points. It was thought that the reason for this difference was the higher serum leuprolide levels for the Lupron® Depot product at the intermediate time points as shown in Table 3.
25 Based upon this data, it was anticipated that the ATRIGEL® product with leuprolide would be effective, but perhaps not as efficacious as the Lupron® Depot product.

Table 2. Serum Testosterone Data in Dogs

	<u>Time, Days</u>	<u>Testosterone Levels, ng/mL</u>	
		<u>ATRIGEL[®]</u>	<u>Lupron[®]</u>
5	1	4.56	5.09
	2	5.81	6.19
	3	6.69	4.99
	7	0.55	1.90
	14	0.66	0.24
	22	0.96	0.15
10	28	0.49	0.11
	30	1.01	0.17
	32	0.90	0.25
	34	1.53	0.35
	36	0.98	0.27
15			

Table 3. Serum Leuprolide Data in Dogs

	<u>Time, Days</u>	<u>Serum Leuprolide Levels, ng/mL</u>	
		<u>ATRIGEL[®]</u>	<u>Lupron[®]</u>
20	1	3.98	1.94
	2	2.34	1.41
	3	0.81	0.93
	7	1.01	1.55
	14	0.29	1.99
25	22	0.58	2.11
	28	0.47	0.70
	30	0.68	0.49
	32	0.51	0.31
	34	0.41	0.53
30	36	0.25	0.18

Example 4

The polymer formulation described in Example 1 was prepared under GMP conditions, loaded into syringes, and irradiated at 20 kilograys. The

sterile polymer solution was then combined with leuprolide acetate which had been sterile filtered into another syringe. The two syringes were coupled, the contents mixed together for 30 cycles, and the contents injected subcutaneously into prostate cancer patients who had been orchiectomized. Samples of serum
 5 were collected over 28 days and analyzed for leuprolide concentration using a validated RIA method. The data given in Table 4 show an initial burst of drug followed by fairly constant levels over 28 days. When these data are compared to those for Lupron® Depot published in the literature, the values are quite similar, and it is expected that both products will provide the same efficacy in
 10 prostate cancer patients.

Table 4. Serum Leuprolide Data in Humans

15	<u>Time, Days</u>	<u>Serum Leuprolide Levels, ng/mL</u>	
		<u>ATRIGEL®</u>	<u>Lupron®¹</u>
	0.167	25.26	20
	14	0.28	—
	17	—	0.8
	21	0.37	—
20	28	0.42	0.36

¹ Sharifi

Example 5

25 The ATRIGEL® leuprolide product described in Example 4 was injected subcutaneously (s.c.) into prostate cancer patients in a pivotal clinical trial. Every 28 days, the patients were given another injection of the product until 6 injections had been received. Samples of serum were collected at various times and analyzed for testosterone concentration by a validated RIA method.
 30 The values given in Table 5 show that the serum testosterone concentrations reached castrate values of 50 ng/dL (0.5 ng/mL) at 21 days. The testosterone

concentrations then declined to 7.77 ng/dL at day 56 and remained at this level throughout the remainder of the study. A comparison of the testosterone concentrations to the published values obtained with Lupron® Depot as given in Table 5 shows the ATRIGEL® leuprolide product to be more effective as it produces a lower testosterone level in humans.

Table 5. Serum Testosterone Data in Humans

		Serum Testosterone Levels, ng/dL	
	Time, Days	ATRIGEL® ¹	Lupron® ²
10	0	397.8	370.6
	4	523.0	552.7
	21	49.37	33.8
	28	23.02	17.0
	56	7.77	≤15.0
15	84	7.77	≤15.0
	112	6.93	≤15.0
	140	7.41	≤15.0
	168	7.58	≤15.0

¹ = 36 patients
² = 56 patients (Sharifi)

Example 6

Poly(DL-lactide-co-glycolide) with a molar ratio of lactide to glycolide of 75/25 (Birmingham Polymer, Inc.) was dissolved in NMP to give a solution with 45% by weight polymer. This solution was filled into 3.0 cc polypropylene syringes with a male luer lock fitting and terminally sterilized by exposure to gamma irradiation at 23.2-24.6 kilograys. The polymer molecular weight after irradiation was 15,094 daltons. Leuprolide acetate was dissolved in water, sterile filtered through a 0.2 mm filter and filled into a polypropylene syringe with a male luer lock fitting. The aqueous solution was frozen and the water removed by vacuum to yield a lyophilized cake of leuprolide. The two syringes were connected together with a coupler immediately prior to use and the

contents of the two syringes mixed by moving the material back and forth between the two syringes for 40 cycles to provide a formulation with 6% by weight of leuprolide acetate. The product was then pulled into the syringe with the male luer lock fitting and a one-half inch 20 gauge needle attached.

5 The formulation containing the leuprolide acetate was then injected subcutaneously into 5 male beagle dogs at a target dose of 25.6 mg/kg/day. The commercially available 3-month Lupron® Depot microspheres were injected intramuscularly into 5 male beagle dogs at the same target dosage. The actual dosages were 31.4 mg/kg/day for the ATRIGEL®
10 formulation with leuprolide and 25.3 mg/kg/day for the Lupron® Depot product. At baseline and on days 1,2, 3, 4, 7, 14, 21, 28, 35, 49, 63, 71, 81, 91, 105, 120, 134, and 150, serum was collected from each of the dogs and analyzed for testosterone by RIA and for leuprolide concentration by LC/MS/MS.

 The data showed that the serum leuprolide levels were actually
15 higher for the ATRIGEL® formulation compared to the Lupron® Depot product over the first 30 days, but then declined to the same levels as the Lupron® Depot product over the next 120 days (Figure 1). However, the testosterone levels were comparable for the two product during the 70 days, but then the Lupron® Depot
20 product failed to maintain human castration levels of testosterone. This result was surprising based upon the comparable leuprolide levels of the two products over the later time points.

Example 7

 The same polymer formulation as described in Example 6 was
25 prepared and filled into 1.25 cc polypropylene syringes with a female luer lock fitting at a volume of 440 mL. The product was terminally sterilized by exposure to gamma irradiation at 23-25 kilograys. The molecular weight of the polymer after irradiation was 14,800 daltons. Leuprolide acetate was dissolved in water, sterile filtered using a 0.2 mm filter, and filled into a 1.00 cc
30 polypropylene syringe with a male luer lock fitting. The aqueous solution was frozen and the water removed by vacuum to give a 28.2 mg lyophilized cake of

leuprolide acetate. Immediately before use, the two syringes were coupled together and the contents mixed by moving the materials back and forth between the two syringes for 40 cycles to provide a homogeneous mixture with 6% by weight leuprolide acetate. The formulation was then pulled into the syringe with the male luer lock fitting, the syringes disconnected, and a one-half inch 20 gauge needle attached.

The formulation was injected subcutaneously into 8 male beagle dogs to give a total delivered dose of 22.5 mg of leuprolide acetate. The commercially available 3-month Lupron® Depot microspheres were injected intramuscularly into 8 male beagle dogs. At 6 and 12 hours, and on days 1, 2, 3, 7, 14, 21, 28, 35, 49, 64, 77, and 91 serum samples were collected for analysis of testosterone and leuprolide concentrations. On day 91, the animals were injected again with the formulations and serum collected at 6 and 12 hours on day 91 and again on days 92, 93, 94, 99, and 105. The mean serum leuprolide concentrations were much higher for the Lupron® Depot product than the ATRIGEL® formulation at the extended time points as shown in Table 6 and Figure 3. However, the testosterone concentrations were actually lower for the ATRIGEL® formulation as shown in Table 7 and Figure 4.

Table 6. Mean (SD) Serum Leuprolide Levels (ng/ml) in Dogs (n = 8) after ATRIGEL® and LUPRON® 3-Month Administration

	<u>Time, day</u>	<u>Mean, LA (ATRIGEL)</u>	<u>Mean, LA (Lupron)</u>
	0	0.1	0.1
	0.25	221.38	21.5
25	0.5	54.13	5.99
	1	24.29	4.43
	2	9.01	3.43
	3	6.23	1.61
	7	1.25	1.08
30	14	0.99	1.16
	21	0.35	4.16
	28	0.31	1.24

	<u>Time, day</u>	<u>Mean, LA (ATRIGEL)</u>	<u>Mean, LA (Lupron)</u>
	35	0.27	1.73
	49	0.45	1.04
	64	0.34	1.78
	77	0.29	1.59
5	91	0.17	0.78
	91.25	254.88	25.15
	91.5	84.74	6.85
	92	17.61	4.63
	93	7.32	4.36
10	94	5.27	4.11
	99	2.04	2.48
	105	0.85	1.35

Table 7. Mean (SD) Serum Testosterone Levels (ng/ml) in Dogs (n = 8)
after ATRIGEL[®] and LUPRON[®] 3- Month Administration

	<u>Time, day</u>	<u>Baseline, T</u>	<u>Mean T (ATRIGEL)</u>	<u>Mean T (Lupron)</u>
	0	2.29	1.42	3.38
5	0.25	2.29	3.45	5.25
	0.5	2.29	2.92	5.67
	1	2.29	2.99	6.35
	2	2.29	4.14	5.74
	3	2.29	3.98	6.92
10	7	2.29	1.51	3.46
	14	2.29	0.17	0.95
	21	2.29	0.06	1.38
	28	2.29	0.14	1.13
	35	2.29	0.29	1.11
15	49	2.29	0.2	0.07
	64	2.29	0.05	0.07
	77	2.29	0.05	0.08
	91	2.29	0.06	0.34
	91.25	2.29	0.06	0.22
20	91.5	2.29	0.05	0.22
	92	2.29	0.05	0.14
	93	2.29	0.09	0.22
	94	2.29	0.07	0.22
	99	2.29	0.06	0.08
25	105	2.29	0.05	0.08

Example 8

Three polymer formulations containing 45% by weight of 75/25
30 poly(DL-lactide-co-glycolide) having different molecular weights were prepared and filled into 1.25 cc polypropylene syringes with female luer lock fittings at a volume of 440 mL. The syringes were terminally sterilized by exposure to gamma irradiation at 23-25 kilograys. The molecular weights of the three polymers after irradiation were 11,901, 13,308, and 21,268. These polymer

solutions were combined with lyophilized leuprolide acetate in another syringe and injected subcutaneously in dogs at a dosage of 22.5 mg as described in Example 7. Serum samples were collected at baseline and days 1, 7, 14, 21, 28, 35, 42, 56, 70, 84, 98, 112, and 126. The serum was analyzed for testosterone concentration by RIA. The data showed that the two lower molecular weight polymer formulations failed to suppress the testosterone concentrations below castrate for the full 90 days whereas the polymer with the molecular weight of 21,268 was effective over the 3 months evaluated.

10 Example 9

Two polymer formulations containing 45% by weight 75/25 poly(DL-lactide-co-glycolide) having different molecular weights were prepared and filled into 1.25 cc polypropylene syringes. The syringes were terminally sterilized by exposure to gamma irradiation at 24-27 kilograys. The molecular weights of the two polymers after irradiation were 14,864 and 26,234 daltons. These polymer solutions were combined with lyophilized leuprolide acetate in another 1.25 cc polypropylene syringe and mixed back and forth for 40 cycles to produce a homogenous mixture with leuprolide acetate at 6% by weight. The contents were then pulled into one syringe, the syringes disconnected, and a one-half inch 20 gauge needle attached. The formulation with leuprolide acetate was then injected subcutaneously into 5 rats per group at a dosage of 100 mg/kg/day (12 mg/kg). At baseline and on days 3, 7, 14, 21, 35, 49, 63, 70, 80, 91, 105, 120, and 132 serum samples were collected from all of the animals and analyzed for testosterone concentration using an RIA method. The data shown in Figure 5 indicate that both polymer molecular weight formulations were effective in suppressing testosterone below the human castrate level for 132 days.

CLAIMS

What is claimed is:

1. A flowable composition suitable for use as a controlled release implant, the composition comprising:
 - (a) a biodegradable thermoplastic polyester that is at least substantially insoluble in aqueous medium or body fluid;
 - (b) a biocompatible polar aprotic solvent selected from the group consisting of an amide, an ester, a carbonate, a ketone, an ether, and a sulfonyl; wherein the biocompatible polar aprotic solvent is miscible to dispersible in aqueous medium or body fluid; and
 - (c) leuprolide acetate.
2. The composition of claim 1 wherein the biodegradable thermoplastic polyester is a polylactide, a polyglycolide, a polycaprolactone, a copolymer thereof, a terpolymer thereof, or any combination thereof.
3. The composition of claim 1 wherein the biodegradable thermoplastic polyester is a polylactide, a polyglycolide, a copolymer thereof, a terpolymer thereof, or a combination thereof.
4. The composition of claim 1 wherein the biodegradable thermoplastic polyester is 50/50 poly (DL-lactide-co-glycolide) having a carboxy terminal group.
5. The composition of claim 1 wherein the biodegradable thermoplastic polyester is 75/25 poly (DL-lactide-co-glycolide) without a carboxy terminal group.

6. The composition of claim 1 wherein the biodegradable thermoplastic polyester is present in about 30 wt.% to about 40 wt.% or about 40 wt.% to about 50 wt.% of the composition.

7. The composition of claim 1 wherein the biodegradable thermoplastic polyester has an average molecular weight of about 23,000 to about 45,000 or about 15,000 to about 24,000.

8. The composition of claim 1 wherein the biocompatible polar aprotic solvent is N-methyl-2-pyrrolidone, 2-pyrrolidone, N, N-dimethylformamide, dimethyl sulfoxide, propylene carbonate, caprolactam, triacetin, or any combination thereof.

9. The composition of claim 1 wherein the biocompatible polar aprotic solvent is N-methyl-2-pyrrolidone.

10. The composition of claim 1 wherein the biocompatible polar aprotic solvent is present in about 60 wt.% to about 70 wt.% of the composition.

11. The composition of claim 1 wherein the biocompatible polar aprotic solvent is present in about 50 wt.% to about 60 wt.% of the composition.

12. The composition of claim 1 wherein the leuprolide acetate is present in about 2 wt.% to about 4 wt.% of the composition.

13. The composition of claim 1 wherein the leuprolide acetate is present in about 4 wt.% to about 8 wt.% of the composition.

14. The composition of claim 1 that is formulated as an injectable subcutaneous delivery system.

15. The composition of claim 14 having a volume of about 0.20 mL to about 0.40 mL.
16. The composition of claim 14 having a volume of about 0.30 mL to about 0.50 mL.
17. The composition of claim 14 that is formulated for administration about once per month.
18. The composition of claim 14 that is formulated for administration about once per three months.
19. The composition of claim 14 that is formulated for administration about once per four months to about once per six months.
20. A method for forming a flowable composition for use as a controlled release implant, comprising the step of mixing, in any order:
- (a) a biodegradable thermoplastic polyester that is at least substantially insoluble in aqueous medium or body fluid;
 - (b) a biocompatible polar aprotic solvent selected from the group consisting of an amide, an ester, a carbonate, a ketone, an ether, and a sulfonyl; wherein the biocompatible polar aprotic solvent is miscible to dispersible in aqueous medium or body fluid; and
 - (c) leuprolide acetate.
- wherein the mixing is performed for a sufficient period of time effective to form the flowable composition for use as a controlled release implant.
21. The method of claim 20 wherein the biocompatible thermoplastic polyester and the biocompatible polar aprotic solvent are mixed together to form a mixture and the mixture is then mixed with the leuprolide acetate to form the flowable composition.

22. Use of a biodegradable thermoplastic polyester, biocompatible polar, aprotic solvent and leuprolide in the manufacture of a composition that is capable of forming a biodegradable implant in situ, in a patient when injected and allowed to produce a solid biodegradable implant wherein the composition comprises an effective amount of a biodegradable thermoplastic polyester that is at least substantially insoluble in aqueous medium or body fluid; an effective amount of a biocompatible polar aprotic solvent selected from the group consisting of an amide, an ester, a carbonate, a ketone, an ether, and a sulfonyl and the biocompatible polar aprotic solvent is miscible to dispersible in aqueous medium or body fluid; and an effective amount of leuprolide acetate.
23. The use according to claim 22 wherein the patient is a human.
24. The use according to claim 22 wherein the solid implant releases the effective amount of leuprolide as the solid implant biodegrades in the patient.
25. The use according to claim 22 wherein the solid biodegradable implant adheres to tissue within the body of the patient.
26. The use according to claim 22 wherein the solid biodegradable implant releases the effective amount of leuprolide acetate by diffusion, erosion, or a combination of diffusion and erosion as the solid implant biodegrades in the patient.
27. The use according to claim 22 wherein the patient has cancer and the composition is useful in the treatment of cancer.
28. The use according to claim 27 wherein the cancer is prostate cancer.
29. The use according to claim 28 wherein the patient is a human.

30. The use according to claim 22 wherein the implant is capable of reducing LHRH levels in a patient through the presence of an effective amount of the composition.

31. The use according to claim 30 wherein the reduction of LHRH levels is useful to treat endometriosis.

32. A kit comprising:

(a) a first container comprising a composition comprising a biodegradable thermoplastic polyester that is at least substantially insoluble in aqueous medium or body fluid and a biocompatible polar aprotic solvent selected from the group consisting of an amide, an ester, a carbonate, a ketone, an ether, and a sulfonyl; wherein the biocompatible polar aprotic solvent is miscible to dispersible in aqueous medium or body fluid; and

(b) a second container comprising leuprolide acetate.

33. The kit of claim 32 wherein the first container is a syringe.

34. The kit of claim 32 wherein the second container is a syringe.

35. The kit of claim 32 wherein the leuprolide acetate is lyophilized.

36. The kit of claim 32 further comprising instructions.

37. The kit of claim 32 wherein the first container can be connected to the second container.

38. The kit of claim 32 wherein the first container and the second container are each configured to be directly connected to each other.

39. **A solid implant comprising:**
- (a) **a biocompatible thermoplastic polyester that is at least substantially insoluble in aqueous medium or body fluid; and**
 - (b) **leuprolide acetate; wherein**
the solid implant has a solid or gelatinous microporous matrix, the matrix being a core surrounded by a skin.
40. **The solid implant of claim 39 further comprising a biocompatible organic solvent that is miscible to dispersible in aqueous or body fluid and dissolves the thermoplastic polyester.**
41. **The solid implant of claim 40 wherein the amount of biocompatible organic solvent is minimal.**
42. **The solid implant of claim 39 wherein the amount of biocompatible organic solvent decreases over time.**
43. **The solid implant of claim 39 wherein the core contains pores of diameters from about 1 to about 1000 microns.**
44. **The solid implant of claim 39 wherein the skin contains pores of smaller diameters than those of the core pores.**
45. **The solid implant of claim 39 wherein the skin pores are of a size such that the skin is functionally non-porous in comparison with the core.**

42. The solid implant of claim 41 wherein the amount of biocompatible organic solvent is minimal.
43. The solid implant of claim 41 wherein the amount of
5 biocompatible organic solvent decreases over time.
44. The solid implant of claim 40 wherein the core contains pores of diameters from about 1 to about 1000 microns.
- 10 45. The solid implant of claim 40 wherein the skin contains pores of smaller diameters than those of the core pores.
46. The solid implant of claim 40 wherein the skin pores are of a size such that the skin is functionally non-porous in comparison with the core.
15

Figure 1. Serum leuprolide levels in dogs after administering ATRIGEL® -- 6% w/w drug and LUPRON® formulations




Figure 2: Testosterone Suppression in Dogs w/ ATRIGEL and Lupron 90-Day Formulations




FIGURE 3: Serum Leuprolide Levels after ATRIGEL and LUPRON 90-Day Formulations Administration in Dogs (n=8), Dosed at 22.5 mg LA




FIGURE 4: Serum Testosterone Levels after ATRIGEL and LUPRON 90-day Formulations Administration in Dogs (n=8), Dosed at 22.5 mg LA





Figure 5.
Serum Testosterone Levels in Rats - 4 Month Formulations
14,860 Daltons vs. 26,234 Daltons



Serum leuprolide levels in dogs after administering ATRIGEL[®] - 6% w/w drug and LUPRON[®] formulations

