



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C04B 14/10, 33/04	A1	(11) International Publication Number: WO 95/09135 (43) International Publication Date: 6 April 1995 (06.04.95)
(21) International Application Number: PCT/US94/10770 (22) International Filing Date: 23 September 1994 (23.09.94) (30) Priority Data: 08/129,416 30 September 1993 (30.09.93) US (60) Parent Application or Grant (63) Related by Continuation US 08/129,416 (CIP) Filed on 30 September 1993 (30.09.93) (71) Applicant (for all designated States except US): VININGS INDUSTRIES, INC. [US/US]; 3950 Cumberland Parkway, Atlanta, GA 30339-4501 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): PAYTON, James [US/US]; 3571 Downing Street, Marietta, GA 30066 (US). CANARIS, Nicholas [US/US]; 2607 Paces Ridge, N.W., Atlanta, GA 30339 (US). MIRANDA, Jorge [CA/US]; 4030 Addie Lane, Marietta, GA 30068 (US).		(74) Agent: KLAUBER, Stefan, J.; Klauber & Jackson, Continental Plaza, 4th floor, 411 Hackensack Avenue, Hackensack, NJ 07601 (US). (81) Designated States: AU, BR, CA, FI, JP, NO, NZ, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: STABILIZED, HIGH SOLIDS, LOW VISCOSITY SMECTITE SLURRIES, AND METHOD OF PREPARATION		
(57) Abstract <p>An aqueous slurry of smectite clay of elevated solids content, comprising an aqueous solution or emulsion of at least 0.2 % by weight of said slurry of a salt of a low molecular weight amine salt, in which is dispersed from about 10 to 47 % by weight of the slurry, of a smectite clay. The amine salt is effective to prevent the smectite from swelling appreciably, whereby the slurry can be shipped and stored without creating a gelling problem. The inhibiting or suppressing effect of the amine salt on the swelling of the clay and on gelling of the slurry is reversible upon subsequent dilution with water, thereby facilitating use of the smectite in typical applications, e.g. as a retention aid in paper making, or as a viscosifier.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

STABILIZED, HIGH SOLIDS, LOW VISCOSITY SMECTITE SLURRIES,
AND METHOD OF PREPARATION

FIELD OF THE INVENTION

5

This invention relates generally to smectite clays, and more specifically relates to aqueous low viscosity smectite clay slurries of elevated solids content, and to a method for producing same which while suppressing swelling of the smectite in the high solids slurry, enables the normal viscosifying and other properties of a swelled smectite to be restored at the point of slurry use.

15

BACKGROUND OF THE INVENTION

Smectite clays are phyllosilicates of the 2:1 layered type. The smectite group includes inter alia the mineral sub-groups montmorillonite, beidellite, nontronite, saponite, hectorite and sauconite. Among the smectite clays to which the present invention is applicable are the naturally occurring Wyoming variety of swelling bentonite and similar clays, and hectorite, which is a swelling magnesium-lithium silicate. For use in the invention, these clays are preferably converted to the sodium form if they are not already in this form. This can be effected by a cation exchange reaction with a soluble sodium compound. These methods are well-known in the art.

30

Smectite-type clays prepared synthetically can also be used in the slurries of the invention. Representative of such clays are montmorillonite, bentonite, beidellite, hectorite, saponite and stevensite. Representative hydrothermal processes for preparing synthetic smectites are described in U.S. Patents Nos. 3,252,757 to Granguist; 3,586,478 to Neumann; 3,666,407 to Orlemann;

35

3,671,190 to Neumann; 3,844,978 and 3,844,979 to Hickson; and 3,852,405 and 3,855,147 to Granquist.

Smectite clays are commercially important minerals.

5 Appropriately processed, smectite clays are excellent viscosifiers, binders, film formers, fabric softeners and retention aid additives in paper making. These clays are platey-type materials having a micaceous structure. They are highly colloidal and readily swell in water to form
10 viscous, thixotropic gels which renders the clays useful as viscosity builders in many industries and applications including, for example, in foundry molding compositions, as suspension aids in agricultural sprays, and for thickening cosmetics. The high surface area generated by
15 swelling in water also makes these clays useful in fabric softening and in paper making applications. In the latter environment smectite clays are particularly useful as retention aids. In such use it is often of interest to intermix an aqueous slurry of the smectite clay with a
20 cellulosic suspension, and thereafter drain the cellulosic suspension.

Most smectite clays are sold as fine powders. As with most minerals, however, these powders are difficult and
25 expensive to handle. They also are subject to considerable "dusting", i.e. to evolution of dust during handling, so that they can in some cases cause environmental problems, and even health risks. To minimize these problems and to provide the user of the
30 mineral with a product which is more ready for the user's application, many minerals are sold or shipped by the manufacturer or distributor as high solids aqueous slurries. Such high solids slurries can be easily stored, shipped, transferred, e.g. pumped and metered, with
35 significantly less capital expenditure and many fewer problems than are associated with dry mineral powders.

In most applications, nevertheless, it is not economical or practical to ship smectite clays as aqueous slurries because of the large quantity of water normally required in such slurries. This problem arises because smectites
5 are indeed good viscosifiers, whereby it has not generally been possible to produce high solids aqueous slurries by the usual methods. In general, only about 8% - 10% solids slurries of good quality swelling smectite
10 can be produced in water, and at solids contents greater than about 10%, the viscosities of the slurries can become so high that they cannot readily be pumped by conventional equipment and gelling upon standing becomes a problem.

15 Thus, there is a need for aqueous slurries containing substantially greater than 10% by weight of smectite clay, which have viscosities low enough to allow pumping. At the same time the high solids slurry must retain the smectite in a form in which it can be readily activated,
20 i.e. to restore the normal properties associated with a swelled bentonite, such as the viscosifying properties, and the ability to effectively function as a retention aid in paper making.

25 Among the prior art that is pertinent to the present invention are the following:

Van Fisk, U.S. Patent No. 4,359,339 proposes the addition of water soluble aluminum salt, such as aluminum sulfate,
30 to permit the making of pumpable aqueous slurries of bentonite of up to 26% by weight of clay, primarily for use in making foundry sand compositions used in the making of molds. While apparently suitable for the purpose disclosed, aluminum salts have not been found to
35 be satisfactory for making smectite clay slurries of higher solids content, which are frequently desired for many purposes, especially when shipping is involved. Van

Fisk also points out that certain other ions, such as calcium ion have been known to depress the gelling properties of bentonites in aqueous slurries, but that the properties are not readily reversible upon later
5 dilution, thus limiting the value of such use. While aluminum ion appears to be less subject to this objection, to a considerable extent it suffers from the same problem. All multivalent cations tend to strongly bind the clay platelets together, which prevents
10 dispersion and inhibits performance in applications where good dispersion is needed (viscosifiers, fabric softeners, paper making retention aids).

In recently published International Application,
15 W092/11218, a smectite clay is provided as an elevated solids aqueous slurry, e.g. up to 50% solids, which is composed of the smectite clay slurried or dispersed in water containing an effective concentration of a monovalent salt. When such a salt is present in the clay
20 slurry, the clay does not swell appreciably, is essentially inactive, and the slurry can be shipped and stored without creating a gelling problem. When this slurry is diluted with fresh water at the point of application to make it of the desired solids content for
25 use, the smectite clay is activated and exhibits the desired properties, such as viscosity, retention, etc.

A concept similar to that of W092/11218 is disclosed in Cluyse et al., U.S. Patent No. 5,223,098. Bentonite
30 swelling clay is provided to a paper making mill as a fluid concentrate containing more than 15% bentonite. Swelling of the bentonite is suppressed by an inorganic electrolyte in the concentrate. The bentonite swells upon dilution either before addition of the cellulosic
35 suspension or after addition. While both W092/11218 and U.S. 5,223,098 therefore disclose high solids smectite slurries which meet the needs above discussed, they are

nonetheless sharply focused on use of certain inorganic electrolytes, which can introduce undesired ionic species into the smectite slurry. Furthermore, the efficacy of these salts for use as reversible swelling suppressants at higher smectite solids can be undesirably limited.

In accordance with the foregoing, it may be regarded as an object of the present invention, to provide a method for preparing a time-stable low viscosity, high solids aqueous slurry of a swelling smectite clay.

It is a further object of the invention to provide a method as aforementioned, wherein the smectite reversibly is inhibited from swelling in the resultant slurry, whereby upon dilution in or with water at the point of use, the smectite can be easily reactivated and swollen to generate the large surface area needed for maximum performance in many applications.

It is a further object of the invention, to provide a smectite clay slurry of the foregoing character, which remains pumpable and shippable without prohibitive gelling even at elevated solids content -- e.g. up to 47% clay solids.

It is a still further object of the present invention to provide an aqueous smectite clay slurry of up to 47% solids content, which is pumpable and shippable, and in which the swelling properties of the smectite can be readily restored during a typical use in paper making.

SUMMARY OF THE INVENTION

Now in accordance with the present invention, the foregoing objects, and others as will become apparent in the course of the ensuing specification, are achieved in an aqueous slurry of smectite clay of elevated solids

content, comprising an aqueous solution or emulsion of at least 0.2% by weight of said slurry of a salt of a low molecular weight amine salt, in which is dispersed from about 10 to 47% by weight of the slurry, of a smectite clay. The amine salt is effective to prevent the smectite from swelling appreciably, whereby the slurry can be shipped and stored without creating a gelling problem. The inhibiting or suppressing effect of the amine salt on the swelling of the clay and on gelling of the slurry is reversible upon subsequent dilution with water, thereby facilitating use of the smectite in typical applications, e.g. as a retention aid in paper making, or as a viscosifier.

Although not sharply critical, the upper limit for the quantity of amine salt to be used in the invention is in general that level at which the time-stability of the slurry becomes appreciably impaired. This level varies somewhat depending on the specific smectite, the smectite solids content in the slurry, and with the particular amine; but preferably is not more than about 5% by weight of the slurry. As increasingly high levels of the salt are used, i.e. beyond the level of stability impairment, the slurry remains pumpable but the smectite tends to increasingly settle and separate, which creates a need for inconvenient mixing during transport or for such mixing before or during transfer of the slurry between containers or between the transport container and the utilization point.

The smectite clay can typically comprise a bentonite, such as a natural swelling Wyoming bentonite; or other natural and/or synthetic swelling smectites can be used. The slurry may further include up to 0.2% by weight of the slurry, of a wetting agent, such as a non-ionic surfactant. The low molecular weight amine is in general selected from one or more members of the group consisting

of ethoxylated tallow amine, bis(2 -hydroxyethyl) soyamine, bis(2-hydroxyethyl)cocoamine, tributylamine, N-benzylethanolamine, triethanolamine, methyliminobispropylamine, hexamethylenetetramine, 5 diisopropylamine, 3,3'-iminobispropylamine, diisobutylamine, 2-(2-aminoethoxy)ethanol, diethanolamine, biuret, 1-methyl-2-pyrrolidone, aniline, methylpyrrolidone, morpholine, ethanolamine, hydroxylamine, ethylenediamine, triethylenetetramine, 10 diethylenetriamine, dimethylamine, and methylamine. Preferable amines include methylamine, dimethylamine, hydroxylamine, 2-(2-aminoethoxy)ethanol, aniline, and morpholine. The amine salt is preferably that of an acid selected from one or more members of the group consisting 15 of hydrochloric acid, sulfurous acid, sulfuric acid, phosphoric acid, formic acid, acetic acid, hydroxyacetic acid, propionic acid, oxalic acid and citric acid; of these the acid is more preferably hydrochloric acid, formic acid, acetic acid, and/or hydroxyacetic acid. The 20 slurry may further contain 0.1 to 15% polyacrylate polymer by weight, of a polyacrylate polymer having an average molecular weight of from 1,500 to 15,000 daltons.

Pursuant to the method of the invention a time-stable, 25 low viscosity, high solids aqueous slurry of a swelling smectite clay is prepared, by first preparing an aqueous solution or emulsion of a salt of a low molecular weight amine wherein the salt comprises from about 0.5 to 13% by weight of the slurry, and then dispersing therein at 30 least 10% by weight of a powdered smectite clay. The amine salt is effective to prevent the smectite from swelling appreciably, whereby the slurry can be shipped and stored without creating a gelling problem. The inhibiting effect of the amine salt on the swelling of 35 the smectite and gelling of the slurry is reversible upon subsequent dilution with water. The aqueous salt solution or emulsion is preferably prepared as an initial

step, and the smectite powder is then added thereto with mixing. The smectite is added to the solution or emulsion as from 10 to 47% by weight of the slurry.

5 The invention also resides in a method for shipping a swelling smectite clay from a shipping point to a utilization point such as a paper mill, and providing at the utilization point an aqueous swelled smectite slurry. A high solids, low viscosity shippable slurry is thus
10 prepared at the shipping point, comprising an aqueous solution or emulsion of at least about 0.2% by weight of the shippable slurry of a salt of a low molecular weight amine, in which is dispersed at least 10% by weight of a powdered smectite. The amine salt is effective to
15 prevent the smectite from swelling appreciably, whereby the slurry can be shipped and stored without creating a gelling problem, and the inhibiting effect of the salt on the swelling of the smectite and gelling of the slurry is reversible upon subsequent dilution with water. The
20 slurry is shipped to the utilization point, and activated and swelled by diluting the high solids slurry with water. Dilution of the high solids slurry at the utilization point typically brings the smectite clay solids to the range of .01 to 10%. Where the utilization
25 is in a paper making process, dilution of the slurry can be effected by adding the slurry to an aqueous cellulosic suspension which is being employed in the process, or by diluting the smectite slurry with water prior to its addition to the cellulosic suspension.

30

Smectite clays of the type which have been described in the Background portion of this specification are among those which may comprise the swelling smectite clay component of the aqueous slurries of the invention. In
35 some instances these smectites may be modified by surface treatment to provide properties of special interest. For example, smectite clays that have been modified by

reaction with low molecular weight (1,000 to 100,000 daltons), high charge density (4 to 24 meq/g) water soluble polymers of the anionic or cationic type can be used in the slurries to which the invention is

5 applicable. Examples of suitable anionic high charge density water-soluble polymers are polyacrylic acid, polymethacrylic acid, polymaleic acid, polyvinyl sulphonic acids, polyhydroxy carboxylic acids, polyaldehyde carboxylic acids, alkyl acrylate/acrylic

10 acid copolymers, acrylamide/acrylic acid copolymers and salts of any of the above, for example, the alkali metal or ammonium salts of any of the above. Suitable cationic high charge density water-soluble polymers include polyethyleneimines, polyamidoamines, polyvinylamines, and

15 polydiallyl ammonium compounds.

In the polymer modified clays, the low molecular weight, high charge density, water soluble anionic or cationic polymers are present in an amount of 0.5 to 25% based

20 upon the dry weight of the clay. The polymer modification to the clay is facilitated by adding both the amine salt and the polymer to the water before the addition of the clay.

25 The preparation of polymer modified clays is disclosed in U.S. Pat. 5,015,334, which issued on May 14, 1991, and is incorporated herein by reference. The polymer modified clays are used as retention/drainage agents in paper or paperboard production. Polymer modified clays, such as

30 taught in U.S. Patent 5,015,334, are commercially available under the LAPOTAIN mark from Laporte Industries Ltd., London England, and from Vinings Industries, Inc., Atlanta, GA.

35 Another synthetic analogue that is useful in the smectite slurries of the invention is the synthetic hectorite material that is commercially available under the trade

names LAPONITE or LAPOMER from Laporte Industries Limited, London or Southern Clay Products, Inc., Gonzales, Texas.

- 5 The smectite swelling suppressant employed in the present invention is the salt of a low molecular weight amine. By the term "low molecular weight amine," as used herein, is meant a primary, secondary, tertiary or quaternary amine having a molecular weight within the range of about
10 31 to about 500 daltons. Such amines were used in preparing the examples shown in TABLES I and II herein. Illustrative of such amines are the following: ethoxylated tallow amine, bis(2-hydroxyethyl)soyamine, bis(2 hydroxyethyl) cocoamine, tributylamine,
15 N-benzylethanolamine, triethanolamine, methyliminobispropylamine, hexamethylenetetramine, diisopropylamine, 3,3'-iminobispropylamine, diisobutylamine, 2-(2-aminoethoxy)ethanol, diethanolamine, biuret, 1-methyl-2-pyrrolidone, aniline,
20 methylpyrrolidone, morpholine, ethanolamine, hydroxylamine, ethylenediamine, triethylenetetramine, diethylenetriamine, dimethylamine, and methylamine.

- Generally, the amines with the lower molecular weights
25 are preferred. The more preferred amines include methylamine, dimethylamine, hydroxylamine, 2-(2-aminoethoxy)ethanol, aniline and morpholine.

- The acid component that is used to form the salt of the
30 low molecular weight amine may be an organic acid or a mineral acid. Suitable organic acids include the following: formic, acetic, hydroxyacetic, propionic, oxalic, citric, palmitic, and the like. Suitable mineral acids include the following: hydrochloric, sulfurous,
35 sulfuric and phosphoric.

Preferably, the acid has a low molecular weight, such as hydrochloric, formic, acetic, or hydroxyacetic acids. Hydrochloric acid is especially preferred.

- 5 A wetting agent, i.e., a surfactant, may be optionally used in the slurries prepared by the present invention. The function of the surfactant is to speed the wetting of the clay. Although the smectite clay will eventually wet without the surfactant, it will take significantly
10 longer. When present, an effective amount of the surfactant in the aqueous slurry is from about 0.01 to about 0.2 percent by weight of the slurry, typically, from about 0.06 to about 0.1% by weight. Any non-interfering surfactant may be used. Such surfactants are
15 typically non-ionic, such as the polyalkoxylated alcohol sold under the tradename TRITON. A suitable surfactant is TRITON DF-16, which is commercially available from Sigma Chemical Company, St. Louis, MO.
- 20 Optionally, the composition of the present invention may also include less than 15% by weight of the slurry of a low molecular weight polyacrylate polymer. By the term "polyacrylate polymer" as used herein is meant a water soluble or dispersible homopolymer, copolymer, or
25 terpolymer wherein at least one of the monomer units is acrylic acid, methacrylic acid or maleic acid. To facilitate the spacing of the charges, the polyacrylate polymer may also include monomer units of methyl acrylate, ethyl acrylate, and vinyl sulfonic acid. It is
30 also within the scope of the present invention to employ other monomeric units in amounts that do not preclude the water solubility or dispersibility of the polyacrylate polymer.
- 35 By the term "low molecular weight polyacrylate polymer," as used herein, is meant a polyacrylate polymer of sufficiently low molecular weight so as to be water

- soluble or water dispersible. Typically, the mean molecular weight of a suitable low molecular weight polyacrylate polymer is from 1,500 to 15,000 daltons. The polyacrylate polymer contributes to modification of
- 5 the surface charge on the clay particles. Typically, an effective amount of polyacrylate polymer in the slurry composition of the present invention is 0.1 to about 15% by weight of the smectite slurry.
- 10 To facilitate its solubility or dispersibility in water, the polyacrylate polymer is employed in the form of a partially neutralized salt of its carboxylic acid moieties. Preferably, the partially neutralized salt of the polyacrylate polymer is a sodium, potassium, lithium
- 15 or ammonium salt, or a combination thereof.

DESCRIPTION OF PREFERRED EMBODIMENTS

- In a preferred procedure pursuant to the invention the
- 20 selected amine (or amines) and acid(s) are added to water with mixing, where they react to form the desired amine salt(s). The amine depending on its structure and molecular weight, is commonly available as a liquid, a liquid solution, or as a solid. In each instance the
- 25 amine should be water soluble or water dispersible. The order of addition of the amine and acid is not critical. The resulting amine salt should likewise be water soluble or at least be water dispersible, so that at least an emulsion is formed. The surfactant (if used) is then
- 30 added, and the optional polyacrylate polymer. Thereafter, the desired amount of the smectite clay, e.g. a sodium bentonite, is added to and dispersed in the aqueous solution or emulsion. Unlike certain prior art, the clay may be added rapidly and with rapid mixing. The
- 35 mode of mixing is not critical. Various instrumentalities may be used, including paddle wheel mixing and the like.

TABLES I and II herein reflect various compositions of the present invention. In particular, TABLE I discloses various compositions of the present invention that differ
5 from one another in either the amount or selection of a primary, secondary, tertiary or quaternary amine, and in the presence or absence of a polyacrylate polymer. In TABLE I, the various components of each slurry, i.e., amine, acid (HCl), water, clay, polyacrylate polymer
10 (polymer 9000 (Acumer 9000)), and surfactant (TRITON DF-16), are provided in parts per 100 parts slurry by weight. Acumer 9000 is a low molecular weight polyacrylate polymer that is commercially available from Rohm and Haas Company, Philadelphia, PA. TRITON DF-16 is
15 a polyalkoxylated alcohol (i.e., non-ionic) wetting agent that is commercially available from Sigma Chemical Co., St. Louis, MO. For convenience, the amount of TRITON DF-16 is not listed in TABLE I. However, it is present in each slurry from 0.06 to 0.10 parts by weight
20 per 100 parts slurry. The last column of TABLE I reflects stability by reporting the appearance of each composition five days after its preparation. When observed on the fifth day, the appearance of the various compositions ran the continuum from liquid to solid. For
25 purposes of this invention, the best results were obtained with slurries that appeared "liquid" after five days. Slurries that appeared "liquid, weeps" ran close behind. By "weeps" is meant that some water separated from the slurry and was visible as pooling on top.
30 These slurries ("liquid" and "weeps") were amine salt stabilized, high solids, low viscosity bentonite slurries of the present invention.

TABLE I indicates that methylamine hydrochloride provided
35 a high solids, low viscosity bentonite slurry that had 42.9 parts clay by weight, but still remained liquid, and therefore pumpable, after five days.

TABLE II is similar to TABLE I except that TABLE II reflects the effect of various acids on the resulting amine salts' ability to suppress the gelling properties of a high solids bentonite slurry. As already discussed herein, the greatest suppression of gelling generally occurs with the smallest amines and the smallest acids. For example, methylamine with acetic acid (formula weight 60.05) or with propionic acid (formula weight 74.08) provides a "liquid" slurry at 30 parts clay per hundred parts slurry by weight, whereas the same amine (methylamine) with the higher molecular weight acid, palmitic acid (F.W. 256.43) provides a more viscous "paste" slurry at 20.7 parts clay per hundred parts slurry by weight.

TABLE I
AMINE HYDROCHLORIDE SALTS AND BLANKS

Amine or Amine Salt	Amine	Salt	Amine	HCl	Water	Clay	Poly 9000	pH	Appearance
Reaction: (1 mole amine + 1 mole HCl)	% Purity	Total	STOIC	STOIC	AMT.	AMT.	AMT.	FIN	5 DAYS
		Parts	Parts	Parts	Parts	Parts	Parts		
Proset 1810 (DMA + epichlorohydrin polymer)	50	3.1		-	64.9	31.3	0.63	-	Solid
"	50	1.8		-	80.3	17.5	0.35	9.0	Solid Paste
Ethox TAM-5 or POE(5) tallow amine	100	6.0	5.6	1.2	62.6	30.0	0.60	-	Solid
"	100	4.6	4.3	0.9	71.3	23.0	0.46	7.7	Liquid
Aliquat 336 or tricaprylmethylammonium chloride	100	6.0		-	63.3	30.0	0.60	-	Solid
"	100	3.8		-	76.9	18.9	0.38	-	Liquid
Stepan BTC 99 or Didecyl Dimethylammonium Cl	50	12.0		-	57.3	30.0	0.60	-	Solid
"	50	6.9		-	75.5	17.2	0.34	9.3	Solid Paste
bis(2-hydroxyethyl)-tallow amine	100	6.0	5.4	1.5	62.3	30.0	0.60	7.5	Paste

TABLE I (cont'd.)

Amine or Amine Salt	Amine	Salt	Amine	HCl	Water	Clay	Poly 9000	pH	Appearance
Reaction: (1 mole amine + 1 mole HCl)	% Purity	Total	STOIC	STOIC	AMT.	AMT.	AMT.	FIN	5 DAYS
		Parts	Parts	Parts	Parts	Parts	Parts		
"	100	4.4	4.0	1.1	72.1	22.2	0.44	-	Thixo-tropic Liquid
bis(2-hydroxyethyl)-tallow amine	100	4.6	4.2	1.2	70.8	23.2	0.46	7.2	Liquid
POE(2) tallow amine	100	6.0	5.4	1.6	62.3	30.0	0.60		Solid
"	100	5.0	4.5	1.3	68.9	24.8	0.50	7.3	Liquid
bis(2-hydroxyethyl)-soyamine	100	6.0	5.4	1.6	62.3	30.0	0.60	7.4	Paste
"	100	4.4	4.0	1.2	72.1	22.2	0.44		Thixo-tropic Liquid
"	100	4.6	4.2	1.2	70.8	23.2	0.46	7.3	Liquid
bis(2-hydroxyethyl)-cocoamine	100	6.0	5.4	1.7	62.2	30.0	0.60	8.1	Solid
"	100	5.1	4.6	1.4	67.7	25.6	0.51		Thixo-tropic Liquid
"	100	5.1	4.6	1.4	68.1	25.4	0.51	8.1	Liquid

TABLE I (cont'd.)

Amine or Amine Salt	Amine	Salt	Amine	HCl	Water	Clay	Poly 9000	pH	Appearance
Reaction: (1 mole amine + 1 mole HCl)	% Purity	Total	STOIC	STOIC	AMT.	AMT.	AMT.	FIN	5 DAYS
		Parts	Parts	Parts	Parts	Parts	Parts		
Tetrabutylammonium hydroxide	40	6.0	14.0	2.1	53.2	30.0	0.60	8.5	Liquid
1-Amino-2-Naphthol-4-sulfonic acid	100	6.0	5.2	2.1	61.9	30.0	0.60	5.0	Purple Paste
"	100	5.3	4.6	1.9	66.6	26.3	0.53	5.5	Purple Liquid
N-Benzylethanolamine	99	6.0	4.9	3.2	61.3	30.0	0.60	7.5	Liquid
"	99	4.5	4.9	2.4	62.0	30.0	0.60	8.7	Viscous Liquid
Triethanol amine	99.9	6.0	4.8	3.2	61.3	30.0	0.60	7.3	Liquid
							0.60		Liquid
Methyliminobis-propylamine	100	6.0	4.8	3.3	61.3	30.0	0.60	9.9	Liquid
Hexamethylene-tetramine	99.4	6.0	4.8	3.3	61.2	30.0	0.60	5.9	Liquid
"	99.4	4.5	4.8	2.5	62.0	30.0	0.60	5.9	Liquid
Diisopropanolamine	100	6.0	4.7	3.5	61.1	30.0	0.60	7.2	Liquid

TABLE I (cont'd.)

Amine or Amine Salt	Amine	Salt	Amine	HCl	Water	Clay	Poly 9000	pH	Appearance
Reaction: (1 mole amine + 1 mole HCl)	% Purity	Total	STOIC	STOIC	AMT.	AMT.	AMT.	FIN	5 DAYS
		Parts	Parts	Parts	Parts	Parts	Parts		
3,3'-Iminobis- propylamine	100	6.0	4.7	3.5	61.1	30.0	0.60	9.9	Liquid
Diisobutylamine	100	6.0	4.7	3.6	61.1	30.0	0.60	7.4	Liquid
"	100	5.4	4.2	3.2	55.1	36.8	0.54	7.4	Liquid
2-(2-aminoethoxy)-ethanol	100	6.0	4.5	4.2	60.7	30.0	0.60	7.4	Liquid
"	100	5.2	3.9	3.6	52.7	39.2	0.52	7.4	Liquid
Diethanol amine	85	6.0	5.2	4.2	59.9	30.0	0.60	8.1	Liquid
Biuret	100	6.0	4.4	4.2	60.6	30.0	0.60	2.7	Liquid
"	100	4.5	4.4	3.2	61.7	30.0	0.60	3.3	Thixo-tropic Liquid
1-Methyl-2-Pyrrolidone	100	6.0	4.4	4.4	60.6	30.0	0.60	2.9	Liquid
Aniline, purified	100	6.0	4.3	4.6	60.4	30.0	0.60	4.6	Liquid
"	100	4.5	4.3	3.4	61.6	30.0	0.60	4.6	Thixo-tropic Liquid
Methyl Pyrrolidone	100	6.0	4.4	4.4	60.6	30.0	0.60	2.7	Liquid

TABLE I (cont'd.)

Amine or Amine Salt	Amine	Salt	Amine	HCl	Water	Clay	Poly 9000	pH	Appearance
Reaction: (1 mole amine + 1 mole HCl)	% Purity	Total	STOIC	STOIC	AMT.	AMT.	AMT.	FIN	5 DAYS
		Parts	Parts	Parts	Parts	Parts	Parts		
"	100	4.5	4.4	3.3	61.6	30.0	0.60	4.2	Liquid
Morpholine	100	6.0	4.2	4.8	60.3	30.0	0.60	7.0	Liquid
Hydroxylamine Hydrochloride	98.9	6.1			63.2	30.0	0.60	5.9	Liquid
"	98.9	5.9			64.5	28.9	0.58	5.9	Liquid
Ethanolamine	99	6.0	3.7	6.1	59.4	30.0	0.60	8.1	Liquid
Ethylenediamine	100	6.0	3.7	6.1	59.4	30.0	0.60	8.3	Liquid, weeps
Triethylenetetramine mix	100	6.0	3.6	6.5	59.2	30.0	0.60	10.0	Liquid, weeps
Diethylenetetramine mix	100	6.0	3.6	6.6	59.1	30.0	0.60	7.0	Liquid, weeps
Dimethylamine	40	6.1	8.3	7.3	63.2	30.0	0.60		Liquid, weeps
"	40	5.1	6.9	6.1	52.7	41.7	0.50		Liquid, weeps
Methylamine	40	6.0	6.9	8.8	53.6	30.0	0.60	7.0	Liquid
"	40	6.0	5.8	7.3	44.7	41.7	0.50	7.5	Liquid
"	40	6.0	6.9	8.8	40.7	42.9	0.60		Liquid

TABLE I (cont'd.)

Amine or Amine Salt	Amine	Salt	Amine	HCl	Water	Clay	Poly 9000	pH	Appearance
Reaction: (1 mole amine + 1 mole HCl)	% Purity	Total	STOIC	STOIC	AMT.	AMT.	AMT.	FIN	5 DAYS
		Parts	Parts	Parts	Parts	Parts	Parts		
(CH ₃) ₂ NH ₄ Cl, parts of salt variations	99	6.1			63.2	30.0	0.60		Liquid, weeps
"	99	3.0			66.2	30.0	0.60	8.5	Liquid
"	99	1.5			67.7	30.0	0.60		Paste
"	99	0.0			69.2	30.0	0.60		Solid
<u>Inorganic Ammonium Salts:</u>									
Ammonium Phosphate Monobasic	100	6.0			63.3	30.0	0.60	6.5	Thick Liquid
Ammonium Chloride	100	6.0			63.3	30.0	0.60	7.8	Liquid
Ammonium Chloride, maximum clay	100	6.0			54.0	39.3	0.60	7.6	Thick Liquid
<u>Blanks:</u>									
Maximum Clay					81.0	18.3	0.60	10.1	Grainy Liquid
Maximum Clay					94.9	5.0		9.9	Grainy Liquid

PARTS = parts based upon 100 parts by weight of ingredients.

TABLE I (cont'd.)

Each composition also contains from 0.35 to 0.60 parts by weight Poly 9000 and from 0.06 to 0.10 parts by weight of TRITON DF-16 wherein the ratio by weight of Poly 9000 to TRITON DF-16 is about 6:1.

POLY 9000 = Acumer 9000 as supplied by Rohm & Haas.

TRITON DF-16 is a polyalkoxylate alcohol surfactant.

CLAY = Bentolite 642 as supplied by Southern Clay Products Inc., Gonzales, Texas.

WEEPS = Some water split on top after standing.

TABLE II

SALTS OF AMINES OTHER THAN HYDROCHLORIDES

Amine Source	Amine % Act.	Amine Stoich Parts	Acid Stoich Parts	Water Amount Parts	Clay Amount Parts	Poly 9000 Amount Parts	pH FIN.	Appearance
<u>Acetic Acid (F.W. 60.05, 95%</u>								
Ethox TAM-5, POE (5) tallow amine	100	27.0	0.7	41.6	30.0	0.60	-	Solid

Table II (cont'd)

Amine Source	Amine % Act.	Amine Stoich Parts	Acid Stoich Parts	Water Amount Parts	Clay Amount Parts	Poly 9000 Amount Parts	pH FIN.	Appearance
- <u>ACID SOURCE</u>								
Ethox TAM-2, POE (2) tallow amine	100	19.5	0.9	48.9	30.0	0.60	-	Solid Amine
Tetrabutylammonium hydroxide $[\text{CH}_3(\text{CH}_2)_3\text{OH}]$	40	12.9	1.3	55.1	30.0	0.60	9.2	Thick Liquid
Ethylenediamine, $\text{H}_2\text{NCH}_2\text{CH}_2\text{NH}_2$	100	3.0	3.2	63.1	30.0	0.60	9.0	Liquid
Triethylenetriamine mix	100	2.9	3.3	63.1	30.0	0.60	8.9	Liquid
Diethylenetriamine mix	100	2.8	3.4	63.1	30.0	0.60	8.3	Liquid
Dimethylamine, $(\text{CH}_3)_2\text{NH}$	40	6.4	3.6	59.3	30.0	0.60	6.1	Liquid
Methylamine, CH_3NH_2	40	4.4	4.2	60.7	30.0	0.60	6.8	Liquid
Hydroxyacetic acid (F.W. 76.05, 57%)								
Triethylenetetramine mix	100	2.5	6.1	60.7	30.0	0.60	8.6	Liquid
Diethylenetriamine mix	100	2.5	6.2	60.6	30.0	0.60	9.1	Liquid
Methylamine, CH_3NH_2	40	3.9	7.5	58.0	30.0	0.60	7.3	Liquid
Propionic acid (F.W. 74.08, 99.68%)								
Methylamine, CH_3NH_2	40	3.9	4.2	61.1	30.0	0.60	6.9	Liquid

TABLE II (cont'd.)

Amine Source	Amine % Act.	Amine Stoich Parts	Acid Stoich Parts	Water Amount Parts	Clay Amount Parts	Poly 9000 Amount Parts	pH FIN.	Appearance
<u>Sulfuric acid (F.W. 98.08, 96.1%)</u>								
Methylamine, CH ₃ NH ₂	40	3.3	4.7	61.3	30.0	0.60	2.3	Liquid
Methylamine, CH ₃ NH ₂ , amine to acid 2:1	40	5.8	3.8	59.7	30.0	0.60	8.5	Liquid
<u>Phosphoric acid (F.W. 98.00, 85%)</u>								
Methylamine, CH ₃ NH ₂	40	3.3	5.4	60.7	30.0	0.60	6.0	Liquid
Methylamine, CH ₃ NH ₂ , amine to acid 2:1	40	5.8	4.3	59.2	30.0	0.60	8.5	Liquid
Methylamine, CH ₃ NH ₂ , amine to acid 3:1	40	7.3	3.6	58.4	30.0	0.60	11.1	Liquid
<u>Palmitic acid (F.W. 256.43, 95%)</u>								
Methylamine, CH ₃ NH ₂	40	1.8	6.4	70.3	20.7	0.68		Paste
"	40	1.0	3.5	83.9	11.2	0.37	10.0	Light Paste

TABLE II (cont'd.)

Amine Source	Amine % Act.	Amine Stoich Parts	Acid Stoich Parts	Water Amount Parts	Clay Amount Parts	Poly 9000 Amount Parts	pH FIN.	Appearance
<u>ACID SOURCE</u>								
"	40	0.8	2.8	87.1	9.0	0.29		Fluffy Paste

PARTS = parts based upon 100 parts by weight of ingredients.

Each composition also contains from 0.35 to 0.60 parts by weight Poly 9000 and from 0.06 to 0.10 parts by weight of TRITON DF-16 wherein the ratio by weight of Poly 9000 to TRITON DF-16 is about 6:1.

POLY 9000 = Acumer 9000 as supplied by Rohm & Haas.

TRITON DF-16 is a polyalkoxylate alcohol surfactant.

CLAY = Bentolite 642 as supplied by Southern Clay Products Inc., Gonzales, Texas.

WEEPS = Some water split on top after standing.

TABLE III illustrates that the optional polyacrylate polymer has a very small positive effect on the ability to make the amine salt stabilized high solids bentonite slurries of the present invention.

5

TABLE III

	Acumer 9000 Sodium polyacrylate (parts)	Dimethylamine hydrochloride (parts)	Maximum Bentonite Solids (parts)
10	0	0	8
	4	0	13
	0	6	45
	15	6	47

15

In TABLE III, all "parts" represent "parts per hundred parts slurry by weight."

The inhibitory effect on the swelling of bentonite clay by the organic amine salts is reversible as is shown for dimethylamine hydrochloride in TABLE IV. The data for dimethylamine hydrochloride was determined by preparing an aqueous high solids bentonite slurry wherein the amount of bentonite was 37.9 parts per hundred parts per slurry by weight, the amount of dimethylamine hydrochloride was 2.07 parts per hundred parts slurry by weight, and an effective amount of surfactant was used. Aliquots of this slurry were diluted with water with agitation. The resulting dilute slurries were sealed and allowed to sit for 24 hours at which time they were compared to the original.

After 24 hours, the samples diluted with the largest amount of water had the greatest amount of weeping or splitting of excess water from the bentonite layer. The clear liquid on top of the slurry was removed and

weighed. This "free water" is regarded as excess water or water that had not been bound by the swelling of the bentonite. The difference between the free water and the amount of dilution water added is a measure of how much additional water is absorbed by the bentonite due to swelling. The percent swelling of the bentonite clay is calculated as follows:

$$\% \text{ Clay Swelling} = \frac{(\text{Dilution Water Added} - \text{Free Water}) \times 100}{\text{Total Weight of Slurry}}$$

For each dilution, the free water, after diluting and settling, was less than the dilution water added to the sample. See TABLE IV. These results indicate that the bentonite layer was holding additional water because of swelling. Swelling was observed to increase with increasing dilution.

TABLE IV

Original Slurry Weight	Dilution Water Weight	% Bentonite	Free Water Weight (24 Hours)	(Dilution Water - Free Water)	% Clay Swelling
500	0	37.9	1.1	1.1	-0.2
95	5	36	0.6	4.4	4.6
90	10	34.1	1	9	10
70	30	26.5	4.8	25.2	36
150	150	19	66.7	83.3	55.5
100	200	12.6	115.9	84.1	84.1
100	300	9.5	183.4	116.6	116.6

The efficacy of the invention is fully achieved at even very low levels of the amine salt. This is shown in the series of tests tabularized in Table V, which illustrates both the ease of manufacture and the stabilization of bentonite slurries using a dimethylamine hydrochloride salt to temporarily inhibit the swelling properties of

the clay. Moderate solids bentonite slurries were thus prepared using a "Lightning" propeller mixer at moderate speed. All slurries were prepared at the same speed using the same percentage of bentonite solids in the resulting slurries. The sodium polyacrylate level used in the slurry to modify the electrophoretic mobility of the bentonite remained constant in all the tests. The only difference in the prepared suspensions was the level of amine salt.

10

The slurries were prepared by adding the sodium polyacrylate dispersant to the water for the slurry preparation, followed by the dimethylamine and the hydrochloric acid solution. The Bentolite® 642, a sodium bentonite supplied by Southern Clay Products, Inc. was added over a one minute period. The slurries were observed as they were stirred. Mixing continued until the slurries had a smooth, uniform appearance, with no noticeable lumps of unwetted bentonite.

20

Tests 1-6 were all extremely easy to prepare, with the bentonite wetting out very quickly and clumps disappearing very rapidly. The resulting bentonite suspensions all settled very fast because the amine salt produced a total, temporary inhibition of swelling of the bentonite. These examples would not be preferred for transport because they settle in the shipping container before arriving at the application site. The settled bentonite will, however, go back into suspension rapidly with agitation.

30

Tests 7-9 exhibit fast wetting and preparation time and form suspensions that are stable or have a slight water separation at the top. These are judged to be acceptable for manufacturing and shipment to an application site. Tests 10-12 exhibit slower wetting and preparation time than the previous tests with the formation of a grainy

35

appearance, which became smooth and uniform with additional agitation. Tests 10-12 were storage stable for 35 days and remained pourable with no agitation.

- 5 Tests 13-14 test the effect of minimizing the amount of amine salt. Test 13 wetted slower than the previous examples and became grainy before finally forming a uniform dispersion. Test 13 produced a stable slurry, but it had almost gelled. Test 14 wetted slower than 13
10 and took longer agitation to form a smooth lump free suspension. Test 14 gelled. The control suspension (untreated with the amine salt) was Test 15. It gave very slow wetting and had lumps of unwetted bentonite for considerably longer than Test 14 before it became
15 uniform. Test 15 gelled on standing. Bentonite slurries that gel (do not pour) are difficult to pump from a shipping container at the point of use, without first agitating the suspension. Gelled suspensions are judged to be unacceptable for present purposes.

TABLE V

Test	Water	Sodium	HCl 37%	DMA 40%	Amine	Bentolite	% Amine	Preparation	Appearance
No.		Polyacrylate			Salt	642	Salt on	Wetting Speed & Slurry Appearance	35 Days
							Bentonite		Not Agitated
1	82.90	1.69	2.41	2.76	2.00	10.24	19.49%	Instantaneous, no lumps	Separates Quickly
2	83.93	1.69	1.93	2.21	1.60	10.24	15.61%	Very fast wetting, no lumps	Separates Quickly
3	84.76	1.69	1.54	1.77	1.28	10.24	12.48%	Very fast wetting, no lumps	Separates Quickly
4	85.43	1.69	1.23	1.41	1.02	10.24	9.95%	Very fast wetting, no lumps	Separates Quickly
5	85.95	1.69	0.99	1.13	0.82	10.24	7.99%	Fast wetting, small amount on walls	Separates Quickly
6	86.38	1.69	0.79	0.90	0.65	10.24	6.37%	Fast wetting, small amount on walls	Separates Slowly
7	86.72	1.69	0.63	0.72	0.52	10.24	5.09%	Fast wetting, small amount on walls	Slight Separation

TABLE V (Cont'd)

Test	Water	Sodium	HCl 37%	DMA 40%	Amine	Bentolite	% Amine	Preparation	Appearance
No.		Polyacrylate			Salt	642	Salt on	Wetting Speed & Slurry Appearance	35 Days
							Bentonite		Not Agitated
8	86.98	1.69	0.51	0.58	0.42	10.24	4.11%	Fast wetting, small amount on walls	Very slight separation
9	87.21	1.69	0.40	0.46	0.33	10.24	3.24%	Fast wetting, small amount on walls	Stable, pours OK
10	87.38	1.69	0.32	0.37	0.27	10.24	2.60%	Moderate wetting rate, grainy before getting smooth	Stable, pours OK
11	87.42	1.69	0.32	0.33	0.25	10.24	2.45%	Moderate wetting rate, grainy before getting smooth	Stable, pours OK
12	87.51	1.69	0.26	0.30	0.22	10.24	2.11%	Moderate wetting rate, grainy before getting smooth	Stable, moves very slowly
13	87.71	1.69	0.17	0.19	0.14	10.24	1.36%	Moderate to slow, grainy before getting smooth	Stable, doesn't pour

TABLE V (Cont'd)

Test	Water	Sodium	HCl 37%	DMA 40%	Amine	Bentolite	% Amine	Preparation	Appearance
No.		Polyacrylate			Salt	642	Salt on	Wetting Speed & Slurry Appearance	35 Days
							Bentonite		Not Agitated
14	87.84	1.69	0.11	0.12	0.09	10.24	0.87%	Slow wetting, but much faster than water only	Stable, gelled
15	88.07	1.69	0.00	0.00	0.00	10.24	0.00%	Very slow wetting, lumps, long time to become uniform	Stable, gelled

The sodium polyacrylate used was Accumer 9000, as supplied by Rohm & Haas.

Bentolite 642 is a sodium bentonite clay supplied by Southern Clay Products.

Slurries were prepared with a Lightning propeller mixer, run at moderate speed. The agitation rate was the same for all samples.

Acceptable products must be easily produced and remain stable and flowable after storage.

While the present invention has been set forth in terms of specific embodiments thereof, it will be appreciated in view of the foregoing disclosure, that numerous variations upon the invention are now enabled to those skilled in the art, which variations yet reside within the scope of the invention. For example, it is also within the scope of the present invention that the amine salt be selected to suit a particular application. Thus, in certain instances, the amine that is most effective at suppressing the viscosity of a bentonite slurry is not always chosen. For example, the salt of a fatty amine with a mineral acid may be used to render the bentonite more hydrophobic. The solids level of the slurry would necessarily have to be lower than if prepared with the optimal low molecular weight amine salts. However, the maximal solids content is sacrificed to provide a high solids, low viscosity bentonite suspension having distinct end use properties. By selecting an amine salt having properties suited for a particular end use, e.g., polar, non-polar, etc., one can use the method of the present invention to form compositions of the present invention that are customized to a particular end-users requirements. Such (amine salt) customized high solids, low viscosity bentonite slurries would exhibit viscosities that increased upon dilution.

Accordingly, the invention is to be broadly construed, and limited only by the scope and spirit of the claims now appended hereto.

WHAT IS CLAIMED IS:

1 1. An aqueous slurry of smectite clay of elevated
2 solids content, comprising an aqueous solution or
3 emulsion of at least 0.2% by weight of said slurry of a
4 salt of a low molecular weight amine, in which is
5 dispersed from about 10 to 47% by weight of said slurry,
6 of a smectite clay; said amine salt being effective to
7 prevent the said smectite from swelling appreciably,
8 whereby the slurry can be shipped and stored without
9 creating a gelling problem; and the inhibiting effect of
10 said salt on said swelling of the clay and on gelling of
11 said slurry being reversible upon subsequent dilution
12 with water.

1 2. An aqueous slurry in accordance with claim 1,
2 wherein said slurry is time-stable and has a sufficiently
3 low viscosity to enable pumpability; and wherein the
4 quantity of said amine salt is below that at which the
5 time-stability of the slurry becomes appreciably
6 impaired.

1 3. An aqueous slurry in accordance with claim 2,
2 wherein said amine salt is present in the range of 0.2 to
3 about 5% by weight of said slurry.

1 4. An aqueous slurry in accordance with claim 1,
2 wherein the smectite clay is a bentonite.

1 5. An aqueous slurry in accordance with claim 1,
2 wherein said smectite has been modified by surface
3 treatment with a low molecular weight, high charge
4 density water soluble polymer.

1 6. An aqueous slurry in accordance with claim 1,
2 further comprising up to 0.2% by weight of the slurry, of
3 a wetting agent.

1 7. An aqueous slurry in accordance with claim 1,
2 wherein said low molecular weight amine is selected from
3 one or more members of the group consisting of
4 ethoxylated tallow amine, bis(2 -hydroxyethyl) soyamine,
5 bis(2-hydroxyethyl)cocoamine, tributylamine,
6 N-benzylethanolamine, triethanolamine,
7 methyliminobispropylamine, hexamethylenetetramine,
8 diisopropylamine, 3,3'-iminobispropylamine,
9 diisobutylamine, 2-(2-aminoethoxy)ethanol,
10 diethanolamine, biuret, 1-methyl-2-pyrrolidone, aniline,
11 methylpyrrolidone, morpholine, ethanolamine,
12 hydroxylamine, ethylenediamine triethylenetetramine,
13 diethylenetriamine, dimethylamine, and methylamine.

1 8. An aqueous slurry in accordance with claim 7,
2 further containing 0.1 to 15% polyacrylate polymer by
3 weight of said slurry, said polyacrylate polymer having
4 an average molecular weight from 1,500 to 15,000 daltons.

1 9. An aqueous slurry in accordance with claim 8,
2 wherein said amine is selected from one or more members
3 of the group consisting of methylamine, dimethylamine,
4 hydroxylamine, 2-(2-aminoethoxy)ethanol, aniline, and
5 morpholine.

1 10. An aqueous slurry in accordance with claim 9,
2 wherein said salt is that of an acid selected from one or
3 more members of the group consisting of hydrochloric
4 acid, sulfurous acid, sulfuric acid, phosphoric acid,
5 formic acid, acetic acid, hydroxyacetic acid, propionic
6 acid, oxalic acid and citric acid.

1 11. An aqueous slurry in accordance with claim 10,
2 wherein said acid is selected from one or more members of
3 the group consisting of hydrochloric acid, formic acid,
4 acetic acid and hydroxyacetic acid.

1 12. An aqueous slurry in accordance with claim 10,
2 wherein the bentonite clay content is 30 to 47% by weight
3 of said slurry.

1 13. An aqueous slurry in accordance with claim 11,
2 wherein the bentonite clay content is 30 to 47% by weight
3 of said slurry.

1 14. An aqueous slurry in accordance with claim 13,
2 wherein the bentonite clay content is 40 to 47% by weight
3 of said slurry.

1 15. An aqueous slurry in accordance with claim 14,
2 wherein the wetting agent is a non-ionic surfactant.

1 16. An aqueous slurry in accordance with claim 15,
2 wherein the non-ionic surfactant is a polyalkoxylated
3 alcohol.

1 17. A method for preparing a time-stable, low
2 viscosity, high solids aqueous slurry of a swelling
3 smectite clay, comprising:

4
5 preparing an aqueous solution or emulsion of a salt
6 of a low molecular weight amine, wherein said salt
7 comprises at least 0.2% by weight of said slurry, and
8 dispersing therein at least 10% by weight of a powdered
9 smectite clay; said salt being effective to prevent the
10 said smectite from swelling appreciably, whereby the
11 slurry can be shipped and stored without creating a
12 gelling problem; and the inhibiting effect of said salt
13 on said swelling of the smectite and gelling of said

14 slurry being reversible upon subsequent dilution with
15 water.

1 18. A method in accordance with claim 17, wherein
2 the quantity of said amine salt is below that at which
3 the time-stability of the slurry becomes appreciably
4 impaired.

1 19. A method in accordance with claim 18, wherein
said amine salt is present in the range of 0.2 to about
5% by weight of said slurry.

1 20. A method in accordance with claim 17, wherein
2 said aqueous salt solution or emulsion is prepared as an
3 initial step, and said smectite powder is then added
4 thereto with mixing.

1 21. A method in accordance with claim 20, wherein
2 said smectite is a sodium bentonite, which is added to
3 said solution or emulsion as from 10 to 47% by weight of
4 said slurry.

1 22. A method in accordance with claim 20, further
2 including adding to said slurry up to 0.2% by weight of
3 said slurry, of a wetting agent; and wherein said low
4 molecular weight amine has a molecular weight within the
5 range of 31 to 500 daltons.

1 23. A method in accordance with claim 22, wherein
2 said aqueous solution or emulsion further contains from
3 0.2 to 15% by weight of said slurry of a low molecular
4 weight polyacrylate polymer.

1 24. A method in accordance with claim 23, wherein
2 said low molecular weight amine is selected from one or
3 more members of the group consisting of: ethoxylated
4 tallow amine, bis(2-hydroxyethyl) soyamine,

5 bis(2-hydroxyethyl) cocoamine, tributylamine,
6 N-benzylethanolamine, triethanolamine,
7 methyliminobispropylamine, hexamethylenetetramine,
8 diisopropylamine, 3,3'-iminobispropylamine,
9 diisobutylamine, 2-(2-aminoethoxy)ethanol,
10 diethanolamine, biuret, 1-methyl-2-pyrrolidone, aniline,
11 methylpyrrolidone, morpholine, ethanolamine,
12 hydroxylamine, ethylenediamine, triethylenetetramine,
13 diethylenetriamine dimethylamine, and methylamine.

1 25. A method in accordance with claim 24, wherein
2 said low molecular weight amine is selected from one or
3 more members of the group consisting of methylamine,
4 dimethylamine, hydroxylamine, 2-(2-aminoethoxy)ethanol,
5 aniline and morpholine.

1 26. A method in accordance with claim 25, wherein
2 said salt is that of an acid selected from one or more
3 members of the group consisting of hydrochloric acid,
4 sulfurous acid, sulfuric acid, phosphoric acid, formic
5 acid, acetic acid, hydroxyacetic acid, propionic acid,
6 oxalic acid and citric acid.

1 27. A method in accordance with claim 26, wherein
2 the acid component of said salt is a member of the group
3 consisting of hydrochloric acid, formic acid, acetic acid
4 and hydroxyacetic acid.

1 28. A method in accordance with claim 27, wherein
2 from 30 to 47% by weight of said slurry of said powdered
3 smectite are added to said solution or emulsion.

1 29. A method in accordance with claim 28, wherein
2 from 40 to 47% by weight of said slurry of said powdered
3 smectite are added to said solution or emulsion.

1 30. A method for shipping a swelling smectite clay
2 from a shipping point to a utilization point such as a
3 paper mill, and providing at the utilization point an
4 aqueous swelled smectite slurry; comprising the steps of
5 preparing at said shipping point, a high solids, low
6 viscosity shippable slurry comprising an aqueous solution
7 or dispersion of at least 0.2% by weight of the shippable
8 slurry of a salt of a low molecular weight amine, in
9 which is dispersed at least 10% by weight of a powdered
10 smectite; said salt being effective to prevent the said
11 smectite from swelling appreciably, whereby the slurry
12 can be shipped and stored without creating a gelling
13 problem, and the inhibiting effect of said salt on said
14 swelling of the smectite and gelling of said slurry being
15 reversible upon subsequent dilution with water; shipping
16 said slurry to the said utilization point; and activating
17 and swelling the smectite at the utilization point by
18 diluting the high solids slurry with fresh water.

1 31. A method in accordance with claim 30, wherein
2 said smectite is a sodium bentonite, which is present in
3 the high solids shippable slurry as from 10 to 47% by
4 weight of the slurry.

1 32. A method in accordance with claim 31, wherein
2 the dilution of the high solids slurry at the utilization
3 point brings said clay solids to the range of .01 to 10%.

1 33. A method in accordance with claim 31, wherein
2 said sodium bentonite is present in the range of from 30
3 to 47% by weight.

1 34. A method in accordance with claim 33, wherein
2 dilution of said slurry is effected by adding the slurry
3 to an aqueous cellulosic suspension which is being
4 employed in a paper making process.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US94/10770

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) : C04B 14/10, 33/04

US CL : 106/416,487, DIG 4; 501/145,148

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 106/416,487, DIG 4; 501/145,148 nad IPC(6): C04B 14/10, 33/04

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y,P	US, A, 5,266,538 (KNUDSON ET AL.) 30 NOVEMBER 1993 SEE COL. 2 LINES 9-60 AND THE CLAIMS.	1-34
Y	US, A, 3,298,849 (DOHMAN ET AL.) 17 JANUARY 1967 SEE COL. 1 LINE 15- COL. 2 LINE 65.	1-34
Y	US, A, 5,057,467 (CROFT) 15 OCTOBER 1991 SEE COL. 1 LINE 10- COL. 2 LINE 68.	1-34
Y	US, A, 3,961,979 (ABERCROMBIE, JR.) 08 JUNE 1976 SEE COL. 2 LINES 29-68	1-34
Y	US, A, 4,078,941 (BUNDY ET AL.) 14 MARCH 1978 SEE COL. 1 LINES 5-37 AND THE CLAIMS.	1-34

☒ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	*T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
A document defining the general state of the art which is not considered to be of particular relevance	*X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
E earlier document published on or after the international filing date	*Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*Z*	document member of the same patent family
O document referring to an oral disclosure, use, exhibition or other means		
P document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

09 DECEMBER 1994

Date of mailing of the international search report

06 JAN 1995

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

MARK L. BELL

Telephone No. (703) 308-3823

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US94/10770

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US, A, 5,015,334 (DERRICK) 14 MAY 1991 SEE COL. 2 LINE 32- COL. 3 LINE 65	1-34
Y	US, A, 4,017,324 (EGGERS) 12 APRIL 1977 SEE COL. 2 LINES 9-40.	1-34