



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2038931 C 2002/06/25

(11)(21) **2 038 931**

(12) **BREVET CANADIEN
CANADIAN PATENT**

(13) **C**

(86) Date de dépôt PCT/PCT Filing Date: 1990/08/06
(87) Date publication PCT/PCT Publication Date: 1991/02/21
(45) Date de délivrance/Issue Date: 2002/06/25
(85) Entrée phase nationale/National Entry: 1991/04/04
(86) N° demande PCT/PCT Application No.: EP 1990/001286
(87) N° publication PCT/PCT Publication No.: 1991/002025
(30) Priorité/Priority: 1989/08/07 (67691 A/89) IT

(51) Cl.Int.⁵/Int.Cl.⁵ C08L 3/02, C08L 23/08

(72) Inventeurs/Inventors:
Bastioli, Catia, IT;
Bellotti, Vittorio, IT;
Del Tredici, Gianfranco, IT

(73) Propriétaire/Owner:
Novamont S.p.A., IT

(74) Agent: MACRAE & CO.

(54) Titre : COMPOSITION POLYMERIQUE RENFERMANT DE L'AMIDON DESTRUCTURE ET UN COPOLYMER
D'ETHYLENE

(54) Title: POLYMER COMPOSITION INCLUDING DESTRUCTURED STARCH AND AN ETHYLENE COPOLYMER

(57) **Abrégé/Abstract:**

A polymer composition useful for the production of articles of biodegradable plastics material includes destructured starch and a copolymer selected from the group consisting of ethylene-vinyl acetate, ethylene-glycidyl acrylate, ethylene-methyl methacrylate, ethylene-maleic anhydride and possibly ethylene vinyl alcohol.





PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C08L 3/02, 23/08	A1	(11) International Publication Number: WO 91/02025 (43) International Publication Date: 21 February 1991 (21.02.91)
(21) International Application Number: PCT/EP90/01286 (22) International Filing Date: 6 August 1990 (06.08.90) (30) Priority data: 67691 A/89 7 August 1989 (07.08.89) IT (71) Applicant (for all designated States except US): BUTTERFLY S.R.L. [IT/IT]; Via XIII Giugno, 8, I-48100 Ravenna (IT). (72) Inventors; and (75) Inventors/Applicants (for US only) : BASTIOLI, Catia [IT/IT]; Via della Noce, 63, I-28100 Novara (IT). BELLOTTI, Vittorio [IT/IT]; Via Mora e Gibin, 9, I-28010 Fontaneto d'Agogna (IT). DEL TREDICI, Gianfranco [IT/IT]; Via Sempione, 31, I-21018 Sesto Calende (IT).		(74) Agents: RAMBELLI, Paolo et al.; Jacobacci-Casetta & Perani S.p.A., Via Alfieri, 17, I-10121 Torino (IT). (81) Designated States: AT (European patent), AU, BE (European patent), BR, CA, CH (European patent), DE (European patent)*, DK (European patent), ES (European patent), FI, FR (European patent), GB (European patent), HU, IT (European patent), JP, KP, LU (European patent), NL (European patent), NO, SE (European patent), SU, US. Published <i>With international search report.</i>
(54) Title: A POLYMER COMPOSITION INCLUDING DESTRUCTURED STARCH AND AN ETHYLENE COPOLYMER (57) Abstract A polymer composition useful for the production of articles of biodegradable plastics material includes destructured starch and a copolymer selected from the group consisting of ethylene-vinyl acetate, ethylene-glycidyl acrylate, ethylene-methyl methacrylate, ethylene-maleic anhydride and possibly ethylene vinyl alcohol.		

- 1 -

A polymer composition including destructured starch and an ethylene copolymer

The present invention relates to polymer compositions including starch and an ethylene copolymer useful for the production of articles of biodegradable plastics material and to a method for their preparation.

Compositions which can be formed into films and which are constituted by starch and an ethylene copolymer, particularly an ethylene-acrylic acid copolymer (EAA) are described in U.S. Patent No. 4,133,784. These compositions are transformed into flexible, water-resistant, heat sealable and biodegradable films by casting, simple extrusion or milling techniques. These processes are, however, slow and very expensive and, moreover, with certain starch contents necessary to achieve the desired mechanical properties, the degree of biodegradability and UV stability of the products are greatly compromised.

It has been proposed in U.S. Patent No. 4,337,181 that sufficient quantity of neutralising agent, such as ammonia or an amine, should be added to the starch-EAA copolymer composition to neutralise some or all of the acid groups in the EAA, and that the formulation thus obtained, with a moisture content between 2 and 10% should then be blow-moulded.

It has also been proposed in Ind. Eng. Chem. Res. 1987, 26, pp. 1659-1663 that urea and/or polyols should be added to the starch-EAA copolymer compositions in order to facilitate the preparation and improve the resulting films from a cost and qualitative point of

- 2 -

view. The effect of the presence of urea is to enable the crystalline structure of the starch to be destroyed by small quantities of water and hence to enable granules for filming to be produced directly from a composition with a water content of around 16% and also to avoid the need to premix the starch-EAA copolymer mixture with large quantities of water in a very complex mixer before the extrusion process.

Copending Canadian Application No. 2,017,654 describes compositions which can be formed into films with good mechanical properties and into moulded articles and which include a destructured starch and an ethylene-vinyl alcohol copolymer. In this case, the compositions are preferably produced by the mixing, in a heated extruder, of the ethylene-vinyl alcohol copolymer with a starch component constituted by a destructured starch compositions produced beforehand by the mixing of starch in an extruder with a high-boiling plasticizer and a destructuring agent such as, for example, urea.

The compositions thus obtained are suitable both for filming by extrusion and blowing and for the production of moulded articles.

Within the scope of the research carried out by the Applicant in relation to the production of biodegradable polymer compositions based on destructured starch, other ethylene copolymers have been identified as being compatible with the starch, thus making available new polymer compositions useful both for the formation of films and for the production of moulded arti-

JJ:in

2038931

- 3 -

cles.

The subject of the invention is constituted by a polymer composition including destructured starch and a copolymer selected from the group consisting of ethylene-vinyl acetate having a vinyl acetate molar content of from 5 to 90%, modified ethylene-vinyl acetate having from 5 to 90% of hydrolyzed acetate groups, ethylene-glycidyl acrylate, ethylene-methyl methacrylate, ethylene-maleic anhydride, and mixtures thereof.

Of these polymers, the above defined ethylene-vinyl acetate copolymer is preferred particularly for the production of compositions for films and particularly preferred are ethylene-vinyl acetate copolymers having a vinyl acetate molar content of from 12 to 80%. Copolymers of ethylene-vinyl acetate are available commercially. For example, the ELVAX (registered trade mark) copolymer can conveniently be used.

The other ethylene copolymers mentioned above, which, as a result of the tests carried out by the Applicant, have been found to be compatible with starch and therefore able to form starch and copolymer composites, may be considered in dependence on the specific properties desired for the biodegradable articles to be produced.

The term "starch" as used in the present description and in the claims covers in general all the starches of natural or vegetable origin composed essentially of amylose and amylopectin. They can be extracted from various plants, such as, for example, potatoes, rice, tapioca, maize and cereals such as rye, oats and

- 4 -

wheat. Maize starch is preferred. The term "starch" also covers modified starches whose acidity index has been reduced to between 3 and 6, as well as potato starch in which the type and concentration of the cations associated with the phosphate group have been modified. Starch ethoxylates, starch acetates, cationic starches, oxidised starches, cross-linked starches and the like may be used in the preparation of the compositions according to the invention.

10 In the composition according to the invention, destructured starch and the ethylene copolymer may be present in a ratio of from 1:9 to 9:1, preferably from 1:4 to 4:1.

15 The ethylene copolymers mentioned above may be used in mixtures with each other or, to advantage, may be mixed with an ethylene-acrylic acid (EAA) copolymer whose use in biodegradable starch compositions is described in Patent No. US-A-4,133,784, or with an ethylene-vinyl alcohol copolymer (EVOH) as described in copending Canadian Patent
20 Application No. 2,017,654.

The EAA copolymer, which may be present in the composition at concentrations of up to 25% by weight, is a water-dispersible copolymer produced by the copolymerization of a mixture comprising from 3 to 30%, preferably 20%, by weight of acrylic acid and correspondingly from 97 to 70%, preferably 80%, by weight of ethylene. Polyvinyl alcohol may also be used as the polymeric additive to the composition.

30 The preferred ethylene-vinyl alcohol copolymer has an ethylene content of from 10 to 90% by weight,

JJ:in

- 5 -

preferably from 10 to 40% by weight (15-50% mol), more preferably 30-45% mol, with a melt flow index (210°C, 2.16 Kg) of between 2 and 50, preferably between 6 and 20.

5 Further preferred features for the EVOH copolymer are as follows:

Intrinsic viscosity, $[\eta]$ 0.50-0.9
(in DMSO at 30°) preferably 0.65-0.80

10 Molecular weight distribution Mw/Mn 1.3-4
(GPC in tetrahydrofurane)

Melting point temperature < 180°C
..... preferably 160-170°C

Hydrolysis degree * 90-99.9%

15 * Basic hydrolysis and titration of the residual
base with acid.

The EVOH copolymer is preferably used at a concentration up to 40% wt with respect to the weight of the composition.

20 Particularly when it is desired to improve the toughness and elongation (breaking strain) properties, a preferred embodiment of the invention contemplates the use of a composition wherein the synthetic polymer portion consists of or comprises a blend of the above defined EVOH and EVA copolymers. It has been found
25 that the addition of EVA to blends based on starch and EVOH provides for a reduction of the Young's modulus and for a significant increase of the breaking strain and toughness properties of the material. However when the vinyl acetate content is below a value of about 15%
30 wt or 5% mol, the compatibility between the components

- 6 -

becomes too low and homogenous film cannot be obtained. On the other hand the nature of the starch does not seem to significantly influence the properties of the material.

In this embodiment the weight ratio between EVOH and EVA copolymers is preferably in the range of from 8:1 to 2:1.

The EVA copolymer in the composition according to the invention, is generally used at a concentration of from 3-40% wt, preferably 3-20% wt with respect to the weight of the composition.

The modified EVAs having hydrolised acetate groups, which may be defined as ethylene-vinyl acetate-vinyl alcohol terpolymers, when used in a blend of EVOH, EVA and starch provide for an increased compatibility of the components so that a higher modulus and a higher breaking strain are obtained.

Cross-linking agents, such as formaldehyde, paraformaldehyde, paraldehyde and epichlorohydrin may also be present. Additives for imparting specific properties to the articles for which the composition is intended may also be introduced into the composition. These additives include UV stabilizers, flame-proofing agents, fungicides, herbicide, antioxidants, fertilisers, opacifying agents, stabilisers, plasticizers, antiblocking agents, and lubricants.

The method of preparing the compositions according to the invention is carried out in an extruder at a temperature of between 80 and 180°C, under conditions such as to destructure the starch.

When the ethylene copolymer is EVA or a blend of EVA and EAA the temperature within the extruder is in the range of 80-140°C, preferably 90-120°C.

In order to encourage the destructuring of the starch, urea may to advantage be added to the composition

35

- 7 -

in quantities of up to 20% by weight of the weight of the starch component. Other destructuring agents include alkali metal of alkaline earth metal hydroxides. Ammonia may be added to the composition supplied to the extruder and its concentration is reduced to below 0.2% by weight as a result of the extrusion.

A high-boiling plasticizer, such as polyethylene glycol, ethylene glycol, propylene glycol, sorbitol, glycerine and mixtures thereof, may also be added to the composition in a quantity of from 0.05 to 100% by weight of the weight of the starch, preferably from 20 to 60% by weight.

The process of destructuring the starch in the extruder is preferably carried with the addition of water the concentration of which may reach values of up to 20% by weight, preferably up to 15%, of the total weight of the composition supplied. This value includes the intrinsic bound water content of the starch used and any water added as required. The water content is at any rate reduced to values below 6%, preferably below 4% by weight by degassing at the output of the extruder or in an intermediate degassing stage interposed between a mixing stage and a transportation and compression stage, as described in copending Canadian Application No. 2,028,130, or even by the drying of the granulate at 70°C for 8 hours after the extrusion.

If a mixture of ethylene copolymers and, in particular, a mixture of ethylene-vinyl acetate and ethylene acrylic acid is used, a blend is preferably produced beforehand by the mixing of the copolymers in an

- 8 -

extruder and the pelletising of the extrusion. In a second stage, the pellets are then mixed with starch with the addition of water and any of the destructuring and plasticizing agents mentioned above, in a heated extruder under conditions such as to destructure the starch.

Further methods for preparing the polymer compositions which are the subject of the invention are described in copending Canadian Patent Application No. 2,017,654 in the name of the Applicant.

Further advantages and characteristics of the invention will become clear from the following examples, provided purely by way of illustration where all concentrations are in % wt, unless otherwise indicated.

Example 1

A HAAKE REOMEX* Model 252 extruder with an L/D ratio of 19, a screw diameter of 19 mm and a compression ratio of 1:3 was supplied with a composition constituted by:

38.5% of the ethylene-vinyl acetate copolymer ELVAX 260 (registered trade mark, 28% wt vinyl acetate (11.2% mol)

38.5% of the Dow Chemical copolymer EAA 5981* con-

* Trade-mark

taining 20% of acrylic acid,
11.5% of urea,
3.8% of ammonia,
and 7.7% of water.

5 The extrusion temperature was approximately 100°C
and the speed of the screw approximately 60 rpm. 50
parts of the product thus obtained were mixed with 50
parts of the starch GLOBE 03401 Cerestar (registered
trade mark) and 10 parts of water, and the mixture was
10 extruded with the same extruder at a temperature of
between 90 and 110°C. The extrusion thus obtained was
formed into pellets with a water content of 4% and the
pellets were supplied to the same extruder with the use
of a film-blowing head, at a temperature of 100°C and a
15 screw rotation rate of 40 rmp. Rectangular test pieces
for tensile testing according to ASTM 882 were formed
from the films which were approximately 100 microns
thick.

The test pieces were conditioned at 23 ± 1°C and
20 at 55 ± 5% relative humidity for 24 hours. The mechani-
cal strength tests gave the following results expressed
as average values:

	Young's modulus	91 MPa
	breaking strain	93.8%
25	breaking stress	14.8 MPa

Example 2

The extruder described in Example 1 was supplied
with a composition comprising:

	76% of copolymer ELVAX - 260
30	14% of urea

- 10 -

10% of water
and was operated under the same conditions as described in
Example 1.

5 50 parts of the product thus obtained were mixed in an
extruder at 90°C and a screw rotation rate of 40 rpm with
50 parts of the starch GLOBE 03401 Cerestar (registered
trade mark) and 7 parts of water.

10 Test pieces of the film were made as described in
Example 1 and when subjected to mechanical strength tests
gave the following values:

Young's modulus	90 MPa
breaking strain	120%
breaking stress	7 MPa

Examples 3-22

15 In all the following examples, the components were
pre-mixed and then fed from a Licoarbo DC10* batcher to a
Haake Reomex extruder, model 252, with L/D ratio of 19,
screw diameter of 19 mm, and a compression ratio of 1:3,
with the screw revolving at 45 rpm.

20 The temperature profile in the extruder was as
follows:

-	feeding zone	30°C
-	first zone	90°C
-	second zone	variable as shown in Table
25		1 hereinafter
-	third zone	130°C
-	fourth zone	100°C.

30 The extruded material was formed into pellets, was
compression moulded in a heated press at temperatures of
from 110 and 140°C, to obtain films having the thickness

* Trade-mark

JJ:in

- 11 -

of about 300 microns which, after having been conditioned at 23°C and 55% relative humidity, were subjected to tensile testing according to ASTM 882.

TABLE 1

5	Temperature of the second zone of the extruder	
	Example	°C
	3-6	170
	7	140
	8	180
10	9	170
	10-14	140
	15-22	170

In the example the following materials were used:

	Starch	Globe 03401 produced by Cerestar
15	Starch-A	Snowflake* 3183 - Cerestar
	Starch-B	Pea starch with 96% wt amylose - Cerestar (not available on the market)
	Starch-C	Amisol* 05582 (oxydized) - Cerestar
	Starch-D	Amisol Q TAC 0596 (cationic starch) - 20 Cerestar
	EVOH-1	Ethylene-vinyl alcohol copolymer R-20, 40% mol ethylene - Solvay
	EVOH-2	Ethylene-vinyl alcohol copolymer obtained by 4 hydrolysis of Riblene* JV 1055, produced 25 by Enichem (28% wt vinyl acetate, 1.2% mol)
	EVOH-3	Ethylene-vinyl alcohol copolymer "L-6"* 29% mol ethylene - Solvay
	EAA-20	Ethylene-acrylic acid copolymer, 20% wt (8.8% mol) acrylic acid - Du Pont

30 * Trade-mark

JJ:in

2038931

- 12 -

EAA-9	Ethylene-acrylic acid copolymer 9% wt (3.7% mol) acrylic acid - Du Pont
EVA-1	Elvax 260 (28% wt (11.2% mol) vinyl acetate) - Du Pont
5 EVA-2	Elvax 550, 15% wt (5.3% mol) vinyl acetate - Du Pont
Modified EVA	Experimental product obtained by partial hydrolysis of EVA having 20% molar con- tent of ethylene, hydrolysis value of the final product 270
10	Plasticizer Glycerine containing 15% of a 30% wt water solution of urea or 15% wt of a 30% water solution of ammonia

The compositions shown in Tables 2-5 were prepared.

TABLE 2

Compositions containing starch-EVOH-EVA (% wt)

Example	Starch	EVOH-1	EVOH-2	EVOH-3	EVA-1	EVA-2	Plast.
20	3	40	40	-	-	-	20
	4	40	35	-	-	5	20
	5	40	30	-	-	10	20
	6	40	25	-	-	15	20
	7	40	-	30	-	10	20
	8	40	-	-	30	10	20
	9	40	30	-	-	10	20

- 13 -

TABLE 3

Compositions based on starch-EAA-EVA (wt %)

Example	Starch	EAA-9	EAA-20	EVA-1	EVA-2	Plast.
5	10	40	-	5	35	- 20
	11	40	-	10	30	- 20
	12	40	-	15	25	- 20
	13	40	10	-	30	- 20
	14	40	-	10	- 30	20

TABLE 4

10

Compositions based on modified starch-EVOH-EVA (% wt)

Example	Starch-A	Starch-B	Starch-C	Starch-D	EVOH-1	EVA-1	Plast.
15	15	40	-	-	-	30	10 20
	16	-	40	-	-	30	10 20
	17	-	-	40	-	30	10 20
	18	-	-	-	40	30	10 20

TABLE 5

Compositions based on starch-EVOH-EVA-modified EVA (%wt)

Example	Starch	EVOH-1	EVA	EVA mod.	Plast.
20	19	40	35	-	5 20
	20	40	25	-	15 20
	21	40	30	5	5 20
	22	40	25	10	5 20

25 The mechanical properties of the blends are shown in the following Table 6.

2038931

- 14 -

TABLE 6

Mechanical properties of the blends

	Example No.	Breaking stress MPa	Breaking strain %	Modules MPa	Notes
5	3	10	90	250	a
	4	7	200	60	a
	5	6	260	45	a
	6	5	350	30	a
	7	nd	nd	nd	a
	8	10	120	130	a
	9	nd	nd	nd	a,d
10	10	1.8	330	5	b
	11	1.9	300	8	b
	12	1.5	160	9	b
	13	nd	nd	nd	b,c
	14	nd	nd	nd	b,c
	15	8	210	65	a
	16	10	110	80	a
15	17	7	190	40	a
	18	8	90	35	a
	19	8	130	190	a
	20	7	175	170	a
	21	7	180	185	a
	22	6	245	130	a

- 20 a = urea in the plasticizer
 b = ammonia in the plasticizer
 c = unblended phases
 nd= not determined
 d = non uniform film

25 The films produced from the composition according to the invention are suitable for the production of packaging and mulching materials and also have satisfactory shear- and puncture-strength characteristics. The films are flexible, heat sealable and water-resistant.

-15-

THE EMBODIMENTS OF THE INVENTION IN WHICH AN EXCLUSIVE PROPERTY OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:

1. A polymer composition useful for the production of articles of biodegradable plastic material, said composition including destructured starch and a copolymer selected from the group consisting of ethylene-vinyl acetate having a vinyl acetate molar content of from 5 to 90%, modified ethylene-vinyl acetate having from 5 to 90% of hydrolyzed acetate groups, ethylene-glycidyl acrylate, ethylene-methyl methacrylate, ethylene-maleic anhydride and mixtures thereof.
2. A composition according to claim 1, in which the ethylene copolymer and the starch are present in a weight ratio of from 1:4 to 4:1.
3. A composition according to claim 1, wherein the ethylene-vinyl acetate copolymer has a vinyl acetate molar content of from 12 to 80%.
4. A composition according to claim 1, further including up to 25% by weight of ethylene-acrylic acid copolymer with respect to the total weight of the composition.
5. A composition according to claim 1, further including up to 40% by wt of an ethylene-vinyl alcohol copolymer with respect to the total weight of the composition.
6. A polymer composition useful for the production of articles of biodegradable plastic material, said composition including destructured starch and a first copolymer selected from the group consisting of ethylene-vinyl acetate having a vinyl acetate molar content of from 5 to 90%, modified ethylene-vinyl acetate having from 5 to 90% of hydrolyzed acetate groups, ethylene-glycidyl acrylate, ethylene-methyl methacrylate, ethylene-maleic anhydride and mixtures thereof

-16-

wherein said composition includes up to 40% by wt with respect to the total weight of the composition of a second copolymer which is ethylene-vinyl alcohol wherein the weight ratio of the second copolymer to the first copolymer is from
5 2:1 to 8:1.

7. A polymer composition useful for the production of articles of biodegradable plastic material, said composition including destructured starch and a first copolymer which is
10 ethylene-vinyl acetate having a vinyl acetate molar content of from 5 to 90%

wherein said composition includes up to 40% by wt with respect to the total weight of the composition of a second copolymer which is ethylene-vinyl alcohol wherein the weight
15 ratio of the second copolymer to the first copolymer is from 2:1 to 8:1.

8. A polymer composition useful for the production of articles of biodegradable plastic material, said composition
20 including destructured starch and a first copolymer which is a mixture of ethylene-vinyl acetate having a vinyl acetate molar content of from 5 to 90% and modified ethylene-vinyl acetate having from 5 to 90% of hydrolyzed acetate groups

25 wherein said composition includes up to 40% by wt with respect to the total weight of the composition of a second copolymer which is ethylene-vinyl alcohol.

9. A polymer composition useful for the production of
30 articles of biodegradable plastic material, said composition including:

destructured starch,
a high-boiling plasticizer, and
a copolymer portion comprising
35 a first copolymer which is a mixture of ethylene-

-17-

vinyl acetate having a vinyl acetate molar content of from 5 to 90% and modified ethylene-vinyl acetate having from 5 to 90% of hydrolyzed acetate groups, and

5 a second copolymer which is ethylene-vinyl alcohol wherein said copolymer portion of the composition comprises 40% by wt with respect to the total weight of the composition.

10. A composition according to claim 1, further including a
10 high-boiling plasticizer at a concentration of from 20 to 60% by weight of the weight of the starch component.

11. A composition according to claim 10, wherein the
15 high-boiling plasticizer is selected from a group consisting of glycerine, polyethylene glycol, ethylene glycol, propylene glycol, sorbitol and mixtures thereof.

12. A polymer composition useful for the production of articles of biodegradable plastic material, said composition
20 including destructured starch and a copolymer selected from the group consisting of ethylene-vinyl acetate having a vinyl acetate molar content of from 5 to 90%, modified ethylene-vinyl acetate having from 5 to 90% of hydrolyzed acetate groups, ethylene-glycidyl acrylate, ethylene-methyl
25 methacrylate, ethylene-maleic anhydride and mixtures thereof, further including urea in an amount up to 20% by weight of the weight of the starch component in said composition.

13. A composition according to claim 1, including water at
30 a concentration of no greater than 6% by weight of the total weight of the composition.

14. A polymer composition useful for the production of articles of biodegradable plastic material, said composition
35 including destructured starch and a first copolymer selected

-18-

from the group consisting of ethylene-vinyl acetate having a vinyl acetate molar content of from 5 to 90%, modified ethylene-vinyl acetate having from 5 to 90% of hydrolyzed acetate groups, ethylene-glycidyl acrylate, ethylene-methyl methacrylate, ethylene-maleic anhydride and mixtures thereof, which further includes a second copolymer which is ethylene-acrylic acid in an amount up to 25% with respect to the total weight of the composition.

15. A polymer composition useful for the production of articles of biodegradable plastic material, said composition including destructured starch and a first copolymer which is ethylene-vinyl acetate having a vinyl acetate molar content of from 5 to 90%, which further includes a second copolymer which is ethylene-acrylic acid in an amount up to 25% with respect to the total weight of the composition.

16. Articles in the form of films and moulded articles constituted by a composition according to claim 1.

17. A method for the preparation of a polymer composition useful for the production of articles of biodegradable plastics material, comprising the steps of:

a. Mixing a composition including starch, a copolymer selected from the group consisting of ethylene-vinyl acetate, having a vinyl acetate molar content of from 5 to 90%, modified ethylene-vinyl acetate having from 5 to 90% of hydrolyzed acetate groups, ethylene-glycidyl acrylate, ethylene-methyl methacrylate, ethylene-maleic anhydride and mixtures thereof, water, and optionally urea, ammonia or a mixture thereof in an extruder heated to a temperature of between 80° and 180°C, and

b. bringing the water content to below 6% by weight, and any ammonia content to below 0.2% by weight.

-19-

18. A method according to claim 17, in which the composition supplied to the extruder includes a quantity of water of up to 20% by weight of the total weight of the composition.

5 19. A method for the preparation of a polymer composition useful for the production of articles of biodegradable plastics material, comprising the steps of:

10 a. mixing a composition including starch, a copolymer selected from the group consisting of ethylene-vinyl acetate, having a vinyl acetate molar content of from 5 to 90%, modified ethylene-vinyl acetate having from 5 to 90% of hydrolyzed acetate groups, ethylene-glycidyl acrylate, ethylene-methyl methacrylate, ethylene-maleic anhydride and
15 mixtures thereof, water, and optionally urea, ammonia or a mixture thereof, in an extruder heated to a temperature of between 80° and 180°C, and

b. bringing the water content to below 6% by weight, and any ammonia content to below 0.2% by weight, wherein the
20 composition fed to the extruder further includes up to 40% wt of an ethylene-vinyl alcohol copolymer with respect to the total weight of the composition.

20. A method according to claim 19, wherein the ethylene
25 copolymer portion of the composition consists of ethylene-vinyl alcohol and ethylene-vinyl acetate in a weight ratio of from 2:1 and 8:1.

21. A method according to claim 19, wherein the ethylene
30 copolymer portion of the composition consists of ethylene-vinyl alcohol, ethylene-vinyl acetate and modified ethylene-vinyl acetate.

22. A method according to claim 17, wherein the ethylene
35 copolymer and the starch in the composition are present in

-20-

a weight ratio of from 1:9 to 9:1.

23. A method according to claim 22, wherein the ethylene copolymer and the starch in the composition are present in
5 a weight ratio of from 1:4 to 4:1.

24. A method for the preparation of a polymer composition useful for the production of articles of biodegradable plastics material, comprising the steps of:

10 a. mixing a composition including starch, a copolymer selected from the group consisting of ethylene-vinyl acetate, having a vinyl acetate molar content of from 5 to 90%, modified ethylene-vinyl acetate having from 5 to 90% of hydrolyzed acetate groups, ethylene-glycidyl acrylate,
15 ethylene-methyl methacrylate, ethylene-maleic anhydride and mixtures thereof, water, and a starch destructuring agent selected from the group consisting of urea, alkali metal hydroxides, alkaline earth metal hydroxides and ammonia, in an extruder heated to a temperature of between 80° and 180°C,
20 and

b. bringing the water content to below 6% by weight, and any ammonia content to below 0.2% by weight.

25. A method according to claim 24, wherein said urea is
25 present in said composition in a quantity of up to 20% by weight, based on the weight of said starch.

26. A method according to claim 17, in which said composition supplied to said extruder further includes a high boiling
30 plasticizer in an amount from 0.05 to 100% by weight of the weight of the starch present in said composition.

27. A method according to claim 26, wherein said plasticizer is selected from the group consisting of polyethylene glycol,
35 ethylene glycol, propylene glycol, sorbitol and glycerine.