



US010784371B2

(12) **United States Patent**
Gluschenkov et al.

(10) **Patent No.:** **US 10,784,371 B2**
(45) **Date of Patent:** ***Sep. 22, 2020**

(54) **SELF ALIGNED TOP EXTENSION FORMATION FOR VERTICAL TRANSISTORS**

(71) Applicant: **INTERNATIONAL BUSINESS MACHINES CORPORATION**, Armonk, NY (US)

(72) Inventors: **Oleg Gluschenkov**, Tannersville, NY (US); **Sanjay C. Mehta**, Niskayuna, NY (US); **Shogo Mochizuki**, Clifton Park, NY (US); **Alexander Reznicek**, Troy, NY (US)

(73) Assignee: **INTERNATIONAL BUSINESS MACHINES CORPORATION**, Armonk, NY (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **16/555,187**

(22) Filed: **Aug. 29, 2019**

(65) **Prior Publication Data**
US 2019/0386137 A1 Dec. 19, 2019

Related U.S. Application Data

(60) Continuation of application No. 16/043,637, filed on Jul. 24, 2018, which is a continuation of application No. 15/626,680, filed on Jun. 19, 2017, now Pat. No. 10,079,299, which is a division of application No. 15/332,181, filed on Oct. 24, 2016, now Pat. No. 9,748,382.

(51) **Int. Cl.**
H01L 31/072 (2012.01)
H01L 29/78 (2006.01)
(Continued)

(52) **U.S. Cl.**
CPC **H01L 29/7827** (2013.01); **H01L 21/0257** (2013.01); **H01L 21/26506** (2013.01);
(Continued)

(58) **Field of Classification Search**
CPC H01L 21/0257; H01L 21/26506; H01L 29/7827; H01L 29/0847; H01L 29/1037
See application file for complete search history.

(56) **References Cited**
U.S. PATENT DOCUMENTS

9,018,055 B2 4/2015 Currie
9,159,812 B1 10/2015 Hsiao et al.
(Continued)

FOREIGN PATENT DOCUMENTS

WO 2015147866 A1 10/2015

OTHER PUBLICATIONS


Gluschenkov et al., U.S. Appl. No. 16/043,637.*
List of IBM Patents or Patent Applications Treated as Related dated Aug. 29, 2019, 2 pages.

Primary Examiner — Samuel A Gebremariam
(74) *Attorney, Agent, or Firm* — Tutunjian & Bitetto, P.C.; Daniel Morris

(57) **ABSTRACT**

A method of forming a semiconductor device that includes providing a vertically orientated channel region; and converting a portion of an exposed source/drain contact surface of the vertically orientated channel region into an amorphous crystalline structure. The amorphous crystalline structure is from the vertically orientated channel region. An in-situ doped extension region is epitaxially formed on an exposed surface of the vertically orientated channel region. A source/drain region is epitaxially formed on the in-situ doped extension region.

20 Claims, 5 Drawing Sheets



- (51) **Int. Cl.**
H01L 29/66 (2006.01)
H01L 21/265 (2006.01)
H01L 21/306 (2006.01)
H01L 21/02 (2006.01)
H01L 29/08 (2006.01)
H01L 29/10 (2006.01)
H01L 29/165 (2006.01)

- (52) **U.S. Cl.**
 CPC *H01L 21/30604* (2013.01); *H01L 29/0847*
 (2013.01); *H01L 29/1037* (2013.01); *H01L*
29/66666 (2013.01); *H01L 21/0262* (2013.01);
H01L 21/02532 (2013.01); *H01L 21/02636*
 (2013.01); *H01L 29/165* (2013.01)

(56) **References Cited**

U.S. PATENT DOCUMENTS

9,263,580	B2	2/2016	Jacob et al.	
9,324,713	B1	4/2016	Yu et al.	
9,337,306	B2	5/2016	Peng et al.	
9,362,285	B2	6/2016	Basker et al.	
9,397,200	B2	7/2016	Qi	
2006/0197125	A1	9/2006	Langdo et al.	
2011/0024794	A1*	2/2011	Ko	<i>H01L 29/66795</i> 257/190
2013/0248942	A1	9/2013	Okano	
2014/0021485	A1*	1/2014	Cho	<i>H01L 29/1054</i> 257/77
2015/0279975	A1	10/2015	Hsiao et al.	
2016/0064387	A1	3/2016	Jeong et al.	
2016/0163826	A1	6/2016	Cheng et al.	
2016/0190251	A1	6/2016	Feng et al.	

* cited by examiner




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5

SELF ALIGNED TOP EXTENSION FORMATION FOR VERTICAL TRANSISTORS

BACKGROUND

Technical Field

The present invention generally relates to vertically orientated semiconductor devices, and more particularly to vertical fin field effect transistors (V-FinFETs).

Description of the Related Art

The dimensions of semiconductor field effect transistors (FETs) have been steadily shrinking, as scaling to smaller dimensions leads to continuing device performance improvements. Planar FET devices typically have a conducting gate electrode positioned above a semiconducting channel, and electrically isolated from the channel by a thin layer of gate oxide. Current through the channel is controlled by applying voltage to the conducting gate. With conventional planar FET scaling reaching fundamental limits, the semiconductor industry is looking at more unconventional geometries that will facilitate continued device performance improvements. One such class of device is a fin field effect transistor (FinFET).

SUMMARY

In one embodiment, a method of forming a semiconductor device is provided that includes providing a vertically orientated channel region; and converting a portion of an exposed source/drain contact end of the vertically orientated channel region into an amorphous crystalline structure. A remainder of the vertically oriented channel region has a non-amorphous crystal structure. The amorphous crystalline structure is removed selectively to the remainder of the vertically oriented channel region that has a non-amorphous crystal structure. An in-situ doped extension region is epitaxially formed on an exposed surface of the vertically orientated channel region. A source/drain region is epitaxially formed on the in-situ doped extension region.

In another embodiment, the method of forming the semiconductor device includes providing a vertically orientated channel region to a first source/drain region; and forming a gate structure onto the vertically orientated channel. An exposed source/drain contact surface is present on a side of the vertically orientated channel region opposite the first source/drain region. The exposed source/drain contact surface extends through a spacer dielectric layer. A portion of the exposed source/drain contact surface is converted into an amorphous crystalline structure. A remainder of the vertically oriented channel region has a non-amorphous crystal structure. The amorphous crystalline structure is removed from the vertically orientated channel region. The method continues with epitaxially forming an in-situ doped extension region on an exposed surface of the vertically orientated channel region, and epitaxially forming a second source/drain region on the in-situ doped extension region.

In another aspect of the disclosure, a semiconductor device is provided that includes a first source/drain region on a supporting substrate; and a vertically orientated channel region atop the first source/drain region. An extension of the first source/drain region is present in a first end of the vertically orientated channel region including diffused dopant extending from the first source/drain region. An extension

of the first source/drain region is present at a first end of the vertically orientated channel region that includes a portion of the doped semiconductor material that provided the first source/drain region. The epitaxial uniformly doped extension region layer is a separate layer from the vertically orientated channel region and the second source/drain region.

These and other features and advantages will become apparent from the following detailed description of illustrative embodiments thereof, which is to be read in connection with the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

The following description will provide details of preferred embodiments with reference to the following figures wherein:

FIG. 1 is a side cross-sectional view depicting a structure including a vertically orientated channel region atop a first source/drain region that is present on a supporting substrate, in which a gate structure is present around the vertically orientated channel region, and a dielectric cap is present on upper most surface of the vertically oriented channel region that is opposite the side of the vertically orientated channel region that is in direct contact with the first source/drain region.

FIG. 2 is a side cross-sectional view depicting converting a portion of an exposed source/drain contact end of the vertically orientated channel region into an amorphous crystalline structure, in accordance with one embodiment of the present disclosure.

FIG. 3 is a side cross-sectional view depicting removing the amorphous crystalline structure selectively to the remainder of the vertically oriented channel region that has a non-amorphous crystal structure, in accordance with one embodiment of the present disclosure.

FIG. 4 is a side cross-sectional view depicting one embodiment of an in-situ doped extension region layer being epitaxially formed on an exposed surface of the vertically orientated channel region.

FIG. 5 is a side cross-sectional view depicting epitaxially forming a second source/drain region on the in-situ doped extension region, in accordance with one embodiment of the present disclosure.

DETAILED DESCRIPTION

Detailed embodiments of the claimed structures and methods are disclosed herein; however, it is to be understood that the disclosed embodiments are merely illustrative of the claimed structures and methods that may be embodied in various forms. In addition, each of the examples given in connection with the various embodiments is intended to be illustrative, and not restrictive. Further, the figures are not necessarily to scale, some features may be exaggerated to show details of particular components. Therefore, specific structural and functional details disclosed herein are not to be interpreted as limiting, but merely as a representative basis for teaching one skilled in the art to variously employ the methods and structures of the present disclosure. For purposes of the description hereinafter, the terms "upper", "lower", "right", "left", "vertical", "horizontal", "top", "bottom", and derivatives thereof shall relate to the embodiments of the disclosure, as it is oriented in the drawing figures. The terms "positioned on" means that a first element, such as a first structure, is present on a second element, such as a second structure, wherein intervening

elements, such as an interface structure, e.g. interface layer, may be present between the first element and the second element. The term “direct contact” means that a first element, such as a first structure, and a second element, such as a second structure, are connected without any intermediary conducting, insulating or semiconductor layers at the interface of the two elements.

In some embodiments, the methods and structures disclosed herein form a FinFET. A field effect transistor (FET) is a semiconductor device in which output current, i.e., source-drain current, is controlled by the voltage applied to a gate structure to the semiconductor device. A field effect transistor has three terminals, i.e., gate structure, source region and drain region. As used herein, a “fin structure” refers to a semiconductor material, which is employed as the body of a semiconductor device, in which the gate structure is positioned around the fin structure such that charge flows down the channel of the fin structure. A FinFET is a semiconductor device that positions the channel region of the semiconductor device in a fin structure. The source and drain regions of the fin structure are the portions of the fin structure that are on opposing sides of the channel region of the fin structure.

A FinFET semiconductor device has the drain, fin channel, and source device components arranged perpendicular to the plane of the substrate surface, which is referred to as a vertical stack (also referred to as vertical FinFET). In some embodiments, the methods and structures disclosed herein apply to vertical FinFETs, which are also referred to as a vertically stacked FinFET. A vertically stacked FinFET can have a longer gate length (i.e., height) and larger dielectric spacer than a horizontal (i.e., having the drain, fin channel, and source device components arranged parallel with the plane of the substrate surface) FinFET having comparable contact gate pitch.

It has been determined that forming the top contact, e.g., source/drain region, of a vertically orientated transistor, as well as the extension region, can be challenging, as alignment of these structures with respect to the gate structure can be dependent upon lithography and etch processes that can be reaching their limits with increased scaling of devices. In some embodiments, the methods and structures disclosed herein can provide a method for controlling the extension region placement in vertical field effect transistor (VFET) and vertical tunnel junctions. In some embodiments, the methods and structures disclosed herein provide for precise placement of the extension region that is present overlying the supporting substrate by converting a portion of a vertically orientated channel region into an amorphous semiconductor material and employing a selective etch process that removes an amorphous semiconductor material selectively to a non-amorphous semiconductor material, which is followed by an epitaxial in-situ growth process for forming the extension region junction. Further details of the methods and structures of the present disclosure are now provided with reference to FIGS. 1-5.

FIG. 1 depicts one embodiment of a partial vertical transistor, i.e., vertical FinFET, which includes a vertically orientated channel that is positioned within a fin structure 10 composed of semiconductor material. The vertically orientated channel region that is present in the fin structure 10 is atop a first source/drain region 5 that is present overlying a supporting substrate 1. In some embodiments, a gate structure 15, 20 is present around the vertically orientated channel region that is provided by the fin structure 10. The gate structure 15, 20 may include at least one gate dielectric 15,

and at least one gate conductor 20. A first dielectric spacer 30 is present between the gate structure 15, 20 and the first source/drain region 5.

In some embodiments, a dielectric cap 25 (also referred to as a hardmask) is present on upper most surface of the vertically oriented channel region that is positioned with the fin structure 10. The dielectric cap 25 is present on the end of the fin structure 10 that is opposite the side of the fin structure 10 that is in direct contact with the first source/drain region 5. The dielectric cap 25 is present atop the fin structure 10 and has an upper surface that is coplanar with a dielectric stack of a second dielectric spacer 35 and an interlevel dielectric 40. The structure depicted in FIG. 1 may also include a punch through stopper (PTS) region 2 that is present between the first source/drain region 5 and the supporting substrate 1.

In some embodiments, the supporting substrate 1 is composed of a type I-V semiconductor material. By “type IV semiconductor” it is meant that the semiconductor material includes at least one element from Group IVA (i.e., Group 14) of the Periodic Table of Elements. Examples of type IV semiconductor materials that are suitable for the supporting substrate 5 include silicon (Si), germanium (Ge), silicon germanium (SiGe), silicon doped with carbon (Si:C), silicon germanium doped with carbon (SiGe:C) and a combination thereof. In other embodiments, the supporting substrate 1 may be a III-V semiconductor material or a type II/VI semiconductor material. By “III-V semiconductor material” it is meant that the semiconductor material includes at least one element from Group IIIA (i.e., Group 13) of the Periodic Table of Elements and at least one element from Group VA (i.e., Group 15) of the Periodic Table of Elements. Examples of compound semiconductor materials that are suitable for the supporting substrate 5 include at least one of aluminum antimonide (AlSb), aluminum arsenide (AlAs), aluminum nitride (AlN), aluminum phosphide (AlP), gallium arsenide (GaAs), gallium phosphide (GaP), indium antimonide (InSb), indium arsenic (InAs), indium nitride (InN), indium phosphide (InP), aluminum gallium arsenide (AlGaAs), indium gallium phosphide (InGaP), aluminum indium arsenic (AlInAs), aluminum indium antimonide (AlInSb), gallium arsenide nitride (GaAsN), gallium arsenide antimonide (GaAsSb), aluminum gallium nitride (AlGaN), aluminum gallium phosphide (AlGaP), indium gallium nitride (InGaN), indium arsenide antimonide (InAsSb), indium gallium antimonide (InGaSb), aluminum gallium indium phosphide (AlGaInP), aluminum gallium arsenide phosphide (AlGaAsP), indium gallium arsenide phosphide (InGaAsP), indium arsenide antimonide phosphide (InArSbP), aluminum indium arsenide phosphide (AlInAsP), aluminum gallium arsenide nitride (AlGaAsN), indium gallium arsenide nitride (InGaAsN), indium aluminum arsenide nitride (InAlAsN), gallium arsenide antimonide nitride (GaAsSbN), gallium indium nitride arsenide aluminum antimonide (GaInNAsSb), gallium indium arsenide antimonide phosphide (GaInAsSbP), and combinations thereof. In an embodiment, the supporting substrate 1 is a single crystal silicon wafer.

The punch-through stopper (PTS) region 2 can reduce the incidence of leakage based performance degradation in FinFETs. The punch-through stopper (PTS) 2 improves FinFET characteristics. The dopant for forming the punch-through stop (PTS) region 2 may be an n-type or p-type dopant that has an opposite conductivity type as the dopant that determined the conductivity type of the FinFET. The term “conductivity type” denotes whether a region is doped to an n-type or p-type conductivity. For example, the punch-through stop (PTS) region dopant may be an n-type or p-type

dopant that has an opposite conductivity type as the dopant that dictates the conductivity type of the source and drain region of the FinFET. The punch-through stopper region 2 may be forming in an upper surface of the supporting substrate 1 by ion implantation. In other embodiments, the punch-through stopper region 2 is formed by epitaxially forming an in-situ doped semiconductor material atop the supporting substrate 1. Although the supplied figures depict the presence of the PST region, the PST region 2 is optional, and may be omitted.

The first source/drain region 5 is present atop the PST region 2. The first source/drain region 5 may be composed of a type IV or type III-V semiconductor. The above examples of semiconductor materials that are suitable for providing the supporting substrate 1, are suitable for providing examples of materials that can be used for the first source/drain region 5. In some embodiments, the first source/drain region 5 provides the source region of the device, and the later formed second source/drain region provides the drain region of the device. In some other embodiments, the first source/drain region 5 provides the drain region of the device and the later formed second source/drain region provides the source region of the device. The first source/drain region 5 is typically doped to a conductivity type that provides the conductivity type of the semiconductor device. For example, if the first source/drain region 5 is doped to an n-type conductivity, the semiconductor device is an n-type device, e.g., an n-type vertical FinFET. For example, if the first source/drain region 5 is doped to a p-type conductivity, the semiconductor device is a p-type device, e.g., a p-type vertical FinFET.

The first source/drain region 5 may be provided by an upper surface of the supporting substrate 1 that is doped to the required conductivity type using ion implantation. In other embodiments, the first source/drain region 5 may be composed of a semiconductor material that is deposited atop the PST region 2 (when present) or the supporting substrate. When the first source/drain region 5 is composed of a deposited material, the semiconductor material that provides the first source/drain region 5 may be epitaxially formed, i.e., formed by an epitaxial growth and/or deposition process. The terms "epitaxial growth and/or deposition" means the growth of a semiconductor material on a deposition surface of a semiconductor material, in which the semiconductor material being grown has substantially the same crystalline characteristics as the semiconductor material of the deposition surface. The term "epitaxial semiconductor material" denotes a material that is formed using epitaxial growth. In some embodiments, when the chemical reactants are controlled and the system parameters set correctly, the depositing atoms arrive at the deposition surface with sufficient energy to move around on the surface and orient themselves to the crystal arrangement of the atoms of the deposition surface. Thus, in some examples, an epitaxial film deposited on a {100} crystal surface will take on a {100} orientation. The epitaxial deposition process may employ a chemical vapor deposition apparatus, e.g., plasma enhanced chemical vapor deposition (PECVD), metal organic chemical vapor deposition (MOCVD). In the embodiments, in which the first source/drain region 5 is composed of an epitaxially formed silicon containing material, the silicon gas source for epitaxial deposition may be selected from the group consisting of Silane (SiH₄), disilane (Si₂H₆), or higher order silanes, hexachlorodisilane (Si₂Cl₆), tetrachlorosilane (SiCl₄), dichlorosilane (Cl₂SiH₂), trichlorosilane (Cl₃SiH), and combinations thereof.

To provide the appropriate conductivity type of the first source/drain region 5, the semiconductor material that provides the source/drain region may be doped with an n-type or p-type dopant. As used herein, "p-type" refers to the addition of impurities to an intrinsic semiconductor that creates deficiencies of valence electrons. In a type IV semiconductor material, such as silicon and germanium, examples of p-type dopants, i.e., impurities, include but are not limited to: boron, aluminum, gallium and indium. As used herein, "n-type" refers to the addition of impurities that contributes free electrons to an intrinsic semiconductor. In a type IV semiconductor material, such as silicon or germanium, examples of n-type dopants, i.e., impurities, include but are not limited to antimony, arsenic and phosphorous. In some embodiments, the dopant that dictates the conductivity type of the first source/drain region is introduced in-situ. By "in-situ" it is meant that the dopant that dictates the conductivity type of the semiconductor material that provides the first source/drain region 5 is introduced during the process step, e.g., epitaxial deposition. Alternatively, the dopant that provides the conductivity type of the first source/drain region 5 is introduced by ion implantation. The dopant for the epitaxial semiconductor material that dictates the conductivity type of the first source/drain region is typically present in a concentration ranging from 2×10^{20} atoms/cm³ to 2×10^{21} atoms/cm³.

The fin structure 10 is present in direct contact with the first source/drain region 5. The fin structure 10 may be composed of a type IV or type III-V semiconductor. The above examples of semiconductor materials that are suitable for providing the supporting substrate 1, are suitable for providing examples of materials that can be used for the fin structure 10. The fin structure 10 may be formed using an epitaxial growth process atop the semiconductor material layer that provides the first source/drain region 5. In some embodiments, when the first source/drain region 5 is composed of a crystalline semiconductor, such as a single crystal semiconductor, e.g., monocrystalline silicon (c-Si), the epitaxially formed semiconductor material layer for providing the fin structure 10 will also be composed of monocrystalline silicon.

In some embodiments, a blanket deposition is first conducted, in which the blanket deposited material layer is patterned and etched to provide the fin structure 10. In some embodiments, the etch process for forming the fin structure 10, also etches a portion of the semiconductor material layer that provides the first source/drain region 5. This can provide a pedestal of semiconductor material from the first source/drain region 5 having a width dimension equal to the width of the fin structure 5.

The pattern and etch processes for forming the fin structure 5 may employ a hard mask, which can provide the dielectric cap 25. More specifically, after forming a blanket layer of semiconductor material for the fin structure 5 atop the first source/drain region 5, a dielectric material layer may be deposited for forming the hard mask, i.e., dielectric cap 25. The dielectric material layer may then be patterned using photolithography, e.g., by forming a photoresist mask, and etched using an anisotropic etch process, such as reactive ion etch (RIE). Following patterning of the dielectric material layer for forming the hard mask, i.e., dielectric cap 25, the epitaxial semiconductor material, e.g., crystalline semiconductor material, may be etched to provide the fin structure 10. The etch process for forming the fin structure 10 may be an anisotropic etch, such as reactive ion etch (RIE).

It is noted that the above subtractive method for defining the geometry of the fin structure 10 is only one example of

a method for forming the fin structure **10**. In another example, a dielectric material layer may be deposited first source/drain region **5**. The dielectric material layer may be a dielectric material, such as silicon nitride, that can be deposited using chemical vapor deposition (CVD), such as plasma enhanced chemical vapor deposition (PECVD). A trench may be formed in the dielectric material layer using etch processes, such as reactive ion etch (RIE), wherein the base of the trench exposes a surface of the first source/drain region **5** to provide an epitaxial growth site. The fin structure **10** is then epitaxially formed extending from the epitaxial growth site at the bottom of the trench provided by the first source/drain region **5**, in which the epitaxial semiconductor material fills the trench. The dielectric material layer that provided the trench dictating the geometry for the fin structure **10** may then be removed, e.g., by selective etching.

Each of the fin structures **10** may have a height ranging from 5 nm to 200 nm. In another embodiment, each of the fin structures **10** has a height ranging from 10 nm to 100 nm. In one example, each of the fin structures **10** has a height ranging from 20 nm to 50 nm. Each of the plurality of fin structures **10** may have a width of less than 20 nm. In another embodiment, each of the fin structures **10** has a width ranging from 3 nm to 8 nm.

Still referring to FIG. 1, following formation of the fin structure **10**, the first dielectric spacer **30** may be formed. The first dielectric spacer **30** may be composed of an oxide, nitride or oxynitride material. In some embodiments, the first dielectric spacer **20** is composed of silicon nitride formed using chemical vapor deposition (CVD), e.g., plasma enhanced chemical vapor deposition (PECVD).

In some embodiments, the first dielectric spacer **30** may be composed of a low-k dielectric material. The term "low-k" denotes a dielectric material having a dielectric constant equal to the dielectric constant of silicon oxide (SiO_2) or less, i.e., less than 3.9. In one embodiment, the low-k dielectric material has a dielectric constant ranging from 1.75 to 3.5. Examples of materials suitable for the low-k dielectric material include diamond like carbon (DLC), organosilicate glass (OSG), fluorine doped silicon dioxide, carbon doped silicon dioxide, porous silicon dioxide, porous carbon doped silicon dioxide, spin-on organic polymeric dielectrics (e.g., SILK™), spin-on silicone based polymeric dielectric (e.g., hydrogen silsesquioxane (HSQ) and methylsilsesquioxane (MSQ)), and combinations thereof. The low-k spacer material may be deposited using at least one of spin on deposition, chemical vapor deposition (CVD), plasma-assisted CVD, evaporation and chemical solution deposition.

Referring to FIG. 1, in some embodiments, during patterning of the fin structure **10**, a portion of the first source/drain region **5** is etched, in which a pedestal portion of the first source/drain region **5** has a same width as the fin structure **10**. The overlap of the pedestal portion of the first source/drain region **5** and the first dielectric spacer **20** provides an extension region of n-type or p-type dopant that extends from the first source/drain region **5** towards the vertically orientated channel region that is positioned within the fin structure **10**. It is noted that the degree of overlap is exaggerated in the supplied figures. Typically, the fin structures **10** are formed using SIT processing. In some embodiments, the source/drain epitaxial is grown at the bottom of the fin structures **10** and between the fin structures **10** at the bottom. In which the source/drain epitaxial material is underlying the fin structures **10**. The epitaxial material for the source/drain regions is between the fins at the bottom. Thereafter, dopant from the epitaxial material is diffused

into the bottom portion of the fin structures **10** forming the bottom extension region. As noted, the height of the extension region has been exaggerated for ease of depiction, and the height of the extension is not this high in the device.

Following formation of the first dielectric spacer **30**, the gate structure **15, 20** can be formed around the fin structure **10**. The gate structure **15, 20** includes at least one gate dielectric **15** and at least one gate conductor **20**. The gate dielectric **15** of the gate structure **15, 20** is first formed on the channel portion of the fin structure **10**. Typically, the gate dielectric **15** is formed using a conformal deposition process. The gate dielectric **15** may be composed of any dielectric material, such as an oxide, nitride or oxynitride material. In some embodiments, the gate dielectric is a high-k dielectric material. As used herein, "high-k" denotes a dielectric material featuring a dielectric constant (k) higher than the dielectric constant of SiO_2 at room temperature. For example, the least one gate dielectric layer **15** may be composed of a high-k oxide such as, for example, HfO_2 , ZrO_2 , Al_2O_3 , TiO_2 , La_2O_3 , SrTiO_3 , LaAlO_3 , Y_2O_3 and mixtures thereof. Other examples of high-k dielectric materials for the at least one gate dielectric **15** include hafnium silicate, hafnium silicon oxynitride or combinations thereof.

To provide the conformal layer, the gate dielectric **15** may be deposited using atomic layer deposition (ALD). In other embodiments, the gate dielectric **15** may be deposited using chemical vapor deposition methods, such as plasma enhanced chemical vapor deposition (PECVD). In one embodiment, the thickness of the at least one gate dielectric layer **15** is greater than 0.8 nm. More typically, the at least one gate dielectric layer **15** has a thickness ranging from about 1.0 nm to about 6.0 nm. In some embodiments, conformal deposition of the gate dielectric **15** produces a vertical portion on the channel portion of the fin structure **10**, and a horizontal portion that is present on the upper surfaces of the first dielectric spacer **30**.

Following formation of the gate dielectric **15**, a work function metal (not shown) may be deposited. The work function metal (not shown) may be selected to provide a p-type work function metal layer and an n-type work function metal layer. In one embodiment, the p-type work function metal layer is composed of titanium nitride (TiN). The p-type work function metal layer may also be composed of TiAlN, Ru, Pt, Mo, Co and alloys and combinations thereof. In one embodiment, the n-type work function metal layer is composed of at least one of TiAl, TaN, TiN, HfN, HfSi, or combinations thereof. It is noted that the work function metal is optional and may be omitted.

The gate conductor **20** may be blanket deposited over the work function metal (when present), as well as over the gate dielectric **15**, or directly on the gate dielectric **15** when the work function metal is not present. In various embodiments, the gate conductor **20** is a metal, where the metal may be tungsten (W), tungsten nitride (WN) or combinations thereof. In one or more embodiments, the gate conductor **20** is tungsten (W). The gate conductor **20** may be deposited by CVD or PECVD or PVD.

FIG. 1 further depicts recessing the gate structure **15, 20** and forming a second dielectric spacer **35**. Recessing the gate structure **15, 20** may begin with recessing the gate conductor **20**, as well as the portion of the gate dielectric **15** to a depth below the upper surface of the fin structure **10**. This etch step may be performed using reactive ion etch (RIE). The etch process for recessing the gate conductor **20** and the gate dielectric **15** to expose at least a portion of the fin structure **10** containing the vertically orientated channel

region may be an etch that is selective to the dielectric cap **25** that is present on the upper surface the fin structure **10**.

The second dielectric spacer **35** may be composed of an oxide, nitride or oxynitride material. In some embodiments, the second dielectric spacer **35** is composed of silicon nitride formed using chemical vapor deposition (CVD), e.g., plasma enhanced chemical vapor deposition (PECVD). In some embodiments, the second dielectric spacer **35** may be composed of a low-k dielectric material. It noted that any of the low-k dielectric materials that are described above for the first dielectric spacer **30** are suitable for describing the second dielectric spacer **30**. The second dielectric spacer **35** is in direct contact with the sidewall of the fin structure **10** containing the vertically orientated channel region and is in direct contact with a portion of the gate dielectric **15** that is present on the fin structure **10**.

The second dielectric spacer **35** is the lower layer of the dielectric stack that also includes an interlevel dielectric **40**, in which the dielectric cap **25** that is present atop the fin structure **10** and has an upper surface that is coplanar with the dielectric stack of a second dielectric spacer **35** and an interlevel dielectric (ILD) **40**. The interlevel dielectric (ILD) **40** may be blanket deposited over the second dielectric spacer **35**, and blanket deposited over the distal end of the fin structure **10** including the vertically orientated channel region, as well as being deposited over the dielectric cap **25**. The interlevel dielectric layer (ILD) **40** may be composed of any dielectric material, such as an oxide, nitride or oxynitride material. In various embodiments, the interlevel dielectric (ILD) **40** is SiO_2 . In various other embodiments, the interlevel dielectric (ILD) **40** is Si_3N_4 . A portion of the inter-layer dielectric (ILD) material layer **40** may be removed by chemical-mechanical polishing to provide a flat, uniform surface, where the top surface of the inter-layer dielectric (ILD) material layer **40** may be coplanar with the top of the dielectric cap **25** that is present on the fin structure **10**.

FIG. 2 depicts converting a portion of an exposed source/drain contact end of the fin structure **10** including the vertically orientated channel region into an amorphous crystalline structure. Removing the dielectric cap **25** and the interlevel dielectric layer **40** exposes the portion of the fin structure **10** that will be subsequently processed to provide the second source/drain region of the device. The dielectric cap **25** and the interlevel dielectric layer **40** may be removed by a selective etch process. As used herein, the term “selective” in reference to a material removal process denotes that the rate of material removal for a first material is greater than the rate of removal for at least another material of the structure to which the material removal process is being applied. For example, in one embodiment, a selective etch may include an etch chemistry that removes a first material selectively to a second material by a ratio of 100:1 or greater. The dielectric cap **25** and the interlevel dielectric layer **40** may be removed using a wet or dry etch process. In one embodiment, the dielectric cap **25** and the interlevel dielectric layer **40** is removed by reactive ion etch (RIE).

Following removal of the dielectric cap **25** and the interlevel dielectric layer **40**, a portion of the fin structure **10** that extends above the second dielectric layer **35** is exposed. The exposed portion of the second dielectric layer **35** is converted into an amorphous material **45** by an amorphous region forming dopant. Prior to the method steps for converting the exposed portion of the fin structure **10** to an amorphous material **45**, the entirety of the fin structure **10** that contains the vertically orientated channel region is typically crystalline. The term “crystalline” includes single

crystal and polycrystalline crystal structures. The term “single crystalline” denotes a crystalline solid, in which the crystal lattice of the entire sample is substantially continuous and substantially unbroken to the edges of the sample, with substantially no grain boundaries. Contrary to a single crystal crystalline structure, a polycrystalline structure is a form of semiconductor material made up of randomly oriented crystallites. In some embodiments, the fin structure **10** has a single crystal crystalline structure, e.g., the fin structure **10**

The amorphous region forming dopant when implanted **50** into the fin structure **10** changes the crystal structure of the fin structure, i.e., impacts the crystalline lattice, to change the crystalline material to an amorphous crystal state, i.e., produces an amorphous material **45**. The term “amorphous” denotes that the non-crystalline solid is a solid that lacks the long-range order characteristic of a crystal.

The amorphous region forming dopant is ion implanted **50**, in which the mass of the amorphous region forming dopant is selected to impact the crystal lattice of the fin structure **10** in a manner that converts it to an amorphous material **45**, and does not substantially diffuse in concentrations to depths beyond those at which the extension region for the corresponding source/drain region, i.e., second source/drain region, is to be positioned. The amorphous region forming dopant is also selected so that it does not contribute electrically to the vertically orientated channel region, as well as the source and drain regions of the device, i.e., the amorphous region forming dopant does not contribute the concentration of the n-type/p-type dopants in the device.

In some embodiments, the amorphous region forming dopant is selected from the group consisting of argon (Ar), silicon (Si), germanium (Ge), helium (He), neon (Ne), krypton (Kr), xenon (Xe) and combinations thereof. The amorphous region forming dopant is implanted **50** into the exposed end of the fin structure **10** using ion implantation. Ion implantation is a materials engineering process by which ions of a material, e.g., the amorphous region forming dopant, such as germanium, are accelerated in an electrical field and impacted into a solid. In some embodiments, to convert the exposed end of the fin structure **10** to an amorphous material **45**, the amorphous region forming dopant is implanted at an energy ranging from 2 keV to 10 keV. In another embodiment, to convert the exposed end of the fin structure **10** into an amorphous material **45**, the amorphous region forming dopant may be implanted at an energy ranging from 4 keV to 8 keV. In some embodiments, to convert the exposed end of the fin structure **10** into an amorphous crystalline material, the amorphous region forming dopant is implanted into the exposed end of the fin structure **10** at a concentration ranging from $1 \times 10^{13} \text{ cm}^{-2}$ to $1 \times 10^{15} \text{ cm}^{-2}$. In another embodiment, to convert the exposed end of the fin structure **10** into an amorphous material **45**, the amorphous region forming dopant is implanted into the exposed end of the fin structure **10** at a concentration ranging from $5 \times 10^{13} \text{ cm}^{-2}$ to $5 \times 10^{14} \text{ cm}^{-2}$. The portion of the fin structure **10** that is converted into an amorphous material **45** may range from the upper surface of the fin structure **10** to a depth below the lower surface of the second dielectric spacer **35**, as depicted in FIG. 2.

FIG. 3 depicts removing the amorphous material **45** of the fin structure **10** selectively to the remainder of the vertically orientated channel region that has a non-amorphous crystal structure. The etch process for selectively removing the amorphized material may be a wet chemical etch. Converting the exposed portion of the fin structure **10** to an amor-

phous material while the remainder of the fin structure is crystalline allows for the amorphous portion of the fin structure **10** to be removed by a wet etch that does not substantially etch the portion of the fin structure **10** that has a crystalline crystal structure. For example, when the fin structure **10** is composed of silicon, e.g., monocrystalline silicon, the portion of the fin structure **10** that has been converted to an amorphous material can be selectively removed using a hydrochloric etch (HCl). The hydrochloric etch composition is only one example of a selective etch composition that is suitable for removing the portion of the structure **10** that has been converted to amorphous material. Any etch composition that can remove the amorphous material selectively to the remaining crystalline portion of the fin structure **10** is suitable for use with the present disclosure. In some embodiments, the etch process for removing the amorphous material is also selective to the second dielectric spacer **35** and the first source/drain region **5**.

FIG. **4** depicting one embodiment of an in-situ doped extension region layer **55** being epitaxially formed on an exposed surface of the fin structure **10** containing vertically orientated channel region after removing the amorphous material portion. The remaining portion of the fin structure **10** has a crystalline crystal structure, e.g., may be composed of monocrystalline silicon (c-Si), which provides a crystalline surface for epitaxial growth of the in-situ extension region layer **55**. The crystalline surface of the fin structure **10** is positioned just below the lower surface of the second dielectric spacer **35**. This provides a precise location for the extension region for the subsequently formed second source/drain region. The in-situ doped extension region layer **55** may have a thickness ranging from 1 nm to 10 nm. In other embodiments, the in-situ doped extension region layer **55** may have a thickness ranging from 2 nm to 5 nm. The in-situ doped extension region is at a depth below the second dielectric spacer **35**.

The in-situ doped extensions region layer **55** may be composed of a type IV or type III-V semiconductor material. Any of the type IV and type III-V semiconductor materials that have been described above for the supporting substrate **1** are suitable for providing the in-situ doped extension region layer **55**. For example, the type IV semiconductor material that provides the in-situ doped extension region layer **55** may be composed of silicon (Si). In other examples, the type IV semiconductor material may include germanium (Ge), e.g., silicon germanium (SiGe).

The epitaxial deposition process for forming the in-situ doped extension layer **55** may be a selective growth process. By "selective growth" it is meant that the epitaxial material for the in-situ doped extension layer **55** is formed on semiconductor surfaces, such as the exposed surface of the fin structure **10**, but is not formed on dielectric surfaces, such as the second dielectric spacer **35**. A mask may be employed to cover exposed portions of the first source/drain region **5** at this stage of the process flow.

The epitaxial deposition process for forming the in-situ doped extension layer **55** is similar to the epitaxial deposition process that is described above for the fin structure **10** and the first source/drain region. For example, if the in-situ doped extension layer **55** is composed of epitaxial silicon, i.e., crystalline silicon, e.g., monocrystalline silicon, the silicon containing gas sources for epitaxial growth include silane (SiH₄), disilane (Si₂H₆), trisilane (Si₃H₈), tetrasilane (Si₄H₁₀), hexachlorodisilane (Si₂Cl₆), tetrachlorosilane (SiCl₄), dichlorosilane (Cl₂SiH₂), trichlorosilane (Cl₃SiH), and combinations thereof. In another example, when the

in-situ doped extension layer **55** is composed of a germanium containing material, like SiGe, the epitaxially formed second semiconductor layer **30** may be composed of germanium (Ge), the germanium containing gas sources for epitaxial growth include germane (GeH₄), digermane (Ge₂H₆), halogermane, dichlorogermane, trichlorogermane, tetrachlorogermane and combinations thereof.

In some embodiments, the in-situ doped extension layer **55** is doped to an n-type conductivity or p-type conductivity to have the same conductivity type as the first source/drain region **5**. The dopant concentration of the n-type or p-type dopant is less in the in-situ doped extension layer **55** than the dopant concentration in the first source/drain region **5** and/or the subsequently formed second source/drain region. In one example, the n-type or p-type dopant concentration for the in-situ doped extension layer **55** ranges from 1×10^{19} atoms/cm³ to 5×10^{19} atoms/cm³. The n-type or p-type conductivity dopant is introduced to the epitaxial semiconductor material of the in-situ doped extension layer **55** during the formation of the material layer, in which the dopant may be uniform in concentration from the lower surface of the in-situ doped extension layer **55** to the upper surface of the in-situ doped extension layer **55**.

FIG. **5** depicts epitaxially forming a second source/drain region **60** on the in-situ doped extension region **55**. In some embodiments, the second source/drain region **60** is a source region when the first source/drain region **5** is a drain region. In some other embodiments, the second source/drain region **60** is a drain region when the first source/drain region is a source region. The second source/drain region **60** is composed of a type IV semiconductor or a type III-V semiconductor material. Any of the type IV semiconductor or type III-V semiconductor materials that have been described above for the supporting substrate are suitable for providing examples of the semiconductor materials that can be suitable for the second source/drain region **60**. The semiconductor material of the second source/drain region **60** is typically crystalline, e.g., having a single crystal crystalline structure. In some embodiments, the source/drain region **60** is composed of silicon, e.g., monocrystalline silicon.

The second source/drain region **60** may be epitaxially formed. The epitaxial growth process for forming the second source/drain region **60** is similar to the epitaxial growth process for forming the in-situ doped extension layer **55**. Therefore, some of the process conditions described for forming the in-situ doped extension layer **55** is suitable for providing some examples for the process conditions for forming the second source/drain region **60**. For example, the epitaxial deposition process for forming the second source/drain region **60** may be a selective deposition process that only aligns the semiconductor material being formed to semiconductor surfaces, such as the exposed surface of the in-situ doped extension region **55**, and is not formed on dielectric surfaces, such as the second dielectric spacer **35**.

In some embodiments, forming the second source/drain region **60** may include epitaxially forming the second source/drain region **60** on the in-situ doped extension region **55**, which may include in-situ doping with a same conductivity type dopant as the conductivity type dopant that is present in the in-situ doped extension region **55**, wherein the conductivity type dopant concentration in the source/drain region **60** is greater than the dopant concentration of the conductivity type dopant in the in-situ doped extension region **55**. In one example, the n-type or p-type dopant concentration for the second source/drain region **60** ranges from 1×10^{20} atoms/cm³ to 5×10^{21} .

FIG. 5 depicts one embodiment of a semiconductor device that includes a first source/drain region 5 on a supporting substrate 1, and a vertically orientated channel region (positioned within the fin structure 10 between the first source/drain region 5 and the second source/drain region 60). The stack of the source region layer 9, the channel region (i.e., first in-situ doped epitaxial semiconductor material 20, and second in-situ doped epitaxial semiconductor material 25), and the drain region in a direction of stacking perpendicular to the upper surface of the supporting substrate 1 may be referred to as “vertically orientated”. An extension 65 of the first source/drain region 5 is present at a first end of the vertically orientated channel region and includes a portion of the doped semiconductor material that provided the first source/drain region 5. Because the extension 65 is formed of the same material as the first source/drain region 5, the extension 65 and the first source/drain region 5 will be composed of a same composition semiconductor, be doped to a same conductivity type, and will have a same concentration of dopant that provides the conductivity type of the extension 65 and the first source/drain region 5.

An epitaxial uniformly doped extension region layer 55 is present at a second end of the vertically orientated channel region. The epitaxial uniformly doped extension region layer 55 has been described above in reference to FIGS. 1-5 as the in-situ doped extension region 55, in which the terms for this structure may be used interchangeably. The epitaxial uniformly doped extension region layer 55 is at a depth below the second dielectric spacer. The epitaxially uniformly doped extension region layer has a thickness ranging from 1 nm to 10 nm. The epitaxial uniformly doped extension region layer 55 may be composed of a different base semiconductor material than the vertically orientated channel region. By “base semiconductor material” it is meant the type IV or type III-IV semiconductor material without including p-type and n-type dopants. In other embodiments, the epitaxial uniformly doped extension region layer 55 is composed of a same base semiconductor material as the vertically orientated channel region.

Still referring to FIG. 1, the second source/drain region 60 is present on the epitaxial uniformly doped extension region layer 55. The second/drain region 60 may be composed of a same or different base material as the epitaxial uniformly doped extension region layer 55. The second source/drain region 60 is typically doped to the same conductivity type as the epitaxial uniformly doped extension region layer 55, but the dopant concentration for the p-type or n-type dopant in the second source/drain region 60 is greater than the dopant concentration in the epitaxial uniformly doped extension region layer 55. The epitaxial uniformly doped extension region layer 55 is a separate layer from the vertically orientated channel region 10 and the second source/drain region 60. By “separate layer” it is meant that a first discernible interface is present between the vertical oriented channel region 10 and the epitaxial uniformly doped extension region layer 55, and a second discernible interface is present between the second source/drain region 60 and the epitaxial uniformly doped extension region layer 55.

It is to be appreciated that the use of any of the following “/”, “and/or”, and “at least one of”, for example, in the cases of “A/B”, “A and/or B” and “at least one of A and B”, is intended to encompass the selection of the first listed option (A) only, or the selection of the second listed option (B) only, or the selection of both options (A and B). As a further example, in the cases of “A, B, and/or C” and “at least one of A, B, and C”, such phrasing is intended to encompass the

selection of the first listed option (A) only, or the selection of the second listed option (B) only, or the selection of the third listed option (C) only, or the selection of the first and the second listed options (A and B) only, or the selection of the first and third listed options (A and C) only, or the selection of the second and third listed options (B and C) only, or the selection of all three options (A and B and C). This may be extended, as readily apparent by one of ordinary skill in this and related arts, for as many items listed.

Having described preferred embodiments of a system and method (which are intended to be illustrative and not limiting), it is noted that modifications and variations can be made by persons skilled in the art in light of the above teachings. It is therefore to be understood that changes may be made in the particular embodiments disclosed which are within the scope of the invention as outlined by the appended claims. Having thus described aspects of the invention, with the details and particularity required by the patent laws, what is claimed and desired protected by Letters Patent is set forth in the appended claims.

The invention claimed is:

1. A semiconductor device comprising:

a vertically orientated channel region;

a gate structure present around the vertically orientated channel region having at least one gate sidewall spacer;

a uniformly doped extension region layer present at an end of the vertically orientated channel region, wherein a channel interfacing edge of the uniformly doped extension region is in directed contact with the vertically orientated channel region and an outer edge of the uniformly doped extension region is aligned to an edge of one of said at least one gate sidewall spacer that is interfacing with a sidewall of the gates structure; and

a source/drain region formed on the outer edge of the uniformly doped extension region layer present at the end of the vertically orientated channel region, the source/drain region having a diamond geometry with sidewall having an apex.

2. The semiconductor device of claim 1, wherein the vertically orientated channel region is present on a supporting substrate.

3. The semiconductor device of claim 2, wherein the supporting substrate includes a punch through stop layer over a type IV semiconductor base.

4. The semiconductor device of claim 1, wherein a lower source/drain region is present on the supporting substrate, and the source/drain region formed on the uniformly doped extension region layer is an upper source/drain region.

5. The semiconductor device of claim 4, further comprising a gate structure on the vertically orientated channel region and separated from the lower source/drain region by a first dielectric spacer layer.

6. The semiconductor device of claim 1, wherein the uniformly doped extension region layer is epitaxially formed.

7. The semiconductor device of claim 1, wherein the source/drain region formed on the uniformly doped extension region layer is epitaxially formed.

8. The semiconductor device of claim 1, wherein the uniformly doped extension region layer is composed of a different base semiconductor material than the vertically orientated channel region.

9. The semiconductor device of claim 1, wherein the uniformly doped extension region layer is composed of a same base semiconductor material than the vertically orientated channel region.

15

10. The semiconductor device of claim 1, wherein the uniformly doped extension region layer has a thickness ranging from 1 nm to 10 nm.

11. The semiconductor device of claim 1, wherein the semiconductor device is a vertical field effect transistor.

12. A semiconductor device comprising:

a vertically orientated channel region;

a gate structure present around the vertically orientated channel region having at least one gate sidewall spacer;

a uniformly doped epitaxial material present at an end of the vertically orientated channel region to provide an

extension region layer, wherein a channel interfacing edge of the uniformly doped extension region is in

directed contact with the vertically orientated channel region and an outer edge of the uniformly doped

extension region is aligned to an edge of one of said at least one gate sidewall spacer that is interfacing with a

sidewall of the gates structure; and

a source/drain region formed on the outer edge of the extension region layer, wherein the extension region

layer is a separate layer from the vertically orientated channel region and the source/drain region has a dia-

mond geometry.

13. The semiconductor device of claim 12, wherein the vertically orientated channel region is present on a supporting substrate.

16

14. The semiconductor device of claim 13, wherein the supporting substrate includes a punch through stop layer over a type IV semiconductor base.

15. The semiconductor device of claim 14, further comprising a gate structure on the vertically orientated channel region.

16. The semiconductor device of claim 12, wherein a lower source/drain region is present on the supporting substrate, and the source/drain region formed on the uniformly doped extension region layer is an upper source/drain region.

17. The semiconductor device of claim 12, wherein a dopant concentration that provides the conductivity type of the extension region layer is less than a dopant concentration that provides the conductivity type of the second source/drain region.

18. The semiconductor device of claim 12, wherein the extension region layer is composed of a different base semiconductor material than the vertically orientated channel region.

19. The semiconductor device of claim 12, wherein the extension region layer is composed of a same base semiconductor material than the vertically orientated channel region.

20. The semiconductor device of claim 12, wherein the semiconductor device is a vertical field effect transistor.

* * * * *