

(43) International Publication Date
20 December 2012 (20.12.2012)

- (51) **International Patent Classification:**
A61K 8/90 (2006.01) *A61Q 17/04* (2006.01)
- (21) **International Application Number:**
PCT/US2012/034522
- (22) **International Filing Date:**
20 April 2012 (20.04.2012)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**
61/477,944 21 April 2011 (21.04.2011) US
- (71) **Applicant (for all designated States except US):** **PLAY-
TEX PRODUCTS, LLC.** [US/US]; 6 Research Drive,
Shelton, CT 06484 (US).
- (72) **Inventors; and**
- (75) **Inventors/Applicants (for US only):** **SPAULDING,
Laura, A.** [US/US]; 7 Lockley Court, Wayne, NJ 07470
(US). **SCOTT, Patricia, L.** [US/US]; 713 Pinehurst Court,
Union, NJ 07083 (US). **FRONTAURIA, Alissa, R.**
[US/US]; 53 Trudy Drive, Lodi, NJ 07644 (US).
- (74) **Agent:** **RUGGIERO, Charles;** OHLANDT, GREELEY,
RUGGIERO & PERLE, LLP, One Landmark Square 10th
Floor, Stamford, Connecticut 06902 (US).

(81) **Designated States** (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.


(84) **Designated States** (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

— of inventorship (Rule 4.17(iv))

Published:

— without international search report and to be republished upon receipt of that report (Rule 48.2(g))

(54) **Title:** ENHANCED PHOTOACTIVITY OF SEMICONDUCTORS AND/OR SUNSCREENS

(57) **Abstract:** A composition comprising a physical sunscreen, one or more adjuvants, and a carrier oil is provided. The composition also includes at least one of a compound having multiple phenyl groups, a film former or dispersant, and a silicone surfactant. The composition may also include an organic sunscreen. The combination of these ingredients exhibits an unexpected synergistic effect, in that the photoactive properties of the composition (e.g., SPF, UV absorption) are significantly higher than would be predicted based on the values for each of the components individually.

ENHANCED PHOTOACTIVITY OF SEMICONDUCTORS AND/OR SUNSCREENS

BACKGROUND OF THE DISCLOSURE

5

1. Field of the Disclosure

The present disclosure relates to enhancing the photoactivity, such as the sun protection factor (SPF), and/or the UVA (ultraviolet-A) and/or UVB (ultraviolet-B) absorption, of semiconductors that behave as physical sunscreens. In particular, the present disclosure relates to enhancing the photoactivity of physical sunscreens by placing the sunscreens in a composition with one or more compounds that exhibit minimal, if any, photoactivity on their own. The physical sunscreens may also be subsequently placed in photoprotective compositions that include additional sunscreens.

15

2. Description of the Related Art

It is always a goal in the field of suncare to either use less sunscreen active material while maintaining a desired level of SPF and/or UVA absorption, or to achieve a very high SPF or UVA absorption rate overall. Thus, there is a need for a way of enhancing the photoactivity of semiconductor materials, which can boost the SPF, and/or UVA absorption of these materials.

20

SUMMARY OF THE DISCLOSURE

25

The present disclosure provides a composition (e.g., a dispersion or emulsion) of one or more physical sunscreens and/or one or more adjuvants. The one or more adjuvants are selected from the group consisting of ethylhexyl methoxycrylene (or derivatives thereof), compounds having multiple phenyl rings, silicone surfactant, a film former/dispersant, carrier oil, and any combinations thereof. The carrier oil may be aromatic or non-aromatic. The compositions of the present disclosure can take the form

30

of oil-in-water emulsion, water-in-oil emulsion, or an oily liquid that is not an emulsion. They can also be in the form of a cream, lotion, liquid or stick composition.

5 In one exemplary embodiment, the composition comprises a physical sunscreen, ethylhexyl methoxycrylene, a compound having multiple phenyl rings, and an aromatic and/or non-aromatic carrier oil.

10 In another exemplary embodiment, the composition comprises a physical sunscreen that is complexed with a silicone surfactant, and an aromatic and/or non-aromatic carrier oil. In a further embodiment of this composition, the composition also has a compound having multiple phenyl rings.

15 In a further exemplary embodiment, the composition comprises a physical sunscreen that is complexed with a silicone surfactant, ethylhexyl methoxycrylene, and an aromatic and/or non-aromatic carrier oil. In further embodiment of this composition, the composition also has a compound having multiple phenyl rings.

20 In a still further exemplary embodiment, the composition has ethylhexyl methoxycrylene and a film former/dispersant.

25 In a yet further exemplary embodiment, the composition comprises a physical sunscreen that is either plain or complexed with a silicone surfactant, a film former/dispersant, and an aromatic and/or non-aromatic carrier oil. In a further embodiment of this composition, the composition also has ethylhexyl methoxycrylene, and a compound having multiple phenyl rings.

30 In another exemplary embodiment, the composition comprises a physical sunscreen that is complexed with a silicone surfactant, ethylhexyl methoxycrylene, a film former/dispersant, and an aromatic and/or non-aromatic carrier oil.

In another exemplary embodiment, the present disclosure provides composition comprising 0.5% wt% to 30 wt% of a physical sunscreen, 0.1 wt% to 6.0 wt% of ethylhexyl methoxycrylene, a carrier oil, and at least one of a compound having multiple phenyl groups, a silicone surfactant, and a dispersant.

5

In another exemplary embodiment, the present disclosure provides a composition comprising 0.5% wt% to 30 wt% of a physical sunscreen selected from the group consisting of titanium dioxide, zinc oxide, coated zinc oxide, or a combination thereof, 0.1 wt% to 6.0 wt% of ethylhexyl methoxycrylene, 0.2 wt% to 1.0 wt% of a
10 compound having multiple phenyl groups selected from the group consisting of benzene sulfonic acids, salts of benzene sulfonic acids, styrenic block copolymers with a hydrogenated midblock of styrene-ethylene/butylene-styrene, styrenic block copolymers with a hydrogenated midblock of styrene-ethylene/propylene-styrene, styrene/butadiene/styrene block copolymers, styrene/isoprene/styrene block
15 copolymers, ethylene/butadiene/styrene block copolymer, ethylene/propylene/styrene block copolymer, styrene/ethylene/butadiene block copolymer, styrene/propylene/butadiene block copolymer, and derivatives or combinations thereof, and a carrier oil.

20

BRIEF DESCRIPTION OF THE DRAWINGS

Figs. 1-12 depict graphs that illustrate the photoactivity of the compositions of the present disclosure, and are discussed in greater detail below.

25

DETAILED DESCRIPTION OF THE DISCLOSURE

The present disclosure has unexpectedly discovered that when one or more physical sunscreens and/or one or more adjuvants are combined, the photoactivity of
30 the physical sunscreens and/or adjuvants are greatly enhanced. As is discussed in

greater detail below, this result is surprising in that the one or more additional components exhibit very little, if any, photoactivity on their own.

A “synergistic effect” is defined as the difference in an observed property
5 between a combination of elements, and the sum of the values of that property for each of those elements individually. For example, a synergistic effect on the SPF of a sunscreen composition is observed when the SPF of the composition is greater than the *sum of the SPF values for each of the ingredients in the composition.*

10 The physical sunscreen can be any compound that at least partially physically blocks UVR, although it may absorb UVR as well. Suitable physical sunscreens for the compositions of the present disclosure can be one or more semiconductors selected from the group recited in the Wikipedia page, “List of semiconductor materials,” found at http://en.wikipedia.org/wiki/List_of_semiconductor_materials, which is herein
15 incorporated by reference. In one embodiment, the physical sunscreen is titanium dioxide, zinc oxide, complexed zinc oxide, or a combination thereof. In a further embodiment, such as those shown below in the experimental data, the sunscreen is zinc oxide.

20 The physical sunscreen can be present in an amount of from 0.5% w/w to 30% w/w based on the total weight of the composition, or any subranges in between. The zinc oxide can be in the powder form, such as that sold under the trade name Zano® 10, from Umicore. An example of complexed zinc oxide is Zano® 10 Plus, also from Umicore. Titanium dioxide is sold under the trade names Kemira UV Titan, or those
25 available from Kobo. Many other trade names for treated and plain zinc oxide and titanium dioxide exist, as listed in the International Cosmetic Ingredient Dictionary and Handbook.

Ethylhexyl methoxycrylene (EHM), sold under the trade name Solastay® S1 by
30 Hallstar, or derivatives thereof can be present in the composition. EHM can be present in an amount of from 0.1% w/w to 6.0% w/w, based on the total weight of the

composition, from 0.2 % w/w to 2.0% w/w based on the total weight of the composition, from 0.5% w/w to 2.0% w/w based on the total weight of the composition, or any subranges in between.

5 The compounds having multiple phenyl compounds can be selected from: benzene sulfonic acids or salts thereof, styrenic block copolymers with a hydrogenated midblock of styrene-ethylene/butylene-styrene (SEBS), styrenic block copolymers with a
10 *hydrogenated midblock of styrene-ethylene/propylene-styrene (SEPS)*, styrene/butadiene/styrene (SBS) block copolymers, styrene/isoprene/styrene (SIS) block copolymers, an ethylene/butadiene/styrene (EBS) block copolymer, an
15 ethylene/propylene/styrene (EPS) block copolymer, styrene/ethylene/butadiene (SEB) block copolymer, styrene/propylene/butadiene (SPB) block copolymer, and any derivatives, or any combinations thereof. Examples of the SEBS, SEPS, SBS, SIS, EBS, EPS, SEB, and SPB block copolymers are the Kraton® D and Kraton® G series
20 from Kraton Polymers. In one embodiment, the compound having multiple phenyl groups is the SEB block copolymer, sold under the trade name Kraton® G1650. An example of a benzene sulfonic acid salt is sodium polystyrene benzene sulfonate
25 (available, for example, as Flexan® II, from AzkoNobel).

20 The compound with multiple phenyl groups can be present in an amount of from 0.1% w/w to 4.0% w/w, based on the total weight of the composition, from 0.2% w/w to 1.0% w/w, based on the total weight of the composition, from 0.25% w/w to 0.5% w/w, based on the total weight of the composition, or any subranges in between.

25 In one embodiment, the silicone surfactant can be lauryl polyethylene glycol (PEG)-8 dimethicone. Examples include Silube® J208-612 and J208-812, sold by Siltech LLC. The differences between the two types are discussed in greater detail below. The silicone surfactants of the present disclosure may also include variations of the lauryl PEG-8 dimethicone where the PEG group is up to and including PEG-20. In
30 addition, the polypropylene oxide (PPO) and the PEG/PPO variations of the dimethicone may be used. Any of these compounds may be straight chain, have

increased alkyl chain length, and/or can be branched, saturated or unsaturated, or aromatic. The silicone surfactant may be present in an amount of from 0.1% w/w to 10.0% w/w based on the total weight of the composition, or any subranges in between.

5 In one embodiment, the film former/dispersant can be octyldodecyl-propyl-citrate. One commercially available example is Cosmosurf® CE100, available from SurfaTech. The film former/dispersant can be present in an amount of from 0.5% w/w to 20% w/w based on the total weight of the composition, or any subranges in between. Octyldodecyl-propyl-citrate can also exhibit adjuvating activity.

10 The carrier oil can be one or more oils suitable for the purpose of allowing the phenyl compounds to interact with the semiconductors in the manner discussed below. In one embodiment, the carrier oil can be one or more esters. The esters can be benzoate or non-benzoate esters, with alkyl chain lengths that are branched or non-
15 branched. In another embodiment, the carrier oils used in this disclosure can be those with low polarity that do not exhibit meaningful SPF, such as mineral oil and isopropyl myristate. The carrier oils can also be those with comparatively higher polarity and measurable SPF, such as butyloctyl salicyclate and ethylhexyl salicyclate, the latter of which is also known as octisalate. Examples of commercially available esters suitable
20 for use in the composition of the present disclosure include, but are not limited to, the Finsolv® benzoate esters available from Innospec Active Chemicals, the Schercemol® or Hydramol® esters available from the Lubrizol Corporation, or the Crodamol® esters available from Croda Worldwide. In general, carrier oils can be aromatic and/or non-aromatic esters, and aromatic and/or nonaromatic hydrocarbon liquids. Nonaromatic
25 versions can include straight and/or branched hydrocarbon chains, and saturated and/or unsaturated hydrocarbon chains.

The amount of carrier oil used in the composition will depend on the amounts of the other ingredients. In one embodiment, the amount of carrier oil that will be present
30 in the composition is the remainder after any or all of the ingredients above are incorporated into the composition. The amount of carrier oil may also be such that

another carrier may be used, such as water. In one embodiment, the carrier oil is present in an amount of 5 – 95% w/w, based on the total weight of the emulsion or other type of photoprotective composition, or any subranges in between.

5 The compositions of the present disclosure can be further used in conjunction with compositions containing organic sunscreens, as the compositions of the present disclosure may enhance the photoactivity of those sunscreens as well as the physical sunscreens discussed above. Suitable organic sunscreens may include, but are not limited to, cinnamates, octisalate, p-aminobenzoic acid, its salts and its derivatives
 10 (ethyl, isobutyl, glyceryl esters; p-dimethylaminobenzoic acid); anthranilates (o-aminobenzoates; methyl, menthyl, phenyl, benzyl, phenylethyl, linalyl, terpinyl, and cyclohexenyl esters), salicylates (octyl, amyl, phenyl, benzyl, menthyl (homosalate), glyceryl, and dipropylene glycol esters), cinnamic acid derivatives (menthyl and benzyl esters, alpha-phenyl cinnamitrile; butyl cinnamoyl pyruvate), dihydroxycinnamic acid
 15 derivatives (umbelliferone, methylumbelliferone, methylaceto-umbelliferone), camphor derivatives (3-benzylidene, 4-methylbenzylidene, polyacrylamidomethyl benzylidene, benzalkonium methosulfate, benzylidene camphor sulfonic acid, and terephthalylidene dicamphor sulfonic acid), trihydroxycinnamic acid derivatives (esculetin, methylesculetin, daphnetin, and the glucosides, esculin and daphnin), hydrocarbons
 20 (diphenylbutadiene, stilbene), dibenzalacetone and benzalacetophenone, naphtholsulfonates (sodium salts of 2-naphthol-3,6-disulfonic and of 2-naphthol-6,8-disulfonic acids), dihydroxy-naphthoic acid and its salts, o- and p-hydroxydiphenyldisulfonates, coumarin derivatives (7-hydroxy, 7-methyl, 3-phenyl), diazoles (2-acetyl-3-bromoindazole, phenyl benzoxazole, methyl naphthoxazole, various aryl benzothiazoles), quinine salts (bisulfate, sulfate, chloride, oleate, and
 25 tannate), quinoline derivatives (8-hydroxyquinoline salts, 2-phenylquinoline), hydroxy- or methoxy-substituted benzophenones, uric and vilouric acids, tannic acid and its derivatives, hydroquinone, benzophenones (oxybenzone, sulisobenzene, dioxybenzone, benzoescorcinol, 2,2',4,4'-tetrahydroxybenzophenone, 2,2'-dihydroxy-
 30 4,4'-dimethoxybenzophenone, octabenzene), dibenzoylmethane derivatives, avobenzene, 4-isopropylidibenzoylmethane, butylmethoxydibenzoylmethane, 4-

isopropyl-dibenzoylmethane, octocrylene, drometrizole trisiloxane, bemotrizinol (sold under the trade name Tinasorb®), ecamsule (sold under the trade name Mexoryl®), and any combinations thereof.

Data illustrating the benefits of the above-described embodiments of the composition of the present disclosure are shown below. For convenience's sake, the compounds are referred to by their trade names.

Materials Used

ZnO Powder, Zano 10 from Umicore
Physical Sunscreen Active


INCI: Zinc oxide

Solastay S1 from Hallstar
Sunscreen Photostabilizer

INCI: Ethylhexyl methoxycrylene


Silube J208-612, SILTECHLLC
Water-in-oil silicone surfactant

INCI: Lauryl PEG-8 Dimethicone




Silube J208-812, SILTECH LLC
Water-in-oil Silicone Surfactant

INCI: Lauryl PEG-8 Dimethicone



Cosmosurf CE100, SurfaTech
Film Former, Dispersant

INCI: Octyldodecyl-propyl-citrate



Dispersions Used

K/MO 5% Kraton G1650 (K, Kraton) in Isopropyl Myristate (IPM)
 K/IPM 5% Kraton G1650 (K, Kraton) in Isopropyl Myristate (IPM)
 K/BHB 5% Kraton G1650 (K, Kraton) in Butyloctyl Salicylate (BHB)
 K/OS 5% Kraton G1650 (K, Kraton) in Ethylhexyl Salicylate (OS)

ZnO-GEMS (Gelling Electrostatic Matrix)

ZnO-612: 2% J208-612 electrostatically complexed with 98% ZnO

ZnO-812: 2% J208-812 electrostatically complexed with 98% ZnO

Other ratios of GEM complexed with ZnO are contemplated by the present disclosure.

Instrumentation

The *in-vitro* SPF was determined using the Labsphere 2000S UV Transmittance Analyzer and PMMA roughened surface substrates. Exceptions and dose amounts are noted at the bottom of the Tables. The Labsphere uses a xenon flashlamp supplying sufficient energy for the spectral range of 250 – 450 nm.

The *in-vivo* data was generated using an outside testing facility; FDA monograph; 3 subject panels; static testing only.

Solvent polarity was determined using the Scientifica 870 Liquid Dielectric Constant Meter.

Study 1

In a cursory study to identify active agents causing the synergy, a series of
 5 dispersions were prepared for UVR absorption analyses. Table I-A summarizes the
 sample ID, the *in-vitro* SPF data and the UVA1 wavelength at which 0.5 absorbance
 units occurred. The former measurement provides a relative difference of the
 magnitude of UVR absorption. The latter measurement becomes important when
 evaluating the breadth of UVR absorption. The data clearly showed that not only does
 10 Kraton enhance the absorption activity of ZnO, but individually, Solastay (SS) does as
 well. Surprisingly, and more importantly, the presence of the combination of Kraton and
 Solastay together with ZnO showed a significant increase in both *in-vitro* SPF
 magnitude and UVA1 breadth of absorption, much greater than what would be expected
 based on the corresponding values for each component individually.

15

Table I-A UVR Absorption Responses of ZnO in Kraton / Solastay Carrier Oil Dispersions				
<u>Sample ID</u>	<u>Ingredients</u>	<u>Ratio</u>	<u><i>in-vitro</i> SPF (units)</u>	<u>UVA1 (λ nm @0.5 abs)</u>
3043-3-15	IPM / ZnO	4.0 / 1.0	3 ± 0 STD	--
3043-3-1	OS	4.0 (Neat)	14 ± 0 STD	--
3043-3-2	OS / K	3.8 / 0.2	14 ± 1 STD	--
3043-3-6	OS / K / ZnO	3.8 / 0.2 / 1.0	170 ± 5 STD	384.0
3043-3-14	IPM / SS	4.0 / 0.4	21 ± 3 STD	380.0
3043-3-9	OS / SS	4.0 / 0.4	117 ± 7 STD	383.5
3043-3-11	OS / SS / ZnO	4.0 / 0.4 / 1.0	258 ± 6 STD	393.0
3043-3-12	OS / K / SS / ZnO	3.8 / 0.2 / 0.4 / 1.0	372 ± 10 STD	397.0

Dose: 1.0 mg/cm² Clear Quartz Glass Slide

In using the data in Table I-A above, the unexpected synergy is evaluated from
 two different perspectives. Through the various dispersion combinations described in
 20 Table 1-B below, the theoretical expected *in-vitro* SPF values were 287 for Scenario 1,
 and 272 units for Scenario 2. These values were significantly lower than the observed
in-vitro SPF value of 372 units for the presence of the combination of Kraton and
 Solastay with ZnO in a carrier oil dispersion.

Table I-B UV Absorption Synergy of ZnO in Kraton / Solastay Carrier Oil Dispersions				
<u>Sample ID</u>	<u>Ingredients</u>	<u>Ratio</u>	<i>in-vitro</i> SPF (units)	
Synergy Scenario 1				
3043-3-6	OS / K / ZnO	3.8 / 0.2 / 1.0	170 + 5 STD	
3043-3-9	OS / SS	4.0 / 0.4	117 + 7 STD	
	OS / K / SS / ZnO	3.8 / 0.2 / 0.4 / 1.0	287	Theoretical
3043-3-12	OS / K / SS / ZnO	3.8 / 0.2 / 0.4 / 1.0	372 + 10 STD	Observed
Synergy Scenario 2				
3043-3-2	OS / K	3.8 / 0.2	14 + 1 STD	
3043-3-11	OS / SS / ZnO	4.0 / 0.4 / 1.0	258 + 6 STD	
	OS / K / SS / ZnO	3.8 / 0.2 / 0.4 / 1.0	272	Theoretical
3043-3-12	OS / K / SS / ZnO	3.8 / 0.2 / 0.4 / 1.0	372 + 10 STD	Observed

Dose: 1.0 mg/cm² Clear Quartz Glass Substrate

5 Study 2

A second study was performed to characterize the interaction of ZnO and ZnO-GEM complexes with Kraton and Solastay in carrier oil dispersions. The GEM stands for Gelling Electrostatic Matrix, whereby an alkyl silicone ethoxylated polymer such as Siltech J208-812 attaches itself via electrostatic interaction to the ZnO crystal lattice structure, thereby forming a lowest free energy complex. The complex is designated as ZnO-812. The dose of 0.55 mg/cm² on PMMA substrate was selected for this and future studies so that the data range would fall below the maximum absorbance range limit of the instrument. The isopropyl myristate (IPM) and Cosmosurf CE100 (CE) neat materials listed in Table II-A had no UVR absorption activity on their own, and are thus used as q.s. diluents to maintain the remaining ingredient ratios. Key observations were as follows:

1. The GEM complex of ZnO-812 absorbed more UVR than plain ZnO. This is an unexpected result, as silicone surfactant exhibited essentially no UVR attenuation on its own.

2. Solastay adjuvated UVR attenuation capability of both ZnO-612 and ZnO-812.

The amount of the increase in UVR attenuation for the ZnO-612 and ZnO-812 complexes was unexpected based on the UVR values for the individual compounds.

3. Kraton/Solastay combination synergistically adjuvated UVR attenuation (magnitude and breadth) of both ZnO, ZnO-612, and ZnO-812. This is unexpected, since Kraton
5 has very little UVR attenuation ability on its own.

4. CE100 further maximized UVR attenuation capability of ZnO, ZnO-612, and ZnO-812 with and without Kraton and Solastay. Again, this is very much unexpected, since as shown, CE100 has almost no UVR attenuation ability on its own.

Table II-A UVR Absorption Responses of ZnO and ZnO-812 in Kraton / Solastay Carrier Oil Dispersions

<u>Sample ID</u>	<u>Ingredients</u>	<u>Ratio</u>	<u>in-vitro SPF (units)</u>	<u>UVA1 (λ nm@0.5abs)</u>
3088-76-1	IPM	Neat	1 $\pm$ 0 STD	--
0031-17-26	IPM-K (5% gel)	Neat	1 $\pm$ 0 STD	--
3088-72-1	ZnO	Neat	4 $\pm$ 0 STD	375.5
3088-72-2	IPM / ZnO	4.0 / 1.0	4 $\pm$ 0 STD	376.5
0031-17-28	IPM / ZnO-812	4.0 / 1.0	7 $\pm$ 0 STD	378.5
3088-75-11	IPM / OS	4.0 / 1.0	7 $\pm$ 0 STD	--
3088-74-17	IPM / SS	4.5 / 0.5	12 $\pm$ 0 STD	372.0
3088-72-3	IPM / OS-K / ZnO	3.0 / 1.0 / 1.0	17 $\pm$ 1 STD	377.0
3088-72-16	IPM / ZnO / SS	3.5 / 1.0 / 0.5	31 $\pm$ 1 STD	386.5
3088-75-9	IPM / ZnO-812 / SS	3.5 / 1.0 / 0.5	52 $\pm$ 3 STD	388.0
3088-72-4	IPM / OS-K / ZnO / SS	2.5 / 1.0 / 1.0 / 0.5	105 $\pm$ 3 STD	389.0
3088-75-10	IPM / OS-K / ZnO-812 / SS	2.5 / 1.0 / 1.0 / 0.5	129 $\pm$ 4 STD	390.5
3088-75-8	CE / OS-K / ZnO-812 / SS	2.5 / 1.0 / 1.0 / 0.5	156 $\pm$ 10 STD	393.5
3088-75-7	CE / OS / ZnO-812 / SS	2.5 / 1.0 / 1.0 / 0.5	133 $\pm$ 6 STD	391.0
3088-72-18	CE / OS / ZnO / SS	2.5 / 1.0 / 1.0 / 0.5	64 $\pm$ 2 STD	389.0
3088-75-6	CE / ZnO-812 / SS	3.5 / 1.0 / 0.5	44 $\pm$ 2 STD	390.0
3088-75-5	CE / OS-K / ZnO-812	3.0 / 1.0 / 1.0	44 $\pm$ 2 STD	380.0
3088-75-4	CE / OS / ZnO-812	3.0 / 1.0 / 1.0	22 $\pm$ 0 STD	377.5
3088-75-3	CE / ZnO-812	4.0 / 1.0	17 $\pm$ 1 STD	380.0
0008-85-6	CE / SS	4.5 / 0.5	21 $\pm$ 1 STD	381.0
0008-87-2	CE / OS	4.0 / 1.0	8 $\pm$ 0 STD	--
0008-104-1	CE / ZnO	4.0 / 1.0	5 $\pm$ 0 STD	376.0
0008-85-3	CE-K	Incompatible	--	--
0008-85-1	CE	Neat	1 $\pm$ 0 STD	--
0008-106	SS	Neat *	4 $\pm$ 0 STD	373.0

Dose: 0.55 mg/cm² PMMA substrate*Solastay target dose on PMMA substrate was 0.11 mg/cm² PMMA substrate to account for ratio proportion.

5

The enhanced UVR absorption responses of ZnO-812 versus the plain ZnO are clearly shown in Figure 1. Also, the synergy between the ZnO-812 and the Kraton/Solastay combination significantly enhanced the UVR absorption responses.

Table II-B summarizes three different scenarios that establish the synergy of ZnO with Kraton/Solastay in a carrier oil dispersion. The observed *in-vitro* SPF value of 105 is significantly higher than the theoretical *in-vitro* SPF values of 24, 29, and 48.

Table II-B UV Absorption Synergy of ZnO in Kraton / Solastay Polar Dispersions				
<u>Sample ID</u>	<u>Ingredients</u>	<u>Ratio</u>	<u><i>in-vitro</i> SPF (units)</u>	
Scenario 1				
0031-17-26	IPM-K (5% gel)	Neat	1 + 0 STD	
3088-72-2	IPM / ZnO	4.0 / 1.0	4 + 0 STD	
3088-75-11	IPM / OS	4.0 / 1.0	7 + 0 STD	
3088-74-17	IPM / SS	4.5 / 0.5	12 + 0 STD	
	IPM / OS- K / ZnO / SS	2.5 / 1.0 / 1.0 / 0.5	24	Theoretical
3088-72-4	IPM / OS- K / ZnO / SS	2.5 / 1.0 / 1.0 / 0.5	105 + 3 STD	Observed
Scenario 2				
3088-72-3	IPM / OS-K / ZnO	3.0 / 1.0 / 1.0	17 + 1 STD	
3088-74-17	IPM / SS	4.5 / 0.5	12 + 0 STD	
	IPM / OS- K / ZnO / SS	2.5 / 1.0 / 1.0 / 0.5	29	Theoretical
3088-72-4	IPM / OS- K / ZnO / SS	2.5 / 1.0 / 1.0 / 0.5	105 + 3 STD	Observed
Scenario 3				
3088-72-3	IPM / OS-K / ZnO	3.0 / 1.0 / 1.0	17 + 1 STD	
3088-72-16	IPM / ZnO / SS	3.5 / 1.0 / 0.5	31 + 1 STD	
	IPM / OS- K / ZnO / SS	2.5 / 1.0 / 1.0 / 0.5	48	Theoretical
3088-72-4	IPM / OS- K / ZnO / SS	2.5 / 1.0 / 1.0 / 0.5	105 + 3 STD	Observed

5 Dose: 0.55 mg/cm² PMMA substrate

Table II-C summarizes two different scenarios that establish the synergy of ZnO-812 with Kraton/Solastay in a carrier oil dispersion. The observed *in-vitro* SPF value of 129 is significantly higher than the theoretical *in-vitro* SPF values of 27 and 60.

Table II-C UV Absorption Synergy of ZnO-812 in Kraton / Solastay Carrier Oil Dispersions				
<u>Sample ID</u>	<u>Ingredients</u>	<u>Ratio</u>	<i>in-vitro</i> SPF (units)	
Scenario 1				
0031-17-26	IPM-K (5% gel)	Neat	1 + 0 STD	
3088-72-2	IPM / ZnO-812	4.0 / 1.0	7 + 0 STD	
3088-75-11	IPM / OS	4.0 / 1.0	7 + 0 STD	
3088-74-17	IPM / SS	4.5 / 0.5	12 + 0 STD	
	IPM / OS- K / ZnO-812 / SS	2.5 / 1.0 / 1.0 / 0.5	27	Theoretical
3088-72-4	IPM / OS- K / ZnO-812 / SS	2.5 / 1.0 / 1.0 / 0.5	129 + 3 STD	Observed
Scenario 2				
0031-17-26	IPM-K (5% gel)	Neat	1 + 0 STD	
3088-75-11	IPM / OS	4.0 / 1.0	7 + 0 STD	
3088-75-9	IPM / ZnO-812 / SS	3.5 / 1.0 / 0.5	52 + 3 STD	
	IPM / OS- K / ZnO-812 / SS	2.5 / 1.0 / 1.0 / 0.5	60	Theoretical
3088-72-4	IPM / OS- K / ZnO-812 / SS	2.5 / 1.0 / 1.0 / 0.5	129 + 3 STD	Observed

5 Dose: 0.55 mg/cm² PMMA substrate

Table II-D summarizes two different scenarios that establish the synergy of ZnO-812 with Kraton/Solastay in a CE100 carrier oil dispersion. The observed *in-vitro* SPF value of 156 is significantly higher than the theoretical *in-vitro* SPF values of 47 and 65.

Table II-D UV Absorption Synergy of ZnO-812 and CE100 / Kraton / Solastay Carrier Oil Dispersions				
<u>Sample ID</u>	<u>Ingredients</u>	<u>Ratio</u>	<u>in-vitro SPF (units)</u>	
Scenario 1				
0008-85-1	CE	Neat	1 ± 0 STD	
0008-85-3	CE-K	Incompatible	--	
3088-75-3	CE / ZnO-812	4.0 / 1.0	17 ± 1 STD	
0008-87-2	CE / OS	4.0 / 1.0	8 ± 0 STD	
0008-85-6	CE / SS	4.5 / 0.5	21 ± 1 STD	
	CE / OS-K / ZnO-812 / SS	2.5 / 1.0 / 1.0 / 0.5	47	Theoretical
3088-75-8	CE / OS-K / ZnO-812 / SS	2.5 / 1.0 / 1.0 / 0.5	156 ± 10 STD	Observed
Scenario 2				
0008-85-6	CE / SS	4.5 / 0.5	21 ± 1 STD	
3088-75-5	CE / OS-K / ZnO-812	3.0 / 1.0 / 1.0	44 ± 2 STD	
	CE / OS-K / ZnO-812 / SS	2.5 / 1.0 / 1.0 / 0.5	65	Theoretical
3088-75-8	CE / OS-K / ZnO-812 / SS	2.5 / 1.0 / 1.0 / 0.5	156 ± 10 STD	Observed

Dose: 0.55 mg/cm² PMMA substrate

Table II-E shows another unexpected synergy with Solastay in combination with
 5 CE100 versus the Solastay dispersed in IPM. Both CE100 and IPM are transparent to
 UVA, and therefore it is remarkable that the Solastay *in-vitro* SPF magnitude would
 increase by 11 units, almost double, upon dispersion in CE100 versus IPM.

Table II-E UV Absorption Synergy of Solastay / CE100 Dispersion versus Solastay / IPM				
<u>Sample ID</u>	<u>Ingredients</u>	<u>Ratio</u>	<u>in-vitro SPF (units)</u>	
Scenario 1				
3088-76-1	IPM	Neat	1 ± 0 STD	
0008-106	SS	Neat *	4 ± 0 STD	
	IPM / SS	4.5 / 0.5	5	Theoretical
3088-74-17	IPM / SS	4.5 / 0.5	12 ± 0 STD	Observed
0008-85-1	CE	Neat	1 ± 0 STD	
0008-106	SS	Neat *	4 ± 0 STD	
	CE / SS	4.5 / 0.5	5	Theoretical
0008-85-6	CE / SS	4.5 / 0.5	21 ± 1 STD	Observed

Study 3

The purpose of this study was to further characterize the interaction of CE100 with ZnO and the ZnO-GEMs prepared with J208-612 and J208-812. J208-612 is slightly more water soluble, with 6 sites containing C12 groups, and 4 sites containing eight moles of ethoxylation. J208-812 is completely hydrophobic with 8 sites containing C12 groups, and 2 sites containing eight moles of ethoxylation. Kraton is not directly compatible with CE100, and therefore not included in this study. The carrier oil, octisalate, is also absent. The data in Table III-A below clearly shows the increasing UVR absorption capability of the ZnO-GEMs versus plain ZnO. Also, the influence of Solastay to adjuvate UVR absorption capability of the ZnO-GEM's is noted.

Table III-A UVR Absorption Responses of ZnO and ZnO-GEM in CE / Solastay Dispersions

Sample ID	Ingredients	Ratio	<i>in-vitro</i> SPF (units)	UVA1 λ nm@0.5abs
0008-85-1	CE100	Neat	1 $\pm$ 0 STD	--
0008-104-1	CE100/ZnO	4.0 / 1.0	5 $\pm$ 0 STD	376
0008-104-2	CE100/ZnO-612	4.0 / 1.0	9 $\pm$ 0 STD	378
0008-85-11	CE100/ZnO-812	4.0 / 1.0	16 $\pm$ 1 STD	380
0008-85-6	CE100/SS	4.5 / 0.5	21 $\pm$ 1 STD	381
0008-104-3	CE100/ZnO/SS	3.5 / 1.0 / 0.5	47 $\pm$ 1 STD	388
0008-104-4	CE100/ZnO-612/SS	3.5 / 1.0 / 0.5	57 $\pm$ 0 STD	389
0008-85-12	CE100/ZnO-812/SS	3.5 / 1.0 / 0.5	70 $\pm$ 2 STD	392

Dose: 0.55 mg/cm² PMMA substrate

Table III-B establishes the synergy of the ZnO-GEMs with Solastay in CE100 dispersion. The observed *in-vitro* SPF value of 57 was significantly higher than the theoretical *in-vitro* SPF value of 30 for ZnO-612. The observed *in-vitro* SPF value of 70 was significantly higher than the theoretical *in-vitro* SPF value of 37 for ZnO-812.

Table III-B UV Absorption Synergy of ZnO and ZnO-GEM in CE100 / Solastay Dispersions				
<u>Sample ID</u>	<u>Ingredients</u>	<u>Ratio</u>	<u><i>in-vitro</i> SPF (units)</u>	
Synergy with ZnO-612				
0008-104-2	CE100/ZnO-612	4.0 / 1.0	9 $\pm$ 0 STD	
0008-85-6	CE100/SS	4.5 / 0.5	21 $\pm$ 1 STD	
	CE100/ZnO-612/SS	3.5 / 1.0 / 0.5	30	Theoretical
0008-104-4	CE100/ZnO-612/SS	3.5 / 1.0 / 0.5	57 $\pm$ 0 STD	Observed
Synergy with ZnO-812				
0008-85-11	CE100/ZnO-812	4.0 / 1.0	16 $\pm$ 1 STD	
0008-85-6	CE100/SS	4.5 / 0.5	21 $\pm$ 1 STD	
	CE100/ZnO-812/SS	3.5 / 1.0 / 0.5	37	Theoretical
0008-85-12	CE100/ZnO-812/SS	3.5 / 1.0 / 0.5	70 $\pm$ 2 STD	Observed

Dose: 0.55 mg/cm² PMMA substrate

5 **Study 4**

The purpose of this study was to explore the interrelationship between CE100, Kraton and Solastay, since it had been observed that sometimes dispersions were uniform and other times a non-uniform dispersion with agglomerate would occur. The first set of data in Table IV shows increasing *in-vitro* SPF magnitude as Solastay concentration increased, which was expected. Since CE100 had no UV absorption capability, the *in-vitro* SPF contribution was provided by the Solastay material. In previous experiments, the CE100/OS-K/SS ratio was 3.5:1.0:0.5. In those experiments, it appeared that the Kraton gellant migrated from octisalate to the preferred, relatively more hydrocarbon alkyl chains on the CE100, and thus, non-uniform agglomerate formed. To change dispersion dynamics and achieve a uniform dispersion, the OS-K content in the ratio was increased. Uniform dispersions were obtained and satisfactorily spread on the PMMA substrate. The second data set in Table IV shows the impact of the UV absorbing compound, octisalate, had on increasing the *in-vitro* SPF magnitude of the CE100/SS dispersion. The unexpected results for the absorption responses shown in the third data set came from the synergistic impact Kraton had with Solastay. The control sample of Kraton added to CE100/OS had no impact on increasing *in-vitro* SPF, as indicated by the same value of 10 units. However, a comparison of

CE100/OS/SS dispersions to the corresponding CE100/OS-K/SS dispersions showed synergistic absorption responses at each ratio, as shown in Figure 2. Surprisingly, the *in-vitro* SPF values for the samples containing Solastay fit a polynomial curve as opposed to a linear regression.

5

Table IV UVR Absorption Responses of Kraton / Solastay in CE100 and CE100 / Carrier Oil Dispersions						
<u>Sample ID</u>	<u>CE100</u>	<u>Ingredient Ratio</u>			<u>Absorption Response</u>	
		<u>OS</u>	<u>OS/K</u>	<u>SS</u>	<i>in-vitro</i> SPF (units)	UVA1 (λ nm@0.5abs)
0008-85-1	10.0	--	--	--	1 + 0 STD	
0008-96-1	9.8	--	--	0.2	2 + 0 STD	-
0008-96-2	9.8	--	--	0.5	4 + 0 STD	364.0
0008-96-3	9.0	--	--	1.0	27 + 0 STD	382.0
0008-96-4	8.0	--	--	2.0	57 + 2 STD	389.5
0008-96-13	5.0	5.0	--	0.0	10+ 1 STD	-
0008-96-5	4.8	5.0	--	0.2	22 + 1 STD	340.0
0008-96-6	4.5	5.0	--	0.5	34 + 4 STD	368.0
0008-96-7	4.0	5.0	--	1.0	96 + 4 STD	382.0
0008-96-8	3.0	5.0	--	2.0	130+ 4 STD	388.0
0008-96-14	5.0	--	5.0	0.0	10+ 1 STD	-
0008-96-9	4.8	--	5.0	0.2	37+ 4 STD	382.0
0008-96-10	4.5	--	5.0	0.5	68+ 4 STD	386.0
0008-96-11	4.0	--	5.0	1.0	118+ 4 STD	386.5
0008-96-12	3.0	--	5.0	2.0	169+ 4 STD	390.0

Dose: 0.55 mg/cm² PMMA substrate

Study 5

10 It is known that solvent polarity affects the UV absorption spectrum of sunscreen active materials, in that generally increasing polarity enhances sunscreen performance. It is also known that there is an upper limit and the effect is system dependent. Therefore, knowledge of solvent polarity based on dielectric constant, Table V, helps to understand simple systems such as the dispersions listed below.

Table V Solvent Polarity	
<u>Solvent</u>	<u>Dielectric Constant</u>
Mineral Oil	2.30
Isopropyl Myristate	3.25
Ethylhexyl Benzoate	4.61
Butyloctyl Salicylate	5.27
Ethylhexyl Salicylate	6.25

The purpose of Study 5 was to investigate the UV absorption responses of two ZnO-GEMs versus plain ZnO as a function of solvent polarity. The data in Table VI-a showed the following trends in the absorption response for *in-vitro* SPF:

1. The GEM materials, J208-612 and 812 were transparent to UVR, and thus had no effect on *in-vitro* SPF magnitude.
2. The ZnO-GEM materials attenuated UVR more so than plain ZnO in the aromatic carrier oils of BHB and OS. Thus increases in *in-vitro* SPF magnitudes were observed, and were synergistic because it was the GEM materials complexed with ZnO that caused the enhancement in UVR activity.
3. ZnO-812 attenuated UVR more efficiently than ZnO-612.

Table VI-A ZnO and ZnO-GEMs in Carrier Oil Dispersions					
Absorption Response of <i>in-Vitro</i> SPF					
		<i>in-vitro</i> SPF (units)			
<u>Sample</u>	<u>Ratio</u>	<u>IPM</u>	<u>EB</u>	<u>BHB</u>	<u>OS</u>
Solvent	Neat	1 $\pm$ 0 STD	1 $\pm$ 0 STD	12 $\pm$ 0 STD	12 $\pm$ 0 STD
+ J208-612	4.9 / 0.1	1 $\pm$ 0 STD	1 $\pm$ 0 STD	12 $\pm$ 0 STD	13 $\pm$ 0 STD
+ J208-812	4.9 / 0.1	1 $\pm$ 0 STD	1 $\pm$ 0 STD	13 $\pm$ 0 STD	12 $\pm$ 0 STD
+ ZnO	4.0 / 1.0	8 $\pm$ 1 STD	14 $\pm$ 1 STD	63 $\pm$ 2 STD	76 $\pm$ 0 STD
+ ZnO-612	4.0 / 1.0	7 $\pm$ 0 STD	13 $\pm$ 1 STD	71 $\pm$ 1 STD	84 $\pm$ 2 STD
+ ZnO-812	4.5 / 0.5	--	--	--	41 $\pm$ 2 STD
+ ZnO-812	4.0 / 1.0	7 $\pm$ 0 STD	14 $\pm$ 1 STD	85 $\pm$ 4 STD	94 $\pm$ 1 STD
+ ZnO-812	3.0 / 2.0	---	--	--	118 $\pm$ 3 STD

Dose: 0.55 mg/cm² PMMA substrate

Figure 3 depicts the trend in *in-vitro* SPF of ZnO and the ZnO-GEM materials as they were influenced by solvent polarity. It can be seen clearly that the presence of a Gelling Electrostatic Matrix (GEM) enhanced the UV absorption capability of ZnO.

Table VI-B summarizes the UVA1 absorption response data by determining the wavelength at 0.5 absorbance units in the 340 – 400 nm region. Although the wavelengths @0.5abs were similar between the plain ZnO and the ZnO-GEMs, it is in Figure 5 that the differences in UVA1 magnitude are shown amongst the dispersions.

Table VI-B ZnO and ZnO-GEMs in Carrier Oil Dispersions Absorption Response of UVA1					
Sample	Ratio	UVA1 (λ nm @0.5 abs)			
		IPM	EB	BHB	OS
Solvent	Neat	--	--	--	--
+ J208-612	4.9 / 0.1	--	--	--	--
+ J208-812	4.9 / 0.1	--	--	--	--
+ ZnO	4.0 / 1.0	379.5	381.0	379.5	381.0
+ ZnO-612	4.0 / 1.0	378.0	381.5	380.0	382.0
+ ZnO-812	4.5 / 0.5	--	--	--	375.0
+ ZnO-812	4.0 / 1.0	378.5	381.0	380.0	381.5
+ ZnO-812	3.0 / 2.0	--	--	--	384.0

Dose: 0.55 mg/cm² PMMA substrate

Study 6

This study was a continuation of Study 5 whereby the effects of the addition of Kraton to the plain ZnO and the ZnO-Gem dispersions were investigated. The carrier oils were gelled with 5% Kraton, which was transparent to UVR. The *in-vitro* SPF data summarized in Table VII-A were the same as those noted above. However, the magnitudes of absorption for the Kraton containing dispersions were unexpectedly higher and clearly illustrated in Figure 4.

Table VII-A ZnO and ZnO-GEMs in Kraton / Carrier Oil Dispersions					
Absorption Response of <i>in-vitro</i> SPF					
		<i>in-vitro</i> SPF (units)			
Sample	Ratio	IPM/K	EB/K	BHB/K	OS/K
Solvent	Neat	1 ± 0 STD	1 ± 0 STD	13 ± 0 STD	12 ± 0 STD
+ J208-612	4.9 / 0.1	1 ± 0 STD	1 ± 0 STD	12 ± 0 STD	13 ± 0 STD
+ J208-812	4.9 / 0.1	1 ± 0 STD	1 ± 0 STD	13 ± 0 STD	12 ± 0 STD
+ ZnO	4.0 / 1.0	8 ± 0 STD	19 ± 1 STD	93 ± 2 STD	110 ± 2 STD
+ ZnO-612	4.0 / 1.0	13 ± 1 STD	25 ± 2 STD	102 ± 0 STD	123 ± 3 STD
+ ZnO-812	4.5 / 0.5	--	--	--	64 ± 3 STD
+ ZnO-812	4.0 / 1.0	15 ± 1 STD	27 ± 1 STD	121 ± 2 STD	135 ± 1 STD
+ ZnO-812	3.0 / 2.0	--	--	--	151 ± 2 STD

Dose: 0.55 mg/cm² PMMA substrate

The data in Table VII-B shows essentially the same behavior for UVA1 as noted in the previous study in that the wavelength at 0.5 absorbance units occurred nearly at the same point. It is in Figure 5 that the increases in UVA 1 absorbance from 340 – 380 nm were noticeably higher for the Kraton dispersions versus the non-Kraton dispersions. Since Kraton is transparent to UVR, the increases in UVA1 were synergistic for the combination with ZnO-GEM materials.

Table VII-B ZnO and ZnO-GEMs in Kraton / Carrier Oil Dispersions					
Absorption Response of UVA1					
		UVA1 (λ nm @0.5 abs)			
Sample	Ratio	IPM/K	EB/K	BHB/K	OS/K
Solvent	Neat	--	--	--	--
+ J208-612	4.9 / 0.1	--	--	--	--
+ J208-812	4.9 / 0.1	--	--	--	--
+ ZnO	4.0 / 1.0	379.0	382.0	381.0	381.0
+ ZnO-612	4.0 / 1.0	381.0	383.5	381.0	382.5
+ ZnO-812	4.5 / 0.5	--	--	--	378.0
+ ZnO-812	4.0 / 1.0	381.5	382.0	382.0	382.5
+ ZnO-812	3.0 / 2.0	--	--	--	386.0

Dose: 0.55 mg/cm² PMMA substrate

Study 7

This study was also a continuation of Study 5 and focused on the addition of Solastay to the ZnO and ZnO-GEM carrier oil dispersions. It was important to note the baseline *in-vitro* SPF contribution of Solastay in the carrier oils as presented in Table

VIII-A, and also note that the presence of the GEM materials J208-612 and 812 had no effect on *in-vitro* SPF. Interestingly, the non-aromatic as well as the aromatic carrier oils were showing significant, higher increases in *in-vitro* SPF versus those presented in Tables VI-A and VII-A.

5

Table VIII-A ZnO and ZnO-GEMs in Solastay Carrier Oil Dispersions					
Absorption Response of In-vitro SPF					
<u>Sample</u>	<u>Ratio</u>	<u><i>in-vitro</i> SPF (units)</u>			
		<u>IPM</u>	<u>EB</u>	<u>BHB</u>	<u>OS</u>
Solvent	Neat	1 ± 0 STD	1 ± 0 STD	12 ± 0 STD	12 ± 0 STD
+ SS	4.5 / 0.5	13 ± 1 STD	21 ± 1 STD	50 ± 2 STD	65 ± 2 STD
+ J208-612/SS	4.4 / 0.1 / 0.5	13 ± 0 STD	21 ± 2 STD	53 ± 1 STD	67 ± 1 STD
+ J208-812/SS	4.4 / 0.1 / 0.5	13 ± 1 STD	22 ± 2 STD	52 ± 2 STD	67 ± 2 STD
+ ZnO SS	3.5 / 1.0 / 0.5	18 ± 1 STD	51 ± 3 STD	89 ± 2 STD	117 ± 2 STD
+ ZnO-612/SS	3.5 / 1.0 / 0.5	23 ± 1 STD	63 ± 2 STD	152 ± 2 STD	145 ± 4 STD
+ ZnO-812/SS	3.8 / 1.0 / 0.2	--	--	----	74 ± 2 STD
+ ZnO-812/SS	3.5 / 1.0 / 0.5	29 ± 0 STD	73 ± 3 STD	136 ± 4 STD	167 ± 3 STD
+ ZnO-812/SS	3.0 / 1.0 / 1.0	--	--		201 ± 4 STD

Dose: 0.55 mg/cm² PMMA substrate

Figure 6 shows the significant, synergistic increases in *in-vitro* SPF across the aromatic and non-aromatic carrier oils.

10

The UVA1 data summarized in Table VIII-B shows higher values for wavelengths at 0.5 absorbance units. However, the trend was the same as noted previously in that the UVA1 wavelength numbers @0.5 abs were similar between the plain ZnO and the ZnO-GEMs. As shown in Figure 8, the synergistic differences in UVA1 magnitudes between the ZnO and the ZnO-GEMs became more apparent in the 340 – 370 nm region.

15

Table VIII-B ZnO and ZnO-GEMs in Solastay Carrier Oil Dispersions					
Absorption Response of UVA1					
		UVA1 (λ nm @0.5 abs)			
<u>Sample</u>	<u>Ratio</u>	<u>IPM</u>	<u>EB</u>	<u>BHB</u>	<u>OS</u>
Solvent	Neat	--	--	--	--
+ SS	4.5 / 0.5	374.0	380.0	376.0	377.0
+ J208-612 / SS	4.4 / 0.1 / 0.5	374.0	381.0	375.5	378.5
+ J208-812 / SS	4.4 / 0.1 / 0.5	374.5	382.0	375.0	378.5
+ ZnO / SS	3.5 / 1.0 / 0.5	381.5	393.0	387.0	391.5
+ ZnO-612 / SS	3.5 / 1.0 / 0.5	385.0	397.0	391.5	390.0
+ ZnO-812 / SS	3.8 / 1.0 / 0.2	--	--	--	382.0
+ ZnO-812 / SS	3.5 / 1.0 / 0.5	384.0	394.0	389.0	390.5
+ ZnO-812 / SS	3.0 / 1.0 / 1.0	--	--	--	397.0

Dose: 0.55 mg/cm² PMMA substrate

Study 8

5 This Study was a continuation of Study 7 whereby the effects of the addition of Kraton to the ZnO and ZnO-GEM Solastay/carrier oil dispersions were investigated. The *in-vitro* SPF data in Table IX-A showed increasing magnitudes across the non-aromatic and aromatic carrier oils.

Table IX-A ZnO and ZnO-GEMs in Kraton / Solastay Carrier Oil Dispersions					
Absorption Response of In-vitro SPF					
		<i>in-vitro</i> SPF (units)			
<u>Sample</u>	<u>Ratio</u>	<u>IPM/K</u>	<u>EB/K</u>	<u>BHB/K</u>	<u>OS/K</u>
Solvent	Neat	1 $\pm$ 0 STD	1 $\pm$ 0 STD	13 $\pm$ 0 STD	12 $\pm$ 0 STD
+ SS	4.5 / 0.5	22 $\pm$ 1 STD	32 $\pm$ 0 STD	61 $\pm$ 2 STD	80 $\pm$ 1 STD
+J208- 612 / SS	4.4 / 0.1 / 0.5	20 $\pm$ 1 STD	32 $\pm$ 0 STD	71 $\pm$ 2 STD	81 $\pm$ 3 STD
+J208- 812 / SS	4.4 / 0.1 / 0.5	22 $\pm$ 1 STD	31 $\pm$ 1 STD	71 $\pm$ 2 STD	81 $\pm$ 3 STD
+ ZnO / SS	3.5 / 1.0 / 0.5	42 $\pm$ 1 STD	92 $\pm$ 2 STD	162 $\pm$ 6 STD	214 $\pm$ 3 STD
+ ZnO-612 / SS	3.5 / 1.0 / 0.5	56 $\pm$ 2 STD	113 $\pm$ 3 STD	181 $\pm$ 2 STD	232 $\pm$ 2 STD
+ ZnO-812 / SS	3.8 / 1.0 / 0.2	--	--	--	103 $\pm$ 3 STD
+ ZnO-812 / SS	3.5 / 1.0 / 0.5	77 $\pm$ 7 STD	131 $\pm$ 4 STD	194 $\pm$ 2 STD	255 $\pm$ 3 STD
+ ZnO-812 / SS	3.0 / 1.0 / 1.0	--	--	--	304 $\pm$ 5 STD

10 Dose: 0.55 mg/cm² PMMA substrate

The synergies between the Kraton/Solastay combination with the ZnO and ZnO-GEMs in carrier oil dispersions are shown in Figure 7.

15 The UVA1 data summarized in Table IX-B shows higher values for wavelengths at 0.5 absorbance compared to those in Table VIII-B. However, the trend was the same

as noted previously in that the wavelength numbers @0.5abs were similar between the plain ZnO and the ZnO-GEMs. It was in Figure 8 that the synergistic differences in UVA1 magnitudes between the wavelengths of 340 – 380 nm were demonstrated amongst the dispersions.

5

Table IX-B ZnO and ZnO-GEMs in Kraton / Solastay Carrier Oil Dispersions					
Absorption Response of UVA1					
		UVA1 (λ nm @0.5 abs)			
<u>Sample</u>	<u>Ratio</u>	<u>IPM/K</u>	<u>EB/K</u>	<u>BHB/K</u>	<u>OS/K</u>
Solvent	Neat	--	--	--	--
+ SS	4.5 / 0.5	377.0	383.0	377.0	379.5
+ J208-612 / SS	4.4 / 0.1 / 0.5	377.0	384.0	380.0	380.5
+ J208-812 / SS	4.4 / 0.1 / 0.5	377.0	383.5	380.0	381.0
+ ZnO / SS	3.5 / 1.0 / 0.5	390.5	395.5	391.0	394.0
+ ZnO-612 / SS	3.5 / 1.0 / 0.5	392.0	398.0	392.0	395.5
+ ZnO-812 / SS	3.8 / 1.0 / 0.2	--	--	--	384.0
+ ZnO-812 / SS	3.5 / 1.0 / 0.5	392.0	396.0	392.5	395.0
+ ZnO-812 / SS	3.0 / 1.0 / 1.0	--	--	--	400.0

Dose: 0.55 mg/cm² PMMA substrate

Study 9

10 Samples prepared for Study 9, 10, and 11 contain carrier oils at 20% of the concentration used in Study 5, 6, 7, and 8. Therefore, the *in-vitro* SPF absorption response data for Study 9, 10 and 11 are approximately 20 – 30% of the values observed for the latter studies. The remaining amount of carrier oil was replaced with the transparent UV absorbing material, Cosmosurf CE100, to investigate its effects on the

15 UVR absorption responses of plain ZnO and ZnO-GEMs. The dilution effect was necessary to be able to spread enough dispersion over the PMMA substrate and have measureable values that would fall below the maximum absorbance range limit of the instrument.

20 The data in Table X-A shows an unexpected increase in *in-vitro* SPF values across the aromatic and non-aromatic polar diluents, and from plain ZnO to ZnO-GEMs. Surprisingly, the *in-vitro* SPF data in Table X-A multiplied by a factor of 3 or 4 (OS content is 1/4 amount previously used), yielded significantly larger values than those listed in Table V-A. As a conservative theoretical example, the CE100/OS/ZnO-812

(ratio of 3:1:1) SPF value of $93 \times 3 = 279$ SPF units is significantly higher compared to the *in-vitro* SPF 94 of OS/ZnO-812 (ratio 4:1) dispersion.

Table X-A ZnO and ZnO-GEMs in CE100 Carrier Oil Dispersions					
Absorption Response of In-Vitro SPF					
		<i>in-vitro</i> SPF (units)			
Sample	Ratio	IPM	EB	BHB	OS
CE100/Solvent	4.0 / 1.0	1 $\pm$ 0 STD	1 $\pm$ 0 STD	4 $\pm$ 0 STD	8 $\pm$ 0 STD
+ J208-612	3.9 / 1.0 / 0.1	1 $\pm$ 0 STD	1 $\pm$ 0 STD	3 $\pm$ 0 STD	6 $\pm$ 0 STD
+ J208-812	3.9 / 1.0 / 0.1	1 $\pm$ 0 STD	1 $\pm$ 0 STD	3 $\pm$ 0 STD	6 $\pm$ 0 STD
+ ZnO	3.0 / 1.0 / 1.0	11 $\pm$ 0 STD	31 $\pm$ 0 STD	51 $\pm$ 3 STD	46 $\pm$ 1 STD
+ ZnO-612	3.0 / 1.0 / 1.0	--	--	--	65 $\pm$ 2 STD
+ ZnO-812	3.5 / 1.0 / 0.5	--	--	--	38 $\pm$ 1 STD
+ ZnO-812	3.0 / 1.0 / 1.0	19 $\pm$ 1 STD	40 $\pm$ 2 STD	80 $\pm$ 3 STD	93 $\pm$ 4 STD
+ ZnO-812	2.0 / 1.0 / 2.0	--	--	--	121 $\pm$ 3 STD

Dose: 0.55 mg/cm² PMMA substrate

5

Figure 9 illustrates the synergistic increase in UVR absorption response between plain ZnO and the ZnO-GEMS in the presence of CE100 and carrier oil. Since the GEM materials of J208-612 and J208-812 are transparent to UVR, it is unexpected that electrostatic complexation with ZnO would enhance absorption throughout the entire UVR region.

10

Small increases in UVA1 wavelength at 0.5 absorbance units were also noted between the ZnO and ZnO-GEM materials, as shown in Table X-B. However, Figure 9 also clearly shows the UVA1 absorption synergy in the 340 to 400 nm region between ZnO and the ZnO-GEMs.

15

Table X-B ZnO and ZnO-GEMs in CE100 Carrier Oil Dispersions					
Absorption Response of UVA1					
		UVA1 (λ nm @0.5 abs)			
Sample	Ratio	IPM	EB	BHB	OS
CE100/Solvent	4.0 / 1.0	--	--	--	--
+ 612	3.9 / 1.0 / 0.1	--	--	--	--
+ 812	3.9 / 1.0 / 0.1	--	--	--	--
+ ZnO	3.0 / 1.0 / 1.0	380.0	383.0	381.0	378.0
+ ZnO-612	3.0 / 1.0 / 1.0	--	--	--	379.0
+ ZnO-812	3.5 / 1.0 / 0.5	--	--	--	376.0
+ ZnO-812	3.0 / 1.0 / 1.0	381.0	384.5	382.0	381.5
+ ZnO-812	2.0 / 1.0 / 2.0	--	--	--	386.0

Dose: 0.55 mg/cm² PMMA substrate

Study 10

- 5 As a follow-up to Study 9, Solastay was introduced to the ZnO and ZnO-GEM CE100/carrier oil dispersions. The results were quite surprising because the *in-vitro* SPF values for the ZnO and ZnO-GEM CE100/Solvent/SS dispersions were higher than those for the analogous Solvent/SS dispersions. For example,
- CE100/Octisalate/Solastay/ZnO-812 (ratio 2.5/1.0/0.5/1.0) *in-vitro* SPF was 193 units,
- 10 whereas the *in-vitro* SPF for Octisalate/Solastay/ZnO-812 (ratio 3.5/0.5/1.0) was 167 units. The difference between 193 *in-vitro* SPF units versus 167 *in-vitro* SPF units was very surprising because the former contained only about 30% of the amount of octisalate versus the latter. Figure 10 demonstrates the further synergistic increase in UVR absorption response between plain ZnO and the ZnO-GEMS when Solastay is
- 15 added to CE100 and carrier oil.

Table XI-A ZnO and ZnO-GEMs in Solastay CE100 Carrier Oil Dispersions					
Absorption Response of In-Vitro SPF					
		<i>in-vitro</i> SPF (units)			
Sample	Ratio	IPM	EB	BHB	OS
CE100/Solvent	4.0/1.0	1 $\pm$ 0 STD	1 $\pm$ 0 STD	4 $\pm$ 0 STD	8 $\pm$ 0 STD
CE100/Solvent/SS	3.5/1.0/0.5	21 $\pm$ 1 STD	34 $\pm$ 2 STD	55 $\pm$ 1 STD	70 $\pm$ 3 STD
+ ZnO	2.5/1.0/0.5/1.0	56 $\pm$ 1 STD	83 $\pm$ 2 STD	119 $\pm$ 2 STD	131 $\pm$ 3 STD
+ ZnO-612	2.5/1.0/0.5/1.0	--	--	--	170 $\pm$ 2 STD
+ ZnO-812	2.5/1.0/0.5/1.0	74 $\pm$ 2 STD	116 $\pm$ 3 STD	171 $\pm$ 3 STD	193 $\pm$ 7 STD

Dose: 0.55 mg/cm² PMMA substrate

Control Sample: CE100/SS, Ratio 4.5/0.5, *in-vitro* SPF = 21 ± 1 STD, UVA1 (λ nm @0.5 abs) = 381

The UVA1 data presented in Table XI-B shows an overall increase in breadth of absorption, especially noted for the ZnO-812 complex. Figure 12 clearly shows the further enhanced UVA1 absorption synergy of ZnO-812 in the 340 to 380 nm region when Solastay is present in the CE100/Solvent dispersion.

**Table XI-B ZnO and ZnO-GEMs in Solastay CE100 Carrier Oil Dispersions
Absorption Response of UVA1**

Sample	Ratio	UVA1 (λ nm @0.5 abs)			
		IPM	EB	BHB	OS
CE100/Solvent	4.0 / 1.0	--	--	--	--
CE100/Solvent/SS	3.5/1.0/0.5	380.0	383.0	381.0	382.0
+ ZnO	2.5/1.0/0.5/1.0	392.5	395.5	393.0	394.0
+ ZnO-612	2.5/1.0/0.5/1.0	--	--	--	389.0
+ ZnO-812	2.5/1.0/0.5/1.0	392.5	395.0	394.0	397.0

Dose: 0.55 mg/cm² PMMA substrate

Control Sample: CE100/SS, Ratio 4.5/0.5, *in-vitro* SPF = 21 ± 1 STD, UVA1 (λ nm @0.5 abs) = 381

Study 11

In Study 11, the effects of Kraton on UVR absorption in ZnO and ZnO-GEM dispersions containing CE100 with Solastay and carrier oil were investigated. Kraton remained uniformly dispersed in the aromatic carrier oil dispersions that contained Solastay as well as CE100. If Solastay was absent the Kraton polymer agglomerated in a non-uniform manner. The observed *in-vitro* SPF values were significantly higher than those values in the previous study. The combination of Kraton and Solastay synergistically enhanced the UVR absorption responses of ZnO and ZnO-GEMs in CE100/carrier oil dispersions containing BHB and octisalate. Figure 11 demonstrates the further synergistic increase in UVR absorption response between plain ZnO and the ZnO-GEMS when Kraton is added to CE100/Carrier Oil/Solastay dispersion.

Table XII-A ZnO and ZnO-GEMs in Kraton / Solastay CE100 Carrier Oil Dispersions					
Absorption Response of In-Vitro SPF					
		<i>in-vitro</i> SPF (units)			
<u>Sample</u>	<u>Ratio</u>	<u>IPM/K</u>	<u>EB/K</u>	<u>BHB/K</u>	<u>OS/K</u>
CE100/Solvent	4.0 / 1.0	Incompatible	Incompatible	--	--
CE100/Solvent/SS	3.5/1.0/0.5	Incompatible	Incompatible	70 $\pm$ 3 STD	94 $\pm$ 3 STD
+ ZnO	2.5/1.0/0.5/1.0	--	--	139 $\pm$ 4 STD	168 $\pm$ 3 STD
+ ZnO-612	2.5/1.0/0.5/1.0	--	--	--	213 $\pm$ 2 STD
+ ZnO-812	2.5/1.0/0.5/1.0	Incompatible	Incompatible	201 $\pm$ 5 STD	253 $\pm$ 4 STD

Dose: 0.55 mg/cm² PMMA substrate

Figure 12 clearly shows the further enhanced UVA1 absorption synergy of ZnO-812 in the 340 to 380 nm region when Kraton is added to CE100 / Carrier Oil / Solastay dispersion.

Table XII-B ZnO and ZnO-GEMs in Kraton / Solastay CE100 Carrier Oil Dispersions					
Absorption Response of UVA1					
		UVA1 (λ nm @0.5 abs)			
<u>Sample</u>	<u>Ratio</u>	<u>IPM/K</u>	<u>EB/K</u>	<u>BHB/K</u>	<u>OS/K</u>
CE100/Solvent	4.0 / 1.0	Incompatible	Incompatible	Incompatible	Incompatible
CE100/Solvent/SS	3.5/1.0/0.5	Incompatible	Incompatible	381.0	383.0
+ ZnO	2.5/1.0/0.5/1.0	--	--	395.0	395.0
+ ZnO-612	2.5/1.0/0.5/1.0	--	--	--	393.5
+ ZnO-812	2.5/1.0/0.5/1.0	Incompatible	Incompatible	395.0	397.0

Dose: 0.55 mg/cm² PMMA substrate

Study 12

A series of oil-in-water sunscreen emulsions were prepared to examine the synergistic SPF boosting effect of Kraton 1650G, Solastay and Cosmosurf CE-100 on various physical sunscreens – uncoated ZnO, and ZnO-GEM complexes. It should be noted that organic sunscreens were also included in the formulas. The *in-vitro* and *in-vivo* data are summarized separately in Table XIII below. The addition of CE-100 further boosts the efficiency of ZnO and ZO-812 to absorb UV radiation.

Table XIII - Oil-in-Water Emulsion Lotion SPF 30

%	<u>E0057-37</u>	<u>E0057-13</u>	<u>E0057-35</u>	<u>E0057-36</u>	<u>E0057-34</u>	<u>E0057-10</u>
	ZnO-812	ZnO-812	ZnO-812	ZnO-812	ZnO-812	ZnO-812
3.00	CE-100	--	CE-100	CE-100	CE-100	--
3.00	Kraton	Kraton	--	Kraton	--	--
0.26	Solastay	Solastay	Solastay	--	--	--
1.00						
.....						
SPF <i>in-vitro</i>	75 ± 2	70 ± 1	66 ± 2	30 ± 1	29 ± 1	28 ± 2
SPF <i>in-vivo</i>	48 ± 0	40 ± 3	37 ± 2	39 ± 2	38 ± 0	32 ± 0
%	<u>E0057-29</u>	<u>E0057-09</u>	<u>E0057-35</u>	<u>E0057-36</u>	<u>E0057-34</u>	<u>E0057-06</u>
	ZnO	ZnO	ZnO	ZnO	ZnO	ZnO
3.00	CE-100	--	CE-100	CE-100	CE-100	--
3.00	Kraton	Kraton	--	Kraton	--	--
0.26	Solastay	Solastay	Solastay	--	--	--
1.00						
.....						
SPF <i>in-vitro</i>	68 ± 2	60 ± 2	57 ± 1	29 ± 1	27 ± 0	26 ± 1
SPF <i>in-vivo</i>	41 ± 0	41 ± 3	Not tested	Not tested	31 ± 0	32 ± 1

5 First, it should be noted that the trends noted in the *in-vitro* SPF data of Table XIII match the trends noted in the oil phases summarized in Tables I-A through XII-A.

Surprisingly, for a low (3%) concentration level of physical sunscreen, there was an increase of 16 *in-vivo* SPF units for ZnO-812 with no adjuvants compared to the formula with the synergistic system (Kraton, Solastay, CE-100) of adjuvants. Interestingly, in the analogous ZnO series, there was an increase of 9 *in-vivo* SPF units for ZnO with no adjuvants compared to the formula with the synergistic system (Kraton, Solastay, CE-100) of adjuvants. At higher concentrations of ZnO and ZnO-812 it is possible that more of a differential would be noted in the *in-vivo* SPF data.

15

Ingredient ranges were varied as follows:

	ZnO	0.00, 3.00
	ZnO-812	0.00, 3.00
	Cosmosurf CE-100	0.00, 3.00%
5	Kraton 1650G	0.00, 0.26%
	Solastay	0.00, 1.00%
	Octisalate	0.00, 5.00%
	Homosalate	0.00, 10.00%
10	Octocrylene	0.00, 2.40%

Study 13

A series of water-in-oil sunscreen lotion emulsions were prepared to confirm that
 15 the *synergistic in-vitro* effects noted above would translate to an inverse emulsion.
 Also, ingredient ranges were varied as follows:

	ZnO	0.00, 3.00 – 15.00%
	ZnO-812	0.00, 3.00 – 15.00%
20	Cosmosurf CE-100	0.00, 0.50 – 20.00%
	Kraton 1650G	0.00, 0.10 – 0.52%
	Solastay	0.00, 1.00 – 3.00%
	Octisalate	0.00, 3.00 – 5.00%
25	Homosalate	0.00, 6.00 – 10.00%
	Octocrylene	0.00, 2.40 – 5.00%
	Avobenzene	0.00, 2.00 – 3.00%

The *in-vitro* data summarized in Table IV below confirm that the combination of
 30 Kraton and Solastay synergistically enhances the UV absorption ability of ZnO and
 ZnO-812. The presence of Cosmosurf CE-100 further enhances that synergy as
 indicated in Table XIV below. This holds true despite the fact that, as previously

established (e.g., in Table IIA above, sample ID# 0008-85-1), CE100 has minimal if any SPF on its own.

Table XIV - Water-in-Oil Emulsion Lotion SPF 30

%	<u>E0057-141</u>	<u>E0057-135</u>	%	<u>E0091-015</u>	<u>E0091-011</u>
3.00	ZnO-812	ZnO-812	5.00	ZnO-812	ZnO-812
3.00	CE-100	--	3.00	CE-100	--
0.26	Kraton	Kraton	0.26	Kraton	Kraton
1.00	Solastay	Solastay	1.00	Solastay	Solastay
.....					
SPF <i>in-vitro</i>	227 ± 4	212 ± 3	SPF <i>in-vitro</i>	232 ± 2	217 ± 3
%	<u>E0057-138</u>	<u>E0057-09</u>	%	<u>E0091-012</u>	<u>E0091-010</u>
3.00	ZnO	ZnO	5.00	ZnO	ZnO
3.00	CE-100	--	3.00	CE-100	--
0.26	Kraton	Kraton	0.26	Kraton	Kraton
1.00	Solastay	Solastay	1.00	Solastay	Solastay
.....					
SPF <i>in-vitro</i>	211 ± 6	191 ± 2	SPF <i>in-vitro</i>	218 ± 1	203 ± 3

Study 14

A series of oil-in-water sunscreen crème emulsions were prepared to confirm that the synergistic *in-vitro* effects noted above would translate to a different product form, in this case a cream (Table XV) and a stick (Table XVI). Ingredient ranges were varied as follows:

15	ZnO	0.00, 3.00 – 15.00%
	ZnO-812	0.00, 3.00 – 15.00%
	Cosmosurf CE-100	0.00, 0.50 – 20.00%
	Kraton 1650G	0.00, 0.10 – 0.52%
	Solastay	0.00, 1.00 – 3.00%
20	Octisalate	0.00, 3.00 – 5.00%
	Homosalate	0.00, 6.00 – 10.00%

Octocrylene 0.00, 2.40 – 5.00%

Avobenzene 0.00, 2.00 – 3.00%

The in-vitro data summarized in Table XV confirm that the combination of Kraton and Solastay synergistically enhances the UV absorption ability of ZnO and ZnO-812 in cream form. The presence of Cosmosurf CE-100 further enhances that synergy as indicated.

Table XV - Oil-in-Water Emulsion Crème SPF 30

%	<u>E0057-083</u>	<u>E0057-079</u>	%	<u>E0057-124</u>	<u>E0057-120</u>
3.00	ZnO-812	ZnO-812	5.00	ZnO-812	ZnO-812
3.00	CE-100	--	3.00	CE-100	--
0.26	Kraton	Kraton	0.26	Kraton	Kraton
1.00	Solastay	Solastay	1.00	Solastay	Solastay
.....					
SPF <i>in-vitro</i>	165 ± 2	135 ± 2	SPF <i>in-vitro</i>	128 ± 1	117 ± 1
%	<u>E0057-081</u>	<u>E0057-078</u>	%	<u>E0057-121</u>	<u>E0057-119</u>
3.00	ZnO	ZnO	5.00	ZnO	ZnO
3.00	CE-100	--	3.00	CE-100	--
0.26	Kraton	Kraton	0.26	Kraton	Kraton
1.00	Solastay	Solastay	1.00	Solastay	Solastay
.....					
SPF <i>in-vitro</i>	150 ± 3	124 ± 3	SPF <i>in-vitro</i>	116 ± 0	109 ± 3

A series of sunscreen sticks were prepared to confirm that the *synergistic in-vitro* effects noted above would translate to a different product form. Ingredient ranges were varied as follows:

ZnO 0.00, 3.00 – 15.00%

ZnO-812 0.00, 3.00 – 15.00%

Cosmosurf CE-100 0.00, 0.50 – 20.00%

Kraton 1650G 0.00, 0.10 – 0.52%

Solastay 0.00, 1.00 – 3.00%

Octisalate	0.00, 3.00 – 5.00%
Homosalate	0.00, 6.00 – 10.00%
Octocrylene	0.00, 2.40 – 5.00%
Avobenzene	0.00, 2.00 – 3.00%

5

The in-vitro data summarized in Table XVI confirm that the combination of Kraton and Solastay synergistically enhances the UV absorption ability of ZnO and ZnO-812 in a stick form. The presence of Cosmosurf CE-100 further enhances that synergy as indicated in the Table below.

10

Table XVI - Sunscreen Stick SPF 30

%	<u>E0057-103</u>	<u>E0057-097</u>	<u>E0057-101</u>
3.00	ZnO-812	ZnO-812	ZnO-812
3.00	CE-100	--	CE-100
0.26	Kraton	Kraton	--
1.00	Solastay	Solastay	--
.....			
SPF <i>in-vitro</i>	91 $\pm$ 0	84 $\pm$ 3	64 $\pm$ 3
%	<u>E0057-100</u>	<u>E0057-078</u>	<u>E0057-098</u>
3.00	ZnO	ZnO	ZnO
3.00	CE-100	--	CE-100
0.26	Kraton	Kraton	--
1.00	Solastay	Solastay	--
.....			
SPF <i>in-vitro</i>	81 $\pm$ 1	67 $\pm$ 4	56 $\pm$ 1

Study 15

15

Previously, the SPF boosting effects of Kraton 1650G and Solastay on uncoated ZnO and GEM (gelling electrostatic matrix) ZnO were illustrated. In Table XVII, ZnO is complexed with Triethoxycaprylsiloxane (TECS). The data indicate that the combination of Kraton 1650G and Solastay boosted the UV absorption ability of the ZnO-TECS, and that the addition of CE-100 further boosted that capability as shown below.

20

Table XVII - ZnO Coated with Triethoxycaprylylsiloxane (TECS) and Kratons

	<u>E0091-095-1</u> ZnO-TECS CE-100 Kraton 1650G Solastay	<u>E0057-078</u> ZnO-TECS -- Kraton 1650G Solastay		<u>E0057-098</u> ZnO-TECS -- Kraton 1650G --
..... SPF <i>in-vitro</i>	107 $\pm$ 3	99 $\pm$ 1		26 $\pm$ 1
For Relative Comparison	<u>E3088-75-8</u> ZnO-812 CE-100 Kraton 1650G Solastay	<u>E0057-075-10</u> ZnO-812 -- Kraton 1650G Solastay	<u>E0057-075-10</u> ZnO-812 -- -- Solastay	
..... SPF <i>in-vitro</i>	156 $\pm$ 10	129 $\pm$ 4	52 $\pm$ 3	

5

Study 16

In another study, the SPF boosting effects of Kraton 1650G and Solastay on two complexed titanium dioxides was examined. The data indicated that the combination of Kraton 1650G and Solastay boosted the UV absorption ability of the TiO₂-M262 and TiO₂-JTTO, and that the addition of CE-100 further boosted that capability as shown below.

10

Table XVIII - TiO₂ Complexed with Alumina/Dimethicone (M262) or Alumina/Methicone (JTTO)

	<u>E0091-078-10</u> <u>TiO₂-M262</u> CE-100 Kraton 1650G Solastay	<u>E0091-077-4</u> <u>TiO₂-M262</u> -- Kraton 1650G Solastay	<u>E0091-077-3</u> <u>TiO₂-M262</u> -- Kraton 1650G --
..... SPF <i>in-vitro</i>	130 ± 2	103 ± 5	48 ± 2
	<u>E0091-078-13</u> <u>TiO₂-JTTO</u> CE-100 Kraton 1650G Solastay	<u>E0091-077-7</u> <u>TiO₂-JTTO</u> -- Kraton 1650G Solastay	<u>E0091-077-4</u> <u>TiO₂-JTTO</u> -- Kraton 1650G --
..... SPF <i>in-vitro</i>	144 ± 2	120 ± 3	103 ± 5

5

10

Finally, in the data of Tables II - XVIII, Kraton G1650 was used. However, as previously discussed, other Kraton® polymers are suitable, such as Kraton D1164PT (styrene/isoprene copolymer) and Kraton G1702HU (hydrogenated styrene/isoprene copolymer). In testing data similar to that provided above, these two additional Kratons were evaluated based on their effectiveness in boosting SPF of ZnO and ZnO-812. Kraton 1650G was found to be the most effective, but the other Kraton polymers may be preferred in other compositions or for other reasons. It is also expected that the trends noted for the octisalate solvent/Kraton variants would be the same for the less polar solvents of Hallbrite BHB, Finsolv EB, and isopropyl myristate.

15

20

While the present disclosure has been described with reference to one or more exemplary embodiments, it will be understood by those skilled in the art that various changes may be made and equivalents may be substituted for elements thereof without departing from the scope of the present disclosure. In addition, many modifications may be made to adapt a particular situation or material to the teachings of the disclosure without departing from the scope thereof. Therefore, it is intended that the present

disclosure not be limited to the particular embodiment(s) disclosed as the best mode contemplated.

What is claimed is:

1. A composition, comprising:

0.5% wt% to 30 wt% of a physical sunscreen;

0.1 wt% to 6.0 wt% of ethylhexyl methoxycrylene;

a carrier oil; and

at least one of a compound having multiple phenyl groups, a silicone surfactant, and a dispersant.

2. The composition of claim 1, wherein said compound having multiple phenyl groups is present and is selected from the group consisting of benzene sulfonic acids, salts of benzene sulfonic acids, styrenic block copolymers with a hydrogenated midblock of styrene-ethylene/butylene-styrene, styrenic block copolymers with a hydrogenated midblock of styrene-ethylene/propylene-styrene, styrene/butadiene/styrene block copolymers, styrene/isoprene/styrene block copolymers, ethylene/butadiene/styrene block copolymer, ethylene/propylene/styrene block copolymer, styrene/ethylene/butadiene block copolymer, styrene/propylene/butadiene block copolymer, derivatives of any of said compounds having multiple phenyl groups, and any combinations thereof.

3. The composition of claim 1, wherein said compound having multiple phenyl groups is selected from the group consisting of benzene sulfonic acids, salts of benzene sulfonic acids, styrene/ethylene/butadiene block copolymer, and any combinations thereof.

4. The composition of claim 1, wherein said compound having multiple phenyl groups is a styrene/ethylene/butadiene block copolymer.

5. The composition of claim 2, wherein said compound having multiple phenyl groups is present in an amount of 0.1% wt% to 4.0% wt%.

6. The composition of claim 2, wherein said compound having multiple phenyl groups is present in an amount of 0.2 wt% to 1.0 wt%.

7. The composition of claim 1, wherein said ethylhexyl methoxycrylene is present in an amount of 0.2 wt% to 2.0 wt%.

8. The composition of claim 1, wherein said dispersant is octyldodecyl-propyl-citrate, present in an amount of 0.5% wt% to 20% wt%.

9. The composition of claim 1, wherein said silicone surfactant is present, and is selected from the group consisting of lauryl polyethylene glycol-8 dimethicone, a derivative thereof, or a combination of the two.

10. The composition of claim 9, wherein said silicone surfactant is present in an amount of 0.1 wt% to 10.0 wt%.

11. The composition of claim 1, wherein said carrier oil is selected from the group consisting of mineral oil, isopropyl myristate, butyloctyl salicylate, ethylhexyl salicylate, and any combinations thereof.

12. The composition of claim 1, further comprising water.

13. The composition of claim 12, wherein the composition is an oil-in-water emulsion.

14. The composition of claim 12, wherein the composition is a water-in-oil emulsion.

15. The composition of claim 1, further comprising an organic sunscreen.

16. The composition of claim 15, wherein said organic sunscreen is selected from the group consisting of octisalate, homosalate, octocrylene, avobenzone, and any combinations thereof.

17. A composition, comprising:

0.5% wt% to 30 wt% of a physical sunscreen selected from the group consisting of titanium dioxide, zinc oxide, coated zinc oxide, or a combination thereof;

5 0.1 wt% to 6.0 wt% of ethylhexyl methoxycrylene;

0.2 wt% to 1.0 wt% of a compound having multiple phenyl groups selected from the group consisting of benzene sulfonic acids, salts of benzene sulfonic acids, styrenic block copolymers with a hydrogenated midblock of styrene-ethylene/butylene-styrene, styrenic block copolymers with a hydrogenated midblock of styrene-ethylene/propylene-
10 styrene, styrene/butadiene/styrene block copolymers, styrene/isoprene/styrene block copolymers, ethylene/butadiene/styrene block copolymer, ethylene/propylene/styrene block copolymer, styrene/ethylene/butadiene block copolymer, styrene/propylene/butadiene block copolymer, and derivatives or combinations thereof;
and

15 a carrier oil.

18. The composition of claim 17, wherein said compound having multiple phenyl groups is a styrene/ethylene/butadiene block copolymer.

20 19. The composition of claim 17, further comprising 0.5% wt% to 20% wt% of octyldodecyl-propyl-citrate.

20. The composition of claim 17, further comprising 0.1 wt% to 10.0 wt% of a silicone surfactant selected from the group consisting of lauryl polyethylene glycol-8
25 dimethicone, a derivative thereof, or a combination of the two.

**Figure 1 UVR Absorption Synergy of ZnO-812
versus ZnO with and without Solastay**







Figure 2 *in-vitro* SPF Synergy between Kraton and Solastay in CE100 /Polar Solvent Dispersions




**Figure 3 *in-vitro* SPF Synergy of ZnO-GEMs
in Polar Solvent Dispersions**




**Figure 4 *in-vitro* SPF Synergy of ZnO-GEMs
in Polar Solvent / Kraton Dispersions**



**Figure 5 UVA1 Absorption Synergy of ZnO-GEMs in
Kraton & non-Kraton Polar Solvent Dispersions**



**Figure 6 *in-vitro* SPF Synergy of ZnO-GEMs
in Polar Solvent / Solastay Dispersions**



**Figure 7 *in-vitro* SPF Synergy of ZnO-GEMs
in Polar Solvent / Kraton / Solastay Dispersions**






Figure 8 UVA1 Absorption Synergy of ZnO-GEMS in Kraton
& non-Kraton Polar Solvent / Solastay Dispersions



**Figure 9 UVR Absorption Synergy of ZnO-GEMs
in CE100 and Polar Solvent Dispersions**



**Figure 10 UVR Absorption Synergy of ZnO-812
in CE100 and Polar Solvent / Solastay Dispersions**




Figure 11 UVR Absorption Synergy of ZnO-GEMs in CE100 and Kraton / Polar Solvent / Solastay Dispersions




Figure 12 UVA1 Absorption Synergy of ZnO-812 in Kraton & non-Kraton CE100 / Polar Solvent / Solastay Dispersions

