



(51) International Patent Classification:

C30B 29/04 (2006.01) **C30B 31/20** (2006.01)
C30B 33/02 (2006.01)

(21) International Application Number:

PCT/EP2010/059084

(22) International Filing Date:

25 June 2010 (25.06.2010)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

0911075.0	26 June 2009 (26.06.2009)	GB
0917219.8	1 October 2009 (01.10.2009)	GB
1003613.5	4 March 2010 (04.03.2010)	GB
1005573.9	1 April 2010 (01.04.2010)	GB
1007728.7	10 May 2010 (10.05.2010)	GB

(71) Applicant (for all designated States except US): **ELEMENT SIX LIMITED** [GB/GB]; Isle of Man Freeport, P O Box 6, Ballasalla, IM99 6AQ (GB).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **TWITCHEN, Daniel James** [GB/GB]; Element Six Limited, King's Ride Park, Ascot Berkshire SL5 8BP (GB). **GEOGHEGAN, Sarah Louise** [GB/GB]; Element Six Limited, King's Ride Park, Ascot Berkshire SL5 8BP (GB). **PERKINS, Neil** [GB/GB]; Element Six Limited, King's Ride Park, Ascot Berkshire SL5 8BP (GB).(74) Agent: **ATKINSON, Ian Anthony**; Element Six Limited, Group Intellectual Property, 3rd Floor, Building 4,

Chiswick Park, 566 Chiswick High Road London Greater London W4 5YE (GB).

(81) **Designated States** (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) **Designated States** (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

— as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))

Published:

— with international search report (Art. 21(3))

(54) Title: METHOD FOR MAKING FANCY PALE BLUE OR FANCY PALE BLUE /GREEN SINGLE CRYSTAL CVD DIAMOND AND PRODUCT OBTAINED




Figure 1

(57) **Abstract:** A method of making fancy pale blue or fancy pale blue/green CVD diamond material is described. The method comprises irradiating single crystal diamond material that has been grown by a CVD process with electrons to introduce isolated vacancies into the diamond material, the irradiated diamond material having (or after a further post- irradiation treatment having) a total vacancy concentration $[V_T]$ and a path length L such that $[V_T] \times L$ is at least 0.072 ppm cm and at most 0.36 ppm cm, and the diamond material becomes fancy pale blue or fancy pale blue/green in colour. Fancy pale blue diamonds are also described.

**METHOD FOR MAKING FANCY PALE BLUE OR FANCY PALE BLUE /GREEN
SINGLE CRYSTAL CVD
DIAMOND AND PRODUCT OBTAINED**

This invention relates to a method of making fancy pale blue or fancy pale blue/green diamond material by irradiating diamond material that has been made by a CVD (chemical vapour deposition) process. The invention also relates to a fancy pale blue or fancy pale blue/green CVD diamond material per se. The invention further provides a system for being able to make a desired colour of diamond material within the fancy blue to blue/green colour range.

The term "fancy-coloured diamond" is a well-established gem trade classification and is used to refer to unusual coloured diamonds. A useful history and background to the grading of fancy coloured diamond gemstones, including the use of Munsell colour charts is given by King et al, in Gems & Gemology, Vol. 30, No. 4, 1994 (pp.220-242).

Diamond materials that exhibit a pronounced amount of colour are known as "fancy" coloured diamonds in the field. Other diamond materials that do not show such pronounced colour may be graded using the Gemological Institute of America (GIA) scale. That scale grades diamond materials alphabetically from D to Z. The GIA scale is well known. D represents the highest grade and most colourless diamond material on the GIA scale, and Z represents the lowest grade on the GIA scale, diamond material of grade Z appearing light yellow to the naked eye. Higher grade diamond materials (those on the GIA scale nearer to grade D) are generally considered more desirable than lower grade diamond materials (those nearer to grade Z), both in the gem trade and for industrial applications. When the colour of diamond material is more intense than the Z grading it is termed a "fancy" diamond whatever its colour. However when an attractive colour such as blue is seen in diamond material it is frequently described as fancy coloured diamond, even though its saturation may be such as to grade it earlier in the alphabet than Z. When grading according to the GIA scale, diamond graders use a master set of diamond stones graded D, E, F etc. up to Z, and ranging in colour from colourless (for all grades up to F) through pale yellows to darker yellows (G to Z). The diamond material to be graded is compared against the master set, and then positioned against its nearest stone in the master set according to its colour saturation. That establishes the colour grade letter for the diamond to be graded, e.g. H or K. After that colour grade letter has been established, for grades from G-Z the colour-grader will also establish a colour to accompany the colour-grade letter. This colour might be for example,

brown, yellow, or blue. Thus, for example, a stone might be graded H(brown), if its colour saturation puts it nearest to the H stone in the colour-grader's master set of colourless to dark yellow stones, and it has a noticeable brown colouration. In terms of colour designations brown stones have a hue angle in the range 0° to less than 90° , and yellow stones have a hue angle in the range 90° - 130° .

Naturally occurring blue diamonds are known. Type IIb diamond material which contains substantially no nitrogen, but does contain boron, absorbs red, orange and yellow light. This diamond material therefore usually appears blue. The introduction in EP0615954A (Sumitomo) includes a table setting out the original colours of various natural rough diamonds including type IIb natural blue diamonds.

It is also known to form fancy coloured diamonds, including blue by treating diamonds that are not originally blue. For example, "Optical Absorption and Luminescence" by John Walker, "Reports on Progress in Physics", Volume 42, 1979, describes *inter alia* that irradiation of any diamond produces a blue-green colouration due to the absorption bands in the red and violet part of the absorption spectrum. This so-called GR1 absorption band is understood to be caused by neutral isolated vacancies V^0 in the diamond structure, each isolated vacancy being known as a "GR1 centre". The strength of the GR1 band is linearly related to the irradiation dose, indicating that the GR1 centre is a purely lattice defect and not related to any impurity in the diamond. The blue-green colouration of diamond material caused by irradiation is exemplified in the Walker publication.

EP615954A and EP316856A describe irradiation of synthetic High Pressure/High Temperature (HPHT) diamond material with an electron beam or a neutron beam to form lattice defects (interstitials and isolated vacancies) in the crystal. Thereafter the diamond crystal is annealed in a prescribed temperature range to form colour centres. These publications describe the production of purple and red/pink diamond materials.

A first aspect of the present invention provides a method of making fancy pale blue or fancy pale blue/green CVD single crystal diamond material comprising the steps of:

i) providing single crystal diamond material that has been grown by a CVD process, the diamond material having a $[N_s^0]$ concentration less than 1 ppm, which provided CVD diamond material is colourless, or if not colourless is colour-graded either brown

or yellow, and if colour-graded brown has a colour grade for a 0.5 ct Round Brilliant Cut diamond stone of G (brown) or better, and if colour-graded yellow has a colour grade for a 0.5 ct Round Brilliant Cut diamond stone of T (yellow) or better; and

- 5 (ii) irradiating, the provided CVD diamond material with electrons so as to introduce isolated vacancies into the diamond material, so that the product of the total vacancy concentration x path length ($[V_T] \times L$) in the irradiated diamond material at this stage, or after a further post-irradiation treatment, is at least 0.072 ppm cm and at most 0.36 ppm cm, whereby the diamond material becomes fancy pale blue or fancy pale
10 blue/green in colour.

The term N_s^0 refers to single substitutional nitrogen atoms in the diamond material.

The perceived colour of any particular diamond stone depends on the size and cut of
15 the diamond. Therefore, where reference is given to the colour-grade of diamond material it is usual in the field to quote this in terms of a standard size, usually 0.5 carat (ct), and a standard cut, usually round brilliant cut (often known as RBC or rbc). For any given diamond stone, be it larger or smaller than 0.5 carat, or round brilliant cut or any other cut, models are available to adjust the colour-grade to that for the
20 standard size and cut. Therefore, the provided diamond material used in the method according to the first aspect of the invention may have any size or cut, but its colour grade where specified is adjusted to the colour grade for that diamond material of standard 0.5 carat size, and standard round brilliant cut .

- 25 The product of isolated vacancy concentration x path length limits can be expressed as:

$$0.36 \text{ ppm cm} \geq [V_T] \times L \geq 0.072 \text{ ppm cm}$$

- 30 Knowing that $1 \text{ ppm} = 1.76 \times 10^{17} \text{ cm}^{-3}$ this can alternatively be written as:

$$2.04 \times 10^{-18} \text{ cm}^{-2} \geq [V_T] \times L \geq 4.09 \times 10^{-19} \text{ cm}^{-2}$$

The path length for a round brilliant polished gem is assumed to be 2 times the depth
35 of the stone. For example, for a 0.5 ct round brilliant cut diamond material with a stone depth of 0.3 cm and therefore an average path length of 0.6 cm – the limits would be:

$$0.6 \text{ ppm} \geq [V_T] \geq 0.12 \text{ ppm}$$

The CVD diamond provided in step (i) of the method according to the first aspect of the invention shall be referred to in this specification as "the provided CVD diamond".

- 5 The step of actually growing the CVD diamond material may or may not form part of the method of embodiments of the invention. Providing a CVD diamond material may simply mean, for example, selecting a pre-grown CVD diamond material.

10 The provided CVD diamond material in the method of the present invention has a $[N_s^0]$ concentration (that is a concentration of single substitutional nitrogen defects) less than 1 ppm. The colour of the provided CVD diamond material may vary according to the $[N_s^0]$ concentration, and the manner in which the diamond material has been grown. It is known that $[N_s^0]$ defects themselves introduce a yellow colouration into diamond material, particularly at concentrations greater than 0.3 ppm
15 in stones bigger than a 0.3 ct rbc.

It is also known that the presence of the low concentrations of nitrogen in a CVD growth environment can affect the nature and concentration of other defects that are incorporated in a CVD synthetic diamond material as the diamond material grows,
20 and that at least some of these other defects provide colour centres contribute to the colour of CVD diamond material, typically introducing a brown colouration to the diamond material.

It is also known that these colour centres that contribute to the brown colouration of
25 CVD diamond grown in the presence of low concentrations of nitrogen are unique to single crystal CVD diamond, or to pieces cut or produced from layers of single crystal CVD diamond. It is furthermore known that the colour centres contributing to brown colouration in CVD diamond are different from those contributing to any brown colouration observed in natural diamond because the defects in the CVD diamond
30 material cause absorption bands in the absorption spectra of the grown CVD diamond material that are not found in the absorption spectra of natural diamond. Evidence for this comes from Raman scattering from non-diamond carbon observable with an infrared excitation source (e.g. 785 nm or 1064 nm) which is not observed for brown natural diamond. Further, it is known that these colour centres in
35 natural diamond material anneal at a different temperature to those in CVD diamond material.

It is believed that some of the colour centres contributing to the brown colouration seen in CVD synthetic diamond grown in processes in which low concentrations of nitrogen are introduced relate to localised disruption of the diamond bonding within the single crystal CVD diamond. The exact nature of the defects is not fully understood, but the use of electron paramagnetic resonance (EPR) and optical absorption spectroscopy techniques have been used to study the nature of the defects and improve our understanding somewhat. The presence of the nitrogen in the grown CVD synthetic diamond material can be evidenced by looking at absorption spectra for the grown CVD diamond material, and analysis of these spectra gives some indication of the relative proportions of different types of defect present. A typical spectrum for grown CVD synthetic diamond material grown with nitrogen added to the synthesis environment shows a peak at about 270 nm, which is generated by the presence of neutral single substitutional nitrogen (N_s^0) atoms in the diamond lattice. Additionally peaks have been observed at about 350 nm and approximately 510 nm corresponding to other defects characteristic and unique to CVD synthetic diamond material, and furthermore a so-called "ramp", that is a rising background of the form $c \times \lambda^{-3}$ has been observed, where c is a constant and λ is the wavelength. While the N_s^0 is primarily identifiable by its peak at 270 nm, it also contributes in smaller amounts to the absorption spectrum at higher wavelengths, in particular at wavelengths in the visible part of the spectrum, which is generally considered to cover the wavelength range 350 nm to 750 nm.

It is the combination of features evident in the visible part of the absorption spectrum of the CVD diamond material, i.e. (a) the N_s^0 contribution in the visible part of the spectrum, (b) the 350 nm peak, (c) the 510 nm peak and (d) the ramp feature, that affect the perceived colour of the diamond material and are believed to be responsible for the brown colour typically seen in nitrogen doped CVD synthetic diamond material. The peaks at 350 nm and 510 nm, are not seen in the absorption spectra of natural diamonds, nor in the absorption spectra of other synthetic diamonds, for example synthetic HPHT diamonds of the type described in EP615954A. For the purposes of this specification, all defects other than the N_s^0 defects that contribute to the absorption spectrum in the visible part of the spectrum, which we have discussed above as the 350 nm, 510 nm and ramp features, will be referred to collectively as "X defects". As noted above, at this time the structural nature of these defects at an atomic level is not understood, merely their effect on the grown diamond material's absorption spectra. Without binding the invention in any way, it is thought that the nature of the defects responsible for the brown colouration

might be related to the presence of multi-vacancy clusters (each cluster being made up of tens of vacancies e.g. 30 or 40 vacancies or more) that are grown-in under large growth rates, concomitant with the addition of nitrogen to the plasma to a hydrogen / methane (H_2/CH_4) source gas. Such clusters are thermally unstable and may be removed to some degree, by high-temperature treatment (i.e. annealing). It is thought that smaller vacancy-related defects, such as a NVH^- (nitrogen-vacancy-hydrogen) defects that are made up of nitrogen and hydrogen and a missing carbon atom, may be partially responsible for the brown colour and these defects may also be removed by high-temperature treatment.

Depending on the method of manufacture, and the $[N_s^0]$ concentration, the provided CVD diamond material used in methods according to the invention may appear colourless, near colourless, pale yellow, or pale brown. According to methods of the present invention, the colour of the provided CVD diamond is graded either colourless or brown or yellow, and if brown is graded G (brown) or better, and if yellow is graded T (yellow) or better (for a 0.5 carat round brilliant cut – RBC) using the Gemological Institute of America (GIA) scale. As noted above that scale grades diamond materials alphabetically from D to Z, diamond material being colour-graded by comparing their colour intensity or saturation (rather than the actual hue – e.g. yellow or brown) to stones of known saturation under controlled lighting and precise viewing conditions. D represents the highest grade and most colourless diamond material on the GIA scale and Z represents the lowest grade on the GIA scale, diamond material of grade Z typically appearing pale yellow or brown to the naked eye. Higher grade diamond materials (those on the GIA scale nearer to grade D) are generally considered more desirable than lower grade diamond materials (those nearer to grade Z), both in the gem trade and for other applications; therefore when we say graded G or better we mean graded G or a letter earlier in the alphabet than G. Diamond materials with a yellow or brown hue are graded alphabetically on the same scale and against the same master set of diamonds for each colour-grade. Therefore a grade of G (brown) means there is some colour and the colour component is brown. Diamond material graded G (yellow) would have the same amount of colour as diamond material graded G (brown) but the colour component would be yellow rather than brown. Typically brown diamond material has a hue angle $<90^\circ$, and yellow diamond material has a hue angle between $90^\circ - 130^\circ$. Diamond material graded F or better has no visible colour and is graded alphabetically only, or alphabetically followed by “colourless” in parentheses. If diamond material has a colour with a yellow or brown hue that is more intense than

the Z grading it enters the realm of “fancy” coloured diamond material. As noted above, diamond material with a detectable hue other than yellow or brown, such as blue, which has a colour strong enough to be recorded, is also referred to as being “fancy”. Diamond material with a blue hue will therefore be termed “fancy” when the intensity of colour is lower than would be the case for yellow or brown coloured diamond.

According to the present invention, a colour grade of G or better is advantageous for any brown provided diamond material, in order after irradiation to achieve a fancy pale blue diamond material. On the other hand, a colour grade of T or better is advantageous for any yellow provided diamond material, this resulting in a fancy pale blue/green diamond material after irradiation. The amount of yellow in the provided diamond material may be increased by increasing the $[N_s^0]$ concentration, providing this can be done without increasing the X defects, and their associated brown colouration. We have advantageously been able to grow CVD diamond with low and controlled levels of nitrogen whilst keeping the concentration of X defects to a minimum. This is not trivial for CVD growth. It advantageously not only provides nitrogen in the CVD growth process which may be advantageous for morphology reasons, but also for some embodiments allows sufficient nitrogen to be present to provide a yellow hue in the provided diamond, which after irradiation according to the invention results in a pale blue/green diamond material. We have advantageously discovered that it is possible to control the nitrogen concentration in the CVD diamond to within 20% of the target whilst maintaining a low concentration of brown defects. This advantageously allows the hue angle of the treated (irradiated) diamond material to be controlled in the range of blue to blue-green as desired.

An alternative or additional manner of defining the colour of the provided CVD diamond material is in terms of its room temperature absorption spectrum. It is advantageous if the above-mentioned X-defects are minimised, and contribute little to the absorption spectrum of the provided diamond material. Typically, where $[N_s^0]$ concentrations are greater than 0.1 ppm in the provided diamond material, but less than 1 ppm, it is preferred that the total integrated absorption in the visible range from 350 nm to 750 nm that is attributable to defects other than N_s^0 is less than 90%, i.e. the brown inducing X-defects are minimised. Where $[N_s^0]$ concentrations are zero or very low, for example less than 0.1 ppm, the total integrated absorption in the visible range from 350 nm to 750 nm that is attributable to defects other than N_s^0 is likely to be greater than 90% even if the brown-inducing X-defects are very low, simply

because $[N_s^0]$ concentrations alone are zero or very low. In these cases it is advantageous if the absorption coefficient (when the spectra have been normalised to 0 cm^{-1} at 800 nm) at 350 nm is less than 0.5 cm^{-1} and at 510 nm is less than 0.3 cm^{-1} , these low absorption coefficients being an indicator of a low level of brown inducing X-defects in the diamond material. It is noted that where $[N_s^0]$ concentrations are greater than 0.1 ppm the absolute values of the absorption coefficients at 350 nm and 510 nm could be greater than 0.5 cm^{-1} and 0.3 cm^{-1} respectively even when $[X \text{ defect}]$ concentrations are low, because of the contribution to the absorption spectra at the 350 nm and 510 nm wavelengths from the N_s^0 defects themselves.

Another aspect of the present invention provides a method of making fancy pale blue or fancy pale blue/green CVD single crystal diamond material comprising the steps of:

i) providing single crystal diamond material that has been grown by a CVD process, the diamond material having a $[N_s^0]$ concentration less than 1 ppm, wherein the total integrated absorption in the visible range from 350 nm to 750 nm that is attributable to defects other than N_s^0 is greater than 90% then the absorption coefficient at 350 nm is less than 0.5 cm^{-1} and the absorption coefficient at 510 nm is less than 0.3 cm^{-1} and

(ii) irradiating, the provided CVD diamond material with electrons so as to introduce isolated vacancies into the diamond material, so that the product of the total vacancy concentration x path length, $[V_T] \times L$ in the irradiated diamond material at this stage, or after a further post-irradiation treatment, being at least 0.072 ppm cm and at most 0.36 ppm cm , whereby the diamond material becomes fancy pale blue or fancy pale blue/green in colour.

For all examples used in this specification absorption peak heights and integrated absorption values used to calculate the percentage of the absorption of the provided CVD diamond attributable to defects other than N_s^0 quoted in this specification are measured using a UV/visible absorption spectrum of the synthetic CVD diamond material taken at room temperature.

All room temperature absorption spectra mentioned herein were collected using a Perkin Elmer Lambda-19 spectrometer. The data recorded in the spectra ("the measured spectrum") were processed in the following way to give information on the

proportion of the measured absorption in the range 350 nm to 750 nm that could be attributed to N_s^0 and the proportion of that measured absorption that can be attributed to other defects (the X defects).

5 a. A reflection loss spectrum was created using tabulated refractive index data and standard expressions for the reflection loss for a parallel-sided plate. The refractive index was determined according to Peter's equation [Z. Phys., 15 (1923), 358-368)] and subsequent reflection loss derived using the standard Fresnel equation.

10

b. The reflection loss spectrum was subtracted from the measured absorbance data and an absorption coefficient spectrum for the example is created from the resulting spectrum.

15 c. In order to determine the component of the measured spectrum that was attributable to N_s^0 , an absorption spectrum for type Ib HPHT synthetic diamond (for which the absorption is attributed solely to N_s^0) was scaled until it is substantially removed the 270 nm peak from the measured spectrum when subtracted from it. This scaling allows the concentration of nitrogen to be determined.

20

d. Using the visible region of the spectrum as stretching from 350 nm (*i.e.* 3.2618 eV) to 750 nm (*i.e.* 1.6527 eV), the integrated absorption in the visible region was determined for the measured example spectrum and for the component of it attributable to N_s^0 , and the percentage of the integrated absorption that is attributable to N_s^0 defects calculated.

25

e. In practice reflection losses are generally greater than the theoretical values and this makes it difficult without resorting to wavelength specific calorimetry methods to determine absolute absorption coefficient values. In order to correct for additional losses not directly related to absorption the following routine was used. Towards lower energies it was generally the case that below a particular energy the measured absorption no longer showed significant variation with energy. Absorption coefficient data were shifted so that absorption coefficient was zero at 800 nm

30

35 According to different embodiments of methods according to the present invention, the provided CVD diamond may or may not contain N_s^0 . Where it does contain N_s^0 ,

the concentration of $[N_s^0]$ present in the synthetic CVD diamond material of the present invention may be measured using EPR for levels $<5 \times 10^{15} \text{ cm}^{-3}$ and using UV visible optical absorption techniques for higher concentrations.

- 5 $[N_s^0]$ in the neutral charge state content can be measured by using electron paramagnetic resonance (EPR). Whilst the method is well-known in the art, for completeness it is summarised here. In measurements conducted using EPR, the abundance of a particular paramagnetic defect (e.g. the neutral single-substitutional nitrogen defect) is proportional to the integrated intensity of all the EPR absorption
- 10 resonance lines originating from that centre. This permits the concentration of the defect to be determined by comparing the integrated intensity to that which is observed from a reference sample, provided care is taken to prevent or correct for the effects of microwave power saturation. Since continuous wave EPR spectra are recorded using field modulation, double integration is required to determine the EPR
- 15 intensity and hence the defect concentration. To minimise the errors associated with double integration, base line correction, finite limits of integration, etc., especially in cases where overlapping EPR spectra are present, a spectral fitting method (using a Nelder-Mead simplex algorithm (J. A. Nelder and R. Mead, The Computer Journal, 7 (1965), 308)) is employed to determine the integrated intensity of the EPR centres
- 20 present in the example of interest. This entails fitting the experimental spectra with simulated spectra of the defects present in the example and determining the integrated intensity of each from the simulation. Experimentally it is observed that neither a Lorentzian nor Gaussian line shape provides a good fit to the experimental EPR spectra, therefore a Tsallis function is used to produce the simulated spectra
- 25 (D.F. Howarth, J.A. Weil, Z. Zimpel, J. Magn. Res., 161 (2003), 215). Furthermore, in the case of low nitrogen concentrations, it is often necessary to use modulation amplitudes approaching or exceeding the line width of the EPR signals to achieve a good signal/noise ratio (enabling accurate concentration determination within a reasonable time frame). Hence pseudo-modulation is employed, with the Tsallis line
- 30 shape in order to produce a good fit to the recorded EPR spectra (J.S. Hyde, M. Pasenkiewicz-Gierula, A. Jesmanowicz, W.E. Antholine, Appl. Magn. Reson., 1 (1990), 483). Using this method the concentration in ppm can be determined with a reproducibility of better than $\pm 5\%$.
- 35 The technique of UV-visible absorption spectroscopy for measuring higher $[N_s^0]$ concentrations is well-known in the art, and involves measurements using the 270 nm peak of the absorption spectrum of the diamond material.

Nitrogen may also be present in the positive charge state (N^+), the concentration of N^+ is found by measuring the peak height of the feature at 1332 cm^{-1} in the FTIR spectrum. SIMS techniques may also be used to obtain a total nitrogen
5 concentration for the diamond material if the concentration is within the detection limit.

As noted above, a colour grade of G or better is advantageous for any brown provided diamond material, while a colour grade of T or better is acceptable for any
10 yellow provided diamond material. Also as noted above, where small amounts of nitrogen are present in the source gas, and hence in the provided diamond material, then this is usually associated with the introduction also of so-called X-defects that introduce a brown colouration to the CVD diamond material. According to certain embodiments of the invention, where small amounts of nitrogen are present in the
15 CVD diamond material special methods are carried out in order to result in a provided CVD diamond material in which any brown colouration (thought to be due to these X-defects) is avoided, or at least minimised. Where such brown colouration is minimised in this way, then $[N_s^0]$ concentrations may be up to 1 ppm, since any yellow colouration resulting from the presence of the N_s^0 defects themselves will result in
20 levels of N_s^0 that give a colour grade of T (yellow) or better. Practically for reasons of gas purity or diamond properties, or where it is desirable to achieve a more blue-green hue rather than a blue hue, it may be advantageous to have $[N_s^0]$ concentrations towards the upper limit of 1 ppm.

Especially where the provided CVD diamond material used in the method according to the present invention has a $[N_s^0]$ concentrations towards the upper limit of 1 ppm, then the absorption spectrum may have a total integrated absorption in the visible range from 350 nm to 750 nm such that less than 90% of the integrated absorption is attributable to defects other than N_s^0 defects. i.e. the so-called X-defects thought to
30 be responsible for the brown colouration contribute less than 90% of the integrated absorption in the visible range.

It is also envisaged in this invention to use provided CVD diamond material with no, or only very small amounts of $[N_s^0]$ present. In these cases since there are only very
35 small amounts of $[N_s^0]$ present, in general there will consequently be similarly very low or no X- defects and consequently little or no brown colouration (although under certain growth conditions this may not be case). This can be quantified by specifying

that the absolute coefficients in the absorption spectrum 350 nm and 510 nm respectively are less than 0.5 cm^{-1} and 0.3 cm^{-1} . So where there is little or no $[N_s^0]$ present, then any colouration of the diamond material is likely to be due to any small amounts of brown (rather than yellow which results from N_s^0 itself), and in this case

5 the provided CVD diamond material has a colour grade G (brown) or better. Advantageously such a material may have the following characteristics in its absorption spectrum (when the absorption at 800 nm has been scaled to 0 cm^{-1}):

Designation	Starts (nm)	Ends (nm)	Peak (nm)	Absorption coefficient at peak (cm^{-1})
270 nm N_s^0	220	325	270	< 0.8
350 nm band Part of "X"	270	450	350 ± 10	< 0.5
510 nm band Part of "X"	420	640	510 ± 50	< 0.3

10 Methods of CVD diamond material growth are well established and have been described extensively in the patent and other literature, for example in WO 03/052177. These previously documented methods for growing CVD diamond material are believed to result in diamond material with an absorption spectrum with a total integrated absorption in the visible range from 350 nm to 750 nm such that the

15 contribution of other defects to the visible part of the spectrum would be greater than 90%. Since these other defects are known to lead to the characteristic brown colouration of CVD diamond containing nitrogen, these known prior art CVD growth processes are not suitable for directly growing the provided CVD diamond material used in the method of the present invention.

20

One of the above-mentioned special methods that can be carried out in order to result in a provided CVD diamond material in which any brown colouration (thought to be due to the aforementioned X-defects) is avoided is by using a CVD growth process in which the source gas contains carbon, hydrogen, nitrogen and oxygen,

25 rather than the more usual carbon hydrogen and nitrogen. For example, oxygen may be added to the process gas at a concentration of at least 10000 ppm in the gas phase. In particular, the provided CVD diamond material in step (i) of the method according to the first aspect of the invention may be grown directly by the process described in GB application GB0922449.4 and US provisional application USSN

30 61/289,282 the entire disclosures of which are incorporated herein by reference. Specifically the method involves providing a substrate; providing a source gas; and

allowing homoepitaxial diamond synthesis on the substrate; wherein the synthesis environment comprises nitrogen at an atomic concentration of from about 0.4 ppm to about 50 ppm; and wherein the source gas comprises: (a) an atomic fraction of hydrogen H_f , from about 0.4 to about 0.75; (b) an atomic fraction of carbon, C_f , from about 0.15 to about 0.3; (c) an atomic fraction of oxygen, O_f , from about 0.13 to about 0.4; wherein $H_f + C_f + O_f = 1$; wherein the ratio of atomic fraction of carbon to the atomic fraction of oxygen $C_f:O_f$, satisfies the ratio of about 0.45:1 $< C_f:O_f <$ about 1.25:1; wherein the source gas comprises hydrogen atoms added as hydrogen molecules, H_2 , at an atomic fraction of the total number of hydrogen, oxygen and carbon atoms present of between 0.05 and 0.4; and wherein the atomic fractions H_f , C_f and O_f are fractions of the total number of hydrogen, oxygen and carbon atoms present in the source gas. This method of growing CVD diamond material shall be referred to in the specification as the "added oxygen CVD growth process".

Depending on the exact process parameters used (for example the growth substrate used, the pressure used, and the amount of nitrogen in the source gas), the above added oxygen CVD growth process may result directly in providing diamond material in which less than 90% of the integrated absorption in the visible range from 350 nm to 750 nm is attributable to defects other than N_s^0 defects (the X-defects), or not. In general the added oxygen CVD growth process allows a skilled worker to introduce higher percentages of nitrogen than would be possible with standard CVD processes, while reducing the number of X defects leading to the brown colouration. Thus, the present invention also envisages using the added oxygen CVD growth process to introduce such high concentrations of nitrogen that the number of other defects is also significant and the resultant grown diamond material has greater than 90% of the integrated absorption in the visible spectrum from 350 nm to 750 nm attributable to X defects. Such provided diamond material could then be treated by a subsequent high temperature anneal as described hereinafter to remove some or all of those defects. Tailoring the added oxygen CVD growth process so as to produce the desired diamond material defect concentration, and consequent absorption spectrum, will be a matter of simple experimentation for the person skilled in the art.

The CVD diamond material grown by the added oxygen CVD growth process may be used directly as the provided CVD diamond material in the method according to the invention. This route from CVD growth stage to formation of the provided diamond material is illustrated as "route A" in Figure 1 of the accompanying drawings.

Instead of being used directly as the provided diamond material in the method according to the invention, the CVD diamond material grown by the added oxygen CVD growth process may be considered to be a added-oxygen-CVD-grown-precursor-diamond-material that is then subjected to a high temperature anneal at a temperature of at least 1600°C, or at least 1800°C, or at least 2000°C in order to form the provided CVD diamond material. A CVD diamond material made by the added oxygen CVD growth process and then subjected to the high temperature annealing process may form the provided CVD diamond as used in methods according to the invention. This route to the provided CVD diamond material is illustrated as route B in Figure 2. It is thought that this preliminary high temperature annealing process may reduce still further any X defects in the grown CVD diamond material, and that this may be advantageous for certain embodiments. The high temperature annealing step might be done on an as grown or processed stone.

Another possibility is for precursor CVD diamond material to be grown using a more conventional CVD process, for example of the type disclosed in WO 03/052177. Such a process, as noted above may result in diamond material with an absorption spectrum with a total integrated absorption in the visible range from 350 nm to 750 nm such that greater than 90% of the integrated absorption would be attributable to the undesirable brown colouring X-defects. We shall refer to this diamond material as the "traditional-CVD-grown precursor diamond material" in this specification, the word precursor being used to show it is a grown CVD diamond material that is different from and precedes the "provided CVD diamond material" defined by the method of the present invention. The word traditional is used to distinguish the route to the CVD grown precursor material from that described for route B above. We have found that if the traditional-CVD-grown precursor diamond material is subjected to the above mentioned high temperature annealing process it can result in diamond material in which less than 90% of the integrated absorption is attributable to defects other than N_s^0 defects (the brown-inducing X-defects). This route to the provided diamond material is shown in Figure 1 as "route C".

It is also envisaged in the present invention to use as the provided diamond material a material containing very low $[N_s^0]$ concentrations, e.g. less than 0.1 ppm. These materials may be grown using a process with very low, or zero, nitrogen concentrations in the source gas. The resultant grown CVD diamond materials consequently contain no or minimal X defects, since these X defects are thought to result from structural and charge changes in the diamond material as a result of

nitrogen in the diamond atomic structure; if the nitrogen is absent or minimal, then those structural changes do not take place or take place to a minimal extent. Therefore, certain embodiments of method according to the invention use a provided CVD diamond material having a $[N_s^0]$ concentration less than 0.1 ppm.

5

Methods of making CVD diamond material containing very low or zero $[N_s^0]$ concentrations are known in the art. For example, they are described in WO/019663A1, WO/019664A1, WO 2010/010352A1, and WO 2010/010344A1, the entire disclosures of which are incorporated herein by reference.

10

WO/019663A1, for example, describes a CVD diamond material particularly suitable for electronic applications, where the level of any single impurity is not greater than 5 ppm and the total impurity content is not greater than 10 ppm. Preferably the level of any impurity is not greater than 0.5 to 1 ppm and the total impurity content is not greater 2 to 5 ppm (where "impurity" excludes hydrogen and its isotopic forms). In the method described in WO/019663A1 the impurity content of the environment in which the CVD growth takes place is controlled such that growth is in the presence of an atmosphere containing substantially no nitrogen, i.e. less than 300 ppb, has a molecular fraction of the total gas volume, and preferably less than 100 ppb, and the substrate onto which it is grown is substantially defect free.

20

WO2010/010352 A1, for example, describes a method of making high chemical purity and high isotropic purity diamond material suitable for use in spintronic applications. In particular, the method of CVD growth comprises providing a diamond substrate having a surface which is substantially free of crystal defects, and providing a source gas mixture comprising high purity gases where the concentration of nitrogen is about 300 ppb or less, and solid carbon source comprising ^{12}C in an amount of at least 99% of the total carbon content of the source and activating and/or disassociating at least a portion of the source gas and the solid carbon source to form gaseous carbon species and allowing homoepitaxial diamond growth on the surface of the substrate.

25

30

CVD diamond material made by processes described above. e.g. of the type described in WO/019663A1, WO/019664A1, WO 2010/010352A1, and WO 2010/010344A1, which use substantially no nitrogen will be referred to hereinafter as "high purity CVD diamond material growth processes". These processes are suitable for forming the provided CVD diamond material used in methods according to the

35

invention. Since the high purity provided CVD diamond material so formed contains substantially no nitrogen, and consequently substantially no X-defects, the provided CVD diamond material made by these high purity methods will be colourless, near colourless or pale brown.

5

The colour of the irradiated diamond material is a combination of the starting colour, if any, of the provided diamond material and the colour introduced by the irradiation step introducing isolated vacancies. Other impurities that could introduce colour into the provided diamond material may in certain embodiments be minimised. For example, uncompensated boron (isolated boron) may itself introduce a blue colour to the diamond material. For some embodiments the boron concentration [B] in the provided diamond material is less than $5 \times 10^{15} \text{ cm}^{-3}$.

10

15

It is known that if there is uncompensated boron in diamond material this may be compensated for by irradiating to introduce isolated vacancies, the isolated vacancies combining with the boron so that neither the boron, nor those compensating isolated vacancies impart any colour to the diamond material. Therefore in some embodiments according to the present invention, if the diamond material does contain uncompensated boron (for example in a concentration of $>5 \times 10^{15} \text{ cm}^{-2}$), then the irradiation step may be carried out so as to introduce sufficient isolated vacancies not only to combine with the boron but also to achieve the specified isolated vacancy concentration $[V_T]$. The level of additional irradiation needed for boron-compensation can be determined empirically by the person skilled in the art.

20

25

By adding more nitrogen to the provided diamond material using methods in which brown inducing X-defects are not simultaneously introduced (e.g. the aforementioned oxygen process), or by eliminating those defects (e.g. by a high temperature annealing step) then more yellow can be introduced into the provided CVD diamond material, and hence a blue/green diamond material results after the irradiation step. This is thought to be because the presence of the N_s^0 in the material results in a charge transfer of V^0 to V^- . For example, where there is relatively low $[N_s^0]$ concentrations, most of the vacancies present in the provided diamond material are neutral vacancies V^0 which tend to impart a blue colour. When there is relatively higher $[N_s^0]$ concentrations more negative vacancies V^- are present in the provided diamond material, and these tend to impart a blue/green colour. Thus the invention proved a convenient means of tailoring the irradiated diamond material through all

30

35

shades of pale blue to pale blue/green by simple modification of the $[N_s^0]$ concentration. Advantageously controlling the ratio of V/V^0 by starting with different concentrations of nitrogen in the provided diamond material means that the hue angle can be varied to achieve the desired colour (between blue and green). Some
5 embodiments of the invention comprise selecting the $[N_s^0]$ concentration of the provided diamond material so as to provide a target V/V^0 ratio in the provided diamond material. In addition to the blue to blue/green colour difference imparted by the different V/V^0 ratio, there may also be a residual yellow hue from any remaining nitrogen, which would also tend to result in a greener blue/green diamond material
10 post treatment.

Another aspect of the present invention provides a system for being able to select and make a desired colour of diamond material within the fancy blue to blue/green colour range, having a hue angle within the range 100° - 270° ; the system comprising
15 the steps of:

(a) predetermining a target $[N_s^0]$ concentration for a grown CVD diamond material, that after irradiation of that grown CVD diamond material will result in the said desired colour;
20

(b) growing diamond material by a CVD process that includes introducing sufficient nitrogen in a process gas in the CVD process so as to achieve the said target $[N_s^0]$ concentration in the grown CVD diamond material, which CVD diamond material has the properties of the provided diamond material set out in step (i) of method claim 1;
25 then;

(c) carrying out the irradiation step set out in step (ii) of method claim 1 on the grown CVD diamond material.

30 The provided CVD diamond material used in the method according to the first aspect of the present invention preferably may have at least about 50%, alternatively at least about 80%, alternatively at least about 90%, alternatively at least about 95% of the volume of the synthetic CVD diamond material formed from a single growth sector. This single growth sector is preferably a $\{100\}$ or a $\{110\}$ growth sector. The material
35 of the single growth sector preferably has N_s^0 levels within $\pm 10\%$ of the mean for greater than about 50% of the volume of the growth sector, alternatively greater than about 60% of the volume of the growth sector, alternatively greater than about 80%

of the volume of the growth sector. Using a provided synthetic CVD diamond material that has been grown from a single growth sector is advantageous as the CVD diamond material will have fewer surfaces with different crystallographic orientation (which are the surfaces corresponding to differing growth sectors).

5 Surfaces with different crystallographic orientations exhibit strongly differential uptake of nitrogen impurity and a synthetic CVD diamond material comprising more growth sectors therefore tends to show more undesirable zones with different colour, resulting from the different concentrations of N_s^0 in different growth sectors.

10 Where methods according to the invention comprise a preliminary process of growing the provided CVD diamond, these methods preferably comprise growing the diamond material to have the above stated percentages formed from a single growth sector.

Another advantage of having provided CVD diamond from predominantly a single
15 growth sector is that in different growth sectors there may be different quantities, distributions and types of defects

Using CVD synthetic diamond material rather than natural diamond or HPHT
synthetic diamond material to produce pale blue diamond is advantageous for a
20 number of reasons. For example, natural diamond is variable in its properties; therefore making it more difficult to find matching diamonds to be set together for ornamental use. An advantage of CVD diamond material over natural diamond material is that the synthetic CVD process and the post growth treatment can be
tailored to achieve the exact hue and saturation of colour desired rather than having
25 to accept what is available. As another example, diamond material produced using HPHT synthesis techniques exhibits strongly differential uptake of nitrogen impurity on the surfaces with different crystallographic orientation (which are the surfaces corresponding to differing growth sectors) that form during synthesis. HPHT does not normally have a single dominant growth sector, unlike that typically achieved in
30 CVD. The diamond material therefore tends to show zones with different colours, resulting from the differing nitrogen impurity concentrations in different growth sectors. In addition, it is hard to control the HPHT diamond material synthesis process sufficiently to give a uniform and desired nitrogen concentration throughout even a single growth sector within the synthesized diamond material. Furthermore,
35 in HPHT diamond material synthesis, it is typical to see impurities resulting from the synthesis process and the catalysts used – examples would be inclusions comprising cobalt or nickel – features that can result in localised and inhomogeneous strain that

degrade the optical and thermal properties. In contrast, CVD diamond material is much more uniform in colour than either natural or HPHT synthetic diamond material, and will not have any issues with metallic inclusions.

- 5 A synthetic CVD diamond material may be unequivocally distinguished from a synthetic diamond material synthesized using HPHT techniques by the dislocation structure. In synthetic CVD diamond, dislocations generally thread in a direction that is roughly perpendicular to the initial growth surface of the substrate, i.e. where the substrate is a (001) substrate, the dislocations are approximately aligned parallel to
10 the [001] direction. In synthetic diamond material synthesized using HPHT techniques, dislocations that nucleate on surface of the seed crystal (often a surface close to {001}) typically grow in $\langle 110 \rangle$ directions. Thus the two types of material can be distinguished by their different dislocation structures observed, for example, in an X-ray topograph. This also provides a route to distinguish CVD from natural type IIa,
15 as natural diamond does not show these clear parallel dislocations.

However, obtaining X-ray topographs is an onerous task and clearly an alternative, less onerous method that enables positive distinction would be desirable.

- 20 A synthetic CVD diamond material may be positively distinguished from a synthetic diamond material synthesized using HPHT techniques by the presence of metallic inclusions in the HPHT-synthesized material that are incorporated as a result of the synthesis process. The inclusions are comprised of the metals used as the solvent catalyst metal, e.g. Fe, Co, Ni etc. Inclusions can vary in size from less than 1 μm to
25 more than 100 μm . Larger inclusions can be observed using a stereo-microscope (e.g. a Zeiss DV4); whilst smaller inclusion can be observed using transmitted light in a metallurgical microscope (e.g. a Zeiss "Axiophot").

- A further method that can be used to provide positive distinction between synthetic
30 diamonds produced by CVD and HPHT methods is photoluminescence spectroscopy (PL). In the case of HPHT-synthesised material, defects containing atoms from the catalyst metals (typically transition metals) used in the synthesis process (e.g. Ni, Co, Fe etc.) are frequently present and the detection of such defects by PL positively indicates that the material has been synthesised by an HPHT method.

Step (ii) of methods according to the invention comprises irradiating the provided diamond with electrons. The step of irradiation acts to introduce isolated vacancies V into the diamond, as discussed hereinbefore.

- 5 We have found that irradiating the diamond material with radiation other than electron radiation does not result in a fancy pale blue or fancy pale blue/green coloured diamond. In particular we have found that irradiation with neutrons produces a yellow green coloured diamond.

- 10 In general the greater the irradiation dose, the greater the number of isolated vacancies created. The level of the irradiation dose and any post irradiation treatment is selected so that $[V_T] \times L$ is at least 0.072 ppm cm and at most 0.36 ppm cm. Typically for a 0.5 ct rbc this corresponds to a concentration range for $[V_T]$ of 0.12 –
15 0.6 ppm.

- In some embodiments according to the invention the dose of electrons is selected so as to introduce $[V_T] \times L$ in the irradiated diamond material of at least 0.072 ppm cm and at most 0.36 ppm cm. In these cases there is preferably no further post-
20 irradiation treatment applied to the diamond material that could significantly affect the isolated vacancy concentration in the diamond material.

- It is possible for the diamond material to be irradiated so as to introduce more than the final desired concentration of isolated vacancies. In these cases it is possible to
25 subsequently decrease the concentration of isolated vacancies by a post irradiation treatment step. We have found that it is possible to decrease the concentration of isolated vacancies by up to about 50% by such a post irradiation step. The post irradiation step may comprise annealing the sample, for example at a temperature of at least 300°C, or at a temperature of at most 600°C. The period of the anneal may
30 be short, for example, simply ramping up the temperature from room temperature to the anneal temperature, and then allowing the sample to cool down again, or the sample may be held at the anneal temperature for a period, of a few or several hours, for example 2 hours. Without limiting the invention in any way, we believe that annealing at this temperature may cause any interstitials present in the material to
35 become mobile and therefore diffuse and recombine with some of the isolated vacancies and consequently reduce the concentration of the isolated vacancies. This over-irradiation (to produce surplus isolated vacancies) followed by an anneal to

remove those surplus isolated vacancies disadvantageously involves an extra step, but it may be used in certain circumstances, and provided the resultant post treatment isolated vacancy concentration is within the prescribed limits falls within the scope of the present invention.

5

Therefore other embodiments of method according to the invention comprise an additional step of post-irradiation treating the irradiated diamond material so as to achieve $[V_T] \times L$ in the irradiated diamond material of at least 0.072 ppm cm and at most 0.36 ppm cm. This post-irradiation treatment step may comprise annealing the irradiated diamond material at a temperature of at least 300°C and at most 600°C. In these embodiments since a post irradiation anneal may decrease the concentration of isolated vacancies by up to 50%, then the initial dose of electrons may be selected so as to introduce $[V_T] \times L$ in the irradiated diamond material of at most 0.72 ppm cm.

10

15

An additional benefit of irradiating the CVD diamond material is that typically the colour of the material will be more stable to low temperature annealing and exposure to UV light compared to untreated CVD diamond. This stabilisation effect is discussed in GB Application Number 0911075.0, and US Application Number 61/220,663 both filed 26th June 2009, and in GB Application Number 0917219.8 and US Application Number 61/247,735 both filed 1st October 2009, the entire disclosures of which are incorporated herein by reference. Thus an advantage of the present invention is that it results in a blue or blue green diamond material which, in the absence of the irradiation step of the method of the present invention would show a measurable difference in at least one of its absorption characteristics in first and second states, the first state being after exposure to irradiation having an energy of at least 5.5 eV and the second state being after thermal treatment at 798 K (525°C), but which following the method of the present invention results in diamond material that shows little or no colour change when in the said first and second states, given that the concentration of interstitials has been minimised. Advantageously, in some embodiments, post irradiation the change in colour saturation value C^* between the first and second states is reduced by at least 0.5 compared with the diamond material that has not been subjected to irradiation. In some embodiments the change in C^* , post irradiation, of the diamond material in the first and second states is <1 . In some embodiments the irradiated diamond material, or the irradiated diamond material after a further post-irradiation treatment, may have an absorption coefficient measured at 77 K of at least 0.01 cm^{-1} at a wavelength of 741 nm; or an absorption coefficient measured at 77 K of at least 0.01 cm^{-1} at a wavelength of 394 nm.

20

25

30

35

It is known that the energy of the irradiation determines the penetration of the irradiation. As a rough approximation every additional MeV of energy of an electron beam will penetrate an additional 0.7 mm of diamond. Typical electron irradiation sources are available at 1.5 MeV and 4.5 MeV, and we have found that it is preferable to use a 4.5 MeV electron source for irradiation to achieve the desired penetration for typical sized diamonds; e.g. for a 0.5 carat diamond having a thickness of about 3 mm. Typically the electron beam source may have a 50% scan width and a 20 mA current for example at the facility used at Isotron plc.

Electron irradiation is typically carried out with a beam source in the energy range 0.8 MeV to 12 MeV. Optionally the energy that is used is that which introduces a near uniform concentration of isolated vacancies in the N doped diamond material, while minimizing the formation of cascade damage e.g. vacancy chains. For the optimum results reported here it was found that 4.5 MeV provided a good compromise between these two factors.

Optionally, and particularly for larger samples, rotation of the sample during irradiation, or repeated rotation followed by irradiation, may be used to assist in achieving uniformity of the created isolated vacancies throughout the volume of the stone.

Factors such as diamond temperature, beam energy, beam flux, and even the starting diamond's properties can affect the $[V_T]$ produced for a fixed experimental irradiation set-up and time. Irradiation is typically carried out with the sample mounted under ambient conditions ~300 K with only minimal temperature rise during the irradiation dose (e.g. less than 100 K). However, factors such as beam energy and beam flux can lead to sample heating. Preferably the sample is held as cold as possible (with even cryogenic cooling at 77 K being advantageous under some circumstances) to enable high dose rates without compromising temperature control and thus minimize the irradiation time. This is advantageous for commercial reasons. Calibration of the dose applied against the isolated vacancies produced for the particular provided diamond being used in order to satisfy these limits on $[V_T]$ concentration introduced will form part of the skilled person's responsibilities before carrying out the method of the present invention. Such calibration techniques are routine for the person skilled in the art.

We have also found that the period of irradiation affects the number of isolated vacancies that are incorporated into the diamond material and the isolated vacancy incorporation rate is different for different starting materials and starting temperatures.

5

A typical irradiation dose for a 0.5 ct rbc diamond stone, when the sample temperature is ~350 K, is $1 \times 10^{17} - 1 \times 10^{18} \text{ e}^- \text{cm}^{-2}$.

10

A typical irradiation time for a 0.5 ct rbc diamond stone, when the sample temperature is ~350 K, is 5 – 30 minutes at 4.5 MeV, 20 mA and 50% scan width using an instrument such as that found at Isotron plc.

15

Throughout this specification to measure concentrations of isolated vacancies, spectra are obtained at 77 K, using liquid nitrogen to cool the samples, since at that temperature sharp peaks at 741 nm and 394 nm are seen that are attributable to neutral and negatively charged isolated vacancies respectively. The coefficients that are used for the calculations of concentrations of isolated vacancies in the present specification are those set out by G. Davies in Physica B, 273-274 (1999), 15-23, as detailed in Table 1 below.

20

Table 1

Defect	Calibration
V^-	$A_{ND1} = (4.8 \pm 0.2) \times 10^{-16} [V^-]$
V^0	$A_{GR1} = (1.2 \pm 0.3) \times 10^{-16} [V^0]$

25

In Table 1, “A” is the integrated absorption (meV cm^{-1}) in the zero phonon line of the transition, measured at 77 K, with the absorption coefficient in cm^{-1} and the photon energy in meV. The concentration is in cm^{-3} .

According to methods of our invention $[V_T] \times L$ after irradiation, or after a further post-irradiation treatment, is at least 0.072 ppm cm, and at most 0.36 ppm cm.

30

The provided CVD diamond material used in the method according to the present invention, and also the irradiated CVD diamond material resulting from the method of the present invention may, or may not, form part of a larger piece of diamond material. For example part only of the larger piece of diamond material may be irradiated and turned blue, and/or part only of the larger piece of diamond material

35

may have the defined absorption characteristics. As would be apparent to the person skilled in the art multiple layers could also be irradiated and/or have the required absorption characteristics, so that the provided CVD diamond material used in the method according to the invention may form part, e.g. one or multiple layers of

5 a larger piece of diamond material. It is well known that the depth of penetration of irradiation is dependent on the energy of the irradiation. So in preferred embodiments an irradiation energy is selected such that the irradiation penetrates only part of the depth of a CVD diamond material. This means that isolated vacancies would be introduced only in the penetrated part of the irradiated CVD

10 diamond material, and hence that penetrated part of the CVD diamond material would be the "diamond material" used formed by the method of the present invention.

Where the provided CVD diamond material provides only part of a larger piece of diamond material, as discussed above that provided CVD diamond material alone

15 may have the advantageous optical properties described for certain embodiments of the invention. Thus for example a top or embedded layer or layers of a large piece of CVD diamond material may have a pale blue or pale blue/green colouration. Where any other non-pale-blue, or blue/green layers are substantially colourless the colour of the larger piece of diamond material is dominated by the pale blue or pale

20 blue/green layer(s).

In some embodiments according to the invention at least 50% or at least 60% or at least 70% or at least 80% or at least 90% or substantially the whole diamond stone may have substantially the same colour.

25 In other embodiments according to the invention of diamond stone may comprise layers or pockets of diamond material of the same colour.

It is an advantage of the present invention that by starting with a CVD diamond material with a specific nitrogen concentration, that is substantially colourless or pale-coloured, and irradiating the CVD diamond material with electrons, pale blue or pale blue/green diamond material can be produced. The precise colour (between blue and green) can be altered by controlling the nitrogen concentration. Advantageously, low levels of everything else, e.g. other elements that might introduce other colour

30 are maintained. The irradiation is controlled to introduce a particular concentration of isolated vacancies in the diamond material, thereby introducing a fancy pale blue or fancy pale blue/green colour. These coloured diamond materials may find particular

35

application as gemstones, or as coloured filters or as a cutting tool for example a scalpel and the like. It should be noted that the terms “colourless” and “white” are sometimes used synonymously in the field to describe the colour of diamond materials for gemstones.

5

The present invention also provides diamond material whenever made by a method according to the first aspect of the invention.

10

A fancy pale blue or pale blue/green CVD diamond material in which the colour does not come solely, or at all, from boron is also new per se. Therefore a second aspect of the present invention provides a fancy pale blue, or fancy pale blue/green CVD synthetic single crystal diamond material having either $[B] < 1 \times 10^{15} \text{ cm}^{-3}$ or $[N] - [B] < 1 \text{ ppm}$ and the following colour characteristics:

Characteristic	Range
Hue angle α	100°-270° optionally 110°-230° optionally 120°-200°
Saturation - C^*	At least 2 and at most 10 optionally 2 – 8 optionally 2 - 6
Lightness - L^*	>65 optionally >70 optionally >72

15

The colour of the irradiated and annealed diamond can be quantified in a well established manner using “CIE $L^*a^*b^*$ Chromaticity Coordinates”. The use of CIE $L^*a^*b^*$ Chromaticity Coordinates in diamond is described in WO 2004/022821, the entire disclosure of which is incorporated herein by reference. This method is particularly useful for assessing the colour of plates or blocks of diamond material. The colour of a round brilliant polished diamond can either be assessed by eye by a trained person or using the CIE $L^*a^*b^*$ Chromaticity Coordinates if a flat is polished on to the culet so that there are two parallel polished sides to take a measurement through. a^* and b^* are plotted as x and y axes of a graph and the hue angle is measured from the positive a^* axis towards the positive b^* axis. Thus a hue angle of greater than 90° and less than 180° lies in the upper left quadrant of the a^*b^* graph.

20

25

In this scheme for describing colour L^* is the lightness and a fourth coordinate C^* is the saturation.

- 5 The perceived colour of an object depends on the transmittance/absorbance spectrum of the object, the spectral power distribution of the illumination source and the response curves of the observer's eyes. The CIE $L^*a^*b^*$ chromaticity coordinates (and therefore hue angles) quoted herein have been derived in the way described below. Using a standard D65 illumination spectrum and standard (red, green and blue) response curves of the eye (G. Wyszecki and W. S. Stiles, John Wiley, New York-London-Sydney, 1967) CIE $L^*a^*b^*$ chromaticity coordinates of a parallel-sided plate of diamond have been derived from its transmittance spectrum using the relationships below, between 350 nm and 800 nm with a data interval of 1 nm:

S_λ = transmittance at wavelength λ

- 15 L_λ = spectral power distribution of the illumination

x_λ = red response function of the eye

y_λ = green response function of the eye

z_λ = blue response function of the eye

- 20 $X = \sum_\lambda [S_\lambda x_\lambda L_\lambda] / Y_0$

$$Y = \sum_\lambda [S_\lambda y_\lambda L_\lambda] / Y_0$$

$$Z = \sum_\lambda [S_\lambda z_\lambda L_\lambda] / Y_0$$

$$\text{Where } Y_0 = \sum_\lambda y_\lambda L_\lambda$$

- 25 $L^* = 116 (Y/Y_0)^{1/3} - 16 = \text{Lightness}$ (for $Y/Y_0 > 0.008856$)

$$a^* = 500[(X/X_0)^{1/3} - (Y/Y_0)^{1/3}] \quad (\text{for } X/X_0 > 0.008856, Y/Y_0 > 0.008856)$$

$$b^* = 200[(Y/Y_0)^{1/3} - (Z/Z_0)^{1/3}] \quad (\text{for } Z/Z_0 > 0.008856)$$

$$C^* = (a^{*2} + b^{*2})^{1/2} = \text{saturation}$$

$$h_{ab} = \arctan(b^* / a^*) = \text{hue angle}$$

Modified versions of these equations must be used outside the limits of Y/Y_0 , X/X_0 and Z/Z_0 . The modified versions are given in a technical report prepared by the Commission Internationale de L'Eclairage (Colorimetry (1986)).

- 5 It is standard to plot a^* and b^* coordinates on a graph with a^* corresponding to the x axis and b^* corresponding to the y axis. Positive a^* and b^* values correspond respectively to red and yellow components to the hue. Negative a^* and b^* values correspond respectively to green and blue components. The positive quadrant of the graph then covers hues ranging from yellow through orange to red, with saturations
10 (C^*) given by the distance from the origin.

- It is possible to predict how the a^*b^* coordinates of diamond with a given absorption coefficient spectrum will change as the optical path length is varied. In order to do this, the reflection loss must first be subtracted from the measured absorbance
15 spectrum. The absorbance is then scaled to allow for a different path length and then the reflection loss is added back on. The absorbance spectrum can then be converted to a transmittance spectrum which is used to derive the CIE $L^*a^*b^*$ coordinates for the new thickness. In this way the dependence of the hue, saturation and lightness on optical path length can be modelled to give an understanding of how
20 the colour of diamond with given absorption properties per unit thickness will depend on the optical path length.

- L^* , the lightness, forms the third dimension of the CIE $L^*a^*b^*$ colour space. It is important to understand the way in which the lightness and saturation vary as the
25 optical path length is changed for diamond with particular optical absorption properties. The method described in the preceding paragraph can also be used to predict how the L^*C^* coordinates of diamond with a given absorption coefficient spectrum depend on the optical path length.

- 30 The C^* (saturation) numbers can be divided into saturation ranges of 10 C^* units and assigned descriptive terms as below.

- | | |
|----------|-----------------|
| 0-10 | weak |
| 10-20 | weak-moderate |
| 35 20-30 | moderate |
| 30-40 | moderate-strong |
| 40-50 | strong |

50-60	strong-very strong
60-70	very strong
70-80+	very very strong

5 Similarly the L* numbers can be divided up into lightness ranges as follows:

	5-15	very very dark
	15-25	very dark
	25-35	dark
10	35-45	medium/dark
	45-55	medium
	55-65	light/medium
	65-75	light
	75-85	very light
15	85-95	very very light

There are four basic colour tones defined by the following combinations of lightness and saturation:

20 Bright: Light and high saturation, Pale: Light and low saturation,
 Deep: High saturation and dark, Dull: Low saturation and dark.

Embodiments of the invention will now be described, by way of example, with reference to the accompanying drawings and examples, wherein:

25

Figure 1, which has been referred to hereinbefore, is a flow chart which shows routes for methods according to the invention for obtaining pale blue or pale blue/green diamond material;

30 Figure 2 are absorption spectra A, B and C measured at room temperature, where A is the spectrum for the starting diamond material used in examples 2-4 and 9, B is the spectrum for the starting material used in example 1 and 8, and C is the spectrum for the starting material used in examples 5-7;

35 Figure 3 are UV Visible absorption spectra A,B and C measured at 77 K, where A, B and C are respectively the absorption spectra for examples 2, 3 and 4 each shown after irradiation as specified; and

Figure 4 are absorption spectra A and B measured at 77 K for examples 2 and 6 respectively post irradiation, showing the ND1 and GR1 peaks, which are indicative of V^- and V^0 defects respectively.

5

Examples

HPHT diamond substrates suitable for synthesising single crystal CVD diamond of the invention were laser sawn, lapped into substrates, polished to minimise subsurface defects such that the density of defects is below 5×10^3 /mm², and generally is below 10^2 /mm. Polished HPHT plates 3.6 mm x 3.6 mm square by 500 μ m thick, with all faces {100} having a surface roughness R_q at this stage of less than 1 nm were mounted on a refractory metal disk, and introduced into a CVD diamond growing reactor.

15 *Growth stages*

- 1) The CVD diamond reactor was pre-fitted with point of use purifiers, reducing unintentional contaminant species in the incoming gas stream to below 80 ppb.
- 2) An *in situ* oxygen plasma etch was performed using 50/40/3000 sccm (standard cubic centimetre per second) of O_2 /Ar/ H_2 and a substrate temperature of 760°C.
- 3) This moved without interruption into a hydrogen etch with the removal of the O_2 from the gas flow.
- 4) This moved into the growth process by the addition of the carbon source (in this case CH_4) and dopant gases. For these examples the CH_4 flowing at 165 sccm, nitrogen was present in the process gas at different levels for the different examples, provided from a calibrated source of for example a source containing 100 ppb N_2 either as air in Ar or N_2 in H_2 , and for some examples O_2 was also present in the process gas.

30

5)

Example	Nitrogen dopant present in the process gas (ppm)	Oxygen (O_2) flow present in the process gas (ppm)
1 and 8	1.8	0
2 – 4 and 9	0.09	0
5-7	1.0	13700

- 6) On completion of the growth period, the substrate was removed from the reactor and the CVD diamond layer removed from the substrate by laser sawing and mechanical polishing techniques.
- 7) This produced a CVD sample which had typical dimensions $\sim 3.1 \times 5 \times 5$ mm and a typical average path length for light of 6 mm.

This grown CVD diamond is the "provided diamond" defined by the claims of the present specification.

- Figure 2 are absorption spectra A, B and C, where spectrum A is that of the starting diamond material used in examples 2-4 and 9, and represents diamond material grown by a high purity CVD growth process. In these examples the percentage of the integrated absorption in the visible spectrum of the provided CVD diamond attributable to defects other than N_s^0 is $>90\%$. In these examples, this is because the absolute $[N_s^0]$ concentration is low, as is shown by the fact that there is no distinct peak at 270 nm. The material does not have a brown colouration as the absorption at 510 and 350 nm are <0.5 and 0.3 cm^{-1} respectively. These high purity materials are colourless and are a suitable provided CVD diamond material for irradiation according to the method of the invention. In Figure 2, spectrum B is that of the starting material used in examples 1 and 8. This starting material is a CVD diamond material grown by a traditional CVD growth process with no oxygen in the source gas. In these examples the percentage of the integrated absorption in the visible spectrum of the starting CVD diamond material attributable to defects other than N_s^0 is $>90\%$, and furthermore the absorption at 510 nm and 350 nm are $>0.5 \text{ cm}^{-1}$ and 0.3 cm^{-1} respectively. The starting diamond materials of examples 1 and 8 are, therefore not untreated suitable starting materials for the irradiation method of the present invention and are pale brown prior to irradiation. However if treated, e.g. HPHT annealed prior to irradiation as shown in example 8 they are suitable precursor diamond materials for the irradiation method of the present invention. In Figure 2, spectrum C is that of the starting material used in examples 5-7 which are diamond materials grown by a CVD growth process with added oxygen in the source gas. In this spectrum, the absorption at 510 nm and 350 nm are $>0.5 \text{ cm}^{-1}$ and 0.3 cm^{-1} respectively, however the percentage of the integrated absorption in the visible spectrum of the provided CVD diamond attributable to defects other than N_s^0 is now $<90\%$. These examples are suitable starting material for irradiation according to the method of the present invention, and are pale yellow prior to irradiation.

The electron irradiation of all samples was carried out with a 4.5 MeV electron beam on 50% scan width and 20 mA beam current). Diamond samples to be irradiated are mounted in indium on a water cooled copper block to prevent the samples being heated above 350 K.

5

Table 3 shows the CVD growth process (or route to the provided CVD diamond material as indicated in Figure 1, where applicable), the N_s^0 concentrations in ppm, the percentage of the total integrated absorption attributable to N_s^0 defects for the diamond material samples provided as above, the absorption coefficients at 270 nm, 10 350 nm and 510 nm, the irradiation dose, the total isolated vacancy concentration (and breakdown to neutral and negative isolated vacancy concentrations), and the colour before and after irradiation.

Table 3 includes a number of comparative examples. Considering each of the 15 examples in table 3 in turn, example 1 (which is a comparative example) shows traditionally grown CVD diamond material in which the percentage of integrated absorption in the provided diamond attributable to defects other than N_s^0 is 91.6%, and its absorption coefficients at 350 nm is 1.19 cm^{-1} and at 510 nm is 0.45 cm^{-1} ; its colour pre-irradiation is pale brown, in other words the provided CVD diamond 20 material falls outside the criteria set out in method step (i). After irradiation the observed colour of the diamond material is dull brownish - blue, not the desired fancy pale blue or fancy pale blue/green of the present invention. Also the colour characteristics of example number 1 fall outside those specified by the main article claim of the present invention. Example 1 could be HPHT annealed as shown in 25 example 8 to make it suitable to make a pale blue/blue-green material, but untreated is not suitable.

Example 2, 4, 5 and 7 (again comparative examples), uses the provided diamond falling within the scope of step 1 of the method claim of the present invention, but 30 introduce a product of total isolated vacancy concentration x path length that are either lower than required minimum of at least 0.072 ppm cm (examples 2 and 5) or higher than the maximum (examples 4 and 7) 0.36 ppm cm . The colour of these examples after irradiation are not the desired fancy pale blue and fancy pale blue/green, and the colour characteristics fall outside those defined by the main 35 article claims.

Figure 3 shows UV Visible spectra A,B and C taken at 77 K post irradiation where spectrum A is that of example 2 and indicates (by the height of the GR1 peak) an isolated vacancy concentration that is too low to impart the desired fancy pale blue/blue-green colour desired for the present invention; spectrum B is that of example 3 and indicates an isolated vacancy concentration that is within the scope of the claim, and will impart the desired fancy pale blue/blue-green colour desired for the present invention, and spectrum C is that of example 4 and indicates an isolated vacancy concentration that is too high to impart the desired fancy pale blue/blue-green colour desired for the present invention. Another indicator of the isolated vacancy concentrations post irradiation of these samples is shown in Table 3 which includes columns indicating the V^0 and V^- concentrations post irradiation in ppm, this data having been calculated by integrating the area under the GR1 and ND1 peaks respectively.

Example 9 (again a comparative example) uses neutron irradiation rather than electronic radiation. This results in a vivid yellow diamond material after irradiation, the C^* and L^* values are outside the limits of the claims of this patent.

Comparison of the examples also shows how it is possible to modify the hue angle (and hence the precise perceived colour) within the claimed range by altering the concentration of N_S^0 in the provided diamond. Examples 3 and 6 both produce pale blue / pale blue green, but the exact hue angle has been modified by introducing different concentrations of N_S^0 .

Figure 4 which are absorption spectra taken post irradiation for examples 3 and 6, shows the different ratio of V^0 and V^- defects formed following the same irradiation for starting materials containing different concentrations of N_S^0 . Spectrum A which is that of example 3, which contains low $[N_S^0]$ concentration shows virtually no ND1 peak at 394 nm (indicating that the sample contains virtually no V^- defects). In contrast spectrum B which is that of example 6 which contains higher $[N_S^0]$ concentration shows an increased height of ND1 peak at 394 nm (indicating increased presence of V^- defects). Both spectra A and B show comparable GR1 peaks, and so the ratio of GR1 peak: ND1 peak, indicating the ratio of V^0 : V^- defects is higher for spectrum A (example 3) than for spectrum B (example 6).

Example Number	CVD Growth chemistry treatment (+ initial treatment e.g. high T anneal)	N _s ⁰ conc. in the provided CVD diamond (ppm)	Percentage of integrated absorption in visible spectrum of provided CVD diamond, attributable to defects other than N _s ⁰	Abs at 270 nm	Abs at 350 nm	Abs at 510 nm	V ⁰ conc (ppm)	V ⁻ conc (ppm)	Colour in the provided diamond Pre-irradiation (Colour grade if 0.5 ct RBC)	Irradiation dose e ⁻ /cm ²	V ⁰ conc (ppm) post irradiation	V ⁻ conc (ppm) post irradiation	Observed colour after irradiation	Colour characteristics (C*, L* and α)
1*	Traditional CVD growth process no treatment	0.4	91.6	2.23	1.09	0.45	<0.003	<0.003	Pale brown	2.6 x 10 ¹⁷ e ⁻ /cm ²	0.25	0.12	Dull brownish blue	L* = 54.8 C* = 9.88 α = 94.41°
2*	High Purity CVD growth process (low X- defects – brown- and low nitrogen) – no treatment	0.012	98.5	0.15	0.13	0.06 ₀	<0.003	<0.003	Colourless	9.7 x 10 ¹⁶ e ⁻ /cm ²	0.093	0.0054	Colourless	L* = 84.9 C* = 1.7 α = 74.6°
3	High Purity CVD growth process (low X- defects – brown- and low nitrogen) – no treatment	0.012	98.5	0.15	0.13	0.06 ₀	<0.003	<0.003	Colourless	2.4 x 10 ¹⁷ e ⁻ /cm ²	0.17	0.006	Pale, bright greenish blue	L* = 75.8 C* = 3.7 α = 179.5°

* Comparative Example

Example Number	CVD Growth chemistry (+ initial treatment e.g. high T anneal)	N _s ⁰ conc. In provided CVD diamond (ppm)	Percentage of integrated absorption in visible spectrum of provided CVD diamond, attributable to defects other than N _s ⁰	Abs at 270 nm	Abs at 350 nm	Abs at 510 nm	V ⁰ conc (ppm)	V ⁻ conc (ppm)	Colour Pre-irradiation (Colour grade if 0.5 ct RBC)	Irradiation dose	V ⁰ conc (ppm) post irradiation	V ⁻ conc (ppm) post irradiation	Observed colour after irradiation	Colour characteristics (c*, L* and α)
4*	High Purity CVD growth process (low X- defects – brown- and low nitrogen) – no treatment	0.012	98.5	0.15	0.13	0.06 0	<0.003	<0.003	Colourless	1.9 x 10 ¹⁸ e ⁻ /cm ²	0.68	0.020	Vivid, bright greenish blue	L* = 61.4 C* = 20.2 α = 195.7°
5*	Added oxygen CVD growth process – low brown	0.35	71.6	1.42	0.63	0.23	<0.003	<0.003	Pale yellow	6.5 x 10 ¹⁶ e ⁻ /cm ²	0.049	0.052	Colourless	L* = 80.97 C* = 4.75 α = 83.5°

* Comparative example

Example Number	CVD Growth chemistry (+ initial treatment e.g. high T anneal)	N_s^0 conc. In provided CVD diamond (ppm)	Percentage of integrated absorption in visible spectrum of provided CVD diamond, attributable to defects other than N_s^0	Abs at 270 nm	Abs at 350 nm	Abs at 510 nm	V^0 conc (ppm)	V' conc (ppm)	Colour Pre-irradiation (Colour grade if 0.5 ct RBC)	Irradiation dose e^-/cm^2	V^0 conc (ppm) post irradiation	V' conc (ppm) post irradiation	Observed colour after irradiation	Colour characteristics (c^* , L^* and α)
6	Added oxygen CVD growth process – low brown	0.35	71.6	1.42	0.63	0.23	<0.003	<0.003	Pale yellow	$2.4 \times 10^{17} e^-/cm^2$	0.19	0.082	Pale blue - green	$L^* = 80.7$ $C^* = 3.21$ $\alpha = 142.1^\circ$
7*	Added oxygen CVD growth process – low brown	0.35	71.6	1.42	0.63	0.23	<0.003	<0.003	Pale yellow	$1.9 \times 10^{18} e^-/cm^2$	1.1	0.3	Vivid, bright blue - green	$L^* = 54.3$ $C^* = 19.3$ $\alpha = 189.6^\circ$

* comparative example

Example Number	CVD Growth chemistry (+ initial treatment e.g. high T anneal)	N _s ^v conc. In provided CVD diamond (ppm)	Percentage of integrated absorption in visible spectrum of provided CVD diamond, defects other than N _s ^v	Abs at 270 nm	Abs at 350 nm	Abs at 510 nm	V ^v conc (ppm)	V ^v conc (ppm)	Colour Pre-irradiation (Colour grade if 0.5 ct RBC)	Irradiation dose	V ^v conc (ppm) post irradiation	V ^v conc (ppm) post irradiation	Observed colour after irradiation	Colour characteristics (c*, L* and a)
8	Traditional CVD growth process + HPHT anneal	0.4	91.6	2.23 (0.37 post HPHT anneal)	1.09 (0.13 post HPHT anneal)	0.45 (0.04 post HPHT anneal)	<0.003	<0.003	Pale brown pre HPHT anneal, pale yellow after HPHT anneal	2.4×10^{17} e ⁻ /cm ²			Pale greenish blue	
9*	High Purity CVD growth process (low X-defects – brown- and low nitrogen) – no treatment neutron irradiated	0.012	98.5	0.15	0.13	0.060	<0.003	<0.003	Colourless	1×10^{16} n/cm ²	0.51	0 (within error of measurement)	Vivid green yellow	L* = 48.4 C* = 25.23 a = 135.1°

* comparative example

CLAIMS

1. A method of making fancy pale blue or fancy pale blue/green CVD single crystal diamond material comprising the steps of:

5

i) providing single crystal diamond material that has been grown by a CVD process, the diamond material having a $[N_s^0]$ concentration less than 1 ppm, which provided CVD diamond material is colourless, or if not colourless is colour-graded brown or yellow, and if colour-graded brown has a colour grade for a 0.5 ct Round Brilliant Cut diamond stone of G (brown) or better, and if colour-graded yellow has a colour grade for a 0.5 ct Round Brilliant Cut diamond stone of T (yellow) or better; and

10

(ii) irradiating, the provided CVD diamond material with electrons so as to introduce isolated vacancies into the diamond material, so that the product of the total vacancy concentration x path length, $[V_T] \times L$ in the irradiated diamond material at this stage, or after a further post-irradiation treatment, being at least 0.072 ppm cm and at most 0.36 ppm cm, whereby the diamond material becomes fancy pale blue or fancy pale blue/green in colour.

15

20

2. A method according to claim 1, wherein the provided diamond material is colour-graded brown or yellow, and if colour-graded brown has a hue angle in the range 0° to less than 90° for a 0.5 ct Round Brilliant Cut diamond stone, and if colour-graded yellow has a hue angle in the range 90° - 130° for a 0.5 ct Round Brilliant Cut diamond stone.

25

3. A method according to claim 1 or 2, wherein there is no further post irradiation treatment, and the dose of electrons is selected so as to introduce the product of total isolated vacancy concentration x path length, $[V_T] \times L$ in the irradiated diamond material of at least 0.072 ppm cm and at most 0.36 ppm cm.

30

4. A method according to claim 1 or 2, comprising an additional step of post-irradiation treating the irradiated diamond material so as to achieve the product of total isolated vacancy and at most 0.36 ppm cm.

35

5. A method according to claim 4, wherein the post-irradiation treatment step comprises annealing the irradiated diamond material at a temperature of at least 300°C and at most 600°C.
- 5 6 A method according to claim 5, wherein the dose of electrons is selected so as to introduce the product of total isolated vacancy concentration x path length, $[V_T] \times L$ in the irradiated diamond material of at most 0.72 ppm cm prior to the post-irradiation treatment step.
- 10 7. A method according to any of claims 1-6, wherein with respect to the provided diamond material, if the total integrated absorption in the visible range from 350 nm to 750 nm that is attributable to defects other than N_s^0 is greater than 90% then the absorption coefficient at 350 nm is less than 0.5 cm^{-1} and the absorption coefficient at 510 nm is less than 0.3 cm^{-1} .
- 15 8. A method according to any of claims 1-6, comprising growing precursor diamond material for use directly, or after further treatment, as the provided diamond material, the precursor diamond material having an absorption spectrum with a total integrated absorption in the visible range from 350 nm to 750 nm such that at most 90% of the integrated absorption is attributable to defects other than $[N_s^0]$.
- 20 9. A method according to claim 8 wherein the CVD process includes adding oxygen in a process gas at a concentration of >10000 ppm of oxygen molecules in the gas phase.
- 25 10. A method according to claim 8 or 9, wherein the step of growing precursor diamond material comprises providing a substrate and a source gas; and allowing homoepitaxial diamond synthesis on the substrate to wherein the synthesis environment comprises nitrogen at an atomic concentration of from about 0.4 ppm to about 50 ppm; and wherein the source gas comprises: (a) an atomic fraction of hydrogen H_f , from about 0.4 to about 0.75; (b) an atomic fraction of carbon, C_f , from about 0.15 to about 0.3; (c) an atomic fraction of oxygen, O_f , from about 0.13 to about 0.4; wherein $H_f + C_f + O_f = 1$; wherein the ratio of atomic fraction of carbon to the atomic fraction of oxygen $C_f:O_f$, satisfies the ratio of about 0.45:1 < $C_f:O_f$ < about 1.25:1; wherein the source gas comprises hydrogen atoms added as hydrogen molecules, H_2 , at an atomic
- 30
- 35

fraction of the total number of hydrogen, oxygen and carbon atoms present of between 0.05 and 0.4; and wherein the atomic fractions H_f , C_f and O_f are fractions of the total number of hydrogen, oxygen and carbon atoms present in the source gas.

5

11. A method according to any of claims 1-7, wherein a target $[N_s^0]$ concentration is predetermined according to the desired final colour of the irradiated diamond material, and the actual $[N_s^0]$ concentration in the provided CVD diamond material is controlled to within 20% of the said target $[N_s^0]$ concentration.

10

12. A method according to any preceding claim, comprising growing a precursor diamond material, and then annealing the grown CVD diamond material at a temperature of at least 1600°C to produce the said CVD diamond provided by step (i).

15

13. A method according to any preceding claim, wherein the irradiated diamond material, or the irradiated diamond material after a further post-irradiation treatment, has (i) an absorption coefficient measured at 77 K of at least 0.01 cm^{-1} at a wavelength of 741 nm; or (ii) an absorption coefficient measured at 77 K of at least 0.01 cm^{-1} at a wavelength of 394 nm.

20

14. A method according to any preceding claim, wherein the provided CVD diamond material in step (i) has a boron concentration $[B]$ of less than $5 \times 10^{15} \text{ atoms/cm}^3$.

25

15. A method according to any of claims 1-13, wherein uncompensated boron is present in the provided diamond material in a concentration of $>5 \times 10^{15} \text{ cm}^{-3}$, and the irradiation step introduces sufficient isolated vacancies into the diamond material so that the excess product of isolated vacancy concentration x path length, after isolated vacancies have been used to compensate the boron, after irradiation, or after a further post-irradiation treatment, is at least 0.072 ppm cm and at most 0.36 ppm cm .

30

16. A method according to any preceding claim, wherein at least 50 % of the provided CVD diamond has been formed from a single growth sector.

35

17. A method according to any preceding claim, wherein the irradiation dose is $1 \times 10^{17} - 1 \times 10^{18} \text{ e}^- \text{ cm}^{-2}$ for a 0.5 ct Round Brilliant Cut diamond stone.
18. A method according to any preceding claim wherein the provided diamond material shows a measurable difference in at least one of its absorption characteristics in first and second states, the first state being after exposure to irradiation having an energy of at least 5.5 eV and the second state being after thermal treatment at 798 K (525°C), and wherein post irradiation the change in colour saturation value C^* between the diamond material in the first and second states is reduced by at least 0.5.
19. A method according to any preceding claim wherein post irradiation, the change in C^* of the diamond material in first and second states is less than 1, the first state being after exposure to irradiation having an energy of at least 5.5 eV and the second state being after thermal treatment at 798 K (525°C).
20. A method according to any preceding claim, comprising selecting the $[N_s^0]$ concentration of the provided diamond material so as to provide a target V/V^0 ratio in the provided diamond material.
21. A CVD diamond material when made by a method according to any preceding claim.
22. A fancy pale blue or fancy pale blue/green CVD synthetic single crystal diamond having a boron concentration $[B]$ of $<5 \times 10^{15} \text{ atoms/cm}^3$ and the following colour characteristics:

Characteristic	Range
Hue angle α	100°-270°
Saturation C^*	At least 2 and at most 10
Lightness L^*	>65

23. A fancy pale blue or fancy pale blue/green CVD synthetic single crystal diamond material according to claim 20 or 21, having a product of total isolated vacancy concentration x path length, $[V_T] \times L$ of at least 0.072 ppm cm and at most 0.36 ppm cm.

24. Diamond material according to any of claims 21-23, having (i) an absorption coefficient measured at 77 K of at least 0.01 cm^{-1} at a wavelength of 741 nm; and (ii) an absorption coefficient measured at 77 K of at least 0.01 cm^{-1} at a wavelength of 394 nm.

25. Diamond material according to any of claims 21-24, which is a gemstone.

26. Use of a CVD diamond material according to any of claims 21-25, as a gemstone.

27. A system for being able to select and make a desired colour of diamond material within the fancy blue to blue/green colour range, having a hue angle within the range 100° - 270° ; the system comprising the steps of:

(a) predetermining a target $[N_s^0]$ concentration for a grown CVD diamond material, that after irradiation of that grown CVD diamond material will result in the said desired colour;

(b) growing diamond material by a CVD process that includes introducing sufficient nitrogen in a process gas in the CVD process so as to achieve the said target $[N_s^0]$ concentration in the grown CVD diamond material, which CVD diamond material has the properties of the provided diamond material set out in step (i) of method claim 1; then

(c) carrying out the irradiation step set out in step (ii) of method claim 1 on the grown CVD diamond material.




Figure 1




Figure 2




Figure 3




Figure 4

INTERNATIONAL SEARCH REPORT

International application No

PCT/EP2010/059084

A. CLASSIFICATION OF SUBJECT MATTER

INV. C30B29/04 C30B33/02 C30B31/20
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C30B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, INSPEC, COMPENDEX

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	COLLINS A T ET AL: "The annealing of radiation damage in De Beers colourless CVD diamond" DIAMOND AND RELATED MATERIALS, ELSEVIER SCIENCE PUBLISHERS, AMSTERDAM, NL LNKD-DOI:10.1016/0925-9635(94)90302-6, vol. 3, no. 4-6, 1 April 1994 (1994-04-01), pages 932-935, XP024179154 ISSN: 0925-9635 [retrieved on 1994-04-01]	21-24
Y	*section 2. "Experimental details", particularly second paragraph*	1-22, 25-27
Y	WO 01/96634 A1 (DE BEERS IND DIAMOND [ZA]; SCARSBROOK GEOFFREY ALAN [GB]; MARTINEAU PH) 20 December 2001 (2001-12-20) cited in the application figure 4; examples 1-3 ----- -/--	1-22, 25-27

☒ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

18 August 2010

Date of mailing of the international search report

20/09/2010

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Cook, Steven

INTERNATIONAL SEARCH REPORT

International application No

PCT/EP2010/059084

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2007/092647 A1 (SCARSBROOK GEOFFREY A [GB] ET AL) 26 April 2007 (2007-04-26) paragraph [0040] -----	1-27
A	WO 03/014427 A1 (APOLLO DIAMOND INC [US]) 20 February 2003 (2003-02-20) page 22, line 19 - line 24 -----	1-27
A	US 2008/241049 A1 (HEMLEY RUSSELL J [US] ET AL) 2 October 2008 (2008-10-02) example 4 -----	1-27
A	JP 2 184600 A (UMEDA IWA0) 19 July 1990 (1990-07-19) * abstract -----	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2010/059084

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 0196634	A1	20-12-2001	AT 311486 T	15-12-2005
			AU 6624601 A	24-12-2001
			AU 2001266246 B2	07-10-2004
			CA 2412855 A1	20-12-2001
			CN 1441859 A	10-09-2003
			CZ 20024228 A3	17-12-2003
			DE 60115435 D1	05-01-2006
			DE 60115435 T2	31-08-2006
			EP 1290251 A1	12-03-2003
			ES 2252244 T3	16-05-2006
			GB 2379451 A	12-03-2003
			HK 1057584 A1	13-01-2006
			IL 153381 A	10-12-2006
			JP 4469552 B2	26-05-2010
			JP 2004503461 T	05-02-2004
			RU 2287028 C2	10-11-2006
			TW 250231 B	01-03-2006
			US 2007148079 A1	28-06-2007
			US 2004182308 A1	23-09-2004
US 2007092647	A1	26-04-2007	NONE	
WO 03014427	A1	20-02-2003	AU 2001281404 B2	03-07-2008
			CA 2456847 A1	20-02-2003
			EP 1415022 A1	06-05-2004
			EP 2189555 A2	26-05-2010
			JP 2004538230 T	24-12-2004
US 2008241049	A1	02-10-2008	US 2006185583 A1	24-08-2006
			US 2005034650 A1	17-02-2005
JP 2184600	A	19-07-1990	JP 1844418 C	25-05-1994
			JP 5036399 B	28-05-1993