

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C09D 11/02, 5/02, C09C 1/56	A1	(11) International Publication Number: WO 96/18696 (43) International Publication Date: 20 June 1996 (20.06.96)
(21) International Application Number: PCT/US95/16453 (22) International Filing Date: 14 December 1995 (14.12.95) (30) Priority Data: 08/356,660 15 December 1994 (15.12.94) US 08/356,653 15 December 1994 (15.12.94) US (71) Applicant: CABOT CORPORATION [US/US]; 75 State Street, Boston, MA 02109-1806 (US). (72) Inventor: BELMONT, James, A.; 8 Conant Street, Acton, MA 01720 (US). (74) Agent: CHALETSKY, Lawrence, A.; Cabot Corporation, 157 Concord Road, P.O. Box 7001, Billerica, MA 01821-7001 (US).		(81) Designated States: AL, AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TT, UA, UG, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, LS, MW, SD, SZ, UG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: AQUEOUS INKS AND COATINGS CONTAINING MODIFIED CARBON PRODUCTS (57) Abstract Aqueous ink compositions are described which include a modified carbon product comprising a carbon having attached at least one organic group that is substituted with an ionic or an ionizable group. A coating composition is also described and comprises water, a binder, and a modified carbon product having at least one organic group attached to carbon wherein the organic group is substituted with an ionic or an ionizable group.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

- 1 -

AQUEOUS INKS AND COATINGS CONTAINING MODIFIED CARBON PRODUCTS

This application is a continuation-in-part of U.S. patent application serial nos. 08/356,660 and 08/356,653, both filed December 15, 1994, the disclosures of which are herein incorporated by reference.

FIELD OF THE INVENTION

This invention relates to aqueous inks and coatings which contain a modified carbon product.

BACKGROUND OF THE INVENTION

There are various classifications of inks used presently. These categories include printing inks, ultraviolet cure inks, ball-point inks, and stamp pad or marking inks. Fundamentally, inks may be composed of four major material categories. They are colorants, vehicles or varnishes, additives, and solvents.

In more detail, colorants, which include pigments, toners and dyes, provide the color contrast with the substrate. Vehicles or varnishes act as carriers for the colorants during the printing operation. Upon drying, the vehicles bind the colorants to the substrate. Additives influence the printability, film characteristics, drying speed, and end-use properties. Finally, solvents, besides participating in formation of the vehicles, are used to reduce ink viscosity and adjust drying ease and resin capability. Generally, ingredients from these four classes are weighed, mixed, and ground (i.e., dispersed) together, or separately, according to desired formulas.

Presently, predominant black pigments are carbon blacks such as furnace blacks which are used as the colorants either in dry, powdered form, a flushed paste, or liquid concentrate form. The flush paste and liquid concentrate forms are more economical since they require a minimum of dispersing effort. Generally, the form of the colorant influences the hue, permanency, bulk, opacity, gloss, rheology, end use, and print quality.

Generally, inks can be applied by letter press, lithographic, flexographic, gravure, silk screen, stencil, duplicating, and electrostatic. Inks thus can be found in such end uses as news, publication, commercial, folding carton, book, corrugated box, paper bag, wrapper, label, metal container, plastic container, plastic film, foil, laminating, food insert, sanitary paper, textile and the like. McGraw-Hill's *Encyclopedia of Science and Technology*, Vol. 7,

- 2 -

pgs. 159-164, provides further details of the types of inks available and their uses, all of which is incorporated herein by reference.

Even with the inks commercially available, there is still a need to provide inks which may be more readily prepared.

Coatings are used for decorative, protective, and functional treatments of many kinds of surfaces. These surfaces include, coils, metals, appliances, furniture, hardboard, lumber and plywood, marine, maintenance, automobile, cans, and paperboard. Some coatings, such as those on undersea pipelines, are for protective purposes. Others, such as exterior automobile coatings, fulfill both decorative and protective functions. Still others provide friction control on boat decks or car seats. Some coatings control the fouling of ship bottoms, others protect food and beverages in cans. Silicon chips, printed circuit panels, coatings on waveguide fibers for signal transmission, and magnetic coatings on video tapes and computer disks are among many so-called hi-tech applications for coatings.

Each year, tens of thousands of coating types are manufactured. In general, they are composed of one or more binders, for example resins or polymers, and at least one solvent, one or more pigments, and optionally several additives. Most coatings are manufactured and applied as liquids and are converted to "solid" films after application to the substrate.

Pigments and coatings provide opacity and color. Pigment content governs the gloss of the final film and can have important effects on its mechanical properties. Some pigments even inhibit corrosion. Further, pigments affect the viscosity and enhance the application properties of the coating. An important variable determining the properties of pigments is their particle size and particle-size distribution. Pigment manufacturing processes are designed to afford the particle size and particle-size distribution that provide the best compromise of particles for that pigment. In manufacturing coatings, it is desirable to disperse the pigment in such a way as to achieve a stable dispersion where most, if not all, of the pigment particles are separated into the individual particles designed into the product by the pigment manufacturer. The dispersion of pigment involves wetting, separation, and stabilization.

There are three categories of vehicles: those in which the binder is soluble in water, those in which it is colloiddally dispersed, and those in which it is emulsified to form a latex. Surface coating compositions are usually more or less viscous liquids with three based components: a film-forming substance or combination of substances called the binder, a pigment or combination of pigments, and a volatile liquid. The combination of binder and volatile liquid is called the vehicle which may be a solution or a dispersion of fine binder particles in a non-solvent. Pigments are finely divided, insoluble, solid particles dispersed in

- 3 -

the coating vehicle and distributed throughout the binder in the final film. Surfactants are used as pigment dispersants. The components and manufacturing of aqueous coatings are further discussed in the *Concised Encyclopedia of Polymers, Science and Engineering*, pgs. 160-171 (1990), which is incorporated herein by reference.

There is still a need for an aqueous coating that may be more readily prepared in both aqueous inks and coatings. The solvent is, or contains, water.

SUMMARY OF THE INVENTION

Accordingly, the present invention relates to an aqueous ink composition or aqueous coating composition comprising water and a modified carbon product comprising a carbon having attached an organic group. The organic group is substituted with an ionic or an ionizable group. Carbon, as used herein, is capable of reacting with a diazonium salt to form the above-mentioned modified carbon product. The carbon may be of the crystalline or amorphous type. Examples include, but are not limited to, graphite, carbon black, vitreous carbon, activated charcoal, activated carbon, and mixtures thereof. Finely divided forms of the above are preferred.

The organic group comprises a) at least one aromatic group and b) at least one ionic group, at least one ionizable group, or a mixture of an ionic group and an ionizable group. The organic group having an aromatic group is directly attached to the carbon by the aromatic group.

Alternatively, the organic group of the modified carbon product comprises a) at least one C₁-C₁₂ substituted or unsubstituted alkyl group and b) at least one ionic group, at least one ionizable group, or a mixture of an ionic group and an ionizable group.

The aqueous inks and coatings of this invention offer desirable dispersion stability, print quality, and image optical density.

The description which follows sets out additional features and advantages of the invention. These functions will be apparent from that description or may be learned by practice of the invention as described. The objectives and other advantages will be realized and attained by the processes, products, and compositions particularly pointed out in the description below and the appended claims.

DETAILED DESCRIPTION

Carbon, as used herein, is capable of reacting with a diazonium salt to form the above-mentioned modified carbon product. The carbon may be of the crystalline or

amorphous type. Examples include, but are not limited to, graphite, carbon black, vitreous carbon, activated charcoal, activated carbon, and mixtures thereof. Finely divided forms of the above are preferred.

The present invention relates to aqueous ink and coating compositions comprising an aqueous vehicle and the modified carbon product. In contrast to conventional carbon pigments, the modified carbon products for use in the ink or coating of the present invention are not difficult to disperse in an aqueous vehicle. The modified carbon products do not necessarily require a conventional milling process, nor are dispersants necessarily needed to attain a usable ink or coating. Preferably, the modified carbon products only require low shear stirring or mixing to readily disperse the pigment in water.

The carbon products may be prepared by reacting carbon as defined above, with a diazonium salt in a liquid reaction medium to attach at least one organic group to the surface of the carbon. Preferred reaction media include water, any medium containing water, and any medium containing alcohol. Water is the most preferred medium. These modified carbon products, wherein the carbon is carbon black, and various methods for their preparation are described in U.S. patent application 08/356,660 entitled "Reaction of Carbon Black with Diazonium Salts, Resultant Carbon Black Products and Their Uses," filed December 15, 1994, and its continuation-in-part application, filed concurrently with this application, both of which are incorporated herein by reference. These modified carbon products, wherein the carbon is not carbon black, and various methods for their preparation are described in patent application serial number 08/356,653 entitled "Reaction of Carbon Materials With Diazonium Salts and Resultant Carbon Products," filed December 15, 1994, also incorporated herein by reference.

To prepare the above modified carbon products, the diazonium salt need only be sufficiently stable to allow reaction with the carbon. Thus, that reaction can be carried out with some diazonium salts otherwise considered to be unstable and subject to decomposition. Some decomposition processes may compete with the reaction between the carbon and the diazonium salt and may reduce the total number of organic groups attached to the carbon. Further, the reaction may be carried out at elevated temperatures where many diazonium salts may be susceptible to decomposition. Elevated temperatures may also advantageously increase the solubility of the diazonium salt in the reaction medium and improve its handling during the process. However, elevated temperatures may result in some loss of the diazonium salt due to other decomposition processes.

Carbon black can be reacted with a diazonium salt when present as a dilute, easily stirred, aqueous slurry, or in the presence of the proper amount of water for carbon black

- 5 -

pellet formation. If desired, carbon black pellets may be formed utilizing a conventional pelletizing technology. Other carbon can be similarly reacted with the diazonium salt. In addition, when modified carbon products utilizing carbon other than carbon black for used in aqueous inks and coatings are used, the carbon should preferably be ground to a fine particle size before reaction with the diazonium salt to prevent unwanted precipitation in the ink. The organic groups which may be attached to the carbon are organic groups substituted with an ionic or an ionizable group as a functional group. An ionizable group is one which is capable of forming an ionic group in the medium of use. The ionic group may be an anionic group or a cationic group and the ionizable group may form an anion or a cation.

Ionizable functional groups forming anions include, for example, acidic groups or salts of acidic groups. The organic groups, therefore, include groups derived from organic acids. Preferably, when it contains an ionizable group forming an anion, such an organic group has a) an aromatic group or a C_1 - C_{12} substituted or unsubstituted alkyl group and b) at least one acidic group having a pKa of less than 11, or at least one salt of an acidic group having a pKa of less than 11, or a mixture of at least one acidic group having a pKa of less than 11 and at least one salt of an acidic group having a pKa of less than 11. The pKa of the acidic group refers to the pKa of the organic group as a whole, not just the acidic substituent. More preferably, the pKa is less than 10 and most preferably less than 9. Preferably, the aromatic group or the alkyl group of the organic group is directly attached to the carbon. The aromatic group may be further substituted or unsubstituted, for example, with alkyl groups. The C_1 - C_{12} alkyl group may be branched or unbranched and is preferably ethyl. More preferably, the organic group is a phenyl or a naphthyl group and the acidic group is a sulfonic acid group, a sulfinic acid group, a phosphonic acid group, or a carboxylic acid group. Examples include $-COOH$, $-SO_3H$ and $-PO_3H_2$, $-SO_2NH_2$, $-SO_2NHCOR$, and their salts, for example $-COONa$, $-COOK$, $-COO^-NR_4^+$, $-SO_3Na$, $-HPO_3Na$, $-SO_3^-NR_4^+$, and PO_3Na_2 , where R is an alkyl or phenyl group. Particularly preferred ionizable substituents are $-COOH$ and $-SO_3H$ and their sodium and potassium salts.

Most preferably, the organic group is a substituted or unsubstituted sulfophenyl group or a salt thereof; a substituted or unsubstituted (polysulfo)phenyl group or a salt thereof; a substituted or unsubstituted sulfonaphthyl group or a salt thereof; or a substituted or unsubstituted (polysulfo)naphthyl group or a salt thereof. A preferred substituted sulfophenyl group is hydroxysulfophenyl group or a salt thereof.

Specific organic groups having an ionizable functional group forming an anion are p-sulfophenyl, 4-hydroxy-3-sulfophenyl, and 2-sulfoethyl.

Amines represent examples of ionizable functional groups that form cationic groups and can be attached to the same organic groups as discussed above for the ionizable groups which form anions. For example, amines may be protonated to form ammonium groups in acidic media. Preferably, an organic group having an amine substituent has a pK_b of less than 5. Quaternary ammonium groups ($-NR_3^+$) and quaternary phosphonium groups ($-PR_3^+$) also represent examples of cationic groups and can be attached to the same organic groups as discussed above for the ionizable groups which form anions. Preferably, the organic group contains an aromatic group such as a phenyl or a naphthyl group and a quaternary ammonium or a quaternary phosphonium group. The aromatic group is preferably directly attached to the carbon. Quaternized cyclic amines, and quaternized aromatic amines, can also be used as the organic group. Thus, N-substituted pyridinium compounds, such as N-methyl-pyridyl, can be used in this regard. Examples of organic groups include, but are not limited to, $(C_5H_4N)C_2H_5^+$, $C_6H_4(NC_5H_5)^+$, $C_6H_4COCH_2N(CH_3)_3^+$, $C_6H_4COCH_2(NC_5H_5)^+$, $(C_5H_4N)CH_3^+$, and $C_6H_4CH_2N(CH_3)_3^+$.

An advantage of the modified carbon products having an attached organic group substituted with an ionic or an ionizable group is that the modified carbon products may have increased water dispersibility relative to the corresponding untreated carbon. In general, water dispersibility of the modified carbon products increases with the number of organic groups attached to the carbon having an ionizable group or the number of ionizable groups attached to a given organic group. Thus, increasing the number of ionizable groups associated with the modified carbon products should increase their water dispersibility and permits control of the water dispersibility to a desired level. It can be noted that the water dispersibility of modified carbon products containing an amine as the organic group attached to the carbon may be increased by acidifying the aqueous vehicle.

Because the water dispersibility of the modified carbon products depends to some extent on charge stabilization, it is preferable that the ionic strength of the aqueous medium be less than 0.1 molar. More preferably, the ionic strength is less than 0.01 molar. It is preferred that the modified carbon product of the present invention contain no by-products or salts.

When water dispersible modified carbon products of the present invention are prepared, it is preferred that the ionic or ionizable groups be ionized in the reaction medium. The resulting product dispersion or slurry may be used as is or diluted prior to use. Alternatively, the modified carbon products may be dried by techniques used for conventional carbon blacks. These techniques include, but are not limited to, drying in ovens and rotary

- 7 -

kilns. Overdrying, however, may cause a loss in the degree of water dispersibility. In the event that the modified carbon products above do not disperse in the aqueous vehicle as readily as desired, the modified carbon products may be dispersed using conventionally known techniques such as milling or grinding.

The modified carbon black products of this invention are particularly useful in aqueous ink formulations. Thus, the invention provides an improved ink composition comprising water and a modified carbon product according to the invention. Other known aqueous ink additives may be incorporated into the aqueous ink formulation.

In general, an ink may consist of four basic components: (1) a colorant or pigment, (2) a vehicle or varnish which functions as a carrier during printing, (3) additives to improve printability drying, and the like, and (4) solvents to adjust viscosity, drying and the compatibility of the other ink components. For a general discussion on the properties, preparation and uses of aqueous inks, see *The Printing Manual*, 5th Ed., Leach et al, Eds. (Chapman and Hall, 1993), incorporated herein by references. Various aqueous ink compositions are also disclosed, for example, in United States Patents Nos. 2,833,736, 3,607,813, 4,104,833, 4,308,061, 4,770,706, and 5,026,755, all incorporated herein by reference.

The modified carbon products of the invention, either as predispersion or as a solid, can be incorporated into an aqueous ink formulation using standard techniques. Use of a water dispersible modified carbon product of the invention provides a significant advantage and cost savings by reducing or eliminating the milling steps generally used with other conventional carbon blacks.

Flexographic inks represent a group of aqueous ink compositions. Flexographic inks generally include a colorant, a binder, and a solvent. The modified carbon products of the invention are useful as flexographic ink colorants. Example 3 shows the use of a modified carbon product of the invention in an aqueous flexographic ink formulation.

The modified carbon products of the invention can be used in aqueous news inks. For example, an aqueous news ink composition may comprise water, the modified carbon products of the invention, a resin and conventional additives such as antifoam additives or a surfactant.

The modified carbon products of this invention may also be used in aqueous coating compositions such as paints or finishes. Thus, an embodiment of the invention is an improved aqueous coating composition comprising water, resin and a modified carbon product according to the invention. Other known aqueous coating additives may be incorporated the aqueous coating composition. See, for example, McGraw-Hill Encyclopedia of Science &

Technology, 5th Ed. (McGraw-Hill, 1982), incorporated herein by reference. See also United States Patents Nos. 5,051,464, 5,319,044, 5,204,404, 5,051,464, 4,692,481, 5,356,973, 5,314,945, 5,266,406, and 5,266,361, all incorporated herein by reference.

The modified carbon products of the invention, either as a predispersion or as a solid, can be incorporated into an aqueous coating composition using standard techniques. Use of a water dispersible modified carbon product provides a significant advantage and cost savings by reducing or eliminating the milling steps generally used with other conventional carbon blacks. Some of the Examples below show the use of modified carbon products according to the invention in aqueous automotive topcoat formulations.

An aqueous ink or coating containing an aqueous vehicle and stably dispersed modified carbon product as pigment can be formed with a minimum of components and processing steps when the above carbon products are utilized. Such an ink or coating may be used for a variety of uses. Preferably, in aqueous inks and coatings of the present invention, the modified carbon products are present in an amount of less than or equal to 20% by weight of the ink or coating. It is also within the bounds of the present invention to use an aqueous ink or coating formulation containing a mixture of unmodified carbon with the modified carbon products of the present invention. Common additives such as those discussed below may be added to the dispersion to further improve the properties of the aqueous ink or coating.

EXAMPLES

Analytical Methods

BET nitrogen surface areas were obtained according to ASTM D-4820 for surface area measurements. DBPA data were obtained according to ASTM D-2414.

Volatile content was determined as follows. A carbon black sample was dried to constant weight at 125°C. A 45 mL sample of the dry carbon black was placed in a covered 50 mL crucible that had been dried at 950°C and heated in a muffle furnace for 7 minutes at 950°C. The volatile content is expressed as the percentage of weight lost by the carbon sample.

The following procedure was used in various Examples below to determine the aqueous residue of carbon black products according to this invention and untreated carbon blacks. The carbon black product (5 g) was shaken with 45 g of water for 5 minutes. The resulting dispersion was poured through a screen and rinsed with water until the washings were colorless. A 325 mesh screen was used unless indicated otherwise. After drying the

screen, the weight of residue on the screen was determined and expressed as a percentage of the carbon black product used in the test.

Example 1

Preparation of a carbon black product with a preformed diazonium salt in a pin pelletizer

This example shows another method for the preparation of a carbon black product of the present invention. A pin pelletizer was charged with 400 g of a fluffy carbon black with a surface area of $80 \text{ m}^2/\text{g}$ and a DBPA of 85 ml/100 g. A cold suspension of 4-sulfobenzenediazonium hydroxide inner salt prepared from 27.1 g of the sodium salt of sulfanilic acid, 10.32 g of sodium nitrite, 29.0 g of concentrated HCl and 293.5 g of water and was added to the pelletizer. After pelletizing for 2 minutes, the sample was removed and dried at 115°C to constant weight. The product had a 325 mesh residue of 0.1%, compared to 81% for the unreacted carbon black. Soxhlet extraction with ethanol overnight gave a carbon black product containing 1.1% sulfur, compared against 0.8% for the untreated carbon black. This shows that 27% of the $\text{p-C}_6\text{H}_4\text{SO}_3^-$ groups were attached to the carbon black product. Therefore, the carbon black product had 0.09 mmol/g of attached $\text{p-C}_6\text{H}_4\text{SO}_3^-$ groups.

Example 2

Preparation of a carbon black product with a diazonium salt generated *in situ*

This example illustrates another method for the preparation of a carbon black product of the present invention. A fluffy carbon black with a surface area of $560 \text{ m}^2/\text{g}$, a DBPA of 90 ml/100 g and a volatile content of 9.5% was used. Fifty grams of the fluffy carbon black were added to a solution of 8.83 g of sulfanilic acid dissolved in 420 g of water. The resulting suspension was cooled to 30°C and 4.6 g of concentrated nitric acid was added. An aqueous solution containing 3.51 g of sodium nitrite was then added gradually with stirring, forming 4-sulfobenzenediazonium hydroxide inner salt *in situ*, which reacts with the fluffy carbon black. The resulting product was dried in an oven at 125°C , leaving the carbon black product. The product had a 325 mesh residue of 0.1%, compared to 6% for the unreacted carbon black. The carbon black product contained 1.97% sulfur after Soxhlet extraction with ethanol overnight, compared to 0.24% sulfur for the untreated fluffy carbon black. This corresponds to attaching 53% of the $\text{p-C}_6\text{H}_4\text{SO}_3^-$ groups to the carbon black

- 10 -

product. Therefore, the carbon black product had 0.54 mmol/g of attached $\text{p-C}_6\text{H}_4\text{SO}_3^-$ groups.

Example 3

Use of a carbon black product in the preparation of an aqueous ink

This example illustrates the advantages of using a carbon black product of the present invention in an aqueous ink formulation. Ink composition A was prepared by adding 3.13 parts of the carbon black product of Example 1 to a vehicle made by mixing 2.92 parts JONCRYL 61LV resin, 0.21 parts isopropanol, 0.31 parts ARROWFLEX defoamer, 7.29 parts JONCRYL 89 resin and 6.98 parts water, and shaking the composition for 10 minutes on a paint shaker. The table below shows the 635 mesh residue level.

JONCRYL is a registered trademark for resins produced and sold by SC Johnson Polymer, Racine, WI. ARROWFLEX is a registered trademark for defoamers produced and sold by Witco, New York, NY.

Ink composition B was prepared by grinding a mixture of 120 parts of the carbon black product used in Example 1, 112 parts of JONCRYL 61LV resin, 8 parts of isopropanol, 4 parts of ARROWFLEX defoamer, 156 parts of water and 400 g of grinding media. In order to check the grind level, samples were periodically let down to composition C that contained 15.0 parts carbon black product, 14.0 parts JONCRYL 61LV resin, 1.0 parts isopropanol, 1.7 parts ARROWFLEX DEFOAMER, 35.1 parts Joncrl 89 and 33.4 parts water.

Ink composition D was prepared by grinding a mixture of 120 parts of the untreated carbon black used in Example 1, 112 parts of JONCRYL 61LV resin, 8 parts of isopropanol, 4 parts of ARROWFLEX defoamer, 156 parts of water and 400 g of grinding media. In order to check the grind level, samples were periodically let down to composition E that contained 15.0 parts carbon black product, 14.0 parts JONCRYL 61LV resin, 1.0 parts isopropanol, 1.7 parts ARROWFLEX defoamer, 35.1 parts JONCRYL 89 resin and 33.4 parts water.

The residues from ink compositions A, C and E as a function of grinding time are provided in the following table, and clearly show that a carbon black product of the present invention disperses more readily than the corresponding unreacted carbon black in these aqueous inks.

- 11 -

Dispersion time	Ink A 635 Mesh Residue, %	Ink C 635 Mesh Residue, %	Ink E 635 Mesh Residue, %
10 Minutes shaking	2.6	-	-
20 Minutes Ball Mill	-	0.3	-
40 Minutes Ball Mill	-	0.2	-
1 Hour Ball Mill	-	0.02	about 100
2 Hours Ball Mill	-	-	10.8
3 Hours Ball Mill	-	-	5.8
4 Hours Ball Mill	-	-	0.9
10 Hours Ball Mill	-	-	0.5
14 Hours Ball Mill	-	-	0.3
15 Hours Ball Mill	-	-	1.0
16 Hours Ball Mill	-	-	1.0

Example 4

Use of a carbon black product in the preparation of an aqueous coating

This example shows that carbon black products of the present invention are useful for the preparation of aqueous coatings. The carbon black product from Example 2 (10 g) was dispersed in 90 g of water by stirring for 10 minutes. Coating composition A was prepared by stirring 4.3 g of this dispersion into a mixture of 7.53 g of CARGILL 17-7240 acrylic resin, 0.80 g of dimethylethanolamine (DMEA), 19.57 g water, 0.37 g SURFYNOL CT136 surfactant, 1.32 g CARGILL 23-2347 melamine resin, 0.53 g ethylene glycol monobutyl ether and 0.075 g BYK-306 surfactant. CARGILL 17-7240 acrylic resin and CARGILL 23-2347 melamine resin are available from Cargill Inc., Minneapolis, MN. SURFYNOL CT136 is a registered trademark for surfactants produced and sold by Air Products and Chemicals, Inc., Allentown, PA. BYK-306 is a registered trademark for surfactants produced and sold by BYK-Chemie USA, Wallingford.

A millbase was prepared by grinding an oxidized carbon black product (15 g) with a surface area of 560 m²/g, a DBPA of 80ml/100g and a volatile content of 9% in a mixture of 74.6 g of CARGILL 17-7240 acrylic resin, 9.53 g DMEA, 236.5 g water and 16.35 g CT-136 surfactant until its mean volume particle size was 0.18 microns. Comparative coating

- 12 -

composition B was prepared by mixing 24.4 g of this millbase with a mixture of 17.51 g CARGILL 17-7240 acrylic resin, 1.74 g DMEA, 50.56 g water, 3.97 g CARGILL 23-2347 melamine resin, 1.59 g ethylene glycol monobutyl ether and 0.23 g BYK-306 surfactant.

Glossy lenetta paper coated with compositions A and B was dried at 350°F for 10 minutes. A clear coat was applied, and the samples were dried again. The paper coated with composition A had Hunter L,a,b values of 1.0, 0.01 and 0.03, respectively, compared to 1.1, 0.01 and -0.06, respectively for the paper coated with comparative composition B.

Example 5

Preparation of a carbon black product and its use in an aqueous coating

This example illustrates the preparation of a carbon black product of the present invention and the use of this carbon black product in an aqueous coating. A carbon black (200 g) with a CTAB surface area of 350 m²/g and a DBPA of 120 ml/100g was added to a stirred solution of 42.4 g sulfanilic acid in 2800 g of water. Nitrogen dioxide (25.5 g) was dissolved in 100 g of cold water and added to the carbon black product suspension. Bubbles were released. 4-Sulfobenzenediazonium hydroxide inner salt was formed *in situ*, which reacted with the carbon black. After stirring for one hour, 5 g of additional NO₂ was added directly to the carbon black dispersion. The dispersion was stirred for an additional 15 minutes, and left overnight. The resulting carbon black product was recovered by drying the dispersion in an oven at 130°C.

A dispersion of this carbon black product was prepared by stirring 10 g of the carbon black product in 90 g of water. Coating composition C was prepared by stirring 4.3 g of this dispersion into a mixture of 7.53 g of CARGILL 17-7240 acrylic resin, 0.80 g of DMEA, 19.57 g water, 0.37 g SURFYNOL CT136 surfactant, 1.32 g CARGILL 23-2347 melamine resin, 0.53 g ethylene glycol monobutyl ether and 0.075 g BYK-306 surfactant.

A millbase was prepared by grinding (in an attritor) an oxidized carbon black product (15 g) with a surface area of 560 m²/g, a DBPA of 91ml/100g and a volatile content of 9.5 % in a mixture of 74.6 g of CARGILL 17-7240 acrylic resin, 9.53 g DMEA, 236.5 g water and 16.35 g SURFYNOL CT-136 surfactant for 24 hours. Comparative coating composition D was prepared by mixing 24.4 g of this millbase with a mixture of 17.51 g CARGILL 17-7240 acrylic resin, 1.74 g DMEA, 50.56 g water, 3.97 g CARGILL 23-2347 melamine resin, 1.59 g ethylene glycol monobutyl ether and 0.23 g BYK-306 surfactant.

- 13 -

Glossy lenetta paper coated with compositions A and B was dried at 350°F for 10 minutes. A clear coat was applied, and the samples were dried again. The paper coated with composition C had Hunter L, a, and b values of 1.0, 0.01 and 0.03, respectively, compared to 1.1, 0.01 and -0.06, respectively for the paper coated with comparative composition D.

What is claimed is:

1. An aqueous ink composition comprising water and a modified carbon product having at least one organic group attached to the carbon wherein the organic group is substituted with an ionic or an ionizable group.
2. The aqueous ink composition of claim 1 wherein the ionic or ionizable group is a sulfonic acid group or a salt thereof, a sulfinic acid group or a salt thereof, a carboxylic acid group or a salt thereof, a phosphonic acid group or a salt thereof, or a quaternary ammonium group.
3. The aqueous ink composition of claim 1 wherein the organic group is a substituted or unsubstituted sulfophenyl group or a salt thereof, or the organic group is a substituted or unsubstituted (polysulfo)phenyl group or a salt thereof.
4. The aqueous ink composition of claim 1 wherein the organic group is a substituted or unsubstituted sulfonaphthyl group or a salt thereof, or the organic group is a substituted or unsubstituted (polysulfo)naphthyl group or a salt thereof.
5. The aqueous ink composition of claim 3 wherein the organic group is a substituted or unsubstituted p-sulfophenyl or a salt thereof.
6. The aqueous ink composition of claim 5 wherein the organic group is $p\text{-C}_6\text{H}_4\text{SO}_3\text{Na}$.
7. The aqueous ink composition of claim 1, wherein said carbon is carbon black, graphite, vitreous carbon, finely-divided carbon, activated carbon, activated charcoal, or mixtures thereof.
8. The aqueous ink composition of claim 7 wherein said carbon is carbon black.
9. An aqueous coating composition comprising water, a binder, and a modified carbon product having at least one organic group attached to carbon wherein the organic group is substituted with an ionic or an ionizable group.
10. The aqueous coating composition of claim 9 wherein the ionic or ionizable group is a sulfonic acid group or a salt thereof, a sulfinic acid group or a salt thereof, a carboxylic acid group or a salt thereof, a phosphonic acid group or a salt thereof, or a quaternary ammonium group.
11. The aqueous coating composition of claim 9 wherein the organic group is a substituted or unsubstituted sulfophenyl group or a salt thereof, or the organic group is a substituted or unsubstituted (polysulfo)phenyl group or a salt thereof.

- 15 -

12. The aqueous coating composition of claim 9 wherein the organic group is a substituted or unsubstituted sulfonaphthyl group or a salt thereof, or the organic group is a substituted or unsubstituted (polysulfo)naphthyl group or a salt thereof.

13. The aqueous coating composition of claim 11 wherein the organic group is p-sulfophenyl or a salt thereof.

14. The aqueous coating composition of claim 13 wherein the organic group is p-C₆H₄SO₃Na.

15. The aqueous coating composition of claim 9 wherein said carbon is carbon black, graphite, vitreous carbon, finely-divided carbon, activated carbon, activated charcoal, or mixtures thereof.

16. The aqueous coating composition of claim 15 wherein said carbon is carbon black.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 95/16453

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C09D11/02 C09D5/02 C09C1/56

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C09D C09C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US,A,2 867 540 (DARREL MELVIN HARRIS) 6 January 1959 see column 1, line 55-63 see column 2, line 3-32 see column 3, line 19-29 ---	1,7-9, 15,16
X	GB,A,1 191 872 (JAPAN GAS-CHEMICAL COMPANY) 13 May 1970 see page 1, line 61-67 see page 2, line 53-85 see page 3, line 117-127 see page 4, line 38-41 --- -/--	9,10,15, 16

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

23 April 1996

Date of mailing of the international search report

15. 05. 96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+ 31-70) 340-3016

Authorized officer

Girard, Y

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 95/16453

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>DATABASE WPI Section Ch, Week 8214 Derwent Publications Ltd., London, GB; Class A97, AN 82-28019E XP002001333 & SU,A,834 062 (KIEV COPYING PROBLE) , 30 May 1981 see abstract</p> <p>---</p>	1,7,8
A	<p>WO,A,91 15425 (CABOT CORP.) 17 October 1991</p> <p>---</p>	
A	<p>US,A,3 528 840 (PETER ABOYTES) 15 September 1970</p> <p>-----</p>	

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 95/16453

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-2867540	06-01-59	NONE	
GB-A-1191872	13-05-70	DE-A- 1720988 FR-A- 1544050	31-05-72
WO-A-9115425	17-10-91	US-A- 5200164 AU-B- 7666891 CA-A- 2056625 DE-D- 69113736 DE-T- 69113736 EP-A- 0481034 JP-T- 4506683	06-04-93 30-10-91 05-10-91 16-11-95 21-03-96 22-04-92 19-11-92
US-A-3528840	15-09-70	NONE	