

Office de la Propriété Intellectuelle du Canada

Un organisme d'Industrie Canada Canadian
Intellectual Property
Office

An agency of Industry Canada

CA 2465701 C 2009/01/20

(11)(21) 2 465 701

(12) BREVET CANADIEN CANADIAN PATENT

(13) **C**

(86) Date de dépôt PCT/PCT Filing Date: 2002/11/05

(87) Date publication PCT/PCT Publication Date: 2003/05/15

(45) Date de délivrance/Issue Date: 2009/01/20

(85) Entrée phase nationale/National Entry: 2004/05/04

(86) N° demande PCT/PCT Application No.: US 2002/035490

(87) N° publication PCT/PCT Publication No.: 2003/040431

(30) Priorité/Priority: 2001/11/06 (US10/012,981)

(51) Cl.Int./Int.Cl. C23C 22/34 (2006.01)

(72) Inventeurs/Inventors:

MATZDORF, CRAIG A., US;

KANE, MICHAEL J., US;

GREEN, JAMES L., III, US

(73) Propriétaire/Owner:

THE UNITED STATES OF AMERICA AS

REPRESENTED BY THE SECRETARY OF THE

NAVY, US

(74) Agent: MCFADDEN, FINCHAM

(54) Titre: POST-TRAITEMENT POUR SUBSTRATS REVETUS DE METAL

(54) Title: POST-TREATMENT FOR METAL COATED SUBSTRATES

(57) Abrégé/Abstract:

An aqueous composition for post-treating metal coated substrates such as cadmium-plated steel or zinc-nickel coated substrates and the process for using said composition to improve the corrosion-resistance, abrasion, and adhesion bonding properties of the metal coatings. The composition comprising an acidic aqueous solution having a pH ranging from about 2.5 to 4.5 containing effective amounts of trivalent chromium salts, an alkali metal hexafluorozirconate, at least one alkali metal fluorocompound, and effective amounts of water soluble thickeners and/or surfactants.





(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization

International Bureau



(43) International Publication Date 15 May 2003 (15.05.2003)

PCT

(10) International Publication Number WO 2003/040431 A3

(51) International Patent Classification⁷: C23C 22/34

(21) International Application Number:

PCT/US2002/035490

(22) International Filing Date:

5 November 2002 (05.11.2002)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

10/012,981

6 November 2001 (06.11.2001) US

- (71) Applicant (for all designated States except US): THE UNITED STATES OF AMERICA as represented by the SECRETARY OF THE NAVY [US/US]; Bldg. 435, Suite A, Naval Air Warfare Center Aircraft Division, 47076 Liljencrantz Road, Patuxent River, MD 20670-1550 (US).
- (72) Inventors; and


(75) Inventors/Applicants (for US only): MATZDORF, Craig, A. [US/US]; 44576 Spinnaker Way, California, MD 20619 (US). KANE, Michael, J. [US/US]; 20830

Harlequin Lane, Callaway, MD 20620 (US). **GREEN, James, L., III** [US/US]; 11550 Senora Lane, Lusby, MD 20657 (US).

- (74) Agents: BILLI, Ron et al.; Bldg. 435, Suite A, Naval Air Warfare Center Aircraft Division\, 47076 Liljencrantz Road, Patuxent River, MD 20670-1550 (US).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

[Continued on next page]

(54) Title: POST-TREATMENT FOR METAL COATED SUBSTRATES



CADMIUM PLATED 4130 STEEL WITH CHROMATE POST TREATMENT AFTER 1000 HOUR EXPOSURE TO ASTM B117 NEUTRAL SALT FOG

(57) Abstract: An aqueous composition for post-treating metal coated substrates such as cadmium-plated steel or zinc-nickel coated substrates and the process for using said composition to improve the corrosion-resistance, abrasion, and adhesion bonding properties of the metal coatings. The composition comprising an acidic aqueous solution having a pH ranging from about 2.5 to 4.5 containing effective amounts of trivalent chromium salts, an alkali metal hexafluorozirconate, at least one alkali metal fluorocompound, and effective amounts of water soluble thickeners and/or surfactants.

2003/040431 A3 III

Declarations under Rule 4.17:

as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)

— as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations

Published:

— with international search report

(88) Date of publication of the international search report: 4 March 2004

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

POST-TREATMENT FOR METAL COATED SUBSTRATES

BACKGROUND OF THE INVENTION

Field of the Invention

5

10

This invention relates to a process of post-treating metal coated substrates, and to the composition for treating metal coated substrates to improve the adhesion-bonding, abrasion, and corrosion-resistant properties of the coated substrates. More specifically, this invention relates to a novel composition, and to the process of using the composition to post-treat metal coated substrates. The composition comprises an acidic aqueous solution comprising effective amounts of at least one water-soluble trivalent chromium salt, an alkali metal hexafluorozirconate, at least one tetrafluoroborate and/or hexafluorosilicate and effective amounts of water-soluble thickeners and/or water-soluble surfactants.

DESCRIPTION OF PRIOR ART

15

Current high-performance post treatments for metal coated substrates are based on hexavalent chromium chemistry. Hexavalent chromium is highly toxic and a known carcinogen. As a result, the solutions used to deposit post-treatment coatings and the coating, per se are toxic. These coatings do, however, yield outstanding paint adhesion and corrosion resistance to the base metal. Typically, post-treatments or seal coatings are deposited onto the metal coating at about elevated temperatures and usually applied by immersion or spray processes. Post treatments are usually specified by the military or commercial specifications that govern each metal coating being treated. As such, there is not a unique "post treatment" specification for all metal coatings as there is for "conversion coated" aluminums.

25

20

Further, environmental laws, executive orders, and local occupational, safety, and health (OSH) regulations are driving military and commercial users in the search for chromate-free post treatments. In the case of coated metals, the metal substrates and the coatings per se are relatively non-toxic. With the addition of a chromate post treatment, however, these coatings become toxic. In addition, the use of chromate post treatments is becoming more expensive as regulations

Moreover, certain processes like spraying chromate coating solutions are forbidden at some facilities due to OSH risk, thereby forcing the use of less-than-optimum solutions. Thus, while existing chromate post treatments are outstanding in their technical performance in that they provide enhanced corrosion protection and adhesion bonding e.g. paint and other coating at a low application cost, from a life-cycle cost, environmental, and OSH perspective, chromate coatings are detrimental for people and the environment.

10 SUMMARY OF THE INVENTION

15

20

25

This invention relates to trivalent chromium post treatment (TCP) compositions and to the processes for improving the adhesion and corrosion resistant properties of metal coated substrates. These coatings and processes are generally known as "post-treatments". Post-treatments are coatings in contact with the metal being treated after formation of the initial coating and therefore the post-treatments normally have no direct contact with the underlying substrate, except possibly through some pores in the metal coating.

More specifically, this invention relates to a composition and to the process of using said composition to post-treat metal coated substrates at ambient temperatures or higher e.g. temperatures ranging up to about 200°F. Specifically, this invention relates to a composition for posttreating metal coatings to improve the corrosion-resistance and adhesion bonding properties thereof e.g. paint adhesion etc. The composition comprises an acidic aqueous solution having a pH ranging from about 2.5 to 4.5 and preferably 3.7 to 4.0, and comprises, per liter of said solution, from about 0.01 to 22 grams of a water-soluble trivalent chromium salt, about 0.01 to 12 grams of an alkali metal hexafluorozirconate, about 0.01 to 12 grams of at least one fluoro-compound selected from the group consisting of an alkali metal tetrafluoroborate, an alkali metal hexafluorosilicate and various combinations thereof, from about 0 to 10 grams per liter and preferably 0 to 2.0 grams of at least one water-soluble thickener, and from 0 to 10 grams per liter and preferably 0 to 2.0 grams of at least one water-soluble non-ionic, cationic or anionic surfactant.

DESCRIPTION OF THE DRAWINGS

5

Fig. 1 photo shows TCP post-treatment of cadmium plated steel.
Fig. 2 photo shows chromate post-treatment of cadmium plated steel.
Fig. 3 photo shows cadmium plated steel without TCP post-treatment.
Fig. 4 photo shows cadmium plated steel with TCP post-treatment.
Fig. 5 photo shows cadmium plated steel with chromate post-treatment.
Fig. 6 shows cadmium plated steel without post-treatment.
Fig. 7 photo shows basic zinc-nickel plated steel with TCP post-treatment.
Fig. 8 photo shows acid zinc-nickel plated steel with TCP post-treatment.
Fig. 9 photo shows basic zinc-nickel plated steel with chromate post-treatment
Fig. 10 photo shows acid zinc-nickel plated steel with chromate post-treatment
Fig. 11 photo shows basic zinc-nickel plated steel with TCP post-treatment.
Fig. 12 photo shows acid zinc-nickel plated steel with TCP post-treatment.
Fig. 13 photo shows basic zinc-nickel plated steel with chromate post-treatmen
Fig. 14 photo shows acid zinc-nickel plated steel with chromate post-treatment

Fig. 15 photo shows zinc-nickel coating with no post-treatment.

Fig. 16 photo shows zinc-nickel coating with TCP post-treatment.

25

20

Fig. 17 photo shows zinc-nickel coating with no post-treatment after 24 hours in ASTM B 117 neutral salt fog.

Fig. 18 photo shows zinc-nickel coating with TCP post-treatment after 24 hours in ASTM B 117 neutral salt fog.

5

10

15

DETAILED DESCRIPTION OF THE INVENTION

The invention is directed to a composition and to the process of post-treating metal coated substrates such as coatings of cadmium, zinc and zinc alloys such as tin-zinc and zinc-nickel, aluminum and aluminum alloys such as aluminum-manganese, copper, silver and other metals and their alloys that require a post treatment to enhanced corrosion protection, paint adhesion, or tarnish resistance.

More specifically, this invention relates an acidic aqueous solution having a pH ranging from about 2.5 to 4.5, and preferably from about 3.7 to 4.0 and to the use of said solution for post-treating metal coated substrates to improve the adhesive bonding, abrasion, and corrosion resistance properties of the metal coatings. The compositions of this invention comprise, per liter of solution, from about 0.01 to 22 grams and preferably from about 4.0 to 8.0 grams e.g. 6.0 grams of at least one water soluble trivalent chromium salt e.g. chromium sulfate, about 0.01 to 12 grams and preferably about 6 to 10 grams e.g. 8.0 grams of at least one alkali metal hexafluorozirconate, about 0.01 to 12 grams and preferably from about 0.12 to 1.2 grams e.g. 0.24 to 0.36 grams of at least one alkali metal tetrafluoroborate and/or an alkali metal hexafluorosilicate and mixtures thereof at various ratio.

25

20

In some processes, depending on the physical character of the metal coated substrate, the addition of a water soluble thickener to the solution aids in optimum film formation during spray and wipe-on applications by slowing down solution evaporation. This also mitigates the formation of powdery deposits that degrade paint adhesion. In addition, the use of thickeners aid in proper film formation during large area applications and mitigates the diluent effect of rinse water remaining on the substrate during processing from previous steps. This feature yields films that have no streaks and are better in coloration and corrosion protection. A water-soluble thickener such as cellulose are present in the acidic solution in amounts ranging from about 0 to 10 grams per liter and preferably 0 to 2.0 grams and more preferably from 0.5 to 1.5 e.g. about 1.0 gram per liter of the aqueous solution. Depending on the

character of the coated substrate, an effective but small amount of at least one water-soluble surfactant can be added to the acidic solution in amounts ranging from about 0 to about 10 grams per liter and preferably 0 to 2.0 grams and more preferably from 0.5 to 1.5 grams e.g. 1.0 gram per liter of the acidic solution. These surfactants are known in the art of aqueous solutions and are organic compounds selected from the group consisting of non-ionic, cationic and anionic surfactants.

The trivalent chromium may be added as a water-soluble trivalent chromium compound, preferably as a trivalent chromium salt. Although the resultant coating is rinsed with water, it is desirable to use chromium salts that provide anions not as corrosive as the chlorides. Preferably these anions are selected from the group consisting of nitrates, sulphate, phosphate and acetates. Specifically, in formulating the acidic aqueous solutions of this invention, the chromium salt is added conveniently to the solution in its water soluble form wherein the valence of the chromium is plus 3. Some preferred chromium compounds are added to the solution in the form of $Cr_2(SO_4)_3$, $(NH_4)Cr(SO_4)_2$ or $KCr(SO_4)_2$ and various mixtures of these compounds. The most preferred trivalent chromium concentration is within the range of about 4 to 8 grams or 6.0 grams per liter of the aqueous solution. It has been found that particularly good results are obtained when the trivalent chromium compound is present in solution in this preferred range. The preferred metal fluorozirconate addition to the solution ranges from about 6 to 10 grams or 8.0 grams per liter. The post treatment of the metal coating can be carried out at low temperatures including the temperature of the solution e.g. temperatures ranging up to about 200°F or at ambient temperatures. Room temperature treatment is preferred in that this eliminates the necessity for heating equipment. The coating may be air dried by any of the methods known in the art, for example, oven drying, forced air drying, exposure to infra-red lamps and the like.

10

15

20

25

30

The following Examples illustrate the aqueous solutions of this invention and the method of using the solutions in post treating metal coated substrates.

EXAMPLE 1

An acidic aqueous solution having a pH ranging from about 3.7 to 4.0 for post-treating coating metals to improve the corrosion-resistant and adhesion bonding properties comprising from about 6.0 grams of trivalent chromium sulfate per liter of solution, about 8.0 grams of potassium hexafluorozirconate per liter of solution, about

0.01 grams of potassium tetrafluoroborate, about 1.0 gram of a cellulose thickener per liter and about 1.0 gram of a water soluble nonionic surfactant per liter of solution.

EXAMPLE 2

5

An acidic aqueous solution having a pH ranging from 3.7 to 4.0 for post-treating coated metal to improve adhesion bonding and corrosion-resistant which comprises, per liter of solution, from about 0.01 to 22 grams of trivalent chromium sulfate, about 0.01 to 12 grams of potassium hexafluorozirconate, about 0.01 to 12 grams of potassium tetrafluoroborate and from about 0.5 to 1.5 grams of methylcellulose thickener.

10

EXAMPLE 3

An acidic aqueous solution having a pH ranging from 3.7 to 4.0 for post-

treating coated metals to improve adhesion bonding and corrosion resistant which comprises, per liter of solution, from about 4.0 to 8.0 grams of trivalent potassium-chromium sulfate ($KCr(SO_4)_2$), about 6 to 10 grams of potassium hexafluorozirconate

about 0.01 to 12 grams of potassium hexafluorosilicate and from about 0.5 to 1.5

grams of methylcellulose thickener.

20

25

15

EXAMPLE 4

A preferred method of preparing the acidic solution comprises mixing about 0.01 to 22 grams per liter of basic chromium III sulfate and preferably about 6.0 grams per liter with about 0.01 to 12 grams per liter of potassium hexafluorozirconate, preferably 8.0 grams per liter in distilled or deionized water. The solution is ready to use after a dwell period of 24 hours, and preferably after the pH of the solution has risen between 3.7 and 4.0. About 0.1 weight percent of Methocel F4M, or 1.0 gram per liter is added for optimum performance. Potassium tetrafluoroborate and/or potassium hexafluorosilicate is added in amounts ranging from 0.01 grams per liter up to their solubility limit. Preferably, about 50% weight percent of the fluorosilicate is added based on the weight of the fluorozirconate. About 1.0 to 10 weight percent of the fluorozirconate salt is added to the solution based on the weight of the fluorozirconate salt. More preferably, about 3.0 weight percent of the potassium tetrafluoroborate, based on the weight of the fluorozirconate is added to the solution.

The above examples may be stabilized by the manipulation of this pH. For example, to a freshly made solution of 8 grams per liter of potassium hexafluorozirconate and 6 grams per liter of chromium III sulfate dilute sulfuric acid is added to lower the pH to about 3.0. After about 1 week, the pH rises to about 3.6 where it stabilized without further chemical manipulation.

EXAMPLE 5

A post-treatment was applied to metal coated substrates as follows: Mix 0.01 to 22 grams per liter chromium III sulfate basic (or up to solubility limit), preferably 6.0 grams per liter with 0.01 to 12 grams per liter of potassium hexafluorozirconate (or up to solubility limit), preferably 8.0 grams per liter in distilled or deionized water. The composition is ready to use after a dwell of 24 hours, most preferably after the pH of the solution has risen to about 3.7 to 4.0.

EXAMPLE 6

10

15

25

30

To Example 5, add 0.01 to 30% by weight of the solution of thickener and/or a surfactant to aid in spraying or wiping solution. Preferably, add 0.1 weight percent Methocel F4M, or 1.0 gram per liter for optimum performance.

EXAMPLE 7

hexafluorosilicate was added in an amount ranging from 0.01 grams per liter up to their solubility limits. Preferably, add about 50% weight percent of the fluorosilicate to Example 6 based on the weight of the fluorozirconate. An alternative is the addition of about 0.01 to 100 weight percent of the fluoroborate salt based on the weight of the fluorozirconate salt based on the fluorozirconate salt. Preferably, 1 to 10 weight percent of the fluoroborate salt based on the weight of the fluorozirconate salt is added to the solution. More preferably, about 3.0 weight percent of the potassium tetrafluoroborate based on the weight of the fluorozirconate salt is added to the solution. A preferred solution comprises 8 grams per liter of potassium hexafluorozirconate, 6 grams per liter of chromium III sulfate basic, and 0.24 grams per liter of potassium tetrafluoroborate. This preferred ratio of the tetrafluoroborate to hexafluorozirconate holds for all concentrations of the hexafluorozirconate.

EXAMPLE 8

A post treatment was applied to a cadmium coat metal as follows. Immediately after plating a 4" by 6" by 0.040" piece of AISI 4130 steel with 0.5 mils (0.0005 inches) of cadmium metal using standard electroplating methods, the panel was rinsed thoroughly two times in deionized water. Immediately after rinsing, the panel was immersed into a solution of Example 7 for 5 minutes at ambient conditions. The 5-minute immersion was immediately followed by two deionized water rinses. The panel was air-dried at ambient conditions before being scribed through the cadmium coating to the steel substrate and subjected to 1000 hours of neutral salt fog per ASTM B 117. The coupon was held in a rack at 15 degrees for the duration of the test. This was tested alongside a "control" that consisted of a similarly-plated cadmium coating on 4130 steel that was post treated by immersing in a 5% solution of potassium dichromate for 2 minutes.

Fig. 1 and 2 (Photos 1 and 2) show the post treatment and chromate control on cadmium-plated steel as made. Fig. 3 (Photo 3) shows a cadmium coating without a post treatment. Figs. 4 and 5 (Photos 4 and 5) show the same panels after the 1000-hour exposure to the neutral salt fog. Fig. 6 (Photo 6) shows the cadmium coating without a post treatment after only 72 hours. As shown in the photos, the post treatment provides significant corrosion protection to the cadmium coating and is more or less equivalent to the chromate post treatment control.

EXAMPLE 9

Post treatment coatings were applied to two types of zinc-nickel alloy plating as follows. Zinc-nickel alloys are potential alternatives to cadmium and have similar corrosion and other requirements. The first type of zinc-nickel, called "basic" zinc-nickel, as plated by standard industry methods from a composition sold by Dipsol-Gumm. The second type of zinc-nickel, called "acid" zinc-nickel, was plated by the Boeing Company using a proprietary composition. Each coating is different due to variations in zinc content, brightness, density and performance in qualifying tests as an alternative to cadmium. As a result each is treated as a separate competitor although they are related alloys.

25

20

10

One panel each of the basic- and acid-zinc-nickel was immersed for 5 minutes in a solution of Example 7 at ambient conditions. Two deionized water rinses were completed after the 5-minute immersion. The panels were air-dried at ambient conditions before being scribed through the zinc-nickel coating to the steel substrate and subjected to 1000 hours of neutral salt fog per ASTM B 117. The coupons were held in a rack at 15 degrees for the duration of the test. This was tested alongside a "control" that consisted of similarly-plated zinc-nickel coatings on 4130 steel that were post treated by immersing in a 5% solution of potassium dichromate for 2 minutes.

Fig. 7, 8, 9 and 10 (Photos 7, 8, 9 and 10) show the post treatment and

chromate control on basic- and acid zinc-nickel as made. Figs. 11-14 (Photos

11 to 14) show the same panels after the 1000-hour exposure to the neutral salt

10

fog. As shown by the photos, the post treatment provides significant corrosion protection to the zinc-nickel coatings and is more or less equivalent to the chromate post treatment controls. Zinc-nickel coatings without post

15

treatments will show red corrosion products after about 72 hours, similar to cadmium. The post treatment (TCP), as well as the chromate control, provides a substantial boost in corrosion resistance compared to none.

20

25

30

EXAMPLE 10

Post treatment coatings were applied to "basic" zinc-nickel, which was plated by standard industry methods from a composition sold by Dipsol-Gumm. One panel with a 0.005" (0.5 mil) thick basic-zinc-nickel electroplated coating was immersed for 5 minutes in a solution of Example 7 at ambient conditions. A second panel was plated but not post treated. Two deionized water rinses were completed after the 5-minute immersion. The panels were air-dried at ambient and subjected to 24 hours of neutral salt fog per ASTM B 117. The coupons were held in a rack at 15° for the duration of the test. Figs. 15-18 (photos 15, 16, 17, and 18) show the post-treatment and control before and after exposure to the salt fog. As seen, the post-treatment (TCP) provides significant corrosion protection to the zinc-nickel coating.

For purposes of this invention, the water soluble surfactants are added to the chromate solution in amounts ranging from about 0 to 10 grams per liter and

preferably 0.0 to about 2.0 grams per liter and more preferably from about 0.5 to 1.5 grams per liter of the trivalent chromium solution. The surfactants are added to the aqueous (TCP) solution to provide better wetting properties by lowering the surface tension thereby insuring complete coverage, and a more uniform film on the coated substrate. The surfactants include at least one water soluble compound selected from the group consisting of the non-ionic, anionic and cationic surfactants. Some of the preferred water soluble surfactants include the monocarboxyl imidoazoline, alkyl sulfate sodium salts (DUPONOL®), tridecyloxy poly(alkyleneoxy ethanol), ethoxylated or propoxylated alkyl phenol (IGEPAL®), alkyl sulfoamides, alkaryl sulfonates, palmitic alkanoyl amides (CENTROL®), octylphenyl polyethoxy ethanol (TRITON®), sorbitan monopalmitate (SPAN®), dodecylphenyl polyethylene glycol ether (e.g. TERGITROL®), alkyl pyrrolidone, polyalkoxylated fatty acid esters, alkylbenzene sulfonates and mixtures thereof. Other known water soluble surfactants are disclosed by "Surfactants and Detersive Systems", published by John Wiley & Sons in Kirk-Othmer's Encyclopedia of Chemical Technology, 3rd Ed.

10

15

20

25

30

When large surfaces do not permit immersion or where vertical surfaces are to be sprayed, thickening agents are added also to retain the aqueous (TCP) solution on the surface for sufficient contact time. The thickeners employed are known inorganic and organic water soluble thickeners which can be added to the trivalent chromium solutions in effective amounts ranging from about 0 to 10 grams per liter and preferably 0.0 and about 2.0 grams per liter and more preferably from about 0.5 to 1.5 grams per liter of the acidic solution. Specific examples of the preferred thickeners include the cellulose compounds, e.g. hydroxypropyl cellulose (e.g. KlucelTM), ethyl cellulose, hydroxypethyl cellulose, and methyl cellulose. Some of the water soluble inorganic thickeners include colloidal silica, clays such as bentonite, starches, gum arabic, tragacanth, agar and various combinations thereof.

While this invention has been described by a number of specific examples, it is obvious that there are other variations and modifications which can be made without departing from the spirit and scope of the invention as particularly set forth in the appended claims.

CLAIMS:

- 1. A process for post treating metal coated substrates to improve the corrosion-resistance, abrasion, and adhesion bonding properties which comprises treating the metal coated substrates with an acidic aqueous solution having a pH ranging from about 2.5 to 4.5 comprising, per liter of said solution, from about 0.01 to 22 grams of a water soluble trivalent chromium salt, about 0.01 to 12 grams of an alkali metal hexafluorozirconate and about 0.01 to 12 grams of at least one fluoro-compound selected from the group consisting of alkali metal tetrafluoroborates, alkali metal hexafluorosilicate and mixtures thereof.
- 2. The process of claim 1, wherein the pH of the aqueous solution ranges from about 3.7 to 4.0 and the temperature of the solution is about room temperature.
- 3. The process of claim 2, wherein the trivalent chromium salt ranges from about 4 to 8 grams, the hexafluorozirconate ranges from about 6 to 10 grams, and the tetrafluoroborate ranges from about 0.12 to 1.2 grams.
- 4. The process of any one of claims 1 to 3, wherein said acidic aqueous solution further comprises, per liter of said solution, 10 grams or less of at least one water soluble thickener and 10 grams or less of at least one water soluble surfactant.
- 5. The process of claim 4, wherein the thickener is a cellulose compound ranging from about 0.5 to 1.5 grams.
- 6. The process of claim 4 or 5, wherein the surfactant is a nonionic surfactant ranging from about 0.5 to 1.5 grams.
- 7. A process for post treating metal coated substrates to improve the corrosion-resistance, abrasion, and adhesion bonding properties which comprises treating the metal coated substrates with an aqueous solution having a pH ranging from about 3.7 to 4.0 which comprises, per liter of solution, from about 4.0 to 8.0 grams of a water soluble trivalent chromium salt, about 6.0 to 10 grams of an alkali metal hexafluorozirconate, and about 0.12 to 1.2 grams of at least one fluoro-compound selected from the group consisting of tetrafluoroborate, hexafluorosilicate and mixtures

thereof.

- 8. The process of claim 7, wherein the tetrafluoroborate is present in the solution in an amount ranging from about 0.24 to 0.36 grams and the post-treated metal coated substrate is subsequently treated with hot water at temperatures ranging up to about 200°F.
- 9. The process of claim 7, wherein about 0.5 to 1.5 grams of a cellulose thickener is added to the acidic solution.
- 10. The process of claim 7, wherein the chromium salt is trivalent chromium sulfate.
- 11. The process of claim 7, wherein the alkali metal zirconate is potassium hexafluorozirconate.
- 12. The process of claim 7, wherein the metal coated substrate is a cadmium-plated steel.
- 13. The process of claim 7, wherein the metal coated substrate is a zinc nickel alloy coated substrate.
- 14. A composition for post-treating metal coated substrates to improve the corrosion-resistance, abrasion, and adhesion bonding properties which comprises an acidic aqueous solution having a pH ranging from about 2.5 to 4.5, and containing per liter of said solution, from about 0.01 to 22 grams of a water-soluble trivalent chromium salt, about 0.01 to 12 grams of an alkali metal hexafluorozirconate and about 0.01 to 12 grams of at least one fluoro-compound selected from the group consisting of an alkali metal tetrafluoroborate, an alkali metal hexafluorosilicate and mixtures thereof.
- 15. The composition of claim 14, wherein the pH of the aqueous solution ranges from about 3.7 to 4.0
- 16. The composition of claim 15, wherein the trivalent chromium salt ranges from about 4.0 to 8.0 grams, the hexafluorozirconate ranges from about 6.0 to 10 grams, and

the tetrafluoroborate ranges from about 0.12 to 1.2 grams.

- 17. The composition of any one of claims 13 to 15, wherein said acidic aqueous solution further comprises, per liter of said solution, 10 grams or less of at least one water soluble thickener and 10 grams or less of at least one water soluble surfactant.
- 18. The composition of claim 17, wherein the thickener ranges from about 0.5 to 1.5 grams.
- 19. The composition of claim 17 or 18, wherein the surfactant ranges from about 0.5 to 1.5 grams.
- 20. A composition for post-treating metal coated substrates to improve the corrosion-resistance, abrasion, and adhesion bonding properties which comprises an acidic aqueous solution having a pH ranging from about 3.7 to 4.0 and containing per liter of said solution, from about 4.0 to 8 grams of a water soluble trivalent chromium salt, about 6.0 to 10 grams of an alkali metal hexafluorozirconate and about 0.01 to 12 grams of at least one fluoro-compound selected from the group consisting of tetrafluoroborate, hexafluorosilicate and mixtures thereof.
- 21. The composition of claim 20, wherein the tetrafluoroborate is present in the solution in an amount ranging from about 0.24 to 0.36 grams.
- 22. The composition of claim 21, wherein about 0.5 to 1.5 grams of a cellulose thickener is added to the solution.
- 23. The composition of claim 22, wherein the chromium salt is trivalent chromium sulfate.
- 24. The composition of claim 23, wherein the alkali metal zirconate is potassium hexafluorozirconate.
- 25. The composition of claim 20 or 21, wherein said acidic aqueous solution further comprises, per liter of said solution, 2.0 grams or less of at least one water soluble thickener and 2.0 grams or less of at least one water soluble surfactant.


Application number / numéro de demande: 2465701	
Figures: 1-6, 9,10,13-18	
Pages:	

Unscannable item(s)
received with this application
To inquire if you can order a copy of the unscannable items, please visit the
CIPO WebSite at HTTP://CIPO.GC.CA

Item(s) ne pouvant être balayés


Documents reçus avec cette demande ne pouvant être balayés.

Pour vous renseigner si vous pouvez commander une copie des items ne pouvant être balayés, veuillez visiter le site web de l'OPIC au HTTP://CIPO.GC.CA



BASIC ZINC-NICKEL PLATED 4130 STEEL WITH TCP POST TREATMENT-AS TREATED


FIG-7




ACID ZINC-NICKEL PLATED 4130 STEEL WITH TCP POST TREATMENT-AS TREATED

FIG-8

WO 03/040431



BASIC ZINC-NICKEL PLATED 4130 STEEL WITH TCP POST TREATMENT— FIG — 11 AFTER 1000 HOUR EXPOSURE TO ASTM B117 NEUTRAL SALT FOG



ACID ZINC-NICKEL PLATED 4130 STEEL WITH TCP POST TREATMENT— FIG — 12 AFTER 1000 HOUR EXPOSURE TO ASTM B117 NEUTRAL SALT FOG