

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
2 March 2006 (02.03.2006)

PCT

(10) International Publication Number
WO 2006/021526 A1

- (51) International Patent Classification⁷: **A61K 8/49**, C11D 3/28, D01F 1/10, A61Q 1/00, 3/00, 5/00, 9/00, 15/00, 17/00, 19/00
- (21) International Application Number: PCT/EP2005/053990
- (22) International Filing Date: 15 August 2005 (15.08.2005)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 60/603,590 23 August 2004 (23.08.2004) US
- (71) Applicant (for all designated States except US): **CIBA SPECIALTY CHEMICALS HOLDING INC.** [CH/CH]; Klybeckstrasse 141, CH-4057 Basel (CH).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **LUPIA, Joseph Anthony** [US/CH]; Wielandstrasse 2, CH-4153 Reinach (CH). **SUHADOLNIK, Joseph** [US/US]; 337 Hallocks Mill Road, Yorktown Heights, NY 10598 (US). **WOOD, Mervin Gale** [US/US]; 4320 Carlyle Way, Apt. #312, Mobile, AL 36609 (US). **MARTIN, De Wanda H.** [US/US]; Route 2 Box 24, 383 Central Avenue, Fruitdale, AL 36539 (US).
- (74) Common Representative: **CIBA SPECIALTY CHEMICALS HOLDING INC.**; Patent Department, Klybeckstrasse 141, CH-4057 Basel (CH).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 2006/021526 A1

(54) Title: STABILIZED BODY CARE PRODUCTS, HOUSEHOLD PRODUCTS, TEXTILES AND FABRICS

(57) Abstract: Disclosed are stabilized body care products, household products, textiles and fabrics which comprise certain sterically hindered alkoxyamine salt compounds. Dyed products and articles are effectively stabilized against color degradation. The products are for example skin-care products, hair-care products, dentifrices, cosmetics, laundry detergents and fabric softeners, non-detergent based fabric care products, household cleaners and textile-care products.

Stabilized Body Care Products, Household Products Textiles And Fabrics

The present invention relates to the use of certain sterically hindered amine salt compounds for the protection of body care products, household products, textiles and fabrics against the deleterious effects of light, heat and oxygen.

The stabilized compositions for example comprise dyes that are stabilized against color change.

10 Background

WO 00/25730 and WO 00/25731 are aimed at the stabilization of body care and household products.

U.S. Pat. app. No. 60/377,381, filed 05/02/2002, discloses the use of selected hindered nitroxyl, hydroxylamine and hydroxylamine salt compounds in formulations of body care products, household products, textiles and fabrics, and is incorporated herein by reference.

WO 01/07550 teaches the treatment of fabric with hindered amine stabilizers.

20 U.S. Pat. No. 6,254,724 teaches the stabilization of pulp and paper with hindered-amine based compounds.


It is now found that certain sterically hindered amine salt compounds provide outstanding protection against light-induced fading of home personal care products.

25

Detailed Disclosure

The present invention pertains to a stabilized composition comprising

- (a) a body care product, household product, textile or fabric and
- (b) an effective stabilizing amount of one or more compounds of formula



wherein

G_1 and G_2 are independently alkyl of 1 to 4 carbon atoms or are together pentamethylene;

Z_1 and Z_2 are each methyl, or Z_1 and Z_2 together form an unsubstituted linking moiety or a
linking moiety substituted by one or more groups selected from an ester, ether, hydroxy,
5 oxo, cyanohydrin, amide, amino, carboxy or an urethane group;

E is alkoxy of 1 to 18 carbon atoms, cycloalkoxy of 5 to 12 carbon atoms or aralkoxy of 7 to
15 carbon atoms, or E is $-O-T-(OH)_b$;

T is a straight or branched chain alkylene of 1 to 18 carbon atoms, cycloalkylene of 5 to 18
carbon atoms, cycloalkenylene of 5 to 18 carbon atoms, a straight or branched chain
10 alkylene of 1 to 4 carbon atoms substituted by phenyl or by phenyl substituted by one or
two alkyl groups of 1 to 4 carbon atoms;

b is 1, 2 or 3 with the proviso that b cannot exceed the number of carbon atoms in T, and
when b is 2 or 3, each hydroxyl group is attached to a different carbon atoms of T; and

HY is an inorganic or organic acid; wherein the total charge of cations is equal to the total
15 charge of anions.

For example, Y is phosphate, phosphonate, carbonate, bicarbonate, nitrate, chloride,
bromide, bisulfite, sulfite, bisulfate, sulfate, borate, formate, acetate, benzoate, citrate,
oxalate, tartrate, acrylate, polyacrylate, fumarate, maleate, itaconate, glycolate, gluconate,
20 malate, mandelate, tigliate, ascorbate, polymethacrylate, a carboxylate of nitrilotriacetic acid,
a carboxylate of hydroxyethylethylenediaminetriacetic acid, a carboxylate of ethylene-
diaminetetraacetic acid, a carboxylate of diethylenetriaminepentaacetic acid, a carboxylate of
diethylenediaminetetraacetic acid, a carboxylate of diethylenetriaminepentaacetic acid,
alkylsulfonate, arylsulfonate, or alkyl-substituted arylsulfonate.

25

Y is a carboxylate, especially a carboxylate of a mono-, di-, tri- or tetracarboxylic acid, mainly
of 1-18 carbon atoms, such as a formate, acetate, benzoate, citrate, or oxalate.

For example, Y is chloride, bisulfate, sulfate, phosphate, nitrate, ascorbate, formate, acetate,
30 benzoate, oxalate, citrate, a carboxylate of ethylenediaminetetraacetic acid or of diethylene-
triaminepentaacetic acid or polyacrylate.

For instance, Y is chloride, bisulfate, ascorbate, or citrate.

The total charge for the salt is neutral. For example, the total number of cations is equal to the total number of anions.

5 The certain hindered amine compounds described herein are acid salts of the corresponding hindered amine compounds.

For example, Z_1 and Z_2 together are a hydrocarbon linking moiety containing 1-200 carbon and heteroatoms; for instance, 1-60 carbon atoms and 0-60 heteroatoms; especially, 0-30 heteroatoms selected from oxygen atoms and nitrogen atoms.

10

For instance, Z_1 and Z_2 as a linking moiety are a chain of 2 or 3 carbon atoms or 1 or 2 carbon atoms and a nitrogen or oxygen atom forming together with the remaining structure in formula (I) a saturated unsubstituted 5- or 6-membered heterocyclic ring or a 5- or 6-membered heterocyclic ring substituted by one or more groups selected from an ester, ether, hydroxy, oxo, cyanohydrin, amide, amino, carboxy or an urethane group. The substituents in Z_1 and Z_2 themselves may contain hindered amine moieties. For example, the compounds of the formula (I) contain 1-4 hindered amine or hindered ammonium groups. For instance, the compounds of formula (I) contain 1 or 2 hindered amine or hindered ammonium moieties.

15

20 Any group denoted as aryl mainly means C_6 - C_{12} aryl; for example, aryl is phenyl or naphthyl; for instance, aryl is phenyl.

Group denoted as alkyl are, within the definitions given, mainly C_1 - C_{18} alkyl, for example methyl, ethyl, propyl such as n- or isopropyl, butyl such as n-, iso-, sec- and tert-butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, or octadecyl.

25

Groups denoted as alkylene are, within the definitions given, for example methylene, 1,2-ethylene, 1,1-ethylene, 1,3-propylene, 1,2-propylene, 1,1-propylene, 2,2-propylene, 1,4-butylene, 1,3-butylene, 1,2-butylene, 1,1-butylene, 2,2-butylene, 2,3-butylene, or $-C_5H_{10}-$, $-C_6H_{12}-$, $C_7H_{14}-$, $-C_8H_{16}-$, $-C_9H_{18}-$, $-C_{10}H_{20}-$, $-C_{11}H_{22}-$, $-C_{12}H_{24}-$, $-C_{13}H_{26}-$, $-C_{14}H_{28}-$, $-C_{15}H_{30}-$, $-C_{16}H_{32}-$, $-C_{17}H_{34}-$, or $-C_{18}H_{36}-$.

30

Groups denoted as cycloalkyl or cycloalkoxy are mainly C₅-C₁₂cycloalkyl or C₅-C₁₂cycloalkoxy, the cycloalkyl part being, for example, cyclopentyl, cyclohexyl, cycloheptyl, cyclooctyl, cyclononyl, cyclodecyl, cycloundecyl, or cyclododecyl. Cycloalkenyl is mainly C₅-C₁₂cycloalkenyl including cyclopentenyl, cyclohexenyl, cycloheptenyl, cyclooctenyl, cyclononenyl, cyclodecenyl, cycloundecenyl, or cyclododecenyl.

Aralkyl or aralkoxy is, for example, phenylalkyl or phenylalkoxy, which is alkyl or alkoxy substituted by phenyl. Examples for phenylalkyl or phenylalkoxy are, within the definitions given, benzyl, benzyloxy, alpha-methylbenzyl, alpha-methylbenzyloxy, cumyl, or cumyloxy.

Alkenyl residues are mainly alkenyl of 2 to 18 carbon atoms; for example, allyl.

Alkynyl residues are mainly alkynyl of 2 to 12 carbon atoms; for example, propargyl.

A group denoted as acyl is mainly R(C=O)-, where R is an aliphatic or aromatic moiety.

An aliphatic or aromatic moiety, such as mentioned above or other definitions, mainly is an aliphatic or aromatic C₁-C₃₀hydrocarbon; examples are aryl, alkyl, cycloalkyl, alkenyl, cycloalkenyl, bicycloalkyl, bicycloalkenyl, and combinations of these groups.

Examples for acyl groups are alkanoyl of 2 to 12 carbon atoms, alkenoyl of 3 to 12 carbon atoms, or benzoyl.

Alkanoyl embraces, for example, formyl, acetyl, propionyl, butyryl, pentanoyl, or octanoyl; for example, C₂-C₈alkanoyl; for instance, acetyl.

Alkenoyl residues are, for example, acryloyl, or methacryloyl.

The alkyl groups in the different substituents may be linear or branched.









Examples for alkenyl groups with 2 to 4 carbon atoms are ethenyl, propenyl, or butenyl.













Examples for alkyl groups with 1 to 4 carbon atoms interrupted by one or two oxygen atoms are -CH₂-O-CH₃, -CH₂-CH₂-O-CH₃, -CH₂-CH₂-O-CH₂-CH₃, -CH₂-O-CH₂-CH₂-O-CH₃, or -CH₂-O-CH₂-O-CH₃.











Examples for hydroxy substituted alkyl groups with 2 to 6 carbon atoms are hydroxy ethyl, di-hydroxy ethyl, hydroxy propyl, di-hydroxy propyl, hydroxy butyl, hydroxy pentyl, or hydroxy hexyl.


5

Examples of especially suited compounds of component (b) formula (I) are selected from the group consisting of formulae A* to EE* and (III) to (IIIc)

(A*)		(B*)	
(C*)		(D*)	
(E*)		(F*)	
(G*)		(H*)	

(I*)		(J*)	
(K*)		(L*)	
(M*)		(O*)	
(P*)		(Q*)	
(R*)		(T*)	
(U*)		(V*)	

(W*)		(Y*)	
(Z*)		(AA*)	
(BB*)		(DD*)	
(EE*)		(III)	
(IIIa)		(IIIb)	



wherein

E is alkoxy of 1 to 18 carbon atoms, cycloalkoxy of 5 to 12 carbon atoms or aralkoxy of 7 to 15 carbon atoms, or E is -O-T-(OH)_b,

5 T is a straight or branched chain alkylene of 1 to 18 carbon atoms, cycloalkylene of 5 to 18 carbon atoms, cycloalkenylene of 5 to 18 carbon atoms, a straight or branched chain alkylene of 1 to 4 carbon atoms substituted by phenyl or by phenyl substituted by one or two alkyl groups of 1 to 4 carbon atoms;

b is 1, 2 or 3 with the proviso that b cannot exceed the number of carbon atoms in T, and
10 when b is 2 or 3, each hydroxyl group is attached to a different carbon atoms of T;

R is hydrogen or methyl; and

in formula (A*) n is 1 or 2,

when n is 1,

15 R₁ is hydrogen, alkyl of 1 to 18 carbon atoms, alkenyl of 2-18 carbon atoms, propargyl, glycidyl, alkyl of 2 to 50 carbon atoms interrupted by one to twenty oxygen atoms, said alkyl substituted by one to ten hydroxyl groups or both interrupted by said oxygen atoms and substituted by said hydroxyl groups, or

R₁ is alkyl of 1 to 4 carbon atoms substituted by a carboxy group or by -COOZ where Z is hydrogen, alkyl of 1 to 4 carbon atoms or phenyl, or where Z is said alkyl substituted by -
20 (COO⁻)_n Mⁿ⁺ where n is 1-3 and M is a metal ion from the 1st, 2nd or 3rd group of the periodic table or is Zn, Cu, Ni or Co, or M is a group Nⁿ⁺(R₂)₄ where R₂ is alkyl of 1 to 8 carbon atoms or benzyl,

when n is 2,

25 R₁ is alkylene of 1 to 12 carbon atoms, alkenylene of 4 to 12 carbon atoms, xylylene or alkylene of 1 to 50 carbon atoms interrupted by one to twenty oxygen atoms, substituted by one to ten hydroxyl groups or both interrupted by said oxygen atoms and substituted by said hydroxyl groups;

in formula (B*), m is 1 to 4, and

when m is 1,

R₂ is alkyl of 1 to 18 carbon atoms, alkyl of 3 to 18 carbon atoms interrupted by -COO-, alkyl of 3 to 18 carbon atoms substituted by COOH or COO-, or R₂ is -CH₂(OCH₂CH₂)_nOCH₃ where n is 1 to 12, or

5 R₂ is cycloalkyl of 5 to 12 carbon atoms, aryl of 6 to 12 carbon atoms, or said aryl substituted by one to four alkyl groups of 1 to 4 carbon atoms, or

R₂ is -NHR₃ where R₃ is alkyl of 1 to 18 carbon atoms, cycloalkyl of 5 to 12 carbon atoms, aryl of 6 to 12 carbon atoms, or said aryl substituted by one to four alkyl of 1 to 4 carbon atoms, or

10 R₂ is -N(R₃)₂ where R₃ is as defined above,

when m is 2,

R₂ is alkylene of 1 to 12 carbon atoms, alkenylene of 4 to 12 carbon atoms, xylylene, alkylene of 2 to 12 carbon atoms interrupted by -COO-, alkylene of 3 to 18 carbon atoms substituted by COOH or COO-, or R₂ is -CH₂(OCH₂CH₂)_nOCH₂- where n is 1 to 12, or

15 R₂ is cycloalkylene of 5 to 12 carbon atoms, aralkylene of 7 to 15 carbon atoms or arylene of 6 to 12 carbon atoms, or

R₂ is -NHR₄NH- where R₄ is alkylene of 2 to 18 carbon atoms, cycloalkylene of 5 to 12 carbon atoms, aralkylene of 8 to 15 carbon atoms or arylene of 6 to 12 carbon atoms, or

R₂ is -N(R₃)R₄N(R₃)- where R₃ and R₄ are as defined above, or

20 R₂ is -CO-, -NH-CO-NH-, or -N(R₃)-CO-N(R₃)-,

when m is 3,

R₂ is alkanetriyl of 3 to 8 carbon atoms or benzenetriyl, or

when m is 4,

R₂ is alkanetetrayl of 5 to 8 carbon atoms or benzenetetrayl,

25 in formula (C*),

R₁₀ is hydrogen, alkyl of 1 to 18 carbon atoms, cycloalkyl of 5 to 12 carbon atoms, aralkyl of 7 to 15 carbon atoms, alkanoyl of 2 to 18 carbon atoms, alkenoyl of 3 to 5 carbon atoms or benzoyl,

x is 1 or 2, and

30 when x is 1,

R₁₁ is hydrogen, alkyl of 1 to 18 carbon atoms, alkenyl of 2 to 18 carbon atoms, propargyl, glycidyl, alkyl of 2 to 50 carbon atoms interrupted by one to twenty oxygen atoms, said alkyl substituted by one to ten hydroxyl groups or both interrupted by said oxygen atoms and substituted by said hydroxyl groups, or

R₁₁ is alkyl of 1 to 4 carbon atoms substituted by a carboxy group or by -COOZ where Z is hydrogen, alkyl of 1 to 4 carbon atoms or phenyl, or where Z is said alkyl substituted by - (COO⁻)_nMⁿ⁺ where n is 1-3 and M is a metal ion from the 1st, 2nd or 3rd group of the periodic table or is Zn, Cu, Ni or Co, or M is a group Nⁿ⁺(R₂)₄ where R₂ is hydrogen, alkyl
5 of 1 to 8 carbon atoms or benzyl, or

when x is 2,

R₁₁ is alkylene of 1 to 12 carbon atoms, alkenylene of 4 to 12 carbon atoms, xylylene or alkylene of 1 to 50 carbon atoms interrupted by one to twenty oxygen atoms, substituted by one to ten hydroxyl groups or both interrupted by said oxygen atoms and substituted
10 by said hydroxyl groups,

in formula (D*), y is 1 to 4,

R₁₀ is as defined above,

and R₁₂ is defined as R₂ above,

in formula (E*), k is 1 or 2,

15 when k is 1,

R₂₀ and R₂₁ are independently alkyl of 1 to 12 carbon atoms, alkenyl of 2 to 12 carbon atoms or aralkyl of 7 to 15 carbon atoms, or R₂₀ is also hydrogen, or

R₂₀ and R₂₁ together are alkylene of 2 to 8 carbon atoms or said alkylene substituted by hydroxyl, or are acyloxy-alkylene of 4 to 22 carbon atoms, or

20 when k is 2,

R₂₀ and R₂₁ are together (-CH₂)₂C(CH₂-)₂,

in formula (F*),

R₃₀ is hydrogen, alkyl of 1 to 18 carbon atoms, benzyl, glycidyl, or alkoxyalkyl of 2 to 6 carbon atoms,

25 g is 1 or 2,

when g is 1, R₃₁ is defined as R₁ above when n is 1,

when g is 2, R₃₁ is defined as R₁ above when n is 2,

in formula (G*),

Q₁ is -NR₄₁- or -O-,

30 E₁ is alkylene of 1 to 3 carbon atoms, or E₁ is -CH₂-CH(R₄₂)-O- where R₄₂ is hydrogen, methyl or phenyl, or E₁ is -(CH₂)₃-NH- or E₁ is a direct bond,

R₄₀ is hydrogen or alkyl of 1 to 18 carbon atoms,

R₄₁ is hydrogen, alkyl of 1 to 18 carbon atoms, cycloalkyl of 5 to 12 carbon atoms, aralkyl of 7 to 15 carbon atoms, aryl of 6 to 10 carbon atoms, or R₄₁ is -CH₂-CH(R₄₂)-OH where R₄₂ is as defined above,

in formula (H*), p is 1 or 2,

5 T₄ is as defined for R₁₁ when x is 1 or 2,

M and Y are independently methylene or carbonyl, preferably M is methylene and Y is carbonyl,

in formula (I*),

this formula denotes a recurring structural unit of a polymer where T₁ is ethylene or 1,2-

10 propylene or is the repeating structural unit derived from an alpha-olefin copolymer with an alkyl acrylate or methacrylate, and where

q is 2 to 100,

Q₁ is -N(R₄₁)- or -O- where R₄₁ is as defined above,

in formula (J*),

15 r is 1 or 2,

T₇ is as defined for R₁ when n is 1 or 2 in formula (A*),

preferably T₇ is octamethylene when r is 2,

in formula (L*), u is 1 or 2,

T₁₃ is as defined for R₁ when n is 1 or 2 in formula (A*), with the proviso that T₁₃ is not

20 hydrogen when u is 1,

in formula (M*),

E₁ and E₂, being different, each are -CO- or -N(E₅)- where E₅ is hydrogen, alkyl of 1 to 12 carbon atoms or alkoxyalkyl of 4 to 22 carbon atoms, preferably E₁ is -CO- and E₂ is -N(E₅)-,

25 E₃ is hydrogen, alkyl of 1 to 30 carbon atoms, phenyl, naphthyl, said phenyl or said naphthyl substituted by chlorine or by alkyl of 1 to 4 carbon atoms, or phenylalkyl of 7 to 12 carbon atoms, or said phenylalkyl substituted by alkyl of 1 to 4 carbon atoms,

E₄ is hydrogen, alkyl of 1 to 30 carbon atoms, phenyl, naphthyl or phenylalkyl of 7 to 12 carbon atoms, or

30 E₃ and E₄ together are polymethylene of 4 to 17 carbon atoms, or said polymethylene substituted by one to four alkyl of 1 to 4 carbon atoms, preferably methyl,

in formula (O*),

R₁₀ is as defined for R₁₀ in formula (C*),

in formula (P*),

E_6 is an aliphatic or aromatic tetravalent radical, preferably neopentane-tetrayl or benzenetetrayl,

in formula (T*),

R_{51} is hydrogen, alkyl of 1 to 18 carbon atoms, cycloalkyl of 5 to 12 carbon atoms, or aryl of 5
6 to 10 carbon atoms,

R_{52} is hydrogen or alkyl of 1 to 18 carbon atoms, or

R_{51} and R_{52} together of alkylene of 4 to 8 carbon atoms,

f is 1 or 2,

when f is 1,

10 R_{50} is as defined for R_{11} in formula (C*) when x is 1, or R_{50} is $-(CH_2)_zCOOR_{54}$ where z is 1 to 4 and R_{54} is hydrogen or alkyl of 1 to 18 carbon atoms, or R_{54} is a metal ion from the 1st, 2nd or 3rd group of the periodic table or a group $-N(R_{55})_4$ where R_{55} is hydrogen, alkyl of 1 to 12 carbon atoms or benzyl,

when f is 2,

15 R_{50} is as defined for R_{11} in formula (C*) when x is 2, in formula (U*),

R_{53} , R_{54} , R_{55} and R_{56} are independently alkyl of 1 to 4 carbon atoms or are together pentamethylene,

in formula (V*),

20 R_{57} , R_{58} , R_{59} and R_{60} are independently alkyl of 1 to 4 carbon atoms or are together pentamethylene,

in formula (W*),

R_{61} , R_{62} , R_{63} and R_{64} are independently alkyl of 1 to 4 carbon atoms or are together pentamethylene,

25 R_{65} is alkyl of 1 to 5 carbon atoms,

M is hydrogen or oxygen,

wherein in formulas (Y*) to (BB*),

n is 2 to 3,

G_1 is hydrogen, methyl, ethyl, butyl or benzyl,

30 m is 1 to 4,

x is 1 to 4,

when x is 1, R_1 and R_2 are independently alkyl of 1 to 18 carbon atoms, said alkyl interrupted by one to five oxygen atoms, said alkyl substituted by 1 to 5 hydroxyl groups or said alkyl both interrupted by said oxygen atoms and substituted by said hydroxyl groups; cycloalkyl of

5 to 12 carbon atoms, aralkyl of 7 to 15 carbon atoms, aryl of 6 to 10 carbon atoms or said aryl substituted by one to three alkyl of 1 to 8 carbon atoms, or R₁ is also hydrogen, or R₁ and R₂ are together tetramethylene, pentamethylene, hexamethylene or 3-oxapentamethylene,

5 when x is 2,

R₁ is hydrogen, alkyl of 1 to 8 carbon atoms, said alkyl interrupted by one or two oxygen atoms, said alkyl substituted by a hydroxyl group, or said alkyl both interrupted by one or two oxygen atoms and substituted by a hydroxyl group,

10 R₂ is alkylene of 2 to 18 carbon atoms, said alkylene interrupted by one to five oxygen atoms, said alkylene substituted by 1 to 5 hydroxyl groups or said alkylene both interrupted by said oxygen atoms and substituted by said hydroxyl groups; o-, m- or p-phenylene or said phenylene substituted by one or two alkyl of 1 to 4 carbon atoms, or

R₂ is $-(\text{CH}_2)_k\text{O}[(\text{CH}_2)_k\text{O}]_h(\text{CH}_2)_k-$ where k is 2 to 4 and h is 1 to 40, or

R₁ and R₂ together with the two N atoms to which they are attached are piperazin-1,4-diyl,

15 when x is 3,

R₁ is hydrogen,

R₂ is alkylene of 4 to 8 carbon atoms interrupted by one nitrogen atom,

when x is 4,

R₁ is hydrogen,

20 R₂ is alkylene of 6 to 12 carbon atoms interrupted by two nitrogen atoms,

R₃ is hydrogen, alkyl of 1 to 8 carbon atoms, said alkyl interrupted by one or two oxygen atoms, said alkyl substituted by a hydroxyl group, or both interrupted by one or two oxygen atoms and substituted by a hydroxyl group,

p is 2 or 3,

25 in formula (DD*),

m is 2 or 3,

when m is 2,

G is $-(\text{CH}_2\text{CHR-O})_r\text{CH}_2\text{CHR}-$, where r is 0 to 3, and R is hydrogen or methyl, and

when m is 3, G is glyceryl,

30 in formula (EE*),

G₂ is -CN, -CONH₂ or -COOG₃ where G₃ is hydrogen, alkyl of 1 to 18 carbon atoms or phenyl,

in formulae (III) to (IIIc),

A₁₁ is OR₁₀₁ or NR₁₁₁R₁₁₂,

- R_{101} is alkenyl of 2 to 4 carbon atoms, propargyl, glycidyl, alkyl of 2 to 6 carbon atoms interrupted by one or two oxygen atoms, substituted by one to three hydroxyl groups or both interrupted by said oxygen atoms and substituted by said hydroxyl groups, or R_{101} is alkyl of 1 to 4 carbon atoms substituted by carboxy or by the alkali metal, ammonium or C₁-C₄alkylammonium salts thereof; or R_{101} is alkyl substituted by COO E_{10} where E_{10} is methyl or ethyl,
- R_{102} is alkyl of 3 to 5 carbon atoms interrupted by -COO- or by -CO-, or R_{102} is -CH₂(OCH₂CH₂)_cCOCH₃ where c is 1 to 4; or
- R_{102} is -NHR₁₀₃ where R_{103} is alkyl of 1 to 4 carbon atoms,
- 10 a is 2 to 4,
when a is 2,
 T_{11} is -(CH₂CHR₁₀₀-O)_dCH₂CHR₁₀₀-, where d is 0 or 1, and R_{100} is hydrogen or methyl,
when a is 3, T_{11} is glyceryl,
when a is 4, T_{11} is neopentetetrayl,
- 15 b is 2 or 3,
when b is 2,
 G_{11} is -(CH₂CHR₁₀₀-O)_dCH₂CHR₁₀₀-, where d is 0 or 1, and R_{100} is hydrogen or methyl, and
when b is 3, G_{11} is glyceryl;
- R_{111} is hydrogen, unsubstituted alkyl of 1 to 4 carbon atoms, alkyl of 1 to 4 carbon atoms substituted by one or two hydroxyl, alkyl of 1 to 4 carbon atoms interrupted by one or two oxygen atoms, or both substituted by one hydroxyl and interrupted by one or two oxygen atoms,
- 20 R_{112} is -CO- R_{113} where R_{113} has the same meaning as R_{111} , or R_{113} is NHR₁₁₄, wherein R_{114} is unsubstituted alkyl of 1 to 4 carbon atoms, alkyl of 1 to 4 carbon atoms substituted by one or two hydroxyl, alkyl of 1 to 4 carbon atoms substituted by alkoxy of 1 to 2 carbon atoms, or both substituted by one hydroxyl and by alkoxy of 1 to 2 carbon atoms, or
- 25 R_{111} and R_{112} together are -CO-CH₂CH₂-CO-, or (CH₂)₆CO-;
- HY is an inorganic or organic acid; wherein the total charge of cations is equal to the total charge of anions; and
- 30 Y is phosphate, phosphonate, carbonate, bicarbonate, nitrate, chloride, bromide, bisulfite, sulfite, bisulfate, sulfate, borate, formate, acetate, benzoate, citrate, oxalate, tartrate, acrylate, polyacrylate, fumarate, maleate, itaconate, glycolate, gluconate, malate, mandelate, tiglate, ascorbate, polymethacrylate, a carboxylate of nitrilotriacetic acid, a carboxylate of hydroxyethylethylenediaminetriacetic acid, a carboxylate of ethylene-

diaminetetraacetic acid, a carboxylate of diethylenetriaminepentaacetic acid, a carboxylate of diethylenediaminetetraacetic acid, a carboxylate of diethylenetriaminepentaacetic acid, alkylsulfonate, arylsulfonate, or alkyl-substituted arylsulfonate.

- 5 Another embodiment of the instant invention is the compounds of component (b) formula (I) selected from the group consisting of (A*), (B*), (C*), (D*), (Q*), (R*), (Y*), and (Z*), wherein
- E is alkoxy of 1 to 10 carbon atoms, cycloalkoxy of 5 to 8 carbon atoms or aralkoxy of 7 to 12 carbon atoms, or E is -O-T-(OH)_b,
- 10 T is a straight or branched chain alkylene of 1 to 10 carbon atoms, cycloalkylene of 5 to 10 carbon atoms, cycloalkenylene of 5 to 10 carbon atoms, a straight or branched chain alkylene of 1 to 4 carbon atoms substituted by phenyl or by phenyl substituted by one or two alkyl groups of 1 to 4 carbon atoms;
- b is 1, 2 or 3 with the proviso that b cannot exceed the number of carbon atoms in T, and
- 15 when b is 2 or 3, each hydroxyl group is attached to a different carbon atoms of T;
- R is hydrogen;
- in formula (A*), n is 1 or 2,
- when n is 1,
- R₁ is hydrogen, alkyl of 1 to 6 carbon atoms, alkenyl of 2-6 carbon atoms, propargyl,
- 20 glycidyl, alkyl of 2 to 20 carbon atoms interrupted by one to ten oxygen atoms, said alkyl substituted by one to five hydroxyl groups or both interrupted by said oxygen atoms and substituted by said hydroxyl groups, or
- R₁ is alkyl of 1 to 4 carbon atoms substituted by a carboxy group or by -COOZ where Z is hydrogen or alkyl of 1 to 4 carbon atoms,
- 25 when n is 2,
- R₁ is alkylene of 1 to 8 carbon atoms, alkenylene of 4 to 8 carbon atoms, alkylene of 1 to 20 carbon atoms interrupted by one to ten oxygen atoms, substituted by one to five hydroxyl groups or both interrupted by said oxygen atoms and substituted by said hydroxyl groups,
- 30 in formula (B*), m is 1 or 2,
- when m is 1,
- R₂ is alkyl of 1 to 4 carbon atoms or R₂ is CH₂(OCH₂CH₂)_nOCH₃ where n is 1 to 12, or
- R₂ is phenyl, or said phenyl substituted by one to three methyl groups, or

R_2 is $-NHR_3$ where R_3 is alkyl of 1 to 4 carbon atoms or phenyl, or said phenyl substituted by one or two methyl groups,

when m is 2,

R_2 is alkylene of 1 to 8 carbon atoms, alkenylene of 4 to 8 carbon atoms, or R_2 is -

5 $CH_2(OCH_2CH_2)_nOCH_2-$ where n is 1 to 12, or

R_2 is $-NHR_4NH-$ where R_4 is of 2 to 6 carbon atoms, aralkylene of 8 to 15 carbon atoms or arylene of 6 to 12 carbon atoms, or

R_2 is $-CO-$ or $-NHCONH-$,

in formula (C*),

10 R_{10} is hydrogen or, alkanoyl of 1 to 3 carbon atoms,

x is 1 or 2,

when x is 1,

R_{11} is hydrogen, alkyl of 1 to 6 carbon atoms or glycidyl, or

R_{11} is alkyl of 1 to 4 carbon atoms substituted by a carboxy group or by $COOZ$ where Z is

15 hydrogen or alkyl of 1 to 4 carbon atoms,

when x is 2,

R_{11} is alkylene of 1 to 6 carbon atoms,

in formula (D*),

R_{10} is hydrogen,

20 y is 1 or 2,

R_{12} is defined as R_2 above,

in formula (Y*) and (Z*),

x is 1 or 2,

when x is 1,

25 R_1 and R_2 are independently alkyl of 1 to 4 carbon atoms or R_1 and R_2 are together tetramethylene, or pentamethylene,

R_2 is hydrogen or alkyl of 1 to 4 carbon atoms, said alkyl group substituted by a hydroxyl group,

when x is 2,

30 R_1 is hydrogen, alkyl of 1 to 4 carbon atoms, said alkyl substituted by a hydroxyl group,

R_2 is alkylene of 2 to 6 carbon atoms,

R_3 is as defined above,

HY is an inorganic or organic acid; wherein the total charge of cations is equal to the total charge of anions; and

Y is phosphate, phosphonate, carbonate, bicarbonate, chloride, bromide, bisulfate, sulfate, borate, formate, acetate, benzoate, citrate, oxalate, tartrate, acrylate, fumarate, maleate, itaconate, glycolate, gluconate, malate, mandelate, tiglate, ascorbate, a carboxylate of nitrilotriacetic acid, a carboxylate of hydroxyethylethylenediaminetriacetic acid, a carboxylate of ethylenediaminetetraacetic acid, a carboxylate of diethylenetriaminepentaacetic acid, a carboxylate of diethylenediaminetetraacetic acid, a carboxylate of diethylenetriaminepentaacetic acid, alkylsulfonate, arylsulfonate, or alkyl-substituted arylsulfonate.

Still another embodiment of the instant invention is the compounds of component (b) formula (I) selected from the group consisting of (A*), (B*), (C*), (D*), (Q*), and (R*), wherein

E is alkoxy of 1 to 10 carbon atoms, cycloalkoxy of 5 to 8 carbon atoms or aralkoxy of 7 to 12 carbon atoms, or E is -O-T-(OH)_b,

T is a straight or branched chain alkylene of 1 to 10 carbon atoms, cycloalkylene of 5 to 10 carbon atoms, cycloalkenylene of 5 to 10 carbon atoms, a straight or branched chain alkylene of 1 to 4 carbon atoms substituted by phenyl or by phenyl substituted by one or two alkyl groups of 1 to 4 carbon atoms;

b is 1, 2 or 3 with the proviso that b cannot exceed the number of carbon atoms in T, and when b is 2 or 3, each hydroxyl group is attached to a different carbon atoms of T;

R is hydrogen, in formula (A*),

n is 1,

R₁ is hydrogen, alkyl of 1 to 4 carbon atoms, glycidyl, alkyl of 2 to 4 carbon atoms interrupted by one or two oxygen atoms, said alkyl substituted by one or two hydroxyl groups or both interrupted by said oxygen atoms and substituted by said hydroxyl groups, or

R₁ is alkyl of 1 to 4 carbon atoms substituted by -COOZ where Z is hydrogen or alkyl of 1 to 4 carbon atoms,

in formula (B*),

m is 1 or 2,

R₂ is alkyl of 1 to 4 carbon atoms or R₂ is CH₂(OCH₂CH₂)_nOCH₃ where n is 1 to 4,

when m is 2,

R₂ is alkylene of 1 to 8 carbon atoms,

in formula (C*),

5 R₁₀ is hydrogen or alkanoyl of 1 or 2 carbon atoms,

x is 1 or 2,

when x is 1,

R₁₁ is hydrogen, alkyl of 1 to 4 carbon atoms or glycidyl,

R₁₁ is alkyl of 1 to 4 carbon atoms substituted by COOZ where Z is hydrogen or alkyl of 1 to

10 4 carbon atoms,

when x is 2,

R₁₁ is alkylene of 1 to 6 carbon atoms,

in formula (D*),

R₁₀ is hydrogen,

15 y is 1 or 2,

R₁₂ is defined as R₂ above;

HY is an inorganic or organic acid; wherein the total charge of cations is equal to the total charge of anions; and

Y is phosphate, phosphonate, carbonate, bicarbonate, chloride, bromide, bisulfate, sulfate,

20 borate, formate, acetate, benzoate, citrate, oxalate, tartrate, ascorbate, acrylate,

fumarate, maleate, itaconate, glycolate, gluconate, malate, mandelate, tigate, a carboxylate of nitrilotriacetic acid, a carboxylate of hydroxyethylethylenediaminetriacetic acid, a carboxylate of ethylenediaminetetraacetic acid, a carboxylate of diethylene-

triaminepentaacetic acid, a carboxylate of diethylenediaminetetraacetic acid, a

25 carboxylate of diethylenetriaminepentaacetic acid, alkylsulfonate, arylsulfonate, or alkyl-substituted arylsulfonate.

Yet another embodiment of the instant invention is a compound of component (b) formula (I) selected from the group consisting of

30 (a) bis(1-octyloxy-2,2,6,6-tetramethylpiperidin-4-yl) sebacate hydrochloride;

(b) 1-methoxy-2,2,6,6-tetramethyl-4-acetoxypiperidinium citrate;

(c) 1-methoxy-2,2,6,6-tetramethyl-4-acetamidopiperidinium phosphate;

(d) 1-butoxy-2,2,6,6-tetramethyl-4-acetamidopiperidinium bisulfate;

(e) 1-methoxy-2,2,6,6-tetramethyl-4-oxo-piperidinium methyl sulfonate;

- (f) 1-methoxy -2,2,6,6-tetramethyl-4-oxo-piperidinium acetate;
- (g) 1-phenoxy-2,2,6,6-tetramethyl-4-methoxy-piperidinium tartrate;
- (h) 1-benzoxy-2,2,6,6-tetramethyl-4-methoxy-piperidinium acetate;
- (i) 1-ethoxy-2,2,6,6-tetramethyl-4-acetoxypiperidinium maleate;
- 5 (j) 1-methoxy-2,2,6,6-tetramethyl-4-propoxy-piperidinium mandelate;
- (k) 1-methoxy-2,2,6,6-tetramethyl-4-propoxy-piperidinium oxalate;
- (l) 1-methoxy-2,2,6,6-tetramethyl-4-(2-hydroxy-4-oxapentoxy)piperidinium bicarbonate;
- (m) 1-methoxy-2,2,6,6-tetramethyl-4-(2-hydroxy-4-oxapentoxy)piperidinium glycolate;
- (n) 1-methoxy-2,2,6,6-tetramethyl-4-hydroxypiperidinium gluconate;
- 10 (o) 1-methoxy-2,2,6,6-tetramethyl-4-hydroxypiperidinium ascorbate;
- (p) 1-methoxy-2,2,6,6-tetramethyl-4-hydroxypiperidinium benzene sulfonate;
- (q) 1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium ascorbate;
- (r) 1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium citrate;
- (s) bis(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium) citrate;
- 15 (t) tris(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium) citrate;
- (u) tetra(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium) ethylenediaminetetraacetate;
- (v) tetra(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-acetamidopiperidinium) ethylenediaminetetraacetate;
- 20 (w) tetra(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-oxopiperidinium) ethylenediaminetetraacetate;
- (x) penta(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium) diethylenetriaminepentaacetate;
- (y) penta(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-acetamidopiperidinium) diethylenetriaminepentaacetate;
- 25 (z) penta(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-oxopiperidinium) diethylenetriaminepentaacetate;
- (aa) tri(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium) nitrilotriacetate;
- 30 (bb) tri(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-acetamidopiperidinium) nitrilotriacetate;
- (cc) tri(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-oxopiperidinium) nitrilotriacetate;

- 20 -

- (dd) penta(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium) diethylenetriaminepentamethylenephosphonate;
- (ee) penta(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-acetamidopiperidinium) diethylenetriaminepentamethylenephosphonate; and,
- 5 (ff) penta(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-oxopiperidinium) diethylenetriaminepentamethylenephosphonate.

Another embodiment of the instant invention is a compound of component (b) formula (I) selected from the group consisting of

10

- (a) bis(1-octyloxy-2,2,6,6-tetramethylpiperidin-4-yl) sebacate hydrochloride;
- (b) 1-methoxy-2,2,6,6-tetramethyl-4-acetoxypiperidinium citrate;
- (c) 1-butoxy-2,2,6,6-tetramethyl-4-acetamidopiperidinium bisulfate;
- (d) 1-methoxy-2,2,6,6-tetramethyl-4-oxo-piperidinium methyl sulfonate;
- 15 (e) 1-methoxy -2,2,6,6-tetramethyl-4-oxo-piperidinium acetate;
- (f) 1-ethoxy-2,2,6,6-tetramethyl-4-acetoxypiperidinium maleate;
- (g) 1-methoxy-2,2,6,6-tetramethyl-4-propoxy-piperidinium oxalate;
- (h) 1-methoxy-2,2,6,6-tetramethyl-4-(2-hydroxy-4-oxapentoxy)piperidinium glycolate;
- (i) 1-methoxy-2,2,6,6-tetramethyl-4-hydroxypiperidinium ascorbate;
- 20 (j) 1-methoxy-2,2,6,6-tetramethyl-4-hydroxypiperidinium benzene sulfonate;
- (k) 1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium ascorbate;
- (l) 1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium citrate;
- (m) bis(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium) citrate;
- (n) tris(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium) citrate;
- 25 (o) tetra(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium) ethylenediaminetetraacetate;
- (p) tetra(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-acetamidopiperidinium) ethylenediaminetetraacetate;
- (q) penta(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium) diethylenetriaminepentaacetate;
- 30 (r) tri(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium) nitrilotriacetate;
- (s) penta(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium) diethylenetriaminepentamethylenephosphonate; and,

- 21 -

- (t) penta(1-(2-hydroxy-2-methylpropoxy)-2,2,6,6-tetramethyl-4-acetamidopiperidinium) diethylenetriaminepentamethylenephosphonate.

The compounds of component (b) formula (I) can be prepared according to methods known
5 in the art or in analogy to those methods. For example, these compounds may be prepared according to US 6,392,041; US 6,586,507; US 6,166,212; US 5,374,729; US 5,015,683; US 5,021,483; US 4,921,962; US 5,112,890; and, 5,204,473, incorporated herein by reference.

10 The present compositions may comprise further traditional additives, for example ultraviolet (UV) light absorbers and antioxidants.

The present invention pertains to a stabilized composition comprising

- (a) a body care product, household product, textile or fabric,
15 (b) an effective stabilizing amount of one or more compounds of formula (I), and
(c) one or more compounds selected from the group consisting of the ultraviolet light absorbers, antioxidants, tocopherol, tocopherol acetate, hindered amine light stabilizers, complex formers, optical brighteners, surfactants, and polyorganosiloxanes.

20 The additional additives of present component (c) are for example those disclosed in co-pending U.S. application Nos. 09/830,788, filed May 1, 2001 and 09/830,787, filed May 1, 2001, published as WO 00/25730 and WO 00/25731. The disclosures of these co-pending applications are hereby incorporated by reference.

25 The UV absorbers are for example selected from group consisting of the 2H-benzotriazoles, the s-triazines, the benzophenones, the alpha-cyanoacrylates, the oxanilides, the benzoxazinones, the benzoates and the alpha-alkyl cinnamates.

The UV absorbers are for example
30 2,4,6-tris(2-hydroxy-4-octyloxyphenyl)-1,3,5-triazine; 2-(2,4-dihydroxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine; 2,4-bis(2-hydroxy-4-propyloxyphenyl)-6-(2,4-dimethylphenyl)-1,3,5-triazine; 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(4-methylphenyl)-1,3,5-triazine; 2-(2-hydroxy-4-dodecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine; 2-[2-hydroxy-4-(2--hydroxy-3-butyloxypropyloxy)phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine; 2-[2-hydroxy-
35 4-(2-hydroxy-3-octyloxypropyloxy)phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine; 2-[2-



hydroxy-4-(2-hydroxy-3-tridecyloxy-propyloxy)phenyl]-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine; 5-chloro-2-(2-hydroxy-3,5-di-tert-butylphenyl)-2H-benzotriazole; 2-(2-hydroxy-3-dodecyl-5-methylphenyl)-2H-benzotriazole; 5-chloro-2-(2-hydroxy-3-tert-butyl-5-methylphenyl)-2H-benzotriazole; bis-(3-(2H-benzotriazol-2-yl)-2-hydroxy-5-tert-octyl)methane; 2-(2-hydroxy-3,5-di-tert-butylphenyl)-2H-benzotriazole; 2-(2-hydroxy-3,5-di-tert-amylphenyl)-2H-benzotriazole; 2-(2-hydroxy-3,5-di-alpha-cumylphenyl)-2H-benzotriazole; 2-(2-hydroxy-3-alpha-cumyl-5-tert-octylphenyl)-2H-benzotriazole; 2-(2-hydroxy-5-tert-octylphenyl)-2H-benzotriazole; 3-(2H-benzotriazol-2-yl)-4-hydroxy-5-(1-methylpropyl)-benzenesulfonic acid monosodium salt; 3-tert-butyl-4-hydroxy-5-(2H-benzotriazol-2-yl)-hydrocinnamic acid and sodium salt; 12-hydroxy-3,6,9-trioxadodecyl 3-tert-butyl-4-hydroxy-5-(2H-benzotriazol-2-yl)-hydrocinnamate; octyl 3-tert-butyl-4-hydroxy-5-(2H-benzotriazol-2-yl)-hydrocinnamate; 4,6-bis(2,4-dimethylphenyl)-2-(4-(3-dodecyloxy*-2-hydroxypropoxy)-2-hydroxyphenyl)-s-triazine (*is mixture of C₁₂₋₁₄oxy isomers); 4,6-bis(2,4-dimethylphenyl)-2-(4-octyloxy-2-hydroxyphenyl)-s-triazine; 2,4-dihydroxybenzophenone; 2,2'-dihydroxy-4,4'-dimethoxy-5,5'-disulfobenzophenone, disodium salt; 2-hydroxy-4-octyloxybenzophenone; 2-hydroxy-4-dodecyloxybenzophenone; 2,4-dihydroxybenzophenone; 2,2',4,4'-tetrahydroxy-benzophenone; 4-amino-benzoic acid; 2,3-dihydroxypropyl-4-aminobenzoic acid; 3-(4-imidazolyl)acrylic acid; 2-phenyl-5-benzimidazole sulfonic acid; N,N,N-trimethyl-alpha-(2-oxo-3-bornylidene)-p-toluidinium methyl sulfate; 5-benzoyl-4-hydroxy-2-methoxybenzenesulfonic acid, sodium salt; 3-(4-benzoyl-3-hydroxyphenoxy)-2-hydroxy-N,N,N-trimethyl-1-propanaminium chloride; 3-[4-(2H-benzotriazol-2-yl)-3-hydroxyphenoxy]-2-hydroxy-N,N,N-trimethyl-1-propanaminium, chloride; 2-(2-hydroxy-5-methylphenyl)-2H-benzotriazole; or 2,2'-dihydroxy-4,4'-dimethoxy-benzophenone (Uvinul® 3049).

25 For instance, suitable UV absorbers are selected from 3-(2H-benzotriazol-2-yl)-4-hydroxy-5-(1-methylpropyl)-benzenesulfonic acid monosodium salt; 3-tert-butyl-4-hydroxy-5-(2H-benzotriazol-2-yl)-hydrocinnamic acid and sodium salt; 2-(2-hydroxy-3,5-di-tert-butylphenyl)-2H-benzotriazole; 2-(2-hydroxy-3,5-di-tert-amylphenyl)-2H-benzotriazole; 4,6-bis(2,4-dimethylphenyl)-2-(4-(3-dodecyloxy*-2-hydroxypropoxy)-2-hydroxyphenyl)-s-triazine (*is mixture of C₁₂₋₁₄oxy isomers); 12-hydroxy-3,6,9-trioxadodecyl 3-tert-butyl-4-hydroxy-5-(2H-benzotriazol-2-yl)-hydrocinnamate; 2,4-dihydroxybenzophenone; 2,2'-dihydroxy-4,4'-dimethoxy-5,5'-disulfobenzophenone, disodium salt; 2,2',4,4'-tetrahydroxybenzophenone; 3-(4-benzoyl-3-hydroxyphenoxy)-2-hydroxy-N,N,N-trimethyl-1-propanaminium chloride; 3-[4-(2H-benzotriazol-2-yl)-3-hydroxyphenoxy]-2-hydroxy-N,N,N-trimethyl-1-propanaminium, chloride; 5-



benzoyl-4-hydroxy-2-methoxy-benzenesulfonic acid, sodium salt; or 2-(2-hydroxy-3-alpha-cumyl-5-tert-octylphenyl)-2H-benzotriazole.



Additional suitable antioxidants are for example selected from the hindered phenolic and
5 benzofuranone stabilizers.

Suitable antioxidants are for example selected from the group consisting of









10





5






The hindered amine light stabilizers (HALS) of component (c) are for example known commercial compounds. They are for example selected from the group consisting of


10

bis(2,2,6,6-tetramethylpiperidin-4-yl)sebacate, bis(2,2,6,6-tetramethylpiperidin-4-yl)succinate, bis(1,2,2,6,6-pentamethylpiperidin-4-yl)sebacate, n-butyl-3,5-di-tert-butyl-4-hydroxybenzyl-malonic acid-bis(1,2,2,6,6-pentamethylpiperidyl)ester, the condensate of 1-hydroxyethyl-2,2,6,6-tetramethyl-4-hydroxypiperidine and succinic acid, the condensate of N,N'-


15 bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-tert-octylamino-2,6-dichloro-1,3,5-s-triazine, tris(2,2,6,6-tetramethyl-4-piperidyl)nitrilotriacetate, tetrakis(2,2,6,6-tetramethyl-4-piperidyl)-1,2,3,4-butanetetraoate, 1,1'-(1,2-ethanediyl)-bis(3,3,5,5-

tetramethylpiperazinone), 4-benzoyl-2,2,6,6-tetramethylpiperidine, 4-stearyloxy-2,2,6,6-tetramethylpiperidine, bis(1,2,2,6,6-pentamethylpiperidyl)-2-n-butyl-2-(2-hydroxy-3,5-di-tert-butylbenzyl)malonate, 3-n-octyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decane-2,4-dione, the condensate of N,N-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-morpholino-2,6-dichloro-1,3,5-triazine, the condensate of 2-chloro-4,6-di(4-n-butylamino-2,2,6,6-tetramethylpiperidyl)-1,3,5-triazine and 1,2-bis(3-aminopropylamino)ethane, the condensate of 2-chloro-4,6-di(4-n-butylamino-1,2,2,6,6-pentamethylpiperidyl)-1,3,5-triazine and 1,2-bis(3-aminopropylamino)ethane, 8-acetyl-3-dodecyl-7,7,9,9-tetramethyl-1,3,8-triazaspiro[4.5]decane-2,4-dione, 3-dodecyl-1-(2,2,6,6-tetramethyl-4-piperidyl)pyrrolidin-2,5-dione, 3-dodecyl-1-(1,2,2,6,6-pentamethyl-4-piperidyl)-pyrrolidine-2,5-dione, a mixture of 4-hexadecyloxy- and 4-stearyloxy-2,2,6,6-tetramethylpiperidine, the condensate of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-cyclohexylamino-2,6-dichloro-1,3,5-triazine, the condensate of 1,2-bis(3-aminopropylamino)ethane and 2,4,6-trichloro-1,3,5-triazine and 4-butylamino-2,2,6,6-tetramethylpiperidine (CAS reg. No. [136504-96-6]); (2,2,6,6-tetramethyl-4-piperidyl)-n-dodecylsuccinimide, (1,2,2,6,6-pentamethyl-4-piperidyl)-n-dodecylsuccinimide, 2-undecyl-7,7,9,9-tetramethyl-1-oxa-3,8-diaza-4-oxo-spiro[4,5]decane, the reaction product of 7,7,9,9-tetramethyl-2-cycloundecyl-1-oxa-3,8-diaza-4-oxospiro[4,5]decane and epichlorohydrin, tetra(2,2,6,6-tetramethylpiperidin-4-yl)-butane-1,2,3,4-tetracarboxylate, tetra(1,2,2,6,6-pentamethylpiperidin-4-yl)-butane-1,2,3,4-tetracarboxylate, 2,2,4,4-tetramethyl-7-oxa-3,20-diaza-21-oxo-dispiro[5.1.11.2] - heneicosan, 8-acetyl-3-dodecyl-1,3,8-triaza-7,7,9,9-tetramethylspiro[4,5] -decane-2,4-dione,





and



where R = H or CH₃





5

The complex formers of component (c) are for example nitrogen-containing complex formers or polyanionically-derived natural polysaccharides, for example those containing phosphate, phosphonate or methylphosphonate groups, such as chitin derivatives, e.g. sulfochitin, carboxymethylchitin, phosphochitin or chitosan derivatives, for example sulfochitosan,

10

carboxymethylchitosan or phosphochitosan.

The complex formers are for example selected from the group consisting of ethylenediamine-tetracetic acid (EDTA), nitrilotriacetic acid (NTA), beta-alaninediacetic acid (EDET) or ethylenediaminedisuccinic acid (EDDS),



The present stabilizer systems are particularly suitable for stabilizing body care products, in particular for use in skin-care products, as bath and shower products, preparations containing fragrances and odoriferous substances, hair-care products, dentifrices, deodorizing and antiperspirant preparations, decorative preparations, light protection formulations and preparations containing active ingredients.

Suitable skin-care products are, in particular, body oils, body lotions, body gels, treatment creams, skin protection ointments, shaving preparations, such as shaving foams or gels, skin powders, such as baby powder, moisturising gels, moisturising sprays, revitalising body sprays, cellulite gels and peeling preparations.

Preparations containing fragrances and odoriferous substances are in particular scents, perfumes, toilet waters and shaving lotions (aftershave preparations).

Suitable hair-care products are, for example, shampoos for humans and animals, in particular dogs, hair conditioners, products for styling and treating hair, perming agents, hair sprays and lacquers, hair gels, hair fixatives and hair dyeing or bleaching agents.

- 5 Suitable dentifrices are in particular tooth creams, toothpastes, mouth-washes, mouth rinses, anti-plaque preparations and cleaning agents for dentures.

Suitable decorative preparations are in particular lipsticks, nail varnishes, eye shadows, mascaras, dry and moist make-up, rouge, powders, depilatory agents and suntan lotions.

10

Suitable cosmetic formulations containing active ingredients are in particular hormone preparations, vitamin preparations, vegetable extract preparations and antibacterial preparations.

- 15 The present body care products can be in the form of creams, ointments, pastes, foams, gels, lotions, powders, make-ups, sprays, sticks or aerosols. The present stabilizer systems may be present in the oil phase or in the aqueous or aqueous/alcoholic phase.

The additives of component (b) are present, for example, in the body care and household products in a concentration of about 5 to about 10000 ppm, based on the total formulation by weight, for example from about 10 to about 5000 ppm, for example from about 100 to about 5000 ppm. For example the additives of component (b) are present in the body care and household products in a concentration of about 5, 10, 15, 20, 25, 35, 40, 45 or 50 ppm, based on the total formulation by weight. For example, the additives of component (b) are present from about 5 to about 5000 ppm in the formulations (compositions) of this invention.

Laundry detergents, fabric softeners or other products, from which the additives of component (b) are intended for deposition onto fabrics with use, are considered household products of this invention, and the above concentration levels also pertain thereto. The present additives of component (b) are effective at stabilizing the laundry detergents and fabric softeners, as well as the fabrics treated therewith.

30 Creams are oil-in-water emulsions containing more than 50% water. The oil-containing base used therein is usually mainly fatty alcohols, for example lauryl, cetyl or stearyl alcohol, fatty

acids, for example palmitic or stearic acid, liquid to solid waxes, for example isopropylmyristate or beeswax and/or hydrocarbon compounds, such as paraffin oil. Suitable emulsifiers are surfactants having primarily hydrophilic properties, such as the corresponding non-ionic emulsifiers, for example fatty acid esters of polyalcohols or ethylene oxide adducts, such as polyglycerol fatty acid ester or polyoxyethylenesorbitan fatty acid ether (Tween trademarks); polyoxyethylene fatty alcohol ether or their esters or the corresponding ionic emulsifiers, such as the alkali metal salts of fatty alcohol sulfonates, sodium cetyl sulfate or sodium stearyl sulfate, which are usually used together with fatty alcohols, such as cetyl alcohol or stearyl alcohol. In addition, creams contain agents which reduce water loss during evaporation, for example polyalcohols, such as glycerol, sorbitol, propylene glycol, and/or polyethylene glycols.

Ointments are water-in-oil emulsions which contain up to 70%, for instance not more than 20 to 50%, of water or of an aqueous phase. The oil-containing phase contains predominantly hydrocarbons, such as paraffin oil and/or solid paraffin which for instance contains hydroxy compounds, for example fatty alcohol or their esters, such as cetyl alcohol or wool wax for improving the water absorption. Emulsifiers are corresponding lipophilic substances, such as sorbitan fatty acid ester. In addition, the ointments contain moisturisers such as polyalcohols, for example glycerol, propylene glycol, sorbitol and/or polyethylene glycol as well as preservatives.

Rich creams are anhydrous formulations and are produced on the basis of hydrocarbon compounds, such as paraffin, natural or partially synthetic fats, for example coconut fatty acid triglycerides or, for instance, hardened oils and glycerol partial fatty acid esters.

Pastes are creams and ointments containing powdered ingredients which absorb secretions, for example metal oxides, such as titanium dioxide or zinc oxide, and also tallow and/or aluminium silicates which bind the moisture or the absorbed secretion.

Foams are liquid oil-in-water emulsions in aerosol form. Hydrocarbon compounds are used, inter alia, for the oil-containing phase, for example paraffin oil, fatty alcohols, such as cetyl alcohol, fatty acid esters, such as isopropylmyristate and/or waxes. Suitable emulsifiers are, inter alia, mixtures of emulsifiers having predominantly hydrophilic properties, for example polyoxyethylenesorbitan fatty acid ester, and also emulsifiers having predominantly lipophilic

properties, for example sorbitan fatty acid ester. Commercially available additives are usually additionally employed, for example preservatives.

Gels are, in particular, aqueous solutions or suspensions of active substances in which gel
 5 formers are dispersed or swelled, in particular cellulose ethers, such as methyl cellulose, hydroxyethyl cellulose, carboxymethyl cellulose or vegetable hydrocolloids, for example so-
 dium alginate, tragacanth or gum Arabic and polyacrylate thickener systems. The gels for
 example additionally contain polyalcohols, such as propylene glycol or glycerol as
 moisturisers and wetting agents, such as polyoxyethylenesorbitan fatty acid ester. The gels
 10 furthermore contain commercially available preservatives, such as benzyl alcohol, phenethyl alcohol, phenoxyethanol and the like.

The following is a list of examples of body care products of this invention and their ingredients:

15

<u>Body care product</u>	<u>Ingredients</u>
moisturising cream	vegetable oil, emulsifier, thickener, perfume, water, anti-oxidant, UV absorbers
shampoo	surfactant, emulsifier, preservatives, perfume, antioxidant, UV absorbers
toothpaste	cleaning agent, thickener, sweetener, flavor, colorant, anti-oxidant, water, UV absorbers
lip-care stick	vegetable oil, wax, TiO ₂ , antioxidant, UV absorbers

The present body care products, household products, textiles and fabrics have high stability
 towards color changes and chemical degradation of the ingredients present in these
 products. For example, present compositions that comprise a dye are found to have
 20 excellent color stability.

Accordingly, the present invention further pertains to a stabilized composition comprising

- (a) a body care product, household product, textile or fabric,
 - (b) an effective stabilizing amount of one or more compounds of formula (I), and
 - (d) a dye.
- 25

Dyes according to the present invention are for example:

- inorganic pigments, for example iron oxide (Iron Oxide Red, Iron Oxide Yellow, Iron Oxide Black, etc.), Ultramarines, Chromium Oxide Green or Carbon Black;
- natural or synthetic organic pigments;
- disperse dyes which may be solubilized in solvents like direct hair dyes of the HC type, for
5 example HC Red No. 3, HC Blue No. 2 and all other hair dyes listed in International
Cosmetic Ingredient Dictionary and Handbook, 7th edition 19997) or the dispersion dyes
listed in Color Index International or Society of Dyers and Colourists;
- color varnishes (insoluble salts of soluble dyes, like many Ca-, Ba- or Al-salts of anionic
dyes);
- 10 - soluble anionic or cationic dyes, like acid dyes (anionic), basic dyes (cationic), direct dyes,
reactive dyes or solvent dyes.

Generally, for the coloration of household- and body care products all substances are
suitable which have an absorption in the visible light of electromagnetic radiation (wavelength
15 of ca. 4000 to 700 nm). The absorption is often caused by the following chromophores:
Azo- (mono-, di, tris-, or poly-)stilbene-, carotenoide-, diarylmethan-, triarylmethan-, xanthen-,
acridin-, quinoline, methin- (also polymethin-), thiazol-, indamin-, indophenol-, azin-, oxazin,
thiazin-, anthraquinone-, indigoid-, phtalocyanine- and further synthetic, natural and/or
inorganic chromophores.

20

The present stabilizer systems are also used in household cleaning and treatment agents, for
example in laundry products and fabric softeners, liquid cleansing and scouring agents, glass
detergents, neutral cleaners (all-purpose cleaners), acid household cleaners (bath),
bathroom cleaners, for instance in washing, rinsing and dishwashing agents, kitchen and
25 oven cleaners, clear rinsing agents, dishwasher detergents, shoe polishes, polishing waxes,
floor detergents and polishes, metal, glass and ceramic cleaners, textile-care products, rug
cleaners and carpet shampoos, agents for removing rust, color and stains (stain remover
salt), furniture and multipurpose polishes and leather and vinyl dressing agents (leather and
vinyl sprays) and solid and liquid air fresheners.

30

The present invention also concerns home care and fabric care products such as drain
cleaners, disinfectant solutions, upholstery cleaners, automotive care products (e.g., to clean
and/or polish and protect paint, tires, chrome, vinyl, leather, fabric, rubber, plastic and fabric),
degreasers, polishes (glass, wood, leather, plastic, marble, granite, and tile, etc.), and metal

polishes and cleaners. Antioxidants are suitable to protect fragrances in above products as well as in dryer sheets. The present invention also relates to home care products such as candles, gel candles, air fresheners and fragrance oils (for the home).

- 5 The stabilizers of the present invention may be employed in fabric treatment that takes place after use of the fabric, referred to as fabric care. Such treatments include laundering, which uses detergents and/or fabric conditioner, and the application of non-detergent based fabric care products, such as spray-on products. When employed in this fashion, the present stabilizers are intended for deposition onto the fabric and used to protect the fabric, colorants
- 10 and fragrances associated with said these fabrics from environmental damage.

Typical examples of household cleaning and treating agents are:

<u>Household cleaners/household treating agents</u>	<u>Ingredients</u>
detergent concentrate	surfactant mixture, ethanol, antioxidant, water, UV absorbers, antioxidant
shoe polish	wax, wax emulsifier, antioxidant, water, preservative, UV absorbers, antioxidant
wax-containing floor cleaning agent	emulsifier, wax, sodium chloride, antioxidant, water, preservative, UV absorbers, antioxidant

- 15 The present stabilizers are for example incorporated by dissolution in an oil phase or alcoholic or water phase, where required at elevated temperature.

- The present invention also pertains to a method of stabilizing a body care product, household product, textile or fabric, which comprises incorporating therein or applying thereto one or
- 20 more compounds of the formulae (III) to (IIIc), for example one or more compounds of the formulae A* to EE*.

In the case of stabilized fabrics, for example dyed fabrics, the present stabilizers are applied thereto via deposition from for instance detergents, fabric conditioners or non-detergent based fabric care products.

5 The present fabrics are natural or synthetic, and may be woven or nonwoven.

The present invention also pertains to a method of stabilizing a body care product, household product, textile or fabric, each of which contain a dye, which comprises incorporating therein or applying thereto one or more compounds of the formulae (III) to (IIIc), for example one or
10 more compounds of the formulae A* to EE*. The stabilizers of formulae (III) to (IIIc) are very effective towards the stabilization of dyes in the present compositions.

The textiles of this invention are for example textile fiber materials, for example nitrogen-containing or hydroxy-group-containing fiber materials, for instance textile fiber materials
15 selected from cellulose, silk, wool, synthetic polyamides, leather and polyurethanes. Included are cotten, linen and hemp, pulp and regenerated cellulose. Included also are cellulosic blends, for example mixtures of cotton and polyamide or cotton/polyester blends.

The additives of the present invention are for example applied to textiles in a dyeing or
20 printing process, or in a finishing process. For instance, the additives may be applied as part of a dye formulation. The additives may be applied to textiles for example in an ink-jet printing process. The additives are for example applied as part of an aqueous dye solution or printing paste. They may be applied in an exhaust method or dyeing by the padder dyeing method, in which the textiles are impregnated with aqueous dye solutions, which may contain
25 salts, and the dyes and additives are fixed, after an alkali treatment or in the presence of alkali, if appropriate with the action of heat or by storage at room temperature for several hours. After fixing, the dyeings or prints are rinsed thoroughly with cold and hot water, if appropriate with the addition of an agent which has a dispersing action and promotes diffusion of the non-fixed portions.


30

The dye or ink formulations for application to textiles may comprise further customary additves, for example surfactants, antifoams, antimicrobials and the like, for example as disclosed in U.S. Pat. Nos. 6,281,339, 6,353,094 and 6,323,327, the disclosures of which are hereby incorporated by reference.

The following Examples illustrate the invention. Percentages are in weight percent unless indicated otherwise.


- 5 About 20 mL of each of the aqueous test formulations are placed in a borosilicate glass bottle.

The bottles are also exposed to accelerated fluorescent lighting, Philips, 40 Watt, Daylight Deluxe (D65), full exposure to light.

Example 1

4-Hydroxy-1-(2-hydroxy-2-methylpropoxy)-2,2,6,6-tetramethylpiperidine (5 g, 0.02 mole),
 5 citric acid (1.43 g, 0.0067 mole) and methanol (50 g, 1.6 mole) are added to a round bottom
 flask. The mixture is stirred at ambient temperature for 30 minutes to ensure complete
 dissolution. The methanol is removed by distillation and the resulting solid product is dried to
 constant weight. The title compound is obtained (6 g, 93% yield) as a white solid with a
 melting point of 112-122C whose structure is consistent with HNMR. The HNMR spectrum
 10 indicates a ratio of about four to one.

^1H NMR (CD_3OD): δ 3.88 (t, 1 H), 3.63 (s, 2 H), 2.84 (s, 4 H), 1.74 (d, 2 H), 1.42 (t, 2 H),
 1.23 (s, 6 H), 1.21 (s, 6 H), 1.20 (s, 6 H).

Example 2


15

4-Hydroxy-1-(2-hydroxy-2-methylpropoxy)-2,2,6,6-tetramethylpiperidine (5 g, 0.02 mole),
 citric acid (2.13 g, 0.01 mole) and methanol (50 g, 1.6 mole) are added to a round bottom
 flask. The mixture is stirred at ambient temperature for 30 minutes to ensure complete
 20 dissolution. The methanol is removed by distillation and the resulting solid product is dried to
 constant weight. The title compound is obtained (6.4 g, 90% yield) as a white solid with a

melting point of 103-113C whose structure is consistent with HNMR. The HNMR spectrum indicates a ratio of about 2.5 to one.


¹H NMR (CD₃OD): δ 3.88 (t, 1 H), 3.63 (s, 2 H), 2.84 (s, 4 H), 1.74 (d, 2 H), 1.42 (t, 2 H),
5 1.23 (s, 6 H), 1.21 (s, 6 H), 1.20 (s, 6 H).

Example 3



10 4-Hydroxy-1-(2-hydroxy-2-methylpropoxy)-2,2,6,6-tetramethylpiperidine (5 g, 0.02 mole),
citric acid (4.29 g, 0.02 mole) and methanol (50 g, 1.6 mole) are added to a round bottom
flask. The mixture is stirred at ambient temperature for 30 minutes to ensure complete
dissolution. The methanol is removed by distillation and the resulting solid product is dried to
constant weight. The title compound is obtained (8.6 g, 92.5% yield) as a white solid with a
15 melting point of 93-110C whose structure is consistent with HNMR. The HNMR spectrum
indicates a ratio of about one to one.

¹H NMR (CD₃OD): δ 3.88 (t, 1 H), 3.63 (s, 2 H), 2.84 (s, 4 H), 1.75 (d, 2 H), 1.42 (t, 2 H),
20 1.23 (s, 6 H), 1.21 (s, 6 H), 1.20 (s, 6 H).

Example 4

4-Hydroxy-1-(2-hydroxy-2-methylpropoxy)-2,2,6,6-tetramethylpiperidine (5 g, 0.02 mole),
 5 ascorbic acid (3.59 g, 0.02 mole) and methanol (200 g, 6.2 mole) are added to a round
 bottom flask. The mixture is stirred at ambient temperature for 60 minutes to ensure
 complete dissolution. The methanol is removed by distillation and the resulting solid product
 is dried to constant weight. The title compound is obtained (8.1 g, 94% yield) as a white solid
 with a melting point of 131-137C whose structure is consistent with HNMR. The HNMR
 10 spectrum indicates a ratio of about one to one.

$^1\text{H NMR}$ (CD_3OD): δ 4.79 (s, 1H), 3.89 (t, 2H), 3.88 (t, 1 H), 3.67 (d, 1H), 3.63 (s, 2 H), 1.74
 (d, 2 H), 1.42 (t, 2 H), 1.22 (s, 6 H), 1.20 (s, 6 H), 1.20 (s, 6 H).

15 Example 5

The instant compounds are added to a commercial shampoo formulation and are evaluated
 for their ability to reduce the amount of dye fading when the samples are exposed to
 fluorescent lighting. The instant compounds (0.36 g) are dissolved in 5 mL of methanol which
 is then added to 120 g of shampoo (Suave^R Natural Fresh Mountain Strawberry Shampoo)
 20 with agitation. The stabilized shampoo formulation is agitated for 15 minutes and put into 20
 mL glass scintillation vials. These formulations are weathered under fluorescent light aging at
 ambient temperature. The CIEL*a*b coordinates before and after exposure are measured
 using X-Rite 938 Spectrodensitometer. Color change is expressed as Delta E (DE). The
 color change is given by Delta E (DE) which is calculated by:

25

$$\text{DE} = [(\text{DL}^*)^2 + (\text{Da}^*)^2 + (\text{Db}^*)^2]^{1/2}$$

<u>Stabilizer (loading at 0.30 wt%)</u>	<u>DE after 4 weeks</u>
None	21.6
Compound A	15.6
Example 3	12.3
Example 2	12.1
Example 1	11.7

Compound A is 1-oxyl-2,2,6,6-tetramethyl-4-hydroxypiperidine which is disclosed in WO 2003103622, the publication of U.S. Pat. app. No. 60/377,381, filed 05/02/2002, incorporated
5 herein by reference.

The compounds according to this invention are able to improve clearly the light fastness of shampoo formulations.

10 Example 6

The instant compounds are added to a commercial shampoo formulation and are evaluated for their ability to reduce the amount of dye fading when the samples are exposed to fluorescent lighting. The instant compounds (0.36 g) are dissolved in 5 mL of methanol which is then added to 120 g of shampoo (Clairol^R Herbal Essences Shampoo) with agitation. The
15 stabilized shampoo formulation is agitated for 15 minutes and put into 20 mL glass scintillation vials. These formulations are weathered under fluorescent light aging at ambient temperature. The CIEL*a*b coordinates before and after exposure are measured using X-Rite 938 Spectrodensitometer. Color change is expressed as Delta E (DE).

<u>Stabilizer (loading at 0.30 wt%)</u>	<u>DE after 4 weeks</u>
None	21.6
Compound A	1.32
Example 2	0.95
Example 1	0.87

20 Compound A is 1-oxyl-2,2,6,6-tetramethyl-4-hydroxypiperidine which is disclosed in WO2003103622, the publication of U.S. Pat. app. No. 60/377,381, filed 05/02/2002, incorporated herein by reference.

The compounds according to this invention are able to improve clearly the light fastness of shampoo formulations.

Example 7

- 5 The instant compounds are added to a commercial mouthwash formulation and are evaluated for their ability to reduce the amount of dye fading when the samples are exposed to fluorescent lighting. The instant compounds (0.36 g) are dissolved in 5 mL of methanol which is then added to 120 g of mouthwash (Scope^R Original Mint) with agitation. The stabilized mouthwash formulation is agitated for 15 minutes and put into 20 mL glass
- 10 scintillation vials. These formulations are weathered under fluorescent light aging at ambient temperature. The CIEL*a*b coordinates before and after exposure are measured using X-Rite 938 Spectrodensitometer. Color change is expressed as Delta E (DE).

<u>Stabilizer (loading at 0.30 wt%)</u>	<u>DE after 4 weeks</u>
None	3.26
Compound A	2.93
Example 2	1.98
Example 1	2.45

- Compound A is 1-oxyl-2,2,6,6-tetramethyl-4-hydroxypiperidine which is disclosed in WO
- 15 2003103622, the publication of U.S. Pat. app. No. 60/377,381, filed 05/02/2002, incorporated herein by reference.

The compounds according to this invention are able to improve clearly the light fastness of mouthwash formulations.

20

Example 8

- The instant compounds are added to a commercial mouthwash formulation and are evaluated for their ability to reduce the amount of dye fading when the samples are exposed to fluorescent lighting. The instant compounds (0.36 g) are dissolved in 5 mL of methanol
- 25 which is then added to 120 g of mouthwash (Listerine^R Tartar Control Wintermint) with agitation. The stabilized mouthwash formulation is agitated for 15 minutes and put into 20 mL glass scintillation vials. These formulations are weathered under fluorescent light aging at ambient temperature. The CIEL*a*b coordinates before and after exposure are measured using X-Rite 938 Spectrodensitometer. Color change is expressed as Delta E (DE).

<u>Stabilizer (loading at 0.30 wt%)</u>	<u>DE after 1 week</u>
Compound A	9.23
None	1.17
Example 1	0.69
Example 3	0.66
Example 2	0.60

Compound A is 1-oxyl-2,2,6,6-tetramethyl-4-hydroxypiperidine which is disclosed in WO 2003103622, the publication of U.S. Pat. app. No. 60/377,381, filed 05/02/2002, incorporated herein by reference.

5

The compounds according to this invention are able to improve clearly the light fastness of mouthwash formulations.

Example 9

10 The instant compounds are added to a commercial shampoo formulation and are evaluated for their ability to reduce the amount of dye fading when the samples are exposed to fluorescent lighting. The instant compounds are dissolved in a shampoo formulation with agitation. 3-(2H-benzotriazol-2-yl)-4-hydroxy-5-(1-methylpropyl)-benzenesulfonic acid monosodium salt, a benzotriazole UV absorber, is added to the shampoo formulation. These
15 formulations are weathered under fluorescent light at ambient temperature. The CIEL*a*b coordinates before and after exposure are measured. The change in color is expressed by Delta E (DE). The compounds according to this invention are quite efficacious in improving light fastness of shampoo formulations.

20 Example 10

The instant compounds are added to a commercial shampoo formulation and are evaluated for their ability to reduce the amount of dye fading when the samples are exposed to fluorescent lighting. The instant compounds are dissolved in a shampoo formulation with agitation. An s-triazine UV absorber is added to the shampoo formulation. These
25 formulations are weathered under fluorescent light at ambient temperature. The CIEL*a*b coordinates before and after exposure are measured. The change in color is expressed by Delta E (DE). The compounds according to this invention are quite efficacious in improving light fastness of shampoo formulations.

Example 11

The instant compounds are added to a commercial shampoo formulation and are evaluated for their ability to reduce the amount of dye fading when the samples are exposed to fluorescent lighting. The instant compounds are dissolved in a shampoo formulation with agitation. A benzophenone UV absorber is added to the shampoo formulation. These formulations are weathered under fluorescent light at ambient temperature. The CIEL*a*b coordinates before and after exposure are measured. The change in color is expressed by Delta E (DE). The compounds according to this invention are quite efficacious in improving light fastness of shampoo formulations.

Example 12

The instant compounds are added to a commercial mouthwash formulation and are evaluated for their ability to reduce the amount of dye fading when the samples are exposed to fluorescent lighting. The instant compounds are added to a mouthwash formulation with agitation. 3-(2H-benzotriazol-2-yl)-4-hydroxy-5-(1-methylpropyl)-benzenesulfonic acid monosodium salt, a benzotriazole UV absorber, is added to the mouthwash formulation. These formulations are weathered under fluorescent lighting at ambient temperature. The CIEL*a*b coordinates before and after exposure are measured. Color change is expressed as Delta E (DE). The compounds according to this invention are quite efficacious in improving light fastness of mouthwash formulations.

Example 13

The instant compounds are added to a commercial mouthwash formulation and are evaluated for their ability to reduce the amount of dye fading when the samples are exposed to fluorescent lighting. The instant compounds are added to a mouthwash formulation with agitation. An s-triazine UV absorber is added to the mouthwash formulation. These formulations are weathered under fluorescent lighting at ambient temperature. The CIEL*a*b coordinates before and after exposure are measured. Color change is expressed as Delta E (DE). The compounds according to this invention are quite efficacious in improving light fastness of mouthwash formulations.

Example 14

The instant compounds are added to a commercial mouthwash formulation and are evaluated for their ability to reduce the amount of dye fading when the samples are exposed to fluorescent lighting. The instant compounds are added to a mouthwash formulation with
5 agitation. A benzophenone UV absorber is added to the mouthwash formulation. These formulations are weathered under fluorescent lighting at ambient temperature. The CIEL*a*b coordinates before and after exposure are measured. Color change is expressed as Delta E (DE). The compounds according to this invention are quite efficacious in improving light fastness of mouthwash formulations.

10

Example 15

An aqueous based test formulation is prepared as follows:

sodium laureth sulfate (30%, TEXAPON NSO, Cognis) 30%

cocamidopropylbetaine (30%, DEHYTON K, Cognis) 10%

15 colorant* 0.001%

instant stabilizer 0.05%

citric acid (10% aqueous solution) to pH 6

deionized water to 100%

*Colorant is PURICOLOR BLUE ABL9 (FD&C Blue No. 1)

20

About 20 mL of each of the aqueous test formulations are placed in a borosilicate glass bottle. The glass bottles are exposed in an Atlas Ci-65 Xenon arc WeatherOmeter, AATCC Test Method 16. Color measurements are performed on a Hunter Ultrascan XE spectrophotometer. Delta L, a and b values are the difference between the initial values and the
25 values at each interval. It is seen that the stabilizers of the present invention provide excellent color stability in personal care products.

Example 16

An aqueous based test formulation is prepared as follows:

30

sodium laureth sulfate (30%, TEXAPON NSO, Cognis) 30%

cocamidopropylbetaine (30%, DEHYTON K, Cognis) 10%

colorant* 0.001%

instant stabilizer 0.05%

- 44 -

citric acid (10% aqueous solution) to pH 6
 deionized water to 100%

*Colorant is PURICOLOR RED ARE33 (FD&C Red No. 33).

5 About 20 mL of each of the aqueous test formulations are placed in a borosilicate glass bottle. The glass bottles are exposed in an Atlas Ci-65 Xenon arc WeatherOmeter, AATCC Test Method 16, option E. Color measurements are performed on a Hunter Ultrascan XE spectrophotometer. Delta L, a and b values are the difference between the initial values and the values at each interval. It is seen that the stabilizers of the present invention provide
 10 excellent color stability in personal care products.

Example 17

An aqueous based test formulation is prepared as follows:

15 sodium laureth sulfate (30%, TEXAPON NSO, Cognis) 30%
 cocamidopropylbetaine (30%, DEHYTON K, Cognis) 10%
 colorant* 0.001%
 instant stabilizer 0.05%
 citric acid (10% aqueous solution) to pH 6
 20 deionized water to 100%

*Colorant is FD&C Red No. 40.

About 20 mL of each of the aqueous test formulations are placed in a borosilicate glass bottle. The glass bottles are exposed in an Atlas Ci-65 Xenon arc WeatherOmeter, AATCC
 25 Test Method 16. Color measurements are performed on a Hunter Ultrascan XE spectrophotometer. Delta L, a and b values are the difference between the initial values and the values at each interval. It is seen that the stabilizers of the present invention provide excellent color stability in personal care products.

30 Example 18

An aqueous based test formulation is prepared as follows:

sodium laureth sulfate (30%, TEXAPON NSO, Cognis) 30%
 cocamidopropylbetaine (30%, DEHYTON K, Cognis) 10%
 35 colorant* 0.001%

instant stabilizer	0.05%
citric acid (10% aqueous solution)	to pH 6
deionized water	to 100%

*Colorant is PURICOLOR BLUE ABL9 (FD&C Blue No. 1)

5

About 20 mL of each of the aqueous test formulations are placed in a borosilicate glass bottle. The glass bottles are also exposed to accelerated fluorescent lighting, Philips, 40 Watt, Daylight Deluxe (D65), full exposure to light. Color measurements are performed on a Hunter Ultrascan XE spectrophotometer. Delta L, a and b values are the difference between the initial values and the values at each interval. It is seen that the stabilizers of the present invention provide excellent color stability in personal care products.

10

Example 19

An aqueous based test formulation is prepared as follows:

15

sodium laureth sulfate (30%, TEXAPON NSO, Cognis)	30%
cocamidopropylbetaine (30%, DEHYTON K, Cognis)	10%
colorant*	0.001%
instant stabilizer	0.05%
citric acid (10% aqueous solution)	to pH 6
deionized water	to 100%

20

*Colorant is PURICOLOR RED ARE33 (FD&C Red No. 33).

About 20 mL of each of the aqueous test formulations are placed in a borosilicate glass bottle. The glass bottles are also exposed to accelerated fluorescent lighting, Philips, 40 Watt, Daylight Deluxe (D65), full exposure to light. Color measurements are performed on a Hunter Ultrascan XE spectrophotometer. Delta L, a and b values are the difference between the initial values and the values at each interval. It is seen that the stabilizers of the present invention provide excellent color stability in personal care products.

25

30

Example 20

An aqueous based test formulation is prepared as follows:

35

sodium laureth sulfate (30%, TEXAPON NSO, Cognis)	30%
cocamidopropylbetaine (30%, DEHYTON K, Cognis)	10%
colorant*	0.001%
instant stabilizer	0.05%

citric acid (10% aqueous solution) to pH 6
 deionized water to 100%

*Colorant is FD&C Red No. 40.

- 5 About 20 mL of each of the aqueous test formulations are placed in a borosilicate glass bottle. The glass bottles are also exposed to accelerated fluorescent lighting, Philips, 40 Watt, Daylight Deluxe (D65), full exposure to light. Color measurements are performed on a Hunter Ultrascan XE spectrophotometer. Delta L, a and b values are the difference between the initial values and the values at each interval. It is seen that the stabilizers of the present
 10 invention provide excellent color stability in personal care products.

Example 21

- The components of phase A are thoroughly mixed in a homogenizer for 10 min at 75-80°C. The water phase B, likewise heated to 75-80°C beforehand, is slowly added and the mixture
 15 is homogenized for 1 min. The mixture is cooled, with stirring, to 40°C and then phases C and E are added and the mixture is homogenized for 1 min. Subsequently, phase D is added and the mixture is homogenized for 1/2 min and cooled, with stirring, to room temperature.

<u>Phase</u>	<u>Ingredients</u>	<u>(w/w) %</u>
A	passionflower oil	8
	glyceryl dioleate	4
	dicapryl ether	4
	Isopropylisostearate	4
	instant stabilizer	0.05
B	water, demin.	ad. 100
	EDTA	0.1
C	Carbomer	0.15
D	sodium hydroxide	10%
		0.20
E	perfume; preservative	q.s.

20

It is seen that the stabilizers of the present invention provide excellent color stability in personal care products.

Example 22

The components below are thoroughly mixed in the cited sequence at 50°C, a clear homogeneous solution being obtained. The UV absorber is, for example, 3-(2H-benzotriazol-2-yl)-4-hydroxy-5-(1-methylpropyl)-benzenesulfonic acid monosodium salt.

5

<u>Ingredients</u>	<u>(w/w) %</u>
ethanol, 96%	60
d-limonene	5
cedrene	1.5
citronellol	0.5
savin	0.5
instant stabilizer	0.08
UV absorber	0.1
S,S-EDDS	0.005
colorant (D&C Yellow No.5)	0.02
water	ad. 100

Excellent results are achieved for this example of a toilet water formulation.

Example 23

- 10 The hydroxypropyl cellulose is first predissolved in half of the alcohol (Vortex mixer) and is charged with the aminomethylpropanol. The other components - with the exception of the acrylate resin - are dissolved in alcohol and this solution is added, with stirring, to the hydroxypropyl cellulose. Subsequently, the acrylate resin is added and stirred until completely dissolved. The UV absorber used is, for example, benzophenone-4 is 5-benzoyl-4-
- 15 hydroxy-2-methoxybenzenesulfonic acid, sodium salt.

Excellent results are achieved for this example of a hair styling spray formulation.

Example 24

- 20 The components listed below are mixed, with stirring, at room temperature until they are completely dissolved. The pH is 6.5. The UV absorber is, for example, 2-(2-hydroxy-3-dodecyl-5-methylphenyl)-2H-benzotriazole.

- 48 -

<u>Ingredients</u>	<u>(w/w) %</u>
sodium myreth sulfate	50.00
TEA abietoyl collagen hydrolysate	3.50
laureth-3	3.00
colorant (D&C Red No. 33)	0.20
instant stabilizer	0.05
UV absorber	0.15
phosphonomethylchitosan, sodium salt	0.01
perfume oil	0.10
water	ad. 100

Excellent results are achieved for this example of a shampoo composition for oily hair.

5 Example 25

The stabilizer is predissolved in the terpene. The components are then stirred in the cited sequence at about 65°C until homogeneous. The mixture is then cooled to room temperature.

<u>Ingredients</u>	<u>(w/w) %</u>
synthetic soap (Zetesap 813)	7.85
Glycerol	6.00
anionic surfactant (Lumorol 4192; Mulsifan RT 13)	22.00
Vaseline	11.00
paraffin 52/54	20.00
Talcum	2.00
orange terpene	4.00
instant stabilizer	0.02
Water	27.13

10

Excellent results are achieved for this example of a leather dressing and cleaning agent composition.

Example 26

The components listed below are dissolved in the cited sequence until a clear homogeneous mixture is obtained.

<u>Ingredients</u>	<u>(w/w) %</u>
anionic / amphoteric surfactants (Lumorol RK)	0.7
butyl glycol	5.0
Isopropanol	20.0
d-limonene	4.00
instant stabilizer	0.02
water, demin.	ad. 100

5

Excellent results are achieved for this example of a glass detergent formulation.

Example 27

The instant stabilizers are each deposited (from water) on a dyed cotton fabric at 0.05, 0.1, 0.2, 0.5 and 1.0 percent by weight, based on the weight of the cotton. The dyed fabrics contain the following dyes at 0.05, 0.1, 0.2 and 0.5 percent by weight based on cotton. These results in 60 separate formulations for each dye listed:

10

Scarlet HE-3G	Crimson HE-XL	Yellow HE-6G
Red HE-XL	Blue HE-XL	Turquoise H-A
Navy HE-XL	Remazol	Red RB
Brilliant Red RBS	Orange FR	Navy CG
Turquoise G	Black B	

15 The cotton fabrics are subjected to light exposure in an Atlas Ci-65 Xenon arc WetherOmeter or to accelerated fluorescent lighting. The present stabilizers provide outstanding color protection to the dyed fabrics. This experiment simulates dye protection achievable through deposition of the present stabilizers via treatment with, for example, stabilizer-containing laundry detergent or fabric conditioner.

20

Example 28

The instant stabilizers and UV absorbers, for example 3-(2H-benzotriazol-2-yl)-4-hydroxy-5-(1-methylpropyl)-benzenesulfonic acid monosodium salt, are each deposited (from water) on a dyed cotton fabric at 0.05, 0.1, 0.2, 0.5 and 1.0 percent by weight, based on the weight of the cotton. The dyed fabrics contain the following dyes at 0.05, 0.1, 0.2 and 0.5 percent by weight based on cotton. This results in 60 separate formulations for each dye listed:

Scarlet HE-3G	Crimson HE-XL	Yellow HE-6G
Red HE-XL	Blue HE-XL	Turquoise H-A
Navy HE-XL	Remazol	Red RB
Brilliant Red RBS	Orange FR	Navy CG
Turquoise G	Black B	


The cotton fabrics are subjected to light exposure in an Atlas Ci-65 Xenon arc WetherOmeter or to accelerated fluorescent lighting. The present stabilizers provide outstanding color protection to the dyed fabrics. This experiment simulates dye protection achievable through deposition of the present stabilizers via treatment with for example stabilizer-containing laundry detergent or fabric conditioner.

What is claimed is:

1. A stabilized composition comprising

(a) a body care product, household product, textile or fabric and

5 (b) an effective stabilizing amount of one or more compounds of formula



wherein

G_1 and G_2 are independently alkyl of 1 to 4 carbon atoms or are together pentamethylene; Z_1 and Z_2 are each methyl, or Z_1 and Z_2 together form an unsubstituted linking moiety or a linking moiety substituted by one or more groups selected from an ester, ether, hydroxy, oxo, cyanohydrin, amide, amino, carboxy or an urethane group;

E is alkoxy of 1 to 18 carbon atoms, cycloalkoxy of 5 to 12 carbon atoms or aralkoxy of 7 to 15 carbon atoms, or E is $-\text{O}-\text{T}-(\text{OH})_b$,

T is a straight or branched chain alkylene of 1 to 18 carbon atoms, cycloalkylene of 5 to 18 carbon atoms, cycloalkenylene of 5 to 18 carbon atoms, a straight or branched chain alkylene of 1 to 4 carbon atoms substituted by phenyl or by phenyl substituted by one or two alkyl groups of 1 to 4 carbon atoms;


b is 1, 2 or 3 with the proviso that b cannot exceed the number of carbon atoms in T, and when b is 2 or 3, each hydroxyl group is attached to a different carbon atoms of T; and













HY is an inorganic or organic acid; wherein the total charge of cations is equal to the total charge of anions.











2. A stabilized composition according to claim 1 wherein Z_1 and Z_2 as a linking moiety are a chain of 2 or 3 carbon atoms or 1 or 2 carbon atoms and a nitrogen or oxygen atom forming together with the remaining structure in formula (I) a saturated unsubstituted 5- or 6-membered heterocyclic ring or a 5- or 6-membered heterocyclic ring substituted by one or more groups selected from the group consisting of ester, ether, hydroxy, oxo, cyanohydrin, amide, amino, carboxy, and urethane.


3. A stabilized composition according to claim 1 wherein Y in formula (I) is selected from the group consisting of phosphate, phosphonate, carbonate, bicarbonate, nitrate, chloride, bromide, bisulfite, sulfite, bisulfate, sulfate, borate, formate, acetate, benzoate, citrate, oxalate, tartrate, acrylate, polyacrylate, fumarate, maleate, itaconate, glycolate, gluconate, malate, mandelate, tiglite, ascorbate, polymethacrylate, a carboxylate of nitrilotriacetic acid, a carboxylate of hydroxyethylethylenediaminetriacetic acid, a carboxylate of ethylenediaminetetraacetic acid, a carboxylate of diethylenetriaminepentaacetic acid, a carboxylate of diethylenediaminetetraacetic acid, a carboxylate of diethylenetriaminepentaacetic acid, alkylsulfonate, arylsulfonate, and alkyl-substituted arylsulfonate.

4. A stabilized composition according to claim 1 wherein the compounds of formula (I) are selected from the group consisting of formulae (A*) to (EE*) and (III) to (IIIc)









wherein

E is alkoxy of 1 to 18 carbon atoms, cycloalkoxy of 5 to 12 carbon atoms or aralkoxy of 7 to 15 carbon atoms, or E is -O-T-(OH)_b,

5 T is a straight or branched chain alkylene of 1 to 18 carbon atoms, cycloalkylene of 5 to 18 carbon atoms, cycloalkenylene of 5 to 18 carbon atoms, a straight or branched chain alkylene of 1 to 4 carbon atoms substituted by phenyl or by phenyl substituted by one or two alkyl groups of 1 to 4 carbon atoms;

b is 1, 2 or 3 with the proviso that b cannot exceed the number of carbon atoms in T, and
10 when b is 2 or 3, each hydroxyl group is attached to a different carbon atoms of T;

R is hydrogen or methyl; and

in formula (A*) n is 1 or 2,

when n is 1,

15 R₁ is hydrogen, alkyl of 1 to 18 carbon atoms, alkenyl of 2-18 carbon atoms, propargyl, glycidyl, alkyl of 2 to 50 carbon atoms interrupted by one to twenty oxygen atoms, said alkyl substituted by one to ten hydroxyl groups or both interrupted by said oxygen atoms and substituted by said hydroxyl groups, or

R₁ is alkyl of 1 to 4 carbon atoms substituted by a carboxy group or by -COOZ where Z is hydrogen, alkyl of 1 to 4 carbon atoms or phenyl, or where Z is said alkyl substituted by -
20 (COO⁻)_nMⁿ⁺ where n is 1-3 and M is a metal ion from the 1st, 2nd or 3rd group of the periodic table or is Zn, Cu, Ni or Co, or M is a group Nⁿ⁺(R₂)₄ where R₂ is alkyl of 1 to 8 carbon atoms or benzyl,

when n is 2,

R₁ is alkylene of 1 to 12 carbon atoms, alkenylene of 4 to 12 carbon atoms, xylylene or alkylene of 1 to 50 carbon atoms interrupted by one to twenty oxygen atoms, substituted by one to ten hydroxyl groups or both interrupted by said oxygen atoms and substituted
5 by said hydroxyl groups;

in formula (B*), m is 1 to 4, and

when m is 1,

R₂ is alkyl of 1 to 18 carbon atoms, alkyl of 3 to 18 carbon atoms interrupted by -COO-, alkyl of 3 to 18 carbon atoms substituted by COOH or COO-, or R₂ is -CH₂(OCH₂CH₂)_nOCH₃
10 where n is 1 to 12, or

R₂ is cycloalkyl of 5 to 12 carbon atoms, aryl of 6 to 12 carbon atoms, or said aryl substituted by one to four alkyl groups of 1 to 4 carbon atoms, or

R₂ is -NHR₃ where R₃ is alkyl of 1 to 18 carbon atoms, cycloalkyl of 5 to 12 carbon atoms, aryl of 6 to 12 carbon atoms, or said aryl substituted by one to four alkyl of 1 to 4 carbon
15 atoms, or

R₂ is -N(R₃)₂ where R₃ is as defined above,

when m is 2,

R₂ is alkylene of 1 to 12 carbon atoms, alkenylene of 4 to 12 carbon atoms, xylylene, alkylene of 2 to 12 carbon atoms interrupted by -COO-, alkylene of 3 to 18 carbon atoms
20 substituted by COOH or COO-, or R₂ is -CH₂(OCH₂CH₂)_nOCH₂- where n is 1 to 12, or

R₂ is cycloalkylene of 5 to 12 carbon atoms, aralkylene of 7 to 15 carbon atoms or arylene of 6 to 12 carbon atoms, or

R₂ is -NHR₄NH- where R₄ is alkylene of 2 to 18 carbon atoms, cycloalkylene of 5 to 12 carbon atoms, aralkylene of 8 to 15 carbon atoms or arylene of 6 to 12 carbon atoms, or

25 R₂ is -N(R₃)R₄N(R₃)- where R₃ and R₄ are as defined above, or

R₂ is -CO-, -NH-CO-NH-, or -N(R₃)-CO-N(R₃)-,

when m is 3,

R₂ is alkanetriyl of 3 to 8 carbon atoms or benzenetriyl, or

when m is 4,

30 R₂ is alkanetetrayl of 5 to 8 carbon atoms or benzenetetrayl,

in formula (C*),

R₁₀ is hydrogen, alkyl of 1 to 18 carbon atoms, cycloalkyl of 5 to 12 carbon atoms, aralkyl of 7 to 15 carbon atoms, alkanoyl of 2 to 18 carbon atoms, alkenoyl of 3 to 5 carbon atoms or benzoyl,

x is 1 or 2, and

when x is 1,

R₁₁ is hydrogen, alkyl of 1 to 18 carbon atoms, alkenyl of 2 to 18 carbon atoms, propargyl, glycidyl, alkyl of 2 to 50 carbon atoms interrupted by one to twenty oxygen atoms, said
5 alkyl substituted by one to ten hydroxyl groups or both interrupted by said oxygen atoms and substituted by said hydroxyl groups, or

R₁₁ is alkyl of 1 to 4 carbon atoms substituted by a carboxy group or by -COOZ where Z is hydrogen, alkyl of 1 to 4 carbon atoms or phenyl, or where Z is said alkyl substituted by -
10 (COO⁻)_n Mⁿ⁺ where n is 1-3 and M is a metal ion from the 1st, 2nd or 3rd group of the periodic table or is Zn, Cu, Ni or Co, or M is a group Nⁿ⁺(R₂)₄ where R₂ is hydrogen, alkyl of 1 to 8 carbon atoms or benzyl, or

when x is 2,

R₁₁ is alkylene of 1 to 12 carbon atoms, alkenylene of 4 to 12 carbon atoms, xylylene or
15 alkylene of 1 to 50 carbon atoms interrupted by one to twenty oxygen atoms, substituted by one to ten hydroxyl groups or both interrupted by said oxygen atoms and substituted by said hydroxyl groups,

in formula (D*), y is 1 to 4,

R₁₀ is as defined above,

and R₁₂ is defined as R₂ above,

20 in formula (E*), k is 1 or 2,

when k is 1,

R₂₀ and R₂₁ are independently alkyl of 1 to 12 carbon atoms, alkenyl of 2 to 12 carbon atoms
or aralkyl of 7 to 15 carbon atoms, or R₂₀ is also hydrogen, or

R₂₀ and R₂₁ together are alkylene of 2 to 8 carbon atoms or said alkylene substituted by
25 hydroxyl, or are acyloxy-alkylene of 4 to 22 carbon atoms, or

when k is 2,

R₂₀ and R₂₁ are together (-CH₂)₂C(CH₂-)₂,

in formula (F*),

R₃₀ is hydrogen, alkyl of 1 to 18 carbon atoms, benzyl, glycidyl, or alkoxyalkyl of 2 to 6
30 carbon atoms,

g is 1 or 2,

when g is 1, R₃₁ is defined as R₁ above when n is 1,

when g is 2, R₃₁ is defined as R₁ above when n is 2,

in formula (G*),

Q_1 is $-NR_{41}-$ or $-O-$,

E_1 is alkylene of 1 to 3 carbon atoms, or E_1 is $-\text{CH}_2-\text{CH}(\text{R}_{42})-\text{O}-$ where R_{42} is hydrogen, methyl or phenyl, or E_1 is $-(\text{CH}_2)_3-\text{NH}-$ or E_1 is a direct bond,

R_{40} is hydrogen or alkyl of 1 to 18 carbon atoms,

- 5 R_{41} is hydrogen, alkyl of 1 to 18 carbon atoms, cycloalkyl of 5 to 12 carbon atoms, aralkyl of 7 to 15 carbon atoms, aryl of 6 to 10 carbon atoms, or R_{41} is $-\text{CH}_2-\text{CH}(\text{R}_{42})-\text{OH}$ where R_{42} is as defined above,

in formula (H*), p is 1 or 2,

T_4 is as defined for R_{11} when x is 1 or 2,

- 10 M and Y are independently methylene or carbonyl, preferably M is methylene and Y is carbonyl,

in formula (I*),

this formula denotes a recurring structural unit of a polymer where T_1 is ethylene or 1,2-propylene or is the repeating structural unit derived from an alpha-olefin copolymer with an

- 15 alkyl acrylate or methacrylate, and where

q is 2 to 100,

Q_1 is $-\text{N}(\text{R}_{41})-$ or $-\text{O}-$ where R_{41} is as defined above,

in formula (J*),

r is 1 or 2,

- 20 T_7 is as defined for R_1 when n is 1 or 2 in formula (A*),

preferably T_7 is octamethylene when r is 2,

in formula (L*), u is 1 or 2,

T_{13} is as defined for R_1 when n is 1 or 2 in formula (A*), with the proviso that T_{13} is not hydrogen when u is 1,

- 25 in formula (M*),

E_1 and E_2 , being different, each are $-\text{CO}-$ or $-\text{N}(\text{E}_5)-$ where E_5 is hydrogen, alkyl of 1 to 12 carbon atoms or alkoxy carbonylalkyl of 4 to 22 carbon atoms, preferably E_1 is $-\text{CO}-$ and E_2 is $-\text{N}(\text{E}_5)-$,

- 30 E_3 is hydrogen, alkyl of 1 to 30 carbon atoms, phenyl, naphthyl, said phenyl or said naphthyl substituted by chlorine or by alkyl of 1 to 4 carbon atoms, or phenylalkyl of 7 to 12 carbon atoms, or said phenylalkyl substituted by alkyl of 1 to 4 carbon atoms,

E_4 is hydrogen, alkyl of 1 to 30 carbon atoms, phenyl, naphthyl or phenylalkyl of 7 to 12 carbon atoms, or

E₃ and E₄ together are polymethylene of 4 to 17 carbon atoms, or said polymethylene substituted by one to four alkyl of 1 to 4 carbon atoms, preferably methyl, in formula (O*),

R₁₀ is as defined for R₁₀ in formula (C*),

5 in formula (P*),

E₆ is an aliphatic or aromatic tetravalent radical, preferably neopentantetrayl or benzenetetrayl,

in formula (T*),

10 R₅₁ is hydrogen, alkyl of 1 to 18 carbon atoms, cycloalkyl of 5 to 12 carbon atoms, or aryl of 6 to 10 carbon atoms,

R₅₂ is hydrogen or alkyl of 1 to 18 carbon atoms, or

R₅₁ and R₅₂ together of alkylene of 4 to 8 carbon atoms,

f is 1 or 2,

when f is 1,

15 R₅₀ is as defined for R₁₁ in formula (C*) when x is 1, or R₅₀ is -(CH₂)_zCOOR₅₄ where z is 1 to 4 and R₅₄ is hydrogen or alkyl of 1 to 18 carbon atoms, or R₅₄ is a metal ion from the 1st, 2nd or 3rd group of the periodic table or a group -N(R₅₅)₄ where R₅₅ is hydrogen, alkyl of 1 to 12 carbon atoms or benzyl,

when f is 2,

20 R₅₀ is as defined for R₁₁ in formula (C*) when x is 2, in formula (U*),

R₅₃, R₅₄, R₅₅ and R₅₆ are independently alkyl of 1 to 4 carbon atoms or are together pentamethylene,

in formula (V*),

25 R₅₇, R₅₈, R₅₉ and R₆₀ are independently alkyl of 1 to 4 carbon atoms or are together pentamethylene,

in formula (W*),

R₆₁, R₆₂, R₆₃ and R₆₄ are independently alkyl of 1 to 4 carbon atoms or are together pentamethylene,

30 R₆₅ is alkyl of 1 to 5 carbon atoms,

M is hydrogen or oxygen,

wherein in formulas (Y*) to (BB*),

n is 2 to 3,

G₁ is hydrogen, methyl, ethyl, butyl or benzyl,

m is 1 to 4,

x is 1 to 4,

when x is 1, R₁ and R₂ are independently alkyl of 1 to 18 carbon atoms, said alkyl interrupted by one to five oxygen atoms, said alkyl substituted by 1 to 5 hydroxyl groups or said alkyl

5 both interrupted by said oxygen atoms and substituted by said hydroxyl groups; cycloalkyl of 5 to 12 carbon atoms, aralkyl of 7 to 15 carbon atoms, aryl of 6 to 10 carbon atoms or said aryl substituted by one to three alkyl of 1 to 8 carbon atoms, or R₁ is also hydrogen, or R₁ and R₂ are together tetramethylene, pentamethylene, hexamethylene or 3-oxapentamethylene,

10 when x is 2,

R₁ is hydrogen, alkyl of 1 to 8 carbon atoms, said alkyl interrupted by one or two oxygen atoms, said alkyl substituted by a hydroxyl group, or said alkyl both interrupted by one or two oxygen atoms and substituted by a hydroxyl group,

15 R₂ is alkylene of 2 to 18 carbon atoms, said alkylene interrupted by one to five oxygen atoms, said alkylene substituted by 1 to 5 hydroxyl groups or said alkylene both interrupted by said oxygen atoms and substituted by said hydroxyl groups; o-, m- or p-phenylene or said phenylene substituted by one or two alkyl of 1 to 4 carbon atoms, or

R₂ is $-(\text{CH}_2)_k\text{O}[(\text{CH}_2)_k\text{O}]_h(\text{CH}_2)_k-$ where k is 2 to 4 and h is 1 to 40, or

R₁ and R₂ together with the two N atoms to which they are attached are piperazin-1,4-diyl,

20 when x is 3,

R₁ is hydrogen,

R₂ is alkylene of 4 to 8 carbon atoms interrupted by one nitrogen atom,

when x is 4,

R₁ is hydrogen,

25 R₂ is alkylene of 6 to 12 carbon atoms interrupted by two nitrogen atoms,

R₃ is hydrogen, alkyl of 1 to 8 carbon atoms, said alkyl interrupted by one or two oxygen atoms, said alkyl substituted by a hydroxyl group, or both interrupted by one or two oxygen atoms and substituted by a hydroxyl group,

p is 2 or 3,

30 in formula (DD*),

m is 2 or 3,

when m is 2,

G is $-(\text{CH}_2\text{CHR-O})_r\text{CH}_2\text{CHR}-$, where r is 0 to 3, and R is hydrogen or methyl, and

when m is 3, G is glyceryl,

in formula (EE*),

G_2 is -CN, -CONH₂ or -COOG₃ where G₃ is hydrogen, alkyl of 1 to 18 carbon atoms or phenyl,

in formulae (III) to (IIIc),

5 A₁₁ is OR₁₀₁ or NR₁₁₁R₁₁₂,

R₁₀₁ is alkenyl of 2 to 4 carbon atoms, propargyl, glycidyl, alkyl of 2 to 6 carbon atoms interrupted by one or two oxygen atoms, substituted by one to three hydroxyl groups or both interrupted by said oxygen atoms and substituted by said hydroxyl groups, or R₁₀₁ is alkyl of 1 to 4 carbon atoms substituted by carboxy or by the alkali metal, ammonium or C₁-C₄alkylammonium salts thereof; or R₁₀₁ is alkyl substituted by COOE₁₀ where E₁₀ is methyl or ethyl,

R₁₀₂ is alkyl of 3 to 5 carbon atoms interrupted by -COO- or by -CO-, or R₁₀₂ is -CH₂(OCH₂CH₂)_cCOCH₃ where c is 1 to 4; or

R₁₀₂ is -NHR₁₀₃ where R₁₀₃ is alkyl of 1 to 4 carbon atoms,

15 a is 2 to 4,

when a is 2,

T₁₁ is -(CH₂CHR₁₀₀-O)_dCH₂CHR₁₀₀-, where d is 0 or 1, and R₁₀₀ is hydrogen or methyl,

when a is 3, T₁₁ is glyceryl,

when a is 4, T₁₁ is neopentane tetrayl,

20 b is 2 or 3,

when b is 2,

G₁₁ is -(CH₂CHR₁₀₀-O)_dCH₂CHR₁₀₀-, where d is 0 or 1, and R₁₀₀ is hydrogen or methyl, and when b is 3, G₁₁ is glyceryl;

R₁₁₁ is hydrogen, unsubstituted alkyl of 1 to 4 carbon atoms, alkyl of 1 to 4 carbon atoms

25 substituted by one or two hydroxyl, alkyl of 1 to 4 carbon atoms interrupted by one or two oxygen atoms, or both substituted by one hydroxyl and interrupted by one or two oxygen atoms,

R₁₁₂ is -CO-R₁₁₃ where R₁₁₃ has the same meaning as R₁₁₁, or R₁₁₃ is NHR₁₁₄, wherein R₁₁₄ is unsubstituted alkyl of 1 to 4 carbon atoms, alkyl of 1 to 4 carbon atoms substituted by one or two hydroxyl, alkyl of 1 to 4 carbon atoms substituted by alkoxy of 1 to 2 carbon atoms, or both substituted by one hydroxyl and by alkoxy of 1 to 2 carbon atoms, or

30

R₁₁₁ and R₁₁₂ together are -CO-CH₂CH₂-CO-, or (CH₂)₆CO-;

HY is an inorganic or organic acid; wherein the total charge of cations is equal to the total charge of anions; and

- Y is phosphate, phosphonate, carbonate, bicarbonate, nitrate, chloride, bromide, bisulfite, sulfite, bisulfate, sulfate, borate, formate, acetate, benzoate, citrate, oxalate, tartrate, acrylate, polyacrylate, fumarate, maleate, itaconate, glycolate, gluconate, malate, mandelate, tiglate, ascorbate, polymethacrylate, a carboxylate of nitrilotriacetic acid, a
5 carboxylate of hydroxyethylethylenediaminetriacetic acid, a carboxylate of ethylenediaminetetraacetic acid, a carboxylate of diethylenetriaminepentaacetic acid, a carboxylate of diethylenediaminetetraacetic acid, a carboxylate of diethylenetriaminepentaacetic acid, alkylsulfonate, arylsulfonate, or alkyl-substituted arylsulfonate.
- 10 5. A stabilized composition according to claim 4 wherein the compounds of formula (I) are selected from the group consisting of (A*), (B*), (C*), (D*), (Q*), (R*), (Y*), and (Z*), wherein
- E is alkoxy of 1 to 10 carbon atoms, cycloalkoxy of 5 to 8 carbon atoms or aralkoxy of 7 to 12 carbon atoms, or E is -O-T-(OH)_b,
- 15 T is a straight or branched chain alkylene of 1 to 10 carbon atoms, cycloalkylene of 5 to 10 carbon atoms, cycloalkenylene of 5 to 10 carbon atoms, a straight or branched chain alkylene of 1 to 4 carbon atoms substituted by phenyl or by phenyl substituted by one or two alkyl groups of 1 to 4 carbon atoms;
- b is 1, 2 or 3 with the proviso that b cannot exceed the number of carbon atoms in T, and
20 when b is 2 or 3, each hydroxyl group is attached to a different carbon atoms of T;
- R is hydrogen;
in formula (A*), n is 1 or 2,
when n is 1,
- R₁ is hydrogen, alkyl of 1 to 6 carbon atoms, alkenyl of 2-6 carbon atoms, propargyl,
25 glycidyl, alkyl of 2 to 20 carbon atoms interrupted by one to ten oxygen atoms, said alkyl substituted by one to five hydroxyl groups or both interrupted by said oxygen atoms and substituted by said hydroxyl groups, or
- R₁ is alkyl of 1 to 4 carbon atoms substituted by a carboxy group or by -COOZ where Z is hydrogen or alkyl of 1 to 4 carbon atoms,
30 when n is 2,
- R₁ is alkylene of 1 to 8 carbon atoms, alkenylene of 4 to 8 carbon atoms, alkylene of 1 to 20 carbon atoms interrupted by one to ten oxygen atoms, substituted by one to five hydroxyl groups or both interrupted by said oxygen atoms and substituted by said hydroxyl groups,

in formula (B*), m is 1 or 2,

when m is 1,

R₂ is alkyl of 1 to 4 carbon atoms or R₂ is CH₂(OCH₂CH₂)_nOCH₃ where n is 1 to 12, or

5 R₂ is phenyl, or said phenyl substituted by one to three methyl groups, or

R₂ is -NHR₃ where R₃ is alkyl of 1 to 4 carbon atoms or phenyl, or said phenyl substituted by one or two methyl groups,

when m is 2,

R₂ is alkylene of 1 to 8 carbon atoms, alkenylene of 4 to 8 carbon atoms, or R₂ is -

10 CH₂(OCH₂CH₂)_nOCH₂- where n is 1 to 12, or

R₂ is -NHR₄NH- where R₄ is of 2 to 6 carbon atoms, aralkylene of 8 to 15 carbon atoms or arylene of 6 to 12 carbon atoms, or

R₂ is -CO- or -NHCONH-,

in formula (C*),

15 R₁₀ is hydrogen or, alkanoyl of 1 to 3 carbon atoms,

x is 1 or 2,

when x is 1,

R₁₁ is hydrogen, alkyl of 1 to 6 carbon atoms or glycidyl, or

R₁₁ is alkyl of 1 to 4 carbon atoms substituted by a carboxy group or by COOZ where Z is

20 hydrogen or alkyl of 1 to 4 carbon atoms,

when x is 2,

R₁₁ is alkylene of 1 to 6 carbon atoms,

in formula (D*),

R₁₀ is hydrogen,

25 y is 1 or 2,

R₁₂ is defined as R₂ above,

in formula (Y*) and (Z*),

x is 1 or 2,

when x is 1,

30 R₁ and R₂ are independently alkyl of 1 to 4 carbon atoms or R₁ and R₂ are together tetramethylene, or pentamethylene,

R₂ is hydrogen or alkyl of 1 to 4 carbon atoms, said alkyl group substituted by a hydroxyl group,

when x is 2,

R₁ is hydrogen, alkyl of 1 to 4 carbon atoms, said alkyl substituted by a hydroxyl group,

R₂ is alkylene of 2 to 6 carbon atoms,

R₃ is as defined above,

5 HY is an inorganic or organic acid; wherein the total charge of cations is equal to the total charge of anions; and

Y is phosphate, phosphonate, carbonate, bicarbonate, chloride, bromide, bisulfate, sulfate, borate, formate, acetate, benzoate, citrate, oxalate, tartrate, acrylate, fumarate, maleate, itaconate, glycolate, gluconate, malate, mandelate, tiglate, ascorbate, a carboxylate of
10 nitrilotriacetic acid, a carboxylate of hydroxyethylethylenediaminetriacetic acid, a carboxylate of ethylenediaminetetraacetic acid, a carboxylate of diethylenetriamine-pentaacetic acid, a carboxylate of diethylenediaminetetraacetic acid, a carboxylate of diethylenetriaminepentaacetic acid, alkylsulfonate, arylsulfonate, or alkyl-substituted arylsulfonate.

15

6. A stabilized composition according to claim 5 wherein the compounds of formula (I) are selected from the group consisting of (A*), (B*), (C*), (D*), (Q*), and (R*),

wherein

E is alkoxy of 1 to 10 carbon atoms, cycloalkoxy of 5 to 8 carbon atoms or aralkoxy of 7 to
20 12 carbon atoms, or E is -O-T-(OH)_b,

T is a straight or branched chain alkylene of 1 to 10 carbon atoms, cycloalkylene of 5 to 10 carbon atoms, cycloalkenylene of 5 to 10 carbon atoms, a straight or branched chain alkylene of 1 to 4 carbon atoms substituted by phenyl or by phenyl substituted by one or two alkyl groups of 1 to 4 carbon atoms;

25 b is 1, 2 or 3 with the proviso that b cannot exceed the number of carbon atoms in T, and when b is 2 or 3, each hydroxyl group is attached to a different carbon atoms of T;

R is hydrogen,

in formula (A*),

n is 1,

30 R₁ is hydrogen, alkyl of 1 to 4 carbon atoms, glycidyl, alkyl of 2 to 4 carbon atoms interrupted by one or two oxygen atoms, said alkyl substituted by one or two hydroxyl groups or both interrupted by said oxygen atoms and substituted by said hydroxyl groups, or

R_1 is alkyl of 1 to 4 carbon atoms substituted by -COOZ where Z is hydrogen or alkyl of 1 to 4 carbon atoms,

in formula (B*),

m is 1 or 2,

5 R_2 is alkyl of 1 to 4 carbon atoms or R_2 is $\text{CH}_2(\text{OCH}_2\text{CH}_2)_n\text{OCH}_3$ where n is 1 to 4, when m is 2,

R_2 is alkylene of 1 to 8 carbon atoms,

in formula (C*),

R_{10} is hydrogen or alkanoyl of 1 or 2 carbon atoms,

10 x is 1 or 2,

when x is 1,

R_{11} is hydrogen, alkyl of 1 to 4 carbon atoms or glycidyl,

R_{11} is alkyl of 1 to 4 carbon atoms substituted by COOZ where Z is hydrogen or alkyl of 1 to 4 carbon atoms,

15 when x is 2,

R_{11} is alkylene of 1 to 6 carbon atoms,

in formula (D*),

R_{10} is hydrogen,

y is 1 or 2,

20 R_{12} is defined as R_2 above;

HY is an inorganic or organic acid; wherein the total charge of cations is equal to the total charge of anions; and

Y is phosphate, phosphonate, carbonate, bicarbonate, chloride, bromide, bisulfate, sulfate, borate, formate, acetate, benzoate, citrate, oxalate, tartrate, ascorbate, acrylate,

25 fumarate, maleate, itaconate, glycolate, gluconate, malate, mandelate, tiglinate, a carboxylate of nitrilotriacetic acid, a carboxylate of hydroxyethylethylenediaminetriacetic acid, a carboxylate of ethylenediaminetetraacetic acid, a carboxylate of diethylenetriaminepentaacetic acid, a carboxylate of diethylenediaminetetraacetic acid, a carboxylate of diethylenetriaminepentaacetic acid, alkylsulfonate, arylsulfonate, or alkyl-

30 substituted arylsulfonate.

7. A stabilized composition according to claim 1 wherein the compound of formula (I) is selected from the group consisting of

- (a) bis(1-octyloxy-2,2,6,6-tetramethylpiperidin-4-yl) sebacate hydrochloride;
- (b) 1-methoxy-2,2,6,6-tetramethyl-4-acetoxypiperidinium citrate;
- (c) 1-methoxy-2,2,6,6-tetramethyl-4-acetamidopiperidinium phosphate;
- (d) 1-butoxy-2,2,6,6-tetramethyl-4-acetamidopiperidinium bisulfate;
- 5 (e) 1-methoxy-2,2,6,6-tetramethyl-4-oxo-piperidinium methyl sulfonate;
- (f) 1-methoxy-2,2,6,6-tetramethyl-4-oxo-piperidinium acetate;
- (g) 1-phenoxy-2,2,6,6-tetramethyl-4-methoxy-piperidinium tartrate;
- (h) 1-benzyloxy-2,2,6,6-tetramethyl-4-methoxy-piperidinium acetate;
- (i) 1-ethoxy-2,2,6,6-tetramethyl-4-acetoxypiperidinium maleate;
- 10 (j) 1-methoxy-2,2,6,6-tetramethyl-4-propoxy-piperidinium mandelate;
- (k) 1-methoxy-2,2,6,6-tetramethyl-4-propoxy-piperidinium oxalate;
- (l) 1-methoxy-2,2,6,6-tetramethyl-4-(2-hydroxy-4-oxapentoxy)piperidinium bicarbonate;
- (m) 1-methoxy-2,2,6,6-tetramethyl-4-(2-hydroxy-4-oxapentoxy)piperidinium glycolate;
- (n) 1-methoxy-2,2,6,6-tetramethyl-4-hydroxypiperidinium gluconate;
- 15 (o) 1-methoxy-2,2,6,6-tetramethyl-4-hydroxypiperidinium ascorbate;
- (p) 1-methoxy-2,2,6,6-tetramethyl-4-hydroxypiperidinium benzene sulfonate;
- (q) 1-(2-hydroxy-2-methylpropoxy)-2,2,6,6-tetramethyl-4-hydroxypiperidinium ascorbate;
- (r) 1-(2-hydroxy-2-methylpropoxy)-2,2,6,6-tetramethyl-4-hydroxypiperidinium citrate;
- (s) bis(1-(2-hydroxy-2-methylpropoxy)-2,2,6,6-tetramethyl-4-hydroxypiperidinium) citrate;
- 20 (t) tris(1-(2-hydroxy-2-methylpropoxy)-2,2,6,6-tetramethyl-4-hydroxypiperidinium) citrate;
- (u) tetra(1-(2-hydroxy-2-methylpropoxy)-2,2,6,6-tetramethyl-4-hydroxypiperidinium) ethylenediaminetetraacetate;
- (v) tetra(1-(2-hydroxy-2-methylpropoxy)-2,2,6,6-tetramethyl-4-acetamidopiperidinium) ethylenediaminetetraacetate;
- 25 (w) tetra(1-(2-hydroxy-2-methylpropoxy)-2,2,6,6-tetramethyl-4-oxopiperidinium) ethylenediaminetetraacetate;
- (x) penta(1-(2-hydroxy-2-methylpropoxy)-2,2,6,6-tetramethyl-4-hydroxypiperidinium) diethylenetriaminepentaacetate;
- (y) penta(1-(2-hydroxy-2-methylpropoxy)-2,2,6,6-tetramethyl-4-acetamidopiperidinium) diethylenetriaminepentaacetate;
- 30 (z) penta(1-(2-hydroxy-2-methylpropoxy)-2,2,6,6-tetramethyl-4-oxopiperidinium) diethylenetriaminepentaacetate;
- (aa) tri(1-(2-hydroxy-2-methylpropoxy)-2,2,6,6-tetramethyl-4-hydroxypiperidinium) nitrilotriacetate;

- (bb) tri(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-acetamidopiperidinium) nitrilotriacetate;
- (cc) tri(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-oxopiperidinium) nitrilotriacetate;
- 5 (dd) penta(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium) diethylenetriaminepentamethylenephosphonate;
- (ee) penta(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-acetamidopiperidinium) diethylenetriaminepentamethylenephosphonate; and,
- (ff) penta(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-oxopiperidinium)
- 10 diethylenetriaminepentamethylenephosphonate.
8. A stabilized composition according to claim 7 wherein the compound of formula (I) is selected from the group consisting of
- (a) bis(1-octyloxy-2,2,6,6-tetramethylpiperidin-4-yl) sebacate hydrochloride;
- 15 (b) 1-methoxy-2,2,6,6-tetramethyl-4-acetoxypiperidinium citrate;
- (c) 1-butoxy-2,2,6,6-tetramethyl-4-acetamidopiperidinium bisulfate;
- (d) 1-methoxy-2,2,6,6-tetramethyl-4-oxo-piperidinium methyl sulfonate;
- (e) 1-methoxy -2,2,6,6-tetramethyl-4-oxo-piperidinium acetate;
- (f) 1-ethoxy-2,2,6,6-tetramethyl-4-acetoxypiperidinium maleate;
- 20 (g) 1-methoxy-2,2,6,6-tetramethyl-4-propoxy-piperidinium oxalate;
- (h) 1-methoxy-2,2,6,6-tetramethyl-4-(2-hydroxy-4-oxapentoxo)piperidinium glycolate;
- (i) 1-methoxy-2,2,6,6-tetramethyl-4-hydroxypiperidinium ascorbate;
- (j) 1-methoxy-2,2,6,6-tetramethyl-4-hydroxypiperidinium benzene sulfonate;
- (k) 1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium ascorbate;
- 25 (l) 1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium citrate;
- (m) bis(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium) citrate;
- (n) tris(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium) citrate;
- (o) tetra(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium) ethylenediaminetetraacetate;
- 30 (p) tetra(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-acetamidopiperidinium) ethylenediaminetetraacetate;
- (q) penta(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium) diethylenetriaminepentaacetate;

(r) tri(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium) nitrilotriacetate;

(s) penta(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-hydroxypiperidinium) diethylenetriaminepentamethylenephosphonate; and,

5 (t) penta(1-(2-hydroxy-2-methylpropoxy) -2,2,6,6-tetramethyl-4-acetamidopiperidinium) diethylenetriaminepentamethylenephosphonate.

9. A composition according to claim 1 further comprising

10 (c) one or more compounds selected from the group consisting of the ultraviolet light absorbers, antioxidants, tocopherol, tocopherol acetate, hindered amine light stabilizers, complex formers, optical brighteners, surfactants, and polyorganosiloxanes.

15 10. A composition according to claim 9 where the ultraviolet light absorbers are selected from the group consisting of the 2H-benzotriazoles, the s-triazines, the benzophenones, the alpha-cyanoacrylates, the oxanilides, the benzoxazinones, the benzoates, and the alpha-alkyl cinnamates.

11. A composition according to claim 1 further comprising

20 (d) a dye.

12. A composition according to claim 1 where the compounds of component (b) are present in the body care or household products in a concentration of about 5 to about 10000 ppm based on the total formulation by weight.

25 13. A composition according to claim 12 where the compounds of component (b) are present in a concentration of about 10 to about 5000 ppm based on the total formulation by weight.

30 14. A composition according to claim 1 wherein the body care product is selected from the group consisting of skin-care products, bath and shower products, liquid soaps, bar soaps, preparations containing fragrances and odoriferous substances, hair-care products, dentifrices, deodorizing and antiperspirant preparations, decorative preparations, light protection formulations, and preparations containing active ingredients.

15. A composition according to claim 14 wherein the skin-care products are selected from the group consisting of body oils, body lotions, body gels, treatment creams, skin protection ointments, shaving preparations, and skin powders.

5 16. A composition according to claim 14 wherein the preparations containing fragrances and olfactory substances are selected from the group consisting of scents, perfumes, toilet waters, and shaving lotions.

10 17. A composition according to claim 14 wherein the hair-care products are selected from the group consisting of shampoos, hair conditioners, 2 in 1 conditioners, leave in and rinse off conditioners, agents for styling and treating hair, perming agents, relaxants, hair sprays and lacquers, hair dyeing systems, permanent, demi-permanent, semi-permanent and temporary hair dyeing systems, and hair bleaching agents.

15 18. A composition according to claim 14 wherein the decorative preparations are selected from the group consisting of lipsticks, nail varnishes, eye shadows, mascaras, dry and moist make-up, rouge, powders, depilatory agents, sun care, and after sun products.

20 19. A composition according to claim 14 wherein the preparations containing active ingredients are selected from the group consisting of hormone preparations, vitamin preparations, vegetable extract preparations, and antibacterial preparations.

25 20. A composition according to claim 1 wherein the household product is selected from household cleaning and treating agents.

30 21. A composition according to claim 20 wherein the household cleaning and treating agents are selected from the group consisting of laundry detergents and fabric softeners, non-detergent based fabric care products, liquid cleansing and scouring agents, glass detergents, neutral cleaners (all-purpose cleaners), acid household cleaners (bath), bathroom cleaners, washing, rinsing and dishwashing agents, kitchen and oven cleaners, clear rinsing agents, dishwasher detergents, shoe polishes, polishing waxes, floor detergents and polishes, metal, glass and ceramic cleaners, textile-care products, rug cleaners and carpet shampoos, agents for removing rust, color and stains (stain remover salt), furniture and multipurpose polishes

and leather and vinyl dressing agents (leather and vinyl sprays) and solid and liquid air fresheners.

22. A method of stabilizing a body care product, household product, textile or fabric, which
5 comprises incorporating therein or applying thereto one or more compounds of the formulae
(III) to (IIIc) according to claim 4.

23. A method of stabilizing a body care product, household product, textile or fabric, which
10 comprises incorporating therein or applying thereto one or more compounds of the formulae
A* to EE* according to claim 4.

24. A method of stabilizing a body care product, household product, textile or fabric, each of
which contain a dye, which comprises incorporating therein or applying thereto one or more
15 compounds of the formulae (III) to (IIIc) according to claim 4.

25. A method of stabilizing a body care product, household product, textile or fabric, each of
which contain a dye, which comprises incorporating therein or applying thereto one or more
20 compounds of the formulae A* to EE* according to claim 4.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP2005/053990

A. CLASSIFICATION OF SUBJECT MATTER
 A61K8/49 C11D3/28 D01F1/10 A61Q1/00 A61Q3/00
 A61Q5/00 A61Q9/00 A61Q15/00 A61Q17/00 A61Q19/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED
 Minimum documentation searched (classification system followed by classification symbols)
 A61K C11D D01F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)
 EPO-Internal, WPI Data, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	WO 2004/076419 A (CIBA SPECIALTY CHEMICALS HOLDING INC; WOOD, MERVIN GALE; DETLEFSEN, RO) 10 September 2004 (2004-09-10) examples 43-53,57	1-25
X	DE 100 08 367 A1 (CIBA SPECIALTY CHEMICALS HOLDING INC., BASEL) 31 August 2000 (2000-08-31) examples 80,140	1-11, 22-25
X	WO 01/07550 A (UNILEVER PLC; UNILEVER NV; HINDUSTAN LEVER LIMITED) 1 February 2001 (2001-02-01) example 2; table 2	1-11, 22-25
Y		1-25
	-/--	

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed
- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search 28 November 2005	Date of mailing of the international search report 06/12/2005
--	---

Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Authorized officer Werner, S
--	--

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP2005/053990

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	<p>WO 03/103622 A (CIBA SPECIALTY CHEMICALS HOLDING INC; LUPIA, JOSEPH, ANTHONY; SUHADOLN) 18 December 2003 (2003-12-18) cited in the application the whole document</p> <p style="text-align: center;">-----</p>	1-25

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP2005/053990

Patent document cited in search report	Publication date	Publication date	Patent family member(s)	Publication date
WO 2004076419	A	10-09-2004	CA 2517334 A1	10-09-2004
DE 10008367	A1	31-08-2000	AU 773104 B2	13-05-2004
			AU 1945400 A	14-09-2000
			BE 1013530 A5	05-03-2002
			BR 0000666 A	16-01-2001
			CA 2299754 A1	25-08-2000
			CN 1273241 A	15-11-2000
			ES 2195674 A1	01-12-2003
			FR 2790259 A1	01-09-2000
			GB 2347928 A	20-09-2000
			IT MI20000327 A1	23-08-2001
			JP 2000302758 A	31-10-2000
			MX PA00001961 A	23-05-2002
			NL 1014414 C2	17-07-2001
			NL 1014414 A1	28-08-2000
			RU 2243216 C2	27-12-2004
			TW 491876 B	21-06-2002
WO 0107550	A	01-02-2001	AU 5078200 A	13-02-2001
WO 03103622	A	18-12-2003	AU 2003233054 A1	22-12-2003
			BR 0309692 A	29-03-2005
			CN 1649566 A	03-08-2005
			EP 1499286 A1	26-01-2005