



- (51) **International Patent Classification:**
C09K 8/42 (2006.01) *E21B 33/14* (2006.01)
E21B 33/13 (2006.01)
- (21) **International Application Number:**
PCT/US2014/056809
- (22) **International Filing Date:**
22 September 2014 (22.09.2014)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**
14/077,554 12 November 2013 (12.11.2013) US
- (71) **Applicant:** **BAKER HUGHES INCORPORATED**
[US/US]; 2929 Allen Parkway, Suite 2100, Houston, Texas
77019-2118 (US).
- (72) **Inventors:** **VORDERBRUGGEN, Mark A.**; 815 Becketts
Crossing Ln, Spring, Texas 77373 (US). **NARVAEZ,**
Guido G.; 66 Arbor Bend Dr., Houston, Texas Code
Country (US). **CARDONA, Diana**; 2700 Travis Street,
Houston, Texas 77006 (US). **SHEN, Dong**; 62 S Piney
Plains Cir., The Woodlands, Texas 77382 (US).
- (74) **Agents:** **LAKE, James** et al.; Parsons Behle & Latimer,
800 W. Main Street, Suite 1300, Boise, Idaho 83702 (US).

- (81) **Designated States** (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) **Designated States** (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) **Title:** WELLBORE CEMENT COMPOSITIONS AND WELLBORE CEMENTING METHODS

(57) **Abstract:** A wellbore cement composition includes substantially unhydrated cement powder and additive powder for cement. The additive powder is formulated from ingredients including a liquid additive for cement and solid carrier particles. The liquid additive is absorbed by the solid carrier particles. A wellbore cementing method includes using a dry cement composition, adding water to the dry cement composition, forming a cement slurry, placing the slurry in a wellbore, and setting the placed slurry. The dry cement composition contains substantially unhydrated cement powder and retarder powder for cement. The retarder powder contains a retarder absorbed by solid carrier particles.



Wellbore Cement Compositions and Wellbore Cementing Methods

TECHNICAL FIELD

[0001] Compositions and methods herein pertain to wellbore cement compositions and wellbore cementing methods, such as those that include or use an additive powder.

BACKGROUND

[0002] The process of preparing wells drilled in subterranean formations, such as hydrocarbon production wells, often includes cementing the well. Known techniques for well cementing protect and seal the wellbore. Cementing may be used to seal the annulus between the wellbore wall and casing in the wellbore. Cementing may also be used to plug portions of a well, including for the purpose of abandonment, to seal a lost circulation zone, etc.

[0003] Cement powder may be mixed with water on-site to provide cement slurry or, less preferably, mixed with water off-site and transported to the well site. Cement slurry pumped into a wellbore, such as into the annulus, displaces fluids in the wellbore and replaces them with cement. A wide variety of additives may be included in the cement slurry to provide desired time for setting the cement, density, viscosity, strength, etc. Additives may be liquid or solid. Liquid additives use additional personnel and equipment for storage, handling, and dosing into cement slurry and increase the complexity of a cementing job compared to solid additives. Unfortunately, some additives are only available in liquid form. Accordingly,

additives suitable as solid replacements for known liquid additives are desirable.

Solid additives may be mixed with cement powder before transport to a well site and do not use extra personnel or equipment at the site, resulting in economic savings.

SUMMARY

[0004] A wellbore cement composition includes substantially unhydrated cement powder and additive powder for cement. The additive powder is formulated from ingredients including a liquid additive for cement and solid carrier particles. The liquid additive is absorbed by the solid carrier particles.

[0005] A wellbore cementing method includes using a dry cement composition, adding water to the dry cement composition, forming a cement slurry, placing the slurry in a wellbore, and setting the placed slurry. The dry cement composition contains substantially unhydrated cement powder and retarder powder for cement. The retarder powder contains a retarder absorbed by solid carrier particles.

[0006] A wellbore cementing method includes absorbing a liquid retarder for cement using solid carrier particles and thus forming a retarder powder for cement, forming a dry cement composition, adding water to the dry cement composition, forming a cement slurry, placing the slurry in a wellbore, and setting the placed slurry. The retarder powder contains a mass of the liquid retarder at least two times a mass of the solid carrier particles. The dry cement composition contains an admixture of substantially unhydrated cement powder and the retarder powder.

DETAILED DESCRIPTION

[0007] According to one method, absorption of known liquid additives, or perhaps new liquid additives, for cement by a substrate may provide a delivery mechanism for liquid additives in a substantially dry state. As the term is used herein, “absorption” refers to the taking up of the liquid by the substrate. Absorption may occur by a variety of known physical mechanisms. Even though a liquid is absorbed by a finely divided substrate, such as powder, the substrate may nonetheless exhibit flow properties similar to those of the substrate prior to the absorption. Absorbed liquid additives may thus exhibit the properties of known solid additives that may be mixed with cement powder. For example, absorbed liquid additives may have particle size distributions similar to known solid additives. Absorbed liquid additives may be flowable to facilitate handling.

[0008] Accordingly, absorbed liquid additives may be handled as solids, reducing the amount and complexity of additive handling equipment and reducing the likelihood of error when cementing wellbores. Knowing the amount of a liquid additive absorbed by the substrate, cement powder may be prepared in advance with a desired loading of liquid additive merely by adding a corresponding amount of the substrate with absorbed liquid additive. Once liquid additive absorbs by a substrate, it may be handled in a similar manner to solid additives, such as dry powder additives. Then, the absorbed liquid additive may be mixed with other dry powder additives and cement powder without causing viscosity issues or other incompatibility issues in the cement powder. Consequently, liquid additive absorbed by a solid substrate affords the benefits of simplified handling available for dry

powder additives while still allowing use of known liquid additives available in the petroleum industry.

[0009] A variety of finely-divided solid substrates might be suitable. Microporous substrates may be used, defined as substrates exhibiting pore sizes less than 2 nanometers (nm) per IUPAC notation. Absorption of the liquid additive may be accomplished at standard temperature and pressure, increased temperature and pressure, standard temperature and reduced pressure, or increased temperature and reduced pressure. Various physical and chemical properties of a liquid additive, such as viscosity and/or vapor pressure, may affect absorption. One of the listed sets of temperature and pressure operating conditions may be selected for the absorption process to produce desired characteristics for the resulting solid additive, as discussed further below. Known techniques for absorbing liquids using microporous powders may be used. Fine or coarse powder of various particle sizes may be selected to distribute the powder additive in cement powder, depending on desired characteristics of the powder mixture.

[0010] US Patent Nos. 7,086,466 issued to Roddy and 6,648,962 issued to Berke describe adding water to hydratable cement particulates, setting and hardening the particulates by reaction with water, comminuting the substantially hydrated mass, and providing substantially hydrated cement particulates. Additives for cement may be included in the cement particulates with the addition of water to form the hardened, substantially hydrated mass or may be coated on the resulting cement particulates. However, such a method adds the complexity of hydrating and comminuting cement particulates. The Roddy and Berke methods may be

contrasted with the compositions and methods herein that rely on known solid substrates readily commercially available.

[0011] According to one composition, a wellbore cement includes substantially unhydrated cement powder and additive powder for cement. The additive powder is formulated from ingredients including a liquid additive for cement and solid carrier particles. The liquid additive is absorbed by the solid carrier particles. “Unhydrated” cement powder refers to cement powder that since its production has not been hydrated sufficiently to produce a cementitious reaction that bonds particles together. “Unhydrated” thus differs from “dehydrated,” referring to the absence of water. Commercially available cement powder is generally unhydrated, but is not necessarily dehydrated since some absorption of atmospheric moisture may occur.

[0012] By way of example, the liquid additive may include a material selected from retarders, drilling mud surfactants, fluid loss agents, dispersants, antifoam agents, cement set accelerators, foamers, foam stabilizers, and combinations thereof in accordance with the known usage for such terms in the petroleum industry. Retarders increase the duration of curing for cement, such as the set time and thickening time. Since cement slurry placed in a wellbore may be exposed to elevated bore temperatures, set time may decrease at the higher temperatures. A retarder may allow control of set time at the elevated temperatures.

[0013] Drilling mud surfactants may be added in the initial volume of cement pumped into a wellbore to clean out drilling mud. A cleaning agent containing surfactant, water, weighting agent (bentonite, etc.) may be placed as a plug ahead

of cement to remove incompatible components of drilling mud that may negatively impact cement quality.

[0014] Due to chemical and/or physical similarities, antifoam agents might perform similarly to retarders with regard to absorption by and release from solid carrier particles. Examples include polyglycol ether polymers, vegetable oils, silicone oils, and C₇ to C₁₂ alcohols (especially C₈ to C₁₀). Foam stabilizers may also perform similarly. Dispersants, such as polynaphthalene sulfonate formaldehyde polymer, acetone formaldehyde polymers, and acrylic acid polycarboxylate polymer, may further perform similarly.

[0015] The liquid additive may include a liquid retarder for cement, discussed further below as providing unexpected benefits when absorbed by solid carrier particles and used in cement. The liquid retarder may include modified phosphonate/gluconic acid-based polymer or acrylic acid-polyethylene glycol copolymer. The solid carrier particles may include a microporous material. Solid carrier particles may also be a non-cementitious material. More specifically, solid carrier particles may include a material selected from diatomaceous earth, zeolite, aerogel, expanded ceramic, pumice, porous silica, and combinations thereof.

[0016] Depending on the properties of the liquid additive and the solid carrier particles, various liquid loadings absorbed by the solid may be provided. The additive powder may include a mass of the liquid additive at least one-half a mass of the solid carrier particles, such as at least two times a mass of the solid carrier particles. Beneficially, a loading may be selected for the liquid additive in the solid carrier particles to provide an additive powder. Then, the amount of additive powder

in the cement composition may be varied to provide a desired liquid additive content in the wellbore cement composition or resulting cement slurry.

[0017] According to one method, wellbore cementing includes using a dry cement composition, adding water to the dry cement composition, forming a cement slurry, placing the slurry in a wellbore, and setting the placed slurry. The dry cement composition contains substantially unhydrated cement powder and retarder powder for cement. The retarder powder contains a retarder absorbed by solid carrier particles.

[0018] By way of example, the retarder powder may delay the set of the placed slurry longer than the slurry without the retarder powder. More specifically, the retarder powder may delay set of the cement for at least three hours following addition of the water. Unexpectedly, liquid retarder may perform better when absorbed by a substrate than when used in liquid form. For example, an amount of the retarder absorbed by the solid carrier particles may delay the set of the placed slurry longer than an equal amount of retarder in liquid form added to the cement slurry.

[0019] The method may further include dissolving the retarder from the solid particles into the cement slurry. Without being limited to any particular theory, it is possible that retarder absorbed by solid carrier particles may gradually dissolve from the carrier over a period of time. It is also possible that the process of absorbing retarder using solid carrier particles changes the physical structure of a retarder, such as a polymer, so that it becomes more effective when dissolved into cement slurry.

[0020] Retarder may release from the solid carrier particles into the cement slurry over a longer period of time than liquid retarder added to the cement slurry. The gradually dissolving and distributing retarder may contribute to the benefit of using less retarder when absorbed by solid carrier particles to provide a given set time. That is, for an amount of liquid retarder added directly to cement slurry and known for producing a certain set time, less retarder may be used when absorbed by solid carrier particles to produce the same set time. As a result, liquid additive absorption may reduce the cost of retarder usage. The cost of the retarder not needed for retarder powder may be greater than the cost of the solid carrier particles used in retarder powder.

[0021] In testing, retarder was extracted from retarder powder with water after liquid retarder absorption by solid carrier particles. The cement set time was compared for the original liquid retarder, extracted liquid retarder, and retarder powder. Although equivalent amounts of retarder were compared, extracted liquid retarder yielded about five times the set time of original liquid retarder and retarder powder yielded about ten times the set time of original liquid retarder. As a result, a beneficial physical change in the retarder apparently occurred. Thus, the distribution of retarder when absorbed by solid carrier particles may also contribute to the benefit of using less retarder to provide a given set time.

[0022] As indicated above, the solid carrier particles used in the subject method may include a microporous, non-cementitious material. Also, the solid carrier particle materials listed above for the cement composition may be used in the present method. Further, the retarder powder may exhibit the property of

maintaining strength of the set cement compared to the set cement without the retarder powder. That is, the addition of solid carrier particles does not affect cured cement quality.

[0023] According to another method, wellbore cementing includes absorbing a liquid retarder for cement using solid carrier particles and thus forming a retarder powder for cement, forming a dry cement composition, adding water to the dry cement composition, forming a cement slurry, placing the slurry in a wellbore, and setting the placed slurry. The retarder powder contains a mass of the liquid retarder at least two times a mass of the solid carrier particles. The dry cement composition contains an admixture of substantially unhydrated cement powder and the retarder powder.

[0024] By way of example, an amount of the retarder absorbed by the solid carrier particles may delay the set of the placed slurry longer than an equal amount of retarder in liquid form added to the cement slurry. The liquid retarder may include modified phosphonate/gluconic acid-based polymer or acrylic acid-polyethylene glycol copolymer. The solid carrier particles may include microporous, non-cementitious material.

EXAMPLE 1

[0025] Liquid retarders R-450L and SR-34L were absorbed by diatomaceous earth in amounts that nevertheless maintained a free-flowing solid product. Both R-450L and SR-34L are modified phosphonate/gluconic acid-based polymers available from Nalco Co. in Naperville, Illinois. The absorption was done by warming

the fluids and adding them to the diatomaceous earth under vacuum. Using this method, loadings of 1.69 grams (g) of R-450L per 1.0g of diatomaceous earth and 2.24g of SR-34L per 1.0g of diatomaceous earth were achieved as the absorbable limits.

EXAMPLE 2

[0026] Comparison of thickening times for liquid retarder (R-450L) and absorbed liquid retarder (R-450L-SORB) under the same conditions of temperature and pressure, density, and slurry design are shown in Table 1, Table 2, and Table 3. The amount of retarder absorbed by the diatomaceous earth (DE) in grams per sack (gps) was equal to be the amount of the liquid retarder used in the slurry.

[0027] Data in Table 1 was collected from a slurry at 258° F containing 15.80 pounds per thousand gallons (ppg) Dykerhoff G cement and 35% by weight of cement (BWOC) silica flour. The R-450L-SORB contained 1.69g R-450L per 1.0g DE). Measurements were taken using a known consistometer in which “Bc” refers to Bearden Units of Consistency, giving an indication of pumpability. “Shear Pin” refers to the breaking of a shear pin when the cement sets, avoiding damage to the consistometer. To reduce settling, ASA-301 free fluid control agent available from Fritz Industries, Inc. in Mesquite, Texas was included in samples that showed solid components in the cement slurry beginning to settle out.

TABLE 1

Retarder	Retarder % BWOC	Equivalent gps Retarder	70 Bc hr:mn	100 Bc hr:mn	Shear Pin hr:mn
R-450L-SORB	0.25	0.017	0:54	0:59	1:18

R-450L-SORB	1	0.066	1:45	1:46	2:16
R-450L-SORB	1.25	0.83	1:55	1:57	2:31
R-450L-SORB	2	0.132	3:36	3:37	3:48
none	0	0	1:01	1:04	1:17
No retarder, 1% DE	0	0	0:41	0:51	1:07
R-450L*	1	0.066	1:27	1:28	1:30
R-450L*	2	0.132	1:50	1:51	1:51

(*contained 0.15% BWOC (by weight of cement) ASA-301)

[0028] Data in Table 2 was collected from a slurry at 291° F containing 15.80 ppg Dykerhoff G cement and 35% BWOC silica flour. The R-450L-SORB contained 1.69g R-450L per 1.0g DE)

TABLE 2

Retarder	Retarder % BWOC	Equivalent gps Retarder	70 Bc hr:mn	100 Bc hr:mn	Shear Pin hr:mn
R-450L-SORB	2	0.132	1:30	1:37	1:48
R-450L-SORB	4	0.26	2:03	2:04	2:10
R-450L	2	0.132	1:26	1:27	1:30
R-450L	4	0.26	1:46	1:47	1:49

[0029] Data in Table 3 was collected from a slurry at 258° F containing 15.80 ppg Dykerhoff G cement and 35% BWOC silica flour. The SR-34L-SORB contained 2.24g SR-34L per 1.0g DE.

TABLE 3

Retarder	Retarder % BWOC	Equivalent gps Retarder	70 Bc hr:mn	100 Bc hr:mn	Shear Pin hr:mn
SR-34L-SORB*	2	0.132	28:54	28:54	29:10
SR-34L*	2	0.132	3:16	3:18	3:25
SR-34L + DE*	2	0.132	2:51	2:54	3:40

(*contained 0.15% BWOC ASA-301)

[0030] Absorption of R-450L by diatomaceous earth increased its retardation ability approximately 20 minutes beyond the equivalent amount of unabsorbed R-450L at 291° F. At 258° F, 1% of the retarder showed a twenty minute difference between the absorbed and unabsorbed R-450L. Increasing the concentration to 2% resulted in more than doubling the retardation time of the absorbed R-450L.

[0031] Without being limited to any particular theory, it is believed that the release of R-450L from the diatomaceous earth was not instantaneous, but followed a short amount of time which then delayed its effect. However, the theory was not tested.

[0032] Absorption of SR-34L by diatomaceous earth resulted in a material which gave an extreme lengthening of retardation time compared to the equal amount of liquid SR-34L. It was not determined why such an increase occurred. One theory was that the process to absorb the SR-34L resulted in breaking the polymer chain into smaller pieces. It was reported elsewhere that such lower molecular weight materials are stronger retarders than higher molecular weight polymers. No synergy was observed in extending retardation when liquid SR-34L and plain diatomaceous earth were combined separately in the cement.

EXAMPLE 3

[0033] Using the same process as Example 1, S-5 liquid spacer surfactant package available from Baker Hughes, Inc. in Houston, Texas was absorbed by diatomaceous earth with a loading of 0.84g of S-5 per 1.0g diatomaceous earth as the absorbable limit.

EXAMPLE 4

[0034] A 15.5 ppg oil-based synthetic mud was obtained from the Newfield Morro Creek H&P 389 site, lot #16150P130261. A 17.5 ppg spacer system was created containing ASA-301, Barite (barium sulfate weighting additive), FP-6L defoamer available from Geo Specialty Chemicals in Ambler, Pennsylvania, water, and the S-5 surfactant (either liquid or absorbed). Various amounts of each component were evaluated at 160° F in a compatibility mud test performed for different rates of pure liquid S-5 and absorbed S-5 surfactant in a spacer system. Rheologies were measured for 100% mud, 75% mud-25% spacer, 50% mud-50% spacer, 25% mud-75% spacer, and 100% spacer. Incompatibilities were detected when rheologies between 100% oil based mud and 100% spacer fluid exceeded the viscosity of the pure fluids.

[0035] In each test using the absorbed S-5, viscosities significantly higher than pure mud and pure spacer were observed. The high viscosity indicated the S-5 was not available to help homogenize the mud/spacer system, but instead the system formed viscose emulsion-type fluids. The presence of the emulsion-type fluids suggested S-5 might have remained trapped in the diatomaceous earth for an undetermined reason.

[0036] In compliance with the statute, the embodiments have been described in language more or less specific as to structural and methodical features. It is to be understood, however, that the embodiments are not limited to the specific features shown and described. The embodiments are, therefore, claimed in any of their

forms or modifications within the proper scope of the appended claims appropriately interpreted in accordance with the doctrine of equivalents.

CLAIMS

What is claimed is:

1. A wellbore cement composition comprising:
substantially unhydrated cement powder; and
additive powder for cement, the additive powder being formulated from ingredients including a liquid additive for cement and solid carrier particles, the liquid additive being absorbed by the solid carrier particles.
2. The composition of claim 1 wherein the liquid additive comprises a material selected from retarders, drilling mud surfactants, fluid loss agents, dispersants, antifoam agents, cement set accelerators, foamers, foam stabilizers, and combinations thereof.
3. The composition of claim 1 wherein the liquid additive comprises a liquid retarder for cement.
4. The composition of claim 3 wherein the liquid retarder comprises modified phosphonate/gluconic acid-based polymer or acrylic acid-polyethylene glycol copolymer.
5. The composition of claim 1 wherein the solid carrier particles comprise a microporous, non-cementitious material.
6. The composition of claim 1 wherein the solid carrier particles comprise a material selected from diatomaceous earth, zeolite, aerogel, expanded ceramic, pumice, porous silica, and combinations thereof.

7. The composition of claim 1 wherein the additive powder comprises a mass of the liquid additive at least one-half a mass of the solid carrier particles.

8. The composition of claim 1 wherein the additive powder comprises a mass of the liquid additive at least two times a mass of the solid carrier particles.

9. A wellbore cementing method comprising:
using a dry cement composition containing:
substantially unhydrated cement powder; and
retarder powder for cement, the retarder powder containing a retarder absorbed by solid carrier particles;
adding water to the dry cement composition and forming a cement slurry;
and
placing the slurry in a wellbore and setting the placed slurry.

10. The method of claim 9 wherein the retarder powder delays the set of the placed slurry longer than the slurry without the retarder powder.

11. The method of claim 9 wherein the retarder powder delays set of the cement for at least three hours following addition of the water.

12. The method of claim 9 wherein an amount of the retarder absorbed by the solid carrier particles delays the set of the placed slurry longer than an equal amount of retarder in liquid form added to the cement slurry.

13. The method of claim 9 wherein the solid carrier particles comprise a microporous, non-cementitious material.

14. The method of claim 9 wherein the solid carrier particles comprise a material selected from diatomaceous earth, zeolite, aerogel, expanded ceramic, pumice, porous silica, and combinations thereof.

15. The method of claim 9 further comprising dissolving the retarder from the solid carrier particles into the cement slurry.

16. The method of claim 9 wherein the retarder powder exhibits the property of maintaining strength of the set cement compared to the set cement without the retarder powder.

17. A wellbore cementing method comprising:
absorbing a liquid retarder for cement using solid carrier particles and thus forming a retarder powder for cement, the retarder powder containing a mass of the liquid retarder at least two times a mass of the solid carrier particles;
forming a dry cement composition containing an admixture of:
substantially unhydrated cement powder; and
the retarder powder;
adding water to the dry cement composition and forming a cement slurry;
and
placing the slurry in a wellbore and setting the placed slurry.

18. The method of claim 17 wherein an amount of the retarder absorbed by the solid carrier particles delays the set of the placed slurry longer than an equal amount of retarder in liquid form added to the cement slurry.

19. The method of claim 17 wherein the liquid retarder comprises modified phosphonate/gluconic acid-based polymer or acrylic acid-polyethylene glycol copolymer.

20. The method of claim 17 wherein the solid carrier particles comprise a microporous, non-cementitious material.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US2014/056809**A. CLASSIFICATION OF SUBJECT MATTER****C09K 8/42(2006.01)i, E21B 33/13(2006.01)i, E21B 33/14(2006.01)i**

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C09K 8/42; C09K 8/504; C04B 28/02; C09K 8/46; C04B 24/26; E21B 33/13; C04B 24/10; E21B 33/14

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Korean utility models and applications for utility models

Japanese utility models and applications for utility models

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

eKOMPASS(KIPO internal) & Keywords: wellbore, cement powder, unhydrated, additive powder, liquid, solid carrier particle, absorbing, cement slurry

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2011-0108274 A1 (CARITEY, J. P. et al.) 12 May 2011 See abstract, claims 1, 9, 16 and paragraph [0016].	1-20
A	US 2009-0283017 A1 (SPANGLE, L. B. et al.) 19 November 2009 See abstract, claims 33, 35, 36, 43, 45-51, 53 and paragraphs [0012]-[0015].	1-20
A	US 2004-0211562 A1 (BROTHERS, L. E. et al.) 28 October 2004 See abstract and claims 1, 24.	1-20
A	WO 2011-027122 A1 (HALLIBURTON ENERGY SERVICES, INC.) 10 March 2011 See abstract and claims 1, 12.	1-20
A	US 2012-0210911 A1 (TARAFDAR, A. et al.) 23 August 2012 See abstract, claims 1, 14 and paragraphs [0002], [0039].	1-20



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

09 January 2015 (09.01.2015)

Date of mailing of the international search report

09 January 2015 (09.01.2015)

Name and mailing address of the ISA/KR

International Application Division
Korean Intellectual Property Office
189 Cheongsa-ro, Seo-gu, Daejeon Metropolitan City, 302-701,
Republic of Korea

Facsimile No. ++82 42 472 3473

Authorized officer

HONG, Sung Ran

Telephone No. +82-42-481-5405



INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/US2014/056809

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2011-0108274 A1	12/05/2011	None	
US 2009-0283017 A1	19/11/2009	CA 2635925 A1 CA 2635925 C US 7998269 B2 WO 2007-143581 A2 WO 2007-143581 A3	13/12/2007 07/01/2014 16/08/2011 13/12/2007 31/01/2008
US 2004-0211562 A1	28/10/2004	AR 047871 A1 CA 2522540 A1 CA 2523088 A1 CA 2555348 A1 EP 1613836 A1 EP 1616074 A1 EP 1714002 A1 NO 20054752 A NO 20054937 A US 2004-0206502 A1 US 2004-0211564 A1 US 2005-0056191 A1 US 2005-0274291 A1 US 2006-0225622 A1 US 6904971 B2 US 7147055 B2 US 7255739 B2 US 7273100 B2 US 7297207 B2 WO 2004-094776 A1 WO 2004-094778 A1 WO 2005-080746 A1	01/03/2006 04/11/2004 04/11/2004 01/09/2005 11/01/2006 18/01/2006 25/10/2006 14/11/2005 23/11/2005 21/10/2004 28/10/2004 17/03/2005 15/12/2005 12/10/2006 14/06/2005 12/12/2006 14/08/2007 25/09/2007 20/11/2007 04/11/2004 04/11/2004 01/09/2005
WO 2011-027122 A1	10/03/2011	AU 2010-290979 A1 AU 2010-290979 B2 CA 2772374 A1 EP 2473460 A1 US 2011-0048709 A1 US 2012-157578 A1 US 8157009 B2	15/03/2012 25/07/2013 10/03/2011 11/07/2012 03/03/2011 21/06/2012 17/04/2012
US 2012-0210911 A1	23/08/2012	US 2011-297377 A1 US 8245784 B2 US 8877692 B2 WO 2011-154693 A1	08/12/2011 21/08/2012 04/11/2014 15/12/2011